

A-A-1552A
 March 24, 1981
 SUPERSEDING
 A-A-1552
 August 22, 1980

COMMERCIAL ITEM DESCRIPTION

PRIMER COATING (FERRIC OXIDE, AEROSOL)

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification TT-E-488, Primer.

This description covers an aerosol primer for general purpose interior and exterior use on metal surfaces.

Salient characteristics:

The aerosol primer shall be furnished in nominal 1-pint commercial pressurized dispensers, with a total solids content of 50g minimum and a maximum lead content of 0.06 percent by weight. The primer shall contain ferric oxide and other lead free pigments as needed. The contents shall be dispersible by hand shaking for 1 minute at standard conditions, and the valve shall spray easily with moderate finger pressure and close immediately upon release of pressure. The spraying shall be without sputtering and a smooth and uniform film shall be deposited. The can shall deliver at least 98 percent by weight of contents.

Drying time. ^{1/} The primer shall dry-to-touch within 30 minutes, dry-through within 2 hours, and have no aftertack after 48 hours (ASTM D 1640).

Color. ^{1/} The color shall be a general match to the color specified (ASTM D 1729).

Specular gloss. ^{1/} The 60° specular gloss shall be 10 maximum (ASTM D 523).

Flexibility. ^{1/} The primer shall bend over a 1/4-inch mandrel at 0° and 25° C without cracking or flaking (ASTM D 1737).

Lifting. ^{1/} The primer shall not wrinkle or lift when exposed to drops of toluene covered with a watch glass for 15 minutes.

Knife test. ^{1/} The primer shall ribbon or curl and not flake or powder, and show beveled edges at a cut made with a craftsman's knife (curved blade).

Water resistance. ^{1/} The primer shall not blister, soften, or show other defects after immersion in distilled water for 18 hours at 25° C, followed by a recovery period of 1 hour at standard conditions.

Salt spray (fog) testing. ^{1/} There shall be not more than 0.1 percent of rust (rust grade 8 of ASTM D 610) and no blistering under the film after 200 hours of salt spray exposure (ASTM D 1117).

The issues of the ASTM test methods in effect on the date of the solicitation shall be used to determine compliance with these requirements.

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices, and is the same product sold in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements. The manufacturer shall utilize recovered materials to the maximum extent practicable.

Packaging, packing, and marking. The items shall be packaged in accordance with normal commercial practice and packed to assure acceptance by common carrier and provide product protection against loss and damage during multiple shipments, handling, and storage. The shipping container shall be in compliance with the National Motor Freight Classification and Uniform Freight Classification. Shipping containers shall be marked as specified in the contract or order.

NOTE: Procedure for the preparation of primer coating relative to the above salient characteristics:

1/ Spray two coats, each consisting of one horizontal and one vertical pass, from a distance of 175 to 225mm to clean cold rolled steel panels (SAE Steel No. 1010, Dead Soft, Finish A, 1/32 inch). Unless otherwise specified allow to dry for 48 hours at standard conditions.

ASTM standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

Preparing activity:

GSA-FSS