

KK-L-254D
AMENDMENT-1
November 27, 1978

FEDERAL SPECIFICATION

LEATHER, SHEEPSKIN, CHROME TANNED

This amendment, which forms a part of Federal Specification KK-L-254D, dated September 15, 1975, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 7

Table II, in test method after 3211: Add "3/".

Table II, in test method column, after 3041: Add "4/".

PAGE 8

At bottom of table II: Add the following:

3/ Exceptions to Method 3211: The suction flask shall contain 15 ± 1 ml of artificial perspiration solution per specimen and the circulating air oven shall be preheated to $68 \pm 2^\circ\text{C}$.

4/ Exception to method 3041: Only one specimen shall be tested from each 8 by 8 inch sample unit"

Custodians:

Army - GL
Navy - SA
Air Force - 11

Review activities:

Army - MD
Air Force - 99
DLA - CT

Preparing activity:

Army - GL

Civil Agency Coordinating Activities:

GSA - FSS

Project No. 8330-0178

FSC 8330