

QQ-A-250/5F
 AMENDMENT-1
October 22, 1974

FEDERAL SPECIFICATION

ALUMINUM ALLOY ALCLAD 2024, PLATE AND SHEET

This amendment, which forms part of Federal Specification QQ-A-250/5F, dated January 18, 1971, was approved by Commissioner, Federal Supply Service, General Services, Administration, for the use of all Federal agencies.

PAGE 3

Table II - Mechanical properties, for "Temper T3 5/" delete in its entirety and substitute:

"Temper	Widths	Thickness	Tensile strength, minimum	Yield strength at 0.2 percent offset or at extension indicated		Elongation in 2 in. or 4 times D ₁ / 2 / . minimum
				Minimum	Extension under load	
	Inches	Inches	P.s.i.	P.s.i.	Inch/Inch	Percent
T3 5/	All	0.008 thru 0.009	58,000	39,000	0.0061	10
	All	.010 thru .020	59,000	39,000	.0061	12
	All	.021 thru .062	59,000	39,000	.0061	15
	All	.063 thru .128	61,000	40,000	.0060	15
	All	.129 thru .249	62,000	40,000	.0060	15"

MILITARY CUSTODIANS:

Army - MR
 Navy - AS
 Air Force - 11

Review activities:

Army - MI, MU, WC, EL
 Navy - SH, EC
 Air Force - 84

User activities:

Army - ME
 Navy - MC, OS

Preparing activity:

Navy - AS
 (Project 9535-0231)

U. S. GOVERNMENT PRINTING OFFICE : 1974 - 585-693/2372

FSC 9535