

QQ-A-200/7E
April 7, 1981
SUPERSEDING
Fed. Spec. QQ-A-200/7D
September 17, 1970

FEDERAL SPECIFICATION

ALUMINUM ALLOY 5456, BAR, ROD, SHAPES, TUBE AND WIRE, EXTRUDED

This specification was approved by the Commissioner,
Federal Supply Service, General Services Administration,
for the use of all Federal agencies.

(This specification forms a part of the latest
issue of Federal Specification QQ-A-200.)

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the specific requirements for aluminum alloy 5456 bar, rod, shapes, tube and wire produced by extrusion. The general requirements are covered in QQ-A-200.

1.2 Classification.

1.2.1 Tempers. Bar, rod, shapes, tube and wire shall be classified as 0, H111, or H112 tempers, as specified (see 6.2).

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specification:

QQ-A-200

-Aluminum Alloy Bar, Rod, Shapes,
Structural Shapes, Tube and Wire,
Extruded; General Specification for.

(Activities outside the Federal Government may obtain copies of Federal specifications, standards, and commercial item descriptions, as outlined under General Information in the Index of Federal Specifications, Standards, and Commercial Item Descriptions. The Index, which includes cumulative bimonthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification, other Federal specifications, standards, and commercial item descriptions required by activities outside the Federal Government for bidding purposes are available without charge from General Services Administration Business Service Centers in Boston; New York; Philadelphia; Washington, DC; Atlanta; Chicago; Kansas City, MO; Fort Worth; Houston; Denver; San Francisco; Los Angeles; and Seattle, WA.

FSC
4710, 9525
9530, 9540

QQ-A-200/7E

(Federal Government activities may obtain copies of Federal Specifications, standards commercial item descriptions, and the Index of Federal Specifications, Standards, and Commercial Item Descriptions from established distribution points in their agencies.)

3. REQUIREMENTS

3.1 Chemical composition.

3.1.1 The chemical composition shall conform to the requirements specified in table I.

TABLE I. Chemical composition. 1/

Element	Percent	
	Minimum	Maximum
Magnesium	4.7	5.5
Manganese	0.50	1.0
Chromium	0.05	0.20
Silicon	--	0.25
Iron	--	0.40
Zinc	--	0.25
Titanium	--	0.20
Copper	--	0.10
Other, each	--	0.05
Others, total	--	0.15
Aluminum	Remainder	

1/ Analysis shall regularly be made only for the elements specifically mentioned in the table. If, however, the presence of other elements is indicated in the course of routine analysis, further analysis shall be made to determine conformance to the limits specified for other elements.

3.2 Mechanical properties.

3.2.1 Mechanical properties of material as supplied. The mechanical properties in the direction of extrusion shall conform to the requirements specified in table II.

TABLE II. Mechanical Properties.

Temper	Thickness, (bar, and shapes); diameter, (rod and wire); wall thickness, (tube) Inches	Area Square inches	Tensile strength, minimum ksi	Yield strength at 0.2 percent offset or at extension indicated		Elongation in 2 in. or 4 times D ^{1/4} minimum Percent
				Minimum ksi	Extension under load Inch per inch	
0	Up to 5.0, Incl.	Up to 32, Incl.	^{2/} 41.0	19.0	0.0038	14
H111	Up to 5.0, Incl.	Up to 32, Incl.	42.0	26.0	0.0045	12
H112	Up to 5.0, Incl.	Up to 32, Incl.	41.0	19.0	0.0038	12

^{1/} D represents specimen diameter.

^{2/} Maximum tensile strength is 53.0 ksi.

^{3/} See QQ-A-200 for elongation requirement exceptions.

4. QUALITY ASSURANCE PROVISIONS (see QQ-A-200)

5. PREPARATION FOR DELIVERY (see QQ-A-200)

6. NOTES

6.1 Intended use. This alloy is intended for applications requiring a weldable moderate strength non-heat treatable aluminum alloy.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in acquisition documents:

- (a) Title, number, and date of this specification.
- (b) Form, quantity and temper required (see 1.2.1).
- (c) Dimensions required.
- (d) Requirements for sizes not specifically covered (see QQ-A-200).

QQ-A-200/7E

- (e) Requirement stating suitability for an important end use, if necessary.
- (f) Selection of applicable levels of preservation and packing, whether level A, level B or commercial (see QQ-A-200).

6.3 Certain provisions of this specification are the subject of international standardization agreement ABC-NAVY-STD-44. When amendment, revision, or cancellation of this specification is proposed which will affect or violate the international agreement concerned, the preparing activity will take appropriate reconciliation action through international standardization channels including departmental standardization offices, if required.

MILITARY INTEREST:**CIVIL AGENCY COORDINATING ACTIVITIES:**Custodians:

GSA-FSS

Army-MR
Navy-AS
Air Force -11

Review activities:

Army-AR, GL, MI
DLA-IS

User activities:

Army-EL
Navy-MC, SH

Preparing Activity:

Navy - AS
Project No. 9530-0181

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein.