

QQ-A-591F
January 19, 1981
SUPERSEDING
Fed. Spec. QQ-A-591E
March 28, 1973

FEDERAL SPECIFICATION

ALUMINUM ALLOY DIE CASTINGS

This specification was approved by the Commissioner,
Federal Supply Service, General Services Administration,
for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers aluminum alloy die castings.

1.2 Classification.

1.2.1 Alloys. Aluminum die castings shall be furnished in the alloys shown in table I, as specified (see 6.2).

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein (see 6.6):

Federal Standards:

- Fed. Test Method Std. No. 151 - Metals; Test Methods
- Fed. Test Method Std. No. 184 - Identification Marking of Aluminum, Magnesium and Titanium.

(Activities outside the Federal Government may obtain copies of Federal specifications, standards, and commercial item descriptions as outlined under General Information in the Index of Federal Specifications, Standards and Commercial Item Descriptions. The Index, which includes cumulative bi monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification, other Federal specifications, and commercial item descriptions required by activities outside the Federal Government for bidding purposes are available without charge from General Services Administration Business Service Centers in Boston; New York; Washington, DC; Philadelphia; Atlanta; Chicago; Kansas City, MO; Fort Worth; Houston; Denver; San Francisco; Los Angeles; and Seattle, WA.

AREA MECA

QQ-A-591F

(Federal Government activities may obtain copies of Federal specifications, standards, and commercial item descriptions, and the Index of Federal Specifications, Standards and Commercial Item Descriptions from established distribution points in their agencies.)

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of military specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM) STANDARDS:

B85 - Casting, Die Aluminum Alloy

B557 - Aluminum and Magnesium Alloy Products,
Tension Testing Wrought and Cast

(Application for copies should be addressed to The American Society For Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Traffic Department, 1616 P Street, N.W., Washington, D.C. 20036.)

UNIFORM CLASSIFICATION COMMITTEE, AGENT:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Manufacture. The die castings shall be made by forcing molten material under pressure into a mold or die. Unless otherwise specified or shown on the applicable drawing (see 6.2), die castings shall be made by the cold-chamber process.

3.2 Chemical composition.

3.2.1 The chemical composition of the material shall be within the limits shown in table I.

3.2.2 The supplier shall furnish an analysis of each lot showing the percentage of each of the elements specified in table I. Chemical analysis of the individual lots by the contractor may be waived at the discretion of the Government inspector, provided that the foundry's method of composition control is acceptable to him, or that all the material in the lot can be identified as being from melts previously analyzed and found to be in conformance with the chemical composition requirements of the alloy specified herein.

3.3 Soundness.

3.3.1 When specified (see 6.2), the soundness of die castings shall conform to standards furnished or approved by the purchaser. The number and extent of blowholes, sponginess, and other defects in the die castings shall not exceed those shown by the standards, and such defects shall be substantially absent in designated areas.

3.3.1.1 The standards supplied or approved by the purchaser for determining conformance with soundness requirements shall consist of either sectionalized die castings, photographs thereof, or radiographs of at least the important sections of die castings.

3.3.2 When specified (see 6.2), the weight of each casting shall be not less than a specified minimum when weighed in accordance with 4.5.3.3.

3.4 Foundry control. Unless otherwise specified (see 6.2), die castings shall be produced under foundry control approved by the purchaser. Foundry control shall consist of examination of die castings by radiographic or other approved methods for determining internal defects until the gating and other foundry practices have been established to produce die castings meeting the quality standards furnished by the purchaser or agreed upon by the purchaser and supplier. When foundry practices have been so established, the production method shall not be changed without demonstrating to the satisfaction of the purchaser that the change does not adversely affect the quality of the die castings.

Table I. Chemical composition - percent maximum except where indicated as a range ^{1/}

Alloy	Silicon	Iron	Copper	Manga- nese	Magne- sium	Nickel	Zinc	Tin	Other elements total	Aluminum
360.0	9.0-10.0	2.0	0.6	0.35	0.40-0.60	0.50	0.50	0.15	0.25	Remainder
A360.0	9.0-10.0	1.3	0.6	0.35	0.40-0.60	0.50	0.50	0.15	0.25	Remainder
380.0	7.5- 9.5	2.0	3.0-4.0	0.50	0.10	0.50	3.0	0.35	0.50	Remainder
A380.0	7.5- 9.5	1.3	3.0-4.0	0.50	0.10	0.50	3.0	0.35	0.50	Remainder
383-0	9.5-11.5	1.3	2.0-3.0	0.50	0.10	0.30	3.0	0.15	0.50	Remainder
384-0	10.5-12.0	1.3	3.0-4.5	0.50	0.10	0.50	3.0	0.35	0.50	Remainder
413.0	11.0-13.0	2.0	1.0	0.35	0.10	0.50	0.50	0.15	0.25	Remainder
A413.0	11.0-13.0	1.3	1.0	0.35	0.10	0.50	0.50	0.15	0.25	Remainder
C443.0	4.5- 6.0	2.0	0.6	0.35	0.10	0.50	0.50	0.15	0.25	Remainder
518.0	0.35	1.8	0.25	0.35	7.50-8.50	0.15	0.15	0.15	0.25	Remainder

^{1/}Analysis shall be made regularly only for the elements specifically mentioned in table I. If, however, the presence of other elements is suspected or indicated in the course of routine analysis, further analysis shall be made to determine that the total of other elements is not in excess of the limits specified.

QQA-5015

3.5 Dimensions. The dimensions of the die casting shall be within the dimensions and tolerances specified on the applicable drawings.

3.6 Repair. Die castings shall not be repaired in any manner without documented permission of the purchaser. When such permission is granted, it shall not relieve the supplier from his responsibility of supplying castings which shall meet all the requirements of the drawings and the specification.

3.7 Identification marking. Unless otherwise specified (see 6.2), each die casting shall be identified with the part number and manufacturer's name, brand, or trademark, by the use of raised numerals in a location indicated on the drawing. When no location is shown on the drawing, the number shall be so located as not to be removed when machining to the required dimension. Marking shall be in accordance with Fed. Std. No. 184.

3.7.1 Die castings on which it is impracticable to provide raised numerals shall be marked by impression stamping or by any other method as agreed upon by the purchaser and supplier. The location of impression stamping must be approved by the purchaser when no location is shown on the drawing.

3.8 Location of ejector pin marks and parting lines. Unless otherwise specified (see 6.2), the location of ejector pin marks and parting lines shall be at the option of the producer.

3.9 Workmanship. The die castings shall be of uniform quality, free from injurious blowholes, porosity, hard spots, shrinkage defects, cracks, and other discontinuities that will adversely affect the serviceability of the castings.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Lot.

4.2.1 Inspection lot. The supplier has the option of operating on the basis of either one of the following two definitions of an inspection lot:

QQ-A-591F

4.2.1.1 An inspection lot shall consist of not more than 1,000 pounds (454 kg) of die castings of the same part number submitted for inspection at one time. However, if this method of inspection is used, the foundry's method of periodic composition control shall be acceptable to the procuring agency and no die castings shall be released for finishing until the composition of the representative chemical samples has been found to conform with the composition limits of this specification.

4.2.1.2 An inspection lot shall consist of the production of each die or compound die of each machine for each 24 hour period during the first week of continuous operation, and the production for each 48 hour period thereafter of continuous operation. Any change in the machine, composition, die or continuity of operation shall be considered as the start of a new lot. Die castings inspected by this method shall be so marked or handled during the finishing operations as not to lose their identity.

4.3 Sampling. Samples taken for purposes of tests prescribed in this specification shall be selected in such manner as to represent correctly the material furnished and avoid needless destruction of finished material when samples representatives of the material are available from other sources.

4.3.1 For chemical analysis. Two samples shall be taken from each of two representative castings selected from each lot.

4.3.1.1 If the producer's method of composition control is acceptable, sampling for chemical analysis may be waived at the discretion of the purchaser.

4.3.2 For soundness. Unless otherwise specified (see 6.2), the sampling for radiographic inspection or comparison with standards shall be in accordance with table II.

Table II. Size of radiographic or comparative sample

Number of die castings in lot	Sample number of die castings	Acceptable number of defective die castings, maximum
1-5	All	0
6-100	6	0
101-500	7	0
501-2000	17	1
2001-6000	27	2
Over 6000	39	3

4.4 Examination.

4.4.1 Workmanship. Each die casting shall be carefully examined to determine conformance with the requirements of this specification with respect to workmanship.

4.4.2 Dimensional. The first completely formed, apparently sound casting made from each die intended for use in lot production, shall be measured and gaged for conformance with 3.5. When nonconformance occurs, corrective action shall be taken and first casting dimensional examination again performed. Unless otherwise specified (see 6.2), at least 0.1 percent of the die castings subsequently made with the die shall be measured and gaged.

4.4.3 Examination of preparation for delivery. An examination shall be made to determine compliance with the requirements of section 5. The sample unit shall be one shipping container fully prepared for delivery. Sampling shall be in accordance with MIL-STD-105. The inspection level shall be S-2 with an accepted quality level (AQL) of 4.0 expressed in terms of percent defective.

4.5 Tests.

4.5.1 Chemical analysis. The sample selected in accordance with 4.3.1 shall be analyzed in accordance with method 111 or 112 of Fed. Test Method Std. No. 151. A single analysis of a composite sample may be made. In case of dispute, reference analysis shall be by method 111. If another method of analysis is desired, it shall be as agreed upon by the supplier and the purchaser.

4.5.2 Foundry control. Unless otherwise specified (see 6.2), all die castings produced shall be examined radiographically, or by other approved methods, until such time as the proper die casting practice has been reached that will produce die castings free from serious internal defects in all parts of the die castings subject to stress in service.

4.5.3 Soundness.

4.5.3.1 Unless otherwise specified (see 6.2), when soundness is required in accordance with 3.3.1, it shall be determined by radiographic examination of die castings selected in accordance with 4.3.2.

4.5.3.2 When specified (see 6.2), soundness shall be determined by comparison with sectionalized standard die castings.

4.5.3.3 When the minimum weight of the individual casting is specified (see 6.2), a sufficient number of the die castings in each lot shall be weighed to establish compliance with the weight requirement. If any of the castings so weighed fall below the specified weight, each casting of the lot shall be weighed, and those weighing less than the specified weight shall be rejected.

4.6 Rejection and retest. If any sample except soundness fails to conform to this specification, the entire lot shall be rejected subject to retest provisions in Fed. Test Method Std. No. 151. If the number of defective die castings in any soundness sample (see table II) exceeds the acceptable number for that sample, the lot represented by that sample shall be rejected subject to retest provisions in Fed. Test Method Std. No. 151.

QQ-A-591F

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or commercial, as specified (see 6.2).

5.1.1 Level A. The aluminum alloy die castings shall be packaged in accordance with the level A packaging requirements of MIL-STD-649.

5.1.2 Level B. The aluminum alloy die castings shall be packaged in accordance with level B packaging requirements of MIL-STD-649.

5.1.3 Commercial. The aluminum alloy die castings shall be packaged in accordance with normal commercial practice. The complete package shall be designed to protect the castings against damage during multiple shipments, handling, and storage.

5.2 Packing. Packing shall be level A, B, or commercial, as specified (see 6.2).

5.2.1 Level A. The aluminum alloy die castings, packaged as specified in 5.1, shall be packed in accordance with level A packing requirements of MIL-STD-649.

5.2.2 Level B. The aluminum alloy die castings, packaged as specified in 5.1, shall be packed in accordance with the level B packing requirements of MIL-STD-649.

5.2.3 Commercial. The aluminum alloy die castings, packaged as specified in 5.1, shall be packed in fiberboard boxes to insure delivery at destination; provide for redistribution by the initial receiving activity; and be acceptable by common carrier under the National Motor Freight Classification and Uniform Freight Classification.

5.3 Marking.

5.3.1 Civil agencies. Marking shall be as specified in the contract or order.

5.3.2 Military agencies. Marking shall be as specified in MIL-STD-129.

6. NOTES

6.1 Intended use.

6.1.1 The aluminum alloy die castings covered by this specification have good resistance to corrosion, although alloys 360.0, A360.0, 383.0, 413.0, A413.0, C443.0 and 518.0 are, as a group, more resistant to corrosion than 380.0, A380.0, and 384.0.

6.1.2 Alloys 360.0, A360.0, 413.0, and A413.0, have excellent casting qualities, good mechanical qualities, and good resistance to corrosion. Alloy C443.0 has a high elongation but a comparatively low yield strength and is not as suitable for the production of intricate die castings as are alloys 360.0, A360.0, 413.0, and A413.0. Die castings of alloy 518.0 have good strength, ductility, resistance to corrosion, finishing qualities, and color. However, this alloy is extremely difficult to die cast.

6.1.3 Alloys 380.0, A380.0, and 384.0 are used for a wide variety of die castings generally not required to withstand severely corrosive conditions. When suitably protected, however, they will satisfactorily withstand rather severe exposure. They develop relatively high tensile properties and are of a composition which can be made largely from good grades of secondary materials. Alloys of this type would be in more abundant supply in an emergency period.

6.1.4 Alloy 383.0 is superior to alloy A380.0 with respect to hot cracking, pressure tightness, and die-filling capacity. Tensile properties are approximately the same.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

- a. Title, number, and date of this specification.
- b. Alloy required (see 1.2.1).
- c. When other than the cold chamber process is required (see 3.2.1).
- d. When soundness standards will be furnished (see 3.3.1, 4.5.3.1, and 4.5.3.2).
- e. When weighing is required and the minimum weight (see 3.3.2 and 4.5.3.3).
- f. Foundry control (see 3.4 and 4.5.2).
- g. Dimensions required (see 3.5).
- h. When identification marking other than as specified herein is required (see 3.7).
- i. Location of ejector pin marks and parting lines, when special locations are required (see 3.8).
- j. When special sampling for soundness is required (see 4.3.2).
- k. When other than 0.1 percent of the die castings shall be measured and gaged (see 4.4.2).
- l. Levels of packaging and packing required (see 5.1 and 5.2).

QQ-A-591F

6.3 The use of separately die-cast test bars was omitted from this specification revision because they are considered unreliable. Different machines and dies continue to be necessary for die castings and test bars. Comparison between static breakdown or proof test and the mechanical properties of separately die-cast test bars revealed that test bars made in a different machine in a different die had no correlation with the die casting, other than a common chemical composition. For this reason, it is considered that the only practical method is to have mechanical property control based on proof testing of whole die castings.

6.4 For information only, typical separately die-cast specimen tensile properties are presented in table III. These properties are of tension specimens of the form and dimensions shown in ASTM B557, when cast in a die in regular production routine and conforming to the chemical composition specified in Table I.

Table III. Typical tensile properties

Alloy	Tensile strength ksi (MPa)	Yield strength at 0.2 percent offset, ksi (MPa)	Elongation in 2 inches, percent
360.0	44 (300)	25 (170)	2.5
A360.0	46 (320)	24 (170)	3.5
380.0	46 (320)	23 (160)	2.5
A380.0	47 (320)	23 (160)	3.5
383.0	45 (310)	22 (150)	3.5
384.0	48 (330)	24 (170)	2.5
413.0	43 (300)	21 (140)	2.5
A413.0	42 (290)	19 (130)	3.5
C443.0	33 (230)	14 (100)	9.0
518.0	45 (310)	28 (190)	5.0

6.5 The chemical requirements and the suggested mechanical property values of the alloys of this specification are similar to those alloys having the same designations in ASTM B85. The commercial designations are also the same. Table IV lists the commercial designations and for informational purposes, the corresponding UNS numbers.

Table IV. Equivalent alloy designations

ASTM B85	UNS number ^{1/}
360.0	A03600
A360.0	A13600
380.0	A03800
A380.0	A13800
383.0	A03830
384.0	A03840
413.0	A04130
A413.0	A14130
C443.0	A34430
518.0	A05180

^{1/}The Unified Numbering System (UNS) was developed jointly by the Society of Automotive Engineers (SAE) and the American Society for Testing and Materials (ASTM). For cast aluminum alloys, the second, third, and fourth digits of the UNS number correspond to the first three digits, respectively, of the commercial designation. The first digit denotes the alloy modification (zero if original alloy). To these digits, a prefix letter "A" and a suffix number "0" are added.

6.6 Specifications and standards applicable to military (levels A and B) preparation for delivery requirements. In addition to the documents listed in 2.1, the following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification for military procurements where levels A and B packaging are specified.

Military Standards:

MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-649 - Aluminum and Magnesium Products; Preparation for Shipment and Storage

Military Custodians:

Army - MR
Navy - AS
Air Force - 99

CIVIL AGENCY COORDINATING ACTIVITIES:

JUSTICE - FPI
NASA - MSF
GSA - FSS

Review activities:

Army - ME, CR, AR
Navy - OS

Preparing activity:

Army - MR

User activities:

Army - EL
Navy - SH

Project No. MECA-0177

U.S. GOVERNMENT PRINTING OFFICE : 1981 - 341-705/1230

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge (*DO NOT STAPLE*), and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY




NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE \$300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Director
Army Materials & Mechanics Research Center
ATTN: DRXMR-LS
Watertown, MA 02172



STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions - Reverse Side)

1. DOCUMENT NUMBER

2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION

4. TYPE OF ORGANIZATION (Mark one)

 VENDOR USER MANUFACTURER OTHER (Specify): _____

b. ADDRESS (Street, City, State, ZIP Code)

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER (Last, First, MI) - Optional

b. WORK TELEPHONE NUMBER (Include Area Code) - Optional

c. MAILING ADDRESS (Street, City, State, ZIP Code) - Optional

8. DATE OF SUBMISSION (YYMMDD)

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)