

QQ-C-533B
MARCH 10, 1988

CANCELLATION NOTICE

FEDERAL SPECIFICATION

Copper-Beryllium Alloy Strip (Copper Alloy Numbers 170 and 172)

Federal Specification QQ-C-533B, dated 20 March, 1972 is hereby cancelled. Future procurements for this material should refer to ASTM B194, "Copper-Beryllium Alloy Plate, Sheet, Strip and Rolled Bar", in accordance with the following supersession table:

For Documents Listing QQ-C-533*, QQ-C-533A, and QQ-C-533B	Use ASTM B194
Alloy Numbers	UNS Alloy Numbers
170 172	C17000 C17200

Tempers (Solution Heat Treated)

A	TB00
(Solution Heat Treated and Cold Rolled)	
1/4 H	TD01
1/2 H	TD02
H	TD04

(Precipitation Heat Treated)

AT	TF00
1/4 HT	TH01
1/2 HT	TH02
HT	TH04

(Mill Hardened)**

(No Equivalent)

TM00
TM01
TM02
TM03
TM04
TM05
TM06

* Alloy defined by Beryllium content of 1.80 - 2.05% only.

** Precipitation heat treated by the material manufacturer and no further thermal treatment is normally required.

Custodians:

Army -- MR
Navy -- AS
Air Force -- 20

Preparing Activity:

Army -- MR

FSC 9535