

| INCH-POUND |

SS-S-200E
AMENDMENT-2
July 16, 1993
SUPERSEDING
Amendment-1
August 23, 1988

FEDERAL SPECIFICATION

SEALANTS, JOINT, TWO-COMPONENT, JET-BLAST-RESISTANT,
COLD-APPLIED, FOR PORTLAND CEMENT CONCRETE PAVEMENT

This amendment, which forms a part of SS-S-200E, dated August 15, 1984, is approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

Page 3

Paragraph 2.2

DELETE: C220 - Flat Asbestos-Cement Sheets

Page 11

Paragraph 4.4.10.2a

DELETE: Panel specimens of the dimensions described in 4.4.4, but with 4.8 millimeter (0.19-inch) asbestos-cement composition base plates conforming to ASTM C220, Type U (see 3.2.3).

ADD: Panel specimens as described in 4.4.4, and primed when required (see 3.2.3).

Page 5

Paragraph 3.3.2d, second line

DELETE: less than 3 hours after mixing,

ADD: less than 1 hour after mixing,

FSC 8030

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

SS-S-200E
AMENDMENT-2

Page 8

Paragraph 4.4.3.2.2, third line

DELETE: Three hours after mixing,

ADD: One hour after mixing,

Page 14

Paragraph 4.4.11.4, lines 6 and 7

DELETE: Remove the specimens from the extension machine, reinsert the 12.7-mm spacers, and examine the specimens as described in 4.4.6.7.

ADD: Remove the specimens from the extension machine and reinsert the 12.7-mm spacers.

Paragraph 4.4.11.5, last sentence

DELETE: Three cycles of immersion, conditioning, extension, and recovery shall constitute one complete test for fuel-immersed bond (see 4.4.11.7).

ADD: Two additional cycles of extension and recovery shall constitute one complete test for fuel-immersed bond (see 4.4.11.7).

Paragraph 4.4.11.6, last sentence

DELETE: Three cycles of immersion, conditioning, extension, and recovery shall constitute one complete test for water-immersed bond (see 4.4.11.7).

ADD: Two additional cycles of extension and recovery shall constitute one complete test for water-immersed bond (see 4.4.11.7).

Page 15

Paragraph 4.4.11.7, next to last sentence

DELETE: This shall be accomplished without distorting the specimens, but after recovery as specified in 4.4.6.4, the specimens may be extended uniformly up to 6.35mm (0.25 inch) to permit further detailed examination.

ADD: This shall be accomplished without distorting the specimens, but the specimens may be extended uniformly up to 6.35mm (0.25 inch) to permit further detailed examination.

MILITARY INTERESTS:

Custodians

Army - ME
Navy - YD
Air Force - 99

Review Activities

Army - MD, MR
Air Force - 84

User Activities

Army - CE
Navy - MC

CIVIL AGENCY COORDINATING ACTIVITIES:

GSA - FSS (9FTE-10)
DOT - APM, NHT

PREPARING ACTIVITY:

Navy - YD

(Project 8030-0664)