

**MIL-HDBK-5H**  
**1 DECEMBER 1998**

# **MILITARY HANDBOOK**

## **METALLIC MATERIALS AND ELEMENTS FOR AEROSPACE VEHICLE STRUCTURES**



**AMSC N/A**

**FSC 1560**

**DISTRIBUTION STATEMENT A. Approved for public release: distribution is unlimited.**

**MIL-HDBK-5H****1 December 1998*****FOREWORD***

1. This military handbook is approved for use by all Departments and Agencies of the Department of Defense and the Federal Aviation Administration.

2. Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Chairman, MIL-HDBK-5 Coordination Activity (937-656-9134 voice, 937-255-4997 fax), AFRL/MLSC, 2179 Twelfth St., Room 122, Wright-Patterson AFB, OH 45433-7718, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of Chapter 1 or by letter if using the hard copy.

3. This document contains design information on the strength properties of metallic materials and elements for aerospace vehicle structures. All information and data contained in this handbook have been coordinated with the Air Force, Army, Navy, Federal Aviation Administration, and industry prior to publication, and are being maintained as a joint effort of the Department of Defense and the Federal Aviation Administration.

4. The electronic copy of the Handbook is technically consistent with the paper copy Handbook; however, minor differences exist in format, i.e., table or figure position. Depending on monitor size and resolution setting, more data may be viewed without on-screen magnification. The figures were converted to electronic format using one of several methods. For example, digitization or recomputation methods were used on most of the engineering figures like typical stress-strain and effect of temperature, etc. Scanning was used to capture informational figures such as those found in Chapters 1 and 9, as well as most of the S/N curves and the majority of graphics in Chapters 4 through 7. These electronic figures were also used to generate the paper copy figures to maintain equivalency between the paper copy and electronic copy. In all cases, the electronic figures have been compared to the paper copy figures to ensure the electronic figure was technically equivalent. Appendix E provides a detailed listing of all the figures in the Handbook, along with a description of each figure's format.

**Custodians:**

Army—AV  
Navy—AS  
Air Force—11  
FAA

**Preparing activity:**

Air Force: 11

(Project No. 1560-0187)

**Review activities:**

Army—ME, MI  
Navy—CG  
Air Force—80, 82, 84, 99



**MIL-HDBK-5H****1 December 1998*****EXPLANATION OF NUMERICAL CODE***

For chapters containing materials properties, a deci-numeric system is used to identify sections of text, tables, and illustrations. This system is explained in the examples shown below. Variations of this deci-numerical system are also used in Chapters 1, 8, and 9.

Example A

2.4.2.1.1

General material category (in this case, steel) .....			
A logical breakdown of the base material by family characteristics (in this case, intermediate alloy steels); or for element properties .....			
Particular alloy to which all data are pertinent. If zero, section contains comments on the family characteristics .....			
If zero, section contains comments specific to the alloy; if it is an integer, the number identifies a specific temper or condition (heat treatment) .....			
Type of graphical data presented on a given figure (see following description) .....			

Example B

3.2.3.1.X

Aluminum .....			
2000 Series Wrought Alloy .....			
2024 Alloy .....			
T3, T351, T3510, T3511, T4, and T42 Tempers .....			
Specific Property as Follows .....			
Tensile properties (ultimate and yield strength) .....			1
Compressive yield and shear ultimate strengths .....			2
Bearing properties (ultimate and yield strength) .....			3
Modulus of elasticity, shear modulus .....			4
Elongation, total strain at failure, and reduction of area .....			5
Stress-strain curves, tangent-modulus curves .....			6
Creep .....			7
Fatigue .....			8
Fatigue-Crack Propagation .....			9
Fracture Toughness .....			10

**MIL-HDBK-5H**  
**1 December 1998**

***CONTENTS***

<b><u>Section</u></b>	<b><u>Page</u></b>
<b>Chapter 1</b>	
1.0 General .....	1-1
1.1 Purpose, Procurement, and Use of Document .....	1-1
1.1.1 Introduction .....	1-1
1.1.2 Scope of Document .....	1-1
1.1.3 Use of Design Mechanical Properties .....	1-2
1.2 Symbols, Abbreviations, and Systems of Units .....	1-2
1.2.1 Symbols and Abbreviations .....	1-2
1.2.2 International System of Units (SI) .....	1-5
1.3 Commonly Used Formulas .....	1-6
1.3.1 General .....	1-6
1.3.2 Simple Unit Stresses .....	1-6
1.3.3 Combined Stresses (see Section 1.5.3.5) .....	1-7
1.3.4 Deflections (Axial) .....	1-7
1.3.5 Deflections (Bending) .....	1-7
1.3.6 Deflections (Torsion) .....	1-7
1.3.7 Biaxial Elastic Deformation .....	1-8
1.3.8 Basic Column Formula .....	1-8
1.4 Basic Principles and Definitions .....	1-8
1.4.1 General .....	1-8
1.4.2 Stress .....	1-9
1.4.3 Strain .....	1-10
1.4.4 Tensile Properties .....	1-11
1.4.5 Compressive Properties .....	1-13
1.4.6 Shear Properties .....	1-13
1.4.7 Bearing Properties .....	1-14
1.4.8 Temperature Effects .....	1-15
1.4.9 Fatigue Properties .....	1-17
1.4.10 Metallurgical Instability .....	1-19
1.4.11 Biaxial Properties .....	1-19
1.4.12 Fracture Strength .....	1-21
1.4.13 Fatigue-Crack-Propagation Behavior .....	1-25
1.5 Types of Failures .....	1-29
1.5.1 General .....	1-29
1.5.2 Material Failures .....	1-29
1.5.3 Instability Failures .....	1-30
1.6 Columns .....	1-31
1.6.1 General .....	1-31
1.6.2 Primary Instability Failures .....	1-31
1.6.3 Local Instability Failure .....	1-32

NOTE: Information and data for alloys deleted from MIL-HDBK-5 may be obtained through the Chairman, MIL-HDBK-5 Coordination Activity.

**MIL-HDBK-5H****1 December 1998*****CONTENTS (Continued)***

<b><u>Section</u></b>	<b><u>Page</u></b>
1.6.4 Correction of Column Test Results . . . . .	1-33
1.7 Thin-Walled and Stiffened Thin-Walled Sections . . . . .	1-39
References . . . . .	1-39
<b>Chapter 2</b>	
2.0 Steel . . . . .	2-1
2.1 General . . . . .	2-1
2.1.1 Alloy Index . . . . .	2-1
2.1.2 Material Properties . . . . .	2-2
2.1.3 Environmental Considerations . . . . .	2-5
2.2 Carbon Steels . . . . .	2-6
2.2.0 Comments on Carbon Steels . . . . .	2-6
2.2.1 AISI 1025 . . . . .	2-7
2.3 Low-Alloy Steels (AISI Grades and Proprietary Grades) . . . . .	2-10
2.3.0 Comments on Low-Alloy Steels (AISI and Proprietary Grades) . . . . .	2-10
2.3.1 Specific Alloys . . . . .	2-15
2.4 Intermediate Alloy Steels . . . . .	2-67
2.4.0 Comments on Intermediate Alloy Steels . . . . .	2-67
2.4.1 5Cr-Mo-V . . . . .	2-67
2.4.2 9Ni-4Co-0.20C . . . . .	2-75
2.4.3 9Ni-4Co-0.30C . . . . .	2-80
2.5 High-Alloy Steels . . . . .	2-92
2.5.0 Comments on High-Alloy Steels . . . . .	2-92
2.5.1 18 Ni Maraging Steels . . . . .	2-94
2.5.2 AF1410 . . . . .	2-105
2.5.3 AerMet 100 . . . . .	2-108
2.6 Precipitation and Transformation-Hardening Steels (Stainless) . . . . .	2-116
2.6.0 Comments on Precipitation and Transformation-Hardening Steels (Stainless) . . . . .	2-116
2.6.1 AM-350 . . . . .	2-116
2.6.2 AM-355 . . . . .	2-123
2.6.3 Custom 450 . . . . .	2-129
2.6.4 Custom 455 . . . . .	2-141
2.6.5 PH13-8Mo . . . . .	2-152
2.6.6 15-5PH . . . . .	2-162
2.6.7 PH15-7Mo . . . . .	2-177
2.6.8 17-4PH . . . . .	2-189
2.6.9 17-7PH . . . . .	2-207
2.7 Austenitic Stainless Steels . . . . .	2-214
2.7.0 Comments on Austenitic Stainless Steel . . . . .	2-214
2.7.1 AISI 301 . . . . .	2-216
2.8 Element Properties . . . . .	2-231
2.8.1 Beams . . . . .	2-231
2.8.2 Columns . . . . .	2-231

NOTE: Information and data for alloys deleted from MIL-HDBK-5 may be obtained through the Chairman, MIL-HDBK-5 Coordination Activity.

**MIL-HDBK-5H****1 December 1998*****CONTENTS (Continued)***

<b><u>Section</u></b>	<b><u>Page</u></b>
2.8.3 Torsion .....	2-234
References .....	2-240
<b>Chapter 3</b>	
3.0 Aluminum .....	3-1
3.1 General .....	3-1
3.1.1 Aluminum Alloy Index .....	3-2
3.1.2 Material Properties .....	3-2
3.1.3 Manufacturing Considerations .....	3-22
3.2 2000 Series Wrought Alloys .....	3-26
3.2.1 2014 Alloy .....	3-26
3.2.2 2017 Alloy .....	3-64
3.2.3 2024 Alloy .....	3-67
3.2.4 2025 Alloy .....	3-149
3.2.5 2090 Alloy .....	3-152
3.2.6 2124 Alloy .....	3-155
3.2.7 2219 Alloy .....	3-164
3.2.8 2519 Alloy .....	3-193
3.2.9 2524 Alloy .....	3-196
3.2.10 2618 Alloy .....	3-198
3.3 3000 Series Wrought Alloys .....	3-207
3.4 4000 Series Wrought Alloys .....	3-207
3.5 5000 Series Wrought Alloys .....	3-207
3.5.1 5052 Alloy .....	3-207
3.5.2 5083 Alloy .....	3-220
3.5.3 5086 Alloy .....	3-226
3.5.4 5454 Alloy .....	3-235
3.5.5 5456 Alloy .....	3-240
3.6 6000 Series Wrought Alloys .....	3-246
3.6.1 6013 Alloy .....	3-246
3.6.2 6061 Alloy .....	3-250
3.6.3 6151 Alloy .....	3-278
3.7 7000 Series Wrought Alloys .....	3-281
3.7.1 7010 Alloy .....	3-281
3.7.2 7049/7149 Alloy .....	3-289
3.7.3 7050 Alloy .....	3-306
3.7.4 7075 Alloy .....	3-344
3.7.5 7150 Alloy .....	3-403
3.7.6 7175 Alloy .....	3-415
3.7.7 7249 Alloy .....	3-430
3.7.8 7475 Alloy .....	3-434
3.8 200.0 Series Cast Alloys .....	3-462
3.8.1 A201.0 Alloy .....	3-462
3.9 300.0 Series Cast Alloys .....	3-472

NOTE: Information and data for alloys deleted from MIL-HDBK-5 may be obtained through the Chairman, MIL-HDBK-5 Coordination Activity.

**MIL-HDBK-5H****1 December 1998*****CONTENTS (Continued)***

<b><u>Section</u></b>	<b><u>Page</u></b>
3.9.1 354.0 Alloy .....	3-472
3.9.2 355.0 Alloy .....	3-474
3.9.3 C355.0 Alloy .....	3-476
3.9.4 356.0 Alloy .....	3-478
3.9.5 A356.0 Alloy .....	3-480
3.9.6 A357.0 Alloy .....	3-484
3.9.7 D357.0 Alloy .....	3-487
3.9.8 359.0 Alloy .....	3-490
3.11 Element Properties .....	3-492
3.11.1 Beams .....	3-492
3.11.2 Columns .....	3-492
3.11.3 Torsion .....	3-495
References .....	3-499
 <b>Chapter 4</b>	
4.0 Magnesium Alloys .....	4-1
4.1 General .....	4-1
4.1.1 Alloy Index .....	4-1
4.1.2 Material Properties .....	4-1
4.1.3 Physical Properties .....	4-2
4.1.4 Environmental Considerations .....	4-2
4.1.5 Alloy and Temper Designations .....	4-3
4.1.6 Joining Methods .....	4-3
4.2 Magnesium-Wrought Alloys .....	4-6
4.2.1 AZ31B .....	4-6
4.2.2 AZ61A .....	4-17
4.2.3 ZK60A .....	4-19
4.3 Magnesium Cast Alloys .....	4-27
4.3.1 AM100A .....	4-27
4.3.2 AZ91C/AZ91E .....	4-29
4.3.3 AZ92A .....	4-33
4.3.4 EZ33A .....	4-39
4.3.5 QE22A .....	4-44
4.3.6 ZE41A .....	4-48
4.4 Element Properties .....	4-53
4.4.1 Beams .....	4-53
4.4.2 Columns .....	4-53
4.4.3 Torsion .....	4-56
References .....	4-57
 <b>Chapter 5</b>	
5.0 Titanium .....	5-1
5.1 General .....	5-1
5.1.1 Titanium Index .....	5-1

NOTE: Information and data for alloys deleted from MIL-HDBK-5 may be obtained through the Chairman, MIL-HDBK-5 Coordination Activity.

**MIL-HDBK-5H****1 December 1998*****CONTENTS (Continued)***

<b><u>Section</u></b>	<b><u>Page</u></b>
5.1.2 Material Properties .....	5-1
5.1.3 Manufacturing Considerations .....	5-2
5.1.4 Environmental Considerations .....	5-2
<b>5.2 Unalloyed Titanium .....</b>	<b>5-5</b>
5.2.1 Commercially Pure Titanium .....	5-5
<b>5.3 Alpha and Near-Alpha Titanium Alloys .....</b>	<b>5-15</b>
5.3.1 Ti-5Al-2.5Sn .....	5-15
5.3.2 Ti-8Al-1Mo-1V .....	5-27
5.3.3 Ti-6Al-2Sn-4Zr-2Mo .....	5-43
<b>5.4 Alpha-Beta Titanium Alloys .....</b>	<b>5-51</b>
5.4.1 Ti-6Al-4V .....	5-51
5.4.2 Ti-6Al-6V-2Sn .....	5-94
<b>5.5 Beta, Near-Beta, and Metastable-Beta Titanium Alloys .....</b>	<b>5-112</b>
5.5.1 Ti-13V-11Cr-3Al .....	5-112
5.5.2 Ti-15V-3Cr-3Sn-3Al (Ti-15-3) .....	5-129
5.5.3 Ti-10V-2Fe-3Al (Ti-10-2-3) .....	5-133
<b>5.6 Element Properties .....</b>	<b>5-138</b>
5.6.1 Beams .....	5-138
<b>References .....</b>	<b>5-139</b>
 <b>Chapter 6</b>	
<b>6.0 Heat-Resistant Alloys .....</b>	<b>6-1</b>
<b>6.1 General .....</b>	<b>6-1</b>
6.1.1 Material Properties .....	6-3
<b>6.2 Iron-Chromium-Nickel-Base Alloys .....</b>	<b>6-4</b>
6.2.0 General Comments .....	6-4
6.2.1 A-286 .....	6-4
6.2.2 N-155 .....	6-15
<b>6.3 Nickel-Base Alloys .....</b>	<b>6-19</b>
6.3.0 General Comments .....	6-19
6.3.1 Hastelloy X .....	6-21
6.3.2 Inconel 600 .....	6-27
6.3.3 Inconel 625 .....	6-34
6.3.4 Inconel 706 .....	6-45
6.3.5 Inconel 718 .....	6-51
6.3.6 Inconel X-750 .....	6-77
6.3.7 Rene 41 .....	6-83
6.3.8 Waspaloy .....	6-90
<b>6.4 Cobalt-Base Alloys .....</b>	<b>6-96</b>
6.4.0 General Comments .....	6-96
6.4.1 L-605 .....	6-97
6.4.2 HS 188 .....	6-104
<b>References .....</b>	<b>6-120</b>

NOTE: Information and data for alloys deleted from MIL-HDBK-5 may be obtained through the Chairman, MIL-HDBK-5 Coordination Activity.

**MIL-HDBK-5H****1 December 1998*****CONTENTS (Continued)***

<b><u>Section</u></b>	<b><u>Page</u></b>
<b>Chapter 7</b>	
7.0 Miscellaneous Alloys and Hybrid Materials . . . . .	7-1
7.1 General . . . . .	7-1
7.2 Beryllium . . . . .	7-1
7.2.1 Standard Grade Beryllium . . . . .	7-1
7.3 Copper and Copper Alloys . . . . .	7-7
7.3.0 General . . . . .	7-7
7.3.1 Maganese Bronzes . . . . .	7-8
7.3.2 Copper Beryllium . . . . .	7-11
7.4 Multiphase Alloys . . . . .	7-20
7.4.0 General . . . . .	7-20
7.4.1 MP35N Alloy . . . . .	7-20
7.4.2 MP159 Alloy . . . . .	7-26
7.5 Aluminum Alloy Sheet Laminates . . . . .	7-31
7.5.0 General . . . . .	7-31
7.5.1 2024-T3 Aramid Fiber Reinforced Sheet Laminate . . . . .	7-31
References . . . . .	7-49
<b>Chapter 8</b>	
8.0 Structural Joints . . . . .	8-1
8.1 Mechanically Fastened Joints . . . . .	8-2
8.1.1 Introduction and Fastener Indexes . . . . .	8-2
8.1.2 Solid Rivets . . . . .	8-9
8.1.3 Blind Fasteners . . . . .	8-34
8.1.4 Swaged Collar/Upset-Pin Fasteners . . . . .	8-96
8.1.5 Threaded Fasteners . . . . .	8-111
8.1.6 Special Fasteners . . . . .	8-133
8.2 Metallurgical Joints . . . . .	8-136
8.2.1 Introduction and Definitions . . . . .	8-136
8.2.2 Welded Joints . . . . .	8-136
8.2.3 Brazing . . . . .	8-158
8.3 Bearings, Pulleys, and Wire Rope . . . . .	8-158
References . . . . .	8-159
<b>Chapter 9</b>	
9.0 Summary . . . . .	9-2
9.1 General . . . . .	9-5
9.1.1 Introduction . . . . .	9-5
9.1.2 Applicability . . . . .	9-5
9.1.3 Approval Procedures . . . . .	9-5
9.1.4 Documentation Requirements . . . . .	9-5
9.1.5 Symbols and Definitions . . . . .	9-6
9.1.6 Data Requirements for Incorporation of a New Product into MIL-HDBK-5 . . . . .	9-7
9.1.7 Procedures for the Submission of Mechanical Property Data . . . . .	9-12

NOTE: Information and data for alloys deleted from MIL-HDBK-5 may be obtained through the Chairman, MIL-HDBK-5 Coordination Activity.

**MIL-HDBK-5H****1 December 1998*****CONTENTS (Continued)***

<b><u>Section</u></b>	<b><u>Page</u></b>
<b>9.2 Room-Temperature Design Properties</b>	<b>9-18</b>
9.2.1 Introduction	9-18
9.2.2 Designations and Symbols	9-18
9.2.3 Computational Procedures, General	9-21
9.2.4 Specifying the Population	9-23
9.2.5 Deciding Between Direct and Indirect Computation	9-25
9.2.6 Determining the Appropriate Computation Procedure	9-26
9.2.7 Direct Computation for the Normal Distribution	9-29
9.2.8 Direct Computation for the Weibull Distribution	9-31
9.2.9 Direct Computation for an Unknown Distribution	9-32
9.2.10 Computation of Derived Properties	9-33
9.2.11 Determining Design Allowables by Regression Analysis	9-37
9.2.12 Examples of Computational Procedures	9-41
9.2.13 Modulus of Elasticity and Poisson's Ratio	9-59
9.2.14 Physical Properties	9-59
9.2.15 Presentation of Room-Temperature Design Properties	9-60
<b>9.3 Graphical Mechanical Property Data</b>	<b>9-65</b>
9.3.1 Elevated Temperature Curves	9-65
9.3.2 Typical Stress-Strain, Compression Tangent-Modulus, and Full-Range Stress-Strain Curves	9-73
9.3.3 Biaxial Stress-Strain Behavior	9-90
9.3.4 Fatigue Data Analysis	9-92
9.3.5 Fatigue-Crack-Propagation Data	9-147
9.3.6 Creep and Creep-Rupture Data	9-150
<b>9.4 Properties of Joints and Structures</b>	<b>9-169</b>
9.4.1 Mechanically Fastened Joints	9-169
9.4.2 Fusion-Welded Joints	9-195
<b>9.5 Miscellaneous Properties</b>	<b>9-206</b>
9.5.1 Fracture Toughness	9-206
<b>9.6 Statistical Procedures and Tables</b>	<b>9-213</b>
9.6.1 Goodness-of-Fit Tests	9-213
9.6.2 Tests of Significance	9-217
9.6.3 Data-Regression Techniques	9-223
9.6.4 Tables	9-234
9.6.5 Estimation Procedures for the Weibull Distribution	9-256
<b>References</b>	<b>9-258</b>
 <b>Appendices</b>	
A.0 Glossary	A-1
B.0 Alloy Index	B-1
C.0 Specification Index	C-1
D.0 Subject Index	D-1
E.0 Figure Index	E-1

NOTE: Information and data for alloys deleted from MIL-HDBK-5 may be obtained through the Chairman, MIL-HDBK-5 Coordination Activity.



**MIL-HDBK-5H****1 December 1998*****CHAPTER 1*****GENERAL****1.1 PURPOSE, PROCUREMENT, AND USE OF DOCUMENT**

**1.1.1 INTRODUCTION** — Since many aerospace companies manufacture both commercial and military products, the standardization of metallic materials design data, which are acceptable to Government procuring or certification agencies is very beneficial to those manufacturers as well as governmental agencies. Although the design requirements for military and commercial products may differ greatly, the required design values for the strength of materials and elements and other needed material characteristics are often identical. Therefore, this publication is to provide standardized design values and related design information for metallic materials and structural elements used in aerospace structures. The data contained herein or from approved items in the minutes of MIL-HDBK-5 coordination meetings are acceptable to the Air Force, the Navy, the Army, and the Federal Aviation Administration. Approval by the procuring or certifying agency must be obtained for the use of design values for products not contained herein.

This printed document is distributed by the Defense Area Printing Service (DAPS). It is the only official form of MIL-HDBK-5. If computerized MIL-HDBK-5 databases are used, caution should be exercised to ensure that the information in these databases is identical to that contained in this Handbook.

A copy of this Handbook can be requested by mail or FAX on company letterhead, showing the complete mailing address and point of contact. Assistance in ordering may be obtained by calling (215) 697-2179. The FAX number is (215) 697-1462.

Alternatively, the DD Form 1425, enclosed on page 1-43, may be filled out and mailed to:

DODSSP  
700 Robbins Avenue Bldg 4D  
Philadelphia, PA 19111-5094.

**1.1.2 SCOPE OF DOCUMENT** — This document is intended primarily as a source of design allowables, which are those strength properties of metallic materials and elements (primarily fasteners) that are widely used in the design of aerospace structures. These metallic materials include all systems potentially useful in aerospace and aircraft applications, including those involving reinforcing components. This document also contains information and data for other properties and characteristics, such as fracture toughness strength, fatigue strength, creep strength, rupture strength, fatigue-crack propagation rate, and resistance to stress corrosion cracking. The use of this type of information is not mandatory. Those properties presented as design allowables are listed as A-, B-, or S-basis values (see Section 1.4.1.1 for definition of basis). Data for other properties are presented as typical. The materials included in this document are standardized with regard to composition and processing methods and are described by industry or government specifications. When needed design allowables are not available in this document, the procuring or certifying government agency should be contacted to determine data requirements and documentation, which may be required to justify design values used by the aerospace company.

In addition to the properties of the materials and elements themselves, there are contained herein some of the more commonly used methods and formulas by which the strengths of various structural elements or

**MIL-HDBK-5H****1 December 1998**

components are calculated. In some cases, the methods presented are empirical and subject to further refinements. Any further expansion of information on element behavior in MIL-HDBK-5 will emphasize those material characteristics needed to assist the design function. Methods of structural analysis are not within the scope of this document.

Where available, applicable references are listed at the end of each chapter. The reference numbers correspond to the paragraph to which they most generally apply. References are provided for guidance to further information on a particular subject, but since data therein may not have met the guidelines criteria of Chapter 9, such material is not to be considered approved by virtue of its listing.

**1.1.3 USE OF DESIGN MECHANICAL PROPERTIES** — It is customary to assign minimum values to certain mechanical properties of materials as procurement specification requirements. In the absence of acceptable statistical data, the design mechanical properties given herein are based on these minimum values (see S-Basis in Section 1.4.1.1). The manner in which these design mechanical properties are to be used will depend on the type of structure being considered and will be specified in the detailed structural requirements of the procuring or certificating agency. The use of the different design mechanical properties, such as ultimate tensile strength, yield strength, etc.; the factors of safety associated with them; and the arbitrary reductions in allowable stresses (which may be in the nature of specific requirements, or may be considered necessary in particular cases); will not be taken up in detail since information of this sort does not affect the material properties as such.

## **1.2 SYMBOLS, ABBREVIATIONS, AND SYSTEMS OF UNITS**

**1.2.1 SYMBOLS AND ABBREVIATIONS** — The symbols and abbreviations used in this document are defined in this section with the exception of statistical symbols. These latter symbols are defined in Appendix A.

A	Area of cross section, square inches; ratio of alternating stress to mean stress; subscript “axial”; A basis for mechanical-property values (see Section 1.4.1.1)
AISI	American Iron and Steel Institute
AMS	Aerospace Materials Specification (published by Society of Automotive Engineers, Inc.)
AN	Air Force-Navy Aeronautical Standard
Ann	Annealed
ASTM	American Society for Testing and Materials
a	Amplitude; crack or flaw dimension
$a_c$	Critical half crack length
$a_o$	Initial half crack length
B	Biaxial ratio (see Equation 1.3.2.8); B basis for mechanical-property values (see Section 1.4.1.1)
Btu	British thermal unit(s)
BUS	Individual or typical bearing ultimate strength
BYS	Individual or typical bearing yield strength
b	Width of sections; subscript “bending”
br	Subscript “bearing”
C	Specific heat; Celsius; Constant
CEM	Consumable electrode melted
CRES	Corrosion resistant steel (stainless steel)
C(T)	Compact tension
CYS	Individual or typical compressive yield strength
c	Fixity coefficient for columns; subscript “compression”
cpm	Cycles per minute
D	Diameter; hole or fastener diameter; dimpled hole
d	Mathematical operator denoting differential

**MIL-HDBK-5H****1 December 1998**

E	Modulus of elasticity in tension; average ratio of stress to strain for stress below proportional limit
$E_c$	Modulus of elasticity in compression; average ratio of stress to strain below proportional limit
$E_s$	Secant modulus of elasticity
$E_t$	Tangent modulus of elasticity
e	Elongation in percent, a measure of the ductility of a material based on a tension test; unit deformation or strain; subscript “fatigue or endurance”; the minimum distance from a hole center to the edge of the sheet
$e_e$	Elastic strain
$e_p$	Plastic strain
e/D	Ratio of edge distance to hole diameter (bearing strength)
ELI	Extra low interstitial (grade of titanium alloy)
ER	Equivalent round
ESR	Electro-slag remelted
F	Design stress; Fahrenheit
$F_A$	Design axial stress
$F_b$	Design bending stress; modulus of rupture in bending
$F_{bru}$	Design ultimate bearing stress
$F_{bry}$	Design bearing yield stress
$F_c$	Design column stress
$F_c'$	Maximum test column stress
$F_{cc}$	Design crushing or crippling stress (upper limit of column stress for local failure)
$F_{cu}$	Design ultimate compressive stress
$F_{cy}$	Design compressive yield stress at which permanent strain equals 0.002
$F_{cy}'$	Standard material column compressive yield stress
$F_H$	Design Hoop stress
$F_s$	Design shear stress
$F_{sp}$	Design proportional limit in shear
$F_{st}$	Design modulus of rupture in torsion
$F_{su}$	Design ultimate stress in pure shear (this value represents the average shear stress over the cross section)
$F_{sy}$	Design shear yield stress
$F_{tp}$	Design proportional limit in tension
$F_{tu}$	Design tensile stress
$F_{ty}$	Design tensile yield stress at which permanent strain equals 0.002
f	Internal (or calculated) stress; stress applied to the gross flawed section; creep stress
$f_b$	Internal (or calculated) primary bending stress
$f_c$	Internal (or calculated) compressive stress; maximum stress at fracture: gross stress limit (for screening elastic fracture data)
$f_c'$	Test material critical column stress
$f_{cy}'$	Test material column compressive yield stress
$f_{pl}$	Plastic stress
$f_s$	Internal (or calculated) shear stress
$f_t$	Internal (or calculated) tensile stress
ft	Foot: feet
G	Modulus of rigidity (shear modulus)
GPa	Gigapascal(s)
g	Gram(s)
H	Subscript “hoop”
HIP	Hot isostatically pressed
hr	Hour(s)

**MIL-HDBK-5H****1 December 1998**

I	Moment of inertia
i	Slope (due to bending) of neutral plane of a beam, in radians (1 radian = 57.3 degrees)
in.	Inch(es)
J	Torsion constant (= $I_p$ for round tubes); Joule
K	A constant, generally empirical; thermal conductivity; stress intensity; Kelvin; correction factor
$K_{app}$	Apparent plane stress fracture toughness or residual strength
$K_c$	Critical plane stress fracture toughness, a measure of fracture toughness at point of crack growth instability
$K_{Ic}$	Plane strain fracture toughness
$K_N$	Empirically calculated fatigue notch factor
$K_t$	Theoretical elastic stress concentration factor
k	Strain at unit stress
ksi	Kips (1,000 pounds) per square inch
L	Length; subscript “lateral”; longitudinal (grain direction)
$L'$	Equivalent column length in buckling
LT	Long transverse (grain direction)
lb	Pound
M	Applied moment or couple, usually a bending moment
Mc	Machine countersunk
Mg	Megagram(s)
MIG	Metal-inert-gas (welding)
MPa	Megapascal(s)
MS	Military Standard
M.S.	Margin of safety
M(T)	Middle tension
m	Subscript “mean”; meter; slope
mm	Millimeter(s)
N	Fatigue cycles to failure; Newton; normalized
NAS	National Aerospace Standard
n	Subscript “normal”; cycles applied to failure; shape parameter for the standard stress-strain curve (Ramberg-Osgood parameter); number of fatigue cycles endured
P	Applied load (total, not unit, load); exposure parameter; probability
Pu	Test ultimate load, pounds per fastener
Py	Test yield load, pounds per fastener
p	Subscript “polar”; subscript “proportional limit”
psi	Pounds per square inch
Q	Static moment of a cross section
Q&T	Quenched and tempered
R	Stress ratio, ratio of minimum stress to maximum stress in a fatigue cycle; reduced ratio
$R_b$	Stress ratio in bending
$R_c$	Stress ratio in compression; Rockwell hardness - C scale
$R_s$	Stress ratio in shear or torsion; ratio of applied load to allowable shear load
$R_t$	Ratio of applied load to allowable tension load
R.H.	Relative humidity
RA	Reduction of area
RMS	Root-mean-square (surface finish)
RT	Room temperature
r	Radius; root radius; reduced ratio (regression analysis)
S	Shear force; nominal stress, fatigue; S basis for mechanical-property values (see Section 1.4.1.1)
$S_a$	Stress amplitude, fatigue
$S_e$	Fatigue limit
$S_{eq}$	Equivalent stress

**MIL-HDBK-5H****1 December 1998**

$S_m$	Mean stress, fatigue
$S_{max}$	Highest algebraic value of stress in the stress cycle
$S_{min}$	Lowest algebraic value of stress in the stress cycle
$S_r$	Algebraic difference between the maximum and minimum stresses in one cycle
SAE	Society of Automotive Engineers
SCC	Stress-corrosion cracking
ST	Short transverse (grain direction)
STA	Solution treated and aged
SUS	Individual or typical shear ultimate strength
SYS	Individual or typical shear yield strength
s	Subscript “shear”
S/N	S = stress; N = number of cycles
T	Applied torsional moment; transverse (grain direction); subscript “transverse”
TIG	Tungsten-inert-gas (welding)
TUS	Individual or typical tensile ultimate strength
TYS	Individual or typical tensile yield strength
$T_F$	Exposure temperature
t	Thickness; subscript “tension”; exposure time; elapsed time
U	Factor of utilization
u	Subscript “ultimate”
W	Width of M(T) specimen; Watt
x	Distance along a coordinate axis
Y	Nondimensional factor relating component geometry and flaw size
y	Deflection (due to bending) of elastic curve of a beam; distance from neutral axis to given fiber; subscript “yield”; distance along a coordinate axis
Z	Section modulus, $I/y$
z	Distance along a coordinate axis
$\alpha$	Coefficient of thermal expansion, mean; constant
$\beta$	Constant
$\delta$	Deflection
$\epsilon_t$	Total (elastic plus plastic) strain at failure determined from tensile stress-strain curve
$\Phi$	Angular deflection
$\rho$	Radius of gyration; Neubur constant (block length)
$\mu$	Poisson’s ratio
$\omega$	Density; flank angle
$\infty$	Infinity

**1.2.2 INTERNATIONAL SYSTEM OF UNITS (SI)** — The design allowables listed in MIL-HDBK-5 are given in customary units of U.S. measure to ensure compatibility with government and industry material specifications and current aerospace design practice. Table 1.2.2 may be used to assist in the conversion of these units to SI units when desired. Prefixes for the SI units shown in this table were selected to give the same number of significant figures as are currently used in MIL-HDBK-5.

**MIL-HDBK-5H****1 December 1998****Table 1.2.2. Conversion of U.S. Units of Measure Used in MIL-HDBK-5 to SI Units**

Quantity or Property	To Convert From U. S. Unit	Multiply by <sup>a</sup>	SI Unit <sup>b</sup>
Area	in. <sup>2</sup>	645.16 <sup>c</sup>	Millimeter <sup>2</sup> (mm <sup>2</sup> )
Force	lb	4.4482	Newton (N)
Length	in.	25.4 <sup>c</sup>	Millimeter (mm)
Stress	ksi	6.895	Megapascal (MPa) <sup>d</sup>
Stress intensity factor	ksi $\sqrt{\text{in.}}$	1.0989	Megapascal $\sqrt{\text{meter}}$ (MPa $\cdot \text{m}^{1/2}$ ) <sup>d</sup>
Modulus	10 <sup>3</sup> ksi	6.895	Gigapascal (GPa) <sup>d</sup>
Temperature	°F	$\frac{F + 459.67}{1.8}$	Kelvin (K)
Density ( $\omega$ )	lb/in. <sup>3</sup>	27.680	Megagram/meter <sup>3</sup> (Mg/m <sup>3</sup> )
Specific heat (C)	Btu/lb·F (or Btu·lb <sup>-1</sup> ·F <sup>-1</sup> )	4.1868 <sup>c</sup>	Joule/(gram·Kelvin) (J/g·K) or (J·g <sup>-1</sup> ·K <sup>-1</sup> )
Thermal conductivity (K)	Btu/[(hr)(ft <sup>2</sup> )(F)/ft] (or Btu·hr <sup>-1</sup> ·ft <sup>-2</sup> ·F <sup>-1</sup> ·ft)	1.7307	Watt/(meter·Kelvin) W/(m·K) or (W·m <sup>-1</sup> ·K <sup>-1</sup> )
Thermal expansion ( $\alpha$ )	in./in./F (or in.·in. <sup>-1</sup> ·F <sup>-1</sup> )	1.8	Meter/meter/Kelvin m/(m·K) or (m·m <sup>-1</sup> ·K <sup>-1</sup> )

a Conversion factors to give significant figures are as specified in ASTM E 380, NASA SP-7012, second revision. NBS Special Publication 330, and *Metals Engineering Quarterly*.

b Prefix Multiple Prefix Multiple  
giga (G) 10<sup>9</sup> milli (m) 10<sup>-3</sup>  
mega (M) 10<sup>6</sup> micro ( $\mu$ ) 10<sup>-6</sup>  
kilo (k) 10<sup>3</sup>

c Conversion factor is exact.

d One Pascal (Pa) = one Newton/meter<sup>2</sup>.

## 1.3 COMMONLY USED FORMULAS

**1.3.1 GENERAL** — The formulas in the following sections are listed for reference purposes. The sign conventions generally accepted in their use are that quantities associated with tensile action (load, stress, strain, etc.) are considered as positive, and quantities associated with compressive action are considered as negative. When compressive action is of primary interest, however, it is sometimes convenient to consider the associated quantities to be positive. Formulas for statistical computations to obtain design allowables are presented in Chapter 9.

### 1.3.2 SIMPLE UNIT STRESSES

**1.3.2.1**  $f_t = P/A$  (tension)

**1.3.2.2**  $f_c = P/A$  (compression)

**1.3.2.3**  $f_b = My/I = M/Z$

**MIL-HDBK-5H****1 December 1998**

- 1.3.2.4**  $f_s = S/A$  (average direct shear stress)  
**1.3.2.5**  $f_s = SQ/I_b$  (longitudinal or transverse shear stress)  
**1.3.2.6**  $f_s = Ty/I_p$  (shear stress in round tubes due to torsion)  
**1.3.2.7**  $f_s = T/2At$  (shear stress due to torsion in thin-walled structures of closed section; note that A is the area enclosed by the median line of the section)  
**1.3.2.8**  $f_A = Bf_H$ ;  $f_T = Bf_L$

**1.3.3 COMBINED STRESSES (SEE SECTION 1.5.3.5)**

- 1.3.3.1**  $f_A = f_c + f_b$  (compression and bending)  
**1.3.3.2**  $f_{s \max} = \left[ f_s^2 + (f_n/2)^2 \right]^{1/2}$  (compression, bending, and torsion)  
**1.3.3.3**  $f_{n \max} = (f_n/2) + f_{s \max}$

**1.3.4 DEFLECTIONS (AXIAL)**

- 1.3.4.1**  $e = \delta/L$  (unit deformation or strain)  
**1.3.4.2**  $E = f/e$  (This equation applies when E is to be found from tests in which f and e are measured.)  
**1.3.4.3**  $\delta = eL = (f/E)L$   
 $= PL/(AE)$  (This equation applies when the deflection is to be calculated using a known value of E.)

**1.3.5 DEFLECTIONS (BENDING)**

- 1.3.5.1**  $di/dx = M/(EI)$  (change of slope per unit length of beam, radians per unit length)

- 1.3.5.2**  $i_2 = i_1 + \int_{x_1}^{x_2} M/(EI) dx$  — slope at Point 2. (The integral denotes the area under the curve of  $M/(EI)$  plotted against x, between the limits of  $x_1$  and  $x_2$ .)

- 1.3.5.3**  $y_2 = y_1 + i_1(x_2 - x_1) + \int_{x_1}^{x_2} M/(EI) (x_2 - x_1) dx$  — deflection at Point 2. (The integral denotes the area under the curve having ordinates equal to  $M/(EI)$  multiplied by the corresponding distances to Point 2, plotted against x, between the limits of  $x_1$  and  $x_2$ .)

- 1.3.5.3(a)**  $y_2 = y_1 + \int_{x_1}^{x_2} i dx$  — deflection at Point 2. (The integral denotes the area under the curve of  $x_1(i)$  plotted against x, between the limits  $x_1$  and  $x_2$ .)

**1.3.6 DEFLECTION (TORSION)**

- 1.3.6.1**  $d\Phi/dx = T/(GJ)$  (change of angular deflection or twist per unit length of member, radians per unit length)

**MIL-HDBK-5H****1 December 1998**

$$1.3.6.2 \quad \Phi = \int_{x_1}^{x_2} T/(GJ) \, dx \quad (\text{Total twist over a length from } x_1 \text{ to } x_2. \text{ The integral denotes the area under the curve of } T/GJ \text{ plotted against } x, \text{ between the limits of } x_1 \text{ and } x_2.)$$

$$1.3.6.2 (a) \quad \Phi = LT/(GJ) \quad (\text{used when torque } T/GJ \text{ is constant over length } L.)$$

**1.3.7 BIAXIAL ELASTIC DEFORMATION**

$$1.3.7.1 \quad \mu = e_y/e_x \quad \frac{\text{unit lateral deformation}}{\text{unit axial deformation}} \quad (\text{Poisson's ratio in uniaxial loading})$$

$$1.3.7.2 \quad Ee_x = f_x - \mu f_y$$

$$1.3.7.3 \quad Ee_y = f_y - \mu f_x$$

$$1.3.7.4 \quad E_{\text{biaxial}} = E/(1-\mu B) \quad (\text{biaxial elastic modulus})$$

**1.3.8 BASIC COLUMN FORMULA**

$$1.3.8.1 \quad F_c = \pi^2 E_c / (L'/\rho)^2 \quad \text{where } L' = L/\sqrt{c} \quad (\text{see References 1.3.8.1 and 1.7.1(b) for values for } c)$$

**1.4 BASIC PRINCIPLES AND DEFINITIONS**

**1.4.1 GENERAL** — It is assumed that engineers using this document are thoroughly familiar with the basic principles of strength of materials. A brief summary of such material is presented here for the sake of uniformity and to emphasize certain principles of special importance. Complete lists of abbreviations, definitions, and symbols are located in Appendix A. The design mechanical-property values of various metals and elements are provided in the tables in each chapter.

As a means of maintaining uniformity in the presentation of mechanical-property values in this document and a high level of assurance in the values reported, statistical techniques are employed where possible and requirements have been established to ensure adequacy of supporting data and description of the product represented by the mechanical-property values.

**1.4.1.1 Basis** — Primary strength properties ( $F_{tu}$ ,  $F_{ty}$ ,  $F_{cy}$ ,  $F_{su}$ ,  $F_{bru}$ , and  $F_{bry}$ ) presented in the design mechanical-property tables are minimum values at room temperature, established on an A-, B-, or S-basis, as defined in Section 9.2.2.1. Properties at other temperatures, when determined in accordance with Section 9.2.10, shall be regarded as having the same basis as the corresponding room-temperature values.

The use of B-basis values is permitted in design by the Air Force, Navy, and Federal Aviation Administration, subject to certain limitations as specified by each agency. Reference should be made to specific requirements of the applicable agency before using the B values in design.

Elongation and reduction of area properties listed in the design mechanical-property tables are minimum values at room temperature and are presented on an S-basis only. Elongation and reduction in area at other temperatures, as well as elastic properties ( $E$ ,  $E_c$ ,  $G$ , and  $\mu$ ), physical properties ( $\omega$ ,  $C$ ,  $K$ , and  $\alpha$ ), creep properties, fatigue properties, and fracture toughness properties shall be regarded as typical values unless a basis is specifically indicated.



**MIL-HDBK-5H****1 December 1998**

Percentages selected from effect-of-temperature curves represent reduced ratios of the property-at-temperature to the room-temperature value for that property. The product of a percentage and the room-temperature value for a property shall be regarded as yielding a property-at-temperature value having the same basis as that indicated for the room-temperature value of the property. Unless otherwise indicated, the percentage curves for these properties apply to all forms and thicknesses shown in the design mechanical-property table for the temper indicated. Normally, these curves represent materials exposed at testing temperatures for times up to one-half hour and strained at the rate specified for the individual property. When data are adequate, curves for other exposure times are also presented and are labeled appropriately. See Section 9.3.1.

**1.4.1.2 Directly Calculated Values** — A directly calculated value is a mechanical property determined directly from mechanical property data. The statistical methods, minimum data requirements, and process to arrive at the A- and B-basis values are described in Sections 9.2.4 through 9.2.9.

**1.4.1.3 Derived Mechanical Properties** — A derived value is a mechanical property that is determined through its relationship to an established property. A derived property may be a tensile strength in a different grain direction from the established direction, or it may be another strength property (compression, shear, or bearing), or it may be the same strength property at a different temperature. They are presented in tabular form in stress units in design mechanical-properties tables or in graphical form in percentage units of the room temperature strength property. Tabular values will have both their dimensional units and data basis indicated. The methods to compute the derived properties are discussed in Sections 9.2.10 and 9.2.11.

**1.4.2 STRESS**

**1.4.2.1 General** — The term “stress” as used herein always implies a force per unit area and is a measure of the intensity of the force acting on a definite plane passing through a given point (see Equations 1.3.3.1 and 1.3.2.2). The stress distribution may or may not be uniform, depending on the nature of the loading condition. For example, tensile stresses as found from Equation 1.3.2.1 are considered to be uniform. The bending stress determined from Equation 1.3.2.3 refers to the stress at a point located at a distance  $y$  from the neutral axis. The shear stress over the cross section of a member subjected to bending is not uniform. (Equation 1.3.2.4 gives the average shear stress.)

**1.4.2.2 Normal, Shear, and Principal Stresses** — The stresses acting at a point in any stressed member can be resolved into components acting on planes through the point.

The normal and shear stresses acting on any particular plane are the stress components perpendicular and parallel, respectively, to the plane. A simple conception of these stresses is that normal stresses tend to pull apart (tensile stresses) or press together (compressive stresses) adjacent particles of the material, whereas shear stresses tend to cause such particles to slide on each other. Tensile stresses are denoted arbitrarily (+) stresses and compressive stresses are called negative (-) stresses.

If one selects three mutually perpendicular planes through a point, there is always some orientation of this system such that only normal stresses exist, all other stresses being zero. These normal stresses are known as principal stresses, and the numerically largest of these is called the maximum principal stress.

**1.4.2.3 State of Stress** — A triaxial stress state is defined as one in which there are three principal stresses, none of which is equal to zero. When one of the principal stresses is equal to zero, the stress state is called biaxial. When two of the principal stresses are equal to zero, a uniaxial state of stress is said to exist.

**MIL-HDBK-5H****1 December 1998****1.4.3 STRAIN**

**1.4.3.1 General** — Strain is the change in length per unit length in a member or portion of a member. As in the case of stress, the strain distribution may or may not be uniform in a complex structural element, depending on the nature of the loading condition. Strains usually are present also in directions other than the direction or directions of the applied stresses.

**1.4.3.2 Normal and Principal Strains; Poisson's Ratio** — A normal strain is the strain associated with a normal stress; a normal strain takes place in the direction in which its associated normal stress acts. Normal strains that result from an increase in length are denoted arbitrarily as positive (+) strains and those that result from a decrease in length are called negative (-) strains.

If one selects three mutually perpendicular planes through a point, there is always some orientation of this system such that only normal strains exist, all shear strains being zero. These normal strains are known as principal strains. The direction of the principal strains coincides with the direction of the principal stresses only for isotropic materials.

In uniaxial loading, strain in the direction of the applied stress varies with that stress. The ratio of stress to strain has a constant value ( $E$ ) within the elastic range of a material but decreases when plastic strain is encountered. The axial strain is always accompanied by lateral strains of opposite sign in the two directions mutually perpendicular to the axial strain. Under uniaxial conditions, the absolute value of the ratio of either of the lateral strains to the axial strain is called Poisson's ratio. For stresses within the elastic range, this ratio is approximately constant. For stresses beyond the elastic limit, this ratio is a function of the axial strain and is then sometimes called the lateral contraction ratio. Information on the variation of Poisson's ratio with strain and with testing direction is available in Reference 1.4.3.2.

In multiaxial loading, the strains resulting from the application of each of the stresses are additive; thus, the strains in each of the principal directions must be calculated, taking into account each of the principal stresses and Poisson's ratio (see Equations 1.3.7.2 and 1.3.7.3 for biaxial loading).

**1.4.3.3 Shear Strain** — If an element of uniform thickness is subjected to pure shear, there will be a displacement of each side of the element relative to the opposite side. The shear strain is obtained by dividing this displacement by the distance between the sides of the element. It should be noted that shear strain is obtained by dividing a displacement by a distance at right angles to the displacement, whereas axial strain is obtained by dividing the deformation by a length measured in the same direction as the deformation.

**1.4.3.4 Strain Rate** — Loads on structures will result in conditions ranging from those where strains are constant to those where strains are rapidly changing. The stress-strain curve, ultimate tensile strength, and ductility of some materials are affected by changes in the rate of strain. For this reason, where available, statements or data relative to strain-rate effects are provided in connection with specific metals. These data apply only up to the value stated or to a rate of 1 percent per second, which is considered the maximum rate likely to occur in aircraft or missile structures except for nuclear effects. Unless otherwise stated for specific materials, strain rates can be assumed to have been between 0.001- and 0.01-inch per inch per minute to the yield strength. After yield strength was reached, the speed of testing can be assumed to have been increased to a rate, which did not exceed 0.5-inch per inch of gage length per minute to failure (ultimate strength). Property variations within this range of strain rate are considered too small to necessitate consideration in design. Most of the strain rates used to determine yield strength were between 0.003- and 0.007-inch per inch per minute.

**1.4.3.5 Elongation and Reduction of Area** — Elongation and reduction of area are measured in accordance with specification ASTM E 8.

## MIL-HDBK-5H


1 December 1998

**1.4.4 TENSILE PROPERTIES**

**1.4.4.1 General** — When a specimen of a certain material is tested in tension using the standard testing procedures in ASTM E 8, it is customary to plot the results of such a test as a “stress-strain diagram”. Typical tensile diagrams, not to scale, are shown in Figure 1.4.4.1. Typical stress-strain diagrams drawn to scale appear in appropriate chapters for the general information of the users of this document. These diagrams have been adjusted in such a manner that the slopes of the straight-line portions of the curves are equal to the elastic modulus values reported elsewhere for the specific material. It should be noted that the strain scale is nondimensional, whereas the stress scale is in pounds per square inch. The important mechanical properties, which can be shown in the stress-strain diagram, are discussed in Sections 1.4.4.2 to 1.4.4.7.

**1.4.4.2 Modulus of Elasticity ( $E$ )** — Referring to Figure 1.4.4.1, it will be noted that the first part of the diagram is typically a straight line. This indicates a constant ratio between stress and strain over that range. The numerical value of the ratio is called the “modulus of elasticity”, denoted by  $E$ . It will be noted that  $E$  is the slope of the straight portion of the stress-strain diagram and is determined by dividing the stress (in kilopounds per square inch [ksi]) by the strain (which is nondimensional). See Equation 1.3.4.2. Therefore,  $E$  has the same dimensions as stress; in this case, pounds per square inch.

Other moduli that are often of interest are the tangent modulus,  $E_t$ , and the secant modulus,  $E_s$ ;  $E_t$  and  $E_s$  change with stress above the proportional limit. The tangent modulus for a particular stress is the slope of the stress-strain diagram at a point corresponding to that stress, and the corresponding secant



**Figure 1.4.4.1. Typical tensile stress-strain diagrams.**

**MIL-HDBK-5H****1 December 1998**

modulus is the slope of a line drawn through the origin and a point on the diagram at the same stress.

Clad aluminum alloys may have two separate modulus values, as indicated in the typical curve presented in Figure 1.4.4.1. The initial, or primary, modulus is typically an average of the elastic moduli of the core and cladding, and it applies only up to the proportional limit of the cladding. For example, the primary modulus of 2024-T3 clad sheet applies only up to about 6 ksi. Similarly, the primary modulus of 7075-T6 clad sheet applies only up to approximately 12 ksi. A typical use of primary moduli is for low amplitude, high frequency fatigue. However, primary moduli should not be used for general stress analysis or structural design. Immediately above this point there is a short transition range, and the material then exhibits a secondary modulus up to the proportional limit of the core material. This secondary modulus is the slope of the second straight-line portion of the diagram. In some cases, the cladding is so little different from the core that a single modulus value is used.

**1.4.4.3 Tensile Proportional Limit ( $F_{ip}$ )** — The tensile proportional limit is the maximum stress in which strain remains directly proportional to stress. Since it is practically impossible to determine precisely this point on a stress-strain diagram, it is customary to assign a small value of permanent strain and identify the corresponding stress value (at the intersection with the stress strain curve) as the proportional limit. The selected permanent strain offset value should be stated when using the proportional limit.

**1.4.4.4 Tensile Yield Stress ( $F_y$ )** — The stress-strain diagrams for some steels show a sharp break at a stress below the ultimate tensile stress. At this critical stress, the material elongates considerably with no increase in stress (see Figure 1.4.4.1). The stress at which this takes place is referred to as the yield point. Most nonferrous metals and most high strength steels do not show this sharp break, but yield more gradually so that there is no yield point. This condition is illustrated in Figure 1.4.4.1. Since permanent deformations of any appreciable amount are undesirable in most structures, it is customary to adopt an arbitrary amount of permanent strain that is considered admissible for general purposes. The value of this strain has been established by material testing engineers as 0.002 in./in. and the corresponding stress is called the yield stress. For practical purposes, this may be determined from the stress-strain diagram by drawing a line parallel to the straight (or elastic) portion of the curve through a point representing zero stress and 0.002 strain (see Figure 1.4.4.1). The yield stress is taken as the stress at the intersection of this straight line with the stress-strain curve.

**1.4.4.5 Ultimate Tensile Stress ( $F_u$ )** — Figure 1.4.4.1 shows how the ultimate tensile stress is determined from the stress-strain diagram. It is simply the stress at the maximum load reached in the test. It should be noted that all stresses are based on the original cross-sectional area of the test specimen, without regard to the lateral contraction of the specimen, which actually occurs during the test. The ultimate tensile stress is commonly used as a criterion of the strength of the material for structural application, but it should be kept in mind that other strength properties may often be more important.

**1.4.4.6 Elongation ( $e$ )** — An additional property that is determined from the tensile test is elongation, which is a measure of ductility. Elongation is the increase in gage length, measured after fracture of the tensile specimen within the gage length, expressed as a percentage of the original gage length. Elongation is usually measured in 2 inches for rectangular tensile specimens and in 4D for round specimens, except welded specimens. See applicable material specification for specified gage length. Although tensile elongation is widely used as an indicator of ductility, the measurement can be significantly affected by testing variables, such as thickness and gage length of the test specimen. See Section 1.4.1.1 for data basis.

**1.4.4.7 Reduction of Area (RA)** — Another property determined from the tensile test is reduction of area, which is also a measure of ductility. Reduction of area is the difference, expressed as a percentage of original area, between the original cross sectional area of the tensile test specimen and the minimum cross-sectional area measured after fracture of the tensile specimen. The reduction of area

**MIL-HDBK-5H****1 December 1998**

measurement is less affected by testing variables than the elongation measurement, but it is more difficult to use on products having thin sections. See Section 1.4.1.1 for data basis.

**1.4.5 COMPRESSIVE PROPERTIES**

**1.4.5.1 General** — The results of compression tests can be plotted as stress-strain diagrams similar to those shown in Figure 1.4.4.1 for tension. The preceding remarks (with the exception of those pertaining to ultimate stress) concerning the specific tensile properties of the material apply in a similar manner to the compressive properties. It should be noted that the moduli of elasticity in tension and compression are approximately equal (or slightly greater in compression) for most of the commonly used structural materials. Special considerations concerning the ultimate compressive stress are taken up in the following section. An evaluation of techniques of obtaining compressive strength properties of thin sheet material is outlined in Reference 1.4.5.1.

**1.4.5.2 Ultimate Compressive Stress ( $F_{cu}$ )** — It is difficult to discuss this property without reference to column action. Almost any piece of material, unless very short, tends to buckle laterally as a column under compressive loadings, and the load at failure usually depends on the relation of the length of the piece to its cross-sectional dimensions. Column failure cannot occur, however, when a piece is very short in comparison with its cross-sectional dimensions, or when it is restrained laterally by external means. Under these conditions, some metallic materials will fail by fracture, thus giving a definite value for the ultimate compressive stress. Most metals, however, are so ductile that no fracture is encountered in compression. Instead of fracturing, the material yields and swells out, so that the increasing area continues to support the increasing load. It is almost impossible to select a value for the ultimate compressive stress of such materials without having some arbitrary criterion. For wrought metals, it is common practice to assume that the ultimate compressive stress is equal to the ultimate tensile stress. For some cast metals, which are relatively weak in tension, an ultimate compressive stress may be obtained from tests on short compact specimens. When tests are made on such specimens having an  $L/\rho$  approximately equal to 12, the ultimate stress obtained is called the block compressive stress.

**1.4.6 SHEAR PROPERTIES —**

**1.4.6.1 General** — The results of torsion tests on round tubes or round solid sections are sometimes plotted as torsion stress-strain diagrams. The modulus of elasticity in shear as determined from such a diagram is a basic shear property. Other properties, such as the proportional limit and ultimate shear stress, cannot be treated as basic properties because of the “form factor” effects.

**1.4.6.2 Modulus of Rigidity ( $G$ )** — This property is the ratio of the shear stress to the shear strain at low loads, or simply the initial slope of the stress-strain diagram for shear. It is also called the modulus of elasticity in shear. The relation between this property, Poisson’s ratio, and the modulus of elasticity in tension is expressed for homogeneous isotropic materials by the following equation:

$$G = \frac{E}{2(1 + \mu)} \quad [1.4.6.2]$$

**1.4.6.3 Proportional Limit in Shear ( $F_{sp}$ )** — This property is of particular interest in connection with formulas, which are based on considerations of perfect elasticity, as it represents the limiting value of shear stress to which these formulas can be accurately applied. As previously noted, this property cannot be determined directly from torsion tests. The results of research at the National Institute of Standards and Technology (NIST) show that the ratio of the proportional limit in shear to the proportional limit in tension can be assumed to be approximately 0.55 for the most materials.

**MIL-HDBK-5H****1 December 1998**

**1.4.6.4 Yield and Ultimate Stress in Shear** — These properties, as usually obtained from torsion tests, are not strictly basic properties, as they will depend on the shape of the test specimen. In such cases, they should be treated as moduli and should be used only with specimens, which are geometrically similar to those from which the test results were obtained.

The values for ultimate shear stress reported in the room-temperature property tables for the aluminum and magnesium sheet alloys are based on “punch” shear-type tests except as noted. Heavy section data are based on pin tests. The shear data on other alloys were also obtained from “pin” shear tests, except where thicknesses were too small.

**1.4.6.5 Shear Yield Strength** — An estimate of shear yield strength can be computed from tensile and compressive strength properties as follows:

$$F_{sy} = \frac{F_{ty}(L) + F_{ty}(LT) + F_{cy}(L) + F_{cy}(LT)}{4} \times \frac{2F_{su}}{F_{tu}(L) + F_{tu}(LT)} \quad [1.4.6.5]$$

where

- $(p)$  = primary load direction for shear
- $F_{tu}(L)$  = tensile ultimate strength, longitudinal direction
- $F_{tu}(LT)$  = tensile ultimate strength, long transverse direction
- $F_{ty}(L)$  = tensile yield strength, longitudinal direction
- $F_{ty}(LT)$  = tensile yield strength, long transverse direction
- $F_{cy}(L)$  = compressive yield strength, longitudinal direction
- $F_{cy}(LT)$  = compressive yield strength, long transverse direction
- $F_{su}$  = shear ultimate strength

**1.4.7 BEARING PROPERTIES**

**1.4.7.1 General** — Bearing strengths are of value in the design of joints and lugs. Only yield and ultimate values are obtained from bearing tests. The bearing stress is obtained by dividing the load on a pin, which bears against the edge of a hole, by the bearing area, where the area is the product of the pin diameter and sheet thickness.

The bearing test requires the use of special cleaning procedures as specified in ASTM E 238. In the various room-temperature property tables in this document, when the indicated values are based on tests with clean pins, the values are footnoted as “dry pin values”. See Reference 1.4.7.1 for additional information. Designers should consider the use of a reduction factor in applying these values to structural analyses.

In the definition of bearing values,  $t$  is sheet thickness,  $D$  is the hole diameter, and  $e$  is the edge distance measured from the hole center to the edge of the material in the direction of applied stress. Tabular values of static joint strengths are for  $e/D$  equal to 2. Bearing stress values for  $e/D$  of 1.5 shall not



**MIL-HDBK-5H****1 December 1998**

be used for  $e/D < 1.5$ . Bearing values for  $e/D < 1.5$  shall be substantiated by adequate tests, subject to the approval of the procuring or certificating agency. For edge distance ratios between  $e/D$  equal to 2 and  $e/D$  equal to 1.5, linear interpolation may be used.

Bearing values are applicable to  $t/D$  ratios from 0.18 to 1.00. Bearing values for  $t/D < 0.18$  or  $> 1.00$  must be substantiated by test. The percentage curves showing temperature effects on bearing strength may be used with  $e/D$  values of 1.5 and 2.0.

**1.4.7.2 Yield and Ultimate Bearing Stresses** —  $F_{bru}$  is the maximum stress withstood by a bearing specimen, and  $F_{bry}$  is the stress at an offset of 2 percent of the hole diameter of a bearing stress-deformation curve.

**1.4.8 TEMPERATURE EFFECTS**

**1.4.8.1 Low Temperature** — Temperatures below room temperature generally cause an increase in all strength properties of metals. Ductility usually decreases. For specific information, see the applicable chapter and references noted therein.

**1.4.8.2 Elevated Temperature** — Temperatures above room temperature usually cause a decrease in the strength properties of metals. This decrease is dependent on many factors, such as temperature and time of exposure and the characteristics of the material. Ductility may increase or decrease with increasing temperature depending on the same variables. Because of this dependence of strength and ductility at elevated temperatures on many variables, it is emphasized that the elevated-temperature properties given hereafter for specific materials apply only to the stated condition.

The effect of temperature on the static mechanical properties of various metals illustrated by means of a series of graphs of property (as percent of room temperature design allowable) versus temperature. The data for these graphs have been obtained from tests made over a limited range of strain rate. Some caution should be observed in using these static property curves at very high temperatures, particularly if the strain rate in the structure is much less than the strain rate used to obtain the basic material properties. The reason for this is that at very low strain rates or under sustained stresses, plastic deformation or creep deformation may occur to the detriment of the intended structural use.

**1.4.8.2.1 Creep- and Stress-Rupture Properties** —

*General* — Creep is defined as the time-dependent deformation of a material under an applied load. It is usually regarded as an elevated-temperature phenomenon, although some materials creep at room temperature. If permitted to continue indefinitely, creep terminates in rupture. Since creep in service is usually typified by complex conditions of loading and temperature, the number of possible stress-temperature-time profiles is infinite. For economic reasons, creep data for general design use are usually obtained under conditions of constant uniaxial load and temperature. Creep data are sometimes obtained under conditions of cyclic uniaxial load and constant temperature (see Section 9.3.6). It is recognized that, when significant creep appears likely to occur, it may be necessary to test under actual service conditions because of difficulties in extrapolating from the simple to the complex stress-temperature-time conditions.

Damage incurred in a material as a result of creep (including effects resulting from elevated-temperature exposure) is cumulative. This damage may involve the tempering or annealing of hardened materials and the initiation and growth of cracks and voids (initially of microscopic size) within a material. Its effects are often recognizable as a reduction in short-time strength properties or ductility, both at room and at elevated temperatures.

*Creep-Rupture Curve* — The results of tests of materials under a constant load and temperature are usually plotted as strain versus time up to a rupture. A typical plot of creep-rupture data is shown in

## MIL-HDBK-5H

1 December 1998

Figure 1.4.8.2.1(a). The strain indicated in this curve includes both the instantaneous deformation due to loading and the plastic strain due to creep. Other definitions and terminology are included in Section 9.3.6.2.




Figure 1.4.8.2.1(a). Typical creep-rupture curve.

*Creep- or Stress-Rupture Data Presentations* — The results of creep- or stress-rupture tests conducted over a range of stresses and temperatures are presented as creep- or stress-rupture curves such as those presented in Figure 1.4.8.2.1(b). The data points represent time to X percent strain or stress rupture for specific stresses and temperatures. The curves represent a best-fit representation of the data trends using a Larson-Miller parameter or similar consolidation equation. Further details on the analysis methods are given in Section 9.3.6 and Reference 1.4.8.2.1(a).




Figure 1.4.8.2.1(b). Typical creep- or stress-rupture curves.



**MIL-HDBK-5H****1 December 1998**

Some creep data are still presented in creep nomographs as shown in Figures 5.4.1.2.7, 6.3.7.1.7, and 6.4.1.1.7. For these cases, the analysis and presentation were based primarily on Reference 1.4.8.2.1(b). The presentation of creep data in the form of a nomograph is not in compliance with Section 9.3.6. Therefore, these creep nomographs will be replaced in the near future.

**1.4.9 FATIGUE PROPERTIES**

**1.4.9.1 General** — Repeated loads are one of the major causes for reducing design allowable stresses below those listed in the various tables of static properties ( $F_u$ ,  $F_{ty}$ , etc.). These reductions vary extensively in degree and are a function of the design practices of the producer of parts. Therefore, no discussion of design use of fatigue (repeated load) data is included herein. However, some basic laboratory test data are useful in the materials selection and preliminary design processes and such data are therefore provided in the appropriate materials section, whenever available.

In the past, common methods of obtaining and reporting repeated load (fatigue) data included axial-loading tests, plate bending tests, rotating bending tests, and torsion tests. Rotating bending tests apply completely reversed (tension-compression) stressing to round specimens. Tests of this type are now seldom conducted for aerospace use and have therefore been dropped. For similar reasons, flexure fatigue data also have been dropped. No significant amount of torsional fatigue data have ever been available. Axial-loading tests, the only type retained herein, not only can consist of completely reversed loading (mean stress equals zero), but the mean stress can be varied.

**1.4.9.2 Terminology** — A number of symbols and definitions are commonly used in fatigue studies. The most important of these are presented in Section 9.3.4.2.

**1.4.9.3 Graphical Display of Fatigue Data** — The results of axial-load and axial-strain fatigue tests are reported on S/N and  $\epsilon/N$  diagrams, respectively. Figure 1.4.9.3(a) shows a family of axial load S/N curves for a material, the data for each curve having been taken at a single stress ratio, R.

S/N and  $\epsilon/N$  diagrams are shown in MIL-HDBK-5 with the raw data plotted for each stress or strain ratio or, in some cases, mean stress. A best-fit curve is drawn through the data at each test condition. For load-control fatigue data, the individual curves are normally based on an equivalent stress consolidation of the data at all stress ratios, as shown in Figure 1.4.9.3(b). For strain-control fatigue data, an equivalent strain consolidation is used.

Elevated temperature fatigue data are treated in the same manner as room temperature data, as long as creep is not a major factor and room temperature analysis methods can be successfully applied. In the limited number of cases where creep-strain data have been recorded as a part of an elevated temperature fatigue test series, S/N (or  $\epsilon/N$ ) plots are constructed for specific creep-strain levels, in addition to the customary plot of maximum stress (or strain) versus cycles to failure.

The S/N or  $\epsilon/N$  curves may not apply directly to the design of structures because they may not take into account the effect of specific stress concentration associated with reentrant corners, notches, holes, joints, rough surfaces, and other similar conditions, which are present in fabricated parts. The localized high stresses induced in fabricated parts by such stress raisers are of much greater importance for repeated loading than they are for static loading. They reduce the fatigue life of fabricated parts far below that which would be predicted by comparing the smooth-specimen fatigue strength directly with the nominal calculated stresses for the parts in question. Fabricated parts in test have been found to fail at less than 50,000 repetitions of load when the nominal stress was far below that which could be repeated many millions of times of a smooth machined specimen.

MIL-HDBK-5H  
1 December 1998




Figure 1.4.9.3(a). Best-fit S/N curve diagram for a material at various stress ratios.




Figure 1.4.9.3(b). Consolidated fatigue data for a material using the equivalent stress parameter.

**MIL-HDBK-5H****1 December 1998**

The notched fatigue data in the figures are presented so that by comparing the notched data with those from smooth specimens, the serious effect of a sharp notch on fatigue strength can be seen. All of the mean fatigue curves presented in MIL-HDBK-5, including both the notched fatigue and smooth specimen fatigue curves, should be reduced either by a factor in life or stress (strain where applicable) or both if they are going to be used in design. The specific reduction factor that is required depends on the criticality of the application, the sources of uncertainty in the analysis, and the requirements of the certifying body.

References 1.4.9.3(a) and (b) contain more specific information on fatigue testing procedures, organization of data, the influence of various factors on fatigue, and on design considerations.

**1.4.10 METALLURGICAL INSTABILITY** — In addition to the retention of load-carrying ability and ductility, a structural material must also retain surface and internal stability. Surface stability refers to the resistance of the material to oxidizing or corrosive environments. Lack of internal stability is generally manifested by carbide precipitation, spheroidization, sigma-phase formation, temper embrittlement, and internal or structural transformation, depending upon the material and conditions.

Environmental conditions, which may influence metallurgical stability, include (a) heat, (b) stress, (c) oxidizing or corrosive media, and (d) nuclear radiation. The effect of the environment on the material may be indicated as either improvement or deterioration of properties, depending upon the way the material is evaluated. For example, prolonged heating may progressively raise the strength of a metal as measured on smooth tensile or fatigue specimens, but at the same time lower the ductility to such an extent that notched behavior is erratic or unpredictable. The metallurgy of each alloy should be considered in selecting any material listed herein.

Under normal temperature, i.e., between -65°F and 160°F, the stability of most structural materials is relatively independent of time. However, as the temperature increases the metallurgical stability of a material becomes increasingly time dependent and the factor of time assumes a more prominent role in material behavior and selection.


**1.4.11 BIAXIAL PROPERTIES**

**1.4.11.1 General** — Discussions up to this point have been directed primarily to uniaxial conditions, whether the subject was static, fatigue, or creep loading. In actuality, many structural geometries, or load applications, are such that induced stresses are not uniaxial, but are bi- or triaxial. Because of the difficulty in testing, few triaxial stress data exist. However, considerable biaxial testing has been conducted and the following paragraphs describe how the results are presented in this Handbook. If stresses are referred to the mutually perpendicular x, y, and z directions of the usual rectangular coordinates, a biaxial stress is a condition such that there are either positive or negative stresses in the x and y directions and the stress in the z direction is essentially zero. Most of the discussion hereafter is concerned with x and y direction stresses, which are both tensile (see Reference 1.4.11.1).

When a specimen of a material is tested under biaxial loading conditions, it is customary to plot the results of such a test as a “biaxial stress-strain diagram”. These diagrams are similar to the tensile stress-strain diagrams shown in Figure 1.4.4.1. Usually, only the maximum (algebraically larger) principal stress and strain are shown for each test. When tests of the same material are conducted at various biaxial ratios, the resulting curves may be plotted simultaneously, producing a “family” of biaxial stress-strain curves as shown in Figure 1.4.11.1 for an isotropic material. For an anisotropic material, the curve for a given biaxial ratio would not coincide with the curve for the reciprocal of the biaxial ratio. The reference direction for biaxial ratio (i.e., direction corresponding to  $B = 0$ ) should clearly be indicated on the figure. The reference direction is the longitudinal (rolling) direction for flat products and the hoop (circumferential) direction for shells of revolution (tubes, cones, etc.).

MIL-HDBK-5H

1 December 1998




**Figure 1.4.11.1 Typical biaxial stress-strain diagrams for isotropic materials.**

The biaxial property data presented in the Handbook are to be considered basic material properties obtained from tests on carefully prepared specimens. The stress values reported here may not be attainable in full-scale structures, depending upon weld quality and other fabrication factors (see Reference 1.4.11.1 for further information).

**1.4.11.2 Biaxial Modulus of Elasticity** — Referring to Figure 1.4.11.1, it will be noted that the first part of the diagram is substantially a straight line. In uniaxial tension, the slope of this line is defined as the “modulus of elasticity” (see Section 1.4.4.2). Under biaxial loading conditions this slope, now called the “biaxial modulus of elasticity”, is affected by the biaxial ratio and Poisson’s ratio (see Equation 1.3.7.4).

**1.4.11.3 Biaxial Yield Stress** — Just as the tensile yield stress ( $F_y$ ) is defined arbitrarily as the uniaxial stress 0.002 inch/inch “offset” or permanent strain, as determined from the tensile stress-strain curve, the biaxial yield stress is defined as the maximum principal stress at 0.002 inch/inch offset strain, as determined from the biaxial stress-strain curve.

In design of aircraft and missile structures, biaxial ratios other than those normally used in biaxial testing are frequently encountered. For convenience in interpolating at intermediate biaxial ratios, biaxial yield-stress values are shown as biaxial yield-stress “envelopes”, as illustrated in Figure 1.4.11.3. In preparing these envelopes, data are first reduced to nondimensional form (percent of uniaxial tensile yield stress in the specified reference direction), then a best fit curve is fitted to the reduced data. Biaxial yield-strength values



**Figure 1.4.11.3. Typical biaxial yield-stress envelope.**

**MIL-HDBK-5H****1 December 1998**

for design are then obtained by multiplying the  $F_y$  for the specified material by the coordinates of the curve (in percent) at the appropriate biaxial ratio. To avoid possible confusion, the reference direction used for the uniaxial yield strength is indicated on each figure.

The local value of the biaxial ratio should be used in approving biaxial yield-stress data to design. Thus, although a sheet may have a gross loading with a biaxial ratio of one, at each free (unloaded) edge or hole, the local stress system is uniaxial and the local biaxial ratio is either zero or infinity. A similar precaution applies to material in the vicinity of loaded holes (e.g., rivet holes, bolt holes) and to discontinuities in cross section, such as those occurring as a result of integral stiffeners.

**1.4.11.4 Biaxial Ultimate Stress** — Biaxial ultimate stress is defined as the highest nominal principal stress reached in specimens of a given configuration, tested at a given biaxial ratio. Unlike uniaxial ultimate tensile stress ( $F_u$ ), biaxial ultimate stress is often highly dependent upon the geometrical configuration. Thus, ultimate stress data obtained from tests on cylindrical vessels should be limited to cylindrical-vessel applications, flat-sheet data only to flat-sheet applications, etc.

The method of presenting biaxial ultimate-stress data is similar to that described in Section 1.4.11.3. Where nominal strains at biaxial ultimate-stress values are available, they are reported as a function of biaxial ratio.


**1.4.12 FRACTURE STRENGTH**

**1.4.12.1 General** — The occurrence of flaws in a structural component is an unavoidable circumstance of material processing, fabrication, or service. The flaws may be cracks, metallurgical inclusions or voids, weld defects, design discontinuities, or some combination thereof. If severe enough, these flaws can induce structural failure at loads below those of the nominal design. The fracture strength of a component containing a flaw is dependent on the flaw size, the component geometry, and a material property termed “fracture toughness”.

The fracture toughness of a material is literally a measure of its resistance to fracture. It also is considered a measure of its tolerance or lack of sensitivity to flaws. As with many other material properties, fracture toughness is dependent on processing variables, product form, geometry, temperature loading rate, and other environmental factors. Many measures of fracture toughness have evolved. Those based on crack stress or strain analysis are more meaningful for use in design applications. Other measures are useful for qualitative evaluation of materials; however, they have proven to be difficult to apply to specific design configurations.

While there are several types of fracture, this discussion is limited to brittle fracture, which is characteristic of high-strength materials in structural configurations, which approach plane-strain conditions by nature of their bulk thickness or geometric constraint. Little plasticity accompanies the fracture. The following is based on the current practice of testing specimens of materials under slowly increasing loads. Attendant and interacting conditions of cyclic loading, prolonged static loadings, environmental influences other than temperature, and high-strain rate loading are not considered.

**1.4.12.2 Brittle Fracture** — For materials that have little capacity for plastic flow, or for flaw and structural configurations, which induce triaxial tension stress states adjacent to the flaw, component behavior is essentially elastic until the fracture stress is reached. Then, a crack propagates from the flaw suddenly and completely through the component. A convenient illustration of brittle fracture is a typical load-compliance record of a brittle structural component containing a flaw, as illustrated in Figure 1.4.12.2. Since little or no plastic effects are noted, this mode is termed brittle fracture. This mode of fracture is somewhat characteristic of the very high-strength metallic materials under plane-strain conditions.

**MIL-HDBK-5H****1 December 1998**

**Figure 1.4.12.2. Typical load-deformation record of a structural component containing a flaw subject to brittle fracture.**

**1.4.12.2.1 Brittle Fracture Analysis** — The application of linear elastic fracture mechanics has led to the stress intensity concept to relate flaw size, component geometry, and fracture toughness. In a very general form, the stress intensity factor,  $K$ , can be expressed as

$$K = f\sqrt{a} Y, \text{ ksi} \cdot \text{in.}^{1/2} \quad [1.4.12.2.1]$$

where

- $f$  = stress applied to the gross, flawed section, ksi
- $a$  = measure of flaw size, inches
- $Y$  = factor relating component geometry and flaw size, nondimensional. See Reference 1.4.12.2.1(a) for values.

For every structural material, which exhibits brittle fractures (by nature of low ductility or plane-strain stress conditions), there is a lower limiting value of  $K$  termed the plane-strain fracture toughness,  $K_{Ic}$ .

The specific application of this relationship is dependent on flaw type, structural configuration and type of loading, and a variety of these parameters can interact in a real structure. Flaws may occur through the thickness, may be imbedded as voids or metallurgical inclusions, or may be partial-through (surface) cracks. Loadings of concern may be tension and/or flexure. Structural components may vary in section size and may be reinforced in some manner. The ASTM Committee E-8 on Fatigue and Fracture has developed testing and analytical techniques for many practical situations of flaw occurrence subject to brittle fracture. They are summarized in References 1.4.12.2.1(a), (b), and (c).


**1.4.12.3 Critical Plane-Strain Fracture-Toughness Values** — In the general discussion prefacing each alloy chapter, a tabulation of fracture toughness values is printed. These critical plane-strain fracture-toughness values,  $K_{Ic}$ , have been determined by the recommended ASTM testing practice. Since the data on a given alloy and product form are generally limited, these data are for information only and do not have the statistical reliability normally associated with the room-temperature mechanical properties. In general, these data are available only for the high-strength alloys in relatively thick sections.

**MIL-HDBK-5H****1 December 1998**

The directional significance of the fracture-toughness value relative to the grain direction of the material may be identified by an ordered pair of grain direction symbols. The first digit of the pair denotes the grain direction normal to the crack plane; the second digit of the pair denoted the grain direction parallel to the fracture direction. Thus, the six principal fracture-path directions may be denoted as:

L-T	T-S
L-S	S-L
T-L	S-T

Figure 1.4.12.3 illustrates the six principal fracture-path directions.



**Figure 1.4.12.3. Typical principal fracture-path directions.**

**1.4.12.3.1 Environmental Effects** — As noted in 1.4.12.1, all fracture-toughness data presented in this document represent data obtained under single application of a steadily increasing load in air. Cyclic loading, even well below the fracture-threshold stress, may result in propagation of flaws, leading to fracture. Strain rates in excess of those normally used in testing may cause variations in material behavior. There are distinct effects of temperature on fracture-toughness properties.

A very limited quantity of effect of temperature data is available for fracture-toughness properties. Where these are available, they are incorporated in each alloy section.


It has been noted that under sustained loads some materials exhibit increased flaw-propagation tendencies in aqueous or corrosive environments. When such is known to be the case, appropriate precautionary notes have been included in the alloy chapters.

**1.4.12.4 Fracture in Plane Stress and Transitional Stress States** — In many structural components, plane-strain conditions are never manifested because of the thinness of the product form and the intrinsic ductility of the material. In these cases, the actual stress state may approach the opposite extreme, plane-stress, or, more generally, some intermediate or transitional stress state. Flaws or cracks, which may occur in these stress states, behave differently than those in plane-strain. Under loading, due to lesser crack tip constraint, significant plastic zones may develop adjacent to the crack tip, and stable extension of the crack may occur by a slow tearing process. This more complex behavior is exhibited in the compliance record as a significant nonlinearity prior to fracture such as shown in Figure 1.4.12.4. This nonlinearity results from the lessening stiffness, which accompanies plastic-zone development and from the reduced cross-sectional area resulting from crack extension.



## MIL-HDBK-5H


1 December 1998



**Figure 1.4.12.4. Typical load-deformation record for nonplane strain fracture.**

**1.4.12.4.1 Analysis of Plane Stress and Transitional Stress State Fracture** — Although the physical problem is much more complex, the basic concepts of linear elastic fracture mechanics as used in plane-strain fracture analysis may be applied here also. The stress-intensity factor concept, as expressed in general form by Equation 1.4.12.2.1, is used to relate load or stress, flaw size, component geometry, and fracture toughness. However, the interpretation and assignation of critical stress-intensity factors must be accomplished with much greater care. In Figure 1.4.12.4, it can be seen that there are at least two and possibly more points on the load-deformation curve to which it would be important to assign  $K$  values. These are the point of onset of nonlinearity and the point of fracture, each of which generally will occur at different stress levels, as well as different crack lengths due to stable tear.

This becomes clearer when the compliance record is transformed into the crack-growth curve on the stress-flaw size coordinate system format illustrated in Figure 1.4.12.4.1. In most practical cases, however, the definition and precise experimental discrimination of the point of onset of nonlinearity and the point of fracture are very elusive.



**Figure 1.4.12.4.1. Crack-growth curve for M(T) fracture specimen.**



**MIL-HDBK-5H****1 December 1998**

As a result, an alternate characterization of the fracture behavior can be achieved by calculating an artificial or “apparent” stress intensity factor,

$$K_{app} = f\sqrt{a_0} Y \quad [1.4.12.4.1]$$

using the maximum stress and the initial flaw size. This datum coordinate corresponds to the Point A in Figure 1.4.12.4.1 and its associated stress intensity factor,  $K_{app}$ , is a first approximation to the actual  $K$  values which may be associated with either the onset of nonlinearity or the point of fracture.

**1.4.12.5 Apparent Fracture-Toughness Values for Plane Stress and Transitional Stress States** — In each alloy chapter, basic fracture data are presented on a graphical format of stress versus flaw size for each alloy, temper, product form, grain direction, thickness, and specimen configuration where data are available. The data points shown represent the initial flaw size and maximum stress for that test point. The data presented have been screened to assure that there was a bona fide elastic instability at fracture consistent with the specimen type. The average  $K_{app}$  curve, as defined in the following subsections, is shown for each set of data.

**1.4.12.5.1 Middle Tension or M(T) Specimens** — The formulation of the apparent fracture toughness for middle tension or M(T) specimens is

$$K_{app} = f_c(\pi a_0 \sec \pi a_0/W)^{1/2} \quad [1.4.12.5.1(a)]$$

The data points used to determine the  $K_{app}$  values have been screened to assure that the net section stress at failure did not exceed 80% of the tensile yield strength; that is, they satisfied the criterion

$$f_c \leq 0.8 (TYS)/(1-2a/W) \quad [1.4.12.5.1(b)]$$

This criterion assures that the fracture was an elastic instability and that plastic effects are negligible.

The average  $K_{app}$  parametric curve is presented on each figure as a solid line with multiple extensions where width effects are displayed in the data. As additional information, where data are available, the propensity for slow stable tear prior to fracture is indicated by a crack extension ratio,  $2a/2a_0$ . In some cases, where data exist covering a wide range of thickness, graphs of  $K_{app}$  versus thickness are presented.

### **1.4.13 FATIGUE-CRACK-PROPAGATION BEHAVIOR**


**1.4.13.1 General** — Between the crack-initiating phenomenon of fatigue and the critical instability of cracked structural elements as identified by fracture toughness and residual strength lies an important facet of material behavior known as fatigue-crack propagation. In small-size laboratory fatigue specimens, crack initiation and specimen failure may be nearly synonymous. However, in larger structural components, the existence of a crack does not necessarily imply imminent failure of the component. Significant structural life is accountable in the cyclic crack extension (subcritical crack growth) which can be tolerated prior to reaching conditions critical for fracture.

**1.4.13.2 Fatigue-Crack Growth** — The physical or mechanical phenomenon of fatigue-crack propagation is manifested as the growth or extension of a crack under cyclic loading. While this process is principally controlled by maximum load and stress ratio, there are a number of additional factors, such as environment, frequency, temperature, and grain direction, which may exert a strong influence, depending on the material sensitivities. While it is important to alert the Handbook user to the complexity of this mode of crack behavior, only certain basic principles can be considered here. In particular, it should be noted that in addition to stress ratio effects, the next important consideration is the potentially synergistic interaction of

**MIL-HDBK-5H****1 December 1998**

environment and frequency. When environment is important, it is usually important from the perspective of corrosion processes. Thus, time-at-stress as controlled by frequency also becomes an important factor.

The basic experimental data characterizing fatigue-crack growth that are shown in this Handbook are based on constant amplitude crack-growth experiments. It should be acknowledged that data trends based on constant amplitude cycling may be different than those generated by spectrum cycling. The constant-amplitude data presented consist of crack-length measurements and the associated counts of loading cycles accumulated. Such data may be displayed in a crack growth curve as illustrated in Figure 1.4.13.2(a).



**Figure 1.4.13.2(a). Crack-growth curve.**

However, since the crack-growth curve is dependent on initial crack length and the loading conditions, the presentation of crack-growth curves is not the most concise means of representing crack behavior in a material. As with many dynamic processes, the rate behavior or slope,  $\Delta a / \Delta N$ , of the crack-growth curve provides a more fundamental characterization of the behavior. In general, fatigue-crack-propagation rate behavior is evaluated as a function of the applied stress-intensity factor range, as illustrated in Figure 1.4.13.2(b).

**1.4.13.3 Fatigue-Crack-Propagation Analysis**— It is known that fatigue-crack-propagation behavior under constant-amplitude cyclic conditions is influenced by maximum cyclic stress,  $S_{\max}$ , and some measure of cyclic stress range,  $\Delta S$  (such as stress ratio,  $R$ , or minimum cyclic stress,  $S_{\min}$ ), the instantaneous crack size,  $a$ , and other factors such as environment, frequency, and temperature. Thus, fatigue-crack-propagation rate behavior can be characterized, in general form, by the relation

$$da/dN \approx \Delta a / \Delta N = g(S_{\max}, \Delta S \text{ or } R \text{ or } S_{\min}, a, \dots). \quad [1.4.13.3(a)]$$

## MIL-HDBK-5H

1 December 1998




Figure 1.4.13.2(b). Crack-growth-rate curve.

By applying concepts of linear elastic fracture mechanics, the stress and crack size parameters can be combined into the stress-intensity factor parameter,  $K$ , such that Equation 1.4.13.3(a) may be simplified to

$$da/dN \approx \Delta a/\Delta N = g(K_{\max}, \Delta K, \dots) \quad [1.4.13.3(b)]$$

where

$K_{\max}$  = the maximum cyclic stress-intensity factor

$\Delta K$  =  $(1-R)K_{\max}$ , the range of the cyclic stress-intensity factor, for  $R \geq 0$

$\Delta K$  =  $K_{\max}$ , for  $R \leq 0$ .

At present, in the Handbook, the independent variable is considered to be simply  $\Delta K$  and the data are considered to be parametric on the stress ratio,  $R$ , such that Equation 1.4.13.3(b) becomes

$$da/dN \approx \Delta a/\Delta N = g(\Delta K, R). \quad [1.4.13.3(c)]$$

**1.4.13.4 Fatigue-Crack-Propagation Data Presentation** — Fatigue-crack-propagation rate data for constant-amplitude cycling conditions are presented on a doubly logarithmic graphical format of rate,  $da/dN$ , versus applied stress-intensity-factor range,  $\Delta K$ . The figures, illustrated in Figure 1.4.13.4, are ordered by material, alloy, and heat treatment, in the respective alloy chapters. Parametric variations of rate behavior presented as graphical data with stress ratio,  $R$ , environment, and frequency are displayed where data are available. Background information, test procedures, and interpretative discussion of this type of crack behavior are presented in Chapter 9.

## MIL-HDBK-5H

1 December 1998




Figure 1.4.13.4. Sample display of fatigue crack propagation rate data.

**MIL-HDBK-5H****1 December 1998****1.5 TYPES OF FAILURES**

**1.5.1 GENERAL** — In the following discussion, “failure” will usually denote actual fracture of the member, or the condition of the member when it has just attained its maximum load.

**1.5.2 MATERIAL FAILURES**

**1.5.2.1 General** — Fracture of a metal can be very complex and will not be discussed thoroughly herein. Many references can be consulted for such information. It should be noted, however, that fracture can occur in either a ductile or brittle fashion, in the same material, depending on the state of stress and the environment. Additionally, metals are being used, which have higher strength and have resulted in lower ductility prior to fracture. Fracture can occur after elongation of the metal over a relatively large uniform length, or after a concentrated elongation in a short length. Shear deformation will also vary depending on metal and stress state. Because of these variations in magnitude and mode of deformation, the ductility of a metal can have a profound effect on the ability of a fabricated part to withstand applied loads. Although not a specific design property, some ductility data are provided for each metal to assist in materials selections. Following paragraphs discuss the relation of failure to applied or induced stresses.

**1.5.2.2 Direct Tension or Compression** — This type of failure is associated with ultimate tensile or compressive stress of the material. For compression, it can apply only to members having large cross-sectional dimension as compared to the length in the direction of the load (see Section 1.4.5.2).

**1.5.2.3 Shear** — Pure shear failures are usually obtained only when shear load is transmitted over a very short length of the member. This condition is approached in the case of rivets and bolts. In cases where ultimate shear stress is relatively low, a pure shear failure may result, but in general a member subjected to a shear load fails under the action of the resulting normal stress (Equation 1.3.3.3), usually the compressive stress. The failure of a tube in torsion, for instance, is not usually caused by exceeding the allowable shear stress, but by exceeding a certain allowable normal compressive stress, which causes the tube to buckle. It is customary, for convenience, to determine the allowable stresses for members subjected to shear in the form of shear stresses. Such allowable shear stresses are therefore an indirect measure of the stresses actually causing failure.

**1.5.2.4 Bearing** — The failure of a material in bearing may consist of crushing, splitting, or progressive rapid yielding in the region where the load is applied. Failure of this type will depend, to a large extent, on the relative size and shape of the two connecting parts. The allowable bearing stress will not always be applicable to cases in which one of the contacting members is relatively thin. It is also necessary, for practical reasons, to limit the working bearing stress to low values in such cases as joints subjected to reversals of load or in bearings between removable surfaces. These special cases are covered by specific rulings of the procuring or certifying agency, involving the use of higher factors of safety in most cases.

**1.5.2.5 Bending** — For compact sections not subject to instability, a bending failure can be classed as a tensile or compressive failure caused by exceeding a certain allowable stress in some portion of the specimen. It is customary to determine, experimentally, the “modulus of rupture in bending”, which is a stress derived from test results through the use of Equation 1.3.2.3, in which Case M is the value of bending moment which caused failure. For compact sections not subject to instability, the treatment of bending in the plastic range by linear analog methods, for example, Cozzone (Reference 1.5.2.5), provides a method by which actual bending stresses above the material proportional limit can be related to the “bending modulus of rupture”. From simple bending theory, the bending modulus of rupture is determined by Equation 1.3.2.3. When the modulus of rupture is less than or equal to the proportional limit, it represents an actual stress. When the modulus of rupture is greater than the proportional limit, it represents an apparent stress, which cannot be

**MIL-HDBK-5H****1 December 1998**

considered as the actual stress at the point of rupture. This should be borne in mind in dealing with combined stresses such as bending and compression or bending and torsion.

**1.5.2.6 Failure Due to Stress Concentration** — The static strength properties listed for various materials were determined on machined specimens containing no notches, holes, or other avoidable stress raisers. In the design of aircraft structures, such simplicity is unattainable, and stress distributions are not of the uniform type obtained in the specimen tests. Consideration must be given to the effect of stress raisers since maximum stress in a material, and not average stress, is the critical factor in design. The effects of stress raisers vary, and references to available specific data are given in the sections pertaining to each material.

**1.5.2.6.1 Failure, Due to Unintentional Flaws** — As stated in Section 1.4.12.1, unintentional flaws may be metallurgical defects, such as inclusions, voids, seams, weld defects; they also may be surface defects from service, such as corrosion pits, stress-corrosion cracks, and fatigue cracks. Some high-strength materials are extremely sensitive to such small cracks or flaws, and their use has resulted in structural failure. In this context, the word “sensitive” means that for certain of the high-strength materials that inadvertently contain flaws, failure of the material or a part fabricated from it may occur at gross stress levels substantially below the yield strength. Universal agreement on a design accounting for this type of failure is still evolving. Plain-strain fracture toughness data are included in certain material chapters. Since for these high-strength materials premature fracture may occur, the possibility should be considered in design.

**1.5.2.7 Failure Resulting From Fatigue** — Aircraft structures are subjected to repeated loads. It is well known that the strength of a material under such repeated loads is less than it would be under static loading. This phenomenon of the decreased strength of a material under repeated loading is commonly called fatigue. Stress raisers, such as abrupt changes in cross section, holes, notches, and reentrant corners, have a much greater effect on the fatigue strength than on static strength. The local high stress concentrations caused by such stress raisers are often greatly in excess of the nominal calculated stress on the part, and consequently it is at such locations that fatigue fractures usually begin. Other factors of major importance in fatigue are the range of the repeated stress cycle (from maximum to minimum stress), and the mean stress in the stress cycle. In the following chapters fatigue data are presented for various materials from axial load fatigue tests. The data are average or typical data and are not to be used as allowable stress values unless their applicability to the case at hand has been established.

**1.5.2.8 Failure From Combined Stresses** — In combined-stress conditions where failure is not due to buckling or instability, it is necessary to refer to some theory of failure. The “maximum shear” theory has received wide acceptance as a simple working basis in the case of isotropic ductile materials. It should be noted that this theory interprets failure as the first yielding of the materials, so that any extension of the theory to cover conditions of final rupture must be based on the experience of the designer. The failure of brittle materials under combined stresses can generally be treated by the “maximum stress” theory. Section 1.4.11 has a more complete discussion of biaxial behavior. References 1.5.2.8(a) through (c) may also be helpful.

**1.5.3 INSTABILITY FAILURES**

**1.5.3.1 General** — Practically all structural members such as beams and columns, particularly those made from thin material, are subject to failure through instability. In general, instability can be classed as: (1) primary or (2) local. For example, the failure of a tube under compression may occur either through lateral deflection of the tube as a column (primary instability) or by collapse of the tube wall at a stress lower than that required to produce a general column failure. Similarly, an I-beam or other shape may fail by a general sidewise deflection of the compression flange, by local wrinkling of thin outstanding flanges, or by torsional instability. It is obviously necessary to consider all types of failure, unless it is apparent that the critical load for one type is definitely less than that for the other type.

**MIL-HDBK-5H****1 December 1998**

Instability failures may occur in either the elastic range (below the proportional limit) or in the plastic range (above the proportional limit). To distinguish between these two types of action, it is not uncommon to refer to them as “elastic instability failures” and “plastic instability failures”, respectively. It is important to note that instability failures are not usually associated with the ultimate stresses of the material. This should be borne in mind when correcting test results for material variations. This point also has a bearing on the choice of a material for a given type of construction, as the “strength-weight ratio” will be determined from different physical characteristics when this type of failure can be expected.

A method of determining the local stability of aluminum alloy column sections is outlined in Reference 1.7.1(b).

**1.5.3.2 Instability Failures Under Compressive Loading** — Failures of this type are discussed in Section 1.6 (Columns).

**1.5.3.3 Bending Instability Failures** — Failures of round tubes of usual size when subjected to bending are usually of the plastic-instability type. In such cases, the criterion of strength is the modulus of rupture (Equation 1.3.2.3) which was derived from theory and checked by test. Elastic instability failures of thin-walled tubes having high D/t ratios are treated in later sections.

**1.5.3.4 Torsional Instability Failures** — The remarks of the preceding section apply in a similar manner to round tubes under torsional loading. In such cases, the modulus of rupture in torsion is derived through the use of Equation 1.3.2.6. See Reference 1.5.3.4.

**1.5.3.5 Failure Under Combined Loadings** — For combined-loading conditions in which failure is caused by buckling or instability, no general theory exists, which will apply in all cases. Due to the various design philosophies and analytical techniques used throughout the aerospace industry, methods for computing margin of safety are not within the scope of MIL-HDBK-5.

## **1.6 COLUMNS**

**1.6.1 GENERAL** — A theoretical treatment of columns can be found in standard textbooks on the strength of materials. The problems confronting the designer, however, include many points, which are not well defined by theory and which frequently cause some confusion. These are discussed in this section. Actual strengths of columns of various types are given in subsequent chapters.

### **1.6.2 PRIMARY INSTABILITY FAILURES**

**1.6.2.1 General** — A column may fail through primary instability by bending laterally (stable sections) or by twisting about some axis parallel to its own axis. This latter type of primary failure is particularly common to columns having unsymmetrical open sections. The twisting failure of a closed-section column is precluded by its inherently high torsional rigidity. Since the information available on twisting instability is somewhat limited, it may be advisable to conduct tests on all columns subject to this type of failure.

**1.6.2.2 Columns with Stable Sections** — The tangent modulus formula for columns which fail by lateral bending is given by Equation 1.3.8. No explanation of this formula need be offered, as its derivation can be found in many standard textbooks on the strength of materials. The value to be used for the restraint coefficient,  $c$ , depends upon the degree of end fixity.

The true significance of the restraint coefficient is best understood by considering the end restraint as modifying the effective column length, as indicated by Equation 1.3.8. For a pin-ended column having




**MIL-HDBK-5H****1 December 1998**

zero end restraint,  $c = 1.0$  and  $L' = L$ . A fixity coefficient of 2 corresponds to a reduction of the effective length to  $1/\sqrt{2}$  or 0.707 times the total length.

The tangent modulus Equation 1.3.8 takes into account the plasticity of the material and is valid if the following conditions are met:

- (a) The column adjusts itself to forcible shortening only by bending and not by twisting.
- (b) No buckling of any portion of the cross section has occurred.
- (c) Load is concentric with the longitudinal axis of the unloaded column.
- (d) The cross section of the column does not vary along the column length.

The value of the compressive tangent modulus,  $E_t$ , at any given compressive stress,  $F_c$ , can be determined from stress-strain curves for the material. Figure 1.6.2.2 illustrates the use of this equation. For example, assume an  $L'/\rho$  of 22.2, and computing  $\pi^2/(L'/\rho)^2$  gives a value of 0.02, which also equals  $F_c/E_t$ . Plot the line  $F_c/E_t = 0.02$  on the tangent modulus curve. The point of intersection gives a value of 60 ksi for  $F_c$  and  $3 \times 10^6$  psi for  $E_t$ .



**Figure 1.6.2.2. Relation of  $\pi^2/(L'/\rho)^2$  to tangent modulus.**

**1.6.2.3 Column Yield Stress ( $F_{co}$ )** — The upper limit of the allowable column stress for primary failure, designated  $F_{co}$ , may be obtained when not available elsewhere, from the compressive tangent modulus Equation 1.3.8 for columns including those having geometrical proportions for low values of  $L'/\rho$ , with the restriction that  $F_{co}$  shall not exceed  $F_{cu}$ , the material ultimate compressive stress. As discussed in 1.4.5.2, it is common practice to assume for wrought metals that the material ultimate compressive stress,  $F_{cu}$ , is equal to the ultimate tensile stress.

**1.6.2.4 Other Considerations** — Methods of analysis are available by which column failing stresses can be computed taking into account various fixities, torsional instability, load eccentricity, combined lateral loads, or varying column sections. References 1.6.2.4(a), (b), (c), and (d) present such methods.

### **1.6.3 LOCAL INSTABILITY FAILURE**

**1.6.3.1 General** — Columns may fail by a local collapse of the wall at a stress below the primary failure stress. The buckling analysis of a column subject to local instability requires taking into account the shape of the column cross section and may be quite complex. Local buckling, which may combine with primary buckling, leads to an instability failure commonly termed crippling.



## MIL-HDBK-5H

1 December 1998

**1.6.3.2 Crushing or Crippling Stress ( $F_{cc}$ )** — The upper limit of the allowable column stress for local failure is called the crushing or crippling stress and is designated  $F_{cc}$ . The crushing or crippling stresses of round tubes have been investigated frequently and considerable useful data exist. Fewer data are available for stresses of columns having other section configurations, and testing may be required to establish the curve of transition from local to primary failure.

#### 1.6.4 CORRECTION OF COLUMN TEST RESULTS

**1.6.4.1 General** — In the case of columns having unconventional cross sections, which are particularly subject to local instability, it is necessary to establish the curve of transition from local to primary failure. In determining the strength curves for such columns, sufficient tests should be made to cover the following points.

**1.6.4.2 Nature of "Short-Column Curve"** — The test specimens should cover a range of  $L'/\rho$ , which will extend to the Euler range, or at least well beyond the values to be used in construction. When columns are to be attached eccentrically in the structure, some tests should be made to determine the effects of eccentricity. This is important particularly in the case of open sections, as the allowable loads may be affected considerably by the location of the point of application of the column load.

**1.6.4.3 Local Failure** — When local failure occurs, the crushing or crippling stress,  $F_{cc}$ , can be determined by extending the "short-column" curve for the specific cross section under consideration to a point corresponding to zero  $L'/\rho$ . When a family of columns of the same general cross section is used, it is often possible to determine a relationship between  $F_{cc}$  and some factor depending on the wall thickness, width, diameter, or some combination of these dimensions. Extrapolations of such data should be avoided by covering an adequate range in the tests.

**1.6.4.4 Reduction of Column Test Results on Aluminum and Magnesium Alloys to Standard Material** — The use of the correction factors given in Figures 1.6.4.4(a) through (i) is considered satisfactory and is acceptable in the Air Force, Navy, Army, and the Federal Aviation Administration for use in connection with tests on aluminum and magnesium alloys. (Note that an alternate method is given in Section 1.6.4.5). In using Figures 1.6.4.4(a) through (i), the correction of column test results to standard material is made by multiplying the stress obtained from testing a column specimen by the factor  $K$ . This factor may be considered applicable regardless of the type of failure involved (i.e., column crushing or crippling or twisting). In Figures 1.6.4.4(a) through (i),  $f_c'$  is the maximum test column stress of the test column material, and  $F_{cy}$  is the compressive yield stress as given in the design allowable property tables for the individual alloys.

Acceptable methods for obtaining compressive yield strength,  $F_{cy}'$ , of column material for use in determining values of  $K$  from Figures 1.6.4.4(a) through (i) are as follows:

- (a) Using a compression test specimen, obtain the compressive yield strength of the material from which the test column is made in the direction of loading of the test column.
- (b) If Method (a) is not feasible, the compressive yield strength of column material may be obtained from the tensile yield strength as follows: Determine the tensile yield strength of the column material by conducting a standard tensile test in a direction parallel to the test-column length. Compute the compressive yield strength of the test column material by multiplying the tensile yield strength by the proper ratio of the design allowable compressive yield strength to the design allowable tensile yield strength. The ratio used should be compatible with the grain direction of the test column material. If the compression test column is manufactured indiscriminately with respect to material grain direction, the tensile test specimen should be oriented parallel to column length and the  $F_{cy}(L)/F_{ty}(L)$  ratio for the material should be used.

**MIL-HDBK-5H****1 December 1998**

- (c) If neither Method (a) nor (b) is feasible, it can be assumed that compressive yield strength of column test specimen parallel to length is 15 percent greater than minimum established design allowable longitudinal tensile yield strength for material in the column test specimen.

**1.6.4.5 Reduction of Column Test Results to Standard Material-Alternate Method** — For materials that are not covered by Figures 1.6.4.4(a) through (i), the following method should be used to reduce column test results to standard material. This method is acceptable to the Air Force, Navy, Army, and the Federal Aviation Administration.

- (1) Determine the standard material compression allowables:  $F_{cy}$ ,  $E_c$ , and  $n_c$ .
- (2) Determine the test material critical column stress,  $f_c'$ , and compression yield strength,  $f_{cy}'$ .
- (3) Assume  $E_c$  and  $n_c$  of (1) apply to (2).
- (4) Assume that the standard material and the column test material have the same critical slenderness ratio of  $(L'/\rho)$ .

From (4), using the basic column formula from 1.3.8:

$$F_c/E_t(\text{std. mat 'l.}) = f_c'/E_t'(\text{test mat 'l.}) \quad (1)$$

where

$$E_t = F_c/[F_c/E_c + n_c(0.002)(F_c/F_{cy})^{n_c}] \quad (2)$$

and

$$E_t' = f_c'/[f_c'/E_c + n_c(0.002)(f_c'/f_{cy}')^{n_c}] \quad (3)$$


By substitution of Equations (2) and (3) into (1), simplification gives:

$$F_c/E_c + n_c(0.002)(F_c/F_{cy})^{n_c} = f_c'/E_c + n_c(0.002)(f_c'/f_{cy}')^{n_c} \quad (4)$$


The only unknown in (4) is  $F_c$ , which is the test material critical column compression allowable. It is determined by iteration.

This method is applicable at elevated temperatures, provided Young's modulus of the standard and test materials are equal. If modulus and shape factor of the test material are not the same as those of the standard material, the assumption stated in (3) is not valid. Equation (4) must account for these differences.


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 1.6.4.4(a). Nondimensional material correction chart for 2024-T3 sheet.**




**Figure 1.6.4.4(b). Nondimensional material correction chart for 2024-T3 clad sheet.**

**MIL-HDBK-5H****1 December 1998**


**Figure 1.6.4.4(c). Nondimensional material correction chart for 2024-T4 extrusion less than 1/4 inch thick.**




**Figure 1.6.4.4(d). Nondimensional material correction chart for 2024-T4 extrusion 1/4 to 1-1/2 inches thick.**

**MIL-HDBK-5H****1 December 1998**


**Figure 1.6.4.4(e). Nondimensional material correction chart for 2024-T3 tubing.**




**Figure 1.6.4.4(f). Nondimensional material correction chart for clad 2014-T3 sheet.**

**MIL-HDBK-5H****1 December 1998**

**Figure 1.6.4.4(g). Nondimensional material correction chart for 7075-T6 sheet.**



**Figure 1.6.4.4(h). Nondimensional material correction chart for AZ31B-F and AZ61A-F extrusion.**

**MIL-HDBK-5H****1 December 1998**

**Figure 1.6.4.4(i). Nondimensional material correction chart for AZ31B-H24 sheet.**

## 1.7 THIN-WALLED AND STIFFENED THIN-WALLED SECTIONS

**1.7.1 GENERAL** — A bibliography of information on thin-walled and stiffened thin-walled sections is contained in References 1.7.1(a) and (b).

### REFERENCES

- 1.3.8.1 ASTM E9-89a, "Standard Test Methods for Compression Testing at Metallic Materials at Room Temperature."
- 1.4.3.2 Goodman, S., and Russell, S. 13., U.S. Air Force, "Poisson", Ratio of Aircraft Sheet Materials for Large Strain", WADCTR 53-7, 58 pp (June 1953).
- 1.4.5.1 Hyler, W. S., "An Evaluation of Compression-Testing Techniques for Determining Elevated-Temperature Properties of Titanium Sheet", Titanium Metallurgical Laboratory Report No. 43, Battelle Memorial Institute, 38 pp, Appendix 28 pp (June 8, 1956).
- 1.4.6.1 Stange, A. H., Ramberg, W., and Back, G., "Torsion Tests of Tubes", National Advisory Committee for Aeronautics, Report No. 601, pp 515-535 (February 1937).
- 1.4.7.1 Stickley, G. W., and Moore, A. A., "Effects of Lubrication and Pin Surface on Bearing Strengths of Aluminum and Magnesium Alloys", *Materials Research and Standards*, **2**, (9), pp 747-751 (September 1962).

**MIL-HDBK-5H****1 December 1998**

- 1.4.8.2.1(a) Rice, Richard, "Reference Document for the Analysis of Creep and Stress Rupture Data in MIL-HDBK-5", AFWAL-TR-91-4097 (September 1991).
- 1.4.8.2.1(b) Aarnes, M. N., and Tuttle, M. M., "Presentation of Creep Data for Design Purposes", ASD Technical Report 61-216 (June 1961) (MCIC 45114).
- 1.4.9.3(a) Grover, H. J., "Fatigue of Aircraft Structures", Prepared for Naval Air Systems Command, Department of the Navy, 335 pp (1966).
- 1.4.9.3(b) Osgood, C. C., "Fatigue Design", Wiley-Interscience, a Division of John Wiley and Sons, Inc., 523 pp (1970).
- 1.4.11.1 Bert, C. W., Mills, E. J., and Hyler, W. S., "Mechanical Properties of Aerospace Structural Alloys Under Biaxial-Stress Conditions", AFML-TR-66-229 (August 1966).
- 1.4.12.2.1(a) Brown, W. F., Jr., and Srawley, J. E., "Plane-Strain Crack Toughness Testing of High Strength Metallic Materials", ASTM Special Technical Publication No. 410, American Society for Testing and Materials, Philadelphia (1967).
- 1.4.12.2.1(b) "Fracture Toughness Testing and Its Applications", ASTM Special Technical Publication No. 381, American Society for Testing and Materials, Philadelphia (1965).
- 1.4.12.2.1(c) "Standard Method of Test for Plane-Strain Fracture Toughness of Metallic Materials", ASTM E399.
- 1.5.2.5 Cozzzone, F. P., "Bending Strength in the Plastic Range", *Journal of the Aeronautical Sciences*, **10**, pp 137-151 (1943).
- 1.5.2.8(a) Dieter, G. E., Jr., "Mechanical Metallurgy", McGraw-Hill Book Company, Inc., 615 pp (1961).
- 1.5.2.8(b) Freudenthal, A. M., "The Inelastic Behavior of Engineering Materials and Structures", John Wiley and Sons, Inc., New York, 587 pp (1950).
- 1.5.2.8(c) Parker, E. R., "Brittle Behavior of Engineering Structures", John Wiley and Sons, Inc., New York, 323 pp (1957).
- 1.5.3.4 Lundquist, E. E., "Strength Tests of Thin-Walled Duralumin Cylinders in Pure Bending", U.S. National Advisory Committee for Aeronautics, Technical Note No. 479, 17 pp (December 1933).
- 1.6.2.4(a) Hill, H. N., and Clark, J. W., "Straight-Line Column Formulas for Aluminum Alloys", Aluminum Company of America, Aluminum Research Laboratories, Technical Paper No. 12, 8 pp (1955).
- 1.6.2.4(b) AFFDL-TR-69-42, "Stress Analysis Manual", Air Force Flight Dynamics Laboratory, Air Force Systems Command, Wright-Patterson Air Force Base (February 1970).
- 1.6.2.4(c) "Astronautic Structure Manual", George C. Marshall Space Flight Center (August 15, 1970).
- 1.6.2.4(d) Niles, A. S., and Newell, J. S., "Airplane Structure", 2, Third Edition, John Wiley and Sons (1943).



**MIL-HDBK-5H**

**1 December 1998**

- 1.7.1(a) “Index of Aircraft Structures Research Reports”, U.S. National Advisory Committee for Aeronautics, Index No. 7E29, 40 pp (June 1947).
- 1.7.1(b) Gerard, and Becker, H., “Handbook of Structural Stability”, National Advisory Committee for Aeronautics Technical Note, Nos. 3781, 102 pp (July 1957); 3782, 72 pp (July 1957); 3783, 154 pp (August 1957); 3784, 93 pp (August 1957), and 3785, 89 pp (August 1957).

**MIL-HDBK-5H**  
**1 December 1998**

This page intentionally blank.

**MIL-HDBK-5H****1 December 1998****SPECIFICATIONS AND STANDARDS REQUISITION**

*Form Approved  
OMB No. 0704-0230  
Expires Dec 31, 1991*

Public reporting burden for this collection of information is estimated to average 30 minutes per response, including the time of reviewing instructions, searching existing data sources, gathering and maintaining the data needed. And completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0230), Washington, DC 20503. Please DO NOT RETURN your form to either of these addresses. Send your completed form to address in item 9 of instructions.

**1. CUSTOMER NUMBER (Mandatory for Repeat Orders to expedite requests), CAGE CODE, OR UIC NUMBER**

--	--	--	--	--	--	--	--	--	--

**2. YOUR ADDRESS (Print or Type)**

•

•

☐

IF YOUR ADDRESS HAS CHANGED, X THIS BLOCK

•

•

**3. ATTENTION:****4. DOCUMENTS REQUESTED**

a. STANDARDIZATION DOCUMENT NUMBER	b. QUANTITY (Restricted to 5)	c. TITLE (From DoD Index of Specifications and Standards)

**INSTRUCTIONS****1. PRINT OR TYPE ALL INFORMATION.**

2. Enter your customer number, CAGE (formerly FSCM), or UIC number at the top of this form. It will expedite your order.

3. If you have a customer number, use the Telephone Order Entry System (TOES) for telephone orders: (215) 697-1187 between the hours of 8 a.m. and 8 p.m. Eastern Standard Time, Monday through Friday. See "Guide to Private Industry" for details.

4. Documents ordered must appear in the DoD Index of Specifications and Standards (DODISS) or DODISS Notice. Requests submitted on this form will speed service. Reorder forms will be enclosed with each shipment.

5. Requests for Official Use Documents or documents without Distribution Statement "A" must be submitted via cognizant DoD Inspection Officer or Contract Administrator for certification of "need to know."

6. Non Government Standardization Documents will not be furnished to commercial concerns. Copies may be purchased from the appropriate Non Government Standards Body.

7. Questions concerning documents not listed in the Department of Defense Index of Specifications and Standards (DODISS) or DODISS Notice should be directed to: NPFC Attn: Code 105. Telephone: (215) 697-2667 or (215) 697-2179.

8. Further information may be obtained from NPFC "Guide to Private Industry." Order as GUIDE-1.

**9. FORWARD REQUEST TO:**

Standardization Document Order Desk  
700 Robbins Avenue  
Building #4, Section D  
Philadelphia, PA 19111-5094

**5. SIGNATURE OF REQUESTER****6. DATE SIGNED (YYMMDD)****7. CLOSING DATE (YYMMDD)  
(IFB, RFQ, or RFP)**

**MIL-HDBK-5H****1 December 1998**

<b>STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL</b>		
<b>INSTRUCTIONS</b>		
<p>1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.</p> <p>2. The submitter of this form must complete blocks 4, 5, 6, and 7, and send to preparing activity.</p> <p>3. The preparing activity must provide a reply within 30 days from receipt of the form.</p> <p>NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.</p>		
<b>I RECOMMEND A CHANGE:</b>	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYYYMMDD)
3. DOCUMENT TITLE		
4. NATURE OF CHANGE <i>(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)</i>		
5. REASON FOR RECOMMENDATION		
6. SUBMITTER		
a. NAME <i>(Last, First, Middle Initial)</i>	b. ORGANIZATION	
c. ADDRESS <i>(Include ZIP Code)</i>	d. TELEPHONE <i>(Include Area Code)</i> (1) Commercial (2) DSN <i>(If applicable)</i>	7. DATE SUBMITTED (YYYYMMDD)
8. PREPARING ACTIVITY		
a. NAME	b. TELEPHONE <i>(Include Area Code)</i> (1) Commercial (2) DSN	
c. ADDRESS <i>(Include ZIP Code)</i>	<b>IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:</b> Defense Standardization Program Office (DLSC-LM) 8725 John J. Kingman Road, Suite 2533 Fort Belvoir, Virginia 22060-6221 Telephone (703) 767-6888 DSN 427-6888	

**DD FORM 1426, FEB 1999 (EG)**

PREVIOUS EDITION IS OBSOLETE.

WHS/DIOR, Feb 99

**CHAPTER 2****STEEL**

This chapter contains the engineering properties and related characteristics of steels used in aircraft and missile structural applications. General comments on engineering properties and other considerations related to alloy selection are presented in Section 2.1. Mechanical and physical property data and characteristics pertinent to specific steel groups or individual steels are reported in Sections 2.2 through 2.7. Element properties are presented in Section 2.8.

**2.1 GENERAL**

The selection of the proper grade of steel for a specific application is based on material properties and on manufacturing, environmental, and economic considerations. Some of these considerations are outlined in the sections that follow.

**2.1.1 ALLOY INDEX** — The steel alloys listed in this chapter are arranged in major sections that identify broad classifications of steel partly associated with major alloying elements, partly associated with processing, and consistent generally with steel-making technology. Specific alloys are identified as shown in Table 2.1.1.

**Table 2.1.1. Steel Alloy Index**

Section	Alloy Designation
<b>2.2</b>	<b>Carbon steels</b>
2.2.1	AISI 1025
<b>2.3</b>	<b>Low-alloy steels (AISI and proprietary grades)</b>
2.3.1	Specific alloys
<b>2.4</b>	<b>Intermediate alloy steels</b>
2.4.1	5Cr-Mo-V
2.4.2	9Ni-4Co-0.20C
2.4.3	9Ni-4Co-0.30C
<b>2.5</b>	<b>High alloy steels</b>
2.5.1	18 Ni maraging steels
2.5.2	AF1410
2.5.3	AerMet 100
<b>2.6</b>	<b>Precipitation and transformation hardening steel (stainless)</b>
2.6.1	AM-350
2.6.2	AM-355
2.6.3	Custom 450
2.6.4	Custom 455
2.6.5	PH13-8Mo
2.6.6	15-5PH
2.6.7	PH15-7Mo
2.6.8	17-4PH
2.6.9	17-7PH
<b>2.7</b>	<b>Austenitic stainless steels</b>
2.7.1	AISI Type 301

**MIL-HDBK-5H****1 December 1998**

**2.1.2 MATERIAL PROPERTIES** — One of the major factors contributing to the general utility of steels is the wide range of mechanical properties which can be obtained by heat treatment. For example, softness and good ductility may be required during fabrication of a part and very high strength during its service life. Both sets of properties are obtainable in the same material.

All steels can be softened to a greater or lesser degree by annealing, depending on the chemical composition of the specific steel. Annealing is achieved by heating the steel to an appropriate temperature, holding, then cooling it at the proper rate.

Likewise, steels can be hardened or strengthened by means of cold working, heat treating, or a combination of these.

Cold working is the method used to strengthen both the low-carbon unalloyed steels and the highly alloyed austenitic stainless steels. Only moderately high strength levels can be attained in the former, but the latter can be cold rolled to quite high strength levels, or “tempers”. These are commonly supplied to specified minimum strength levels.

Heat treating is the principal method for strengthening the remainder of the steels (the low-carbon steels and the austenitic steels cannot be strengthened by heat treatment). The heat treatment of steel may be of three types: martensitic hardening, age hardening, and austempering. Carbon and alloy steels are martensitic-hardened by heating to a high temperature, or “austenitizing”, and cooling at a recommended rate, often by quenching in oil or water. This is followed by “tempering”, which consists of reheating to an intermediate temperature to relieve internal stresses and to improve toughness.

The maximum hardness of carbon and alloy steels, quenched rapidly to avoid the nose of the isothermal transformation curve, is a function in general of the alloy content, particularly the carbon content. Both the maximum thickness for complete hardening or the depth to which an alloy will harden under specific cooling conditions, and the distribution of hardness can be used as a measure of a material’s hardenability.

A relatively new class of steels is strengthened by age hardening. This heat treatment is designed to dissolve certain constituents in the steel, then precipitate them in some preferred particle size and distribution. Since both the martensitic hardening and the age-hardening treatments are relatively complex, specific details are presented for individual steels elsewhere in this chapter.

Recently, special combinations of working and heat treating have been employed to further enhance the mechanical properties of certain steels. At the present time, the use of these specialized treatments is not widespread.

Another method of heat treatment for steels is austempering. In this process, ferrous steels are austenitized, quenched rapidly to avoid transformation of the austenite to a temperature below the pearlite and above the martensite formation ranges, allowed to transform isothermally at that temperature to a completely bainitic structure, and finally cooled to room temperature. The purpose of austempering is to obtain increased ductility or notch toughness at high hardness levels, or to decrease the likelihood of cracking and distortion that might occur in conventional quenching and tempering.

**2.1.2.1 Mechanical Properties** —

**2.1.2.1.1 Strength (Tension, Compression, Shear, Bearing)** — The strength properties presented are those used in structural design. The room-temperature properties are shown in tables following the comments for individual steels. The variations in strength properties with temperature are presented

**MIL-HDBK-5H**  
**1 December 1998**

graphically as percentages of the corresponding room-temperature strength property, also described in Section 9.3.1 and associated subsections. These strength properties may be reduced appreciably by prolonged exposure at elevated temperatures.

The strength of steels is temperature-dependent, decreasing with increasing temperature. In addition, steels are strain rate-sensitive above about 600 to 800°F, particularly at temperatures at which creep occurs. At lower strain rates, both yield and ultimate strengths decrease.

The modulus of elasticity is also temperature-dependent and, when measured by the slope of the stress-strain curve, it appears to be strain rate-sensitive at elevated temperatures because of creep during loading. However, on loading or unloading at high rates of strain, the modulus approaches the value measured by dynamic techniques.

Steel bars, billets, forgings, and thick plates, especially when heat treated to high strength levels, exhibit variations in mechanical properties with location and direction. In particular, elongation, reduction of area, toughness, and notched strength are likely to be lower in either of the transverse directions than in the longitudinal direction. This lower ductility and/or toughness results both from the fibering caused by the metal flow and from nonmetallic inclusions which tend to be aligned with the direction of primary flow. Such anisotropy is independent of the depth-of-hardening considerations discussed elsewhere. It can be minimized by careful control of melting practices (including degassing and vacuum-arc remelting) and of hot-working practices. In applications where transverse properties are critical, requirements should be discussed with the steel supplier and properties in critical locations should be substantiated by appropriate testing.

**2.1.2.1.2 Elongation** — The elongation values presented in this chapter apply in both the longitudinal and long transverse directions, unless otherwise noted. Elongation in the short transverse (thickness) direction may be lower than the values shown.

**2.1.2.1.3 Fracture Toughness** — Steels (as well as certain other metals), when processed to obtain high strength, or when tempered or aged within certain critical temperature ranges, may become more sensitive to the presence of small flaws. Thus, as discussed in Section 1.4.12, the usefulness of high-strength steels for certain applications is largely dependent on their toughness. It is generally noted that the fracture toughness of a given alloy product decreases relative to increase in the yield strength. The designer is cautioned that the propensity for brittle fracture must be considered in the application of high-strength alloys for the purpose of increased structural efficiency.

Minimum, average, and maximum values, as well as coefficient of variation of plane-strain fracture toughness for several steel alloys, are presented in Table 2.1.2.1.3. These values are presented as indicative information and do not have the statistical reliability of room-temperature mechanical properties. Data showing the effect of temperature are presented in the respective alloy sections where the information is available.

**2.1.2.1.4 Stress-Strain Relationships** — The stress-strain relationships presented in this chapter are prepared as described in Section 9.3.2.

**2.1.2.1.5 Fatigue** — Axial-load fatigue data on unnotched and notched specimens of various steels at room temperature and at other temperatures are shown as S/N curves in the appropriate section. Surface finish, surface finishing procedures, metallurgical effects from heat treatment, environment and other factors influence fatigue behavior. Specific details on these conditions are presented as correlative information for the S/N curve.

**Table 2.1.2.1.3. Values of Room Temperature Plane-Strain Fracture Toughness of Steel Alloys<sup>a</sup>**

Alloy	Heat Treat Condition	Product Form	Orientation <sup>b</sup>	Yield Strength Range, ksi	Product Thickness Range, inches	Number of Sources	Sample Size	Specimen Thickness Range, inches	K <sub>IC</sub> , ksi √in.			
									Max.	Avg.	Min.	Coefficient of Variation
D6AC	1650 °F, Aus-Bay Quench 975 °F, SQ 375 °F, 1000 °F 2 + 2	Plate	L-T	217	1.5	1	19	0.6	88	62	40	22.5
D6AC	1650 °F, Aus-Bay Quench 975 °F, SQ 400 °F, 1000 °F 2 + 2	Plate	L-T	217	0.8	1	103	0.6-0.8	92	64	44	18.9
D6AC	1650 °F, Aus-Bay Quench 975 °F, SQ 400 °F, 1000 °F 2 + 2	Forging	L-T	214	0.8-1.5	1	53	0.6-0.8	96	66	39	18.6
D6AC	1700 °F, Aus-Bay Quench 975 °F, OQ 140 °F, 1000 °F 2 + 2	Plate	L-T	217	0.8-1.5	1	30	0.6-0.8	101	92	64	8.9
D6AC	1700 °F, Aus-Bay Quench 975 °F, OQ 140 °F, 1000 °F 2 + 2	Forging	L-T	214	0.8-1.5	1	34	0.7	109	95	81	6.7
9Ni-4Co-.20C	Quench and Temper	Hand Forging	L-T	185-192	3.0	2	27	1.0-2.0	147	129	107	8.3
9Ni-4Co-.20C	1650 °F, 1-2 Hr, AC, 1525 °F, 1-2 Hr, OQ, -100 °F, Temp	Forging	L-T	186-192	3.0-4.0	3	17	1.5-2.0	147	134	120	8.5
PH13-8Mo	H1000	Forging	L-T	205-212	4.0-8.0	3	12	0.7-2.0	104	90	49	21.5

<sup>a</sup> These values are for information only.

<sup>b</sup> Refer to Figure 1.4.12.3 for definition of symbols.



**MIL-HDBK-5H****1 December 1998**

**2.1.2.2 Physical Properties** — The physical properties ( $\omega$ ,  $C$ ,  $K$ , and  $\alpha$ ) of steels may be considered to apply to all forms and heat treatments unless otherwise indicated.

**2.1.3 ENVIRONMENTAL CONSIDERATIONS** — The effects of exposure to environments such as stress, temperature, atmosphere, and corrosive media are reported for various steels. Fracture toughness of high-strength steels and the growth of cracks by fatigue may be detrimentally influenced by humid air and by the presence of water or saline solutions. Some alleviation may be achieved by heat treatment and all high-strength steels are not similarly affected.

In general, these comments apply to steels in their usual finished surface condition, without surface protection. It should be noted that there are available a number of heat-resistant paints, platings, and other surface coatings that are employed either to improve oxidation resistance at elevated temperature or to afford protection against corrosion by specific media. In employing electrolytic platings, special consideration should be given to the removal of hydrogen by suitable baking. Failure to do so may result in lowered fracture toughness or embrittlement.

**MIL-HDBK-5H****1 December 1998****2.2 CARBON STEELS****2.2.0 COMMENTS ON CARBON STEELS**

**2.2.0.1 Metallurgical Considerations** — Carbon steels are those steels containing carbon up to about 1 percent and only residual quantities of other elements except those added for deoxidation.

The strength that carbon steels are capable of achieving is determined by carbon content and, to a much lesser extent, by the content of the residual elements. Through cold working or proper choice of heat treatments, these steels can be made to exhibit a wide range of strength properties.

The finish conditions most generally specified for carbon steels include hot-rolled, cold-rolled, cold-drawn, normalized, annealed, spheroidized, stress-relieved, and quenched-and-tempered. In addition, the low-carbon grades (up to 0.25 percent C) may be carburized to obtain high surface hardness and wear resistance with a tough core. Likewise, the higher carbon grades are amenable to selective flame hardening to obtain desired combinations of properties.

**2.2.0.2 Manufacturing Considerations** —

*Forging* — All of the carbon steels exhibit excellent forgeability in the austenitic state provided the proper forging temperatures are used. As the carbon content is increased, the maximum forging temperature is decreased. At high temperatures, these steels are soft and ductile and exhibit little or no tendency to work harden. The resulfurized grades (free-machining steels) exhibit a tendency to rupture when deformed in certain high-temperature ranges. Close control of forging temperatures is required.

*Cold Forming* — The very low-carbon grades have excellent cold-forming characteristics when in the annealed or normalized conditions. Medium-carbon grades show progressively poorer formability with higher carbon content, and more frequent annealing is required. The high-carbon grades require special softening treatments for cold forming. Many carbon steels are embrittled by warm working or prolonged exposure in the temperature range from 300 to 700°F.

*Machining* — The low-carbon grades (0.30 percent C and less) are soft and gummy in the annealed condition and are preferably machined in the cold-worked or the normalized condition. Medium-carbon (0.30 to 0.50 percent C) grades are best machined in the annealed condition, and high-carbon grades (0.50 to 0.90 percent C) in the spheroidized condition. Finish machining must often be done in the fully heat-treated condition for dimensional accuracy. The resulfurized grades are well known for their good machinability. Nearly all carbon steels are now available with 0.15 to 0.35 percent lead, added to improve machinability. However, resulfurized and leaded steels are not generally recommended for highly stressed aircraft and missile parts because of a drastic reduction in transverse properties.

*Welding* — The low-carbon grades are readily welded or brazed by all techniques. The medium-carbon grades are also readily weldable but may require preheating and postwelding heat treatment. The high-carbon grades are difficult to weld. Preheating and postwelding heat treatment are usually mandatory for the latter, and special care must be taken to avoid overheating. Furnace brazing has been used successfully with all grades.

*Heat Treatment* — Due to the poor oxidation resistance of carbon steels, protective atmospheres must be employed during heat treatment if scaling of the surface cannot be tolerated. Also, these steels are subject to decarburization at elevated temperatures and, where surface carbon content is critical, should be heated in reducing atmospheres.

**MIL-HDBK-5H****1 December 1998**

**2.2.0.3 Environmental Considerations** — Carbon steels have poor oxidation resistance above about 900 to 1000°F. Strength and oxidation-resistance criteria generally preclude the use of carbon steels above 900°F.

Carbon steels may undergo an abrupt transition from ductile to brittle behavior. This transition temperature varies widely for different carbon steels depending on many factors. Cautions should be exercised in the application of carbon steels to assure that the transition temperature of the selected alloy is below the service temperature. Additional information is contained in References 2.2.0.3(a) and (b).

The corrosion resistance of carbon steels is relatively poor; clean surfaces rust rapidly in moist atmospheres. Simple oil film protection is adequate for normal handling. For aerospace applications, the carbon steels are usually plated to provide adequate corrosion protection.

**2.2.1 AISI 1025**

**2.2.1.0 Comments and Properties** — AISI 1025 is an excellent general purpose steel for the majority of shop requirements, including jigs, fixtures, prototype mockups, low torque shafting, and other applications. It is not generally classed as an airframe structural steel. However, it is available in aircraft quality as well as commercial quality.

*Manufacturing Considerations* — Cold-finished flat-rolled products are supplied principally where maximum strength, good surface finish, or close tolerance is desirable. Reasonably good forming properties are found in AISI 1025. The machinability of bar stock is rated next to these sulfurized types of free-machining steels, but the resulting surface finish is poorer.

*Specifications and Properties* — Material specifications for AISI 1025 steel are presented in Table 2.2.1.0(a). The room-temperature mechanical and physical properties are shown in Table 2.2.1.0(b). The effect of temperature on thermal expansion is shown in Figure 2.2.1.0.

**Table 2.2.1.0(a). Material Specifications for AISI 1025 Carbon Steel**


Specification	Form
MIL-S-7097, Comp. 3	Bar
AMS 5075	Seamless tubing
AMS 5077	Tubing
MIL-T-5066	Tubing
AMS 5046	Sheet, strip, and plate
MIL-S-7952,1025	Sheet and strip

**MIL-HDBK-5H****1 December 1998****Table 2.2.1.0(b). Design Mechanical and Physical Properties of AISI 1025 Carbon Steel**

Specification .....	AMS 5046, Type 2, and MIL-S-7952, 1025	AMS 5075, AMS 5077, and MIL-T-5066	MIL-S-7097, Comp. 3
Form .....	Sheet, strip, and plate	Tubing	Bar
Condition .....	Annealed	Normalized	All
Thickness, in. ....	...	...	...
Basis .....	S	S	S
<b>Mechanical Properties:</b>			
$F_u$ , ksi:			
L .....	55	55	55
LT .....	55	55	55
ST .....	...	...	55
$F_y$ , ksi:			
L .....	36	36	36
LT .....	36	36	36
ST .....	...	...	36
$F_{cy}$ , ksi:			
L .....	36	36	36
LT .....	36	36	36
ST .....	...	...	36
$F_{su}$ , ksi .....	35	35	35
$F_{bru}$ , ksi:			
(e/D = 1.5) .....	...	...	...
(e/D = 2.0) .....	90	90	90
$F_{brγ}$ , ksi:			
(e/D = 1.5) .....	...	...	...
(e/D = 2.0) .....	...	...	...
$e$ , percent:			
L .....	...	a	a
LT .....	a	...	...
$E$ , $10^3$ ksi .....	29.0		
$E_c$ , $10^3$ ksi .....	29.0		
$G$ , $10^3$ ksi .....	11.0		
$\mu$ .....	0.32		
<b>Physical Properties:</b>			
$\omega$ , lb/in. <sup>3</sup> .....	0.284		
$C$ , Btu/(lb)(°F) .....	0.116 (122 to 212°F)		
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] ..	30.0 (at 32°F)		
$\alpha$ , $10^{-6}$ in./in./°F .....	See Figure 2.2.1.0		

a See applicable specification for variation in minimum elongation with ultimate strength.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.2.1.0. Effect of temperature on the thermal expansion of 1025 steel.**

## MIL-HDBK-5H

1 December 1998

## 2.3 LOW-ALLOY STEELS (AISI GRADES AND PROPRIETARY GRADES)

### 2.3.0 COMMENTS ON LOW-ALLOY STEELS (AISI AND PROPRIETARY GRADES)

**2.3.0.1 Metallurgical Considerations** — The AISI or SAE alloy steels contain, in addition to carbon, up to about 1 percent (up to 0.5 percent for most airframe applications) additions of various alloying elements to improve their strength, depth of hardening, toughness, or other properties of interest. Generally, alloy steels have better strength-to-weight ratios than carbon steels and are somewhat higher in cost on a weight, but not necessarily strength, basis. Their applications in airframes include landing-gear components, shafts, gears, and other parts requiring high strength, through hardening, or toughness.

Some alloy steels are identified by the AISI four-digit system of numbers. The first two digits indicate the alloy group and the last two the approximate carbon content in hundredths of a percent. The alloying elements used in these steels include manganese, silicon, nickel, chromium, molybdenum, vanadium, and boron. Other steels in this section are proprietary steels which may be modifications of the AISI grades. The alloying additions in these steels may provide deeper hardening, higher strength and toughness.

These steels are available in a variety of finish conditions, ranging from hot- or cold-rolled to quenched-and-tempered. They are generally heat treated before use to develop the desired properties. Some steels in this group are carburized, then heat treated to produce a combination of high surface hardness and good core toughness.

#### 2.3.0.2 Manufacturing Conditions —

*Forging* — The alloy steels are only slightly more difficult to forge than carbon steels. However, maximum recommended forging temperatures are generally about 50°F lower than for carbon steels of the same carbon content. Slower heating rates, shorter soaking period, and slower cooling rates are also required for alloy steels.

*Cold Forming* — The alloy steels are usually formed in the annealed condition. Their formability depends mainly on the carbon content and is generally slightly poorer than for unalloyed steels of the same carbon content. Little cold forming is done on these steels in the heat-treated condition because of their high strength and limited ductility.

*Machining* — The alloy steels are generally harder than unalloyed steels of the same carbon content. As a consequence, the low-carbon alloy steels are somewhat easier to finish machine than their counterparts in the carbon steels. It is usually desirable to finish machine the carburizing and through-hardening grades in the final heat-treated condition for better dimensional accuracy. This often leads to two steps in machining: rough machining in the annealed or hot-finished condition, then finish machining after heat treating. The latter operation, because of the relatively high hardness of the material, necessitates the use of sharp, well-designed, high-speed steel cutting tools, proper feeds, speeds, and a generous supply of coolant. Medium- and high-carbon grades are usually spheroidized for optimum machinability and, after heat treatment, may be finished by grinding. Many of the alloy steels are available with added sulfur or lead for improved machinability. However, resulfurized and leaded steels are not recommended for highly stressed aircraft and missile parts, because of drastic reductions in transverse properties.

*Welding* — The low-carbon grades are readily welded or brazed by all techniques. Alloy welding rods comparable in strength to the base metal are used, and moderate preheating (200 to 600°F) is usually necessary. At higher carbon levels, higher preheating temperatures, and often postwelding stress relieving, are required. Certain alloy steels can be welded without loss of strength in the heat-affected zone provided that the welding heat input is carefully controlled. If the composition and strength level are such that the

**MIL-HDBK-5H****1 December 1998**

strength of the welded joint is reduced, the strength of the joint may be restored by heat treatment after welding.

*Heat Treatment* — For the low alloy steels, there are various heat treatment procedures that can be applied to a particular alloy to achieve any one of a number of specific mechanical (for example tensile) properties. Within this chapter, there are mechanical properties for three thermal processing conditions: annealed, normalized, and quenched and tempered. The specific details of these three thermal processing conditions are reviewed in Reference 2.3.0.2.5. In general, the annealed condition is achieved by heating to a suitable temperature and holding for a specified period of time. Annealing generally softens the material, producing the lowest mechanical properties. The normalized condition is achieved by holding to a slightly higher temperature than annealing, but for a shorter period of time. The purpose of normalizing varies depending on the desired properties; it can be used to increase or decrease mechanical properties. The quenched and tempered condition, discussed in more detail below, is used to produce the highest mechanical properties while providing relatively high toughness. The mechanical properties for these three processing conditions for specific steels are as shown in Tables 2.3.1.0(c), (f), and (h).

Maximum hardness in these steels is obtained in the as-quenched condition, but toughness and ductility in this condition are comparatively low. By means of tempering, their toughness is improved, usually accompanied by a decrease in strength and hardness. In general, tempering temperatures to achieve very high strength should be avoided when toughness is an important consideration.

In addition, these steels may be embrittled by tempering or by prolonged exposure under stress within the “blue brittle” range (approximately 500 to 700°F). Strength levels that necessitate tempering within this range should be avoided.

The mechanical properties presented in this chapter represent steels heat treated to produce a quenched structure containing 90 percent martensite at the center and tempered to the desired  $F_{tu}$  level. This degree of through hardening is necessary (regardless of strength level) to insure the attainment of reasonably uniform mechanical properties throughout the cross section of the heat-treated part. The maximum diameter of round bars of various alloy steels capable of being through hardened consistently are given in Table 2.3.0.2. Limiting dimensions for common shapes other than round are determined by means of the “equivalent round” concept in Figure 2.3.0.2. This concept is essentially a correlation between the significant dimensions of a particular shape and the diameter of a round bar, assuming in each instance that the material, heat treatment, and the mechanical properties at the centers of both the respective shape and the equivalent round are substantially the same.

For the quenched and tempered condition, a large range of mechanical property values can be achieved as indicated in Table 2.3.0.2. Various quench media (rates), tempering temperatures, and times can be employed allowing any number of processing routes to achieve these values. As a result of these processing routes, there are a large range of mechanical properties that can be obtained for a specific alloy. Therefore, the properties of a steel can be tailored to meet the needs for a specific component/application.

Because of the potential for several different processing methods for these three conditions, the MIL, Federal, and AMS specifications do not always contain minimum mechanical property values (S-basis). They may contain minimum mechanical property values for one specific quenched and tempered condition. Those specifications cited in this Handbook that do not contain mechanical properties are identified with a footnote in Tables 2.3.1.0(a) and (b). The possible mechanical properties for these alloys covered in the specifications for the normalized, and quenched and tempered conditions in Table 2.3.0.2 are presented in Tables 2.3.1.0 ( $h_1$ ) and ( $h_2$ ). Users must rely on their own in-house specifications or appropriate industry specifications to validate that the required strength was achieved. Therefore, no statistical basis (A, B, S) for these values are indicated in Tables 2.3.1.0 ( $h_1$ ) and ( $h_2$ ).

**MIL-HDBK-5H****1 December 1998****Table 2.3.0.2. Maximum Round Diameters for Low-Alloy Steel Bars (Through Hardening to at Least 90 Percent Martensite at Center)**

	Diameter of Round or Equivalent Round, in. <sup>a</sup>						
$F_{tu}$ , ksi	0.5	0.8	1.0	1.7	2.5	3.5	5.0
270 & 280	...	...	...	...	...	...	300M <sup>c</sup>
260	...	...	...	AISI 4340 <sup>b</sup>	AISI 4340 <sup>c</sup>	AISI 4340 <sup>d</sup>	...
220	...	...	...	AMS Grades <sup>be</sup>	AMS Grades <sup>ce</sup>	D6AC <sup>b</sup>	D6AC <sup>c</sup>
200	...	AISI 8740	AISI 4140	AISI 4340 <sup>b</sup> AMS Grades <sup>be</sup>	AISI 4340 <sup>c</sup> AMS Grades <sup>ce</sup>	AISI 4340 <sup>d</sup>	D6AC <sup>c</sup>
≤180	AISI 4130 and 8630	AISI 8735 4135 and 8740	AISI 4140	AISI 4340 <sup>b</sup> AMS Grades <sup>be</sup>	AISI 4340 <sup>c</sup> AMS Grades <sup>ce</sup>	AISI 4340 <sup>d</sup> D6AC <sup>b</sup>	D6AC <sup>c</sup>

a This table indicates the maximum diameters to which these steels may be through hardened consistently by quenching as indicated. Any steels in this table may be used at diameters less than those indicated. The use of steels at diameters greater than those indicated should be based on hardenability data for specific heats of steel.

b Quenched in molten salt at desired tempering temperature ("martempering").

c Quenched in oil at a flow rate of 200 feet per minute.







d Quenched in water at a flow rate of 200 feet per minute.

e 4330V, 4335V, and Hy-Tuf.



## MIL-HDBK-5H

1 December 1998

SOLIDS, LENGTH L			
ROUND	HEXAGON	SQUARE	RECTANGULAR OR PLATE
			
$ER^a = T$	$ER = 1.1 T$	$ER = 1.25 T$	$ER = 1.5 T$
WHEN L IS LESS THAN T, CONSIDER SECTION AS A PLATE OF L THICKNESS			
TUBE (ANY SECTION)		RESTRICTED OR CLOSED AT ONE OR BOTH ENDS	
OPEN BOTH ENDS		RESTRICTED OR CLOSED AT ONE OR BOTH ENDS	
 $ER = 2 T$ NOTE: WHEN L IS LESS THAN D, CONSIDER AS A PLATE OF T THICKNESS. WHEN L IS LESS THAN T, CONSIDER SECTION AS A PLATE OF L THICKNESS.		 $ER = 2.5 T$ WHEN D IS LESS THAN 2.5 INCHES. $ER = 3.5 T$ WHEN D IS GREATER THAN 2.5 INCHES.	

<sup>a</sup>ER = equivalent round. (Illustration after MIL-H-6875.)<sup>b</sup>Use maximum thickness for calculation.

**Figure 2.3.0.2. Correlation between significant dimensions of common shapes other than round, and the diameters of round bars.**

**MIL-HDBK-5H****1 December 1998**

**2.3.0.3 Environmental Considerations** — Alloy steels containing chromium or high percentages of silicon have somewhat better oxidation resistance than the carbon or other alloy steels. Elevated-temperature strength for the alloy steels is also higher than that of corresponding carbon steels. The mechanical properties of all alloy steels in the heat-treated condition are affected by extended exposure to temperatures near or above the temperature at which they were tempered. The limiting temperatures to which each alloy may be exposed for no longer than approximately 1 hour per inch of thickness or approximately one-half hour for thicknesses under one-half inch without a reduction in strength occurring are listed in Table 2.3.0.3. These values are approximately 100°F below typical tempering temperatures used to achieve the designated strength levels.

**Table 2.3.0.3. Temperature Exposure Limits for Low-Alloy Steels**

$F_m$ , ksi	Exposure Limit, °F						
	125	150	180	200	220	260	270 & 280
Alloy:							
AISI 4130 and 8630	925	775	575	...	...	...	...
AISI 4140 and 8740	1025	875	725	625	...	...	...
AISI 4340	1100	950	800	700	...	350	...
AISI 4135 and 8735	975	825	675	...	...	...	...
D6AC	1150	1075	1000	950	900	500	...
Hy-Tuf	875	750	650	550	450	...	...
4330V	925	850	775	700	500	...	...
4335V	975	875	775	700	500	...	...
300M	...	...	...	...	...	...	475

a Quenched and tempered to  $F_m$  indicated. If the material is exposed to temperatures exceeding those listed, a reduction in strength is likely to occur.

Low-alloy steels may undergo a transition from ductile to brittle behavior at low temperatures. This transition temperature varies widely for different alloys. Caution should be exercised in the application of low-alloy steels at temperatures below -100°F. For use at a temperature below -100°F, an alloy with a transition temperature below the service temperature should be selected. For low temperatures, the steel should be heat treated to a tempered martensitic condition for maximum toughness.

Heat-treated alloy steels have better notch toughness than carbon steels at equivalent strength levels. The decrease in notch toughness is less pronounced and occurs at lower temperatures. Heat-treated alloy steels may be useful for subzero applications, depending on their alloy content and heat treatment. Heat treating to strength levels higher than 150 ksi  $F_{ty}$  may decrease notch toughness.

The corrosion properties of the AISI alloy steels are comparable to the plain carbon steels.

**MIL-HDBK-5H****1 December 1998****2.3.1 SPECIFIC ALLOYS**

**2.3.1.0 Comments and Properties** — AISI 4130 is a chromium-molybdenum steel that is in general use due to its well-established heat-treating practices and processing techniques. It is available in all sizes of sheet, plate, and tubing. Bar stock of this material is also used for small forgings under one-half inch in thickness. AISI 4135, a slightly higher carbon version of AISI 4130, is available in sheet, plate, and tubing.

AISI 4140 is a chromium-molybdenum steel that can be heat treated in thicker sections and to higher strength levels than AISI 4130. This steel is generally used for structural machined and forged parts one-half inch and over in thickness. It can be welded but it is more difficult to weld than the lower carbon grade AISI 4130.

AISI 4340 is a nickel-chromium-molybdenum steel that can be heat treated in thicker sections and to higher strength levels than AISI 4140.

AISI 8630, 8735, and 8740 are nickel-chromium-molybdenum steels that are considered alternates to AISI 4130, 4135, and 4140, respectively.

There are a number of steels available with compositions that represent modifications to the AISI grades described above. Four of the steels that have been used rather extensively at  $F_m = 220$  ksi are D6AC, Hy-Tuf, 4330V, and 4335V. It should be noted that this strength level is not used for AISI 4340 due to embrittlement encountered during tempering in the range of 500 to 700°F. In addition, AISI 4340 and 300M are utilized at strength levels of  $F_m = 260$  ksi or higher. The alloys, AISI 4340, D6AC, 4330V, 4335V, and 300M, are available in the consumable electrode melted grade. Material specifications for these steels are presented in Tables 2.3.1.0(a) and (b).

The room-temperature mechanical and physical properties for these steels are presented in Tables 2.3.1.0(c) through 2.3.1.0(g). Mechanical properties for heat-treated materials are valid only for steel heat treated to produce a quenched structure containing 90 percent or more martensite at the center. Figure 2.3.1.0 contains elevated temperature curves for the physical properties of AISI 4130 and AISI 4340 steels.

**2.3.1.1 AISI Low-Alloy Steels** — Elevated temperature curves for heat-treated AISI low-alloy steels are presented in Figures 2.3.1.1.1 through 2.3.1.1.4. These curves are considered valid for each of these steels in each heat-treated condition but only up to the maximum temperatures listed in Table 2.3.0.1(b).

**2.3.1.2 AISI 4130 and 8630 Steels** — Typical stress-strain and tangent-modulus curves for AISI 8630 are shown in Figures 2.3.1.2.6(a) through (c). Best-fit S/N curves for AISI 4130 steel are presented in Figures 2.3.1.2.8(a) through (h).

**2.3.1.3 AISI 4340 Steel** — Typical stress-strain and tangent-modulus curves for AISI 4340 are shown in Figures 2.3.1.3.6(a) through (c). Typical biaxial stress-strain curves and yield-stress envelopes for AISI 4340 alloy steel are presented in Figures 2.3.1.3.6(d) through (g). Best-fit S/N curves for AISI 4340 are presented in Figures 2.3.1.3.8(a) through (o).

**2.3.1.4 300M Steel** — Best-fit S/N curves for 300M steel are presented in Figures 2.3.1.4.8(a) through (d). Fatigue-crack-propagation data for 300M are shown in Figure 2.3.1.4.9.

**2.3.1.5 D6AC Steel** — Fatigue-crack-propagation data for D6AC steel are presented in Figure 2.3.1.5.9.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 2.3.1.0(a). Material Specifications for Air Melted Low-Alloy Steels**

Alloy	Form		
	Sheet, strip, and plate	Bars and forgings	Tubing
4130	MIL-S-18729, AMS 6350 <sup>a</sup> , AMS 6351 <sup>a</sup>	MIL-S-6758 <sup>a</sup> , AMS 6348 <sup>a</sup> , AMS 6370 <sup>a</sup> , AMS 6528 <sup>a</sup>	MIL-T-6736, AMS 6371 <sup>a</sup> , AMS 6360, AMS 6361, AMS 6362, AMS 6373, AMS 6374
8630	MIL-S-18728, AMS 6355	MIL-S-6050, AMS 6280 <sup>a</sup>	AMS 6281 <sup>a</sup>
4135	AMS 6352 <sup>a</sup>	...	AMS 6372 <sup>a</sup> , AMS 6365, MIL-T-6735
8735	AMS 6357 <sup>a</sup>	AMS 6320 <sup>a</sup>	AMS 6282 <sup>a</sup>
4140	AMS 6395 <sup>a</sup>	MIL-S-5626 <sup>a</sup> , AMS 6382 <sup>a</sup> , AMS 6349 <sup>a</sup> , AMS 6529 <sup>a</sup>	AMS 6381 <sup>a</sup> , AMS 6390 <sup>a</sup>
4340	AMS 6359 <sup>a</sup>	MIL-S-5000 <sup>a</sup> , AMS 6415 <sup>a</sup>	AMS 6415 <sup>a</sup>
8740	AMS 6358 <sup>a</sup>	MIL-S-6049, AMS 6327, AMS 6322 <sup>a</sup>	AMS 6323 <sup>a</sup>
4330V	...	AMS 6427 <sup>a</sup>	AMS 6427 <sup>a</sup>
Hy-Tuf	...	AMS 6418	AMS 6418
4335V	AMS 6433	AMS 6430	AMS 6430

<sup>a</sup> Specification does not contain minimum mechanical properties.

**Table 2.3.1.0(b). Material Specifications for Consumable Electrode Melted Low-Alloy Steels**

Alloy	Form		
	Sheet, strip, and plate	Bar and forgings	Tubing
4340	AMS 6454 <sup>a</sup>	AMS 6414, MIL-S-8844	AMS 6414, MIL-S-8844
D6AC	MIL-S-8949	MIL-S-8949, AMS 6431	AMS 6431
4330V	...	AMS 6411	AMS 6411
Hy-Tuf	...	AMS 6425	AMS 6425
4335V	AMS 6435	AMS 6429	AMS 6429
300M (0.40C)	...	AMS 6417	AMS 6417
300M (0.42C)	...	AMS 6419, MIL-S-8844 AMS 6257	AMS 6419, MIL-S-8844 AMS 6257

<sup>a</sup> Specification does not contain minimum mechanical properties.

**MIL-HDBK-5H****1 December 1998****Table 2.3.1.0(c<sub>1</sub>). Design Mechanical and Physical Properties of Air Melted Low-Alloy Steels**

Alloy .....	AISI 4130		AISI 4135		AISI 8630	
	AMS 6360 AMS 6373 AMS 6374 MIL-T-6736 MIL-S-18729		AMS 6365 MIL-T-6735		MIL-S-18728	
Specification [see Tables 2.3.1.0(a) and (b)] .....						
Form .....	Sheet, strip, plate, and tubing		Tubing		Sheet, strip, and plate	
Condition .....	Normalized and tempered, stress relieved <sup>a</sup>					
Thickness or diameter, in. ...	≤0.187	>0.187	≤0.187	≤0.187	≤0.187	≤0.187
Basis .....	S	S	S	S	S	S
Mechanical Properties:						
$F_{tu}$ , ksi .....	95	90	100	95	95	90
$F_{ty}$ , ksi .....	75	70	85	80	75	70
$F_{cy}$ , ksi .....	75	70	89	84	75	70
$F_{su}$ , ksi .....	57	54	60	57	57	54
$F_{bru}$ , ksi:						
(e/D = 1.5) .....	...	...	...	...	...	...
(e/D = 2.0) .....	200	190	190	180	200	190
$F_{bry}$ , ksi:						
(e/D = 1.5) .....	...	...	...	...	...	...
(e/D = 2.0) .....	129	120	146	137	129	120
$e$ , percent .....	See Table 2.3.1.0(d)					
$E$ , 10 <sup>3</sup> ksi .....	29.0					
$E_c$ , 10 <sup>3</sup> ksi .....	29.0					
$G$ , 10 <sup>3</sup> ksi .....	11.0					
$\mu$ .....	0.32					
Physical Properties:						
$\omega$ , lb/in. <sup>3</sup> .....	0.283					
$C$ , $K$ , and $\alpha$ .....	See Figure 2.3.1.0					

<sup>a</sup> Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.

**MIL-HDBK-5H****1 December 1998****Table 2.3.1.0(c<sub>2</sub>). Design Mechanical and Physical Properties of Air Melted Low-Alloy Steels**

Alloy . . . . .	AISI 4130		
Specification [see Tables 2.3.1.0(a) and (b)] . . . . .	AMS 6361 MIL-T-6736	AMS 6362 MIL-T-6736	MIL-T-6736
Form . . . . .	Tubing		
Condition . . . . .	Quenched and tempered <sup>a</sup>		
Thickness or diameter, in. . . . .	≤0.188	≤0.188	All Walls
Basis . . . . .	S	S	S
Mechanical Properties:			
$F_{tu}$ , ksi . . . . .	125	150	180
$F_{ty}$ , ksi . . . . .	100	135	165
$F_{cy}$ , ksi . . . . .	109	141	173
$F_{su}$ , ksi . . . . .	75	90	108
$F_{bru}$ , ksi:			
(e/D = 1.5) . . . . .	194	231	277
(e/D = 2.0) . . . . .	251	285	342
$F_{bry}$ , ksi:			
(e/D = 1.5) . . . . .	146	210	257
(e/D = 2.0) . . . . .	175	232	284
$e$ , percent . . . . .	See Table 2.3.1.0(e)		
$E$ , 10 <sup>3</sup> ksi . . . . .	29.0		
$E_c$ , 10 <sup>3</sup> ksi . . . . .	29.0		
$G$ , 10 <sup>3</sup> ksi . . . . .	11.0		
$\mu$ . . . . .	0.32		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.283		
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 2.3.1.0		

a Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.

**MIL-HDBK-5H****1 December 1998****Table 2.3.1.0(c<sub>3</sub>). Design Mechanical and Physical Properties of Air Melted Low-Alloy Steels**

Alloy .....	AISI 8630	AISI 8740	
Specification [see Tables 2.3.1.0(a) and (b)] .....	MIL-S-6050	MIL-S-6049	AMS 6327
Form .....	Bars and forgings		
Condition .....	Quenched and tempered <sup>a</sup>		
Thickness or diameter, in. ...	≤1.500	≤1.750	
Basis .....	S	S	
Mechanical Properties:			
$F_{tu}$ , ksi .....	125	125	125
$F_{ty}$ , ksi .....	100	103	100
$F_{cy}$ , ksi .....	109	108	109
$F_{su}$ , ksi .....	75	75	75
$F_{bru}$ , ksi:			
(e/D = 1.5) .....	194	192	194
(e/D = 2.0) .....	251	137	251
$F_{bry}$ , ksi:			
(e/D = 1.5) .....	146	160	146
(e/D = 2.0) .....	175	177	175
$e$ , percent .....	See Table 2.3.1.0(e)		
$E$ , 10 <sup>3</sup> ksi .....	29.0		
$E_c$ , 10 <sup>3</sup> ksi .....	29.0		
$G$ , 10 <sup>3</sup> ksi .....	11.0		
$\mu$ .....	0.32		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> .....	0.283		
$C$ , $K$ , and $\alpha$ .....	See Figure 2.3.1.0		

<sup>a</sup> Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 2.3.1.0(c<sub>4</sub>). Design Mechanical and Physical Properties of Air Melted Low-Alloy Steels**

Alloy . . . . .	AISI 4135			
Specification [see Tables 2.3.1.0(a) and (b)] . . . . .	MIL-T-6753			
Form . . . . .	Tubing			
Condition . . . . .	Quenched and tempered <sup>a</sup>			
Thickness or diameter, in. . . . .	See Table 2.3.0.2			
Basis . . . . .	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi . . . . .	125	150	180	200
$F_{ty}$ , ksi . . . . .	100	135	165	176 <sup>b</sup>
$F_{cy}$ , ksi . . . . .	109	141	173	181
$F_{su}$ , ksi . . . . .	75	90	108	120
$F_{bru}$ , ksi:				
(e/D = 1.5) . . . . .	194	231	277	272
(e/D = 2.0) . . . . .	251	285	342	355
$F_{bry}$ , ksi:				
(e/D = 1.5) . . . . .	146	210	257	255
(e/D = 2.0) . . . . .	175	232	284	280
$e$ , percent . . . . .	See Table 2.3.1.0(e)			
$E$ , 10 <sup>3</sup> ksi . . . . .	29.0			
$E_c$ , 10 <sup>3</sup> ksi . . . . .	29.0			
$G$ , 10 <sup>3</sup> ksi . . . . .	11.0			
$\mu$ . . . . .	0.32			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.283			
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 2.3.1.0			

a Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.

b The S-basis value in MIL-T-6735 is 165 ksi.



**MIL-HDBK-5H**  
**1 December 1998**

**Table 2.3.1.0(d). Minimum Elongation Values for Low-Alloy Steels in Condition N**

Form	Thickness, in.	Elongation, percent	
		Full tube	Strip
Sheet, strip, and plate (T) . . . . .	Less than 0.062 . . . . .	--	8
	Over 0.062 to 0.125 incl. . . . .	--	10
	Over 0.125 to 0.187 incl. . . . .	--	12
	Over 0.187 to 0.249 incl. . . . .	--	15
	Over 0.249 to 0.749 incl. . . . .	--	16
	Over 0.749 to 1.500 incl. . . . .	--	18
Tubing (L) . . . . .	Up to 0.035 incl. (wall) . . . . .	10	5
	Over 0.035 to 0.188 incl. . . . .	12	7
	Over 0.188 . . . . .	15	10

**Table 2.3.1.0(e). Minimum Elongation Values for Heat-Treated Low-Alloy Steels**

F <sub>tu</sub> , ksi	Round specimens (L)		Elongation in 2 in., percent				
			Sheet specimens			Tubing (L)	
	Elongation in 4D, percent	Reduction of area, percent	Less than 0.032 in. thick	0.032 to 0.060 in. thick	Over 0.060 in. thick	Full tube	Strip
125	17	55	5	7	10	12	7
140	15	53	4	6	9	10	6
150	14	52	4	6	9	10	6
160	13	50	3	5	8	9	6
180	12	47	3	5	7	8	5
200	10	43	3	4	6	6	5

**MIL-HDBK-5H****1 December 1998****Table 2.3.1.0(f<sub>1</sub>). Design Mechanical and Physical Properties of Low-Alloy Steels**

Alloy . . . . .	Hy-Tuf	4330V	4335V	4335V	D6AC	AISI 4340a	0.40C 300M	0.42C 300M
Specification . . . . .	AMS 6418 AMS 6425	AMS 6411	AMS 6430	AMS 6429	AMS 6431	AMS 6414	AMS 6417	AMS 6257 AMS 6419
Form . . . . .	Bar, forging, tubing							
Condition . . . . .	Quenched and tempered <sup>b</sup>							
Thickness or diameter, in. . . . .	See Table 2.3.0.2							
Basis . . . . .	S	S	S	S	S	S	S	S
Mechanical Properties:								
$F_{tu}$ , ksi . . . . .	220	220	205	240	220	260	270	280
$F_{ty}$ , ksi . . . . .	185	185	190	210	190	217	220	230
$F_{cy}$ , ksi . . . . .	193	193	199	220	198	235	236	247
$F_{su}$ , ksi . . . . .	132	132	123	144	132	156	162	168
$F_{bru}$ , ksi:								
(e/D = 1.5) . . . . .	297	297	315	369	297	347	414 <sup>c</sup>	430 <sup>c</sup>
(e/D = 2.0) . . . . .	385	385	389	465	385	440	506 <sup>c</sup>	525 <sup>c</sup>
$F_{bry}$ , ksi:								
(e/D = 1.5) . . . . .	267	267	296	327	274	312	344 <sup>c</sup>	360 <sup>c</sup>
(e/D = 2.0) . . . . .	294	294	327	361	302	346	379 <sup>c</sup>	396 <sup>c</sup>
$e$ , percent:								
L . . . . .	10	10	10	10	<sup>d</sup>	10	8	7
LT . . . . .	5 <sup>a</sup>	5 <sup>a</sup>	7	7	<sup>d</sup>	...	...	...
$E$ , 10 <sup>3</sup> ksi . . . . .	29.0							
$E_c$ , 10 <sup>3</sup> ksi . . . . .	29.0							
$G$ , 10 <sup>3</sup> ksi . . . . .	11.0							
$\mu$ . . . . .	0.32							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.283							
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 2.3.1.0							

a Applicable to consumable-electrode vacuum-melted material only.

b Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.

c Bearing values are "dry pin" values per Section 1.4.7.1.

d See Table 2.3.1.0(g) for elongation applicable to consumable-electrode vacuum-melted D6AC.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 2.3.1.0(f<sub>2</sub>). Design Mechanical and Physical Properties of Low-Alloy Steels**

Alloy .....	4335V	D6AC
Specification .....	AMS 6435	MIL-S-8949
Form .....	Sheet, strip, and plate	
Condition .....	Quenched and tempered <sup>b</sup>	
Thickness or diameter, in. . .	See Table 2.3.0.2	
Basis .....	S	S
Mechanical Properties:		
$F_{tu}$ , ksi .....	220	220
$F_{ty}$ , ksi .....	190	190
$F_{cy}$ , ksi .....	198	198
$F_{su}$ , ksi .....	132	132
$F_{bru}$ , ksi: <sup>c</sup>		
(e/D = 1.5) .....	297	297
(e/D = 2.0) .....	385	385
$F_{bry}$ , ksi: <sup>c</sup>		
(e/D = 1.5) .....	274	274
(e/D = 2.0) .....	302	302
$e$ , percent:		
L .....	10	d
LT .....	7	d
$E$ , 10 <sup>3</sup> ksi .....	29.0	
$E_c$ , 10 <sup>3</sup> ksi .....	29.0	
$G$ , 10 <sup>3</sup> ksi .....	11.0	
$\mu$ .....	0.32	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> .....	0.283	
$C$ , $K$ , and $\alpha$ .....	See Figure 2.3.1.0	

- a Applicable to consumable-electrode vacuum-melted material only.
- b Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.
- c Bearing values are “dry pin” values per Section 1.4.7.1.
- d See Table 2.3.1.0(g) for elongation applicable to consumable-electrode vacuum-melted D6AC.

**MIL-HDBK-5H****1 December 1998****Table 2.3.1.0(g). Minimum Elongation Values for Heat-Treated Consumable-Electrode Vacuum-Melted D6AC at  $F_{tu} = 220$  ksi**

Form	Size	Elongation, percent	
		L	T
Bar and forging	$\leq 50$ sq in.	12	10
	$> 50, \leq 200$ sq in.	12	8
	$> 200$ sq in.	10	7
Sheet and plate	$< 5/8$ in.	10	8

**MIL-HDBK-5H**  
**1 December 1998**

**Table 2.3.1.0(h<sub>1</sub>). Design Mechanical and Physical Properties of Low-Alloy Steels**

Alloy . . . . .	AISI 4130		AISI 4135		AISI 8630		AISI 8735	
Specification [see Tables 2.3.1.0(a) and (b)] . . . . .	AMS 6350 AMS 6528 MIL-S-6758		AMS 6352 AMS 6372		AMS 6281		AMS 6357	
Form . . . . .	Sheet, strip, plate, bars, and forgings		Sheet, strip, plate, and tubing		Tubing		Sheet, strip, and plate	
Condition . . . . .	Normalized and tempered, stress relieved <sup>a</sup>							
Thickness or diameter, in. . . . .	≤0.187	>0.187	≤0.187	>0.187	≤0.187	>0.187	≤0.187	>0.187
Basis . . . . .	b							
Mechanical Properties:								
$F_{tu}$ , ksi . . . . .	95	90	95	90	95	90	95	90
$F_{ty}$ , ksi . . . . .	75	70	75	70	75	70	75	70
$F_{cy}$ , ksi . . . . .	75	70	75	70	75	70	75	70
$F_{su}$ , ksi . . . . .	57	54	57	54	57	54	57	54
$F_{bru}$ , ksi:								
(e/D = 1.5) . . . . .	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	200	190	200	190	200	190	200	190
$F_{bry}$ , ksi:								
(e/D = 1.5) . . . . .	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	129	120	129	120	129	120	129	120
$e$ , percent . . . . .	See Table 2.3.1.0(d)							
$E$ , 10 <sup>3</sup> ksi . . . . .	29.0							
$E_c$ , 10 <sup>3</sup> ksi . . . . .	29.0							
$G$ , 10 <sup>3</sup> ksi . . . . .	11.0							
$\mu$ . . . . .	0.32							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.283							
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 2.3.1.0							

a Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.

b There is no statistical basis ( $T_{99}$  or  $T_{90}$ ) or specification basis (S) to support the mechanical property values in this table. See Sections 2.3.0.2.5 and 2.3.0.2.5.1.


**MIL-HDBK-5H**  
**1 December 1998**

**Table 2.3.1.0(h<sub>2</sub>). Design Mechanical and Physical Properties of Low-Alloy Steels**

Alloy . . . . .	4330V	See steels listed in Table 2.3.0.2 for the applicable strength levels					
Specification . . . . .	AMS 6427	See Tables 2.3.1.0(a) and (b)					
Form . . . . .	All wrought forms						
Condition . . . . .	Quenched and tempered <sup>a</sup>						
Thickness or diameter, in. . . . .	See Table 2.3.0.2						
Basis . . . . .	b						
Mechanical Properties:							
$F_{tu}$ , ksi . . . . .	220	125	140	150	160	180	200
$F_{ty}$ , ksi . . . . .	185	100	120	132	142	163	176
$F_{cy}$ , ksi . . . . .	193	109	131	145	154	173	181
$F_{su}$ , ksi . . . . .	132	75	84	90	96	108	120
$F_{bru}$ , ksi:							
(e/D = 1.5) . . . . .	297	209	209	219	230	250	272
(e/D = 2.0) . . . . .	385	251	273	287	300	326	355
$F_{bry}$ , ksi:							
(e/D = 1.5) . . . . .	267	146	173	189	202	230	255
(e/D = 2.0) . . . . .	294	175	203	218	231	256	280
$e$ , percent:							
L . . . . .	10	See Table 2.3.1.0(e)					
LT . . . . .	5 <sup>a</sup>						
$E$ , 10 <sup>3</sup> ksi . . . . .	29.0						
$E_c$ , 10 <sup>3</sup> ksi . . . . .	29.0						
$G$ , 10 <sup>3</sup> ksi . . . . .	11.0						
$\mu$ . . . . .	0.32						
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.283						
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 2.3.1.0						

a Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.

b There is no statistical basis ( $T_{99}$  or  $T_{90}$ ) or specification basis (S) to support the mechanical property values in this table. See Sections 2.3.0.2.5 and 2.3.0.2.5.1.

**MIL-HDBK-5H****1 December 1998**

**Figure 2.3.1.0. Effect of temperature on the physical properties of 4130 and 4340 alloy steels.**

MIL-HDBK-5H  
1 December 1998






Figure 2.3.1.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and tensile yield strength ( $F_{ty}$ ) of AISI low-alloy steels (all products).



**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.3.1.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of heat-treated AISI low-alloy steels (all products).**




**Figure 2.3.1.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of heat-treated AISI low-alloy steels (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.3.1.1.4. Effect of temperature on the tensile and compressive modulus (E and E<sub>c</sub>) of AISI low-alloy steels.**




**Figure 2.3.1.2.6(a). Typical tensile stress-strain curves at room temperature for heat-treated AISI 8630 alloy steel (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.3.1.2.6(b). Typical compressive tangent-modulus curves at room temperature for heat-treated AISI 8630 alloy steel (all products).**



**Figure 2.3.1.2.6(c). Typical tensile stress-strain curves at elevated temperatures for heat-treated AISI 8630 alloy steel,  $F_{tu} = 125$  ksi (all products).**

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.2.8(a). Best-fit S/N curves for unnotched 4130 alloy steel sheet, normalized, longitudinal direction.**

Correlative Information for Figure 2.3.1.2.8(a)

Product Form: Sheet, 0.075-inch thick

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial

Frequency - 1100-1800 cpm

Temperature - RT

Environment - Air

117 99 RT

Specimen Details: Unnotched  
2.88-3.00 inches gross width  
0.80-1.00 inch net width  
12.0 inch net section radius

No. of Heats/Lots: Not specified

Equivalent Stress Equations:

For stress ratios of -0.60 to +0.02

$\log N_f = 9.65 - 2.85 \log (S_{eq} - 61.3)$

$S_{eq} = S_{max} (1-R)^{0.41}$

Standard Error of Estimate = 0.21

Standard Deviation in Life = 0.45

$R^2 = 78\%$

Surface Condition: Electropolished

References: 3.2.3.1.8(a) and (f)

Sample Size = 23

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

For a stress ratio of -1.0


$\log N_f = 9.27 - 3.57 \log (S_{max} - 43.3)$



[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.2.8(c). Best-fit S/N curves for notched,  $K_t = 2.0$ , 4130 alloy steel sheet, normalized, longitudinal direction.**

Correlative Information for Figure 2.3.1.2.8(c)

Product Form: Sheet, 0.075-inch thick

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial

Frequency - 1100-1800 cpm

Temperature - RT

Environment - Air

117 99 RT  
(unnotched)

120 -- RT  
(notched)  
 $K_t 2.0$

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

Specimen Details: Notched,  $K_t = 2.0$

$\log N_f = 17.1 - 6.49 \log (S_{eq})$

Notch Type	Gross Width	Net Width	Notch Radius
Edge	2.25	1.500	0.3175
Center	4.50	1.500	1.500
Fillet	2.25	1.500	0.1736

$S_{eq} = S_{max} (1-R)^{0.86}$

Standard Error of Estimate = 0.19

Standard Deviation in Life = 0.78

$R^2 = 94\%$

Sample Size = 107


Surface Condition: Electropolished

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

References: 3.2.3.1.8(b) and (f)

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.2.8(d). Best-fit S/N curves for notched,  $K_t = 4.0$ , 4130 alloy steel sheet, normalized, longitudinal direction.**

Correlative Information for Figure 2.3.1.2.8(d)

Product Form: Sheet, 0.075-inch thick

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial

Frequency - 1100-1800 cpm

Temperature - RT

Environment - Air

117 99 RT  
(unnotched)

120 — RT  
(notched)

$K_t = 4.0$

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

Specimen Details: Notched,  $K_t = 4.0$

$\log N_f = 12.6 - 4.69 \log (S_{eq})$

Notch Gross Net Notch

$S_{eq} = S_{max} (1-R)^{0.63}$

Type Width Width Radius

Standard Error of Estimate = 0.24

Edge 2.25 1.500 0.057

Standard Deviation in Life = 0.70

Edge 4.10 1.496 0.070

$R^2 = 88\%$

Fillet 2.25 1.500 0.0195

Sample Size = 87


Surface Condition: Electropolished

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

References: 3.2.3.1.8(b), (f), and (g)

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.2.8(e). Best-fit S/N curves diagram for notched,  $K_t = 5.0$ , 4130 alloy steel sheet, normalized, longitudinal direction.**

Correlative Information for Figure 2.3.1.2.8(e)

Product Form: Sheet, 0.075-inch thick

Properties: TUS, ksi TYS, ksi Temp., °F

117	99	RT (unnotched)
120	—	RT (notched)

$K_t = 5.0$

Specimen Details: Edge Notched,  $K_t = 5.0$   
 Gross width = 2.25 inches  
 Net width = 1.50 inches  
 Notch radius = 0.075 inch

Surface Condition: Electropolished

Reference: 3.2.3.1.8(c)

Test Parameters:  
 Loading - Axial  
 Frequency - 1100-1500 cpm  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 12.0 - 4.57 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.56}$   
 Standard Error of Estimate = 0.18  
 Standard Deviation in Life = 0.87  
 $R^2 = 96\%$


Sample Size = 38

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.2.8(f). Best-fit S/N curves for unnotched 4130 alloy steel sheet,  $F_u = 180$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.2.8(f)

Product Form: Sheet, 0.075-inch thick

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

180 174 RT

Loading - Axial  
Frequency - 20-1800 cpm  
Temperature - RT  
Environment - Air

Specimen Details: Unnotched  
2.88 inches gross width  
1.00 inch net width  
12.0 inch net section radius

No. of Heats/Lots: Not specified

Surface Condition: Electropolished

Equivalent Stress Equation:

$\log N_f = 20.3 - 7.31 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.49}$   
Standard Error of Estimate = 0.39  
Standard Deviation in Life = 0.89  
 $R^2 = 81\%$


Reference: 3.2.3.1.8(f)

Sample Size = 27

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.2.8(g). Best-fit S/N curves for notched,  $K_t = 2.0$ , 4130 alloy steel sheet,  $F_{tu} = 180$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.2.8(g)

Product Form: Sheet, 0.075-inch thick

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

180 174 RT

Loading - Axial  
Frequency - 21-1800 cpm  
Temperature - RT  
Environment - Air

Specimen Details: Edge Notched  
2.25 inches gross width  
1.50 inches net width  
0.3175-inch notch radius

No. of Heats/Lots: Not specified

Surface Condition: Electropolished

Equivalent Stress Equation:

$\log N_f = 8.87 - 2.81 \log (S_{eq} - 41.5)$   
 $S_{eq} = S_{max} (1-R)^{0.46}$   
Standard Error of Estimate = 0.18  
Standard Deviation in Life = 0.77  
 $R^2 = 94\%$


Reference: 3.2.3.1.8(f)

Sample Size = 19

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.2.8(h). Best-fit S/N curves for notched,  $K_t = 4.0$ , 4130 alloy steel sheet,  $F_{tu} = 180$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.2.8(h)

Product Form: Sheet, 0.075-inch thick

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

180 174 RT

Loading - Axial

Frequency - 23-1800 cpm

Temperature - RT

Environment - Air

Specimen Details: Edge Notched  
2.25 inches gross width  
1.50 inches net width  
0.057-inch notch radius

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 12.4 - 4.45 \log (S_{eq})$

$S_{eq} = S_{max} (1-R)^{0.60}$

Standard Error of Estimate = 0.11

Standard Deviation in Life = 0.90

$R^2 = 98\%$


Surface Condition: Electropolished

Reference: 3.2.3.1.8(f)


Sample Size = 20

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.3.1.3.6(a). Typical tensile stress-strain curves at room temperature for heat-treated AISI 4340 alloy steel (all products).**




**Figure 2.3.1.3.6(b). Typical tensile stress-strain curves at cryogenic and room temperature for AISI 4340 alloy steel bar,  $F_{tu} = 260$  ksi.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.3.1.3.6(c). Typical compressive stress-strain and compressive tangent-modulus curves at room temperature for AISI 4340 alloy steel bar,  $F_{tu} = 260$  ksi.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.3.1.3.6(d). Typical biaxial stress-strain curves at room temperature for AISI 4340 alloy steel (machined thin-wall cylinders, axial direction = longitudinal direction of bar stock),  $F_{tu} = 180$  ksi. A biaxial ratio,  $B$ , denotes the ratio of hoop stresses to axial stresses.**


## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.3.6(e). Biaxial yield-stress envelope at room temperature for AISI 4340 alloy steel (machined thin-wall cylinders, axial direction = longitudinal direction of bar stock),  $F_{tu} = 180$  ksi,  $F_{ty}$  measured in the hoop direction.**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.3.1.3.6(f). Typical biaxial stress-strain curves at room temperature for AISI 4340 alloy steel (machined thin-wall cylinders, axial direction = longitudinal direction of bar stock),  $F_{tu} = 260$  ksi. A biaxial ratio  $B$  of zero corresponds to the hoop direction.**



**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.3.1.3.6(g). Biaxial yield-stress envelope at room temperature for AISI 4340 alloy steel (machined thin-wall cylinders, axial direction = longitudinal direction of bar stock),  $F_{tu} = 260$  ksi,  $F_{ty}$  measured in the hoop direction.**

**MIL-HDBK-5H****1 December 1998**

**Figure 2.3.1.3.8(a). Best-fit S/N curves for unnotched AISI 4340 alloy steel bar,  $F_{tu} = 125$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(a)

Product Form: Rolled bar, 1-1/8 inches diameter, air melted

Properties:

TUS, ksi	TYS, ksi	Temp., °F
125	—	RT (unnotched)
150	—	RT (notched)

Specimen Details: Unnotched  
0.400-inch diameter

Surface Condition: Hand polished to RMS 10

Reference: 2.3.1.3.8(a)

Test Parameters:

Loading - Axial  
Frequency - 2000 to 2500 cpm  
Temperature - RT  
Atmosphere - Air

No. of Heat/Lots: 1

Equivalent Stress Equation:


$\log N_f = 14.96 - 6.46 \log (S_{eq} - 60)$   
 $S_{eq} = S_{max} (1-R)^{0.70}$   
Standard Error of Estimate = 0.35  
Standard Deviation in Life = 0.77  
 $R^2 = 75\%$

Sample Size = 9

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.3.8(b). Best-fit S/N curves for unnotched,  $K_t = 3.3$ , AISI 4340 alloy steel bar,  $F_{tu} = 125$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(b)

Product Form: Rolled bar, 1-1/8 inches diameter, air melted

Properties: TUS, ksi TYS, ksi Temp., °F

125	—	RT
		(unnotched)
150	—	RT
		(notched)

Specimen Details: Notched, V-Groove,  $K_t = 3.3$   
 0.450-inch gross diameter  
 0.400-inch net diameter  
 0.010-inch root radius,  $r$   
 60° flank angle,  $\omega$

Surface Condition: Lathe turned to RMS 10

Reference: 2.3.1.3.8(a)

Test Parameters:

Loading - Axial  
 Frequency - 2000 to 2500 cpm  
 Temperature - RT  
 Atmosphere - Air

No. of Heat/Lots: 1

Equivalent Stress Equation:


$\log N_f = 9.75 - 3.08 \log (S_{eq} - 20.0)$   
 $S_{eq} = S_{max} (1 - R)^{0.84}$   
 Standard Error of Estimate = 0.40  
 Standard Deviation in Life = 0.90  
 $R^2 = 80\%$

Sample Size = 11

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.3.8(c). Best-fit S/N curves for unnotched AISI 4340 alloy steel bar,  $F_{tu} = 150$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(c)

Product Form: Rolled bar, 1.125 inches diameter, air melted

Properties:

TUS, ksi	TYS, ksi	Temp., °F
158	147	RT (unnotched)
190	—	RT (notched)

Specimen Details: Unnotched  
0.400-inch diameter

Surface Condition: Hand polished to RMS 10

Reference: 2.3.1.3.8(b)

Test Parameters:

Loading - Axial  
Frequency - 2000 to 2500 cpm  
Temperature - RT  
Atmosphere - Air

No. of Heat/Lots: 1

Equivalent Stress Equation:


$\log N_f = 10.76 - 3.91 \log (S_{eq} - 101.0)$   
 $S_{eq} = S_{max} (1-R)^{0.77}$   
Standard Deviation of Log (Life) = 0.33  
Adjusted  $R^2$  Statistic = 73%

Sample Size = 9

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.3.8(d). Best-fit S/N curves for unnotched AISI 4340 alloy steel bar,  $F_{tu} = 150$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(d)

Product Form: Rolled bar, 1-1/8 inches diameter, air melted

Properties: TUS, ksi TYS, ksi Temp., °F  
 158 147 RT  
 (unnotched)  
 190 — RT  
 (notched)

Specimen Details: Notched, V-Groove,  $K_t = 3.3$   
 0.450-inch gross diameter  
 0.400-inch net diameter  
 0.010-inch root radius,  $r$   
 60° flank angle,  $\omega$

Surface Condition: Lathe turned to RMS 10

Reference: 2.3.1.3.8(a)

Test Parameters:

Loading - Axial  
 Frequency - 2000 to 2500 cpm  
 Temperature - RT  
 Atmosphere - Air

No. of Heat/Lots: 1

Equivalent Stress Equation:


$\log N_f = 7.90 - 2.00 \log (S_{eq} - 40.0)$   
 $S_{eq} = S_{max} (1 - R)^{0.60}$   
 Standard Error of Estimate = 0.27  
 Standard Deviation in Life = 0.74  
 $R^2 = 86\%$

Sample Size = 11

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.3.8(e). Best-fit S/N curves for unnotched AISI 4340 alloy steel bar at 600°F,  $F_{tu} = 150$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(e)

Product Form: Rolled bar, 1-1/8 inches diameter, air melted

Properties: TUS, ksi TYS, ksi Temp., °F

158	147	RT (unnotched)
153	121	600 (unnotched)
190	—	RT (notched)
176	—	600 (notched)

Test Parameters:

Loading - Axial  
Frequency - 2000 to 2500 cpm  
Temperature - 600°F  
Atmosphere - Air

No. of Heat/Lots: 1

Equivalent Stress Equation:

$\log N_f = 22.36 - 9.98 \log (S_{eq} - 60.0)$   
 $S_{eq} = S_{max} (1-R)^{0.66}$   
Standard Error of Estimate = 0.24  
Standard Deviation in Life = 1.08  
 $R^2 = 95\%$

Specimen Details: Unnotched  
0.400-inch diameter

Sample Size = 11


Surface Condition: Hand polished to RMS 10

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

Reference: 2.3.1.3.8(b)

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.3.8(f). Best-fit S/N curves for notched,  $K_t = 3.3$ , AISI 4340 alloy steel bar at 600°F,  $F_{tu} = 150$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(f)

Product Form: Rolled bar, 1-1/8 inches diameter, air melted

Reference: 2.3.1.3.8(b)

Properties:

TUS, ksi	TYS, ksi	Temp., °F
158	147	RT (unnotched)
153	121	600 (unnotched)
190	—	RT (notched)
176	—	600 (notched)

Test Parameters:

Loading - Axial  
Frequency - 2000 to 2500 cpm  
Temperature - RT  
Atmosphere - Air

No. of Heat/Lots: 1

Equivalent Stress Equation:

$$\log N_f = 10.39 - 3.76 \log (S_{eq} - 30.0)$$

$$S_{eq} = S_{max} (1 - R)^{0.62}$$

Standard Error of Estimate = 0.36

Standard Deviation in Life = 1.06

$R^2 = 89\%$

Specimen Details: Notched, V-Groove,  $K_t = 3.3$   
0.450-inch gross diameter  
0.400-inch net diameter  
0.010-inch root radius,  $r$   
60° flank angle,  $\omega$


Sample Size = 11

Surface Condition: Lathe turned to RMS 10

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.3.8(g). Best-fit S/N curves for unnotched AISI 4340 alloy steel bar at 800°F,  $F_{tu} = 150$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(g)

Product Form: Rolled bar, 1-1/8 inches diameter, air melted

Properties: TUS, ksi TYS, ksi Temp., °F

158	147	RT
		(unnotched)
125	101	800
		(unnotched)
190	—	RT
		(notched)
154	—	800
		(notched)

Test Parameters:

Loading - Axial  
Frequency - 2000 to 2500 cpm  
Temperature - 800°F  
Atmosphere - Air

No. of Heat/Lots: 1

Equivalent Stress Equation:

$$\log N_f = 17.53 - 7.35 \log (S_{eq} - 60.0)$$

$$S_{eq} = S_{max} (1 - R)^{0.66}$$

Standard Error of Estimate = 0.42

Standard Deviation in Life = 0.99

$R^2 = 82\%$

Specimen Details: Unnotched  
0.400-inch diameter

Sample Size = 15

Surface Condition: Hand polished to RMS 10


[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

Reference: 2.3.1.3.8(b)



## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.3.8(h). Best-fit S/N curves for notched,  $K_t = 3.3$ , AISI 4340 alloy steel bar at 800°F,  $F_{tu} = 150$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(h)

Product Form: Rolled bar, 1-1/8 inches diameter, air melted

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	158	147	RT
			(unnotched)
	125	101	800
			(unnotched)
	190	—	RT
			(notched)
	154	—	800
			(notched)

Specimen Details: Notched, V-Groove,  $K_t = 3.3$   
 0.450-inch gross diameter  
 0.400-inch net diameter  
 0.010-inch root radius,  $r$   
 60° flank angle,  $\omega$

Surface Condition: Lathe turned to RMS 10

Reference: 2.3.1.3.8(b)

Test Parameters:

Loading - Axial  
 Frequency - 2000 to 2500 cpm  
 Temperature - 800°F  
 Atmosphere - Air


No. of Heat/Lots: 1

Equivalent Stress Equation:

$\log N_f = 7.31 - 2.01 \log (S_{eq} - 48.6)$   
 $S_{eq} = S_{max} (1-R)^{0.92}$   
 Standard Error of Estimate = 0.60  
 Standard Deviation in Life = 1.14  
 $R^2 = 72\%$

Sample Size = 9

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998**

**Figure 2.3.1.3.8(i). Best-fit S/N curves for unnotched AISI 4340 alloy steel bar at 1000°F,  $F_{tu} = 150$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(i)

Product Form: Rolled bar, 1-1/8 inches diameter, air melted

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	158	147	RT
			(unnotched)
	81	63	1000°F
			(unnotched)
	190	—	RT
			(notched)
	98	—	1000°F
			(notched)

Specimen Details: Unnotched  
0.400-inch diameter

Surface Condition: Hand polished to RMS 10

Reference: 2.3.1.3.8(b)

Test Parameters:

Loading - Axial  
Frequency - 2000 to 2500 cpm  
Temperature - 1000°F  
Atmosphere - Air

No. of Heat/Lots: 1

Equivalent Stress Equation:

$\log N_f = 16.85 - 7.02 \log (S_{eq} - 40.0)$

$S_{eq} = S_{max} (1-R)^{0.80}$

Standard Error of Estimate = 0.42

Standard Deviation in Life = 1.20


$R^2 = 88\%$

Sample Size = 13

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.3.8(j). Best-fit S/N curves for notched,  $K_t = 3.3$ , AISI 4340 alloy steel bar at 1000°F,  $F_{tu} = 150$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(j)

Product Form: Rolled bar, 1-1/8 inches diameter, air melted

Properties:

TUS, ksi	TYS, ksi	Temp., °F
158	147	RT
		(unnotched)
81	63	1000°F
		(unnotched)
190	—	RT
		(notched)
98	—	1000°F
		(notched)

Specimen Details: Notched, V-Groove,  $K_t = 3.3$   
0.450-inch gross diameter  
0.400-inch net diameter  
0.010-inch root radius,  $r$   
60° flank angle,  $\omega$

Surface Condition: Lathe turned to RMS 10

Reference: 2.3.1.3.8(b)

Test Parameters:

Loading - Axial  
Frequency - 2000 to 2500 cpm  
Temperature - 1000°F  
Atmosphere - Air


No. of Heat/Lots: 1

Equivalent Stress Equation:

$\log N_f = 9.76 - 3.75 \log (S_{eq} - 30.0)$   
 $S_{eq} = S_{max} (1 - R)^{0.50}$   
Standard Error of Estimate = 0.40  
Standard Deviation in Life = 1.22  
 $R^2 = 89\%$

Sample Size = 12

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998**

**Figure 2.3.1.3.8(k). Best-fit S/N curves for unnotched AISI 4340 alloy steel bar and die forging,  $F_u = 200$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(k)

Product Form: Rolled bar, 1-1/8 inches  
diameter, air melted  
Die forging (landing gear-  
B36 aircraft), air melted

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	208, 221	189, 217	RT (unnotched)
	251	—	RT (notched)

Specimen Details: Unnotched  
0.300 and 0.400-inch diameter

Surface Condition: Hand polished to RMS 5-10

References: 2.3.1.3.8(a) and (c)

Test Parameters:  
Loading - Axial  
Frequency - 2000 to 2500 cpm  
Temperature - RT  
Atmosphere - Air

No. of Heat/Lots: 2


Equivalent Stress Equation:  
 $\log N_f = 9.31 - 2.73 \log (S_{eq} - 93.4)$   
 $S_{eq} = S_{max} (1 - R)^{0.59}$   
Standard Error of Estimate = 0.49  
Standard Deviation in Life = 0.93  
 $R^2 = 72\%$

Sample Size = 26

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.3.8(l). Best-fit S/N curves for notched,  $K_t = 3.3$ , AISI 4340 alloy steel bar,  $F_u = 200$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(l)

Product Form: Rolled bar, 1-1/8 inches diameter, air melted

Properties: TUS, ksi TYS, ksi Temp., °F

208	—	RT
		(unnotched)
251	—	RT
		(notched)

Specimen Details: Notched, V-Groove,  $K_t = 3.3$   
0.450-inch gross diameter  
0.400-inch net diameter  
0.010-inch root radius, r  
60° flank angle,  $\omega$

Surface Condition: Lathe turned to RMS 10

Reference: 2.3.1.3.8(a)

Test Parameters:

Loading - Axial  
Frequency - 2000 to 2500 cpm  
Temperature - RT  
Atmosphere - Air

No. of Heat/Lots: 1

Equivalent Stress Equation:

$$\log N_f = 7.52 - 1.96 \log (S_{eq} - 31.2)$$

$$S_{eq} = S_{max} (1 - R)^{0.65}$$

Standard Error of Estimate = 0.16

Standard Deviation in Life = 0.62

$R^2 = 93\%$


Sample Size = 26

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.3.8(n). Best-fit S/N curves for notched,  $K_t = 2.0$ , AISI 4340 alloy steel bar,  $F_u = 260$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(n)

Product Form: Rolled bar, 1-1/8 inches diameter, air melted

Properties: TUS, ksi TYS, ksi Temp., °F

266	232	RT
		(unnotched)
390	—	RT
		(notched)

Specimen Details: Notched, V-Groove,  $K_t = 3.3$   
0.300-inch gross diameter  
0.220-inch net diameter  
0.030-inch root radius, r  
60° flank angle,  $\omega$

Surface Condition: Lathe turned to RMS 10

Reference: 2.3.1.3.8(a)

Test Parameters:

Loading - Axial  
Frequency - 2000 to 2500 cpm  
Temperature - RT  
Atmosphere - Air


No. of Heat/Lots: 1

Equivalent Stress Equation:

$\log N_f = 9.46 - 2.65 \log (S_{eq} - 50.0)$   
 $S_{eq} = S_{max} (1 - R)^{0.64}$   
Standard Error of Estimate = 0.22  
Standard Deviation in Life = 0.34  
 $R^2 = 58\%$

Sample Size = 30

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998**

**Figure 2.3.1.3.8(o). Best-fit S/N curves for notched,  $K_t = 3.0$ , AISI 4340 alloy steel bar,  $F_{tu} = 260$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.3.8(o)

Product Form: Rolled bar, 1-1/8 inches diameter,  
air melted

Properties: TUS, ksi TYS, ksi Temp., °F

266	232	RT
		(unnotched)
352	—	RT
		(notched)

Specimen Details: Notched, V-Groove,  $K_t = 3.0$   
0.270-inch gross diameter  
0.220-inch net diameter  
0.010-inch root radius, r  
60° flank angle,  $\omega$

Surface Condition: Lathe turned to RMS 10

Reference: 2.3.1.3.8(a)

Test Parameters:

Loading—Axial  
Frequency—2000 to 2500 cpm  
Temperature—RT  
Atmosphere—Air

No. of Heats/Lots: 1

Equivalent Stress Equation:

$\log N_f = 7.14 - 1.74 \log (S_{eq} - 56.4)$   
 $S_{eq} = S_{max} (1-R)^{0.51}$   
Standard Error of Estimate = 0.32  
Standard Deviation in Life = 0.59  
 $R^2 = 71\%$


Sample Size = 29

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.4.8(a). Best-fit S/N curves for unnotched 300M alloy forging,  $F_{tu} = 280$  ksi, longitudinal and transverse directions.**

Correlative Information for Figure 2.3.1.4.8(a)

Product Forms: Die forging, 10 x 20 inches  
CEVM  
Die forging, 6-1/2 x 20 inches  
CEVM  
RCS billet, 6 inches CEVM  
Forged Bar, 1-1/4 x 8 inches  
CEVM

References: 2.3.1.4.8(a), (c), (d), (e)

Test Parameters:

Loading - Axial  
Frequency - 1800 to 2000 cpm  
Temperature - RT  
Atmosphere - Air

Properties: TUS, ksi TYS, ksi Temp., °F  
274-294 227-247 RT

No. of Heat/Lots: 6

Specimen Details: Unnotched  
0.200 - 0.250-inch diameter

Equivalent Stress Equation:

$\log N_f = 14.8 - 5.38 \log (S_{eq} - 63.8)$   
 $S_{eq} = S_a + 0.48 S_m$   
Standard Deviation in Log (Life) = 55.7 (1/ $S_{eq}$ )  
Adjusted  $R^2 = 82.0$


Surface Condition: Heat treat and finish grind to a surface finish of RMS 63 or better with light grinding parallel to specimen length, stress relieve

Sample Size = 104

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.4.8(b). Best-fit S/N curves for unnotched,  $K_t = 2.0$ , 300M alloy forged billet,  $F_{tu} = 280$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.4.8(b)

Product Form: Forged billet, unspecified size,  
CEVM

Properties: TUS, ksi TYS, ksi Temp., °F  
290 242 RT  
(unnotched)  
456 — RT  
(notched)

Specimen Details: Notched, 60° V-Groove,  $K_t = 2.0$   
0.500-inch gross diameter  
0.250-inch net diameter  
0.040-inch root radius,  $r$   
60° flank angle,  $\omega$

Surface Condition: Heat treat and finish grind  
notch to  $RMS\ 63 \pm 5$ ; stress  
relieve

Reference: 2.3.1.4.8(b)

Test Parameters:

Loading - Axial  
Frequency -  
Temperature - RT  
Atmosphere - Air

No. of Heats/Lots: 3

Equivalent Stress Equation:


$\log N_f = 12.87 - 5.08 \log (S_{eq} - 55.0)$   
 $S_{eq} = S_{max} (1-R)^{0.36}$   
Standard Deviation in Life = 0.79  
 $R^2 = 79\%$

Sample Size = 70

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.4.8(c). Best-fit S/N curves for notched,  $K_t = 3.0$ , 300M alloy forging,  $F_{tu} = 280$  ksi, longitudinal and transverse directions.**

Correlative Information for Figure 2.3.1.4.8(c)

Product Forms: Forged billet, unspecified size,  
CEVM

Die forging, 10 x 20 inches,  
CEVM

Die forging, 6-1/2 x 20 inches,  
CEVM

Properties: TUS, ksi TYS, ksi Temp., °F  
290-292 242-247 RT  
(unnotched)  
435 — RT  
(notched)

Specimen Details: Notched 60° V-Groove,  
 $K_t = 3.0$   
0.500-inch gross diameter  
0.250-inch net diameter  
0.0145-inch root radius, r  
60° flank angle,  $\omega$

Surface Condition: Heat treat and finish grind  
notch to RMS 63 or better;  
stress relieve

References: 2.3.1.4.8(a), (b), (c)

Test Parameters:

Loading - Axial

Frequency -

Temperature - RT

Atmosphere - Air

No. of Heats/Lots: 5

Equivalent Stress Equation:

$\log N_f = 10.40 - 3.41 \log (S_{eq} - 20.0)$

$S_{eq} = S_{max} (1-R)^{0.51}$

Standard Deviation in Log (Life) = 18.3 (1/ $S_{eq}$ )


Adjusted  $R^2 = 97.4$

Sample Size = 99

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.3.1.4.8(d). Best-fit S/N curves for notched,  $K_t = 5.0$ , 300M alloy forged billet,  $F_{tu} = 280$  ksi, longitudinal direction.**

Correlative Information for Figure 2.3.1.4.8(d)

Product Forms: Forged billet, unspecified size,  
CEVM

Properties:

TUS, ksi	TYS, ksi	Temp., °F
290	242	RT
		(unnotched)
379	—	RT
		(notched)

Specimen Details: Notched, 60° V-Groove,  
 $K_t = 5.0$   
0.500-inch gross diameter  
0.250-inch net diameter  
0.0042-inch root radius,  $r$   
60° flank angle,  $\omega$

Surface Condition: Heat treat and finish grind  
notch to RMS 63 maximum;  
stress relieve

Reference: 2.3.1.4.8(b)

Test Parameters:

Loading - Axial  
Frequency -  
Temperature - RT  
Atmosphere - Air

No. of Heat/Lots: 2

Equivalent Stress Equation:

$\log N_f = 9.61 - 3.04 \log (S_{eq} - 10.0)$   
 $S_{eq} = S_{max} (1-R)^{0.52}$   
Standard Error of Estimate = 0.28  
Standard Deviation in Life = 0.81  
 $R^2 = 88\%$

Sample Size = 48

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

MIL-HDBK-5H  
1 December 1998





Figure 2.3.1.4.9. Fatigue-crack-propagation data for 3.00-inch hand forging and 1.80-inch thick, 300M steel alloy plate (TUS: 280-290 ksi). [References - 2.3.1.4.9(a) and (b).]

Specimen Thickness: 0.900-1.000 inches  
Specimen Width: 3.09-7.41 inches  
Specimen Type: CT

Environment: Low-humidity air  
Temperature: RT  
Orientation: L-T and T-L

MIL-HDBK-5H  
1 December 1998



**Figure 2.3.1.5.9. Fatigue-crack-propagation data for 0.80-inch D6AC steel alloy plate. Data include material both oil quenched and salt quenched (TUS: 230-240 ksi). [Reference - 2.3.1.5.9.]**

Specimen Thickness: 0.70-0.75 inch  
Specimen Width: 1.5-5.0 inches  
Specimen Type: CT

Environment: Dry air and lab air  
Temperature: RT  
Orientation: L-T

**MIL-HDBK-5H****1 December 1998****2.4 INTERMEDIATE ALLOY STEELS**

**2.4.0 COMMENTS ON INTERMEDIATE ALLOY STEELS** — The intermediate alloy steels in this section are those steels that are substantially higher in alloy content than the alloy steels described in Section 2.3, but lower in alloy content than the stainless steels. Typical of the intermediate alloy steels is the 5Cr-Mo-V aircraft steel and the 9Ni-4Co series of steels.

**2.4.0.1 Metallurgical Considerations** — The alloying elements added to these steels are similar to those used in the lower alloy steels and, in general, have the same effects. The difference lies in the quantity of alloying additions and the extent of these effects. Thus, higher chromium contents provide improved oxidation resistance. Additions of molybdenum, vanadium, and tungsten, together with the chromium, provide deep air-hardening properties and improve the elevated-temperature strength by retarding the rate of tempering at high temperatures. Additions of nickel to nonsecondary hardening steels lower the transition temperature and improve low-temperature toughness.

**2.4.1 5Cr-Mo-V**

**2.4.1.0 Comments and Properties** — Alloy 5Cr-Mo-V aircraft steel exhibits high strength in the temperature range up to 1000°F. Its characteristics also include air hardenability in thick sections; consequently, little distortion is encountered in heat treatment. This steel is available either as air-melted or consumable electrode vacuum-melted quality although only consumable electrode vacuum-melted quality is recommended for aerospace applications.

The heat treatment recommended for this steel consists of heating to 1850°F ± 50, holding 15 to 25 minutes for sheet or 30 to 60 minutes for bars depending on section size, cooling in air to room temperature, tempering three times by heating to the temperature specified in Table 2.4.1.0(a) for the strength level desired, holding at temperature for 2 to 3 hours, and cooling in air.

**Table 2.4.1.0(a). Tempering Temperatures for 5Cr-Mo-V Aircraft Steel**

$F_m$ , ksi	Temperature, °F	Hardness, $R_c$
280	1000 ± 10	54-56
260	1030 ± 10	52-54
240	1050 ± 10	49-52
220	1080 ± 10	46-49

Material specifications for 5Cr-Mo-V aircraft steel are presented in Table 2.4.1.0(b). The room-temperature mechanical and physical properties are shown in Tables 2.4.1.0(c) and (d). The mechanical properties are for 5Cr-Mo-V steel heat treated to produce a structure containing 90 percent or more martensite at the center prior to tempering.


**Table 2.4.1.0(b). Material Specifications for 5Cr-Mo-V Aircraft Steel**

Specification	Form
AMS 6437	Sheet, strip, and plate (air melted)
AMS 6488	Bar and forging (air melted, premium quality)
AMS 6487	Bar and forging (CEVM)

**MIL-HDBK-5H****1 December 1998**

The room-temperature properties of 5Cr-Mo-V aircraft steel are affected by extended exposure to temperatures near or above the tempering temperature. The limiting temperature to which the alloy may be exposed for extended periods without significantly affecting its room-temperature properties may be estimated at 100°F below the tempering temperature for the desired strength level. The effect of temperature on the physical properties is shown in Figure 2.4.1.0.

**2.4.1.1 Heat-Treated Condition** — The effect of temperature on various mechanical properties for heat-treated 5Cr-Mo-V aircraft steel is presented in Figures 2.4.1.1.1(a) through 2.4.1.1.4.



**Figure 2.4.1.0. Effect of temperature on the physical properties of 5Cr-Mo-V aircraft steel.**



**MIL-HDBK-5H****1 December 1998****Table 2.4.1.0(c). Design Mechanical and Physical Properties of 5Cr-Mo-V Aircraft Steel Bar and Forging**

Specification . . . . .	AMS 6487 and AMS 6488		
Form . . . . .	Bars and forgings		
Condition . . . . .	Quenched and tempered		
Cross-sectional area, in. <sup>2</sup> . . . . .	b,c		
Basis . . . . .	S <sup>a</sup>	S <sup>a</sup>	S <sup>a</sup>
Mechanical Properties:			
<i>F<sub>tu</sub></i> , ksi:			
L . . . . .	...	260 <sup>b</sup>	...
T . . . . .	240	260 <sup>c</sup>	280
<i>F<sub>ty</sub></i> , ksi:			
L . . . . .	...	215 <sup>b</sup>	...
T . . . . .	200	215 <sup>c</sup>	240
<i>F<sub>cy</sub></i> , ksi:			
L . . . . .	...	...	...
T . . . . .	220	234	260
<i>F<sub>su</sub></i> , ksi . . . . .	144	156	168
<i>F<sub>bru</sub></i> , ksi:			
(e/D = 1.5) . . . . .	...	...	...
(e/D = 2.0) . . . . .	400	435	465
<i>F<sub>bry</sub></i> , ksi:			
(e/D = 1.5) . . . . .	...	...	...
(e/D = 2.0) . . . . .	315	333	365
<i>e</i> , percent:			
L . . . . .	9	8 <sup>b</sup>	7
T . . . . .	...	...	...
<i>RA</i> , percent:			
L . . . . .	...	30 <sup>b</sup>	...
T . . . . .	...	6 <sup>c</sup>	...
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	30.0		
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	30.0		
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	11.0		
<i>μ</i> . . . . .	0.36		
Physical Properties:			
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.281		
<i>C</i> , Btu/(lb)(°F) . . . . .	0.11 (32°F) <sup>d</sup>		
<i>K</i> and <i>α</i> . . . . .	See Figure 2.4.1.0		

a Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.b Longitudinal properties applicable to cross-sectional area  $\leq 25$  sq. in.

c Transverse properties applicable only to product sufficiently large to yield tensile specimens not less than 4.50 inches in length.

d Calculated value.

**MIL-HDBK-5H****1 December 1998****Table 2.4.1.0(d). Design Mechanical and Physical Properties of 5Cr-Mo-V Aircraft Steel Sheet, Strip, and Plate**


Specification .....	AMS 6437		
Form .....	Sheet, strip, and plate		
Condition .....	Quenched and tempered		
Thickness, in. ....	...		
Basis .....	S <sup>a</sup>	S <sup>a</sup>	S <sup>a</sup>
Mechanical Properties:			
$F_{tu}$ , ksi:			
L .....	...	...	...
LT .....	240	260	280
$F_{ty}$ , ksi:			
L .....	...	...	...
LT .....	200	220	240
$F_{cy}$ , ksi:			
L .....	...	...	...
LT .....	220	240	260
$F_{su}$ , ksi .....	144	156	168
$F_{bru}$ , ksi:			
(e/D = 1.5) .....	...	...	...
(e/D = 2.0) .....	400	435	465
$F_{brγ}$ , ksi:			
(e/D = 1.5) .....	...	...	...
(e/D = 2.0) .....	315	340	365
$e$ , percent:			
L .....	...	...	...
LT, in 2 inches <sup>b</sup> .....	6	5	4
LT, in 1 inch .....	8	7	6
$E$ , 10 <sup>3</sup> ksi .....	30.0		
$E_c$ , 10 <sup>3</sup> ksi .....	30.0		
$G$ , 10 <sup>3</sup> ksi .....	11.0		
$μ$ .....	0.36		
Physical Properties:			
$ω$ , lb/in. <sup>3</sup> .....	0.281		
$C$ , Btu/(lb)(°F) .....	0.11 <sup>c</sup> (32°F)		
$K$ and $α$ .....	See Figure 2.4.1.0		

a Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.


b For sheet thickness greater than 0.050 inch.

c Calculated value.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.4.1.1(a). Effect of temperature on the ultimate tensile strength ( $F_{tu}$ ) of 5Cr-Mo-V aircraft steel.**




**Figure 2.4.1.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 5Cr-Mo-V aircraft steel.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.4.1.1.2(a). Effect of temperature on the compressive yield strength ( $F_{cy}$ ) of 5Cr-Mo-V aircraft steel.**




**Figure 2.4.1.1.2(b). Effect of temperature on the ultimate shear strength ( $F_{su}$ ) of 5Cr-Mo-V aircraft steel.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.4.1.1.3(a). Effect of temperature on the ultimate bearing strength ( $F_{bru}$ ) of 5 Cr-Mo-V aircraft steel.**



**Figure 2.4.1.1.3(b). Effect of temperature on the bearing yield strength ( $F_{bry}$ ) of 5Cr-Mo-V aircraft steel.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.4.1.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of 5Cr-Mo-V aircraft steel.**

**MIL-HDBK-5H****1 December 1998****2.4.2 9Ni-4Co-0.20C**

**2.4.2.0 Comments and Properties** — The 9Ni-4Co-0.20C alloy was developed specifically to have excellent fracture toughness, excellent weldability, and high hardenability when heat-treated to 190 to 210 ksi ultimate tensile strength. The alloy can be readily welded in the heat-treated condition with preheat and post-heat usually not required. The alloy is through hardening in section sizes up to at least 8 inches thick. The alloy may be exposed to temperatures up to 900°F (approximately 100°F below typical tempering temperature) without microstructural changes which degrade room temperature strength.

The heat treatment for this alloy consists of normalizing at  $1650 \pm 25^\circ\text{F}$  for 1 hour per inch of cross section, cooling in air to room temperature, heating to  $1525 \pm 25^\circ\text{F}$  for 1 hour per inch of cross section, quenching in oil or water, hold at  $-100 \pm 20^\circ\text{F}$  for 2 hours within 2 hours after quenching, and double tempering at  $1035 \pm 10^\circ\text{F}$  for 2 hours.

A material specification for 9Ni-4Co-0.20C steel is presented in Table 2.4.2.0(a). Room temperature mechanical and physical properties are shown in Table 2.4.2.0(b). The effect of temperature on thermal expansion is shown in Figure 2.4.2.0.

**Table 2.4.2.0(a). Material Specification for 9Ni-4Co-0.20C Steel**

Specification	Form
AMS 6523	Sheet, strip, and plate

**2.4.2.1 Heat-Treated Condition** — Effect of temperature on various mechanical properties is presented in Figures 2.4.2.1.1, 2.4.2.1.2, and 2.4.2.1.4. Typical tensile stress-strain curves at room and elevated temperatures are shown in Figure 2.4.2.1.6(a). Typical compression stress-strain and tangent-modulus curves are presented in Figure 2.4.2.1.6(b).


**MIL-HDBK-5H****1 December 1998****Table 2.4.2.0(b). Design Mechanical and Physical Properties of 9Ni-4Co-0.20C Steel Plate**

Specification .....	AMS 6523	
Form .....	Plate	
Condition .....	Quenched and tempered	
Thickness, in. ....	<0.250	≥0.250
Basis .....	S <sup>a</sup>	S <sup>a</sup>
Mechanical Properties:		
$F_{tu}$ , ksi:		
L .....	186	186
LT .....	190	190
$F_{ty}$ , ksi:		
L .....	173	173
LT .....	175	175
$F_{cy}$ , ksi:		
L .....	188	188
LT .....	187	187
$F_{su}$ , ksi .....	114	114
$F_{bru}$ , ksi:		
(e/D = 1.5) .....	...	...
(e/D = 2.0) .....	...	...
$F_{bry}$ , ksi:		
(e/D = 1.5) .....	...	...
(e/D = 2.0) .....	...	...
$e$ , percent:		
LT .....	5	10
$RA$ , percent:		
LT .....	45	45
$E$ , 10 <sup>3</sup> ksi .....	28.8	
$E_c$ , 10 <sup>3</sup> ksi .....	28.8	
$G$ , 10 <sup>3</sup> ksi .....	11.1	
$\mu$ .....	0.30	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> .....	0.283	
$C$ , Btu/(lb)(°F) .....	...	
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	14.2 (75°F)	
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	See Figure 2.4.2.0	


a Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.



**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.4.2.0. Effect of temperature on the thermal expansion of 9Ni-4Co-0.20C steel.**




**Figure 2.4.2.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and tensile yield strength ( $F_{ty}$ ) of 9Ni-4Co-0.20C steel plate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.4.2.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of 9Ni-4Co-0.20C steel plate.**




**Figure 2.4.2.1.4. Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of 9Ni-4Co-0.20C steel plate.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.4.2.1.6(a). Typical tensile stress-strain curves for 9Ni-4Co-0.20C steel plate at various temperatures.**



**Figure 2.4.2.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 9Ni-4Co-0.20C steel plate at various temperatures.**

**MIL-HDBK-5H****1 December 1998****2.4.3 9Ni-4Co-0.30C**

**2.4.3.0 Comments and Properties** — The 9Ni-4Co-0.30C alloy was developed specifically to have high hardenability and good fracture toughness when heat treated to 220 to 240 ksi ultimate tensile strength. The alloy is through hardening in section sizes up to 4 inches thick. The alloy may be exposed to temperatures up to 900°F (approximately 100°F below typical tempering temperature) without microstructural changes which degrade room temperature strength. This grade must be formed and welded in the annealed condition. Preheat and post-heat of the weldment is required. The steel is produced by consumable electrode vacuum melting.

The heat treatment for this alloy consists of normalizing at  $1650 \pm 25^\circ\text{F}$  for 1 hour per inch of cross section, cooling in air to room temperature, heating to  $1550 \pm 25^\circ\text{F}$  for 1 hour per inch of cross section but not less than 1 hour, quenching in oil or water, subzero treating at  $-100^\circ\text{F}$  for 1 to 2 hours, and double tempering at  $975 \pm 10^\circ\text{F}$  (sheet, strip, and plate) or  $1000 \pm 10^\circ\text{F}$  (bars, forgings, and tubings) for 2 hours.

Material specifications for 9Ni-4Co-0.30C steel are presented in Table 2.4.3.0(a). The room temperature mechanical and physical properties are shown in Table 2.3.4.0(b). The effect of temperature on thermal expansion is shown in Figure 2.4.3.0.

**Table 2.4.3.0(a). Material Specifications for 9Ni-4Co-0.30C Steel**

Specification	Form
AMS 6524	Sheet, strip, and plate
AMS 6526	Bar, forging, and tubing

**2.4.3.1 Heat-Treated Condition** — Effect of temperature on various mechanical properties is presented in Figures 2.4.3.1.1. through 2.4.3.1.4. Typical stress-strain and tangent-modulus curves are presented in Figures 2.4.3.1.6(a) through (d). Notched fatigue data at room temperature are illustrated in Figure 2.4.3.1.8.

## MIL-HDBK-5H

1 December 1998


**Table 2.4.3.0(b). Design Mechanical and Physical Properties of 9Ni-4Co-0.30C Steel**

Specification .....	AMS 6524		AMS 6526
Form .....	Sheet, strip, and plate		Bar, forging, and tubing
Condition .....	Quenched and tempered		Quenched and tempered
Thickness, in. ....	$\leq 0.249$	$\geq 0.250$	$\leq 4.000$
Basis .....	S <sup>a</sup>	S <sup>a</sup>	S <sup>a</sup>
Mechanical Properties:			
$F_{tu}$ , ksi:			
L .....	...	...	220
LT .....	220	220	...
$F_{ty}$ , ksi:			
L .....	...	...	190
LT .....	185	190	...
$F_{cy}$ , ksi:			
L .....	...	...	209
LT .....	...	209	...
$F_{su}$ , ksi .....	...	137	137
$F_{bru}^b$ , ksi:			
(e/D = 1.5) .....	...	346	346
(e/D = 2.0) .....	...	440	440
$F_{bry}^b$ , ksi:			
(e/D = 1.5) .....	...	291	291
(e/D = 2.0) .....	...	322	322
$e$ , percent:			
L .....	...	...	10
LT .....	6	10	...
$RA$ , percent:			
L .....	...	...	40
LT .....	...	35	...
$E$ , $10^3$ ksi .....	28.5		
$E_c$ , $10^3$ ksi .....	29.8		
$G$ , $10^3$ ksi .....	...		
$\mu$ .....	...		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> .....	0.28		
$C$ , Btu/(lb)(°F) .....	...		
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	13.3 (75°F)		
$\alpha$ , $10^{-6}$ in./in./°F .....	See Figure 2.4.3.0		

a Design values are applicable only to parts for which the indicated  $F_{tu}$  has been substantiated by adequate quality control testing.


b Bearing values are “dry pin” values per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.4.3.0. Effect of temperature on the thermal expansion of 9Ni-4Co-0.30C steel.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.4.3.1.1. Effect of temperature on the tensile yield strength ( $F_{ty}$ ) and the tensile ultimate strength of 9Ni-4Co-0.30C steel hand forging.**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.4.3.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of 9Ni-4Co-0.30C steel hand forging.**




**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.4.3.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of 9Ni-4Co-0.30C steel hand forging.**


**MIL-HDBK-5H****1 December 1998**

**Figure 2.4.3.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of 9Ni-4Co-0.30C steel.**

**MIL-HDBK-5H****1 December 1998**


**Figure 2.4.3.1.6(a). Typical compressive stress-strain and compressive tangent-modulus curves for 9Ni-4Co-0.30C steel hand forging at various temperatures.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.4.3.1.6(b). Typical tensile stress-strain curves (full range) for 9Ni-4Co-0.30C hand forging at various temperatures.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.4.3.1.6(c). Typical tensile stress-strain curves (full range) for 9Ni-4Co-0.30C hand forging at various temperatures.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.4.3.1.6(d). Typical tensile stress-strain curves (full range) for 9Ni-4Co-0.30C hand forging at various temperatures.**

## MIL-HDBK-5H

1 December 1998



**Figure 2.4.3.1.8. Best-fit S/N curves for notched,  $K_t = 3.0$ , 9Ni-4Co-0.30C steel hand forging, long and short transverse directions.**

Correlative Information for Figure 2.4.3.1.8

Product Form: Hand forging, 3 x 9 inches

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial  
Frequency - 1800 cpm  
Temperature - RT  
Environment - Air

231 197 RT (LT)

Specimen Details: Notched, V-Groove  $K_t=3.0$   
0.354-inch gross diameter  
0.250-inch net diameter  
0.01-inch root radius  
60° flank angle,  $\omega$

No. of Heats/Lots: 3

Equivalent Stress Equation:

$$\log N_f = 7.77 - 2.15 \log (S_{eq} - 28.32)$$

$$S_{eq} = S_{max} (1-R)^{0.79}$$

Standard Error of Estimate = 0.12

Standard Deviation in Life = 0.47

$R^2 = 93\%$

Surface Condition: Not specified

Reference: 2.4.3.1.8

Sample Size = 22

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998**

## **2.5 HIGH-ALLOY STEELS**

**2.5.0 COMMENTS ON HIGH-ALLOY STEELS** — The high-alloy steels in this section are those steels that are substantially higher in alloy content than the intermediate alloy steels described in Section 2.4 but are not stainless steels. The 18 Ni maraging and AF1410 steels are in this category.

**2.5.0.1 Metallurgical Considerations** — The 18 Ni maraging steels are iron base alloys with nominally 18 percent nickel, 7 to 9 percent cobalt, 3 to 5 percent molybdenum, less than 1 percent titanium, and very low carbon content, below 0.03 percent. Upon cooling from the annealing or hot-working temperature, these steels transform to a soft martensite which can be easily machined or formed. The steels can be subsequently aged (maraged) to high strengths by heating to a lower temperature, 900 °F.


AF1410 is an iron base alloy with nominally 14 percent cobalt, 10 percent nickel, 2 percent chromium, 1 percent molybdenum, and 0.15 percent carbon. When quenched from austenitizing temperatures, AF1410 forms a highly dislocated lath martensitic structure with very little twinning or retained austenite. At aging temperatures ranging from 900 to 1000 °F, a precipitation of extremely fine alloy carbide containing chromium and molybdenum occurs, which simultaneously develops strength and toughness properties.

**2.5.0.2 Environmental Considerations** — The stress corrosion cracking resistance of high strength steels is of concern for highly loaded structural components such as landing gears and wing attach fittings that are subjected to corrosive environments such as sea spray or water. Figure 2.5.0.2(a) indicates the relative stress corrosion cracking resistance of several high-strength steel alloys. The data in this figure were obtained from Reference (2.5.0.2). The stress corrosion cracking threshold stress intensity ( $K_{Isc}$ ) for each steel was defined as the value at which cracking did not occur. For most of these alloys, this value is about 20 ksi $\sqrt{\text{in}}$ . As indicated, there is a definite difference in the stress corrosion resistance between the alloys.

In general, the high-strength steels do not reach a true threshold stress intensity until after 1000 hours of exposure. The highest stress corrosion cracking resistance in high-strength steels is associated with low carbon levels and lath martensite microstructure containing a fine distribution of  $M_2C$  type carbides; alloys AF1410 and AerMet 100. The effect of low carbon is indicated between the AF1410 and 0.20AF1410 where the carbon levels are 0.15 and 0.20%, respectively. The lower stress cracking corrosion resistance is associated with higher carbon and the martensite is of plate morphology that exhibits a twinned structure; alloys 4340 and 300M. A slight anisotropic effect was observed for Hy-Tuf (TL vs LT); however, the effect was not apparent for AF1410. The differences in anisotropic properties may be due to differences in the cleanliness of the steels since Hy-Tuf was an air melted product and the others were either vacuum induction melted (VIM) or electroslag remelted (ESR).



**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.5.0.2(a). The relative stress corrosion cracking resistance of several high-strength steels tested in an environment of 3.5% NaCl (Reference 2.5.0.2).**

**MIL-HDBK-5H****1 December 1998****2.5.1 18 Ni MARAGING STEELS**

**2.5.1.0 Comments and Properties** — The 250 and 280 (300) maraging steels are normally supplied in the annealed condition and are heat treated to high strengths, without quenching, by aging at 900°F. The steels are characterized by high hardenability and high strength combined with good toughness. The 250 and 280 (300) designation refers to the nominal yield strengths of the two alloys. The two alloys are available in the form of sheet, plate, bar, and die forgings. Only the consumable electrode-vacuum-melted quality grades are considered in this section.

*Manufacturing Considerations* — The 250 and 280 grades are readily hot worked by conventional rolling and forging operations. These grades also have good cold forming characteristics in spite of the relatively high hardness in the annealed (martensitic) condition. The machinability of the 250 and 280 grades is not unlike 4330 steel at equivalent hardness. The 18 Ni maraging steels can be readily welded in either the annealed or aged conditions without preheating. Welding of aged material should be followed by aging at 900°F to strengthen the weld area.

*Environmental Considerations* — Although the 18 Ni maraging steels are high in alloy content, these grades are not corrosion resistant. Since the general corrosion resistance is similar to the low-alloy steels, these steels require protective coatings. The 250 grade reportedly has better resistance to stress corrosion cracking than the low-alloy steels at the same strength.

*Specifications and Properties* — Material specifications for these steels are shown in Table 2.5.1.0(a). The room temperature properties for material aged at 900°F are shown in Tables 2.5.1.0(b) and (c), and the effect of temperature on physical properties is shown in Figure 2.5.1.0.

**Table 2.5.1.0(a). Material Specifications for 18 Ni Maraging Steels**

Grade	Specification	Form
250	AMS 6520	Sheet and plate
250	AMS 6512	Bar
280 (300)	AMS 6521	Sheet and plate
280 (300)	AMS 6514	Bar

**2.5.1.1 Maraged Condition (aged at 900 °F)** — Effect of temperature on 250 and 280 grade maraging steel is presented in Figures 2.5.1.1.1 through 2.5.1.1.4. Figures 2.5.1.1.6(a) and (b) are room and elevated temperature tensile stress-strain curves. Typical compressive stress-strain and tangent-modulus curves at room temperature are presented in Figures 2.5.1.1.6(c) and (d). Figure 2.5.1.1.6(e) is a full-range stress-strain curve at room temperature for 280 grade maraging steel.

**MIL-HDBK-5H****1 December 1998****Table 2.5.1.0(b). Design Mechanical and Physical Properties of 250 Maraging Steel**

AMS 6520 Mechanical and Physical Properties of Low Maraging Steel					
Specification	AMS 6520			AMS 6512	
Form	Sheet	Plate		Bar	
Condition	Maraged at 900°F			Maraged at 900°F	
Thickness or diameter, in.	≤0.187	0.187-0.250	>0.250	<4.000	4.000-10.000
Basis	S	S	S	S	S
Mechanical Properties:					
$F_{tu}$ ksi:					
L	247	252	...	255	245
T	255	255	255	255	245
$F_{ty}$ ksi:					
L	238	242	...	250	240
T	245	245	245	250	240
$F_{cy}$ ksi:					
L	221	...	...	260	...
T	225	255	...	...	...
$F_{su}$ ksi	148	155	...	148	...
$F_{bru}$ ksi:					
(e/D = 1.5)	327	352	...	...	...
(e/D = 2.0)	444	448	...	...	...
$F_{bry}$ ksi:					
(e/D = 1.5)	278	324	...	...	...
(e/D = 2.0)	353	354	...	...	...
$e$ , percent:					
L	...	...	...	6	5
T	a	a	a	4	3
$RA$ , percent:					
L	...	...	...	45	30
T	...	...	...	35	20
$E$ , 10 <sup>3</sup> ksi	26.5				
$E_c$ , 10 <sup>3</sup> ksi:					
L	28.2				
T	29.4				
$G$ , 10 <sup>3</sup> ksi	...				
$\mu$	0.31				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup>	0.286				
$C$ , $K$ , and $\alpha$	See Figure 2.5.1.0				

a Elongation properties vary with thickness as follows:

≤0.090	2.5%
0.091-0.125	3.0%
0.126-0.250	4.0%
0.251-0.375	5.0%
≥0.376	6.0%


**MIL-HDBK-5H****1 December 1998****Table 2.5.1.0(c). Design Mechanical and Physical Properties of 280 Maraging Steel**

Specification	AMS 6521			AMS 6514	
Form	Sheet	Plate		Bar	
Condition	Maraged at 900°F			Maraged at 900°F	
Thickness or diameter, in.	≤0.187	0.188-0.250	>0.250	<4.000	4.000-10.000
Basis	S	S	S	S	S
Mechanical Properties:					
$F_{tu}$ ksi:					
L	271	276	...	280	275
T	280	280	280	280	275
$F_{ty}$ ksi:					
L	262	267	...	270	270
T	270	270	270	270	270
$F_{cy}$ ksi:					
L	244	...	...	281	...
T	248	281	...	...	...
$F_{su}$ ksi	163	170	...	162	...
$F_{bru}$ ksi:					
(e/D = 1.5)	359	386	...	...	...
(e/D = 2.0)	487	492	...	...	...
$F_{bry}$ ksi:					
(e/D = 1.5)	306	357	...	...	...
(e/D = 2.0)	389	390	...	...	...
$e$ , percent:					
L	...	...	...	5	4
T	a	a	a	4	2
$RA$ , percent:					
L	...	...	...	30	25
T	...	...	...	25	20
$E$ , 10 <sup>3</sup> ksi	26.5				
$E_c$ , 10 <sup>3</sup> ksi:					
L	28.6				
T	29.6				
$G$ , 10 <sup>3</sup> ksi	...				
$\mu$	0.31				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup>	0.286				
$C$ , $K$ , and $\alpha$	See Figure 2.5.1.0				

a Elongation properties vary with thickness as follows:


≤0.090	2.5%
0.091-0.125	3.0%
0.126-0.250	4.0%
0.251-0.375	5.0%
≥0.376	6.0%

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.5.1.0. Effect of temperature on the physical properties of 250 and 280 maraging steels.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.5.1.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of 250 and 280 maraging steel sheet and plate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.5.1.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of 250 and 280 maraging steel sheet and plate.**



**Figure 2.5.1.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of 250 and 280 maraging steel sheet and plate.**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.5.1.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of 250 and 280 maraging steel.**




**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.5.1.1.6(a). Typical tensile stress-strain curves at room and elevated temperatures for 250 maraging steel bar.**




**Figure 2.5.1.1.6(b). Typical tensile stress-strain curves at room and elevated temperatures for 280 maraging steel bar.**

**MIL-HDBK-5H****1 December 1998**


**Figure 2.5.1.1.6(c). Typical compressive stress-strain and compressive tangent-modulus curves for 250 maraging steel bar at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.5.1.1.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for 280 maraging steel bar at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.5.1.1.6(e). Typical tensile stress-strain curve (full range) for 280 maraging steel bar at room temperature.**

**MIL-HDBK-5H****1 December 1998****2.5.2 AF1410**

**2.5.2.0 Comments and Properties** — AF1410 alloy was developed specifically to have high strength, excellent fracture toughness, and excellent weldability when heat treated to 235 to 255 ksi ultimate tensile strength. AF1410 has good weldability and does not require preheating prior to welding. The alloy maintains good toughness at cryogenic temperatures, as well as high strength and stability at temperatures up to 800°F. The alloy is available in a wide variety of sizes and forms, including billet, bar, plate, and die forgings. The alloy is produced by vacuum induction melting followed by vacuum remelting.

**Heat Treatment** — The heat treatment for this alloy consists of heating to  $1650 \pm 25^\circ\text{F}$  for 1 hour, forced-air cooling to room temperature, reheating to  $1525 \pm 25^\circ\text{F}$  for 1 hour, forced-air cooling to room temperature, cooling to  $-100 \pm 15^\circ\text{F}$ , holding at temperature for 1 hour, warming to room temperature, and aging at  $950 \pm 10^\circ\text{F}$  for 5 hours, and air cooling. A forced-air cool from austenitizing temperatures should be used for section thicknesses up to 2 inches. For sections of greater thickness, an oil quench should be utilized. A single austenitizing treatment ( $1525 \pm 25^\circ\text{F}$ ) can be used to minimize heat treating distortion with a resulting slight decrease in fracture toughness.

**Environmental Considerations** — AF1410 has general corrosion resistance similar to the maraging steels. It should not be used in the unprotected condition. The alloy is highly resistant to stress-corrosion cracking compared to other high-strength steels.

**Specification and Properties** — A material specification for AF1410 is presented in Table 2.5.2.0(a). Room temperature mechanical properties are shown in Table 2.5.2.0(b).

**Table 2.5.2.0(a). Material Specification for AF1410 Steel**

Specification	Form
AMS 6527	Bar and forging

**2.5.2.1 Heat-Treated Condition** — Typical stress-strain curves at room temperature are shown in Figures 2.5.2.1.6(a) and (b).

**MIL-HDBK-5H****1 December 1998****Table 2.5.2.0(b). Design Mechanical and Physical Properties of AF1410 Steel Bar**

Specification . . . . .	AMS 6527
Form . . . . .	Bar
Condition . . . . .	a
Cross-sectional area, sq. in. . . . .	$\leq 100^b$
Thickness or diameter, in. . . . .	$\leq 4.25^b$
Basis . . . . .	S
Mechanical Properties:	
$F_{tu}$ , ksi:	
L . . . . .	235
LT <sup>c</sup> . . . . .	235
ST <sup>c</sup> . . . . .	235
$F_{ty}$ , ksi:	
L . . . . .	215
LT <sup>c</sup> . . . . .	215
ST <sup>c</sup> . . . . .	215
$F_{cy}$ , ksi:	
L . . . . .	223
ST <sup>c</sup> . . . . .	225
$F_{su}$ , ksi . . . . .	141
$F_{bru}$ , ksi:	
(e/D = 1.5) . . . . .	334
(e/D = 2.0) . . . . .	435
$F_{bry}$ , ksi:	
(e/D = 1.5) . . . . .	269
(e/D = 2.0) . . . . .	300
$e$ , percent:	
L . . . . .	12
LT <sup>c</sup> . . . . .	12
ST <sup>c</sup> . . . . .	12
$RA$ , percent:	
L . . . . .	60
LT <sup>c</sup> . . . . .	55
ST <sup>c</sup> . . . . .	55
$E$ , $10^3$ ksi . . . . .	29.4
$E_c$ , $10^3$ ksi . . . . .	30.9
$G$ , $10^3$ ksi . . . . .	...
$\mu$ . . . . .	...
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.283
$C$ , $K$ , and $\alpha$ . . . . .	...

a Heat at  $1650 \pm 25^\circ\text{F}$  for one hour, forced-air cool to room temperature, heat at  $1525 \pm 25^\circ\text{F}$  for one hour, forced-air cool to room temperature, cool at  $-100 \pm 15^\circ\text{F}$  for one hour, age at  $950 \pm 10^\circ\text{F}$  for 5 hours, and air cool.

b Maximum size from which test specimens were rough machined prior to heat treatment.

c Applicable providing LT or ST dimension is  $\geq 2.500$  inches.

MIL-HDBK-5H  
1 December 1998




Figure 2.5.2.1.6(a). Typical tensile stress-strain curves at room temperature for heat-treated AF1410 steel bar.




Figure 2.5.2.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves at room temperature for heat-treated AF1410 steel bar.

**MIL-HDBK-5H****1 December 1998****2.5.3 AERMet 100**

**2.5.3.0 Comments and Properties** — AerMet 100 is a higher strength derivative of AF1410. The Ni-Co-Fe alloy can be heat treated to 280-300 ksi or to 290-310 ksi tensile strength while exhibiting excellent fracture toughness and high resistance to stress-corrosion cracking. AerMet 100 has good weldability and does not require preheating prior to welding. AerMet 100 is available in a wide variety of sizes and forms including billet, bar, sheet, strip, plate, wire, and die forgings. The alloy is produced by vacuum induction melting followed by vacuum-arc remelting.

**Heat Treatment** — The heat treatment for this alloy consists of heating to  $1625 \pm 25^\circ\text{F}$ , holding for  $60 + 15, -0$  minutes, cooling to  $-100 \pm 15^\circ\text{F}$ , holding for  $60 \pm 5$  minutes, warming in air to room temperature. Parts over 1.25 inches in thickness shall be oil quenched from  $1625^\circ\text{F}$ . Parts  $\leq 1.25$  inches in thickness may be cooled in air from  $1625^\circ\text{F}$ . To achieve the 280-300 ksi tensile strength, aging is conducted at  $900 \pm 10^\circ\text{F}$  for 5 to 8 hours and subsequently cooled in air. To achieve the 290-310 ksi tensile strength, aging is conducted at  $875 \pm 10^\circ\text{F}$  for 5 to 8 hours and subsequently cooled in air.

**Environmental Considerations** — AerMet 100 is not considered corrosion resistant; consequently, parts should be protected with a corrosion resistant coating. The alloy is highly resistant to stress corrosion cracking compared to other high-strength steels of the same strength level.

This alloy displays good toughness at cryogenic temperatures as well as high strength and stability at temperatures up to  $800^\circ\text{F}$ .

**Specification and Properties** — A material specification for AerMet 100 is shown in Table 2.5.3.0(a). Room temperature mechanical properties are presented in Table 2.5.3.0(b) for both heat treated conditions.

**Table 2.5.3.0(a). Material Specification for AerMet 100 Steel**

Specification	Form
AMS 6532	Bar and forging
AMS 6478	Bar and forging

**2.5.3.1 280-300 ksi Heat-Treated Condition** — Typical stress-strain curves at room temperature are shown in Figures 2.5.3.1.6(a) and (b). A full-range tensile stress-strain curve is presented in Figure 2.5.3.1.6(c).

**2.5.3.2 290-310 ksi Heat-Treated Condition** — Typical tensile and compression stress-strain curves and compression tangent-modulus curves at room temperature are shown in Figures 2.5.3.2.6(a) and (b). A full-range tensile stress-strain curve is presented in Figure 2.5.3.2.6(c).




**MIL-HDBK-5H****1 December 1998****Table 2.5.3.0(b). Design Mechanical and Physical Properties of AerMet 100 Steel Bar**

Specification . . . . .	AMS 6532	AMS 6478
Form . . . . .	Bar and forging	
Condition . . . . .	Solution treated and aged	
Cross-sectional area, in. <sup>2</sup> . .	≤ 100	
Thickness or diameter, in. . .	≤ 10.000	
Basis . . . . .	S	S
Mechanical Properties:		
$F_{tu}$ , ksi:		
L . . . . .	280	290
LT <sup>a</sup> . . . . .	280	290
ST <sup>a</sup> . . . . .	280	290
$F_{ty}$ , ksi:		
L . . . . .	235	245
LT <sup>a</sup> . . . . .	235	245
ST <sup>a</sup> . . . . .	235	245
$F_{cy}$ , ksi:		
L . . . . .	262	281
ST <sup>a</sup> . . . . .	263	279
$F_{su}$ , ksi . . . . .	175	182
$F_{bru}^b$ , ksi:		
(e/D = 1.5) . . . . .	433	448
(e/D = 2.0) . . . . .	571	581
$F_{bry}^b$ , ksi:		
(e/D = 1.5) . . . . .	361	378
(e/D = 2.0) . . . . .	411	442
$e$ , percent:		
L . . . . .	10	10
LT <sup>a</sup> . . . . .	8	8
ST <sup>a</sup> . . . . .	8	8
$RA$ , percent:		
L . . . . .	55	50
LT <sup>a</sup> . . . . .	45	35
ST <sup>a</sup> . . . . .	45	35
$E$ , 10 <sup>3</sup> ksi . . . . .	28.0	
$E_c$ , 10 <sup>3</sup> ksi . . . . .	28.1	
$G$ , 10 <sup>3</sup> ksi . . . . .	...	
$\mu$ . . . . .	...	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.285	
$C$ , $K$ , and $\alpha$ . . . . .	...	


a Applicable providing LT or ST dimension is ≤2.500 inches.

b Bearing values are "dry pin" values per Section 1.4.7.1.


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.5.3.1.6(a). Typical tensile stress-strain curve at room temperature for AerMet 100 steel bar, heat treated to 280-300 ksi.**

**MIL-HDBK-5H****1 December 1998**


**Figure 2.5.3.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves at room temperature for AerMet 100 steel bar, heat treated to 280-300 ksi.**



**Figure 2.5.3.1.6(c). Typical tensile stress-strain curve (full range) at room temperature for AerMet 100 steel bar, heat treated to 280-300 ksi.**


**MIL-HDBK-5H****1 December 1998**

**Figure 2.5.3.2.6(a). Typical tensile stress-strain curve at room temperature for AerMet 100 steel bar, heat treated to 290-310 ksi.**

**MIL-HDBK-5H****1 December 1998**

**Figure 2.5.3.2.6(b). Typical compressive stress-strain and compressive tangent-modulus curves at room temperature for AerMet 100 steel bar, heat treated to 290-310 ksi.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.5.3.2.6(c). Typical tensile stress-strain curve (full range) at room temperature for AerMet 100 steel bar, heat treated to 290-310 ksi.**

**MIL-HDBK-5H****1 December 1998****2.6 PRECIPITATION AND TRANSFORMATION-HARDENING STEELS (STAINLESS)****2.6.0 COMMENTS ON PRECIPITATION AND TRANSFORMATION-HARDENING STEELS (STAINLESS)**

**2.6.0.1 Metallurgical Considerations** — The transformation and precipitation-hardening stainless steels are martensitic or semiaustenitic stainless steels that are hardenable by heat treatment.\* The martensitic alloys require only a single step heat treatment to develop maximum strength. The others are austenitic in the fully annealed condition but become martensitic during subsequent heat treatment or as a result of extensive cold working. During a final heat treatment designed to temper the martensite, several of these steels are hardened further by the precipitation of copper, aluminum, or titanium.

Some dimensional change may be experienced during the heat treatment of the semiaustenitic steels. A dimensional expansion of approximately 0.0045-in./in. occurs during the transformation from the austenitic to the martensitic condition; during aging, a contraction of about 0.0005-in./in. takes place.

**2.6.0.2. Manufacturing Considerations** — The martensitic precipitation-hardening steels, before age hardening, are similar to the straight-chromium martensitic stainless steels (Type 410 or 431) in their general fabricating characteristics. The semiaustenitic grades, in the annealed condition, are similar to the austenitic stainless steels (Types 301, etc.) in this respect, and are readily cold formed. Forming of hardened steels after final heat treatment should be avoided.

These alloys can be welded by the conventional methods used for the austenitic stainless steels. Inert-gas-shielded welding is recommended to prevent the loss of titanium or aluminum in certain of these alloys. Postweld annealing is recommended for some grades.

The heat treatments for these steels are compatible with the cycles used for honeycomb panel brazing. Vapor blasting of scaled parts, after final heat treatment, is recommended because of the hazards of intergranular corrosion in inadequately controlled acids pickling operations.

**2.6.0.3 Environmental Considerations** — The precipitation-hardening stainless steels have good strength and oxidation and corrosion resistance in their service range. Prolonged exposures above 600°F and below the tempering range may cause further hardening, with possible decrease in ductility. Prolonged exposures in or above the temperature range result in loss of strength due to overtempering, overaging, or reaustenizing.

**2.6.1 AM-350**

**2.6.1.0 Comments and Properties** — AM-350 has high strength up to 800°F and good oxidation resistance up to about 1000°F. The alloy can be hardened by subzero cooling and tempering (Condition SCT).

*Manufacturing Considerations* — AM-350 is readily formed, welded, and brazed. Its forming characteristics are similar to the AISI 300 series stainless steels; however, it does have a higher rate of strain hardening. When fabricating AM-350 in the annealed condition, proper design allowance must be made for growth which occurs upon hardening. To obtain proper response to the SCT treatment after welding, the alloy must be reannealed.

---

\* Heat treating procedures for these steels are specified in MIL-H-6875 and are further described in producers' literature.



**MIL-HDBK-5H****1 December 1998**

*Environmental Considerations* — AM-350 shows good corrosion-resisting properties in ordinary atmospheres and also in a number of chemical environments. Exposure in the 600 to 800°F range for 1,000 hours at stress levels below the short-time yield strength tends to increase room-temperature yield strength and room-temperature tensile strength slightly. Exposure to 800°F results in a decrease in elongation. Typical data are presented in Table 2.6.1.0(a).

**Table 2.6.1.0(a). Effect of Elevated Temperature Exposure on Typical Tensile Properties of AM-350 Alloy in the SCT 850 Condition**

Exposure temperature, °F	Exposure stress, ksi	Exposure time, hr	Room-temperature properties		
			TUS, ksi	TYS, ksi	e, %
RT .....	...	...	201	158	12.0
600 .....	60	1,000	198	162	14.0
700 .....	60	1,000	204	169	11.0
800 .....	60	1,000	220	190	7.0
600 .....	90	1,000	202	177	13.0
700 .....	90	1,000	206	180	11.0
800 .....	90	1,000	214	192	7.0

*Specifications and Properties* — A material specification for AM-350 stainless steel is presented in Table 2.6.1.0(b). The room-temperature properties of AM-350 in the SCT 850 condition are shown in Table 2.6.1.0(c). Figure 2.6.1.0 presents elevated temperature physical property information.

**Table 2.6.1.0(b). Material Specifications for AM-350 Stainless Steel**

Specification	Form
AMS 5548	Sheet and strip

**2.6.1.1 SCT 850 Condition** — Effect of temperature on various mechanical properties of AM-350 is presented in Figures 2.6.1.1.1 through 2.6.1.1.4. Typical stress-strain and tangent-modulus curves at several temperatures are shown in Figures 2.6.1.1.6(a) and (b).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 2.6.1.0(c). Design Mechanical and Physical Properties  
of AM-350 Stainless Steel Sheet and Strip**

Specification . . . . .	AMS 5548
Form . . . . .	Sheet and strip <sup>a</sup>
Condition . . . . .	SCT 850
Thickness, in. . . . .	≤ 0.187
Basis . . . . .	S
<b>Mechanical Properties:</b>	
$F_{tu}$ , ksi:	
L . . . . .	183
LT . . . . .	185
$F_{ty}$ , ksi:	
L . . . . .	147
LT . . . . .	150
$F_{cy}$ , ksi:	
L . . . . .	163
LT . . . . .	...
$F_{su}$ , ksi . . . . .	121
$F_{bru}$ , ksi:	
(e/D = 1.5) . . . . .	...
(e/D = 2.0) . . . . .	373
$F_{bry}$ , ksi:	
(e/D = 1.5) . . . . .	...
(e/D = 2.0) . . . . .	252
$e$ , percent: . . . . .	
LT . . . . .	10 <sup>b</sup>
$E$ , 10 <sup>3</sup> ksi . . . . .	29.0
$E_c$ , 10 <sup>3</sup> ksi . . . . .	30.0
$G$ , 10 <sup>3</sup> ksi . . . . .	11.0
$\mu$ . . . . .	0.32
<b>Physical Properties:</b>	
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.282
$C$ , Btu/(lb)(°F) . . . . .	0.12 (32 to 212°F)
$K$ and $\alpha$ . . . . .	See Figure 2.6.1.0

a Test direction longitudinal for widths less than 9 in.; transverse for widths 9 in. and over.

b Elongation is 8 percent for sheet thickness in the range 0.010 to 0.050 inch. Listed value is for thickness > 0.050 inch.

MIL-HDBK-5H  
1 December 1998




Figure 2.6.1.0. Effect of temperature on the physical properties of AM-350 stainless steel.

## MIL-HDBK-5H

1 December 1998




Figure 2.6.1.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ), the tensile yield strength ( $F_{ty}$ ), and the compressive yield strength ( $F_{cy}$ ) of AM-350 (SCT 850) stainless steel sheet.




Figure 2.6.1.1.2. Effect of temperature on the shear ultimate strength ( $F_{su}$ ) of AM-350 (SCT 850) stainless steel sheet.

MIL-HDBK-5H  
1 December 1998




Figure 2.6.1.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of AM-350 (SCT 850) stainless steel sheet.






Figure 2.6.1.1.4. Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of AM-350 (SCT 850) stainless steel sheet.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.6.1.1.6(a). Typical tensile stress-strain curves at various temperature for AM-350 (SCT 850) stainless steel sheet.**



**Figure 2.6.1.1.6(b). Typical compressive stress-strain compressive tangent-modulus curves at various temperatures for AM-350 (SCT 850) stainless steel sheet.**

**MIL-HDBK-5H****1 December 1998****2.6.2 AM-355**

**2.6.2.0 Comments and Properties** — AM-355, like AM-350, has high strength up to 800°F and good oxidation resistance up to 1000°F. The AM-355 alloy is generally hardened by subzero cooling and tempering (Condition SCT).

AM-355 is available in all mill products. The manufacturing considerations for AM-355 are similar to those for AM-350. Machining of AM-355 bars and forgings is best accomplished after overtempering at 1000 to 1100°F.

The differences between AM-350 and AM-355 are a result of higher carbon, lower chromium, and reduced delta ferrite in AM-355. This difference in composition makes AM-355 slightly stronger but slightly less corrosion resistant than AM-350.

*Environmental Considerations* — Exposure in the 600 to 800°F range for 100 hours at stress levels below the short time yield strength tends to increase room-temperature yield strength and room-temperature tensile strength slightly, with little change in elongation. Typical data are shown in Table 2.6.2.0(a).

**Table 2.6.2.0(a). Effect of Elevated Temperature Exposure on Typical Tensile Properties of AM-355 Alloy in the SCT 850 Condition**

Exposure temperature, °F	Exposure stress, ksi	Exposure time, hr	Room-temperature properties		
			TUS, ksi	TYS, ksi	e, %
RT .....	...	...	211	170	11.5
600 .....	66	1,000	213	172	12.0
700 .....	65	1,000	218	178	10.5
800 .....	62	1,000	227	200	12.5
600 .....	99	1,000	214	180	10.5
700 .....	97	1,000	218	189	11.5
800 .....	93	1,000	224	204	12.5

*Specifications and Properties* — Material specifications for AM-355 are presented in Table 2.6.2.0(b). The room temperature properties of AM-355 SCT are shown in Table 2.6.2.0(c) through (e). The physical properties of this alloy are presented in Figure 2.6.2.0.

**Table 2.6.2.0(b). Material Specifications for AM-355 Stainless Steel**

Specification	Form
AMS 5547	Sheet and strip
AMS 5549	Plate
AMS 5743	Bar, forging, and forging stock

**2.6.2.1 SCT Condition** — Elevated-temperature properties for AM-355 in the SCT (subzero cooled and tempered) condition are presented in Figures 2.6.2.1.1 through 2.6.2.1.4.

**MIL-HDBK-5H****1 December 1998****Table 2.6.2.0(c). Design Mechanical and Physical Properties of AM-355 Stainless Steel**

Specification	AMS 5547		AMS 5743	
Form	Sheet and strip <sup>a</sup>		Bar and forging	
Condition	SCT850 <sup>b</sup>	SCT1000	SCT850 <sup>b</sup>	SCT1000
Thickness or diameter, in.	0.005-0.187	0.010-0.187	...	...
Basis	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L	188	...	200	170
LT	190	165	...	...
$F_{ty}$ , ksi:				
L	162	...	165	155
LT	165	140	...	...
$F_{cy}$ , ksi:				
L	180	...	...	...
LT	...	...	...	...
$F_{su}$ , ksi	124	...	...	...
$F_{bru}$ , ksi:				
(e/D = 1.5)	...	...	...	...
(e/D = 2.0)	383	...	...	...
$F_{bry}$ , ksi:				
(e/D = 1.5)	...	...	...	...
(e/D = 2.0)	278	...	...	...
$e$ , percent:				
L	...	...	10	12
LT	<sup>c</sup>	10	...	...
$RA$ , percent:				
L	...	...	20	25
$E$ , 10 <sup>3</sup> ksi	29.0			
$E_c$ , 10 <sup>3</sup> ksi	29.0			
$G$ , 10 <sup>3</sup> ksi	11.0			
$\mu$	0.32			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup>	0.282			
$C$ , $K$ , and $\alpha$	See Figure 2.6.2.0			

a Test direction longitudinal for widths less than 9 inches; transverse for widths 9 inches and over.

b Note: Condition SCT850 has been superseded by Condition SCT1000 in the applicable specifications. The tensile properties in these columns are the values previously specified for Condition SCT850.

c See Table 2.6.2.0(e).



**MIL-HDBK-5H****1 December 1998****Table 2.6.2.0(d). Design Mechanical and Physical Properties of AM-355 Stainless Steel Plate**

Specification	AMS 5549			
Form	Plate <sup>a</sup>			
Condition	SCT850 <sup>b</sup>			SCT 1000
Thickness, in.	<0.375	0.375-1.000	>1.000	<0.187
Basis	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L	188	...	...	...
LT	190	190	190	165
$F_{ty}$ , ksi:				
L	162	...	...	...
LT	165	150	<sup>c</sup>	140
$F_{cy}$ , ksi:				
L	180	...	...	...
LT	...	...	...	...
$F_{su}$ , ksi	124	...	...	...
$F_{bru}$ , ksi:				
(e/D = 1.5)	...	...	...	...
(e/D = 2.0)	383	...	...	...
$F_{bry}$ , ksi:				
(e/D = 1.5)	...	...	...	...
(e/D = 2.0)	278	...	...	...
$e$ , percent:				
LT	10	10	10	12
$E$ , 10 <sup>3</sup> ksi	29.0			
$E_c$ , 10 <sup>3</sup> ksi	29.0			
$G$ , 10 <sup>3</sup> ksi	11.0			
$\mu$	0.32			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup>	0.282			
$C$ , $K$ , and $\alpha$	See Figure 2.6.2.0			

a Test direction longitudinal for widths less than 9 inches; transverse for widths 9 inches and over.

b Note: Condition SCT850 has been superseded by Condition SCT1000 in the applicable specifications. The tensile properties in these columns are the values previously specified for Condition SCT850.


c As agreed upon by purchaser and vendor.

## MIL-HDBK-5H

1 December 1998

**Table 2.6.2.0(e). Minimum Elongation Values for AM-355 (SCT 850) Stainless Steel Sheet and Strip**

Thickness, inches	e (LT), percent in 2 inches
0.005 to 0.0015 .....	2
Over 0.0015 to 0.0020 .....	3
Over 0.0020 to 0.0050 .....	5
Over 0.0050 to 0.0100 .....	7
Over 0.0100 to 0.1875 .....	8

**Figure 2.6.2.0. Effect of temperature on the physical properties of AM-355 stainless steel.**

## MIL-HDBK-5H

1 December 1998




Figure 2.6.2.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ), the tensile yield strength ( $F_{ty}$ ), and the compressive yield strength ( $F_{cy}$ ) of AM-355 (SCT 850) stainless steel (all products).




Figure 2.6.2.1.2. Effect of temperature on the shear ultimate strength ( $F_{su}$ ) of AM-355 (SCT 850) stainless steel (all products).

## MIL-HDBK-5H

1 December 1998




Figure 2.6.2.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of AM-355 (SCT 850) stainless steel sheet.




Figure 2.6.2.1.4. Effect of temperature on the tensile modulus (E) of AM-355 (SCT 850) stainless steel (all products).

**MIL-HDBK-5H****1 December 1998****2.6.3 CUSTOM 450**

**2.6.3.0 Comments and Properties** — Custom 450 is a martensitic, precipitation-hardening stainless steel used for parts requiring corrosion resistance and high strength at temperatures up to 800°F for aged conditions. It is available in the form of forgings, billet, bar, wire, strip, and welded tubing.

*Manufacturing Considerations* — Custom 450 is normally supplied and fabricated in the solution-treated condition except wire for cold heading is supplied in the H1150M condition. Forming, machining, and joining operations are similar to those employed for other precipitation hardening stainless steels.

*Heat Treatment* — Among the alloys of its type, Custom 450 is the only one recommended for use in the solution-treated condition at temperatures up to 500°F. The alloy can also be heat treated to various strength levels having a wide range of properties. Consult the applicable material specification or MIL-H-6875 for specific heat treatment procedures.

In all heat treat conditions, Custom 450 has excellent ductility and toughness. Cryogenic properties are optimum in the H1150 condition. Maximum strength is achieved with the 900°F aging treatment while optimum fatigue life is exhibited with a 1050°F age.

When the as-supplied solution-treated condition is altered during processing by hot working, severe cold working, or welding, parts should be resolution annealed prior to aging. A dimensional contraction of about 0.0002 in./in. with the 900°F age and about 0.001 in./in. for the 1050°F aging treatment can be expected.

*Environmental Considerations* — The general corrosion resistance of Custom 450 is similar to AISI Type 304 stainless steel. Custom 450 shows excellent resistance to atmosphere corrosion and mild chemical environments. It has good resistance to stress corrosion cracking in the solution-treated condition. Like all martensitic precipitation hardening alloys, if stress corrosion is of concern, it should be aged at the highest temperature compatible with strength requirements. It offers the best resistance to stress corrosion cracking and hydrogen embrittlement when aged at 1150°F. The general corrosion resistance is very slightly decreased by the higher aging temperatures.

Material specifications for Custom 450 are shown in Table 2.6.3.0(a). The room-temperature mechanical properties are presented in Tables 2.6.3.0(b) and (c). The effect of temperature on thermal expansion is shown in Figure 2.6.3.0.

**Table 2.6.3.0(a). Material Specifications for Custom 450 Stainless Steel**

Specification	Form
AMS 5763	Bar, forging, tubing, wire, and ring (air melted)
AMS 5773	Bar, forging, tubing, wire, and ring (CEM)

**2.6.3.1 H900 Condition** — Elevated temperature curves are presented in Figures 2.6.3.1.1, 2.6.3.1.2, and 2.6.3.1.5. A tensile stress-strain curve at room temperature is shown in Figure 2.6.3.1.6. Fatigue data at room temperature are presented in Figure 2.6.3.1.8.

**2.6.3.2 H1050 Condition** — Elevated temperature curves are presented in Figures 2.6.3.2.1, 2.6.3.2.2, and 2.6.3.2.5. A tensile stress-strain curve at room temperature is shown in Figure 2.6.3.2.6. Fatigue data at room temperature are presented in Figure 2.6.3.2.8.

**MIL-HDBK-5H****1 December 1998****Table 2.6.3.0(b). Design Mechanical and Physical Properties of Custom 450 Stainless Steel Bar**


Specification .....	AMS 5763		
Form .....	Bar		
Condition .....	Solution Treated	H900	H1050
Thickness or diameter, in. ....	≤8.000	≤8.000	≤8.000
Basis .....	S	S	S <sup>a</sup>
Mechanical Properties:			
$F_m$ , ksi:			
L .....	125	180	145
ST .....	...	179	144
$F_y$ , ksi:			
L .....	95	170	135
ST .....	...	168	133
$F_{cy}$ , ksi:			
L .....	...	175	143
ST .....	...	173	141
$F_{su}$ , ksi .....	...	114	93
$F_{bru}$ , ksi:			
(e/D = 1.5) .....	...	298	239
(e/D = 2.0) .....	...	381	307
$F_{bry}$ , ksi:			
(e/D = 1.5) .....	...	265	204
(e/D = 2.0) .....	...	326	257
$e$ , percent:			
L .....	10	10	12
$RA$ , percent:			
L .....	40	40	45
$E$ , $10^3$ ksi .....	28.0	29.0	
$E_c$ , $10^3$ ksi .....	...	31.0	
$G$ , $10^3$ ksi .....	...	11.2	
$\mu$ .....	...	0.29	
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> .....	0.28		
$C$ , Btu/(lb)(°F) .....	...		
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	...		
$\alpha$ , $10^{-6}$ in./in./°F .....	See Figure 2.6.3.0		

a Suppliers guaranteed minimum properties.

**MIL-HDBK-5H****1 December 1998****Table 2.6.3.0(c). Design Mechanical and Physical Properties of Custom 450 Stainless Steel Bar**

Specification .....	AMS 5773						
Form .....	Bar						
Condition .....	Solution treated	H900	H950	H1000	H1050	H1100	H1150
Thickness or diameter, in. ....	≤ 12.000						
Basis .....	S	S	S	S	S	S	S
Mechanical Properties:							
$F_{tu}$ , ksi:							
L .....	125	180	170	160	145	130	125
T .....	...	180	170	160	145	130	125
$F_{ty}$ , ksi:							
L .....	95	170	160	150	135	105	75
T .....	...	170	160	150	135	105	75
$F_{cy}$ , ksi:							
L .....	...	175	...	...	143	...	...
T .....	...	173	...	...	141	...	...
$F_{su}$ , ksi .....	...	114	...	...	93	...	...
$F_{bru}$ , ksi:							
(e/D = 1.5) .....	...	298	...	...	239	...	...
(e/D = 2.0) .....	...	381	...	...	307	...	...
$F_{bry}$ , ksi:							
(e/D = 1.5) .....	...	265	...	...	204	...	...
(e/D = 2.0) .....	...	326	...	...	257	...	...
$e$ , percent:							
L .....	10	10	10	12	12	16	18
T .....	...	6	7	8	9	11	12
$R$ , percent:							
L .....	40	40	40	45	45	50	55
T .....	...	20	22	27	30	30	35
$E$ , $10^3$ ksi .....	28.0	29.0					
$E_c$ , $10^3$ ksi .....	...	31.0					
$G$ , $10^3$ ksi .....	...	11.2					
$\mu$ .....	...	0.29					
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> .....		0.28					
$C$ , Btu/(lb)(°F) .....		...					
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....		...					
$\alpha$ , $10^{-6}$ in./in./°F .....		See Figure 2.6.3.0					


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.6.3.0. Effect of temperature on the physical properties of Custom 450 stainless steel.**




**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.6.3.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of Custom 450 (H900) stainless steel bar.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.6.3.1.2. Effect of temperature on the ultimate shear strength ( $F_{su}$ ) of Custom 450 (H900) stainless steel bar.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.6.3.1.5. Effect of temperature on the elongation (e) and the reduction of area (RA) of Custom 450 (H900) stainless steel bar.**



**Figure 2.6.3.1.6. Typical tensile stress-strain curve for Custom 450 (H900) stainless steel bar at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.3.1.8. Best-fit S/N curves for notched,  $K_t = 3.0$ , Custom 450 (H900) stainless steel (ESR) bar, longitudinal direction.**

## Correlative Information for Figure 2.6.3.1.8

Product Form: Bar, 1-1/6-inch diameter

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial  
Frequency - 1800 cpm  
Temperature - RT  
Environment - Air

192 188 RT  
(unnotched)  
304 — RT  
(notched)

No. of Heats/Lots: 1

Specimen Details: Notched, V-Groove,  
 $K_t = 3.0$   
0.283-inch gross diameter  
0.200-inch net diameter  
0.010-inch root radius,  $r$   
60° flank angle,  $\omega$

Equivalent Stress Equation:

$$\log N_f = 9.64 - 3.21 \log (S_{eq} - 39.28)$$

$$S_{eq} = S_{max} (1-R)^{0.65}$$

Standard Error of Estimate = 0.228

Standard Deviation in Life = 0.656

$R^2 = 88\%$

Surface Condition: Polished with abrasive  
nylon cord

Sample Size = 19

Reference: 2.6.3.1.8

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

MIL-HDBK-5H  
1 December 1998






Figure 2.6.3.2.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of Custom 450 (H1050) stainless steel bar.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.6.3.2.2. Effect of temperature on the ultimate shear strength ( $F_{su}$ ) of Custom 450 (H1050) stainless steel bar.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.6.3.2.5. Effect of temperature on the elongation (e) and the reduction of area (RA) of Custom 450 (H1050) stainless steel bar.**



**Figure 2.6.3.2.6. Typical tensile stress-strain curve for Custom 450 (H1050) stainless steel bar at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.3.2.8. Best-fit S/N curves for notched,  $K_t = 3.0$ , Custom 450 (H1050) stainless steel (ESR) bar, longitudinal direction.**

Correlative Information for Figure 2.6.3.2.8

Product Form: Bar, 1-1/6-inch diameter

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial  
Frequency - 1800 cpm  
Temperature - RT  
Environment - Air

156 151 RT  
(unnotched)  
244 — RT  
(notched)

No. of Heats/Lots: 1

Specimen Details: Notched, V-Groove,  
 $K_t = 3.0$   
0.283-inch gross diameter  
0.200-inch net diameter  
0.010-inch root radius,  $r$   
60° flank angle,  $\omega$

Equivalent Stress Equation:

$\log N_f = 9.59 - 3.15 \log (S_{eq} - 33.23)$

$S_{eq} = S_{max} (1-R)^{0.607}$

Standard Error of Estimate = 0.188

Standard Deviation in Life = 0.649

$R^2 = 92\%$

Sample Size = 18

Surface Condition: Polished with abrasive  
nylon cord

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

Reference: 2.6.3.1.8



**MIL-HDBK-5H****1 December 1998****2.6.4 CUSTOM 455**

**2.6.4.0 Comments and Properties** — Custom 455 is a precipitation hardenable stainless steel with a martensitic structure in both the solution annealed and hardened conditions. It is used for parts requiring corrosion resistance and high strength at temperatures up to 800°F. It is produced by consumable electrode remelting and is available in the form of forgings, billet, bar, wire, strip, and welded tubing.

*Manufacturing Considerations* — Custom 455 is normally supplied and fabricated in the solution annealed condition. Forming, machining, and joining operations are similar to those employed for other precipitation hardening stainless steels. Optimum weld ductility is obtained by postweld solution annealing prior to aging.

*Heat Treatment* — The alloy can be heat treated to several strength levels. Consult the applicable materials specification or MIL-H-6875 for specific procedures. The minimum recommended hardening temperature to produce the optimum combination of strength, fracture toughness, and stress corrosion cracking resistance is 950°F. Higher strength is attainable with the 900°F aging treatment but at a sacrifice of fracture toughness and stress corrosion cracking resistance. Like other precipitation hardening stainless steels, the fracture toughness and stress intensity below which stress corrosion cracking does not occur improve with increasing aging temperature within the range of 900°F to 1000°F.

Usually parts are aged directly from the as-supplied solution annealed condition. When this condition has been altered during processing by hot working, severe cold working, or welding, the parts should be resolution annealed prior to aging. A dimensional contraction of about 0.0009 in./in. should be expected with the 950°F aging treatment.

*Environmental Considerations* — The general corrosion resistance of Custom 455 is about equivalent to that of AISI Type 430 stainless steel.

Hydrogen embrittlement tests in 5 percent by weight acid saturated with H<sub>2</sub>S at room temperature show the same degree of susceptibility as other high-strength martensitic stainless steels.

When stress-corrosion cracking is of concern, one should use the highest aging temperature consistent with the strength properties required. The 900°F aging treatment should not be employed when stress corrosion cracking is a consideration. Consult the material producers literature for available stress corrosion data.

Like other precipitation hardening stainless steels, Custom 455 increases slightly in tensile strength and loses some toughness when exposed for long periods of time at temperatures around 700°F. For most applications, the loss in toughness which occurs is not detrimental to performance.

*Specifications and Properties* — Material specifications for Custom 455 are presented in Table 2.6.4.0(a). The room-temperature mechanical properties of Custom 455 are presented in Table 2.6.4.0(b). Physical properties at elevated temperatures are presented in Figure 2.6.4.0.

**Table 2.6.4.0(a). Material Specifications for Custom 455 Stainless Steel**

Specification	Form
AMS 5578	Tubing (welded)
AMS 5617	Bar and forging


**MIL-HDBK-5H****1 December 1998****Table 2.6.4.0(b). Design Mechanical and Physical Properties of Custom 455 Stainless Steel**

Table 2.6.4.0(b). Design Mechanical and Physical Properties of Custom 435 Stainless Steel					
Specification . . . . .	AMS 5578		AMS 5617		
Form . . . . .	Tubing (Welded)		Bar		
Condition . . . . .	H950		H950		H1000
Thickness or diameter, in. <sup>a</sup> . . . . .	0.020-0.062	>0.062	≤4.000	4.001-6.000	≤8.000
Basis . . . . .	S	S	S	S	S
Mechanical Properties:					
<i>F<sub>m</sub></i> , ksi:					
L . . . . .	220	220	225	220	200
LT . . . . .	...	...	225 <sup>b</sup>	220 <sup>b</sup>	...
ST . . . . .	...	...	225 <sup>b</sup>	220 <sup>b</sup>	...
<i>F<sub>ty</sub></i> , ksi:					
L . . . . .	205	205	210	205	185
LT . . . . .	...	...	210 <sup>b</sup>	205 <sup>b</sup>	...
ST . . . . .	...	...	210 <sup>b</sup>	205 <sup>b</sup>	...
<i>F<sub>cy</sub></i> , ksi:					
L . . . . .	...	...	219	214	193
LT . . . . .	...	...	219	214	193
ST . . . . .	...	...	219	214	193
<i>F<sub>su</sub></i> , ksi . . . . .	...	...	133	130	124
<i>F<sub>bru</sub></i> , ksi:					
(e/D = 1.5) . . . . .	...	...	355	347	324
(e/D = 2.0) . . . . .	...	...	450	440	409
<i>F<sub>bry</sub></i> , ksi:					
(e/D = 1.5) . . . . .	...	...	311	303	285
(e/D = 2.0) . . . . .	...	...	366	358	343
<i>e</i> , percent:					
L . . . . .	3	4	10	10	10
LT . . . . .	...	...	5 <sup>b</sup>	5 <sup>b</sup>	...
ST . . . . .	...	...	5 <sup>b</sup>	5 <sup>b</sup>	...
<i>RA</i> , percent:					
L . . . . .	...	...	40	40	40
LT . . . . .	...	...	20 <sup>b</sup>	20 <sup>b</sup>	...
ST . . . . .	...	...	20 <sup>b</sup>	20 <sup>b</sup>	...
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	28.5				28.9
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	30.0				30.0
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	11.3				11.5
<i>μ</i> . . . . .	0.27				0.26
Physical Properties:					
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.28				
<i>C</i> , Btu/(lb)(°F) . . . . .	...				
<i>K</i> , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] . . . . .	See Figure 2.6.4.0				
<i>α</i> , 10 <sup>-6</sup> in./in./°F . . . . .	See Figure 2.6.4.0				

a Wall thickness for tubing.

b For Grade 2 material only.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.6.4.0. Effect of temperature on the physical properties of Custom 455 (H950) stainless steel.**

**2.6.4.1 H950 Condition** — Elevated temperature curves are presented in Figure 2.6.4.1.1, 2.6.4.1.2, and 2.6.4.1.5. A tensile stress-strain curve at room temperature is shown in Figure 2.6.4.1.6. Fatigue data at room temperature are presented in Figure 2.6.4.1.8(a) and (b).

**2.6.4.2 H1000 Condition** — Elevated temperature curves are shown in Figures 2.6.4.2.1, 2.6.4.2.2, and 2.6.4.2.5. A tensile stress-strain curve at room temperature is presented in Figure 2.6.4.2.6. Fatigue data at room temperature are shown in Figure 2.6.4.2.8.

## MIL-HDBK-5H

1 December 1998





Figure 2.6.4.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of Custom 455 (H950) stainless steel bar.


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.6.4.1.2. Effect of temperature on the ultimate shear strength ( $F_{su}$ ) of Custom 455 (H950) stainless steel bar.**

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.4.1.5. Effect of temperature on the elongation (e) and reduction of area (RA) of Custom 455 (H950) stainless steel bar.**




**Figure 2.6.4.1.6. Typical tensile stress-strain curve for Custom 455 (H950) stainless steel bar at room temperature.**



[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.4.1.8(b). Best-fit S/N curves for notched,  $K_t = 3.0$ , Custom 455 (H950) stainless steel bar, longitudinal direction.**

Correlative Information for Figure 2.6.4.1.8(b)

Product Form: Bar, 1-1/16-inch diameter

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial  
Frequency - 1800 cpm  
Temperature - RT  
Environment - Air

245 242 RT  
(unnotched)  
361 — RT  
(notched)

No. of Heats/Lots: 1

Specimen Details: Notched, V-Groove,  $K_t = 3.0$   
0.283-inch gross diameter  
0.200-inch net diameter  
0.010-inch root radius,  $r$   
60° flank angle,  $\omega$

Equivalent Stress Equation:

$\log N_f = 7.42 - 1.90 \log (S_{eq} - 47.34)$   
 $S_{eq} = S_{max} (1-R)^{0.515}$   
Standard Error of Estimate = 0.246  
Standard Deviation in Life = 0.568  
 $R^2 = 81\%$

Surface Condition: Polished with abrasive nylon cord


Sample Size = 17

Reference: 2.6.3.1.8


[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.6.4.2.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of Custom 455 (H1000) stainless steel bar.**




**Figure 2.6.4.2.2. Effect of temperature on the ultimate shear strength ( $F_{su}$ ) of Custom 455 (H1000) stainless steel bar.**

## MIL-HDBK-5H

1 December 1998




**Figure 2.6.4.2.5. Effect of temperature on the elongation (e) and the reduction of area (RA) of Custom 455 (H1000) stainless steel bar.**



**Figure 2.6.4.2.6. Typical tensile stress-strain curve for Custom 455 (H1000) stainless steel bar at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.4.2.8. Best-fit S/N curves for notched,  $K_t = 3.0$ , Custom 455 (H1000) stainless steel bar, longitudinal direction.**

Correlative Information for Figure 2.6.4.2.8

Product Form: Bar, 1-1/16-inch diameter

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial  
Frequency - 1800 cpm  
Temperature - RT  
Environment - Air

214 209 RT  
(unnotched)  
335 — RT  
(notched)

No. of Heats/Lots: 1

Specimen Details: Notched, V-Groove,  
 $K_t = 3.0$   
0.283-inch gross diameter  
0.200-inch net diameter  
0.010-inch root radius,  $r$   
60° flank angle,  $\omega$

Equivalent Stress Equation:

$\log N_f = 12.37 - 4.44 \log (S_{eq} - 21.43)$   
 $S_{eq} = S_{max} (1 - R)^{0.561}$   
Standard Error of Estimate = 0.359  
Standard Deviation in Life = 0.540  
 $R^2 = 56\%$

Surface Condition: Polished with abrasive nylon cord

Sample Size = 18

Reference: 2.6.3.1.8

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998****2.6.5 PH13-8Mo**

**2.6.5.0 Comments and Properties** — PH13-8Mo is a martensitic precipitation-hardening stainless steel used for parts requiring corrosion resistance, high strength, high fracture toughness, and oxidation resistance up to 800°F. When used at temperatures between 600 and 800°F, some loss in notch toughness will occur. The loss is time-temperature dependent and will occur gradually over thousands of hours at 600°F and hundreds of hours at 800°F. Depending upon the application, this loss in notch toughness may not be important and useful engineering properties may still be available. Good transverse mechanical properties are one of the major advantages of PH13-8Mo. PH13-8Mo is produced by double vacuum melting and is available in the form of forgings, plate, bar, and wire, normally furnished in the solution-treated (A) condition.

*Manufacturing Considerations* — Forming, joining, and machining operations are usually performed on material in Condition A, using similar procedures and equipment to those employed for other precipitation-hardening stainless steels. Best machinability is exhibited by Conditions H1150 and H1150M. A dimensional contraction of 0.0004 to 0.0006 and 0.0008 to 0.0012 in./in. occurs upon hardening to the H1000 and H1100 conditions, respectively.

*Heat Treatment* — PH13-8Mo must be used in the heat-treated condition and should not be placed in service in Condition A. The alloy can be heat treated to various strength levels having a wide range of properties. Consult the applicable material specification or MIL-H-6875 for specific heat treatment procedures.

*Environmental Considerations* — PH13-8Mo is nearly equal to 17-4PH in general corrosion resistance and surpasses the other hardenable stainless steels in stress-corrosion resistance. However, for tensile application where stress corrosion is a possibility, PH13-8Mo should be aged at the highest temperature compatible with strength requirements and at a temperature not lower than 1000°F for 4 hours minimum aging time.

*Specification and Properties* — A material specification for PH13-8Mo is presented in Table 2.6.5.0(a). The room-temperature mechanical and physical properties for PH13-8Mo are presented in Table 2.6.5.0(b) and (c). The physical properties of this alloy at elevated temperatures are presented in Figure 2.6.5.0.

**Table 2.6.5.0(a). Material Specification for PH13-8Mo Stainless Steel**

Specification	Form
AMS 5629	Bar, forging, ring, and extrusion (VIM plus CEVM)

**2.6.5.1 H950 and H1000 Conditions** — Elevated temperature curves for tensile yield and ultimate strengths are presented in Figure 2.6.5.1.1. Typical tensile and compressive stress-strain and tangent-modulus curves for the H1000 condition at room temperature are depicted in Figures 2.6.5.1.6(a) and (b). Figure 2.6.5.1.6(c) contains typical full-range stress-strain curves at room temperature for various heat-treated conditions. Unnotched and notched fatigue information for H1000 condition at room temperature is presented in Figures 2.6.5.1.8(a) through (c).

## MIL-HDBK-5H

1 December 1998

**Table 2.6.5.0(b). Design Mechanical and Physical Properties of PH13-8Mo Stainless Steel**

Specification . . . . .	AMS 5629							
	Round, hex, square and flat bar							
	H950		H1000		H1025	H1050	H1100	H1150
	<9.0		<8.0		≤12.0			
	A	B	A	B	S	S	S	S
Mechanical Properties: <sup>b</sup>								
$F_{tu}$ , ksi:								
L . . . . .	217	221	201	208	185	175	150	135
T . . . . .	217	221	201	208	185	175	150	135
$F_{ty}$ , ksi:								
L . . . . .	198	205	190 <sup>a</sup>	200	175	165	135	90
T . . . . .	198	205	190 <sup>a</sup>	200	175	165	135	90
$F_{cy}$ , ksi:								
L . . . . .	...	...	200	211	...	...	...	...
T . . . . .	...	...	200	211	...	...	...	...
$F_{su}$ , ksi . . . . .	...	...	117	122	...	...	...	...
$F_{bru}$ , ksi:								
(e/D = 1.5) . . . . .	...	...	302	313	...	...	...	...
(e/D = 2.0) . . . . .	...	...	402	416	...	...	...	...
$F_{bry}$ , ksi:								
(e/D = 1.5) . . . . .	...	...	263	277	...	...	...	...
(e/D = 2.0) . . . . .	...	...	338	356	...	...	...	...
$e$ , percent (S-basis):								
L . . . . .	10	...	10	...	11	12	14	14
T . . . . .	10	...	10	...	11	12	14	14
$RA$ , percent (S-basis):								
L . . . . .	45	...	50	...	50	50	50	50
T . . . . .	35	...	40	...	45	45	50	50
$E$ , 10 <sup>3</sup> ksi . . . . .	28.3							
$E_c$ , 10 <sup>3</sup> ksi . . . . .	29.4							
$G$ , 10 <sup>3</sup> ksi . . . . .	11.0							
$\mu$ . . . . .	0.28							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.279							
$C$ , Btu/(lb)(°F) . . . . .	0.11 (32 to 212°F) (Est.)							
$K$ and $\alpha$ . . . . .	See Figure 2.6.5.0							

a S-basis. Rounded  $T_{99}$  value = 193 ksi.


b Design allowables were based mainly upon data from samples of material, supplied in the solution treated condition, which were aged to demonstrate response to heat treatment by suppliers.

**MIL-HDBK-5H****1 December 1998****Table 2.6.5.0(c). Design Mechanical and Physical Properties of PH13-8Mo Stainless Steel**


Specification	AMS 5629					
Form	Forging, flash welded ring, and extrusion					
Condition	H950	H1000	H1025	H1050	H1100	H1150
Thickness or diameter, in.	≤12					
Basis	S	S	S	S	S	S
Mechanical Properties:						
$F_m$ , ksi:						
L	220	205	185	175	150	135
T	220	205	185	175	150	135
$F_{ty}$ , ksi:						
L	205	190	175	165	135	90
T	205	190	175	165	135	90
$F_{cy}$ , ksi:						
L	...	...	...	...	...	...
T	...	...	...	...	...	...
$F_{su}$ , ksi	...	...	...	...	...	...
$F_{bru}$ , ksi:						
(e/D = 1.5)	...	...	...	...	...	...
(e/D = 2.0)	...	...	...	...	...	...
$F_{bry}$ , ksi:						
(e/D = 1.5)	...	...	...	...	...	...
(e/D = 2.0)	...	...	...	...	...	...
$e$ , percent:						
L	10	10	11	12	14	14
T	10	10	11	12	14	14
$RA$ , percent:						
L	45	50	50	50	50	50
T	35	40	45	45	50	50
$E$ , 10 <sup>3</sup> ksi	28.3					
$E_c$ 10 <sup>3</sup> ksi	29.4					
$G$ , 10 <sup>3</sup> ksi	11.0					
$\mu$	0.28					
Physical Properties:						
$\omega$ , lb/in. <sup>3</sup>	0.279					
$C$ , Btu/(lb)(°F)	0.11 (32 to 212°F) (Est.)					
$K$ and $\alpha$	See Figure 2.6.5.0					

## MIL-HDBK-5H

1 December 1998




**Figure 2.6.5.0. Effect of temperature on the physical properties of PH13-8Mo stainless steel.**


**MIL-HDBK-5H****1 December 1998**

**Figure 2.6.5.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of PH13-8Mo (H950 and H1000) stainless steel bar.**




**MIL-HDBK-5H****1 December 1998**

**Figure 2.6.5.1.6(a). Typical tensile stress-strain curve at room temperature for PH13-8Mo (H1000) stainless steel bar.**




**Figure 2.6.5.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves at room temperature for PH13-8Mo (H1000) stainless steel bar.**

**MIL-HDBK-5H****1 December 1998**

**Figure 2.6.5.1.6(c). Typical tensile stress-strain curves (full range) at room temperature for various heat treated conditions of PH13-8Mo stainless steel bar.**

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.5.1.8(a). Best-fit S/N curves for unnotched PH13-8Mo (H1000) forged bar, longitudinal and transverse directions.**

Correlative Information for Figure 2.6.5.1.8(a)

Product Form: Forged bar, 4 x 5 and 2 x 6 inches

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

205 197 RT

Loading - Axial

Frequency - Not Specified

Temperature - RT

Environment - Air

Specimen Details: Unnotched

No. of Heats/Lots: 4

Gross Diameter	Net Diameter
0.50	0.25
0.75	0.25

Equivalent Stress Equation:

$\log N_f = 16.32 - 5.75 \log (S_{eq} - 92.6)$

$S_{eq} = S_{max} (1 - R)^{0.64}$

Standard Error of Estimate = 0.461

Standard Deviation of Life = 0.919


$R^2 = 75\%$

Surface Condition: Polished to RMS 10

Sample Size: 86

References: 2.6.5.1.8(a), (b), (d)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998**

**Figure 2.6.5.1.8(b). Best-fit S/N curves for notched,  $K_t = 3.0$ , PH13-8Mo (H1000) forged bar, longitudinal and long transverse directions.**

Correlative Information for Figure 2.6.5.1.8(b)

Product Form: Forged bar, 4 x 5 and 2 x 6 inches

Properties: TUS, ksi TYS, ksi Temp., °F

205 197 RT

Specimen Details: Notched,  $K_t = 3.0$

Gross Diameter	Net Diameter	Notch Root Radius
0.750	0.252	0.013
0.500	0.250	0.013

60° flank angle

Surface Condition: Notch was polished with abrasively charged wire and rotating wire with oil and aluminum grit

References: 2.6.5.1.8(a), (b), (d)

Test Parameters:

Loading - Axial

Frequency - Not Specified

Temperature - RT

Environment - Air

No. of Heats/Lots: 4

Equivalent Stress Equation:

$\log N_f = 9.90 - 3.13 \log (S_{eq} - 34.4)$

$S_{eq} = S_{max} (1 - R)^{0.68}$

Standard Deviation of Log (Life) = 23.1 ( $1/S_{eq}$ )


Adjusted  $R^2$  Statistic = 92%

Sample Size: 104

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.5.1.8(c). Best-fit S/N curves for unnotched PH13-8Mo (H1000) hand forging, longitudinal direction.**

Correlative Information for Figure 2.6.5.1.8(c)

Product Form: Forged bar, 7 x 7 inches

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial

Frequency - Not Specified

Temperature - RT

Environment - Air

210 204 RT

Specimen Details: Unnotched  
0.500-inch gross diameter  
0.250-inch net diameter

No. of Heats/Lots: 2

Surface Condition: Machined to RMS 63-270,  
solution treated and aged,  
grit blasted

Equivalent Stress Equation:

$\log N_f = 18.12 - 6.54 \log (S_{eq})$

$S_{eq} = S_{max} (1-R)^{0.11}$

Standard Error of Estimate = 0.263

Standard Deviation of Life = 0.475

$R^2 = 69\%$

Reference: 2.6.5.1.8(c)

Sample Size: 20

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998****2.6.6 15-5PH**

**2.6.6.0 Comments and Properties** — 15-5PH is a precipitation-hardening, martensitic stainless steel used for parts requiring corrosion resistance and high strength at temperatures up to 600°F. Alloy 15-5PH has good transverse ductility and strength in large section sizes. This material is supplied in either the annealed or overaged condition and is heat treated after fabrication. Parts should never be used in Condition A. When good fracture toughness or impact properties are required, both at or below room temperature, conditions H900 and H925 should not be used. Conditions H1025, H1075, H1100, and H1150 provide lower transition temperatures and more useful levels of fracture toughness than the H900 and H925 conditions. The H1150M condition has the best notch toughness and is recommended for cryogenic applications.

*Manufacturing Considerations* — 15-5PH is readily forged and welded. Forging procedures are similar to those used for 17-4PH, the forgeability of 15-5PH being superior to that of 17-4PH in critical types of upset-forging and hot-flattening operations. Machining in the solution-treated condition is done at rates similar to Type 304 and 60 percent of these rates work well for Condition H900. Highest machining rates are possible with Conditions H1150 and H1150M. Material which is hot worked must be solution-treated before hardening. A dimensional contraction of 0.0004 to 0.0006 and 0.0008 to 0.0010 in./in. will occur on hardening to the H900 and H1150 conditions, respectively.

*Heat Treatment* — 15-5PH must be used in the heat-treated condition and should not be placed in service in Condition A. The alloy can be heat treated to various strength levels having a wide range of properties. Consult the applicable material specification or MIL-H-6875 for specific heat treatment procedures.

*Environmental Considerations* — The corrosion resistance of 15-5PH is comparable to that of 17-4PH. For tensile applications where stress corrosion is a possibility, 15-5PH should be aged at the highest temperature compatible with strength requirements and at a temperature not lower than 1025°F for 4 hours minimum aging time.

*Specifications and Properties* — Material specifications for 15-5PH are presented in Table 2.6.6.0(a). Room-temperature mechanical and physical properties of 15-5PH are shown in Tables 2.6.6.0(b) through (d). The effect of temperature on physical properties is depicted in Figure 2.6.6.0.

**Table 2.6.6.0(a). Material Specifications for 15-5PH Stainless Steel**

Specification	Form
AMS 5659	Bar, forging, ring, and extrusion (CEVM)
AMS 5862	Sheet, strip, and plate (CEVM)
AMS 5400	Investment casting

**2.6.6.1 Various Heat-Treated Conditions** — Elevated temperature curves for the various mechanical properties are shown in Figures 2.6.6.1.1 and 2.6.6.1.4. Typical stress-strain and tangent-modulus curves are shown in Figures 2.6.6.1.6(a) through (c).

**2.6.6.2 H1025 Condition** — An elevated temperature curve for compressive yield strength is presented in Figure 2.6.6.2.2. Stress-strain and tangent-modulus curves are shown in Figures 2.6.6.2.6(a) and (b). Fatigue data at room temperature are illustrated in Figures 2.6.6.2.8(a) through (c).

**2.6.6.3 H1150 Condition** — An elevated temperature curve for compressive yield strength is presented in Figure 2.6.6.3.2. Compressive stress-strain and tangent-modulus curves at various temperatures are shown in Figure 2.6.6.3.6.

**MIL-HDBK-5H****1 December 1998****Table 2.6.6.0(b). Design Mechanical and Physical Properties of 15-5PH Stainless Steel Bar and Forging**

Specification .....	AMS 5659						
Form .....	Bar and forging						
Condition .....	H900	H925	H1025	H1075	H1100	H1150	H1150M <sup>a</sup>
Thickness or diam., in. .	≤12	≤12	≤12	≤12	≤12	≤12	≤12
Basis .....	S	S	S	S	S	S	S
Mechanical Properties:							
$F_{tu}$ , ksi:							
L .....	190	170	155	145	140	135	115
T .....	190	170	155	145	140	135	115
$F_{ty}$ , ksi:							
L .....	170	155	145	125	115	105	75
T .....	170	155	145	125	115	105	75
$F_{cy}$ , ksi:							
L .....	...	...	143	...	...	99	...
T .....	...	...	143	...	...	99	...
$F_{su}$ , ksi .....	...	...	97	...	...	85	...
$F_{bru}^b$ , ksi:							
(e/D = 1.5) .....	...	...	263	...	...	230	...
(e/D = 2.0) .....	...	...	332	...	...	293	...
$F_{bry}^b$ , ksi:							
(e/D = 1.5) .....	...	...	211	...	...	166	...
(e/D = 2.0) .....	...	...	250	...	...	201	...
$e$ , percent:							
L .....	10	10	12	13	14	16	18
T .....	6	7	8	9	10	11	14
RA, percent:							
L .....	35	38	45	45	45	50	55
T .....	20	25	32	33	34	35	35
$E$ , 10 <sup>3</sup> ksi .....	28.5						
$E_c$ , 10 <sup>3</sup> ksi .....	29.2						
$G$ , 10 <sup>3</sup> ksi .....	11.2						
$\mu$ .....	0.27						
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> .....	0.283						
$C$ , Btu/(lb)(°F) .....	...						
$K$ and $\alpha$ .....	See Figure 2.6.6.0						

a H1150M condition is not covered by AMS 5659; properties reflect producers' guaranteed minimum tensile properties.

b Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 2.6.6.0(c). Design Mechanical and Physical Properties of 15-5PH Stainless Steel Plate**

Specification .....	AMS 5862			
Form .....	Plate			
Condition .....	H1025 <sup>a</sup>			
Thickness, in. ....	0.187-0.625	0.626-2.000	2.001-3.000	3.001-4.000
Basis .....	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	154	154	154	...
LT .....	155	155	155	155
$F_{ty}$ , ksi:				
L .....	143	143	143	...
LT .....	145	145	145	145
$F_{cy}$ , ksi:				
L .....	150	150	150	...
LT .....	152	149	146	...
$F_{su}$ , ksi .....	97	97	96	...
$F_{bru}^b$ , ksi:				
(e/D = 1.5) .....	257	257	257	...
(e/D = 2.0) .....	331	331	331	...
$F_{bry}^b$ , ksi:				
(e/D = 1.5) .....	211	211	211	...
(e/D = 2.0) .....	246	246	246	...
$e$ , percent:				
LT .....	8	12	12	12
$RA$ , percent:				
LT .....	35	40	40	40
$E$ , $10^3$ ksi .....	28.5			
$E_c$ , $10^3$ ksi .....	29.2			
$G$ , $10^3$ ksi .....	11.2			
$\mu$ .....	0.27			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.283			
$C$ , Btu/(lb)(°F) .....	...			
$K$ and $\alpha$ .....	See Figure 2.6.6.0			

a The H900, H925, H1075, H1100, and H1150 conditions are included in AMS 5862.

b Bearing values are "dry pin" values per Section 1.4.7.1.



**MIL-HDBK-5H****1 December 1998****Table 2.6.6.0(d). Design Mechanical and Physical Properties of 15-5PH Stainless Steel Investment Casting**


Specification .....	AMS 5400
Form .....	Investment casting
Condition .....	H935
Location within casting .....	Any area
Basis .....	S
Mechanical Properties: <sup>a</sup>	
$F_{tu}$ , ksi .....	170
$F_{ty}$ , ksi .....	150
$F_{cy}$ , ksi .....	155
$F_{su}$ , ksi .....	107
$F_{bru}^b$ , ksi:	
( $e/D = 1.5$ ) .....	269
( $e/D = 2.0$ ) .....	349
$F_{bry}^b$ , ksi:	
( $e/D = 1.5$ ) .....	209
( $e/D = 2.0$ ) .....	240
$e$ , percent .....	6
$RA$ , percent .....	14
$E$ , $10^3$ ksi .....	28.5
$E_c$ , $10^3$ ksi .....	29.2
$G$ , $10^3$ ksi .....	11.2
$\mu$ .....	0.27
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.283
$C$ , Btu/(lb)(°F) .....	...
$K$ , and $\alpha$ .....	See Figure 2.6.6.0

a Properties apply only when drawing specifies that conformance to tensile property requirements shall be determined from specimens cut from castings or integrally cast specimens.


b Bearing values are "dry pin" values per Section 1.4.7.1.

## MIL-HDBK-5H

1 December 1998




**Figure 2.6.6.0. Effect of temperature on the physical properties of 15-5PH stainless steel.**

**MIL-HDBK-5H****1 December 1998**


**Figure 2.6.6.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of 15-5PH (H925, H1025, and H1100) stainless steel bar.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.6.6.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of 15-5PH stainless steel.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.6.6.1.6(a). Typical tensile stress-strain curves at room temperature for various heat treated conditions of 15-5PH stainless steel bar.**



**Figure 2.6.6.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves at room temperature for various heat-treated conditions of 15-5PH stainless steel bar.**

## MIL-HDBK-5H

1 December 1998






Figure 2.6.6.1.6(c). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 15-5PH (H935) stainless steel casting.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.6.6.2.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) of 15-5PH (H1025) stainless steel bar.**



**Figure 2.6.6.2.6(a). Typical compressive stress-strain and compressive tangent-modulus curves at various temperatures for 15-5PH (H1025) stainless steel bar.**

## MIL-HDBK-5H

1 December 1998





Figure 2.6.6.2.6(b). Tensile and compressive stress-strain and compressive tangent-modulus curves for 15-5PH (H1025) stainless steel plate.



**MIL-HDBK-5H****1 December 1998**

**Figure 2.6.6.2.8(a). Best-fit S/N curves for notched,  $K_t = 3.0$ , 15-5PH (H1025) stainless steel bar, longitudinal and long transverse directions.**

Correlative Information for Figure 2.6.6.2.8(a)

Product Form: Bar, 2 x 6 inches

Properties: TUS, ksi TYS, ksi Temp, °F

Longitudinal 163 159 RT

Long Transverse 164 160 RT

Longitudinal 278 — RT

(notched)

Long Transverse 277 — RT

(notched)

Specimen Details: Notched, V-Groove,  $K_t = 3.0$   
0.375-inch gross diameter  
0.250-inch net diameter  
0.013-inch root radius,  $r$   
60° flank angle,  $\omega$

Surface Condition: Ground notch

Reference: 2.6.6.2.8(a)

Test Parameters:

Loading - Axial

Frequency - 1800 cpm

Temperature - RT

Environment - Air

No. of Heats/Lots: 3

Equivalent Stress Equation:

$\log N_f = 19.69 - 9.14 \log (S_{eq} - 18.16)$

$S_{eq} = S_{max} (1 - R)^{0.595}$


Standard Error of Estimate = 0.449

Standard Deviation in Life = 0.627

$R^2 = 49\%$

Sample Size: 40

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998**

**Figure 2.6.6.2.8(b). Best-fit S/N curve for unnotched,  $K_t = 1.0$ , 15-5PH (H1025) stainless steel plate, longitudinal and long transverse directions.**

Correlative Information for Figure 2.6.6.2.8(b)

Product Form: Plate, 0.808 inch, 2.024 inch, and 2.579 inch thick

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp, °F</u>
Longitudinal	169.9	165.7	RT
Long Transverse	170.2	166.1	RT

Specimen Details: Unnotched  
0.250-inch diameter

Surface Condition: Axial, ground RMS 8

Reference: 2.6.6.2.8(b)

Test Parameters:

Loading - Axial  
Frequency - 30 Hz  
Temperature - RT  
Atmosphere - Air

No. of Heats/Lots: 4


Fatigue Life Equation:

$$\log N_f = 110.1 - 47.22 \log (S_{\max})$$

Standard Deviation in Log (Life) = 0.58

Adjusted  $R^2$  = 52.8%

Sample Size = 19

**MIL-HDBK-5H****1 December 1998**

**Figure 2.6.6.2.8(c). Best-fit S/N curve for notched,  $K_t = 3.0$ , 15-5PH (H1025) stainless steel plate, longitudinal and long transverse directions.**

Correlative Information for Figure 2.6.6.2.8(c)

Product Form: Plate, 0.215 inch, 0.269 inch,  
0.277 inch, 0.394 inch,  
0.524 inch, 0.908 inch,  
2.024 inch, and 2.579 inch

<u>Properties:</u>	<u>TUS,ksi</u>	<u>TYS,ksi</u>	<u>Temp,°F</u>
Longitudinal	170.8	165.6	RT
Long Transverse	170.2	166.1	RT

Specimen Details: Notched, V-Groove,  $K_t = 3.0$   
Flat, 0.590-inch gross width  
0.500-inch net width  
0.025-inch root radius  
60° flank angle,  $\omega$

Round, 0.374-inch gross diameter  
0.252-inch net diameter  
0.013-inch root radius  
60° flank angle,  $\omega$

Surface Condition: RMS 32 notch

Reference: 2.6.6.2.8(b)

Test Parameters:  
Loading - Axial  
Frequency - 30 Hz  
Temperature - RT  
Atmosphere - Air

No. of Heats/Lots: 10

Fatigue Life Equation:  
 $\log N_f = 8.72 - 2.56 \log (S_{\max} - 34.9)$

Standard Deviation in Log (Life) = 10.9 ( $1/S_{\max}$ )

Adjusted  $R^2$  = 88.2%

Sample Size = 55

## MIL-HDBK-5H

1 December 1998




Figure 2.6.6.3.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) of 15-5PH (H1150) stainless steel bar.




Figure 2.6.6.3.6. Typical compressive stress-strain and tangent-modulus curves at various temperatures for 15-5PH (H1150) stainless steel bar.

**MIL-HDBK-5H****1 December 1998****2.6.7 PH15-7Mo**

**2.6.7.0 Comments and Properties** — PH15-7Mo is a semiaustenitic stainless steel used where high strength and good corrosion and oxidation resistance are needed up to 600°F. This steel is supplied in Condition A for ease of forming or in Condition C when highest strength is required.

*Manufacturing Considerations* — PH15-7Mo in Condition A is readily cold formed. Conventional inert-gas shielded arc and resistance techniques are generally used for welding. The heat treatments for this steel are compatible with the cycles used for honeycomb panel brazing. Vapor blasting of scaled Condition TH1050 parts is recommended because of the hazards of intergranular corrosion in adequately controlled pickling operations.

In hardening this steel from Condition A to Condition TH1050 a net dimensional growth of 0.004 in./in. should be anticipated. Use of this steel in Conditions T and T-100 is not recommended.

*Environmental Considerations* — The resistance of PH15-7Mo to stress-corrosion cracking in chloride environments has been evaluated and found to be superior to that of the alloy steels and the hardenable chromium steels. Conditions C and CH 900 provide maximum resistance to stress corrosion.

*Specification and Properties* — A material specification for PH15-7Mo stainless steel is presented in Table 2.6.7.0(a). The room-temperature properties of PH15-7Mo are shown in Tables 2.6.7.0(b) and (c). The physical properties of this alloy at room and elevated temperatures are presented in Figure 2.6.7.0.

**Table 2.6.7.0(a). Material Specification for PH15-7Mo Stainless Steel**

Specification	Form
AMS 5520	Plate, sheet, and strip

**2.6.7.1 TH1050 Condition** — Effect of temperature on various mechanical properties for this condition is presented in Figures 2.6.7.1.1 and 2.6.7.1.4. Typical stress-strain and tangent-modulus curves at room temperature and elevated temperature are presented in Figures 2.6.7.1.6(a) through (c). Unnotched and notched fatigue information at room and elevated temperatures are illustrated in Figures 2.6.7.1.8(a) through (f).

**MIL-HDBK-5H****1 December 1998****Table 2.6.7.0(b). Design Mechanical and Physical Properties of PH15-7Mo Stainless Steel Sheet, Strip, and Plate**

Specification .....	AMS 5520
Form .....	Sheet, strip, and plate
Condition .....	TH1050
Thickness, in. ....	0.0015-0.500
Basis .....	S
Mechanical Properties:	
$F_{tu}$ , ksi:	
L .....	185
LT .....	190
$F_{ty}$ , ksi:	
L .....	165
LT .....	170
$F_{cy}$ , ksi:	
L .....	182
LT .....	188
$F_{su}$ , ksi .....	120
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	327
(e/D = 2.0) .....	377
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	259
(e/D = 2.0) .....	272
$e$ , percent:	
LT .....	a
$E$ , $10^3$ ksi .....	29.0
$E_c$ , $10^3$ ksi .....	30.0
$G$ , $10^3$ ksi .....	11.4
$\mu$ .....	0.28
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.277
$C$ , Btu(lb)(°F) .....	...
$K$ and $\alpha$ .....	See Figure 2.6.7.0


a See Table 2.6.7.0(c).

## MIL-HDBK-5H

1 December 1998

**Table 2.6.7.0(c). Minimum Elongation Values for PH15-7Mo (TH1050) Stainless Steel Sheet**

Thickness, inches	e (LT), percent
0.0015 to 0.0049 .....	2
0.0050 to 0.0099 .....	3
0.010 to 0.019 .....	4
0.020 to 0.1874 .....	5
0.1875 to 0.500 .....	6

**Figure 2.6.7.0. Effect of temperature on the physical properties of PH15-7Mo (TH1050) stainless steel.**



MIL-HDBK-5H  
1 December 1998




Figure 2.6.7.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ), tensile yield strength ( $F_{ty}$ ), and compressive yield strength ( $F_{cy}$ ) of PH15-7Mo (TH1050) stainless steel sheet.





Figure 2.6.7.1.4. Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of PH15-7Mo (TH1050) stainless steel sheet.




## MIL-HDBK-5H

1 December 1998




**Figure 2.6.7.1.6(a). Typical tensile stress-strain curves at various temperatures for PH15-7Mo (TH1050) stainless steel sheet.**



**Figure 2.6.7.1.6(b). Typical compressive stress-strain curves at various temperatures for PH15-7Mo (TH1050) stainless steel sheet.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.6.7.1.6(c). Typical compressive tangent-modulus curves at various temperatures for PH15-7Mo (TH1050) stainless steel sheet.**

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.7.1.8(a). Best-fit S/N curves for unnotched PH15-7Mo (TH1050) sheet, longitudinal direction.**

Correlative Information for Figure 2.6.7.1.8(a)

Product Form: Sheet, 0.025-inch

Properties: TUS, ksi TYS, ksi Temp, °F

201 196 RT

Specimen Details: Unnotched  
2.0-inch gross width  
0.75-inch net width

Surface Condition: Specimen edges machined in longitudinal direction, edges polished with 320 grit emery paper

References: 2.6.7.1.8(a) and (b)

Test Parameters:

Loading - Axial

Frequency - 24 and 1800 cpm

Temperature - RT

Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 23.24 - 8.32 \log S_{eq}$

$S_{eq} = S_{max} (1-R)^{0.47}$

Standard Error of Estimate = 0.35

Standard Deviation in Life = 0.94


$R^2 = 86\%$

Sample Size: 124

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.7.1.8(b). Best-fit S/N curves for notched,  $K_t = 4.0$ , PH15-7Mo (TH1050) sheet, longitudinal direction.**

Correlative Information for Figure 2.6.7.1.8(b)

Product Form: Sheet, 0.025-inch

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp, °F

Loading - Axial

Frequency - 24 and 1800 cpm

Temperature - RT

Environment - Air

201

196

RT

Specimen Details: Edge Notched,  $K_t = 4.0$   
2.25-inch gross width  
1.50-inch net width  
0.058-inch notch radius  
0° flank angle,  $\omega$

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 10.42 - 3.91 \log (S_{eq} - 32)$

$S_{eq} = S_{max} (1 - R)^{0.58}$

Standard Error of Estimate = 0.36

Standard Deviation in Life = 1.07

$R^2 = 89\%$

Surface Condition: Drilled holes near edges  
and slots milled from  
edge, corners of notch were  
beveled with rubber abrasive


Sample Size: 74

Reference: 2.6.7.1.8(b)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.7.1.8(c). Best-fit S/N curves for unnotched PH15-7Mo (TH1050) sheet at 500°F, longitudinal direction.**

Correlative Information for Figure 2.6.7.1.8(c)

Product Form: Sheet, 0.025-inch

Properties: TUS, ksi    TYS, ksi    Temp, °F

201	196	RT
179	173	500

Specimen Details: Unnotched  
2.0-inch gross width  
0.75-inch net width

Surface Condition: Machined in longitudinal direction, edges polished with 320 grit emery paper

Reference: 2.6.7.1.8(b)

Test Parameters:

Loading - Axial  
Frequency - 24 and 1800 cpm  
Temperature - 500°F  
Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 11.71 - 4.00 \log (S_{eq} - 96)$

$S_{eq} = S_{max} (1-R)^{0.70}$

Standard Error of Estimate = 0.44

Standard Deviation in Life = 1.79


$R^2 = 69\%$

Sample Size: 55

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.7.1.8(d). Best-fit S/N curves for notched,  $K_t = 4.0$ , PH15-7Mo (TH1050) sheet at 500°F, longitudinal direction.**

Correlative Information for Figure 2.6.7.1.8(d)

Product Form: Sheet, 0.025-inch

Properties: TUS, ksi    TYS, ksi    Temp, °F

201	196	RT
179	173	500

Specimen Details: Edge Notched,  $K_t = 4.0$   
 2.25-inch gross width  
 1.50-inch net width  
 0.058-inch notch radius  
 0° flank angle,  $\omega$

Surface Condition: Drilled holes near edges  
 and slots milled from  
 edge, corners of notch were  
 beveled with rubber abrasive

Reference: 2.6.7.1.8(b)

Test Parameters:

Loading - Axial

Frequency - 24 and 1800 cpm

Temperature - 500°F

Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 18.60 - 7.92 \log (S_{eq})$

$S_{eq} = S_{max} (1-R)^{0.55}$

Standard Error of Estimate = 0.41

Standard Deviation in Life = 0.86

$R^2 = 77\%$


Sample Size: 37

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 2.6.7.1.8(e). Best-fit S/N curves for PH15-7Mo (TH1050) sheet at 700°F, transverse direction.**

Correlative Information for Figure 2.6.7.1.8(e)

Product Form: Sheet, 0.050-inch

Properties: TUS, ksi    TYS, ksi    Temp, °F  
175            161            700 (LT)

Specimen Details: Unnotched  
2.0-inch gross width  
0.375-inch net width

Surface Condition: Polished in longitudinal  
direction with wet 600 grit  
silicon carbide paper

Reference: 2.6.7.1.8(c)

Test Parameters:

Loading - Axial  
Frequency - 1200 cpm  
Temperature - 700°F  
Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:


$\log N_f = 56.92 - 24.46 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.58}$   
Standard Error of Estimate = 0.77  
Standard Deviation in Life = 0.99  
 $R^2 = 39\%$

Sample Size: 17

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.7.1.8(f). Best-fit S/N curves for notched,  $K_t = 3.0$ , PH15-7Mo (TH1050) sheet at 1000°F, transverse direction.**

Correlative Information for Figure 2.6.7.1.8(f)

Product Form: Sheet, 0.050-inch

Properties: TUS, ksi    TYS, ksi    Temp, °F

88                      88                      1000 (LT)

Specimen Details: Edge Notched,  $K_t = 3.0$   
0.535-inch gross width  
0.375-inch net width  
0.021-inch notch radius  
60° flank angle,  $\omega$

Surface Condition: Polished longitudinally

Reference: 2.6.7.1.8(c)

Test Parameters:

Loading - Axial

Frequency - 1200 cpm

Temperature - 1000°F

Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 21.00 - 9.80 \log (S_{eq})$

$S_{eq} = S_{max} (1-R)^{0.78}$

Standard Error of Estimate = 0.33

Standard Deviation in Life = 0.99

$R^2 = 89\%$

Sample Size: 16

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



**MIL-HDBK-5H****1 December 1998****2.6.8 17-4PH**

**2.6.8.0 Comments and Properties** — Alloy 17-4PH is a precipitation-hardening, martensitic stainless steel used for parts requiring high strength and good corrosion and oxidation resistance up to 600°F. The alloy is available in all product forms.

*Manufacturing Considerations* — 17-4PH is readily forged, machined, welded, and brazed. Machining requires the same precautions as the austenitic stainless steels except that work-hardening is not a problem. Best machinability is exhibited by Conditions H1150 and H1150M. A dimensional contraction of 0.0004 to 0.0006 and 0.0008 to 0.0010 in./in. occurs upon hardening to the H900 and H1150 conditions, respectively. This fact should be considered before finish machining prior to aging treatment.

When permanent deformation is performed, such as cold straightening of hardened parts, reaging is recommended to minimize internal stresses.

Alloy 17-4PH can be fusion welded with any of the normal processes using 17-4PH filler metal without preheat. For details up to ½-inch thickness, Condition A is satisfactory prior to welding, but for heavy sections, an overaged condition (H1150) is recommended to preclude cracking. After welding, weldments should be aged or solution treated and aged.

Alloy 17-4PH castings are produced in sand molds, investment molds, and by centrifugal casting. While 17-4PH has good castability, it is subject to hot-tearing, so heavy X or T sections, sharp corners, and abrupt changes in section size should be avoided. Alloy 17-4PH castings are susceptible to microshrinkage which will decrease the ductility but have no effect on the yield or ultimate strength. During heat treatment, care must be exercised to avoid carbon or nitrogen contamination from furnace atmospheres. Combusted hydrocarbon and dissociated ammonia atmospheres have been sources of contamination. Air is commonly used and both vacuum and dry argon are effective for minimizing scaling. Oxides formed during solution treating in air may be removed by grit blasting or abrasive tumbling.

Alloy 17-4PH can be heat treated to develop a wide range of properties. Heat treatment procedures are specified in applicable material specifications and MIL-H-6875.

*Design and Environmental Considerations* — For tensile applications where stress corrosion is a possibility, 17-4PH should be aged at the highest temperature compatible with strength requirements and at a temperature not lower than 1025°F for 4 hours minimum.

The impact strength of 17-4PH, especially large size bar in the H900 and H925 conditions, may be very low at subzero temperatures; consequently, the use of 17-4PH for critical applications at low temperatures should be avoided. For non-impact applications, such as valve seats, parts in the H925 condition have performed satisfactorily down to -320°F. The H1100 and H1150 conditions have improved impact strength so that parts made from small diameter bar can be used down to -100°F with low risk. For critical low temperature applications, a similar alloy, 15-5PH (consumable electrode vacuum melted), should be used instead of 17-4PH because of its superior impact strength at low temperature.

*Specifications and Properties* — Material specifications for 17-4PH are presented in Table 2.6.8.0(a). Room temperature mechanical and physical properties for various conditions of 17-4PH products are presented in Table 2.6.8.0(b) through (f). The physical properties of this alloy at room and elevated temperatures are presented in Figure 2.6.8.0.

**MIL-HDBK-5H****1 December 1998****Table 2.6.8.0(a). Material Specifications for 17-4PH Stainless Steel**

Specification	Form
AMS 5604	Sheet, strip, and plate
AMS 5643	Bar, forging, and ring
AMS 5342	Investment casting (H1100)
AMS 5343	Investment casting (H1000)
AMS 5344	Investment casting (H900)

**2.6.8.1 H900 Condition** — Elevated temperature curves for various mechanical properties are presented in Figures 2.6.8.1.2 through 2.6.8.1.4. Unnotched and notched fatigue information at room temperature is presented in Figures 2.6.8.1.8(a) through (c).

**2.6.8.2 Various Heat Treat Conditions** — Elevated temperature curves for tensile yield and ultimate strengths are depicted in Figure 2.6.8.2.1. Room temperature stress-strain and tangent-modulus curves are shown in Figures 2.6.8.2.6(a) and (b).

**2.6.8.3 H1000 Condition** — Room temperature stress-strain and tangent-modulus curves for castings are shown in Figures 2.6.8.3.6(a) and (b).

**2.6.8.4 H1025 Condition** — Notched fatigue information is presented in Figure 2.6.8.4.8 for bar.

**2.6.8.5 H1100 Condition** — Notched fatigue information is presented in Figure 2.6.8.5.8 for bar.

**2.6.8.6 H1150 Condition** — Elevated temperature curves for tensile yield and ultimate strengths are shown in Figure 2.6.8.6.1.

**MIL-HDBK-5H****1 December 1998****Table 2.6.8.0(b). Design Mechanical and Physical Properties of 17-4PH Stainless Steel Sheet, Strip, and Plate**

Specification .....	AMS 5604					
Form .....	Sheet, strip <sup>a</sup> , and plate					
Condition .....	H900	H925	H1025	H1075	H1100	H1150
Thickness, in. ....	≤ 4.000					
Basis .....	S	S	S	S	S	S
Mechanical Properties:						
$F_m$ , ksi:						
L .....	...	...	...	...	...	...
LT .....	190	170	155	145	140	135
$F_y$ , ksi:						
L .....	...	...	...	...	...	...
LT .....	170	155	145	125	115	105
$F_{cy}$ , ksi:						
L .....	...	...	...	...	...	...
LT .....	...	...	...	...	...	...
$F_{su}$ , ksi .....	...	...	...	...	...	...
$F_{bru}$ , ksi:						
(e/D = 1.5) .....	...	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...	...
$F_{bry}$ , ksi:						
(e/D = 1.5) .....	...	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...	...
$e$ , percent:						
LT .....	b	b	b	b	b	b
$E$ , 10 <sup>3</sup> ksi .....	28.5					
$E_c$ , 10 <sup>3</sup> ksi .....	30.0					
$G$ , 10 <sup>3</sup> ksi .....	11.2					
$\mu$ .....	0.27					
Physical Properties:						
$\omega$ , lb/in. <sup>3</sup> .....	0.282 (H900), 0.283 (H1075), 0.284 (H1150)					
$C$ , $K$ , and $\alpha$ .....	See Figure 2.6.8.0					

a Test direction longitudinal for widths less than 9 inches; long transverse for widths 9 inches and over.

b See Table 2.6.8.0(c).

**Table 2.6.8.0(c). Minimum Elongation Values for 17-4PH Sheet, Strip, and Plate**

Thickness	e, percent (LT)					
	H900	H925	H1025	H1075	H1100	H1150
0.015 through 0.186	5	5	5	5	5	8
0.187 through 0.625	8	8	8	9	10	10
0.626 through 4.000	10	10	12	13	14	16

**MIL-HDBK-5H**  
**1 December 1998**

**Table 2.6.8.0(d). Design Mechanical and Physical Properties of 17-4PH Stainless Steel Forging, Tubing, and Rings**

Specification .....	AMS 5643						
Form .....	Forging, tubing, and rings						
Condition .....	H900	H925	H1025	H1075	H1100	H1150	H1150M <sup>a</sup>
Thickness, in. ....	<8.000						
Basis .....	S	S	S	S	S	S	S
Mechanical Properties:							
$F_m$ , ksi:							
L .....	190	170	155	145	140	135	115
T .....	...	...	...	...	...	...	...
$F_{ty}$ , ksi:							
L .....	170	155	145	125	115	105	75
T .....	...	...	...	...	...	...	...
$F_{cy}$ , ksi:							
L .....	...	...	...	...	...	...	...
T .....	...	...	...	...	...	...	...
$F_{su}$ , ksi .....	...	...	...	...	...	...	...
$F_{bru}$ , ksi:							
(e/D = 1.5) .....	...	...	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...	...	...
$F_{bry}$ , ksi:							
(e/D = 1.5) .....	...	...	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...	...	...
$e$ , percent:							
L .....	10	10	12	13	14	16	18
$E$ , 10 <sup>3</sup> ksi .....	28.5						
$E_c$ , 10 <sup>3</sup> ksi .....	30.0						
$G$ , 10 <sup>3</sup> ksi .....	11.2						
$\mu$ .....	0.27						
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> .....	0.282 (H900), 0.283 (H1075), 0.284 (H1150)						
$C$ , $K$ , and $\alpha$ .....	See Figure 2.6.8.0						

a Not covered by AMS 5643. S values are producers' guaranteed minimum tensile properties.

**MIL-HDBK-5H****1 December 1998****Table 2.6.8.0(e). Design Mechanical and Physical Properties of 17-4PH Stainless Steel Bar**

Specification . . . . .	AMS 5643										
Form . . . . .	Bar										
Condition . . . . .	H900		H925		H1025	H1075	H1100		H1150		H1150M <sup>a</sup>
Thickness or diameter, in. .	<8.000										
Basis . . . . .	A	B	A	B	S	A	B	S	A	B	S <sup>a</sup>
Mechanical Properties: <sup>°</sup>											
$F_{tu}$ , ksi:											
L . . . . .	190	195	170	178	155	143	150	140	125	134	115
T . . . . .	...	...	...	...	...	...	...	...	...	...	...
$F_{ty}$ , ksi:											
L . . . . .	170	175	155 <sup>b</sup>	167	145	125 <sup>c</sup>	143	115	100	115	75
T . . . . .	...	...	...	...	...	...	...	...	...	...	...
$F_{cy}$ , ksi:											
L . . . . .	170	175	...	...	139	...	...	...	90	104	...
T . . . . .	...	...	...	...	...	...	...	...	...	...	...
$F_{su}$ , ksi . . . . .	123	126	...	...	95	...	...	...	79	85	...
$F_{bru}$ , ksi:											
(e/D = 1.5) . . . . .	313	322	...	...	263 <sup>d</sup>	...	...	...	213 <sup>d</sup>	228 <sup>d</sup>	...
(e/D = 2.0) . . . . .	380	390	...	...	332 <sup>d</sup>	...	...	...	270 <sup>d</sup>	289 <sup>d</sup>	...
$F_{bry}$ , ksi:											
(e/D = 1.5) . . . . .	255	262	...	...	211 <sup>d</sup>	...	...	...	152 <sup>d</sup>	175 <sup>d</sup>	...
(e/D = 2.0) . . . . .	280	288	...	...	250 <sup>d</sup>	...	...	...	181 <sup>d</sup>	208 <sup>d</sup>	...
$e$ , percent (S-basis):											
L . . . . .	10	...	10	...	12	13	...	14	16	...	18
$E$ , 10 <sup>3</sup> ksi . . . . .	28.5										
$E_c$ , 10 <sup>3</sup> ksi . . . . .	30.0										
$G$ , 10 <sup>3</sup> ksi . . . . .	11.2										
$\mu$ . . . . .	0.27										
Physical Properties:											
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.282 (H900), 0.283 (H1075), 0.284 (H1150)										
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 2.6.8.0										

a Not covered by AMS 5643. S values are producer's guaranteed minimum tensile properties.

b S-basis. Rounded  $T_{99}$  value = 157 ksi.c S-basis. Rounded  $T_{99}$  value = 136 ksi.

d Bearing values are "dry pin" values per Section 1.4.7.1.

e Design allowables were based upon data from samples of material, supplied in the solution treated condition, which were aged to demonstrate response to heat treatment by suppliers.

**MIL-HDBK-5H****1 December 1998****Table 2.6.8.0(f). Design Mechanical and Physical Properties of 17-4PH Stainless Steel Investment Casting**

Specification .....	AMS 5344	AMS 5343	AMS 5342
Form .....	Investment Casting		
Condition .....	<sup>a</sup>	H1000 <sup>b</sup>	H1100 <sup>c</sup>
Location within casting .....	Any area		
Basis .....	S	S	S
Mechanical Properties <sup>d</sup> :			
$F_{tu}$ , ksi .....	180	150	130
$F_{ty}$ , ksi .....	160	130	120
$F_{cy}$ , ksi .....	...	132	...
$F_{su}$ , ksi .....	...	98	...
$F_{bru}^e$ , ksi:			
(e/D = 1.5) .....	...	254	...
(e/D = 2.0) .....	...	329	...
$F_{bry}^e$ , ksi:			
(e/D = 1.5) .....	...	189	...
(e/D = 2.0) .....	...	222	...
$e$ , percent .....	4	4	6
$RA$ , percent .....	12	12	15
$E$ , $10^3$ ksi .....	28.5		
$E_c$ , $10^3$ ksi .....	30.0		
$G$ , $10^3$ ksi .....	12.7		
$\mu$ .....	0.27		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> .....	0.282 (H900)		
$C$ , $K$ , and $\alpha$ .....	See Figure 2.6.8.0		

a Aged at 900 to 925°F for 90 minutes.

b Aged at 985 to 1015°F for 90 minutes.


c Aged at 1085 to 1115°F for 90 minutes.

d Properties apply only when drawing specifies that conformance to tensile property requirements shall be determined from specimens cut from casting or integrally cast specimens.

e Bearing values are "dry pin" values per Section 1.4.7.1.


## MIL-HDBK-5H

1 December 1998




**Figure 2.6.8.0. Effect of temperature on the physical properties of 17-4PH stainless steel.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.6.8.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of 17-4PH (H900) stainless steel bar and forging.**



**Figure 2.6.8.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of 17-4PH (H900) stainless steel bar and forging.**




**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.6.8.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of 17-4PH (H900) stainless steel bar and forging.**

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.8.1.8(a). Best-fit S/N curves for unnotched 17-4PH (H900) bar, longitudinal direction.**

Correlative Information for Figure 2.6.8.1.8(a)

Product Form: Bar, 1-inch and 1-1/8-inch diameter

Properties: TUS, ksi TYS, ksi Temp, °F

202 195 RT

Specimen Details: Unnotched  
1.25-inch gross diameter  
0.252-inch net diameter

Surface Condition: Polished

References: 2.6.8.1.8(a)

Test Parameters:

Loading - Axial

Frequency - 1800 cpm

Temperature - RT

Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 30.6 - 11.2 \log (S_{eq})$

$S_{eq} = S_{max} (1-R)^{0.52}$

Standard Error of Estimate = 0.531

Standard Deviation in Life = 0.672


$R^2 = 38\%$

Sample Size: = 42

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.8.1.8(b). Best-fit S/N curves for notched,  $K_t = 3.0$ , 17-4PH (H900) bar, longitudinal direction.**

Correlative Information for Figure 2.6.8.1.8(b)

Product Form: Bar, 1-inch and 1-1/8-inch diameter

Test Parameters:

Loading - Axial

Frequency - Not specified

Temperature - RT

Environment - Air

Properties: TUS, ksi    TYS, ksi    Temp, °F

202

195

RT

Specimen Details: Circumferential V-Groove,  
 $K_t = 3.0$

No. of Heats/Lots: Not specified

Gross diameter inches	Net diameter inches	Notch radius inches
0.430	0.300	0.016
0.357	0.252	0.013

Equivalent Stress Equation:

$$\log N_f = 9.10 - 2.79 \log (S_{eq} - 48.4)$$

$$S_{eq} = S_{max} (1-R)^{0.67}$$

Standard Error of Estimate = 0.235

Standard Deviation in Life = 0.897

$R^2 = 93\%$

60° flank angle,  $\omega$

Sample Size: 39


Surface Condition: Polished

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

Reference: 2.6.8.1.8(a)

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.8.1.8(c). Best-fit S/N curves for notched,  $K_t = 4.0$ , 17-4PH (H900) bar, longitudinal direction.**

Correlative Information for Figure 2.6.8.1.8(c)

Product Form: Bar, 0.787-inch diameter,  
vacuum melted

Properties: TUS, ksi TYS, ksi Temp, °F

207 — RT

Specimen Details: Circumferential  
V-Groove,  $K_t = 4.0$   
0.492-inch gross diameter  
0.256-inch net diameter  
0.008-inch notch radius, n  
60° flank angle,  $\omega$

Surface Condition: Machined and aged

Reference: 2.6.8.1.8(b)

Test Parameters:

Loading - Axial

Frequency - 2000 cpm

Temperature - RT

Environment - Air

No. of Heats/Lots: 1

Equivalent Stress Equation:

$\log N_f = 9.03 - 2.91 \log (S_{eq} - 26.1)$

$S_{eq} = S_{max} (1-R)^{0.51}$

Standard Error of Estimate = 0.345


Standard Deviation in Life = 0.812

$R^2 = 82\%$

Sample Size: = 22

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.6.8.2.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of 17-4PH (H900, H925, H1025, and H1075) stainless steel bar.**

MIL-HDBK-5H  
1 December 1998




Figure 2.6.8.2.6(a). Typical tensile stress-strain curves at room temperature for various heat treated conditions of 17-4PH stainless steel bar.






Figure 2.6.8.2.6(b). Typical compressive stress-strain and compressive tangent-modulus curves at room temperature for various heat treated conditions of 17-4PH stainless steel bar.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 2.6.8.3.6(a). Typical tensile stress-strain curve for 17-4PH (H1000) stainless steel casting at room temperature.**



**Figure 2.6.8.3.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 17-4PH (H1000) stainless steel casting at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 2.6.8.4.8. Best-fit S/N curves for notched,  $K_t = 3.0$ , fatigue behavior of 17-4PH (H1025) stainless steel bar, longitudinal and long transverse directions.**

Correlative Information for Figure 2.6.8.4.8

Product Form: Bar, 2 x 6 inches

Test Parameters:

Loading - Axial

Frequency - 1800 cpm

Temperature - RT

Environment - Air

Properties: TUS, ksi TYS, ksi Temp, °F

Longitudinal 165 161 RT

Long 164 158 RT

Transverse

Longitudinal 280 — RT  
(notched)

Long 275 — RT  
Transverse (notched)

No. of Heats/Lots: 3

Equivalent Stress Equation:

$\log N_f = 21.60 - 9.24 \log (S_{eq})$

$S_{eq} = S_{max} (1-R)^{0.581}$

Standard Error of Estimate = 0.413

Standard Deviation in Life = 0.724

$R^2 = 67\%$

Specimen Details: Notched V-Groove,  $K_t = 3.0$   
0.375-inch gross diameter  
0.250-inch net diameter  
0.013-inch root radius, r  
60° flank angle,  $\omega$

Sample Size: = 44

Surface Condition: Notched: Ground notch


[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

Reference: 2.6.6.2.8



## MIL-HDBK-5H

1 December 1998



**Figure 2.6.8.5.8. Best-fit S/N curves for notched,  $K_t = 4.0$ , 17-4PH (H1100) bar, longitudinal direction.**

Correlative Information for Figure 2.6.8.5.8

Product Form: Bar, 0.787-inch diameter

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp, °F

Loading - Axial

Frequency - 2000 cpm

Temperature - RT

Environment - Air

151 — RT

Specimen Details: Circumferential V-Groove,

No. of Heats/Lots:

$K_t = 4.0$

Equivalent Stress Equation:

0.492-inch gross diameter

$\log N_f = 14.6 - 5.56 \log (S_{eq})$

0.256-inch net diameter

$S_{eq} = S_{max} (1-R)^{0.69}$

0.008-inch notch radius, r

Standard Error of Estimate = 0.301

60° flank angle,  $\omega$

Standard Deviation in Life = 0.556

Surface Condition: Machined then aged


$R^2 = 71\%$

Reference: 2.6.8.1.8(b)

Sample Size: = 21

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.6.8.6.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of 17-4PH (H1150) stainless steel bar.**

**MIL-HDBK-5H****1 December 1998****2.6.9 17-7PH**

**2.6.9.0 Comments and Properties** — 17-7PH is a semiaustenitic stainless steel used where high strength and good corrosion and oxidation resistance are needed up to 600°F. This steel is supplied in Condition A for ease of forming.

*Manufacturing Considerations* — 17-7PH in Condition A is readily cold formed. Conventional inert-gas shielded arc and resistance techniques are generally used for welding. Vapor blasting of scaled Condition TH1050 parts is recommended because of the hazards of intergranular corrosion during pickling operations.

*Heat Treatment* — 17-7PH must be used in the heat-treated condition and should not be placed in service in Condition A or T. Condition A should be restored by resolution treating when this condition has been altered during processing operations such as hot working, welding, or brazing. The heat-treatment procedures for this steel are compatible with the cycles used for honeycomb panel brazing. In hardening this steel from Condition A to Condition TH1050 a net dimensional growth of 0.0045 in./in. will occur.

The heat treatment to anneal is:

<u>Treatment</u>	<u>Designation</u>
1950 ± 25°F and air cool	Condition A

The transformation treatment from Condition A is as follows:

<u>Treatment</u>	<u>Designation</u>
1400 ± 25°F - 90 minutes and cool to 55 ± 5°F for 30 minutes	Condition T

The aging treatment is:

<u>Treatment</u>	<u>Designation</u>
1050 ± 10°F - 90 minutes and air cool	TH1050

*Environmental Considerations* — The resistance of 17-7PH to stress-corrosion cracking in chloride environs has been evaluated and found to be superior to that of the alloy steels and the hardenable chromium steels. Strength properties are lowered by exposure to temperatures above about 975°F for periods longer than one-half hour.

*Specifications and Properties* — Material specifications for 17-7PH stainless steel is presented in Table 2.6.9.0(a). The room-temperature properties of 17-7PH are shown in Tables 2.6.9.0(b) and (c). The effect of temperature on the physical properties of this alloy are presented in Figure 2.6.9.0.

**Table 2.6.9.0(a). Material Specification for 17-7PH Stainless Steel**

Specification	Form
AMS 5528	Plate, sheet, and strip
MIL-S-25043	Plate, sheet, and strip

**MIL-HDBK-5H****1 December 1998****Table 2.6.9.0(b). Design Mechanical and Physical Properties of 17-7PH Stainless Steel Sheet and Plate**

Sheet and Plate		AMS 5528 and MIL-S-25043		AMS 5528	
Specification	Form	Sheet		Plate	
Condition	Thickness, in.	TH1050			
Basis		0.015-0.187		0.188-0.500	0.501-1.000
		A	B	S	S
Mechanical Properties: <sup>a</sup>					
$F_{tu}$ , ksi:					
L		177	183	...	...
LT		177	184	180	180
$F_{ty}$ , ksi:					
L		150 <sup>b</sup>	167	...	...
LT		150 <sup>c</sup>	167	150	150
$F_{cy}$ , ksi:					
L		160	179	160	...
LT		166	185	166	...
$F_{su}$ , ksi		112	117	114	...
$F_{bru}$ , ksi:					
(e/D = 1.5)		305	317	310	...
(e/D = 2.0)		351	365	357	...
$F_{bry}$ , ksi:					
(e/D = 1.5)		228	254	228	...
(e/D = 2.0)		240	267	240	...
$e$ , percent (S-basis):					
LT		d,e	...	6 <sup>e</sup>	6
$E$ , 10 <sup>3</sup> ksi		29.0			
$E_c$ , 10 <sup>3</sup> ksi		30.0			
$G$ , 10 <sup>3</sup> ksi		11.5			
$\mu$		0.28			
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup>		0.276			
$C$ , $K$ , and $\alpha$		See Figure 2.6.9.0			

a Design allowables were based upon data from samples of material, supplied in the solution treated condition, which were austenite conditioned and aged to demonstrate response to heat treatment by suppliers. Properties obtained by the user may be different if the material has been formed or otherwise cold worked.

b The rounded  $T_{99}$  value of 158 ksi was reduced to agree with transverse specification value.

c S-Basis. The rounded  $T_{99}$  value equals 159 ksi.

d See Table 2.6.9.0(c).


e For MIL-S-25043, elongation values may be different than those presented.

**MIL-HDBK-5H****1 December 1998**


**2.6.9.1 TH1050 Condition** — Elevated temperature curves for various mechanical properties are presented in Figures 2.6.9.1.1, 2.6.9.1.2, and 2.6.9.1.4(a) and (b). Tensile and compression stress-strain curves at room temperature and at several elevated temperatures are presented in Figures 2.6.9.1.6(a) and (b). Typical compressive tangent-modulus curves at various temperatures are presented in Figure 2.6.9.1.6(c).

**Table 2.6.9.0(c). Minimum Elongation Values for 17-7PH (TH1050) Stainless Steel Sheet**


Thickness, in.	Elongation (LT), percent
0.005 to 0.010	4
0.011 to 0.019	5
0.020 to 0.187	6




**Figure 2.6.9.0. Effect of temperature on the physical properties of 17-7PH stainless steel.**

**MIL-HDBK-5H****1 December 1998**


**Figure 2.6.9.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ), tensile yield strength ( $F_{ty}$ ), and compressive yield strength ( $F_{cy}$ ) of 17-7PH (TH1050) stainless steel sheet.**



**Figure 2.6.9.1.2. Effect of temperature on the ultimate shear strength ( $F_{su}$ ) of 17-7PH (TH1050) stainless steel sheet.**


**MIL-HDBK-5H****1 December 1998**

**Figure 2.6.9.1.4(a). Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of 17-7PH (TH1050) stainless steel sheet.**




**Figure 2.6.9.1.4(b). Effect of temperature on Poisson's ratio ( $\mu$ ) for 17-7PH (TH1050) stainless steel sheet.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.6.9.1.6(a). Typical tensile stress-strain curves at various temperatures for 17-7PH (TH1050) stainless steel sheet.**



**Figure 2.6.9.1.6(b). Typical compressive stress-strain curves at various temperatures for 17-7PH (TH1050) stainless steel sheet.**



MIL-HDBK-5H  
1 December 1998




Figure 2.6.9.1.6(c). Typical compressive tangent-modulus curves at various temperatures for 17-7PH (TH1050) stainless steel sheet.

## 2.7 AUSTENITIC STAINLESS STEELS

### 2.7.0 COMMENTS ON AUSTENITIC STAINLESS STEEL

**2.7.0.1 Metallurgical Considerations** — The austenitic (“18-8”) stainless steels were developed as corrosion-resistant alloys. However, they possess excellent oxidation resistance and good creep strength at elevated temperatures, along with good cold formability and other properties in airframe and missile applications. They are used in sheet form for portions of the airframe having ambient temperatures too high for aluminum alloys and, with the development of sandwich structures, are gaining additional uses. These steels are also used extensively at cryogenic temperatures.

The two alloying elements in the austenitic stainless steels are chromium and nickel. Chromium adds corrosion and oxidation resistance and high-temperature strength, and nickel gives an austenitic structure, with its associated toughness and ductility. The AISI 300 series stainless steels constitute a wide variety of compositions designed for different applications. The basic grade, Type 302, contains 18 percent chromium and 8 percent nickel. Varying one or both of these elements creates special characteristics. Type 301 (17 percent chromium and 7 percent nickel) work hardens to very high strengths. Type 310 (25 percent chromium and 20 percent nickel) has higher elevated temperature strength and greater oxidation resistance than Type 302. Sulfur and selenium additions promote free machining. Low carbon and/or columbium or titanium additions minimize intergranular corrosion for elevated temperature applications and welded construction. The addition of molybdenum improves corrosion resistance in reducing environments and gives improved creep resistance over Type 302. The characteristics of some of the AISI 300 series stainless steels are presented in Table 2.7.0.1.

These alloys are not hardenable by heat treatment but can achieve high-strength levels through cold working. The strength imparted by cold working is decreased by exposure to temperatures above about 900°F.

#### 2.7.0.2 Manufacturing Considerations —

*Forging* — The stainless steels have lower thermal conductivity than lower alloy steels and are susceptible to grain growth at forging temperatures. Hence, soaking times must be adequate to permit thorough heating of the billet but must be controlled carefully to limit grain growth when small reductions are involved during forging. At forging temperatures, the stainless steels are stronger than alloy steels, and forging must be conducted at higher temperatures and heavier forging equipment and more frequent reheating are required. The stainless steel billets forge much better when the surface is free of defects, and machine turning of the billets is advisable.

*Cold Forming* — Because of their austenitic structure at room temperature, the stainless steels have excellent ductility for cold-forming operations when in the annealed condition. These steels work harden rapidly, and intermediate anneals may be required in deep drawing.

*Machining* — The machining of the austenitic stainless steels is not difficult if proper steps are taken to combat the work-hardening tendencies of these steels. The use of heavy machines, slow speeds, deep cuts, and properly designed cutting tools with a fairly steep top rake produces the best results. Cold-worked material possesses somewhat better machinability than hot-finished, annealed material. These steels also are available in free-machining grades, containing sulfur or selenium.

*Welding* — The austenitic stainless steels can be welded by almost any usual technique except carbon arc, provided adequate steps are taken to prevent oxidation or carburization of the weldment. The stabilized grades are preferred for welded parts that are used in the as-welded condition under corrosive conditions. The free-machining grades are not recommended for welding. Filler rods should be the same composition, or

**MIL-HDBK-5H****1 December 1998****Table 2.7.0.1. Characteristics of Some AISI 300 Series Stainless Steels**

AISI	Characteristics
301	High work-hardening rate; applications requiring high strength and ductility.
302	Higher carbon modification of Type 304 for higher strength on cold rolling.
303	Free machining sulfur modification of Type 302.
303Se	Free machining selenium modification of Type 302.
304	General purpose austenitic grade for enhanced corrosion resistance.
304L	Low-carbon modification of Type 304 for welding applications.
305	Low work-hardening rate; spin forming and severe spin drawing operations.
309	High-temperature strength and oxidation resistance.
309S	Low-carbon modification of Type 309 for welded construction.
310	High-temperature strength and oxidation resistance greater than Type 309.
310S	Low-carbon modification of Type 310 for welded construction.
314	Increased oxidation resistance over Type 310.
316	Mo added to improve corrosion resistance in reducing environments; improved creep resistance over Type 302.
316L	Low-carbon modification of Type 316 for welded construction.
317	Increased Mo to improve corrosion resistance over Type 316 in reducing media.
321	Titanium stabilized for service in 800 to 1600°F range and to minimize carbide precipitation when welding for resistance to intergranular corrosion.
347	Columbium stabilized for service in 800 to 1600°F range and to minimize carbide precipitation when welding for resistance to intergranular corrosion.

slightly higher in alloy content, as the material to be welded. Special fluxes designed for use with stainless steels should be employed, except in atomic hydrogen or inert-gas-shielded arc welding. Spot and roll seam welding also are used to a considerable extent.

*Brazing* — Special techniques have been developed for silver-soldering and brazing these steels. Solders and fluxes especially designed should be used, surfaces must be thoroughly cleaned, and close control of temperature must be followed.

**2.7.0.3 Environmental Considerations** — The austenitic stainless steels have excellent oxidation resistance at high temperatures, and their elevated-temperature service is usually limited by strength criteria. They also possess unusually good resistance to corrosion by most media. Prolonged exposure of the nonstabilized grades to temperatures between 700 and 1650°F makes them susceptible to intergranular corrosion.

**MIL-HDBK-5H****1 December 1998****2.7.1 AISI 301**

**2.7.1.0 Comments and Properties** — Of the austenitic stainless steels, AISI 301 is the one most frequently used at high-strength levels in aircraft, mainly because of its greater work-hardening characteristics.

Type 301 is strengthened by cold working. If cold-worked Type 301 is subjected to temperatures above 900°F, its room-temperature strength is reduced.

Type 301 should not be used for extended periods at temperatures of 750 to 1650°F and should not be cooled slowly from higher temperatures through this range.

Material specifications for AISI 301 stainless steel are presented in Table 2.7.1.0(a). The room-temperature mechanical and physical properties for AISI 301 stainless steel are presented in Tables 2.7.1.0(b) and (c). The physical properties of this alloy at room and elevated temperatures are presented in Figure 2.7.1.0.

**Table 2.7.1.0(a). Material Specifications for AISI 301 Stainless Steel**

Specification	Form
MIL-S-5059	Plate, sheet, and strip
AMS 5517	Sheet and strip
AMS 5518	Sheet and strip
AMS 5519	Sheet and strip

**2.7.1.1 Annealed Condition** — Elevated temperature curves for tensile yield and ultimate strengths are presented in Figures 2.7.1.1.1(a) and (b).

**2.7.1.2 1/4 Hard Condition** — Typical room-temperature stress-strain and tangent-modulus curves are presented in Figures 2.7.1.2.6(a) and (b).

**2.7.1.3 1/2 Hard Condition** — Elevated temperature curves for various mechanical properties are presented in Figures 2.7.1.3.1 through 2.7.1.3.4. Typical stress-strain and tangent-modulus curves are presented in Figures 2.7.1.3.6(a) and (b).

**2.7.1.4 3/4 Hard Condition** — Typical room-temperature stress-strain and tangent-modulus curves are presented in Figures 2.7.1.4.6(a) and (b).

**2.7.1.5 Full-Hard Condition** — The full-hard condition is a standard AISI temper and is developed by cold rolling 40 to 50 percent. Elevated temperature curves for various mechanical properties are presented in Figure 2.7.1.5.1 through 2.7.1.5.4. Tensile and compressive stress-strain as well as tangent-modulus curves at room temperature and several elevated temperatures are presented in Figures 2.7.1.5.6(a) through (d).

**MIL-HDBK-5H****1 December 1998****Table 2.7.1.0(b). Design Mechanical and Physical Properties of AISI 301 and Other<sup>a</sup> Annealed Stainless Steel**

Annealed Stainless Steel									
Specification . . . . .	MIL-S-5059	AMS 5517 & MIL-S-5059		AMS 5518 & MIL-S-5059		MIL-S-5059		AMS 5519 & MIL-S-5059	
Form . . . . .	Sheet and strip								
Condition . . . . .	Annealed <sup>a</sup>	¼ Hard		½ Hard		¾ Hard		Full Hard	
Thickness, in. . . . .	≤0.187	...		...		...		...	
Basis . . . . .	S	A	B	A	B	A	B	A	B
Mechanical Properties:									
$F_{tu}$ , ksi:									
L . . . . .	73	124	129	141	151	157	168	174	185
LT . . . . .	75	122	127	142	152	163	173	175	186
$F_{ty}$ , ksi:									
L . . . . .	26	69	83	93	110	118	135	137	153
LT . . . . .	30	67	82	92	105	113	133	125	142
$F_{cy}$ , ksi:									
L . . . . .	23	44	54	61	69	75	88	83	94
LT . . . . .	29	71	88	100	116	127	152	142	164
$F_{su}$ , ksi . . . . .	50	66	69	77	82	88	93	95	100
$F_{bru}$ , ksi:									
(e/D = 1.5) . . . . .	...	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	162	262	273	292	310	327	342	346	361
$F_{bry}$ , ksi:									
(e/D = 1.5) . . . . .	...	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	55	123	149	167	189	202	234	222	249
$e$ , percent (S basis):									
LT . . . . .	40	25	...	b	...	b	...	b	...
$E$ , 10 <sup>3</sup> ksi:									
L . . . . .	29.0	27.0		26.0		26.0		26.0	
LT . . . . .	29.0	28.0		28.0		28.0		28.0	
$E_c$ , 10 <sup>3</sup> ksi:									
L . . . . .	28.0	26.0		26.0		26.0		26.0	
LT . . . . .	28.0	27.0		27.0		27.0		27.0	
$G$ , 10 <sup>3</sup> ksi . . . . .	11.2	10.6		10.5		10.5		10.5	
$\mu$ . . . . .	0.27	0.27		0.27		0.27		0.27	
Physical Properties:									
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.286								
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 2.7.1.0								


a Properties for annealed (solution heat treated) condition also applicable to AISI 301 plate and to AISI 302, 303, 304, 321, and 347 sheet, strip, and plate, supplied to industry specifications.

b See Table 2.7.1.0(c).


Note: Yield strength, particularly in compression, and modulus of elasticity in the longitudinal direction may be raised appreciably by thermal stress-relieving treatment in the range 500 to 800 °F.

**MIL-HDBK-5H****1 December 1998****Table 2.7.1.0(c). Minimum Elongation Values for AISI 301 Stainless Steel Sheet and Strip**

Condition	Thickness, inches	Elongation (LT), percent
½ hard .....	0.015 and under	15
	0.016 and over	18
¾ hard .....	0.015 and under	10
	0.016 and over	12
Full hard .....	0.015 and under	8
	0.016 and over	9


**Figure 2.7.1.0. Effect of temperature on the physical properties of AISI 301 stainless steel.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.7.1.1.1(a). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of AISI 301, 302, 304, 304L, 321, and 347 annealed stainless steel.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.7.1.1(b). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of AISI 301, 302, 304, 304L, 321, and 347 annealed stainless steel.**



MIL-HDBK-5H  
1 December 1998




Figure 2.7.1.2.6(a). Typical tensile stress-strain curves at room temperature for AISI 301 1/4-hard stainless steel sheet.






Figure 2.7.1.2.6(b). Typical compressive stress-strain and compressive tangent-modulus curves at room temperature for AISI 301 1/4-hard stainless steel sheet.

## MIL-HDBK-5H

1 December 1998




**Figure 2.7.1.3.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of AISI 301 1/2-hard stainless steel sheet.**




**Figure 2.7.1.3.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of AISI 301 1/2-hard stainless steel sheet.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.7.1.3.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of AISI 301 1/2-hard stainless steel sheet.**



**Figure 2.7.1.3.4. Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of AISI 301 1/2-hard stainless steel sheet.**

MIL-HDBK-5H  
1 December 1998




Figure 2.7.1.3.6(a). Typical tensile stress-strain curves at room temperature for AISI 301 1/2-hard stainless steel sheet.




Figure 2.7.1.3.6(b). Typical compressive stress-strain and compressive tangent-modulus curves at room temperature for AISI 301 1/2-hard stainless steel sheet.

MIL-HDBK-5H  
1 December 1998




Figure 2.7.1.4.6(a). Typical tensile stress-strain curves at room temperature for AISI 301 3/4-hard stainless steel sheet.







Figure 2.7.1.4.6(b). Typical compressive stress-strain and compressive tangent-modulus curves at room temperature for AISI 301 3/4-hard stainless steel sheet.

**MIL-HDBK-5H****1 December 1998**


**Figure 2.7.1.5.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of AISI 301 full-hard stainless steel sheet.**

**MIL-HDBK-5H****1 December 1998**


**Figure 2.7.1.5.2(a). Effect of temperature on the compressive yield strength ( $F_{cy}$ ) of AISI 301 (full-hard) stainless steel sheet.**



**Figure 2.7.1.5.2(b). Effect of temperature on the ultimate shear strength ( $F_{su}$ ) of AISI 301 (full-hard) stainless steel sheet.**

**MIL-HDBK-5H****1 December 1998**

**Figure 2.7.1.5.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of AISI 301 (full-hard) stainless steel sheet.**



**Figure 2.7.1.5.4. Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of AISI 301 (full-hard) stainless steel sheet.**



## MIL-HDBK-5H

1 December 1998




Figure 2.7.1.5.6(a). Typical tensile stress-strain curves at room and elevated temperatures for AISI 301 (full-hard) stainless steel sheet.




Figure 2.7.1.5.6(b). Typical tensile stress-strain curves at room and elevated temperatures for AISI 301 (full-hard) stainless steel sheet.

MIL-HDBK-5H

1 December 1998




Figure 2.7.1.5.6(c). Typical compressive stress-strain and compressive tangent-modulus curves at room and elevated temperatures for AISI 301 (full-hard) stainless steel sheet.




Figure 2.7.1.5.6(d). Typical compressive stress-strain and compressive tangent-modulus curves at room and elevated temperatures for AISI 301 (full-hard) stainless steel sheet.

**MIL-HDBK-5H****1 December 1998****2.8 ELEMENT PROPERTIES****2.8.1 BEAMS**

See Equation 1.3.2.3, Section 1.5.2.5, and References 1.7.1(a) and (b) for general information on stress analysis of beams.

**2.8.1.1 Simple Beams** — Beams of solid, tubular, or similar cross sections, not subject to instability (buckling, crippling, column, lateral bending) can be assumed to fail through exceeding an allowable modulus of rupture in bending,  $F_b$ , the value of which will depend upon beam cross-section geometry and beam material stress-strain characteristics. The modulus of rupture in bending is further discussed in Section 1.5.2.5. See Reference 2.8.1.1.

*Round Tubes* — For round tubes, the value of  $F_b$  will depend on the D/t ratio, as well as the ultimate tensile stress. Figures 2.8.1.1(a) and (b) give the bending modulus of rupture for round alloy-steel tubing.

*Unconventional Cross Sections* — Sections other than solid or tubular should be tested to determine the allowable bending stress.

**2.8.1.2 Built-Up Beams** — Built-up beams usually fail because of local failures of the component parts. In welded steel tube beams, the allowable tensile stresses should be reduced properly for the effects of welding.


**2.8.1.3 Thin-Web Beams** — The allowable stresses for thin-web beams will depend on the nature of the failure and are determined from the allowable stresses of the web in tension and of the flanges and stiffeners in compression.

**2.8.2 COLUMNS**

**2.8.2.1 General** — The general formula for primary instability is given in Section 1.3.8. Both primary and local instability are discussed in Section 1.6.

**2.8.2.2 Effects of Welding** — The primary failure stress of a column having welded ends can be determined from column curves or the column formula with the restriction that the column stress shall not exceed a “cut-off” stress which accounts for the effect of welding on the local failure of the column.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.8.1.1(a). Bending modulus of rupture for round low-alloy steel tubing.**

## MIL-HDBK-5H

1 December 1998





Figure 2.8.1.1(b). Bending modulus of rupture for round high-alloy steel tubing.

**MIL-HDBK-5H****1 December 1998****2.8.3 TORSION**

**2.8.3.1 General** — The torsion failure of steel tubes may be due to material failure, or to elastic or plastic buckling. Pure shear failure usually will not occur within the range of wall thickness commonly used for aircraft tubing.

**2.8.3.2 Torsion Properties** — The curves of Figures 2.8.3.2(a) through (j) are derived from the method outlined in Reference 2.8.3.2 and take into account the parameter  $L/D$ ; the theoretical results set forth in Reference 2.8.3.2 have been found to be in good agreement with the experimental results.



**Figure 2.8.3.2(a). Torsional modulus of rupture—plain carbon steels  $F_{tu} = 55$  ksi.**

## MIL-HDBK-5H

1 December 1998




Figure 2.8.3.2(b). Torsional modulus of rupture—low-alloy steels treated to  $F_{tu} = 90$  ksi.




Figure 2.8.3.2(c). Torsional modulus of rupture—low-alloy steels heat treated to  $F_{tu} = 95$  ksi.

## MIL-HDBK-5H

1 December 1998




Figure 2.8.3.2(d). Torsional modulus of rupture—low-alloy steels, heat treated to  $F_{tu} = 125$  ksi.




Figure 2.8.3.2(e). Torsional modulus of rupture—low-alloy steels heat treated to  $F_{tu} = 150$  ksi.



## MIL-HDBK-5H

1 December 1998




Figure 2.8.3.2(f). Torsional modulus of rupture—alloy steels heat treated to  $F_{tu} = 180$  ksi.






Figure 2.8.3.2(g). Torsional modulus of rupture—alloy steels heat treated to  $F_{tu} = 200$  ksi.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 2.8.3.2(h). Torsional modulus of rupture—alloy steels heat treated to  $F_{tu} = 220$  ksi.**



**Figure 2.8.3.2(i). Torsional modulus of rupture—alloy steels heat treated to  $F_{tu} = 240$  ksi.**

MIL-HDBK-5H  
1 December 1998




Figure 2.8.3.2(j). Torsional modulus of rupture—alloy steels heat treated to  $F_{tu} = 260 \text{ ksi}$ .

**MIL-HDBK-5H****1 December 1998****REFERENCES**

- 2.2.0.3(a) "Low Temperature Properties of Ferrous Materials," Society of Automotive Engineers, Special Publication SP-61 (1950).
- 2.2.0.3(b) "The Selection of Steel for Notch Toughness," ASM Metals Handbook, 8th Edition, Vol. I, pp. 225-243 (1961).
- 2.3.0.2.5 "Heat Treating," ASM Handbook, Volume 4, 1991.
- 2.3.1.3.8(a) Brodrick, R. F., and Rich, E. L., "Evaluation of the Fatigue Properties of SAE 4340. Thermold J, and Tricent Steel Under Axial Loading Conditions," Technical Report No. 588/c39, Lessells and Associates (July 30, 1958) (MCIC 109748).
- 2.3.1.3.8(b) Trapp, W. J., "Elevated Temperature Fatigue Properties of SAE 4340 Steel," WADC TR 52-325, Part I (December 1952).
- 2.3.1.3.8(c) Oberg, T. T., and Ward, E. J., "Fatigue of Alloy Steels at High Stress Levels," Wright Air Dev. Center TR 53-256 (October 1953) (MCIC 108310).
- 2.3.1.3.8(d) Thrash, C. V., "Evaluation of High Strength Steels for Heavy Section Applications," Douglas Aircraft Engineering TR No. LB-32437 (November 29, 1965) (MCIC 70834).
- 2.3.1.4.8(a) Deel, O. L., and Mindlin, H., "Engineering Data on New and Emerging Structural Materials," AFML-TR-70-252 (October 1970) (MCIC 79662).
- 2.3.1.4.8(b) Bateh, E. J., "300M Steel Fatigue Program Structural Requirements," Lockheed-Georgia Report No. 72-26-591 (January 5, 1967) (MCIC 74342).
- 2.3.1.4.8(c) Harmsworth, C. L., "Low Cycle Fatigue Evaluation of Titanium 6Al-6V-2Sn and 300-M Steel for Landing Gear Applications," AFML-TR-69-48 (June 1969) (MCIC 75621).
- 2.3.1.4.8(d) Thrash, C. V., "Evaluation of High Strength Steels for DC-10," Douglas Aircraft Company Report No. ETR-DAC-67520 (May 27, 1969) (MCIC 110145).
- 2.3.1.4.8(e) Boswell, L. E., et al., "Fatigue Test for Landing Gear Material 300M Forgings," Vought Corporation Report No. 70-59910-047 (May 22, 1970) (MIL-HDBK-5 Source M-74).
- 2.3.1.4.9(a) Dill, D. H., "Evaluation of Steel Alloys 300M, HP-9Ni-4Co-0.20, HP-9Ni-4Co-0.30, and PH13-8Mo," Report MDC-A2639, McDonnell Aircraft Co., McDonnell Douglas Corp. (December 21, 1973) (MCIC 88136).
- 2.3.1.4.9(b) "B-1 Program da/dN Data for Steel Alloys," Rockwell International Corp., Memorandum to N. D. Moran from E. W. Cawthorne, Battelle, Columbus, Ohio (April 3, 1974) (MCIC 88579).
- 2.3.1.5.9 Feddersen, C. E., et al., "Crack Behavior in D6AC Steel," Report MCIC 72-04, Battelle, Columbus, Ohio (January 1972).
- 2.4.3.1.8 Bullock, D. E., et al., "Evaluation of Mechanical Properties of 9Ni-4Co Steel Forgings," AFML-TR-68-57 (March 1968).

**MIL-HDBK-5H****1 December 1998**

- 2.5.0.2 Kozol, J. and Neu, C.E., "Stress Corrosion Susceptibility of Ultra-High Strength Steels for Naval Aircraft Applications," Report No. NAWCADWAR-9208-60 (January 10, 1992) (MIL-HDBK-5 Source M-805).
- 2.6.3.1.8 Technical Memorandum (Progress Report), "Evaluation of Custom 455 and Custom 450 for MIL-HDBK-5," Carpenter Technology (November 14, 1974) (MIL-HDBK-5 Source M-350).
- 2.6.5.1.8(a) Deel, O. L., and Mindlin, H., "Engineering Data on New Aerospace Structural Materials," AFML-TR-72-196, Vol. II (September, 1972) (MCIC 85292) (MIL-HDBK-5 Source M-466).
- 2.6.5.1.8(b) Deel, O. L., and Mindlin, H., "Fatigue Evaluation of PH13-8Mo Stainless Steel," Battelle Memorial Institute (July 31, 1970) (MCIC 79332) (MIL-HDBK-5 Source M-34).
- 2.6.5.1.8(c) Unpublished data, Lockheed-Georgia Company, Report No. ER 9347 (October 2, 1968) (MIL-HDBK-5 Source M-44).
- 2.6.5.1.8(d) Unpublished data, Letter report to Paul Ruff from ARMCO (March 29, 1972) (MIL-HDBK-5 Source M-141).
- 2.6.6.2.8(a) Unpublished data, Armco Research Lab, Armco Steel Corp., Baltimore, Maryland (April 11, 1977) (MIL-HDBK-5 Source M-364).
- 2.6.6.2.8(b) Doepper, P. E., "Effect of Manufacturing Process on Structural Allowables," AFWAL-TR-85-4049 (May 1985) (MIAC 126632).
- 2.6.7.1.8(a) Illg, W., and Castle, C. B., "Fatigue of Four Stainless Steels and Three Titanium Alloys Before and After Exposure to 550°F—Up to 8800 Hours," Langley Research Center, NASA TN D-2899 (July 1965) (MCIC 61319) (MIL-HDBK-5 Source M-579).
- 2.6.7.1.8(b) Illg, W., and Castle, C. B., "Axial-Load Fatigue Properties of PH15-7Mo Stainless Steel in Condition TH1050 at Ambient Temperature and 500°F," Langley Research Center, NASA TN D-2358 (July 1964) (MCIC 56366).
- 2.6.7.1.8(c) Roach, T. A., "Development of Fatigue Data for Several Alloys for Use in Aerospace Design," Air Force Flight Dynamics Laboratory, Air Force Systems Command, Wright-Patterson Air Force Base, Ohio, Technical Report AFML-TR-69-175 (June 1969) (MCIC 76622) (MIL-HDBK-5 Source M-316).
- 2.6.8.1.8(a) Wolanski, Z. R., "Material Evaluation—17-4PH Cres, H-900 Condition Fatigue Characteristics," General Dynamics—Fort Worth (June 12, 1964) (MCIC 66105).
- 2.6.8.1.8(b) Larsson, N., "Fatigue Testing of Precipitating Steel 17-4PH With Aging as the Final Process," Aeronautical Research Institute of Sweden, Technical Note HU-1964 (August 1978) (MCIC 106285).
- 2.8.1.1 Ades, C. S., "Bending Strength of Tubing in the Plastic Range," Journal of the Aeronautical Sciences, Vol. 24, pp 605-610 (1957).
- 2.8.3.2 Lee, L.H.N., and Ades, C. S., "Plastic Torsional Buckling Strength of Cylinders Including the Effects of Imperfections," Journal of the Aeronautical Sciences, Vol. 24, No. 4, pp 241-248 (April 1957).

**MIL-HDBK-5H**  
**1 December 1998**

This page intentionally blank.

**CHAPTER 3****ALUMINUM****3.1 GENERAL**

This chapter contains the engineering properties and related characteristics of wrought and cast aluminum alloys used in aircraft and missile structural applications.

General comments on engineering properties and the considerations relating to alloy selection are presented in Section 3.1. Mechanical and physical property data and characteristics pertinent to specific alloy groups or individual alloys are reported in Sections 3.2 through 3.10. Element properties are presented in Section 3.11.

Aluminum is a lightweight, corrosion-resistant structural material that can be strengthened through alloying and, dependent upon composition, further strengthened by heat treatment and/or cold working [Reference 3.1(a)]. Among its advantages for specific applications are: low density, high strength-to-weight ratio, good corrosion resistance, ease of fabrication and diversity of form.

Wrought and cast aluminum and aluminum alloys are identified by a four-digit numerical designation, the first digit of which indicates the alloy group as shown in Table 3.1. For structural wrought aluminum alloys the last two digits identify the aluminum alloy. The second digit indicates modifications of the original alloy or impurity limits. For cast aluminum and aluminum alloys the second and third digits identify the aluminum alloy or indicate the minimum aluminum percentage. The last digit, which is to the right of the decimal point, indicates the product form: XXX.0 indicates castings, and XXX.1 and XXX.2 indicate ingot.

**Table 3.1. Basic Designation for Wrought and Cast Aluminum Alloys**  
**[Reference 3.1(b)]**

Alloy Group	Major Alloying Elements	Alloy Group	Major Alloying Groups
	Wrought Alloys		Cast Alloys
1XXX	99.00 percent minimum aluminum	1XX.0	99.00 percent minimum aluminum
2XXX	Copper	2XX.0	Copper
3XXX	Manganese	3XX.0	Silicon with added copper and/or magnesium
4XXX	Silicon	4XX.0	Silicon
5XXX	Magnesium	5XX.0	Magnesium
6XXX	Magnesium and Silicon	6XX.0	Unused Series
7XXX	Zinc	7XX.0	Zinc
8XXX	Other Elements	8XX.0	Tin
9XXX	Unused Series	9XX.0	Other Elements



**MIL-HDBK-5H****1 December 1998****Table 3.1.1. Aluminum Alloy Index**

Section	Alloy Designation	Section	Alloy Designation
3.2	2000 series wrought alloys	3.6.3	6151
3.2.1	2014	3.7	7000 series wrought alloys
3.2.2	2107	3.7.1	7010
3.2.3	2024	3.7.2	7049/7149
3.2.4	2025	3.7.3	7050
3.2.5	2090	3.7.4	7075
3.2.6	2124	3.7.5	7150
3.2.7	2219	3.7.6	7175
3.2.8	2519	3.7.7	7249
3.2.9	2618	3.7.8	7475
3.3	3000 series wrought alloys	3.8	200.0 series cast alloys
3.4	4000 series wrought alloys	3.8.1	A201.0
3.5	5000 series wrought alloys	3.9	300.0 series cast alloys
3.5.1	5052	3.9.1	354.0
3.5.2	5083	3.9.2	355.0
3.5.3	5086	3.9.3	C355.0
3.5.4	5454	3.9.4	356.0
3.5.5	5456	3.9.5	A356.0
3.6	6000 series wrought alloys	3.9.6	A357.0
3.6.1	6013	3.9.7	D357.0
3.6.2	6061	3.9.8	359.0

**3.1.1 ALUMINUM ALLOY INDEX** — The layout of this chapter is in accordance with this four-digit number system for both wrought and cast alloys [Reference 3.1(b)]. Table 3.1.1 is the aluminum alloy index that illustrates both the general section layout as well as details of those specific aluminum alloys presently contained in this chapter. The wrought alloys are in Sections 3.2 through 3.7; whereas the cast alloys are in Sections 3.8 and 3.9.

**3.1.2 MATERIAL PROPERTIES** — The properties of the aluminum alloys are determined by the alloy content and method of fabrication. Some alloys are strengthened principally by cold work, while others are strengthened principally by solution heat treatment and precipitation hardening [Reference 3.1(a)]. The temper designations, shown in Table 3.1.2 (which is based on Reference 3.1.2), are indicative of the type of strengthening mechanism employed.

Among the properties presented herein, some, such as the room-temperature, tensile, compressive, shear and bearing properties, are either specified minimum properties or derived minimum properties related directly to the specified minimum properties. They may be directly useful in design. Data on the effect of temperature on properties are presented so that percentages may be applied directly to the room-temperature minimum properties. Other properties, such as the stress-strain curve, fatigue and fracture toughness data, and modulus of elasticity values, are presented as average or typical values, which may be used in assessing the usefulness of the material for certain applications. Comments on the effect of temperature on properties are given in Sections 3.1.2.1.7 and 3.1.2.1.8; comments on the corrosion resistance are given in Section 3.1.2.3; and comments on the effects of manufacturing practices on these properties are given in Section 3.1.3.



## MIL-HDBK-5H

1 December 1998

**Table 3.1.2. Temper Designation System for Aluminum Alloys**

<b>Temper Designation System<sup>ab</sup></b>	
<p>The temper designation system is used for all forms of wrought and cast aluminum and aluminum alloys except ingot. It is based on the sequences of basic treatments used to produce the various tempers. The temper designation follows the alloy designation, the two being separated by a hyphen. Basic temper designations consist of letters. Subdivisions of the basic tempers, where required, are indicated by one or more digits following the letter. These designate specific sequences of basic treatments, but only operations recognized as significantly influencing the characteristics of the product are indicated. Should some other variation of the same sequence of basic operations be applied to the same alloy, resulting in different characteristics, then additional digits are added to the designation.</p>	<p>the period of natural aging is indicated: for example, W ½ hr.</p>
<b>Basic Temper Designations</b>	<p><b>T thermally treated to produce stable tempers other than F, O, or H.</b> Applies to products which are thermally treated, with or without supplementary strain-hardening, to produce stable tempers. The T is always followed by one or more digits.</p>
	<p><b>Subdivisions of H Temper: Strain-hardened.</b></p>
<p><b>F as fabricated.</b> Applies to the products of shaping processes in which no special control over thermal conditions or strain-hardening is employed. For wrought products, there are no mechanical property limits.</p>	<p>The first digit following H indicates the specific combination of basic operations, as follows:</p>
<p><b>O annealed.</b> Applies to wrought products which are annealed to obtain the lowest strength temper, and to cast products which are annealed to improve ductility and dimensional stability. The O may be followed by a digit other than zero.</p>	<p><b>H1 strain-hardened only.</b> Applies to products which are strain-hardened to obtain the desired strength without supplementary thermal treatment. The number following this designation indicates the degree of strain-hardening.</p>
<p><b>H strain-hardened (wrought products only).</b> Applies to products which have their strength increased by strain-hardening, with or without supplementary thermal treatments to produce some reduction in strength. The H is always followed by two or more digits.</p>	<p><b>H2 strain-hardened and partially annealed.</b> Applies to products which are strain-hardened more than the desired final amount and then reduced in strength to the desired level by partial annealing. For alloys that age-soften at room temperature, the H2 tempers have the same minimum ultimate tensile strength as the corresponding H3 tempers. For other alloys, the H2 tempers have the same minimum ultimate tensile strength as the corresponding H1 tempers and slightly higher elongation. The number following this designation indicates the degree of strain-hardening remaining after the product has been partially annealed.</p>
<p><b>W solution heat-treated.</b> An unstable temper applicable only to alloys which spontaneously age at room temperature after solution heat-treatment. This designation is specific only when</p>	<p><b>H3 strain-hardened and stabilized.</b> Applies to products which are strain-hardened and whose mechanical properties are stabilized either by a low temperature thermal treatment or as a result</p>

a From reference 3.1.2.

b Temper designations conforming to this standard for wrought aluminum and wrought aluminum alloys, and aluminum alloy castings may be registered with the Aluminum Association provided: (1) the temper is used or is available for use by more than one user, (2) mechanical property limits are registered, (3) characteristics of the temper are significantly different from those of all other tempers which have the same sequence of basic treatments and for which designations already have been assigned for the same alloy and product, and (4) the following are also registered if characteristics other than mechanical properties are considered significant: (a) test methods and limits for the characteristics or (b) the specific practices used to produce the temper.

**MIL-HDBK-5H****1 December 1998****Table 3.1.2. Temper Designation System for Aluminum Alloys — Continued**

of heat introduced during fabrication. Stabilization usually improves ductility. This designation is applicable only to those alloys which, unless stabilized, gradually age-soften at room temperature. The number following this designation indicates the degree of strain-hardening remaining after the stabilization treatment.

The digit following the designations H1, H2, and H3 indicates the degree of strain hardening. Numeral 8 has been assigned to indicate tempers having an ultimate tensile strength equivalent to that achieved by a cold reduction (temperature during reduction not to exceed 120°F) of approximately 75 percent following a full anneal. Tempers between O (annealed) and 8 are designated by numerals 1 through 7. Material having an ultimate tensile strength about midway between that of the O temper and that of the 8 temper is designated by the numeral 4; about midway between the O and 4 tempers by the numeral 2; and about midway between 4 and 8 tempers by the numeral 6. Numeral 9 designates tempers whose minimum ultimate tensile strength exceeds that of the 8 temper by 2.0 ksi or more. For two-digit H tempers whose second digit is odd, the standard limits for ultimate tensile strength are exactly midway between those of the adjacent two digit H tempers whose second digits are even.

NOTE: For alloys which cannot be cold reduced an amount sufficient to establish an ultimate tensile strength applicable to the 8 temper (75 percent cold reduction after full anneal), the 6 temper tensile strength may be established by a cold reduction of approximately 55 percent following a full anneal, or the 4 temper tensile strength may be established by a cold reduction of approximately 35 percent after a full anneal.

The third digit<sup>c</sup>, when used, indicates a variation of a two-digit temper. It is used when the degree of control of temper or the mechanical properties or both differ from, but are close to, that (or those) for the two-digit H temper designation to which it is

added, or when some other characteristic is significantly affected.

NOTE: The minimum ultimate tensile strength of a three-digit H temper must be at least as close to that of the corresponding two-digit H temper as it is to the adjacent two-digit H tempers. Products of the H temper whose mechanical properties are below H\_1 shall be variations of H\_1.

**Three-digit H Tempers**

**H\_11** Applies to products which incur sufficient strain hardening after the final anneal that they fail to qualify as annealed but not so much or so consistent an amount of strain hardening that they qualify as H\_1.

**H112** Applies to products which may acquire some temper from working at an elevated temperature and for which there are mechanical property limits.

**Subdivisions of T Temper:  
Thermally Treated**

Numerals 1 through 10 following the T indicate specific sequences of basic treatments, as follows.<sup>d</sup>

**T1 cooled from an elevated temperature shaping process and naturally aged to a substantially stable condition.** Applies to products which are not cold worked after cooling from an elevated temperature shaping process, or in which the effect of cold work in flattening or straightening may not be recognized in mechanical property limits.

**T2 cooled from an elevated temperature shaping process, cold worked and naturally aged to a substantially stable condition.** Applies to products which are cold worked to improve strength after cooling from an elevated temperature shaping process, or in which the effect of

<sup>c</sup> Numerals 1 through 9 may be arbitrarily assigned as the third digit and registered with The Aluminum Association for an alloy and product to indicate a variation of a two-digit H temper (see footnote b).

<sup>d</sup> A period of natural aging at room temperature may occur between or after the operations listed for the T tempers. Control of this period is exercised when it is metallurgically important.

## MIL-HDBK-5H

1 December 1998

**Table 3.1.2. Temper Designation System for Aluminum Alloys — Continued**

cold work in flattening or straightening is recognized in mechanical property limits.	artificially aged after solution heat-treatment to provide dimensional and strength stability.
<b>T3 solution heat-treated<sup>e</sup>, cold worked, and naturally aged to a substantially stable condition.</b> Applies to products which are cold worked to improve strength after solution heat-treatment, or in which the effect of cold work in flattening or straightening is recognized in mechanical property limits.	<b>T8 solution heat-treated<sup>e</sup>, cold worked, and artificially aged.</b> Applies to products which are cold worked to improve strength, or in which the effect of cold work in flattening or straightening is recognized in mechanical property limits.
<b>T4 solution heat-treated<sup>e</sup> and naturally aged to a substantially stable condition.</b> Applies to products which are not cold worked after solution heat-treatment, or in which the effect of cold work in flattening or straightening may not be recognized in mechanical property limits.	<b>T9 solution heat-treated<sup>e</sup>, artificially aged, and cold worked.</b> Applies to products which are cold worked to improve strength.
<b>T5 cooled from an elevated temperature shaping process and artificially aged.</b> Applies to products which are not cold worked after cooling from an elevated temperature shaping process, or in which the effect of cold work in flattening or straightening may not be recognized in mechanical property limits.	<b>T10 cooled from an elevated temperature shaping process, cold worked, and artificially aged.</b> Applies to products which are cold worked to improve strength, or in which the effect of cold work in flattening or straightening is recognized in mechanical property limits.
<b>T6 solution heat-treated<sup>e</sup> and artificially aged.</b> Applies to products which are not cold worked after solution heat-treatment or in which the effect of cold work in flattening or straightening may not be recognized in mechanical property limits.	Additional digits <sup>f</sup> , the first of which shall not be zero, may be added to designations T1 through T10 to indicate a variation in treatment which significantly alters the product characteristics <sup>g</sup> that are or would be obtained using the basic treatment.
<b>T7 solution heat-treated<sup>e</sup> and overaged/stabilized.</b> Applies to wrought products that are artificially aged after solution heat-treatment to carry them beyond a point of maximum strength to provide control of some significant characteristic. Applies to cast products that are	The following specific additional digits have been assigned for stress-relieved tempers of wrought products:  <b>Stress Relieved by Stretching</b>
	<b>T_51</b> Applies to plate and rolled or cold-finished rod and bar when stretched the indicated amounts after solution heat-treatment or after cooling from an elevated temperature shaping process. The products receive no further straightening after stretching.

e Solution heat treatment is achieved by heating cast or wrought products to a suitable temperature, holding at that temperature long enough to allow constituents to enter into solid solution and cooling rapidly enough to hold the constituents in solution. Some 6000 series alloys attain the same specified mechanical properties whether furnace solution heat-treated or cooled from an elevated temperature shaping process at a rate rapid enough to hold constituents in solution. In such cases the temper designations T3, T4, T6, T7, T8, and T9 are used to apply to either process and are appropriate designations.

f Additional digits may be arbitrarily assigned and registered with the Aluminum Association for an alloy and product to indicate a variation of tempers T1 through T10 even though the temper representing the basic treatment has not been registered (see footnote b). Variations in treatment which do not alter the characteristics of the product are considered alternate treatments for which additional digits are not assigned.

g For this purpose, characteristic is something other than mechanical properties. The test method and limit used to evaluate material for this characteristic are specified at the time of the temper registration.

**MIL-HDBK-5H****1 December 1998****Table 3.1.2. Temper Designation System for Aluminum Alloys — Continued**

Plate .... 1½ to 3% permanent set. Rolled or Cold-Finished Rod and Bar .... 1 to 3% permanent set. Die or Ring Forgings and Rolled Rings .... 1 to 5% permanent set.	The following temper designations have been assigned for wrought product test material heat-treated from annealed (O, O1, etc.) or F temper. <sup>h</sup>
<b>T<sub>510</sub></b> Applies to extruded rod, bar, shapes and tube and to drawn tube when stretched the indicated amounts after solution heat-treatment or after cooling from an elevated temperature shaping process. These products receive no further straightening after stretching.  Extruded Rod, Bar, Shapes and Tube .... 1 to 3% permanent set. Drawn Tube .... ½ to 3% permanent set.	<b>T42</b> Solution heat-treated from annealed or F temper and naturally aged to a substantially stable condition.  <b>T62</b> Solution heat-treated from annealed or F temper and artificially aged.  Temper designations T42 and T62 may also be applied to wrought products heat-treated from any temper by the user when such heat-treatment results in the mechanical properties applicable to these tempers.
<b>T<sub>511</sub></b> Applies to extruded rod, bar, shapes and tube and to drawn tube when stretched the indicated amounts after solution heat-treatment or after cooling from an elevated temperature shaping process. These products may receive minor straightening after stretching to comply with standard tolerances.	<b>Variations of O Temper: Annealed</b>  A digit following the O, when used, indicates a product in the annealed condition have special characteristics. NOTE: As the O temper is not part of the strain-hardened (H) series, variations of O temper shall not apply to products which are strain-hardened after annealing and in which the effect of strain-hardening is recognized in the mechanical properties or other characteristics.
<b>Stress Relieved by Compressing</b>  <b>T<sub>52</sub></b> Applies to products which are stress-relieved by compressing after solution heat-treatment or cooling from an elevated temperature shaping process to produce a set of 1 to 3 percent.	<b>Assigned O Temper Variations</b>  The following temper designation has been assigned for wrought products high temperature annealed to accentuate ultrasonic response and provide dimensional stability.
<b>Stress Relieved by Combined Stretching and Compressing</b>  <b>T<sub>54</sub></b> Applies to die forgings which are stress relieved by restriking cold in the finish die.  NOTE: The same digits (51, 52, 54) may be added to the designation W to indicate unstable solution heat-treated and stress-relieved treatment.	<b>O1</b> Thermally treated at approximately same time and temperature required for solution heat treatment and slow cooled to room temperature. Applicable to products which are to be machined prior to solution heat treatment by the user. Mechanical Property limits are not applicable.  <b>Designation of Unregistered Tempers</b>  The letter P has been assigned to denote H, T and O temper variations that are negotiated between manufacturer and purchaser. The letter P immediately follows the temper designation that

<sup>h</sup> When the user requires capability demonstrations from T-temper, the seller shall note "capability compliance" adjacent to the specified ending tempers. Some examples are: "-T4 to -T6 Capability Compliance as for aging" or "-T351 to -T4 Capability Compliance as for resolution heat treating."

**MIL-HDBK-5H****1 December 1998****Table 3.1.2. Temper Designation System for Aluminum Alloys — Continued**

most nearly pertains. Specific examples where such designation may be applied include the following:	The test conditions (sampling location, number of samples, test specimen configuration, etc.) are different from those required for registration with the Aluminum Association.
The use of the temper is sufficiently limited so as to preclude its registration. (Negotiated H temper variations were formerly indicated by the third digit zero.)	The mechanical property limits are not established on the same basis as required for registration with the Aluminum Association.

It should be recognized not all combinations of stress and environment have been investigated, and it may be necessary to evaluate an alloy under the specific conditions involved for certain critical applications.


**3.1.2.1 Mechanical Properties —**

**3.1.2.1.1 Strength (Tension, Compression, Shear, Bearing) —** The design strength properties at room temperature are listed at the beginning of the section covering the properties of an alloy. The effect of temperature on these properties is indicated in figures which follow the tables.

The A- and B-basis values for tensile properties for the direction associated with the specification requirements are based upon a statistical analysis of production quality control data obtained from specimens tested in accordance with procurement specification requirements. For sheet and plate of heat-treatable alloys, the specified minimum values are for the long-transverse (LT) direction, while for sheet and plate of nonheat treatable alloys and for rolled, drawn, or extruded products, the specified minimum values are for the longitudinal (L) direction. For forgings, the specified minimum values are stated for at least two directions. The design tensile properties in other directions and the compression, shear, and bearing properties are “derived” properties, based upon the relationships among the properties developed by tests of at least ten lots of material and applied to the appropriate established A, B, or S properties. All of these properties are representative of the regions from which production quality control specimens are taken, but may not be representative of the entire cross section of products appreciably thicker than the test specimen or products of complex cross sections.

Tensile and compressive strengths are given for the longitudinal, long-transverse, and short-transverse directions wherever data are available. Short-transverse strengths may be relatively low, and transverse properties should not be assumed to apply to the short-transverse direction unless so stated. In those instances where the direction in which the material will be used is not known, the lesser of the applicable longitudinal or transverse properties should be used.

Bearing strengths are given without reference to direction and may be assumed to be about the same in all directions, with the exception of plate, die forging, and hand forging. A reduction factor is used for edgewise bearing load in thick bare and clad plate of 2000 and 7000 series alloys. The results of bearing tests on longitudinal and long-transverse specimens taken edgewise from plate, die forging, and hand forging have shown that the edgewise bearing strengths are substantially lower than those of specimens taken parallel to the surface. The bearing specimen orientations in thick plate are shown in Figure 3.1.2.1.1(a). For plate, bearing specimens are oriented so that the width of the specimen is parallel to the surfaces of the plate (flatwise); consequently, in cases where the stress condition approximates that of the longitudinal or long-transverse edgewise orientations, the reductions in design values shown in Table 3.1.2.1.1 should be made.

**MIL-HDBK-5H****1 December 1998**

**Figure 3.1.2.1.1(a). Bearing specimen orientation in thick plate.**

**Table 3.1.2.1.1. Bearing Property Reductions for Thick Plate of 2000 and 7000 Series Alloys**

Thickness (in.) ...	Bearing Property Reduction, percent
	1.001-6.000
$F_{bru}$ ( $e/D = 1.5$ )	15
$F_{bru}$ ( $e/D = 2.0$ )	10
$F_{bry}$ ( $e/D = 1.5$ )	5
$F_{bry}$ ( $e/D = 2.0$ )	5


It should be noted that in recent years, bearing data have been presented from tests made in accordance with ASTM E 238 which requires clean pins and specimens. See Reference 3.1.2.1.1 for additional information. Designers should consider a reduction factor in applying these values to structural analyses.

For die and hand forgings, bearing specimens are taken edgewise so that no reduction factor is necessary. In the case of die forgings, the location of bearing specimens is shown in Figures 3.1.2.1.1(b) and (c). For die forgings with cross-sectional shapes in the form of an I-beam or a channel, longitudinal bearing specimens are oriented so the width of the specimens is normal to the parting plane (edgewise). The specimens are positioned so the bearing test holes are midway between the parting plane and the top of the flange. The severity of metal flow at the parting plane near the flash can be expected to vary considerably for web-flange type die forgings; therefore, for consistency, the bearing test hole should not be located on the parting plane. However, in the case of large, bulky-type die forgings, with a cross-sectional shape similar to a square, rectangle, or trapezoid, as shown in Figure 3.1.2.1.1(c), longitudinal bearing specimens are oriented edgewise to the parting plane, but the specimens are positioned so the bearing test holes are located on the parting plane. Similarly, for hand forgings, bearing specimens are oriented edgewise and the specimens are positioned at the  $\frac{1}{2}$  thickness location.


Shear strengths also vary to some extent with plane of shear and direction of loading but the differences are not so consistent [Reference 3.1.2.1.1(c)]. The standard test method for the determination of shear strength of aluminum alloy products, 3/16 inch and greater in thickness, is contained in ASTM B 769.

Shear strength values are presented without reference to grain direction, except for hand forgings. For products other than hand forgings, the lowest shear strength exhibited by tests in the various grain



**MIL-HDBK-5H****1 December 1998**

**Figure 3.1.2.1.1(b). Bearing specimen orientation for web-flange type die forging.**



**Figure 3.1.2.1.1(c). Bearing specimen orientation for thick cross-section die forging.**

directions is the design value. For hand forgings, the shear strength in short-transverse direction may be significantly lower than for the other two grain directions. Consequently, the shear strength for hand forgings is presented for each grain direction.

For clad sheet and plate (i.e., containing thin surface layers of material of a different composition for added corrosion protection), the strength values are representative of the composite (i.e., the cladding and the core). For sheet and thin plate ( $\leq 0.499$  inch), the quality-control test specimens are of the full thickness, so that the guaranteed tensile properties and the associated derived values for these products directly represent the composite. For plate  $\geq 0.500$  inch in thickness, the quality-control test specimens are machined from the core so the guaranteed tensile properties in specifications reflect the core material only, not the composite. Therefore, the design tensile properties for the thicker material are obtained by adjustment of the specification tensile properties and the other related properties to represent the composite, using the nominal total cladding thickness and the typical tensile properties of the cladding material.

For clad aluminum sheet and plate products, it is also important to distinguish between primary and secondary modulus values. The initial, or primary, modulus represents an average of the elastic moduli of the core and cladding; it applies only up to the proportional limit of the cladding. For example, the primary modulus of 2024-T3 clad sheet applies only up to about 6 ksi. Similarly, the primary modulus of 7075-T6 clad sheet applies only up to approximately 12 ksi. A typical use of primary moduli is for low amplitude, high frequency fatigue.

**3.1.2.1.2 Elongation** — Elongation values are included in the tables of room-temperature mechanical properties. In some cases where the elongation is a function of material thickness, a supplemental table is provided. Short-transverse elongations may be relatively low, and long-transverse values should not be assumed to apply to the short-transverse direction.

**3.1.2.1.3 Stress-Strain Relationship** — The stress-strain relationships presented, which include elastic and compressive tangent moduli, are typical curves based on three or more lots of test data. Being typical, these curves will not correspond to yield strength data presented as design allowables (minimum values). However, the stress-strain relationships are no less useful, since there are well-known methods for using these curves in design by reducing them to a minimum curve affine to the typical curve or by using Ramberg-Osgood parameters obtained from the typical curves.

**MIL-HDBK-5H****1 December 1998**

**3.1.2.1.4 Creep and Stress Rupture** — Sustained stressing at elevated temperature sufficient to result in appreciable amounts of creep deformation (e.g., more than 0.2 percent) may result in decreased strength and ductility. It may be necessary to evaluate an alloy under its stress-temperature environment for critical applications where sustained loading is anticipated (see Reference 3.1.2.1.4).

**3.1.2.1.5 Fatigue** — Fatigue S/N curves are presented for those alloys for which sufficient data are available. Data for both smooth and notched specimens are presented. The data from which the curves were developed were insufficient to establish scatter bands and do not have the statistical reliability of the room-temperature mechanical properties; the values should be considered to be representative for the respective alloys.

The fatigue strengths of aluminum alloys, with both notched and unnotched specimens, are at least as high or higher at subzero temperatures than at room temperature [References 3.1.2.1.5(a) through (c)]. At elevated temperatures, the fatigue strengths are somewhat lower than at room temperature, the difference increasing with increase in temperature.

The data presented do not apply directly to the design of structures because they do not take into account the effect of stress raisers such as reentrant corners, notches, holes, joints, rough surfaces, and other similar conditions which are present in fabricated parts. The localized high stresses induced in fabricated parts by such stress raisers are of much greater importance for repeated loading than they are for static loading and may reduce the fatigue life of fabricated parts far below that which would be predicted by comparing the smooth-specimen fatigue strength directly with the nominal calculated stresses for the parts in question. See References 3.1.2.1.5 (d) through (q) for information on how to use high-strength aluminum alloys, Reference 3.1.2.1.5(r) for details on the static and fatigue strengths of high-strength aluminum-alloy bolted joints, Reference 3.1.2.1.5(s) for single-rivet fatigue-test data, and Reference 1.4.9.3(b) for a general discussion of designing for fatigue. Fatigue-crack-growth data are presented in the various alloy sections.

**3.1.2.1.6 Fracture Toughness** — Typical values of plane-strain fracture toughness,  $K_{Ic}$ , [Reference 3.1.2.1.6(a)] for the high-strength aluminum alloy products are presented in Table 3.1.2.1.6. Minimum, average, and maximum values as well as coefficient of variation are presented for the alloys and tempers for which valid data are available [References 3.1.2.1.6(b) through (j)]. Although representative, these values do not have the statistical reliability of the room-temperature mechanical properties.

Graphic displays of the residual strength behavior of center-cracked tension panels are presented in the various alloy sections. The points denote the experimental data from which the curve of fracture toughness was derived.

**3.1.2.1.7 Cryogenic Temperatures** — In general, the strengths (including fatigue strengths) of aluminum alloys increase with decrease in temperature below room temperature [References 3.1.2.1.7(a) and (b)]. The increase is greatest over the range from about -100 to -423 °F (liquid hydrogen temperature); the strengths at -452 °F (liquid helium temperature) are nearly the same as at -423 °F [References 3.1.2.1.7(c) and (d)]. For most alloys, elongation and various indices of toughness remain nearly constant or increase with decrease in temperature, while for the 7000 series, modest reductions are observed [References 3.1.2.1.7(d) and (e)]. None of the alloys exhibit a marked transition in fracture resistance over a narrow range of temperature indicative of embrittlement.



**Table 3.1.2.1.6. Values of Room-Temperature Plane-Strain Fracture Toughness of Aluminum Alloys<sup>a</sup>**

Alloy/Temper	Product Form	Orientation <sup>b</sup>	Product Thickness Range, inches	Number of Sources	Sample Size	Specimen Thickness Range, inches	K <sub>IC</sub> , ksi √in.				
							Max.	Avg.	Min.	Coefficient of Variation	Minimum Specification Value
2014-T651	Plate	L-T	≥0.5	1	24	0.5-1.0	25	22	19	8.4	24 20 18
2014-T651	Plate	T-L	≥0.5	2	34	0.5-1.0	23	21	18	6.5	
2014-T652	Hand Forging	L-T	≥0.5	2	15	0.8-2.0	48	31	24	21.8	
2014-T652	Hand Forging	T-L	≥0.8	2	15	0.8-2.0	30	21	18	14.4	
2024-T351	Plate	L-T	≥1.0	2	11	0.8-2.0	43	31	27	16.5	
2024-T851	Plate	L-S	1.4-3.0	4	11	0.5-0.8	32	25	20	17.8	
2024-T851	Plate	L-T	≥0.5	11	102	0.4-1.4	32	23	15	10.1	
2024-T851	Plate	T-L	0.4-4.0	9	80	0.4-1.4	25	20	18	8.8	
2024-T852	Forging	T-L	2.0-7.0	3	20	0.7-2.0	25	19	15	15.5	
2024-T852	Hand Forging	L-T	----	4	35	0.8-2.0	38	28	19	18.4	
2024-T852	Hand Forging	T-L	----	2	17	0.7-2.0	22	18	14	14.4	
2124-T851	Plate	L-T	≥0.8	13	497	0.5-2.5	38	29	18	10.4	
2124-T851	Plate	T-L	0.6-6.0	10	509	0.5-2.0	32	25	19	9.7	
2124-T851	Plate	S-L	≥0.5	6	489	0.3-1.5	27	21	16	9.8	
2219-T851	Plate	L-T	----	4	67	1.0-2.5	38	33	30	7.2	
2219-T851	Plate	T-L	≥1.0	6	108	0.8-2.5	37	29	20	10.1	
2219-T851	Plate	S-L	≥0.8	3	24	0.5-1.5	26	22	20	9.6	
2219-T851	Forging	S-L	----	1	85	1.0-1.5	34	25	19	12.1	
2219-T8511	Extrusion	T-L	----	1	19	1.8-2.0	34	29	23	12.3	
2219-T852	Forging	S-L	----	2	60	0.8-2.0	35	25	20	12.1	
2219-T852	Hand Forging	L-T	----	2	32	1.5-2.5	46	38	30	9.7	
2219-T852	Hand Forging	T-L	≥1.5	2	28	1.5-2.5	30	27	22	8.4	
2219-T87	Plate	L-T	≥1.5	3	11	0.8-2.0	34	27	25	9.3	
2219-T87	Plate	T-L	----	1	11	1.0	22	22	19	3.9	
7049-T73	Die Forging	L-T	1.4	3	21	0.5-1.0	34	30	27	7.4	
7049-T73	Die Forging	S-L	≥0.5	3	46	0.5-1.0	26	22	18	9.7	
7049-T73	Hand Forging	L-T	≥0.5	2	28	0.5-1.0	37	30	23	12.1	
7049-T73	Hand Forging	T-L	2.0-7.1	2	27	1.0	28	22	18	12.5	
7049-T73	Hand Forging	S-L	1.0	2	24	0.8-1.0	22	19	14	14.2	
7050-T7351	Plate	L-T	1.0-6.0	2	31	1.0-2.0	43	35	28	11.3	
7050-T7351	Plate	T-L	2.0-6.0	1	29	1.5-2.0	35	30	25	8.5	
7050-T7351	Plate	S-L	2.0-6.0	1	30	0.8-1.5	30	28	25	4.6	
7050-T74	Die Forging	S-L	0.6-7.1	3	12	0.6-2.0	27	24	21	8.8	

<sup>a</sup> These values are for information only.

<sup>b</sup> Refer to Figure 1.4.12.3 for definition of symbols.

<sup>c</sup> Varies with thickness.

**Table 3.1.2.1.6. Values of Room-Temperature Plane-Strain Fracture Toughness of Aluminum Alloys<sup>a</sup>—Continued**

Alloy/Temper	Product Form	Orientation <sup>b</sup>	Product Thickness Range, inches	Number of Sources	Sample Size	Specimen Thickness Range, inches	K <sub>IC</sub> , ksi√in.				
							Max.	Avg.	Min.	Coefficient of Variation	Minimum Specification Value
7050-T7451	Plate	L-T	----	13	96	1.0-2.0	39	32	25	11.7	c
7050-T7451	Plate	T-L	≥1.0	9	97	0.5-2.0	38	28	21	15.6	c
7050-T7451	Plate	S-L	≥1.0	6	44	0.7-2.0	28	23	21	6.3	c
7050-T7452	Hand Forging	L-T	3.5-5.5	1	11	1.5	34	31	26	8.0	c
7050-T7452	Hand Forging	T-L	3.5-7.5	1	13	1.5	22	21	18	6.7	c
7050-T7452	Hand Forging	S-L	3.5-7.5	1	17	0.8-1.5	21	19	16	7.5	c
7050-T76511	Extrusion	L-T	----	2	38	0.6-2.0	40	31	27	7.8	c
7075-T651	Plate	L-T	≥0.6	7	99	0.5-2.0	30	26	20	7.6	c
7075-T651	Plate	T-L	≥0.5	5	135	0.4-2.0	27	22	18	8.9	c
7075-T651	Plate	S-L	----	2	37	0.5-1.5	22	18	14	10.4	c
7075-T6510	Extrusion	L-T	0.7-3.5	1	26	0.5-1.2	32	27	23	7.8	c
7075-T6510	Extrusion	T-L	0.7-3.5	1	25	0.5-1.2	28	24	21	8.0	c
7075-T6510	Forged Bar	L-T	0.7-5.0	1	13	0.6-2.0	35	29	24	11.6	c
7075-T6510	Forged Bar	T-L	0.7-5.0	1	13	0.5-2.5	24	21	17	8.2	c
7075-T73	Die Forging	T-L	≥0.5	1	22	0.5-0.8	25	21	18	9.9	c
7075-T73	Hand Forging	L-T	----	2	10	1.0-1.5	39	31	29	8.8	c
7075-T73	Hand Forging	T-L	≥1.0	2	14	1.0-1.5	27	23	20	9.0	c
7075-T7351	Plate	L-T	≥1.0	8	65	0.5-2.0	36	30	25	8.2	c
7075-T7351	Plate	T-L	≥0.5	6	56	0.5-2.0	47	27	21	20.1	c
7075-T7351	Plate	S-L	≥0.5	3	20	0.5-1.5	38	22	17	32.5	c
7075-T73511	Extrusion	T-L	1.0-7.0	1	19	0.9-1.0	22	20	19	3.7	c
7075-T73511	Extrusion	L-T	≥0.9	3	28	0.7-2.0	43	35	31	9.4	c
7075-T73511	Extrusion	T-L	≥0.7	3	35	0.5-1.8	35	23	12	20.3	c
7075-T73511	Extrusion	S-L	≥0.5	3	15	0.4-1.0	22	20	17	9.0	c
7075-T7352	Hand Forging	L-T	----	2	27	0.8-2.0	39	33	30	9.2	c
7075-T7352	Hand Forging	T-L	≥0.8	3	20	0.8-2.0	33	26	23	9.9	c
7075-T7651	Plate	L-T	≥0.8	6	82	0.5-2.0	43	29	22	17.8	c
7075-T7651	Plate	T-L	≥0.5	7	96	0.5-2.0	28	23	20	7.6	c
7075-T7651	Plate	S-L	≥0.5	5	28	0.4-0.8	20	18	15	7.7	c
7075-T7651	Clad Plate	L-T	0.5-0.6	2	30	0.5-0.6	30	25	22	7.1	c
7075-T7651	Clad Plate	T-L	0.5-0.6	2	56	0.5-0.6	28	24	21	7.7	c
7075-T76511	Extrusion	L-T	1.3-7.0	4	11	1.2-2.0	41	35	31	11.0	c
7075-T76511	Extrusion	T-L	1.2	3	42	0.6-2.0	36	23	20	15.5	c

<sup>a</sup> These values are for information only.

<sup>b</sup> Refer to Figure 1.4.12.3 for definition of symbols.

<sup>c</sup> Varies with thickness.

**Table 3.1.2.1.6. Values of Room-Temperature Plane-Strain Fracture Toughness of Aluminum Alloys<sup>a</sup>—Continued**

Alloy/Temper	Product Form	Orientation <sup>b</sup>	Product Thickness Range, inches	Number of Sources	Sample Size	Specimen Thickness Range, inches	K <sub>IC</sub> , ksi√in.				
							Max.	Avg.	Min.	Coefficient of Variation	Minimum Specification Value
7175-T6/T6511	Extrusion	T-L	----	2	25	0.8-1.0	24	21	18	7.9	
7175-T651	Plate	L-T	----	1	17	0.7-0.8	30	26	24	9.2	
7175-T651	Plate	T-L	----	1	10	0.7-0.8	26	22	20	9.8	
7175-T6511	Extrusion	L-T	----	2	14	0.8-1.0	36	32	24	13.8	
7175-T7351	Plate	L-T	----	2	30	0.7-1.6	36	33	32	3.3	
7175-T7351	Plate	T-L	----	2	32	0.7-1.6	30	27	25	4.5	
7175-T73511	Extrusion	L-T	≥0.7	5	43	0.5-1.5	47	33	23	16.0	30
7175-T73511	Extrusion	T-L	≥0.5	5	43	0.5-1.5	35	25	20	10.9	22
7175-T74	Die Forging	L-T	≥0.5	3	14	0.5-1.0	38	30	22	15.0	27
7175-T74	Die Forging	T-L	≥0.5	2	13	0.5-1.0	33	24	21	15.7	21
7175-T74	Die Forging	S-L	≥0.5	4	41	0.5-0.8	31	26	20	8.6	21
7175-T74	Hand Forging	T-L	3.0-5.0	2	10	1.0-1.5	29	26	24	4.8	25
7175-T7651	Clad Plate	L-T	----	1	53	1.5	33	32	30	4.3	
7175-T7651	Clad Plate	T-L	----	1	50	0.6	28	27	25	3.1	
7175-T7651	Plate	L-T	----	1	12	1.5	32	32	31	1.7	
7175-T7651	Plate	T-L	----	1	11	1.5	26	25	24	3.3	
7175-T76511	Extrusion	L-T	1.4-3.8	2	48	0.6-2.0	39	33	27	10.7	
7175-T76511	Extrusion	T-L	≥0.6	4	49	0.6-1.8	31	22	20	9.8	
7475-T651	Plate	L-T	----	3	34	0.9-2.0	49	38	33	9.2	30
7475-T651	Plate	T-L	0.6-2.0	2	143	0.6-2.0	43	34	27	9.8	28
7475-T651	Plate	S-L	≥0.6	1	23	0.5-1.0	36	28	20	14.9	
7475-T7351	Plate	L-T	1.3-4.0	8	151	1.3-3.0	60	47	34	10.4	c
7475-T7351	Plate	T-L	≥1.3	7	132	0.7-3.0	50	37	29	10.4	c
7475-T7351	Plate	S-L	≥0.7	7	74	0.5-1.5	36	30	25	8.7	25
7475-T7651	Plate	L-T	1.0-2.0	4	10	1.0-2.0	46	41	36	6.2	33
7475-T7651	Plate	T-L	≥1.0	2	15	0.9-2.0	50	36	29	14.5	30

<sup>a</sup> These values are for information only.

<sup>b</sup> Refer to Figure 1.4.12.3 for definition of symbols.

<sup>c</sup> Varies with thickness.

**MIL-HDBK-5H****1 December 1998**

The tensile and shear moduli of aluminum alloys also increase with decreasing temperature so that at -100, -320, and -423°F, they are approximately 5, 12, and 16 percent, respectively, above the room temperature values [Reference 3.1.2.1.7(f)].

**3.1.2.1.8 Elevated Temperatures** — In general, the strengths of aluminum alloys decrease and toughness increases with increase in temperature and with time at temperature above room temperature; the effect is generally greatest over the temperature range from 212 to 400°F. Exceptions to the general trends are tempers developed by solution heat treatment without subsequent aging, for which the initial elevated temperature exposure results in some age hardening and reduction in toughness; further time at temperature beyond that required to achieve peak hardness results in the aforementioned decrease in strength and increase in toughness [Reference 3.1.2.1.8].

**3.1.2.2 Physical Properties** — Where available from the literature, the average values of certain physical properties are included in the room-temperature tables for each alloy. These properties include density,  $\omega$ , in lb/in.<sup>3</sup>; the specific heat,  $C$ , in Btu/(lb)(°F); the thermal conductivity,  $K$ , in Btu/[(hr)(ft<sup>2</sup>)(°F)/ft]; and the mean coefficient of thermal expansion,  $\alpha$ , in in./in./°F. Where more extensive data are available to show the effect of temperature on these physical properties, graphs of physical property as a function of temperature are presented for the applicable alloys.

**3.1.2.3 Corrosion Resistance** —

**3.1.2.3.1 Resistance to Stress-Corrosion Cracking [see References 3.1.2.3.1(a) through (d)]** — The high-strength heat treatable wrought aluminum alloys in certain tempers are susceptible to stress-corrosion cracking, depending upon product, section size, direction and magnitude of stress. These alloys include 2014, 2025, 2618, 7075, 7150, 7175, and 7475 in the T6-type tempers and 2014, 2024, 2124, and 2219 in the T3 and T4-type tempers. Other alloy-temper combinations, notably 2024, 2124, 2219, and 2519 in the T6- or T8-type tempers and 7010, 7049, 7050, 7075, 7149, 7175, and 7475 in the T73-type tempers, are decidedly more resistant and sustained tensile stresses of 50 to 75 percent of the minimum yield strength may be permitted without concern about stress corrosion cracking. The T74 and T76 tempers of 7010, 7075, 7475, 7049, 7149, and 7050 provide an intermediate degree of resistance to stress-corrosion cracking, i.e., superior to that of the T6 temper, but not as good as that of the T73 temper of 7075. To assist in the selection of materials, letter ratings indicating the relative resistance to stress-corrosion cracking of various mill product forms of the wrought 2000, 6000, and 7000 series heat-treated aluminum alloys are presented in Table 3.1.2.3.1(a). This table is based upon ASTM G 64 which contains more detailed information regarding this rating system and the procedure for determining the ratings. In addition, more quantitative information in the form of the maximum specified tension stresses at which test specimens will not fail when subjected to the alternate immersion stress-corrosion test described in ASTM G 47 are shown in Tables 3.1.2.3.1(b) through (e) for various heat-treated aluminum product forms, alloys, and tempers.

Where short times at elevated temperatures of 150 to 500°F may be encountered, the precipitation heat-treated tempers of 2024 and 2219 alloys are recommended over the naturally aged tempers.

Alloys 5083, 5086, and 5456 should not be used under high constant applied stress for continuous service at temperatures exceeding 150°F, because of the hazard of developing susceptibility to stress-corrosion cracking. In general, the H34 through H38 tempers of 5086, and the H32 through H38 tempers of 5083 and 5456 are not recommended, because these tempers can become susceptible to stress-corrosion cracking.

For the cold forming of 5083 sheet and plate in the H112, H321, H323, and H343 tempers and 5456 sheet and plate in the H112 and H321 tempers, a minimum bend radius of 5T should be used. Hot forming of the O temper for alloys 5083 and 5456 is recommended, and is preferred to the cold worked

**MIL-HDBK-5H****1 December 1998****Table 3.1.2.3.1(a). Resistance to Stress-Corrosion Ratings<sup>a</sup> for High-Strength Aluminum Alloy Products**

Alloy and Temper <sup>b</sup>	Test Direction <sup>c</sup>	Rolled Plate	Rod and Bar <sup>d</sup>	Extruded Shapes	Forging
2014-T6	L	A	A	A	B
	LT	B <sup>e</sup>	D	B <sup>e</sup>	B <sup>e</sup>
	ST	D	D	D	D
2024-T3, T4	L	A	A	A	f
	LT	B <sup>e</sup>	D	B <sup>e</sup>	f
	ST	D	D	D	f
2024-T6	L	f	A	f	A
	LT	f	B	f	A <sup>e</sup>
	ST	f	B	f	D
2024-T8	L	A	A	A	A
	LT	A	A	A	A
	ST	B	A	B	C
2124-T8	L	A	f	f	f
	LT	A	f	f	f
	ST	B	f	f	f
2219-T351X, T37	L	A	f	A	f
	LT	B	f	B	f
	ST	D	f	D	f
2219-T6	L	A	A	A	A
	LT	A	A	A	A
	ST	A	A	A	A
2219-T85XX, T87	L	A	f	A	A
	LT	A	f	A	A
	ST	A	f	A	A
6061-T6	L	A	A	A	A
	LT	A	A	A	A
	ST	A	A	A	A
7049-T73	L	A	f	A	A
	LT	A	f	A	A
	ST	A	f	B	A
7049-T76	L	f	f	A	f
	LT	f	f	A	f
	ST	f	f	C	f
7050-T74	L	A	f	A	A
	LT	A	f	A	A
	ST	B	f	B	B
7050-T76	L	A	A	A	f
	LT	A	B	A	f
	ST	C	B	C	f
7075-T6	L	A	A	A	A
	LT	B <sup>e</sup>	D	B <sup>e</sup>	B <sup>e</sup>
	ST	D	D	D	D
7075-T73	L	A	A	A	A
	LT	A	A	A	A
	ST	A	A	A	A

**MIL-HDBK-5H****1 December 1998****Table 3.1.2.3.1(a). Resistance to Stress-Corrosion Ratings<sup>a</sup> for High-Strength Aluminum Alloy Products—Continued**

Alloy and Temper <sup>b</sup>	Test Direction <sup>c</sup>	Rolled Plate	Rod and Bar <sup>d</sup>	Extruded Shapes	Forging
7075-T74	L	f	f	f	A
	LT	f	f	f	A
	ST	f	f	f	B
7075-T76	L	A	f	A	f
	LT	A	f	A	f
	ST	C	f	C	f
7149-T73	L	f	f	A	A
	LT	f	f	A	A
	ST	f	f	B	A
7175-T74	L	f	f	f	A
	LT	f	f	f	A
	ST	f	f	f	B
7475-T6	L	A	f	f	f
	LT	B <sup>e</sup>	f	f	f
	ST	D	f	f	f
7475-T73	L	A	f	f	f
	LT	A	f	f	f
	ST	A	f	f	f
7475-T76	L	A	f	f	f
	LT	A	f	f	f
	ST	C	f	f	f

a Ratings were determined from stress corrosion tests performed on at least ten random lots for which test results showed 95% conformance at the 95% confidence level when tested at the stresses indicated below. A practical interpretation of these ratings follows the rating definition.

- A - Equal or greater than 75% of the specified minimum yield strength. Very high. No record of service problems and SCC not anticipated in general applications.
- B - Equal or greater than 50% of the specified minimum yield strength. High. No record of service problems and SCC not anticipated at stresses of the magnitude caused by solution heat treatment. Precautions must be taken to avoid high sustained tensile stress exceeding 50% of the minimum specified yield strength produced by any combination of sources including heat treatment, straightening, forming, fit-up, and sustained service loads.
- C - Equal or greater than 25% of the specified minimum yield strength. Intermediate. SCC not anticipated if the total sustained tensile strength is less than 25% of the minimum specified yield strength. This rating is designated for the short transverse direction in improved products used primarily for high resistance to exfoliation corrosion in relatively thin structures where applicable short transverse stresses are unlikely.
- D - Fails to meet the criterion for the rating C. Low. SCC failures have occurred in service or would be anticipated if there is any sustained tensile stress in the designated test direction. This rating currently is designated only for the short transverse direction in certain materials.

NOTE - The above stress levels are not to be interpreted as "threshold" stresses, and are not recommended for design. Other documents, such as MIL-STD-1568, NAS SD-24, and MSFC-SPEC-522A, should be consulted for design recommendations.

**MIL-HDBK-5H****1 December 1998****Table 3.1.2.3.1(a). Resistance to Stress-Corrosion Ratings<sup>a</sup> for High Strength Aluminum Alloy Products—Continued**

---

- b The ratings apply to standard mill products in the types of tempers indicated, including stress-relieved tempers, and could be invalidated in some cases by application of nonstandard thermal treatments or mechanical deformation at room temperature by the user.
- c Test direction refers to orientation of the stressing direction relative to the directional grain structure typical of wrought materials, which in the case of extrusions and forgings may not be predictable from the geometrical cross section of the product.
  - L—Longitudinal: parallel to the direction of principal metal extension during manufacture of the product.
  - LT—Long Transverse: perpendicular to direction of principal metal extension. In products whose grain structure clearly shows directionality (width to thickness ratio greater than two) it is that perpendicular direction parallel to the major grain dimension.
  - ST—Short Transverse: perpendicular to direction of principal metal extension and parallel to minor dimension of grains in products with significant grain directionality.
- d Sections with width-to-thickness ratio equal to or less than two for which there is no distinction between LT and ST.
- e Rating is one class lower for thicker sections: extrusion, 1 inch and over; plate and forgings, 1.5 inches and over.
- f Ratings not established because the product is not offered commercially.

---

NOTE: This table is based upon ASTM G 64.

---

**MIL-HDBK-5H****1 December 1998****Table 3.1.2.3.1(b). Maximum Specified Tension Stress at Which Test Specimens Will Not Fail in 3½% NaCl Alternate Immersion Test<sup>d</sup> for Various Stress Corrosion Resistant Aluminum Alloy Plate**

Alloy and Temper	Test Direction	Thickness, inches	Stress, ksi	Referenced Specifications
2024-T851	ST	1.001-4.000	28 <sup>a</sup>	Company specification
		4.001-6.000	27 <sup>a</sup>	
2090-T81 <sup>c</sup>	ST	0.750-1.500	20	AMS 4303
2124-T851	ST	1.500-1.999	28 <sup>a</sup>	AMS 4101
		2.000-4.000	28 <sup>a</sup>	AMS-QQ-A-0025/29, ASTM B 209, AMS 4101
		4.001-6.000	27 <sup>a</sup>	
2124-T8151 <sup>c</sup>	ST	1.500-3.000	30 <sup>a</sup>	AMS 4221
		3.001-5.000	29 <sup>a</sup>	
		5.001-6.000	28 <sup>a</sup>	AMS-QQ-A-250/30
2219-T851	ST	0.750-2.000	34 <sup>b</sup>	
		2.001-4.000	33 <sup>b</sup>	
		4.001-5.000	32 <sup>b</sup>	
		5.001-6.000	31 <sup>b</sup>	AMS-QQ-A-250/30
2219-T87	ST	0.750-3.000	38 <sup>b</sup>	
		3.001-4.000	37 <sup>b</sup>	
		4.001-5.000	36 <sup>b</sup>	
2519-T87	ST	0.750-4.000	43 <sup>b</sup>	MIL-A-46192
7010-T7351 <sup>c</sup>	ST	0.750-3.000	41 <sup>b</sup>	AMS 4203
		3.001-5.000	40 <sup>b</sup>	
		5.001-5.500	39 <sup>b</sup>	
7010-T7451	ST	0.750-3.000	31 <sup>a</sup>	AMS 4205
		3.001-5.500	35	
7010-T7651	ST	0.750-5.500	25	AMS 4204
7049-T7351	ST	0.750-5.000	45	AMS 4200
7050-T7451	ST	0.750-6.000	35	AMS 4050
7050-T7651	ST	0.750-3.000	25	AMS 4201
7075-T7351	ST	0.750-2.000	42 <sup>b</sup>	AMS-QQ-A-250/12, AMS 4078, ASTM B 209
		2.001-2.500	39 <sup>b</sup>	
		2.501-4.000	36 <sup>b</sup>	
7075-T7651	ST	0.750-1.000	25	AMS-QQ-A-00250/24, ASTM B 209
Clad 7075-T7651	ST	0.750-1.000	25	AMS-QQ-A-00250/25, ASTM B 209
7150-T7751	ST	0.750-3.000	25	AMS 4252
7475-T7351	ST	0.750-4.000	40	AMS 4202
7475-T7651	ST	0.750-1.500	25	AMS 4089

a 50% of specified minimum long transverse yield strength.

b 75% of specified minimum long transverse yield strength.

c Design values are not included in MIL-HDBK-5.

d Most specifications reference ASTM G 47, which requires exposures of 10 days for 2XXX alloys and 20 days for 7XXX alloys in ST test direction.

**DO NOT USE STRESS VALUES FOR DESIGN**



**Table 3.1.2.3.1(c). Maximum Specified Tension Stress at Which Test Specimens Will Not Fail in 3½% NaCl Alternate Immersion Test<sup>e</sup> for Various Stress Corrosion Resistant Aluminum Alloy Rolled Bars, Rods, and Extrusions**

Alloy and Temper	Product Form	Test Direction	Thickness, inches	Stress, ksi	Referenced Specifications
7075-T73-T7351	Rolled Bar and Rod	ST	0.750-3.000	42 <sup>a</sup>	AMS-QQ-A-225/9, AMS 4124, ASTM B211
2219-T8511	Extrusion	ST	0.750-3.000	30	AMS 4162, AMS 4163
7049-T73511	Extrusion	ST	0.750-2.999	41 <sup>b</sup>	AMS 4157
			3.000-5.000	40 <sup>b</sup>	
7049-T76511 <sup>d</sup>	Extrusion	ST	0.750-5.000	20	AMS 4159
7050-T73511	Extrusion	ST	0.750-5.000	45	AMS 4341
7050-T74511	Extrusion	ST	0.750-5.000	35	AMS 4342
7050-T76511	Extrusion	ST	0.750-5.000	17	AMS 4340
7075-T73-T73510-T73511	Extrusion	ST	0.750-1.499	45 <sup>a</sup>	AMS-QQ-A-200/11, AMS 4166, AMS 4167, ASTM B 211
			1.500-2.999	44 <sup>a</sup>	
			3.000-4.999	42 <sup>a</sup>	
			3.000-4.999	41 <sup>a,c</sup>	
7075-T76-T76510-T76511	Extrusion	ST	0.750-1.000	25	AMS-QQ-A-200/15, ASTM B 221
7149-T73511 <sup>d</sup>	Extrusion	ST	0.750-2.999	41 <sup>b</sup>	AMS 4543
			3.000-5.000	40 <sup>b</sup>	
7150-T77511	Extrusion	ST	0.750-2.000	25	AMS 4345
7175-T73511	Extrusion	ST	0.750-2.000	44	AMS 4344

a 75% of specified minimum longitudinal yield strength.

b 65% of specified minimum longitudinal yield strength.

c Over 20 square inches cross-sectional area.

d Design values are not included in MIL-HDBK-5.

e Most specifications reference ASTM G 47, which requires exposures of 10 days for 2XXX alloys and 20 days for 7XXX alloys in ST test direction.

**DO NOT USE STRESS VALUES FOR DESIGN**

**MIL-HDBK-5H****1 December 1998****Table 3.1.2.3.1(d). Maximum Specified Tension Stress at Which Test Specimens Will Not Fail in 3½% NaCl Alternate Immersion Test<sup>d</sup> for Various Stress Corrosion Resistant Aluminum Die Forgings**

Alloy and Temper	Test Direction	Thickness, inches	Stress, ksi	Referenced Specifications
7049-T73	ST	0.750-2.000	46 <sup>a</sup>	QQ-A-367, AMS 4111, ASTM B 247
		2.001-5.000	45 <sup>a</sup>	
7050-T74	ST	0.750-6.000	35	AMS 4107
7050-T7452	ST	0.750-4.000	35	AMS 4333
7075-T73	ST	0.750-3.000	42 <sup>a</sup>	MIL-A-22771, QQ-A-367
		3.001-4.000	41 <sup>a</sup>	AMS 4241, ASTM B 247
		4.001-5.000	39 <sup>a</sup>	AMS 4141
		5.001-6.000	38 <sup>a</sup>	
7075-T7352	ST	0.750-4.000	42 <sup>a</sup>	MIL-A-22771, QQ-A-367, AMS 4147, ASTM B 247
		3.001-4.000	39 <sup>a</sup>	
7075-T7354 <sup>c</sup>	ST	0.750-3.000	42	Company Specification
7075-T74 <sup>c</sup>	ST	0.750-3.000	35	AMS 4131
		3.001-4.000	31 <sup>b</sup>	
		4.001-5.000	30 <sup>b</sup>	
		5.001-6.000	29 <sup>b</sup>	
7149-T73	ST	0.750-2.000	46 <sup>a</sup>	AMS 4320
		2.001-5.000	45 <sup>a</sup>	
7175-T74	ST	0.750-3.000	35	AMS 4149, ASTM B 247
		3.001-4.000	31 <sup>b</sup>	
		4.001-5.000	30 <sup>b</sup>	
		5.001-6.000	29 <sup>b</sup>	
7175-T7452 <sup>c</sup>	ST	0.750-3.000	35	AMS 4179

a 75% of specified minimum longitudinal yield strength.

b 50% of specified minimum longitudinal yield strength.

c Design values are not included in MIL-HDBK-5.

d Most specifications Reference ASTM G 47, which requires 20 days of exposure for 7XXX alloys in ST test direction.

**DO NOT USE STRESS VALUES FOR DESIGN**

**MIL-HDBK-5H****1 December 1998****Table 3.1.2.3.1(e). Maximum Specified Tension Stress at Which Test Specimens Will Not Fail in 3½% NaCl Alternate Immersion Test<sup>f</sup> for Various Stress Corrosion Resistant Aluminum Hand Forgings**

Alloy and Temper	Test Direction	Thickness, inches	Stress, ksi	Referenced Specifications
7049-T73	ST	2.001-3.000	45 <sup>a</sup>	QQ-A-367, AMS 4111, ASTM B 247
		3.001-4.000	44 <sup>a</sup>	
		4.001-5.000	42 <sup>a</sup>	
7049-T7352 <sup>e</sup>	ST	0.750-3.000	44 <sup>a</sup>	AMS 4247
		3.001-4.000	43 <sup>a</sup>	
		4.001-5.000	40 <sup>a</sup>	
7050-T7452	ST	0.750-8.000	35	AMS 4108
7075-T73	ST	0.750-3.000	42 <sup>a</sup>	MIL-A-22771, QQ-A-367, ASTM B 247
		3.001-4.000	41 <sup>a</sup>	
		4.001-4.000	39 <sup>a</sup>	
7075-T7352	ST	5.001-6.000	38 <sup>a</sup>	AMS 4147
		0.750-3.000	39 <sup>c</sup>	
		3.001-4.000	37 <sup>c</sup>	
7075-T74 <sup>e</sup>	ST	4.001-5.000	36 <sup>c</sup>	AMS 4131
		5.001-6.000	34 <sup>c</sup>	
		0.750-3.000	35	
7075-T7452 <sup>e</sup>	ST	3.001-4.000	30 <sup>b</sup>	AMS 4323
		4.001-5.000	28 <sup>b</sup>	
		5.001-6.000	27 <sup>b</sup>	
7149-T73	ST	0.750-2.000	35	AMS 4320
		2.001-3.000	29 <sup>d</sup>	
		3.001-4.000	28 <sup>d</sup>	
7175-T74	ST	4.001-5.000	26 <sup>d</sup>	AMS 4149
		5.001-6.000	24 <sup>d</sup>	
		2.000-3.000	44 <sup>c</sup>	
7175-T7452	ST	3.001-4.000	43 <sup>c</sup>	AMS 4179
		4.001-5.000	42 <sup>c</sup>	
		0.750-3.000	35	
7175-T7452	ST	3.001-4.000	29 <sup>d</sup>	AMS 4179
		4.001-5.000	28 <sup>d</sup>	
		4.001-6.000	26 <sup>d</sup>	
7175-T7452	ST	0.750-3.000	35	AMS 4179
		3.001-4.000	27 <sup>d</sup>	
		4.001-5.000	26 <sup>d</sup>	
7175-T7452	ST	5.001-6.000	24 <sup>d</sup>	AMS 4179
		0.750-3.000	35	
		3.001-4.000	27 <sup>d</sup>	

a 75% of specified minimum longitudinal yield strength.

b 50% of specified minimum longitudinal yield strength.

c 75% of specified minimum long transverse yield strength.

d 50% of specified minimum long transverse yield strength.

e Design values are not included in MIL-HDBK-5.

f Most specifications Reference ASTM G 47, which requires 20 days of exposure for 7XXX alloys in ST test direction.

**DO NOT USE STRESS VALUES FOR DESIGN**

**MIL-HDBK-5H****1 December 1998**

temper to avoid excessive cold work and high residual stress. If the cold worked tempers are heat-treatable alloys are heated for hot forming, a slight decrease in mechanical properties, particularly yield strength, may result.

**3.1.2.3.2 Resistance to Exfoliation [Reference 3.1.2.3.2]** — The high-strength wrought aluminum alloys in certain tempers are susceptible to exfoliation corrosion, dependent upon product and section size. Generally those alloys and tempers that have the lowest resistance to stress-corrosion cracking also have the lowest resistance to exfoliation. The tempers that provide improved resistance to stress-corrosion cracking also provide improved resistance or immunity to exfoliation. For example, the T76 temper of 7075, 7049, 7050, and 7475 provides a very high resistance to exfoliation, i.e., decidedly superior to the T6 temper, and almost the immunity provided by the T73 temper of 7075 alloy (see Reference 3.1.2.3.2).

**3.1.3 MANUFACTURING CONSIDERATIONS**

**3.1.3.1 Avoiding Stress-Corrosion Cracking** — In order to avoid stress-corrosion cracking (see Section 3.1.2.3), practices, such as the use of press or shrink fits; taper pins; clevis joints in which tightening of the bolt imposes a bending load on female lugs; and straightening or assembly operations; which result in sustained surface tensile stresses (especially when acting in the short-transverse grain orientation), should be avoided in these high-strength alloys: 2014-T451, T4, T6, T651, T652; 2024-T3, T351, T4; 7075-T6, T651, T652; 7150-T6151, T61511; and 7475-T6, T651.

Where straightening or forming is necessary, it should be performed when the material is in the freshly quenched condition or at an elevated temperature to minimize the residual stress induced. Where elevated temperature forming is performed on 2014-T4 T451, or 2024-T3 T351, a subsequent precipitation heat treatment to produce the T6 or T651, T81 or T851 temper is recommended.

It is good engineering practice to control sustained short-transverse tensile stress at the surface of structural parts at the lowest practicable level. Thus, careful attention should be given in all stages of manufacturing, starting with design of the part configuration, to choose practices in the heat treatment, fabrication, and assembly to avoid unfavorable combinations of end grain microstructure and sustained tensile stress. The greatest danger arises when residual, assembly, and service stress combine to produce high sustained tensile stress at the metal surface. Sources of residual and assembly stress have been the most contributory to stress-corrosion-cracking problems because their presence and magnitude were not recognized. In most cases, the design stresses (developed by functional loads) are not continuous and would not be involved in the summation of sustained tensile stress. It is imperative that, for materials with low resistance to stress-corrosion cracking in the short-transverse grain orientation, every effort be taken to keep the level of sustained tensile stress close to zero.

**3.1.3.2 Cold-Formed Heat-Treatable Aluminum Alloys** — Cold working such as stretch forming of aluminum alloy prior to solution heat treatment may result in recrystallization or grain growth during heat treatment. The resulting strength, particularly yield strength, may be significantly below the specified minimum values. For critical applications, the strength should be determined on the part after forming and heat treating including straightening operations. To minimize recrystallization during heat treatment, it is recommended that forming be done after solution heat treatment in the as-quenched condition whenever possible, but this may result in compressive yield strength in the direction of stretching being lower than MIL-HDBK-5 design allowables for user heat treat tempers.

**3.1.3.3 Dimensional Changes** — The dimensional changes that occur in aluminum alloy during thermal treatment generally are negligible, but in a few instances these changes may have to be considered in manufacturing. Because of many variables involved, there are no tabulated values for these dimensional changes. In the artificial aging of alloy 2219 from the T42, T351, and T37 tempers to the T62, T851, and T87 tempers, respectively, a net dimensional growth of 0.00010 to 0.0015 in./in. may be

**MIL-HDBK-5H****1 December 1998**

anticipated. Additional growth of as much as 0.0010 in./in. may occur during subsequent service of a year or more at 300°F or equivalent shorter exposures at higher temperatures. The dimensional changes that occur during the artificial aging of other wrought heat-treatable alloys are less than one-half that for alloy 2219 under the same conditions.

**3.1.3.4 Welding** — The ease with which aluminum alloys may be welded is dependent principally upon composition, but the ease is also influenced by the temper of the alloy, the welding process, and the filler metal used. Also, the weldability of wrought and cast alloys is generally considered separately.

Several weldability rating systems are established and may be found in publications by the Aluminum Association, American Welding Society, and the American Society for Metals. Handbooks from these groups can be consulted for more detailed information. Specification AA-R-566 also contains useful information. This document follows most of these references in adopting a four level rating system. An “A” level, or readily weldable, means that the alloy (and temper) is routinely welded by the indicated process using commercial procedures. A “B” level means that welding is accomplished for many applications, but special techniques are required, and the application may require preliminary trials to develop procedures and tests to demonstrate weld performance. A “C” level refers to limited weldability because crack sensitivity, loss of corrosion resistance, and/or loss of mechanical properties may occur. A “D” level indicates that the alloy is not commercially weldable.

The weldability of aluminum alloys is rated by alloy, temper, and welding process (arc or resistance). Tables 3.1.3.4(a) and (b) list the ratings in the alloy section number order in which they appear in Chapter 3.

When heat-treated or work-hardened materials of most systems are welded, a loss of mechanical properties generally occurs. The extent of the loss (if not reheat treated) over the table strength allowables will have to be established for each specific situation.

**MIL-HDBK-5H****1 December 1998****Table 3.1.3.4(a). Fabrication Weldability of Wrought Aluminum Alloys**

MIL-HDBK-5 Section No.	Alloy	Tempers	Weldability <sup>a,c</sup>	
			Inert Gas Metal or Tungsten Arc	Resistance Spot <sup>b</sup>
3.2.1	2014	O T6, T62, T651, T652, T6510, T6511	C B	D B
3.2.2	2017	T4, T42, T451	C	B
3.2.3	2024	O T3, T351, T361, T4, T42 T6, T62, T81, T851, T861 T8510, T8511, T3510, T3511	D C C C	D B B B
3.2.4	2025	T6	C	B
3.2.5	2090	T83	B	B
3.2.6	2124	T851	C	B
3.2.7	2219	O T62, T81, T851, T87, T8510, T8511	A A	B-D A
3.2.8	2618	T61	C	B
3.2.9	2519	T87	A	...
3.5.1	5052	O H32, H34, H36, H38	A A	B A
3.5.2	5083	O H321, H323, H343, H111, H112	A A	B A
3.5.3	5086	O H32, H34, H36, H38, H111, H112	A A	B A
3.5.4	5454	O H32, H34, H111, H112	A A	B A
3.5.5	5456	O H111, H321, H112	A A	B A
3.6.1	6013	T6	A	A
3.6.2	6061	O T4, T42, T451, T4510, T4511, T6 T62, T651, T652, T6510, T6511	A A A	B A A
3.6.3	6151	T6	A	A
3.7.1	7010	All	C	B
3.7.2	7049	All	C	B
	7149			
3.7.3	7050	All	C	B
3.7.4	7075	All	C	B
3.7.5	7150	All	C	B
3.7.6	7175	All	C	B
3.7.7	7475	All	C	B

a Ratings A through D are relative ratings defined as follows:

A - Generally weldable by all commercial procedures and methods.

B - Weldable with special techniques or for specific applications which justify preliminary trials or testing to develop welding procedures and weld performance.

C - Limited weldability because of crack sensitivity or loss in resistance to corrosion and mechanical properties.

D - No commonly used welding methods have been developed.

b See MIL-W-6858 for permissible combinations.

c When using filler wire, the wire should contain less than 0.0008 percent beryllium to avoid toxic fumes.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.1.3.4(b). Fabrication Weldability<sup>a</sup> of Cast Aluminum Alloys**

MIL-HDBK-5 Section No.	Alloy	Weldability <sup>b,c</sup>	
		Inert Gas Metal or Tungsten Arc	Resistance Spot
3.8.1	A201.0	C	C
3.9.1	354.0	B	B
3.9.2	355.0	B	B
3.9.3	C355.0	B	B
3.9.4	356.0	A	A
3.9.5	A356.0	A	A
3.9.6	A357.0	A	B
3.9.7	D357.0	A	A
3.9.8	359.0	A	B

a Weldability related to joining a casting to another part of same composition. The weldability ratings are not applicable to minor weld repairs. Such repairs shall be governed by the contractors procedure for in-process welding of castings, after approval by the procuring agency.

b Ratings A through D are relative ratings defined as follows:

- A - Generally weldable by all commercial procedures and methods.
- B - Weldable with special techniques or for specific applications which justify preliminary trials or testing to develop welding procedure and weld performance.
- C - Limited weldability because of crack sensitivity or loss in resistance to corrosion and mechanical properties.
- D - No commonly used welding methods have been developed.

c When using filler wire, the wire should contain less than 0.0008 percent beryllium to avoid toxic fumes.

**MIL-HDBK-5H****1 December 1998****3.2 2000 SERIES WROUGHT ALLOYS**

Alloys of the 2000 series contain copper as the principal alloying element and are strengthened by solution heat treatment and aging. As a group, these alloys are noteworthy for their excellent strengths at elevated and cryogenic temperatures, and creep resistance at elevated temperatures.

**3.2.1 2014 ALLOY**

**3.2.1.0 Comments and Properties** — 2014 is an Al-Cu alloy available in a wide variety of product forms. Refer to Section 3.1.2.3 for comments regarding the resistance of the alloy to stress-corrosion cracking, and to Section 3.1.3.4 for comments regarding the weldability of the alloy.

The properties of extrusions should be based upon the thickness at the time of quenching prior to machining. Selection of the mechanical properties based upon its final machined thickness may be unconservative; therefore, the thickness at the time of quenching to achieve properties is an important factor in the selection of the proper thickness column. For extrusions having sections with various thicknesses, consideration should be given to the properties as a function of thickness.

Material specifications for 2014 aluminum alloy are presented in Table 3.2.1.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.2.1.0(b) through (g). Stress-strain parameters in accordance with Section 9.3.2.5 are given in Table 3.2.1.0(h). Figure 3.2.1.0 shows the effect of temperature on the physical properties of 2014 alloy.

**Table 3.2.1.0(a). Material Specifications for 2014 Aluminum Alloy**

Specification	Form
AMS 4028	Bare sheet and plate
AMS 4029	Bare sheet and plate
AMS-QQ-A-250/3	Clad sheet and plate
AMS-QQ-A-225/4	Rolled or drawn bar, rod, and shapes
AMS 4121	Bar and rod, rolled or cold finished
AMS-QQ-A-200/2	Extruded bar, rod, and shapes
AMS 4153	Extrusion
MIL-A-22771	Forging
QQ-A-367	Forging
AMS 4133	Forging

The temper index for 2014 is as follows:

Section	Temper
3.2.1.1	T6, T62, T651, T652, T6510, and T6511

**3.2.1.1 T6, T62, T651, T652, T6510, and T6511 Temper** — Figures 3.2.1.1.1(a) through 3.2.1.1.5(b) present elevated-temperature curves for various mechanical properties. Figures 3.2.1.1.6(a) through (r) present tensile and compressive stress-strain and tangent-modulus curves for various tempers, product forms, and temperatures. Figures 3.2.1.1.6(s) through (v) are full-range tensile stress-strain curves for various products and tempers. Figures 3.2.1.1.8(a) through (e) contain S/N fatigue curves for various wrought products in the T6 temper.



**Table 3.2.1.0(b<sub>1</sub>). Design Mechanical and Physical Properties of 2014 Aluminum Alloy Sheet and Plate**

Specification . . . . .	AMS 4029															
Form . . . . .	Sheet				Plate											
Temper . . . . .	T6				T651 <sup>a</sup>											
Thickness, in. . . . .	0.020-0.039		0.040-0.249		0.250-0.499		0.500-1.000		1.001-2.000		2.001-2.500		2.501-3.000		3.001-4.000	
Basis . . . . .	A	B	A	B	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:																
$F_{tu}$ , ksi:																
L . . . . .	65	67	67	68	66	68	66	67	66	67	64	65	...	...	...	...
LT . . . . .	64	66	66	67	67	69	67	68	67	68	65	66	63	64	59	60
ST . . . . .	...	...	...	...	...	...	...	...	...	...	59 <sup>b</sup>	60 <sup>b</sup>	...	...	...	...
$F_{ty}$ , ksi:																
L . . . . .	58	60	59	60	60	62	60	61	60	62	59	61	...	...	...	...
LT . . . . .	57	59	58	59	59	61	59	60	59	61	58	60	57	59	55	57
ST . . . . .	...	...	...	...	...	...	...	...	...	...	54 <sup>b</sup>	56 <sup>b</sup>	...	...	...	...
$F_{cy}$ , ksi:																
L . . . . .	58	60	59	60	58	60	58	59	58	60	57	59	...	...	...	...
LT . . . . .	59	61	60	61	61	63	61	62	61	63	60	62	...	...	...	...
ST . . . . .	...	...	...	...	...	...	...	...	...	...	59	61	...	...	...	...
$F_{su}$ , ksi . . . . .	39	40	40	41	40	41	40	41	40	41	38	39	...	...	...	...
$F_{bru}$ , ksi:																
(e/D = 1.5) . . . . .	97	100	100	102	105	108	105	107	105	107	102	104	...	...	...	...
(e/D = 2.0) . . . . .	123	127	127	129	134	138	134	136	134	136	130	132	...	...	...	...
$F_{bry}$ , ksi:																
(e/D = 1.5) . . . . .	81	84	83	84	90	93	90	92	90	93	88	92	...	...	...	...
(e/D = 2.0) . . . . .	93	96	94	96	106	110	106	109	106	110	104	109	...	...	...	...
$e$ , percent (S-basis):																
LT . . . . .	6	...	7	...	7	...	6	...	4	...	2	...	2	...	1	...
$E$ , 10 <sup>3</sup> ksi . . . . .	10.5				10.7											
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.7				10.9											
$G$ , 10 <sup>3</sup> ksi . . . . .	4.0				4.0											
$\mu$ . . . . .	0.33				0.33											
Physical Properties:																
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.101															
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.2.1.0															

a Bearing values are "dry pin" values per Section 1.4.7.1. See Table 3.1.2.1.1.

b Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.2.1.0(b<sub>2</sub>). Design Mechanical and Physical Properties of 2014 Aluminum Alloy Sheet and Plate —Continued**

Specification . . . . .	AMS 4028							
	Sheet				Plate <sup>a</sup>			
	T62 <sup>b</sup>							
	0.020-0.039		0.040-0.249		0.250-0.499		0.500-1.000	
	A	B	A	B	A	B	A	B
Mechanical Properties:								
$F_{tu}$ , ksi:								
L . . . . .	65	67	67	68	65	67	65	67
LT . . . . .	64	66	66	67	67	69	67	69
$F_{ty}$ , ksi:								
L . . . . .	58	60	59	60	57	59	57	59
LT . . . . .	57	59	58	59	59	61	59	61
$F_{cy}$ , ksi:								
L . . . . .	58	60	59	60	59	61	59	61
LT . . . . .	59	61	60	61	60	62	60	62
$F_{su}$ , ksi . . . . .	39	40	40	41	37	39	37	39
$F_{bru}$ , ksi:								
(e/D = 1.5) . . .	97	100	100	102	100	103	100	103
(e/D = 2.0) . . .	123	127	127	129	127	131	127	131
$F_{bry}$ , ksi:								
(e/D = 1.5) . . .	81	84	83	84	84	87	84	87
(e/D = 2.0) . . .	93	96	95	96	99	103	99	103
$e$ , percent (S-basis):								
LT . . . . .	6	...	7	...	7	...	6	...
$E$ , 10 <sup>3</sup> ksi . . . . .	10.5				10.7			
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.7				10.9			
$G$ , 10 <sup>3</sup> ksi . . . . .	4.0				4.0			
$\mu$ . . . . .	0.33				0.33			
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.101							
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.2.1.0							

a Bearing values are “dry pin” values per Section 1.4.7.1.

b Design allowables were based upon data obtained from testing samples of material, supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.

**Table 3.2.1.0(c<sub>1</sub>). Design Mechanical and Physical Properties of Clad 2014 Aluminum Alloy Sheet and Plate**

Specification	AMS-QQ-A-250/3															
Form	Sheet				Plate											
Temper	T6				T651 <sup>a</sup>											
Thickness, in.	0.020-0.039		0.040-0.249		0.250-0.499		0.500-1.000 <sup>b</sup>		1.001-2.000 <sup>b</sup>		2.001-2.500 <sup>b</sup>		2.501-3.000 <sup>b</sup>		3.001-4.000 <sup>b</sup>	
Basis	A	B	A	B	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:																
$F_u$ , ksi:																
L	62	64	65	67	63	65	63	64	63	64	61	62	...	...	...	...
LT	61	63	64	66	64	66	64	65	64	65	62	63	60	61	56	57
ST	...	...	...	...	...	...	...	...	...	...	59 <sup>c</sup>	60 <sup>c</sup>	...	...	...	...
$F_y$ , ksi:																
L	54	56	57	59	58	60	57	58	57	59	56	58	...	...	...	...
LT	53	55	56	58	57	59	56	57	56	58	55	57	54	56	52	54
ST	...	...	...	...	...	...	...	...	...	...	54 <sup>c</sup>	56 <sup>c</sup>	...	...	...	...
$F_{cy}$ , ksi:																
L	54	56	57	59	56	58	55	56	55	57	54	56	...	...	...	...
LT	55	57	58	60	59	61	58	59	58	60	57	59	...	...	...	...
ST	...	...	...	...	...	...	...	...	...	...	59	61	...	...	...	...
$F_{su}$ , ksi	37	38	39	40	38	39	38	38	38	38	37	37	...	...	...	...
$F_{bru}$ , ksi:																
(e/D = 1.5)	93	96	97	100	101	104	101	102	101	102	97	99	...	...	...	...
(e/D = 2.0)	117	121	123	127	128	132	128	130	128	130	124	126	...	...	...	...
$F_{bry}$ , ksi:																
(e/D = 1.5)	76	78	80	83	87	90	85	87	85	88	84	87	...	...	...	...
(e/D = 2.0)	86	89	91	94	102	106	100	102	100	104	98	102	...	...	...	...
$e$ , percent (S-basis):																
LT	7	...	8	...	8	...	6	...	4	...	2	...	2	...	1	...
$E$ , 10 <sup>3</sup> ksi	10.5				10.7											
$E_c$ , 10 <sup>3</sup> ksi	10.7				10.9											
$G$ , 10 <sup>3</sup> ksi	4.0				4.0											
$\mu$	0.33				0.33											
Physical Properties:																
$\omega$ , lb/in. <sup>3</sup>	0.101															
$C$ , $K$ , and $\alpha$	...															

a Bearing values are "dry pin" values per Section 1.4.7.1. See Table 3.1.2.1.1.

b These values, except in the ST direction, have been adjusted to represent the average properties across the whole section, including the 2-½ percent per side nominal cladding thickness.

c Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).

**MIL-HDBK-5H****1 December 1998****Table 3.2.1.0(c<sub>2</sub>). Design Mechanical and Physical Properties of Clad 2014 Aluminum Alloy Sheet and Plate—Continued**

Specification . . . . .	AMS-QQ-A-250/3									
Form . . . . .	Sheet				Plate <sup>a</sup>					
Temper . . . . .	T62 <sup>b</sup>									
Thickness, in. . . . .	0.020-0.039		0.040-0.249		0.250-0.499	0.500-1.000 <sup>c</sup>	1.001-2.000 <sup>c</sup>	2.001-2.500 <sup>c</sup>	2.501-3.000 <sup>c</sup>	3.001-4.000 <sup>c</sup>
Basis . . . . .	A	B	A	B	S	S	S	S	S	S
Mechanical Properties:										
$F_{tu}$ , ksi:										
L . . . . .	62	64	65	67	62	62	62	60	...	...
LT . . . . .	61	63	64	66	64	64	64	62	60	56
$F_{ty}$ , ksi:										
L . . . . .	54	56	57	59	55	54	54	53	...	...
LT . . . . .	53	55	56	58	57	56	56	55	54	52
$F_{cy}$ , ksi:										
L . . . . .	54	56	57	59	57	56	56	55	...	...
LT . . . . .	55	57	58	60	58	57	56	55	...	...
$F_{su}$ , ksi . . . . .	37	38	39	40	36	36	36	35	...	...
$F_{bru}$ , ksi:										
(e/D = 1.5) . . . .	93	96	97	100	96	96	96	93	...	...
(e/D = 2.0) . . . .	117	121	123	127	121	121	121	118	...	...
$F_{bry}$ , ksi:										
(e/D = 1.5) . . . .	76	78	80	83	81	79	79	78	...	...
(e/D = 2.0) . . . .	86	89	91	94	96	94	94	92	...	...
$e$ , percent (S-basis):										
LT . . . . .	7	...	8	...	8	6	4	2	2	1
$E$ , 10 <sup>3</sup> ksi . . . . .	10.5				10.7					
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.7				10.9					
$G$ , 10 <sup>3</sup> ksi . . . . .	4.0				4.0					
$\mu$ . . . . .	0.33				0.33					
Physical Properties:										
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.101									
$C$ , $K$ , and $\alpha$ . . . . .	...									

a Bearing values are “dry pin” values per Section 1.4.7.1. See Table 3.1.2.1.1.

b Design allowables were based upon data obtained from testing samples of material, supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.

c These values have been adjusted to represent the average properties across the whole section, including the 2-½ percent per side nominal cladding thickness.

**MIL-HDBK-5H****1 December 1998****Table 3.2.1.0(d). Design Mechanical and Physical Properties of 2014 Aluminum Alloy Bar, Rod, and Shapes; Rolled, Drawn, or Cold-Finished**

Specification . . . . .	AMS 4121 and AMS-QQ-A-225/4							AMS-QQ-A-225/4
Form . . . . .	Bar, rod, and shapes, rolled, drawn, or cold-finished							
Temper . . . . .	T6 and T651							T62 <sup>a</sup>
Thickness, in. . . . .	Up to 1.000	1.001-2.000	2.001-3.000	3.001-4.000	4.001-5.000 <sup>b</sup>	5.001-6.000 <sup>b</sup>	6.001-8.000 <sup>b</sup>	≤8.000 <sup>b</sup>
Basis . . . . .	S	S	S	S	S	S	S	S
Mechanical Properties:								
$F_{tu}$ , ksi:								
L . . . . .	65	65	65	65	65	65	65	65
LT . . . . .	64 <sup>c</sup>	63 <sup>c</sup>	62 <sup>c</sup>	61 <sup>c</sup>	60 <sup>c</sup>	59 <sup>c</sup>	...	...
$F_{ty}$ , ksi:								
L . . . . .	55	55	55	55	55	55	55	55
LT . . . . .	53 <sup>c</sup>	52 <sup>c</sup>	51 <sup>c</sup>	50 <sup>c</sup>	49 <sup>c</sup>	48 <sup>c</sup>	...	...
$F_{cy}$ , ksi:								
L . . . . .	53	53	53	53	53	53	53	...
LT . . . . .	...	...	...	...	...	...	...	...
$F_{su}$ , ksi . . . . .	38	38	38	38	38	38	38	...
$F_{bru}$ , ksi:								
(e/D = 1.5) . . . . .	98	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	124	...	...	...	...	...	...	...
$F_{bry}$ , ksi:								
(e/D = 1.5) . . . . .	77	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	88	...	...	...	...	...	...	...
$e$ , percent:								
L . . . . .	8	8	8	8	8	8	8	8
$E$ , 10 <sup>3</sup> ksi . . . . .	10.5							
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.7							
$G$ , 10 <sup>3</sup> ksi . . . . .	4.0							
$\mu$ . . . . .	0.33							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.101							
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.2.1.0							

a Design allowables were based upon data obtained from testing samples of material, supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers.

b For square, rectangular, hexagonal, or octagonal bar, maximum thickness is 4 in., and maximum cross-sectional area is 36 sq. in.

c Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).

**Table 3.2.1.0(e). Design Mechanical and Physical Properties of 2014 Aluminum Alloy Die Forging**

Specification . . . . .	AMS 4133, MIL-A-22771, and QQ-A-367							MIL-A-22771 and QQ-A-367						
	Die forging													
	T6 <sup>c</sup>							T652						
	≤ 1.000		1.001-2.000		2.001-3.000		3.001-4.000	≤ 1.000		1.001-2.000		2.001-3.000		3.001-4.000
Basis . . . . .	A	B	A	B	A	B	S	A	B	A	B	A	B	S
Mechanical Properties:														
<i>F<sub>tu</sub></i> , ksi:														
L . . . . .	65	67	65	67	65	67	63	65	67	65	67	65	67	63
T <sup>a</sup> . . . . .	64 <sup>d</sup>	...	64 <sup>d</sup>	...	63 <sup>d</sup>	...	63	64 <sup>d</sup>	...	64 <sup>d</sup>	...	63 <sup>d</sup>	...	63
<i>F<sub>ty</sub></i> , ksi:														
L . . . . .	56	59	56	59	55	58	55	56	59	56	59	55	58	55
T <sup>a</sup> . . . . .	55 <sup>d</sup>	...	55 <sup>d</sup>	...	54 <sup>d</sup>	...	54	55 <sup>d</sup>	...	55 <sup>d</sup>	...	54 <sup>d</sup>	...	54
<i>F<sub>cy</sub></i> , ksi:														
L . . . . .	59	62	59	62	58	61	58	56	59	56	59	55	58	55
ST . . . . .	56	59	56	59	55	58	55	59	62	59	62	58	61	58
<i>F<sub>su</sub></i> , ksi . . . . .	40	41	40	41	39	40	39	40	41	40	41	39	40	39
<i>F<sub>bru</sub></i> <sup>b</sup> , ksi:														
(e/D = 1.5) . . . .	91	94	91	94	91	94	88	91	94	91	94	91	94	88
(e/D = 2.0) . . . .	123	127	123	127	123	127	120	123	127	123	127	123	127	120
<i>F<sub>bry</sub></i> <sup>b</sup> , ksi:														
(e/D = 1.5) . . . .	73	77	73	77	71	75	71	73	77	73	77	71	75	71
(e/D = 2.0) . . . .	90	94	90	94	88	93	88	90	94	90	94	88	93	88
<i>e</i> , percent (S-basis):														
L . . . . .	6	...	6	...	6	...	6	6	...	6	...	6	...	6
T <sup>a</sup> . . . . .	3	...	2	...	2	...	2	3	...	2	...	2	...	2
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	10.5													
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	10.8													
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	4.0													
<i>μ</i> . . . . .	0.33													
Physical Properties:														
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.101													
<i>C</i> , <i>K</i> , and <i>α</i> . . . . .	See Figure 3.2.1.0													

a T indicates any grain direction not within  $\pm 15^\circ$  of being parallel to the forging flow lines.  $F_{cy}(T)$  values are based upon short transverse (ST) test data.

b Bearing values are “dry pin” values per Section 1.4.7.1.

c When die forgings are machined before heat treatment, the mechanical properties are applicable, provided the as-forged thickness is not greater than twice the thickness at the time of heat treatment.

d Specification value. T tensile properties are presented on S basis only.

e Thickness at time of heat treatment.

**Table 3.2.1.0(f). Design Mechanical and Physical Properties of 2014 Aluminum Alloy Hand Forging**

Specification . . . . .	AMS 4133, MIL-A-22771, and QQ-A-367							MIL-A-22771 and QQ-A-367						
	Hand forging													
Form . . . . .	T6 <sup>a</sup>							T652 <sup>b</sup>						
Temper . . . . .														
Cross-Sectional Area, in. <sup>2</sup>	≤ 256													
Thickness, in. . . . .	≤2.000	2.001-3.000	3.001-4.000	4.001-5.000	5.001-6.000	6.001-7.000	7.001-8.000	≤2.000	2.001-3.000	3.001-4.000	4.001-5.000	5.001-6.000	6.001-7.000	7.001-8.000
Basis . . . . .	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:														
<i>F<sub>u</sub></i> , ksi:														
L . . . . .	65	64	63	62	61	60	59	65	64	63	62	61	60	59
LT . . . . .	65	64	63	62	61	60	59	65	64	63	62	61	60	59
ST . . . . .	...	62 <sup>c</sup>	61 <sup>c</sup>	60 <sup>c</sup>	59 <sup>c</sup>	58 <sup>c</sup>	57 <sup>c</sup>	...	62 <sup>c</sup>	61 <sup>c</sup>	60 <sup>c</sup>	59 <sup>c</sup>	58 <sup>c</sup>	57 <sup>c</sup>
<i>F<sub>y</sub></i> , ksi:														
L . . . . .	56	56	55	54	53	52	51	56	56	55	54	53	52	51
LT . . . . .	56	55	55	54	53	52	51	56	55	55	54	53	52	51
ST . . . . .	...	55 <sup>c</sup>	54 <sup>c</sup>	53 <sup>c</sup>	53 <sup>c</sup>	52 <sup>c</sup>	51 <sup>c</sup>	...	52 <sup>c</sup>	51 <sup>c</sup>	50 <sup>c</sup>	50 <sup>c</sup>	49 <sup>c</sup>	48 <sup>c</sup>
<i>F<sub>cys</sub></i> , ksi:														
L . . . . .	56	56	55	54	53	...	...	56	56	55	54	53	...	...
LT . . . . .	56	55	55	54	53	...	...	57	56	56	55	54	...	...
ST . . . . .	...	...	...	...	...	...	...	...	57	56	55	55	...	...
<i>F<sub>su</sub></i> , ksi . . . . .	40	39	39	38	38	...	...	38	37	37	36	36	...	...
<i>F<sub>bru</sub></i> , ksi:														
(e/D = 1.5) . . . . .	91	90	88	87	85	...	...	88	87	85	84	83	...	...
(e/D = 2.0) . . . . .	117	115	113	112	110	...	...	115	113	111	110	108	...	...
<i>F<sub>bry</sub></i> , ksi:														
(e/D = 1.5) . . . . .	78	78	77	76	74	...	...	77	76	76	74	73	...	...
(e/D = 2.0) . . . . .	90	90	88	87	85	...	...	91	89	89	87	86	...	...
<i>e</i> , percent:														
L . . . . .	8	8	8	7	7	6	6	8	8	8	7	7	6	6
LT . . . . .	3	3	3	2	2	2	2	3	3	3	2	2	2	2
ST . . . . .	...	2	2	1	1	1	1	...	2	2	1	1	1	1
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	10.5													
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	10.8													
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	4.0													
<i>μ</i> . . . . .	0.33													
Physical Properties:														
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.101													
<i>C</i> , <i>K</i> , and <i>α</i> . . . . .	See Figure 3.2.1.0													

a When hand forgings are machined before heat treatment, the section thickness at time of heat treatment shall determine the minimum mechanical properties as long as the original (as-forged) thickness does not exceed the maximum thickness for the alloy as shown in the table.

b Bearing values are "dry pin" values per Section 1.4.7.1.

c Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).

**Table 3.2.1.0(g). Design Mechanical and Physical Properties of 2014 Aluminum Alloy Extrusion**

Specification . . . . .	AMS 4153 and AMS-QQ-A-200/2											AMS-QQ-A-200/2			
	Extruded bar, rod, and shapes														
	T6, T6510, and T6511											T62 <sup>a</sup>			
	≤25											>25-≤32	All	≤25	>25-≤32
	0.125-0.499		0.500-0.749		0.750-1.499		1.500-1.750		1.751-2.999	3.000-4.499	≥0.750	≤0.749	≥0.750	≥0.750	
Basis . . . . .	A	B	A	B	A	B	A	B	S	S	S	S	S	S	
Mechanical Properties:															
<i>F<sub>tu</sub></i> , ksi:															
L . . . . .	60	62	64	68	68	70	68	71	68	68	68	60	60	60	
LT . . . . .	60 <sup>e</sup>	...	64 <sup>e</sup>	...	63 <sup>e</sup>	...	61 <sup>e</sup>	...	61	58	56	...	...	...	
<i>F<sub>ty</sub></i> , ksi:															
L . . . . .	53	57	58	62	60	63	60	63	60	60	58	53	53	53	
LT . . . . .	53 <sup>e</sup>	...	55 <sup>e</sup>	...	54 <sup>e</sup>	...	52 <sup>e</sup>	...	52	49	47	...	...	...	
<i>F<sub>cy</sub></i> , ksi:															
L . . . . .	52	56	57	61	59	62	59	62	...	...	...	...	...	...	
LT . . . . .	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
<i>F<sub>su</sub></i> , ksi . . . . .	35	36	37	39	39	41	39	41	...	...	...	...	...	...	
<i>F<sub>bru</sub><sup>c</sup></i> , ksi:															
(e/D = 1.5) . . . . .	90	93	96	102	102	105	102	106	...	...	...	...	...	...	
(e/D = 2.0) . . . . .	116	120	124	132	132	136	132	138	...	...	...	...	...	...	
<i>F<sub>bry</sub><sup>c</sup></i> , ksi:															
(e/D = 1.5) . . . . .	73	78	80	85	82	86	82	86	...	...	...	...	...	...	
(e/D = 2.0) . . . . .	85	91	93	99	96	101	96	101	...	...	...	...	...	...	
<i>e</i> , percent (S-basis):															
L . . . . .	7	...	7	...	7	...	7	...	7	7	6	7	7	6	
LT . . . . .	5 <sup>d</sup>	...	5	...	2	...	2	...	2	1	1	...	...	...	
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	10.8														
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	11.0														
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	4.1														
<i>μ</i> . . . . .	0.33														
Physical Properties:															
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.101														
<i>C</i> , <i>K</i> , and <i>α</i> . . . . .	See Figure 3.2.1.0														

a Design allowables were based upon data obtained from testing samples of material, supplied in O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers.

b The mechanical properties are to be based upon the thickness at the time of quench.

c Bearing values are "dry pin" values per Section 1.4.7.1.


d For 0.375-0.499 in.

e S-basis.



**MIL-HDBK-5H****1 December 1998****Table 3.2.1.0(h). Typical Stress-Strain Parameters for 2014 Aluminum Alloy**

Temper/Product Form	Condition	Temper- ature, °F	Grain Direction	Tension, ksi			Compression, ksi		
				n	TYS	TUS	n <sub>c</sub>	CYS	
T6 Clad Sheet	0.02-0.039 in. thickness	RT	L	32	57		17	57	
			LT	17	57		13	60	
	0.04-0.249 in. thickness		L	27	62		15	62	
			LT	20	60		17	65	
	½ hr. exposure	200°F	LT				9.5	60	
	100 hr. exposure						8.0	62	
	½ and 2 hr. exposure	300°F					4.0	54	
	1000 hr. exposure						6.4	46	
	½ hr. exposure	400°F					8.2	47	
	100 hr. exposure						10	20	
	1000 hr. exposure						6.0	16	
	½ hr. exposure	500°F					7.0	22	
	½ hr. exposure						4.3	9	
	10 hr. exposure						6.0	8	
	100 hr. exposure						13	7	
	T62 Clad Plate	0.250 - 2.000 in. thickness		RT	L	29	64		27
LT					29	64		27	70
T651 Plate	0.250 - 2.000 in. thickness	RT		L	30	66		15	68
				LT	19	65		18	66
T6 Bar, Rod and Shapes	> 3 in. thickness	RT		L	31	62		25	60
T6 Forging		RT	L			70			
			LT			68			
T652 Hand Forging	2.001 - 3.000 in. thickness	RT	L	18	62	67	17	63	
			LT	18	62	66	18	65	
			ST	13	60		22	67	
T6 Extrusion	0.125 - 0.499 in. thickness	RT	L	23	62		15	64	
	> 0.500 in. thickness			26	68		14	72	
T62 Extrusion	< 0.499 in. thickness	RT	L	29	64	71	17	68	
			LT	29	64		32	68	
T651X Extrusion	0.500 - 0.749 in. thickness	RT	L	32	64	74	16	68	
			LT	18	64	70	18	68	

**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.1.0. Effect of temperature on the physical properties of 2014 aluminum alloy.**

MIL-HDBK-5H

1 December 1998






Figure 3.2.1.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2014-T6, T651, T6510 and T6511 aluminum alloy (bare and clad sheet and plate 0.040-1.500 in. thick; extruded bar, rod and shapes  $\geq 0.750$  in. thick with cross-sectional area  $\leq 32$  sq. in.).


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.1.1(b). Effect of temperature on the ultimate strength ( $F_{tu}$ ) of 2014-T6, T651, T6510 and T6511 aluminum alloy (bare and clad sheet 0.020-0.039 in. thick; bare and clad plate 1.501-4.000 in. thick; rolled bar, rod and shapes; hand and die forgings; extruded bar, rod and shapes 0.125-0.749 in. thick with cross-sectional area  $\leq 25$  sq. in.).**

**MIL-HDBK-5H****1 December 1998**


**Figure 3.2.1.1(c). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2014-T6, T651, T6510 and T6511 aluminum alloy (bare and clad plate 3.001-4.000 in. thick; rolled bar, rod and shapes; hand and die forgings; extruded bar, rod and shapes 0.125-0.499 in. thick with cross-sectional area  $\leq 25$  sq. in.).**

**MIL-HDBK-5H****1 December 1998**


**Figure 3.2.1.1(d). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2014-T6, T651, T6510, and T6511 aluminum alloy (bare and clad sheet and plate 0.020-3.000 in. thick; extruded bar, rod and shapes 0.500-0.749 in. thick with cross-sectional area  $\leq 25$  sq. in. and  $\geq 0.750$  in. thick with cross-sectional area  $\leq 32$  sq. in.).**

**MIL-HDBK-5H****1 December 1998**


**Figure 3.2.1.1(e). Effect of exposure at elevated temperatures on the room-temperature tensile ultimate strength ( $F_{tu}$ ) of 2014-T6, T651, T6510, and T6511 aluminum alloy (all products except thick extrusions).**



**Figure 3.2.1.1(f). Effect of exposure at elevated temperature on the room-temperature tensile yield strength ( $F_{ty}$ ) of 2014-T6, T651, T6510, and T6511 aluminum alloy (all products except thick extrusions).**

**MIL-HDBK-5H****1 December 1998**


**Figure 3.2.1.1.2(a). Effect of temperature on the compressive yield strength ( $F_{cy}$ ) of 2014-T6, T651, T6510 and T6511 aluminum alloy (all products except thick extrusions).**




**Figure 3.2.1.1.2(b). Effect of temperature on the shear ultimate strength ( $F_{su}$ ) of 2014-T6, T651, T6510 and T6511 aluminum alloy (all products except thick extrusions).**



**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.1.1.3(a). Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) of 2014-T6, T651, T6510 and T6511 aluminum alloy (all products except thick extrusions).**



**Figure 3.2.1.1.3(b). Effect of temperature on the bearing yield strength ( $F_{bry}$ ) of 2014-T6, T651, T6510 and T6511 aluminum alloy (all products except thick extrusions).**

MIL-HDBK-5H

1 December 1998






Figure 3.2.1.1.4. Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of 2014 aluminum alloy.


**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.1.1.5(a). Effect of temperature on the elongation of 2014-T6, T651, T6510 and T6511 aluminum alloy (all products except thick extrusions).**




**Figure 3.2.1.1.5(b). Effect of exposure at elevated temperatures on the room-temperature elongation of 2014-T6, T651, T6510 and T6511 aluminum alloy (all products except thick extrusions).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.1.1.6(a). Typical tensile stress-strain curves for clad 2014-T6 aluminum alloy sheet at room temperature.**




**Figure 3.2.1.1.6(b). Typical tensile stress-strain curves for clad 2014-T6 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.1.1.6(c). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2014-T6 aluminum alloy sheet at room temperature.**



**Figure 3.2.1.1.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2014-T6 aluminum alloy sheet at room temperature.**

## MIL-HDBK-5H

1 December 1998




Figure 3.2.1.1.6(e). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2014-T6 aluminum alloy sheet at 200°F.




Figure 3.2.1.1.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2014-T6 aluminum alloy sheet at 300°F.

MIL-HDBK-5H  
1 December 1998




Figure 3.2.1.1.6(g). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2014-T6 aluminum alloy sheet at 400°F.






Figure 3.2.1.1.6(h). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2014-T6 aluminum alloy sheet at 500°F.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.1.1.6(i). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2014-T6 aluminum alloy sheet at 600°F.**




**Figure 3.2.1.1.6(j). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for clad 2014-T62 aluminum alloy plate at room temperature.**




**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.1.1.6(k). Typical tensile stress-strain curves for 2014-T651 aluminum alloy plate at room temperature.**



**Figure 3.2.1.1.6(l). Typical compressive stress-strain and compressive tangent-modulus curves for 2014-T651 aluminum alloy plate at room temperature.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.1.1.6(m). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2014-T6 aluminum alloy rolled bar, rod, and shapes at room temperature.**




**Figure 3.2.1.1.6(n). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2014-T652 aluminum alloy hand forging at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.1.1.6(o). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2014-T6 aluminum alloy extrusion at room temperature.**



**Figure 3.2.1.1.6(p). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2014-T6 aluminum alloy extrusion at room temperature.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.1.1.6(q). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2014-T62 aluminum alloy extrusion at room temperature.**




**Figure 3.2.1.1.6(r). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2014-T651X aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.1.1.6(s). Typical tensile stress-strain curves (full range) for 2014-T6 aluminum alloy forging at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.1.1.6(t). Typical tensile stress-strain curves (full range) for 2014-T652 aluminum alloy forging at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.1.1.6(u). Typical tensile stress-strain curves (full range) for 2014-T62 aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.1.1.6(v). Typical tensile stress-strain curves (full range) for 2014-T651X aluminum alloy extrusion at room temperature.**



**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.1.1.8(a). Best-fit S/N curves for unnotched 2014-T6 aluminum alloy, various wrought products, longitudinal direction.**

Correlative Information for Figure 3.2.1.1.8(a)

Product Form: Drawn rod, 3/4-inch diameter  
 Rolled bar, 1 x 7-1/2-inch and  
 1-1/8-inch diameter  
 Rolled rod, 4-1/2-inch diameter  
 Extruded rod, 1-1/4-inch diameter  
 Extruded bar, 1-1/4 x 4 inch  
 Hand forging, 3 x 6 inch  
 Die forging, 4-1/2-inch diameter  
 Forged slab, 7/8-inch

References: 3.2.1.1.8(a), (b), (d), and (e)

Test Parameters:

Loading - Axial  
 Frequency - 1100 to 3600 cpm  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: Not specified

Properties: TUS, ksi TYS, ksi Temp., °F  
 67-78 60-72 RT

Equivalent Stress Equation:

$\log N_f = 21.49 - 9.44 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.67}$   
 Standard Error of Estimate = 0.51  
 Standard Deviation in Life = 1.25  
 $R^2 = 83\%$

Specimen Details: Unnotched

Gross Diameter, inches	Net Diameter, inches
1.00	0.400
0.273	0.100
---	0.200
---	0.160
1.00	0.500

Sample Size = 127


[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

Surface Condition:

Mechanically polished and as-machined

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.1.1.8(b). Best-fit S/N curves for notched,  $K_t = 1.6$ , 2014-T6 aluminum alloy rolled bar, longitudinal direction.**

Correlative Information for Figure 3.2.1.1.8(b)

Product Form: Rolled bar, 1-1/8-inch diameter

Test Parameters:

Properties:      TUS, ksi    TYS, ksi      Temp., °F

Loading - Axial  
Frequency - 3600 cpm  
Temperature - RT  
Environment - Air

72          64                  RT

Specimen Details:    Semicircular circumferential notch,  $K_t = 1.6$   
0.45-inch gross diameter  
0.4-inch net diameter  
0.01-inch root radius  
60° flank angle,  $\omega$

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$$\log N_f = 10.65 - 4.02 \log (S_{eq} - 20.2)$$

$$S_{eq} = S_{max} (1-R)^{0.55}$$

Standard Error of Estimate = 0.33

Standard Deviation in Life = 0.87

$$R^2 = 86\%$$

Surface Condition: Polished


Reference:          3.2.1.1.8(b)

Sample Size = 33

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.1.1.8(c). Best-fit S/N curves for notched,  $K_t = 2.4$ , 2014-T6 aluminum alloy rolled bar, longitudinal direction.**

Correlative Information for Figure 3.2.1.1.8(c)

Product Form: Rolled bar, 1-1/8-inch diameter

Test Parameters:

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     72            64            RT

Loading - Axial  
 Frequency - 1800 cpm  
 Temperature - RT  
 Environment - Air

Specimen Details:    Circumferential V-notch,  
                                      $K_t = 2.4$   
                                     0.500-inch gross diameter  
                                     0.400-inch net diameter  
                                     0.032-inch notch radius  
                                     60° flank angle,  $\omega$

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$$\log N_f = 10.59 - 4.36 \log (S_{eq} - 11.7)$$

$$S_{eq} = S_{max} (1 - R)^{0.52}$$

Standard Error of Estimate = 0.38

Standard Deviation in Life = 1.18

$$R^2 = 75\%$$

Surface Condition: Polished


Reference:        3.2.1.1.8(b)

Sample Size = 39

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.1.1.8(d). Best-fit S/N curves for notched,  $K_t = 3.4$ , 2014-T6 aluminum alloy rolled and extruded bar, longitudinal direction.**

## Correlative Information for Figure 3.2.1.1.8(d)

Product Form: Extruded bar, 1-1/8-inch diameter

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial  
Frequency - 3600 cpm  
Temperature - RT  
Environment - Air

75 67 RT

Specimen Details: Circumferential V-notch,  
 $K_t = 3.4$   
0.450-inch gross diameter  
0.400-inch net diameter  
0.010-inch notch radius  
60° flank angle,  $\omega$

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$$\log N_f = 8.35 - 3.10 \log (S_{eq} - 10.6)$$

$$S_{eq} = S_{max} (1-R)^{0.52}$$

Standard Error of Estimate = 0.34

Standard Deviation in Life = 1.10

$$R^2 = 90\%$$

Surface Condition: Smooth machine finish


References: 3.2.1.1.8(b) and (c)

Sample Size = 45

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.1.1.8(e). Best-fit S/N curves for notched,  $K_t = 2.4$ , 2014-T6 aluminum alloy hand forging, longitudinal and short transverse directions.**

## Correlative Information for Figure 3.2.1.1.8(e)

Product Form: Hand forging, 3 x 6 inch

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial

Frequency - Not specified

Not specified

RT

Temperature - RT

Environment - Air

Specimen Details: Circumferential V-notch,  
 $K_t = 2.4$   
 0.273-inch gross diameter  
 0.100-inch net diameter  
 0.010-inch notch radius  
 60° flank angle,  $\omega$

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 12.4 - 5.95 \log (S_{\max})$

Standard Error of Estimate = 0.53

Standard Deviation in Life = 0.91

$R^2 = 66\%$

Surface Condition: Mechanically polished

Sample Size = 28

Reference: 3.2.1.1.8(d)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]


**MIL-HDBK-5H****1 December 1998****3.2.2 2017 ALLOY**

**3.2.2.0 Comments and Properties** — 2017 is a heat-treatable Al-Cu alloy available in the form of rolled bar, rod, and wire, and is used principally for fasteners. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

A material specification for 2017 aluminum alloy is presented in Table 3.2.2.0(a). Room-temperature mechanical and physical properties are shown in Table 3.2.2.0(b). Figure 3.2.2.0 shows the effect of temperature on thermal expansion.

**Table 3.2.2.0(a). Material Specifications for 2017 Aluminum Alloy**

Specification	Form
AMS-QQ-A-225/5	Rolled bar and rod
AMS 4118	Bar and rod, rolled or cold-finished

**Figure 3.2.2.0. Effect of temperature on the thermal expansion of 2017 aluminum alloy.**

**MIL-HDBK-5H****1 December 1998**

The temper index for 2017 is as follows:

Section  
3.2.2.1

Temper  
T4, T451, and T42

**3.2.2.1 T4, T451, and T42 Temper** — The effect of temperature on modulus elasticity is presented in Figure 3.2.2.1.4.


**Table 3.2.2.0(b). Design Mechanical and Physical Properties of 2017 Aluminum Alloy Bar and Rod; Rolled, Drawn, or Cold-Finished**

Specification .....	AMS 4118 and AMS-QQ-A-225/5
Form .....	Bar and rod; rolled, drawn, or cold-finished
Temper .....	T4, T451, T42 <sup>a</sup>
Cross-Sectional Area, in. <sup>2</sup> ...	≤50
Thickness or Diameter, in. ...	≤8.000
Basis .....	S
Mechanical Properties:	
$F_{tu}$ , ksi:	
L .....	55
LT .....	...
$F_{ty}$ , ksi:	
L .....	32
LT .....	...
$F_{cy}$ , ksi:	
L .....	32 <sup>b</sup>
LT .....	...
$F_{su}$ , ksi .....	33
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	83
(e/D = 2.0) .....	105
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	45
(e/D = 2.0) .....	51
e, percent (S-basis):	
L .....	12
E, 10 <sup>3</sup> ksi .....	10.4
$E_c$ , 10 <sup>3</sup> ksi .....	10.6
G, 10 <sup>3</sup> ksi .....	3.95
$\mu$ .....	0.33
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.101
C, Btu/(lb)(°F) .....	0.23 (at 212°F)
K, Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] ..	78 (at 77°F)
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	See Figure 3.2.2.0

a Design allowables were based upon data obtained from testing T4 material and from testing samples of bar and rod, supplied in the O or F temper, which were heat treated to T42 temper to demonstrate response to heat treatment by suppliers.

b For the stress-relieved temper T451, the  $F_{cy}$  value may be somewhat lower.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.2.1.4. Effect of temperature on the tensile and compression moduli (E and E<sub>c</sub>) of 2017 aluminum alloy.**



**MIL-HDBK-5H****1 December 1998****3.2.3 2024 ALLOY**

**3.2.3.0 Comments and Properties** — 2024 is a heat-treatable Al-Cu alloy which is available in a wide variety of product forms and tempers. The properties vary markedly with temper; those in T3 and T4 type tempers are noteworthy for their high toughness, while T6 and T8 type tempers have very high strength. This alloy has excellent properties and creep resistance at elevated temperatures. The T6 and T8 type tempers have very high resistance to corrosion, while T3 and T4 type tempers should be considered in light of Section 3.1.2.3. The weldability of the alloy is discussed in Section 3.1.3.4.

The properties of extrusions should be based upon the thickness at the time of quenching prior to machining. Selection of the mechanical properties based upon its final machined thickness may be unconservative; therefore, the thickness at the time of quenching to achieve properties is an important factor in the selection of the proper thickness column. For extrusions having sections with various thicknesses, consideration should be given to the properties as a function of thickness.

Material specifications for 2024 are presented in Table 3.2.3.0(a). Room-temperature mechanical properties are shown in Tables 3.2.3.0(b) through (j). The effect of temperature on the physical properties of this alloy is shown in Figure 3.2.3.0.

**Table 3.2.3.0(a). Material Specifications for 2024 Aluminum Alloy**

Specification	Form
AMS 4037	Bare sheet and plate
AMS 4035	Bare sheet and plate
AMS-QQ-A-250/4	Bare sheet and plate
AMS-QQ-A-250/5	Clad sheet and plate
AMS 4120	Bar and rod, rolled or cold-finished
AMS-QQ-A-225/6	Rolled or drawn bar, rod, and wire
AMS 4086	Tubing, hydraulic, seamless, drawn
WW-T-700/3	Tubing
AMS 4152	Extrusion
AMS 4164	Extrusion
AMS 4165	Extrusion
AMS-QQ-A-200/3	Extruded bar, rod, and shapes


The following temper designations are more specifically described than in Table 3.1.2.:

T81—The applicable designation for 2024-T3 sheet artificially aged to the required strength level.

T361—Solution heat treated and naturally aged followed by cold rolling and natural aging treatment.

T861—Solution heat treated and naturally aged followed by cold rolling and artificial aging treatment.

T72—Solution heat treated and aged by user in accordance with MIL-H-6088 to provide high resistance to stress-corrosion cracking, applicable only to sheet.

**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.3.0. Effect of temperature on the physical properties of 2024 aluminum alloy.**

The temper index for 2024 is as follows:

<u>Section</u>	<u>Temper</u>
3.2.3.1	T3, T351, T3510, T3511, T4, and T42
3.2.3.2	T361 (supersedes T36)
3.2.3.3	T62 and T72
3.2.3.4	T81, T851, T8510, and T8511
3.2.3.5	T861 (supersedes T86)

**3.2.3.1 T3, T351, T3510, T3511, T4, and T42 Temper** — Figures 3.2.3.1.1(a) through 3.2.3.1.5(b) present elevated temperature curves for various properties. Figures 3.2.3.1.6(a) through (q) present tensile and compressive stress-strain curves and tangent-modulus curves for various product forms and tempers at various temperatures. Figures 3.2.3.1.6(r) through (w) are full-range, stress-strain curves at room temperature for various product forms. Figures 3.2.3.1.8(a) through (i) provide S/N fatigue curves for unnotched and notched specimens for T3 and T4 tempers.

**MIL-HDBK-5H****1 December 1998****3.2.3.2 T361 (supersedes T36) Temper —**

**3.2.3.3 T62 and T72 Temper** — Figures 3.2.3.3.1(a) through (d) and 3.2.3.3.5(a) and (b) show the effect of temperature on the tensile properties of the T62 temper. Figure 3.2.3.1.4 can be used for the elevated temperature curve for elastic moduli for this temper. Tensile and compressive stress-strain and tangent-modulus curves at room temperature are shown in Figure 3.2.3.3.6.

**3.2.3.4 T81, T851, T852, T8510, and T8511 Temper** — Figures 3.2.3.4.1(a) through (d), 3.2.3.4.2(a) and (b), 3.2.3.4.3(a) and (b), and 3.2.3.4.5(a) and (b) present elevated temperature curves for various mechanical properties for the T8XXX temper. Figures 3.2.3.4.1(e) and (f) contain graphs for determining tensile properties after complex thermal exposure. See Section 3.7.4.1 for a detailed discussion of their use. Figures 3.2.3.4.6(a) through (g) present tensile and compressive stress-strain and tangent-modulus curves for various products and tempers. Figures 3.2.3.4.6(h) through (j) are full-range stress-strain curves at room temperature for various product forms.

**3.2.3.5 T861 (T86) Temper** — Figures 3.2.3.5.1(a) through (d), 3.2.3.5.2(a) and (b), 3.2.3.5.3(a) through (c), and 3.2.3.5.5(a) and (b) present effect-of-temperature curves for various mechanical properties. Figures 3.2.3.5.6(a) through (d) present compressive stress-strain and tangent-modulus curves for sheet material at various temperatures. Graphical displays of the residual strength behavior of center-cracked tension panels are presented in Figures 3.2.3.5.10(a) and (b).

**Table 3.2.3.0(b<sub>1</sub>). Design Mechanical and Physical Properties of 2024 Aluminum Alloy Sheet and Plate**

Specification . . . . .	AMS 4037 and AMS-QQ-A-250/4																	AMS-QQ-A-250/4		
	Sheet					Plate												Sheet		Plate
	T3					T351												T361		
	0.008-0.009	0.010-0.128	0.129-0.249			0.250-0.499	0.500-1.000		1.001-1.500		1.501-2.000		2.001-3.000		3.001-4.000		0.020-0.062	0.063-0.249	0.250-0.500	
	S	A	B	A	B	A	B	A	B	A	B	A	B	A	B	A	B	S	S	S
Mechanical Properties:																				
$F_{tu}$ , ksi:																				
L . . . . .	64	64	65	65	66	64	66	63	65	62	64	62	64	60	62	57	59	68	69	67
LT . . . . .	63	63	64	64	65	64	66	63	65	62	64	62	64	60	62	57	59	67	68	66
ST . . . . .	...	...	...	...	...	...	...	...	...	...	...	...	...	52 <sup>a</sup>	54 <sup>a</sup>	49 <sup>a</sup>	51 <sup>a</sup>	...	...	...
$F_{ty}$ , ksi:																				
L . . . . .	47	47	48	47	48	48	50	48	50	47	50	47	49	46	48	43	46	56	56	54
LT . . . . .	42	42	43	42	43	42	44	42	44	42	44	42	44	42	44	41	43	50	51	49
ST . . . . .	...	...	...	...	...	...	...	...	...	...	...	...	...	38 <sup>a</sup>	40 <sup>a</sup>	38 <sup>a</sup>	39 <sup>a</sup>	...	...	...
$F_{cy}$ , ksi:																				
L . . . . .	39	39	40	39	40	39	41	39	41	39	40	38	40	37	39	35	37	47	48	46
LT . . . . .	45	45	46	45	46	45	47	45	47	44	46	44	46	43	45	41	43	53	54	52
ST . . . . .	...	...	...	...	...	...	...	...	...	...	...	...	...	46	48	44	47	...	...	...
$F_{su}$ , ksi	39	39	40	40	41	38	39	37	38	37	38	37	38	35	37	34	35	42	42	41
$F_{bru}^b$ , ksi:																				
(e/D = 1.5) . . . . .	104	104	106	106	107	97	100	95	98	94	97	94	97	91	94	86	89	111	112	109
(e/D = 2.0) . . . . .	129	129	131	131	133	119	122	117	120	115	119	115	119	111	115	106	109	137	139	135
$F_{bry}^b$ , ksi:																				
(e/D = 1.5) . . . . .	73	73	75	73	75	72	76	72	76	72	76	72	76	72	76	70	74	82	84	81
(e/D = 2.0) . . . . .	88	88	90	88	90	86	90	86	90	86	90	86	90	86	90	84	88	97	99	96
$e$ , percent (S-basis):																				
LT . . . . .	10	c	...	c	...	12	...	8	...	7	...	6	...	4	...	4	...	8	9	9 <sup>d</sup>
$E$ , 10 <sup>3</sup> ksi . . . . .	10.5					10.7												10.5		10.7
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.7					10.9												10.7		10.9
$G$ , 10 <sup>3</sup> ksi . . . . .	4.0					4.0												4.0		4.0
$\mu$ . . . . .	0.33					0.33												0.33		0.33
Physical Properties:																				
$\omega$ , lb/in. . . . .	0.100																			
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.2.3.0																			

a Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).

b Bearing values are "dry pin" values per Section 1.4.7.1. See Table 3.1.2.1.1.

c See Table 3.2.3.0(c).

d 10% for 0.500 inch.

**Table 3.2.3.0(b<sub>2</sub>). Design Mechanical and Physical Properties of 2024 Aluminum Alloy Sheet and Plate—Continued**

Specification . . . . .	AMS-QQ-A-250/4		AMS 4035 and AMS-QQ-A-250/4					AMS-QQ-A-250/4				
	Coiled Sheet		Flat Sheet and Plate									
	T4		T42 <sup>a</sup>					T62 <sup>a</sup>				T72 <sup>a</sup>
	0.010-0.249		0.010-0.249	0.250-0.499	0.500-1.000	1.001-2.000	2.001-3.000	0.010-0.249	0.250-0.499	0.500-2.000	2.001-3.000	0.010-0.249
Basis . . . . .	A	B	S <sup>b</sup>	S <sup>b</sup>	S <sup>b</sup>	S <sup>b,c</sup>	S	S <sup>b</sup>	S <sup>b</sup>	S <sup>b,c</sup>	S	S
Mechanical Properties:												
<i>F<sub>tu</sub></i> , ksi:												
L . . . . .	62	64	62	62	61	60	...	63	63	63	...	...
LT . . . . .	62	64	62	62	61	60	58	64	64	63	63	60
<i>F<sub>ty</sub></i> , ksi:												
L . . . . .	40	42	38	38	38	38	...	50	50	50	...	...
LT . . . . .	40	42	38	38	38	38	38	50	50	50	50	46
<i>F<sub>cy</sub></i> , ksi:												
L . . . . .	40	42	42	42	40	37	...	52	52	52	...	...
LT . . . . .	40	42	41	41	41	41	...	53	52	48	...	...
<i>F<sub>su</sub></i> , ksi . . . . .	37	38	37	37	36	36	...	38	38	37	...	...
<i>F<sub>bru</sub></i> , ksi:												
(e/D = 1.5) . . . . .	93	96	99	98	94	85	...	103	103	102	...	...
(e/D = 2.0) . . . . .	118	122	123	123	121	119	...	134	134	132	...	...
<i>F<sub>bry</sub></i> , ksi:												
(e/D = 1.5) . . . . .	56	59	67	67	67	67	...	80	80	80	...	...
(e/D = 2.0) . . . . .	64	67	80	80	80	80	...	95	95	95	...	...
<i>e</i> , percent (S-basis):												
LT . . . . .	d	...	d	12	8	d	4	5	5	5	5	5
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	See Table 3.2.3.0(d)											
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	See Table 3.2.3.0(d)											
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	See Table 3.2.3.0(d)											
<i>μ</i> . . . . .	See Table 3.2.3.0(d)											
Physical Properties:												
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.100											
<i>C</i> , Btu/(lb)(°F) . . . . .	See Figure 3.2.3.0											
<i>K</i> , Btu/[ (hr)(ft <sup>2</sup> )(°F)/ft] . . . . .	71 (at 77°F) for T4X and 87 (at 77°F) for T6X, T7X, See Figure 3.2.3.0											
<i>α</i> , 10 <sup>-6</sup> in./in./°F . . . . .	See Figure 3.2.3.0											

a Design allowables in some cases were based upon data obtained from testing samples of material, supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user may be different than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.

b Bearing values are “dry pin” values per Section 1.4.7.1.

c See Table 3.1.2.1.1.

d See Table 3.2.3.0(c).

**MIL-HDBK-5H****1 December 1998****Table 3.2.3.0(b<sub>3</sub>). Design Mechanical and Physical Properties of 2024 Aluminum Alloy Sheet and Plate—Continued**

Specification . . . . .	AMS-QQ-A-250/4								
Form . . . . .	Sheet		Plate				Sheet		Plate
Temper . . . . .	T81		T851 <sup>a</sup>				T861 <sup>a</sup>		
Thickness, in. . . . .	0.010- 0.249		0.250- 0.499		0.500- 1.000	1.001- 1.499	0.020- 0.062	0.063- 0.249	0.250- 0.500
Basis . . . . .	A	B	A	B	S	S <sup>b</sup>	S	S	S
Mechanical Properties:									
$F_{tu}$ , ksi:									
L . . . . .	67	68	67	68	66	66	71	72	70
LT . . . . .	67	68	67	68	66	66	70	71	70
$F_{ty}$ , ksi:									
L . . . . .	59	61	58	60	58	57	63	67	64
LT . . . . .	58	60	58	60	58	57	62	66	64
$F_{cy}$ , ksi:									
L . . . . .	59	61	58	60	58	56	63	67	64
LT . . . . .	58	60	59	61	58	57	65	69	67
$F_{su}$ , ksi . . . . .	40	41	38	39	37	37	40	40	40
$F_{bru}$ , ksi:									
(e/D = 1.5) . . . . .	100	102	102	103	100	100	108	110	108
(e/D = 2.0) . . . . .	127	129	131	133	129	129	140	142	140
$F_{bry}$ , ksi:									
(e/D = 1.5) . . . . .	83	86	86	89	86	85	90	96	93
(e/D = 2.0) . . . . .	94	97	101	105	101	99	105	112	109
$e$ , percent (S-basis):									
LT . . . . .	5	...	5	...	5	5	3	4	4
$E$ , 10 <sup>3</sup> ksi . . . . .	See Table 3.2.3.0(d)								
$E_c$ , 10 <sup>3</sup> ksi . . . . .	See Table 3.2.3.0(d)								
$G$ , 10 <sup>3</sup> ksi . . . . .	See Table 3.2.3.0(d)								
$\mu$ . . . . .	See Table 3.2.3.0(d)								
Physical Properties:									
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.100								
$C$ , Btu/(lb)(°F) . . .	See Figure 3.2.3.0								
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	87 (at 77°F)								
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . .	See Figure 3.2.3.0								

a Bearing values are “dry pin” values per Section 1.4.7.1.

b See Table 3.1.2.1.1.

**MIL-HDBK-5H****1 December 1998****Table 3.2.3.0(c). Minimum Elongation Values for Bare 2024 Aluminum Alloy Sheet and Plate**

Condition .....	Elongation (LT), percent
	T3, T4, and T42
Thickness, in.:	
0.010-0.020 .....	12
0.021-0.249 .....	15
0.250-0.499 .....	12
0.500-1.000 .....	8
1.001-1.500 .....	7
1.501-2.000 .....	6

**Table 3.2.3.0(d). Modulus Values and Poisson's Ratio for Bare 2024 Aluminum Alloy Sheet and Plate, All Tempers**

Property	$E$	$E_c$	$G$	$\mu$
Thickness, in.:				
0.010-0.249 .....	10.5	10.7	4.0	0.33
≥0.250 .....	10.7	10.9	4.0	0.33

**Table 3.2.3.0(e<sub>1</sub>). Design Mechanical and Physical Properties of Clad 2024 Aluminum Alloy Sheet and Plate**

Specification .....	AMS-QQ-A-250/5																			
Form .....	Flat sheet and plate																			
Temper .....	T3								T351											
Thickness, in. ....	0.008-0.009		0.010-0.062		0.063-0.128		0.129-0.249		0.250-0.499		0.500-1.000 <sup>a</sup>		1.001-1.500 <sup>a</sup>		1.501-2.000 <sup>a</sup>		2.001-3.000 <sup>a</sup>		3.001-4.000 <sup>a</sup>	
Basis .....	A	B	A	B	A	B	A	B	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:																				
$F_u$ , ksi:																				
L .....	59	60	60	61	62	63	63	64	62	64	61	63	60	62	60	62	58	60	55	57
LT .....	58	59	59	60	61	62	62	63	62	64	61	63	60	62	60	62	58	60	55	57
ST .....	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	52 <sup>b</sup>	54 <sup>b</sup>	49 <sup>b</sup>	51 <sup>b</sup>
$F_y$ , ksi:																				
L .....	44	45	44	45	45	47	45	47	46	48	45	48	45	48	45	47	44	46	39	41
LT .....	39	40	39	40	40	42	40	42	40	42	40	42	40	42	40	42	40	42	39	41
ST .....	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	38 <sup>b</sup>	40 <sup>b</sup>	38 <sup>b</sup>	39 <sup>b</sup>
$F_{cy}$ , ksi:																				
L .....	36	37	36	37	37	39	37	39	37	39	37	39	37	39	36	38	35	37	33	35
LT .....	42	43	42	43	43	45	43	45	43	45	42	45	42	44	42	44	41	43	39	41
ST .....	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	46	48	44	47
$F_{su}$ , ksi .....	37	37	37	38	38	39	39	40	37	38	36	37	35	37	35	37	34	35	32	34
$F_{bru}^c$ , ksi:																				
(e/D = 1.5) .....	96	97	97	99	101	102	102	104	94	97	92	95	91	94	91	94	88	91	83	86
(e/D = 2.0) .....	119	121	121	123	125	127	127	129	115	119	113	117	111	115	111	115	107	111	102	106
$F_{bry}^c$ , ksi:																				
(e/D = 1.5) .....	68	70	68	70	70	73	70	73	69	72	69	72	69	72	69	72	69	72	67	70
(e/D = 2.0) .....	82	84	82	84	84	88	84	88	82	86	82	86	82	86	82	86	82	86	80	84
$e$ , percent (S-basis):																				
LT .....	10	...	<sup>d</sup>	...	15	...	15	...	12	...	8	...	7	...	6	...	4	...	4	...
$E$ , 10 <sup>3</sup> ksi:																				
Primary .....	10.5								10.7											
Secondary .....	9.5				10.0				10.2											
$E_c$ , 10 <sup>3</sup> ksi:																				
Primary .....	10.7								10.9											
Secondary .....	9.7				10.2				10.4											
$G$ , 10 <sup>3</sup> ksi .....	...																			
$\mu$ .....	0.33																			
Physical Properties:																				
$\omega$ , lb/in. <sup>3</sup> .....	0.100																			
$C$ , $K$ , and $\alpha$ .....	...																			

a These values, except in the ST direction, have been adjusted to represent the average properties across the whole section, including the 2-½ percent nominal cladding thickness.

b Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).

c Bearing values are “dry pin” values per Section 1.4.7.1. See Table 3.1.2.1.1.

d See Table 3.2.3.0(f).



## MIL-HDBK-5H

1 December 1998

**Table 3.2.3.0(e<sub>2</sub>). Design Mechanical and Physical Properties of Clad 2024 Aluminum Alloy Sheet and Plate—Continued**

Specification . . . . .	AMS-QQ-A-250/5							
Form . . . . .	Flat sheet and plate				Coiled sheet			
Temper . . . . .	T361				T4			
Thickness, in. . . . .	0.020-0.062	0.063-0.249	0.250-0.499	0.500 <sup>a</sup>	0.010-0.062		0.063-0.128	
Basis . . . . .	S	S	S	S	A	B	A	B
Mechanical Properties:								
$F_{tu}$ , ksi:								
L . . . . .	62	65	65	64	58	59	61	62
LT . . . . .	61	64	64	63	58	59	61	62
$F_{ty}$ , ksi:								
L . . . . .	53	53	53	52	36	38	38	39
LT . . . . .	47	48	48	47	36	38	38	39
$F_{cy}$ , ksi:								
L . . . . .	44	45	45	44	36	38	38	39
LT . . . . .	50	51	51	50	36	38	38	39
$F_{su}$ , ksi . . . . .	38	40	40	39	37	37	38	39
$F_{bru}$ <sup>b</sup> , ksi:								
(e/D = 1.5) . . . . .	101	105	105	104	96	97	101	102
(e/D = 2.0) . . . . .	125	131	131	129	119	121	125	127
$F_{bry}$ <sup>b</sup> , ksi:								
(e/D = 1.5) . . . . .	78	79	79	78	63	66	66	68
(e/D = 2.0) . . . . .	92	94	94	92	76	80	80	82
$e$ , percent (S-basis):								
LT . . . . .	8	9	9	10	<sup>c</sup>	...	15	...
$E$ , 10 <sup>3</sup> ksi:								
Primary . . . . .	10.5	10.5	10.7		10.5		10.5	
Secondary . . . . .	9.5	10.0	10.2		9.5		10.0	
$E_c$ , 10 <sup>3</sup> ksi:								
Primary . . . . .	10.7	10.7	10.9		10.7		10.7	
Secondary . . . . .	9.7	10.2	10.4		9.7		10.2	
$G$ , 10 <sup>3</sup> ksi . . . . .	...							
$\mu$ . . . . .	0.33							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.100							
$C$ , $K$ , and $\alpha$ . . . . .	...							

a These values have been adjusted to represent the average properties across the whole section, including the 2-½ percent nominal cladding thickness.

b Bearing values are “dry pin” values per Section 1.4.7.1.

c See Table 3.2.3.0(f).

**Table 3.2.3.0(e<sub>3</sub>). Design Mechanical and Physical Properties of Clad 2024 Aluminum Alloy Sheet and Plate—Continued**

Specification . . . . .	AMS-QQ-A-250/5														
Form . . . . .	Flat sheet and plate														
Temper . . . . .	T42 <sup>a</sup>										T62 <sup>a</sup>			T72 <sup>a</sup>	
Thickness, in. . . . .	0.008-0.009		0.010-0.062		0.063-0.249		0.250-0.499	0.500-1.000 <sup>b</sup>	1.001-2.000 <sup>b</sup>	2.001-3.000 <sup>b</sup>	0.010-0.062	0.063-0.249	0.250-0.499	0.010-0.062	0.063-0.249
Basis . . . . .	A	B	A	B	A <sup>c</sup>	B <sup>c</sup>	S <sup>c</sup>	S <sup>c</sup>	S <sup>c,d</sup>	S	S	S <sup>c</sup>	S <sup>c</sup>	S	S
Mechanical Properties:															
$F_{tu}$ , ksi:															
L . . . . .	55	57	57	59	60	62	60	59	58	...	60	62	62	...	...
LT . . . . .	55	57	57	59	60	62	60	59	58	56	60	62	62	56	58
$F_{ty}$ , ksi:															
L . . . . .	34	35	34	35	36	38	36	36	36	...	47	49	49	...	...
LT . . . . .	34	35	34	35	36	38	36	36	36	36	47	49	49	43	45
$F_{cy}$ , ksi:															
L . . . . .	38	39	38	39	40	42	39	38	35	...	49	51	51	...	...
LT . . . . .	37	38	37	38	39	41	39	39	39	...	49	52	51	...	...
$F_{su}$ , ksi . . . . .	33	34	34	35	36	37	36	35	35	...	35	36	36	...	...
$F_{bru}$ , ksi:															
(e/D = 1.5) . . . . .	88	91	91	94	96	99	95	90	83	...	97	100	100	...	...
(e/D = 2.0) . . . . .	109	113	113	117	119	123	119	117	115	...	126	130	130	...	...
$F_{bry}$ , ksi:															
(e/D = 1.5) . . . . .	60	61	60	61	63	67	63	63	63	...	75	79	79	...	...
(e/D = 2.0) . . . . .	72	74	72	74	76	80	76	76	76	...	89	93	93	...	...
$e$ , percent (S-basis):															
LT . . . . .	10	...	<sup>e</sup>	...	15	...	12	8	<sup>e</sup>	4	5	5	5	5	5
$E$ , 10 <sup>3</sup> ksi:															
Primary . . . . .	10.5				10.5		10.7				10.5		10.7	10.5	10.5
Secondary . . . . .	9.5				10.0		10.2				10.0		10.2	9.5	10.0
$E_c$ , 10 <sup>3</sup> ksi:															
Primary . . . . .	10.7				10.7		10.9				10.7		10.9	10.7	10.7
Secondary . . . . .	9.7				10.2		10.4				10.2		10.4	9.7	10.2
$G$ , 10 <sup>3</sup> ksi . . . . .	...														
$\mu$ . . . . .	0.33														
Physical Properties:															
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.100														
$C$ , $K$ , and $\alpha$ . . . . .	...														

- a Design allowables in some cases were based upon data obtained from testing samples of material, supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user may be different than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.
- b These values have been adjusted to represent the average properties across the whole section, including 2½ percent per side nominal cladding thickness.
- c Bearing values are “dry pin” values per Section 1.4.7.1.
- d See Table 3.1.2.1.1.
- e See Table 3.2.3.0(f).

**MIL-HDBK-5H****1 December 1998****Table 3.2.3.0(e<sub>4</sub>). Design Mechanical and Physical Properties of Clad 2024 Aluminum Alloy Sheet and Plate—Continued**

Specification . . . . .	AMS-QQ-A-250/5								
Form . . . . .	Flat sheet and plate								
Temper . . . . .	T81		T851 <sup>a</sup>			T861 <sup>a</sup>			
Thickness, in. . . . .	0.010-0.062	0.063-0.249	0.250-0.499	0.500-1.000 <sup>b</sup>	0.020-0.062	0.063-0.249	0.250-0.499	0.500 <sup>b</sup>	
Basis . . . . .	S	S	A	B	S	S	S	S	S
Mechanical Properties:									
$F_{tu}$ , ksi:									
L . . . . .	64	67	65	66	63	65	70	68	67
LT . . . . .	62	65	65	66	63	64	69	68	67
$F_{ty}$ , ksi:									
L . . . . .	57	59	56	58	56	59	65	62	61
LT . . . . .	54	56	56	58	56	58	64	62	61
$F_{cy}$ , ksi:									
L . . . . .	55	57	56	58	56	59	65	62	61
LT . . . . .	55	57	57	59	56	61	67	65	64
$F_{su}$ , ksi . . . . .	38	39	37	37	36	36	39	39	38
$F_{bru}$ , ksi:									
(e/D = 1.5) . . . . .	96	100	99	100	96	99	107	105	104
(e/D = 2.0) . . . . .	122	127	127	129	123	128	138	136	134
$F_{bry}$ , ksi:									
(e/D = 1.5) . . . . .	78	83	83	86	83	84	93	90	88
(e/D = 2.0) . . . . .	90	94	98	101	98	99	109	105	104
$e$ , percent (S-basis):									
LT . . . . .	5	5	5	...	5	3	4	4	4
$E$ , 10 <sup>3</sup> ksi:									
Primary . . . . .	10.5	10.5		10.7		10.5	10.5		10.5
Secondary . . . . .	9.5	10.0		10.2		9.5	10.0		10.2
$E_c$ , 10 <sup>3</sup> ksi:									
Primary . . . . .	10.7	10.7		10.9		10.7	10.7		10.9
Secondary . . . . .	9.7	10.2		10.4		9.7	10.2		10.4
$G$ , 10 <sup>3</sup> ksi . . . . .	...								
$\mu$ . . . . .	0.33								
Physical Properties:									
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.100								
$C$ , $K$ , and $\alpha$ . . . . .	...								

a Bearing values are “dry pin” values per Section 1.4.7.1.

b These values have been adjusted to represent the average properties across the whole section, including the 2-1/2 percent nominal cladding thickness.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.2.3.0(f). Minimum Elongation Values for Clad 2024 Aluminum Alloy Sheet and Plate**

Temper .....	Elongation (LT), percent
	T3, T4, T42
Thickness, in.:	
0.010-0.020 .....	12
0.021-0.062 .....	15
1.001-1.500 .....	7
1.501-2.000 .....	6

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.2.3.0(g). Design Mechanical and Physical Properties of 2024 Aluminum Alloy Drawn Tubing**

Specification . . . . . Form . . . . . Temper . . . . .  Wall Thickness, in. . . . . Basis . . . . .	AMS 4086 and WW-T-700/3		WW-T-700/3	
	Drawn tubing			
	T3		T42 <sup>a</sup>	T81
	0.018-0.500		0.018-0.500	0.010-0.249
	A	B	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L . . . . .	64	66	62	66
LT . . . . .	...	...	...	...
$F_{ty}$ , ksi:				
L . . . . .	42	45	38	58
LT . . . . .	...	...	...	...
$F_{cy}$ , ksi:				
L . . . . .	42	45	38	...
LT . . . . .	...	...	...	...
$F_{su}$ , ksi . . . . .	39	40	38	...
$F_{bru}$ , ksi:				
(e/D = 1.5) . . . . .	96	99	93	...
(e/D = 2.0) . . . . .	122	126	118	...
$F_{bry}$ , ksi:				
(e/D = 1.5) . . . . .	59	63	53	...
(e/D = 2.0) . . . . .	67	72	61	...
$e$ , percent (S-basis):				
L . . . . .	b	...	b	b
$E$ , 10 <sup>3</sup> ksi . . . . .	10.5			
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.7			
$G$ , 10 <sup>3</sup> ksi . . . . .	4.0			
$\mu$ . . . . .	0.33			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.100			
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.2.3.0			

a Design allowables were based upon data obtained from testing samples of material supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user, however, may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.

b See Table 3.2.3.0(h).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.2.3.0(h). Minimum Elongation Values for 2024 Aluminum Alloy Drawn Tubing**

	Elongation (L), percent <sup>a</sup>
Temper .....	T3, T42
Wall Thickness, in.:	
0.018-0.024 .....	10
0.025-0.049 .....	12
0.050-0.259 .....	14
0.260-0.500 .....	16
Temper .....	T81
0.010-0.024 .....	...
0.025-0.049 .....	5
0.050-0.249 .....	6

a Full section specimen.

**MIL-HDBK-5H****1 December 1998****Table 3.2.3.0(i<sub>1</sub>). Design Mechanical and Physical Properties of 2024 Aluminum Alloy Bar and Rod; Rolled, Drawn, or Cold-Finished**

Specification .....	AMS 4120 and AMS-QQ-A-225/6							AMS-QQ-A-225/6
Form .....	Bar and rod; rolled, drawn, or cold-finished							
Temper .....	T351							T36
Thickness, in. ....	0.500-1.000	1.001-2.000	2.001-3.000	3.001-4.000	4.001-5.000 <sup>a</sup>	5.001-6.000 <sup>a</sup>	6.001-6.500 <sup>a</sup>	≤0.375
Basis .....	S	S	S	S	S	S	S	S
Mechanical Properties:								
$F_{tu}$ , ksi:								
L .....	62	62	62	62	62	62	62	69
LT .....	61 <sup>b</sup>	59 <sup>b</sup>	57 <sup>b</sup>	55 <sup>b</sup>	54 <sup>b</sup>	52 <sup>b</sup>	...	...
$F_{ty}$ , ksi:								
L .....	45	45	45	45	45	45	45	52
LT .....	36 <sup>b</sup>	36 <sup>b</sup>	36 <sup>b</sup>	36 <sup>b</sup>	36 <sup>b</sup>	36 <sup>b</sup>	...	...
$F_{cy}$ , ksi:								
L .....	34	34	34	34	34	34	...	...
LT .....	41	41	41	41	41	41	...	...
$F_{su}$ , ksi .....	37	37	37	37	37	37	...	...
$F_{bru}$ , ksi:								
(e/D = 1.5) .....	90	90	90	90	90	90	...	...
(e/D = 2.0) .....	115	115	115	115	115	115	...	...
$F_{bry}$ , ksi:								
(e/D = 1.5) .....	63	63	63	63	63	63	...	...
(e/D = 2.0) .....	74	74	74	74	74	74	...	...
$e$ , percent:								
L .....	10	10	10	10	10	10	10	10
$E$ , 10 <sup>3</sup> ksi .....	10.5							
$E_c$ , 10 <sup>3</sup> ksi .....	10.7							
$G$ , 10 <sup>3</sup> ksi .....	4.0							
$\mu$ .....	0.33							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> .....	0.100							
$C$ , $K$ , and $\alpha$ .....	See Figure 3.2.3.0							

a For square, rectangular, hexagonal, or octagonal bar, minimum thickness is 4 inches, and maximum cross-sectional area is 36 square inches.

b Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).

**Table 3.2.3.0(i<sub>2</sub>). Design Mechanical and Physical Properties of 2024 Aluminum Alloy Bar and Rod; Rolled, Drawn, or Cold-Finished—Continued**

Specification . . . . .	AMS 4120 and AMS-QQ-A-225/6										AMS-QQ-A-225/6
Form . . . . .	Bar and rod; rolled, drawn, or cold-finished										
Temper . . . . .	T4 <sup>d</sup>										T42 <sup>a</sup>
Thickness, in. . . . .	0.125- 0.499	0.500- 1.000	1.001- 2.000	2.001- 3.000	3.001- 4.000	4.001- 4.500 <sup>b</sup>	4.501- 5.000 <sup>c</sup>	5.001- 6.000 <sup>c</sup>	6.001- 6.500 <sup>c</sup>	6.501- 8.000 <sup>c</sup>	≤6.500 <sup>b</sup>
Basis . . . . .	S	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:											
$F_{tu}$ , ksi:											
L . . . . .	62	62	62	62	62	62	62	62	62	58	62
LT . . . . .	61 <sup>e</sup>	61 <sup>e</sup>	59 <sup>e</sup>	57 <sup>e</sup>	55 <sup>e</sup>	54 <sup>e</sup>	54 <sup>e</sup>	52 <sup>e</sup>	...	...	...
$F_{ty}$ , ksi:											
L . . . . .	45	42	42	42	42	42	40	40	40	38	40
LT . . . . .	45 <sup>e</sup>	42 <sup>e</sup>	41 <sup>e</sup>	40 <sup>e</sup>	39 <sup>e</sup>	39 <sup>e</sup>	37 <sup>e</sup>	36 <sup>e</sup>	...	...	...
$F_{cy}$ , ksi:											
L . . . . .	36	33	33	33	33	33	32	32	...	...	...
LT . . . . .	...	...	...	...	...	...	...	...	...	...	...
$F_{su}$ , ksi . . . . .	37	37	37	37	37	37	37	37	37	...	...
$F_{bru}$ , ksi:											
(e/D = 1.5) . . . . .	93	93	93	93	93	93	93	93	...	...	...
(e/D = 2.0) . . . . .	118	118	118	118	118	118	118	118	...	...	...
$F_{bry}$ , ksi:											
(e/D = 1.5) . . . . .	63	59	59	59	59	59	56	56	...	...	...
(e/D = 2.0) . . . . .	72	67	67	67	67	67	64	64	...	...	...
$e$ , percent:											
L . . . . .	10	10	10	10	10	10	10	10	10	10	10
$E$ , 10 <sup>3</sup> ksi . . . . .	10.5										
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.7										
$G$ , 10 <sup>3</sup> ksi . . . . .	4.0										
$\mu$ . . . . .	0.33										
Physical Properties:											
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.100										
$C$ and $\alpha$ . . . . .	See Figure 3.2.3.0										
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] . . . . .	71 (at 77 °F) for T4X (See Figure 3.2.3.0)										

a These properties apply when samples of material supplied in the O or F temper are heat treated to demonstrate response to heat treatment. Properties obtained by the user, however, may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.

b For square, rectangular, hexagonal, or octagonal bar, maximum thickness is 4 inches, and maximum cross-sectional area is 36 square inches.

c Applies to rod only.

d The T4 temper is obsolete and should not be specified for new designs.

e Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).



**MIL-HDBK-5H****1 December 1998****Table 3.2.3.0(i<sub>3</sub>). Design Mechanical and Physical Properties of 2024 Aluminum Alloy Bar and Rod; Rolled, Drawn, or Cold-Finished—Continued**

Specification . . . . .	QQ-A-225/6		
Form . . . . .	Bar and rod; rolled, drawn, or cold finished		
Temper . . . . .	T6 <sup>a</sup>	T62 <sup>b</sup>	T851
Thickness, <sup>c</sup> in. . . . .	≤6.500	≤6.500	0.500-6.500
Basis . . . . .	S	S	S
Mechanical Properties:			
$F_u$ , ksi:			
L . . . . .	62	60	66
LT . . . . .	...	...	...
$F_y$ , ksi:			
L . . . . .	50	46	58
LT . . . . .	...	...	...
$F_{cy}$ , ksi:			
L . . . . .	...	...	...
LT . . . . .	...	...	...
$F_{su}$ , ksi . . . . .	...	...	...
$F_{bru}$ , ksi:			
(e/D = 1.5) . . . . .	...	...	...
(e/D = 2.0) . . . . .	...	...	...
$F_{bry}$ , ksi:			
(e/D = 1.5) . . . . .	...	...	...
(e/D = 2.0) . . . . .	...	...	...
$e$ , percent:			
L . . . . .	5	5	5
$E$ , 10 <sup>3</sup> ksi . . . . .	10.5		
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.7		
$G$ , 10 <sup>3</sup> ksi . . . . .	4.0		
$\mu$ . . . . .	0.33		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.100		
$C$ and $\alpha$ . . . . .	See Figure 3.2.3.0		
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] . . . . .	87 (at 77 °F) for T6X and T8XX		

a The T6 temper is obsolete and should not be specified for new designs.

b These properties apply when samples of material supplied in the O or F temper are heat treated to demonstrate response to heat treatment. Properties obtained by the user, however, may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.

c For square, rectangular, hexagonal, or octagonal bar, maximum thickness is 4 inches, and maximum cross-sectional area is 36 square inches.

**Table 3.2.3.0(j<sub>1</sub>). Design Mechanical and Physical Properties of 2024 Aluminum Alloy Extrusion**

Specification . . . . .	AMS 4152, AMS 4164, AMS 4165, and AMS-QQ-A-200/3														AMS-QQ-A-200/3		
Form . . . . .	Extruded bar, rod, and shapes																
Temper . . . . .	T3, T3510, and T3511														T81, T8510, and T8511		
Thickness, <sup>b</sup> in. . . . .	≤0.249		0.250-0.499		0.500-0.749		0.750-1.499		1.500-2.999		3.000-4.499		1.500-2.999	3.000-4.499	0.050-0.249	0.250-1.499	1.500-4.500
Cross-Section Area, in. <sup>2</sup>	≤20								≤25				>25, ≤32		≤20		≤32
Basis . . . . .	A	B	A	B	A	B	A	B	A	B	A	B	S	S	S	S	S
Mechanical Properties:																	
<i>F<sub>tu</sub><sup>a</sup></i> , ksi:																	
L . . . . .	57	61	60	62	60	62	65	70	70	74	70	74	68	68	64	66	66
LT . . . . .	54	58	56	57	54	56	56	60	55	58	54	57	53	52	64	64	61
<i>F<sub>ty</sub><sup>a</sup></i> , ksi:																	
L . . . . .	42	47	44	47	44	47	46	54	52	54	52	54	48	48	56	58	58
LT . . . . .	37	41	38	40	37	39	37	43	39	41	39	41	36	36	55	57	57
<i>F<sub>cys</sub><sup>a</sup></i> , ksi:																	
L . . . . .	34	38	37	39	38	40	41	48	49	50	49	51	45	45	57	59	59
LT . . . . .	41	45	41	44	40	43	40	47	42	44	41	43	39	38	57	59	59
<i>F<sub>su</sub><sup>a</sup></i> , ksi . . . . .	29	31	31	32	30	31	33	35	34	36	33	35	33	32	35	36	36
<i>F<sub>bru</sub><sup>a</sup></i> , ksi:																	
(e/D = 1.5) . . . .	84	90	78	81	78	80	84	90	88	93	86	91	86	84	94	96	92
(e/D = 2.0) . . . .	108	114	98	101	97	101	105	113	111	118	109	115	108	106	123	123	117
<i>F<sub>bry</sub><sup>a</sup></i> , ksi:																	
(e/D = 1.5) . . . .	61	68	55	59	55	59	57	67	63	66	62	65	59	57	79	82	82
(e/D = 2.0) . . . .	71	79	67	71	67	71	69	81	77	80	75	78	71	69	93	96	96
<i>e</i> , percent (S-basis):																	
LT . . . . .	12	...	12	...	12	...	10	...	10	...	10	...	8	8	4	5	5
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	10.8																
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	11.0																
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	4.1																
<i>μ</i> . . . . .	0.33																
Physical Properties:																	
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.100																
<i>C</i> , <i>K</i> , and <i>α</i> . . . .	See Figure 3.2.3.0																

a Bearing values are “dry pin” values per Section 1.4.7.1.

b The mechanical properties are to be based upon the thickness at the time of quench.

**Table 3.2.3.0(j<sub>2</sub>). Design Mechanical and Physical Properties of 2024 Aluminum Alloy Extrusion—Continued**


Specification . . . . .	AMS-QQ-A-200/3									
Form . . . . .	Extruded bar, rod, and shapes									
Temper . . . . .	T42 <sup>a</sup>									
Cross-Sectional Area, in. <sup>2</sup>	≤ 25									
Thickness or Diameter, <sup>c</sup> in.	≤ 0.249	0.250- 0.499	0.500- 0.749	0.750- 0.999	1.000- 1.249	1.250- 1.499	1.500- 1.749	1.750- 1.999	2.000- 2.249	2.250- 2.499
Basis . . . . .	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:										
$F_{tu}$ , ksi:										
L . . . . .	57	57	57	57	57	57	57	57	57	57
LT . . . . .	55	54	52	51	49	47	45	43	41	39
$F_{ty}$ , ksi:										
L . . . . .	38	38	38	38	38	38	38	38	38	38
LT . . . . .	36	35	34	33	32	31	30	29	28	27
$F_{cy}$ , ksi:										
L . . . . .	38	38	38	38	38	38	38	38	38	38
LT . . . . .	39	38	37	36	35	34	33	31	30	29
$F_{su}$ , <sup>b</sup> ksi . . . . .	29	29	29	29	29	29	28	27	26	24
$F_{bru}$ , <sup>b</sup> ksi:										
(e/D = 1.5) . . . . .	81	80	79	77	75	74	71	69	67	64
(e/D = 2.0) . . . . .	99	98	97	95	93	91	89	86	83	81
$F_{bry}$ , <sup>b</sup> ksi:										
(e/D = 1.5) . . . . .	56	55	53	51	49	47	44	41	39	36
(e/D = 2.0) . . . . .	69	67	65	63	61	59	56	53	50	47
$e$ , percent:										
L . . . . .	12	12	12	10	10	10	10	10	10	10
$E$ , 10 <sup>3</sup> ksi . . . . .	10.8									
$E_c$ , 10 <sup>3</sup> ksi . . . . .	11.0									
$G$ , 10 <sup>3</sup> ksi . . . . .	4.1									
$\mu$ . . . . .	0.33									
Physical Properties:										
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.100									
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.2.3.0									

a Design allowables were based upon data obtained from testing samples of material supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user, however, may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.

b Bearing values are “dry pin” values per Section 1.4.7.1.


c The mechanical properties are to be based upon the thickness at the time of quench.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2024-T3, T351, and 2024-T4 aluminum alloy (all products except extrusions).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2024-T3, T351, and 2024-T4 aluminum alloy (all products except extrusions).**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.1(c). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2024-T3, T3510, T3511, and T42 aluminum alloy extrusion.**




**Figure 3.2.3.1.1(d). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2024-T3, T3510, T3511, and T42 aluminum alloy extrusion.**

**MIL-HDBK-5H****1 December 1998**


**Figure 3.2.3.1.1(e). Effect of exposure at elevated temperatures on the room-temperature tensile ultimate strength ( $F_{tu}$ ) of 2024-T3, T351, T3510, T3511, and T42 aluminum alloy (all products except thick extrusions).**



**Figure 3.2.3.1.1(f). Effect of exposure at elevated temperatures on the room-temperature tensile yield strength ( $F_{ty}$ ) of 2024-T3, T351, T3510, T3511, T4, and T42 aluminum alloy (all products except thick extrusions).**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.3.1.2(a). Effect of temperature on the compressive yield strength ( $F_{cy}$ ) of flat clad 2024-T3, coiled clad 2024-T4 aluminum alloy sheet, and clad 2024-T351 aluminum alloy plate.**




**Figure 3.2.3.1.2(b). Effect of temperature on the shear ultimate strength ( $F_{su}$ ) of flat clad 2024-T3, coiled clad 2024-T4 aluminum alloy sheet, and clad 2024-T351 aluminum alloy plate.**




**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.3.1.3(a). Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) of flat clad 2024-T3, coiled clad 2024-T4 aluminum alloy sheet, and clad 2024-T351 aluminum alloy plate.**




**Figure 3.2.3.1.3(b). Effect of temperature on the bearing yield strength ( $F_{bry}$ ) of flat clad 2024-T3, coiled clad 2024-T4 aluminum alloy sheet, and clad 2024-T351 aluminum alloy plate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.4. Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of 2024 aluminum alloy.**




**Figure 3.2.3.1.5(a). Effect of temperature on the elongation of 2024-T3, T351, T3510, T3511, T4, and T42 aluminum alloy (all products except thick extrusions).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.5(b). Effect of exposure at elevated temperature on the elongation (e) of 2024-T3, T351, T3510, T3511, T4, and T42 aluminum alloy (all products except thick extrusions).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2024-T3 aluminum alloy sheet at room temperature.**




**Figure 3.2.3.1.6(b). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2024-T3 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(c). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T3 aluminum alloy sheet at 212°F.**




**Figure 3.2.3.1.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T3 aluminum alloy sheet at 300°F.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(e). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T3 aluminum alloy sheet at 400°F.**




**Figure 3.2.3.1.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T3 aluminum alloy sheet at 500°F.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(g). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T3 aluminum alloy sheet at 600°F.**




**Figure 3.2.3.1.6(h). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T3 aluminum alloy sheet at 700°F.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(i). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for clad 2024-T351 aluminum alloy plate at room temperature.**




**Figure 3.2.3.1.6(j). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for clad 2024-T42 aluminum alloy plate at room temperature.**



**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(k) Typical tension and compression stress-strain and compression tangent modulus curves for 2024-T42 aluminum alloy plate at room temperature. Note, the data to generate these curves may have been from clad product, however, they are shown here without secondary modulus since it could not be positively confirmed the product was clad.**




**Figure 3.2.3.1.6(l). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2024-T4 aluminum alloy rolled bar, rod, and shapes at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(m). Typical tensile stress-strain curves for 2024-T351X aluminum alloy extrusion at room temperature.**




**Figure 3.2.3.1.6(n). Typical compressive stress-strain and compressive tangent-modulus curves for 2024-T351X aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(o). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2024-T3 aluminum alloy extrusion at room temperature.**




**Figure 3.2.3.1.6(p). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2024-T3 aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(q). Typical tensile stress-strain curves for 2024-T42 aluminum alloy extrusion at room temperature.**




**Figure 3.2.3.1.6(r). Typical compressive stress-strain and compressive tangent-modulus curves for 2024-T42 aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(s). Typical tensile stress-strain curves for clad 2024-T42 aluminum alloy sheet at room temperature.**




**Figure 3.2.3.1.6(t). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T42 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(u). Typical tensile stress-strain curves (full range) for clad 2024-T3 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.3.1.6(v). Typical tensile stress-strain curve (full range) for 2024-T351 aluminum alloy rolled rod at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.3.1.6(w). Typical tensile stress-strain curve (full range) for 2024-T351X aluminum alloy extrusion at room temperature.**




**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(x). Typical stress-strain curve (full range) for 2024-T3 aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.1.6(y). Typical tensile stress-strain curves (full range) for 2024-T3 aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.3.1.6(z). Typical tensile stress-strain curves (full range) for 2024-T42 aluminum alloy extrusion at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.3.1.6(aa). Typical stress-strain curves (full range) for clad 2024-T42 aluminum alloy sheet at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.3.1.8(a). Best-fit S/N curves for unnotched 2024-T4 aluminum alloy, various wrought products, longitudinal direction.**

Correlative Information for Figure 3.2.3.1.8(a)

Product Form: Rolled bar, 3/4 to 1/8 inch diameter  
 Drawn rod, 3/4-inch diameter  
 Extruded rod, 1-1/4-inch diameter  
 Extruded bar, 1-1/4 x 4-inch

Test Parameters:  
 Loading - Axial  
 Frequency - 1800 to 3600 cpm  
 Temperature - RT  
 Environment - Air

Properties:

TUS, ksi	TYS, ksi	Temp., °F
69	45	RT (rolled)
71	44	RT (drawn)
85	65	RT (extruded)

No. of Heats/Lots: Not specified

Equivalent Stress Equation:  
 $\log N_f = 20.83 - 9.09 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.52}$   
 Standard Error of Estimate = 0.566  
 Standard Deviation in Life = 1.324  
 $R^2 = 82\%$

Specimen Details: Unnotched  
 0.160 to 0.400-inch diameter

Sample Size = 134


Surface Condition: Longitudinally polished

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

References: 3.2.1.1.8(a) through (c) and 3.2.3.1.8(i)

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.3.1.8(b). Best-fit S/N curves for notched,  $K_t = 1.6$ , 2024-T4 aluminum alloy bar, longitudinal direction.**

## Correlative Information for Figure 3.2.3.1.8(b)

Product Form: Rolled bar, 1-1/8-inch diameter

Test Parameters:

Loading - Axial

Frequency - 1800 to 3600 cpm

Temperature - RT

Environment - Air

Properties: TUS, ksi TYS, ksi Temp., °F

73

49

RT

No. of Heats/Lots: Not specified

Specimen Details: Semicircular  
V-Groove,  $K_t = 1.6$   
0.450-inch gross diameter  
0.400-inch net diameter  
0.100-inch root radius, r  
60° flank angle,  $\omega$

Equivalent Stress Equation:

$$\log N_f = 12.25 - 5.16 \log (S_{eq} - 18.7)$$

$$S_{eq} = S_{max} (1-R)^{0.57}$$

Standard Error of Estimate = 0.414

Standard Deviation in Life = 0.989

$R^2 = 82\%$

Surface Condition: As machined


Sample Size = 38

Reference: 3.2.1.1.8(a)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.3.1.8(c). Best-fit S/N curves for notched,  $K_t = 2.4$ , 2024-T4 aluminum alloy bar, longitudinal direction.**

### Correlative Information for Figure 3.2.3.1.8(c)

Product Form: Rolled bar, 1-1/8-inch diameter

Test Parameters:

Loading - Axial

Frequency - 1800 to 3600 cpm

Temperature - RT

Environment - Air

Properties:      TUS, ksi    TYS, ksi    Temp., °F

73

49

RT

No. of Heats/Lots: Not specified

Specimen Details: Circumferential  
V-Groove,  $K_t = 2.4$   
0.500-inch gross diameter  
0.400-inch net diameter  
0.032-inch root radius, r  
60° flank angle,  $\omega$

Equivalent Stress Equation:

$$\log N_f = 14.33 - 6.35 \log (S_{eq} - 3.2)$$

$$S_{eq} = S_{max} (1 - R)^{0.48}$$

Standard Error of Estimate = 0.310

Standard Deviation in Life = 1.084

$R^2 = 92\%$

Surface Condition: As machined


Sample Size = 33

Reference: 3.2.1.1.8(b)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.3.1.8(d). Best-fit S/N curves for notched,  $K_t = 3.4$ , 2024-T4 aluminum alloy, various wrought products, longitudinal direction.**

## Correlative Information for Figure 3.2.3.1.8(d)

Product Form: Rolled bar, 1-1/8-inch diameter  
Extruded bar, 1-1/4-inch diameter

Properties: TUS, ksi TYS, ksi Temp., °F

74.2	—	RT
		(rolled)
84.1	—	RT
		(extruded)

Specimen Details: Circumferential  
V-Groove,  $K_t = 3.4$   
0.450-inch gross diameter  
0.400-inch net diameter  
0.010-inch root radius, r  
60° flank angle,  $\omega$

Surface Condition: As machined

References: 3.2.1.1.8(b) and (c)

Test Parameters:

Loading - Axial  
Frequency - 1800 to 3600 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 8.14 - 2.76 \log (S_{eq} - 11.6)$   
 $S_{eq} = S_{max} (1-R)^{0.52}$   
Standard Error of Estimate = 0.292  
Standard Deviation in Life = 1.011  
 $R^2 = 92\%$


Sample Size = 51

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 3.2.3.1.8(e). Best-fit S/N curves for unnotched, 2024-T3 aluminum alloy sheet, longitudinal direction.**

Correlative Information for Figure 3.2.3.1.8(e)

Product Form: Bare sheet, 0.090-inch

Test Parameters:

Loading - Axial

Properties: TUS, ksi TYS, ksi Temp., °F

Frequency - 1100 to 1800 cpm

72, 73 52, 54 RT

No. of Heats/Lots: Not specified

Specimen Details: Unnotched  
0.8 to 1.0-inch width

Equivalent Stress Equation:

$$\log N_f = 11.1 - 3.97 \log (S_{eq} - 15.8)$$

$$S_{eq} = S_{max} (1-R)^{0.56}$$

Standard Error of Estimate = 0.38

Standard Deviation in Life = 0.90

$R^2 = 82\%$

Surface Condition: Electropolished


References: 3.2.3.1.8(a) and (f)

Sample Size = 107

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.3.1.8(f). Best-fit S/N curves for notched,  $K_t = 1.5$ , 2024-T3 aluminum alloy sheet, longitudinal direction.**

## Correlative Information for Figure 3.2.3.1.8(f)

Product Form: Bare sheet, 0.090-inch

Test Parameters:

Loading - Axial

Frequency - 1100 to 1500 cpm

Temperature - RT

Environment - Air

Properties: TUS, ksi TYS, ksi Temp., °F

73	54	RT
		(unnotched)
76	—	RT
		(notched $K_t = 1.5$ )

No. of Heats/Lots: Not specified

Specimen Details: Edge notched,  $K_t = 1.5$   
3.00-inches gross width  
1.500-inches net width  
0.760-inch notch radius  
0° flank angle

Equivalent Stress Equation:

$$\log N_f = 7.5 - 2.13 \log (S_{eq} - 23.7)$$

$$S_{eq} = S_{max} (1 - R)^{0.66}$$

Standard Error of Estimate = 0.30

Standard Deviation in Life = 0.95

$R^2 = 90\%$

Surface Condition: Electropolished


Sample Size = 26

Reference: 3.2.3.1.8(d)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.3.1.8(g). Best-fit S/N curves for notched,  $K_t = 2.0$ , 2024-T3 aluminum alloy sheet, longitudinal direction.**

## Correlative Information for Figure 3.2.3.1.8(g)

Product Form: Bare sheet, 0.090-inch

Properties:

TUS, ksi	TYS, ksi	Temp., °F
73	54	RT (unnotched)
73	—	RT (notched $K_t = 2.0$ )

Specimen Details: Notched,  $K_t = 2.0$

Notch Type	Gross Width	Net Width	Notch Radius
Center	4.50	1.50	1.50
Edge	2.25	1.50	0.3175
Fillet	2.25	1.50	0.1736

Surface Condition: Electropolished, machined and burrs removed with fine crocus cloth

References: 3.2.3.1.8(b) and (f)

Test Parameters:

Loading - Axial  
Frequency - 1100 to 1800 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:


$\log N_f = 9.2 - 3.33 \log (S_{eq} - 12.3)$   
 $S_{eq} = S_{max} (1 - R)^{0.68}$   
 Standard Error of Estimate = 0.27  
 Standard Deviation in Life = 0.89  
 $R^2 = 91\%$

Sample Size = 113

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.3.1.8(h). Best-fit S/N curves for notched,  $K_t = 4.0$  of 2024-T3 aluminum alloy sheet, longitudinal direction.**

## Correlative Information for Figure 3.2.3.1.8(h)

Product Form: Bare sheet, 0.090-inch

Properties:    TUS, ksi    TYS, ksi    Temp., °F

73	54	RT
		(unnotched)
67	—	RT
		(notched $K_t = 2.0$ )

Specimen Details: Notched,  $K_t = 2.0$

<u>Notch Type</u>	<u>Gross Width</u>	<u>Net Width</u>	<u>Notch Radius</u>
Center	2.25	1.50	0.057
Edge	4.10	1.50	0.070
Fillet	2.25	1.50	0.0195

Surface Condition: Electropolished, machined, and burrs removed with fine crocus cloth

References: 3.2.3.1.8(b), (e), (f), (g), and (h)

Test Parameters:

Loading - Axial  
Frequency - 1100 to 1800 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:


$\log N_f = 8.3 - 3.30 \log (S_{eq} - 8.5)$   
 $S_{eq} = S_{max} (1 - R)^{0.66}$   
Standard Error of Estimate = 0.39  
Standard Deviation in Life = 1.24  
 $R^2 = 90\%$

Sample Size = 126

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.3.1.8(i). Best-fit S/N curves for notched,  $K_t = 5.0$ , 2024-T3 aluminum alloy sheet, longitudinal direction.**

Correlative Information for Figure 3.2.3.1.8(i)

Product Form: Bare sheet, 0.090-inch

Properties:

TUS, ksi	TYs, ksi	Temp., °F
73	54	RT (unnotched)
62	—	RT (notched $K_t = 5.0$ )

Specimen Details: Edge notched,  $K_t = 5.0$   
 2.25-inch gross width  
 1.500-inch net width  
 0.03125-inch notch radius  
 0° flank angle

Surface Condition: Electropolished

Reference: 3.2.3.1.8(c)

Test Parameters:

Loading - Axial  
 Frequency - 1100 to 1800 cpm  
 Temperature - RT  
 Environment - Air


No. of Heats/Lots: Not specified

Equivalent Stress Equation:


$\log N_f = 8.9 - 3.73 \log (S_{eq} - 3.9)$   
 $S_{eq} = S_{max} (1 - R)^{0.56}$   
 Standard Error of Estimate = 0.39  
 Standard Deviation in Life = 1.24  
 $R^2 = 90\%$

Sample Size = 35

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]


**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.3.3.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2024-T62 aluminum alloy (all products).**




**Figure 3.2.3.3.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2024-T62 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.3.1(c). Effect of exposure at elevated temperatures on the room-temperature tensile ultimate strength ( $F_{tu}$ ) of 2024-T62 aluminum alloy (all products).**




**Figure 3.2.3.3.1(d). Effect of exposure at elevated temperatures on the room-temperature tensile yield strength ( $F_{ty}$ ) of 2024-T62 aluminum alloy (all products).**




**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.3.3.5(a). Effect of temperature on the elongation of 2024-T62 aluminum alloy (all products).**




**Figure 3.2.3.3.5(b). Effect of exposure at elevated temperatures on the elongation of 2024-T62 aluminum alloy (all products).**



**MIL-HDBK-5H****1 December 1998**


**Figure 3.2.3.3.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2024-T62 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.3.6(b) Typical tension and compression stress-strain and compression tangent modulus curves for 2024-T62 aluminum alloy plate at room temperature. Note, the data to generate these curves may have been from clad product, however, they are shown here without secondary modulus since it could not be positively confirmed the product was clad.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.3.6(c). Typical tensile stress-strain curves for clad 2024-T62 aluminum alloy sheet at room temperature.**




**Figure 3.2.3.3.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T62 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.3.6(e). Typical stress-strain curves (full range) for clad 2024-T62 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.4.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2024-T81, T851, T8510, and T8511 aluminum alloy (all products).**




**Figure 3.2.3.4.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2024-T81, T851, T8510, and T8511 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.3.4.1(c). Effect of exposure at elevated temperatures on room-temperature tensile ultimate strength ( $F_{tu}$ ) of 2024-T81 aluminum alloy sheet.**



**Figure 3.2.3.4.1(d). Effect of exposure at elevated temperatures on the room temperature tensile yield strength ( $F_{ty}$ ) of 2024-T81 aluminum alloy sheet.**

## MIL-HDBK-5H

1 December 1998




Figure 3.2.3.4.1(e). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2024-T81 aluminum alloy clad sheet. Note: Instructions for use of these curves are presented in Section 3.7.4.1.






Figure 3.2.3.4.1(f). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2024-T81 aluminum alloy clad sheet. Note: Instructions for use of these curves are presented in Section 3.7.4.1.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.4.2(a). Effect of temperature on the compressive yield strength ( $F_{cy}$ ) of 2024-T81, T851, T8510, and T8511 aluminum alloy (all products).**




**Figure 3.2.3.4.2(b). Effect of temperature on the shear ultimate strength ( $F_{su}$ ) of 2024-T81, T851, T8510, and T8511 aluminum alloy (all products).**



**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.4.3(a). Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) of 2024-T81, T851, T8510, and T8511 aluminum alloy (all products).**




**Figure 3.2.3.4.3(b). Effect of temperature on the bearing yield strength ( $F_{bry}$ ) of 2024-T81, T851, T8510, and T8511 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.4.5(a). Effect of temperature on the elongation of 2024-T81, T851, T8510, and T8511 aluminum alloy (all products).**




**Figure 3.2.3.4.5(b). Effect of exposure at elevated temperatures on the elongation of 2024-T81, T851, T8510, and T8511 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.4.6(a). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T81 aluminum alloy sheet at room temperature.**




**Figure 3.2.3.4.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T81 aluminum alloy sheet at 200°F.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.4.6(c). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T81 aluminum alloy sheet at 300°F.**




**Figure 3.2.3.4.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T81 aluminum alloy sheet at 400°F.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.3.4.6(e). Typical tensile stress-strain curves for 2024-T851 aluminum alloy plate at room temperature.**




**Figure 3.2.3.4.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for 2024-T851 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H****1 December 1998**


**Figure 3.2.3.4.6(g). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2024-T851X aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.3.4.6(h). Typical tensile stress-strain curves (full range) for 2024-T81 aluminum alloy sheet at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.3.4.6(i). Typical tensile stress-strain curves (full range) for clad 2024-T81 aluminum alloy sheet at room temperature.**




**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.4.6(i). Typical tensile stress-strain curves (full range) for 2024-T851 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.5.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2024-T861 (T86) aluminum alloy sheet.**




**Figure 3.2.3.5.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2024-T861 (T86) aluminum alloy sheet.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.5.1(c). Effect of exposure at elevated temperatures on the room-temperature tensile ultimate strength ( $F_{tu}$ ) of 2024-T861 (T86) aluminum alloy sheet.**




**Figure 3.2.3.5.1(d). Effect of exposure at elevated temperatures on the room-temperature tensile yield strength ( $F_{ty}$ ) of 2024-T861 (T86) aluminum alloy sheet.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.5.2(a). Effect of temperature on the compressive yield strength ( $F_{cy}$ ) of 2024-T861 (T86) aluminum alloy sheet.**




**Figure 3.2.3.5.2(b). Effect of temperature on the shear ultimate strength ( $F_{su}$ ) of 2024-T861 (T86) aluminum alloy sheet.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.3.5.3(a). Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ,  $e/D = 1.5$ ) of 2024-T861 (T86) aluminum alloy sheet.**



**Figure 3.2.3.5.3(b). Effect of temperature on the bearing yield strength ( $F_{bry}$ ,  $e/D = 1.5$ ) of 2024-T861 (T86) aluminum alloy sheet.**

**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.3.5.3(c). Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ,  $e/D = 2.0$ ) and the bearing yield strength ( $F_{bry}$ ,  $e/D = 2.0$ ) of 2024-T861 (T86) aluminum alloy sheet.**

MIL-HDBK-5H

1 December 1998




Figure 3.2.3.5.5(a). Effect of temperature on the elongation (e) of 2024-T861 (T86) aluminum alloy sheet.






Figure 3.2.3.5.5(b). Effect of exposure at elevated temperatures on the elongation (e) of 2024-T861 (T86) aluminum alloy sheet.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.3.5.6(a). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T861 aluminum alloy sheet at room temperature.**




**Figure 3.2.3.5.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T861 aluminum alloy sheet at 200°F.**



**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.3.5.6(c). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T861 aluminum alloy sheet at 300°F.**



**Figure 3.2.3.5.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for clad 2024-T861 aluminum alloy sheet at 400°F.**

MIL-HDBK-5H  
1 December 1998




Figure 3.2.3.5.10(a). Residual strength behavior of 0.063-inch-thick 2024-T861 aluminum alloy sheet at room temperature. Crack orientation is T-L [Reference 3.1.2.1.6(d)].




Figure 3.2.3.5.10(b). Residual strength behavior of 0.063-inch-thick 2024-T861 aluminum alloy sheet at room temperature. Crack orientation is L-T [Reference 3.1.2.1.6(d)].

**MIL-HDBK-5H****1 December 1998****3.2.4 2025 ALLOY**

**3.2.4.0 Comments and Properties** — 2025 is a heat-treatable Al-Cu forging alloy for which applications have been limited primarily to propellers. Refer to Section 3.1.2.3 for comments regarding the resistance of the alloy to stress-corrosion cracking, and to Section 3.1.2.4 for comments regarding the weldability of the alloy.

A material specification for 2025 aluminum alloy is presented in Table 3.2.4.0(a). Room-temperature mechanical and physical properties are shown in Table 3.2.4.0(b). The effect of temperature on thermal expansion is shown in Figure 3.2.4.0.

**Table 3.2.4.0(a). Material Specification for 2025 Aluminum Alloy**


Specification	Form
AMS 4130	Die forging

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.2.4.0(b). Design Mechanical and Physical Properties of 2025 Aluminum Alloy Die Forging**

Specification .....	AMS 4130
Form .....	Die forging
Temper .....	T6
Thickness, in. ....	≤ 4.000
Basis .....	S
Mechanical Properties:	
$F_{tu}$ , ksi:	
L .....	55
T <sup>a</sup> .....	52
$F_{ty}$ , ksi:	
L .....	33
T <sup>a</sup> .....	32
$F_{cy}$ , ksi:	
L .....	...
T <sup>a</sup> .....	...
$F_{su}$ , ksi .....	...
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$e$ , percent:	
L .....	11
T <sup>a</sup> .....	8
$E$ , 10 <sup>3</sup> ksi .....	10.3
$E_c$ , 10 <sup>3</sup> ksi .....	10.5
$G$ , 10 <sup>3</sup> ksi .....	3.9
$\mu$ .....	0.33
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.101
$C$ , Btu/(lb)(°F) .....	0.23 (at 212 °F)
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] ..	90 (at 77 °F)
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	See Figure 3.2.4.0

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.4.0. Effect of temperature on the thermal expansion of 2025 aluminum alloy.**

**MIL-HDBK-5H****1 December 1998****3.2.5 2090 ALLOY**

**3.2.5.0 Comments and Properties** — 2090 is an Al-Cu-Li alloy developed for applications requiring the high strength of 7075-T6 but with 8 percent lower density and 10 percent higher elastic modulus than 7075-T6. Sheet is available in the T83 temper. 2090 sheet has strength properties nearly equivalent to 7075-T6 sheet with improved exfoliation resistance. Refer to Section 3.1.3.4 for information on weldability of the alloy.

A material specification for 2090 aluminum alloy is shown in Table 3.2.5.0(a). Room-temperature mechanical and physical properties are shown in Table 3.2.5.0(b).

**Table 3.2.5.0(a). Material Specification for 2090 Aluminum Alloy**

Specification	Form
AMS 4251	Sheet

The temper index is as follows:

<u>Section</u>	<u>Temper</u>
3.2.5.1	T83

**3.2.5.1 T83 Temper** — Stress-strain and tangent-modulus curves are represented in Figures 3.2.5.1.6(a) and (b).

## MIL-HDBK-5H


1 December 1998

**Table 3.2.5.0(b). Design Mechanical and Physical Properties of 2090-T83 Aluminum Alloy Sheet**


Specification . . . . .	AMS 4251	
	Sheet	
	T83	
	0.040-0.125	0.126-0.249
Basis . . . . .	S	S
<b>Mechanical Properties:</b>		
$F_{tu}$ , ksi:		
L . . . . .	77	75
45° . . . . .	64	65
LT . . . . .	73	73
$F_{ty}$ , ksi:		
L . . . . .	70	70
45° . . . . .	56	57
LT . . . . .	66	66
$F_{cy}$ , ksi:		
L . . . . .	67	63
45° . . . . .	58	60
LT . . . . .	71	71
$F_{su}$ , ksi . . . . .	37	37
$F_{bru}^a$ , ksi:		
(e/D = 1.5) . . . . .	100	100
(e/D = 2.0) . . . . .	126	126
$F_{bry}^a$ , ksi:		
(e/D = 1.5) . . . . .	84	88
(e/D = 2.0) . . . . .	98	104
$e$ , percent:		
L . . . . .	3	4
LT . . . . .	5	5
$E$ , 10 <sup>3</sup> ksi:		
L & LT . . . . .	11.5	
45° . . . . .	11.0	
$E_c$ , 10 <sup>3</sup> ksi:		
L & LT . . . . .	11.8	
45° . . . . .	11.4	
$G$ , 10 <sup>3</sup> ksi . . . . .	4.3	
$\mu$ . . . . .	0.34	
<b>Physical Properties:</b>		
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.094	
$C$ , $K$ , and $\alpha$ . . . . .	...	

a Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.5.1.6(a). Typical tensile stress-strain curves for 2090-T83 aluminum alloy sheet at room temperature.**



**Figure 3.2.5.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 2090-T83 aluminum alloy sheet at room temperature.**



**MIL-HDBK-5H****1 December 1998****3.2.6 2124 ALLOY**

**3.2.6.0 Comments and Properties** — 2124 is an Al-Cu alloy available in the form of plate in thicknesses of 1 through 6 inches. This alloy is a high purity version of alloy 2024. The higher purity in conjunction with special production processing provides higher elongation in the short-transverse direction and improved fracture toughness over that exhibited by conventionally produced 2024 alloy. The alloy is currently only produced in the T851 temper. The alloy like 2024 has excellent properties and creep resistance at elevated temperatures. The alloy in the T851 temper has good resistance to stress corrosion. Refer to Section 3.1.2.3.1 for information regarding resistance of the alloy to stress-corrosion cracking. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy. The physical properties are essentially the same as those for 2024-T851 plate.

Applicable material specification for 2124-T851 plate is presented in Table 3.2.6.0(a). Room-temperature mechanical properties are shown in Table 3.2.6.0(b).

**Table 3.2.6.0(a). Material Specification for 2124 Aluminum Alloy**

Specification	Form
AMS 4101	Plate
AMS-QQ-A-250/29	Plate

The temper index for 2124 is as follows:

<u>Section</u>	<u>Temper</u>
3.2.6.1	T851


**3.2.6.1 T851 Temper** — Elevated temperature data are presented in Figures 3.2.6.1.1(a) and (b). Typical tensile stress-strain, compressive stress-strain, and compressive tangent-modulus curves are presented in Figures 3.2.6.1.6(a) and (b). Fatigue crack-propagation data for plate are presented in Figures 3.2.6.1.9(a) through (e).

**MIL-HDBK-5H****1 December 1998****Table 3.2.6.0(b). Design Mechanical and Physical Properties of 2124 Aluminum Alloy Plate**


Specification .....	AMS 4101 and AMS-QQ-A-250/29										
Form .....	Plate										
Temper .....	T851										
Thickness, in. ....	1.000- 1.500	1.501- 2.000	2.001- 3.000	3.001- 4.000	4.001- 5.000	5.001- 6.000					
Basis .....	S	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:											
$F_{tu}$ , ksi:											
L .....	66	66	68	65	68	65	67	64	66	63	65
LT .....	66	66	68	65	68	65	67	64	66	63	65
ST .....	64 <sup>b</sup>	64	66	63	64	62	63	61	62	58	59
$F_{ty}$ , ksi:											
L .....	57	57	61	57	61	56	60	55	58	54	56
LT .....	57	57	61	57	61	56	60	55	58	54	56
ST .....	55 <sup>b</sup>	55	59	55	59	54	57	53	55	51	53
$F_{cy}$ , ksi:											
L .....	57	57	61	56	60	55	59	53	56	52	54
LT .....	57	57	61	57	61	56	60	55	58	54	56
ST .....	...	57	61	58	62	57	61	57	60	56	58
$F_{su}$ , ksi:											
L .....	...	38	39	38	39	38	39	37	38	37	38
LT .....	...	38	39	38	39	38	39	37	38	37	38
ST .....	...	36	37	36	37	36	37	35	36	35	36
$F_{bru}^a$ , ksi:											
(e/D = 1.5) .....	...	97	100	96	100	96	99	94	97	93	96
(e/D = 2.0) .....	...	126	130	125	130	125	128	123	126	121	125
$F_{bry}^a$ , ksi:											
(e/D = 1.5) .....	...	79	84	80	85	80	85	79	84	79	82
(e/D = 2.0) .....	...	91	98	92	99	92	99	92	97	91	95
e, percent (S-basis):											
L .....	6	6	...	6	...	5	...	5	...	5	...
LT .....	5	5	...	4	...	4	...	4	...	4	...
ST .....	1.5 <sup>b</sup>	1.5	...	1.5	...	1.5	...	1.5	...	1.5	...
$E$ , 10 <sup>3</sup> ksi .....	10.4										
$E_c$ , 10 <sup>3</sup> ksi .....	10.9										
$G$ , 10 <sup>3</sup> ksi .....	4.0										
$\mu$ .....	0.33										
Physical Properties:											
$\omega$ , lb/in. <sup>3</sup> .....	0.100										
C, Btu/(lb)(°F) .....	0.21 (at 212°F)										
K, Btu/[(hr)(ft <sup>3</sup> )(°F)/ft]	87 (at 77°F)										
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	12.6 (68°F to 212°F)										

a Bearing values are "dry pin" values per Section 1.4.7.1. See Table 3.1.2.1.1.


b Applicable to 1.500-inch thickness only.

**MIL-HDBK-5H****1 December 1998**


**Figure 3.2.6.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2124-T851 aluminum alloy plate.**



**Figure 3.2.6.1.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2124-T851 aluminum alloy plate.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.6.1.6(a). Typical tensile stress-strain curves for 2124-T851 aluminum alloy plate at room temperature.**



**Figure 3.2.6.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 2124-T851 aluminum alloy plate at room temperature.**

MIL-HDBK-5H  
1 December 1998



**Figure 3.2.6.1.9(a).** Fatigue-crack-propagation data for 2.0 to 5.5 inch thick, 2124-T851 aluminum alloy plate. [References 3.2.6.1.9(a), 3.2.6.1.9(c), and 3.2.6.1.9(d)].

Specimen Thickness: 0.25-0.45 and 0.15 inch  
Specimen Width: 11.75 and 3.0 inches  
Specimen Type: M(T) and C(T)

Environment: 95% R.H.  
Temperature: RT  
Orientation: L-T

MIL-HDBK-5H  
1 December 1998




Figure 3.2.6.1.9(b). Fatigue-crack-propagation data for 2.0-inch thick, 2124-T851 aluminum alloy plate. [Reference 3.2.6.1.9(a)].

Specimen Thickness: 0.25-0.45 inch  
Specimen Width: 11.75 inches  
Specimen Type: M(T)

Environment: Lab air  
Temperature: 300-400 °F  
Orientation: L-T

MIL-HDBK-5H  
1 December 1998




Figure 3.2.6.1.9(c). Fatigue-crack-propagation data for 2.5-inch thick, 2124-T851 aluminum alloy plate. [Reference 3.2.6.1.9(b)].

Specimen Thickness:	0.75 inch	Environment:	Lab air
Specimen Width:	1.75 inches	Temperature:	-100 through 400 °F
Specimen Type:	C(T)	Orientation:	L-T

## MIL-HDBK-5H

1 December 1998




Figure 3.2.6.1.9(d). Fatigue-crack-propagation data for 2.0 to 5.5 inch thick, 2124-T851 aluminum alloy plate. [References 3.2.6.1.9(a), 3.2.6.1.9(d), and 3.7.4.2.9(c)].

Specimen Thickness: 0.25-0.75 inch  
 Specimen Width: 4.0-11.75 inches  
 Specimen Type: M(T)

Environment: 90-95% R.H.  
 Temperature: RT  
 Orientation: T-L



MIL-HDBK-5H  
1 December 1998




Figure 3.2.6.1.9(e). Fatigue-crack-propagation data for 2.0-inch thick, 2124-T851 aluminum alloy plate. [Reference 3.2.6.1.9(a)].

Specimen Thickness:	0.25-0.45 inch	Environment:	Lab air
Width:	11.75 inches	Temperature:	300-400 °F
Type:	M(T)	Orientation:	T-L

**MIL-HDBK-5H****1 December 1998****3.2.7 2219 ALLOY**

**3.2.7.0 Comments and Properties** — 2219 is an Al-Cu alloy available in a wide variety of product forms. Refer to Section 3.1.2.3 for comments regarding the resistance of the alloy to stress-corrosion cracking, and to Section 3.1.3.4 for comments regarding the weldability of the alloy. It has been used in critical cryogenic applications as well as those applications in which high strength and creep resistance at relatively high temperatures (400 to 600°F) are required.

The properties of extrusions should be based upon the thickness at the time of quenching prior to machining. Selection of the mechanical properties based upon its final machined thickness may be unconservative; therefore, the thickness at the time of quenching to achieve properties is an important factor in the selection of the proper thickness column. For extrusions having sections with various thicknesses, consideration should be given to the properties as a function of thickness.

Material specifications for 2219 are presented in Table 3.2.7.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.2.7.0(b) through (d). The effect of temperature on the physical properties is shown in Figure 3.2.7.0.

**Table 3.2.7.0(a). Material Specifications  
for 2219 Aluminum Alloy**

Specification	Form
AMS 4031	Sheet and plate
AMS-QQ-A-250/30	Sheet and plate
AMS 4162	Extrusion
AMS 4163	Extrusion
AMS 4144	Hand forging

The temper index for 2219 is as follows:

<u>Section</u>	<u>Temper</u>
3.2.7.1	T62
3.2.7.2	T81, T851, T8510, and T8511
3.2.7.3	T852
3.2.7.4	T87

**3.2.7.1 T62 Temper** — Elevated temperature data for this temper are presented in Figures 3.2.7.1.1(a) and (b). Typical room-temperature tensile and compressive stress-strain, compressive tangent-modulus, and full-range tensile stress-strain curves for 2219 aluminum alloy sheet and plate for this temper are shown in Figures 3.2.7.1.6(a) and (b).

**3.2.7.2 T81 and T851X Tempers** — Elevated temperature data for these tempers are presented in Figures 3.2.7.2.1(a) and (b). Typical room-temperature tensile and compressive stress-strain, compressive tangent-modulus, and full-range tensile stress-strain curves for 2219 aluminum alloy for this condition are shown in Figures 3.2.7.2.6(a) and (b). Notched fatigue data for plate are presented in Figures 3.2.7.2.8(a) through (d).

**MIL-HDBK-5H****1 December 1998**

**3.2.7.3 T852 Temper** — Typical room-temperature tensile and compressive stress-strain, compressive tangent-modulus, and full-range tensile stress-strain curves for 2219 aluminum alloy for this temper are shown in Figures 3.2.7.3.6(a) through (e).

**3.2.7.4 T87 Temper** — Elevated temperature data for this temper are presented in Figures 3.2.7.4.1(a) and (b). Typical room-temperature tensile and compressive stress-strain, compressive tangent-modulus, and full-range tensile stress-strain curves for 2219 aluminum alloy sheet and plate for this temper are shown in Figures 3.2.7.4.6(a) through (e).

**Table 3.2.7.0(b<sub>1</sub>). Design Mechanical and Physical Properties of 2219 Aluminum Alloy Sheet and Plate**

Specification . . . . .	AMS 4031 & AMS-QQ-A- 250/30		AMS-QQ-A-250/30													
Form . . . . .	Sheet and plate															
Temper . . . . .	T62 <sup>a</sup>		T81		T851											
Thickness, in. . . . .	0.020-2.000		0.020-0.249		0.250-1.000		1.001-2.000		2.001-3.000		3.001-4.000		4.001-5.000		5.001-6.000	
Basis . . . . .	A	B	A	B	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:																
$F_{tu}$ , ksi:																
L . . . . .	54	55	61	62	61	62	61	62	...	...	...	...	...	...	...	...
LT . . . . .	54	55	62	63	62	63	62	63	62	63	60	61	59	60	57	58
$F_{ty}$ , ksi:																
L . . . . .	36	37	47	48	47	48	47	48	...	...	...	...	...	...	...	...
LT . . . . .	36	37	46	47	46	47	46	47	45	46	44	45	43	44	42	43
$F_{cy}$ , ksi:																
L . . . . .	37	39	47	48	47	48	47	48	...	...	...	...	...	...	...	...
LT . . . . .	37	38	48	49	48	49	48	49	...	...	...	...	...	...	...	...
$F_{su}$ , ksi . . . . .	31	32	35	35	36	36	36	36	...	...	...	...	...	...	...	...
$F_{bru}^b$ , ksi:																
(e/D = 1.5) . . . . .	84	85	95	96	95	96	95	96	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	107	109	121	123	121	123	121	123	...	...	...	...	...	...	...	...
$F_{bry}^b$ , ksi:																
(e/D = 1.5) . . . . .	62	64	76	78	76	78	76	78	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	79	81	92	94	94	94	92	94	...	...	...	...	...	...	...	...
$e$ , percent (S-basis):																
LT . . . . .	c	...	c	...	8	...	7	...	6	...	5	...	5	...	4	...
$E$ , 10 <sup>3</sup> ksi . . . . .	10.5															
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.8															
$G$ , 10 <sup>3</sup> ksi . . . . .	4.0															
$\mu$ . . . . .	0.33															
Physical Properties:																
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.103															
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.2.7.0															

a Design allowables were based upon data obtained from testing samples of material, supplied in O and F temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by user may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.

b Bearing values are "dry pin" values per Section 1.4.7.1. See Table 3.1.2.1.1.

c T62 and T81: 0.020-0.039 in., 6 percent, 0.040-0.249 in., 7 percent; T62: 0.250-1.000 in., 8 percent, 1.001-2.000 in., 7 percent.

**MIL-HDBK-5H****1 December 1998****Table 3.2.7.0(b<sub>2</sub>). Design Mechanical and Physical Properties of 2219 Aluminum Alloy Sheet — Continued**

Specification . . . . .	AMS-QQ-A-250\30			
Form . . . . .	Sheet			
Condition . . . . .	T87			
Thickness, in. . . . .	0.020-0.039		0.040-0.249	
Basis . . . . .	A	B	A	B
Mechanical Properties:				
$F_{tu}$ , ksi:				
L . . . . .	63	64	63	64
LT . . . . .	64	65	64	65
$F_{ty}$ , ksi:				
L . . . . .	51	52	51	52
LT . . . . .	52	53	52	53
$F_{cy}$ , ksi:				
L . . . . .	52	53	52	53
LT . . . . .	55	56	55	56
$F_{su}$ , ksi . . . . .	36	37	36	37
$F_{bru}^a$ , ksi:				
(e/D = 1.5) . . . . .	99	100	99	100
(e/D = 2.0) . . . . .	126	128	126	128
$F_{bry}^a$ , ksi:				
(e/D = 1.5) . . . . .	83	85	83	85
(e/D = 2.0) . . . . .	96	98	96	98
$e$ , percent (S-basis): . . .				
LT . . . . .	5	...	6	...
$E$ , 10 <sup>3</sup> ksi . . . . .	10.5			
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.8			
$G$ , 10 <sup>3</sup> ksi . . . . .	4.0			
$\mu$ . . . . .	0.33			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.103			
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.2.7.0			

a See Table 3.1.2.1.1. Bearing values are “dry pin” values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 3.2.7.0(b<sub>3</sub>). Design Mechanical and Physical Properties of 2219 Aluminum Alloy Plate — Continued**

Specification . . . . .	AMS-QQ-A-250\30											
Form . . . . .	Plate											
Condition . . . . .	T87											
Thickness, in. . . . .	0.250-1.000		1.001-1.500		1.501-2.000		2.001-3.000		3.001-4.000		4.001-5.000	
Basis . . . . .	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:												
$F_m$ , ksi:												
L . . . . .	63	64	63	64	63	64	63	64	61	62	...	...
LT . . . . .	64	65	64	65	64	65	64	65	62	63	61	62
ST . . . . .	...	...	...	...	59	60	56	57	52	53	...	...
$F_{ty}$ , ksi:												
L . . . . .	50	51	50	51	50	51	50	51	49	50	...	...
LT . . . . .	51	52	51	52	51	52	51	52	51	51	49	50
ST . . . . .	...	...	...	...	51	52	50	51	48	49	...	...
$F_{cy}$ , ksi:												
L . . . . .	51	52	51	52	51	52	...	...	...	...	...	...
LT . . . . .	53	54	52	53	52	53	...	...	...	...	...	...
$F_{su}$ , ksi . . . . .	37	38	37	38	37	38	...	...	...	...	...	...
$F_{bru}^a$ , ksi:												
(e/D = 1.5) . . . . .	99	100	99	100	99	100	...	...	...	...	...	...
(e/D = 2.0) . . . . .	126	128	126	128	126	128	...	...	...	...	...	...
$F_{bry}^a$ , ksi:												
(e/D = 1.5) . . . . .	82	83	82	83	82	83	...	...	...	...	...	...
(e/D = 2.0) . . . . .	94	96	94	96	94	96	...	...	...	...	...	...
$e$ , percent (S-basis): . . . . .												
LT . . . . .	7	...	6	...	6	...	6	...	4	...	3	...
$E$ , 10 <sup>3</sup> ksi . . . . .	10.5											
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.8											
$G$ , 10 <sup>3</sup> ksi . . . . .	4.0											
$\mu$ . . . . .	0.33											
Physical Properties:												
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.103											
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.2.7.0											

a See Table 3.1.2.1.1. Bearing values are “dry pin” values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 3.2.7.0(c). Design Mechanical and Physical Properties of 2219 Aluminum Alloy Hand Forging**

Specification .....	AMS 4144							
Form .....	Hand Forging							
Temper .....	T852							
Thickness, in. ....	<2.000	2.000-4.000	4.001-6.000	6.001-8.000	8.001-10.000	10.001-12.000	12.001-14.000	14.001-17.000
Basis .....	S	S	S	S	S	S	S	S
Mechanical Properties:								
$F_{tu}$ , ksi:								
L .....	62	62	58	57	56	54	53	51
LT .....	62	62	56	55	54	53	52	50
ST .....	...	60	56	55	54	53	52	50
$F_{ty}$ , ksi:								
L .....	50	50	44	43	42	41	40	39
LT .....	49	49	42	41	41	40	40	39
ST .....	...	46	41	40	39	39	38	37
$F_{cy}$ , ksi:								
L.....	...	46	40	39	...	...	...	...
LT .....	...	47	40	39	...	...	...	...
ST .....	...	47	41	40	...	...	...	...
$F_{su}$ , ksi:								
L.....	...	37	35	35	...	...	...	...
LT .....	...	36	34	35	...	...	...	...
ST .....	...	32	32	33	...	...	...	...
$F_{bru}^a$ , ksi:								
(e/D = 1.5) .....	...	...	...	80	...	...	...	...
(e/D = 2.0) .....	...	104	100	102	...	...	...	...
$F_{bry}^a$ , ksi:								
(e/D = 1.5) .....	...	76	65	64	...	...	...	...
(e/D = 2.0) .....	...	89	76	75	...	...	...	...
$e$ , percent:								
L.....	6	6	6	6	6	6	6	6
LT .....	4	4	4	4	3	3	3	3
ST .....	...	3	3	3	3	2	2	2
$E$ , $10^3$ ksi .....	10.2							
$E_c$ , $10^3$ ksi .....	10.4							
$G$ , $10^3$ ksi .....	3.9							
$\mu$ .....	0.33							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> .....	0.103							
$C$ , $K$ , and $\alpha$ .....	See Figure 3.2.7.0							

a Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 3.2.7.0(d). Design Mechanical and Physical Properties of 2219 Aluminum Alloy Extruded Shapes**

Specification .....	AMS 4162 and AMS 4163 <sup>a</sup>	
Form .....	Extruded shapes	
Temper .....	T8511	
Cross-Sectional Area, in. <sup>2</sup> .....	≤25	
Thickness or Diameter, <sup>d</sup> in. ....	≤0.499	0.500-2.999
Basis .....	S	S
Mechanical Properties:		
$F_{tu}$ , ksi:		
L .....	58	58
LT <sup>b</sup> .....	56	56
$F_{ty}$ , ksi:		
L .....	42	42
LT <sup>b</sup> .....	39	39
$F_{cy}$ , ksi:		
L .....	43	42
LT .....	43	41
$F_{su}$ , ksi .....	33	33
$F_{bru}^c$ , ksi:		
(e/D = 1.5) .....	87	81
(e/D = 2.0) .....	113	107
$F_{bry}^c$ , ksi:		
(e/D = 1.5) .....	69	67
(e/D = 2.0) .....	84	82
$e$ , percent:		
L .....	6	6
LT <sup>b</sup> .....	4	4
$E$ , 10 <sup>3</sup> ksi .....	10.5	
$E_c$ , 10 <sup>3</sup> ksi .....	10.8	
$G$ , 10 <sup>3</sup> ksi .....	4.0	
$\mu$ .....	0.33	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> .....	0.103	
$C$ , $K$ , and $\alpha$ .....	See Figure 3.2.7.0	

a Design allowables for extrusions procured to AMS 4163 were based upon data obtained from testing samples of material, supplied in T3511 temper, which were precipitation heat treated by suppliers to demonstrate response to aging treatment.


b Applicable providing LT dimension is ≥2.500 inches.

c Bearing values are "dry pin" values per Section 1.4.7.1.

d The mechanical properties are to be based upon the thickness at the time of quench.




**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.7.0. Effect of temperature on the physical properties of 2219 aluminum alloy.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.7.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2219-T62 aluminum alloy sheet, 0.040-0.249, and plate, 0.250-1.000 in. thick.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.7.1.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2219-T62 aluminum alloy sheet, 0.040-0.249 and plate, 0.250-1.000 in. thick.**

**MIL-HDBK-5H****1 December 1998**


**Figure 3.2.7.1.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2219-T62 aluminum alloy sheet and plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.7.1.6(b). Typical tensile stress-strain (full range) curve for 2219-T62 aluminum alloy sheet and plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.7.2.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2219-T81 aluminum alloy sheet and 2219-T851 aluminum alloy plate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.7.2.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2219-T81 aluminum alloy sheet and 2219-T851 aluminum alloy plate.**

**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.7.2.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2219-T81 aluminum alloy sheet and 2219-T851 aluminum alloy plate at room temperature.**




**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.7.2.6(b). Typical tensile stress-strain curves (full range) for 2219-T81 aluminum alloy sheet and 2219-T851 aluminum alloy plate at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.7.2.8(a). Best-fit S/N curves for notched,  $K_t = 2.0$ , 2219-T851 aluminum alloy plate, longitudinal direction.**

Correlative Information for Figure 3.2.7.2.8(a)

Product Form: Plate, 2.00-inch thick

Properties:

TUS, ksi	TYS, ksi	Temp., °F
68	52	RT (unnotched)
94	—	RT (notched)

Specimen Details: Notched, V-Groove,  $K_t = 2.0$   
 0.195-inch gross diameter  
 0.136-inch net diameter  
 0.020-inch root radius,  $r$   
 60° flank angle,  $\epsilon$

Surface Condition: As machined

Reference: 3.2.7.2.8

Test Parameters:

Loading - Axial  
 Frequency - 7000 to 8000 cpm  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: 1

Equivalent Stress Equation:


$\log N_f = 7.92 - 2.69 \log (S_{eq} - 16.0)$   
 $S_{eq} = S_{max} (1-R)^{0.64}$  ksi  
 Standard Error of Estimate = 0.313  
 Standard Deviation in Life = 0.739  
 $R^2 = 82\%$

Sample Size = 34

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.7.2.8(b). Best-fit S/N curves for notched,  $K_t = 3.2$ , 2219-T851 aluminum alloy plate, longitudinal direction.**

Correlative Information for Figure 3.2.7.2.8(b)

Product Form: Plate, 2.00-inch thick

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	68	52	RT
			(unnotched)
	92	—	RT
			(notched)

Specimen Details: Notched, V-Groove,  $K_t = 3.2$   
 0.195-inch gross diameter  
 0.136-inch net diameter  
 0.006-inch root radius, r  
 60° flank angle,  $\omega$

Surface Condition: As machined

Reference: 3.2.7.2.8

Test Parameters:

Loading - Axial  
 Frequency - 7000 to 8000 cpm  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: 1

Equivalent Stress Equation:


$\log N_f = 8.46 - 2.83 \log (S_{eq}^{-3.93})$   
 $S_{eq} = S_{max} (1-R)^{0.76}$   
 Standard Error of Estimate = 0.292  
 Standard Deviation in Life = 0.64  
 $R^2 = 79\%$

Sample Size = 39

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.7.2.8(c). Best-fit S/N curves for notched,  $K_t = 3.2$ , 2219-T851 aluminum alloy plate, long transverse direction.**

Correlative Information for Figure 3.2.7.2.8(c)

Product Form: Plate, 2.00-inch thick

Test Parameters:

Properties:    TUS, ksi    TYS, ksi    Temp., °F

68	51	RT
		(unnotched)
89	—	RT
		(notched)

Loading - Axial  
Frequency - 7000 to 8000 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: 1

Specimen Details: Notched, V-Groove,  $K_t = 3.2$   
0.195-inch gross diameter  
0.136-inch net diameter  
0.006-inch root radius, r  
60° flank angle,  $\omega$

Equivalent Stress Equation:

$\log N_f = 10.85 - 4.34 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.686}$  ksi  
Standard Error of Estimate = 0.153  
Standard Deviation in Life = 0.610  
 $R^2 = 94\%$

Surface Condition: As machined


Sample Size = 25

Reference: 3.2.7.2.8

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.2.7.2.8(d). Best-fit S/N curves for notched,  $K_t = 5.0$ , 2219-T851 aluminum alloy plate, longitudinal direction.**

Correlative Information for Figure 3.2.7.2.8(d)

Product Form: Plate, 2.00-inch thick

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	68 (L)	52 (L)	RT
			(unnotched)
	91 (L)	—	RT
			(notched)

Specimen Details: Notched, V-Groove,  $K_t = 5.0$   
 0.300-inch gross diameter  
 0.210-inch net diameter  
 0.0035-inch root radius,  $r$   
 60° flank angle,  $\omega$

Surface Condition: As machined

Reference: 3.2.7.2.8

Test Parameters:

Loading - Axial  
 Frequency - 7000 to 8000 cpm  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: 1

Equivalent Stress Equation:


$\log N_f = 8.76 - 3.05 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.722}$  ksi  
 Standard Error of Estimate = 0.194  
 Standard Deviation in Life = 0.660  
 $R^2 = 91\%$

Sample Size = 38


[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

# MIL-HDBK-5H

1 December 1998




**Figure 3.2.7.3.6(a). Typical tensile stress-strain curves for 2219-T852 aluminum alloy hand forging at room temperature.**




**Figure 3.2.7.3.6(b). Typical tensile stress-strain curves for 2219-T852 aluminum alloy hand forging at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.7.3.6(c). Typical compressive stress-strain and compressive tangent-modulus curves for 2219-T852 aluminum alloy hand forging at room temperature.**



**Figure 3.2.7.3.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for 2219-T852 aluminum alloy hand forging at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.7.3.6(e). Typical tensile stress-strain curves (full range) for 2219-T852 aluminum alloy hand forging at room temperature.**




**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.7.4.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2219-T87 aluminum alloy sheet and plate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.7.4.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2219-T87 aluminum alloy sheet and plate.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.7.4.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2219-T87 aluminum alloy sheet and plate at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.7.4.6(b). Typical tensile stress-strain curves (full range) for 2219-T87 aluminum alloy sheet and plate at room temperature.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.7.4.6(c). Typical tensile stress-strain curve for 2219-T87 aluminum alloy plate at room temperature.**



**Figure 3.2.7.4.6(d). Typical tensile stress-strain curve for 2219-T87 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.7.4.6(e). Typical tensile stress-strain curve (full range) for 2219-T87 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H****1 December 1998****3.2.8 2519 ALLOY**

**3.2.8.0 Comments and Properties**— 2519 is an Al-Cu weldable alloy available in plate. This armor plate has equivalent ballistic protection characteristics compared to 7039 and superior stress-corrosion cracking resistance compared to 5083. See Section 3.1.2.3 for comments regarding resistance of the alloy to stress-corrosion cracking. The general corrosion characteristics of 2519 are similar to 2219. 2519 in the T87 temper has approximately 20 percent higher yield strength than 2219-T87 plate. 2519-T87 is easily welded with filler alloy 2319. Yield strengths of welded butt joints are higher than other commercially available alloys. 2519 can be post weld aged or post weld heat treated and aged to obtain improved mechanical properties compared to "as welded" condition. See Section 3.1.3.4 for further information regarding the weldability of the alloy.

A material specification of 2519 is presented in Table 3.2.8.0(a). Room-temperature mechanical and physical properties are shown in Table 3.2.8.0(b).

**Table 3.2.8.0(a). Material Specification for 2519 Aluminum Alloy**

Specification	Form
MIL-A-46192	Plate

The temper index for 2519 is as follows:

<u>Section</u>	<u>Temper</u>
3.2.8.1	T87

**3.2.8.1 T87 Temper**— Typical room-temperature tensile and compressive stress-strain and compressive tangent-modulus curves are presented in Figures 3.2.8.1.6(a) and (b).

**MIL-HDBK-5H****1 December 1998****Table 3.2.8.0(b). Design Mechanical and Physical Properties of 2519 Aluminum Alloy Plate**

Specification.....	MIL-A-46192			
Form.....	Plate			
Temper.....	T87			
Thickness or Diameter, in.....	0.250-1.000	1.001-2.000	2.001-3.000	3.001-4.000
Basis.....	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	66	66	67	68
LT .....	68	68	68	68
ST.....	...	...	63	62
$F_{ty}$ , ksi:				
L .....	59	59	60	61
LT .....	58	58	59	59
ST.....	...	...	55	55
$F_{cy}$ , ksi:				
L .....	57	57	58	58
LT .....	60	60	61	61
ST.....	...	...	58	58
$F_{su}$ , ksi .....	42	41	41	40
$F_{bru}^a$ , ksi:				
(e/D = 1.5) .....	105	105	104	103
(e/D = 2.0) .....	135	134	133	131
$F_{bry}^a$ , ksi:				
(e/D = 1.5) .....	85	85	87	87
(e/D = 2.0) .....	99	99	100	100
$e$ , percent:				
L.....	10	9	8	7
LT .....	7	7	6	5
$E$ , $10^3$ ksi .....	10.5			
$E_c$ , $10^3$ ksi .....	10.8			
$G$ , $10^3$ ksi .....	4.0			
$\mu$ .....	0.33			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.102			
$C$ , $K$ , and $\alpha$ .....	...			

a See Table 3.1.2.1.1. Bearing values are "dry pin" per Section 1.4.7.1.



MIL-HDBK-5H  
1 December 1998




Figure 3.2.8.1.6(a). Typical tensile stress-strain curves for 2519-T87 aluminum alloy plate at room temperature.




Figure 3.2.8.1.6(b). Typical compressive stress-strain and tangent-modulus curves for 2519-T87 plate at room temperature.

**MIL-HDBK-5H****1 December 1998****3.2.9 2524 ALLOY**

**3.2.9.0 Comments and Properties** — 2524 is a heat-treatable Al-Cu alloy offering high toughness and improved resistance to fatigue crack growth relative to other available 2XXX sheet and plate materials. Sheet and plate is available in the T3 temper. Fatigue crack growth improvements are guaranteed through the material specification for Alclad 2524-T3 sheet and plate products. The static mechanical properties and general corrosion performance of Alclad 2524-T3 are similar to those of Alclad 2024-T3. This product has typically been used for formed structural aircraft parts requiring improved resistance to fatigue crack growth and high toughness with strength similar to Alclad 2024-T3, but usage is not limited to such applications.

A material specification for Alclad 2524-T3 sheet and plate is presented in Table 3.2.9.0(a). Room-temperature mechanical properties are shown in Table 3.2.9.0(b).

**Table 3.2.9.0(a). Material Specifications for Alclad 2524-T3**

Specification	Form
AMS 4296	Clad sheet and plate

The temper index for 2524 is as follows:

<u>Section</u>	<u>Temper</u>
3.2.9.1	T3

## MIL-HDBK-5H

1 December 1998

**Table 3.2.9.0(b). Design Mechanical and Physical Properties of Alclad 2524-T3 Aluminum Alloy Sheet and Plate**

Specification . . . . .	AMS 4296						
Form . . . . .	Sheet and Plate						
Condition . . . . .	T3						
Thickness, in. . . . .	0.032-0.062	0.063-0.128		0.129-0.249		0.250-0.310	
Basis . . . . .	S	A	B	A	B	A	B
Mechanical Properties:							
$F_{tu}$ , ksi:							
L . . . . .	59	61	62	62	62	62	63
LT . . . . .	59	61 <sup>c</sup>	62	62	62	62	63
$F_{ty}$ , ksi:							
L . . . . .	44	45	47	45	46	45	46
LT . . . . .	39	40 <sup>d</sup>	42	40	41	40	41
$F_{cy}$ , ksi:							
L . . . . .	38	39	41	39	40	39	40
LT . . . . .	42	43	45	43	44	43	44
$F_{su}^b$ , ksi: . . . . .	40	41	42	42	42	42	43
$F_{bru}^a$ , ksi:							
(e/D = 1.5) . . . . .	93	97	98	98	98	98	100
(e/D = 2.0) . . . . .	117	121	123	123	123	123	125
$F_{bry}^a$ , ksi:							
(e/D = 1.5) . . . . .	65	67	70	67	69	67	69
(e/D = 2.0) . . . . .	76	78	82	78	80	78	80
$e$ , percent (S-basis):							
LT . . . . .	15	15	...	15	...	15	...
$E$ , 10 <sup>3</sup> ksi:							
Primary . . . . .				10.3			
Secondary . . . . .				9.8			
$E_c$ , 10 <sup>3</sup> ksi:							
Primary . . . . .				10.5			
Secondary . . . . .				10.0			
$G$ , 10 <sup>3</sup> ksi . . . . .				...			
$\mu$ . . . . .				0.35			
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> . . . . .				0.100			
$C$ , $K$ , and $\alpha$ . . . . .				not available			

a Bearing values are "dry pin" values per Section 1.4.7.1. See Table 3.1.2.1.1.

b Determined in accordance with ASTM B 831-93.

c S-basis value. The  $T_{99}$  value is 61.80 ksi.d S-basis value. The  $T_{99}$  value is 41.20 ksi.

**MIL-HDBK-5H****1 December 1998****3.2.10 2618 ALLOY**

**3.2.10.0 Comments and Properties** — 2618 is an Al-Cu alloy which is available as hand and die forgings. It has excellent properties over a range of temperatures from -452 to 600°F and is usually used in applications where high strength and creep resistance are important considerations. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy. Refer to Section 3.1.2.3.1 for information regarding resistance of the alloy to stress-corrosion cracking.

Material specifications for 2618 aluminum alloy are presented in Table 3.2.10.0(a). Room-temperature mechanical and physical properties are shown in Table 3.2.10.0(b) and (c). The effect of temperature on the thermal expansion is shown in Figure 3.2.10.0.

**Table 3.2.10.0(a). Material Specifications for 2618 Aluminum Alloy**


Specification	Form
AMS 4132	Die and hand forgings
QQ-A-367	Forgings
MIL-A-22771	Die forging

The temper index for 2618 is as follows:

Section  
3.2.10.1

Temper  
T61

**3.2.10.1 T61 Temper** — Figures 3.2.10.1.1(a) through 3.2.10.1.5 present effect-of-temperature curves for various mechanical properties. Figure 3.2.10.1.6(a) presents tensile and compressive stress-strain and tangent-modulus curves at room temperature. Figure 3.2.10.1.6(b) is a full-range, tensile stress-strain curve at room temperature.



**Figure 3.2.10.0. Effect of temperature on the thermal expansion of 2618 aluminum alloy.**

**MIL-HDBK-5H****1 December 1998****Table 3.2.10.0(b). Design Mechanical and Physical Properties of 2618 Aluminum Alloy Die Forging**

Specification .....	MIL-A-22771 and QQ-A-367
Form .....	Die forging
Temper .....	T61
Thickness, in. ....	$\leq 4.000^a$
Basis .....	S
Mechanical Properties:	
$F_{tu}$ , ksi:	
L .....	58
T <sup>b</sup> .....	55
$F_{ty}$ , ksi:	
L .....	45
T <sup>b</sup> .....	42
$F_{cy}$ , ksi:	
L .....	...
T <sup>b</sup> .....	...
$F_{su}$ , ksi:	...
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$e$ , percent:	
L .....	4
T <sup>b</sup> .....	4
$E$ , $10^3$ ksi .....	10.7
$E_c$ , $10^3$ ksi .....	10.9
$G$ , $10^3$ ksi .....	4.1
$\mu$ .....	0.33
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.100
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)
$K$ , Btu/[(hr)(ft <sup>3</sup> )(°F)/ft] .....	90 (at 77°F)
$\alpha$ , $10^{-6}$ in./in./°F .....	See Figure 3.2.9.0


a Thickness at the time of heat treatment. When die forgings are machined before heat treatment, the mechanical properties are applicable provided the as-forged thickness is not greater than twice the thickness at the time of heat treatment.

b T indicates any grain direction not within  $\pm 15^\circ$  of being parallel to the forging flow lines.


**MIL-HDBK-5H****1 December 1998****Table 3.2.10.0(c). Design Mechanical and Physical Properties of 2618 Aluminum Alloy Hand Forging**

Specification .....	AMS 4132, MIL-A-22771, and QQ-A-367		
Form .....	Hand forging		
Temper .....	T61		
Cross-Sectional Area, in. <sup>2</sup> .....	≤ 144		
Thickness, <sup>a</sup> in .....	< 2.000	2.000-	3.001-4.000
Basis .....	S	S	S
Mechanical Properties:			
$F_m$ , ksi:			
L .....	58	57	56
LT .....	55	55	53
ST .....	...	52	51
$F_y$ , ksi:			
L .....	47	46	45
LT .....	42	42	40
ST .....	...	42	39
$F_{cy}$ , ksi:			
L .....	...	...	44
LT .....	...	...	42
ST .....	...	...	40
$F_{su}$ , ksi .....	...	...	33
$F_{bru}$ , ksi:			
(e/D = 1.5) .....	...	...	...
(e/D = 2.0) .....	...	...	106
$F_{bry}$ , ksi:			
(e/D = 1.5) .....	...	...	...
(e/D = 2.0) .....	...	...	71
$e$ , percent:			
L .....	7	7	7
LT .....	5	5	5
ST .....	...	4	4
$E$ , 10 <sup>3</sup> ksi .....	10.7		
$E_c$ , 10 <sup>3</sup> ksi .....	10.9		
$G$ , 10 <sup>3</sup> ksi .....	4.1		
$\mu$ .....	0.33		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> .....	0.100		
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)		
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	90 (at 77°F)		
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	See Figure 3.2.9.0		

a When hand forgings are machined before heat treatment, the section thickness at time of heat treatment shall determine the minimum mechanical properties as long as the original (as-forged) thickness does not exceed the maximum thickness for the alloy as shown in the table.


**MIL-HDBK-5H****1 December 1998**

**Figure 3.2.10.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 2618-T61 aluminum alloy hand forging.**




**Figure 3.2.10.1.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 2618-T61 aluminum alloy hand forging.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.10.1.1(c). Effect of exposure at elevated temperatures on room-temperature tensile yield strength ( $F_{ty}$ ) of 2618-T61 hand forging.**




**Figure 3.2.10.1.1(d). Effect of exposure at elevated temperatures on room-temperature tensile ultimate strength ( $F_{tu}$ ) of 2618-T61 hand forging.**



**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.10.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and ultimate shear strength ( $F_{su}$ ) of 2618-T61 aluminum alloy hand forging.**




**Figure 3.2.10.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and bearing yield strength ( $F_{bry}$ ) of 2618-T61 aluminum alloy hand forging.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.2.10.1.4. Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of 2618-T61 aluminum alloy hand forging.**




**Figure 3.2.10.1.5. Effect of temperature on the elongation (e) of 2618-T61 aluminum alloy hand forging.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.10.1.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 2618-T61 aluminum alloy forged bar at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.2.10.1.6(b). Typical tensile stress-strain curve (full range) at room temperature for 2618-T61 aluminum alloy forged bar.**

**MIL-HDBK-5H****1 December 1998****3.3 3000 SERIES WROUGHT ALLOYS****3.4 4000 SERIES WROUGHT ALLOYS****3.5 5000 SERIES WROUGHT ALLOYS**

Alloys of the 5000 series contain magnesium as the principal alloying element and are strengthened by cold work. Because of their high toughness at temperatures down to -452°F, they are widely used in cryogenic applications.

Magnesium in excess of that in solid solution forms a constituent that is anodic to the aluminum-magnesium matrix. This constituent may form a network of precipitates at grain boundaries or along slip planes. The formation of this continuous grain boundary precipitates, which is accelerated by prior cold work and by exposure to elevated temperatures, causes stress-corrosion cracking susceptibility. Therefore, it is recommended that the strain-hardened tempers of 5000 series alloys containing more than 3 percent magnesium not be used at temperatures above 150°F because susceptibility to SCC may result.

**3.5.1 5052 ALLOY**

**3.5.1.0 Comments and Properties**—5052 is a low-strength Al-Mg alloy but extremely tough at low temperatures as well as at room temperature. It is highly resistant to corrosion; refer to Section 3.1.2.3 for comments regarding the resistance of the alloy to stress-corrosion cracking. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

Material specifications for 5052 aluminum alloy are presented in Table 3.5.1.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.5.1.0(b<sub>1</sub>) and (b<sub>2</sub>). The effect of temperature on physical properties is shown in Figure 3.5.1.0.

**Table 3.5.1.0(a). Material Specifications  
for 5052 Aluminum Alloy**

Specification	Form
AMS 4015	Sheet and plate
AMS 4016	Sheet and plate
AMS 4017	Sheet and plate
AMS-QQ-A-250/8	Sheet and plate

The temper index for 5052 is as follows:

<u>Section</u>	<u>Temper</u>
3.5.1.1	O
3.5.1.2	H32
3.5.1.3	H34
3.5.1.4	H35
3.5.1.5	H38

**3.5.1.1 O-Temper**—Elevated temperature curves for this temper for various mechanical properties are presented in Figures 3.5.1.1.1, 3.5.1.1.4, and 3.5.1.1.5.

**MIL-HDBK-5H****1 December 1998**

**3.5.1.2 H32 Temper** — Figure 3.5.1.1.4 may be used for the elevated temperature curve for modulus of elasticity.

**3.5.1.3 H34 Temper** — Elevated temperature curves for various mechanical properties are presented in Figures 3.5.1.3.1(a) through (d), and 3.5.1.3.5(a) and (b). Use Figure 3.5.1.1.4 for modulus values.

**3.5.1.4 H36 Temper** — Figure 3.5.1.1.4 may be used for the elevated temperature curve for modulus of elasticity.

**3.5.1.5 H38 Temper** — Elevated temperature curves for this temper for various mechanical properties are presented in Figures 3.5.1.5.1(a) through (d), and 3.5.1.5.5(a) and (b). Use Figure 3.5.1.1.4 for modulus values.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.5.1.0(b<sub>1</sub>). Design Mechanical and Physical Properties of 5052 Aluminum Alloy Sheet and Plate**

Specification . . . . .	AMS 4015	AMS 4016	AMS 4017	AMS-QQ-A-250/8	
Form . . . . .	Sheet and plate			Sheet	
Condition . . . . .	O	H32	H34	H36	H38
Thickness, in. . . . .	0.006-3.000	0.017-2.000	0.009-1.000	0.006-0.162	0.006-0.128
Basis . . . . .	S	S	S	S	S
Mechanical Properties:					
$F_{tu}$ , ksi:					
L . . . . .	25	31	34	37	39
LT . . . . .	...	31	34	37	39
$F_{ty}$ , ksi:					
L . . . . .	9.5	23	26	29 <sup>a</sup>	32 <sup>a</sup>
LT . . . . .	...	22	25	29	32
$F_{cy}$ , ksi:					
L . . . . .	...	22	25	...	...
LT . . . . .	...	23	26	...	...
$F_{su}$ , ksi . . . . .	16	19	20	22	23
$F_{bru}$ , ksi:					
(e/D = 1.5) . . . . .	...	50	54	59	62
(e/D = 2.0) . . . . .	...	65	71	78	82
$F_{bry}$ , ksi:					
(e/D = 1.5) . . . . .	...	32	37	41	44
(e/D = 2.0) . . . . .	...	37	41	46	51
$e$ , percent:					
L . . . . .	b	b	b	b	b
$E$ , 10 <sup>3</sup> ksi . . . . .	10.1				
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.2				
$G$ , 10 <sup>3</sup> ksi . . . . .	3.85				
$\mu$ . . . . .	0.33				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.097				
$C$ , Btu/(lb)(°F) . . .	0.23 (at 212°F)				
$K$ and $\alpha$ . . . . .	See Figure 3.5.1.0				

a From "Aluminum Standards and Data" dated 1982.


b See Table 3.5.1.0(b<sub>2</sub>).

**MIL-HDBK-5H****1 December 1998****Table 3.5.1.0(b<sub>2</sub>). Minimum Elongation Values for 5052 Aluminum Alloy Sheet and Plate**

Temper	Thickness Range, inch	Elongation (L), percent
O .....	0.006-0.007	...
	0.008-0.012	14
	0.013-0.019	15
	0.020-0.031	16
	0.032-0.050	18
	0.051-0.113	19
	0.114-0.249	20
	0.250-3.000	18
H32 .....	0.017-0.019	4
	0.020-0.050	5
	0.051-0.113	7
	0.114-0.249	9
	0.250-0.499	11
	0.500-2.000	12
H34 .....	0.009-0.019	3
	0.020-0.050	4
	0.051-0.113	6
	0.114-0.249	7
	0.250-1.000	10
H36 .....	0.006-0.007	2
	0.008-0.031	3
	0.032-0.162	4
H38 .....	0.006-0.007	2
	0.008-0.031	3
	0.032-0.128	4




**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.1.0. Effect of temperature on the physical properties of 5052 aluminum alloy.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.5.1.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of 5052-0 aluminum alloy (all products).**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.5.1.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of 5052-0 aluminum alloy (all products).**




**Figure 3.5.1.1.5. Effect of temperature on the elongation of 5052-0 aluminum alloy (all products).**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.1.3.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 5052-H34 aluminum alloy sheet and plate.**



**Figure 3.5.1.3.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 5052-H34 aluminum alloy sheet and plate.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.5.1.3.1(c). Effect of exposure at elevated temperatures on the room-temperature tensile ultimate strength ( $F_{tu}$ ) of 5052-H34 aluminum alloy sheet and plate.**




**Figure 3.5.1.3.1(d). Effect of exposure at elevated temperatures on the room-temperature tensile yield strength ( $F_{ty}$ ) of 5052-H34 aluminum alloy sheet and plate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.1.3.5(a). Effect of temperature on the elongation (e) of 5052-H34 aluminum alloy sheet and plate.**




**Figure 3.5.1.3.5(b). Effect of exposure at elevated temperatures on the elongation (e) of 5052-H34 aluminum alloy sheet and plate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.1.5.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 5052-H38 aluminum alloy (all products).**




**Figure 3.5.1.5.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 5052-H38 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.1.5.1(c). Effect of exposure at elevated temperatures on the room-temperature tensile ultimate strength ( $F_{tu}$ ) of 5052-H38 aluminum alloy (all products).**




**Figure 3.5.1.5.1(d). Effect of exposure at elevated temperatures on the room-temperature tensile yield strength ( $F_{ty}$ ) of 5052-H38 aluminum alloy (all products).**



**MIL-HDBK-5H****1 December 1998**

**Figure 3.5.1.5.5(a). Effect of temperature on the elongation of 5052-H38 aluminum alloy (all products).**



**Figure 3.5.1.5.5(b). Effect of exposure at elevated temperatures on the elongation of 5052-H38 aluminum alloy (all products).**

**MIL-HDBK-5H****1 December 1998****3.5.2 5083 ALLOY**

**3.5.2.0 Comments and Properties** — 5083 is a high-strength Al-Mg alloy which has been widely used in cryogenic applications, because of its excellent combination of strength and toughness. It has high resistance to corrosion, but strain-hardened tempers should not be used at temperatures above 150°F because of possible sensitization to stress-corrosion cracking. Refer to Section 3.1.2.3 for comments regarding the resistance of the alloy to stress-corrosion cracking, and to Section 3.1.3.4 for comments regarding the weldability of the alloy.

Material specifications for 5083 aluminum alloy are presented in Table 3.5.2.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.5.2.0(b) and (c). The effect of temperature on thermal expansion is shown in Figure 3.5.2.0.

**Table 3.5.2.0(a). Material Specifications for 5083 Aluminum Alloy**

Specification	Form
AMS 4056	Bare sheet and plate
AMS-QQ-A-250/6	Bare sheet and plate
AMS-QQ-A-200/4	Extruded bar, rod, and shapes

The temper index for 5083 is as follows:

<u>Section</u>	<u>Temper</u>
3.5.2.1	O
3.5.2.2	H111
3.5.2.3	H112
3.5.2.4	H321
3.5.2.5	H323
3.5.2.6	H343

**3.5.2.1 O Temper** — Tensile and compressive stress-strain and tangent-modulus curves at room temperature are presented in Figures 3.5.2.1.6(a) and (b). A full-range tensile stress-strain curve is shown in Figure 3.5.2.1.6(c) at room temperature.

**Table 3.5.2.0(b). Design Mechanical and Physical Properties of 5083 Aluminum Alloy Sheet and Plate**


Specification	AMS 4056 and AMS-QQ-A-250/6							AMS-QQ-A-250/6									
Form	Sheet and plate																
Temper	O							H112		H321		H323			H343		
Thickness, in.	0.051-1.500	1.501-3.000	3.001-4.000	4.001-5.000	5.001-7.000	7.001-8.000	0.250-1.500	1.501-3.000	0.188-1.500	1.501-3.000	0.051-0.125	0.126-0.249	0.051-0.125	0.126-0.249			
Basis	A	B	S	S	S	S	S	S	A	B	S	A	B	S	S	S	
Mechanical Properties:																	
$F_{tu}$ , ksi:																	
L	40	41	39	38	38	37	36	40	39	44	46	41	45	47	45	50	50
LT	40	41	...	...	...	...	...	...	...	44	46	...	...	...	...	...	...
$F_{ty}$ , ksi:																	
L	18	19	17	16	16	15	14	18	17	31	32	29	34	36	34	39	39
LT	18	19	...	...	...	...	...	...	...	28	28	...	...	...	...	...	...
$F_{cy}$ , ksi:																	
L	18	19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
LT	18	19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
$F_{su}$ , ksi	25	26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
$F_{bru}$ , ksi:																	
(e/D = 1.5)	60	62	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
(e/D = 2.0)	76	78	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
$F_{bry}$ , ksi:																	
(e/D = 1.5)	32	34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
(e/D = 2.0)	38	40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
$e$ , percent (S basis):																	
L	16	...	16	16	14	14	12	12	12	12	...	12	8	...	10	6	8
$E$ , 10 <sup>3</sup> ksi	10.2																
$E_c$ , 10 <sup>3</sup> ksi	10.4																
$G$ , 10 <sup>3</sup> ksi	3.85																
$\mu$	0.33																
Physical Properties:																	
$\omega$ , lb/in. <sup>3</sup>	0.096																
$C$ , Btu/(lb)(°F)	0.23 (at 212°F)																
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	68 (at 77°F)																
$\alpha$ , 10 <sup>-6</sup> in./in./°F	See Figure 3.5.2.0																

**MIL-HDBK-5H****1 December 1998****Table 3.5.2.0(c). Design Mechanical and Physical Properties of 5083 Aluminum Alloy Extrusion**

Extrusion				
Specification	AMS-QQ-A-200/4			
Form	Extrusion			
Temper	O	H111		H112
Thickness, in.	≤5.000 <sup>a</sup>	<0.500 <sup>a</sup>	0.501-5.000 <sup>a</sup>	≤5.000 <sup>a</sup>
Basis	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L	39	40	40	39
LT	...	40	32	...
$F_{ty}$ , ksi:				
L	16	24	24	16
LT	...	24	19	...
$F_{cy}$ , ksi:				
L	...	...	...	...
LT	...	...	...	...
$F_{su}$ , ksi	...	...	...	...
$F_{bru}$ , ksi:				
(e/D = 1.5)	...	...	...	...
(e/D = 2.0)	...	...	...	...
$F_{bry}$ , ksi:				
(e/D = 1.5)	...	...	...	...
(e/D = 2.0)	...	...	...	...
$e$ , percent:				
L	14	12	12	12
$E$ , 10 <sup>3</sup> ksi	10.2			
$E_c$ , 10 <sup>3</sup> ksi	10.4			
$G$ , 10 <sup>3</sup> ksi	3.35			
$\mu$	0.33			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup>	0.096			
$C$ , Btu/(lb)(°F)	0.23 (at 212°F)			
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	68 (at 77°F)			
$\alpha$ , 10 <sup>-6</sup> in./in./°F	See Figure 3.5.2.0			


a Cross-sectional area  $\leq 32$ .

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.2.0. Effect of temperature on the thermal expansion of 5083 aluminum alloy.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.2.1.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5083-0 aluminum alloy sheet at room temperature.**



**Figure 3.5.2.1.6(b). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5083-0 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.5.2.1.6(c). Typical tensile stress-strain curve (full range) for 5083-0 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H****1 December 1998****3.5.3 5086 ALLOY**

**3.5.3.0 Comments and Properties** — 5086 is a tough, medium-strength Al-Mg alloy suitable for application over the range of temperatures from -452 to 150°F. Refer to Section 3.1.2.3 for comments regarding resistance of the alloy to stress-corrosion cracking, and to Section 3.1.3.4 for comments regarding the weldability of the alloy.

Material specifications for 5086 aluminum alloy are presented in Table 3.5.3.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.5.3.0(b) and (c).

**Table 3.5.3.0(a). Material Specifications for 5086 Aluminum Alloy**

Specification	Form
AMS-QQ-A-250/7	Sheet and plate
AMS-QQ-A-200/5	Extruded bar, rod, and shapes

The temper index for 5086 is as follows:

<u>Section</u>	<u>Temper</u>
3.5.3.1	O
3.5.3.2	H32
3.5.3.3	H34
3.5.3.4	H36
3.5.3.5	H38
3.5.3.6	H111
3.5.3.7	H112

**3.5.3.1 O Temper** — Tensile, compressive stress-strain and tangent-modulus curves at room temperature are shown in Figures 3.5.3.1.6(a) and (b) for products with this temper. Figure 3.5.3.1.6(c) is a full-range tensile stress-strain curve.

**3.5.3.2 H32 Temper** — Figures 3.5.3.2.6(a) and (b) show tensile and compressive stress-strain and tangent-modulus curves at room temperature.

**3.5.3.3 H34 Temper** — Figures 3.5.3.3.6(a) and (b) show tensile, compressive stress-strain, and tangent-modulus curves for this temper. A full-range tensile stress-strain curve is shown in Figure 3.5.3.3.6(c).

**3.5.3.4 H36 Temper** — Figure 3.5.3.4.6 shows tensile, compressive stress-strain and tangent-modulus curves at room temperature.

**3.5.3.5 H38 Temper** —

**3.5.3.6 H111 Temper** —

**3.5.3.7 H112 Temper** — Figure 3.5.3.7.6 shows tensile, compressive stress-strain and tangent-modulus curves at room temperature.



**Table 3.5.3.0(b). Design Mechanical and Physical Properties of 5086 Aluminum Alloy Sheet, Plate and Extrusion**

Specification . . . .  Form . . . . .  Condition . . . . .  Thickness, in . . .  Basis . . . . .	AMS-QQ-A-250/7										AMS-QQ-A-200/5			
	Sheet and plate										Extrusion			
	O		H32		H34	H36	H38	H112				O	H111	H112
	0.020-2.000		0.020-2.000		0.009-1.000	0.006-0.162	0.006-0.020	0.188-0.499	0.500-1.00	1.001-2.000	2.001-3.000	≤5.000 <sup>a</sup>	≤5.000 <sup>a</sup>	≤5.000 <sup>a</sup>
	A	B	A	B	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:														
$F_{tu}$ , ksi:	35	36	40	41	44	47	50	36	35	35	34	35	36	35
L . . . . .	35	36	40	41	44	47	...	36	35	35	34	...	...	...
LT . . . . .														
$F_{ty}$ , ksi:	14	15	28	30	34	38	41	18	16	14	14	14	21	14
L . . . . .	14	15	26	28	33	37	...	17	16	14	14	...	...	...
LT . . . . .														
$F_{cy}$ , ksi:	14	15	26	28	32	35	...	17	15	14	14	...	...	...
L . . . . .	14	15	28	30	34	38	...	18	16	14	14	...	...	...
LT . . . . .	21	22	24	25	26	27	...	22	21	21	20	...	...	...
$F_{su}$ , ksi . . . . .														
$F_{bru}$ , ksi:	52	53	58	61	64	68	...	54	52	52	51	...	...	...
(e/D=1.5) . . .	70	72	80	82	88	94	...	72	70	70	68	...	...	...
(e/D=2.0) . . .														
$F_{bry}$ , ksi:	24	26	39	42	48	53	...	25	24	24	24	...	...	...
(e/D=1.5) . . .	28	30	48	51	58	65	...	31	28	28	28	...	...	...
(e/D=2.0) . . .														
$e$ , percent (S basis):	b	...	b	...	b	b	3	8	10	14	14	14	12	12
L . . . . .														
$E$ , 10 <sup>3</sup> ksi . . . . .	10.2													
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.4													
$G$ , 10 <sup>3</sup> ksi . . . . .	3.85													
$\mu$ . . . . .	0.33													
Physical Properties:														
$\omega$ , lb/in. <sup>3</sup> . . . .	0.096													
$C$ ,Btu/(lb)(°F)	0.23 (at 212 °F)													
$K$ ,	72 (at 77 °F)													
Btu/[(hr)(ft <sup>2</sup> )(°F)ft]	13.2 (68 to 212 °F)													
$\alpha$ , 10 <sup>-6</sup> in/in/°F														


a Cross-sectional area ≤32.

b See Table 3.5.3.0(c).


**MIL-HDBK-5H****1 December 1998****Table 3.5.3.0(c). Minimum Elongation Values for 5086 Aluminum Alloy Sheet and Plate**

Temper	Thickness Range, inch	Elongation (L), percent
O.....	0.020-0.050	15
	0.051-0.249	18
	0.250-2.000	16
H32.....	0.020-0.050	6
	0.051-0.249	8
	0.250-2.000	12
H34.....	0.009-0.019	4
	0.020-0.050	5
	0.051-0.249	6
H36.....	0.250-1.000	10
	0.006-0.019	3
	0.020-0.050	4
	0.051-0.162	6

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.3.1.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5086-0 aluminum alloy sheet at room temperature.**




**Figure 3.5.3.1.6(b). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5086-0 aluminum alloy plate and extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.3.1.6(c). Typical tensile stress-strain curve (full range) for 5086-0 aluminum alloy sheet at room temperature.**




**Figure 3.5.3.2.6(a). Typical tensile stress-strain curves for 5086-H32 aluminum alloy sheet at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.3.2.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 5086-H32 aluminum alloy sheet at room temperature.**



**Figure 3.5.3.2.6(c). Typical tensile stress-strain curves (full range) for 5086-H32 aluminum alloy sheet at room temperature.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.5.3.3.6(a). Typical tensile stress-strain curves for 5086-H34 aluminum alloy sheet at room temperature.**




**Figure 3.5.3.3.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 5086-H34 aluminum alloy sheet at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.5.3.3.6(c). Typical tensile stress-strain curve (full range) for 5086-H34 aluminum alloy sheet at room temperature.**



**Figure 3.5.3.4.6. Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5086-H36 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H****1 December 1998**

**Figure 3.5.3.7.6. Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5086-H112 aluminum alloy plate at room temperature.**



**MIL-HDBK-5H****1 December 1998****3.5.4 5454 ALLOY**

**3.5.4.0 Comments and Properties** — 5454 is a tough medium-strength Al-Mg alloy. It is the highest strength alloy of the 5000 series which may be used at elevated temperatures without concern about resensitization to stress-corrosion cracking. Refer to Section 3.1.2.3 for comments regarding the resistance of the alloy to stress-corrosion cracking, and to Section 3.1.3.4 for comments regarding the weldability of the alloy.

Materials specifications for 5454 aluminum alloy are presented in Table 3.5.4.0(a). Room-temperature physical properties are shown in Table 3.5.4.0(b) and (c).

**Table 3.5.4.0(a). Material Specifications for 5454 Aluminum Alloy**

Specification	Form
AMS-QQ-A-250/10	Sheet and plate
AMS-QQ-A-200/6	Extruded bar, rod, and shapes

The temper index for 5454 is as follows:

<u>Section</u>	<u>Temper</u>
3.5.4.1	O
3.5.4.2	H32
3.5.4.3	H34

**3.5.4.1 O Temper** — Figure 3.5.4.1.6 presents tensile and compressive stress-strain curves and this temper.

**3.5.4.2 H32 Temper** — Figure 3.5.4.2.6 presents room-temperature tensile stress-strain curves for this temper.

**3.5.4.3 H34 Temper** — Figures 3.5.4.3.6(a) and (b) present room-temperature tensile and compressive stress-strain and tangent-modulus curves for this temper.

**MIL-HDBK-5H****1 December 1998****Table 3.5.4.0(b). Design Mechanical and Physical Properties of 5454 Aluminum Alloy Sheet, Plate, and Extrusion**

Specification .....	AMS-QQ-A-250/10							AMS-QQ-A-200/6		
Form .....	Sheet and plate							Extrusion		
Temper .....	O		H32		H34	H112		O	H111	H112
Thickness, in. ....	0.020-3.000		0.020-2.000		0.020-1.000	0.250-0.499	0.500-3.000	≤5.000 <sup>a</sup>	≤5.000 <sup>a</sup>	≤5.000 <sup>a</sup>
Basis .....	A	B	A	B	S	S	S	S	S	S
Mechanical Properties:										
$F_{tu}$ , ksi:										
L .....	31	32	36	37	39	32	31	31	33	31
LT .....	31	32	36	37	39	32	31	...	...	31
$F_{ty}$ , ksi:										
L .....	12	13	26	27	29	18	12	12	19	12
LT .....	12	13	24	25	28	18	12	...	...	12
$F_{cy}$ , ksi:										
L .....	12	13	24	25	27	17	12	12	...	12
LT .....	12	13	26	27	29	18	12	...	...	12
$F_{su}$ , ksi .....	19	20	21	22	23	20	19	...	...	19
$F_{bru}$ , ksi:										
(e/D = 1.5) .....	46	48	52	54	57	48	46	...	...	43
(e/D = 2.0) .....	62	64	72	74	78	64	62	...	...	56
$F_{bry}$ , ksi:										
(e/D = 1.5) .....	20	22	36	38	41	25	20	...	...	20
(e/D = 2.0) .....	24	26	44	46	49	31	24	...	...	24
$e$ , percent (S-basis):										
L .....	b	...	b	...	b	8	b	14	12	12
$E$ , 10 <sup>3</sup> ksi .....	10.2									
$E_c$ , 10 <sup>3</sup> ksi .....	10.4									
$G$ , 10 <sup>3</sup> ksi .....	3.85									
$\mu$ .....	0.33									
Physical Properties:										
$\omega$ , lb/in. <sup>3</sup> .....	0.097									
$C$ , Btu/(lb)(°F) ....	0.23 (at 212°F)									
$K$ , Btu/[(hr)(ft <sup>3</sup> )(°F)/ft]	78 (at 77°F)									
$\alpha$ , 10 <sup>-6</sup> in./in./°F ....	13.1 (68 to 212°F)									


a Cross-sectional area ≤32.

b See Table 3.5.4.0(c).


**MIL-HDBK-5H****1 December 1998****Table 3.5.4.0(c). Minimum Elongation Values for 5454 Aluminum Alloy Sheet and Plate**

Temper	Thickness Range, inch	Elongation (L), percent
O .....	0.020-0.031	12
	0.030-0.050	14
	0.051-0.113	16
	0.114-3.000	18
H32 .....	0.020-0.050	5
	0.051-0.249	8
	0.250-2.000	12
H34 .....	0.020-0.050	4
	0.051-0.161	6
	0.162-0.249	7
	0.250-1.000	10
H112 .....	0.500-2.000	11
	2.001-3.000	15

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.4.1.6. Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5454-0 aluminum alloy sheet, plate, extrusion at room temperature.**




**Figure 3.5.4.2.6. Typical tensile stress-strain curves for 5454-H32 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.5.4.3.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5454-H34 aluminum alloy sheet at room temperature.**



**Figure 3.5.4.3.6(b). Typical tensile stress-strain curve for 5454-H34 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H****1 December 1998****3.5.5 5456 ALLOY**

**3.5.5.0 Comments and Properties** — 5456 is the highest strength alloy of the Al-Mg group. It has high resistance to corrosion, but should not be used in strain-hardened tempers at temperatures above 150°F because of possible sensitization to stress-corrosion cracking. Refer to Section 3.1.2.3 for comments regarding the resistance of the alloy to stress-corrosion cracking, and to Section 3.1.3.4 for comments regarding the weldability of the alloy.

Some material specifications for 5456 aluminum alloy are presented in Table 3.5.5.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.5.5.0(b) and (c). The effect of temperature on physical properties is shown in Figure 3.5.5.0.

**Table 3.5.5.0(a). Material Specifications for 5456 Aluminum Alloy**

Specification	Form
AMS-QQ-A-250/9	Sheet and plate
AMS-QQ-A-200/7	Extruded bar, rod, and shapes

The temper index for 5456 is as follows:

<u>Section</u>	<u>Temper</u>
3.5.5.1	O
3.5.5.2	H111
3.5.5.3	H112
3.5.5.4	H321

**3.5.5.1 O Temper** — Room-temperature tensile and compressive stress-strain and tangent-modulus curves for this temper are presented in Figures 3.5.5.1.6(a) and (b).

**3.5.5.2 H111 Temper** — Room-temperature tensile and compressive stress-strain and tangent-modulus curves for this temper are presented in Figure 3.5.5.2.6.

**3.5.5.3 H112 Temper** —

**3.5.5.4 H321 Temper** — Room-temperature tensile and compressive stress-strain and tangent-modulus curves for this temper are presented in Figure 3.5.5.4.6.

**Table 3.5.5.0(b). Design Mechanical and Physical Properties of 5456 Aluminum Alloy Sheet and Plate**

Specification .....	AMS-QQ-A-250/9										
Form .....	Sheet and plate										
Temper .....	O					H112		H321			
Thickness, in. ....	0.051-1.500	1.501-3.000	3.001-5.000	5.001-7.000	7.001-8.000	0.250-1.500	1.501-3.000	0.188-0.624	0.625-1.250	1.251-1.500	1.501-3.000
Basis .....	S	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:											
$F_{tu}$ , ksi:											
L .....	42	41	40	39	38	42	41	46	46	44	41
LT .....	42	...	...	...	...	...	...	46	45	43	...
$F_{ty}$ , ksi:											
L .....	19	18	17	16	15	19	18	33	33	31	29
LT .....	19	...	...	...	...	...	...	30	29	28	...
$F_{cy}$ , ksi:											
L .....	19	...	...	...	...	...	...	27	26	24	...
LT .....	19	...	...	...	...	...	...	33	31	29	...
$F_{su}$ , ksi .....	26	...	...	...	...	...	...	27	27	25	...
$F_{bru}$ , ksi:											
(e/D = 1.5) .....	63	...	...	...	...	...	...	67	67	64	...
(e/D = 2.0) .....	84	...	...	...	...	...	...	84	84	80	...
$F_{bry}$ , ksi:											
(e/D = 1.5) .....	32	...	...	...	...	...	...	46	46	43	...
(e/D = 2.0) .....	38	...	...	...	...	...	...	53	53	50	...
$e$ , percent:											
L .....	16	16	14	14	12	12	12	12	12	12	12
$E$ , $10^3$ ksi .....	10.2										
$E_c$ , $10^3$ ksi .....	10.4										
$G$ , $10^3$ ksi .....	3.85										
$\mu$ .....	0.33										
Physical Properties:											
$\omega$ , lb/in. <sup>3</sup> .....	0.096										
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)										
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] ..	...										
$\alpha$ , $10^{-6}$ in./in./°F .....	See Figure 3.5.5.0										


**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.5.5.0(c). Design Mechanical and Physical Properties of 5456 Aluminum Alloy Extrusion**

Specification .....	AMS-QQ-A-200/7		
Form .....	Extruded bar, rod, and shapes		
Temper .....	O	H111	H112
Cross-Sectional Area, in. <sup>2</sup> .....	≤32		
Thickness or Diameter, in. ....	≤5.000	≤5.000	≤5.000
Basis .....	S	S	S
Mechanical Properties:			
$F_{tu}$ , ksi:			
L .....	41	42	41
LT .....	...	...	41
$F_{ty}$ , ksi:			
L .....	19	26	19
LT .....	...	...	19
$F_{cy}$ , ksi:			
L .....	19	...	19
LT .....	...	...	19
$F_{su}$ , ksi .....	...	...	23
$F_{bru}$ , ksi:			
(e/D = 1.5) .....	...	...	57
(e/D = 2.0) .....	...	...	74
$F_{bry}$ , ksi:			
(e/D = 1.5) .....	...	...	34
(e/D = 2.0) .....	...	...	38
$e$ , percent:			
L .....	14	12	12
$E$ , 10 <sup>3</sup> ksi .....	10.2		
$E_c$ , 10 <sup>3</sup> ksi .....	10.4		
$G$ , 10 <sup>3</sup> ksi .....	3.85		
$\mu$ .....	0.33		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> .....	0.096		
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)		
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	...		
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	See Figure 3.5.5.0		




**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.5.0. Effect of temperature on the physical properties of 5456 aluminum alloy.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.5.5.1.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5456-0 aluminum alloy sheet and plate at room temperature.**




**Figure 3.5.5.1.6(b). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5456-0 aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.5.5.2.6. Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5456-H111 aluminum alloy extrusion at room temperature.**



**Figure 3.5.5.4.6. Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 5456-H321 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H****1 December 1998****3.6 6000 SERIES WROUGHT ALLOYS**

Alloys of the 6000 series contain magnesium and silicon as their principal alloying elements.

**3.6.1 6013 ALLOY**

**3.6.1.0 Comments and Properties** — 6013 is a Mg-Si-Cu-Mn alloy which is weldable. This alloy has 25 percent higher strength in the T6 temper than 6061-T6. It has improved toughness, fatigue strength, and stretch forming characteristics compared to 6061 with equivalent stress corrosion characteristics. Refer to 3.1.3.4 for comments regarding weldability of the alloy. Material specifications for 6013 are shown in Table 3.6.1.0(a). Room-temperature mechanical and physical properties are presented in Table 3.6.1.0(b).

**Table 3.6.1.0(a). Material Specifications for 6013 Aluminum Alloy**

Specification	Form
AMS 4347	Sheet (T4)
AMS 4216	Sheet (T6)

The temper index is as follows:

Section  
3.6.1.1

Temper  
T6

**3.6.1.1 T6 Temper** — Stress-strain and tangent-modulus curves are presented in Figures 3.6.1.1.6(a) and (b).


**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.6.1.0(b). Design Mechanical and Physical Properties of 6013 Aluminum Alloy Sheet**


Specification .....	AMS 4216 and AMS 4347		
Form .....	Sheet		
Temper .....	T6		
Thickness, in. ....	0.010-0.062	0.063-0.125	0.126-0.249
Basis .....	S	S	S
Mechanical Properties:			
$F_{tu}$ , ksi:			
L .....	52	52	52
LT .....	52	52	52
$F_{ty}$ , ksi:			
L .....	47	47	48
LT .....	46	46	46
$F_{cy}$ , ksi:			
L .....	48	48	48
LT .....	48	48	49
$F_{su}$ , ksi .....	32	32	32
$F_{bru}^a$ , ksi:			
(e/D=1.5) .....	85	85	85
(e/D=2.0) .....	111	111	111
$F_{bry}^a$ , ksi:			
(e/D=1.5) .....	66	69	71
(e/D=2.0) .....	76	80	82
$e$ , percent:			
LT .....	8	8	8
$E$ , $10^3$ ksi .....	9.9		
$E_c$ , $10^3$ ksi .....	10.1		
$G$ , $10^3$ ksi .....	3.8		
$\mu$ .....	0.33		
Physical Properties:			
$\omega$ , lb/in <sup>3</sup> .....	0.098		
$C$ , $K$ , and $\alpha$ .....	...		

a Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.6.1.1.6(a). Typical tensile stress-strain curves for 6013-T6 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H****1 December 1998**

**Figure 3.6.1.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 6013-T6 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H****1 December 1998****3.6.2 6061 ALLOY**

**3.6.2.0 Comments and Properties** — 6061 has been used in a wide range of applications, including cryogenic applications requiring high toughness. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

The properties of extrusions should be based upon the thickness at the time of quenching prior to machining. Selection of the mechanical properties based upon its final machined thickness may be unconservative; therefore, the thickness at the time of quenching to achieve properties is an important factor in the selection of the proper thickness column. For extrusions having sections with various thicknesses, consideration should be given to the properties as a function of thickness.

Material specifications for 6061 are presented in Table 3.6.2.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.6.2.0(b) through (g). The effect of temperature on the physical properties is shown in Figure 3.6.2.0.

The temper index for 6061 is as follows:

<u>Section</u>	<u>Temper</u>
3.6.2.1	T4, T42, T451, T4510, and T4511
3.6.2.2	T6, T62, T651, T652, T6510, and T6511

**3.6.2.1 T4, T42, T451, T4510, and T4511 Tempers** — For effect of temperature on modulus values, use Figure 3.6.2.2.4.

**3.6.2.2 T6, T62, T651, T652, T6510, and T6511 Tempers** — Figures 3.6.2.2.1(a) through (d), 3.6.2.2.4, and 3.6.2.2.5(a) and (b) present elevated temperature curves for various mechanical properties. Figures 3.6.2.2.6(a) through (k) contain tensile and compression stress-strain curves at room temperature and elevated temperatures, and tangent-modulus curves at room temperature for various products and tempers. Figures 3.6.2.2.6(l) through (o) present full-range tensile stress-strain curves at room temperature for various products and tempers. Figure 3.6.2.2.8 contains unnotched fatigue data for various wrought products at room temperature.



**MIL-HDBK-5H****1 December 1998****Table 3.6.2.0(a). Material Specifications for 6061 Aluminum Alloy**

Specification	Form
AMS 4025	Sheet and plate
AMS 4026	Sheet and plate
AMS 4027	Sheet and plate
AMS-QQ-A-250/11	Sheet and plate
AMS 4115	Bar and rod, rolled or cold-finished
AMS 4116	Bar and rod, cold-finished
AMS 4117	Bar and rod, rolled or cold-finished
AMS-QQ-A-225/8	Rolled bar, rod, and shapes
AMS 4160	Extrusion
AMS 4161	Extrusion
AMS 4172	Extrusion
AMS-QQ-A-200/8	Extruded rod, bar, shapes, and tubing
MIL-A-22771	Forging
AMS 4080	Tubing, seamless, drawn
AMS 4082	Tubing, seamless, drawn
WW-T-700/6	Seamless drawn tubing
MIL-P-25995	Pipe
AMS 4127	Forging
AMS 4248	Hand forging
QQ-A-367	Forging

**MIL-HDBK-5H****1 December 1998****Table 3.6.2.0(b<sub>1</sub>). Design Mechanical and Physical Properties of 6061 Aluminum Alloy Sheet**

Specification . . . . .	AMS 4026 and AMS-QQ-A-250/11		AMS-QQ-A- 250/11	AMS 4025, AMS 4027 and AMS-QQ-A-250/11	
	Sheet				
	T4		T42 <sup>a</sup>	T6 and T62 <sup>b</sup>	
	0.010-0.249		0.010-0.249	0.010-0.249	
	A	B	S	A	B
Mechanical Properties:					
$F_{tu}$ , ksi:					
L . . . . .	...	...	...	42	43
LT . . . . .	30	32	30	42	43
$F_{ty}$ , ksi:					
L . . . . .	...	...	...	36	38
LT . . . . .	16	18	14	35	37
$F_{cy}$ , ksi:					
L . . . . .	...	...	...	35	37
LT . . . . .	16	18	...	36	38
$F_{su}$ , ksi . . . . .	20	21	...	27	28
$F_{bru}$ , ksi:					
(e/D = 1.5) . . . . .	48	51	...	67	69
(e/D = 2.0) . . . . .	63	67	...	88	90
$F_{bry}$ , ksi:					
(e/D = 1.5) . . . . .	22	25	...	50	53
(e/D = 2.0) . . . . .	26	29	...	58	61
$e$ , percent (S-basis):					
LT . . . . .	c	...	c	c	...
$E$ , 10 <sup>3</sup> ksi . . . . .	9.9				
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.1				
$G$ , 10 <sup>3</sup> ksi . . . . .	3.8				
$\mu$ . . . . .	0.33				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.098				
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.6.2.0				

a Design allowables were based upon data obtained from testing samples of material, supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.

b Design allowables were based upon data obtained from testing T6 sheet and from testing samples of sheet, supplied in the O or F temper, which were heat treated to T62 temper to demonstrate response to heat treatment by suppliers. Properties obtained may be lower than those listed if the material has been formed or otherwise cold worked, particularly in the annealed temper, prior to solution heat treatment.

c See Table 3.6.2.0(b<sub>3</sub>).

**MIL-HDBK-5H****1 December 1998****Table 3.6.2.0(b<sub>2</sub>). Design Mechanical and Physical Properties of 6061 Aluminum Alloy Plate**

Specification . . . . .	AMS 4026 and AMS-QQ-A- 250/11				AMS-QQ-A- 250/11		AMS 4025, AMS 4027 and AMS-QQ-A-250/11					
	Plate											
	T451				T42 <sup>a</sup>		T651 and T62 <sup>b</sup>					
	0.250- 2.000		2.001- 3.000		0.250- 1.000	1.001- 3.000	0.250- 2.000	2.001- 3.000		3.001- 4.000	4.001- 6.000 <sup>d</sup>	
	A	B	A	B	S	S	A	B	A	B	S	S
Mechanical Properties:												
$F_{tu}$ , ksi:												
L . . . . .	...	...	...	...	...	...	42	43	...	...	...	...
LT . . . . .	30	32	30	32	30	30	42	43	42	43	42	40
$F_{ty}$ , ksi:												
L . . . . .	...	...	...	...	...	...	36	38	...	...	...	...
LT . . . . .	16	18	16	18	14	14	35	37	35	37	35	35
$F_{cy}$ , ksi:												
L . . . . .	...	...	...	...	...	...	35	37	...	...	...	...
LT . . . . .	16	18	...	...	...	...	36	38	...	...	...	...
$F_{su}$ , ksi . . . . .	20	21	...	...	...	...	27	28	...	...	...	...
$F_{bru}$ , ksi:												
(e/D = 1.5) . . . . .	48	51	...	...	...	...	67	69	...	...	...	...
(e/D = 2.0) . . . . .	63	67	...	...	...	...	88	90	...	...	...	...
$F_{bry}$ , ksi:												
(e/D = 1.5) . . . . .	22	25	...	...	...	...	50	53	...	...	...	...
(e/D = 2.0) . . . . .	26	29	...	...	...	...	58	61	...	...	...	...
$e$ , percent (S-basis):												
LT . . . . .	<sup>c</sup>	...	16	...	18	16	<sup>c</sup>	...	6	...	6	6
$E$ , 10 <sup>3</sup> ksi . . . . .	9.9											
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.1											
$G$ , 10 <sup>3</sup> ksi . . . . .	3.8											
$\mu$ . . . . .	0.33											
Physical Properties:												
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.098											
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.6.2.0											

a Design allowables were based upon data obtained from testing samples of material, supplied in the O temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.

b Design allowables were based upon data obtained from testing T651 plate and from testing samples of plate, supplied in the O temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained may be lower than those listed if the material has been formed or otherwise cold worked, particularly in the annealed temper, prior to solution heat treatment.

c See Table 3.6.2.0(b<sub>3</sub>).

d Properties for this thickness apply only to T651 temper.

**MIL-HDBK-5H****1 December 1998****Table 3.6.2.0(b<sub>3</sub>). Minimum Elongation Values for 6061 Aluminum Alloy Sheet and Plate**

Temper and Product	Thickness, inch	Elongation (LT), percent
T4 or T42 sheet . . . . .	0.010-0.020	14
	0.021-0.249	16
T451 plate . . . . .	0.250-1.000	18
	1.001-2.000	16
T6 or T62 sheet . . . . .	0.010-0.020	8
	0.021-0.249	10
T651 or T62 plate . . . . .	0.250-0.499	10
	0.500-1.000	9
	1.001-2.000	8

**MIL-HDBK-5H****1 December 1998****Table 3.6.2.0(c<sub>1</sub>). Design Mechanical and Physical Properties of 6061 Aluminum Alloy Tube and Pipe**

Specification . . . . .	WW-T-700/6		AMS 4080, AMS 4082, and WW-T-700/6	MIL-P-25995	
Form . . . . .	Drawn tube			Pipe	
Temper . . . . .	T4	T42 <sup>a</sup>	T6 <sup>b</sup> and T62	T6	
Wall Thickness, in. . .	0.025-0.500	0.025-0.500	0.025-0.500	0.049-0.154	0.065-0.687
Outside Diameter, in.	...			<1.000	1.000-12.000
Basis . . . . .	S	S	S	S	S
Mechanical Properties:					
$F_{tu}$ , ksi:					
L . . . . .	30	30	42	42	38
$F_{ty}$ , ksi:					
L . . . . .	16	14	35	35	35
$F_{cy}$ , ksi:					
L . . . . .	14	...	34	34	34
$F_{su}$ , ksi . . . . .	20	...	27	27	24
$F_{bru}$ , ksi:					
( $e/D = 1.5$ ) . . . . .	48	...	67	67	61
( $e/D = 2.0$ ) . . . . .	63	...	88	88	80
$F_{bry}$ , ksi:					
( $e/D = 1.5$ ) . . . . .	22	...	49	49	49
( $e/D = 2.0$ ) . . . . .	26	...	56	56	56
$e$ , percent:					
L . . . . .	c	c	c	12	10 <sup>d</sup>
$E$ , 10 <sup>3</sup> ksi . . . . .	9.9				
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.1				
$G$ , 10 <sup>3</sup> ksi . . . . .	3.8				
$\mu$ . . . . .	0.33				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.098				
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.6.2.0				

a Design allowables were based upon data obtained from testing samples of material, supplied in the O temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.

b Design allowables were based upon data obtained from testing T6 temper tube and from testing samples of tube, supplied in the O temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user may be lower than those listed if the material has been formed or otherwise cold worked, particularly in the annealed temper, prior to solution heat treatment.

c See Table 3.6.2.0(c<sub>2</sub>).

d For wall thickness  $\leq 0.249$  inch,  $e = 8\%$ .

**MIL-HDBK-5H****1 December 1998****Table 3.6.2.0(c<sub>2</sub>). Minimum Elongation Values for 6061 Aluminum Alloy Tubing**

Temper	Wall Thickness, inch	Elongation (LT), percent	
		Full-Section Specimen	Cut-Out Specimen
T4 or T42 . . . . .	0.025-0.049	16	14
	0.050-0.259	18	16
	0.260-0.500	20	18
T6 or T62 . . . . .	0.025-0.049	10	8
	0.050-0.259	12	10
	0.260-0.500	14	12

**MIL-HDBK-5H****1 December 1998****Table 3.6.2.0(d). Design Mechanical and Physical Properties of 6061 Aluminum Alloy Rolled, Drawn, or Cold-Finished Bar, Rod, and Shapes**

Specification .....	AMS 4116 & AMS-QQ-A- 225/8	AMS 4128 & AMS-QQ-A- 225/8	AMS-QQ- A-225/8	AMS 4117 & AMS-QQ-A- 225/8	AMS 4128 & AMS-QQ-A- 225/8	AMS 4115, AMS 4116, & AMS-QQ-A-225/8
Form .....	Rolled, drawn, or cold-finished rod and special shapes					
Condition .....	T4	T451	T42 <sup>a</sup>	T6	T651	T62 <sup>a</sup>
Cross-Sectional Area, in. <sup>2</sup>	≤50					
Thickness, in. ....	≤8.000	0.500-8.000	≤8.000	≤8.000	0.500-8.000	≤8.000
Basis .....	S	S	S	S	S	S
Mechanical Properties:						
$F_{tu}$ , ksi:						
L .....	30	30	30	42	42	42
$F_{ty}$ , ksi:						
L .....	16	16	14	35	35	35
$F_{cy}$ , ksi:						
L .....	14	14	...	34	34	...
$F_{su}$ , ksi .....	20	20	...	27	27	...
$F_{bru}$ , ksi:						
(e/D = 1.5) .....	48	48	...	67	67	...
(e/D = 2.0) .....	63	63	...	88	88	...
$F_{bry}$ , ksi:						
(e/D = 1.5) .....	22	22	...	49	49	...
(e/D = 2.0) .....	26	26	...	56	56	...
$e$ , percent:						
L .....	18	18	18	10	10	10
$E$ , 10 <sup>3</sup> ksi .....	9.9					
$E_c$ , 10 <sup>3</sup> ksi .....	10.1					
$G$ , 10 <sup>3</sup> ksi .....	3.8					
$\mu$ .....	0.33					
Physical Properties:						
$\omega$ , lb/in. <sup>3</sup> .....	0.098					
$C$ , $K$ , and $\alpha$ .....	See Figure 3.6.2.0					

a Design allowables were based upon data obtained from testing samples of material, supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.6.2.0(e). Design Mechanical and Physical Properties of 6061 Aluminum Alloy Die Forging**

Specification .....	AMS 4127, MIL-A-22771, and QQ-A-367
Form .....	Die forging
Temper .....	T6 and T652
Thickness, in. ....	$\leq 4.000^a$
Basis .....	S
Mechanical Properties:	
$F_{tu}$ , ksi:	
L .....	38
T <sup>b</sup> .....	38
$F_{ty}$ , ksi:	
L .....	35
T <sup>b</sup> .....	35
$F_{cy}$ , ksi:	
L .....	36
T <sup>b</sup> .....	36
$F_{su}$ , ksi .....	25
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	61
(e/D = 2.0) .....	76
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	54
(e/D = 2.0) .....	61
$e$ , percent:	
L .....	7
T <sup>b</sup> .....	5
$E$ , $10^3$ ksi .....	9.9
$E_c$ , $10^3$ ksi .....	10.1
$G$ , $10^3$ ksi .....	3.8
$\mu$ .....	0.33
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.098
$C$ , $K$ , and $\alpha$ .....	See Figure 3.6.2.0

a Thickness at the time of heat treatment. When die forgings are machined before heat treatment, the mechanical properties are applicable provided the as-forged thickness is not greater than twice the thickness at the time of heat treatment.

b T indicates any grain direction not within  $\pm 15^\circ$  of being parallel to the forging flow lines.  $F_{cy}(T)$  values are based upon short transverse (ST) test data.



**MIL-HDBK-5H****1 December 1998****Table 3.6.2.0(f). Design Mechanical and Physical Properties of 6061 Aluminum Alloy Hand Forging**

Specification . . . . .	AMS 4127, AMS 4248, MIL-A-22771, and QQ-A-367		
Form . . . . .	Hand forging		
Temper . . . . .	T6 <sup>a</sup> and T652		
Cross-Sectional Area, in. <sup>2</sup> . . . . .	≤256		
Thickness, in. . . . .	≤2.000	2.001-4.000	4.001-8.000
Basis . . . . .	S	S	S
Mechanical Properties:			
$F_{tu}$ , ksi:			
L . . . . .	38	38	37
LT . . . . .	38	38	37
ST . . . . .	...	37	35
$F_{ty}$ , ksi:			
L . . . . .	35	35	34
LT . . . . .	35	35	34
ST . . . . .	...	33	32
$F_{cy}$ , ksi:			
L . . . . .	36	36	35
LT . . . . .	36	36	35
ST . . . . .	...	34	33
$F_{su}$ , ksi . . . . .	25	25	24
$F_{bru}$ , ksi:			
(e/D = 1.5) . . . . .	61	61	59
(e/D = 2.0) . . . . .	76	76	74
$F_{bry}$ , ksi:			
(e/D = 1.5) . . . . .	54	54	53
(e/D = 2.0) . . . . .	61	61	59
$e$ , percent:			
L . . . . .	10	10	8
LT . . . . .	8	8	6
ST . . . . .	...	5	4
$E$ , 10 <sup>3</sup> ksi . . . . .	9.9		
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.1		
$G$ , 10 <sup>3</sup> ksi . . . . .	3.8		
$\mu$ . . . . .	0.33		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.098		
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 3.6.2.0		

a When hand forgings are machined before heat treatment, the section thickness at time of heat treatment shall determine the minimum mechanical properties as long as the original (as-forged) thickness does not exceed the maximum thickness for the alloy as shown in the table.

**MIL-HDBK-5H****1 December 1998****Table 3.6.2.0(g). Design Mechanical and Physical Properties of 6061 Aluminum Alloy Extruded Rod, Bar, and Shapes**

Specification . . . . .	AMS 4161, AMS 4172, & AMS-QQ-A- 200/8	AMS-QQ-A- 200/8	AMS 4160 & AMS-QQ-A- 200/8	AMS-QQ-A-200/8			
Form . . . . .	Extruded rod, bar, and shapes						
Temper . . . . .	T4, T4510, and T4511	T42 <sup>a</sup>	T62 <sup>a</sup>	T6, T6510, and T6511			
Cross-sectional area, in. <sup>2</sup>	...	...	...	≤32			
Thickness, <sup>d</sup> in. . . . .	≤3.000	All	All	≤1.000		1.001- 6.500	
Basis . . . . .	S	S	S	A	B	A	B
Mechanical Properties:							
<i>F<sub>tu</sub></i> , ksi:							
L . . . . .	26	26	38	38	41	38	41
LT . . . . .	...	...	...	37	40	33	35
<i>F<sub>ty</sub></i> , ksi:							
L . . . . .	16	12	35	35	38	35	38
LT . . . . .	...	...	...	33	36	28	31
<i>F<sub>cy</sub></i> , ksi:							
L . . . . .	14	...	...	34	37	34	37
LT . . . . .	...	...	...	35	38	30	33
<i>F<sub>su</sub></i> , ksi . . . . .	16	...	...	26	28	19	21
<i>F<sub>bru</sub></i> <sup>b</sup> , ksi:							
(e/D = 1.5) . . . . .	42	...	...	64	69	52	57
(e/D = 2.0) . . . . .	55	...	...	82	88	69	74
<i>F<sub>bry</sub></i> <sup>b</sup> , ksi:							
(e/D = 1.5) . . . . .	22	...	...	54	58	42	46
(e/D = 2.0) . . . . .	26	...	...	60	65	50	55
<i>e</i> , percent (S-basis):							
L . . . . .	16	16	10 <sup>c</sup>	10 <sup>c</sup>	...	10	...
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	9.9						
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	10.1						
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	3.8						
<i>μ</i> . . . . .	0.33						
Physical Properties:							
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.098						
<i>C</i> , <i>K</i> , and <i>α</i> . . . . .	See Figure 3.6.2.0						

a Design allowables were based upon data obtained from testing samples of material, supplied in the O to F temper which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user, however, may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to solution heat treatment.


b Bearing values are "dry pin" values per Section 1.4.7.1.

c For thicknesses ≤0.249 inch,  $e = 8\%$ .

d The mechanical properties are to be based upon the thickness at the time of quench.


## MIL-HDBK-5H

1 December 1998




**Figure 3.6.2.0. Effect of temperature on the physical properties of 6061 aluminum alloy.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.6.2.2.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 6061-T6 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.6.2.2.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 6061-T6 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.6.2.2.1(c). Effect of exposure at elevated temperatures on the room-temperature tensile ultimate strength ( $F_{tu}$ ) of 6061-T6 aluminum alloy (all products).**




**Figure 3.6.2.2.1(d). Effect of exposure at elevated temperatures on the room-temperature tensile yield strength ( $F_{ty}$ ) of 6061-T6 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.6.2.2.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of 6061 aluminum alloy.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.6.2.2.5(a). Effect of temperature on the elongation of 6061-T6 aluminum alloy (all products).**




**Figure 3.6.2.2.5(b). Effect of exposure at elevated temperatures on the elongation of 6061-T6 aluminum alloy (all products).**




**MIL-HDBK-5H****1 December 1998**


**Figure 3.6.2.2.6(a). Typical tensile stress-strain curves for 6061-T6 aluminum alloy sheet at room temperature.**



**Figure 3.6.2.2.6(b). Typical tensile stress-strain curve for 6061-T6 aluminum alloy sheet at 200°F.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.6.2.2.6(c). Typical tensile stress-strain curves for 6061-T6 aluminum alloy sheet at 300°F.**




**Figure 3.6.2.2.6(d). Typical tensile stress-strain curves for 6061-T6 aluminum alloy sheet at 400°F.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.6.2.2.6(e). Typical tensile stress-strain curves for 6061-T6 aluminum alloy sheet at 500°F.**




**Figure 3.6.2.2.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for 6061-T6 aluminum alloy sheet at room temperature.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.6.2.2.6(g). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 6061-T6 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.6.2.2.6(h). Typical tensile stress-strain curves for 6061-T6 aluminum alloy extrusion at room temperature.**




**Figure 3.6.2.2.6(i). Typical compressive stress-strain and compressive tangent-modulus curves for 6061-T6 aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.6.2.2.6(j). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 6061-T651X aluminum alloy extrusion at room temperature.**




**Figure 3.6.2.2.6(k). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 6061-T651X aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.6.2.2.6(l). Typical tensile stress-strain (full range) for 6061-T6 aluminum alloy sheet at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.6.2.2.6(m). Typical tensile stress-strain curves (full range) for 6061-T62 aluminum alloy extrusion at room temperature.**




**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.6.2.2.6(n). Typical tensile stress-strain curves (full range) for 6061-T651X aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.6.2.2.6(o). Typical tensile stress-strain curves (full range) for 6061-T651X aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H****1 December 1998**

**Figure 3.6.2.2.8. Best-fit S/N curves for unnotched 6061-T6 aluminum alloy, various wrought products, longitudinal direction.**

Correlative Information for Figure 3.6.2.2.8

Product Form: Drawn rod, 3/4-inch diameter  
Rolled bar, 1 x 7-1/2 inch

Properties:      TUS, ksi    TYS, ksi    Temp., °F  
                         45            40            RT

Specimen Details: Unnotched  
0.200-inch net diameter

Surface Condition: Not specified

Reference:        3.2.1.1.8(a)

Test Parameters:

Loading - Axial  
Frequency - 2000 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 20.68 - 9.84 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.63}$   
Standard Error of Estimate = 0.48  
Standard Deviation in Life = 1.18  
 $R^2 = 83\%$

Sample Size = 55

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998****3.6.3 6151 ALLOY**

**3.6.3.0 Comments and Properties** — 6151 is an Al-Mg-Si alloy whose use has been restricted primarily to die forgings. It provides higher strengths than attainable with 6061, and has high resistance to corrosion. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

Material specifications for 6151 aluminum alloy are presented in Table 3.6.3.0(a). Room-temperature mechanical and physical properties are shown in Table 3.6.3.0(b). The effect of temperature on thermal expansion is shown in Figure 3.6.3.0.

**Table 3.6.3.0(a). Material Specifications for 6151 Aluminum Alloy**

Specification	Form
AMS 4125 MIL-A-22771	Die forging Forging

The temper index for 6151 is as follows:

<u>Section</u>	<u>Temper</u>
3.6.3.1	T6

**3.6.3.1 T6 Temper** — Elevated temperature modulus data from Figure 3.6.2.2.4 may be used for this alloy.


**MIL-HDBK-5H****1 December 1998****Table 3.6.3.0(b). Design Mechanical and Physical Properties of 6151 Aluminum Alloy Die Forging**

Specification .....	AMS 4125 and MIL-A-22771
Form .....	Die forging
Temper .....	T6
Thickness <sup>b</sup> , in. ....	≤4.000
Basis .....	S
<b>Mechanical Properties:</b>	
$F_{tu}$ , ksi:	
L .....	44
T <sup>a</sup> .....	44
$F_{ty}$ , ksi:	
L .....	37
T <sup>a</sup> .....	37
$F_{cy}$ , ksi:	
L .....	39
T <sup>a</sup> .....	35
$F_{su}$ , ksi .....	28
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$e$ , percent:	
L .....	10
T <sup>a</sup> .....	6
$E$ , 10 <sup>3</sup> ksi .....	10.1
$E_c$ , 10 <sup>3</sup> ksi .....	10.3
$G$ , 10 <sup>3</sup> ksi .....	3.85
$\mu$ .....	0.33
<b>Physical Properties:</b>	
$\omega$ , lb/in. <sup>3</sup> .....	0.098
$C$ , Btu/(lb)(°F) .....	0.23 (at 212 °F)
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	100 (at 77 °F)
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	See Figure 3.6.3.0

a T indicates any grain direction not within  $\pm 15^\circ$  of being parallel to the forging flow lines.

b Thickness at the time of heat treatment. When die forgings are machined before heat treatment, the mechanical properties are applicable provided the as-forged thickness is not greater than twice the thickness at the time of heat treatment.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.6.3.0. Effect of temperature on the thermal expansion of 6151 aluminum alloy.**

**MIL-HDBK-5H****1 December 1998****3.7 7000 SERIES WROUGHT ALLOYS**

The 7000 series of wrought alloys contain zinc as the principal alloying element and magnesium and copper as other major elements. They are available in a wide variety of product forms. They are strengthened principally by solution heat treatment and precipitation hardening, and are among the highest strength aluminum alloys.

The T6-type tempers of these alloys are susceptible to stress-corrosion cracking under certain conditions while the T7-type tempers are more resistant; these alloys should be considered in the light of the corrosion resistance discussed in Sections 3.1.2.3 and 3.1.3.

**3.7.1 7010 ALLOY**

**3.7.1.0 Comments and Properties** — 7010 is an Al-Zn-Mg-Cu-Zr alloy developed to have a combination of high strength, high resistance to stress-corrosion cracking, and good fracture toughness, particularly in thick sections. The use of zirconium in lieu of chromium provides a low sensitivity to quench, which results in high strength in thick sections. The alloy is available only in plate. Plate, greater than 2½ inches in thickness in the T7451 temper, has static strength equal to or greater than 7075-T651 plate with greater toughness.

Plate in the T7451 temper has a stress-corrosion resistance higher than 7075-T7651. The T73-type temper provides the highest resistance to stress-corrosion for this alloy. The T76-type temper provides for good exfoliation resistance and higher stress-corrosion resistance than T6-type tempers of 7075 and 7178. The T74 type temper provides stress-corrosion and strength characteristics intermediate to those of T76 and T73. Refer to Section 3.1.2.3 for information regarding the resistance of the alloy to stress-corrosion cracking.

Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

Material specifications for 7010 are shown in Table 3.7.1.0(a). Room-temperature mechanical properties are shown in Tables 3.7.1.0(b<sub>1</sub>) and (b<sub>2</sub>).

**Table 3.7.1.0(a). Material Specifications for 7010 Aluminum Alloy**

Specification	Form
AMS 4205	Plate
AMS 4204	Plate

The temper index for 7050 is as follows:

<u>Section</u>	<u>Temper</u>
3.7.1.1	T7451
3.7.1.2	T7651

**3.7.1.1 T7451 Temper** — Elevated temperature curves for plate are presented in Figure 3.7.1.1.1. Figures 3.7.1.1.6(a) through (d) present stress-strain and tangent-modulus curves for plate.

**3.7.1.2 T7651 Temper** — Figures 3.7.1.2.6(a) through (d) present stress-strain and tangent-modulus curves for plate.

**MIL-HDBK-5H****1 December 1998****Table 3.7.1.0(b<sub>1</sub>). Design Mechanical and Physical Properties of 7010 Aluminum Alloy Plate**

Specification .....	AMS 4205									
Form .....	Plate									
Temper .....	T7451									
Thickness, in. ....	0.250- 1.000	1.001- 2.000	2.001- 3.000		3.001- 4.000		4.001- 5.000		5.001- 6.000	
Basis .....	S	S	A	B	A	B	A	B	A	B
Mechanical Properties:										
$F_{tu}$ , ksi:										
L .....	71	71	70	72	70	71	68	71	68 <sup>b</sup>	70
LT .....	72	72	71	72	70	72	69 <sup>b</sup>	71	67 <sup>b</sup>	71
ST .....	...	...	66	68	66	68	65 <sup>b</sup>	67	63 <sup>b</sup>	67
$F_{ty}$ , ksi:										
L .....	62	62	60	62	60	62	59	61	57 <sup>b</sup>	61
LT .....	62	62	60	62	59	61	58	60	57 <sup>b</sup>	60
ST .....	...	...	55	57	54	56	53	55	52	54
$F_{cy}$ , ksi:										
L .....	61	61	59	61	58	60	57	59	56	59
LT .....	63	63	62	64	61	63	60	62	59	63
ST .....	...	...	61	63	60	62	59	61	58	61
$F_{su}$ , ksi .....	41	41	42	42	42	43	42	43	41	43
$F_{bru}^a$ , ksi:										
(e/D = 1.5) .....	100	101	101	102	100	103	100	103	97	103
(e/D = 2.0) .....	127	129	130	132	130	134	129	133	126	133
$F_{bry}^a$ , ksi:										
(e/D = 1.5) .....	81	82	81	84	81	84	81	84	80	84
(e/D = 2.0) .....	94	97	97	100	98	101	98	101	97	102
$e$ , percent (S-basis):										
L .....	9	9	9	...	9	...	9	...	8	...
LT .....	6	6	6	...	6	...	5	...	5	...
ST .....	...	...	2.5	...	2	...	2	...	2	...
$E$ , 10 <sup>3</sup> ksi .....	10.2									
$E_c$ , 10 <sup>3</sup> ksi .....	10.6									
$G$ , 10 <sup>3</sup> ksi .....	3.9									
$\mu$ .....	0.33									
Physical Properties:										
$\omega$ , lb/in. <sup>3</sup> .....	0.102									
$C$ , Btu/(lb)(°F) .....	0.21 (at 214°F)									
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] ....	95 (at 99°F)									
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	13.0 (68-212°F)									

a See Table 3.1.2.1.1. Bearing values are "dry pin" values per Section 1.4.7.1.

b S-basis values. The rounded  $T_{99}$  values are as follows: for 4.001-5.000-inch thickness,  $F_{tu}(L) = 69$ ,  $F_{tu}(LT) = 70$ , and  $F_{tu}(ST) = 66$ ; for 5.001-6.000-inch thickness,  $F_{tu}(LT) = 69$ ,  $F_{tu}(ST) = 65$ ,  $F_{ty}(L) = 59$ , and  $F_{ty}(LT) = 58$ .




**MIL-HDBK-5H****1 December 1998****Table 3.7.1.0(b<sub>2</sub>). Design Mechanical Properties of 7010 Aluminum Alloy Plate—Continued**

Specification . . . . .	AMS 4204						
Form . . . . .	Plate						
Temper . . . . .	T7651						
Thickness, in. . . . .	0.250- 1.000	1.001- 2.000	2.001- 2.500	2.501- 3.000	3.001- 4.000	4.001- 5.000	5.001- 5.500
Basis . . . . .	S	S	S	S	S	S	S
Mechanical Properties:							
$F_{tu}$ , ksi:							
L . . . . .	76	76	75	73	72	72	71
LT . . . . .	76	76	75	74	73	72	72
ST . . . . .	...	...	71	70	69	68	66
$F_{ty}$ , ksi:							
L . . . . .	66	66	65	64	64	63	62
LT . . . . .	66	66	65	64	63	62	61
ST . . . . .	...	...	59	58	56	55	53
$F_{cy}$ , ksi:							
L . . . . .	65	65	64	63	62	61	60
LT . . . . .	67	68	67	67	66	65	64
ST . . . . .	...	...	68	67	65	64	62
$F_{su}$ , ksi . . . . .	42	44	44	44	44	45	46
$F_{bru}^a$ , ksi:							
(e/D = 1.5) . . . . .	105	106	106	105	105	105	105
(e/D = 2.0) . . . . .	135	137	137	136	135	134	134
$F_{bry}^a$ , ksi:							
(e/D = 1.5) . . . . .	85	86	87	87	86	86	86
(e/D = 2.0) . . . . .	103	104	103	102	101	100	99
$e$ , percent:							
L . . . . .	8	8	8	7	7	7	6
LT . . . . .	6	6	6	5	5	5	4
ST . . . . .	...	...	2.5	2.5	2	2	2
$E$ , 10 <sup>3</sup> ksi . . . . .	10.2						
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.6						
$G$ , 10 <sup>3</sup> ksi . . . . .	3.9						
$\mu$ . . . . .	0.33						
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.102						
$C$ , Btu/(lb)(°F) . . . . .	0.21 (at 214 °F)						
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] . . . . .	95 (at 104 °F)						
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . . . .	12.9 (68 to 212 °F)						


a See Table 3.1.2.1.1. Bearing values are “dry pin” values per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.1.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of 7010-T7451 aluminum alloy plate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.1.1.6(a). Typical tensile stress-strain curves for 7010-T7451 plate at room temperature.**




**Figure 3.7.1.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 7010-T7451 plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.1.1.6(c). Typical tensile stress-strain curves for 7010-T7451 aluminum alloy plate at room temperature.**




**Figure 3.7.1.1.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for 7010-T7451 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.1.2.6(a). Typical tensile stress-strain curves for 7010-T7651 plate at room temperature.**




**Figure 3.7.1.2.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 7010-T7651 plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.1.2.6(c). Typical tensile stress-strain curves for 7010-T7651 aluminum alloy plate at room temperature.**



**Figure 3.7.1.2.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for 7010-T7651 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H****1 December 1998****3.7.2 7049/7149 ALLOY**

**3.7.2.0 Comments and Properties** — Alloy 7049/7149 is available in the form of die forging, hand forging, plate, and extrusion. Alloy 7149 contains lower residual iron and silicon content than 7049. The T73XX temper provides good static strength with high resistance to stress-corrosion cracking. The fatigue strength of the T73XX temper is about equal to that of 7075-T6, while the toughness is somewhat higher. Refer to Section 3.1.2.3 for comments regarding the resistance of the alloys to stress-corrosion cracking, and to Section 3.1.3.4 for comments regarding the weldability of the alloys.

The properties of extrusions should be based upon the thickness at the time of quenching prior to machining. Selection of the mechanical properties based upon its final machined thickness may be unconservative; therefore, the thickness at the time of quenching to achieve properties is an important factor in the selection of the proper thickness column. For extrusions having sections with various thicknesses, consideration should be given to the properties as a function of thickness.

Material specifications for 7049/7149 aluminum alloy are presented in Table 3.7.2.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.7.2.0(b) through (e).

**Table 3.7.2.0(a). Material Specifications for 7049/7149 Aluminum Alloy**

Specification	Form
QQ-A-367 (7049)	Forging
AMS 4111 (7049)	Forging
AMS 4320 (7149)	Forging
AMS 4157 (7049)	Extrusion
MIL-A-22771	Forging
AMS 4200 (7049)	Plate
AMS 4343 (7149)	Extrusion

The temper index for 7049/7149 is as follows:

<u>Section</u>	<u>Temper</u>
3.7.2.1	T73 and T73511

**3.7.2.1 T73 and T73511 Tempers** — Figure 3.7.2.1.1 presents elevated temperature curves for various products. Figures 3.7.2.1.6(a) through (g) present tensile and compressive stress-strain and tangent-modulus curves. Fatigue data for 7049-T73 die and hand forgings are shown in Figures 3.7.2.1.8(a) through (g).

**MIL-HDBK-5H****1 December 1998****Table 3.7.2.0(b). Design Mechanical and Physical Properties of 7049 Aluminum Alloy Plate**

Specification . . . . .	AMS 4200							
Form . . . . .	Plate							
Temper . . . . .	T7351							
Thickness, in. . . . .	0.750- 1.000	1.001- 1.500	1.501- 2.000	2.001- 2.500	2.501- 3.000	3.001- 4.000	4.001- 4.500	4.501- 5.000
Basis . . . . .	S	S	S	S	S	S	S	S
Mechanical Properties:								
$F_{tu}$ , ksi:								
L . . . . .	...	...	72	72	71	70	68	68
LT . . . . .	74	73	73	73	72	70	68	68
ST . . . . .	...	...	69	69	68	65	63	63
$F_{ty}$ , ksi:								
L . . . . .	...	...	64	63	62	60	58	58
LT . . . . .	65	64	64	63	62	60	58	58
ST . . . . .	...	...	59	58	57	56	54	54
$F_{cy}$ , ksi:								
L . . . . .	...	...	64	63	62	60	58	...
LT . . . . .	...	...	69	68	67	64	62	...
ST . . . . .	...	...	69	68	67	64	62	...
$F_{su}$ , ksi . . . . .	...	...	41	41	41	39	38	...
$F_{bru}^a$ , ksi:								
(e/D = 1.5) . . . . .	...	...	...	114	112	109	106	...
(e/D = 2.0) . . . . .	...	...	...	146	144	140	136	...
$F_{bry}^a$ , ksi:								
(e/D = 1.5) . . . . .	...	...	...	91	89	86	83	...
(e/D = 2.0) . . . . .	...	...	...	106	104	101	97	...
$e$ , percent:								
L . . . . .	...	...	...	...	...	6	6	5
LT . . . . .	8	8	7	6	6	5	5	5
ST . . . . .	...	...	...	...	...	2	2	2
$E$ , $10^3$ ksi . . . . .	10.1							
$E_c$ , $10^3$ ksi . . . . .	10.4							
$G$ , $10^3$ ksi . . . . .	3.9							
$\mu$ . . . . .	0.33							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.103							
$C$ , Btu/(lb)(°F) . . .	0.23 (at 212°F)							
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	89 (at 77°F)							
$\alpha$ , $10^{-6}$ in./in./°F . . .	13.0 (RT to 212°F)							

a Bearing values are “dry pin” values per Section 1.4.7.1. See Table 3.1.2.1.1.



**MIL-HDBK-5H****1 December 1998****Table 3.7.2.0(c). Design Mechanical and Physical Properties of 7049/7149 Aluminum Alloy Die Forging**

Specification . . . . .	QQ-A-367, AMS 4111, AMS 4320, and MIL-A-22771									
Form . . . . .	Die forging									
Temper . . . . .	T73 <sup>a</sup>									
Thickness <sup>b</sup> , in. . . . .	≤1.000		1.001-2.000		2.001-3.000		3.001-4.000		4.001-5.000	
Basis . . . . .	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:										
$F_{tu}$ , ksi:										
L . . . . .	71	74	70	73	69	72	68	71	67	70
T <sup>c</sup> . . . . .	71 <sup>e</sup>	...	70 <sup>e</sup>	...	70 <sup>e</sup>	...	70 <sup>e</sup>	...	68 <sup>e</sup>	...
$F_{ty}$ , ksi:										
L . . . . .	60	64	59	63	58	61	57	60	55	59
T <sup>c</sup> . . . . .	61 <sup>e</sup>	...	60 <sup>e</sup>	...	60 <sup>e</sup>	...	60 <sup>e</sup>	...	58 <sup>e</sup>	...
$F_{cy}$ , ksi:										
L . . . . .	62	66	61	65	60	63	59	62	57	61
ST . . . . .	56	60	55	59	54	57	53	56	51	55
$F_{su}$ , ksi . . . . .	40	41	39	41	39	40	38	40	37	39
$F_{bru}^d$ , ksi:										
(e/D = 1.5) . . . . .	100	105	99	103	98	102	96	100	95	99
(e/D = 2.0) . . . . .	132	138	130	136	128	134	126	132	125	130
$F_{bry}^d$ , ksi:										
(e/D = 1.5) . . . . .	76	82	75	80	74	78	73	76	70	75
(e/D = 2.0) . . . . .	93	99	91	97	90	94	88	93	85	91
e, percent (S-basis):										
L . . . . .	7	...	7	...	7	...	7	...	7	...
T <sup>c</sup> . . . . .	3	...	3	...	3	...	2	...	2	...
$E$ , 10 <sup>3</sup> ksi . . . . .	10.2									
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.7									
$G$ , 10 <sup>3</sup> ksi . . . . .	3.9									
$\mu$ . . . . .	0.33									
Physical Properties:										
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.103									
$C$ , Btu/(lb)(°F) . . .	0.25 (at 212°F)									
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	89 (at 77°F)									
$\alpha$ , 10 <sup>-6</sup> in./in./°F . .	13.0 (RT to 212°F)									

a Design values were based upon data obtained from testing T73 die forgings, heat treated by suppliers and supplied in T73 temper.

b Thickness at the time of heat treatment. When die forgings are machined before heat treatment, the mechanical properties are applicable provided the as-forged thickness is not greater than twice the thickness at the time of heat treatment.

c T indicates any grain direction not within ±15° of being parallel to the forging flow lines.  $F_{cy}(T)$  values are based upon short transverse (ST) test data.

d Bearing values are "dry pin" values per Section 1.4.7.1.

e Specification value. T tensile properties are presented on an S-basis only.

**MIL-HDBK-5H****1 December 1998****Table 3.7.2.0(d). Design Mechanical and Physical Properties of 7049/7149 Aluminum Alloy Hand Forging**

Specification .....	QQ-A-367, AMS 4111, AMS 4320, and MIL-A-22771		
Form .....	Hand forging		
Temper .....	T73		
Thickness <sup>a</sup> , in. ....	2.001-3.000	3.001-4.000	4.001-5.000
Basis .....	S	S	S
Mechanical Properties:			
$F_{tu}$ , ksi:			
L .....	71	69	67
LT .....	71	69	67
ST .....	69	67	66
$F_{ty}$ , ksi:			
L .....	61	59	56
LT .....	59	57	56
ST .....	58	56	55
$F_{cy}$ , ksi:			
L .....	60	58	57
LT .....	61	59	57
ST .....	61	59	58
$F_{su}$ , ksi:			
L .....	42	41	39
LT .....	41	39	38
ST .....	41	40	39
$F_{bru}^b$ , ksi:			
(e/D = 1.5) .....	102	100	97
(e/D = 2.0) .....	134	130	126
$F_{bry}^b$ , ksi:			
(e/D = 1.5) .....	81	79	77
(e/D = 2.0) .....	96	92	91
$e$ , percent:			
L .....	9	8	7
LT .....	4	3	3
ST .....	3	2	2
$E$ , $10^3$ ksi .....	10.2		
$E_c$ , $10^3$ ksi .....	10.6		
$G$ , $10^3$ ksi .....	3.9		
$\mu$ .....	0.33		
Physical Properties:			
$\omega$ , lb./in. <sup>3</sup> .....	0.103		
$C$ , Btu/(lb)(°F) .....	0.23 (at 212 °F)		
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	89 (at 77 °F)		
$\alpha$ , $10^{-6}$ in./in./°F .....	13.0 (RT to 212 °F)		

a When hand forgings are machined before heat treatment, section thickness at time of heat treatment shall determine minimum mechanical properties as long as original (as-forged) thickness does not exceed maximum thickness for the alloy as shown in the table. The maximum cross-section area of hand forgings is 256 sq. in.

b Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 3.7.2.0(e). Design Mechanical and Physical Properties of 7049/7149 Aluminum Alloy Extrusion**


Specification .....	AMS 4157 and AMS 4343		
Form .....	Extrusion		
Temper .....	T73511		
Thickness, <sup>b</sup> in. ....	≤ 2.499	2.500-2.999	3.000-5.000
Basis .....	S	S	S
Mechanical Properties:			
$F_{tu}$ , ksi:			
L .....	74	74	72
LT .....	70	70	68
ST .....	...	70	68
$F_{ty}$ , ksi:			
L .....	64	64	62
LT .....	60	60	58
ST .....	...	60	58
$F_{cy}$ , ksi:			
L .....	65	65	63
LT .....	...	...	...
ST .....	...	...	...
$F_{su}$ , ksi .....	40	40	39
$F_{bru}^a$ , ksi:			
(e/D = 1.5) .....	110	110	107
(e/D = 2.0) .....	144	144	140
$F_{bry}^a$ , ksi:			
(e/D = 1.5) .....	85	85	83
(e/D = 2.0) .....	105	105	101
$e$ , percent:			
L .....	7	7	7
LT .....	5	5	5
ST .....	...	5	5
$E$ , 10 <sup>3</sup> ksi .....	10.5		
$E_c$ , 10 <sup>3</sup> ksi .....	11.0		
$G$ , 10 <sup>3</sup> ksi .....	4.0		
$\mu$ .....	0.33		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> .....	0.103		
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)		
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] ..	89 (at 77°F)		
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	13.0 (RT to 212°F)		

a Bearing values are "dry pin" values per Section 1.4.7.1.

b The mechanical properties are to be based upon the thickness at the time of quench.


## MIL-HDBK-5H

1 December 1998




**Figure 3.7.2.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ), the tensile yield strength ( $F_{ty}$ ), and the compressive yield strength ( $F_{cy}$ ) of 7049-T7351 plate, 7049/7149-T73 hand forging, and 7049/7149-T7351 extrusion.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.2.1.6(a). Typical tensile stress-strain curves for 7049/7149-T73 aluminum alloy die forging at room temperature.**




**Figure 3.7.2.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 7049/7149-T73 aluminum alloy die forging at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.2.1.6(c). Typical tensile stress-strain curves for 7049/7149-T73 aluminum alloy hand forging at room temperature.**




**Figure 3.7.2.1.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for 7049/7149-T73 aluminum alloy hand forging at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.2.1.6(e). Typical tensile stress-strain curves for 7049-T7351 aluminum alloy plate at room temperature.**



**Figure 3.7.2.1.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for 7049-T7351 aluminum alloy plate at room temperature.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.2.1.6(g). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 7049/7149-T73511 extrusion at room temperature.**



## MIL-HDBK-5H

1 December 1998



**Figure 3.7.2.1.8(a). Best-fit S/N curves for unnotched 7049-T73 die and hand forgings, at room temperature, longitudinal and long-transverse directions.**

Correlative Information for Figure 3.7.2.1.8(a)

Product Form: Die forging, 3 and 4.5-inches thick. Hand forging, 2, 3, 4, and 5 inches thick

Test Parameters:

Loading - Axial  
Frequency - 1800 cpm  
Temperature - RT  
Environment - Lab air

Properties: TUS, ksi TYS, ksi Temp., °F

(L)	78	70	RT
(LT)	74	65	RT

No. of Heats/Lots: 6

Specimen Details: Unnotched

Uniform Gage, 0.200-inch net diameter (Ref. a)

Hourglass, 0.225-inch net diameter (Ref. b)

3.000-inch test section radius

Hourglass, 0.300-inch net diameter (Ref. d)

9.875-inch test section radius

Stress Life Equation:

$$\log N_f = 9.95 - 3.62 \log (S_{eq} - 24.2)$$

$$S_{eq} = S_{max} (1-R)^{0.57}$$

Standard Error of Estimate = 0.346

Standard Deviation in Life = 0.736

$R^2 = 78\%$

Sample Size = 50

Surface Condition:

Longitudinally polished to 4 RMS (Ref. a)

finish or better


Unspecified (Ref. b)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

References: 3.7.2.1.8(a), (b), and 3.2.6.1.9(d)

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.2.1.8(b). Best-fit curves for unnotched 7049-T73 die forging, at room temperature, short transverse direction.**

Correlative Information for Figure 3.7.2.1.8(b)

Product Form: Die forging, 3-inches thick

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial  
Frequency - 1800 cpm  
Temperature - RT  
Environment - Air

73 64 RT

Specimen Details: Unnotched  
0.200-inch net diameter (Ref. a)

No. of Heats/Lots: 1

Surface Condition:

Longitudinally polished to 4μ in. finish with no circumferential marks

Equivalent Stress Equation:


$\log N_f = 16.55 - 6.92 \log (S_{\max})$   
Standard Error of Estimate = 0.371  
Standard Deviation in Life = 0.917  
 $R^2 = 84\%$

Reference: 3.7.2.1.8(a)

Sample Size = 23

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.2.1.8(c). Best-fit S/N curves for notched,  $K_t = 2.4$ , 7049-T73 die forging, at room temperature, longitudinal, long-transverse and short-transverse directions.**

Correlative Information for Figure 3.7.2.1.8(c)

Product Form: Die forging, 3 and 4.5-inches thick

Test Parameters:

Loading - Axial  
Frequency - 1800 cpm  
Temperature - RT  
Environment - Lab air

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
(L)	77	68	RT Unnotched
	95	—	RT Notched
(LT)	73	64	RT Unnotched
	77	—	RT Notched
(ST)	75	66	RT Unnotched
	87	—	RT Notched

No. of Heats/Lots: 2

Stress Life Equation:

$\log N_f = 10.6 - 4.18 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.80}$   
 Standard Error of Estimate = 0.320  
 Standard Deviation in Life = 0.500  
 $R^2 = 59\%$

Specimen Details: Circumferentially notched,  
 $K_t = 2.4$   
 (Ref. a) (Ref. c)  
 0.150 or 0.200 0.350-inch net diameter  
 inch net 0.500-inch gross diameter  
 diameter 0.032-inch notch  
 root radius, r  
 $60^\circ$  flank angle,  $\omega$

Sample Size = 69


[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

Surface Condition: Machined notch

References: 3.7.2.1.8(a) and (c)

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.2.1.8(d). Best-fit S/N curves for unnotched 7049-T73 hand forging, longitudinal direction.**

Correlative Information for Figure 3.7.2.1.8(d)

Product Form: Hand forging, 2.0 to 5.0-inches thick

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
70-80        60-73        RT

Specimen Details: Unnotched  
0.125 and 0.300-inch diameter

Surface Condition:

Polished with increasingly finer grits of emery paper to surface roughness of 10 rms with polishing marks longitudinal, or not specified.

References: 3.2.6.1.9(d) and 3.7.2.1.8(e)

Test Parameters:

Loading - Axial  
Frequency - 800, 1500, or 1725 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: 6

Equivalent Stress Equation:

$$\log N_f = 10.6 - 4.31 \log (S_{eq} - 30)$$

$$S_{eq} = S_{max} (1 - R)^{0.31}$$

Standard Error of Estimate = 0.348

Standard Deviation in Life = 0.944


$R^2 = 86\%$

Sample Size = 28

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.2.1.8(e). Best-fit S/N curves for unnotched 7149-T73 hand forging, long-transverse direction.**

Correlative Information for Figure 3.7.2.1.8(e)

Product Form: Hand forging, 4.00 to 4.75-inches thick

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     73            64            RT

Specimen Details: Unnotched  
 0.250-inch diameter

Surface Condition: Not specified.

Reference: 3.7.2.1.8(e)

Test Parameters:

Loading - Axial  
 Frequency - Not specified  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: 3

Equivalent Stress Equation:

$$\log N_f = 9.9 - 3.46 \log (S_{eq} - 25)$$

$$S_{eq} = S_{max} (1 - R)^{0.39}$$


Standard Error of Estimate = 0.689

Standard Deviation in Life = 0.845

$R^2 = 34\%$

Sample Size = 20

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.2.1.8(f). Best-fit S/N curves for notched,  $K_t = 3.0$ , 7049-T73 hand forging, longitudinal, long-transverse, and short-transverse directions.**

Correlative Information for Figure 3.7.2.1.8(f)

Product Form: Hand forging, 2.0 to 5.0-inches thick

Properties: TUS, ksi TYS, ksi Temp., °F  
71-80 62-73 RT

Specimen Details: Circumferentially notched,  $K_t = 3.0$   
0.200, 0.300, and 0.306-inch gross diameter  
0.175, 0.200, and 0.253-inch net diameter  
0.006, 0.010, and 0.013-inch root radius, r  
60° flank angle,  $\omega$

Surface Condition:  
Polished with oil and alundum grit applied to a rotating wire, or not specified.

References: 3.2.6.1.9(d), 3.7.2.1.8(d) and (e)

Test Parameters:

Loading - Axial  
Frequency - 800, 1500, or 1725 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: 8

Equivalent Stress Equation:


$\log N_f = 9.57 - 3.63 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.49}$   
Standard Error of Estimate = 0.344  
Standard Deviation in Life = 0.562  
 $R^2 = 63\%$

Sample Size = 151

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.2.1.8(g). Best-fit S/N curves for notched,  $K_t = 3.0$ , 7149-T73 hand forging, long transverse direction.**

Correlative Information for Figure 3.7.2.1.8(g)

Product Form: Hand forging, 4.00 to 4.75-inches thick

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     73            64            RT

Specimen Details: Circumferentially notched,  
 $K_t = 3.0$   
 0.375-inch gross diameter  
 0.253-inch net diameter  
 0.013-inch root radius, r  
 60° flank angle,  $\omega$

Surface Condition: Not specified

Reference: 3.7.2.1.8(e)

Test Parameters:

Loading - Axial  
 Frequency - Not specified  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: 3

Equivalent Stress Equation:

$$\log N_f = 10.1 - 4.10 \log (S_{eq} - 5)$$

$$S_{eq} = S_{max} (1 - R)^{0.42}$$

Standard Error of Estimate = 0.450

Standard Deviation in Life = 0.797

$R^2 = 68\%$

Sample Size = 25

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998****3.7.3 7050 ALLOY**

**3.7.3.0 Comments and Properties** — 7050 is an Al-Zn-Mg-Cu-Zr alloy developed to have a combination of high strength, high resistance to stress-corrosion cracking, and good fracture toughness, particularly in thick sections. The use of zirconium in lieu of chromium provides a low sensitivity to quench, which results in high strengths in thick sections. Plate, hand, and die forgings in the T74 temper have static strengths about equivalent to those of corresponding products of 7079 in the T6 tempers and toughness levels equal to or higher than other conventional high-strength alloys.

The properties of extrusions should be based upon the thickness at the time of quenching prior to machining. Selection of the mechanical properties based upon its final machined thickness may be unconservative; therefore, the thickness at the time of quenching to achieve properties is an important factor in the selection of the proper thickness column. For extrusions having sections with various thicknesses, consideration should be given to the properties as a function of thickness.

Plate in the T7451 temper has stress-corrosion resistance higher than 7075-T7651, and hand and die forgings in the T7452 and T74 tempers, respectively, have stress-corrosion resistance similar to 7175-T74 forgings. The T73 temper provides the highest resistance to stress corrosion for this alloy. The T76 temper provides for good exfoliation resistance and higher stress-corrosion resistance than T6 tempers of 7075 and 7178. The T74 temper provides stress-corrosion and strength characteristics intermediate to those of T76 and T73. Refer to Section 3.1.2.3 for further comments regarding the resistance of the alloy to stress-corrosion cracking.

Refer to Section 3.1.3.4 for comments regarding the weldability of this alloy.

Material specifications for 7050 are shown in Table 3.7.3.0(a). Room-temperature properties are shown in Table 3.7.3.0(b<sub>1</sub>) through (e<sub>3</sub>).

**Table 3.7.3.0(a). Material Specifications for 7050 Aluminum Alloy**

Specification	Form
AMS 4050	Bare plate
AMS 4108	Hand forging
AMS 4107	Die forging
AMS 4333	Die forging
AMS 4340	Extruded shape
AMS 4341	Extruded shape
AMS 4342	Extruded shape
AMS 4201	Bare plate
MIL-A-22771	Forging

The temper index for 7050 is as follows:

<u>Section</u>	<u>Temper</u>
3.7.3.1	T73510 and T73511 T74, T7451, and T7452 (formerly T736, T73651, T73652)
3.7.3.3	T76510 and T76511



**MIL-HDBK-5H****1 December 1998**

**3.7.3.1 T73510 and T73511 Tempers** — Figures 3.7.3.1.6(a) through (d) present stress-strain and tangent-modulus curves for extrusions. Fatigue data are presented in Figures 3.7.3.1.8(a) and (b).

**3.7.3.2 T74, T7451, and T7452 Tempers** — Elevated-temperature curves for T7451 plate are presented in Figure 3.7.3.2.1. Figures 3.7.3.2.6(a) through (j) present stress-strain and tangent-modulus curves for various products and tempers. Fatigue data are presented in Figures 3.7.3.2.8(a) through (i). Fatigue-crack-propagation data for T7451 plate are presented in Figures 3.7.3.2.9(a) through (c).

**3.7.3.3 T76510 and T76511 Tempers** — Figures 3.7.3.3.6(a) through (f) present stress-strain and tangent-modulus curves for extruded shapes. Fatigue data are presented in Figure 3.7.3.3.8(a) and (b).

**MIL-HDBK-5H****1 December 1998****Table 3.7.3.0(b<sub>1</sub>). Design Mechanical and Physical Properties of 7050 Aluminum Alloy Plate**

Specification . . . . .	AMS 4050											
Form . . . . .	Plate											
Temper . . . . .	T7451											
Thickness, in. . . . .	0.250- 1.500		1.501- 2.000		2.001- 3.000		3.001- 4.000		4.001- 5.000		5.001- 6.000	
Basis . . . . .	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:												
$F_u$ , ksi:												
L . . . . .	74 <sup>b</sup>	76	74	76	73 <sup>b</sup>	75	72	74	71 <sup>b</sup>	73	70 <sup>b</sup>	72
LT . . . . .	74	76	74 <sup>b</sup>	76	73 <sup>b</sup>	75	72	75	71 <sup>b</sup>	74	70	73
ST . . . . .	...	...	...	...	68	72	68 <sup>b</sup>	71	67	70	66	69
$F_y$ , ksi:												
L . . . . .	64 <sup>b</sup>	67	64 <sup>b</sup>	66	63 <sup>b</sup>	66	62 <sup>b</sup>	65	61 <sup>b</sup>	65	60	63
LT . . . . .	64	66	64	66	63 <sup>b</sup>	66	62	65	61	64	60	62
ST . . . . .	...	...	...	...	59	61	57	60	57 <sup>b</sup>	60	57	59
$F_{cy}$ , ksi:												
L . . . . .	63	64	62	64	61	64	60	63	58	61	57	59
LT . . . . .	66	68	67	69	66	69	65	68	64	67	63	66
ST . . . . .	...	...	...	...	63	66	63	66	63	66	62	64
$F_{su}$ , ksi . . . . .	42	43	43	44	43	44	43	45	43	45	43	45
$F_{bru}$ <sup>a</sup> , ksi:												
(e/D = 1.5) . . . . .	107	110	109	112	108	111	107	111	107	111	105	110
(e/D = 2.0) . . . . .	140	144	142	146	141	144	140	144	138	144	137	142
$F_{bry}$ <sup>a</sup> , ksi:												
(e/D = 1.5) . . . . .	86	89	89	92	89	93	90	94	90	95	91	94
(e/D = 2.0) . . . . .	101	104	104	107	104	109	104	109	105	110	105	108
$e$ , percent (S-basis):												
L . . . . .	10	...	10	...	9	...	9	...	9	...	8	...
LT . . . . .	9	...	9	...	8	...	6	...	5	...	4	...
ST . . . . .	...	...	...	...	2	...	2	...	2	...	2	...
$E$ , 10 <sup>3</sup> ksi . . . . .	10.3											
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.6											
$G$ , 10 <sup>3</sup> ksi . . . . .	3.9											
$\mu$ . . . . .	0.33											
Physical Properties:												
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.102											
$C$ , Btu/(lb)(°F) . . . . .	0.23 (at 212°F)											
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	91 (at 77°F)											
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . . . .	12.8 (68 to 212°F)											

a See Table 3.1.2.1.1. Bearing values are "dry pin" values per Section 1.4.7.1.

b S-basis values. See Table 3.7.3.0(b<sub>2</sub>) for rounded T<sub>99</sub> values.

**MIL-HDBK-5H****1 December 1998****Table 3.7.3.0(b<sub>2</sub>). Rounded T<sub>99</sub> Values for Tensile Yield and Ultimate Strength for 7050-T7451 Plate**

Thickness, in. . . . .	0.250- 1.500	1.501- 2.000	2.001- 3.000	3.001- 4.000	4.001- 5.000	5.001- 6.000
Mechanical Properties:						
<i>F<sub>tu</sub></i> , ksi:						
L . . . . .	75	...	74	...	72	71
LT . . . . .	...	75	74	...	72	...
ST . . . . .	...	...	...	69	...	...
<i>F<sub>ty</sub></i> , ksi:						
L . . . . .	65	65	65	63	62	...
LT . . . . .	...	...	64	...	...	...
ST . . . . .	...	...	...	...	58	...

**MIL-HDBK-5H****1 December 1998****Table 3.7.3.0(b<sub>3</sub>). Design Mechanical and Physical Properties of 7050 Aluminum Alloy Plate**

Specification .....	AMS 4201							
Form .....	Plate							
Temper .....	T7651							
Thickness, in. ....	0.250- 1.000	1.001- 1.500	1.501- 2.000	1.501- 2.000	2.001- 2.500	2.001- 2.500	2.501- 3.000	2.501- 3.000
Basis .....	S	A	B	A	B	A	B	S
Mechanical Properties:								
$F_{tu}$ , ksi:								
L .....	76	77 <sup>b</sup>	80	76	78	75	78	76
LT .....	76	76	79	75	78	75	78	76
ST .....	...	...	...	72	75	70	73	70
$F_{ty}$ , ksi:								
L .....	66	67 <sup>b</sup>	71	66	70	66	70	66
LT .....	66	66	70	65	69	65	69	66
ST .....	...	...	...	59	63	60	62	60
$F_{cy}$ , ksi:								
L .....	64	64	68	64	67	64	67	64
LT .....	68	68	73	68	72	68	72	69
ST .....	...	...	...	67	71	67	71	68
$F_{su}$ , ksi .....	43	44	46	44	46	45	47	46
$F_{bru}^a$ , ksi:								
(e/D = 1.5) .....	110	112	117	112	117	114	118	116
(e/D = 2.0) .....	142	144	150	144	150	146	151	149
$F_{bry}^a$ , ksi:								
(e/D = 1.5) .....	87	90	96	91	96	93	98	96
(e/D = 2.0) .....	102	105	111	105	112	107	114	110
$e$ , percent (S-basis):								
L .....	9	9	...	9	...	8	...	8
LT .....	8	8	...	8	...	7	...	7
ST .....	...	...	...	...	...	1.5	...	1.5
$E$ , 10 <sup>3</sup> ksi .....	10.3							
$E_c$ , 10 <sup>3</sup> ksi .....	10.8							
$G$ , 10 <sup>3</sup> ksi .....	4.0							
$\mu$ .....	0.33							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> .....	0.102							
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)							
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	89 (at 77°F)							
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	12.8 (68 to 212°F)							

a See Table 3.1.2.1.1. Bearing values are "dry pin" values per Section 1.4.7.1.

b S-basis values since T<sub>99</sub> values could not be determined.

**MIL-HDBK-5H****1 December 1998****Table 3.7.3.0(c<sub>1</sub>). Design Mechanical and Physical Properties of 7050 Aluminum Alloy Die Forging**

Specification . . . . .	AMS 4107 and MIL-A-22771			
Form . . . . .	Die forging			
Temper . . . . .	T74 <sup>a</sup>			
Thickness <sup>b</sup> , in. . . . .	≤2.000	2.001-4.000	4.001-5.000	5.001-6.000
Basis . . . . .	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L . . . . .	72	71	70	70
T <sup>c</sup> . . . . .	68	67	66	66
$F_{ty}$ , ksi:				
L . . . . .	62	61	60	59
T <sup>c</sup> . . . . .	56	55	54	54
$F_{cy}$ , ksi:				
L . . . . .	63	63	63	62
ST . . . . .	60	59	58	57
$F_{su}$ , ksi . . . . .	42	42	41	41
$F_{bru}^d$ , ksi:				
(e/D = 1.5) . . . . .	99	98	97	97
(e/D = 2.0) . . . . .	131	129	127	127
$F_{bry}^d$ , ksi:				
(e/D = 1.5) . . . . .	82	81	78	78
(e/D = 2.0) . . . . .	96	95	92	92
$e$ , percent:				
L . . . . .	7	7	7	7
T <sup>c</sup> . . . . .	5	4	3	3
$E$ , 10 <sup>3</sup> ksi . . . . .	10.2			
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.7			
$G$ , 10 <sup>3</sup> ksi . . . . .	3.9			
$\mu$ . . . . .	0.33			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.102			
$C$ , Btu/(lb)(°F) . . . . .	0.23 (at 212°F)			
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	91 (at 77°F)			
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . . . .	12.8 (68 to 212°F)			

a Design values were based upon data obtained from testing T74 die forgings, heat treated by suppliers and supplied in T74 temper.

b Thickness at the time of heat treatment. When die forgings are machined before heat treatment, the mechanical properties are applicable provided the as-forged thickness is not greater than twice the thickness at the time of heat treatment.

c T indicates any grain direction not within ±15° of being parallel to the forging flow lines.  $F_{cy}(T)$  values are based upon short transverse (ST) test data.

d Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 3.7.3.0(c<sub>2</sub>). Design Mechanical and Physical Properties of 7050 Aluminum Alloy Die Forging—Continued**

Specification .....	AMS 4333	
Form .....	Die forging	
Temper .....	T7452	
Thickness <sup>a</sup> , in. ....	≤ 2.000	2.001-4.000
Basis .....	S	S
Mechanical Properties:		
$F_{tu}$ , ksi:		
L .....	72	71
T <sup>a</sup> .....	68	67
$F_{ty}$ , ksi:		
L .....	60	59
T <sup>a</sup> .....	55	53
$F_{cy}$ , ksi:		
L .....	63	62
ST .....	63	62
$F_{su}$ , ksi .....	43	43
$F_{bru}^b$ , ksi:		
(e/D = 1.5) .....	102	101
(e/D = 2.0) .....	136	135
$F_{bry}^b$ , ksi:		
(e/D = 1.5) .....	87	85
(e/D = 2.0) .....	104	102
$e$ , percent:		
L .....	9	8
T <sup>a</sup> .....	5	4
$E$ , 10 <sup>3</sup> ksi .....	10.2	
$E_c$ , 10 <sup>3</sup> ksi .....	10.5	
$G$ , 10 <sup>3</sup> ksi .....	3.9	
$\mu$ .....	0.33	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> .....	0.102	
$C$ , Btu/(lb)(°F) .....	0.23 (at 212 °F)	
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	91 (at 77 °F)	
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	12.8 (68 to 212 °F)	

a T indicates any grain direction within ±15° of being perpendicular to the forging flow lines.  $F_{cy}(T)$  values are based upon short transverse (ST) test data.

b Bearing values are “dry pin” values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 3.7.3.0(d). Design Mechanical and Physical Properties of 7050 Aluminum Alloy Hand Forging**

Specification	AMS 4108 and MIL-A-22771							
Form	Hand Forging							
Temper	T7452							
Thickness, in.	≤2.000	2.001-3.000	3.001-4.000	4.001-5.000	5.001-6.000	6.001-7.000	7.001-8.000	
Basis	S	S	S	S	S	A	B	S
Mechanical Properties:								
$F_{tu}$ , ksi:								
L	72	72	71	70	69	68	71	67
LT	71	70	70	69	68	67	70	66
ST	...	67	67	66	66	65	69	64
$F_{ty}$ , ksi:								
L	63	62	61	60	59	56	61	57
LT	61	60	59	58	56	54 <sup>b</sup>	59	52
ST	...	55	55	54	53	51 <sup>b</sup>	56	50
$F_{cy}$ , ksi:								
L	63	62	61	60	58	56	61	54
LT	64	63	62	61	59	57	62	55
ST	...	63	61	60	58	56	61	54
$F_{su}$ , ksi	42	41	41	41	40	40	41	39
$F_{bru}^a$ , ksi:								
(e/D = 1.5)	98	97	97	96	94	93	97	91
(e/D = 2.0)	131	129	129	127	125	123	129	121
$F_{bry}^a$ , ksi:								
(e/D = 1.5)	86	84	83	82	79	76	83	73
(e/D = 2.0)	101	100	98	96	93	90	98	86
$e$ , percent (S-basis):								
L	9	9	9	9	9	9	...	9
LT	5	5	5	4	4	4	...	4
ST	...	4	4	3	3	3	...	3
$E$ , 10 <sup>3</sup> ksi	10.2							
$E_c$ , 10 <sup>3</sup> ksi	10.6							
$G$ , 10 <sup>3</sup> ksi	3.9							
$\mu$	0.33							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup>	0.102							
$C$ , Btu/(lb)(°F)	0.23 (at 212°F)							
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	91 (at 77°F)							
$\alpha$ , 10 <sup>-6</sup> in./in./°F	12.8 (68 to 212°F)							

a Bearing values are "dry pin" values per Section 1.4.7.1.

b S-basis values. The rounded  $T_{99}$  values for  $F_{ty}(LT) = 56$  ksi and  $F_{ty}(ST) = 52$  ksi.

**MIL-HDBK-5H****1 December 1998****Table 3.7.3.0(e<sub>1</sub>). Design Mechanical and Physical Properties of 7050 Aluminum Alloy Extrusion**

Specification .....	AMS 4341				
Form .....	Extrusion				
Temper .....	T73511				
Cross-Sectional Area, in <sup>2</sup> .....	≤32				
Thickness or Diameter, <sup>b</sup> in. ....	≤1.000	1.001-2.000	2.001-3.000	3.001-4.000	4.001-5.000
Basis .....	S	S	S	S	S
Mechanical Properties:					
<i>F<sub>tu</sub></i> , ksi:					
L .....	70	70	70	70	70
LT .....	68	66	65	63	62
<i>F<sub>ty</sub></i> , ksi:					
L .....	60	60	60	60	60
LT .....	57	56	55	53	52
<i>F<sub>cy</sub></i> , ksi:					
L .....	60	60	60	61	61
LT .....	60	59	58	56	55
<i>F<sub>su</sub></i> , ksi .....	39	39	38	37	36
<i>F<sub>bru</sub></i> <sup>a</sup> , ksi:					
(e/D = 1.5) .....	103	100	96	91	87
(e/D = 2.0) .....	133	129	124	120	115
<i>F<sub>bry</sub></i> <sup>a</sup> , ksi:					
(e/D = 1.5) .....	82	80	78	76	74
(e/D = 2.0) .....	97	95	93	91	88
<i>e</i> , percent:					
L .....	8	8	8	8	8
<i>E</i> , 10 <sup>3</sup> ksi .....	10.3				
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi .....	10.7				
<i>G</i> , 10 <sup>3</sup> ksi .....	3.9				
<i>μ</i> .....	0.33				
Physical Properties:					
<i>ω</i> , lb/in. <sup>3</sup> .....	0.102				
<i>C</i> , Btu/(lb)(°F) .....	0.23 (at 212 °F)				
<i>K</i> , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	93 (at 77 °F)				
<i>α</i> , 10 <sup>-6</sup> in./in./°F .....	12.8 (68 to 212 °F)				

a Bearing values are "dry pin" values per Section 1.4.7.1.

b The mechanical properties are to be based upon the thickness at the time of quench.



**MIL-HDBK-5H****1 December 1998****Table 3.7.3.0(e<sub>2</sub>). Design Mechanical and Physical Properties of 7050 Aluminum Alloy Extrusion**

Specification .....	AMS 4342				
Form .....	Extrusion <sup>b</sup>				
Temper .....	T74511				
Cross-Sectional Area, in <sup>2</sup> .....	≤32				
Thickness or Diameter, <sup>c</sup> in. ....	≤1.000	1.001- 2.000	2.001- 3.000	3.001- 4.000	4.001- 5.000
Basis .....	S	S	S	S	S
Mechanical Properties:					
$F_m$ , ksi:					
L .....	73	73	73	73	73
LT .....	71	69	68	64	64
$F_{ty}$ , ksi:					
L .....	63	63	63	63	63
LT .....	60	59	58	56	54
$F_{cy}$ , ksi:					
L .....	63	63	63	64	64
LT .....	63	62	61	59	57
$F_{su}$ , ksi .....	41	40	40	39	38
$F_{bru}$ <sup>a</sup> , ksi:					
(e/D = 1.5) .....	107	104	100	95	91
(e/D = 2.0) .....	139	135	130	125	121
$F_{bry}$ <sup>a</sup> , ksi:					
(e/D = 1.5) .....	86	84	82	80	78
(e/D = 2.0) .....	106	100	98	95	92
$e$ , percent:					
L .....	7	7	7	7	7
$E$ , 10 <sup>3</sup> ksi .....	10.3				
$E_c$ , 10 <sup>3</sup> ksi .....	10.7				
$G$ , 10 <sup>3</sup> ksi .....	3.9				
$\mu$ .....	0.33				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> .....	0.102				
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)				
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	93 (at 77°F)				
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	12.8 (68 to 212°F)				

a Bearing values are "dry pin" values per Section 1.4.7.1.

b Excluding tubing.

c The mechanical properties are to be based upon the thickness at the time of quench.


**MIL-HDBK-5H****1 December 1998****Table 3.7.3.0(e<sub>3</sub>). Design Mechanical and Physical Properties of 7050 Aluminum Alloy Extrusion**

Specification .....	AMS 4340						
Form .....	Extrusion						
Temper .....	T76511						
Thickness, <sup>b</sup> in. ....	≤0.499	0.500-1.000	1.001-2.000	2.001-3.000	3.001-4.000	4.001-5.000	
Basis .....	A	B	S	S	S	S	S
Mechanical Properties:							
$F_{tu}$ , ksi:							
L .....	77	79	79	79	79	79	79
LT .....	76	78	77	75	73	71	68
$F_{ty}$ , ksi:							
L .....	68	71	69	69	69	69	69
LT .....	67	69	67	65	63	61	59
$F_{cy}$ , ksi:							
L .....	68	71	69	69	69	69	69
LT .....	70	73	70	69	67	66	64
$F_{su}$ , ksi .....	42	44	43	43	42	41	40
$F_{bru}$ <sup>a</sup> , ksi:							
(e/D = 1.5) .....	113	116	115	114	110	107	103
(e/D = 2.0) .....	147	151	150	148	144	140	136
$F_{bry}$ <sup>a</sup> , ksi:							
(e/D = 1.5) .....	94	98	94	92	89	86	82
(e/D = 2.0) .....	109	114	110	108	104	98	93
$e$ , percent (S-basis):							
L .....	7	...	7	7	7	7	7
$E$ , 10 <sup>3</sup> ksi .....	10.3						
$E_c$ , 10 <sup>3</sup> ksi .....	10.7						
$G$ , 10 <sup>3</sup> ksi .....	3.9						
$\mu$ .....	0.33						
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> .....	0.102						
$C$ , Btu/(lb)(°F) .....	0.23 (at 212 °F)						
$K$ , Btu/[ (hr)(ft <sup>2</sup> )(°F)/ft] ....	89 (at 77 °F)						
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	12.8 (68 to 212 °F)						


a Bearing values are “dry pin” values per Section 1.4.7.1.

b The mechanical properties are to be based upon the thickness at the time of quench.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.3.1.6(a). Typical tensile stress-strain curves for 7050-T7351X aluminum alloy extrusion at room temperature.**




**Figure 3.7.3.1.6(b). Typical tensile stress-strain curves for 7050-T7351X aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.3.1.6(c). Typical compressive stress-strain and tangent-modulus curves for 7050-T7351X aluminum alloy extrusion at room temperature.**



**Figure 3.7.3.1.6(d). Typical compressive stress-strain and tangent-modulus curves for 7050-T7351X aluminum alloy extrusion at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.3.1.8(a). Best-fit S/N curves for unnotched 7050-T7351X extruded shape, longitudinal and long transverse directions.**

Correlative Information for Figure 3.7.3.1.8(a)

Product Form: Extruded shape, 0.5 to 5.0-inch thick

Properties:      TUS, ksi    TYS, ksi    Temp., °F  
                      72-79      62-69      RT

Specimen Details: Unnotched  
                                  0.300-inch diameter

Surface Condition: Not specified

References: 3.7.3.2.9(b) and 3.7.7.2.8(b)

Test Parameters:

Loading - Axial  
 Frequency - 800 cpm  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$$\log N_f = 10.5 - 3.79 \log (S_{eq} - 16)$$

$$S_{eq} = S_{max} (1-R)^{0.55}$$

Standard Error of Estimate = 0.516

Standard Deviation in Life = 1.10


$R^2 = 78\%$

Sample Size = 128

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.3.1.8(b). Best-fit S/N curves for notched,  $K_t = 3.0$ , 7050-T7351X extruded shape, longitudinal and long transverse directions.**

Correlative Information for Figure 3.7.3.1.8(b)

Product Form: Extruded shape, 0.5 to 5.0 inch thick

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     72-79       62-69       RT

Specimen Details: Circumferentially notched,  
 $K_t = 3.0$   
 0.359-inch gross diameter  
 0.253-inch net diameter  
 0.013-inch root radius,  $r$   
 60° flank angle,  $\omega$

Surface Condition: Not specified

References: 3.7.3.2.9(b) and 3.7.7.2.8(b)

Test Parameters:

Loading - Axial  
 Frequency - 800 cpm  
 Temperature - RT  
 Environment - Air


No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 7.73 - 2.58 \log (S_{eq} - 5.0)$   
 $S_{eq} = S_{max} (1 - R)^{0.56}$   
 Standard Error of Estimate = 0.268  
 Standard Deviation in Life = 0.733  
 $R^2 = 87\%$


Sample Size = 103

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]


**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.3.2.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of 7050-T7451 aluminum alloy plate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.3.2.6(a). Typical tensile stress-strain curves for 7050-T7451 aluminum alloy plate at room temperature.**




**Figure 3.7.3.2.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 7050-T7451 aluminum alloy plate at room temperature.**



**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.3.2.6(c). Typical tensile stress-strain curves for 7050-T7452 aluminum alloy hand forging at room temperature.**




**Figure 3.7.3.2.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for 7050-T7452 aluminum alloy hand forging at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.3.2.6(e). Typical tensile stress-strain curves for 7050-T74 aluminum alloy die forging at room temperature.**




**Figure 3.7.3.2.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for 7050-T74 aluminum alloy die forging at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.3.2.6(g). Typical tensile stress-strain curves for 7050-T74511 aluminum alloy extrusion at room temperature.**




**Figure 3.7.3.2.6(h). Typical compressive stress-strain and tangent-modulus curves for 7050-T74511 aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.3.2.6(i). Typical tensile stress-strain curves for 7050-T7452 aluminum alloy die forging at room temperature.**



**Figure 3.7.3.2.6(j). Typical compressive stress-strain and tangent-modulus curves for 7050-T7452 aluminum alloy die forging at room temperature.**

**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.3.2.8(a). Best-fit S/N curves for unnotched 7050-T7451 plate, longitudinal direction.**

Correlative Information for Figure 3.7.3.2.8(a)

Product Form: Plate, 1.0-inch thick

Test Parameters:

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     79            72            RT

Loading - Axial  
 Frequency - 800 cpm  
 Temperature - RT  
 Environment - Air

Specimen Details: Unnotched  
                              0.300-inch diameter

No. of Heats/Lots: 10

Surface Condition: Not specified

Equivalent Stress Equation:

$$\log N_f = 9.73 - 3.24 \log (S_{eq} - 15.5)$$

$$S_{eq} = S_{max} (1 - R)^{0.63}$$

Standard Error of Estimate = 0.490

Standard Deviation in Life = 0.942

$R^2 = 73\%$


References: 3.7.3.2.9(b) and 3.7.7.2.8(b)

Sample Size = 35

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.3.2.8(b). Best-fit S/N curves for unnotched 7050-T7451 plate, long transverse direction.**

Correlative Information for Figure 3.7.3.2.8(b)

Product Form: Plate, 1.0 to 6.0 inches thick

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial

Frequency - 800 cpm and unspecified

Temperature - RT

Environment - Air

73-81 62-72 RT

Specimen Details: Unnotched  
0.250- and 0.300-inch  
diameter

No. of Heats/Lots: 15

Surface Condition: Not specified

Equivalent Stress Equation:

$$\log N_f = 10.7 - 3.81 \log (S_{eq} - 10)$$

$$S_{eq} = S_{max} (1 - R)^{0.59}$$

Standard Error of Estimate = 0.507

Standard Deviation in Life = 0.794

$R^2 = 59\%$


References: 3.7.3.2.9(b), 3.7.7.2.8(b) and (e)

Sample Size = 85

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.3.2.8(c). Best-fit S/N curves for notched,  $K_t = 3.0$ , 7050-T7451 plate, longitudinal and long transverse directions.**

Correlative Information for Figure 3.7.3.2.8(c)

Product Form: Plate, 1.0 to 6.0-inches thick

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial

Frequency - 800 cpm and unspecified

Temperature - RT

Environment - Air

75-81 65-72 RT

Specimen Details:

Circumferentially notched,  $K_t = 3.0$   
0.306- and 0.373-inch gross diameter  
0.253-inch net diameter  
0.013-inch notch-tip radius, r  
60° flank angle,  $\omega$

No. of Heats/Lots: 11

Equivalent Stress Equation:

$$\log N_f = 10.0 - 3.96 \log (S_{eq})$$

$$S_{eq} = S_{max} (1-R)^{0.64}$$

Standard Error of Estimate = 0.248

Standard Deviation in Life = 0.728

$R^2 = 88\%$

Surface Condition: Not specified


References: 3.7.3.2.9(b) and 3.7.7.2.8(b) and (c)

Sample Size = 79

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.3.2.8(d). Best-fit S/N curves for notched,  $K_t = 2.6$ , 7050-T7451X extruded shape, longitudinal direction.**

Correlative Information for Figure 3.7.3.2.8(d)

Product Form: Extruded shape, 0.5 to 5.0-inch thick

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     76-77       67-68       RT

Specimen Details:

Notched, center hole,  $K_t = 2.6$   
 0.150-inch diameter  
 0.250-inch thick  
 1.00-inch wide

Surface Condition: Not specified

Reference: 3.7.3.2.8(a)

Test Parameters:

Loading - Axial  
 Frequency - Not specified  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: 6

Equivalent Stress Equation:

$\log N_f = 8.23 - 2.82 \log (S_{eq} - 10)$   
 $S_{eq} = S_{max} (1 - R)^{0.30}$   
 Standard Error of Estimate = 0.243  
 Standard Deviation in Life = 0.724  
 $R^2 = 89\%$


Sample Size = 34

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 3.7.3.2.8(e). Best-fit S/N curves for unnotched 7050-T7452 hand forgings, longitudinal direction.**

Correlative Information for Figure 3.7.3.2.8(e)

Product Form: Hand forgings, 2.0 to 8.0-inch thick

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     76-81       66-72       RT

Specimen Details: Unnotched  
                                  0.300-inch diameter

Surface Condition: Not specified

References: 3.7.3.2.9(b) and 3.7.6.2.8(b)

Test Parameters:

Loading - Axial  
 Frequency - 800 cpm  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: 10

Equivalent Stress Equation:

$$\log N_f = 7.06 - 1.89 \log (S_{eq} - 30)$$

$$S_{eq} = S_{max} (1 - R)^{0.60}$$

Standard Error of Estimate = 0.400

Standard Deviation in Life = 0.982


$$R^2 = 83\%$$

Sample Size = 25

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.3.2.8(f). Best-fit S/N curves for unnotched 7050-T7452 hand forgings, long transverse and short transverse directions.**

Correlative Information for Figure 3.7.3.2.8(f)

Product Form: Hand forgings, 2.0 to 8.0-inch thick

Properties: TUS, ksi TYS, ksi Temp., °F  
73-80 59-70 RT

Specimen Details: Unnotched  
0.300-inch diameter

Surface Condition: Not specified

References: 3.7.3.2.9(b) and 3.7.7.2.8(b)

Test Parameters:

Loading - Axial  
Frequency - 800 cpm and unspecified  
Temperature - RT  
Environment - Air

No. of Heats/Lots: 10

Equivalent Stress Equation:

$$\log N_f = 7.58 - 2.14 \log (S_{eq} - 21)$$

$$S_{eq} = S_{max} (1-R)^{0.57}$$


Standard Error of Estimate = 0.400

Standard Deviation in Life = 0.803

$R^2 = 75\%$

Sample Size = 55

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.3.2.8(g). Best-fit S/N curves for notched,  $K_t = 3.0$ , 7050-T7452 hand forgings, longitudinal, long transverse, and short transverse directions.**

Correlative Information for Figure 3.7.3.2.8(g)

Product Form: Hand forgings, 2.0 to 8.0-inch thick

Test Parameters:

Loading - Axial  
Frequency - 800 cpm  
Temperature - RT  
Environment - Air

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
73-81        59-72        RT

No. of Heats/Lots: 10

Specimen Details:

Circumferentially notched,  $K_t = 3.0$   
0.306-inch gross diameter  
0.253-inch net diameter  
0.013-inch root radius, r  
60° flank angle,  $\omega$

Equivalent Stress Equation:

$\log N_f = 8.21 - 2.96 \log (S_{eq} - 5)$   
 $S_{eq} = S_{max} (1 - R)^{0.68}$   
Standard Error of Estimate = 0.307  
Standard Deviation in Life = 0.735  
 $R^2 = 83\%$

Surface Condition: Not specified


Sample Size = 80

References: 3.7.3.2.9(b) and 3.7.7.2.8(b)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.3.2.8(h). Best-fit S/N curves for unnotched 7050-T74 die forging, longitudinal directions.**

Correlative Information for Figure 3.7.3.2.8(h)

Product Form: Die forging

Test Parameters:

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
74-81        68-71        RT

Loading - Axial  
Frequency - 800 cpm  
Temperature - RT  
Environment - Air

Specimen Details: Unnotched  
0.300-inch diameter

No. of Heats/Lots: 4

Surface Condition: Not specified

Equivalent Stress Equation:

$\log N_f = 16.8 - 6.97 \log (S_{\max})$   
Standard Error of Estimate = 0.381  
Standard Deviation in Life = 0.820  
 $R^2 = 78\%$


References: 3.7.3.2.9(b) and 3.7.7.2.8(b)

Sample Size = 20

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.3.2.8(i). Best-fit S/N curves for notched,  $K_t = 3.0$ , 7050-T74 die forging, longitudinal direction.**

Correlative Information for Figure 3.7.3.2.8(i)

Product Form: Die forging

Test Parameters:

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     77-81       68-71       RT

Loading - Axial  
 Frequency - 800, 1800 cpm  
 Temperature - RT  
 Environment - Air

Specimen Details:

Circumferentially notched,  $K_t = 3.0$   
 0.306- and 0.305-inch gross diameter  
 0.253- or 0.222-inch net diameter  
 0.013- or 0.012-inch root radius, r  
 60° flank angle,  $\omega$

No. of Heats/Lots: 6

Equivalent Stress Equation:

$\log N_f = 10.5 - 4.14 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.629}$   
 Standard Error of Estimate = 0.506  
 Standard Deviation in Life = 0.896  
 $R^2 = 68\%$


Surface Condition: Not specified

References: 3.7.3.2.8(b), 3.7.3.2.9(b), and  
 3.7.7.2.8(b)

Sample Size = 73

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.3.2.9(a). Fatigue-crack-propagation data for 3.15-inch-thick 7050-T7451 aluminum plate [Reference 3.7.3.2.9(a)].**

Specimen Thickness:	0.499-0.500 inch	Environment:	Lab air (~50% humidity) and humid air (100% humidity)
Specimen Width:	2.989-3.000 inches	Temperature:	RT
Specimen Type:	C(T)	Frequency, f:	10-20 Hz
Stress Ratio, R:	0.1		

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.3.2.9(b). Fatigue-crack-propagation data for 1- and 6-inch-thick 7050-T7451 aluminum plate [Reference 3.7.3.2.9(b)].**

Specimen Thickness: 0.999-1.000 inch  
 Specimen Width: 3.805 inches  
 Specimen Type: C(T)  
 Stress Ratio, R: 0.33

Environment: Dry air (< 10% humidity)  
 Temperature: RT  
 Frequency, f: 18.3 Hz

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.3.2.9(c). Fatigue-crack-propagation data for 1- and 6-inch-thick 7050-T7451 aluminum plate [Reference 3.7.3.2.9(b)].**

Specimen Thickness: 0.998-1.000 inch  
 Specimen Width: 3.805 inches  
 Specimen Type: C(T)  
 Stress Ratio, R: 0.33


Environment: Humid air (>90% humidity)  
 Temperature: RT  
 Frequency, f: 18.3 Hz



**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.3.3.6(a). Typical tensile stress-strain curves for 7050-T7651X aluminum alloy extrusion at room temperature.**




**Figure 3.7.3.3.6(b). Typical tensile stress-strain curves for 7050-T7651X aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.3.3.6(c). Typical compressive stress-strain and compressive tangent-modulus curves for 7050-T7651X aluminum alloy extrusion at room temperature.**




**Figure 3.7.3.3.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for 7050-T7651X aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.3.3.6(e). Typical tensile stress-strain curves for 7050-T7651 aluminum alloy plate at room temperature.**



**Figure 3.7.3.3.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for 7050-T7651 aluminum alloy plate at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.3.3.8(a). Best-fit S/N curves for unnotched 7050-T7651X extruded shape, longitudinal and long transverse directions.**

Correlative Information for Figure 3.7.3.3.8(a)

Product Form: Extruded shape, 0.55.0-inch thick

Properties: TUS, ksi TYS, ksi Temp., °F  
84-90 75-81 RT

Specimen Details: Unnotched  
0.300-inch diameter

Surface Condition: Not specified

References: 3.7.3.3.8(b), 3.7.3.2.9(b), and  
3.7.7.2.8(b)

Test Parameters:

Loading - Axial  
Frequency - 800 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: 10

Equivalent Stress Equation:


$\log N_f = 11.8 - 4.38 \log (S_{eq} - 12)$   
 $S_{eq} = S_{max} (1 - R)^{0.61}$   
Standard Error of Estimate = 0.493  
Standard Deviation in Life = 1.01  
 $R^2 = 76\%$

Sample Size = 161

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.3.3.8(b). Best-fit S/N curves for notched,  $K_t = 3.0$ , 7050-T7651X extruded shape, longitudinal and long transverse directions.**

Correlative Information for Figure 3.7.3.3.8(b)

Product Form: Extruded shape, 0.5 to 5.0-inch thick

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     78-90        68-81        RT

Specimen Details:

Circumferentially notched,  $K_t = 3.0$   
 0.359-inch gross diameter  
 0.253-inch net diameter  
 0.013-inch root radius,  $r$   
 60° flank angle,  $\omega$

Surface Condition: Not specified

References: 3.7.3.2.9(b), 3.7.3.3.8(a), and 3.7.7.2.8(b)

Test Parameters:

Loading - Axial  
 Frequency - 800 cpm  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: 10

Equivalent Stress Equation:

$\log N_f = 8.22 - 2.90 \log (S_{eq} - 5)$   
 $S_{eq} = S_{max} (1 - R)^{0.57}$   
 Standard Error of Estimate = 0.414  
 Standard Deviation in Life = 0.778  
 $R^2 = 72\%$

Sample Size = 179

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998****3.7.4 7075 ALLOY**

**3.7.4.0 Comments and Properties** — 7075 is a high-strength Al-Zn-Mg-Cu alloy and is available in a wide variety of product forms. It is also available in several types of tempers, the T6, T73, and T76 type. The T6 temper has the highest strength but lowest toughness and resistance to stress-corrosion cracking. Since toughness decreases with a decrease in temperature, the T6 temper is not generally recommended for cryogenic applications. The T73 temper provides for much improved stress-corrosion resistance over T6 temper with a decrease in strength. The T76 temper provides for improved exfoliation resistance and limited stress-corrosion resistance over T6 temper with some decrease in strength. Refer to Section 3.1.2.3 for comments regarding the resistance of the alloy to stress-corrosion cracking and to Section 3.1.3.4 for comments regarding the weldability of this alloy.

The properties of extrusions should be based upon the thickness at the time of quenching prior to machining. Selection of the mechanical properties based upon its final machined thickness may be unconservative; therefore, the thickness at the time of quenching to achieve properties is an important factor in the selection of the proper thickness column. For extrusions having sections with various thicknesses, consideration should be given to the properties as a function of thickness.

Material specifications for 7075 aluminum alloy are presented in Table 3.7.4.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.7.4.0(b<sub>1</sub>) through (g<sub>4</sub>). The effect of temperature on the physical properties of this alloy is presented in Figure 3.7.4.0.

**Table 3.7.4.0(a). Material Specifications for 7075 Aluminum Alloy**

Specification	Form
AMS 4044	Bare sheet and plate
AMS 4045	Bare sheet and plate
AMS 4078	Bare plate
AMS-QQ-A-250/12, 24	Bare sheet and plate
AMS-QQ-A-250/13, 25	Clad sheet and plate
AMS 4049	Clad sheet and plate
AMS 4122	Bar and rod, rolled or cold finished
AMS 4123	Bar and rod, rolled or cold finished
AMS 4124	Bar and rod, rolled or cold finished
AMS 4186	Bar and rod, rolled or cold finished
AMS 4187	Bar and rod, rolled or cold finished
AMS-QQ-A-225/9	Rolled or drawn bar and rod
AMS-QQ-A-200/11, 15	Extruded bar, rod, and shapes
AMS 4126	Forging
AMS 4141	Die forging
AMS 4147	Forging
MIL-A-22771	Forging
QQ-A-367	Forging

The temper index for 7075 is as follows:

<u>Section</u>	<u>Temper</u>
3.7.4.1	T6, T651, T652, T6510, T6511
3.7.4.2	T73, T7351, T7352, T73510, T73511

**MIL-HDBK-5H****1 December 1998**

**3.7.4.1 T6, T651, T652, T6510, T6511 Temper** — Figures 3.7.4.1.1(a) and (b) permit calculation of residual tensile strengths for complex thermal exposure conditions. They are based upon the rate parameter  $T(C + \log t)$ , in which  $T$  is exposure temperature in degrees Rankine,  $t$  is exposure time in hours and  $C$  is a constant evaluated for each material. These curves have been verified for use only within the ranges of temperatures and exposure times covered in the figures. The following example illustrates their use.

Sample problem: Find  $F_{tu}$  at 250°F following a complex exposure of 300°F, 8 hours plus 350°F, 1 hour.

1. Reduce given complex exposure by converting 350°F exposure to equivalent exposure time at 300°F.\*
  - a. On the 350°F single exposure temperature line find 350°F, 1 hour.
  - b. From this point move vertically to the 300°F exposure temperature line and then read right, 12 hours exposure.
  - c. Total equivalent exposure time at 300°F is therefore 8 hours + 12 hours or 20 hours.
2. Find  $F_{tu}$  at 250°F following 300°F, 20 hours exposure:
  - a. On the 300°F exposure temperature line find 300°F, 20 hours.
  - b. From this point move vertically to the 250°F test temperature curve and then read left, 76 percent  $F_{tu}$ .

Solution:  $F_{tu}$  is 76 percent of the original room temperature  $F_{tu}$ .  $F_{ty}$  is determined in like manner.  $F_{cy}$  can be closely estimated by using the percent reduction factor determined for  $F_{ty}$ . For specific data, see Reference 3.7.4.1.

*Stressed Thermal Exposure* — Stress applied during sample and complex thermal exposure of 7075-T6 can have additional effect in reducing material strength. However, the effect becomes significant only when exposure strains exceed 0.2 percent. For specific data, see Reference 3.7.4.1.

Figures 3.7.4.1.1(c) through 3.7.4.1.5(b) present elevated temperature curves for various mechanical properties. Figures 3.7.4.1.6(a) through (m) present tensile and compressive stress-strain and tangent-modulus curves at several temperatures. Figures 3.7.4.1.6(n) through (q) are full-range stress-strain curves for various products. Figures 3.7.4.1.8(a) through (h) provide room-temperature fatigue curves for T6 temper products. Fatigue-crack propagation data for sheet are presented in Figure 3.7.4.1.9. Graphical displays of the residual strength behavior of center-cracked tension panels are presented in Figure 3.7.4.1.10(a) through (h).

**3.7.4.2 T73, T7351, T7352, T73510, T73511 Tempers** — Figures 3.7.4.2.6(a) through (d) present stress-strain and tangent-modulus curves for various products and tempers. Figures 3.7.4.2.6(e) and (f) are full-range stress-strain curves at room temperature for extrusion. Fatigue-crack-propagation data for plate are presented in Figures 3.7.4.2.9(a) through (c). Graphical displays of the residual strength behavior of center-cracked tension panels are presented in Figures 3.7.4.2.10(a) and (b).

---

\* Choice of reference temperature is optional as long as it permits computation within the bounds of the figures.

**Table 3.7.4.0(b<sub>1</sub>). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Sheet and Plate**

Specification	AMS 4045 and AMS-QQ-A-250/12																				
Form	Sheet								Plate												
Temper	T6 and T62 <sup>a</sup>								T651												
Thickness, in.	0.008-0.011	0.012-0.039	0.040-0.125		0.126-0.249		0.250-0.499		0.500-1.000		1.001-2.000		2.001-2.500		2.501-3.000		3.001-3.500		3.501-4.000		
Basis	S	A	B	A	B	A	B	A	B	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:																					
$F_{tu}$ , ksi:																					
L	...	76	78	78	80	78	80	77	79	77	79	76	78	75	77	71	73	70	72	66	68
LT	74	76	78	78	80	78	80	78	80	78	80	77	79	76	78	72	74	71	73	67	69
ST	...	...	...	...	...	...	...	...	...	...	...	...	...	70 <sup>b</sup>	71 <sup>b</sup>	66 <sup>b</sup>	68 <sup>b</sup>	65 <sup>b</sup>	67 <sup>b</sup>	61 <sup>b</sup>	63 <sup>b</sup>
$F_{ty}$ , ksi:																					
L	...	69	72	70	72	71	73	69	71	70	72	69	71	66	68	63	65	60	62	56	58
LT	63	67	70	68	70	69	71	67	69	68	70	67	69	64	66	61	63	58	60	54	56
ST	...	...	...	...	...	...	...	...	...	...	...	...	...	59 <sup>b</sup>	61 <sup>b</sup>	56 <sup>b</sup>	58 <sup>b</sup>	54 <sup>b</sup>	55 <sup>b</sup>	50 <sup>b</sup>	52 <sup>b</sup>
$F_{cy}$ , ksi:																					
L	...	68	71	69	71	70	72	67	69	68	70	66	68	62	64	58	60	55	57	51	52
LT	...	71	74	72	74	73	75	71	73	72	74	71	73	68	70	65	67	61	64	57	59
ST	...	...	...	...	...	...	...	...	...	...	...	...	...	67	70	64	66	61	63	57	59
$F_{su}$ , ksi	...	46	47	47	48	47	48	43	44	44	45	44	45	44	45	42	43	42	43	39	41
$F_{bru}^c$ , ksi:																					
(e/D = 1.5)	...	118	121	121	124	121	124	117	120	117	120	116	119	114	117	108	111	107	110	101	104
(e/D = 2.0)	...	152	156	156	160	156	160	145	148	145	148	143	147	141	145	134	137	132	135	124	128
$F_{bry}^c$ , ksi:																					
(e/D = 1.5)	...	100	105	102	105	103	106	97	100	100	103	100	103	98	101	94	97	89	93	84	87
(e/D = 2.0)	...	117	122	119	122	121	124	114	118	117	120	117	120	113	117	109	112	104	108	98	103
$e$ , percent (S-basis):																					
LT	5	7	...	8	...	8	...	9	...	7	...	6	...	5	...	5	...	5	...	3	...
$E$ , 10 <sup>3</sup> ksi	10.3								10.3												
$E_c$ , 10 <sup>3</sup> ksi	10.5								10.6												
$G$ , 10 <sup>3</sup> ksi	3.9								3.9												
$\mu$	0.33								0.33												
Physical Properties:																					
$\omega$ , lb/in. <sup>3</sup>	0.101																				
$C$ , $K$ , and $\alpha$	See Figure 3.7.4.0																				

a Design allowables were based upon data obtained from testing T6 temper sheet and from testing samples of sheet, supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained by the user may be lower than those listed if the material has been formed or otherwise cold worked, particularly in the annealed temper, prior to solution heat treatment.

b Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).

c Bearing values are "dry pin" values per Section 1.4.7.1. See Table 3.1.2.1.1.



**Table 3.7.4.0(b<sub>2</sub>). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Plate—Continued**

Specification .....	AMS 4044 and AMS-QQ-A-250/12						AMS-QQ-A-250/12							
Form .....	Plate													
Temper .....	T62 <sup>a</sup>													
Thickness, in. ....	0.250-0.499		0.500-1.000		1.001-2.000		2.001-2.500		2.501-3.000		3.001-3.500		3.501-4.000	
Basis .....	A	B	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:														
$F_{tu}$ , ksi:														
L .....	74	76	74	76	73	75	72	74	69	71	68	70	64	66
LT .....	78	80	78	80	77	79	76	78	72	74	71	73	67	69
ST .....	...	...	...	...	...	...	70 <sup>b</sup>	71 <sup>b</sup>	66 <sup>b</sup>	68 <sup>b</sup>	65 <sup>b</sup>	67 <sup>b</sup>	61 <sup>b</sup>	63 <sup>b</sup>
$F_{ty}$ , ksi:														
L .....	65	67	66	68	64	65	60	62	56	58	52	54	48	49
LT .....	67	69	68	70	67	69	64	66	61	63	58	60	54	56
ST .....	...	...	...	...	...	...	59 <sup>b</sup>	61 <sup>b</sup>	56 <sup>b</sup>	58 <sup>b</sup>	54 <sup>b</sup>	55 <sup>b</sup>	50 <sup>b</sup>	52 <sup>b</sup>
$F_{cy}$ , ksi:														
L .....	70	72	70	72	68	70	63	65	59	61	55	57	50	52
LT .....	70	72	71	73	68	71	65	67	61	63	57	59	52	54
ST .....	...	...	...	...	...	...	63	65	60	62	57	59	53	55
$F_{su}$ , ksi .....	43	44	44	45	44	45	44	45	42	43	42	43	39	41
$F_{bru}^c$ , ksi:														
(e/D = 1.5) .....	117	120	117	120	116	119	114	117	108	111	107	110	101	104
(e/D = 2.0) .....	145	148	145	148	143	147	141	145	134	137	132	135	124	128
$F_{bry}^c$ , ksi:														
(e/D = 1.5) .....	97	100	100	103	100	103	98	101	94	97	89	93	84	87
(e/D = 2.0) .....	114	118	117	120	117	120	113	117	109	112	104	108	98	103
$e$ , percent (S-basis):														
LT .....	9	...	7	...	6	...	5	...	5	...	5	...	3	...
$E$ , 10 <sup>3</sup> ksi .....	10.3													
$E_c$ , 10 <sup>3</sup> ksi .....	10.6													
$G$ , 10 <sup>3</sup> ksi .....	3.9													
$\mu$ .....	0.33													
Physical Properties:														
$\omega$ , lb/in. <sup>3</sup> .....	0.101													
$C$ , $K$ , and $\alpha$ .....	See Figure 3.7.4.0													

a Design allowables were based upon data obtained from testing samples of plate, supplied in O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers.

Properties obtained by the user may be lower than those listed if the material has been formed or otherwise cold worked, particularly in the annealed temper, prior to solution heat treatment.

b Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).

c Bearing values are “dry pin” values per Section 1.4.7.1. See Table 3.1.2.1.1.

**Table 3.7.4.0(b<sub>3</sub>). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Sheet and Plate—Continued**

Specification .....	AMS-QQ-A-250/12	AMS 4078 and AMS-QQ-A-250/12												
Form .....	Sheet	Plate												
Temper .....	T73	T7351												
Thickness, in. ....	0.040-0.249	0.250-0.499	0.500-1.000		1.001-1.500		1.501-2.000		2.001-2.500		2.501-3.000		3.001-3.500	3.501-4.000
Basis .....	S	S	A	B	A	B	A	B	A	B	A	B	S	S
Mechanical Properties:														
$F_{tu}$ , ksi:														
L .....	67	68	68	70	67	69	66	68	65	67	63	65	62	60
LT .....	67	69	69	71	68	70	67	69	66	68	64 <sup>c</sup>	66	63	61
ST .....	...	...	...	...	...	...	63	65	62	64	60	62	59	57
$F_{ty}$ , ksi:														
L .....	56	57	57	59	57	59	55	57	52	55	49	53	49	48
LT .....	56	57	57	59	57	59	55	57	52 <sup>b</sup>	55	49 <sup>c</sup>	53	49	48
ST .....	...	...	...	...	...	...	52	54	49	52	47	50	47	46
$F_{cy}$ , ksi:														
L .....	55	56	56	58	56	58	53	55	50	53	47	51	47	45
LT .....	58	59	59	61	59	61	57	59	54	57	51	55	51	50
ST .....	...	...	...	...	...	...	59	61	55	58	51	55	50	48
$F_{su}$ , ksi .....	38	38	38	39	38	40	39	40	39	40	38	39	38	37
$F_{bru}^a$ , ksi:														
(e/D = 1.5) .....	105	102	103	106	103	106	102	106	102	105	100	103	99	96
(e/D = 2.0) .....	134	131	132	136	132	136	132	136	131	135	128	132	127	124
$F_{bry}^a$ , ksi:														
(e/D = 1.5) .....	84	79	81	83	83	86	82	85	79	83	76	81	76	76
(e/D = 2.0) .....	102	95	97	100	99	102	97	101	93	99	89	96	89	88
$e$ , percent (S-basis):														
LT .....	8	7	7	...	6	...	6	...	6	...	6	...	6	6
$E$ , 10 <sup>3</sup> ksi .....	10.3	10.3												
$E_c$ , 10 <sup>3</sup> ksi .....	10.5	10.6												
$G$ , 10 <sup>3</sup> ksi .....	3.9	3.9												
$\mu$ .....	0.33	0.33												
Physical Properties:														
$\omega$ , lb/in. <sup>3</sup> .....	0.101													
$C$ , $K$ , and $\alpha$ .....	See Figure 3.7.4.0													

a Bearing values are “dry pin” values per Section 1.4.7.1. See Table 3.1.2.1.1.

b S-basis. The rounded  $T_{99}$  value is as follows:  $F_{ty}(LT) = 53$  ksi.c S-basis. The rounded  $T_{99}$  values are as follows:  $F_{tu}(LT) = 65$  ksi and  $F_{ty}(LT) = 52$  ksi.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.7.4.0(b<sub>4</sub>). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Sheet and Plate—Continued**

Specification .....	AMS-QQ-A-250/24				
Form .....	Sheet and plate				
Temper .....	T76	T7651			
Thickness, in. ....	0.063-0.249	0.250-0.499	0.500-1.000	1.001-1.500	1.501-2.000
Basis .....	S	S	S	S	S
Mechanical Properties:					
$F_{tu}$ , ksi:					
L .....	72	71	70	70	70
LT .....	73	72	71	71	71
ST .....	...	...	...	...	65
$F_{ty}$ , ksi:					
L .....	62	60	59	59	59
LT .....	62	61	60	60	60
ST .....	...	...	...	...	56
$F_{cy}$ , ksi:					
L .....	61	60	59	59	59
LT .....	65	64	63	63	63
ST .....	...	...	...	...	63
$F_{su}$ , ksi .....	42	40	41	42	43
$F_{bru}^a$ , ksi:					
(e/D = 1.5) .....	112	109	108	108	108
(e/D = 2.0) .....	145	141	140	140	140
$F_{bry}^a$ , ksi:					
(e/D = 1.5) .....	88	86	86	86	87
(e/D = 2.0) .....	102	99	99	99	100
$e$ , percent:					
LT .....	8	8	6	5	5
$E$ , 10 <sup>3</sup> ksi .....	10.3	10.3			
$E_c$ , 10 <sup>3</sup> ksi .....	10.5	10.6			
$G$ , 10 <sup>3</sup> ksi .....	3.9	3.9			
$\mu$ .....	0.33	0.33			
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> .....	0.101				
$C$ , $K$ , and $\alpha$ .....	See Figure 3.7.4.0				

a Bearing values are “dry pin” values per Section 1.4.7.1. See Table 3.1.2.1.1.

**MIL-HDBK-5H****1 December 1998****Table 3.7.4.0(c<sub>1</sub>). Design Mechanical and Physical Properties of Clad 7075 Aluminum Alloy Sheet**

Specification .....	AMS 4049								
Form .....	Sheet								
Temper .....	T6								
Thickness, in. ....	0.008- 0.011	0.012- 0.039		0.040- 0.062		0.063- 0.187		0.188- 0.249	
Basis .....	S	A	B	A	B	A	B	A	B
Mechanical Properties:									
$F_{tu}$ , ksi:									
L .....	...	71	74	71	75	74	77	75	77
LT .....	68	71	74	71	75	74 <sup>a</sup>	77	75	77
$F_{ty}$ , ksi:									
L .....	...	62	65	63	66	66	69	66	68
LT .....	58	60	63	61	64	64	67	64	66
$F_{cy}$ , ksi:									
L .....	...	61	64	62	65	65	68	65	67
LT .....	...	64	67	65	68	68	71	68	70
$F_{su}$ , ksi .....	...	42	44	42	45	44	46	45	46
$F_{bru}^b$ , ksi:									
(e/D = 1.5) .....	...	110	115	110	116	115	119	116	119
(e/D = 2.0) .....	...	142	148	142	150	148	154	150	154
$F_{bry}^b$ , ksi:									
(e/D = 1.5) .....	...	90	94	91	96	96	100	96	99
(e/D = 2.0) .....	...	105	110	106	112	112	117	112	115
$e$ , percent (S-basis):									
LT .....	5	8	...	9	...	9	...	9	...
$E$ , 10 <sup>3</sup> ksi:									
Primary .....			10.3			10.3		10.3	
Secondary .....			9.5			9.8		10.0	
$E_c$ , 10 <sup>3</sup> ksi:									
Primary .....			10.5			10.5		10.5	
Secondary .....			9.7			10.0		10.2	
$G$ , 10 <sup>3</sup> ksi .....			...			...		...	
$\mu$ .....			0.33			0.33		0.33	
Physical Properties:									
$\omega$ , lb/in. <sup>3</sup> .....					0.101				
$C$ , $K$ , and $\alpha$ .....					...				

a S-Basis. The rounded  $T_{99}$  value is 75 ksi.

b Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 3.7.4.0(c<sub>2</sub>). Design Mechanical and Physical Properties of Clad 7075 Aluminum Alloy Sheet—Continued**

Specification .....	AMS-QQ-A-250/13								
Form .....	Sheet								
Temper .....	T6 and T62 <sup>a</sup>								
Thickness, in. ....	0.008-0.011	0.012-0.039		0.040-0.062		0.063-0.187		0.188-0.249	
Basis .....	S	A	B	A	B	A	B	A	B
Mechanical Properties:									
$F_{tu}$ , ksi:									
L .....	...	70	74	71	75	73	77	75	77
LT .....	68	70 <sup>c</sup>	74	71	75	73 <sup>d</sup>	77	75	77
$F_{ty}$ , ksi:									
L .....	...	62	65	63	66	65	69	66	68
LT .....	58	60	63	61	64	63 <sup>e</sup>	67	64	66
$F_{cy}$ , ksi:									
L .....	...	61	64	62	65	64	68	65	67
LT .....	...	64	67	65	68	67	71	68	70
$F_{su}$ , ksi .....	...	42	44	42	45	44	46	45	46
$F_{bru}^b$ , ksi:									
(e/D = 1.5) .....	...	108	115	110	116	113	119	116	119
(e/D = 2.0) .....	...	140	148	142	150	146	154	150	154
$F_{bry}^b$ , ksi:									
(e/D = 1.5) .....	...	90	94	91	96	94	100	96	99
(e/D = 2.0) .....	...	105	110	106	112	110	117	112	115
$e$ , percent (S-basis):									
LT .....	5	7	...	8	...	8	...	8	...
$E$ , 10 <sup>3</sup> ksi:									
Primary .....	10.3					10.3		10.3	
Secondary .....	9.5					9.8		10.0	
$E_c$ , 10 <sup>3</sup> ksi:									
Primary .....	10.5					10.5		10.5	
Secondary .....	9.7					10.0		10.2	
$G$ , 10 <sup>3</sup> ksi .....	...					...		...	
$\mu$ .....	0.33					0.33		0.33	
Physical Properties:									
$\omega$ , lb/in. <sup>3</sup> .....	0.101								
$C$ , $K$ , and $\alpha$ .....	...								

a Design allowables were based upon data obtained from testing T6 temper sheet and from testing samples of sheet, supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained may be lower than those listed if the material has been formed or otherwise cold worked, particularly in the annealed temper, prior to solution heat treatment.

b Bearing values are “dry pin” values per Section 1.4.7.1.

c S-Basis. The rounded  $T_{99}$  value is 71 ksi.

d S-Basis. The rounded  $T_{99}$  value is 75 ksi.

e S-Basis. The rounded  $T_{99}$  value is 64 ksi.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.7.4.0(c<sub>3</sub>). Design Mechanical and Physical Properties of Clad 7075 Aluminum Alloy Plate—Continued**

Specification .....	AMS 4049 and AMS-QQ-A-250/13													
Form .....	Plate													
Temper .....	T651													
Thickness, in. ....	0.250-0.499		0.500-1.000 <sup>a</sup>		1.001-2.000 <sup>a</sup>		2.001-2.500 <sup>a</sup>		2.501-3.000 <sup>a</sup>		3.001-3.500 <sup>a</sup>		3.501-4.000 <sup>a</sup>	
Basis .....	A	B	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:														
$F_{tu}$ , ksi:														
L .....	74	76	75	77	74	76	73	75	69	71	68	70	64	66
LT .....	75	77	76	78	75	77	74	76	70	72	69	71	65	67
ST .....	...	...	...	...	...	...	70 <sup>b</sup>	71 <sup>b</sup>	66 <sup>b</sup>	68 <sup>b</sup>	65 <sup>b</sup>	67 <sup>b</sup>	61 <sup>b</sup>	63 <sup>b</sup>
$F_{ty}$ , ksi:														
L .....	67	69	68	70	67	69	64	66	61	63	58	60	54	56
LT .....	65	67	66	68	65	67	62	64	59	61	56	58	52	54
ST .....	...	...	...	...	...	...	59 <sup>b</sup>	61 <sup>b</sup>	56 <sup>b</sup>	58 <sup>b</sup>	54 <sup>b</sup>	55 <sup>b</sup>	50 <sup>b</sup>	52 <sup>b</sup>
$F_{cy}$ , ksi:														
L .....	65	67	66	68	64	66	60	62	57	58	53	55	49	51
LT .....	69	71	70	72	69	71	65	68	62	64	59	61	55	57
ST .....	...	...	...	...	...	...	67	70	64	66	61	63	57	59
$F_{su}$ , ksi .....	42	43	42	44	42	44	43	44	41	42	40	42	38	39
$F_{bru}^c$ , ksi:														
(e/D = 1.5) .....	113	116	114	117	113	116	111	114	105	108	104	107	98	101
(e/D = 2.0) .....	139	143	141	145	139	143	137	141	130	134	128	132	121	124
$F_{bry}^c$ , ksi:														
(e/D = 1.5) .....	94	97	97	100	97	100	95	98	90	94	86	89	80	84
(e/D = 2.0) .....	111	114	113	116	113	117	110	113	105	109	100	104	93	97
$e$ , percent (S-basis):														
LT .....	9	...	7	...	6	...	5	...	5	...	5	...	3	...
$E$ , 10 <sup>3</sup> ksi:														
Primary .....							10.3							
Secondary .....							10.0							
$E_c$ , 10 <sup>3</sup> ksi:														
Primary .....							10.6							
Secondary .....							10.3							
$G$ , 10 <sup>3</sup> ksi .....							...							
$\mu$ .....							0.33							
Physical Properties:														
$\omega$ , lb/in. <sup>3</sup> .....							0.101							
$C$ , $K$ , and $\alpha$ .....							...							

- a These values, except in the ST direction, have been adjusted to represent the average properties across the whole section, including the 1-1/2 percent per side nominal cladding thickness.
- b Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).
- c Bearing values are "dry pin" values per Section 1.4.7.1. See Table 3.1.2.1.1

**MIL-HDBK-5H****1 December 1998****Table 3.7.4.0(c<sub>4</sub>). Design Mechanical and Physical Properties of Clad 7075 Aluminum Alloy Plate—Continued**

Specification . . . . .	AMS-QQ-A-250/13													
Form . . . . .	Plate													
Temper . . . . .	T62 <sup>a</sup>													
Thickness, in. . . . .	0.250-0.499		0.500-1.000 <sup>b</sup>		1.001-2.000 <sup>b</sup>		2.001-2.500 <sup>b</sup>		2.501-3.000 <sup>b</sup>		3.001-3.500 <sup>b</sup>		3.501-4.000 <sup>b</sup>	
Basis . . . . .	A	B	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:														
$F_u$ , ksi:														
L . . . . .	72	73	72	74	72	73	71	72	67	69	66	68	62	64
LT . . . . .	75	77	76	78	75	77	74	76	70	72	69	71	65	67
ST . . . . .	...	...	...	...	...	...	70 <sup>c</sup>	71 <sup>c</sup>	66 <sup>c</sup>	68 <sup>c</sup>	65 <sup>c</sup>	67 <sup>c</sup>	61 <sup>c</sup>	63 <sup>c</sup>
$F_y$ , ksi:														
L . . . . .	63	65	64	66	62	64	58	60	54	56	50	52	46	48
LT . . . . .	65	67	66	68	65	67	62	64	59	61	56	58	52	54
ST . . . . .	...	...	...	...	...	...	59 <sup>c</sup>	61 <sup>c</sup>	56 <sup>c</sup>	58 <sup>c</sup>	54 <sup>c</sup>	55 <sup>c</sup>	50 <sup>c</sup>	52 <sup>c</sup>
$F_{cy}$ , ksi:														
L . . . . .	68	70	68	70	66	68	62	63	57	59	53	55	48	50
LT . . . . .	68	70	69	71	66	68	62	65	59	61	55	57	50	52
ST . . . . .	...	...	...	...	...	...	63	65	60	62	57	59	53	55
$F_{su}$ , ksi . . . . .	42	43	42	44	42	44	43	44	41	42	40	42	38	39
$F_{bru}^d$ , ksi:														
(e/D = 1.5) . . . . .	113	116	114	117	113	116	111	114	105	108	104	107	98	101
(e/D = 2.0) . . . . .	139	143	141	145	139	143	137	141	130	134	128	132	121	124
$F_{bry}^d$ , ksi:														
(e/D = 1.5) . . . . .	94	97	97	100	97	100	95	98	90	94	86	89	80	84
(e/D = 2.0) . . . . .	111	114	113	116	113	117	110	113	105	109	100	104	93	97
$e$ , percent (S-basis):														
LT . . . . .	9	...	7	...	6	...	5	...	5	...	5	...	3	...
$E$ , 10 <sup>3</sup> ksi:														
Primary . . . . .	10.3													
Secondary . . . . .	10.0													
$E_c$ , 10 <sup>3</sup> ksi:														
Primary . . . . .	10.6													
Secondary . . . . .	10.3													
$G$ , 10 <sup>3</sup> ksi . . . . .	3.9													
$\mu$ . . . . .	0.33													
Physical Properties:														
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.101													
$C$ , $K$ , and $\alpha$ . . . . .	...													

- a Design allowables were based upon data obtained from testing samples of plate, supplied in the O or F temper, which were heat treated to demonstrate response to heat treatment by suppliers. Properties obtained may be lower than those listed if the material has been formed or otherwise cold worked, particularly in the annealed temper, prior to solution heat treatment.
- b These values, except in the ST direction, have been adjusted to represent the average properties across the whole section.
- c Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).
- d Bearing values are "dry pin" values per Section 1.4.7.1. See Table 3.1.2.1.1.

**MIL-HDBK-5H****1 December 1998****Table 3.7.4.0(c<sub>5</sub>). Design Mechanical and Physical Properties of Clad 7075 Aluminum Alloy Sheet and Plate—Continued**

Specification .....	AMS-QQ-A-250/25				
Form .....	Sheet			Plate	
Temper .....	T76			T7651	
Thickness, in., .....	0.040- 0.062	0.063- 0.187	0.188- 0.249	0.250- 0.499	0.500- 1.000 <sup>a</sup>
Basis .....	S	S	S	S	S
<b>Mechanical Properties:</b>					
$F_{tu}$ , ksi:					
L .....	66	67	69	68	68
LT .....	67	68	70	69	68
$F_{ty}$ , ksi:					
L .....	56	57	59	58	57
LT .....	56	57	59	58	57
$F_{cy}$ , ksi:					
L .....	55	56	58	57	56
LT .....	59	60	62	60	59
$F_{su}$ , ksi .....	41	40	40	40	40
$F_{bru}^b$ , ksi:					
(e/D = 1.5) .....	103	104	107	105	103
(e/D = 2.0) .....	133	135	139	133	131
$F_{bry}^b$ , ksi:					
(e/D = 1.5) .....	80	81	84	87	87
(e/D = 2.0) .....	92	94	97	104	103
$e$ , percent:					
LT .....	8	8	8	8	6
$E$ , 10 <sup>3</sup> ksi:					
Primary .....	10.3		10.3	10.3	
Secondary .....	9.8		10.0	10.0	
$E_c$ , 10 <sup>3</sup> ksi:					
Primary .....	10.5		10.5	10.6	
Secondary .....	10.0		10.2	10.3	
$G$ , 10 <sup>3</sup> ksi .....	...		...	...	
$\mu$ .....	0.33		0.33	0.33	
<b>Physical Properties:</b>					
$\omega$ , lb/in. <sup>3</sup> .....			0.101		
$C$ , $K$ , and $\alpha$ .....			...		

a These values have been adjusted to represent the average properties across the whole section, including the 1-1/2 percent per side nominal cladding thickness.

b Bearing values are "dry pin" values per Section 1.4.7.1. See Table 3.1.2.1.1.



**MIL-HDBK-5H****1 December 1998****Table 3.7.4.0(d). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Bar, Rod, and Shapes: Rolled, Drawn, or Cold-Finished**

Specification . . . . .	AMS 4122, AMS 4123, AMS 4186, AMS 4187, and AMS-QQ-A-225/9								AMS 4124 and AMS-QQ-A- 225/9	
	Bar, rod, and shapes: rolled, drawn, or cold-finished									
Temper . . . . .	T6, T651, and T62 <sup>a</sup>								T73 <sup>b,c</sup> or T7351 <sup>c</sup>	
Thickness <sup>d</sup> , in. . . . .	≤1.000		1.001- 2.000		2.001- 3.000		3.001- 4.000		0.375- 2.000	2.001- 3.000
Basis . . . . .	A	B	A	B	A	B	A	B	S	S
Mechanical Properties:										
<i>F<sub>tu</sub></i> , ksi:										
L . . . . .	77	79	77	79	77	79	77	79	68	68
LT . . . . .	77 <sup>e</sup>	79 <sup>e</sup>	75 <sup>e</sup>	77 <sup>e</sup>	72 <sup>e</sup>	74 <sup>e</sup>	69 <sup>e</sup>	71 <sup>e</sup>	...	65 <sup>e,f</sup>
<i>F<sub>y</sub></i> , ksi:										
L . . . . .	66	68	66	68	66	68	66	68	56	56
LT . . . . .	66 <sup>e</sup>	68 <sup>e</sup>	66 <sup>e</sup>	68 <sup>e</sup>	63 <sup>e</sup>	65 <sup>e</sup>	60 <sup>e</sup>	62 <sup>e</sup>	...	52 <sup>e,f</sup>
<i>F<sub>cy</sub></i> , ksi:										
L . . . . .	64	66	64	66	64	66	64	66	54	54
LT . . . . .	...	...	...	...	...	...	...	...	...	55 <sup>f</sup>
<i>F<sub>su</sub></i> , ksi . . . . .	46	47	46	47	46	47	46	47	42	40
<i>F<sub>bru</sub></i> , ksi:										
(e/D = 1.5) . . . . .	100	103	100	103	100	103	100	103	101	101
(e/D = 2.0) . . . . .	123	126	123	126	123	126	123	126	131	131
<i>F<sub>by</sub></i> , ksi:										
(e/D = 1.5) . . . . .	86	88	86	88	86	88	86	88	81	81
(e/D = 2.0) . . . . .	92	95	92	95	92	95	92	95	100	100
<i>e</i> , percent (S-basis):										
L . . . . .	7	...	7	...	7	...	7	...	10	10
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	10.3									
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	10.5									
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	3.9									
<i>μ</i> . . . . .	0.33									
Physical Properties:										
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.101									
<i>C</i> , <i>K</i> , and <i>α</i> . . . . .	See Figure 3.7.4.0									

a Design allowables were based upon data obtained from testing of T6 and T651 material and from samples of material, supplied in the O or F temper, which were heat treated to T62 temper to demonstrate response to heat treatment by suppliers.

b Design allowables were based upon data obtained from testing T73 and T7351 temper material and from testing samples of material, supplied in the O or F temper, which were heat treated to T73 temper to demonstrate response to heat treatment by suppliers.

c Bearing values are "dry pin" values per Section 1.4.7.1.

d For rounds (rod) maximum diameter is 4 inches; for square bar, maximum size is 3½ inches; for rectangular bar, maximum thickness is 3 inches with corresponding width of 6 inches; for rectangular bar less than 3 inches in thickness, maximum width is 10 inches.

e Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).

f ST grain direction.

**Table 3.7.4.0(e<sub>1</sub>). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Die Forging**

Specification	AMS 4126, MIL-A-22771, and QQ-A-367							MIL-A-22771 and QQ-A-367						
Form	Die forging													
Temper	T6 <sup>b</sup>							T652						
Thickness <sup>c</sup> , in.	≤1.000		1.001-2.000		2.001-3.000		3.001-4.000	≤1.000		1.001-2.000		2.001-3.000		3.001-4.000
Basis	A	B	A	B	A	B	S	A	B	A	B	A	B	S
Mechanical Properties:														
$F_{tu}$ , ksi:														
L	75	78	74	77	74	76	73	75	78	74	77	74	76	73
T <sup>a</sup>	71 <sup>d</sup>	...	71 <sup>d</sup>	...	70 <sup>d</sup>	...	70	71 <sup>d</sup>	...	71 <sup>d</sup>	...	70 <sup>d</sup>	...	70
$F_{ty}$ , ksi:														
L	64	67	63	66	63	65	62	64	67	63	66	63	65	62
T <sup>a</sup>	61 <sup>d</sup>	...	61 <sup>d</sup>	...	60 <sup>d</sup>	...	60	60 <sup>d</sup>	...	60 <sup>d</sup>	...	59 <sup>d</sup>	...	59
$F_{cy}$ , ksi:														
L	67	70	66	69	66	68	65	64	67	63	66	63	65	62
ST	64	68	64	67	63	66	63	65	69	65	68	64	67	64
$F_{su}$ , ksi	43	45	43	44	42	43	42	43	45	43	44	42	43	42
$F_{bru}^c$ , ksi:														
(e/D = 1.5)	105	109	104	108	104	106	102	105	109	104	108	104	106	102
(e/D = 2.0)	135	140	133	138	133	136	131	135	140	133	138	133	136	131
$F_{bry}^c$ , ksi:														
(e/D = 1.5)	83	87	82	86	82	84	81	83	87	82	86	82	84	81
(e/D = 2.0)	96	100	94	99	94	97	93	96	100	94	99	94	97	93
$e$ , percent (S-basis):														
L	7	...	7	...	7	...	7	7	...	7	...	7	...	7
T <sup>a</sup>	3	...	3	...	3	...	2	3	...	3	...	3	...	2
$E$ , 10 <sup>3</sup> ksi	10.0													
$E_c$ , 10 <sup>3</sup> ksi	10.4													
$G$ , 10 <sup>3</sup> ksi	3.8													
$\mu$	0.33													
Physical Properties:														
$\omega$ , lb/in. <sup>3</sup>	0.101													
$C$ , $K$ , and $\alpha$	See Figure 3.7.4.0													

a T indicates any grain direction not within  $\pm 15^\circ$  of being parallel to the forging flow lines.  $F_{cy}(T)$  values are based upon short transverse (ST) test data.

b When die forgings are machined before heat treatment, the mechanical properties are applicable provided the as-forged thickness is not greater than twice the thickness at time of heat treatment.

c Bearing values are "dry pin" values per Section 1.4.7.1.

d Specification value. T tensile properties are presented on an S basis only.

e Thickness at the time of heat treatment.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.7.4.0(e<sub>2</sub>). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Die Forging—Continued**

Specification .....	AMS 4141, MIL-A-22771, and QQ-A-367								AMS 4141		AMS 4147, MIL-A-22771, and QQ-A-367		
Form .....	Die forging												
Temper .....	T73 <sup>a,b</sup>										T7352		
Thickness <sup>c</sup> , in. ....	≤1.000		1.001- 2.000		2.001- 3.000		3.001- 4.000		4.001- 5.000	5.001- 6.000	≤3.000		3.001- 4.000
Basis .....	A	B	A	B	A	B	A	B	S	S	A	B	S
Mechanical Properties <sup>d</sup> :													
<i>F<sub>tu</sub></i> , ksi:													
L .....	66	71	66	71	66	69	64	69	62	61	66	69	64
T <sup>e</sup> .....	62 <sup>g</sup>	...	62 <sup>g</sup>	...	62 <sup>g</sup>	...	61 <sup>g</sup>	...	59 <sup>h</sup>	58 <sup>h</sup>	62 <sup>g</sup>	...	61
<i>F<sub>ty</sub></i> , ksi:													
L .....	56	61	56	59	56	59	55	59	53	51	56	59	53
T <sup>e</sup> .....	53 <sup>g</sup>	...	53 <sup>g</sup>	...	53 <sup>g</sup>	...	52 <sup>g</sup>	...	51 <sup>h</sup>	50 <sup>h</sup>	51 <sup>g</sup>	...	49
<i>F<sub>cy</sub></i> , ksi:													
L .....	58	63	58	61	58	61	57	61	...	...	56	59	53
T <sup>e</sup> .....	55	60	55	59	55	59	54	58	...	...	55	60	53
<i>F<sub>su</sub></i> , ksi .....	39	42	39	42	39	41	38	41	...	...	39	41	38
<i>F<sub>bru</sub></i> <sup>f</sup> , ksi:													
(e/D = 1.5) .....	96	103	96	103	96	100	93	100	...	...	96	100	93
(e/D = 2.0) .....	125	135	125	135	125	131	122	131	...	...	125	131	122
<i>F<sub>bry</sub></i> <sup>f</sup> , ksi:													
(e/D = 1.5) .....	78	85	78	83	78	83	77	83	...	...	78	83	74
(e/D = 2.0) .....	90	98	90	94	90	94	88	94	...	...	90	94	85
<i>e</i> , percent (S-basis):													
L .....	7	...	7	...	7	...	7	...	7	6	7	...	7
T <sup>e</sup> .....	3	...	3	...	3	...	2	...	2	2	3	...	2
<i>E</i> , 10 <sup>3</sup> ksi .....	10.0												
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi .....	10.4												
<i>G</i> , 10 <sup>3</sup> ksi .....	3.8												
<i>μ</i> .....	0.33												
Physical Properties:													
<i>ω</i> , lb/in. <sup>3</sup> .....	0.101												
<i>C</i> , <i>K</i> , and <i>α</i> .....	See Figure 3.7.4.0												

a When die forgings are machined before heat treatment, the mechanical properties are applicable, provided the as-forged thickness is not greater than twice the thickness at the time of heat treatment.

b Design allowables were based upon data obtained from testing die forgings, heat treated by suppliers, and supplied in T73 temper.

c Thickness at the time of heat treatment.

d Most of the A tensile values are higher than specification values; consequently, the A values shown are specification values.

e T indicates any grain direction not within ±15° of being parallel to the forging flow lines. *F<sub>cy</sub>* (T) values are based upon short transverse (ST) test data.

f Bearing values are “dry pin” values per Section 1.4.7.1.

g Specification value. T tensile properties are presented on an S basis only.

h T indicates any grain direction within ±15° of being perpendicular to the forging flow lines.

**MIL-HDBK-5H****1 December 1998****Table 3.7.4.0(f<sub>1</sub>). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Hand Forging**

Specification . . . . .	AMS 4126, MIL-A-22771, and QQ-A-367					MIL-A-22771 and QQ-A-367				
	Hand forging									
	T6 <sup>a</sup>					T652				
	≤2.000	2.001- 3.000	3.001- 4.000	4.001- 5.000	5.001- 6.000	≤2.000	2.001- 3.000	3.001- 4.000	4.001- 5.000	5.001- 6.000
Basis . . . . .	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:										
<i>F<sub>tu</sub></i> , ksi:										
L . . . . .	74	73	71	69	68	74	73	71	69	68
LT . . . . .	73	71	70	68	66	73	71	70	68	66
ST . . . . .	...	69 <sup>b</sup>	68 <sup>b</sup>	66 <sup>b</sup>	65 <sup>b</sup>	...	69 <sup>b</sup>	68 <sup>b</sup>	66 <sup>b</sup>	65 <sup>b</sup>
<i>F<sub>ty</sub></i> , ksi:										
L . . . . .	63	61	60	58	56	63	61	60	58	56
LT . . . . .	61	59	58	56	55	61	59	58	56	55
ST . . . . .	...	58 <sup>b</sup>	57 <sup>b</sup>	56 <sup>b</sup>	55 <sup>b</sup>	...	57 <sup>b</sup>	56 <sup>b</sup>	55 <sup>b</sup>	54 <sup>b</sup>
<i>F<sub>cy</sub></i> , ksi:										
L . . . . .	63	61	...	...	...	63	61	...	...	...
LT . . . . .	61	59	...	...	...	61	59	...	...	...
ST . . . . .	...	...	...	...	...	...	...	...	...	...
<i>F<sub>su</sub></i> , ksi . . . . .	44	44	43	41	41	44	44	43	41	41
<i>F<sub>bru</sub></i> <sup>c</sup> , ksi:										
(e/D = 1.5) . . . . .	...	...	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...	...	...	...	...	...
<i>F<sub>bry</sub></i> <sup>c</sup> , ksi:										
(e/D = 1.5) . . . . .	...	...	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...	...	...	...	...	...
<i>e</i> , percent:										
L . . . . .	9	9	8	7	6	9	9	8	7	6
LT . . . . .	4	4	3	3	3	4	4	3	3	3
ST . . . . .	...	3	2	2	2	...	2	1	1	1
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	10.0									
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	10.4									
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	3.8									
<i>μ</i> . . . . .	0.33									
Physical Properties:										
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.101									
<i>C</i> , <i>K</i> , and <i>α</i> . . . . .	See Figure 3.7.4.0									

- a When hand forgings are machined before heat treatment, the section thickness at time of heat treatment shall determine the minimum mechanical properties as long as the original (as-forged) thickness does not exceed the maximum thickness of the alloy as shown in the table. The maximum cross-sectional area of hand forgings is 256 sq in.
- b Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).
- c Bearing values are "dry pin" values per Section 1.4.7.1.

**Table 3.7.4.0(f<sub>2</sub>). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Hand Forging—Continued**

Specification	MIL-A-22771 and QQ-A-367					AMS 4147, MIL-A-22771, and QQ-A-367					
Form	Hand forging										
Temper	T73 <sup>a</sup>					T7352					
Thickness, in.	≤2.000	2.001-3.000	3.001-4.000	4.001-5.000	5.001-6.000	≤2.000	2.001-3.000	3.001-4.000	4.001-5.000	5.001-6.000	
Basis	S	S	S	S	S	S	S	A	B	S	S
Mechanical Properties:											
$F_u$ , ksi:											
L	66	66	64	62	61	66	66	64	67	62	61
LT	64	64	63	61	59	64	64	63	66	61	59
ST	...	61	60	58	57	...	61	60	63	58	57
$F_y$ , ksi:											
L	56	56	55	53	51	54	54	53	55	51	49
LT	54	54	53	51	50	52	52	50	53	48	46
ST	...	52	51	50	49	...	50	48	51	46	44
$F_{cy}$ , ksi:											
L	56	56	...	...	...	55	55	52	55	49	46
LT	52	52	...	...	...	55	55	52	55	49	46
ST	...	...	...	...	...	55	55	53	56	51	49
$F_{su}$ , ksi:											
L	39	39	...	...	...	39	39	38	40	37	36
LT	...	...	...	...	...	36	36	37	38	36	35
ST	...	...	...	...	...	38	38	37	39	36	35
$F_{bru}^b$ , ksi:											
(e/D = 1.5)	...	...	...	...	...	86	88	89	93	86	84
(e/D = 2.0)	...	...	...	...	...	120	120	118	123	114	110
$F_{bry}^b$ , ksi:											
(e/D = 1.5)	...	...	...	...	...	71	73	73	77	71	68
(e/D = 2.0)	...	...	...	...	...	90	90	87	92	83	80
$e$ , percent (S-basis):											
L	7	7	7	7	6	7	7	7	...	7	6
LT	4	4	3	3	3	4	4	3	...	3	3
ST	...	3	2	2	2	...	3	2	...	2	2
$E$ , 10 <sup>3</sup> ksi	10.2										
$E_c$ , 10 <sup>3</sup> ksi	10.4										
$G$ , 10 <sup>3</sup> ksi	3.8										
$\mu$	0.33										
Physical Properties:											
$\omega$ , lb/in. <sup>3</sup>	0.101										
$C$ , $K$ , and $\alpha$	See Figure 3.7.4.0										

a When hand forgings are machined before heat treatment, the section thickness at time of heat treatment shall determine the minimum mechanical properties as long as the original (as-forged) thickness does not exceed the maximum thickness for the alloy as shown in the table. The maximum cross-sectional area of hand forgings is 256 sq. in.

b Bearing values are “dry pin” values per Section 1.4.7.1.

**Table 3.7.4.0(g.). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Extrusion**

Specification	QQ-A-200/11														
Form	Extrusion (rod, bar, and shapes)														
Temper	T6, T6510, T6511, and T62 <sup>a</sup>														
Cross-Sectional Area, in. <sup>2</sup>	≤20												>20, ≤32	≤32	
Thickness, in. <sup>b</sup>	≤0.249		0.250-0.499		0.500-0.749		0.750-1.499		1.500-2.999		3.000-4.499		4.500-5.000		
Basis	A	B	A	B	A	B	A	B	A	B	A	B	S	A	B
Mechanical Properties:															
$F_{tu}$ , ksi:															
L	78	82	81	85	81	85	81	85	81	85	81	84	78	78	81
LT	75	79	78	82	77	81	75	79	71	75	67	69	64	63	65
ST	...	...	...	...	...	...	...	...	67 <sup>c</sup>	71 <sup>c</sup>	67 <sup>c</sup>	69 <sup>c</sup>	64 <sup>c</sup>	63 <sup>c</sup>	65 <sup>c</sup>
$F_{ty}$ , ksi:															
L	70	74	73	77	72	76	72	76	72	76	71	74	70	68	71
LT	66	70	69	72	67	71	65	69	61	65	56	59	55	52	55
ST	...	...	...	...	...	...	...	...	56 <sup>c</sup>	59 <sup>c</sup>	55 <sup>c</sup>	58 <sup>c</sup>	55 <sup>c</sup>	52 <sup>c</sup>	55 <sup>c</sup>
$F_{cy}$ , ksi:															
L	70	74	73	77	72	76	72	76	72	76	71	74	70	68	71
LT	72	76	74	78	73	77	71	75	67	71	62	64	61	57	60
ST	...	...	...	...	...	...	...	...	62	66	62	64	61	57	60
$F_{su}$ , ksi	41	44	43	45	43	45	43	45	42	44	40	42	39	38	40
$F_{bru}^d$ , ksi:															
(e/D = 1.5)	111	117	115	121	115	120	113	119	110	115	106	110	102	101	105
(e/D = 2.0)	140	148	146	153	145	152	144	151	141	148	137	142	132	131	136
$F_{bry}^d$ , ksi:															
(e/D = 1.5)	92	97	96	101	94	99	93	98	89	94	84	88	83	79	83
(e/D = 2.0)	108	114	113	119	111	117	110	116	106	112	101	105	100	95	100
$e$ , percent (S-basis):															
L	7	...	7	...	7	...	7	...	7	...	7	...	6	6	...
$E$ , 10 <sup>3</sup> ksi	10.4														
$E_c$ , 10 <sup>3</sup> ksi	10.7														
$G$ , 10 <sup>3</sup> ksi	4.0														
$\mu$	0.33														
Physical Properties:															
$\omega$ , lb/in. <sup>3</sup>	0.101														
$C$ , $K$ , and $\alpha$	See Figure 3.7.4.0														

- a Design allowables were based upon data obtained from testing T6, T6510, and T6511 temper extrusions and from testing samples of extrusion supplied in the O or F temper, which were heat treated to T62 temper to demonstrate response to heat treatment by suppliers. Properties obtained by the user may be lower than those listed if the material has been formed or otherwise cold worked, particularly in the annealed temper, prior to solution heat treatment.
- b The mechanical properties are to be based upon the thickness at the time of quench.
- b Caution: This specific alloy, temper, and product form exhibits poor stress-corrosion cracking resistance in this grain direction. It corresponds to an SCC resistance rating of D, as indicated in Table 3.1.2.3.1(a).
- d Bearing values are "dry pin" values per Section 1.4.7.1.

**Table 3.7.4.0(g<sub>2</sub>). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Extrusion—Continued**

Specification .....	AMS-QQ-A-200/11													
Form .....	Extrusion (rod, bars, and shapes)													
Temper .....	T73 <sup>a</sup> , T73510, T73511													
Cross-Sectional Area, in. <sup>2</sup> .....	≤20		≤25								≤20		>20, ≤32	
Thickness, in. <sup>b</sup> .....	0.062-0.249		0.250-0.499		0.500-0.749		0.750-1.499		1.500-2.999		3.000-4.499		3.000-4.499	
Basis .....	A	B	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:														
$F_{tu}$ , ksi:														
L .....	68 <sup>c</sup>	72	70 <sup>c</sup>	74	70 <sup>c</sup>	73	70 <sup>c</sup>	73	69 <sup>c</sup>	74	68 <sup>c</sup>	71	65 <sup>c</sup>	70
LT .....	66	70	68	72	67	70	66	69	62	67	58	61	56	60
$F_{ty}$ , ksi:														
L .....	58	61	60	63	60	63	60	63	59 <sup>c</sup>	65	57 <sup>c</sup>	62	55 <sup>c</sup>	60
LT .....	56	59	57	60	57	60	56	58	51	56	46	50	44	48
$F_{cy}$ , ksi:														
L .....	58	61	60	63	60	63	60	63	59	65	57	62	55	60
LT .....	59	62	60	63	60	63	58	61	54	59	49	53	47	51
$F_{su}$ , ksi:	37	39	38	40	38	39	38	39	37	40	37	38	35	38
$F_{bru}^d$ , ksi:														
(e/D = 1.5) .....	101	107	104	110	103	108	103	107	99	106	95	99	91	98
(e/D = 2.0) .....	129	137	133	141	133	139	132	138	128	138	124	130	119	128
$F_{bry}^d$ , ksi:														
(e/D = 1.5) .....	82	86	84	89	84	88	83	87	79	87	72	79	70	76
(e/D = 2.0) .....	97	102	100	105	100	105	98	103	93	103	86	94	83	91
$e$ , percent (S-basis):														
L .....	7	...	8	...	8	...	8	...	8	...	7	...	7	...
$E$ , 10 <sup>3</sup> ksi .....	10.4													
$E_c$ , 10 <sup>3</sup> ksi .....	10.7													
$G$ , 10 <sup>3</sup> ksi .....	4.0													
$\mu$ .....	0.33													
Physical Properties:														
$\omega$ , lb/in. <sup>3</sup> .....	0.101													
$C$ , $K$ , and $\alpha$ .....	See Figure 3.7.4.0													

a Design allowables were based upon data obtained from testing T7351X temper extrusions and from testing samples of extrusions supplied in the O or F temper, which were heat treated to T73 temper to demonstrate response to treatment by suppliers. Properties obtained by the user may be lower than those listed if the material has been formed or otherwise cold worked, particularly in the annealed temper.

b The mechanical properties are to be based upon the thickness at the time of quench.

c S-basis. See Table 3.7.4.0(g<sub>3</sub>) for the rounded T<sub>99</sub> values.

d Bearing values are “dry pin” values per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.7.4.0(g<sub>3</sub>). Rounded T<sub>99</sub> Values for Tensile Yield and Ultimate Strength for 7075-T73, T73510, and T73511 Extrusion**

Cross-Sectional Area, in. <sup>2</sup> . .	≤20	≤25		≤20	>20, ≤32
Thickness, inch . . . . .	0.062-0.249	0.250-1.499	1.500-2.999	3.000-4.499	3.000-4.499
Mechanical Properties:					
<i>F<sub>tu</sub></i> , ksi:					
L . . . . .	69	71	72	69	68
<i>F<sub>ty</sub></i> , ksi:					
L . . . . .	...	...	62	59	57




**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.7.4.0(g<sub>4</sub>). Design Mechanical and Physical Properties of 7075 Aluminum Alloy Extrusion—Continued**

Specification .....	AMS-QQ-A-200/15						
Form .....	Extrusion (rod, bar, and shapes)						
Temper .....	T76, T76510, T76511						
Cross-Sectional Area, in. <sup>2</sup> ..	≤20						
Thickness, in. <sup>a</sup> .....	0.062-0.249		0.250-0.499	0.500-0.749		0.750-1.000	
Basis .....	A	B	S	A	B	A	B
Mechanical Properties:							
$F_u$ , ksi:							
L .....	71	74	75	75	76	75	76
LT .....	68	71	72	71	73	70	71
$F_y$ , ksi:							
L .....	61	65	65	65	67	65	67
LT .....	57	61	61	60	62	59	61
$F_{cy}$ , ksi:							
L .....	61	65	65	65	67	65	67
LT .....	62	66	66	65	67	64	66
$F_{su}$ , ksi .....	38	40	41	41	42	40	41
$F_{bru}^b$ , ksi:							
(e/D = 1.5) .....	103	107	109	109	110	109	110
(e/D = 2.0) .....	131	137	139	139	141	139	141
$F_{bry}^b$ , ksi:							
(e/D = 1.5) .....	82	88	88	88	90	88	90
(e/D = 2.0) .....	98	104	104	104	107	104	107
$e$ , percent (S-basis):							
L .....	7	...	7	7	...	7	...
$E$ , 10 <sup>3</sup> ksi .....	10.4						
$E_c$ , 10 <sup>3</sup> ksi .....	10.7						
$G$ , 10 <sup>3</sup> ksi .....	4.0						
$\mu$ .....	0.33						
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> .....	0.101						
$C$ , $K$ , and $\alpha$ .....	See Figure 3.7.4.0						

a The mechanical properties are to be based upon the thickness at the time of quench.

b Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.4.0. Effect of temperature on the physical properties of 7075 aluminum alloy.**

## MIL-HDBK-5H

1 December 1998




Figure 3.7.4.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 7075-T6, T651, T6510, and T6511 aluminum alloy (all products). Note: Instructions for use of these curves are presented in Section 3.7.4.1.






Figure 3.7.4.1.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 7075-T6, T651, T6510, and T6511 aluminum alloy (all products). Note: Instructions for use of these curves are presented in Section 3.7.4.1.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.1.1(c). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of 7075-T6, T651, T6510, and T6511 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.1.1(d). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of 7075-T6, T651, T6510, and T6511 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.1.2(a). Effect of temperature on the compressive yield strength ( $F_{cy}$ ) of 7075-T6, T651, T6510, and T6511 aluminum alloy (all products).**




**Figure 3.7.4.1.2(b). Effect of temperature on the shear ultimate strength ( $F_{su}$ ) of 7075-T6, T651, T6510, and T6511 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.1.3(a). Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) of 7075-T6, T651, T6510, and T6511 aluminum alloy (all products).**




**Figure 3.7.4.1.3(b). Effect of temperature on the bearing yield strength ( $F_{bry}$ ) of 7075-T6, T651, T6510, and T6511 aluminum alloy (all products).**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of 7075 aluminum alloy.**




**Figure 3.7.4.1.5(a). Effect of temperature on the elongation of 7075-T6, T651, T6510, and T6511 aluminum alloy (all products except thick extrusions).**




**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.4.1.5(b). Effect of exposure at elevated temperatures on the elongation of 7075-T6, T651, T6510, and T6511 aluminum alloy (all products except thick extrusions).**




**Figure 3.7.4.1.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for clad 7075-T6 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for clad 7075-T6 aluminum alloy sheet at 200°F.**




**Figure 3.7.4.1.6(c). Typical compressive stress-strain and compressive tangent-modulus curves for clad 7075-T6 aluminum alloy sheet at 300°F.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.1.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for clad 7075-T6 aluminum alloy sheet at 400°F.**




**Figure 3.7.4.1.6(e). Typical compressive stress-strain and compressive tangent-modulus curves for clad 7075-T6 aluminum alloy sheet at 500°F.**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.1.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for clad 7075-T6 aluminum alloy sheet at 600°F.**



**Figure 3.7.4.1.6(g). Typical tensile stress-strain curves for 7075-T651 aluminum alloy plate at room temperature.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.4.1.6(h). Typical compressive stress-strain and compressive tangent-modulus curves for 7075-T651 aluminum alloy plate at room temperature.**




**Figure 3.7.4.1.6(i). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 7075-T62 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.1.6(j). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 7075-T6 and T651 aluminum alloy rolled-bar, rod, and shape at room temperature.**




**Figure 3.7.4.1.6(k). Typical tensile stress-strain curves for 7075-T651X aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.1.6(l). Typical compressive stress-strain and compressive tangent-modulus curve for 7075-T651X aluminum alloy extrusion at room temperature.**



**Figure 3.7.4.1.6(m). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 7075-T62 aluminum alloy extrusion at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.4.1.6(n). Typical tensile stress-strain curve (full range) for clad 7075-T6 aluminum alloy sheet at room temperature.**




**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.1.6(o). Typical tensile stress-strain curve (full range) for 7075-T6 and T651 aluminum alloy rolled or cold-finished bar at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.4.1.6(p). Typical tensile stress-strain curves (full range) for 7075-T651X aluminum alloy extrusion at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.4.1.6(q). Typical tensile stress-strain curves (full range) for 7075-T62 aluminum alloy extrusion at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.4.1.8(a). Best-fit S/N curves for unnotched 7075-T6 aluminum alloy, various product forms, longitudinal direction.**

Correlative Information for Figure 3.7.4.1.8(a)

Product Form: 3/4-inch diam. drawn rod, 1-1/4-inch diam. rolled rod, and 1 x 7-1/2-inch bar, extruded 1-1/4-inch bar and 1-1/4-inch rod

Test Parameters:

Loading - Axial  
Frequency - 30 Hz  
Temperature - RT  
Environment - Air

Properties: TUS, ksi TYS, ksi Temp., °F

82 72 RT

No. of Heats/Lots: 8

Specimen Details: Unnotched  
Minimum diameter 0.200-inch

Equivalent Stress Equation:

$$\log N_f = 18.21 - 7.73 \log (S_{eq} - 10)$$

$$S_{eq} = S_{max} (1 - R)^{0.62}$$

$$R^2 = 81\%$$

Surface Condition: Unspecified


Sample Size = 130

Reference: 3.7.4.1.8

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.4.1.8(b). Best-fit S/N curves for notched,  $K_t = 1.6$ , 7075-T6 aluminum alloy rolled bar, longitudinal direction.**

Correlative Information for Figure 3.7.4.1.8(b)

Product Form: 1-1/8-inch diam. rolled bar

Test Parameters:

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                   99.2        —                RT

Loading - Axial  
 Frequency - 60 Hz  
 Temperature - RT  
 Atmosphere - Air

Specimen Details: Notched,  $K_t = 1.6$   
 Notch-root-radius = 0.100  
 Test section diameter (Net) = 0.400 inches  
 Gross diameter = 0.450 inch  
 60° groove

No. of Heats/Lots: 1

Equivalent Stress Equation:  
 $\log N_f = 8.28 - 2.62 \log (S_{eq} - 15)$   
 $S_{eq} = S_{max} (1-R)^{0.53}$   
 $R^2 = 82\%$

Surface Condition: Polished to 10 micro-inches


Sample Size = 34

Reference: 3.2.1.1.8(b)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.4.1.8(c). Best-fit S/N curves for notched,  $K_t = 3.4$ , 7075-T6 aluminum alloy rolled bar, longitudinal direction.**

Correlative Information for Figure 3.7.4.1.8(c)

Product Form: 1-1/8-inch diam. rolled bar

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial  
Frequency - 60 Hz  
Temperature - RT  
Atmosphere - Air

96.5 — RT

Specimen Details: Notched,  $K_t = 3.4$   
Notch-root-radius = 0.010  
Test section diameter (Net)  
= 0.400 inch  
Gross diameter = 0.450 inch  
60° groove

No. of Heats/Lots: 1

Equivalent Stress Equation:  
 $\log N_f = 9.19 - 3.60 \log (S_{eq} - 5)$   
 $S_{eq} = S_{max} (1-R)^{0.39}$   
 $R^2 = 87\%$

Surface Condition: Polished to 10 micro-inches


Sample Size = 48

Reference: 3.2.1.1.8(b)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.4.1.8(d). Best-fit S/N curves for unnotched 7075-T6 aluminum alloy sheet, longitudinal direction.**

Correlative Information for Figure 3.7.4.1.8(d)

Product Form: Bare sheet, 0.090-inch

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     82            76            RT

Specimen Details: Unnotched  
                                  0.5 to 1.0-inch width

Surface Condition: Electropolished  
                                  150 grit emery paper

References: 3.2.3.1.8(a) and (f)

Test Parameters:

Loading - Axial  
 Frequency - 300 to 1800 cpm  
 Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:


$\log N_f = 14.86 - 5.80 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.49}$   
 Standard Error of Estimate = 0.41  
 Standard Deviation in Life = 0.92  
 $R^2 = 80\%$

Sample Size = 176

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.4.1.8(e). Best-fit S/N curves for notched,  $K_t = 1.5$ , 7075-T6 aluminum alloy sheet, longitudinal direction.**

Correlative Information for Figure 3.7.4.1.8(e)

Product Form: Bare sheet, 0.090-inch

Properties:    TUS, ksi    TYS, ksi    Temp., °F

82	76	RT
		(unnotched)
87	—	RT
		(notched)

Specimen Details: Edge Notched  
 3.000-inches gross width  
 1.500-inches net width  
 0.760-inch notch radius  
 60° flank angle

Surface Condition: Electropolished

Reference: 3.2.3.1.8(d)

Test Parameters:

Loading - Axial  
 Frequency - 1100 to 1500 cpm  
 Temperature - RT  
 Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$\log N_f = 9.57 - 3.52 \log (S_{eq} - 18.7)$   
 $S_{eq} = S_{max} (1 - R)^{0.49}$   
 Standard Error of Estimate = 0.41  
 Standard Deviation in Life = 1.00  
 $R^2 = 83\%$


Sample Size = 30

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 3.7.4.1.8(f). Best-fit S/N curves for notched,  $K_t = 2.0$ , 7075-T6 aluminum alloy sheet, longitudinal direction.**

Correlative Information for Figure 3.7.4.1.8(f)

Product Form: Bare sheet, 0.090-inch

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	82	76	RT
			(unnotched)
	88	—	RT
			(notched)

Specimen Details: Notched

<u>Notch Type</u>	<u>Gross Width</u>	<u>Net Width</u>	<u>Notch Radius</u>
Center	4.50	1.50	1.50
Edge	2.25	1.50	0.3175
Fillet	2.25	1.50	0.1736

Surface Condition: Electropolished

References: 3.2.3.1.8(b) and (f)

Test Parameters:

Loading - Axial  
Frequency - 1100 to 1500 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:


$\log N_f = 7.50 - 2.46 \log (S_{eq} - 18.6)$   
 $S_{eq} = S_{max} (1 - R)^{0.54}$   
 Standard Error of Estimate = 0.31  
 Standard Deviation in Life = 0.85  
 $R^2 = 57\%$

Sample Size = 112

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.4.1.8(g). Best-fit S/N curves for notched,  $K_t = 4.0$ , 7075-T6 aluminum alloy sheet, longitudinal direction.**

Correlative Information for Figure 3.7.4.1.8(g)

Product Form: Bare sheet, 0.090-inch

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	82	76	RT
			(unnotched)
	82	—	RT
			(notched)

Specimen Details: Notched

<u>Notch</u>	<u>Gross</u>	<u>Net</u>	<u>Notch</u>
<u>Type</u>	<u>Width</u>	<u>Width</u>	<u>Radius</u>
Edge	2.25	1.500	0.057
Edge	4.10	1.500	0.070
Fillet	2.25	1.500	0.0195

Surface Condition: Electropolished

References: 3.2.3.1.8(b), (f), (g), and (h)

Test Parameters:

Loading - Axial  
Frequency - 1100 to 1800 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$$\log N_f = 10.2 - 4.63 \log (S_{eq} - 5.3)$$

$$S_{eq} = S_{max} (1-R)^{0.51}$$

Standard Error of Estimate = 0.51

Standard Deviation in Life = 1.08


$R^2 = 78\%$

Sample Size = 126

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.4.1.8(h). Best-fit S/N curves for notched,  $K_t = 5.0$ , 7075-T6 aluminum alloy sheet, longitudinal direction.**

Correlative Information for Figure 3.7.4.1.8(h)

Product Form: Bare sheet, 0.090-inch

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	82	76	RT (unnotched)
	77	—	RT (notched)

Specimen Details: Edge Notched  
2.25-inch gross width  
1.500-inch net width  
0.3125-inch notch radius

Surface Condition: Electropolished

Reference: 3.2.3.1.8(c)

Test Parameters:

Loading - Axial  
Frequency - 1100 to 1500 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$$\log N_f = 7.51 - 2.92 \log (S_{eq} - 6.7)$$

$$S_{eq} = S_{max} (1 - R)^{0.58}$$

Standard Error of Estimate = 0.23


Standard Deviation in Life = 1.08

$R^2 = 95\%$

Sample Size = 37

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

MIL-HDBK-5H  
1 December 1998



**Figure 3.7.4.1.9. Fatigue-crack-propagation data for 0.090-inch-thick 7075-T6 aluminum alloy sheet with buckling restraint [References 3.7.4.1.9(a) through (e)].**

Specimen Thickness: 0.090 inch

Environment: Lab air

Specimen Width: 1-1/2 - 12 inches

Temperature: RT

Specimen Type: M(T)

Orientation: L-T

MIL-HDBK-5H  
1 December 1998




Figure 3.7.4.1.10(a). Residual strength behavior of 0.063-inch-thick 7075-T6 aluminum alloy sheet at room temperature. Crack orientation is T-L [Reference 3.1.2.1.6(f)].




Figure 3.7.4.1.10(b). Residual strength behavior of 0.063-inch-thick 7075-T6 aluminum alloy sheet at room temperature. Crack orientation is T-L [References 3.1.2.1.6(d) and (f)].

MIL-HDBK-5H  
1 December 1998




Figure 3.7.4.10(c). Residual strength behavior of 0.090- and 0.100-inch-thick 7075-T6 aluminum alloy sheet at room temperature. Crack orientation is L-T [References 3.1.2.1.6(e), (g), and 3.7.4.1.9(e)].




Figure 3.7.4.10(d). Residual strength behavior of 0.100-inch-thick 7075-T6 aluminum alloy sheet at room temperature. Crack orientation is L-T [Reference 3.1.2.1.6(g)].

MIL-HDBK-5H  
1 December 1998




Figure 3.7.4.1.10(e). Residual strength behavior of 0.313-inch-thick 7075-T6 aluminum alloy plate at room temperature. Crack orientation is L-T [Reference 3.1.2.1.6(g)].




Figure 3.7.4.1.10(f). Residual strength behavior of 0.040-inch-thick 7075-T6 clad aluminum alloy sheet at room temperature. Crack orientation is L-T [References 3.1.2.1.6(f) and 3.7.4.1.10(f)].

MIL-HDBK-5H  
1 December 1998




Figure 3.7.4.1.10(g). Residual strength behavior of 0.080-inch-thick 7075-T6 clad aluminum alloy sheet at room temperature. Crack orientation is L-T [References 3.1.2.1.6(h) and (i)].






Figure 3.7.4.1.10(h). Residual strength behavior of 0.090-inch-thick 7075-T6 clad aluminum alloy sheet at room temperature. Crack orientation is L-T [Reference 3.7.4.1.10(f)].




**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.4.2.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 7075-T73 aluminum alloy extrusion at room temperature.**




**Figure 3.7.4.2.6(b). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for 7075-T7351X aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.4.2.6(c). Typical tensile stress-strain curves for 7075-T7352 aluminum alloy hand forging at room temperature.**




**Figure 3.7.4.2.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for 7075-T7352 aluminum alloy hand forging at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.4.2.6(e). Typical tensile stress-strain curves (full range) for 7075-T7351X aluminum alloy extrusion at room temperature.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.4.2.6(f). Typical tensile stress-strain curves (full range) for 7075-T73 aluminum alloy extrusion at room temperature.**

## MIL-HDBK-5H

1 December 1998




**Figure 3.7.4.2.9(a). Fatigue-crack-propagation data for 0.250-inch-thick, 7075-T7351 aluminum alloy plate with buckling restraint [References 3.2.5.1.9(d) and 3.7.4.2.9(a)].**

Specimen Thickness: 0.250-inch  
 Specimen Width: 8, 16, 36-inches  
 Specimen Type: M(T)

Environment: 50% R.H.  
 Temperature: RT  
 Orientation: L-T

MIL-HDBK-5H  
1 December 1998




**Figure 3.7.4.2.9(b).** Fatigue-crack-propagation data for 0.500-inch-thick, 7075-T7351 aluminum alloy plate with buckling restraint [References 3.1.2.1.6(j) and 3.7.4.2.9(a) through (c)].

Specimen Thickness: 0.475 to 0.500-inch  
Specimen Width: 6, 8, 16, 36-inches  
Specimen Type: M(T)

Environment: 50-95% R.H.  
Temperature: RT  
Orientation: L-T

MIL-HDBK-5H  
1 December 1998



**Figure 3.7.4.2.9(c). Fatigue-crack-propagation data for 1.00-inch-thick, 7075-T7351 aluminum alloy plate without buckling restraint [References 3.2.5.1.9(d) and 3.7.4.2.9(a) and (b)].**

Specimen Thickness: 1.00-inch  
Specimen Width: 6, 8, 16, 36-inches  
Specimen Type: M(T), C(T)

Environment: 50% R.H.  
Temperature: RT  
Orientation: L-T

MIL-HDBK-5H  
1 December 1998




Figure 3.7.4.2.10(a). Residual strength behavior of 0.600-inch-thick 7075-T7351 aluminum alloy plate at room temperature. Crack orientation is L-T [Reference 3.1.2.1.6(g)].




Figure 3.7.4.2.10(b). Residual strength behavior of 1.00-inch-thick 7075-T7351 aluminum alloy plate at room temperature. Crack orientation is L-T [Reference 3.1.2.1.6(i)].



**MIL-HDBK-5H****1 December 1998****3.7.5 7150 ALLOY**

**3.7.5.0 Comments and Properties** — 7150, a second-generation version of 7050, is an Al-Zn-Mg-Cu-Zr alloy developed to provide higher strength properties than 7050 in thicknesses through 3 inches. 7150 is available in the form of plate and extrusion. The T61-type temper provides high strength with guaranteed levels of fracture toughness for plate. The T77-type temper provides high strength with guaranteed toughness and corrosion resistance. The T77-type temper has exfoliation and stress-corrosion resistance comparable to the T76-type temper of the other 7000 series aluminum alloys. Refer to Section 3.1.2.3 for further comments regarding resistance of the alloy to stress-corrosion cracking.

The properties of extrusions should be based upon the thickness at the time of quenching prior to machining. Selection of the mechanical properties based upon its final machined thickness may be unconservative; therefore, the thickness at the time of quenching to achieve properties is an important factor in the selection of the proper thickness column. For extrusions having sections with various thicknesses, consideration should be given to the properties as a function of thickness.

Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

Material specifications for 7150 are shown in Table 3.7.5.0(a). Room-temperature mechanical properties are presented in Tables 3.7.5.0(b<sub>1</sub>) through (c<sub>2</sub>).

**Table 3.7.5.0(a). Material Specifications for 7150 Aluminum Alloy**

Specification	Form
AMS 4306	Bare plate
AMS 4252	Bare plate
AMS 4307	Extrusion
AMS 4345	Extrusion

The temper index for 7150 is as follows:

<u>Section</u>	<u>Temper</u>
3.7.5.1	T6151 and T61511
3.7.5.2	T7751 and T77511

**3.7.5.1 T6151 and T61511 Tempers** — Figures 3.7.5.1.6(a) and (b) present stress-strain and tangent-modulus curves for bare plate. Figures 3.7.5.1.6(c) and (d) depict stress-strain and tangent-modulus curves for extrusion.

**3.7.5.2 T7751 and T77511 Tempers** — Figures 3.7.5.2.6(a) and (b) present stress-strain and tangent-modulus curves for bare plate. Figures 3.7.5.2.6(c) and (d) depict stress-strain and tangent-modulus curves for extrusion.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.7.5.0(b<sub>1</sub>). Design Mechanical and Physical Properties of 7150 Plate**

Specification .....	AMS 4306			
Form .....	Plate			
Temper .....	T6151			
Thickness, in. ....	0.750-1.000		1.001-1.500	
Basis .....	A	B	A	B
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	85	87	86	87
LT .....	84	87	85	86
$F_{ty}$ , ksi:				
L .....	79	81	80	81
LT .....	77	79	76	78
$F_{cy}$ , ksi:				
L .....	77	80	75	77
LT .....	81	83	80	82
$F_{su}$ , ksi .....	45	47	46	46
$F_{bru}^a$ , ksi:				
(e/D = 1.5) .....	121	125	123	124
(e/D = 2.0) .....	155	160	156	158
$F_{bry}^a$ , ksi:				
(e/D = 1.5) .....	102	105	101	104
(e/D = 2.0) .....	119	122	118	121
$e$ , percent (S-basis):				
L .....	9	...	9	...
LT .....	9	...	9	...
$E$ , $10^3$ ksi .....	10.2			
$E_c$ , $10^3$ ksi .....	10.6			
$G$ , $10^3$ ksi .....	3.9			
$\mu$ .....	0.33			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.102			
$C$ , Btu/(lb)(°F) .....	...			

a Bearing values are "dry pin" values per Section 1.4.7.1. See Table 3.1.2.1.1.

**MIL-HDBK-5H****1 December 1998****Table 3.7.5.0(b<sub>2</sub>). Design Mechanical and Physical Properties of 7150 Plate—Continued**

Specification . . . . .	AMS 4252			
Form . . . . .	Plate			
Temper . . . . .	T7751			
Thickness, in. . . . .	0.250-0.499	0.500-0.749	0.750-1.500	1.501-3.000
Basis . . . . .	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L . . . . .	80	83	84	82
LT . . . . .	80	83	84	82
ST . . . . .	...	...	...	77
$F_{ty}$ , ksi:				
L . . . . .	74	77	78	76
LT . . . . .	74	76	77	75
ST . . . . .	...	...	...	67
$F_{cy}$ , ksi:				
L . . . . .	74	76	77	75
LT . . . . .	77	79	81	79
$F_{su}$ , ksi . . . . .	46	47	48	47
$F_{bru}^a$ , ksi:				
(e/D = 1.5) . . . . .	119	124	125	122
(e/D = 2.0) . . . . .	154	160	162	158
$F_{bry}^a$ , ksi:				
(e/D = 1.5) . . . . .	102	105	106	104
(e/D = 2.0) . . . . .	117	120	121	118
$e$ , percent:				
L . . . . .	8	8	8	7
LT . . . . .	8	8	8	6
ST . . . . .	...	...	...	1
$E$ , 10 <sup>3</sup> ksi . . . . .	10.3			
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.7			
$G$ , 10 <sup>3</sup> ksi . . . . .	3.9			
$\mu$ . . . . .	0.33			
Physical Properties:				
$\omega$ , lb./in. <sup>3</sup> . . . . .	0.102			
$C$ , $K$ , and $\alpha$ . . . . .	...			

a Bearing values are “dry pin” values per Section 1.4.7.1. See Table 3.1.2.1.1.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.7.5.0(c<sub>1</sub>). Design Mechanical and Physical Properties of 7150 Aluminum Alloy Extrusion**

Specification .....	AMS 4307					
Form .....	Extrusion					
Temper .....	T61511					
Thickness or diameter, <sup>b</sup> in ....	0.250- 0.499	0.500- 0.749	0.750- 0.999	1.000- 1.499		1.500- 2.000
Basis .....	S	S	S	A	B	S
Mechanical Properties:						
$F_{tu}$ , ksi:						
L .....	87	88	89	89	94	89
LT .....	80	79	79	85	86	74
$F_{ty}$ , ksi:						
L .....	82	83	84	83	88	84
LT .....	73	73	73	77	78	68
$F_{cy}$ , ksi:						
L .....	80	81	82	82	87	84
LT .....	80	80	80	77	81	75
$F_{su}$ , ksi .....	44	45	45	44	46	42
$F_{bru}$ <sup>a</sup> , ksi:						
(e/D = 1.5) .....	119	120	120	118	125	116
(e/D = 2.0) .....	152	153	154	152	161	150
$F_{bry}$ <sup>a</sup> , ksi:						
(e/D = 1.5) .....	100	100	100	96	102	94
(e/D = 2.0) .....	118	120	120	117	124	117
$e$ , percent (S-basis):						
L .....	8	9	8	8	...	8
$E$ , 10 <sup>3</sup> ksi .....	10.4					
$E_c$ , 10 <sup>3</sup> ksi .....	11.0					
$G$ , 10 <sup>3</sup> ksi .....	4.0					
$\mu$ .....	0.33					
Physical Properties:						
$\omega$ , lb/in. <sup>3</sup> .....	0.102					
$C$ , $K$ , and $\alpha$ .....	...					

a Bearing values are "dry pin" values per Section 1.4.7.1.

b The mechanical properties are to be based upon the thickness at the time of quench.

**MIL-HDBK-5H**  
**1 December 1998**


**Table 3.7.5.0(c<sub>2</sub>). Design Mechanical and Physical Properties of 7150 Aluminum Alloy Extrusion—Continued**

Specification .....	AMS 4345			
Form .....	Extrusion			
Temper .....	T77511			
Cross-Sectional Area, in <sup>2</sup> .....	≤20			
Thickness or Diameter, <sup>b</sup> in. ...	≤0.249	0.250-0.499	0.500-0.749	0.750-2.000
Basis .....	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	85	87	88	89
LT .....	81	82	83	83
$F_{ty}$ , ksi:				
L .....	78	82	83	84
LT .....	74	76	79	78
$F_{cy}$ , ksi:				
L .....	78	82	83	84
LT .....	76	80	81	82
$F_{su}$ , ksi .....	44	45	46	46
$F_{bru}^a$ , ksi:				
(e/D = 1.5) .....	122	124	125	123
(e/D = 2.0) .....	158	161	162	159
$F_{bry}^a$ , ksi:				
(e/D = 1.5) .....	100	105	106	108
(e/D = 2.0) .....	118	124	125	127
$e$ , percent:				
L .....	7	8	9	8
$E$ , 10 <sup>3</sup> ksi .....	10.4			
$E_c$ , 10 <sup>3</sup> ksi .....	10.9			
$G$ , 10 <sup>3</sup> ksi .....	4.0			
$\mu$ .....	0.33			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.102			
$C$ , $K$ , and $\alpha$ .....	...			


a Bearing values are “dry pin” values per Section 1.4.7.1.

b The mechanical properties are to be based upon the thickness at the time of quench.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.5.1.6(a). Typical tensile stress-strain curves for 7150-T6151 aluminum alloy plate at room temperature.**




**Figure 3.7.5.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 7150-T6151 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.5.1.6(c). Typical tensile stress-strain curves for 7150-T61511 aluminum alloy extrusion at room temperature.**




**Figure 3.7.5.1.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for 7150-T61511 aluminum alloy extrusion at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.5.2.6(a). Typical tensile stress-strain curves for 7150-T7751 aluminum alloy plate at room temperature.**




**Figure 3.7.5.2.6(b). Typical compressive stress-strain and tangent-modulus curves for 7150-T7751 aluminum alloy plate at room temperature.**




**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.5.2.6(c). Typical tensile stress-strain curves for 7150-T77511 aluminum alloy extrusion at room temperature.**



**Figure 3.7.5.2.6(d). Typical compressive stress-strain and tangent-modulus curves for 7150-T77511 aluminum alloy extrusion.**

**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.5.2.8(a). Best-fit S/N curves for unnotched 7150-T77511 aluminum alloy extrusion, longitudinal orientation.**

Correlative Information for Figure 3.7.5.2.8(a).

Product Forms: Extruded shape, 1.125-inch,  
1.45-inch

Properties:      TUS, ksi   TYS, ksi   Temp., °F  
                     89        84        RT

Specimen Details:    Unnotched  
                                 Round, 0.3-inch diameter,  
                                 removed from center of  
                                 section

Surface Condition:   Polished to 10 micro-inch or  
                                 better

Reference:              3.7.5.2.8

Test Parameters:

Loading - Axial  
Frequency - 25 Hz  
Temperature - RT  
Environment - Air

No. of Heats/Lots:    2


Fatigue Life Equation:

$\text{Log } N_f = 21.89 - 9.32 \log (S_{\max})$   
Standard Error of Estimate,  $\log (\text{Life})$ : 0.321

Adjusted R<sup>2</sup>:    81.8%

Sample Size:        16

(Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios and maximum stress beyond those represented above.)

**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.5.2.8(b). Best-fit S/N curves for unnotched 7150-T77511 aluminum alloy extrusion, long transverse orientation.**

Correlative Information for Figure 3.7.5.2.8(b).

Product Forms: Extruded shape, 1.125-inch,  
1.45-inch

Properties: TUS, ksi TYS, ksi Temp., °F  
83 78 RT

Specimen Details: Unnotched  
Round, 0.3-inch diameter,  
removed from center of  
section

Surface Condition: Polished to 10 micro-inch  
or better

Reference: 3.7.5.2.8

Test Parameters:

Loading - Axial  
Frequency - 25 Hz  
Temperature - RT  
Environment - Air

No. of Heats/Lots: 2

Fatigue Life Equation:

$$\log N_f = 17.98 - 7.57 \log (S_{\max})$$

Standard Deviation in log (life): 22.53 (1/S<sub>max</sub>)


Adjusted R<sup>2</sup>: 74.4 %

Sample Size: 10

(Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios and maximum stress beyond those represented above.)

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.5.2.8(c). Best-fit S/N curves for notched,  $K_t = 3.0$ , 7150-T77511 aluminum alloy extrusion, longitudinal and long transverse orientations.**

Correlative Information for Figure 3.7.5.2.8(c).

Product Forms: Extruded shape, 1.125-inch, 1.45-inch

Properties:

	TUS, ksi	TYS, ksi	Temp., °F
Longitudinal	89	84	RT
Long Transverse	83	78	RT

Specimen Details: Circumferentially notched,  $K_t = 3.0$  round, 0.253-inch net diameter, 0.013-inch root radius, removed from center of section

Surface Condition: Notch

Reference: 3.7.5.2.8

Test Parameters:

Loading - Axial  
Frequency - 25 Hz  
Temperature - RT  
Environment - Air

No. of Heats/Lots: 2

Fatigue Life Equation:

$$\log N_f = 5.71 - 1.31 \log (S_{\max} - 16.92)$$

Standard Error of Estimate, log (Life):

$$4.51 (1/S_{\max})$$

Adjusted  $R^2$ : 92.4%

Sample Size: 25

(Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios and maximum stress beyond those represented above.)

**MIL-HDBK-5H****1 December 1998****3.7.6 7175 ALLOY**

**3.7.6.0 Comments and Properties** — 7175 is a high-purity, high-strength Al-Zn-Mg-Cu alloy. In the form of die forgings the alloy is available in the T66, T74, and T7452 tempers. Die forgings of 7175-T66 develop higher static strength than 7075-T6 forgings with fatigue, fracture, and stress-corrosion properties about equivalent to those of 7075-T6 forgings. 7175-T74-type die and hand forgings develop static strengths about equivalent to those of 7075-T6 forgings, with toughness and fatigue properties equal or superior to those of 7075-T73 forgings. The T74-type temper provides stress-corrosion resistance and strength characteristics intermediate to those of T76 and T73 in 7075. Refer to Section 3.1.2.3 for comments regarding the resistance of the alloy to stress-corrosion cracking, and to Section 3.1.3.4 for comments regarding the weldability of the alloy.

The properties of extrusions should be based upon the thickness at the time of quenching prior to machining. Selection of the mechanical properties based upon its final machined thickness may be unconservative; therefore, the thickness at the time of quenching to achieve properties is an important factor in the selection of the proper thickness column. For extrusions having sections with various thicknesses, consideration should be given to the properties as a function of thickness.

Material specifications for 7175 are presented in Table 3.7.6.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.7.6.0(b) through (d).

**Table 3.7.6.0(a). Material Specifications for 7175 Aluminum Alloy**

Specification	Form
AMS 4148	Die forging
AMS 4149	Die and hand forging
AMS 4179	Hand forging
MIL-A-22771	Forging
AMS 4344	Extrusion

The temper index for 7175 is as follows:

<u>Section</u>	<u>Temper</u>
3.7.6.1	T73511
3.7.6.2	T74 and T7452 (formerly T736, T73652)

**3.7.6.1 T73511 Temper** — Figures 3.7.6.1.6(a) and (b) show tensile and compressive stress-strain and tangent-modulus curves for extrusion. Figures 3.7.6.1.8(a) through (d) present fatigue curves for extrusion.

**3.7.6.2 T74 and T7452 Tempers** — Figures 3.7.6.2.6(a) through (f) present tensile and compressive stress-strain and tangent-modulus curves for die and hand forging. Figures 3.7.6.2.8(a) and (b) present fatigue curves for die and hand forging.

**MIL-HDBK-5H****1 December 1998****Table 3.7.6.0(b). Design Mechanical and Physical Properties of 7175 Aluminum Alloy Die Forging**

Specification . . . . .	AMS 4148	AMS 4149						
Form . . . . .	Die forging							
Temper . . . . .	T66	T74 <sup>a,b</sup>						
Thickness, in. . . . .	≤3.000	<1.000	1.001- 2.000		2.001- 3.000	3.001- 4.000	4.001- 5.000	5.001- 6.000
Basis . . . . .	S	S	A	B	S	S	S	S
Mechanical Properties:								
<i>F<sub>tu</sub></i> , ksi:								
L . . . . .	86	76	74	77	76	73	70	68
T <sup>c</sup> . . . . .	77	71	71 <sup>d</sup>	...	71	70	68	65
<i>F<sub>ty</sub></i> , ksi:								
L . . . . .	76	66	64	67	66	63	61	58
T <sup>c</sup> . . . . .	66	62	62 <sup>d</sup>	...	62	60	58	55
<i>F<sub>cy</sub></i> , ksi:								
L . . . . .	...	67	65	68	67	...	...	...
ST . . . . .	...	63	61	64	63	...	...	...
<i>F<sub>su</sub></i> , ksi . . . . .	...	43	42	44	43	...	...	...
<i>F<sub>bru</sub></i> <sup>e</sup> , ksi:								
(e/D = 1.5) . . . . .	...	106	105	109	106	...	...	...
(e/D = 2.0) . . . . .	...	140	137	142	140	...	...	...
<i>F<sub>bry</sub></i> <sup>e</sup> , ksi:								
(e/D = 1.5) . . . . .	...	86	84	88	86	...	...	...
(e/D = 2.0) . . . . .	...	102	99	103	102	...	...	...
<i>e</i> , percent (S-basis):								
L . . . . .	7	7	7	...	7	7	7	7
T <sup>c</sup> . . . . .	4	4	4	...	4	4	4	4
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	10.2							
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	10.7							
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	3.9							
<i>μ</i> . . . . .	0.33							
Physical Properties:								
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.101							
<i>C</i> , Btu/(lb)(°F) . . . . .	0.23 (at 212°F)							
<i>K</i> , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	76 (at 77°F for T66); 90 (at 77°F for T736)							
<i>α</i> , 10 <sup>-6</sup> in./in./°F . . . . .	12.9 (68 to 212°F)							

a When die forgings are machined before heat treatment, section thickness at time of heat treatment shall determine minimum mechanical properties as long as original (as-forged) thickness does not exceed maximum thickness for the alloy as shown in the table.

b Design allowables were based upon data obtained from testing die forgings, heat treated by suppliers, and supplied in T74 temper.

c T indicates any grain direction not within  $\pm 15^\circ$  of being parallel to the forging flow lines.  $F_{cy}(T)$  values are based upon short transverse (ST) test data.

d Specification value. T tensile properties are presented on an S basis only.

e Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 3.7.6.0(c<sub>1</sub>). Design Mechanical and Physical Properties of 7175 Aluminum Alloy Hand Forging**

Specification	AMS 4149 and MIL-A-22771				
Form	Hand forging				
Temper	T74				
Thickness or Diameter <sup>a,b</sup> , in.	1.001-2.000	2.001-3.000	3.001-4.000	4.001-5.000	5.001-6.000
Basis	S	S	S	S	S
Mechanical Properties:					
$F_{tu}$ , ksi:					
L	73	73	71	68	65
LT	71	71	70	67	64
ST	...	69	68	66	63
$F_{ty}$ , ksi:					
L	63	63	61	57	54
LT	60	60	58	56	52
ST	...	60	57	55	52
$F_{cy}$ , ksi:					
L	63	63	61	59	55
LT	62	63	61	60	56
ST	61	62	60	59	55
$F_{su}$ , ksi:					
L	43	43	43	41	39
LT	42	42	41	39	38
ST	42	42	41	39	38
$F_{bru}^c$ , ksi:					
(e/D = 1.5)	106	106	104	100	95
(e/D = 2.0)	138	138	136	131	125
$F_{bry}^c$ , ksi:					
(e/D = 1.5)	73	78	80	81	76
(e/D = 2.0)	89	94	95	95	90
$e$ , percent:					
L	9	9	9	8	8
LT	5	5	5	5	5
ST	...	4	4	4	4
$E$ , 10 <sup>3</sup> ksi	10.2				
$E_c$ , 10 <sup>3</sup> ksi	10.6				
$G$ , 10 <sup>3</sup> ksi	3.9				
$\mu$	0.33				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup>	0.101				
$C$ , Btu/(lb)(°F)	0.23 (at 212°F)				
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	90 (at 77°F)				
$\alpha$ 10 <sup>-6</sup> in./in./°F	12.9 (68 to 212°F)				

a When hand forgings are machined before heat treatment, the section thickness at time of heat treatment shall determine the minimum mechanical properties as long as the original (as-forged) thickness does not exceed the maximum thickness for the alloy as shown in the table.

b The maximum cross-sectional area of hand forgings in 256 sq. in.

c Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 3.7.6.0(c<sub>2</sub>). Design Mechanical and Physical Properties of 7175 Aluminum Alloy Hand Forging—Continued**

Hand Forging Conditions	AMS 4149 and MIL-A-22771				
Specification .....	Hand forging				
Form .....	T7452				
Temper .....					
Thickness or Diameter <sup>a</sup> , in. . .	1.001- 2.000	2.001- 3.000	3.001- 4.000	4.001- 5.000	5.001- 6.000
Basis .....	S	S	S	S	S
Mechanical Properties:					
$F_{tu}$ , ksi:					
L .....	71	71	68	65	63
LT .....	69	69	67	64	61
ST .....	...	67	65	63	60
$F_{ty}$ , ksi:					
L .....	61	61	57	54	51
LT .....	58	58	55	52	49
ST .....	...	54	51	49	46
$F_{cy}$ , ksi:					
L .....	58	58	55	52	49
LT .....	61	61	57	54	50
ST .....	60	60	57	54	51
$F_{su}$ , ksi:					
L .....	38	39	39	38	37
LT .....	38	39	38	38	36
ST .....	40	41	40	39	38
$F_{bru}^b$ , ksi:					
(e/D = 1.5) .....	102	102	99	95	90
(e/D = 2.0) .....	133	133	130	124	118
$F_{bry}^b$ , ksi:					
(e/D = 1.5) .....	80	82	80	76	72
(e/D = 2.0) .....	95	98	95	92	87
$e$ , percent:					
L .....	9	9	9	8	8
LT .....	5	5	5	5	5
ST .....	...	4	4	4	4
$E$ , 10 <sup>3</sup> ksi .....	10.2				
$E_c$ , 10 <sup>3</sup> ksi .....	10.5				
$G$ , 10 <sup>3</sup> ksi .....	3.9				
$\mu$ .....	0.33				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> .....	0.101				
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)				
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] ....	90 (AT 77°F)				
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	12.9 (68 to 212°F)				

a The maximum cross-sectional area of hand forgings is 256 sq.in.

b Bearing values are "dry pin" values per Section 1.4.7.1.




**MIL-HDBK-5H****1 December 1998****Table 3.7.6.0(d). Design Mechanical and Physical Properties of 7175 Aluminum Alloy Extrusion**

Specification .....	AMS 4344	
Form .....	Extrusion	
Condition .....	T73511	
Cross-Sectional Area, in <sup>2</sup> .....	32-65	
Thickness or Diameter, <sup>b</sup> in. ....	0.250-0.999	1.000-2.000
Basis .....	S	S
Mechanical Properties:		
$F_{tu}$ , ksi:		
L .....	69	69
LT .....	63	63
$F_{ty}$ , ksi:		
L .....	59	59
LT .....	52	52
$F_{cy}$ , ksi:		
L .....	...	59
LT .....	...	59
$F_{su}$ , ksi .....	...	40
$F_{bru}^a$ , ksi:		
(e/D = 1.5) .....	...	97
(e/D = 2.0) .....	...	125
$F_{bry}^a$ , ksi:		
(e/D = 1.5) .....	...	79
(e/D = 2.0) .....	...	95
$e$ , percent:		
L .....	...	8
LT .....	...	4
$E$ , 10 <sup>3</sup> ksi .....	10.1	
$E_c$ , 10 <sup>3</sup> ksi .....	10.5	
$G$ , 10 <sup>3</sup> ksi .....	3.9	
$\mu$ .....	0.33	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> .....	0.101	
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)	
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	...	
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	12.9 (68 to 212°F)	


a Bearing values are "dry pin" values per Section 1.4.7.1.

b The mechanical properties are to be based upon the thickness at the time of quench.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.6.1.6(a). Typical tensile stress-strain curves for aluminum alloy 7175-T73511 extrusion at room temperature.**



**Figure 3.7.6.1.6(b). Typical compressive stress-strain and tangent-modulus curves for aluminum alloy 7175-T73511 extrusion at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.6.1.8(a). Best-fit S/N curves for unnotched 7175-T73511 alloy extrusion, longitudinal direction.**

Correlative Information for Figure 3.7.6.1.8(a)

Product Form: Extrusion 1.8-inch thick,  
extruded round, 3-3/4-inch  
diameter, extruded rectangle,  
2-1/2 x 5-inch thick, extrusion,  
unspecified size

Test Parameters:  
Loading - Axial  
Frequency - Not specified  
Temperature - 70°F  
Environment - Air

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
  
                    76            67            70

No. of Heats/Lots: 11

Specimen Details: 0.25-inch minimum diame-  
ter hourglass gage section  
30-inch diameter

Equivalent Stress Equation:  
 $\log N_f = 12.01 - 5.26 \log (S_{eq})$   
 $S_{eq} = S_a + 0.32 S_m - 15.04$   
Standard Deviation in Log (Life) =  
18.44(1/ $S_{eq}$ )  
Adjusted  $R^2 = 58\%$

Surface Condition: 32 RMS gage section  
specified


Sample Size = 96

References: 3.7.6.1.8(a), (b), and (c)

[Caution: The equivalent stress model may  
provide unrealistic life predictions for stress  
ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.6.1.8(b). Best-fit S/N curves for notched,  $K_t = 3.0$ , 7175-T73511 alloy extrusion, longitudinal direction.**

Correlative Information for Figure 3.7.6.1.8(b)

Product Form: Extrusion 1.8-inch thick, extruded round, 3-3/4-inch diameter, extruded rectangle, 2-1/2 x 5-inch thick, extrusion, unspecified size

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	76	67	70

Specimen Details: Circumferential notch,  $K_t = 3$   
 0.5-inch gross diameter  
 0.36-inch net diameter  
 0.0005-inch notch radius  
 Circumferential 60° V notch

References: 3.7.6.1.8(a), (b), and (c)

Test Parameters:

Loading - Axial  
 Frequency - Not specified  
 Temperature - 70°F  
 Environment - Air

No. of Heats/Lots: 11

Equivalent Stress Equation:


$\log N_f = 6.50 - 2.25 \log (S_{eq})$   
 $S_{eq} = S_a + 0.20 S_m - 7.21$   
 Standard Deviation in Log (Life) =  
 $3.92(1/S_{eq})$   
 Adjusted  $R^2 = 91\%$

Sample Size = 86

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.6.1.8(c). Best-fit S/N curves for notched,  $K_t = 5.0$ , 7175-T73511 alloy extrusion, longitudinal direction.**

Correlative Information for Figure 3.7.6.1.8(c)

Product Form: Extrusion 1.8-inch thick

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     76            67            70

Specimen Details: Circumferential notch,  $K_t = 5$   
                              0.5-inch gross diameter  
                              0.36-inch net diameter  
                              0.0005-inch notch radius

References: 3.7.6.1.8(a) and (b)

Test Parameters:

Loading - Axial  
 Frequency - Not specified  
 Temperature - 70°F  
 Environment - Air

No. of Heats/Lots: 10

Equivalent Stress Equation:

$$\log N_f = 7.12 - 2.78 \log (S_{eq})$$

$$S_{eq} = S_a + 0.28 S_m$$

$$\text{Standard Deviation in Log (Life)} = 3.71(1/S_{eq})$$


$$\text{Adjusted } R^2 = 90\%$$

Sample Size = 136

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.6.1.8(d). Best-fit S/N curves for notched,  $K_t = 7.0$ , 7175-T73511 alloy extrusion, longitudinal direction.**

Correlative Information for Figure 3.7.6.1.8(d)

Product Form: Extrusion 1.8-inch thick

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                      76            67            70

Specimen Details: Circumferential notch,  $K_t = 7$   
                              0.5-inch gross diameter  
                              0.36-inch net diameter  
                              0.0005-inch notch radius

References: 3.7.6.1.8(a) and (b)

Test Parameters:

Loading - Axial  
 Frequency - Not specified  
 Temperature - 70°F  
 Environment - Air


No. of Heats/Lots: 9

Equivalent Stress Equation:


$\log N_f = 7.15 - 2.78 \log (S_{eq})$   
 $S_{eq} = S_a + 0.27 S_m - 2.88$   
 Standard Deviation in Log (Life) =  
 $0.11 + 1.60 (1/S_{eq})$   
 Adjusted  $R^2 = 92\%$

Sample Size = 63

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]


**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.6.2.6(a). Typical tensile stress-strain curves for 7175-T74 aluminum alloy die forging at room temperature.**




**Figure 3.7.6.2.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 7175-T74 aluminum alloy die forging at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.6.2.6(c). Typical tensile stress-strain curves for 7175-T74 aluminum alloy hand forging at room temperature.**




**Figure 3.7.6.2.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for 7175-T74 aluminum alloy hand forging at room temperature.**



**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.6.2.6(e). Typical tensile stress-strain curves for aluminum alloy 7175-T7452 hand forging at room temperature.**



**Figure 3.7.6.2.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for aluminum alloy 7175-T7452 hand forging at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.6.2.8(a). Best-fit S/N curves for notched,  $K_t=3.0$ , 7175-T74 alloy die forging, longitudinal direction.**

Correlative Information for Figure 3.7.6.2.8(a)

Product Form: Die forging, 2.0 to 3.0-inch thick, unspecified thickness

Properties:    TUS, ksi    TYS, ksi

77-82      69-75

Specimen Details: Circumferential notch,  $K_t = 3$   
0.3-inch gross diameter  
0.25-inch net diameter  
Rectangular notched 0.10 x 0.20-inch

Surface Condition: Not specified

References:    3.2.5.1.9(d), 3.7.2.1.8(c), (d),  
3.7.6.2.8(a), (b), and (c)

Test Parameters:

Loading - Axial

Frequency - 1200 cpm unspecified

Temperature - 70°F

Environment - Air

No. of Heats/Lots: 13

Equivalent Stress Equation:

$\log N_f = 7.88 - 3.09 \log (S_{eq} - 7.15)$

$S_{eq} = S_a + 0.37 S_m$

Standard Deviation in Log (Life) =  
7.38 ( $1/S_{eq}$ )


Adjusted  $R^2 = 83\%$

Sample Size = 137

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.6.2.8(b). Best-fit S/N curves for unnotched 7175-T74 alloy hand forging, longitudinal and transverse directions.**

Correlative Information for Figure 3.7.6.2.8(b)

Product Form: Hand forging, 2.0 to 6.25-inch thick

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     71-77        60-68        70

Specimen Details: Uniform gage length  
                              3.0-inch diameter  
                              Hourglass gage section  
                              0.25-inch minimum  
                              diameter

References: 3.2.5.1.9(d) 3.7.2.1.8(c) and (d)

Test Parameters:

Loading - Axial  
 Frequency - 1200 cpm  
 Temperature - 20°F  
 Environment - Air

Equivalent Stress Equation:

$\log N_f = 21.15 - 9.49 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)$   
 Standard Deviation in Log (Life) =  
 $23.33(1/S_{eq})$   
 Adjusted  $R^2 = 76\%$

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998****3.7.7 7249 ALLOY**

**3.7.7.0 Comments and Properties** — 7249 is an Al-Zn-Mg-Cu-Cr alloy developed as a derivative from alloy 7149. Alloy 7249 has tighter compositional tolerances on its major constituents and lowered maximums on the interstitials such as Si, Fe, Mn, and Ti than alloy 7149.

7249-T7452 was developed as a replacement material for 7075-T6 forgings, which are susceptible to stress-corrosion cracking and exfoliation. 7249 also has higher strength at the higher thickness ranges and higher ductility than 7075-T6.

Material specifications for 7249 are shown in Table 3.7.7.0(a). Room temperature mechanical properties are shown in Table 3.7.7.0(b).

**Table 3.7.7.0(a). Material Specification for 7249 Alloy**

Specification	Form
AMS 4334	Hand forging

The temper index for 7249 is as follows:

Section  
3.7.7.1

Temper  
T7452

**3.7.7.1 T7452 Temper** — Figures 3.7.7.1.6(a) and (b) presents the typical tensile and compressive stress-strain curves and compressive tangent-modulus curves at room temperature. Figure 3.7.7.1.6(c) presents the full range stress-strain curves for hand forged material at room temperature.


**MIL-HDBK-5H****1 December 1998****Table 3.7.7.0(b). Design Mechanical and Physical Properties of 7249 Aluminum Alloy Hand Forging**

Specification . . . . .	AMS 4334									
Form . . . . .	Hand forging									
Temper . . . . .	T7452									
Thickness, in. . . . .	≤1.500	1.501-2.000	2.001-2.500	2.501-3.000	3.001-3.500	3.501-3.900	3.901-4.500	4.501-5.000	5.001-5.500	5.501-6.000
Basis . . . . .	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:										
$F_{tu}$ , ksi:										
L . . . . .	76	75	74	73	72	71	69	68	67	66
LT . . . . .	76	75	74	73	72	71	69	68	67	66
ST . . . . .	...	...	...	...	72	71	69	68	67	66
$F_{ty}$ , ksi:										
L . . . . .	68	67	66	64	63	61	59	58	56	55
LT . . . . .	68	67	66	64	63	61	59	58	56	55
ST . . . . .	...	...	...	...	59	58	57	56	54	53
$F_{cy}$ , ksi:										
L . . . . .	66	65	64	62	61	59	57	56	54	53
LT . . . . .	70	69	68	66	65	63	61	60	58	57
ST . . . . .	73	72	71	68	67	65	63	62	60	59
$F_{su}$ , ksi:										
L <sup>b</sup> . . . . .	49	48	47	47	46	46	44	44	43	42
LT <sup>b</sup> . . . . .	47	46	46	45	45	44	43	42	41	41
$F_{bru}^a$ , ksi:										
(e/D = 1.5) . . . . .	107	106	104	103	101	100	97	96	94	93
(e/D = 2.0) . . . . .	137	135	134	132	130	128	125	123	121	119
$F_{bry}^a$ , ksi:										
(e/D = 1.5) . . . . .	94	93	91	88	87	84	82	80	77	76
(e/D = 2.0) . . . . .	109	107	106	102	101	98	94	93	90	88
$e$ , percent:										
L . . . . .	12				12					
LT . . . . .	10				10					
ST . . . . .	...				5					
$E$ , 10 <sup>3</sup> ksi . . . . .	10.1									
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.4									
$G$ , 10 <sup>3</sup> ksi . . . . .	3.8									
$\mu$ . . . . .	0.33									
Physical Properties:										
$\omega$ , lb/in. <sup>3</sup> . . . . .	...									
$C$ , $K$ , and $\alpha$ . . . . .	...									


a Bearing values are “dry pin” values per Section 1.4.7.1.

b Determined in accordance with ASTM B769.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.7.1.6(a). Typical tensile stress-strain curves for 7249-T7452 aluminum alloy hand forging at room temperature.**



**Figure 3.7.7.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 7249-T7452 aluminum alloy hand forging at room temperature.**

MIL-HDBK-5H

1 December 1998




Figure 3.7.7.1.6(c). Typical tensile stress-strain curves (full range) for 7249-T7452 aluminum alloy hand forging at room temperature.

**MIL-HDBK-5H****1 December 1998****3.7.8 7475 ALLOY**

**3.7.8.0 Comments and Properties** — 7475 is an Al-Zn-Mg-Cu alloy developed for applications requiring the high strength of 7075 but having fracture toughness superior to that of 7075. Sheet is available in the T61 and T761 tempers and plate in the T651 and T7651 tempers. Sheet has strength approximately the same as that of 7075 combined with toughness about the same as 2024-T3 at room temperature. Plate has strengths similar to those of corresponding tempers of 7075; the toughness of 7475-T651 equals or exceeds that of 7075-T7351.

Resistance to stress-corrosion cracking and exfoliation are comparable to that of 7075. The T73-type temper provides for much improved stress-corrosion resistance over T6-type temper with a decrease in strength. The T76-type temper provides for improved exfoliation resistance and stress-corrosion resistance over T6-type temper with some decrease in strength. Refer to Section 3.1.2.3.1 for information regarding resistance to stress-corrosion cracking.

Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

Material specifications are shown in Table 3.7.8.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.7.8.0(b) through (d).

**Table 3.7.8.0(a). Material Specifications for 7475 Aluminum Alloy**

Specification	Form
AMS 4084	Bare sheet
AMS 4085	Bare sheet
AMS 4090	Bare plate
AMS 4089	Bare plate
AMS 4202	Bare plate
AMS 4207	Clad sheet
AMS 4100	Clad sheet

The temper index for 7475 is as follows:

<u>Section</u>	<u>Temper</u>
3.7.8.1	T61 and T651
3.7.8.2	T7351
3.7.8.3	T761 and T7651

**3.7.8.1 T61 and T651 Tempers** — Figures 3.7.8.1.6(a) through (f) present tensile and compressive stress-strain and tangent-modulus curves for T61 sheet and T651 plate. Figure 3.7.8.1.6(g) contains full-range tensile curves for T61 sheet. Fatigue data for sheet are shown in Figures 3.7.8.1.8(a) through (c). Graphical displays of the residual behavior strength of center-cracked panels are presented in Figures 3.7.8.1.10(a) through (d).

**3.7.8.2 T7351 Temper** — Figures 3.7.8.2.6(a) and (b) present tensile and compressive stress-strain and tangent-modulus curves for T7351 plate. Fatigue data for 7475-T7351 plate are presented in



**MIL-HDBK-5H**  
**1 December 1998**

Figures 3.7.8.2.8(a) and (b). Figures 3.7.8.2.9(a) and (b) present fatigue-crack-propagation data for T7351 plate.

**3.7.8.3 T761 and T7651 Tempers** — Figures 3.7.8.3.6(a) through (j) present tensile and compressive stress-strain and tangent-modulus curves for T761 bare and clad sheet and T7651 plate. Figures 3.7.8.3.6(k) and (l) contain full-range tensile stress-strain curves for T761 bare and clad sheet, respectively. Fatigue data for 7475-T761 sheet are presented in Figures 3.7.8.1.8(a) through (c). Fatigue data for 7475-T7651 plate are shown in Figure 3.7.8.2.8(b). Graphical displays of the residual strength behavior of center-cracked tension panels are presented in Figures 3.7.8.3.10(a) and (b).

**Table 3.7.8.0(b). Design Mechanical and Physical Properties of 7475 Aluminum Alloy Sheet and Plate**

Specification . . . . .	AMS 4084	AMS 4090			AMS 4085			AMS 4089		
Form . . . . .	Sheet	Plate			Sheet			Plate		
Temper . . . . .	T61	T651			T761			T7651		
Thickness, in. . . . .	0.040-0.249	0.250-0.499	0.500-1.000	1.001-1.500	0.040-0.062	0.063-0.187	0.188-0.249	0.250-0.499	0.500-1.000	1.001-1.500
Basis . . . . .	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:										
$F_{tu}$ , ksi:										
L . . . . .	75	77	77	77	71	71	71	70	69	69
LT . . . . .	75	78	78	78	71	71	71	71	70	70
$F_{ty}$ , ksi:										
L . . . . .	66	69	70	70	61	61	61	60	59	59
LT . . . . .	64	67	68	68	60	60	60	60	59	59
$F_{cy}$ , ksi:										
L . . . . .	64	67	68	67	60	59	58	60	59	59
LT . . . . .	68	70	71	71	61	63	63	63	62	59
$F_{su}$ , ksi . . . . .	45	44	43	41	43	42	41	41	39	37
$F_{bru}^a$ , ksi:										
(e/D = 1.5) . . . . .	120	113	113	113	112	112	111	104	103	103
(e/D = 2.0) . . . . .	154	144	144	144	143	143	142	136	134	134
$F_{bry}^a$ , ksi:										
(e/D = 1.5) . . . . .	97	91	93	93	90	90	90	82	81	81
(e/D = 2.0) . . . . .	110	106	107	107	104	104	104	97	95	95
$e$ , percent:										
L . . . . .	9	10	9	9	9	9	9	9	8	6
LT . . . . .	9	10	9	9	9	9	9	9	8	6
$E$ , 10 <sup>3</sup> ksi . . . . .	10.0	10.2			10.0			10.2		
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.5	10.6			10.5			10.6		
$G$ , 10 <sup>3</sup> ksi . . . . .	3.8	3.9			3.8			3.9		
$\mu$ . . . . .	0.33	0.33			0.33			0.33		
Physical Properties:										
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.101									
$C$ , $K$ , and $\alpha$ . . . . .	0.23 (at 212°F)									
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	80 (at 77°F) for T61 and T651; 90 (at 77°F) for T761 and T7651									
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . . . .	12.9 (68 to 212°F)									

a See Table 3.1.2.1.1. Bearing values are “dry pin” values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 3.7.8.0(c). Design Mechanical and Physical Properties of 7475 Aluminum Alloy Plate**

Specification . . . . .	AMS 4202											
Form . . . . .	Plate											
Temper . . . . .	T7351											
Thickness, in. . . . .	0.250-1.500		1.501-2.000		2.001-2.500		2.501-3.000		3.001-3.500		3.501-4.000	
Basis . . . . .	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:												
$F_{tu}$ , ksi:												
L . . . . .	70	72	70	71	68	70	68	69	64	67	64	66
LT . . . . .	71	73	70	72	68	70	68	69	64	68	64	67
ST . . . . .	66 <sup>b</sup>	70 <sup>b</sup>	65	69	65	69	65	68	63	67	63	66
$F_{ty}$ , ksi:												
L . . . . .	59	62	58	60	56	59	56	58	52	56	52	54
LT . . . . .	60	62	58 <sup>c</sup>	61	56	59	56	58	52	56	52	54
ST . . . . .	54 <sup>b</sup>	57 <sup>b</sup>	53	56	53	56	53	55	50	53	50	52
$F_{cy}$ , ksi:												
L . . . . .	58	60	56	59	54	57	53	55	49	53	49	51
LT . . . . .	61	63	60	63	58	61	58	60	54	58	54	56
ST . . . . .	62	64 <sup>b</sup>	60	63	58	61	58	60	54	58	54	56
$F_{su}$ , ksi . . . . .	41	42	42	43	41	42	41	42	39	42	39	41
$F_{bru}^a$ , ksi:												
(e/D = 1.5) . . . . .	102	105	103	106	101	104	101	103	97	102	97	101
(e/D = 2.0) . . . . .	132	136	134	138	131	135	131	134	125	133	125	131
$F_{bry}^a$ , ksi:												
(e/D = 1.5) . . . . .	81	84	82	86	81	84	81	84	77	82	77	80
(e/D = 2.0) . . . . .	97	101	97	102	95	100	95	99	89	96	89	93
$e$ , percent (S-basis):												
L . . . . .	10	...	10	...	10	...	10	...	10	...	9	...
LT . . . . .	9	...	8	...	8	...	8	...	8	...	7	...
ST . . . . .	4 <sup>b</sup>	...	4	...	4	...	3	...	3	...	3	...
$E$ , 10 <sup>3</sup> ksi . . . . .	10.3											
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.6											
$G$ , 10 <sup>3</sup> ksi . . . . .	3.9											
$\mu$ . . . . .	0.33											
Physical Properties:												
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.101											
$C$ , Btu/(lb)(°F) . . . . .	0.21 (at 212°F)											
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	94 (at 77°F)											
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . . . .	13.0 (68 to 212°F)											

a See Table 3.1.2.1.1. Bearing values are "dry pin" values per Section 1.4.7.1.

b Values applicable to 1.500-inch thickness only.

c S-basis. The rounded  $T_{99}$  value for  $F_{ty}(LT) = 59$  ksi.

**MIL-HDBK-5H****1 December 1998****Table 3.7.8.0(d). Design Mechanical and Physical Properties of Clad 7475 Aluminum Alloy Sheet**


Specification .....	AMS 4207				AMS 4100				
Form .....	Sheet								
Temper .....	T61				T761				
Thickness, in. ....	0.040-0.062	0.063-0.187	0.188-0.249	0.188-0.249	0.040-0.062	0.063-0.187	0.188-0.249	0.188-0.249	0.188-0.249
Basis .....	S	A	B	S	S	A	B	A	B
Mechanical Properties:									
$F_{tu}$ , ksi:									
L .....	69	69	73	72	66	67	70	68	71
LT .....	69	70	73	72	66	68	70	70	72
$F_{ty}$ , ksi:									
L .....	61	64	67	63	56	58	61	59	63
LT .....	59	60 <sup>b</sup>	64	61	55	57	60	60	62
$F_{cy}$ , ksi:									
L .....	60	61	65	62	55	56	59	58	60
LT .....	63	64	68	65	58	59	62	61	63
$F_{su}$ , ksi .....	42	40	41	39	41	40	41	40	41
$F_{bru}^a$ , ksi:									
(e/D = 1.5) .....	110	111	116	115	104	107	110	108	111
(e/D = 2.0) .....	140	142	148	146	133	136	140	138	142
$F_{bry}^a$ , ksi:									
(e/D = 1.5) .....	89	90	96	92	83	86	90	90	93
(e/D = 2.0) .....	102	104	111	106	97	101	106	106	110
$e$ , percent (S-basis):									
LT .....	9	9	...	9	9	9	...	9	...
$E$ , 10 <sup>3</sup> ksi:									
Primary .....	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0
Secondary .....	9.2	9.4	9.7	9.7	9.2	9.4	9.4	9.7	9.7
$E_c$ , 10 <sup>3</sup> ksi:									
Primary .....	10.5	10.5	10.5	10.5	10.5	10.5	10.5	10.5	10.5
Secondary .....	9.4	9.7	10.0	10.0	9.4	9.7	9.7	10.0	10.0
$G$ , 10 <sup>3</sup> ksi .....	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8
$\mu$ .....	0.33	0.33	0.33	0.33	0.33	0.33	0.33	0.33	0.33
Physical Properties:									
$\omega$ , lb/in. <sup>3</sup> .....	0.101								
$C, K, \alpha$ .....	...								

a Bearing values are "dry pin" values per Section 1.4.7.1.


b S-basis. The rounded  $T_{99}$  value is 61 ksi.

# MIL-HDBK-5H


1 December 1998




**Figure 3.7.8.1.6(a). Typical tensile stress-strain curves for 7475-T61 aluminum alloy sheet at room temperature.**



**Figure 3.7.8.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 7475-T61 aluminum alloy sheet at room temperature.**


**MIL-HDBK-5H****1 December 1998**

**Figure 3.7.8.1.6(c). Typical tensile stress-strain curves for clad 7475-T61 aluminum alloy sheet at room temperature.**




**Figure 3.7.8.1.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for clad 7475-T61 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.8.1.6(e). Typical tensile stress-strain curves for 7475-T651 aluminum alloy plate at room temperature.**



**Figure 3.7.8.1.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for 7475-T651 aluminum alloy plate at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.8.1.6(g). Typical tensile stress-strain curves (full range) for 7475-T61 aluminum alloy sheet at room temperature.**



## MIL-HDBK-5H

1 December 1998



**Figure 3.7.8.1.8(a). Best-fit S/N curve for unnotched 7475-T61 and T761 sheet, thickness  $\leq 0.125$  inch, longitudinal and long transverse directions.**

Correlative Information for Figure 3.7.8.1.8(a)

Product Form: Sheet, 0.032 to 0.125-inch thick

Test Parameters:

Properties:	TUS, ksi	TYS, ksi	Temp., °F
T61	81	73-75	RT
T761	77	68-70	RT

Loading - Axial

Frequency - 798, 1500, or 1728 cpm

Temperature - RT

Environment - Air

Specimen Details: Unnotched, hourglass,  
0.500-inch diameter  
4.00-inch test section radius, r

No. of Heats/Lots: 2

Surface Condition: As machined

Equivalent Stress Equation:

$\log N_f = 16.9 - 7.03 \log (S_{\max})$

Standard Error of Estimate = 0.545

Standard Deviation in Life = 0.988


$R^2=70\%$

Reference: 3.2.5.1.9(d)

Sample Size = 67

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.8.1.8(b). Best-fit S/N curve for unnotched 7475-T61 and T761 sheet, thickness  $\leq 0.125$  inch, longitudinal and long transverse directions.**

Correlative Information for Figure 3.7.8.1.8(b)

Product Form: Sheet, 0.032 to 0.125-inch thick

Test Parameters:

Properties:	TUS, ksi	TYS, ksi	Temp., °F
T61	80-81	73-76	RT
T761	75	66-67	RT

Loading - Axial

Frequency - 798, 1500, or 1728 cpm

Temperature - RT

Environment - Air

Specimen Details: Unnotched, hourglass,  
0.500-inch diameter  
4.00-inch test section

No. of Heats/Lots: 2

Equivalent Stress Equation:

$\log N_f = 16.9 - 7.03 \log (S_{\max})$

Standard Error of Estimate = 0.545

Standard Deviation in Life = 0.988

$R^2=70\%$

Surface Condition: Not specified


Reference: 3.2.5.1.9(d)

Sample Size = 67

(Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.)

## MIL-HDBK-5H

1 December 1998



**Figure 3.7.8.1.8(c). Best-fit S/N curve for notched,  $K_t = 3.0$ , 7475-T61 and T761 sheet, longitudinal and long transverse directions.**

Correlative Information for Figure 3.7.8.1.8(c)

Product Form: Sheet, 0.032 to 0.249-inch thick

Test Parameters:

Properties:	TUS, ksi	TYS, ksi	Temp., °F
T61	81-82	73-76	RT
T761	75-77	67-70	RT

Loading - Axial  
Frequency - 798, 1500, or 1728 cpm  
Temperature - RT  
Environment - Air

Specimen Details: Notched, edge notched  
 $K_t = 3.0$

No. of Heats/Lots: 2

1.000-inch gross width  
0.700-inch net width  
0.050-inch root radius,  $r$   
60° flank angle,  $\omega$

Equivalent Stress Equation:

$\log N_f = 13.4 - 6.29 \log (S_{max})$   
Standard Error of Estimate = 0.441  
Standard Deviation in Life = 0.931  
 $R^2 = 78\%$

Surface Condition: As machined

Sample Size = 99

Reference: 3.2.5.1.9(d)

(Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.)

MIL-HDBK-5H  
1 December 1998




Figure 3.7.8.10(a). Residual strength behavior of 0.063-inch-thick 7475-T61 aluminum alloy sheet at room temperature. Crack orientation is L-T. [References 3.1.2.1.6(d) and 3.2.5.1.9(d).]




Figure 3.7.8.10(b). Residual strength behavior of 0.063-inch-thick 7475-T61 aluminum alloy sheet at room temperature. Crack orientation is T-L. [References 3.1.2.1.6(d) and 3.2.5.1.9(d).]

MIL-HDBK-5H  
1 December 1998




Figure 3.7.8.1.10(c). Residual strength behavior of 0.063-inch-thick 7475-T61 clad aluminum alloy sheet at room temperature. Crack orientation is L-T. [Reference 3.2.5.1.9(d).]






Figure 3.7.8.1.10(d). Residual strength behavior of 0.063-inch-thick 7475-T61 clad aluminum alloy sheet at room temperature. Crack orientation is T-L. [Reference 3.2.5.1.9(d).]

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.8.2.6(a). Typical tensile stress-strain curves for 7475-T7351 aluminum alloy plate at room temperature.**




**Figure 3.7.8.2.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 7475-T7351 aluminum alloy plate at room temperature.**



## MIL-HDBK-5H

1 December 1998



**Figure 3.7.8.2.8(a). Best-fit S/N curves for unnotched 7475-T7351 plate, longitudinal and long transverse orientation.**

Correlative Information for Figure 3.7.8.2.8(a)

Product Form: Plate, 0.5, 1.0, 2.0, 3.0, and 4.0-inches thick

Properties: TUS, ksi    TYS, ksi    Temp., °F

L	70	60	RT
LT	71	60	RT

Specimen Details: Unnotched  
Hourglass, 0.300-inch net diameter  
9.875-inch test section radius

Surface Condition: As machined

References: 3.7.8.2.8(a) and (b)

Test Parameters:

Loading — Axial  
Frequency — Not specified  
Temperature — RT  
Environment — Air

No. of Heats/Lots: 5

Equivalent Stress Equation:

$\log N_f = 17.42 - 7.56 \log (S_{eq})$

$S_{eq} = S_{max}(1-R)^{0.40}$

Standard Error of Estimate = 0.433

Standard Deviation of Life = 0.857

$R^2 = 74\%$

Sample Size = 52

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

MIL-HDBK-5H

1 December 1998




Figure 3.7.8.2.8(b). Best-fit S/N curves for notched,  $K_t = 3.0$ , 7475-T7351 and T7651 plate, longitudinal and long transverse direction.

(See following page for correlative information.)



**MIL-HDBK-5H****1 December 1998**Correlative Information for Figure 3.7.8.2.8(b)Product Form: Plate, 0.5, 1.0, 1.5, 2.0, 3.0,  
and 4.0 inches thick

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
L (T7351)	70	60	RT [Ref. (a)]
LT (T7351)	71	61	RT [Ref. (b)]
L (T7351)	72	62	RT [Ref. (c)]
(T7651)	Not specified		[Ref. (d)]
L (T7351)	72	63	RT [Ref. (e)]
LT (T7351)	73	62	RT [Ref. (e)]

Specimen Details: Notched,  $K_t = 3.0$ 

Circumferentially notched [Ref. (a) and (b)]

0.253-inch gross width  
 0.147-inch net width  
 0.013-inch root radius, r  
 60° flank angle,  $\omega$

Edge notched [Ref. (c)]

1.00-inch gross width  
 0.70-inch net width  
 root radius not specified  
 60° flank angle,  $\omega$

Edge notched [Ref. (d)]

2.25-inch gross width  
 1.50-inch net width  
 0.113-inch root radius, r  
 60° flank angle,  $\omega$

Circumferentially notched [Ref. (e)]

1.375-inch gross width  
 0.25-inch net width  
 0.13-inch root radius, r  
 60° flank angle,  $\omega$

References: 3.7.8.2.8 (a) through (e)Surface Condition:

Not specified [Ref. (a) and (b)]

As machined and deburred [Ref. (c)]

32 RMS [Ref. (d)]

10 RMS [Ref. (e)]

Test Parameters:

Loading — Axial

Frequency

— Not specified [Ref. (a) and (b)]

— 1800 cpm [Ref. (c) and (d)]

— 1500 cpm [Ref. (e)]

Temperature — RT

Environment — Air

No. of Heats/Lots: 8Equivalent Strain Equation: $\log N_f = 8.46 - 3.21 \log (S_{eq} - 7.5)$  $S_{eq} = S_{max}(1-R)^{0.72}$ 

Standard Error of Estimate = 0.422

Standard Deviation of Life = 0.923

 $R^2 = 79\%$ Sample Size = 97

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

MIL-HDBK-5H  
1 December 1998





Figure 3.7.8.2.9(a). Fatigue-crack-propagation data for 1.5-inch-thick, 7475-T7351 aluminum alloy plate [References 3.7.8.2.9(a) and (b)].

Specimen Thickness:	0.650-inch	Environment:	Lab air
Specimen Width:	1.500-inches	Temperature:	RT
Specimen Type:	C(T)	Orientation:	L-T

MIL-HDBK-5H  
1 December 1998




**Figure 3.7.8.2.9(b). Fatigue-crack-propagation data for 0.500-inch-thick, 7475-T7351 aluminum alloy plate [Reference 3.7.4.2.9(c)].**


Specimen Thickness: 0.528 to 0.530-inch  
Specimen Width: 4.6-inches  
Specimen Type: M(T)

Environment: 95% R.H.  
Temperature: RT  
Orientation: L-T

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.8.3.6(a). Typical tensile stress-strain curves for 7475-T761 aluminum alloy sheet at room temperature.**




**Figure 3.7.8.3.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for 7475-T761 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.8.3.6(c). Typical tensile stress-strain curves for clad 7475-T761 aluminum alloy sheet at room temperature.**




**Figure 3.7.8.3.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for clad 7475-T761 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.8.3.6(e). Typical tensile stress-strain curves for clad 7475-T761 aluminum alloy sheet at room temperature.**




**Figure 3.7.8.3.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for clad 7475-T761 aluminum alloy sheet at room temperature.**

# MIL-HDBK-5H

1 December 1998




**Figure 3.7.8.3.6(g). Typical compressive stress-strain and compressive tangent-modulus curves for clad 7475-T761 aluminum alloy sheet at room temperature.**




**Figure 3.7.8.3.6(h). Typical compressive stress-strain and compressive tangent-modulus curves for clad 7475-T761 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 3.7.8.3.6(i). Typical tensile stress-strain curves for 7475-T7651 aluminum alloy plate at room temperature.**



**Figure 3.7.8.3.6(j). Typical compressive stress-strain and compressive tangent-modulus curves for 7475-T7651 aluminum alloy plate at room temperature.**




**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.8.3.6(k). Typical tensile stress-strain (full range) curves for 7475-T761 aluminum alloy sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.7.8.3.6(l). Typical tensile stress-strain (full range) curves for clad 7475-T761 aluminum alloy sheet at room temperature.**

MIL-HDBK-5H  
1 December 1998




Figure 3.7.8.3.10(a). Residual strength behavior of 0.063-inch-thick 7475-T761 aluminum alloy sheet at room temperature. Crack orientation is L-T. [References 3.1.2.1.6(d) and 3.2.5.1.9(d).]




Figure 3.7.8.3.10(b). Residual strength behavior of 0.063-inch-thick 7475-T761 aluminum alloy sheet at room temperature. Crack orientation is T-L. [References 3.1.2.1.6(d) and 3.2.5.1.9(d).]

**MIL-HDBK-5H****1 December 1998****3.8 200.0 SERIES CAST ALLOYS**

Alloys of the 200 series contain copper as the principal alloying element, and are particularly useful for elevated temperature applications.

**3.8.1 A201.0 ALLOY**

**3.8.1.0 Comments and Properties** — A201.0 is a high-strength, heat-treatable Al-Cu-Ag casting alloy. In the T7 (overaged) temper, it possesses high strength, moderate ductility and optimum resistance to stress-corrosion cracking. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

A material specification covering this alloy is presented in Table 3.8.1.0(a). Room-temperature mechanical and physical properties are presented in Table 3.8.1.0(b). The effect of temperature on thermal expansion is shown in Figure 3.8.1.0.

**Table 3.8.1.0(a). Material Specification for A201.0 Aluminum Alloy**

Specification	Form
MIL-A-21180	Casting (T7 temper)

The temper index for A201.0 is as follows:

<u>Section</u>	<u>Temper</u>
3.8.1.1	T7

**3.8.1.1 T7 Temper** — Figure 3.8.1.1.6 presents a typical tensile stress-strain curve. Strain control fatigue data are shown in Figures 3.8.1.1.8(a) through (c).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.8.1.0(b). Design Mechanical and Physical Properties of A201.0 Aluminum Alloy Casting**

Specification .....	MIL-A-21180			
Form .....	Casting			
Temper .....	T7			
Location Within Casting ....	Designated area		Nondesignated area	
Strength Class Number <sup>a</sup> ....	1	2	10	11
Basis .....	S	S	S	S
Mechanical Properties <sup>b,c</sup> :				
$F_{tu}$ , ksi: .....	60	60	60	56
$F_{ty}$ , ksi: .....	50	50	50	48
$F_{cy}$ , ksi: .....	51	51	51	49
$F_{su}$ , ksi: .....	36	36	36	34
$F_{bru}^d$ , ksi:				
(e/D = 1.5) .....	95	95	95	88
(e/D = 2.0) .....	122	122	122	114
$F_{bry}^d$ , ksi:				
(e/D = 1.5) .....	74	74	74	71
(e/D = 2.0) .....	87	87	87	83
$e$ , percent .....	3	5	3	1.5
$E$ , 10 <sup>3</sup> ksi .....	10.3			
$E_c$ , 10 <sup>3</sup> ksi .....	10.7			
$G$ , 10 <sup>3</sup> ksi .....	4.0			
$\mu$ .....	0.33			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.101			
$C$ , Btu/(lb)(°F) .....	0.22 (at 212°F)			
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] ....	70 (at 77°F)			
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	See Figure 3.8.1.0			


a The attainable strength class number is dependent on the casting configuration, complexity, and size (both weight and wall thickness). Favorable experience with a particular configuration may allow some foundries to produce a higher strength class number than others. In case of doubt regarding the strength class number, the designer should consult or negotiate with the foundry to determine the proper strength class number to assign for a specific casting.

b For any casting process; i.e., special mold, permanent mold, or sand mold (including chilling).

c The mechanical properties shown are reliably obtainable in castings of this alloy and heat-treat condition when produced under the quality assurance provisions of MIL-A-21180. These provisions require preproduction approval, documentation of foundry procedures, and specific destructive and nondestructive testing procedures for the acceptance of each production lot of castings. Strict adherence to these requirements is mandatory if these properties are to be reliably assured in each casting.


d Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.8.1.0. Effect of temperature on the thermal expansion of A201.0 aluminum alloy casting.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.8.1.1.6. Typical tensile stress-strain curve for A201.0-T7 aluminum alloy casting, designated area, at room temperature.**

MIL-HDBK-5H  
1 December 1998




Figure 3.8.1.1.8(a). Best-fit  $\epsilon/N$  curves, cyclic stress-strain curve, and mean stress relaxation curve for A201.0-T7 casting at 75°F.



**MIL-HDBK-5H****1 December 1998**Correlative Information for Figure 3.8.1.1.8(a)Product Form/Thickness: CastingThermal Mechanical Processing History: T7, HIPProperties:

<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>E, ksi</u>	<u>Temp., °F</u>
57-66	45-57	10,800	75

Stress-Strain Equations:

Cyclic (Companion Specimen)

Proportional Limit = 42 ksi

$$(\Delta\sigma/2) = 72(\Delta\epsilon_p/2)^{0.058}$$

Mean Stress Relaxation, ksi

$$\sigma_m = 33.3 - 4755(\Delta\epsilon/2)$$

Specimen Details: Uniform gage test section  
0.250-inch diameter

References: 3.8.1.1.8(a) and (b)Test Parameters:

Strain Rate/Frequency - 20 cpm

Wave Form - Triangular

Temperature - 75 °F

Atmosphere - Air

No. of Heats/Lots: 3Equivalent Strain Equation:

$$\log N_f = -6.54 - 4.60 \log (\epsilon_{eq})$$

$$\epsilon_{eq} = (\Delta\epsilon)^{0.37} (S_{max}/E)^{0.63}$$

Standard Deviation in Log (Life) = 0.242

Adjusted R<sup>2</sup> Statistic: 83%Sample Size: 26

[Caution: The equivalent strain model may provide unrealistic life predictions for strain ratios and ranges beyond those represented above.]

MIL-HDBK-5H  
1 December 1998




Figure 3.8.1.1.8(b). Best-fit  $\epsilon/N$  curves, cyclic stress-strain curve, and mean stress reduction curve for A201.0-T7 casting at 200°F.

**MIL-HDBK-5H****1 December 1998**Correlative Information for Figure 3.8.1.1.8(b)Product Form/Thickness: CastingThermal Mechanical Processing History: T7, HIPProperties:

<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>E, ksi</u>	<u>Temp., °F</u>
53-59	47-55	10,339	200

Stress-Strain Equations:

Cyclic (Companion Specimen)

Proportional Limit = 39 ksi

$$(\Delta\sigma/2) = 58(\Delta\epsilon_p/2)^{0.041}$$

Mean Stress Relaxation, ksi

$$\sigma_m = 39.7 - 7049(\Delta\epsilon/2)$$

Specimen Details: Uniform gage test section  
0.250-inch diameter

Reference: 3.8.1.1.8(a)Test Parameters:

Strain Rate/Frequency - 20 cpm

Wave Form - Triangular

Temperature - 200 °F

Atmosphere - Air

No. of Heats/Lots: 3Equivalent Strain Equation:

$$\log N_f = -6.68 - 4.66 \log (\epsilon_{eq})$$

$$\epsilon_{eq} = (\Delta\epsilon)^{0.50} (S_{max}/E)^{0.50}$$

Standard Deviation in Log (Life) = 0.359

Adjusted R<sup>2</sup> Statistic: 59%Sample Size: 18

[Caution: The equivalent strain model may provide unrealistic life predictions for strain ratios and ranges beyond those represented above.]

MIL-HDBK-5H

1 December 1998




Figure 3.8.1.1.8(c). Best-fit  $\epsilon/N$  curves, cyclic stress-strain curve, and mean stress relaxation curve for A201.0-T7 casting at 350°F.

**MIL-HDBK-5H****1 December 1998**Correlative Information for Figure 3.8.1.1.8(c)Product Form/Thickness: CastingThermal Mechanical Processing History: T7, HIPProperties:

<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>E, ksi</u>	<u>Temp., °F</u>
48-53	40-48	9,783	350

Stress-Strain Equations:

Cyclic (Companion Specimen)

Proportional Limit = 36 ksi

$$(\Delta\sigma/2) = 50(\Delta\epsilon_p/2)^{0.036}$$

Mean Stress Relaxation, ksi

$$\sigma_m = 30.0 - 5664(\Delta\epsilon/2)$$

Specimen Details: Uniform gage test section  
0.250-inch diameter

Reference: 3.8.1.1.8(a)Test Parameters:

Strain Rate/Frequency - 20 cpm

Wave Form - Triangular

Temperature - 350 °F

Atmosphere - Air

No. of Heats/Lots: 3Equivalent Strain Equation:

$$\text{Log } N_f = -12.44 - 7.07 \log (\epsilon_{eq})$$

$$\epsilon_{eq} = (\Delta\epsilon)^{0.52} (S_{max}/E)^{0.48}$$

Standard Deviation in Log (Life) =

$$0.000817 (1/\epsilon_{eq})$$

Adjusted R<sup>2</sup> Statistic: 93%Sample Size: 18

[Caution: The equivalent strain model may provide unrealistic life predictions for strain ratios and ranges beyond those represented above.]

**MIL-HDBK-5H****1 December 1998****3.9 300.0 SERIES CAST ALLOYS**

Casting alloys of the 300.0 series contain silicon with added copper and/or magnesium as the principal alloying elements. They are heat treatable. Because of the high silicon content, they are among the easiest to cast by a variety of techniques. They have high resistance to corrosion.

**3.9.1 354.0 ALLOY**

**3.9.1.0 Comments and Properties** — 354.0 is a heat-treatable Al-Si-Mg alloy being among the highest strength of commercial casting alloys. It has good casting characteristics; however, its use is generally restricted to permanent mold castings. Refer to Section 3.1.3.4 for comments regarding the weldability.

A material specification for 354.0 aluminum alloy is presented in Table 3.9.1.0(a). Room-temperature mechanical and physical properties are shown in Table 3.9.1.0(b).

**Table 3.9.1.0(a). Material Specifications for 354.0 Aluminum Alloy**

Specification	Form
MIL-A-21180	Casting

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.9.1.0(b). Design Mechanical and Physical Properties of 354.0 Aluminum Alloy Casting**

Specification .....	MIL-A-21180			
Form .....	Casting			
Temper .....	T6			
Location Within Casting ....	Designated area		Nondesignated area	
Strength Class Number <sup>a</sup> ....	1	2	10	11
Basis .....	S	S	S	S
Mechanical Properties <sup>b,c</sup> :				
$F_{tu}$ , ksi .....	47	50	47	43
$F_{ty}$ , ksi .....	36	42	36	33
$F_{cy}$ , ksi .....	36	42	36	33
$F_{su}$ , ksi .....	29	31	29	27
$F_{bru}^d$ , ksi:				
(e/D = 1.5) .....	81	86	81	74
(e/D = 2.0) .....	101	107	101	92
$F_{bry}^d$ , ksi:				
(e/D = 1.5) .....	57	66	57	52
(e/D = 2.0) .....	67	78	67	62
$e$ , percent .....	3	2	3	2
$E$ , $10^3$ ksi .....	10.6			
$E_c$ , $10^3$ ksi .....	10.8			
$G$ , $10^3$ ksi .....	4.0			
$\mu$ .....	0.33			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.098			
$C$ , Btu/(lb)(°F) .....	0.23 (at 212 °F)			
$K$ , Btu/[ (hr)(ft <sup>2</sup> )(°F)/ft] ....	...			
$\alpha$ , $10^{-6}$ in./in./°F .....	1.6 (68 to 212 °F)			

a The attainable strength class number is dependent on the casting configuration, complexity, and size (both weight and wall thickness). Favorable experience with a particular configuration may allow some foundries to produce a higher strength class number than others. In case of doubt regarding the strength class number, the designer should consult or negotiate with the foundry to determine the proper strength class number to assign for a specific casting.

b For any casting process; i.e., special mold, permanent mold, or sand mold (including chilling).

c The mechanical properties shown are reliably obtainable in castings of this alloy and heat-treat condition when produced under the quality assurance provisions of MIL-A-21180. These provisions require preproduction approval, documentation of foundry procedures, and specific destructive and nondestructive testing procedures for the acceptance of each production lot of castings. Strict adherence to these requirements is mandatory if these properties are to be reliably assured in each casting.

d Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****3.9.2 355.0 ALLOY**

**3.9.2.0 Comments and Properties** — 355.0 is a heat-treatable Al-Si-Mg alloy that is readily cast and has good pressure tightness. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

A material specification for 355.0 aluminum alloy is presented in Table 3.9.2.0(a). Room-temperature mechanical and physical properties are shown in Table 3.9.2.0(b). The effect of temperature on thermal expansion is shown in Figure 3.9.2.0.

**Table 3.9.2.0(a). Material Specification for 355.0 Aluminum Alloy**

Specification	Form
AMS 4281	Permanent mold casting

**Table 3.9.2.0(b). Design Mechanical and Physical Properties of 355.0 Aluminum Alloy**


Specification . . . . .	AMS 4281
Form . . . . .	Permanent mold casting
Temper . . . . .	T6
Location Within Casting . . . . .	As specified
Basis . . . . .	S
Mechanical Properties:	
$F_{tu}$ , ksi . . . . .	27 <sup>a</sup>
$F_{ty}$ , ksi . . . . .	17 <sup>a</sup>
$F_{cy}$ , ksi . . . . .	17
$F_{su}$ , ksi . . . . .	17
$F_{bru}^b$ , ksi:	
(e/D = 1.5) . . . . .	46
(e/D = 2.0) . . . . .	58
$F_{bry}^b$ , ksi:	
(e/D = 1.5) . . . . .	27
(e/D = 2.0) . . . . .	32
$e$ , percent . . . . .	0.4 <sup>a</sup>
$E$ , 10 <sup>3</sup> ksi . . . . .	10.3
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.3
$G$ , 10 <sup>3</sup> ksi . . . . .	3.8
$\mu$ . . . . .	0.33
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.098
$C$ , Btu/(lb)(°F) . . . . .	0.23 (at 212 °F)
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] . . . . .	88 (at 77 °F)
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . . . .	See Figure 3.9.2.0

a Conformance to tensile property requirements is determined by testing specimens cut from casting only when specified on drawing.

b Bearing values are “dry pin” values per Section 1.4.7.1.



**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.9.2.0. Effect of temperature on the thermal expansion of 355.0 aluminum alloy casting.**

**MIL-HDBK-5H****1 December 1998****3.9.3 C355.0 ALLOY**

**3.9.3.0 Comments and Properties** — C355.0 is an Al-Si-Mg alloy similar to 355.0 but has impurities controlled to lower limits resulting in higher strengths. It has good casting characteristics. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

A material specification for C355.0 aluminum alloy is presented in Table 3.9.3.0(a). Room-temperature mechanical and physical properties are shown in Table 3.9.3.0(b).

**Table 3.9.3.0(a). Material Specification for C355.0 Aluminum Alloy**

Specification	Form
MIL-A-21180	Casting

**MIL-HDBK-5H****1 December 1998****Table 3.9.3.0(b). Design Mechanical and Physical Properties of C355.0 Aluminum Alloy Casting**

Specification .....	MIL-A-21180					
Form .....	Casting					
Location Within Casting .....	T6					
Strength Class Number <sup>a</sup> .....	1	2	3	10	11	12
Basis .....	S	S	S	S	S	S
Mechanical Properties <sup>b,c</sup> :						
$F_{tu}$ , ksi .....	41	44	50	41	37	35
$F_{ty}$ , ksi .....	31	33	40	31	30	28
$F_{cy}$ , ksi .....	31	33	40	31	30	28
$F_{su}$ , ksi .....	26	28	31	26	23	22
$F_{bru}^d$ , ksi:						
(e/D = 1.5) .....	70	75	86	70	63	60
(e/D = 2.0) .....	88	94	107	88	79	75
$F_{bry}^d$ , ksi:						
(e/D = 1.5) .....	49	52	63	49	47	44
(e/D = 2.0) .....	58	62	75	58	59	52
$e$ , percent .....	3	3	2	3	1	1
$E$ , $10^3$ ksi .....	10.1					
$E_c$ , $10^3$ ksi .....	10.3					
$G$ , $10^3$ ksi .....	3.85					
$\mu$ .....	0.33					
Physical Properties:						
$\omega$ , lb/in. <sup>3</sup> .....	0.098					
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)					
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	88 (at 77°F)					
$\alpha$ , $10^{-6}$ in./in./°F .....	12.4 (68 to 212°F)					

a The attainable strength class number is dependent on the casting configuration, complexity, and size (both weight and wall thickness). Favorable experience with a particular configuration may allow some foundries to produce a higher strength class number than others. In case of doubt regarding the strength class number, the designer should consult or negotiate with the foundry to determine the proper strength class number to assign for a specific casting.

b For any casting process; i.e., special mold, permanent mold, or sand mold (including chilling).

c The mechanical properties shown are reliably obtainable in castings of this alloy and heat-treat condition when produced under the quality assurance provisions of MIL-A-21180. These provisions require preproduction approval, documentation of foundry procedures, and specific destructive and nondestructive testing procedures for the acceptance of each production lot of castings. Strict adherence to these requirements is mandatory if these properties are to be reliably assured in each casting.

d Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****3.9.4 356.0 ALLOY**

**3.9.4.0 Comments and Properties** — 356.0 is among the easiest of alloys to cast by a variety of techniques. It is heat treatable, has intermediate strengths, and has high resistance to corrosion. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

Material specifications for 356.0 aluminum alloy are presented in Table 3.9.4.0(a). Room-temperature mechanical and physical properties are shown in Table 3.9.4.0(b). The effect of temperature on thermal expansion is given in Figure 3.9.4.0.

**Table 3.9.4.0(a). Material Specifications for 356.0 Aluminum Alloy**

Specification	Form
AMS 4284	Permanent mold casting
AMS 4217	Sand casting
AMS 4260	Investment casting

**Table 3.9.4.0(b). Design Mechanical and Physical Properties of 356.0 Aluminum Alloy**

Specification . . . . .	AMS 4217	AMS 4260	AMS 4284
Form . . . . .	Sand casting	Investment casting	Permanent mold casting
Temper . . . . .	T6	T6	T6
Location Within Casting . . . .	Thick and thin areas	As specified	As specified
Basis . . . . .	S	S	S
Mechanical Properties:			
$F_{tu}$ , ksi . . . . .	22 <sup>a,b</sup>	25 <sup>a</sup>	25 <sup>a</sup>
$F_{ty}$ , ksi . . . . .	15 <sup>a,b</sup>	16 <sup>a</sup>	16 <sup>a</sup>
$F_{cy}$ , ksi . . . . .	15	16	16
$F_{su}$ , ksi . . . . .	14	16	16
$F_{bru}^c$ , ksi:			
(e/D = 1.5) . . . . .	38	43	43
(e/D = 2.0) . . . . .	47	53	53
$F_{bry}^c$ , ksi:			
(e/D = 1.5) . . . . .	24	25	25
(e/D = 2.0) . . . . .	28	30	30
$e$ , percent . . . . .	0.7 <sup>a,b</sup>	1 <sup>a</sup>	0.7 <sup>a</sup>
$E$ , 10 <sup>3</sup> ksi . . . . .	10.3		
$E_c$ , 10 <sup>3</sup> ksi . . . . .	10.3		
$G$ , 10 <sup>3</sup> ksi . . . . .	3.85		
$\mu$ . . . . .	0.33		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.097		
$C$ , Btu/(lb)(°F) . . . . .	0.23 (at 212°F)		
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] . . . .	88 (at 77°F)		
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . . . .	See Figure 3.9.4.0		


a Conformance to tensile property requirements is determined by testing specimens cut from casting only when specified on drawing.

b Not minimum values, but based upon average of not less than four specimens.

c Bearing values are "dry pin" values per Section 1.4.7.1.

MIL-HDBK-5H

1 December 1998



**Figure 3.9.4.0. Effect of temperature on the thermal expansion of 356.0 aluminum alloy casting.**

**MIL-HDBK-5H****1 December 1998****3.9.5 A356.0 ALLOY**

**3.9.5.0 Comments and Properties** — A356.0 is an Al-Si-Mg alloy similar to 356.0, but with impurities controlled to lower limits resulting in higher strengths and ductility. It has good casting characteristics and high resistance to corrosion. Refer to 3.1.3.4 for comments regarding the weldability of the alloy.

Material specifications for A356.0 aluminum alloy are presented in Table 3.9.5.0(a). Room-temperature mechanical and physical properties are shown in Tables 3.9.5.0(b) and (c).

**Table 3.9.5.0(a). Material Specifications for A356.0 Aluminum Alloy**

Specification	Form
MIL-A-21180	Casting
AMS 4218	Casting

The temper index for A356.0 is as follows:

<u>Section</u>	<u>Temper</u>
3.9.5.1	T6P
3.9.5.2	T6

**3.9.5.1 T6P Temper** — Tensile stress-strain and full-range stress-strain curves at room temperature are presented in Figures 3.9.5.1.6(a) and (b), respectively.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.9.5.0(b). Design Mechanical and Physical Properties of A356.0 Aluminum Alloy Casting**

Specification .....	MIL-A-21180					
Form .....	Casting					
Temper .....	T6					
Location Within Casting ..	Designated area			Nondesignated area		
Strength Class Number <sup>a</sup> ..	1	2	3	10	11	12
Basis .....	S	S	S	S	S	S
Mechanical Properties <sup>b,c</sup> :						
$F_{tu}$ , ksi .....	38	40	45	38	33	32
$F_{ty}$ , ksi .....	28	30	34	28	27	22
$F_{cy}$ , ksi .....	28	30	34	28	27	22
$F_{su}$ , ksi .....	24	25	28	24	21	20
$F_{bru}^d$ , ksi:						
(e/D = 1.5) .....	65	69	77	65	57	55
(e/D = 2.0) .....	81	86	96	81	71	68
$F_{bry}^d$ , ksi:						
(e/D = 1.5) .....	44	47	54	44	43	35
(e/D = 2.0) .....	52	56	63	52	50	41
$e$ , percent .....	5	3	3	5	3	2
$E$ , $10^3$ ksi .....	10.4					
$E_c$ , $10^3$ ksi .....	10.5					
$G$ , $10^3$ ksi .....	3.9					
$\mu$ .....	0.33					
Physical Properties:						
$\omega$ , lb/in. <sup>3</sup> .....	0.097					
$C$ , Btu/(lb)(°F) .....	0.23 (at 212 °F)					
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] ..	88 (at 77 °F)					
$\alpha$ , $10^{-6}$ in./in./°F .....	See Figure 3.9.4.0					

- a The attainable strength class number is dependent on the casting configuration, complexity, and size (both weight and wall thickness). Favorable experience with a particular configuration may allow some foundries to produce a higher strength class number than others. In case of doubt regarding the strength class number, the designer should consult or negotiate with the foundry to determine the proper strength class number to assign for a specific casting.
- b For any casting process; i.e., special mold, permanent mold, or sand mold (including chilling).
- c The mechanical properties shown are reliably obtainable in castings of this alloy and heat-treat condition when produced under the quality assurance provisions of MIL-A-21180. These provisions require preproduction approval, documentation of foundry procedures, and specific destructive and nondestructive testing procedures for the acceptance of each production lot of castings. Strict adherence to these requirements is mandatory if these properties are to be reliably assured in each casting.
- d Bearing values are “dry pin” values per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 3.9.5.0(c). Design and Physical Properties of A356.0 Aluminum Alloy Casting**


Specification .....	AMS 4218
Form .....	Sand, investment, permanent mold, and composite castings
Temper .....	T6P <sup>a</sup>
Location Within Casting .....	Any
Basis .....	S
Mechanical Properties: <sup>b</sup>	
$F_{tu}$ , ksi .....	32
$F_{ty}$ , ksi .....	22
$F_{cy}$ , ksi .....	22
$F_{su}$ , ksi .....	20
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	55
(e/D = 2.0) .....	68
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	35
(e/D = 2.0) .....	41
$e$ , percent .....	2
$E$ , $10^3$ ksi .....	10.4
$E_c$ , $10^3$ ksi .....	10.5
$G$ , $10^3$ ksi .....	3.9
$\mu$ .....	0.33
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.097
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)
$K$ Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	88 (at 77°F)
$\alpha$ , $10^{-6}$ in./in./°F .....	See Figure 3.9.4.0

a The letter, P, indicates a variation compared to the standard heat treatment procedure of this temper and/or a difference in the minimum tensile property requirements compared to the Aluminum Association's registered limits.


b The mechanical properties shown are reliably obtainable when produced under the quality assurance provisions of AMS 4218. These procedures require radiographic control and specific destructive testing for acceptance of each production lot. Strict adherence to these requirements is mandatory if these properties are to be reliably assured in each casting.



**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.9.5.1.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for A356.0-T6P aluminum alloy casting at room temperature.**



**Figure 3.9.5.1.6(b). Typical tensile stress-strain (full-range) curve for A356.0-T6P aluminum alloy casting at room temperature.**

**MIL-HDBK-5H****1 December 1998****3.9.6 A357.0 ALLOY**

**3.9.6.0 Comments and Properties** — A357.0 is a heat-treatable Al-Si-Mg alloy generally used for permanent mold and premium quality castings in which special properties are developed by careful control of casting and chilling techniques. It has excellent casting characteristics, is heat treatable, and provides high strength, together with good toughness. The alloy also has excellent corrosion resistance. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

A material specification for A357.0 aluminum alloy is presented in Table 3.9.6.0(a). Room-temperature mechanical and physical properties are shown in Table 3.9.6.0(b).

**Table 3.9.6.0(a). Material Specification for A357.0 Aluminum Alloy**

Specification	Form
MIL-A-21180	Casting

The temper index for A357.0 is as follows:

<u>Section</u>	<u>Temper</u>
3.9.6.1	T6

**3.9.6.1 T6 Temper** — Figure 3.9.6.1.6 presents a typical tensile stress-strain curve.

**MIL-HDBK-5H****1 December 1998****Table 3.9.6.0(b). Design Mechanical and Physical Properties of A357.0 Aluminum Alloy Casting**

Specification .....	MIL-A-21180				
Form .....	Casting <sup>b</sup>				
Temper .....	T6				
Location Within Casting .....	Designated area		Nondesignated area		
Strength Class Number <sup>a</sup> .....	1	2	10	11	12
Basis .....	S	S	S	S	S
Mechanical Properties: <sup>c</sup>					
$F_{tu}$ , ksi .....	45	50	38	41	45
$F_{ty}$ , ksi .....	35	40	28	31	35
$F_{cy}$ , ksi .....	35	40	28	31	35
$F_{su}$ , ksi .....	28	31	24	26	28
$F_{bru}^d$ , ksi:					
(e/D = 1.5) .....	77	86	65	70	77
(e/D = 2.0) .....	96	107	81	88	96
$F_{bry}^d$ , ksi:					
(e/D = 1.5) .....	55	63	44	49	55
(e/D = 2.0) .....	65	75	52	58	65
$e$ , percent .....	3	5	5	3	3
$E$ , $10^3$ ksi .....	10.4				
$E_c$ , $10^3$ ksi .....	10.5				
$G$ , $10^3$ ksi .....	3.9				
$\mu$ .....	0.33				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> .....	0.097				
$C$ , Btu/(lb)(°F) .....	0.23 (at 212 °F)				
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	88 (at 77 °F)				
$\alpha$ , $10^{-6}$ in./in./°F .....	12.0 (68 to 212 °F)				


a The attainable strength class number is dependent on the casting configuration, complexity, and size (both weight and wall thickness). Favorable experience with a particular configuration may allow some foundries to produce a higher strength class number than others. In case of doubt regarding the strength class number, the designer should consult or negotiate with the foundry to determine the proper strength class number to assign for a specific casting.

b For any casting process; i.e., special mold, permanent mold, or sand mold (including chilling).

c The mechanical properties shown are reliably obtainable in castings of this alloy and heat-treat condition when produced under the quality assurance provisions of MIL-A-21180. These provisions require preproduction approval, documentation of foundry procedures, and specific destructive and nondestructive testing procedures for the acceptance of each production lot of castings. Strict adherence to these requirements is mandatory if these properties are to be reliably assured in each casting.

d Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.9.6.1.6. Typical tensile stress-strain curve for A357.0-T6 aluminum alloy casting, Class 2, designated area, at room temperature.**

**MIL-HDBK-5H****1 December 1998****3.9.7 D357.0 ALLOY**

**3.9.7.0 Comments and Properties** — D357.0 is a modification of A357.0 with narrower compositional limits and more stringent inspection requirements. These modifications were necessary to reduce variability in mechanical properties to a degree compatible with the determination of A- and B-basis values. D357.0 is a heat-treatable Al-Si-Mg alloy generally used for premium quality castings in which special properties are developed by careful control of casting and chilling techniques. It has excellent casting characteristics and provides high strength together with good toughness. The alloy also has excellent corrosion resistance. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

A material specification for D357.0 aluminum is presented in Table 3.9.7.0(a). Room temperature mechanical and physical properties are shown in Table 3.9.7.0(b).

**Table 3.9.7.0(a). Material Specification for D357.0 Aluminum Alloy**

Specification	Form
AMS 4241	Casting

The temper index for D357.0 is as follows:

<u>Section</u>	<u>Temper</u>
3.9.7.1	T6

**3.9.7.1 T6 Temper** — Figure 3.9.7.1.6 presents a typical tensile stress-strain curve.


**MIL-HDBK-5H****1 December 1998****Table 3.9.7.0(b). Design Mechanical and Physical Properties of D357.0 Aluminum Alloy Casting**

Specification .....	AMS 4241		
Form .....	Casting		
Temper .....	T6		
Thickness, in. ....	≤2.500		...
Location Within Casting .....	Designated area		Nondesignated area
Basis .....	A	B	S
Mechanical Properties <sup>a</sup> :			
$F_{tu}$ , ksi .....	46	49	45
$F_{ty}$ , ksi .....	39	41	36
$F_{cy}$ , ksi .....	39	41	36
$F_{su}$ , ksi .....	29	31	28
$F_{bru}^b$ , ksi:			
(e/D = 1.5) .....	79	84	77
(e/D = 2.0) .....	99	105	96
$F_{bry}^b$ , ksi:			
(e/D = 1.5) .....	62	65	57
(e/D = 2.0) .....	73	77	67
e, percent (S-basis) .....	3	...	2
$E$ , 10 <sup>3</sup> ksi .....	10.4		
$E_c$ , 10 <sup>3</sup> ksi .....	10.5		
$G$ , 10 <sup>3</sup> ksi .....	3.9		
$\mu$ .....	0.33		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> .....	0.097		
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)		
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	88 (at 77°F)		
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	12.0 (68 to 212°F)		

a The mechanical properties shown are reliably obtainable when castings are produced under the quality assurance provisions of AMS 4241. These provisions require preproduction approval, documentation of foundry procedures, and specific destructive and nondestructive testing procedures for the acceptance of each production lot of castings. Strict adherence to these requirements is mandatory if these properties are to be reliably assured in each casting.

b Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 3.9.7.1.6. Typical tensile stress-strain curve for D357.0-T6 aluminum alloy casting, designated area, at room temperature.**

**MIL-HDBK-5H****1 December 1998****3.9.8 359.0 ALLOY**

**3.9.8.0 Comments and Properties** — 359.0 is a relatively high-strength permanent-mold casting alloy. It is heat treatable, and has good corrosion resistance. Refer to Section 3.1.3.4 for comments regarding the weldability of the alloy.

A material specification for 359.0 aluminum alloy is presented in Table 3.9.8.0(a). Room-temperature mechanical and physical properties are shown in Table 3.9.8.0(b).

**Table 3.9.8.0(a). Material Specification for 359.0 Aluminum Alloy**

Specification	Form
MIL-A-21180	Casting



**MIL-HDBK-5H****1 December 1998****Table 3.9.8.0(b). Design Mechanical and Physical Properties of 359.0 Aluminum Alloy Casting**

Specification .....	MIL-A-21180			
Form .....	Casting			
Temper .....	T6			
Location Within Casting ....	Designated area		Nondesignated area	
Strength Class Number <sup>a</sup> ....	1	2	10	11
Basis .....	S	S	S	S
Mechanical Properties <sup>b,c</sup> :				
$F_{tu}$ , ksi: .....	45	47	45	40
$F_{ty}$ , ksi: .....	35	38	34	30
$F_{cy}$ , ksi: .....	35	38	34	30
$F_{su}$ , ksi: .....	28	29	28	25
$F_{bru}^d$ , ksi:				
(e/D = 1.5) .....	77	81	77	69
(e/D = 2.0) .....	96	101	96	86
$F_{bry}^d$ , ksi:				
(e/D = 1.5) .....	55	60	54	47
(e/D = 2.0) .....	65	71	63	56
$e$ , percent .....	4	3	4	3
$E$ , $10^3$ ksi .....	10.5			
$E_c$ , $10^3$ ksi .....	10.7			
$G$ , $10^3$ ksi .....	4.0			
$\mu$ .....	0.33			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.097			
$C$ , Btu/(lb)(°F) .....	0.23 (at 212°F)			
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] ....	88 (at 77°F)			
$\alpha$ , $10^{-6}$ in./in./°F .....	11.0 (68 to 212°F)			

a The attainable strength class number is dependent on the casting configuration, complexity, and size (both weight and wall thickness). Favorable experience with a particular configuration may allow some foundries to produce a higher strength class number than others. In case of doubt regarding the strength class number, the designer should consult or negotiate with the foundry to determine the proper strength class number to assign for a specific casting.

b For any casting process; i.e., special mold, permanent mold, or sand mold (including chilling).

c The mechanical properties shown are reliably obtainable in castings of this alloy and heat-treat condition when produced under the quality assurance provisions of MIL-A-21180. These provisions require preproduction approval, documentation of foundry procedures, and specific destructive and nondestructive testing procedures for the acceptance of each production lot of castings. Strict adherence to these requirements is mandatory if these properties are to be reliably assured in each casting.

d Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****3.11 ELEMENT PROPERTIES**

**3.11.1 BEAMS** — See Chapter 1 and Reference 1.7.1 for general information on stress analysis of beams.

**3.11.1.1 Simple Beams** — Beams of solid, tubular, or similar cross sections can be assumed to fail through exceeding an allowable modulus of rupture in bending ( $F_b$ ). In the absence of specific data, the ratio  $F_b/F_{tu}$  can be assumed to be 1.25 for solid sections.

**3.11.1.1.1 Round Tubes** — For round tubes, the value of  $F_b$  will depend on the  $D/t$  ratio as well as the ultimate tensile stress. The bending moduli of rupture of round tubes of various aluminum alloys are given in Figure 3.11.1.1.1. It should be noted that these values apply only when the tubes are restrained against local buckling at the loading points.


**3.11.1.1.2 Unconventional Cross Section** — Sections other than solid or tubular should be tested to determine the allowable bending stress.

**3.11.1.2 Built-Up Beams** — Built-up beams will usually fail because of local failures of the component parts. In aluminum-alloy construction, the strength of fittings and joints is an important feature (see Reference 3.11.1.2).

**3.11.1.3 Thin-Web Beams** — The allowable stress for thin-web beams will depend on the nature of the failure and is determined from the allowable stresses of the web in tension and of the flanges or stiffeners in compression.

**3.11.2 COLUMNS**

**3.11.2.1 Primary Failure** — The general formula for primary instability is given in Section 1.3.8.



**Figure 3.11.1.1.1. Bending modulus of rupture for aluminum alloy round tubing.**

**MIL-HDBK-5H****1 December 1998**

**3.11.2.2 Local Failure** — The local stability of aluminum alloy column sections may be determined using the methods outlined in References 3.11.2.2(a) through (e).

**3.11.2.3 Column Properties** — Curves of the allowable column stresses for round and stream-line tubing are given in Figure 3.11.2.3. The allowable stress is plotted against the effective slenderness ratio, defined by the formula:

$$\frac{L'}{\rho} = \frac{L}{\rho\sqrt{c}} \quad (3.11.2.3)$$

## MIL-HDBK-5H

1 December 1998






Figure 3.11.2.3. Allowable column and crushing stresses for 2024 and 6061 aluminum alloy tubing.

**MIL-HDBK-5H****1 December 1998****3.11.3 TORSION**


**3.11.3.1 General** — The torsional failure of aluminum-alloy tubes may be due to plastic failure of metal, elastic instability of the walls, or an intermediate condition. Pure shear failure will not usually occur within the range of wall thicknesses commonly used for aircraft tubing.

**3.11.3.2 Torsion Properties** — The curves of Figures 3.11.3.2(a) through (g) are derived from the method outlined in Reference 2.8.1.1 and take into account the parameter  $L/D$ . The theoretical results set forth in Reference 2.8.3.2 have been found to be in good agreement with the experimental results.




**Figure 3.11.3.2(a). Torsional modulus of rupture—2014-T6 aluminum alloy rolled rod.**



**MIL-HDBK-5H**  
**1 December 1998**





**Figure 3.11.3.2(b). Torsional modulus of rupture—2014-T6 aluminum alloy forging.**



**Figure 3.11.3.2(c). Torsional modulus of rupture—2024-T3 aluminum alloy tubing.**

**MIL-HDBK-5H****1 December 1998****Figure 3.11.3.2(d). Torsional modulus of rupture—2024-T4 aluminum alloy tubing.****Figure 3.11.3.2(e). Torsional modulus of rupture—6061-T6 aluminum alloy tubing.**

**MIL-HDBK-5H****1 December 1998****Figure 3.11.3.2(f). Torsional modulus of rupture—7075-T6 aluminum alloy rolled rod.****Figure 3.11.3.2(g). Torsional modulus of rupture—7075-T6 aluminum alloy forging.**



**MIL-HDBK-5H****1 December 1998****REFERENCES**

- 3.1(a) Aluminum, Vol. I, "Properties, Physical Metallurgy and Phase Diagrams," Vol. II, "Design and Application," Vol. III, "Fabrication and Finishing," American Society for Metals (1967).
- 3.1(b) Aluminum Standards and Data, The Aluminum Association.
- 3.1.2 ANSI/ASC H35.1—1988, "American National Standard Alloy and Temper Designation Systems for Aluminum."
- 3.1.2.1.1 Stickley, G. W., and Moore, A. A., "Effects of Lubrication and Pin Surface on Bearing Strengths of Aluminum and Magnesium Alloys," *Material Research & Standards*, Vol. 2, No. 9, pp. 747 (September 1962).
- 3.1.2.1.4 Van Echo, J. A., Page, L. C., Simmons, W. F., and Cross, H. C., Part I, "Short Time Creep Properties of Structural Sheet Materials for Aircraft and Missiles," WADC TR 6731, 65 pp. (August 1952).
- 3.1.2.1.5(a) Gideon, D. N., Favor, R. J., Grover, H. J., and McClure, G. M., "The Fatigue Behavior of Certain Alloys in the Temperature Range from Room Temperature to -423°F," *Advances in Cryogenic Engineering*, Vol. 7, Plenum Press, New York, pp. 503-508 (1962).
- 3.1.2.1.5(b) Keys, R. D., Keifer, T. F., and Schwartzberg, F. R., "Fatigue Behavior of Aluminum and Titanium Sheet Materials Down to -423°F," *Advances in Cryogenic Engineering*, Vol. 10, Plenum Press, New York, pp. 1-13 (1965).
- 3.1.2.1.5(c) DeMoney, F. W., and Wolfer, G. C., "The Fatigue Properties of Aluminum Alloy 5083-H113 and Butt Weldments at 70 and -300°F," *Advances in Cryogenic Engineering*, Vol. 6, Plenum Press, New York, pp. 590-603 (1961).
- 3.1.2.1.5(d) "Fatigue Design Handbook," Vol. 4, Society of Automotive Engineers (1968).
- 3.1.2.1.5(e) Heywood, R. B., "Designing Against Fatigue of Metals," Reinhold Publishing Corp. (1962).
- 3.1.2.1.5(f) Grover, H. J., "Fatigue of Aircraft Structures," Naval Air Systems Command, NAVAIR 01-1A-13 (1966).
- 3.1.2.1.5(g) Harris, W. J., "Metallic Fatigue," International Series of Monographs in Aeronautics and Astronautics, Vol. I (1961).
- 3.1.2.1.5(h) "Effect of Environment and Complex Load History of Fatigue Life," ASTM STP 463 (1970).
- 3.1.2.1.5(i) "Fatigue Crack Propagation," ASTM STP 415 (1967).
- 3.1.2.1.5(j) Pope, J. A., "Metal Fatigue," London, Chapman and Hall (1959).
- 3.1.2.1.5(k) Rassweiler, G. M., and Grube, W. L., "Internal Stress and Fatigue in Metals," Elsevier Publishing Company (1959).
- 3.1.2.1.5(l) "Symposium on Fatigue of Aircraft Structures," WADC TR 59-507 (1959).

**MIL-HDBK-5H****1 December 1998**

- 3.1.2.1.5(m) "Symposium on Fatigue of Aircraft Structures: Low-Cycle, Full-Scale, and Helicopter," ASTM STP 338 (1962).
- 3.1.2.1.5(n) Sines, G., and Waisman, J. L., "Metal Fatigue," McGraw-Hill (1959).
- 3.1.2.1.5(o) "Symposium on the Basic Mechanisms of Fatigue," ASTM STP 237 (1959).
- 3.1.2.1.5(p) Manson, S. S., "Fatigue: A Complex Subject—Some Simple Approximations," *Experimental Mechanics*, Vol. 5, No. 7, pp. 193-226 (July 1965).
- 3.1.2.1.5(q) Morrow, J. D., "Cyclic Plastic Strain Energy and the Fatigue of Metals," Symposium on Internal Friction, Damping and Cyclic Plasticity, ASTM STP 378 (1964).
- 3.1.2.1.5(r) Hartman, E. C., Holt, M., and Eaton, I. D., "Static and Fatigue Strength of High-Strength Aluminum-Alloy Bolted Joints," National Advisory Committee for Aeronautics, Technical Note 2276, p. 61 (February 1952).
- 3.1.2.1.5(s) Holt, M., "Results of Shear Fatigue Tests of Joints with 3/16-Inch-Diameter 24-S T31 Rivets in 0.064-Inch-Thick Al Clad Sheet," U.S. National Advisory Committee for Aeronautics, Technical Note No. 2012, p. 51 (February 1950).
- 3.1.2.1.6(a) "Standard Method of Test for Plane-Strain Fracture Toughness of Metallic Materials," ASTM Designation E399 (Annual).
- 3.1.2.1.6(b) Kaufman, J. G., Shilling, P. E., and Nelson, F. G., "Fracture Toughness of Aluminum Alloys," *Metals Engineering Quarterly*, pp. 39-47 (August 1969).
- 3.1.2.1.6(c) Kaufman, J. G., Moore, R. L., and Schilling, P. E., "Fracture Toughness of Structural Aluminum Alloys," presented at 1969 ASM Materials Engineering Congress, Philadelphia, Pennsylvania (October 14, 1969).
- 3.1.2.1.6(d) Anon., "Fracture Mechanics Data on Aluminum," from Aluminum Company of America (June 12, 1973) (MCIC 86213).
- 3.1.2.1.6(e) Eichenberger, T. W., "Fracture Resistance Data Summary," Report D2-20947, The Boeing Company (June 1962) (MCIC 62306).
- 3.1.2.1.6(f) Smith, S. H., and Liu, A. F., "Fracture Mechanics Application to Materials Evaluation and Selection for Aircraft Structure and Fracture Analysis," D6-17756.
- 3.1.2.1.6(g) Allen, F. C., "Effects of Thickness on the Fracture Toughness of 7075 Aluminum in the T6 and T73 Conditions," Damage Tolerance in Aircraft Structures, ASTM STP 486, pp. 16-38 (1971).
- 3.1.2.1.6(h) Broek, D., "The Residual Strength of Aluminum Alloy Sheet Specimens Containing Fatigue Cracks or Saw Cuts," NLR-TR M. 2143, National Aerospace Laboratory, Amsterdam (1966).
- 3.1.2.1.6(i) Broek, D., "The Effect of Finite Specimen Width on the Residual Strength of Light Alloy Sheet," TR M. 2152, National Aero- and Astronautical Research Institute, Amsterdam (1965) (MCIC 70485).

**MIL-HDBK-5H****1 December 1998**

- 3.1.2.1.6(j) Feddersen, C. E., and Hyler, W. S., "Fracture and Fatigue-Crack-Propagation Characteristics of 7075-T7351 Aluminum Alloy Sheet and Plate," Report No. G-8902, Battelle Memorial Institute, Columbus, Ohio (March 1970) (MCIC 79089).
- 3.1.2.1.7(a) Campbell, J. E., "Aluminum Alloys for Cryogenic Service," *Materials Research & Standards*, Vol. 4, No. 10, pp. 540-548 (October 1964).
- 3.1.2.1.7(b) Bogardus, K. O., Stickley, G. W., and Howell, F. M., "A Review of Information on the Mechanical Properties of Aluminum Alloys at Low Temperatures," National Advisory Committee on Aeronautics, Technical Note 2082, 64 pp. (May 1950).
- 3.1.2.1.7(c) Kaufman, J. G., Bogardus, K. O., and Wanderer, E. T., "Tensile Properties and Notch Toughness of Aluminum Alloys at -452°F in Liquid Helium," *Advances in Cryogenic Engineering*, Vol. 13, Plenum Press, New York, pp. 294-308 (1968).
- 3.1.2.1.7(d) Kaufman, J. G., and Wanderer, E. T., "Tensile Properties and Notch Toughness of 7000 Series Aluminum Alloys, Notably 7005, at -452°F," *Advances in Cryogenic Engineering*, Vol. 15, Plenum Press, New York (to be published).
- 3.1.2.1.7(e) Kaufman, J. G., and Holt, M., "Evaluation of Fracture Characteristics of Aluminum Alloys at Cryogenic Temperatures," *Advances in Cryogenic Engineering*, Vol. 10, Plenum Press, New York, pp. 77-85 (1965).
- 3.1.2.1.7(f) Kaufman, J. G., and Johnson, E. W., "New Data from Alcoa Research Laboratories on Aluminum in Cryogenic Applications," *Advances in Cryogenic Engineering*, Vol. 6, Plenum Press, New York, pp. 637-649 (1960).
- 3.1.2.1.8 Holt, M., and Bogardus, K. O., "The 'Hot' Aluminum Alloys," *Product Engineering* (August 16, 1965).
- 3.1.2.3.1(a) Sprowls, D. O., and Brown, R. H., "Resistance of Wrought High-Strength Aluminum Alloys to Stress Corrosion," *Metal Progress*, Part I (April 1962), and Part II (May 1962).
- 3.1.2.3.1(b) Rutemiller, H. C., and Sprowls, D. O., "Susceptibility of Aluminum Alloys to Stress Corrosion," *Materials Protection* (June 1963).
- 3.1.2.3.1(c) Spuhler, E. H., and Burton, C. L., "Avoiding Stress-Corrosion Cracking in High Strength Aluminum Alloy Structures," Alcoa Green Letter Booklet No. 188 (April 1970).
- 3.1.2.3.1(d) Jackson, J. D., and Boyd, W. K., "Preventing Stress-Corrosion Cracking of High Strength Alloy Parts," *Materials in Design Engineering* (May 1966).
- 3.1.2.3.2 Lifka, B. W., Sprowls, D. O., and Kaufman, J. G., "Exfoliation and Stress-Corrosion Characteristics of High Strength, Heat Treatable Aluminum Alloy Plate," *Corrosion*, Vol. 23, No. 11, pp. 335-342 (November 1967).
- 3.2.1.1.8(a) Howell, F. M., and Miller, J. L., "Axial Stress, Fatigue Strength of Structural Aluminum Alloys," American Society for Testing Materials, Vol. 55 (1955) (MIL-HDBK-5 Item 62-17).

**MIL-HDBK-5H****1 December 1998**

- 3.2.1.1.8(b) Lazan, B. J., and Blatherwick, A. A., "Fatigue Properties of Aluminum Alloys at Various Direct Stress Ratios, Part 1—Rolled Alloys," WADC Technical Report 52307 (December 1952) (MCIC 107775).
- 3.2.1.1.8(c) Lazan, B. J., and Blatherwick, A. A., "Fatigue Properties of Aluminum Alloys at Various Direct Stress Ratios, Part 2—Extruded Alloys," WADC Technical Report 52-307 (December 1952) (MCIC 107776) (MIL-HDBK-5 Source M-535).
- 3.2.1.1.8(d) Wang, D. Y., "Axial Loading Fatigue Properties of 7079-T6, 7075-T6, and 2014-T6 Aluminum Alloy Hand Forgings," WADC Technical Report 58-59 (July 1958) (MCIC 108811).
- 3.2.1.1.8(e) Nordmark, G. E., Lifka, B. W., et al., "Stress-Corrosion and Corrosion-Fatigue Susceptibility of High-Strength Aluminum Alloys," Alcoa Technical Report 70-259 (November 1970) (MCIC 79945).
- 3.2.3.1.8(a) Grover, H. J., Bishop, S. M., and Jackson, L. R., "Fatigue Strengths of Aircraft Materials: Axial-Load Fatigue Tests on Unnotched Sheet Specimens of 24S-T3 and 75S-T6 Aluminum Alloys and of SAE 4130 Steel," National Advisory Committee for Aeronautics, Technical Note 2324 (March 1951) (MIL-HDBK-5 Source M-506).
- 3.2.3.1.8(b) Grover, H. J., Bishop, S. M., and Jackson, L. R., "Fatigue Strengths of Aircraft Materials: Axial-Load Fatigue Tests on Notched Sheet Specimens of 24S-T3 and 75S-T6 Aluminum Alloys and of SAE 4130 Steel with Stress-Concentration Factors of 2.0 and 4.0," National Advisory Committee for Aeronautics, Technical Note 2389 (June 1951) (MIL-HDBK-5 Source M-507).
- 3.2.3.1.8(c) Grover, H. J., Bishop, S. M., and Jackson, L. R., "Fatigue Strengths of Aircraft Materials; Axial-Load Fatigue Tests on Notched Specimens of 24S-T3 and 75S-T6 Aluminum Alloys and of SAE 4130 Steel with Stress-Concentration Factor of 5.0," National Advisory Committee for Aeronautics, Technical Note 2390 (June 1951) (MIL-HDBK-5 Source M-508).
- 3.2.3.1.8(d) Grover, H. J., Hyler, W. S., and Jackson, L. R., "Fatigue Strengths of Aircraft Materials; Axial-Load Fatigue Tests on Notched Sheet Specimens of 24S-T3 and 75S-T6 Aluminum Alloys and of SAE 4130 Steel with Stress-Concentration Factor of 1.5," National Advisory Committee for Aeronautics, Technical Note 2639 (February 1952) (MIL-HDBK-5 Source M-509).
- 3.2.3.1.8(e) Hardrath, H. F., and Ilig, W., "Fatigue Tests at Stresses Producing Failure in 2 to 10,000 Cycles 24S-T3 and 75S-T6 Aluminum Alloy Sheet Specimens with a Theoretical StressConcentration Factor of 4.0 Subjected to Completely Reversed Axial Load," National Advisory Committee of Aeronautics, Technical Note 3132 (January 1954) (MIL-HDBK-5 Source M-510).
- 3.2.3.1.8(f) Ilig, W., "Fatigue Tests on Notched and Unnotched Sheet Specimens of 2024-T3 and 7075-T6 Aluminum Alloys and of SAE 4130 Steel with Special Consideration of the Life Range from 2 to 10,000 Cycles," National Advisory Committee for Aeronautics, Technical Note 3866 (December 1956) (MIL-HDBK-5 Source M-512).
- 3.2.3.1.8(g) Grover, H. J., Hyler, W. S., and Jackson, L. R., "Fatigue Strengths of Aircraft Materials; Axial-Load Fatigue Tests on Edge-Notched Sheet Specimens of 2024-T3 and 7075-T6 Aluminum Alloys and of SAE 4130 Steel with Notch Radii of 0.004 and 0.070 Inch," National

**MIL-HDBK-5H****1 December 1998**

Aeronautics and Space Administration, Technical Note D-111 (September 1959) (MIL-HDBK-5 Source M-513).

- 3.2.3.1.8(h) Naumann, E. C., Hardrath, H. F., and Guthrie, D. E., "Axial-Load Fatigue Tests of 2024-T3 and 7075-T6 Aluminum-Alloy Sheet Specimens Under Constant and Variable Amplitude Loads," National Aeronautics and Space Administration, Technical Note D-212 (December 1959) (MIL-HDBK-5 Source M-514).
- 3.2.3.1.8(i) Topper, T. H., and Morrow, J., "Simulation of the Fatigue Behavior at the Notch Root in Spectrum Loaded Notch Member (u)," Naval Air Development Center, Final Report (January 1970).
- 3.2.5.1.9(a) Pionke, L. J., and Linback, R. K., "Fracture Mechanics Data for 2024-T861 and Aluminum," NASA CR, MDDC E1153, McDonnell Douglas Astronautics Company (October 25, 1974).
- 3.2.6.1.9(b) Cervay, R. R., "Temperature Effect on the Mechanical Properties of Aluminum Alloy 2124-T851," AFML-TR-75-208 (December 1975).
- 3.2.6.1.9(c) Thompson, D. S., and Zinkham, R. E., "Program to Improve the Fracture Toughness and Fatigue Resistance of Aluminum Sheet and Plate for Airframe Applications," AFML-TR-73-247, Vol. II (September 1974).
- 3.2.6.1.9(d) Babilion, C. F., Wygonik, R. H., Nordmark, G. E., and Lifka, B. W., "Mechanical Properties, Fracture Toughness, Fatigue, Environmental Fatigue Crack Growth Rates, and Corrosion Characteristics of High-Toughness Aluminum Alloy Forgings, Sheet, and Plate," AFML-TR-73-83 (April 1973) (MCIC 86842) (MIL-HDBK-5 Source M-118).
- 3.2.7.2.8 Ferguson, R. F., "Axial Stress Fatigue Strength of 2219-T851 Aluminum Alloy Plate," Report No. TFD-71-960, North American Rockwell, Los Angeles Division (July 29, 1971) (MIL-HDBK-5 Source M-216).
- 3.7.2.1.8(a) Rothweiler, C. E., and Maynard, P. S., "Evaluation of 7049-T73 Aluminum Alloy for RA-5C Wing Inner Panel Fold Rib," CMES Contract N00256-71-C-0064, Task No. NAR-18 (P046-10), Report No. NR72H-278, North American Rockwell, Columbus, Ohio (July 14, 1972) (MIL-HDBK-5 Source M-170).
- 3.7.2.1.8(b) Anon., "Boeing Test Data on X7049-T73," Submitted to Battelle to provide input data for Item 68-24 (1969) (MCIC 78639).
- 3.7.2.1.8(c) Mixon, W., and Turley, R. V., "Evaluation of Aluminum Alloys 7049-T73 and 7175-T736 Die Forging," Engineering Technical Report No. ETR-MDC-J0692, McDonnell Douglas (April 7, 1970) (MCIC 110111).
- 3.7.2.1.8(d) VanOrden, J. M., "Evaluation of 7049-T73 Aluminum Alloy Hand-Forged Billet," Lockheed California Company, Report No. LR 23447 (February 1970) (MIL-HDBK-5 Source M-43).
- 3.7.2.1.8(e) "Effect of Manufacturing Processes on Structural Allowables—Phase I," Battelle, Columbus, Ohio, AFWAL-TR-85-4128 (January 1986).

**MIL-HDBK-5H****1 December 1998**

- 3.7.3.2.8(a) Guthorn, P. S., "Design Properties and Processing Limits for Improved Aluminum Alloys," McDonnell Douglas Corporation, MDC-J1912 (December 1983) (MIL-HDBK-5 Source M-629).
- 3.7.3.2.8(b) Garland, K., "Evaluation of X7050-T736 Die Forgings," McDonnell Aircraft Company, McDonnell Douglas Corporation, Report No. 514-131.10 (February 1973) (MCIC 85880).
- 3.7.3.2.8(c) Deel, O. L., Ruff, P. E., and Mindlin, H., "Engineering Data on New Aerospace Structural Materials," AFML-TR-114 (June 1973) (MIL-HDBK-5 Source M-467).
- 3.7.3.2.9(a) Northrop, attachments to letter from V. C. Frost to D. J. Jones (March 4, 1981) (MIL-HDBK-5 Source M-482).
- 3.7.3.2.9(b) Davis, R. E., Nordmark, G. E., and Walsh, J. D., "Design Mechanical Properties, Fracture Toughness, Fatigue Properties, Exfoliation, and Stress-Corrosion Resistance of 7050 Sheet, Plate, Hand Forgings, Die Forgings, and Extrusions," Report N00019-72-C-0512, Aluminum Company of America (July 1975) (MIL-HDBK-5 Source M-322).
- 3.7.3.3.8(a) Staley, J. T., Jacoby, J. E., Davies, R. E., Nordmark, G. E., Walsh, J. D., and Rudolph, F. R., "Aluminum Alloy 7050 Extrusions," AFML-TR-76-129 (March 1977) (MCIC 99225) (MIL-HDBK-5 Source M-374).
- 3.7.4.1 Brownfield, C. D., and Badger, D. M., "Effects of Temperature-Time-Stress Histories on the Mechanical Properties of Aircraft Structural Metallic Materials," WADC TR 56-585, Part II (September 1960).
- 3.7.4.1.8 Howell, F. M., and Miller, J. L., "Axial Fatigue Strengths of Several Structural Aluminum Alloys," Proceedings of the American Society for Testing Materials, Philadelphia, PA (1956).
- 3.7.4.1.9(a) Hudson, C. M., and Hardrath, H. F., "Effects of Changing Stress Amplitude on the Rate of Fatigue-Crack-Propagation in Two Aluminum Alloys," National Aeronautics and Space Administration, Technical Note D-960 (1961).
- 3.7.4.1.9(b) McEvily, A. J., and Ilig, W., "The Rate of Fatigue-Crack Propagation in Two Aluminum Alloys," National Aeronautics and Space Administration, Technical Note 4394 (1958).
- 3.7.4.1.9(c) Brock, D., and Schijve, J., "The Influence of Mean Stress on the Propagation of Fatigue Cracks in Aluminum Alloy Sheet," NLR-TR, M. 2111, Reports and Transactions, National Aero- and Astronautical Research Institute, pp. 41-61 (1965).
- 3.7.4.1.9(d) Dubensky, R. G., "Fatigue-Crack Propagation in 2024-T3 and 7075-T6 Aluminum Alloys at High Stresses," NASA CR-1732 (1971).
- 3.7.4.1.9(e) Hudson, C. M., "Effect of Stress Ratios on Fatigue-Crack Growth in 7075-T6 and 2024-T3 Aluminum Alloy Specimens," National Advisory Committee for Aeronautics, Technical Note D-5390 (August 1969) (MCIC 75599).
- 3.7.4.1.9(f) Gurin, P. J., "Crack Propagation Tests for Some Aluminum Alloy Materials," LR 10498, Lockheed Aircraft Corporation (1955).
- 3.7.4.2.9(a) Unpublished Battelle, Columbus, Ohio data by C. F. Feddersen.



**MIL-HDBK-5H****1 December 1998**

- 3.7.4.2.9(b) “B-1 Program Data for Aluminum Alloys,” Rockwell International Corporation, Memorandum to H. D. Moran from E. W. Cawthorne, Battelle, Columbus, Ohio (April 3, 1974) (MCIC 88579).
- 3.7.4.2.9(c) Ruff, P. E., and Smith, S. H., “Development of MIL-HDBK-5 Design Allowable Properties and Fatigue-Crack-Propagation Data for Several Aerospace Materials,” AFML-TR-77-162 (October 1977).
- 3.7.5.2.8 Unpublished Letter to D. Lahrman, Battelle, from Alcoa, “Fatigue Properties of 7150-T77511 Extruded Shapes.” (December 9, 1993) (MIL-HDBK-5 Source M-798).
- 3.7.6.1.8(a) Unpublished Letter to P. Ruff, Battelle Memorial Institute, from Lockheed-Georgia, “Fatigue Data on 7175-T7351 Extrusions,” January 1982.
- 3.7.6.1.8(b) Carter, F. J., Bateh, E. J., and White, D. L., “C-5A Wing Modification Program, Material Characterization Program, 7175-T7511 Extrusions,” Lockheed-Georgia Company, Report No. LG75ER0186-2, September 1977 (MCIC 122032).
- 3.7.6.1.8(c) Unpublished Letter to P. Ruff, Battelle Memorial Institute, from Aluminum Company of America, “Fatigue Data on 7175-T73511 Extrusions and 7175-T74 Forgings,” January 24, 1990 (MIL-HDBK-5 Source M-748).
- 3.7.6.2.8(a) Schimmelbusch, H. W., “Metallurgical Evaluation of 7175-T736 and 7175-T66 Die Forgings,” Boeing Company Document No. D6-24480, May 1970 (MCIC 78656).
- 3.7.6.2.8(b) Newcomer, R., “Evaluation of Aluminum Forging Alloy 7175-T736,” McDonnell Aircraft Company Report No. MDC 70-024, 1970 (MCIC 85881).
- 3.7.6.2.8(c) Deel, O. L., and Mindlin, H., “Engineering Data on New and Emerging Structural Materials,” AFML Report No. AFML-TR-70-252, October 1970 (MIL-HDBK-5 Source M-464).
- 3.7.8.2.8(d) Doecker, P., “Effect of Manufacturing Process on Structural Allowables,” AFWAL Report No. AFWAL-TR-85-4049 (MIL-HDBK-5 Source M-626).
- 3.7.8.2.8(a) Brownhill, D. J., Davies, R. E., Nordmark, G. E., and Ponchel, B. M., “Exploratory Development for Design Data on Structural Aluminum Alloys in Representative Aircraft Environments,” AFML-TR-77-102 (July 1977) (MCIC 103463) (MIL-HDBK-5 Source M-397).
- 3.7.8.2.8(b) Unpublished letter to P. Vieth, Battelle, Columbus, Ohio from ALCOA, “Fatigue Data for 7050 and 7475 Products” (July 17, 1985) (MIL-HDBK-5 Source M-630).
- 3.7.8.2.8(c) Jones, R. L., and Coyle, T. E., “The Mechanical Stress Corrosion, Fracture Mechanics, and Fatigue Properties of 7050, 7475, and Ti-8Mo-8V-2Fe-3Al Plate and Sheet Alloys,” General Dynamics, Report No. FGT-5791 (July 24, 1973) (MCIC 100670).
- 3.7.8.2.8(d) Figge, F. A., “Advanced Metallic Structure: Air Superiority Fighter Wind Design for Improved Cost, Weight, and Integrity,” AFFDL-TR-73-52, Vol. III (June 1973) (MCIC 86574) (MIL-HDBK-5 Source M-278).

**MIL-HDBK-5H****1 December 1998**

- 3.7.8.2.8(e) Deel, O. L., Ruff, P. E., and Mindlin, H., "Engineering Data on New Aerospace Structural Materials," AFML-TR-75-97 (June 1975) (MCIC 95044) (MIL-HDBK-5 Source M-468).
- 3.7.8.2.9(a) Cervay, R. R., "Engineering Design Data for Aluminum Alloy 7475 in the T761 and T61 Conditions," AFML-TR-72-173 (September 1972) (MCIC 85363).
- 3.7.8.2.9(b) Cervay, R. R., "Static and Dynamic Fracture Properties for Aluminum Alloy 7475-T651 and T7351," AFML-TR-75-20 (April 1975).
- 3.8.1.1.8(a) Unpublished data from Garrett Turbine Engine Company, 1986 (MIL-HDBK-5 Source M-690).
- 3.8.1.1.8(b) Unpublished data from Northrop Corporation, 1988 (MIL-HDBK-5 Source M-701).
- 3.11.1.2 Eato, I. D., and Holt, M., "Flexural Fatigue Strengths of Riveted Box Beams—Alclad 14S-T6, Alclad 75S-T6, and Various Tempers of Alclad 24S," National Advisory Committee for Aeronautics, Technical Note 2452, 25 pp. (November 1951).
- 3.11.2.2(a) Gerard, G., and Becker, H., Handbook of Structural Stability, "Part I—Buckling of Flat Plates," National Advisory Committee for Aeronautics, Technical Note 3781 (July 1957).
- 3.11.2.2(b) Becker, H., Handbook of Structural Stability, "Part II—Buckling of Composite Elements," National Advisory Committee for Aeronautics, Technical Note 3782 (July 1957).
- 3.11.2.2(c) Gerard, G., and Becker, H., Handbook of Structural Stability, "Part III—Buckling of Curved Plates and Shells," National Advisory Committee for Aeronautics, Technical Note 3783 (1957).
- 3.11.2.2(d) Gerard, G., Handbook of Structural Stability, "Part IV—Failure of Plates and Composite Elements," National Advisory Committee for Aeronautics, Technical Note 3784 (1957).
- 3.11.2.2(e) Gerard, G., Handbook of Structural Stability, "Part V—Compressive Strengths of Flat Stiffened Panels," National Advisory Committee for Aeronautics, Technical Note 3785 (August 1957).



**CHAPTER 4****MAGNESIUM ALLOYS****4.1 GENERAL**

This chapter contains the engineering properties and characteristics of wrought and cast magnesium alloys used in aircraft and missile applications. Magnesium is a lightweight structural metal that can be strengthened greatly by alloying, and in some cases by heat treatment or cold work or by both.

**4.1.1 ALLOY INDEX** — The magnesium alloys in this chapter are listed in alphanumeric sequence in each of two parts, the first one being wrought forms of magnesium and the second cast forms. These sections and the alloys covered under each are shown in Table 4.1.

**Table 4.1. Magnesium Alloys Index**

Section	Designation
<b>4.2</b>	<b>Magnesium-Wrought Alloys</b>
4.2.1	AZ31B
4.2.2	AZ61A
4.2.3	ZK60A
<b>4.3</b>	<b>Magnesium-Cast Alloys</b>
4.3.1	AM100A
4.3.2	AZ91C/AZ91E
4.3.3	AZ92A
4.3.4	EZ33A
4.3.5	QE22A
4.3.6	ZE41A

**4.1.2 MATERIAL PROPERTIES**

**4.1.2.1 Mechanical Properties** — The mechanical properties are given either as design values or for information purposes. The tensile strength ( $F_{tu}$ ), tensile yield strength ( $F_{ty}$ ), elongation ( $e$ ), and sometimes the compressive yield strength ( $F_{cy}$ ) are guaranteed by procurement specifications. The properties obtained reflect the location of sample, type of test specimen and method of testing required by the product specification. The remaining design values are “derived” values; that is, sufficient tests have been made to ascertain that if a given material meets the requirements of the product specification, the material will have the compression ( $F_{cy}$ ), shear ( $F_{su}$ ) and bearing ( $F_{bru}$  and  $F_{bry}$ ) strengths listed.

**4.1.2.1.1 Tension Testing** — Room-temperature tension tests are made according to ASTM E 8. The yield strength ( $F_{ty}$ ) is obtained by the “offset method” using an offset of 0.2 percent. The speed of testing for room-temperature tests has a small effect on the strength and elongation values obtained on most magnesium alloys. The rate of stressing generally specified to the yield strength is less than 100,000 psi per

**MIL-HDBK-5H****1 December 1998**

minute and the rate of straining from the yield strength to fracture is less than 0.5 in./in./min. It can be expected that the speed of testing used for room-temperature tension tests will approach the maximum permitted.

Elevated-temperature tension tests are made according to ASTM E 21. The speed of testing has a considerable effect on the results obtained and no one standard rate of straining is given in ASTM E 21. The strain rates most commonly used on magnesium are 0.005 in./in./min. to the yield and 0.10 in./in./min. from yield to fracture [see References 4.1.2.1.1(a) to (d)].

**4.1.2.1.2 Compression Testing** — Compression test methods used for magnesium are specified in ASTM E 9. The values given for the compressive yield strength ( $F_{cy}$ ), are taken at an offset of 0.2 percent. References 4.1.2.1.2(a) and (b) provide information on test techniques.

**4.1.2.1.3 Bearing Testing** — Bearing tests of magnesium alloys are made according to ASTM E 238. The size of pin used has a significant effect on the values obtained, especially the bearing ultimate strength ( $F_{bru}$ ). On tests made to obtain the data on magnesium alloys shown in this document, pin diameters of 0.187 and 0.250 inch were used. For pin diameters significantly larger than 0.250 inch lower values may be obtained. Additional information on bearing testing is given in References 4.1.2.1.3(a) and (b). Bearing values in the property tables are considered to be “dry pin” values in accordance with the discussion in Section 1.4.7.1.

**4.1.2.1.4 Shear Testing** — The shear strength values used in this document were obtained by the “double shear” method using a pin-type specimen, the “punch shear” method and the “tension shear” method as applicable. Just as tensile ultimate strength ( $F_{tu}$ ) values vary with location and direction of sample in relation to the method of fabrication, the shear strength ( $F_{su}$ ) may be expected to reflect the effect of orientation, either as a function of the sampling or the maximum stresses imposed by the method of test. Information on shear testing is given in Reference 4.1.2.1.4.

**4.1.2.1.5 Shear Raisers** — The effect of notches, holes, and stress raisers on the static properties of magnesium alloys is described in References 4.1.2.1.5(a) through (c). Additional data on the strength properties of magnesium alloys are presented in References 4.1.2.1.5(d) through (h).

**4.1.2.1.6 Creep** — Some creep data on magnesium alloys are summarized in Reference 4.1.2.1.6.

**4.1.2.1.7 Fatigue** — Room-temperature axial load fatigue data for several magnesium alloys are presented in appropriate alloy sections. References 4.1.2.1.7(a) and (b) provide additional data on fatigue of magnesium alloys.

**4.1.3 PHYSICAL PROPERTIES** — Selected experimental data from the literature were used in determining values for physical properties. In other cases, enough information was available to calculate the constants. Estimated values of some of the remaining constants were also included. Estimated values are noted.

**4.1.4 ENVIRONMENTAL CONSIDERATIONS** — Corrosion protection must be considered for all magnesium applications. Protection can be provided by anodic films, chemical conversion coatings, paint systems, platings, or a combination of these methods. Proper drainage must be provided to prevent entrapment of water or other fluids. Dissimilar metal joints must be properly and completely insulated, including barrier strips and sealants.

**MIL-HDBK-5H****1 December 1998**

Strain-hardened or age-hardened alloys may be annealed or overaged by prolonged exposure to elevated temperatures, with a resulting decrease in strength. Maximum recommended temperatures for prolonged service are reported, where available, for specific alloys.

**4.1.5 ALLOY AND TEMPER DESIGNATIONS** — Standard ASTM nomenclature is used for the alloys listed. Temper designations are given in ASTM B 296. A summary of the temper designations is given in Table 4.1.5.

**4.1.6 JOINING METHODS** — Most magnesium alloys may be welded; refer to “Comments and Properties” in individual alloy sections. Adhesive bonding and brazing may be used to join magnesium to itself or other alloys. All types of mechanical fasteners may be used to join magnesium. Refer to Section 4.1.4 when using mechanical fasteners or joining of dissimilar materials with magnesium alloys.

## MIL-HDBK-5H

1 December 1998

**Table 4.1.5. Temper Designation System for Magnesium Alloys****Temper Designation System<sup>a</sup>**

This temper designation system is used for all forms of wrought and cast magnesium and magnesium alloy products except ingots. It is based on the sequence of basic treatments used to produce the various tempers. The temper designation follows the alloy designation, the two being separated by a hyphen. Basic temper designations consist of letters. Subdivisions of the basic tempers, where required, are indicated by one or more digits following the letter. These designate specific sequences of basic treatments, but only operations recognized as significantly influencing the characteristics of the product are indicated. Should some other variation of the same sequence of basic operations be applied to the same alloy, resulting in different characteristics, then additional digits are added to the designation.

NOTE—In material specifications containing reference to two or more tempers of the same alloy which result in identical mechanical properties, the distinction between the tempers should be covered in suitable explanatory notes.

**Basic Temper Designations**

- F** **as fabricated.** Applies to the products of shaping processes in which no special control over thermal conditions or strain-hardening is employed.
- O** **annealed recrystallized (wrought products only).** Applies to wrought products which are annealed to obtain the lowest strength temper.
- H** **strain-hardened (wrought products only).** Applies to products which have their strength increased by strain-hardening, with or without supplementary thermal treatments to produce some reduction in strength. The H is always followed by two or more digits.
- W** **solution heat-treated.** An unstable temper applicable only to alloys which spontaneously age at room temperature after solu-

tion heat-treatment. This designation is specific only when the period of natural aging is indicated: for example, W ½ hr.

- T** **thermally treated to product stable tempers other than F, O, or H.** Applies to products which are thermally treated, with or without supplementary strain-hardening, to product stable tempers. The T is always followed by one or more digits.

**Subdivisions of H Temper:  
Strain-Hardened**

The first digit following H indicates the specific combination of basic operations, as follows:

- H1** **strain-hardened only.** Applies to products which are strain-hardened to obtain the desired strength without supplementary thermal treatment. The number following this designation indicates the degree of strain-hardening.
- H2** **strain-hardened and partially annealed.** Applies to products which are strain-hardened more than the desired final amount and then reduced in strength to the desired level by partial annealing. The number following this designation indicates the degree of strain-hardening remaining after the product has been partially annealed.
- H3** **strain-hardened and stabilized.** Applies to products which are strain-hardened and whose mechanical properties are stabilized by a low temperature thermal treatment to slightly lower strength and increase ductility. The number following this designation indicates the degree of strain-hardening remaining after the stabilization treatment.

The digit following the designations H1, H2, and H3 indicates the final degree of strain hardening. Tempers between 0 (annealed) and 8 (full-hard) are designated by numerals 1 through 7. Material having an ultimate tensile strength about midway between

<sup>a</sup> From ASTM B 296.

## MIL-HDBK-5H

1 December 1998

**Table 4.1.5. Temper Designation System for Magnesium Alloys (Continued)**

that of the 0 temper and that of the 8 temper is designated by the numeral 4; about midway between the 0 and 4 tempers by the numeral 2; and about midway between 4 and 8 tempers by the numeral 6, etc. Numeral 9 designates tempers whose minimum ultimate tensile strength exceeds that of the 8 temper.

The third digit, when used, indicates a variation of a two-digit temper. It is used when the degree of control of temper or the mechanical properties or both differ from, but are close to, that (or those) for the two-digit H temper designation to which it is added. Numerals 1 through 9 may be arbitrarily assigned as the third digit for an alloy and product to indicate a specific degree of control of temper or special mechanical property limits.

**Subdivisions of T Temper:  
Thermally Treated**

Numerals 1 through 10 following the T indicate specific sequences of basic treatments, as follows.

- T1**    **cooled from an elevated temperature shaping process and naturally aged to a substantially stable condition.** Applies to products for which the rate of cooling from an elevated temperature shaping process, such as casting or extrusion, is such that their strength is increased by room temperature aging.
- T2**    **annealed (castings only).** Applies to a type of annealing treatment used to improve ductility and increase stability.
- T3**    **solution heat-treated and cold worked.** Applies to products which are cold worked to improve strength after solution heat-treatment, or in which the effect of cold work in flattening or straightening is recognized in mechanical property limits.
- T4**    **solution heat-treated and naturally aged to a substantially stable condition.** Applies to products which are not cold worked after solution heat-treatment, or in which the effect of cold work in flattening or straight-

ening may not be recognized in mechanical property limits.

- T5**    **cooled from an elevated temperature shaping process and artificially aged.** Applies to products which are cooled from an elevated temperature shaping process, such as casting or extrusion, and artificially aged to improve mechanical properties or dimensional stability or both.

- T6**    **solution heat-treated and artificially aged.** Applies to products which are not cold worked after solution heat-treatment, or in which the effect of cold work in flattening or straightening may not be recognized in mechanical property limits.

- T7**    **solution heat-treated and stabilized.** Applies to products that are stabilized after solution heat-treatment to carry them beyond a point of maximum strength to provide control of some special characteristic.

- T8**    **solution heat-treated, cold worked, and artificially aged.** Applies to products which are cold worked to improve strength, or in which the effect of cold work in flattening or straightening is recognized in mechanical property limits.

- T9**    **solution heat-treated, artificially aged, and cold worked.** Applies to products which are cold worked to improve strength.

- T10**    **cooled from an elevated temperature shaping process, artificially aged, and cold worked.** Applies to products which are artificially aged after cooling from an elevated temperature shaping process, such as extrusion, and cold worked to further improve strength.

Additional digits, the first of which shall not be zero, may be added to designations T1 through T10 to indicate a variation in treatment which significantly alters the product characteristics<sup>b</sup> that are or would be obtained using the basic treatment.

<sup>b</sup> For this purpose, characteristic is something other than mechanical properties.

**MIL-HDBK-5H****1 December 1998****4.2 MAGNESIUM-WROUGHT ALLOYS****4.2.1 AZ31B**

**4.2.1.0 Comments and Properties** — AZ31B is a wrought magnesium-base alloy containing aluminum and zinc. It is available in the form of sheet, plate, extruded sections, forgings, and tubes. AZ31B has good room-temperature strength and ductility and is used primarily for applications where the temperature does not exceed 300°F. Increased strength is obtained in the sheet and plate form by strain hardening with a subsequent partial anneal (H24 and H26 temper). No treatments are available for increasing the strength of this alloy after fabrication.

Forming of AZ31B must be done at elevated temperatures if small radii or deep draws are required. If the temperatures used are too high or the times too great, H24 and H26 temper material will be softened. This alloy is readily welded but must be stress relieved after welding to prevent stress corrosion cracking.

Material specifications covering AZ31B wrought products are given in Table 4.2.1.0(a). Room-temperature mechanical and physical properties are shown in Tables 4.2.1.0(b) through (d). The effect of temperature on physical properties is shown in Figure 4.2.1.0.

**Table 4.2.1.0(a). Material Specifications for AZ31B Magnesium Alloy**

Specification	Form
AMS 4375	Sheet and plate
AMS 4376	Plate
AMS 4377	Sheet and plate
ASTM B 107	Extrusion
ASTM B 91	Forging

The temper index for AZ31B is as follows:

<u>Section</u>	<u>Temper</u>
4.2.1.1	O
4.2.1.2	H24
4.2.1.3	H26
4.2.1.4	F

**4.2.1.1 AZ31B-O Temper** — Effect of temperature on the tensile modulus of sheet and plate is presented in Figure 4.2.1.1.4. Typical room-temperature stress-strain and tangent-modulus curves are presented in Figure 4.2.1.1.6.

**4.2.1.2 AZ31B-H24 Temper** — Effect of temperature on the mechanical properties of sheet and plate is shown in Figures 4.2.1.2.1 through 4.2.1.2.4, and 4.2.1.2.6. Typical room-temperature tension and compression stress-strain and tangent-modulus curves for sheet are shown in Figure 4.2.1.2.6.

**4.2.1.3 AZ31B-H26 Temper**

**4.2.1.4 AZ31B-F Temper** — Figures 4.2.1.4.8 (a) and (b) contain fatigue data for forged disk at room temperature.

**MIL-HDBK-5H****1 December 1998****Table 4.2.1.0(b). Design Mechanical and Physical Properties of AZ31B Magnesium Alloy Sheet and Plate**

Specification . . . . .	AMS 4375					AMS 4377						
	Sheet		Plate			Sheet		Plate				
	0					H24						
	0.016-0.060	0.061-0.249	0.250-0.500	0.501-2.000	2.001-3.000	0.016-0.062	0.063-0.249	0.250-0.374	0.375-0.500	0.501-1.000	1.001-2.000	2.001-3.000
Basis . . . . .	S	S	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:												
$F_{tu}$ , ksi:												
L . . . . .	32	32	32	32	32	39	39	38	37	36	34	34
LT . . . . .	...	...	...	...	...	40	40	39	38	37	35	...
$F_{ty}$ , ksi:												
L . . . . .	18	15	15	15	15	29	29	26	24	22	20	18
LT . . . . .	...	...	...	...	...	32	32	29	27	25	23	...
$F_{cy}$ , ksi:												
L . . . . .	...	12	10	10	8	...	24	20	16	13	10	9
LT <sup>a</sup> . . . . .	...	...	...	...	...	...	...	...	...	...	...	...
$F_{su}$ , ksi . . . . .	17	17	17	...	...	18	18	18	18	...	...	...
$F_{bru}^b$ , ksi:												
(e/D = 1.5) . . . . .	50	50	50	...	...	58	58	56	54	...	...	...
(e/D = 2.0) . . . . .	60	60	60	...	...	68	68	65	63	...	...	...
$F_{bry}^b$ , ksi:												
(e/D = 1.5) . . . . .	29	29	27	...	...	43	43	38	34	...	...	...
(e/D = 2.0) . . . . .	29	29	27	...	...	43	43	38	34	...	...	...
$e$ , percent . . . . .												
L . . . . .	12	12	12	10	9	6	6	8	8	8	8	8
$E$ , 10 <sup>3</sup> ksi . . . . .	6.5											
$E_c$ , 10 <sup>3</sup> ksi . . . . .	6.5											
$G$ , 10 <sup>3</sup> ksi . . . . .	2.4											
$\mu$ . . . . .	0.35											
Physical Properties:												
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.0639											
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 4.2.1.0											

a  $F_{cy}$ (LT) allowables are equal to or greater than  $F_{cy}$ (L) allowables.

b Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 4.2.1.0(c). Design Mechanical and Physical Properties of AZ31B Magnesium Alloy Plate**

Specification . . . . .	AMS 4376						
Form . . . . .	Plate						
Temper . . . . .	H26						
Thickness <sup>a</sup> , in. . . . .	0.250- 0.375	0.376- 0.438	0.439- 0.500	0.501- 0.750	0.751- 1.000	1.001- 1.500	1.501- 2.000
Basis . . . . .	S	S	S	S	S	S	S
Mechanical Properties:							
$F_u$ , ksi:							
L . . . . .	39	38	38	37	37	35	35
LT . . . . .	40	39	39	38	38	36	36
$F_{ty}$ , ksi:							
L . . . . .	27	26	26	25	23	22	21
LT . . . . .	30	29	29	28	26	25	24
$F_{cy}$ , ksi:							
L . . . . .	22	21	18	17	16	15	14
LT <sup>a</sup> . . . . .	...	...	...	...	...	...	...
$F_{su}$ , ksi . . . . .	18	18	18	...	...	...	...
$F_{bru}^b$ , ksi:							
(e/D = 1.5) . . . . .	58	56	56	...	...	...	...
(e/D = 2.0) . . . . .	68	65	65	...	...	...	...
$F_{bry}^b$ , ksi:							
(e/D = 1.5) . . . . .	40	39	36	...	...	...	...
(e/D = 2.0) . . . . .	40	39	36	...	...	...	...
$e$ , percent:							
L . . . . .	6	6	6	6	6	6	6
$E$ , 10 <sup>3</sup> ksi . . . . .	6.5						
$E_c$ , 10 <sup>3</sup> ksi . . . . .	6.5						
$G$ , 10 <sup>3</sup> ksi . . . . .	2.4						
$\mu$ . . . . .	0.35						
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.0639						
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 4.2.1.0						

a  $F_{cy}$ (LT) allowables are equal to or greater than  $F_{cy}$ (L) values.

b Bearing values are "dry pin" values per Section 1.4.7.1.



**MIL-HDBK-5H****1 December 1998****Table 4.2.1.0(d). Design Mechanical and Physical Properties of AZ31B Magnesium Alloy Extrusion and Forging**


Specification . . . . .	ASTM B 107							ASTM B 91
Form . . . . .	Extruded bar, rod, and solid shapes				Extruded hollow shapes	Extruded tube		Forging
Temper . . . . .	F							
Thickness <sup>a</sup> , in. . . . .	≤0.249	0.250-1.499	1.500-2.499	2.500-4.999	All	0.028-0.250 <sup>b</sup>	0.251-0.750 <sup>b</sup>	...
Basis . . . . .	S	S	S	S	S	S	S	S
Mechanical Properties:								
$F_{tu}$ , ksi:								
L . . . . .	35	35	34	32	32	32	32	34
LT . . . . .	...	...	...	...	...	...	...	...
$F_{ty}$ , ksi:								
L . . . . .	21	22	22	20	16	16	16	19
LT . . . . .	...	...	...	...	...	...	...	...
$F_{cy}$ , ksi:								
L . . . . .	...	12	12	10	10	10	10	...
LT . . . . .	...	...	...	...	...	...	...	...
$F_{su}$ , ksi . . . . .	17	17	17	...	...	...	...	...
$F_{bru}^c$ , ksi:								
(e/D = 1.5) . . . . .	36	36	36	...	...	...	...	...
(e/D = 2.0) . . . . .	45	45	45	...	...	...	...	...
$F_{bry}^c$ , ksi:								
(e/D = 1.5) . . . . .	23	23	23	...	...	...	...	...
(e/D = 2.0) . . . . .	23	23	23	...	...	...	...	...
$e$ , percent:								
L . . . . .	7	7	7	7	8	8	4	6
$E$ , 10 <sup>3</sup> ksi . . . . .	6.5							
$E_c$ , 10 <sup>3</sup> ksi . . . . .	6.5							
$G$ , 10 <sup>3</sup> ksi . . . . .	2.4							
$\mu$ . . . . .	0.35							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.0639							
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 4.2.1.0							

a Wall thickness for tube.

b For outside diameter ≤6.000 inches.


c Bearing values are “dry pin” values per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 4.2.1.0. Effect of temperature on the physical properties of AZ31B.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 4.2.1.1.4. Effect of temperature on the tensile modulus (E) of AZ31B-O sheet and plate.**



**Figure 4.2.1.1.6. Typical tensile and compressive stress-strain and compressive tangent-modulus curves for AZ31B-O sheet and plate at room temperature.**

## MIL-HDBK-5H

1 December 1998




Figure 4.2.1.2.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of AZ31B-H24 sheet and plate.

MIL-HDBK-5H  
1 December 1998




Figure 4.2.1.2.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of AZ31B-H24 sheet and plate.




Figure 4.2.1.2.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of AZ31B-H24 sheet and plate.

MIL-HDBK-5H  
1 December 1998




Figure 4.2.1.2.4. Effect of temperature on the tensile modulus (E) of AZ31B-H24 sheet and plate.





Figure 4.2.1.2.6. Typical tensile and compressive stress-strain and compressive tangent-modulus curves for AZ31B-H24 sheet at room temperature.

## MIL-HDBK-5H

1 December 1998



**Figure 4.2.1.4.8(a). Best-fit S/N curves for unnotched AZ31B-F magnesium alloy forged disk, transverse direction.**

Correlative Information for Figure 4.2.1.4.8(a)

Product Form: Forged disk, 1-inch thick

No. of Heats/Lots: 1

Properties: TUS, ksi TYS, ksi Temp., °F

38 26 RT

Equivalent Stress Equation:

Specimen Details: Unnotched  
0.75-inch gross diameter  
0.30-inch net diameter

For R values between -1.0 and -0.50  
 $\log N_f = 7.13 - 2.20 \log (S_{eq} - 12.9)$   
 $S_{eq} = S_{max}(1-R)^{0.56}$   
Standard Error of Estimate = 0.613  
Standard Deviation in Life = 0.916  
 $R^2 = 55.2\%$

Surface Condition:

Polished sequentially with No. 320  
aluminum oxide cloth, No. 0, 00, and 000  
emery paper and finally No. 600 aluminum  
oxide powder in water

For R values between 0.0 and 0.50  
 $\log N_f = 8.87 - 3.26 \log (S_{eq} - 15.0)$   
 $S_{eq} = S_{max}(1-R)^{0.33}$   
Standard Error of Estimate = 0.829  
Standard Deviation in Life = 1.014  
 $R^2 = 33.2\%$


References: 4.2.1.1.8

Sample Size = 194

Test Parameters:

Loading - Axial  
Frequency - 1500 cpm  
Temperature - RT  
Environment - Air

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998**

**Figure 4.2.1.4.8(b). Best-fit S/N curves for notched,  $K_t = 3.3$ , AZ31B-F magnesium alloy forged disk, transverse direction.**

Correlative Information for Figure 4.2.1.4.8(b)

Product Form: Forged disk, 1-inch thick

Test Parameters:

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     38            26            RT

Loading - Axial  
 Frequency - 1500 cpm  
 Temperature - RT  
 Environment - Air

Specimen Details: Notched,  $K_t = 3.3$   
 0.350-inch gross diameter  
 0.280-inch net diameter  
 0.01-inch root radius,  $r$   
 60° flank angle,  $\omega$

No. of Heats/Lots: 1

Equivalent Stress Equation:

$\log N_f = 8.28 - 4.34 \log (S_{\max})$   
 Standard Error of Estimate = 0.534  
 Standard Deviation in Life = 0.707  
 $R^2 = 43\%$

Reference:    4.2.1.1.8

Sample Size = 34



**MIL-HDBK-5H****1 December 1998****4.2.2 AZ61A**

**4.2.2.0 Comments and Properties** — AZ61A is a wrought magnesium-base alloy containing aluminum and zinc. It is available in the form of extruded sections, tubes, and forgings in the as-fabricated (F) temper. AZ61A is much like AZ31B in general characteristics. The increased aluminum content increases the strength and decreases the ductility slightly.

Severe forming must be done at elevated temperatures. This alloy is readily welded but must be stress relieved after welding to prevent stress corrosion cracking.

Material specifications covering AZ61A are given in Table 4.2.2.0(a). Room-temperature mechanical and physical properties are shown in Table 4.2.2.0(b).

**Table 4.2.2.0(a). Material Specifications for AZ61A  
Magnesium Alloy**

Specification	Form
AMS 4350	Extrusion
ASTM B 91	Forging

**MIL-HDBK-5H****1 December 1998****Table 4.2.2.0(b). Design Mechanical and Physical Properties of AZ61A Magnesium Alloy Extrusion and Forging**

Specification . . . . .	AMS 4350					ASTM B 91
	Extruded bar, rod, and solid shapes			Extruded hollow shapes	Extruded tube	Forging
	F					
	≤0.249	0.250-2.499	2.500-4.499 <sup>a</sup>	All	0.028-0.750 <sup>b</sup>	...
Basis . . . . .	S	S	S	S	S	S
Mechanical Properties:						
$F_{tu}$ , ksi:						
L . . . . .	38	40	40	36	36	38
LT . . . . .	...	...	...	...	...	...
$F_{ty}$ , ksi:						
L . . . . .	21	24	22	16	16	22
LT . . . . .	...	...	...	...	...	...
$F_{cy}$ , ksi:						
L . . . . .	14	14	14	11	11	14
LT . . . . .	...	...	...	...	...	...
$F_{su}$ , ksi . . . . .	19	19	...	...	...	19
$F_{bru}^c$ , ksi:						
(e/D = 1.5) . . . . .	45	45	...	...	...	50
(e/D = 2.0) . . . . .	55	55	...	...	...	60
$F_{bry}^c$ , ksi:						
(e/D = 1.5) . . . . .	28	28	...	...	...	28
(e/D = 2.0) . . . . .	32	32	...	...	...	32
$e$ , percent:						
L . . . . .	8	9	7	7	7	6
$E$ , 10 <sup>3</sup> ksi . . . . .	6.3					
$E_c$ , 10 <sup>3</sup> ksi . . . . .	6.3					
$G$ , 10 <sup>3</sup> ksi . . . . .	2.4					
$\mu$ . . . . .	0.31					
Physical Properties:						
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.0647					
$C$ , Btu/(lb)(°F) . . . . .	0.25 (at 78° F) <sup>d</sup>					
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	46 (212 to 572° F)					
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . . . .	14 (65 to 212° F)					

a For cross-sectional area ≤25 square inches.

b Wall thickness for outside diameters ≤6.000 inches.

c Bearing values are "dry pin" values per Section 1.4.7.1.

d Estimated.

**MIL-HDBK-5H****1 December 1998****4.2.3 ZK60A**

**4.2.3.0 Comments and Properties** — ZK60A is a wrought magnesium-base alloy containing zinc and zirconium. It is available as extruded sections, tubes, and forgings. Increased strength is obtained by artificial aging (T5) from the as-fabricated (F) temper. ZK60A has the best combination of high room-temperature strength and ductility of the wrought magnesium-base alloys. It is used primarily at temperatures below 300 °F.

ZK60A has good ductility as compared with other high-strength magnesium alloys and can be formed or bent cold into shapes not possible with those alloys having less ductility. It is not considered a weldable alloy.

Material specifications for ZK60A are given in Table 4.2.3.0(a). Room-temperature mechanical and physical properties are shown in Tables 4.2.3.0(b) and (c). Elevated temperature curves for physical properties are shown in Figures 4.2.3.0.

**Table 4.2.3.0(a). Material Specifications for ZK60A  
Magnesium Alloy**

Specification	Form
ASTM B 107	Extrusion
AMS 4352	Extrusion
AMS 4362	Die and hand forgings

The temper index for ZK60A is as follows:

<u>Section</u>	<u>Temper</u>
4.2.3.1	F
4.2.3.2	T5

**4.2.3.1 ZK60A-F Temper**

**4.2.3.2 ZK60A-T5 Temper** — Typical room-temperature tension and compression stress-strain curves for extrusions are shown in Figures 4.2.3.2.6(a) and (b). Fatigue curves are presented in Figure 4.2.3.2.8(a) through (c).

**MIL-HDBK-5H****1 December 1998****Table 4.2.3.0(b). Design Mechanical and Physical Properties of ZK60A Magnesium Alloy Extrusion**

Specification . . . . .	ASTM B 107					
Form . . . . .	Extruded rod, bar, and solid shapes				Extruded hollow shapes	Extruded tube
Temper . . . . .	F					
Cross-sectional area, in. <sup>2</sup> . . . . .	<2.000	2.000-2.999	3.000-4.999	5.000-39.999	All	≤3.000 in. O.D.
Thickness, in. . . . .	All	All	All	All	All	0.028-0.750 wall
Basis . . . . .	S	S	S	S	S	S
Mechanical Properties:						
$F_{tu}$ , ksi:						
L . . . . .	43	43	43	43	40	40
LT . . . . .	...	...	...	...	...	...
$F_{ty}$ , ksi:						
L . . . . .	31	31	31	31	28	28
LT . . . . .	...	...	...	...	...	...
$F_{cy}$ , ksi:						
L . . . . .	27	26	25	20	20	20
LT . . . . .	...	...	...	...	...	...
$F_{su}$ , ksi . . . . .	22	22	22	...	...	...
$F_{bru}^a$ , ksi:						
(e/D = 1.5) . . . . .	...	...	...	...	...	...
(e/D = 2.0) . . . . .	70	70	70	...	...	...
$F_{bry}^a$ , ksi:						
(e/D = 1.5) . . . . .	...	...	...	...	...	...
(e/D = 2.0) . . . . .	45	45	45	...	...	...
$e$ , percent:						
L . . . . .	5	5	5	4	5	5
$E$ , 10 <sup>3</sup> ksi . . . . .	6.5					
$E_c$ , 10 <sup>3</sup> ksi . . . . .	6.5					
$G$ , 10 <sup>3</sup> ksi . . . . .	2.4					
$\mu$ . . . . .	0.35					
Physical Properties:						
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.0659					
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 4.2.3.0					


a Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 4.2.3.0(c). Design Mechanical and Physical Properties of ZK60A Magnesium Alloy Extrusion and Forging**


Specification . . . . .	AMS 4352									AMS 4362	
	Extruded rod, bar, and solid shapes						Extruded hollow shapes	Extruded tube		Die forging	Hand forging
Form . . . . .											
Temper . . . . .	T5										
Cross-sectional area, in. <sup>2</sup> . . . . .	<2.000	2.000-2.999	3.000-4.999	5.000-9.999	10.000-24.999	25.000-39.999	All	≤3.000 in. O.D.	3.000-8.500 in. O.D.	...	...
Thickness, in. . . . .	All	All	All	All	All	All	All	0.028-0.250 wall	0.094-1.188 wall	≤3.000	≤6.000
Basis . . . . .	S	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:											
<i>F<sub>tu</sub></i> , ksi:											
L . . . . .	45	45	45	45	45	43	46	46	44	42	38
LT . . . . .	...	...	...	...	...	...	...	...	...	...	...
<i>F<sub>ty</sub></i> , ksi:											
L . . . . .	36	36	36	34	34	31	38	38	33	26	20
LT . . . . .	...	...	...	...	...	...	...	...	...	...	...
<i>F<sub>cy</sub></i> , ksi:											
L . . . . .	30	28	25	23	22	20	26	26	21	...	...
LT . . . . .	...	...	...	...	...	...	...	...	...	...	...
<i>F<sub>su</sub></i> , ksi . . . . .	22	22	22	...	...	...	...	...	...	...	...
<i>F<sub>bru</sub></i> <sup>a</sup> , ksi:											
(e/D = 1.5) . . . . .	...	...	...	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	71	71	71	...	...	...	...	...	...	...	...
<i>F<sub>bry</sub></i> <sup>a</sup> , ksi:											
(e/D = 1.5) . . . . .	...	...	...	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	47	47	47	...	...	...	...	...	...	...	...
<i>e</i> , percent:											
L . . . . .	4	4	4	6	6	6	4	4	4	7	7
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	6.5										
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	6.5										
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	2.4										
<i>μ</i> . . . . .	0.35										
Physical Properties:											
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.0659										
<i>C</i> , <i>K</i> , and <i>α</i> . . . . .	See Figure 4.2.3.0										

a Bearing values are "dry pin" values per Section 1.4.7.1.


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 4.2.3.0. Effect of temperature on the physical properties of ZK60A magnesium alloy.**

**MIL-HDBK-5H****1 December 1998**

**Figure 4.2.3.2.6(a). Typical tensile stress-strain curve for ZK60A-T5 extrusion at room temperature.**



**Figure 4.2.3.2.6(b). Typical compressive stress-strain curve for ZK60A-T5 extrusion at room temperature.**








## MIL-HDBK-5H

1 December 1998



**Figure 4.2.3.2.8(c). Best-fit S/N curves for notched,  $K_t = 3.4$ , ZK60A-T5 extruded bar, longitudinal direction.**

Correlative Information for Figure 4.2.3.2.8(c)

Product Form: Extruded bar, 0.50-inch diameter

Properties: TUS, ksi TYS, ksi Temp., °F

58.2 40.9 RT  
(notched)

Specimen Details: Circumferential notched,  
 $K_t = 4$   
0.50-inch gross diameter  
0.40-inch net diameter  
0.010-inch notch radius  
60° flank angle,  $\omega$

Surface Condition: Ground with aluminum  
oxide wheel lubricated with  
sulfur cutting oil; lapped  
with a copper rod and  
No. 600 grit alundum  
lapping compound

Reference: 4.2.3.2.8

Test Parameters:

Loading - Axial  
Frequency - 3600 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$$\log N_f = 9.27 - 4.13 \log (S_{eq} - 5.3)$$

$$S_{eq} = S_{max} (1 - R)^{0.46}$$

Standard Error of Estimate = 0.55

Standard Deviation in Life = 0.99

$R^2 = 70\%$

Sample Size = 36

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998****4.3 MAGNESIUM CAST ALLOYS****4.3.1 AM100A**

**4.3.1.0 Comments and Properties** — AM100A is a magnesium-base casting alloy containing aluminum and a small amount of manganese. It is primarily used as permanent mold castings. AM100A has about the same characteristics as AZ92A. AM100A has less tendency to microshrinkage and hot shortness than the Mg-Al-Zn alloys. It has good weldability and fair pressure tightness.

Material specifications for AM100A are given in Table 4.3.1.0(a). Room-temperature mechanical and physical properties are shown in Table 4.3.1.0(b).

**Table 4.3.1.0(a). Material Specifications for AM100A  
Magnesium Alloy**

Specification	Form
AMS 4455	Investment casting
AMS 4483	Permanent mold casting
MIL-M-46062	Casting

**MIL-HDBK-5H**  
**1 December 1998**

**Table 4.3.1.0(b). Design Mechanical and Physical Properties of AM100A Magnesium Alloy Casting**

Specification .....	AMS 4455	AMS 4483	MIL-M-46062			
Form .....	Investment casting	Permanent mold casting	Casting (any method)			
Temper .....	T6	T6	T6			
Location within casting .....	Any area		Designated area			Nondesignated area
			Class 1 <sup>b</sup>	Class 2 <sup>b</sup>	Class 3 <sup>b</sup>	
Basis .....	S	S	S	S	S	S
Mechanical Properties <sup>a</sup> :						
$F_{tu}$ , ksi .....	17 <sup>c</sup>	17 <sup>c</sup>	38	35	30	17
$F_{ty}$ , ksi .....	9.5 <sup>c</sup>	10 <sup>c</sup>	20	18	16	10
$F_{cy}$ , ksi .....	9.5	10	20	18	16	10
$F_{su}$ , ksi .....	...	...	...	...	...	...
$F_{bru}$ , ksi:						
(e/D = 1.5) .....	...	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...	...
$F_{bry}$ , ksi:						
(e/D = 1.5) .....	...	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...	...
$e$ , percent .....	1 <sup>c</sup>	...	3	1.5	1	0.75
$E$ , 10 <sup>3</sup> ksi .....	6.5					
$E_c$ , 10 <sup>3</sup> ksi .....	6.5					
$G$ , 10 <sup>3</sup> ksi .....	2.4					
$\mu$ .....	0.35					
Physical Properties:						
$\omega$ , lb./in. <sup>3</sup> .....	0.0651					
$C$ , $K$ , and $\alpha$ .....	...					

- a Reference should be made to the specific requirements of the procuring or certifying agency with regard to the use of the above values in the design of castings.
- b Class of properties attainable depends on location specified and casting design and should be coordinated with the producer.
- c When specified on drawing, conformance to tensile property requirements is determined by testing specimens cut from castings.

**MIL-HDBK-5H****1 December 1998****4.3.2 AZ91C/AZ91E**

**4.3.2.0 Comments and Properties** — AZ91C is a magnesium-base casting alloy containing aluminum and zinc. AZ91E is a version which contains a significantly lower level of impurities resulting in improved corrosion resistance. These alloys have good castability with a good combination of ductility and strength. AZ91C and AZ91E are the most commonly used sand castings for temperatures under 300 °F. AZ91C is available as sand and investment castings, while AZ91E is available as a sand casting. AZ91C and AZ91E have fair weldability and pressure tightness.

Some material specifications covering AZ91C/AZ91E are presented in Table 4.3.2.0(a). Room-temperature mechanical and physical properties are shown in Tables 4.3.2.0(b) and (c).

**Table 4.3.2.0(a). Material Specifications for AZ91C/AZ91E  
Magnesium Alloy**

Specification	Form
AMS 4437	Sand casting
AMS 4452	Investment casting
MIL-M-46062	Casting
AMS 4446	Sand casting

The temper index for AZ91C/AZ91E is as follows:

Section  
4.3.2.1

Temper  
T6

**4.3.2.1 T6 Temper** — Figure 4.3.2.1.4 contains an elevated temperature curve for tension and compression moduli. Typical tensile stress-strain curves at room temperature and several elevated temperatures are presented in Figure 4.3.2.1.6.

**MIL-HDBK-5H****1 December 1998****Table 4.3.2.0(b). Design Mechanical and Physical Properties of AZ91C Magnesium Alloy Casting**

Specification .....	AMS 4437	AMS 4452	MIL-M-46062			
	Sand casting	Investment casting	Casting (any method)			
Form .....	T6	T6	T6			
Temper .....	Any area		Designated area			Nondesignated area
			Class 1 <sup>b</sup>	Class 2 <sup>b</sup>	Class 3 <sup>b</sup>	
Location within casting .....						
Basis .....	S	S	S	S	S	S
Mechanical Properties <sup>a</sup> :						
$F_{tu}$ , ksi .....	17 <sup>c</sup>	17 <sup>c</sup>	35	29	27	17
$F_{ty}$ , ksi .....	12 <sup>c</sup>	12 <sup>c</sup>	18	16	14	12
$F_{cy}$ , ksi .....	12	12	18	16	14	12
$F_{su}$ , ksi .....	...	...	...	...	...	...
$F_{bru}$ , ksi:						
(e/D = 1.5) .....	...	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...	...
$F_{bry}$ , ksi:						
(e/D = 1.5) .....	...	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...	...
$e$ , percent .....	0.75 <sup>c</sup>	1 <sup>c</sup>	4	3	2	0.75
$E$ , 10 <sup>3</sup> ksi .....	6.5					
$E_c$ , 10 <sup>3</sup> ksi .....	6.5					
$G$ , 10 <sup>3</sup> ksi .....	2.4					
$\mu$ .....	0.35					
Physical Properties:						
$\omega$ , lb./in. <sup>3</sup> .....	0.0652					
$C$ , Btu/(lb)(°F) .....	0.25 <sup>d</sup>					
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	41 (212°F to 572°F)					
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	14 (65°F to 212°F)					

- a Reference should be made to the specific requirements of the procuring or certifying agency with regard to the use of the above values in the design of castings.
- b Class of properties attainable depends on location specified and casting design and should be coordinated with the producer.
- c When specified on drawing, conformance to tensile property requirements is determined by testing specimens cut from castings.
- d Estimated.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 4.3.2.0(c). Design Mechanical and Physical Properties of AZ91E Magnesium Alloy Casting**


Specification .....	AMS 4446
Form .....	Sand casting
Condition .....	T6
Location within casting .....	Any area
Basis .....	S
Mechanical Properties <sup>a</sup> :	
$F_{tu}$ , ksi .....	17 <sup>b</sup>
$F_{ty}$ , ksi .....	12 <sup>b</sup>
$F_{cy}$ , ksi .....	12
$F_{su}$ , ksi .....	...
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$e$ , percent .....	...
$E$ , $10^3$ ksi .....	6.5
$E_c$ , $10^3$ ksi .....	6.5
$G$ , $10^3$ ksi .....	2.4
$\mu$ .....	0.35
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.0652
$C$ , Btu/(lb)(°F) .....	0.25 <sup>c</sup>
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	41 (212°F to 572°F)
$\alpha$ , $10^{-6}$ in./in./F .....	14 (65°F to 212°F)

a Reference should be made to the specific requirements of the procuring or certifying agency with regard to the use of the above values in the design of castings.


b When specified on drawing, conformance to tensile property requirements is determined by testing specimens cut from castings.

c Estimated.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 4.3.2.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of cast AZ91C-T6/AZ91E-T6.**



**Figure 4.3.2.1.6. Typical tensile stress-strain curves for cast AZ91C-T6/AZ91E-T6 at room and elevated temperatures.**



**MIL-HDBK-5H****1 December 1998****4.3.3 AZ92A**

**4.3.3.0 Comments and Properties** — AZ92A is a magnesium-base casting alloy containing aluminum and zinc. It is slightly stronger and less ductile than AZ91C but is much like it in other characteristics. It is available as sand and permanent-mold casting. AZ92A has fair weldability and pressure tightness.

Material specifications for AZ92A are presented in Table 4.3.3.0(a). Room-temperature mechanical and physical properties are shown in Table 4.3.3.0(b). Elevated temperature curves for physical properties are shown in Figure 4.3.3.0.

**Table 4.3.3.0(a). Material Specifications for AZ92A Magnesium Alloy**

Specification	Form
AMS 4434	Sand casting
AMS 4484	Permanent-mold casting
MIL-M-46062	Casting

The temper index for AZ92A is as follows:

<u>Section</u>	<u>Temper</u>
4.3.3.1	T6

**4.3.3.1 AZ92A-T6 Temper** — Elevated temperature curves for various mechanical properties are presented in Figures 4.3.3.1.1(a) through (c), and 4.3.3.1.4. Typical stress-strain and tangent-modulus curves at room temperature and several elevated temperatures are shown in Figures 4.3.3.1.6(a) and (b).

**MIL-HDBK-5H****1 December 1998****Table 4.3.3.0(b). Design Mechanical and Physical Properties of AZ92A Magnesium Alloy Casting**

Specification . . . . .	AMS 4484	AMS 4434	MIL-M-46062			
Form . . . . .	Permanent mold casting	Sand casting	Casting (any method)			
Temper . . . . .	T6	T6	T6			
Location within casting .	Any area		Designated area			Nondesignated area
			Class 1 <sup>b</sup>	Class 2 <sup>b</sup>	Class 3 <sup>b</sup>	
Basis . . . . .	S	S	S	S	S	S
Mechanical Properties <sup>a</sup> :						
$F_{tu}$ , ksi . . . . .	17 <sup>c</sup>	17 <sup>c</sup>	40	34	30	17
$F_{ty}$ , ksi . . . . .	13.5 <sup>c</sup>	13.5 <sup>c</sup>	25	20	18	13
$F_{cy}$ , ksi . . . . .	13.5	13.5 <sup>c</sup>	25	20	18	13
$F_{su}$ , ksi . . . . .	...	...	...	...	...	...
$F_{bru}$ , ksi:						
(e/D = 1.5) . . . . .	...	...	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...	...
$F_{bry}$ , ksi:						
(e/D = 1.5) . . . . .	...	...	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...	...
$e$ , percent . . . . .	...	...	3	1	0.75	0.50
$E$ , 10 <sup>3</sup> ksi . . . . .	6.5					
$E_c$ , 10 <sup>3</sup> ksi . . . . .	6.5					
$G$ , 10 <sup>3</sup> ksi . . . . .	2.4					
$\mu$ . . . . .	0.35					
Physical Properties:						
$\omega$ , lb./in. <sup>3</sup> . . . . .	0.0659					
$C$ , Btu/(lb)(°F) . . . . .	0.25 <sup>d</sup>					
$K$ and $\alpha$ . . . . .	See Figure 4.3.3.0					


a Reference should be made to the specific requirements of the procuring or certifying agency with regard to the use of the above values in the design of castings.

b Class of properties attainable depends on location specified and casting design and should be coordinated with the producer.


c When specified on drawing, conformance to tensile property requirements is determined by testing specimens cut from castings.

d Estimated.


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 4.3.3.0. Effects of temperature on the physical properties of cast AZ92A-T6.**


**MIL-HDBK-5H****1 December 1998**

**Figure 4.3.3.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of cast AZ92A-T6.**




**Figure 4.3.3.1.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of cast AZ92A-T6.**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 4.3.3.1.1(c). Effect of exposure at elevated temperature on the room-temperature tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of cast AZ92A-T6.**



**Figure 4.3.3.1.4. Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of cast AZ92A-T6.**

**MIL-HDBK-5H****1 December 1998**

**Figure 4.3.3.1.6(a). Typical compressive stress-strain and compressive tangent-modulus curves for cast AZ92A-T6 at room temperature.**



**Figure 4.3.3.1.6(b). Typical tensile stress-strain curves for cast AZ92A-T6 at room and elevated temperatures.**

**MIL-HDBK-5H****1 December 1998****4.3.4 EZ33A**

**4.3.4.0 Comments and Properties** — EZ33A is a magnesium-base casting alloy containing rare earths, zinc, and zirconium. It is available as sand castings in the artificially aged (T5) temper. EZ33A has lower strength than the Mg-Al-Zn alloys at room temperature but is less affected by increasing temperature. It is generally used for applications at temperatures of 300 to 500 °F. EZ33A castings are very sound and are sometimes used for pressure tightness. It has good stability in the T5 temper and excellent weldability. It is sometimes used for applications requiring good damping ability.

A material specification for EZ33A is presented in Table 4.3.4.0(a). Room-temperature mechanical and physical properties are shown in Table 4.3.4.0(b). The effect of temperature on physical properties is shown in Figure 4.3.4.0.

**Table 4.3.4.0(a). Material Specification for  
EZ33A Magnesium Alloy**

Specification	Form
AMS 4442	Sand casting

The temper index for EZ33A is as follows:

<u>Section</u>	<u>Temper</u>
4.3.4.1	T5

**4.3.4.1 EZ33A-T5 Temper** — Elevated temperature curves for tensile properties are presented in Figures 4.3.4.1.1(a) through (c). A typical tensile stress-strain curve at room temperature is presented in Figure 4.3.4.1.6.

**MIL-HDBK-5H****1 December 1998****Table 4.3.4.0(b). Design Mechanical and Physical Properties of EZ33A Magnesium Alloy Casting**


Specification .....	AMS 4442
Form .....	Sand casting
Temper .....	T5
Location within casting .....	Any area
Basis .....	S
Mechanical Properties <sup>a</sup> :	
$F_m$ , ksi .....	13 <sup>b</sup>
$F_{ty}$ , ksi .....	11 <sup>b</sup>
$F_{cys}$ , ksi .....	11
$F_{su}$ , ksi .....	...
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$e$ , percent .....	1.5
$E$ , 10 <sup>3</sup> ksi .....	6.5
$E_c$ , 10 <sup>3</sup> ksi .....	6.5
$G$ , 10 <sup>3</sup> ksi .....	2.4
$\mu$ .....	0.35
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.0659
$C$ , Btu/(lb)(°F) .....	0.25
$K$ and $\alpha$ .....	See Figure 4.3.4.0

a Reference should be made to the specific requirements of the procuring or certifying agency with regard to the use of the above values in the design of castings.

b When specified on drawing, conformance to tensile property requirements is determined by testing specimens cut from castings.



**MIL-HDBK-5H**  
**1 December 1998**



**Figure 4.3.4.0. Effect of temperature on the physical properties of cast EZ33A.**

MIL-HDBK-5H  
1 December 1998




Figure 4.3.4.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of cast EZ33A-T5.






Figure 4.3.4.1.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of cast EZ33A-T5.

**MIL-HDBK-5H****1 December 1998**

**Figure 4.3.4.1.1(c). Effect of exposure at elevated temperatures on the room temperature tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of cast EZ33A-T5.**



**Figure 4.3.4.1.6. Typical tensile stress-strain curve for cast EZ33A-T5 at room temperature.**

**MIL-HDBK-5H****1 December 1998****4.3.5 QE22A**

**4.3.5.0 Comments and Properties** — QE22A is a magnesium-base alloy containing silver, rare earths in the form of didymium, and zirconium. It is available as sand and permanent-mold castings. It is used in the solution heat-treated and artificially aged (T6) condition where a high yield strength is needed at temperatures up to 600°F. QE22A has good weldability and fair pressure tightness.

Material specifications for QE22A are presented in Table 4.3.5.0(a). Room-temperature mechanical and physical properties are shown in Table 4.3.5.0(b).

**Table 4.3.5.0(a). Material Specifications for QE22A Magnesium Alloy**

Specification	Form
AMS 4418	Sand casting
MIL-M-46062	Casting

The temper index for QE22A is as follows:

<u>Section</u>	<u>Temper</u>
4.3.5.1	T6

**4.3.5.1 QE22A-T6 Temper** — Elevated temperature curves for various tensile properties and modulus of elasticity are presented in Figures 4.3.5.1.1 and 4.3.5.1.4. Typical tensile stress-strain curves at various temperatures from room temperature through 700°F are shown in Figure 4.3.5.1.6.

**MIL-HDBK-5H****1 December 1998****Table 4.3.5.0(b). Design Mechanical and Physical Properties of QE22A Magnesium Alloy Casting**

Specification . . . . .	AMS 4418	MIL-M-46062			
Form . . . . .	Sand casting	Casting (any method)			
Temper . . . . .	T6				
Location within casting .	Any area	Designated area			Nondesignated area
		Class 1 <sup>b</sup>	Class 2 <sup>b</sup>	Class 3 <sup>b</sup>	
Basis . . . . .	S	S	S	S	S
Mechanical Properties <sup>a</sup> :					
$F_{tu}$ , ksi . . . . .	32 <sup>c</sup>	40	37	33	28
$F_{ty}$ , ksi . . . . .	23 <sup>c</sup>	28	26	23	20
$F_{cy}$ , ksi . . . . .	23	28	26	23	20
$F_{su}$ , ksi . . . . .	...	...	...	...	...
$F_{bru}$ , ksi:					
(e/D = 1.5) . . . . .	...	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...
$F_{bry}$ , ksi:					
(e/D = 1.5) . . . . .	...	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...
$e$ , percent . . . . .	2 <sup>c</sup>	4	2	2	1
$E$ , 10 <sup>3</sup> ksi . . . . .	6.5				
$E_c$ , 10 <sup>3</sup> ksi . . . . .	6.5				
$G$ , 10 <sup>3</sup> ksi . . . . .	2.4				
$\mu$ . . . . .	0.35				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.0653				
$C$ , Btu/(lb)(°F) . . . . .	0.25 <sup>d</sup>				
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .	59				
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . . . .	14 (68°F to 392°F)				

a Reference should be made to the specific requirements of the procuring or certifying agency with regard to the use of the above values in the design of castings.

b Class of properties attainable depends on location specified and casting design and should be coordinated with the producer.

c When specified on drawing, conformance to tensile property requirements is determined by testing specimens cut from castings.

d Estimated.

MIL-HDBK-5H  
1 December 1998




Figure 4.3.5.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of cast QE22A-T6.





Figure 4.3.5.1.4. Effect of temperature on the tensile modulus (E) of cast QE22A-T6.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 4.3.5.1.6. Typical tensile stress-strain curves for cast QE22A-T6 at room and elevated temperatures.**

**MIL-HDBK-5H****1 December 1998****4.3.6 ZE41A**

**4.3.6.0 Comments and Properties** — ZE41A is a magnesium-base casting alloy containing zinc, zirconium, and rare earth elements. It is available as sand or permanent-mold castings in the artificially aged temper (T5). ZE41A has a higher yield strength than the Mg-Al-Zn alloys at room temperature and is more stable at elevated temperatures. It is useful for applications at temperatures up to 320 °F. ZE41A castings possess good weldability and are pressure tight.

A material specification for ZE41A is presented in Table 4.3.6.0(a). Room temperature mechanical and physical properties are shown in Table 4.3.6.0(b). The effect of temperature on thermal conductivity is shown in Figure 4.3.6.0.

**Table 4.3.6.0(a). Material Specification for ZE41A Magnesium Alloy**

Specification	Form
AMS 4439	Sand casting

The temper index for ZE41A is as follows:

<u>Section</u>	<u>Temper</u>
4.3.6.1	T5

**4.3.6.1 T5 Temper** — Elevated temperature curves for tensile yield and ultimate strengths are presented in Figure 4.3.6.1.1. The effect of temperature on the tensile modulus of elasticity is shown in Figure 4.3.6.1.4. Figures 4.3.6.1.6(a) and (b) contain tensile and compressive stress-strain curves as well as a compressive tangent-modulus curve.



**MIL-HDBK-5H****1 December 1998****Table 4.3.6.0(b). Design Mechanical and Physical Properties of ZE41A Magnesium Alloy Casting**

Specification .....	AMS 4439
Form .....	Sand casting
Temper .....	T5
Thickness, in. ....	Any area
Basis .....	S
Mechanical Properties <sup>a</sup> :	
$F_{tu}$ , ksi .....	26 <sup>b</sup>
$F_{ty}$ , ksi .....	17.5 <sup>b</sup>
$F_{cy}$ , ksi .....	15
$F_{su}$ , ksi .....	17
$F_{bru}$ , ksi:	
( $e/D = 1.5$ ) .....	38
( $e/D = 2.0$ ) .....	49
$F_{bry}^c$ , ksi:	
( $e/D = 1.5$ ) .....	31
( $e/D = 2.0$ ) .....	35
$e$ , percent .....	2 <sup>b</sup>
$E$ , $10^3$ ksi .....	6.5
$E_c$ , $10^3$ ksi .....	6.5
$G$ , $10^3$ ksi .....	2.4
$\mu$ .....	0.35
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.0656
$C$ , Btu/(lb)(°F) .....	0.234 (at 68°F)
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	See Figure 4.3.6.0
$\alpha$ , $10^{-6}$ in./in./°F .....	15.5 (68 to 212°F)

a The mechanical properties shown are reliably obtainable when castings are produced under the quality assurance provisions of AMS 4439. These provisions require preproduction approval, documentation of foundry procedures, and specific testing procedures for the acceptance of each production lot of castings. Strict adherence to these requirements is mandatory if these properties are to be reliably assured in each casting.

b Conformance to tensile property requirements is determined by testing specimens cut from casting only when specified on drawing.

c Bearing values are "dry pin" values per Section 1.4.7.1.

MIL-HDBK-5H  
1 December 1998




Figure 4.3.6.0. Effect of temperature on the thermal conductivity (K) of ZE41A-T5 sand casting.

MIL-HDBK-5H  
1 December 1998




Figure 4.3.6.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and tensile yield strength ( $F_{ty}$ ) of ZE41A-T5 sand casting.






Figure 4.3.6.1.4. Effect of temperature on the tensile modulus (E) of ZE41A-T5 sand casting.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 4.3.6.1.6(a). Typical tensile stress-strain curves for ZE41A-T5 sand casting at room and elevated temperatures.**



**Figure 4.3.6.1.6(b). Typical compressive stress-strain and tangent-modulus curves for ZE41A-T5 sand casting at room temperature.**

**MIL-HDBK-5H****1 December 1998****4.4 ELEMENT PROPERTIES**

**4.4.1 BEAMS** — Refer to Chapter 1 and References 1.7.1(a) and (b) for general information on stress analysis of beams.

**4.4.1.1 Simple Beams** — Beams of solid tubular, or similar cross sections can be assumed to fail through exceeding an allowable modulus of rupture in bending ( $F_b$ ). In the absence of specific data, the ratio  $F_b/F_{tu}$  can be assumed to be 1.25 for solid sections.

**4.4.1.1.1 Round Tubes** — For round tubes, the value of  $F_b$  will depend on the  $D/t$  ratio as well as the compressive yield stress.

**4.4.1.1.2 Unconventional Cross Sections** — Sections other than solid or tubular should be tested to determine allowable bending stress.

**4.4.1.2 Built-Up Beams** — Built-up beams will usually fail because of local failure of component parts.

**4.4.1.3 Thin-Web Beams** — The allowable stress for thin-web beams will depend on the nature of the failure and are determined from the allowable stress of the web in tension and of the flanges or stiffeners in compression.

**4.4.2 COLUMNS**

**4.4.2.1 Primary Failure** — The general formula for primary instability is given in Section 1.3.8. Formulas applicable to magnesium-alloy columns are given in Tables 4.4.2.1(a) and (b). See References 4.4.2(a) and (b).

**Table 4.4.2.1(a). Column Formula for Magnesium-Alloy Extruded Open Shapes**

General Formula<sup>a</sup>

$$\frac{P}{A} = \frac{K(F_{cy})^n}{(L'/\rho)^m}$$

(Stress values are in ksi)

Alloy	K	n	m	Max. P/A
AZ31B, AZ61A	2,900	1/4	1.5	$F_{cy}$
ZK60A-T5	3,300	1/4	1.5	$0.96 F_{cy}$

<sup>a</sup> Formula is for members that do not fail by local buckling.  
See Figure 4.4.2.3(a).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 4.4.2.1(b). Column Formula for AZ31B-H24  
Magnesium-Alloy Sheet**

---


$$\frac{P}{A} = 1.05 F_{cy} - \frac{(1.05 F_{cy})^2 (L'/\rho)^2}{4 \pi^2 E}$$

$$\text{MAX } \frac{P}{A} = F_{cy}$$

See Figure 4.4.2.3(b).

---

#### **4.4.2.2 Local Failure**

**4.4.2.3 Column Properties** — Curves of the allowable column stresses for various magnesium alloy columns are given in Figures 4.4.2.3(a) and (b). The allowable stress is plotted against the effective slenderness ratio defined by Equation 3.11.2.3.



## MIL-HDBK-5H

1 December 1998




Figure 4.4.2.3(a). Allowable column stresses for magnesium-alloy columns.




Figure 4.4.2.3(b). Allowable column stresses for AZ31B-H24 magnesium-alloy sheet.

MIL-HDBK-5H  
1 December 1998

#### 4.4.3 TORSION

**4.4.3.1 General** — The general statements relating to aluminum-alloy tubing in 3.11.3 are applicable to magnesium tubing.

**4.4.3.2 Torsion Properties** — An empirical curve of the allowable torsional modulus of rupture for AZ62A-F magnesium-alloy round tubing (specification WW-T-825) is given in Figure 4.4.3.2.




Figure 4.4.3.2. Torsional modulus of rupture for AZ61A-F magnesium-alloy round tubing.



**MIL-HDBK-5H****1 December 1998****REFERENCES**

- 4.1.2.1.1(a) Eastman, E. J., McDonald, J. C., and Moore, A. A., "The Relation of Stress to Strain in Magnesium Alloys", *Journal of the Aeronautical Sciences*, pp 273-280 (July 1945).
- 4.1.2.1.1(b) Moore, A. A., "The Effect of Speed of Testing of Magnesium-Base Alloys", *American Society for Testing and Materials, Proceedings* 48, pp 1133-1138 (1948).
- 4.1.2.1.1(c) Fenn, R. W., Jr., and Gusack, J. C., "Effect of Strain Rate and Temperature on the Strength of Magnesium Alloys", *American Society of Testing and Materials, Proceedings* 58, pp 685-696 (1958).
- 4.1.2.1.1(d) Fenn, R. W., Jr., and Lockwood, L. F., "Low-Temperature, Properties of Welded Magnesium Alloys", *The Welding Journal Research Supplement* (August 1960).
- 4.1.2.1.2(a) Moore, A. A., and McDonald, J. C., "Compression Testing of Magnesium Alloy Sheet", *American Society for Testing and Materials, Bulletin* No. 135, pp 27-30 (August 1945).
- 4.1.2.1.2(b) Fenn, R. W., Jr., "Compression Testing of Sheet Magnesium Utilizing Rapid Heating", *American Society for Testing and Materials, Proceedings* 60, pp 940-956 (1960).
- 4.1.2.1.3(a) Gusack, J. A., and Moore, A. A., "An Autographic Bearing-Strength Test Method, and Typical Test Values on Some Magnesium Alloys at Room and Elevated Temperatures", *American Society for Testing and Materials, Proceedings* 56, pp 834-841 (1956).
- 4.1.2.1.3(b) Stickley, G. W., and Moore, A. A., "Effects of Lubrication and Pin Surface on Bearing Strengths of Aluminum and Magnesium Alloys", *American Society for Testing and Materials, Materials, Research and Standards*, Vol. 2, No. 2, pp 747-751 (September 1962).
- 4.1.2.1.4 Fenn, R. W., Jr., and Clapper, R. B., "Evaluation of Test Variables in the Determination of Shear Strength", *American Society for Testing and Materials, Proceedings* 56, pp 842-858 (1956).
- 4.1.2.1.5(a) Dorn, J. E., and Meriam, J. L., "Properties and Heat Treatment of Magnesium Alloys, Part II, Notch Sensitivity of Magnesium Alloys", *OSRD No. 1819, Report M-104*, pp 68 (September 1943).
- 4.1.2.1.5(b) Dorn, J. E., and others, "Properties and Heat Treatment of Magnesium Alloys, Part V, Section I, The Sensitivity of Magnesium Alloy Sheet to Drilled, Reamed, and Punched Holes. Part V, Section II, The Notch Sensitivity of Magnesium Alloy Extrusions and the Influence of Various Factors", *OSRD No. 3043 (NRC Research Project NRC-21), Final Report M-177*, pp 202 (December 1943).
- 4.1.2.1.5(c) Doan, J. P., and McDonald, J. C., "The Notch Sensitivity in Static and Impact Loading of Some Magnesium-Base and Aluminum-Base Alloys", *American Society for Testing and Materials, Proceedings* 46, pp 1097-1118 (1946).
- 4.1.2.1.5(d) Moore, A. A., and McDonald, J. C., "Tensile and Creep Strengths of Some Magnesium-Base Alloys at Elevated Temperatures", *American Society for Testing and Materials, Proceedings* 46, pp 970-989 (1946).
- 4.1.2.1.5(e) McDonald, J. C., "Tensile, Creep and Fatigue Properties of Some Magnesium-Base Alloys", *American Society for Testing and Materials, Proceedings* 48, pp 737-754 (1948).

**MIL-HDBK-5H****1 December 1998**

- 4.1.2.1.5(f) Wyman, L. L., "High-Temperature Properties of Light Alloys (NA-137). Part II, Magnesium", U.S. Office of Scientific Research and Development Report No. 4150, M-292, pp 101 (1944).
- 4.1.2.1.5(g) Craighead, C. M., Grube, K. P., Eastwood, L. W., and Lorig, C. H., "The Effects of Temperature on the Mechanical Properties of Magnesium Alloy", Rand Corporation Report R-146, pp 210 (October 1949).
- 4.1.2.1.5(h) Wyman, L. L., "High-Temperature Properties of Light Alloys (NA-137). Part II, Magnesium", U.S. Office of Scientific Research and Development Report No. 4150, M-292, pp 101 (1944).
- 4.1.2.1.6 Clapper, R. W., "Isochronous Stress-Strain Curves for Some Magnesium Alloys Showing the Effects of Varying Exposure Time on Their Creep Resistance", American Society for Testing and Materials, Proceedings 58, pp 812-825 (1958).
- 4.1.2.1.7(a) Found, G. H., "The Notch Sensitivity in Fatigue Loading of Some Magnesium-Base and Aluminum-Base Alloys", American Society for Testing and Materials, Proceedings 46, pp 715-740 (1946).
- 4.1.2.1.7(b) Schuette, E. H., "Fatigue Properties of Magnesium Alloy Forgings", Wright-Patterson Air Force Base Technical Report No. 60-854, pp 112 (December 1960) (MCIC 43549).
- 4.2.3.2.8 Blatherwick, A. A., and Lazan, B. J., "Fatigue Properties of Extruded Magnesium Alloy ZK60A Under Various Combinations of Alternating and Mean Axial Stresses", WADC Tech Report 53-181, pp 27 (August 1953) (MCIC 108173).
- 4.4.2(a) Schuette, E. H., "Hyperbolic Column Formulas for Magnesium Alloy Extrusions", Journal of the Aeronautical Sciences, 15, pp 523-529 (1948).
- 4.4.2(b) Schuette, E. H., "Column Curves for Magnesium Alloy Sheet", Journal of the Aeronautical Sciences, 16, pp 301-305 (1949).

**CHAPTER 5****TITANIUM****5.1 GENERAL**

This chapter contains the engineering properties and related characteristics of titanium and titanium alloys used in aircraft and missile structural applications.

General comments on engineering properties and the considerations relating to alloy selection are presented in Section 5.1. Mechanical- and physical-property data and characteristics pertinent to specific alloy groups or individual alloys are reported in Sections 5.2 through 5.5.

Titanium is a relatively lightweight, corrosion-resistant structural material that can be strengthened greatly through alloying and, in some of its alloys, by heat treatment. Among its advantages for specific applications are: good strength-to-weight ratio, low density, low coefficient of thermal expansion, good corrosion resistance, good oxidation resistance at intermediate temperatures, good toughness, and low heat-treating temperature during hardening, and others.

**5.1.1 TITANIUM INDEX** — The coverage of titanium and its alloys in this chapter has been divided into four sections for systematic presentation. The system takes into account unalloyed titanium and three groups of alloys based on metallurgical differences which in turn result in differences in fabrication and property characteristics. The sections and the individual alloys covered under each are shown in Table 5.1.

**5.1.2 MATERIAL PROPERTIES** — The material properties of titanium and its alloys are determined mainly by their alloy content and heat treatment, both of which are influential in determining the allotropic forms in which this material will be bound. Under equilibrium conditions, pure titanium has an “alpha” structure up to 1620°F, above which it transforms to a “beta” structure. The inherent properties of these two structures are quite different. Through alloying and heat treatment, one or the other or a combination of these two structures can be made to exist at service temperatures, and the properties of the material vary accordingly. References 5.1.2(a) and (b) provide general discussion of titanium microstructures and associated metallography.

**Table 5.1. Titanium Alloys Index**

Section	Alloy Designation
<b>5.2</b>	<b>Unalloyed Titanium</b>
5.2.1	Commercially Pure Titanium
<b>5.3</b>	<b>Alpha and Near-Alpha Titanium Alloys</b>
5.3.1	Ti-5Al-2.5Sn (Alpha)
5.3.2	Ti-8Al-1Mo-1V (Near-Alpha)
5.3.3	Ti-6Al-2Sn-4Zr-2Mo (Near-Alpha)
<b>5.4</b>	<b>Alpha-Beta Titanium Alloys</b>
5.4.1	Ti-6Al-4V
5.4.2	Ti-6Al-6V-2Sn
<b>5.5</b>	<b>Beta, Near-Beta, and Metastable Titanium Alloys</b>
5.5.1	Ti-13V-11Cr-3Al
5.5.2	Ti-15V-3Cr-3Sn-3Al
5.5.3	Ti-10V-2Fe-3Al

**MIL-HDBK-5H****1 December 1998**

Titanium and titanium alloys of the alpha and alpha-beta type exhibit crystallographic textures in sheet form in which certain crystallographic planes or directions are closely aligned with the direction of prior working. The presence of textures in these materials lead to anisotropy with respect to many mechanical and physical properties. Poisson's ratio and Young's modulus are among those properties strongly affected by texture. Wide variations experienced in these properties both within and between sheets of titanium alloys have been qualitatively related to variations of texture. In general, the degree of texturing, and hence the variation of Young's modulus and Poisson's ratio, that is developed for alpha-beta alloys tends to be less than that developed in all alpha titanium alloys. Rolling temperature has a pronounced effect on the texturing of titanium alloys which may not in general be affected by subsequent thermal treatments. The degree of applicability of the effect of textural variations discussed above on the mechanical properties of products other than sheet is unknown at present. The values of Young's modulus and Poisson's ratio listed in this document represent the usual values obtained on products resulting from standard mill practices. References 5.1.2(c) and (d) provide further information on texturing in titanium alloys.

**5.1.2.1 Mechanical Properties —**

**5.1.2.1.1 Fracture Toughness** — The fracture toughness of titanium alloys is greatly influenced by such factors as chemistry variations, heat treatment, microstructure, and product thickness, as well as yield strength. For fracture critical applications, these factors should be closely controlled. Typical values of plane-strain fracture toughness for titanium alloys are presented in Table 5.1.2.1.1. Minimum, average, and maximum values, as well as coefficient of variation, are presented for various products for which valid data are available, but these values do not have the statistical reliability of the room-temperature mechanical properties.

**5.1.3 MANUFACTURING CONSIDERATIONS** — Comments relating to formability, weldability, and final heat treatment are presented under individual alloys. These comments are necessarily brief and are intended only to aid the designer in the selection of an alloy for a specific application. In practice, departures from recommended practices are very common and are based largely on in-plant experience. Springback is nearly always a factor in hot or cold forming.

Final heat treatments that are indicated as "specified" heat treatments do not necessarily coincide with the producers' recommended heat treatments. Rather, these treatments, along with the specified room-temperature minimum tensile properties, are contained in the heat treating-capability requirements of applicable specifications, for example, MIL-H-81200. Departures from the specified aging cycles are often necessary to account for aging that may take place during hot working or hot sizing or to obtain more desirable mechanical properties, for example, improved fracture toughness. More detailed recommendations for specific applications are generally available from the material producers.

**5.1.4 ENVIRONMENTAL CONSIDERATIONS** — Comments relating to temperature limitations in the application of titanium and titanium alloys are presented under the individual alloys.

Below about 300°F, as well as above about 700°F, creep deformation of titanium alloys can be expected at stresses below the yield strength. Available data indicate that room-temperature creep of unalloyed titanium may be significant (exceed 0.2 percent creep-strain in 1,000 hours) at stresses that exceed approximately 50 percent  $F_{ty}$ , room-temperature creep of Ti-5Al-1.5Sn ELI may be significant at stresses above approximately 60 percent  $F_{ty}$ , and room-temperature creep of the standard grades of titanium alloys may be significant at stresses above approximately 75 percent  $F_{ty}$ . References 5.1.4(a) through (c) provide some limited data regarding room-temperature creep of titanium alloys.

The use of titanium and its alloys in contact with either liquid oxygen or gaseous oxygen at cryogenic temperatures should be avoided, since either the presentation of a fresh surface (such as produced by tensile rupture) or impact may initiate a violent reaction [Reference 5.1.4(d)]. Impact of the surface in contact with

**MIL-HDBK-5H****1 December 1998**

liquid oxygen will result in a reaction at energy levels as low as 10 ft-lb. In gaseous oxygen, a partial pressure of about 50 psi is sufficient to ignite a fresh titanium surface over the temperature range from -250°F to room temperature or higher.

Titanium is susceptible to stress-corrosion cracking in certain anhydrous chemicals including methyl alcohol and nitrogen tetroxide. Traces of water tend to inhibit the reaction in either environment. However, in  $N_2O_4$ , NO is preferred and inhibited  $N_2O_4$  contains 0.4 to 0.8 percent NO. Red fuming nitric acid with less than 1.5 percent water and 10 to 20 percent  $NO_2$  can crack the metal and result in a pyrophoric reaction.

Titanium alloys are also susceptible to stress corrosion by dry sodium chloride at elevated temperatures. This problem has been observed largely in laboratory tests at 450 to 500°F and higher and occasionally in fabrication shops. However, there have been no reported failures of titanium components in service by hot salt stress corrosion. Cleaning with a nonchlorinated solvent (to remove salt deposits, including fingerprints) of parts used above 450°F is recommended.

In laboratory tests, with a fatigue crack present in the specimen, certain titanium alloys show an increased crack propagation rate in the presence of water or salt water as compared with the rate in air. These alloys also may show reduced sustained load-carrying ability in aqueous environments in the presence of fatigue cracks. Crack growth rates in salt water are a function of sheet or section thickness. These alloys are not susceptible in the form of thin-gauge sheet, but become susceptible as thickness increases. The thickness at which susceptibility occurs varies over a visual range with the alloy and processing. Alloys of titanium found susceptible to this effect include some from alpha, alpha-beta, and beta-type microstructures. In some cases, special processing techniques and heat treatments have been developed that minimize this effect. References 5.1.4(e) through (g) present detailed summaries of corrosion and stress corrosion of titanium alloys.

Under certain conditions, titanium, when in contact with cadmium, silver, mercury, or certain of their compounds, may become embrittled. Refer to MIL-S-5002 and MIL-STD-1568 for restrictions concerning applications with titanium in contact with these metals or their compounds.

**Table 5.1.2.1.1. Values of Room Temperature Plain-Strain Fracture Toughness of Titanium Alloys<sup>a</sup>**

									K <sub>IC</sub> , ksi √in.			
Alloy	Heat Treat Condition	Product Form	Orientation <sup>b</sup>	Yield Strength Range, ksi	Product Thickness Range, inches	Number of Sources	Sample Size	Specimen Thickness Range, inches	Max.	Avg.	Min.	Coefficient of Variation
Ti-6Al-4V	Mill Annealed	Forged Bar	L-T	121-143	<3.5	2	43	0.6-1.1	77	60	38	10.5
Ti-6Al-4V	Mill Annealed	Forged Bar	T-L	124-145	<3.5	2	64	0.5-1.3	81	57	33	11.7

<sup>a</sup> These values are for information only.

<sup>b</sup> Refer to Figure 1.4.12.3 for definition of symbols.

**MIL-HDBK-5H****1 December 1998**

## **5.2 UNALLOYED TITANIUM**

Several grades of unalloyed titanium are offered and are classified on the basis of manufacturing method, degree of purity, or strength, there being a close relationship among these. The unalloyed titanium grades most commonly used are produced by the Kroll process, are intermediate in purity, and are commonly referred to as being of commercial purity.

### **5.2.1 COMMERCIALLY PURE TITANIUM**

**5.2.1.0 Comments and Properties** — Unalloyed titanium is available in all familiar product forms and is noted for its excellent formability. Unalloyed titanium is readily welded or brazed. It has been used primarily where strength is not the main requirement.

*Manufacturing Considerations* — Unalloyed titanium is supplied in the annealed condition permitting extensive forming at room temperature. Severe forming operations also can be accomplished at elevated temperatures (300 to 900°F). Property degradation can be experienced after severe forming if as-received material properties are not restored by re-annealing.

Commercially pure titanium can be welded readily by the several methods employed for titanium joining. Atmospheric shielding is preferable although spot or seam welding may be accomplished without shielding. Brazing requires protection from the atmosphere which may be obtained by fluxing as well as by inert gas or vacuum shielding.

*Environmental Considerations* — Titanium has an unusually high affinity for oxygen, nitrogen, and hydrogen at temperatures above 1050°F. This results in embrittlement of the material, thus usage should be limited to temperatures below that indicated. Additional chemical reactivity between titanium and selected environments such as methyl alcohol, chloride salt solutions, hydrogen, and liquid metal, can take place at lower temperatures, as discussed in Section 5.1.4 and its references.

Under certain conditions, titanium, when in contact with cadmium, silver, mercury, or certain of their compounds, may become embrittled. Refer to MIL-S-5002 and MIL-STD-1568 for restrictions concerning applications with titanium in contact with these metals or their compounds.

*Heat Treatment* — Commercially pure titanium is fully annealed by heating to 1000 to 1300°F for 10 to 30 minutes. It is stress relieved by heating to 900 to 1000°F for 30 minutes. Commercially pure titanium cannot be hardened by heat treatment.

*Specifications and Properties* — Some material specifications for commercially pure titanium are presented in Table 5.2.1.0(a). Room-temperature mechanical properties for commercially pure titanium are shown in Tables 5.1.2.0(b) and (c). The effect of temperature on physical properties is shown in Figure 5.2.1.0.

**5.2.1.1 Annealed Condition** — Elevated-temperature data for annealed commercially pure titanium are presented in Figures 5.2.1.1.1(a) through 5.2.1.1.3(b). Typical full-range stress-strain curves for the 40 and 70 ksi yield strength commercially pure titanium are shown in Figures 5.2.1.1.6(a) and (b).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 5.2.1.0(a). Material Specifications for  
Commercially Pure Titanium**

Specification	Form
AMS 4900	Sheet, strip, and plate
AMS 4901	Sheet, strip, and plate
AMS 4902	Sheet, strip, and plate
MIL-T-9046	Sheet, strip, and plate
MIL-T-9047	Bar
AMS 4921	Bar
MIL-T-81556	Extruded bars and shapes



**MIL-HDBK-5H****1 December 1998****Table 5.2.1.0(b). Design Mechanical and Physical Properties of Commercially Pure Titanium**

Specification . . . . .	MIL-T-9046	AMS 4902 and MIL-T- 9046	AMS 4900 and MIL-T- 9046	AMS 4901 and MIL-T- 9046	AMS 4921 and MIL-T- 9047	MIL-T- 9047
Designation . . . . .	CP-4	CP-3	CP-2	CP-1	CP-70	
Form . . . . .	Sheet, strip, and plate				Bar	
Condition . . . . .	Annealed				Annealed	
Thickness or diameter, in. . . . .	≤1.000				≤2.999 <sup>a</sup>	3.000- 4.000 <sup>a</sup>
Basis . . . . .	S	S	S	S	S	S
Mechanical Properties:						
<i>F<sub>tu</sub></i> , ksi:						
L . . . . .	35	50	65	80	80	80
LT . . . . .	35	50	65	80	80 <sup>b</sup>	80
ST . . . . .	...	...	...	...	...	80
<i>F<sub>ty</sub></i> , ksi:						
L . . . . .	25	40	55	70	70	70
LT . . . . .	25	40	55	70	70 <sup>b</sup>	70
ST . . . . .	...	...	...	...	...	70
<i>F<sub>cy</sub></i> , ksi:						
L . . . . .	...	...	...	70	...	...
LT . . . . .	...	...	...	70	...	...
<i>F<sub>su</sub></i> , ksi . . . . .	...	...	...	42	...	...
<i>F<sub>bru</sub></i> , ksi:						
(e/D = 1.5) . . . . .	...	...	...	120	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...	...
<i>F<sub>bry</sub></i> , ksi:						
(e/D = 1.5) . . . . .	...	...	...	101	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...	...
<i>e</i> , percent:						
L . . . . .	24 <sup>c</sup>	20 <sup>c</sup>	18 <sup>c</sup>	15 <sup>c</sup>	15	15
LT . . . . .	24 <sup>c</sup>	20 <sup>c</sup>	18 <sup>c</sup>	15 <sup>c</sup>	15 <sup>b</sup>	15
ST . . . . .	...	...	...	...	...	15
<i>RA</i> , percent:						
L . . . . .	...	...	...	...	30	30
LT . . . . .	...	...	...	...	30 <sup>b</sup>	30
ST . . . . .	...	...	...	...	...	30
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	15.5					
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	16.0					
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	6.5					
<i>μ</i> . . . . .	...					
Physical Properties:						
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.163					
<i>C</i> , <i>K</i> , and <i>α</i> . . . . .	See Figure 5.2.1.0					

a Maximum of 16-square-inch cross-sectional area.

b Long transverse properties apply to rectangular bar only for thickness >0.500 inches and widths >3.000 inches.  
For AMS 4921, (e) (LT) = 12% and RA (LT) = 25%.

c Thickness of 0.025 inch and above.

**MIL-HDBK-5H****1 December 1998****Table 5.2.1.0(c). Design Mechanical and Physical Properties of Commercially Pure Titanium Extruded Bars and Shapes**

Specification . . . . .	MIL-T-81556			
	Comp. CP-4	Comp. CP-3	Comp. CP-2	Comp. CP-1
Form . . . . .	Extruded bars and shapes			
Condition . . . . .	Annealed			
Thickness or diameter, in. . .	0.188-3.000			
Basis . . . . .	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L . . . . .	40	50	65	80
LT . . . . .	...	...	...	...
$F_{ty}$ , ksi:				
L . . . . .	30	40	55	70
LT . . . . .	...	...	...	...
$F_{cy}$ , ksi:				
L . . . . .	...	...	...	...
LT . . . . .	...	...	...	...
$F_{su}$ , ksi . . . . .	...	...	...	...
$F_{bru}$ , ksi:				
(e/D = 1.5) . . . . .	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...
$F_{bry}$ , ksi:				
(e/D = 1.5) . . . . .	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...
$e$ , percent:				
L . . . . .	a	a	a	a
$E$ , $10^3$ ksi . . . . .	15.5			
$E_c$ , $10^3$ ksi . . . . .	16.0			
$G$ , $10^3$ ksi . . . . .	6.5			
$\mu$ . . . . .	...			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.163			
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 5.2.1.0			

a Elongation in percent as follows:

Thickness, inches	Comp. CP-4	Comp. CP-3	Comp. CP-2	Comp. CP-1
0.188-1.000	25	20	18	15
1.001-2.000	20	18	15	12
2.001-3.000	18	15	12	10

MIL-HDBK-5H

1 December 1998




Figure 5.2.1.0. Effect of temperature on the physical properties of commercially pure titanium.

MIL-HDBK-5H  
1 December 1998




Figure 5.2.1.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of annealed commercially pure titanium.




Figure 5.2.1.1.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of annealed commercially pure titanium.

MIL-HDBK-5H  
1 December 1998




Figure 5.2.1.1.2(a). Effect of temperature on the compressive yield strength ( $F_{cy}$ ) of annealed commercially pure titanium.




Figure 5.2.1.1.2(b). Effect of temperature on the shear ultimate strength ( $F_{su}$ ) of annealed commercially pure titanium.



MIL-HDBK-5H

1 December 1998




Figure 5.2.1.1.3(a). Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) of annealed commercially pure titanium.






Figure 5.2.1.1.3(b). Effect of temperature on the bearing yield strength ( $F_{bry}$ ) of annealed commercially pure titanium.



**Figure 5.2.1.1.6(a). Typical full-range tensile stress-strain curve for commercially pure titanium sheet (40 ksi yield at room temperature).**



**Figure 5.2.1.1.6(b). Typical full-range tensile stress-strain curve for commercially pure titanium sheet (70 ksi yield at room temperature).**



**MIL-HDBK-5H****1 December 1998****5.3 ALPHA AND NEAR-ALPHA TITANIUM ALLOYS**

The alpha titanium alloys contain essentially a single phase at room temperature, similar to that of unalloyed titanium. Alloys identified as near-alpha titanium have principally an all-alpha structure but contain small quantities of a beta phase because the composition contains some beta stabilizing elements. In both alloy types, alpha phase is stabilized by aluminum, tin, and zirconium. These elements, especially aluminum, contribute greatly to strength. The beta stabilizing additions (e.g., molybdenum and vanadium) improve fabricability and metallurgical stability of highly alpha-alloyed materials.

All alpha alloys have excellent weldability, toughness at low temperatures, and long-term elevated-temperature strength. They are well suited to cryogenic applications and to uses requiring good elevated-temperature creep strength. The characteristics of near-alpha alloys are predictably between those of all alpha and alpha-beta alloys in regard to fabricability, weldability, and elevated-temperature strength. The hot workability of both alpha and near-alpha alloys is inferior to that of the alpha-beta or beta alloys and the cold workability is very limited at the high-strength level of these grades. However, considerable forming is possible if correct forming temperatures and procedures are used.

**5.3.1 Ti-5Al-2.5Sn**

**5.3.1.0 Comments and Properties** — Ti-5Al-2.5Sn is an all-alpha alloy available in many product forms and at two purity levels. The high purity grade of this composition is used principally for cryogenic applications and may be characterized as having lower strength but higher ductility and toughness than the standard grade. The normal purity grade also may be used at low temperatures but it is primarily suitable for room to elevated temperature applications (up to 900°F or to 1100°F for short times) where weldability is an important consideration.

*Manufacturing Considerations* — Ti-5Al-2.5Sn is not so readily formed into complex shapes as other alloys with similar room-temperature properties, but far surpasses them in weldability. Except for some forging operations, fabrication of Ti-5Al-2.5Sn is conducted at temperatures where the structure remains all alpha. Severe forming operations may be accomplished at temperatures up to 1200°F. Moderately severe forming can be done at 300 to 600°F and simple forming may be done at room temperature. Most forming and welding operations are followed by an annealing treatment to relieve residual stresses imposed by the prior operation.

Ti-5Al-2.5Sn can be welded readily by inert-gas or vacuum-shielded arc methods or by spot or seam welding without atmospheric shielding. Brazing requires protection from the atmosphere; however, this is accomplished by fluxing as well as by inert gas or vacuum shielding.

*Environmental Considerations* — Ti-5Al-2.5Sn is metallurgically stable at moderate elevated temperatures. The material is susceptible to hot-salt stress corrosion as well as aqueous chloride solution stress corrosion. Care should be exercised in applications involving such environments. The alloy has good oxidation resistance up to 1050°F. Standard grade material has been used at moderately low cryogenic temperatures; however, the ELI grade has higher toughness and has been used in cryogenic applications down to -423°F. Under certain conditions, titanium, when in contact with cadmium, silver, mercury, or certain of their compounds, may become embrittled. Refer to MIL-S-5002 and MIL-STD-1568 for restrictions concerning applications with titanium in contact with these metals or their compounds.

*Heat Treatment* — This alloy is annealed by heating 1400°F for 60 minutes and 1600°F for 10 minutes and cooling in air. Stress relieving requires 1 or 2 hours at 1000 to 1200°F. Ti-5Al-2.5Sn cannot be hardened by heat treatment.

**MIL-HDBK-5H****1 December 1998**

*Specifications and Properties* — Some material specifications for Ti-5Al-2.5Sn are shown in Table 5.3.1.0(a). Room-temperature mechanical properties for Ti-5Al-2.5Sn are shown in Tables 5.3.1.0(b) through (d). The effect of temperature on physical properties is shown in Figure 5.3.1.0.

**Table 5.3.1.0(a). Material Specifications for Ti-5Al-2.5Sn**

Specification	Form
MIL-T-9046	Sheet, strip, and plate
AMS 4926	Bar
MIL-T-9047	Bar
MIL-T-81556	Extruded bar and shapes
AMS 4910	Sheet, strip, and plate
AMS 4966	Forging

**5.3.1.1 Annealed Condition** — Elevated temperature curves for annealed Ti-5Al-2.5Sn are shown in Figures 5.3.1.1.1 through 5.3.1.1.5. Tensile properties cover the range -423°F to 1000°F; whereas other properties are for the range room temperature to 1000°F. Fatigue-crack-propagation data for sheet are shown in Figures 5.3.1.1.9(a) through (c).

**MIL-HDBK-5H****1 December 1998****Table 5.3.1.0(b). Design Mechanical and Physical Properties of Ti-5Al-2.5Sn Sheet, Strip, and Plate**

Specification . . . . .	AMS 4910 and MIL-T-9046, Comp. A-1								
Form . . . . .	Strip	Sheet				Plate			
Condition . . . . .	Annealed								
Thickness, in. . . . .	<0.187	0.015- 0.079		0.080- 0.187		0.188- 0.250		0.251- 1.500	1.501- 4.000
Basis . . . . .	S	A	B	A	B	A	B	S	S
Mechanical Properties:									
$F_{tu}$ , ksi:									
L . . . . .	120	120 <sup>b</sup>	128	120 <sup>b</sup>	131	120 <sup>b</sup>	135	120	115
LT . . . . .	120	120 <sup>b</sup>	129	120 <sup>b</sup>	132	120 <sup>b</sup>	137	120	115
$F_{ty}$ , ksi:									
L . . . . .	113	110	115	113	118	113 <sup>b</sup>	123	113	110
LT . . . . .	113	113	118	113 <sup>b</sup>	121	113 <sup>b</sup>	125	113	110
$F_{cy}$ , ksi:									
L . . . . .	115	115	120	118	123	118	128	118	...
LT . . . . .	118	118	123	118	126	118	130	118	...
$F_{su}$ , ksi . . . . .	75	75	80	75	82	75	85	75	...
$F_{bru}$ , ksi:									
(e/D = 1.5) . . .	167	167	179	167	183	167	190	167	...
(e/D = 2.0) . . .	250	250	268	250	275	250	285	250	...
$F_{bry}$ , ksi:									
(e/D = 1.5) . . .	133	133	139	133	142	133	147	133	...
(e/D = 2.0) . . .	190	190	198	190	203	190	210	190	...
$e$ , percent (S-basis):									
L . . . . .	10	10 <sup>a</sup>	...	10	...	10	...	10	10
LT . . . . .	10	10 <sup>a</sup>	...	10	...	10	...	10	10
$E$ , 10 <sup>3</sup> ksi . . . . .	15.5								
$E_c$ , 10 <sup>3</sup> ksi . . . . .	15.5								
$G$ , 10 <sup>3</sup> ksi . . . . .	...								
$\mu$ . . . . .	...								
Physical Properties:									
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.162								
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 5.3.1.0								

a Thickness 0.025 inch and above.

b S-basis. The rounded  $T_{99}$  values are higher than specification values as follows:

	<u>0.015-0.079</u>	<u>0.080-0.187</u>	<u>0.188-0.250</u>
$F_{tu}$			
L.....	123	126	130
LT.....	123	126	131
$F_{ty}$			
L.....	....	...	118
LT.....	....	115	120

**MIL-HDBK-5H****1 December 1998****Table 5.3.1.0(c). Design Mechanical and Physical Properties of Ti-5Al-2.5Sn Bar and Forging**

Specification .....	AMS 4926 <sup>e</sup> and MIL-T-9047			AMS 4966
Form .....	Bar			Forging
Condition .....	Annealed			Annealed
Thickness or diameter, in. .	≤2.999 <sup>a</sup>		3.000-4.000 <sup>a</sup>	...
Basis .....	A	B	S	
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	115 <sup>b</sup>	126	115	115
LT .....	115 <sup>c</sup>	...	115	115 <sup>d</sup>
ST .....	...	...	115	115 <sup>d</sup>
$F_{ty}$ , ksi:				
L .....	110 <sup>b</sup>	120	110	110
LT .....	110 <sup>c</sup>	...	110	110 <sup>d</sup>
ST .....	...	...	110	110 <sup>d</sup>
$F_{cy}$ , ksi:				
L .....	...	...	...	...
LT .....	...	...	...	...
$F_{su}$ , ksi	...	...	...	...
$F_{bru}$ , ksi:				
(e/D = 1.5) .....	...	...	...	...
(e/D = 2.0) .....	...	...	...	...
$F_{bry}$ , ksi:				
(e/D = 1.5) .....	...	...	...	...
(e/D = 2.0) .....	...	...	...	...
$e$ , percent (S-basis):				
L .....	10	...	10	10
LT .....	10 <sup>c</sup>	...	10	10 <sup>d</sup>
ST .....	...	...	8	10 <sup>d</sup>
$RA$ , percent (S-basis):				
L .....	25	...	25	25
LT .....	25 <sup>c</sup>	...	25	25 <sup>d</sup>
ST .....	...	...	20	25 <sup>d</sup>
$E$ , 10 <sup>3</sup> ksi .....	15.5			
$E_c$ , 10 <sup>3</sup> ksi .....	15.5			
$G$ , 10 <sup>3</sup> ksi .....	...			
$\mu$ .....	...			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.162			
$C$ , $K$ , and $\alpha$ .....	See Figure 5.3.1.0			

a Maximum of 16-square-inch cross-sectional area.

b The rounded  $T_{99}$  values are higher than S values as follows:  $F_{tu} = 117$  ksi,  $F_{ty} = 113$  ksi.

c S-basis. Applicable providing LT dimension is &gt;3.000 inches.

d Applicable, providing LT or ST dimension is ≥ 2.500 inches.


e For AMS 4926, LT and ST values for  $e$  and  $RA$  may be different than those shown.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 5.3.1.0(d). Design Mechanical and Physical Properties of Ti-5Al-2.5Sn Extrusion**

Specification .....	MIL-T-81556, Comp. A-1			
Form .....	Extruded bars and shapes			
Condition .....	Annealed			
Thickness or diameter, in. . .	0.188- 1.000	1.001- 2.000	2.001- 3.000	3.001- 4.000
Basis .....	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	120	115	115	115
LT .....	...	...	...	...
$F_{ty}$ , ksi:				
L .....	115	110	110	110
LT .....	...	...	...	...
$F_{cy}$ , ksi:				
L .....	...	...	...	...
LT .....	...	...	...	...
$F_{su}$ , ksi .....	...	...	...	...
$F_{bru}$ , ksi:				
(e/D = 1.5) .....	...	...	...	...
(e/D = 2.0) .....	...	...	...	...
$F_{bry}$ , ksi:				
(e/D = 1.5) .....				
(e/D = 2.0) .....				
$e$ , percent:				
L .....	10	10	8	6
LT .....	...	...	...	...
$E$ , $10^3$ ksi .....	15.5			
$E_c$ , $10^3$ ksi .....	15.5			
$G$ , $10^3$ ksi .....	...			
$\mu$ .....	...			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.162			
$C$ , $K$ , and $\alpha$ .....	See Figure 5.3.1.0			

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.3.1.0. Effect of temperature on the physical properties of Ti-5Al-2.5Sn alloy.**

## MIL-HDBK-5H

1 December 1998




Figure 5.3.1.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of annealed Ti-5Al-2.5Sn alloy sheet.



MIL-HDBK-5H  
1 December 1998




Figure 5.3.1.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of annealed Ti-5Al-2.5Sn alloy sheet.




Figure 5.3.1.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of annealed Ti-5Al-2.5Sn alloy sheet.



MIL-HDBK-5H

1 December 1998




Figure 5.3.1.1.4. Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of annealed Ti-5Al-2.5Sn alloy sheet.





Figure 5.3.1.1.5. Effect of temperature on the elongation ( $e$ ) of annealed Ti-5Al-2.5Sn alloy sheet.

## MIL-HDBK-5H

1 December 1998




**Figure 5.3.1.1.9(a). Fatigue-crack-propagation data for 0.084-inch-thick Ti-5Al-2.5Sn titanium alloy mill-annealed sheet. [Reference 5.3.1.1.9].**

Specimen Thickness: 0.08 inch  
 Specimen Width: 2.76 inches  
 Specimen Type: M(T)

Environment: Lab air  
 Temperature: RT  
 Orientation: L-T and T-L

## MIL-HDBK-5H

1 December 1998




**Figure 5.3.1.1.9(b).** Fatigue-crack-propagation data for 0.084-inch-thick Ti-5Al-2.5Sn titanium alloy mill-annealed sheet. [Reference 5.3.1.1.9].

Specimen Thickness: 0.08 inch  
 Specimen Width: 2.76 inches  
 Specimen Type: M(T)

Environment: Distilled water  
 Temperature: RT  
 Orientation: L-T and T-L

## MIL-HDBK-5H

1 December 1998



**Figure 5.3.1.1.9(c). Fatigue-crack-propagation data for 0.084-inch-thick Ti-5Al-2.5Sn titanium alloy mill-annealed sheet. [Reference 5.3.1.1.9].**

Specimen Thickness: 0.08 inch  
 Specimen Width: 2.76 inches  
 Specimen Type: M(T)

Environment: 3.5% NaCl  
 Temperature: RT  
 Orientation: L-T and T-L

**MIL-HDBK-5H****1 December 1998****5.3.2 Ti-8Al-1Mo-1V**

**5.3.2.0 Comments and Properties** — Ti-8Al-1Mo-1V alloy is a near-alpha composition developed for improved creep resistance and thermal stability up to about 850°F. The alloy is available as billet, bar, plate, sheet, strip, extrusions, and forgings.

*Manufacturing Considerations* — Room temperature forming of Ti-8Al-1Mo-1V sheet is somewhat more difficult than in Ti-6Al-4V, and for severe operations hot forming is required. Ti-8Al-1Mo-1V can be fusion welded readily with inert-gas protection or spot welding without atmospheric protection. Weld strengths are comparable to those of the parent metal although ductility is somewhat lower in the weldment.

*Environmental Considerations* — Ti-8Al-1Mo-1V exhibits good oxidation resistance and thermal stability up to 850°F. A decrease in tensile elongation has been reported for single-annealed sheet following 150 hours stressed exposure at 1000°F. Extended exposure to temperatures exceeding 600°F adversely affects room-temperature spot-weld tension strength. This alloy is not recommended for structural applications at liquid-hydrogen temperatures (-423°F). The Ti-8Al-1Mo-1V alloy also is susceptible to chloride stress-corrosion attack in either elevated-temperature (hot-salt stress-corrosion) or ambient-temperature (aqueous stress-corrosion) chloride environments. Thus, care should be exercised in applying the material in chloride containing environments. Under certain conditions, titanium, when in contact with cadmium, silver, mercury, or certain of their compounds, may become embrittled. Refer to MIL-S-5002 and MIL-STD-1568 for restrictions concerning applications with titanium in contact with these metals or their compounds.

*Heat Treatment* — Three treatments are used with Ti-8Al-1Mo-1V. These are:

Single Anneal: 1450°F for 8 hours, furnace cool.

Duplex Anneal: 1450°F for 8 hours, furnace cool, followed by 1450°F for 15 to 20 minutes, air cool.

Solution Treated and Stabilized: 1825°F for 1 hour, air cool, 1075°F for 8 hours, air cool.

As a general guide, the single anneal is used to obtain highest room-temperature mechanical properties and the duplex anneal to obtain highest fracture toughness. Both the single anneal and the duplex anneal are compatible with hot-forming operations. The solution treated and stabilized condition is used for forgings.

*Specifications and Properties* — Material specifications for Ti-8Al-1Mo-1V are presented in Table 5.3.2.0(a). Room-temperature mechanical and physical properties for Ti-8Al-1Mo-1V are shown in Tables 5.3.2.0(b) and (c). The effect of temperature on physical properties is shown in Figure 5.3.2.0.

**Table 5.3.2.0(a). Material Specifications for Ti-8Al-1Mo-1V**

Specification	Form
MIL-T-9046	Sheet, strip, and plate
MIL-T-9047	Bar
AMS 4973	Forging
AMS 4915	Sheet, strip, and plate
AMS 4916	Sheet, strip, and plate




## MIL-HDBK-5H

1 December 1998

**5.3.2.1 Single-Annealed Condition** — Cryogenic, room-temperature, and elevated temperature property curves for this condition are shown in Figures 5.3.2.1.1 and 5.3.2.1.4. Typical tensile and compressive stress-strain and tangent-modulus curves are shown in Figures 5.3.2.1.6(a) and (b) for room temperature and several elevated temperatures.

**5.3.2.2 Duplex-Annealed Condition** — Cryogenic, room temperature, and elevated temperature curves for this condition are shown in Figure 5.3.2.2.1. Typical tensile and compressive stress-strain and tangent-modulus curves are shown in Figures 5.3.2.2.6(a) and (b) for room temperature and several elevated temperatures. Fatigue S/N curves for unnotched and notched specimens at room temperature and several elevated temperatures are shown in Figures 5.3.2.2.8(a) through (f).



**Figure 5.3.2.0. Effect of temperature on the physical properties of Ti-8Al-1Mo-1V alloy.**

**MIL-HDBK-5H****1 December 1998****Table 5.3.2.0(b<sub>1</sub>). Design Mechanical and Physical Properties of Ti-8Al-1Mo-1V Sheet and Plate**

Specification	AMS 4915, MIL-T-9046, and Comp A-4				
Form	Sheet	Plate			
Condition	Single Annealed				
Thickness, in.	≤ 0.1875	0.1875-0.500	0.501-1.000	1.001-2.500	2.501-4.000
Basis	S	S	S	S	S
Mechanical Properties:					
$F_{tu}$ , ksi:					
L	145	145	140	130	120
LT	145	145	140	130	120
ST	...	...	...	...	120 <sup>b</sup>
$F_{ty}$ , ksi:					
L	135	135	130	120	110
LT	135	135	130	120	110
ST	...	...	...	...	110 <sup>b</sup>
$F_{cy}$ , ksi:					
L	144	...	...	...	...
LT	149	...	...	...	...
ST	...	...	...	...	...
$F_{su}$ , ksi	93	...	...	...	...
$F_{bru}$ , ksi:					
(e/D = 1.5)	239	...	...	...	...
(e/D = 2.0)	294	...	...	...	...
$F_{bry}$ , ksi:					
(e/D = 1.5)	196	...	...	...	...
(e/D = 2.0)	214	...	...	...	...
$e$ , percent:					
L	a	10	10	10	8
LT	a	10	10	10	8
ST	...	...	...	...	8 <sup>b</sup>
$E$ , 10 <sup>3</sup> ksi	17.5 <sup>c</sup>				
$E_c$ , 10 <sup>3</sup> ksi	18.0 <sup>c</sup>				
$G$ , 10 <sup>3</sup> ksi	6.7				
$\mu$	0.32				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup>	0.158				
C, Btu/(lb)(°F)	0.12				
$K$ and $\alpha$	See Figure 5.3.2.0				

a 0.008-0.014 in. thickness, 6 percent; 0.015-0.024 in. thickness, 8 percent; &gt; 0.025 in. thickness, 10 percent.

b Applicable, providing ST dimension is &gt; 3.000 inches.

c Average, values may vary with test direction.

**MIL-HDBK-5H****1 December 1998****Table 5.3.2.0(b<sub>2</sub>). Design Mechanical and Physical Properties of Ti-8Al-1Mo-1V Sheet and Plate**

Specification . . . . .	AMS 4916, MIL-T-9046, and Comp. A-4					
Form . . . . .	Sheet		Plate			
Condition . . . . .	Duplex Annealed					
Thickness, in. . . . .	0.015-0.024	0.025-0.1875	0.1875-0.500	0.501-1.000	1.001-2.000	2.001-4.000
Basis . . . . .	S	S	S	S	S	S
Mechanical Properties:						
$F_{tu}$ , ksi:						
L . . . . .	135	135	130	130	125	120
LT . . . . .	135	135	130	130	125	120
$F_{ty}$ , ksi:						
L . . . . .	120	120	120	120	115	110
LT . . . . .	120	120	120	120	115	110
$F_{cy}$ , ksi:						
L . . . . .	126	126	...	...	...	...
LT . . . . .	126	126	...	...	...	...
$F_{su}$ , ksi . . . . .	84	84	...	...	...	...
$F_{bru}$ , ksi:						
(e/D = 1.5) . . . . .	223	223	...	...	...	...
(e/D = 2.0) . . . . .	269	269	...	...	...	...
$F_{bry}$ , ksi:						
(e/D = 1.5) . . . . .	174	174	...	...	...	...
(e/D = 2.0) . . . . .	191	191	...	...	...	...
$e$ , percent:						
L . . . . .	8	10	10	10	10	8
LT . . . . .	8	10	10	10	10	8
$E$ , 10 <sup>3</sup> ksi . . . . .	17.5 <sup>a</sup>					
$E_c$ , 10 <sup>3</sup> ksi . . . . .	18.0 <sup>a</sup>					
$G$ , 10 <sup>3</sup> ksi . . . . .	6.7					
$\mu$ . . . . .	0.32					
Physical Properties:						
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.158					
C, Btu/(lb)(°F) . . . . .	0.12					
$K$ and $\alpha$ . . . . .	See Figure 5.3.2.0					

a Average, L and LT; values may vary with test direction.



**MIL-HDBK-5H****1 December 1998****Table 5.3.2.0(c). Design Mechanical and Physical Properties of Ti-8Al-1Mo-1V Bar and Forging**

Specification .....	MIL-T-9047		AMS 4973	
Form .....	Bar		Forging	
Condition .....	Duplex annealed		Solution treated and stabilized	
Thickness or diameter, in. ...	≤ 2.500 <sup>a</sup>	2.501-4.000 <sup>a</sup>	≤ 2.499	2.500-4.000
Basis .....	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	130	120	130	120
LT .....	130 <sup>b</sup>	120 <sup>b</sup>	130 <sup>c</sup>	120
ST .....	...	120 <sup>b</sup>	...	120
$F_{ty}$ , ksi:				
L .....	120	110	120	110
LT .....	120 <sup>b</sup>	110 <sup>b</sup>	120 <sup>c</sup>	110
ST .....	...	110 <sup>b</sup>	...	110
$F_{cy}$ , ksi:				
L .....	...	...	...	...
LT .....	...	...	...	...
ST .....	...	...	...	...
$F_{su}$ , ksi .....	...	...	...	...
$F_{bru}$ , ksi:				
(e/D = 1.5) .....	...	...	...	...
(e/D = 2.0) .....	...	...	...	...
$F_{bry}$ , ksi:				
(e/D = 1.5) .....	...	...	...	...
(e/D = 2.0) .....	...	...	...	...
$e$ , percent:				
L .....	10	10	10	10
LT .....	10 <sup>b</sup>	10 <sup>b</sup>	10 <sup>c</sup>	10
ST .....	...	8 <sup>b</sup>	...	10
$E$ , 10 <sup>3</sup> , ksi .....	17.5 <sup>d</sup>			
$E_c$ , 10 <sup>3</sup> ksi .....	18.0 <sup>d</sup>			
$G$ , 10 <sup>3</sup> ksi .....	6.7			
$\mu$ .....	0.32			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.158			
$C$ , Btu/(lb)(°F) .....	0.12			
$K$ and $\alpha$ .....	See Figure 5.3.2.0			

a Maximum of 16 square-inch cross-sectional area.

b Applicable, providing LT or ST dimension is &gt; 3.000 inches.

c Applicable, providing LT dimension is  $\geq 2.500$  inches.

d Average, values may vary with test direction.

## MIL-HDBK-5H

1 December 1998




Figure 5.3.2.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of single-annealed Ti-8Al-1Mo-1V alloy sheet.

MIL-HDBK-5H

1 December 1998






Figure 5.3.2.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of Ti-8Al-1Mo-1V alloy sheet.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.3.2.1.6(a). Typical tensile stress-strain curves for single-annealed Ti-8Al-1Mo-1V alloy sheet at room and elevated temperatures.**



**Figure 5.3.2.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for single-annealed Ti-8Al-1Mo-1V alloy sheet at room and elevated temperatures.**



## MIL-HDBK-5H

1 December 1998






Figure 5.3.2.2.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of duplex-annealed Ti-8Al-1Mo-1V alloy sheet.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 5.3.2.2.6(a). Typical tensile stress-strain curves for duplex-annealed Ti-8Al-1Mo-1V alloy sheet at room and elevated temperatures.**



**Figure 5.3.2.2.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for duplex-annealed Ti-8Al-1Mo-1V alloy sheet at room and elevated temperatures.**

## MIL-HDBK-5H

1 December 1998



**Figure 5.3.2.2.8(a). Best-fit S/N curves for unnotched, duplex annealed Ti-8Al-1Mo-1V sheet at room temperature, long transverse direction.**

Correlative Information for Figure 5.3.2.2.8(a)

Product Form: Sheet, 0.050-inch thick

Properties: TUS, ksi TYS, ksi Temp., °F

147.2 135.6 RT

Specimen Details: Unnotched  
0.750-inch net width

Surface Condition: HNO<sub>3</sub>/HF pickled

References: 5.3.2.2.8(a) and (b)

Test Parameters:

Loading - Axial  
Frequency - 1800 cpm  
Temperature - RT  
Environment - Air

No. of Heats/Lots: 1

Equivalent Stress Equation:

$$\log N_f = 10.57 - 3.46 \log (S_{eq} - 66.7)$$

$$S_{eq} = S_{max} (1-R)^{0.61}$$

Standard Error of Estimate = 0.47

Standard Deviation in Life = 0.81

R<sup>2</sup> = 66.7%

Sample Size = 24


[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]





## MIL-HDBK-5H

1 December 1998



**Figure 5.3.2.2.8(c). Best-fit S/N curves for unnotched duplex annealed Ti-8Al-1Mo-1V sheet at 400°F, long transverse direction.**

Correlative Information for Figure 5.3.2.2.8(c)

Product Form: Sheet, 0.050-inch thick

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

119.5 100.8 400

Loading - Axial  
Frequency - 1800 cpm  
Temperature - 400°F  
Environment - Air

Specimen Details: Unnotched  
0.750-inch net width

No. of Heats/Lots: 1

Surface Condition: HNO<sub>3</sub>/HF pickled

Equivalent Stress Equation:

References: 5.3.2.2.8(a) and (b)

$$\begin{aligned} \log N_f &= 8.30 - 2.53 \log (S_{eq} - 73.9) \\ S_{eq} &= S_{max} (1 - R)^{0.74} \\ \text{Standard Error of Estimate} &= 0.38 \\ \text{Standard Deviation in Life} &= 0.87 \\ R^2 &= 80.9\% \end{aligned}$$


Sample Size = 23

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 5.3.2.2.8(e). Best-fit S/N curves for unnotched duplex annealed Ti-8Al-1Mo-1V sheet at 650°F, long transverse direction.**

Correlative Information for Figure 5.3.2.2.8(e)

Product Form: Sheet, 0.050-inch thick

Test Parameters:

Loading - Axial

Frequency - 1800 cpm

Temperature - 650°F

Environment - Air

Properties: TUS, ksi TYS, ksi Temp., °F

110.2 86.8 650

Specimen Details: Unnotched  
0.750-inch, net width

No. of Heats/Lots: 1

Surface Condition: HNO<sub>3</sub>/HF pickled

Equivalent Stress Equation:

$$\log N_f = 9.83 - 3.66 \log (S_{eq} - 73)$$

$$S_{eq} = S_{max} (1 - R)^{0.78}$$

Standard Error of Estimate = 0.88

Standard Deviation in Life = 1.18

R<sup>2</sup> = 44.3%

References: 5.3.2.2.8(a) and (b)

Sample Size = 20

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



**MIL-HDBK-5H****1 December 1998****5.3.3 Ti-6Al-2Sn-4Zr-2Mo**

**5.3.3.0 Comments and Properties** — Ti-6Al-2Sn-4Zr-2Mo is a near-alpha titanium composition developed for improved elevated-temperature performance. The alloy has a titanium-aluminum base that is solid solution strengthened by additions of tin and zirconium. Molybdenum improves both room and elevated temperature strength, creep and thermal stability. Introduction of this alloy initially met the requirements for certain advanced performance gas turbine engine applications. Some of the more recent applications, however, require better creep strength than the alloy initially provided. Development work showed that a small addition of silicon, approximately 0.08 percent, substantially improved the creep strength of the alloy without significantly affecting the thermal stability. The alloy is creep resistant and relatively stable to about 1050°F. Creep and thermal stability of the alloy are further enhanced by solution treating high in the alpha-beta phase field. The alloy is available in bar, billet, plate, sheet, strip, and extrusions.

*Manufacturing Conditions* — Forging of Ti-6Al-2Sn-4Zr-2Mo at temperatures below the beta transus temperature is recommended. For optimum creep properties beta forging or a modification of it is recommended with some loss in ductility to be expected. Elevated temperatures may be used for severe sheet forming operations while room-temperature forming may be used for mild contouring. Stress relief annealing may be combined with a final hot-sizing operation. The material can be welded using TIG or MIG fusion processes to achieve 100 percent joint efficiencies but with limited weld zone ductility. As in welding any titanium alloy, shielding from atmospheric contamination is required except for spot or seam welding.

*Environmental Considerations* — Ti-6Al-2Sn-4Zr-2Mo is somewhat more resistant to hot-salt cracking than either Ti-8Al-1Mo-1V or Ti-6Al-4V alloys. The material is marginally susceptible to aqueous chloride solution stress-corrosion cracking. Surface oxides formed during exposure to service temperature (~950°F) do not adversely affect properties. Under certain conditions, titanium, when in contact with cadmium, silver, mercury, or certain of their compounds, may become embrittled. Refer to MIL-S-5002 and MIL-STD-1568 for restrictions concerning applications with titanium in contact with these metals or their compounds.

*Heat Treatment* — Several different annealing treatments, which are described below, are available for Ti-6Al-2Sn-4Zr-2Mo.

For sheet and strip:

Duplex Anneal: 1650°F for ½ hour, air cool, followed by 1450°F for ¼ hour, and air cool.

Triplex Anneal: 1650°F for ½ hour, air cool, followed by 1450°F for ¼ hour, air cool, followed by 1100°F for 2 hours and air cool.

For plate:

Duplex Anneal: 1650°F for 1 hour, air cool, followed by 1100°F for 8 hours and air cool.

Triplex Anneal: 1650°F for ½ hour, air cool, followed by 1450°F for ¼ hour, air cool, followed by 1100°F for 2 hours and air cool.

For bars and forgings:

Duplex Anneal: Solution anneal 25 to 50°F below beta transus temperature for 1 hour, air cool or faster, followed by 1100°F for 8 hours and air cool.

**MIL-HDBK-5H****1 December 1998****Table 5.3.3.0(a). Material Specifications for Ti-6Al-2Sn-4Zr-2Mo**

Specification	Form
MIL-T-9046	Sheet and strip
AMS 4975	Bar
AMS 4976	Forging
AMS 4919	Sheet, strip, and plate

*Specifications and Properties* — Material specifications for Ti-6Al-2Sn-4Zr-2Mo are given in Table 5.3.3.0(a). Room-temperature mechanical and physical properties for Ti-6Al-2Sn-4Zr-2Mo are presented in Table 5.3.3.0(b) and (c). The effect of temperature on physical properties is shown in Figure 5.3.3.0.

**5.3.3.1 Single, Duplex, and Triplex Annealed** — Room and elevated temperature property curves are shown in Figures 5.3.3.1.1, 5.3.3.1.2, and 5.3.3.1.4. Typical stress-strain curves at room and elevated temperatures are shown in Figures 5.3.3.1.6(a) and (b). Full range stress-strain curves at room and elevated temperatures are shown in Figure 5.3.3.1.6(c).

**Table 5.3.3.0(b). Design Mechanical and Physical Properties of Ti-6Al-2Sn-4Zr-2Mo**

Specification .....	AMS 4919								MIL-T-9046, Comp. AB-4
Form .....	Sheet								
Condition .....	Duplex annealed								Triplex annealed
Thickness or diameter, in. .	≤0.046		0.047-0.093		0.094-0.140		0.141-0.187		≤0.187
Basis .....	A	B	A	B	A	B	A	B	S <sup>c</sup>
Mechanical Properties:									
$F_u$ , ksi:									
L .....	135 <sup>a</sup>	143	135 <sup>a</sup>	143	135 <sup>a</sup>	143	135 <sup>a</sup>	143	145
LT .....	135 <sup>a</sup>	143	135 <sup>a</sup>	143	135 <sup>a</sup>	143	135 <sup>a</sup>	143	145
$F_y$ , ksi:									
L .....	125 <sup>b</sup>	136	125 <sup>b</sup>	136	125 <sup>b</sup>	136	125 <sup>b</sup>	136	135
LT .....	125 <sup>b</sup>	134	125 <sup>b</sup>	134	125 <sup>b</sup>	134	125 <sup>b</sup>	134	135
$F_{cy}$ , ksi:									
L .....	132	142	132	142	132	142	132	142	...
LT .....	132	142	132	142	132	142	132	142	...
$F_{su}$ , ksi .....	...	...	...	...	...	...	...	...	...
$F_{bru}^d$ , ksi:									
(e/D=1.5) .....	195	206	205	217	214	227	219	232	...
(e/D=2.0) .....	217	230	243	258	266	282	279	295	...
$F_{bry}^d$ , ksi:									
(e/D=1.5) .....	171	183	171	183	171	183	171	183	...
(e/D=2.0) .....	202	217	202	217	202	217	202	217	...
e, percent (S-basis):									
L .....	8 <sup>c</sup>	...	c	...	10	...	10	...	c
LT .....	8 <sup>c</sup>	...	c	...	10	...	10	...	c
$E$ , 10 <sup>3</sup> ksi .....	16.5								
$E_c$ , 10 <sup>3</sup> ksi .....	18.0								
$G$ , 10 <sup>3</sup> ksi .....	6.2								
$\mu$ .....	0.32								
Physical Properties:									
$\omega$ , lb/in. <sup>3</sup> .....	0.164								
C, K and $\alpha$ .....	See Figure 5.3.3.0								

a S-basis. The rounded  $T_{99}$  values are as follows:  $F_u(L\&LT) = 139$  ksi.

b S-basis. The rounded  $T_{99}$  values are as follows:  $F_y(L) = 131$  ksi and  $F_y(LT) = 129$  ksi.

c 8% for 0.025 through 0.062 inch and 10% for >0.062 inch.

d Bearing values are "dry pin" values per Section 1.4.7.1.

e S-basis values are representative of test specimens excised from duplex annealed material and thermally treated to triplex annealed condition in a laboratory furnace.

**MIL-HDBK-5H****1 December 1998****Table 5.3.3.0(c). Design Mechanical and Physical Properties of Ti-6Al-2Sn-4Zr-2Mo**

Specification.....	AMS 4975		AMS 4976
Form.....	Bar		Forging
Condition.....	STA (Duplex annealed)		STA (Duplex annealed)
Cross-Sectional area, in. <sup>2</sup> .....	≤ 16		≤ 9
Thickness, or diameter, in.....	≤ 3.000		≤ 3.000
Basis.....	A	B	S
<b>Mechanical Properties:</b>			
$F_{tu}$ , ksi:			
L.....	130 <sup>a</sup>	144	130
LT.....	130 <sup>b</sup>	...	130 <sup>b</sup>
ST.....	130 <sup>b</sup>	...	130 <sup>b</sup>
$F_{ty}$ , ksi:			
L.....	120 <sup>a</sup>	131	120
LT.....	120 <sup>b</sup>	...	120 <sup>b</sup>
ST.....	120 <sup>b</sup>	...	120 <sup>b</sup>
$F_{cy}$ , ksi:			
L.....	...	...	...
LT.....	...	...	...
ST.....	...	...	...
$F_{su}$ , ksi.....	...	...	...
$F_{bru}$ , ksi:			
(e/D=1.5).....	...	...	...
(e/D=2.0).....	...	...	...
$F_{bry}$ , ksi:			
(e/D=1.5).....	...	...	...
(e/D=2.0).....	...	...	...
$e$ , percent(S basis):			
L.....	10	...	10
LT.....	10 <sup>b</sup>	...	10 <sup>b</sup>
ST.....	10 <sup>b</sup>	...	10 <sup>b</sup>
$RA$ , percent (S basis):			
L.....	25	...	25
LT.....	25 <sup>b</sup>	...	25 <sup>b</sup>
ST.....	25 <sup>b</sup>	...	25 <sup>b</sup>
$E$ , 10 <sup>3</sup> ksi.....	16.5		
$E_c$ , 10 <sup>3</sup> ksi.....	18.0		
$G$ , 10 <sup>3</sup> ksi.....	6.2		
$\mu$ .....	0.32		
<b>Physical Properties:</b>			
$\omega$ , lb/in. <sup>3</sup> .....	0.164		
$C$ , $K$ , and $\alpha$ .....	See Figure 5.3.3.0		

a S basis. The rounded  $T_{90}$  values are as follows:  $F_{tu}(L) = 138$  ksi and  $F_{ty}(L) = 125$  ksi.

b S basis. Applicable providing transverse dimension is ≥ 2.500 in.



MIL-HDBK-5H  
1 December 1998




Figure 5.3.3.0. Effect of temperature on the physical properties of Ti-6Al-2Sn-4Zr-2Mo alloy.




Figure 5.3.3.1.1. Effect of temperature in the tensile ultimate strength ( $F_u$ ) and tensile yield strength ( $F_y$ ) of duplex- and triplex-annealed Ti-6Al-2Sn-4Zr-2Mo (all products).

## MIL-HDBK-5H

1 December 1998




Figure 5.3.3.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) of duplex annealed Ti-6Al-2Sn-4Zr-2Mo alloy sheet.






Figure 5.3.3.1.4. Effect of temperature on the tensile and compressive moduli (E and  $E_c$ ) of duplex- and triplex-annealed Ti-6Al-2Sn-4Zr-2Mo alloy.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 5.3.3.1.6(a). Typical tensile stress-strain curves for duplex annealed Ti-6Al-2Sn-4Zr-2Mo alloy bar at various temperatures.**



**Figure 5.3.3.1.6(b). Typical tensile stress-strain curves for duplex- and triplex-annealed Ti-6Al-2Sn-4Zr-2Mo alloy sheet at various temperatures.**



**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.3.3.1.6(c). Typical tensile stress-strain curves (full range) for duplex-annealed Ti-6Al-2Sn-4Zr-2Mo alloy sheet at room and elevated temperatures.**

**MIL-HDBK-5H****1 December 1998****5.4 ALPHA-BETA TITANIUM ALLOYS**

The alpha-beta titanium alloys contain both alpha and beta phases at room temperature. The alpha phase is similar to that of unalloyed titanium but is strengthened by alpha stabilizing additions (e.g., aluminum). The beta phase is the high-temperature phase of titanium but is stabilized to room temperature by sufficient quantities of beta stabilizing elements as vanadium, molybdenum, iron, or chromium. In addition to strengthening of titanium by the alloying additions, alpha-beta alloys may be further strengthened by heat treatment. The alpha-beta alloys have good strength at room temperature and for short times at elevated temperature. They are not noted for long-time creep strength. With the exception of annealed Ti-6Al-4V, these alloys are not recommended for cryogenic applications. The weldability of many of these alloys is poor because of the two-phase microstructure. However, some of them can be welded successfully with special precautions.

**5.4.1 Ti-6Al-4V**

**5.4.1.0 Comments and Properties** — Ti-6Al-4V is available in all mill product forms as well as castings and powder metallurgy forms. It can be used in either the annealed or solution treated plus aged (STA) conditions and is weldable. Useful temperature range is from -320 to 750°F. For maximum toughness, Ti-6Al-4V should be used in the annealed or duplex-annealed conditions whereas for maximum strength, the STA condition is used. The full strength potential for this alloy is not available in sections greater than 1 inch.

*Manufacturing Considerations* — Ti-6Al-4V alloy may be forged above the beta transus temperature using procedures to promote a high toughness material. The material is routinely finished below beta transus temperature for good combinations of fabricability, strength, ductility, and toughness. Elevated temperatures are usually used for form flat-rolled products although extensive forming may be accomplished at room temperature. Flat-rolled products are usually formed and used in the annealed condition although some forming in the STA condition is possible.

This alloy can be spot welded and is being fusion welded extensively in certain applications. Established titanium-welding techniques must be employed and special design considerations may be involved in fusion weldments. Stress-relief annealing after welding is recommended.

*Environmental Considerations* — Ti-6Al-4V can withstand prolonged exposure to temperatures up to 750°F without loss of ductility. Its toughness in the annealed condition is adequate at temperatures down to -320°F. (A special low interstitial grade may be used down to -423°F.) Ti-6Al-4V is resistant to hot-salt stress corrosion to about its maximum use temperature depending on exposure time and exposure stress. The material is marginally susceptible to aqueous chloride solution stress corrosion, but is considered to have good resistance to this reaction compared with other commonly used alloys. Under certain conditions, titanium, when in contact with cadmium, silver, mercury, or certain of their compounds, may become embrittled. Refer to MIL-S-5002 and MIL-STD-1568 for restrictions concerning applications with titanium in contact with these metals or their compounds.

*Heat Treatment* — This alloy is commonly specified in either the annealed condition or in the fully heat-treated condition. Annealing requires 1 hour at 1300°F followed by furnace cooling if maximum ductility is required.

The specified fully heat-treated, or solution-treated and aged condition for sheet is as follows:

Solution treat at 1700°F for 5 to 25 minutes, quench in water.

**MIL-HDBK-5H****1 December 1998**

Age at 975°F for 4 to 6 hours, air cool.

For bars and forgings:

Solution treat at 1700°F for 1 hour, quench in water.

Age at 1000°F for 3 hours, air cool.

*Specifications and Properties* — Some material specifications for Ti-6Al-4V are shown in Table 5.4.1.0(a). Room-temperature mechanical properties for Ti-6Al-4V are shown in Tables 5.4.1.0(b) through (g). The effect of temperature on physical properties is shown in Figure 5.4.1.0.

**Table 5.4.1.0(a). Material Specifications for Ti-6Al-4V**

Specification	Form
MIL-T-9046	Sheet, strip, and plate
MIL-T-9047	Bar
AMS 4934	Extrusion
AMS 4935	Extrusion
AMS 4967	Bar
AMS 4928	Bar and die forging
AMS 4911	Sheet, strip, and plate
AMS 4920	Die forging
AMS 4962	Investment casting

**5.4.1.1 Annealed Condition** — Elevated temperature curves for annealed Ti-6Al-4V are shown in Figures 5.4.1.1.1 through 5.4.1.1.5. Typical stress-strain curves at several temperatures are shown in Figures 5.4.1.1.6(a) through (c). Typical full-range stress-strain curves at room temperature are shown in Figure 5.4.1.1.6(d). Unnotched and notched fatigue data are shown in Figures 5.4.1.1.8(a) through (g). Fatigue crack-propagation data for plate are shown in Figure 5.4.1.1.9.

**5.4.1.2 Solution-Treated and Aged Condition** — Elevated temperature curves for solution-treated and aged alloy are shown in Figures 5.4.1.2.1 through 5.4.1.2.4. Typical tensile and compressive stress-strain and tangent-modulus curves are shown in Figures 5.4.1.2.6(a) through (g). Typical full-range stress-strain curves at several temperatures up to 1000°F are shown in Figure 5.4.1.2.6(h). A nomograph of typical creep properties of solution-treated and aged sheet for the temperature range 600°F through 800°F is shown in Figure 5.4.1.2.7. Fatigue data at room and elevated temperatures are shown in Figures 5.4.1.2.8(a) through (i).

**MIL-HDBK-5H****1 December 1998****Table 5.4.1.0(b). Design Mechanical and Physical Properties of Ti-6Al-4V Sheet, Strip, and Plate**

Specification . . . . .	AMS 4911 and MIL-T-9046, Comp. AB-1					MIL-T-9046, Comp. AB-1			
	Sheet		Plate			Sheet, strip, and plate			
	Annealed					Solution treated and aged			
	≤ 0.1875		0.1875-2.000		2.001- 4.000	≤ 0.1875	0.1875- 0.750	0.751- 1.000	1.001- 2.000
	A	B	A	B	S	S	S	S	S
Mechanical Properties:									
$F_{tu}$ , ksi:									
L . . . . .	134	139	130 <sup>a</sup>	135	130	160	160	150	145
LT . . . . .	134	139	130 <sup>a</sup>	138	130	160	160	150	145
$F_{ty}$ , ksi:									
L . . . . .	126	131	120	125	120	145	145	140	135
LT . . . . .	126	131	120 <sup>a</sup>	131	120	145	145	140	135
$F_{cy}$ , ksi:									
L . . . . .	133	138	124	129	124	154	150	145	...
LT . . . . .	135	141	130	142	130	162	...	...	...
$F_{su}$ , ksi . . . . .	87	90	79	84	79	100	93	87	...
$F_{bru}$ , ksi:									
(e/D = 1.5) . . . . .	213 <sup>b</sup>	221 <sup>b</sup>	206 <sup>b</sup>	214 <sup>b</sup>	206 <sup>b</sup>	236	248	233	...
(e/D = 2.0) . . . . .	272 <sup>b</sup>	283 <sup>b</sup>	260 <sup>b</sup>	276 <sup>b</sup>	260 <sup>b</sup>	286	308	289	...
$F_{bry}$ , ksi:									
(e/D = 1.5) . . . . .	171 <sup>b</sup>	178 <sup>b</sup>	164 <sup>b</sup>	179 <sup>b</sup>	164 <sup>b</sup>	210	210	203	...
(e/D = 2.0) . . . . .	208 <sup>b</sup>	217 <sup>b</sup>	194 <sup>b</sup>	212 <sup>b</sup>	194 <sup>b</sup>	232	243	235	...
$e$ , percent (S-basis):									
L . . . . .	8 <sup>c</sup>	...	10	...	10	5 <sup>d</sup>	8	6	6
LT . . . . .	8 <sup>c</sup>	...	10	...	10	5 <sup>d</sup>	8	6	6
$E$ , 10 <sup>3</sup> ksi . . . . .	16.0								
$E_c$ , 10 <sup>3</sup> ksi . . . . .	16.4								
$G$ , 10 <sup>3</sup> ksi . . . . .	6.2								
$\mu$ . . . . .	0.31								
Physical Properties:									
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.160								
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 4.5.1.0								

a The rounded  $T_{99}$  values are higher than specification values as follows:  $F_{tu}(L) = 131$  ksi,  $F_{tu}(LT) = 132$  ksi, and  $F_{ty}(LT) = 123$  ksi.

b Bearing values are “dry pin” values per Section 1.4.7.1.

c 8%—0.025 to 0.062 in. and 10%—0.063 in. and above.

d 5%—0.050 in. and above; 4%—0.033 to 0.049 in. and 3%—0.032 in. and below.

**Table 5.4.1.0(c<sub>1</sub>). Design Mechanical and Physical Properties of Ti-6Al-4V Bar**

Specification .....	AMS 4928												
Form .....	Bar												
Condition .....	Annealed												
Thickness or diameter, in. ....	<0.500	0.500-1.000		1.001-2.000		2.001-3.000		3.001-4.000		4.001-5.000		5.001-6.000	
Basis .....	S	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:													
$F_{tu}$ , ksi:													
L .....	135	135 <sup>a</sup>	142	134	140	130 <sup>a</sup>	138	130	135	128	133	125	131
LT .....	135 <sup>b</sup>	135 <sup>a</sup>	144	135 <sup>a</sup>	143	130 <sup>a</sup>	142	130 <sup>a</sup>	141	130 <sup>a</sup>	139	130 <sup>a</sup>	138
$F_{ty}$ , ksi:													
L .....	125	125 <sup>a</sup>	134	125 <sup>a</sup>	131	120 <sup>a</sup>	128	120	125	117	122	114	119
LT .....	125 <sup>b</sup>	125 <sup>a</sup>	134	125 <sup>a</sup>	132	120 <sup>a</sup>	131	120 <sup>a</sup>	129	120 <sup>a</sup>	127	119	125
$F_{cy}$ , ksi:													
L .....	129	129	138	129	135	...	...	...	...	...	...	...	...
LT .....	...	...	...	...	...	...	...	...	...	...	...	...	...
$F_{su}$ , ksi .....	83	83	87	82	86	...	...	...	...	...	...	...	...
$F_{bru}$ , ksi:													
(e/D = 1.5) .....	201	201	212	200	209	...	...	...	...	...	...	...	...
(e/D = 2.0) .....	253	253	266	251	262	...	...	...	...	...	...	...	...
$F_{bry}$ , ksi:													
(e/D = 1.5) .....	177	177	190	177	186	...	...	...	...	...	...	...	...
(e/D = 2.0) .....	205	205	220	205	215	...	...	...	...	...	...	...	...
$e$ , percent (S-basis):													
L .....	10	10	...	10	...	10	...	10	...	10	...	10	...
LT .....	10 <sup>b</sup>	10 <sup>b</sup>	...	10 <sup>b</sup>	...	10 <sup>b</sup>	...	10	...	10	...	10	...
ST .....	...	...	...	...	...	10 <sup>b</sup>	...	10	...	8	...	8	...
$RA$ , percent (S-basis):													
L .....	25	25	...	25	...	25	...	25	...	20	...	20	...
LT .....	20 <sup>b</sup>	20 <sup>b</sup>	...	20 <sup>b</sup>	...	20 <sup>b</sup>	...	20	...	20	...	20	...
ST .....	...	...	...	...	...	15 <sup>b</sup>	...	15	...	15	...	15	...
$E$ , 10 <sup>3</sup> ksi .....	16.9												
$E_c$ , 10 <sup>3</sup> ksi .....	17.2												
$G$ , 10 <sup>3</sup> ksi .....	6.2												
$\mu$ .....	0.31												
Physical Properties:													
$\omega$ , lb/in. <sup>3</sup> .....	0.160												
$C$ , $K$ , and $\alpha$ .....	See Figure 5.4.1.0												

a S-basis. The rounded  $T_{99}$  values are shown in Table 5.4.1.0(c<sub>2</sub>).b Applicable, providing LT or ST dimension is  $\geq 2.500$  inches.



**MIL-HDBK-5H**  
**1 December 1998**

**Table 5.4.1.0(c<sub>2</sub>). Rounded T<sub>99</sub> Values for Tensile Yield and Ultimate Strength of Ti-6Al-4V Bar**

Thickness or diameter, in. . . . .	0.500- 1.000	1.001- 2.000	2.001- 3.000	3.001- 4.000	4.001- 5.000	5.001- 6.000
Mechanical Properties:						
<i>F<sub>m</sub></i> , ksi:						
L . . . . .	137	...	132	...	...	...
LT . . . . .	140	139	138	136	135	134
<i>F<sub>y</sub></i> , ksi:						
L . . . . .	129	126	123	...	...	...
LT . . . . .	129	127	127	123	121	...

**MIL-HDBK-5H****1 December 1998****Table 5.4.1.0(c<sub>3</sub>). Design Mechanical and Physical Properties of Ti-6Al-4V Bar**

Specification . . . . .	MIL-T-9047												
Form . . . . .	Bar												
Condition . . . . .	Annealed												
Cross-sectional area, in. <sup>2</sup> . . .	≤48												
Thickness, in. . . . .	<0.500	0.500-1.000		1.001-2.000		2.001-3.000		3.001-4.000		4.001-5.000		5.001-6.000	
Basis . . . . .	S	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:													
<i>F<sub>tu</sub></i> , ksi:													
L . . . . .	130	130 <sup>a</sup>	142	130 <sup>a</sup>	140	130 <sup>a</sup>	138	130	135	128	133	125	131
LT . . . . .	130 <sup>b</sup>	130 <sup>a</sup>	144	130 <sup>a</sup>	143	130 <sup>a</sup>	142	130 <sup>a</sup>	141	130 <sup>a</sup>	139	130 <sup>a</sup>	138
<i>F<sub>ty</sub></i> , ksi:													
L . . . . .	120	120 <sup>a</sup>	134	120 <sup>a</sup>	131	120 <sup>a</sup>	128	120	125	117	122	114	119
LT . . . . .	120 <sup>b</sup>	120 <sup>a</sup>	134	120 <sup>a</sup>	132	120 <sup>a</sup>	131	120 <sup>a</sup>	129	120	127	119	125
<i>F<sub>cy</sub></i> , ksi:													
L . . . . .	124	124	138	124	135	...	...	...	...	...	...	...	...
LT . . . . .	...	...	...	...	...	...	...	...	...	...	...	...	...
<i>F<sub>su</sub></i> , ksi . . . . .	80	80	87	80	86	...	...	...	...	...	...	...	...
<i>F<sub>bru</sub></i> , ksi:													
(e/D = 1.5) . . . . .	194	194	212	194	209	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	244	244	266	244	262	...	...	...	...	...	...	...	...
<i>F<sub>brv</sub></i> , ksi:													
(e/D = 1.5) . . . . .	170	170	190	170	186	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	197	197	220	197	215	...	...	...	...	...	...	...	...
<i>e</i> , percent (S basis):													
L . . . . .	10	10	...	10	...	10	...	10	...	10	...	10	...
LT . . . . .	10 <sup>b</sup>	10 <sup>b</sup>	...	10 <sup>b</sup>	...	10 <sup>b</sup>	...	10	...	10	...	10	...
ST . . . . .	...	...	...	...	...	...	...	8	...	8	...	8	...
<i>RA</i> , percent (S-basis):													
L . . . . .	25	25	...	25	...	25	...	25	...	20	...	20	...
LT . . . . .	25 <sup>b</sup>	25 <sup>b</sup>	...	25 <sup>b</sup>	...	25 <sup>b</sup>	...	25	...	20	...	20	...
ST . . . . .	...	...	...	...	...	...	...	15	...	15	...	15	...
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	16.9												
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	17.2												
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	6.2												
<i>μ</i> . . . . .	0.31												
Physical Properties:													
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.160												
<i>C</i> , <i>K</i> , and <i>α</i> . . . . .	See Figure 5.4.1.0												

a S-basis. The rounded T<sub>99</sub> values are shown in Table 5.4.1.0(c<sub>4</sub>).

b Applicable, providing LT dimension is ≥3.000 inches.

**MIL-HDBK-5H****1 December 1998****Table 5.4.1.0(c<sub>4</sub>). Rounded T<sub>99</sub> Values for Tensile Yield and Ultimate Strength of Ti-6Al-4V Bar**

Thickness or diameter, in. . . . .	0.500- 1.000	1.001- 2.000	2.001- 3.000	3.001- 4.000	4.001- 5.000	5.001- 6.000
Mechanical Properties:						
$F_m$ , ksi:						
L . . . . .	137	134	132	...	...	...
LT . . . . .	140	139	138	136	135	134
$F_y$ , ksi:						
L . . . . .	129	126	123	...	...	...
LT . . . . .	129	127	125	123	121	...

**Table 5.4.1.0(d). Design Mechanical and Physical Properties of Ti-6Al-4V Bar**

Specification	AMS 4967 <sup>a</sup> and MIL-T-9047									MIL-T-9047				
Form	Rectangular bar									Round, square, and hexagon bar				
Condition	Solution treated and aged													
Width, in.	0.501-8.000	1.001-4.000	4.001-8.000	1.501-4.000	4.001-8.000	2.001-4.000	4.001-8.000	3.001-8.000	4.001-8.000	...	...	...	...	...
Thickness, in.	≤0.500	0.501-1.000		1.001-1.500		1.501-2.000		2.001-3.000	3.001-4.000	≤0.500	0.501-1.000	1.001-1.500	1.501-2.000	2.001-3.000
Basis	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:														
$F_{tu}$ , ksi:														
L	160	155	150	150	145	145	140	135	130	165	160	155	150	140
LT	160	155	150	150	145	145	140	135	130	165	160	155	150	140
$F_{ty}$ , ksi:														
L	150	145	140	140	135	135	130	125	120	155	150	145	140	130
LT	150	145	140	140	135	135	130	125	120	155	150	145	140	130
$F_{cy}$ , ksi:														
L	...	...	...	...	...	...	...	...	...	...	...	...	...	...
LT	...	...	...	...	...	...	...	...	...	...	...	...	...	...
$F_{su}$ , ksi	92	...	...	...	...	...	...	...	...	...	...	...	...	...
$F_{bru}$ , ksi:														
(e/D = 1.5)	...	...	...	...	...	...	...	...	...	...	...	...	...	...
(e/D = 2.0)	...	...	...	...	...	...	...	...	...	...	...	...	...	...
$F_{bry}$ , ksi:														
(e/D = 1.5)	...	...	...	...	...	...	...	...	...	...	...	...	...	...
(e/D = 2.0)	...	...	...	...	...	...	...	...	...	...	...	...	...	...
$e$ , percent:														
L	10	10	10	10	10	10	10	10	8	10	10	10	10	10
LT	10	10	10	10	10	10	10	10	8	10	10	10	10	10
RA, percent:														
L	25	20	20	20	20	20	20	20	15	20	20	20	20	20
LT	25	20	20	20	20	20	20	20	15	20	20	20	20	20
$E$ , 10 <sup>3</sup> ksi	16.9													
$E_c$ , 10 <sup>3</sup> ksi	17.2													
$G$ , 10 <sup>3</sup> ksi	6.2													
$\mu$	0.31													
Physical Properties:														
$\omega$ , lb/in. <sup>3</sup>	0.160													
$C$ , $K$ , and $\alpha$	See Figure 5.4.1.0													

a For AMS 4967,  $e$  and RA values may be different than those shown.

**Table 5.4.1.0(e). Design Mechanical and Physical Properties of Ti-6Al-4V Extrusion**

Specification . . . . .	AMS 4935				AMS 4934							
Form . . . . .	Extrusion											
Condition . . . . .	Annealed				Solution treated and aged							
Thickness or diameter, in. . . . .	≤2.000		2.001-3.000		<0.500		0.501-0.750		0.751-1.000		1.001-2.000	2.001-3.000
Basis . . . . .	A	B	A	B	A	B	A	B	A	B	S	S
Mechanical Properties:												
$F_{tu}$ , ksi:												
L . . . . .	130 <sup>a</sup>	137	130 <sup>b</sup>	135	155	163	151	157	147	153	140	130
LT <sup>d</sup> . . . . .	130 <sup>a</sup>	139	130 <sup>b</sup>	139	155	163	151	157	147	155	140	130
$F_{ty}$ , ksi:												
L . . . . .	120	124	118	122	138	147	138	143	133	140	130	120
LT <sup>d</sup> . . . . .	120 <sup>a</sup>	128	120	125	138	147	138	145	133	142	130	120
$F_{cy}$ , ksi:												
L . . . . .	128	133	124	128	147	157	147	153	142	150	139	128
LT <sup>d</sup> . . . . .	129	138	...	...	147	157	147	155	139	152	139	128
$F_{su}$ , ksi . . . . .	83	89	...	...	94	99	92	96	89	93	85	79
$F_{bru}^c$ , ksi:												
(e/D = 1.5) . . . . .	214	226	...	...	243	256	237	246	231	240	220	204
(e/D = 2.0) . . . . .	264	278	...	...	311	327	303	315	295	307	281	261
$F_{bry}^c$ , ksi:												
(e/D = 1.5) . . . . .	180	186	...	...	208	222	208	216	201	212	196	182
(e/D = 2.0) . . . . .	210	217	...	...	242	257	242	250	233	245	228	210
$e$ , percent (S-basis):												
L . . . . .	10	...	10	...	6	...	6	...	6	...	6	6
LT <sup>d</sup> . . . . .	8	...	8	...	6	...	6	...	6	...	6	6
$RA$ , percent (S-basis):												
L . . . . .	20	...	20	...	12	...	12	...	12	...	12	12
LT <sup>d</sup> . . . . .	15	...	15	...	12	...	12	...	12	...	12	12
$E$ , 10 <sup>3</sup> ksi . . . . .	16.9											
$E_c$ , 10 <sup>3</sup> ksi . . . . .	17.2											
$G$ , 10 <sup>3</sup> ksi . . . . .	6.2											
$\mu$ . . . . .	0.31											
Physical Properties:												
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.160											
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 5.4.1.0											

a S-basis. The rounded  $T_{99}$  values are higher than specification values as follows:  $F_{tu}$  (L) and (LT) = 132 ksi and  $F_{ty}$  (LT) = 121 ksi.

b S-basis. The rounded  $T_{99}$  values are higher than specification values as follows:  $F_{tu}$  (L) = 132 ksi and  $F_{tu}$  (LT) = 136 ksi.

c Bearing values are "dry pin" values per Section 1.4.7.1.

d Applicable, providing LT dimension is ≥2.500 inches.

**MIL-HDBK-5H****1 December 1998****Table 5.4.1.0(f). Design Mechanical and Physical Properties of Ti-6Al-4V Die Forging**

Specification . . . . .	AMS 4928			AMS 4920	
Form . . . . .	Die forging				
Condition . . . . .	Alpha-beta processed, annealed			Alpha-beta or beta processed, annealed	
Thickness, in. . . . .	≤2.000	2.001-4.000	4.001-6.000	≤2.000	2.001-6.000
Basis . . . . .	S	S	S	S	S
Mechanical Properties:					
$F_{tu}$ , ksi:					
L . . . . .	135	130	130	130	130
LT . . . . .	135 <sup>a</sup>	130 <sup>a</sup>	130	130 <sup>a</sup>	130 <sup>a</sup>
ST . . . . .	...	130 <sup>a</sup>	130	...	130 <sup>a</sup>
$F_{ty}$ , ksi:					
L . . . . .	125	120	120	120	120
LT . . . . .	125 <sup>a</sup>	120 <sup>a</sup>	120	120 <sup>a</sup>	120 <sup>a</sup>
ST . . . . .	...	120 <sup>a</sup>	120	...	120 <sup>a</sup>
$F_{cy}$ , ksi:					
L . . . . .	...	123	123	...	123
LT . . . . .	...	128	128	...	128
ST . . . . .	...	...	...	...	...
$F_{su}$ , ksi . . . . .	...	79	79	...	79
$F_{bru}$ , ksi:					
(e/D = 1.5) . . .	...	203	203	...	203
(e/D = 2.0) . . .	...	257	257	...	257
$F_{bry}$ , ksi:					
(e/D = 1.5) . . .	...	171	171	...	171
(e/D = 2.0) . . .	...	201	201	...	201
$e$ , percent:					
L . . . . .	10	10	10	8	8
LT . . . . .	10 <sup>a</sup>	10 <sup>a</sup>	10	8 <sup>a</sup>	8 <sup>a</sup>
ST . . . . .	...	10 <sup>a</sup>	8	...	8 <sup>a</sup>
$RA$ , percent:					
L . . . . .	25	25	20	15	15
LT . . . . .	20 <sup>a</sup>	20 <sup>a</sup>	20	15 <sup>a</sup>	15 <sup>a</sup>
ST . . . . .	...	15 <sup>a</sup>	15	...	15 <sup>a</sup>
$E$ , 10 <sup>3</sup> ksi . . . . .	16.9				
$E_c$ , 10 <sup>3</sup> ksi . . . . .	17.2				
$G$ , 10 <sup>3</sup> ksi . . . . .	6.2				
$\mu$ . . . . .	0.31				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.160				
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 5.4.1.0				

a Applicable providing LT or ST dimension is ≥ 2.500 inches.


**MIL-HDBK-5H**  
**1 December 1998**

**Table 5.4.1.0(g). Design Mechanical and Physical Properties of Ti-6Al-4V Titanium Alloy Casting**

Specification .....	AMS 4962	
Form .....	HIP Casting	
Temper .....	Annealed	
Thickness, in. ....	≤1.000	
Location within casting .....	Designated area	
Basis .....	A	B
Mechanical Properties:		
$F_{tu}$ , ksi .....	125 <sup>a</sup>	128
$F_{ty}$ , ksi .....	119	122
$F_{cy}$ , ksi .....	...	...
$F_{su}$ , ksi .....	...	...
$F_{bru}$ , ksi:		
(e/D = 1.5) .....	...	...
(e/D = 2.0) .....	...	...
$F_{bry}$ , ksi:		
(e/D = 1.5) .....	...	...
(e/D = 2.0) .....	...	...
$e$ , percent (S-basis) .....	5	...
$E$ , 10 <sup>3</sup> ksi .....	16.9	
$E_c$ , 10 <sup>3</sup> ksi .....	16.9	
$G$ , 10 <sup>3</sup> ksi .....	...	
$\mu$ .....	...	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> .....	...	
$C$ , Btu/(lb)(°F) .....	...	
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	...	
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	...	

a S-basis. The  $T_{99}$  value is 126.36 ksi.


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.4.1.0. Effect of temperature on the physical properties of Ti-6Al-4V alloy (wrought products).**



**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.4.1.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of annealed Ti-6Al-4V alloy (all wrought products).**

MIL-HDBK-5H  
1 December 1998




Figure 5.4.1.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of annealed Ti-6Al-4V alloy (all wrought products).




Figure 5.4.1.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of annealed Ti-6Al-4V alloy (all wrought products).

MIL-HDBK-5H  
1 December 1998




Figure 5.4.1.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of annealed Ti-6Al-4V alloy sheet and bar.






Figure 5.4.1.1.5. Effect of temperature on the elongation of annealed Ti-6Al-4V alloy sheet and bar.


**MIL-HDBK-5H****1 December 1998**

**Figure 5.4.1.1.6(a). Typical tensile stress-strain curves at cryogenic, room, and elevated temperatures for annealed Ti-6Al-4V alloy extrusion.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 5.4.1.1.6(b). Typical compressive stress-strain curves at room and elevated temperatures for annealed Ti-6Al-4V alloy extrusion.**



**Figure 5.4.1.1.6(c). Typical compressive tangent-modulus curves at room and elevated temperatures for annealed Ti-6Al-4V alloy extrusion.**




**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.4.1.1.6(d). Typical tensile stress-strain curves (full range) for annealed Ti-6Al-4V sheet at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.1.8(a). Best-fit S/N curves for unnotched Ti-6Al-4V annealed bar, longitudinal direction.**

Correlative Information for Figure 5.4.1.1.8(a)

Product Form: Bar, 1-1/4-inch diameter

Properties: TUS, ksi    TYS, ksi    Temp., °F  
                   137            129            RT

Specimen Details: Unnotched  
                               0.280-inch diameter

Surface Conditions:

0 ksi mean stress—32 RMS ground  
 47 ksi mean stress—100 RMS machined  
 70 ksi mean stress—32 RMS ground and  
                               100 RMS machined

Reference: 5.4.1.1.8(a)

Test Parameters:

Loading — Axial  
 Frequency — 1800 cpm  
 Temperature — RT  
 Environment — Air

No. of Heats/Lots: Not specified


Equivalent Strain Equation:

$$\begin{aligned}\log N_f &= 19.18 - 7.55 \log S_{\max} S_m = 0 \\ &= 5.70 - 0.94 \log (S_{\max} - 82.3), S_m = 47 \\ &= 7.08 - 2.18 \log (S_{\max} - 99.6), S_m = 70\end{aligned}$$

Sample Size = 134

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.1.8(b). Best-fit S/N curves for notched,  $K_t = 2.43$ , Ti-6Al-4V annealed bar, longitudinal direction.**

Correlative Information for Figure 5.4.1.1.8(b)

Product Form: Bar, 1-inch diameter

Properties: TUS, ksi    TYS, ksi    Temp., °F  
                   150            143            RT

Specimen Details: 60° V-notch  
                               0.025-inch notch radius  
                               0.260-inch test section  
                               diameter at notch

Surface Condition: RMS 100 machined

Reference: 5.4.1.1.8(a)

Test Parameters:

Loading — Axial  
 Frequency — 1800 cpm  
 Temperature — RT  
 Environment — Air

No. of Heats/Lots: Not specified

Equivalent Strain Equation:

$$\log N_f = 24.1 - 10.7 \log S_{eq}$$

$$S_{eq} = S_{max}(1-R)^{0.49}$$

Standard Error of Estimate = 0.677

Standard Deviation in Life = 0.920

$R^2 = 46\%$


Sample Size = 46

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.1.8(c). Best-fit S/N curves for unnotched annealed Ti-6Al-4V extrusion at room temperature, longitudinal direction.**

Correlative Information for Figure 5.4.1.1.8(c)

Product Form: Extrusion, 0.300- and  
0.560-inch thick

Properties:  $\frac{TUS, ksi}{143}$      $\frac{TYS, ksi}{127}$      $\frac{Temp., ^\circ F}{RT}$

Specimen Details: Unnotched  
1.50-inch gross width  
0.75-inch net width  
4.00-inch net section radius

Surface Conditions: RMS 63

Reference: 5.4.1.1.8(b)

Test Parameters:

Loading — Axial  
Frequency — 1800 cpm  
Temperature — RT  
Environment — Air

No. of Heats/Lots: Not specified

Equivalent Strain Equation:


$\log N_f = 24.8 - 9.6 \log (S_{max})$   
Standard Error of Estimate = 0.41  
Standard Deviation in Life = 0.81  
 $R^2 = 75\%$

Sample Size = 30

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.1.8(d). Best-fit S/N curves for notched,  $K_t = 2.8$ , annealed Ti-6Al-4V extrusion at room temperature, longitudinal direction.**

Correlative Information for Figure 5.4.1.1.8(d)

Product Form: Extrusion, 0.300- and 0.560-inch thick

Properties:  $\frac{TUS, ksi}{143}$      $\frac{TYS, ksi}{127}$      $\frac{Temp., ^\circ F}{RT}$

Specimen Details: Notched, hole type,  $K_t = 2.8$   
0.250-inch hole diameter  
1.50-inch gross width  
1.25-inch net width

Surface Conditions: RMS 63

Reference: 5.4.1.1.8(b)

Test Parameters:

Loading — Axial  
Frequency — 1800 cpm  
Temperature — RT  
Environment — Air

No. of Heats/Lots: Not specified

Equivalent Strain Equation:


$\log N_f = 14.8 - 5.8 \log (S_{eq} - 14)$   
 $S_{eq} = S_{max}(1-R)^{0.50}$   
Standard Error of Estimate = 0.41  
Standard Deviation in Life = 0.86  
 $R^2 = 78\%$

Sample Size = 40

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.1.8(e). Best-fit S/N curves for notched,  $K_t = 2.8$ , annealed Ti-6Al-4V extrusion at 400 and 600°F, longitudinal direction.**

Correlative Information for Figure 5.4.1.1.8(e)

Product Form: Extrusion, 0.300- and 0.560-inch thick

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	112	92	400
	101	77	600

Specimen Details: Notched, hole type,  $K_t = 2.8$   
0.250-inch hole diameter  
1.250-inch net width  
1.500-inch gross width

Surface Conditions: RMS 63

Reference: 5.4.1.1.8(b)

Test Parameters:

Loading — Axial

Frequency — 1800 cpm

Temperature — 400°F and 600°F

Environment — Air

No. of Heats/Lots: Not specified

Equivalent Strain Equation:

$$\log N_f = 21.9 - 9.18 \log (S_{eq})$$

$$S_{eq} = S_{max}(1-R)^{0.62}$$

Standard Error of Estimate = 0.50

Standard Deviation in Life = 0.89


$R^2 = 68\%$

Sample Size = 47

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.1.8(f). Best-fit S/N curves for unnotched Ti-6Al-4V annealed sheet, long transverse direction.**

Correlative Information for Figure 5.4.1.1.8(f)

Product Form: Sheet, 0.063, 0.070, 0.078-inch thick

Properties: TUS, ksi    TYS, ksi    Temp., °F  
147-152    136-143    RT

Specimen Details: Unnotched, 0.375-inch width

Surface Conditions: Machined to 32 RMS, lightly polished with 400 grit emery paper

Reference: 5.4.1.1.8(c)

Test Parameters:

Loading — Axial  
Frequency — 10-95 Hz  
Temperature — RT  
Environment — Air

No. of Heats/Lots: 3

Equivalent Strain Equation:

$$\log N_f = 12.59 - 4.89 \log (S_{eq} - 82.8)$$

$$S_{eq} = S_{max}(1-R)^{0.29}$$

Standard Deviation of Log Life = 0.62


Adjusted  $R^2 = 50.6\%$

Sample Size: 47

[Caution: The equivalent strain model may provide unrealistic life predictions for strain ratios and ranges beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.1.8(g). Best-fit S/N curves for notched,  $K_t = 3.0$ , Ti-6Al-4V annealed sheet, longitudinal and long transverse direction.**

Correlative Information for Figure 5.4.1.1.8(g)

Product Form: Sheet, 0.063, 0.070, 0.078-inch thick

Properties: TUS, ksi TYS, ksi Temp., °F  
145-152 136-146 RT

Specimen Details: Notched,  $K_t = 3.0$   
0.487-inch net section

Surface Conditions: Machined to 32 RMS,  
lightly polished with  
400 grit emery paper

Reference: 5.4.1.1.8(c)

Test Parameters:

Loading — Axial  
Frequency — 10-95 Hz  
Temperature — RT  
Environment — Air

No. of Heats/Lots: 3

Equivalent Strain Equation:


$\log N_f = 19.28 - 8.25 \log (S_{eq})$   
 $S_{eq} = S_{max}(1-R)^{0.57}$   
Standard Deviation of Log Life = 0.53  
Adjusted  $R^2 = 62.5\%$

Sample Size: 141

[Caution: The equivalent strain model may provide unrealistic life predictions for strain ratios and ranges beyond those represented above.]

MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.1.9. Fatigue-crack-propagation data for 0.250-inch-thick Ti-6Al-4V mill-annealed titanium alloy plate with buckling restraint. [Reference 5.4.1.1.9.]**

Specimen Thickness: 0.250 inch  
 Specimen Width: 9.6, 16, 32 inches  
 Specimen Type: M(T)

Environment: 50% R.H.  
 Temperature: RT  
 Orientation: L-T



MIL-HDBK-5H

1 December 1998




Figure 5.4.1.2.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of solution-treated and aged Ti-6Al-4V alloy (all products).

MIL-HDBK-5H  
1 December 1998




Figure 5.4.1.2.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of solution-treated and aged Ti-6Al-4V alloy (all products).




Figure 5.4.1.2.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of solution-treated and aged Ti-6Al-4V alloy (all products).



MIL-HDBK-5H  
1 December 1998




Figure 5.4.1.2.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of solution-treated and aged Ti-6Al-4V alloy.






Figure 5.4.1.2.6(a). Typical tensile stress-strain curves for solution-treated and aged Ti-6Al-4V alloy sheet at room and elevated temperatures.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 5.4.1.2.6(b). Typical compressive stress-strain curves for solution-treated and aged Ti-6Al-4V alloy sheet at room and elevated temperatures.**




**Figure 5.4.1.2.6(c). Typical compressive tangent-modulus curves for solution-treated and aged Ti-6Al-4V alloy sheet at room and elevated temperatures.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 5.4.1.2.6(d). Typical compressive stress-strain curves for solution-treated and aged Ti-6Al-4V alloy sheet at room and elevated temperatures.**




**Figure 5.4.1.2.6(e). Typical compressive tangent-modulus curves for solution-treated and aged Ti-6Al-4V alloy sheet at room and elevated temperatures.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.4.1.2.6(f). Typical tensile stress-strain curves for solution-treated and aged Ti-6Al-4V alloy plate at room and elevated temperatures.**



**Figure 5.4.1.2.6(g). Typical compressive stress-strain and tangent-modulus curves for solution-treated and aged Ti-6Al-4V alloy plate at room temperature.**

MIL-HDBK-5H  
1 December 1998





Figure 5.4.1.2.6(h). Typical tensile stress-strain curves (full range) for solution-treated and aged Ti-6Al-4V alloy at room and elevated temperatures.

MIL-HDBK-5H  
1 December 1998




- a This equation should only be used in the same temperature ranges indicated in the nomograph. Creep strains computed outside these temperature ranges may yield unreasonable values.

**Figure 5.4.1.2.7. Typical creep properties of solution-treated and aged Ti-6Al-4V alloy sheet for temperature range 600°F through 800°F.**



## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.2.8(a). Best-fit S/N curves for unnotched solution-annealed and aged Ti-6Al-4V sheet at room temperature, longitudinal direction.**

Correlative Information for Figure 5.4.1.2.8(a)

Product Forms: Sheet, 0.063-inch and 0.125-inch thick

Properties: TUS, ksi    TYS, ksi    Temp., °F  
166-177    153-167    RT

Specimen Details: Unnotched  
Ref. 5.4.3.2.8(a)  
Specimen details not available  
Ref. 5.4.3.2.8(b)  
1.000-inch net width  
8.000-inch test section radius  
3.00-inch gross width

Surface Conditions:

Ref. 5.4.3.2.8(a). Edges finished with a crocus cloth.

Ref. 5.4.3.2.8(b). Machined specimens were cleaned with methyl ethyl ketone. Edges polished with number 1 and 00 grit emery paper, recleaned with methyl ethyl ketone.

References: 5.4.1.2.8(a) and (b)

Test Parameters:

Loading — Axial

Frequency —

Ref. 5.4.3.2.8(a), not specified

Ref. 5.4.3.2.8(b), 1500-2200 cpm

Temperature — RT

Environment — Air

No. of Heats/Lots: 4

Equivalent Strain Equation:

$$\log N_f = 14.29 - 4.91 \log (S_{eq} - 30.6)$$

$$S_{eq} = S_{max} (1 - R)^{0.42}$$

Standard Error of Estimate = 0.48

Standard Deviation in Life = 0.90


$R^2 = 72\%$

Sample Size: 99

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.2.8(b). Best-fit S/N curves for notched,  $K_t = 2.8$ , solution-treated and aged Ti-6Al-4V sheet at room temperature, longitudinal direction.**

Correlative Information for Figure 5.4.1.2.8(b)

Product Forms: Sheet, 0.063-inch and  
0.125-inch thick

Properties: TUS, ksi    TYS, ksi    Temp., °F  
166-177    153-167    RT

Specimen Details: Notched, hole type,  $K_t = 2.8$   
0.9375-inch net width  
1.000-inch gross width  
8.000-inch test section radius  
0.0625-inch-diameter hole

Surface Conditions: Machined specimens were  
cleaned with methyl ethyl  
ketone. Edges polished  
with number 1 and 00 grit  
emery paper and recleaned  
with methyl ethyl ketone.

Reference: 5.4.1.2.8(b)

Test Parameters:

Loading — Axial  
Frequency — 1500-2200 cpm  
Temperature — RT  
Environment — Air

No. of Heats/Lots: 3

Equivalent Strain Equation:

$\log N_f = 10.87 - 3.80 \log (S_{eq} - 24.0)$   
 $S_{eq} = S_{max}(1-R)^{0.50}$   
Standard Error of Estimate = 0.43  
Standard Deviation in Life = 0.98  
 $R^2 = 81\%$


Sample Size: 87

[Caution: The equivalent stress model may  
provide unrealistic life predictions for stress ratios  
beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.2.8(c). Best-fit S/N curves for unnotched solution-treated and aged Ti-6Al-4V sheet at 400°F and 600°F, longitudinal direction.**

Correlative Information for Figure 5.4.1.2.8(c)

Product Forms: Sheet, 0.063-inch and  
0.125-inch thick

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	142-143	117-121	400°F
	125-134	102-113	600°F

Specimen Details: Unnotched  
Ref. 5.4.3.2.8(a)  
Specimen details not  
available  
Ref. 5.4.3.2.8(b)  
1.000-inch gross width  
8.000-inch test section radius  
3.00-inch gross width  
0.9375-inch net width

Surface Conditions:

Ref. 5.4.3.2.8(a). Edges finished with a crocus cloth  
Ref. 5.4.3.2.8(b). Machined specimens were  
cleaned with methyl ethyl ketone. Edges polished  
with number 1 and 00 grit emery paper, recleaned  
with methyl ethyl ketone.

References: 5.4.1.2.8(a) and (b)

Test Parameters:

Loading — Axial

Frequency —

Ref. 5.4.3.2.8(a), not specified

Ref. 5.4.3.2.8(b), 1500-2200 cpm

Temperature — 400°F and 600°F

Environment — Air

No. of Heats/Lots: 4

Equivalent Strain Equation:

$$\log N_f = 14.7 - 5.31 \log (S_{eq} - 21.8)$$

$$S_{eq} = S_{max}(1-R)^{0.54}$$

Standard Error of Estimate = 0.58

Standard Deviation in Life = 0.93


$R^2 = 61\%$

Sample Size: 163

[Caution: The equivalent stress model may provide  
unrealistic life predictions for stress ratios beyond  
those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.2.8(d). Best-fit S/N curves for notched,  $K_t = 2.8$ , solution-treated and aged Ti-6Al-4V sheet at 400 F and 600 F, longitudinal direction.**

Correlative Information for Figure 5.4.1.2.8(d)

Product Forms: Sheet, 0.063-inch and  
0.125-inch thick

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp., °F</u>
	142-143	117-121	400 °F
	129-133	103-105	600 °F

Specimen Details: Notched, hole type,  $K_t = 2.8$   
1.000-inch gross width  
8.000-inch test section radius  
0.0625-inch-diameter hole  
0.9375-inch net width

Surface Conditions: Machined specimens were  
cleaned with methyl ethyl  
ketone. Edges polished  
with number 1 and 00 grit  
emery paper and recleaned  
with methyl ethyl ketone.

Reference: 5.4.1.2.8(b)

Test Parameters:

Loading — Axial

Frequency — 1500-2200 cpm

Temperature — 400 °F and 600 °F

Environment — Air

No. of Heats/Lots: 3

Equivalent Stress Equation:

$\log N_f = 10.64 - 3.77 \log (S_{eq} - 20.9)$

$S_{eq} = S_{max}(1-R)^{0.51}$

Standard Error of Estimate = 0.42

Standard Deviation in Life = 0.93


$R^2 = 80\%$

Sample Size: 175

[Caution: The equivalent stress model may  
provide unrealistic life predictions for stress ratios  
beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.2.8(e). Best-fit S/N curves for unnotched solution-treated and aged Ti-6Al-4V sheet at 800°F and 900°F, longitudinal direction.**

Correlative Information for Figure 5.4.1.2.8(e)

Product Forms: Sheet, 0.063-inch and  
0.125-inch thick

Properties: TUS, ksi    TYS, ksi    Temp., °F  
120-125    93-96    800°F  
110-111    84-86    900°F

Specimen Details: Unnotched  
1.000-inch gross width  
8.000-inch test section radius  
3.00-inch gross width  
0.9375-inch net width

Surface Conditions: Machined specimens were  
cleaned with methyl ethyl  
ketone. Edges polished  
with number 1 and 00 grit  
emery paper and recleaned  
with methyl ethyl ketone.

References: 5.4.1.2.8(b)

Test Parameters:

Loading — Axial  
Frequency — 1500-2200 cpm  
Temperature — 800°F and 900°F  
Environment — Air

No. of Heats/Lots: 3

Equivalent Stress Equation:


$\log N_f = 17.34 - 6.61 \log (S_{eq})$   
 $S_{eq} = S_{max}(1-R)^{0.50}$   
Standard Error of Estimate = 0.58  
Standard Deviation in Life = 0.99  
 $R^2 = 73\%$

Sample Size: 154

[Caution: The equivalent stress model may  
provide unrealistic life predictions for stress ratios  
beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.2.8(f). Best-fit S/N curves for notched,  $K_t = 2.8$ , solution-treated and aged Ti-6Al-4V sheet at 800°F and 900°F, longitudinal direction.**

Correlative Information for Figure 5.4.1.2.8(f)

Product Forms: Sheet, 0.063-inch and  
0.125-inch thick

Properties: TUS, ksi    TYS, ksi    Temp., °F  
120-124    93-96    800°F  
110-111    84-88    900°F

Specimen Details: Notched, hole type,  $K_t = 2.8$   
1.000-inch gross width  
8.000-inch test section radius  
0.0625-inch-diameter hole  
0.9375-inch net width

Surface Conditions: Machined specimens were  
cleaned with methyl ethyl  
ketone. Edges polished  
with number 1 and 00 grit  
emery paper and recleaned  
with methyl ethyl ketone.

Reference: 5.4.1.2.8(b)

Test Parameters:

Loading — Axial  
Frequency — 1500-2200 cpm  
Temperature — 800°F and 900°F  
Environment — Air

No. of Heats/Lots: 3

Equivalent Stress Equation:


$\log N_f = 11.75 - 4.45 \log (S_{eq} - 15.0)$   
 $S_{eq} = S_{max}(1-R)^{0.62}$   
Standard Error of Estimate = 0.43  
Standard Deviation in Life = 0.96  
 $R^2 = 79\%$

Sample Size: 173

[Caution: The equivalent stress model may  
provide unrealistic life predictions for stress ratios  
beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.2.8(g). Best-fit S/N curves for unnotched solution-treated and aged Ti-6Al-4V plate at room temperature, longitudinal direction.**

Correlative Information for Figure 5.4.1.2.8(g)

Product Form: Plate, 1.00-inch

Test Parameters:

Properties: TUS, ksi    TYS, ksi    Temp., °F  
                  158            149            RT  
                  155            145            RT

Loading — Axial  
 Frequency — 1,800-18,000 cpm  
 Temperature — RT  
 Environment — Air

Specimen Details: Unnotched, rounded

No. of Heats/Lots: 2

Uniform

Equivalent Stress Equation:

Gage    Hourglass  
 ---       3.25    Reduced section radius of  
                  curvature, inch  
 0.195    0.250    Diameter, inch

$\log N_f = 24.6 - 9.35 \log (S_{eq})$   
 $S_{eq} = S_{max}(1-R)^{0.48}$   
 Standard Error of Estimate = 0.39  
 Standard Deviation in Life = 0.83  
 $R^2 = 79\%$

Surface Condition: Longitudinally polished with  
 No. 000 emery paper remov-  
 ing all circumferential marks.


Sample Size: 49

References: 5.4.1.2.8(c) and (d)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.2.8(h). Best-fit S/N curves for unnotched solution-treated and aged Ti-6Al-4V plate at room temperature, long transverse direction.**

Correlative Information for Figure 5.4.1.2.8(h)

Product Form: Plate, 0.50-inch thick

Properties: TUS, ksi    TYS, ksi    Temp., °F  
173            164            RT

Specimen Details: Unnotched, flat hourglass  
10-inch reduced section radius of curvature  
1-inch net section width  
0.156-inch net section thickness

Surface Conditions: Machined to 63 RMS

Reference: 5.4.1.2.8(d)

Test Parameters:

Loading — Axial

Frequency — Unspecified

Temperature — RT

Environment — Air

No. of Heats/Lots: 1

Equivalent Stress Equation:

$\log N_f = 47.9 - 20.2 \log (S_{eq})$

Standard Error of Estimate = 0.33

Standard Deviation in Life = 0.89

$R^2 = 87\%$


Sample Size: 14

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 5.4.1.2.8(i). Best-fit S/N curves for notched,  $K_t = 3.0$ , solution-treated and aged Ti-6Al-4V plate at room temperature, longitudinal direction.**

Correlative Information for Figure 5.4.1.2.8(i)

Product Form: Plate, 1.025 and 0.750-inch thick

Test Parameters:

Properties: TUS, ksi    TYS, ksi    Temp., °F  
                   155            145            RT  
                                       (unnotched)  
                   187            —            RT  
                                       (notched)

Loading — Axial  
 Frequency — 1,800-18,000 cpm  
 Temperature — RT  
 Environment — Air

No. of Heats/Lots: 2

Specimen Details: Circumferentially notched,  
 $K_t = 3.0$

Equivalent Stress Equation:

Ref. (c)    Ref. (e)  
 0.195    0.430    Gross diameter, inch  
 0.136    0.300    Net section, inch  
 0.005    0.016    Notch radius, r, inch  
 60°    60°    Flank angle,  $\omega$

$\log N_f = 14.4 - 5.51 \log (S_{eq})$   
 $S_{eq} = S_{max}(1-R)^{0.58}$   
 Standard Error of Estimate = 0.24  
 Standard Deviation of Life = 0.81  
 $R^2 = 92\%$

Surface Condition:

Ref. (c) notch made with light finishing cuts  
 Ref. (e) notch polished in lathe

Sample Size: 31

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

References: 5.4.1.2.8(c) and (e)

**MIL-HDBK-5H****1 December 1998****5.4.2 Ti-6Al-6V-2Sn**

**5.4.2.0 Comments and Properties** — Ti-6Al-6V-2Sn alloy is similar to Ti-6Al-4V alloy in many respects but has higher strength and deeper hardenability (i.e., use of thicker sections possible). A variety of mill product forms are available including billet, bar, plate, sheet, strip, and extrusions and these may be used in either the annealed or the solution-treated and aged (STA) conditions. The maximum strength is developed in the STA condition in sections up to about 2 inches in thickness.

*Manufacturing Considerations* — To ensure optimum mechanical properties in Ti-6Al-6V-2Sn forgings, at least 50 percent reduction should be done at temperatures below the beta transus temperature (i.e., <1735°F). The Ti-6Al-6V-2Sn is readily formable in the annealed condition. In the sheet or plate forms the alloy is generally used in the annealed condition, although the alloy is capable of heat treatment to higher strength levels with some loss of toughness. When the Ti-6Al-6V-2Sn sheet and plate are hot formed at any temperature over 1000°F and air cooled, the material should be stabilized by reheating to 1000°F followed by air cooling. Welding is not usually recommended although limited weld joining operations are possible if the assembly is amenable to post-weld thermal treatments for the restoration of ductility to the weld and heat-affected zones.

*Environmental Considerations* — While the short-time elevated-temperature properties and stability of Ti-6Al-6V-2Sn alloy are good, creep strength above 650°F and long-term stability at temperatures above 800°F are not. The material ages during prolonged exposures around 800°F and above, particularly when under stress. Oxidation resistance of Ti-6Al-6V-2Sn is satisfactory in short-term exposures to 1000°F. The material is nearly equivalent to the Ti-6Al-4V alloy in terms of hot-salt and aqueous chloride solution stress-corrosion resistance. Under certain conditions, titanium, when in contact with cadmium, silver, mercury, or certain of their compounds, may become embrittled. Refer to MIL-S-5002 and MIL-STD-1568 for restrictions concerning applications with titanium in contact with these metals or their compounds.

*Heat Treatment* — This alloy is commonly specified in either the annealed condition or the solution-treated and aged condition. The solution-treated and aged condition is as follows:

Solution treat at 1625°F for ½ to 1 hour, quench in water.

Age at 1000 ± 25°F for 4 to 8 hours, air cool.

*Specifications and Properties* — Material specifications for Ti-6Al-6V-2Sn are shown in Table 5.4.2.0(a). Room-temperature mechanical properties are shown in Tables 5.4.2.0(b) through (e). The effect of temperature on physical properties is shown in Figure 5.4.2.0.

**5.4.2.1 Annealed Condition** — Elevated temperature curves for annealed condition are shown in Figures 5.4.2.1.1(a) through 5.4.2.1.3(b). Typical stress-strain and tangent-modulus curves for this condition are shown in Figures 5.4.2.1.6(a) and (b). A typical full range tensile stress-strain curve is shown in Figure 5.4.2.1.6(c). Unnotched and notched fatigue data are presented in Figures 5.4.2.1.8(a) and (b).

**5.4.2.2 Solution-Treated and Aged Condition** — Elevated temperature curves are shown in Figures 5.4.2.2.1 and 5.4.2.2.2.



**MIL-HDBK-5H****1 December 1998****Table 5.4.2.0(a). Material Specifications for Ti-6Al-6V-2Sn**

Specification	Form
MIL-T-9046	Sheet, strip, and plate
AMS 4979	Bar and forging
MIL-T-81556	Extruded bar and shapes
AMS 4971	Bar and forging
AMS 4978	Bar and forging
AMS 4918	Sheet, strip, and plate

**Table 5.4.2.0(b). Design Mechanical and Physical Properties of Ti-6Al-6V-2Sn Sheet, Strip, and Plate**

Specification .....	MIL-T-9046, Comp. AB-3, and AMS 4918							MIL-T-9046, Comp. AB-3			
Form .....	Sheet, strip, and plate										
Condition .....	Annealed							Solution treated and aged			
Thickness, in. ....	<0.1875		0.1875-0.500	0.501-1.000	1.001-1.500	1.501-2.000	2.001-4.000	≤0.1875	0.1875-1.500	1.501-2.500	2.501-4.000
Basis .....	A	B	S	S	S	S	S	S	S	S	S
Mechanical Properties:											
$F_{tu}$ , ksi:											
L .....	155	160	150	150	150	150	145	170	170	160	150
LT .....	155	150	150	150	150	150	145	170	170	160	150
$F_{ty}$ , ksi:											
L .....	145 <sup>a</sup>	152	140	140	140	140	135	160	160	150	140
LT .....	145 <sup>a</sup>	154	140	140	140	140	135	160	160	150	140
$F_{cy}$ , ksi:											
L .....	...	...	139	142	146	148	...	...	170	...	...
LT .....	...	...	151	147	141	136	...	...	170	...	...
$F_{su}$ , ksi .....	...	...	91	93	95	95	...	...	101	...	...
$F_{bru}$ , ksi:											
(e/D = 1.5) .....	...	...	236	241	247	250	...	...	264	...	...
(e/D = 2.0) .....	...	...	294	303	312	317	...	...	324	...	...
$F_{bry}$ , ksi:											
(e/D = 1.5) .....	...	...	193	196	199	202	...	...	237	...	...
(e/D = 2.0) .....	...	...	215	223	234	240	...	...	266	...	...
$e$ , percent (S-basis):											
L .....	10 <sup>b</sup>	...	10	10	10	10	8	8	8	6	6
LT .....	8 <sup>b</sup>	...	8	8	8	8	6	6	8	6	6
$E$ , 10 <sup>3</sup> ksi .....	16.0										
$E_c$ , 10 <sup>3</sup> ksi .....	16.4										
$G$ , 10 <sup>3</sup> ksi .....	6.2										
$\mu$ .....	0.31										
Physical Properties:											
$\omega$ , lb/in. <sup>3</sup> .....	0.164										
$C$ , $K$ , and $\alpha$ .....	See Figure 5.4.2.0										

a The rounded  $T_{99}$  values are higher than specification values as follows:  $F_{ty}$  (L) = 147 ksi,  $F_{ty}$  (LT) = 149 ksi.

b Longitudinal <0.025 in. = 8 percent. Long transverse < 0.025 in. = 6 percent.

**MIL-HDBK-5H****1 December 1998****Table 5.4.2.0(c). Design Mechanical and Physical Properties of Ti-6Al-6V-2Sn Bar**

Specification . . . . .	AMS 4978						AMS 4971 and AMS 4979			
Form . . . . .	Bar						Bar and forging			
Condition . . . . .	Air-cool annealed <sup>a</sup>						Solution treated and aged			
Thickness or diameter, in. . . . .	≤1.500		1.501-3.000		3.001-4.000		≤1.000	1.001-2.000	2.001-3.000	3.001-4.000
Basis . . . . .	A	B	A	B	A	B	S	S	S	S
Mechanical Properties:										
<i>F<sub>tu</sub></i> , ksi:										
L . . . . .	144	150	139	145	136	142	175	170	155	150
LT <sup>b</sup> . . . . .	147	152	143	148	140	145	175	170	155	150
ST <sup>b</sup> . . . . .	...	...	...	...	...	...	...	...	155	150
<i>F<sub>ty</sub></i> , ksi:										
L . . . . .	131	138	126	132	123	129	160	155	145	140
LT <sup>b</sup> . . . . .	136	141	131	136	127	132	160	155	145	140
ST <sup>b</sup> . . . . .	...	...	...	...	...	...	...	...	145	140
<i>F<sub>cy</sub></i> , ksi:										
L . . . . .	...	...	...	...	...	...	...	...	...	...
LT <sup>b</sup> . . . . .	...	...	...	...	...	...	...	...	...	...
ST <sup>b</sup> . . . . .	...	...	...	...	...	...	...	...	...	...
<i>F<sub>su</sub></i> , ksi . . . . .	...	...	...	...	...	...	...	...	...	...
<i>F<sub>bru</sub></i> <sup>c</sup> , ksi:										
(e/D = 1.5) . . . . .	...	...	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...	...	...	...	...	...
<i>F<sub>bry</sub></i> <sup>c</sup> , ksi:										
(e/D = 1.5) . . . . .	...	...	...	...	...	...	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...	...	...	...	...	...
<i>e</i> , percent (S-basis):										
L . . . . .	10	...	10	...	10	...	8	8	8	8
LT <sup>b</sup> . . . . .	8	...	8	...	8	...	6	6	6	6
ST <sup>b</sup> . . . . .	...	...	8	...	8	...	...	...	6	6
<i>RA</i> , percent (S-basis):										
L . . . . .	20	...	20	...	15	...	20	20	20	20
LT <sup>b</sup> . . . . .	15	...	15	...	15	...	15	15	15	15
ST <sup>b</sup> . . . . .	...	...	15	...	15	...	...	...	15	15
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	16.0									
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	16.4									
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	6.2									
<i>μ</i> . . . . .	0.31									
Physical Properties:										
<i>ω</i> , lb/in. <sup>3</sup> . . . . .	0.164									
<i>C</i> , <i>K</i> , and <i>α</i> . . . . .	See Figure 5.4.2.0									

a 1300 to 1350°F for 1-3 hours, air cool to room temperature.

b Applicable, providing LT or ST dimension is ≥ 2.500 inches.

**MIL-HDBK-5H****1 December 1998****Table 5.4.2.0(d). Design Mechanical and Physical Properties of Ti-6Al-6V-2Sn Forging**

Specification . . . . .	AMS 4978	
Form . . . . .	Forging	
Condition . . . . .	Annealed	
Thickness, or diameter, in. . . . .	≤2.000	2.001-4.000
Basis . . . . .	S	S
Mechanical Properties:		
$F_{tu}$ , ksi:		
L . . . . .	150	145
LT <sup>a</sup> . . . . .	150	145
ST <sup>a</sup> . . . . .	...	145
$F_{ty}$ , ksi:		
L . . . . .	140	135
LT <sup>a</sup> . . . . .	140	135
ST <sup>a</sup> . . . . .	...	135
$F_{cy}$ , ksi:		
L . . . . .	...	...
LT <sup>a</sup> . . . . .	...	...
ST <sup>a</sup> . . . . .	...	...
$F_{su}$ , ksi . . . . .	...	...
$F_{bru}$ , ksi:		
(e/D=1.5) . . . . .	...	...
(e/D=2.0) . . . . .	...	...
$F_{bry}$ , ksi:		
(e/D=1.5) . . . . .	...	...
(e/D=2.0) . . . . .	...	...
$e$ , percent:		
L . . . . .	10	10
LT <sup>a</sup> . . . . .	8	8
ST <sup>a</sup> . . . . .	...	7
$RA$ , percent:		
L . . . . .	20	20
LT <sup>a</sup> . . . . .	15	15
ST <sup>a</sup> . . . . .	15	15
$E$ , 10 <sup>3</sup> ksi . . . . .	16.0	
$E_c$ , 10 <sup>3</sup> ksi . . . . .	16.4	
$G$ , 10 <sup>3</sup> ksi . . . . .	6.2	
$\mu$ . . . . .	0.31	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.164	
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 5.4.2.0	

a Applicable, providing LT or ST dimension is ≥ 2.500 inches.

**MIL-HDBK-5H****1 December 1998****Table 5.4.2.0(e). Design Mechanical and Physical Properties of Ti-6Al-6V-2Sn Extruded Bar and Shapes**

Specification .....	MIL-T-81556, Comp. AB-3							
Form .....	Extruded bar and shapes							
Condition .....	Annealed				Solution treated and aged			
Thickness or diameter, in. .	≤2.000	2.001-3.000	3.001-4.000	0.188-0.500	0.501-1.500	1.501-2.500	2.501-4.000	
Basis .....	A	B	S	S	S	S	S	S
Mechanical Properties:								
$F_{tu}$ , ksi:								
L .....	142	148	145	140	170	165	160	150
LT .....	141	148	145	140	170	165	160	150
$F_{ty}$ , ksi:								
L .....	129	135	135	130	160	155	150	140
LT .....	128	135	135	130	160	155	150	140
$F_{cy}$ , ksi:								
L .....	137	144	140	135	165	160	155	145
LT .....	136	142	140	135	165	160	155	145
$F_{su}$ , ksi .....	93	97	...	...	...	...	...	...
$F_{bru}^a$ , ksi:								
(e/D=1.5) .....	218	229	...	...	...	...	...	...
(e/D=2.0) .....	268	281	...	...	...	...	...	...
$F_{bry}^a$ , ksi:								
(e/D=1.5) .....	196	203	...	...	...	...	...	...
(e/D=2.0) .....	227	235	...	...	...	...	...	...
$e$ , percent (S-basis):								
L .....	10	...	10	10	8	8	8	8
LT .....	8	...	8	8	6	6	6	6
$RA$ , percent (S-basis):								
L .....	20	...	20	20	15	15	15	15
LT .....	15	...	15	15	12	12	12	12
$E$ , $10^3$ ksi .....	16.0							
$E_c$ , $10^3$ ksi .....	16.4							
$G$ , $10^3$ ksi .....	6.2							
$\mu$ .....	0.31							
Physical Properties:								
$\omega$ , lb/in. <sup>3</sup> .....	0.164							
$C$ , $K$ , and $\alpha$ .....	See Figure 5.4.2.0							

a Bearing values are "dry pin" values per Section 1.4.7.1.

## MIL-HDBK-5H

1 December 1998




Figure 5.4.2.0. Effect of temperature on the physical properties of Ti-6Al-6V-2Sn alloy.

MIL-HDBK-5H  
1 December 1998





Figure 5.4.2.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of annealed Ti-6Al-6V-2Sn extrusion.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.4.2.1.1(b). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of annealed Ti-6Al-6V-2Sn plate.**



## MIL-HDBK-5H

1 December 1998





Figure 5.4.2.1.2(a). Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of annealed Ti-6Al-6V-2Sn extrusion.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.4.2.1.2(b). Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of annealed Ti-6Al-6V-2Sn plate.**

MIL-HDBK-5H  
1 December 1998




Figure 5.4.2.1.3(a). Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of annealed Ti-6Al-6V-2Sn extrusion.



## MIL-HDBK-5H

1 December 1998






Figure 5.4.2.1.3(b). Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of annealed Ti-6Al-6V-2Sn plate.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 5.4.2.1.6(a). Typical compressive stress-strain and tangent-modulus curves at room temperature for annealed Ti-6Al-6V-2Sn extrusion.**



**Figure 5.4.2.1.6(b). Typical tensile stress-strain curve at room temperature for annealed Ti-6Al-6V-2Sn extrusion.**


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.4.2.1.6(c). Typical tensile stress-strain curve (full range) for annealed Ti-6Al-6V-2Sn sheet at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.2.1.8(a). Best-fit S/N curves for annealed Ti-6Al-6V-2Sn plate and die forging,  $K_t = 1.0$ , longitudinal direction.**

Correlative Information for Figure 5.4.2.1.8(a)

Product Form: Plate, 1.57-inch thick; die forging, thickness not specified

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp, °F</u>
	154.5	148.5	RT
	159.9	151.5	RT

Specimen Details:

Unnotched  
0.195-inch diameter  
Unspecified diameter from forging

Surface Condition:

RMS 32  
Unspecified from forging

References: 5.4.1.2.8(c) and 5.4.2.1.8

Test Parameters:

Loading—Axial  
Frequency—Unspecified  
Temperature—RT  
Atmosphere—Air

No. of Heats/Lot: 3

Equivalent Stress Equation:

$$\log N_f = 20.90 - 8.10 \log (S_{eq})$$

$$S_{eq} = S_a + 0.41 S_m$$

$$\text{Standard deviation in } \log(\text{Life}) = 23.5 (1/S_{eq})$$


$$\text{Adjusted } R^2 = 89\%$$

Sample Size = 38

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.4.2.1.8(b). Best-fit S/N curves for annealed Ti-6Al-6V-2Sn plate,  $K_t = 3.0$ , longitudinal direction.**

Correlative Information for Figure 5.4.2.1.8(b)

Product Form: Plate, 1.57-inch thick

Properties:  $T_{US}$ , ksi     $T_{YS}$ , ksi     $Temp.$ , °F  
                   154.6        148.5        RT

Specimen Details:

V-Groove,  $K_t = 3.0$   
 0.195-inch gross diameter  
 0.136-inch net diameter  
 0.005-inch root radius  
 60° flank angle

Surface Condition: RMS 32

References: 5.4.1.2.8(c)

Test Parameters:

Loading—Axial  
 Frequency—Unspecified  
 Temperature—RT  
 Atmosphere—Air

No. of Heats/Lot: 1

Equivalent Stress Equation:

$$\log N_f = 8.31 - 2.73 \log (S_{eq} - 16.9)$$

$$S_{eq} = S_a + 0.37 S_m$$

$$\text{Standard deviation in } \log(\text{Life}) = 8.87 (1/S_{eq})$$

$$\text{Adjusted } R^2 = 92\%$$

$$\text{Sample Size} = 32$$

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



MIL-HDBK-5H  
1 December 1998




Figure 5.4.2.2.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of solution-treated and aged Ti-6Al-6V-2Sn plate.




Figure 5.4.2.2.2. Effect of temperature on compressive yield strength ( $F_{cy}$ ) of solution-treated and aged Ti-6Al-6V-2Sn plate.

## 5.5 BETA, NEAR-BETA, AND METASTABLE-BETA TITANIUM ALLOYS

There is no clear-cut definition for beta titanium alloys. Conventional terminology usually refers to near-beta alloys and metastable-beta alloys as classes of beta titanium alloys. A near-beta alloy is generally one which has appreciably higher beta stabilizer content than a conventional alpha-beta alloy such as Ti-6Al-4V, but is not quite sufficiently stabilized to readily retain an all-beta structure with an air cool of thin sections. For such alloys, a water quench even of thin sections is required. Due to the marginal stability of the beta phase in these alloys, they are primarily solution treated below the beta transus to produce primary alpha phase which in turn results in an enriched, more stable beta phase. This enriched beta phase is more suitable for aging. The Ti-10V-2Fe-3Al alloy is an example of a near-beta alloy.

On the other hand, the metastable-beta alloys are even more heavily alloyed with beta stabilizers than near-beta alloys and, as such, readily retain an all-beta structure upon air cooling of thin sections. Due to the added stability of these alloys, it is not necessary to heat treat below the beta transus to enrich the beta phase. Therefore, these alloys do not normally contain primary alpha since they are usually solution treated above the beta transus. These alloys are termed “metastable” because the resultant beta phase is not truly stable—it can be aged to precipitate alpha for strengthening purposes. Alloys such as Ti-15-3, B120VCA, Beta C, and Beta III are considered metastable-beta alloys.

Unfortunately, the classification of an alloy as either near-beta or metastable beta is not always obvious. In fact, the “metastable” terminology is not precise since a near-beta alloy is also metastable—i.e., it also decomposes to alpha plus beta upon aging.

There is one obvious additional category of beta alloys—the stable beta alloys. These alloys are so heavily alloyed with beta stabilizers that the beta phase will not decompose to alpha plus beta upon subsequent aging. There are no such alloys currently being produced commercially. An example of such an alloy is Ti-30Mo.

The interest in beta alloys stems from the fact that they contain a high volume fraction of beta phase which can be subsequently hardened by alpha precipitation. Thus, these alloys can generate quite high-strength levels (in excess of 200 ksi) with good ductilities. Also, such alloys are much more deep hardenable than alpha-beta alloys such as Ti-6Al-4V. Finally, many of the more heavily alloyed beta alloys exhibit excellent cold formability and as such offer attractive sheet metal forming characteristics.

### 5.5.1 Ti-13V-11Cr-3Al

**5.5.1.0 Comments and Properties** — Ti-13V-11Cr-3Al is a heat-treatable alloy possessing good workability and toughness in the annealed condition and high strength in the heat-treated condition. It is noted for its exceptional ability to harden in heavy sections (up to 6-inch diameter or greater) to tensile strength of 170 ksi  $F_{tu}$ .

*Manufacturing Considerations* — This alloy possesses very good formability at room temperature; stretch forming is usually conducted at 500°F. Ti-13V-11Cr-3Al is readily fusion or spot welded. Arc-welded joints are very ductile in the as-welded condition, but have low strengths.

*Environmental Considerations* — Ti-13V-11Cr-3Al is stable for times up to 1000 hours in the annealed condition at 550°F and in the solution treated and aged condition up to 600°F. Prolonged exposure above these temperatures may result in ductility losses. If welding is employed, the stability of the weld should be investigated under the particular exposure conditions to be encountered. While the material is not noted for good creep performance, Ti-13V-11Cr-3Al has exceptional short-time strength at temperatures to 1200°F and above. Oxidation resistance is satisfactory at such temperatures for short-time exposure and for long-time exposure at the lower elevated temperatures. Hot-salt stress corrosion has been shown to be possible in this

**MIL-HDBK-5H****1 December 1998**

alloy at temperatures as low as 500°F in highly stressed applications (e.g., rivet heads). It is generally thought that the material is moderately susceptible to aqueous chloride solution stress corrosion. Ti-13V-11Cr-3Al is not noted for good fracture toughness in the aged or high-strength condition and is not recommended in any condition for cryogenic temperature applications. Under certain conditions, titanium, when in contact with cadmium, silver, mercury, or certain of their compounds, may become embrittled. Refer to MIL-S-5002 and MIL-STD-1568 for restrictions concerning applications with titanium in contact with these metals or their compounds.

*Heat Treatment* — This alloy is commonly specified in either the annealed condition or in the fully heat-treated condition. The specified fully heat-treated, or solution-treated and aged, condition is as follows:

Solution treat at 1450°F for 15 to 60 minutes, air cool (water quench if material is over 2 inches thick).

Age at 900°F for 2 to 60 hours, dependent on strength level. (Note: typical aging time to achieve  $F_{tu} = 170$  ksi is 24 to 36 hours.)

*Specifications and Properties* — Material specifications for Ti-13V-11Cr-3Al are shown in Table 5.5.1.0(a). Room-temperature mechanical and physical properties for Ti-13V-11Cr-3Al are shown in Table 5.5.1.0(b). The effect of temperature on physical properties is shown in Figure 5.5.1.0.

**Table 5.5.1.0(a). Material Specifications for Ti-13V-11Cr-3Al**

Specification	Form
MIL-T-9046	Sheet, strip, and plate
MIL-T-9047	Bar

**5.5.1.1 Annealed Condition** — Elevated temperature curves for annealed Ti-13V-11Cr-3Al are shown in Figures 5.5.1.1.1 through 5.5.1.1.4. Typical tensile stress-strain curves for annealed material at temperatures ranging from room temperature to 1000°F are shown in Figure 5.5.1.1.6. Unnotched and notched fatigue data at room and elevated temperatures for annealed sheet are shown in Figures 5.5.1.1.8(a) through (d).

**5.5.1.2 Solution-Treated and Aged Condition** — Elevated temperature curves for solution-treated and aged Ti-13V-11Cr-3Al are shown in Figures 5.5.1.2.1 through 5.5.2.1.4. Typical tensile stress-strain curves at various temperatures are shown in Figure 5.5.1.2.6. Unnotched fatigue data at room and elevated temperatures for solution-treated and aged sheet are shown in Figures 5.5.1.2.8(a) through (c).

**MIL-HDBK-5H****1 December 1998****Table 5.5.1.0(b). Design Mechanical and Physical Properties of Ti-13V-11Cr-3Al**

Specification . . . . .	MIL-T-9046, Comp. B-1		MIL-T-9047		
Form . . . . .	Sheet, strip, and plate		Bar		
Condition . . . . .	Annealed		Solution treated and aged	Annealed	Solution treated and aged
Thickness or diameter, in.	0.012-0.049	0.050-4.000	≤4.000	≤7.000 <sup>a</sup>	≤4.000 <sup>a</sup>
Basis . . . . .	S	S	S	S	S
Mechanical Properties:					
$F_m$ , ksi:					
L . . . . .	132	125	170	125	170
LT . . . . .	132	125	170	125 <sup>c</sup>	170 <sup>c</sup>
ST . . . . .	...	125	170	125 <sup>c</sup>	170 <sup>c</sup>
$F_{ty}$ , ksi:					
L . . . . .	126	120	160	120	160
LT . . . . .	126	120	160	120 <sup>c</sup>	160 <sup>c</sup>
ST . . . . .	...	120	160	120 <sup>c</sup>	160 <sup>c</sup>
$F_{cy}$ , ksi:					
L . . . . .	...	120	162	...	...
LT . . . . .	...	120	162	...	...
ST . . . . .	...	120	162	...	...
$F_{su}$ , ksi . . . . .	...	92	105	...	...
$F_{bru}$ , ksi:					
(e/D = 1.5) . . . . .	...	207	248	...	...
(e/D = 2.0) . . . . .	...	270	313	...	...
$F_{bry}$ , ksi:					
(e/D = 1.5) . . . . .	...	169	217	...	...
(e/D = 2.0) . . . . .	...	200	247	...	...
$e$ , percent:					
L . . . . .	8	10	4 <sup>b</sup>	10	6
LT . . . . .	8	10	4 <sup>b</sup>	10 <sup>c</sup>	2 <sup>c</sup>
ST . . . . .	...	10	4 <sup>b</sup>	10 <sup>c</sup>	2 <sup>c</sup>
RA, percent:					
L . . . . .	...	...	...	25	10
LT . . . . .	...	...	...	25 <sup>c</sup>	5 <sup>c</sup>
ST . . . . .	...	...	...	25 <sup>c</sup>	5 <sup>c</sup>
$E$ , 10 <sup>3</sup> ksi . . . . .	14.5		15.5	14.5	15.5
$E_c$ , 10 <sup>3</sup> ksi . . . . .	...		...	...	...
$G$ , 10 <sup>3</sup> ksi . . . . .	...		...	...	...
$\mu$ . . . . .	...		...	...	...
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.174				
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 5.5.1.0				

a Maximum of 16 square-inch cross-sectional area.

b Thickness 0.025 inch and above: 3 percent below 0.025 inch.

c Applicable, providing LT or ST dimension is  $\geq 3.000$  inches.

MIL-HDBK-5H

1 December 1998




Figure 5.5.1.0. Effect of temperature on the physical properties of Ti-13V-11Cr-3Al alloy.



MIL-HDBK-5H  
1 December 1998




Figure 5.5.1.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of annealed Ti-13V-11Cr-3Al alloy sheet.




Figure 5.5.1.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of annealed Ti-13V-11Cr-3Al alloy sheet.

## MIL-HDBK-5H

1 December 1998




Figure 5.5.1.1.3(a). Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) of annealed Ti-13V-11Cr-3Al alloy sheet.




Figure 5.5.1.1.3(b). Effect of temperature on the bearing yield strength ( $F_{bry}$ ) of annealed Ti-13V-11Cr-3Al alloy sheet.

MIL-HDBK-5H  
1 December 1998




Figure 5.5.1.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of annealed Ti-13V-11Cr-3Al alloy sheet.





Figure 5.5.1.1.6. Typical tensile stress-strain curves for annealed Ti-13V-11Cr-3Al alloy sheet at room and elevated temperatures.



## MIL-HDBK-5H

1 December 1998



**Figure 5.5.1.1.8(a). Best-fit S/N curves for unnotched, annealed Ti-13V-11Cr-3Al alloy sheet, longitudinal direction.**

Correlative Information for Figure 5.5.1.1.8(a)

Product Form: Sheet, 0.043-inch thick

Properties: TUS, ksi TYS, ksi Temp, °F  
138.50 132.80 RT

Specimen Details: Unnotched, 0.30-inch wide

Surface Condition: As machined, edges  
polished with emery paper.

Reference: 5.5.1.1.8

Test Parameters:

Loading—Axial

Frequency—3600 cpm

Temperature—RT

Atmosphere—Air

No. of Heats/Lot: Not specified

Equivalent Stress Equation:

$$\log N_f = 10.15 - 3.41 \log (S_{eq} - 52.2)$$

$$S_{eq} = S_{max} (1 - R)^{0.97}$$

Standard Error of Estimate = 0.58

Standard Deviation in Life = 0.82


$R^2 = 50\%$

Sample Size = 27

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.5.1.1.8(b). Best-fit S/N curves for notched,  $K_t = 3.0$ , annealed Ti-13V-11Cr-3Al alloy sheet, longitudinal direction.**

Correlative Information for Figure 5.5.1.1.8(b)

Product Form: Sheet, 0.043-inch thick

Properties: TUS, ksi TYS, ksi Temp. °F  
138.50 132.80 RT

Specimen Details: Notched, edge,  $K = 3.0$   
0.448-inch gross width  
0.300-inch net width  
0.022-inch root radius,  $r$   
60° flank angle,  $\omega$

Surface Condition: As machined, edges polished  
with emery paper.

Reference: 5.5.1.1.8

Test Parameters:

Loading—Axial

Frequency—3600 cpm

Temperature—RT

Atmosphere—Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$$\log N_f = 21.93 - 11.03 \log (S_{eq})$$

$$S_{eq} = S_{max} (1-R)^{0.53}$$

Standard Error of Estimate = 0.91

Standard Deviation in Life = 1.11


$R^2 = 33\%$

Sample Size = 19

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.5.1.1.8(c). Best-fit S/N curves for unnotched, annealed Ti-13V-11Cr-3Al alloy sheet at 600°F, longitudinal direction.**

Correlative Information for Figure 5.5.1.1.8(c)

Product Form: Sheet, 0.043-inch thick

Properties: TUS, ksi TYS, ksi Temp, °F  
116.00 102.61 600°F

Specimen Details: Unnotched, 0.300-inch wide

Surface Condition: As machined, edges polished with emery paper.

Reference: 5.5.1.1.8

Test Parameters:

Loading—Axial

Frequency—3600 cpm

Temperature—600°F

Atmosphere—Air

No. of Heats/Lot: Not specified

Equivalent Stress Equation:

$$\log N_f = 35.63 - 16.50 \log (S_{eq})$$

$$S_{eq} = S_{max} (1-R)^{0.34}$$

Standard Error of Estimate = 0.35

Standard Deviation in Life = 1.07


$R^2 = 90\%$

Sample Size = 12

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.5.1.1.8(d). Best-fit S/N curves for unnotched annealed Ti-13V-11Cr-3Al alloy sheet at 800°F, longitudinal direction.**

Correlative Information for Figure 5.5.1.1.8(d)

Product Form: Sheet, 0.043-inch thick

Properties: TUS, ksi TYS, ksi Temp, °F  
115.80 98.61 800°F

Specimen Details: Unnotched, 0.300-inch wide

Surface Condition: As machined, edges polished with emery paper.

Reference: 5.5.1.1.8

Test Parameters:

Loading—Axial

Frequency—3600 cpm

Temperature—800°F

Atmosphere—Air

No. of Heats/Lot: Not specified

Equivalent Stress Equation:

$$\log N_f = 21.67 - 8.88 \log (S_{eq})$$

$$S_{eq} = S_{max} (1-R)^{0.42}$$

Standard Error of Estimate = 0.84

Standard Deviation in Life = 1.07

$R^2 = 39\%$

Sample Size = 26

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



MIL-HDBK-5H  
1 December 1998




Figure 5.5.1.2.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of solution-treated and aged Ti-13V-11Cr-3Al alloy sheet.




Figure 5.5.1.2.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of solution-treated and aged Ti-13V-11Cr-3Al alloy sheet.

MIL-HDBK-5H  
1 December 1998




Figure 5.5.1.2.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of solution-treated and aged Ti-13V-11Cr-3Al alloy sheet.






Figure 5.5.1.2.4. Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of solution-treated and aged Ti-13V-11Cr-3Al alloy sheet.

**MIL-HDBK-5H****1 December 1998**

**Figure 5.5.1.2.6. Typical tensile stress-strain curves for solution-treated and aged Ti-13V-11Cr-3Al alloy sheet at room and elevated temperatures.**

## MIL-HDBK-5H

1 December 1998



**Figure 5.5.1.2.8(a). Best-fit S/N curves for unnotched, solution treated and aged Ti-13V-11Cr-3Al alloy sheet and plate, longitudinal direction.**

Correlative Information for Figure 5.5.1.2.8(a)

Product Form: Sheet, 0.043-inch thick and  
plate, 1.00-inch thick

Properties: TUS, ksi TYS, ksi Temp, °F  
174.5 156.7 RT

Specimen Details: Unnotched, 0.30-inch wide  
Unnotched, 0.20-inch wide

Surface Condition: As machined, edges polished  
with emery paper.

As machined, edges were  
hand-polished.

References: 5.5.1.1.8 and 5.5.1.2.8

Test Parameters:

Loading—Axial

Frequency—3600 cpm, 10,000 cpm

Temperature—RT

Atmosphere—Air

No. of Heats/Lot: Not specified

Equivalent Stress Equation:

$$\log N_f = 8.37 - 2.30 \log (S_{eq} - 20)$$

$$S_{eq} = S_{max} (1 - R)^{0.27}$$

Standard Error of Estimate = 0.093

Standard Deviation in Life = 0.31

$R^2 = 91\%$


Sample Size = 17

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 5.5.1.2.8(b). Best-fit S/N curves for unnotched, solution treated and aged Ti-13V-11Cr-3Al alloy sheet at 600°F, longitudinal direction.**

Correlative Information for Figure 5.5.1.2.8(b)

Product Form: Sheet, 0.043-inch thick

Properties: TUS, ksi TYS, ksi Temp. °F  
156.30 127.0 600°F

Specimen Details: Unnotched, 0.310-inch wide

Surface Condition: As machined, edges polished with emery paper.

Reference: 5.5.1.1.8

Test Parameters:

Loading—Axial

Frequency—3600 cpm

Temperature—600°F

Atmosphere—Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$$\log N_f = 10.39 - 4.33 \log (S_{eq} - 48.5)$$

$$S_{eq} = S_{max} (1 - R)^{0.40}$$

Standard Error of Estimate = 0.90

Standard Deviation in Life = 1.27


R<sup>2</sup> = 50%

Sample Size = 21

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 5.5.1.2.8(c). Best-fit S/N curves for unnotched, solution treated and aged Ti-13V-11Cr-3Al alloy sheet at 800°F, longitudinal direction.**

Correlative Information for Figure 5.5.1.2.8(c)

Product Form: Sheet, 0.043-inch thick

Properties: TUS, ksi TYS, ksi Temp, °F  
149.40 122.30 800°F

Specimen Details: Unnotched, 0.30-inch wide

Surface Condition: As machined, edges  
polished with emery paper.

Reference: 5.5.1.1.8

Test Parameters:

Loading—Axial

Frequency—3600 cpm

Temperature—800°F

Atmosphere—Air

No. of Heats/Lots: Not specified

Equivalent Stress Equation:

$$\log N_f = 30.03 - 14.03 \log (S_{eq})$$

$$S_{eq} = S_{max} (1-R)^{0.11}$$

Standard Error of Estimate = 0.85

Standard Deviation in Life = 1.01

$R^2 = 29\%$

Sample Size = 24

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998****5.5.2 Ti-15V-3Cr-3Sn-3Al (Ti-15-3)**

**5.5.2.0 Comments** — Ti-15V-3Cr-3Sn-3Al is a solute rich (metastable) beta titanium alloy. It was developed primarily to lower the cost of titanium sheet metal parts by reducing materials and processing cost. Contrary to conventional alpha-beta alloys, this alloy is strip producible and has excellent room temperature formability characteristics. It can also be aged to a wide range of strength levels to meet a variety of application needs. Although this alloy was originally developed as a sheet alloy, it has expanded into other areas such as fasteners, foil, plate, tubing, castings, and forgings.

*Manufacturing Considerations* — Ti-15V-3Cr-3Sn-3Al is usually supplied in the solution-annealed condition. In this condition, the alloy has a single phase (beta) structure and, hence, is readily cold formed. After cold forming, the alloy can be resolution-treated in the 1450°F to 1550°F range and subsequently aged in the 900°F to 1100°F range, depending upon desired strength. Care should be exercised to ensure that no surface contamination results from the solution treatment. The alloy can be directly aged after forming; however, strength will vary depending upon the amount of cold work in the part. The alloy can also be hot formed. Heating times prior to hot forming should be minimized in order to prevent appreciable aging prior to forming. Ti-15V-3Cr-3Sn-3Al alloy is readily welded by standard titanium welding techniques.

*Environmental Considerations* — In the aged condition, Ti-15V-3Cr-3Sn-3Al appears to be immune to hot-salt stress corrosion cracking below the 500°F to 440°F range. However, some susceptibility has been noted after 100-hour stressed exposures at 600°F. The presence of salt water does not appear to affect the room temperature crack growth behavior of aged material. Alloy Ti-15V-3Cr-3Sn-3Al should not be used in the solution treated condition. Long time exposure of solution treated and cold worked material to service temperatures above approximately 300°F or solution treated material to service temperatures above approximately 400°F can result in low ductility. Under certain conditions, titanium, when in contact with cadmium, silver, mercury, or certain of their compounds, may become embrittled. Refer to MIL-S-5002 and MIL-STD-1568 for restrictions concerning such applications.

*Heat Treatment* — This alloy should be solution treated for 10-30 minutes in the 1450°F to 1550°F range, cooled at a rate approximating an air cool of 0.125 inch thick sheet and subsequently aged. Aging is generally conducted in the 900°F to 1100°F range, followed by an air cool. Aging times will vary depending upon aging temperature. The material can be used in service in the solution treated condition subject to the temperature limitations described above.

*Specifications and Properties* — A material specification for Ti-15V-3Cr-3Sn-3Al is shown in Table 5.5.2.0(a). Room-temperature mechanical properties for Ti-15V-3Cr-3Sn-3Al are shown in Table 5.5.2.0(b). The effect of temperature on physical properties is shown in Figure 5.5.2.0.

**Table 5.5.2.0(a). Material Specification  
for Ti-15V-3Cr-3Sn-3Al**

Specification	Form
AMS 4914	Sheet and strip

**5.5.2.1 Solution-Treated and Aged (1000°F) Condition** — Typical tensile and compressive stress-strain and compressive tangent-modulus curves are presented in Figures 5.5.2.1.6(a) and (b).

**MIL-HDBK-5H****1 December 1998****Table 5.5.2.0(b). Design Mechanical and Physical Properties of Ti-15V-3Cr-3Sn-3Al Sheet**

Specification .....	AMS 4914
Form .....	Sheet
Condition .....	STA (1000°F/8 Hrs.)
Thickness, in. ....	≤0.125
Basis .....	S
Mechanical Properties:	
$F_{tu}$ , ksi:	
L .....	145
LT .....	145
$F_{ty}$ , ksi:	
L .....	140
LT .....	140
$F_{cy}$ , ksi:	
L .....	139
LT .....	144
$F_{su}$ , ksi .....	92
$F_{bru}^a$ , ksi:	
(e/D = 1.5) .....	216
(e/D = 2.0) .....	276
$F_{bry}^a$ , ksi:	
(e/D = 1.5) .....	203
(e/D = 2.0) .....	233
$e$ , percent:	
L .....	7
LT .....	7
$E$ , 10 <sup>3</sup> ksi:	
L .....	15.2
LT .....	15.7
$E_c$ , 10 <sup>3</sup> ksi:	
L .....	15.3
LT .....	16.0
$G$ , 10 <sup>3</sup> ksi .....	...
$\mu$ .....	...
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.172
$C$ , $K$ , and $\alpha$ .....	See Figure 5.5.2.0

a Bearing values are “dry pin” values per Section 1.4.7.1.

## MIL-HDBK-5H

1 December 1998






Figure 5.5.2.0. Effect of temperature on the physical properties of Ti-15V-3Cr-3Sn-3Al alloy.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.5.2.1.6(a). Typical tensile stress-strain curves at room temperature for solution treated and aged (1000°F) Ti-15V-3Cr-3Sn-3Al alloy sheet.**



**Figure 5.5.2.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves at room temperature for solution treated and aged (1000°F) Ti-15V-3Cr-3Sn-3Al alloy sheet.**

**MIL-HDBK-5H****1 December 1998****5.5.3 Ti-10V-2Fe-3Al (Ti-10-2-3)**

**5.5.3.0 Comments and Properties** — Ti-10V-2Fe-3Al is a solute lean beta (near beta) titanium alloy that was developed primarily as a high-strength forging alloy. It has excellent forging characteristics, possessing flow properties at 1500°F similar to Ti-6Al-4V at 1700°F. This characteristic provides advantages, such as lower die cost and better die fill capability. This alloy also provides the best combination of strength and toughness of any of the commercially available titanium alloys. For example, at the 180 ksi tensile ultimate strength level, the alloy has a  $K_{Ic}$  value of 40 ksi-in.<sup>1/2</sup> minimum.

In addition to this high-strength condition, the alloy can also be processed to intermediate strength levels for higher fracture toughness. This alloy has also been reported to exhibit a shape-memory effect.

*Manufacturing Considerations* — Ti-10V-2Fe-3Al is usually supplied as bar or billet product which has been finish forged (or rolled) in the alpha-beta field. In order to optimize the microstructure for the high-strength condition, the forging is usually given a pre-form forge above the beta transus, followed by a 15 to 25 percent reduction below the beta transus. Ideally, the beta forging operation is finished through the beta transus, followed by a quench. The intent of the two-step forging process is to develop a structure without grain boundary alpha, but with elongated primary alpha needles in an aged beta matrix. The alloy is considered to be deep hardenable, capable of generating high strengths in section thicknesses up to approximately 5 inches. The alloy is also readily weldable by conventional titanium welding techniques.

*Environmental Consideration* — In the solution treated plus aged condition, the material exhibits excellent resistance to stress corrosion cracking, typically exhibiting a  $K_{Isc} > 0.8 K_{Ic}$ . In the solution-treated condition, the material should not be subjected to long-term exposure in the 500 to 800°F range, since such exposure could result in high-strength, low-ductility conditions. Exposure to cadmium, silver, mercury, or certain other compounds should be avoided. Refer to MIL-STD-1568 and MIL-S-5002.

*Heat Treatment* — For the high-strength condition, the alloy is generally solution treated approximately 65°F below the beta transus (which is typically 1460 to 1480°F), followed by a water quench and an 8-hour age at 900 to 950°F. Overaging in the 950°F to 1150°F range may also be used to obtain lower strength levels.

*Beta Flecks* — Ti-10V-2Fe-3Al is a segregation prone alloy which can exhibit a microstructural phenomenon known as “beta-flecks”. Certain areas may possess a lower beta transus than the matrix (due primarily to beta stabilizer enrichment) and, as such, can fully transform during heat treatment just below the matrix transus. In severe cases, this condition can lead to lower ductility and a reduction in fatigue strength due to grain boundary alpha formation in the “flecked” region. Care should be exercised to procure only material which has been melted under strict control to prevent severe “fleck” formation.

*Specifications and Properties* — Material specifications for Ti-10V-2Fe-3Al are shown in Table 5.5.3.0(a). Room temperature mechanical properties for Ti-10V-2Fe-3Al are presented in Table 5.5.3.0(b) and (c) for die and hand forging..

**5.5.3.1 Solution Treated and Aged (900 to 950 °F) Condition** — Typical tensile and compressive stress-strain and compressive tangent-modulus curves are presented in Figure 5.5.3.1.6.

**MIL-HDBK-5H****1 December 1998****Table 5.5.3.0(a). Material Specifications for  
Ti-10V-2Fe-3Al**

Specification	Form
AMS 4983	Forging
AMS 4984	Forging
AMS 4986	Forging

**5.5.3.2 Solution Treated and Aged (950 to 1000 °F) Condition** — Typical tensile and compressive stress-strain and compressive tangent-modulus curves are shown in Figure 5.5.3.2.6.



## MIL-HDBK-5H

1 December 1998

**Table 5.5.3.0(b). Design Mechanical and Physical Properties of Ti-10V-2Fe-3Al Die Forging**

Specification . . . . .	AMS 4983	AMS 4984
Form . . . . .	Conventional die forging	
Condition . . . . .	Solution treated and aged (900-950 °F)	
Thickness, in. . . . .	<1.000	≤3.000
Basis . . . . .	S	S
Mechanical Properties:		
$F_{tu}$ , ksi:		
L . . . . .	180	173
LT . . . . .	180 <sup>b</sup>	173 <sup>b</sup>
ST . . . . .	...	173 <sup>b</sup>
$F_{ty}$ , ksi:		
L . . . . .	160	160
LT . . . . .	160 <sup>b</sup>	160 <sup>b</sup>
ST . . . . .	...	160 <sup>b</sup>
$F_{cy}$ , ksi:		
L . . . . .	168	168
LT . . . . .	166	166
ST . . . . .	...	166
$F_{su}$ , ksi . . . . .	101	97
$F_{bru}^a$ , ksi:		
(e/D = 1.5) . . . . .	244	234
(e/D = 2.0) . . . . .	295	284
$F_{bry}^a$ , ksi:		
(e/D = 1.5) . . . . .	227	227
(e/D = 2.0) . . . . .	261	261
$e$ , percent:		
L . . . . .	4	4
LT . . . . .	4 <sup>b</sup>	4 <sup>b</sup>
ST . . . . .	...	4 <sup>b</sup>
$E$ , 10 <sup>3</sup> ksi . . . . .	15.9	
$E_c$ , 10 <sup>3</sup> ksi . . . . .	16.3	
$G$ , 10 <sup>3</sup> ksi . . . . .	...	
$\mu$ . . . . .	...	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.168	
$a$ , 10 <sup>-6</sup> in./in./°F . . . .	5.4 (68-800 °F)	
$C$ and $K$ . . . . .	...	

a Bearing values are "dry pin" values per Section 1.4.7.1.

b Applicable providing LT or ST dimension is ≥2.500 inches.

**MIL-HDBK-5H****1 December 1998****Table 5.5.3.0(c). Design Mechanical and Physical Properties of Ti-10V-2Fe-3Al Hand Forging**


Specification . . . . .	AMS 4986	
Form . . . . .	Hand forging	
Condition . . . . .	Solution treated and aged (950-1000 °F)	
Thickness, in. . . . .	≤3.000	3.001-4.000
Basis . . . . .	S	S
Mechanical Properties:		
$F_{tu}$ , ksi:		
L . . . . .	160	160
LT . . . . .	160 <sup>a</sup>	160
$F_{ty}$ , ksi:		
L . . . . .	145	145
LT . . . . .	145 <sup>a</sup>	145
$F_{cy}$ , ksi:		
L . . . . .	154	...
LT . . . . .	...	...
$F_{su}$ , ksi . . . . .	97 <sup>b</sup>	...
$F_{bru}^c$ , ksi:		
(e/D = 1.5) . . . . .	241	...
(e/D = 2.0) . . . . .	293	...
$F_{bry}^c$ , ksi:		
(e/D = 1.5) . . . . .	218	...
(e/D = 2.0) . . . . .	245	...
$e$ , percent:		
L . . . . .	6	6
LT . . . . .	6 <sup>a</sup>	6
RA, percent:		
L . . . . .	10	10
LT . . . . .	10 <sup>a</sup>	10
$E$ , 10 <sup>3</sup> ksi . . . . .	15.9	
$E_c$ , 10 <sup>3</sup> ksi . . . . .	16.3	
$G$ , 10 <sup>3</sup> ksi . . . . .	...	
$\mu$ . . . . .	...	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.168	
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . . .	5.4 (68-800 °F)	
$C$ and $K$ . . . . .	...	

a Applicable providing LT dimension is ≥2.500 inches.


b Shear strength determined in accordance with ASTM B 769.

c Bearing values are "dry pin" per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 5.5.3.1.6. Typical tensile stress-strain, compressive stress-strain, and compressive tangent-modulus curves for solution treated and aged (900-950°F) Ti-10V-2Fe-3Al die forging.**



**Figure 5.5.3.2.6. Typical stress-strain, compressive stress-strain, and compressive tangent-modulus curves for solution treated and aged (950-1000°F) Ti-10V-2Fe-3Al hand forging.**


## 5.6 ELEMENT PROPERTIES

**5.6.1 BEAMS** — See Equation 1.3.2.3, Section 1.5.2.5, and References 1.7.1(a) and (b) for general information on stress analysis of beams.

**5.6.1.1 Simple Beams** — Beams of solid, tubular, or similar cross sections can be assumed to fail through exceeding an allowable modulus of rupture in bending ( $F_b$ ). In the absence of specific data, the ratio  $F_b/F_{tu}$  can be assumed to be 1.25 for solid sections.

**5.6.1.1.1 Round Tubes** — For round tubes, the value of  $F_b$  will depend on the  $D/t$  ratio as well as the ultimate tensile stress. The bending modulus of rupture of 6Al-4V titanium alloy is given in Figure 5.6.1.1.1.

**5.6.1.1.2 Unconventional Cross Sections** — Sections other than solid or tubular should be tested to determine the allowable bending stress.



**Figure 5.6.1.1.1.** Bending modulus of rupture for solution-treated and aged Ti-6Al-4V alloy round tubing manufactured from bar material.

**MIL-HDBK-5H****1 December 1998****REFERENCES**

- 5.1.2(a) Jaffe, R. I., "The Physical Metallurgy of Titanium Alloys", Progress in Metal Physics, Vol. 7, Pergamon Press, Oxford, England, pp 65-167 (1958).
- 5.1.2(b) "Aircraft Designer's Handbook for Titanium and Titanium Alloys", AFML-TR-67-142 (March 1967).
- 5.1.2(c) Larson, F. R., "Anisotropy in Titanium Sheet in Uniaxial Tension", *ASM Transactions*, **57**, pp 620-631 (1964).
- 5.1.2(d) Larson, F. R., "Textures in Titanium Sheet and Its Effects on Plastic Flow Properties", Army Materials Research Agency, AMRA-TR-65-24 (October 1965).
- 5.1.4(a) VanEcho, J. A., "Low Temperature Creep Characteristics of Ti-5Al-2.4Sn and Ti-6Al-4V Alloys", DMIC Technical Note, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio (June 8, 1964).
- 5.1.4(b) Broadwell, R. G., Hatch, A. J., Partridge, J. M., "The Room Temperature Creep and Fatigue Properties of Titanium Alloys", *Journal of Materials*, **2**, (1), pp 111-119 (March 1967).
- 5.1.4(c) Reimann, W. H., "Room Temperature Creep in Ti-6Al-4V", AFML-TR-68-171 (June 1968).
- 5.1.4(d) White, E. L., and Ward, J. J., "Ignition of Metals in Oxygen", DMIC Report 224, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio (February 1, 1966).
- 5.1.4(e) Jackson, J. D., and Boyd, W. K., "Corrosion of Titanium", DMIC Memorandum 218, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio (September 1, 1966).
- 5.1.4(f) "Accelerated Crack Propagation of Titanium by Methanol, Halogenated Hydrocarbons, and Other Solutions", DMIC Memorandum 228, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio (March 6, 1967).
- 5.1.4(g) Lectures from AICE Materials Conference, "Titanium for the Chemical Engineer", DMIC Memorandum 234, Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio (April 1, 1968).
- 5.3.1.1.9 Wanhill, R. J. et al, "Fatigue Crack Propagation Data for Titanium Sheet Alloys", Interim Report NLR-TR-72093U, National Aerospace Laboratory, The Netherlands (July 1972) (MCIC 88911).
- 5.3.2.2.8(a) McCulloch, A. J., Melcon, M. A., and Young, L., "Fatigue Behavior of Sheet Materials for the Supersonic Transport, Volume 1—Summary and Analysis of Fatigue and Static Test Data", Lockheed-California Company, AFML-TR-64-399, Volume 1, January 1965 (MCIC 62421).
- 5.3.2.2.8(b) McCulloch, A. J., Melcon, M. A., and Young, L., "Fatigue Behavior of Sheet Materials for the Supersonic Transport: Volume 11—Static Test Data, S/N Test Data and S/N Diagrams", Lockheed-California Company, AFML-TR-64-399, Volume II, January 1965 (MCIC 62422).

**MIL-HDBK-5H****1 December 1998**

- 5.4.1.1.8(a) “Fatigue Evaluation of Ti-6Al-4V Bar Stock”, Sikorsky Aircraft, Report No. SER-50631 (MIL-HDBK-5 Source M-459) (March 1970).
- 5.4.1.1.8(b) Brockett, R. M., and Gottbrath, J. A., “Development of Engineering Data on Titanium Extrusion for Use in Aerospace Design”, Lockheed-California Co., Technical Report AFML-TR-67-189 (July 1967) (MCIC 69807, MIL-HDBK-5 Source M-543).
- 5.4.1.1.8(c) Rhode, T. M., and Ertel, P. W., “Constant Amplitude Fatigue Life Data for Notched and Unnotched Annealed Ti-6Al-4V Sheet”, AFWAL-TR-88-4081, January 1988 (MIL-HDBK-5 Source M-696).
- 5.4.1.1.9 Fedderson, C. E., and Hyler, W. S., “Fracture and Fatigue-Crack Propagation Characteristics of ¼-Inch Mill Annealed Ti-6Al-4V Titanium Alloy Plate”, Report No. G9706, Battelle, Columbus, Ohio (1971).
- 5.4.1.2.8(a) “Fatigue Strength Properties for Heat Treated Ti-4Al-30Mo-1V and Ti-6Al-4V Titanium Alloys (LP-69-132 and LP-69-129)”, North American Aviation, Report No. TFD-60-521 (July 18, 1960) (MCIC 65737).
- 5.4.1.2.8(b) “Determination of Design Data for Heat Treated Titanium Alloy Sheet”, Lockheed-Georgia Co., Report No. ASD-TDR-62-335, Vol. 3, Contract No. AF33(616)-6346 (May 1962) (MCIC 90172).
- 5.4.1.2.8(c) Sommer, A. W., and Martin, G. R., “Design Allowables for Titanium Alloys”, North American Rockwell, AFML-TR-69-161 (June 1969) (MCIC 75727).
- 5.4.1.2.8(d) Marrocco, A. G., “Fatigue Characteristics of Ti-6Al-4V and Ti-6Al-6V-2Sn Sheet and Plate”, Grumman Aircraft Engineering Corp., EMG-81 (November 18, 1968) (MCIC 76303).
- 5.4.1.2.8(e) Sargent, M. R., “Fatigue Characteristics of Ti-6Al-4V Plate and Forgings (SWIP)”, General Dynamics, FGT-3218 (September 22, 1965) (MIL-HDBK-5 Source M-457).
- 5.4.2.1.8 Marrocco, A. G., “Evaluation of Ti-6Al-4V and Ti-6Al-6V-2Sn Forgings”, Grumman Aircraft Engineering Corporation, EMG-82, November 1968 (MIL-HDBK-5 Source M-522).
- 5.5.1 Henning, R. G., “Mechanical Properties of Solution-Treated Titanium Sheet Alloy B120VCA”, ASD TR 61-337 (September 1961).
- 5.5.1.1.8 Blatherwick, A. A., “Fatigue, Creep, and Stress-Rupture Properties of Ti-13V-11Cr-3Al Titanium Alloy (B120VCA)”, AFML-TR-66-293 (September 1966).
- 5.5.1.2.8 Schwartzberg, F. R., Kiefer, T. F., and Keys, R. D., “Determination of Low-Temperature Fatigue Properties of Structural Metal Alloys 1 April 1962 through 30 September 1964”, Martin-Cr-64-74 (October 1964), pp 158 (MCIC 58024).
- 5.6(a) “Theoretical and Experimental Determination of the Bending Modulus of Rupture for Round Titanium Tubing”, Bendix Products Division (July 31, 1958).
- 5.6(b) Cozzone, F. P., “Bending Strength in Plastic Range”, *Journal of the Aeronautical Sciences* (May 1943).

**MIL-HDBK-5H**

**1 December 1998**

- 5.6(c) Ades, C. S., "Bending Strength of Tubing in the Plastic Range", *Journal of Aeronautical Sciences* (August 1957).
- 5.6(d) "Theoretical and Experimental Determination of the Bending Modulus of Rupture of Round Titanium Tubing", Systems Engineering Report, Bendix Energy Controls Division, South Bend, Indiana, MS-58-3 (July 1958).

**MIL-HDBK-5H**  
**1 December 1998**

This page intentionally blank.



**CHAPTER 6****HEAT-RESISTANT ALLOYS****6.1 GENERAL**

Heat-resistant alloys are arbitrarily defined as iron alloys richer in alloy content than the 18 percent chromium, 8 percent nickel types, or as alloys with a base element other than iron and which are intended for elevated-temperature service. These alloys have adequate oxidation resistance for service at elevated temperatures and are normally used without special surface protection. So-called “refractory” alloys that require special surface protection for elevated-temperature service are not included in this chapter.

This chapter contains strength properties and related characteristics of wrought heat-resistant alloy products used in aerospace vehicles. The strength properties are those commonly used in structural design, such as tension, compression, bearing, and shear. The effects of elevated temperature are presented. Factors such as metallurgical considerations influencing the selection of metals are included in comments preceding the specific properties of each alloy or alloy group. Data on creep, stress-rupture, and fatigue strength, as well as crack-growth characteristics, are presented in the applicable alloy section.

There is no standardized numbering system for the alloys in this chapter. For this reason, each alloy is identified by its most widely accepted trade designation.

For convenience in presenting these alloys and their properties, the heat-resistant alloys have been divided into three groups, based on alloy composition. These groups and the alloys for which specifications and properties are included are shown in Table 6.1.

The heat treatments applied to the alloys in this chapter vary considerably from one alloy to another. For uniformity of presentation, the heat-treating terms are defined as follows:

*Stress-Relieving* — Heating to a suitable temperature, holding long enough to reduce residual stresses, and cooling in air or as prescribed.

*Annealing* — Heating to a suitable temperature, holding, and cooling at a suitable rate for the purpose of obtaining minimum hardness or strength.

*Solution-Treating* — Heating to a suitable temperature, holding long enough to allow one or more constituents to enter into solid solution, and cooling rapidly enough to hold the constituents in solution.

*Aging, Precipitation-Hardening* — Heating to a suitable temperature and holding long enough to obtain hardening by the precipitation of a constituent from the solution-treated condition.

The actual temperatures, holding times, and heating and cooling rates used in these treatments vary from alloy to alloy and are described in the applicable specifications.

**MIL-HDBK-5H****1 December 1998****Table 6.1. Heat-Resistant Alloys Index**

Section	Designation
<b>6.2</b>	<b>Iron-Chromium-Nickel-Base Alloys</b>
	A-286
6.2.1	N-155
6.2.2	
<b>6.3</b>	<b>Nickel-Base Alloys</b>
6.3.1	Hastelloy X
6.3.2	Inconel 600 (Inconel)
6.3.3	Inconel 625
6.3.4	Inconel 706
6.3.5	Inconel 718
6.3.6	Inconel X-750 (Inconel X)
6.3.7	René 41
6.3.8	Waspaloy
<b>6.4</b>	<b>Cobalt-Base Alloys</b>
6.4.1	L-605 (Haynes Alloy 25)
6.4.2	HS 188

**MIL-HDBK-5H****1 December 1998****6.1.1 MATERIAL PROPERTIES**

**6.1.1.1 Mechanical Properties** — The mechanical properties of the heat-resistant alloys are affected by relatively minor variations in chemistry, processing, and heat treatment. Consequently, the mechanical properties shown for the various alloys in this chapter are intended to apply only to the alloy, form (shape), size (thickness), and heat treatment indicated. When statistical values are shown, these are intended to represent a fair cross section of all mill production within the indicated scope.

*Strength Properties* — Room-temperature strength properties for alloys in this chapter are based primarily on minimum tensile property requirements of material specifications. Values for nonspecification strength properties are derived. The variation of properties with temperature and other data of interest are presented in figures or tables, as appropriate.

The strength properties of the heat-resistant alloys generally decrease with increasing temperatures or increasing time at temperature. There are exceptions to this statement, particularly in the case of age-hardening alloys; these alloys may actually show an increase in strength with temperature or time, within a limited range, as a result of further aging. In most cases, however, this increase in strength is temporary and, furthermore, cannot usually be taken advantage of in service. For this reason, this increase in strength has been ignored in the preparation of elevated temperature curves as described in Chapter 9.

At cryogenic temperatures, the strength properties of the heat-resistant alloys are generally higher than at room temperature, provided some ductility is retained at the low temperatures. For additional information on mechanical properties at cryogenic temperatures, other references, such as the Cryogenic Materials Data Handbook (OTS PB 161093), should be consulted.

*Ductility* — Specified minimum ductility requirements are presented for these alloys in the room-temperature property tables. The variation in ductility with temperature is somewhat erratic for the heat-resistant alloys. Generally, ductility decreases with increasing temperature from room temperature up to about 1200 to 1400 °F, where it reaches a minimum value, then it increases with higher temperatures. Prior creep exposure may also affect ductility adversely. Below room temperature, ductility decreases with decreasing temperature for some of these alloys.

*Stress-Strain Relationships* — The stress-strain relationships presented are typical curves prepared as described in Section 9.3.2.

*Creep* — Data covering the temperatures and times of exposure and the creep deformations of interest are included as typical information in individual material sections. These presentations may be in the form of creep stress-lifetime curves for various deformation criteria as specified in Chapter 9 or as creep nomographs.

*Fatigue* — Fatigue S/N curves for unnotched and notched specimens at room temperature and elevated temperatures are shown in each alloy section. Fatigue crack propagation data are also presented.

**6.1.1.2 Physical Properties** — Selected physical-property data are presented for these alloys. Processing variables and heat treatment have only a slight effect on these values; thus, the properties listed are applicable to all forms and heat treatments.

**MIL-HDBK-5H****1 December 1998****6.2 IRON-CHROMIUM-NICKEL-BASE ALLOYS**

**6.2.0 GENERAL COMMENTS** — The alloys in this group, in terms of cost and in maximum service temperature, generally fall between the austenitic stainless steels and the nickel- and cobalt-base alloys. They are used in airframes, principally, in the temperature range 1000 to 1200°F, in those applications in which the stainless steels are inadequate and service requirements do not justify the use of the more costly nickel or cobalt alloys.

**6.2.0.1 Metallurgical Considerations**

*Composition* — The complex-base alloys comprising this group range from those in which iron is considered the base element to those which border on the nickel-base alloys. All of them contain sufficient alloying elements to place them in the “Superalloy” category, yet contain enough iron to reduce their cost considerably.

Chromium, in amounts ranging from 10 to 20 percent or higher, primarily increases oxidation resistance and contributes to strengthening of these alloys. Nickel and cobalt strengthen and toughen these materials. Molybdenum, tungsten, and columbium contribute to hardness and strength, particularly at elevated temperatures. Titanium and aluminum are added to provide age-hardening.

*Heat Treatment* — The complex-base alloys are heat treated with conventional equipment and fixtures such as would be used for austenitic stainless steels. Since these alloys are susceptible to carburization during heat treatment, it is good practice to remove all grease, oil, cutting, lubricant, etc., from the surface before heating. A low-sulfur and neutral or slightly oxidizing furnace atmosphere is recommended for heating.

**6.2.0.2 Manufacturing Considerations** — The iron-chromium-nickel-base alloys closely resemble the austenitic stainless steels insofar as forging, cold forming, machining, welding, and brazing are concerned. Their higher strength may require the use of heavier forging or forming equipment, and machining is somewhat more difficult than for the stainless steels. Pertinent comments are included under the individual alloys.

**6.2.1 A-286**

**6.2.1.0 Comments and Properties** — A-286 is a precipitation-hardening iron-base alloy designed for parts requiring high strength up to 1300°F and oxidation resistance up to 1500°F. It is used in jet engines and gas turbines for parts such as turbine buckets, bolts, and discs, and sheet metal assemblies. A-286 is available in the usual mill forms.

A-286 is somewhat harder to hot or cold work than the austenitic stainless steels. Its forging range is 2150 to 1800°F; when finishing below 1800°F, light reductions (under 15 percent) must be avoided to prevent grain coarsening during subsequent heat treatment. A-286 is readily machined in the partially or fully aged condition but is soft and “gummy” in the solution-treated condition. A-286 should be welded in the solution-treated condition. Fusion welding is difficult for large section sizes and moderately difficult for small cross sections and sheet. Cracking may be encountered in the welding of heavy sections or parts under high restraint. A dimensional contraction of 0.0008 inch per inch is experienced during aging. Oxidation resistance of A-286 is equivalent to that of Type 310 stainless steel up to 1800°F.

Some material specifications for A-286 alloy are presented in Table 6.2.1.0(a). Room-temperature mechanical and physical properties are shown in Table 6.2.1.0(b). The effect of temperature on physical properties is shown in Figure 6.2.1.0.


## MIL-HDBK-5H

1 December 1998

**6.2.1.1 Solution-Treated and Aged Condition** — Elevated-temperature data are presented in Figures 6.2.1.1.1, 6.2.1.1.3, and 6.2.1.1.4(a) through (c). Stress rupture properties are specified at 1200 °F; the appropriate specifications should be consulted for detailed requirements. Figures 6.2.1.1.8(a) through (e) are fatigue S/N curves for several elevated temperatures.

**Table 6.2.1.0(a). Material Specifications for A-286 Alloy**

Specification	Form	Condition
AMS 5525	Sheet, strip, and plate	Solution treated (1800 °F)
AMS 5731	Bar, forging, tubing, and ring	Solution treated (1800 °F)
AMS 5732	Bar, forging, tubing, and ring	Solution treated (1800 °F) and aged
AMS 5734	Bar, forging, and tubing	Solution treated (1650 °F)
AMS 5737	Bar, forging, and tubing	Solution treated (1650 °F) and aged

**Figure 6.2.1.0. Effect of temperature on the physical properties of A-286.**

**MIL-HDBK-5H****1 December 1998****Table 6.2.1.0(b). Design Mechanical and Physical Properties of A-286 Alloy**

Specification .....	AMS 5525	AMS 5731 AMS 5732	AMS 5734 AMS 5737		
Form .....	Sheet, strip, and plate	Bar			
Condition .....	Solution treated and aged				
Thickness or diameter, in.	>0.004	≤2.499	2.500-5.000	≤2.499	2.500-5.000
Basis .....	S <sup>a</sup>	S	S	S	S
Mechanical Properties:					
$F_{tu}$ , ksi:					
L .....	...	130	130	140	140
LT .....	140	130 <sup>b</sup>	130	140 <sup>b</sup>	140
ST .....	...	...	130	...	140
$F_{ty}$ , ksi:					
L .....	...	85	85	95	95
LT .....	95	85 <sup>b</sup>	85	95 <sup>b</sup>	95
ST .....	...	...	85	...	95
$F_{cy}$ , ksi:					
L .....	...	85	85	95	95
LT .....	95	...	...	...	...
$F_{su}$ , ksi .....	91	85	85	91	91
$F_{bru}$ , ksi:					
(e/D = 1.5) .....	210	195	195	210	210
(e/D = 2.0) .....	266	247	247	266	266
$F_{bry}$ , ksi:					
(e/D = 1.5) .....	142	127	127	142	142
(e/D = 2.0) .....	171	153	153	171	171
$e$ , percent:					
L .....	...	15	15	12	12
LT .....	15	15 <sup>b</sup>	15	12 <sup>b</sup>	12
ST .....	...	...	15	...	12
$RA$ , percent:					
L .....	...	20	20	15	15
LT .....	...	20 <sup>b</sup>	20	15 <sup>b</sup>	15
ST .....	...	...	20	...	15
$E$ , 10 <sup>3</sup> ksi .....	29.1				
$E_c$ , 10 <sup>3</sup> ksi .....	29.1				
$G$ , 10 <sup>3</sup> ksi .....	11.1				
$\mu$ .....	0.31				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> .....	0.287				
$C$ , $K$ , and $\alpha$ .....	See Figure 6.2.1.0				

a Test direction longitudinal for widths less than 9 inches; transverse for widths 9 inches and over.

b Applicable to widths ≥ 2.500 inches only.



MIL-HDBK-5H

1 December 1998




Figure 6.2.1.1.1. Effect of temperature on the tensile yield strength ( $F_{ty}$ ) and tensile ultimate strength ( $F_{tu}$ ) of A-286 alloy (1800°F solution treatment temperature).

## MIL-HDBK-5H

1 December 1998




Figure 6.2.1.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) for A-286 alloy (1800°F solution treatment temperature).




Figure 6.2.1.1.4(a). Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) for A-286 alloy (1800°F solution treatment temperature).



## MIL-HDBK-5H

1 December 1998




Figure 6.2.1.1.4(b). Effect of temperature on the shear modulus (G) of A-286 alloy.





Figure 6.2.1.1.4(c). Effect of temperature on Poisson's ratio ( $\mu$ ) for A-286 alloy.

## MIL-HDBK-5H

1 December 1998



**Figure 6.2.1.1.8(a). Best-fit S/N curves for unnotched A-286 bar at 800°F, longitudinal direction.**

Correlative Information for Figure 6.2.1.1.8(a)

Product Form: Bar, air melted

Properties: TUS, ksi TYS, ksi Temp., °F

141.4 95.3 800

Specimen Details: Unnotched  
0.250-inch diameter

Heat Treatment: 1650°F for 2 hours, oil  
quenched and 1300°F for  
16 hours, air cooled.

Surface Condition: Not given

Reference: 6.2.1.1.8

Test Parameters:

Loading - Axial  
Frequency - 3600 cpm  
Temperature - 800°F  
Environment - Air

No. of Heats/Lots: 1

Equivalent Stress Equation:


$\log N_f = 45.1 - 19.5 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.47}$   
Standard Error of Estimate = 0.418  
Standard Deviation in Life = 0.717  
 $R^2 = 65.9\%$

Sample Size = 17

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 6.2.1.1.8(b). Best-fit S/N curves for notched,  $K_t = 3.4$ , A-286 alloy bar at 800°F, longitudinal direction.**

Correlative Information for Figure 6.2.1.1.8(b)

Product Form: Bar, air melted

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

Loading - Axial  
Frequency - 3600 cpm  
Temperature - 800°F  
Environment - Air

141.4 95.3 800  
Unnotched

No. of Heats/Lots: 1

Specimen Details: Notched, V-Groove,  
 $K_t = 3.4$   
0.375-inch gross diameter  
0.250-inch net diameter  
0.010-inch root radius, r  
60° flank angle,  $\omega$

Equivalent Stress Equation:

$$\log N_f = 11.4 - 4.4 \log (S_{eq} - 20)$$

$$S_{eq} = S_{max} (1 - R)^{0.75}$$

Standard Error of Estimate = 0.271

Standard Deviation in Life = 0.387

$R^2 = 50.9\%$

Heat Treatment: 1650°F for 2 hours, oil  
quenched and 1300°F for  
16 hours, air cooled.

Sample Size = 13


Surface Condition: As machined

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

Reference: 6.2.1.1.8

## MIL-HDBK-5H

1 December 1998



**Figure 6.2.1.1.8(c). Best-fit S/N curves for unnotched A-286 bar at 1000°F, longitudinal direction.**

Correlative Information for Figure 6.2.1.1.8(c)

Product Form: Bar, air melted

Test Parameters:

Loading - Axial

Properties: TUS, ksi TYS, ksi Temp., °F

Frequency - 3600 cpm

Temperature - 1000°F

137.2 100.6 1000

Environment - Air

Specimen Details: Unnotched  
0.250-inch diameter

No. of Heats/Lots: 1

Heat Treatment: 1650°F for 2 hours, oil  
quenched and 1300°F for  
16 hours, air cooled.

Equivalent Stress Equation:

$$\log N_f = 44.2 - 19.3 \log (S_{eq})$$

$$S_{eq} = S_{max} (1-R)^{0.57}$$

Standard Error of Estimate = 0.566

Standard Deviation in Life = 0.835

$R^2 = 54.0\%$

Surface Condition: Not given

Reference: 6.2.1.1.8

Sample Size = 18


[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]





## MIL-HDBK-5H

1 December 1998



**Figure 6.2.1.1.8(e). Best-fit S/N curves for unnotched A-286 bar at 1250°F, longitudinal direction.**

Correlative Information for Figure 6.2.1.1.8(e)

Product Form: Bar, air melted

Test Parameters:

Properties: TUS, ksi TYS, ksi Temp., °F

109.6 96.5 1250

Loading - Axial  
Frequency - 3600 cpm  
Temperature - 1250°F  
Environment - Air

Specimen Details: Unnotched  
0.250-inch diameter

No. of Heats/Lots: 1

Heat Treatment: 1650°F for 2 hours, oil  
quenched and 1300°F for  
16 hours, air cooled.

Equivalent Stress Equation:

$$\log N_f = 30.8 - 12.8 \log (S_{eq})$$

$$S_{eq} = S_{max} (1-R)^{0.77}$$

Standard Error of Estimate = 0.513

Standard Deviation in Life = 0.788

$$R^2 = 57.6\%$$

Surface Condition: Not given

Reference: 6.2.1.1.8

Sample Size = 13

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998****6.2.2 N-155 ALLOY**

**6.2.2.0 Comments and Properties** — N-155 alloy, also known as Multimet, is designed for applications involving high stress up to 1500°F. It has good oxidation properties and good ductility and can be fabricated readily by conventional methods. This alloy has been used in many aircraft applications, including afterburner parts, combustion chambers, exhaust assemblies, turbine parts, and bolting.


N-155 is forged readily between 1650 and 2200°F. It is easily formed by conventional methods; intermediate anneals may be required to restore its ductility. This alloy is machinable in all conditions; low cutting speeds and ample flow of coolant are required. The weldability of N-155 is comparable to that of the austenitic stainless steels. The oxidation resistance of N-155 sheet is good up to 1500°F.

Some materials specifications for N-155 are presented in Table 6.2.2.0(a). Room-temperature mechanical and physical properties for N-155 sheet and tubing in the solution-treated (annealed) condition are presented in Table 6.2.2.0(b). Bars and forgings are not specified by room-temperature properties but have specific elevated-temperature requirements. The effect of temperature on physical properties is shown in Figure 6.2.2.0.

**Table 6.2.2.0(a). Material Specifications for N-155 Alloy**

Specification	Form	Condition
AMS 5532	Sheet	Solution treated
AMS 5585	Tubing (welded)	Solution treated
AMS 5768	Bar and forging	Solution treated
AMS 5769	Bar and forging	Solution treated and aged
		Solution treated

**6.2.2.1 Solution-Treated Condition** — Elevated-temperature curves are presented in Figures 6.2.2.1.1(a) and (b), as well as 6.2.2.1.4(a) and (b). Stress-rupture properties are specified at 1500°F for sheet and at 1350°F for bars and forgings; the appropriate specifications should be consulted for detailed requirements.

**Figure 6.2.2.0. Effect of temperature on the physical properties of N-155 alloy.**

**MIL-HDBK-5H****1 December 1998****Table 6.2.2.0(b). Design Mechanical and Physical Properties of N-155 Alloy**

Specification .....	AMS 5532		AMS 5585
Form .....	Sheet	Strip and plate	Tubing
Condition .....	Solution treated		
Thickness, in. ....	$\leq 0.187$	...	...
Basis .....	S <sup>a</sup>	S <sup>a</sup>	S
Mechanical Properties:			
$F_{tu}$ , ksi:			
L .....	...	...	100
LT .....	100	100	...
$F_{ty}$ , ksi:			
L .....	...	...	49 <sup>b</sup>
LT .....	49 <sup>b</sup>	...	...
$F_{cy}$ , ksi:			
L .....	...	...	...
LT .....	...	...	...
$F_{su}$ , ksi .....	...	...	...
$F_{bru}$ , ksi:			
(e/D = 1.5) .....	...	...	...
(e/D = 2.0) .....	...	...	...
$F_{bry}$ , ksi:			
(e/D = 1.5) .....	...	...	...
(e/D = 2.0) .....	...	...	...
$e$ , percent:			
L .....	...	...	<sup>c</sup>
LT .....	40	40	...
$E$ , 10 <sup>3</sup> ksi .....	29.2		
$E_c$ , 10 <sup>3</sup> ksi .....	29.2		
$G$ , 10 <sup>3</sup> ksi .....	11.2		
$\mu$ .....	See Figure 6.2.2.1.4(b)		
Physical Properties:			
$\omega$ , lb/in. <sup>3</sup> .....	0.300		
$C$ , Btu/(lb)(°F) .....	0.103 (70 to 212°F)		
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	See Figure 6.2.2.0		
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	See Figure 6.2.2.0		

a Test direction longitudinal for widths less than 9 inches; transverse for widths 9 inches and over.

b Typical value reduced to minimum.

c Strip = 35.

Full section 0.625 thick = 40.

Full section &gt;0.625 thick = 30.



MIL-HDBK-5H

1 December 1998




Figure 6.2.2.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of N-155 alloy.




Figure 6.2.2.1.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of N-155 alloy.

## MIL-HDBK-5H

1 December 1998




Figure 6.2.2.1.4(a). Effect of temperature on the tensile and compressive moduli ( $E$  and  $E_c$ ) of N-155 alloy.




Figure 6.2.2.1.4(b). Effect of temperature on Poisson's ratio ( $\mu$ ) for N-155 alloy.

**MIL-HDBK-5H****1 December 1998****6.3 NICKEL-BASE ALLOYS**

**6.3.0 GENERAL COMMENTS** — Nickel is the base element for most of the higher temperature heat-resistant alloys. While it is more expensive than iron, nickel provides an austenitic structure that has greater toughness and workability than ferritic structures of the same strength level.

**6.3.0.1 Metallurgical Considerations** —

*Composition* — The common alloying elements for nickel are cobalt, iron, chromium, molybdenum, titanium, and aluminum. Cobalt, when substituted for a portion of the nickel in the matrix, improves high-temperature strength; small additions of iron tend to strengthen the nickel matrix and reduce the cost; chromium is added to increase strength and oxidation resistance at very high temperatures; molybdenum contributes to solid solution strengthening. Titanium and aluminum are added to most nickel-base heat resistant alloys to permit age-hardening by the formation of Ni<sub>3</sub> (Ti, Al) precipitates; aluminum also contributes to oxidation resistance.

The nature of the alloying elements in the age-hardenable nickel-base alloys makes vacuum melting of these alloys advisable, if not mandatory. However, the additional cost of vacuum melting is more than compensated for by the resulting improvements in elevated-temperature properties.

*Heat Treatment* — The nickel-base alloys are heat treated with conventional equipment and fixtures such as would be used with austenitic stainless steels. Since nickel-base alloys are more susceptible to sulfur embrittlement than are iron-base alloys, it is essential that sulfur-bearing materials such as grease, oil, cutting lubricants, marking paints, etc., be removed before heat treatment. Mechanical cleaning, such as wire brushing, is not adequate and if used should be followed by washing with a suitable solvent or by vapor degreasing. A low-sulfur content furnace atmosphere should be used. Good furnace control with respect to time and temperature is desirable since overheating some of the alloys as little as 35 °F impairs strength and corrosion resistance.

When it is necessary to anneal the age-hardenable-type alloys, a protective atmosphere (such as argon) lessens the possibility of surface contaminations or depletion of the precipitation-hardening elements. This precaution is not so critical in heavier sections since the oxidized surface layer is a smaller percentage of the cross section. After solution annealing, the alloys are generally quenched in water. Heavy sections may require air cooling to avoid cracking from thermal stresses.

In stress-relief annealing of a structure or assembly composed of an aluminum-titanium hardened alloy, it is vitally important to heat the structure rapidly through the age-hardening temperature range, 1200 to 1400 °F (which is also the low ductility range) so that stress relief can be achieved before any aging takes place. Parts which are to be used in the fully heat-treated condition would have to be solution treated, air cooled, and subsequently aged. In this case, the stress-relief treatment would be conducted in the solution-temperature range. Little difficulty has been encountered with distortion under rapid heating conditions, and distortion of weldments of substantial size has been less than that observed with conventional slow heating methods.

**6.3.0.2 Manufacturing Considerations**

*Forging* — All of the alloys considered, except for the casting compositions, can be forged to some degree. The matrix-strengthened alloys can be forged with proper consideration of cooling rates, atmosphere, etc. Most of the precipitation-hardenable grades can be forged, although heavier equipment is required and a smaller range of reductions can be safely attained.

*Cold Forming* — Almost all of the wrought-nickel-base alloys in sheet form are cold formable. The lower strength alloys offer few problems, but the higher strength alloys require higher forming pressures and more frequent anneals.

*Machining* — All of the alloys in this section are readily machinable, provided the optimum conditions of heat treatment, type of tool speed, feed, depth of cut, etc., are achieved. Specific recommendations on these points are available from various producers of these alloys.



**MIL-HDBK-5H****1 December 1998**

*Welding* — The matrix-strengthening-type alloys offer no serious problems in welding. All of the common resistance- and fusion-welding processes (except submerged arc) have been successfully employed. For the age-hardenable type of alloy, it is necessary to observe some further precautions:

- (1) Welding should be confined to annealed material where design permits. In full age-hardened material, the hazard of cracking in the weld and/or the parent metal is great.
- (2) If design permits joining some portions only after age hardening, the parts to be joined should be “safe ended” with a matrix-strengthened-type alloy (with increased cross section) and then age hardened; welding should then be carried out on the “safe ends.”
- (3) Parts severely worked or deformed should be annealed before welding.
- (4) After welding, the weldment will often require stress relieving before aging.
- (5) Material must be heated rapidly to the stress-relieving temperature.
- (6) In a number of the age-hardenable alloys, fusion welds may exhibit only 70 to 80 percent of the rupture strength of the parent metal. The deficiency can often be minimized by design, such as locating welds in areas of lowest temperature and/or stress. The use of special filler wires to improve weld-rupture properties is under investigation.

*Brazing* — The solid-solution-type chromium-containing alloys respond well to brazing, using techniques and brazing alloys applicable to the austenitic stainless steels. Generally, it is necessary to braze annealed material and to keep stresses low during brazing, especially when brazing with low melting alloys, to avoid embrittlement. As with the stainless steels, dry hydrogen, argon, or helium atmospheres (-80°F dew point or lower) are used successfully, and vacuum brazing is now receiving increasing attention.

The aluminum-titanium age-hardened nickel-base alloys are difficult to braze, even using extremely dry reducing- and inert-gas atmospheres, unless some method of fluxing, solid or gaseous, is used. An alternative technique which is commonly used is to preplate the areas to be brazed with ½ to 1 mil of nickel. For some metal combinations, a few fabricators prefer to apply an iron preplate. In either case, the plating prevents the formation of aluminum or titanium oxide films and results in better joints.

Most of the high-temperature alloys of the nickel-base type are brazed with Ni-Cr-Si-B and Ni-Cr-Si types of brazing alloy. Silver brazing alloys can be used for lower temperature applications. However, since the nickel-base alloys to be brazed are usually employed for higher temperature applications, the higher melting point, stronger, and more oxidation-resistant brazing alloys of the Nicrobraz type are generally used. Some of the gold-base and palladium-base brazing alloys may be useful under some circumstances in intermediate-temperature applications.

**MIL-HDBK-5H****1 December 1998****6.3.1 HASTELLOY X**

**6.3.1.0 Comments and Properties** — Hastelloy X is a nickel-base alloy used for combustor-liner parts, turbine-exhaust weldments, afterburner parts, and other parts requiring oxidation resistance and moderately high strength above 1450°F. It is not hardenable except by cold working and is used in the solution-treated (annealed) condition. Hastelloy X is available in all the usual mill forms.

Hastelloy X is somewhat difficult to forge; forging should be started at 2150 to 2200°F and continued as long as the material flows freely. It should be in the annealed condition for optimum cold forming, and severely formed detail parts should be solution treated at 2150°F for 7 to 10 minutes and cooled rapidly after forming. Machinability of Hastelloy X is similar to that of austenitic stainless steel; the alloy is tough and requires low cutting speeds and ample cutting fluids. Hastelloy X can be resistance or fusion welded or brazed; large or complex fusion weldments require stress relief at 1600°F for 1 hour. Hastelloy X has good oxidation resistance up to 2100°F. It age hardens somewhat during long exposure between 1200 and 1800°F.

Some material specifications for Hastelloy X are presented in Table 6.3.1.0(a). Room-temperature mechanical and physical properties for Hastelloy X sheet are presented in Table 6.3.1.0(b). AMS 5754 does not specify tensile properties for bars and forgings. Figure 6.3.1.0 shows the effect of temperature on physical properties.

**Table 6.3.1.0(a). Material Specifications for Hastelloy X**

Specification	Form	Condition
AMS 5536	Sheet and plate	Solution heat treated (annealed)
AMS 5754	Bar and forging	Solution heat treated (annealed)

**6.3.1.1 Annealed Condition** — The effect of temperature on various mechanical properties is presented in Figures 6.3.1.1.1 and 6.3.1.1.4. In addition, certain stress-rupture requirements at 1500°F are specified in AMS 5536 and 5754 for Hastelloy X. Typical tensile stress-strain curves at room and elevated temperatures are presented in Figure 6.3.1.1.6(a). Typical compressive stress-strain and tangent-modulus curves at room and elevated temperatures are presented in Figure 6.3.1.1.6(b).

**MIL-HDBK-5H****1 December 1998****Table 6.3.1.0(b). Design Mechanical and Physical Properties of Hastelloy X Sheet and Plate**

Specification .....	AMS 5536						
Form .....	Sheet <sup>a</sup> and plate						
Condition .....	Solution treated (annealed)						
Thickness, in. ....	<0.010	0.010-0.019	0.020-0.100		0.101-0.187	0.188-2.000	>2.000
Basis .....	S	S	A	B	S	S	S
Mechanical Properties:							
$F_{tu}$ , ksi:							
L .....	...	...	...	...	...	...	...
LT .....	105	105	102	106	105	100	95
$F_{ty}$ , ksi:							
L .....	...	...	...	...	...	...	...
LT .....	45	45	44	47	45	40	40
$F_{cy}$ , ksi:							
L .....	...	...	...	...	...	...	...
LT .....	...	...	...	...	...	...	...
$F_{su}$ , ksi .....	...	...	...	...	...	...	...
$F_{bru}$ , ksi:							
(e/D = 1.5) .....	...	...	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...	...	...
$F_{bry}$ , ksi:							
(e/D = 1.5) .....	...	...	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...	...	...
$e$ , percent (S-basis):							
L .....	...	...	...	...	...	...	...
LT .....	...	29	35	...	35	35	35
$E$ , $10^3$ ksi .....	29.8						
$E_c$ , $10^3$ ksi .....	29.8						
$G$ , $10^3$ ksi .....	11.3						
$\mu$ .....	0.32						
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> .....	0.297						
$C$ , Btu/(lb)(°F) .....	See Figure 6.3.1.0						
$K$ , Btu/[hr)(ft <sup>2</sup> )(°F)/ft]	See Figure 6.3.1.0						
$\alpha$ , $10^{-6}$ in./in./°F .....	See Figure 6.3.1.0						

a Test direction longitudinal for widths less than 9 inches; transverse for widths 9 inches and over.

## MIL-HDBK-5H

1 December 1998




Figure 6.3.1.0. Effect of temperature on the physical properties of Hastelloy X.

MIL-HDBK-5H  
1 December 1998




Figure 6.3.1.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of Hastelloy X sheet.






Figure 6.3.1.1.4. Effect of temperature on dynamic modulus (E) of Hastelloy X sheet.



**MIL-HDBK-5H**  
**1 December 1998**



**Figure 6.3.1.1.6(a). Typical tensile stress-strain curves for Hastelloy X sheet at room and elevated temperatures.**

**MIL-HDBK-5H****1 December 1998**

**Figure 6.3.1.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for Hastelloy X bar at room and elevated temperatures.**

**MIL-HDBK-5H****1 December 1998****6.3.2 INCONEL 600**

**6.3.2.0 Comments and Properties** — Inconel 600 is a corrosion- and heat-resistant nickel-base alloy used for low-stressed parts operating up to 2000°F. It is not hardenable except by cold working and is usually used in the annealed condition. Inconel 600 is available in all the usual mill forms.

Inconel 600 is readily forged between 1900 and 2250°F; “hot-cold” working between 1200 and 1600°F is harmful and should be avoided; cold working below 1200°F results in improved properties. This alloy is readily formed but should be annealed after severe forming operations. The maximum annealing temperature is 1800°F if minimum yield-strength requirements are to be met consistently. Inconel 600 is susceptible to rapid grain growth at 1800°F or higher, and exposures at these temperatures should be brief if large grain size is objectionable.

Inconel 600 is somewhat difficult to machine because of its toughness and capacity for work hardening; high-speed steel or cemented-carbide tools should be used, and tools should be kept sharp. This alloy can be resistance or fusion welded or brazed (using nonsilver containing brazing alloy); large or complex fusion weldments should be stress relieved at 1600°F for 1 hour. Oxidation resistance of Inconel 600 is excellent up to 2000°F in sulfur-free atmospheres. This alloy is subject to attack in sulfur-containing atmospheres.

**Table 6.3.2.0(a). Material Specifications for Inconel 600**

Specification	Form	Condition
AMS 5540	Plate, sheet, and strip	Annealed
ASTM B166	Bar and rod	Various
AMS 5580	Tubing, seamless	Annealed
ASTM B564	Forging	Annealed

Some material specifications for Inconel 600 are presented in Table 6.3.2.0(a). Room-temperature mechanical and physical properties are shown in Tables 6.3.2.0(b), (c), and (d). Figure 6.3.2.0 shows the effect of temperature on the physical properties.

**6.3.2.1 Annealed Condition** — Elevated-temperature data for this condition are shown in Figures 6.3.2.1.1 through 6.3.2.1.4.

**MIL-HDBK-5H****1 December 1998****Table 6.3.2.0(b). Design Mechanical and Physical Properties of Inconel 600**

Specification .....	AMS 5540	AMS 5580		ASTM B564
Form .....	Sheet, strip, and plate	Tubing		Forging
Condition .....	Annealed	Cold drawn		Annealed
Thickness, in. ....	0.020-2.000	...		...
Outside Diameter, in. ....	...	≤5.000	5.001-6.625	...
Basis .....	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	...	80	80	80
LT .....	80	...	...	...
$F_{ty}$ , ksi:				
L .....	...	35	30	35
LT .....	35	...	...	...
$F_{cy}$ , ksi:				
L .....	...	35	30	35
LT .....	35	...	...	...
$F_{su}$ , ksi .....	51	51	51	51
$F_{bru}$ , ksi:				
(e/D = 1.5) .....	...	...	...	...
(e/D = 2.0) .....	152	152	152	152
$F_{bry}$ , ksi:				
(e/D = 1.5) .....	...	...	...	...
(e/D = 2.0) .....	...	...	...	...
$e$ , percent:				
L .....	...	30	35	30
LT .....	30	...	...	...
$E$ , $10^3$ ksi .....	30.0			
$E_c$ , $10^3$ ksi .....	30.0			
$G$ , $10^3$ ksi .....	11.0			
$\mu$ .....	0.29			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.304			
$C$ , $K$ , and $\alpha$ .....	See Figure 6.3.2.0			

**MIL-HDBK-5H****1 December 1998****Table 6.3.2.0(c). Design Mechanical and Physical Properties of Inconel 600 Bar and Rod**

Specification . . . . .	ASTM B166				
Form . . . . .	Round			Square, hexagon, and rectangle	
Condition . . . . .	Cold-worked				
Thickness, in. . . . .	≤0.499	0.500-1.000	1.001-2.500	≤0.250	0.251-0.499
Basis . . . . .	S	S	S	S	S
Mechanical Properties <sup>a</sup> :					
<i>F<sub>m</sub></i> , ksi:					
L . . . . .	120	110	105	100	95
LT . . . . .	...	...	...	...	...
<i>F<sub>ty</sub></i> , ksi:					
L . . . . .	90	85	80	80	70
LT . . . . .	...	...	...	...	...
<i>F<sub>cy</sub></i> , ksi:					
L . . . . .	...	...	...	...	...
LT . . . . .	...	...	...	...	...
<i>F<sub>su</sub></i> , ksi . . . . .	...	...	...	...	...
<i>F<sub>bru</sub></i> , ksi:					
(e/D = 1.5) . . . . .	...	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...
<i>F<sub>bry</sub></i> , ksi:					
(e/D = 1.5) . . . . .	...	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...	...
<i>e</i> , percent:					
L . . . . .	7 <sup>b</sup>	10	12	5 <sup>b</sup>	7
<i>E</i> , 10 <sup>3</sup> ksi . . . . .	30.0				
<i>E<sub>c</sub></i> , 10 <sup>3</sup> ksi . . . . .	30.0				
<i>G</i> , 10 <sup>3</sup> ksi . . . . .	11.0				
μ . . . . .	0.29				
Physical Properties:					
ω, lb/in. <sup>3</sup> . . . . .	0.304				
<i>C</i> , <i>K</i> , and α . . . . .	See Figure 6.3.2.0				

a Mechanical property requirements apply only when specified by purchaser.

b Not applicable to thickness &lt;0.094 inch.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 6.3.2.0(d). Design Mechanical and Physical Properties of Inconel 600 Bar and Rod**

Specification .....	ASTM B166				
Form .....	Round			Square, hexagon, and rectangle	Bar and rod
Condition .....	Hot-worked				Annealed
Thickness, in. ....	0.250-0.500	0.501-3.000	>3.000	All	All
Basis .....	S	S	S	S	S
Mechanical Properties <sup>a</sup> :					
$F_{tu}$ , ksi:					
L .....	95	90	85	85	80
LT .....	...	...	...	...	...
$F_{ty}$ , ksi:					
L .....	45	40	35	35	35
LT .....	...	...	...	...	...
$F_{cy}$ , ksi:					
L .....	...	...	...	...	35
LT .....	...	...	...	...	...
$F_{su}$ , ksi .....	...	...	...	...	51
$F_{bru}$ , ksi:					
(e/D = 1.5) .....	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	152
$F_{bry}$ , ksi:					
(e/D = 1.5) .....	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...
$e$ , percent:					
L .....	20	25	30	...	30 <sup>b</sup>
$E$ , $10^3$ ksi .....	30.0				
$E_c$ , $10^3$ ksi .....	30.0				
$G$ , $10^3$ ksi .....	11.0				
$\mu$ .....	0.29				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> .....	0.304				
$C$ , $K$ , and $\alpha$ .....	See Figure 6.3.2.0				

a Mechanical property requirements apply only when specified by purchaser.

b Not applicable to thickness >0.094 inch.

MIL-HDBK-5H

1 December 1998




Figure 6.3.2.0. Effect of temperature on the physical properties of Inconel 600.

## MIL-HDBK-5H

1 December 1998




Figure 6.3.2.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of Inconel 600.




Figure 6.3.2.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of Inconel 600.



MIL-HDBK-5H

1 December 1998




Figure 6.3.2.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) of Inconel 600.




Figure 6.3.2.1.4. Effect of temperature on the tensile and compressive moduli (E and  $E_c$ ) of Inconel 600.

**MIL-HDBK-5H****1 December 1998****6.3.3 INCONEL 625**

**6.3.3.0 Comments and Properties** — Inconel 625 is a solid-solution, matrix strengthened nickel-base alloy primarily for applications requiring good corrosion and oxidation resistance at temperatures up to approximately 1800°F and also where such parts may require welding.

The strength of the alloy is derived from the strengthening effect of molybdenum and columbium; thus, precipitation hardening is not required and the alloy is used in the annealed condition. The strength is greatly affected by the amount of cold work prior to annealing and by the annealing temperature. The material is usually annealed at 1700 to 1900°F for time commensurate with thickness. The properties in this section are restricted to that annealing range.


Because the alloy was developed to retain high strength at elevated temperatures, it resists deformation at hot working temperatures but can be readily fabricated with adequate equipment. The combination of strength, corrosion resistance, and ability to be fabricated, including welding by common industrial practices, are the alloy's outstanding features.

Some material specifications for Inconel 625 are listed in Table 6.3.3.0(a). Room-temperature mechanical and physical properties for Inconel 625 are listed in Tables 6.3.3.0(b) and (c). Figure 6.3.3.0 shows the effect of temperature on the physical properties.

**Table 6.3.3.0(a). Material Specifications for Inconel 625**

Specification	Form	Condition
AMS 5599	Sheet, strip, and plate	Annealed
AMS 5666	Bar, forging, and ring	Annealed

**6.3.3.1 Annealed Condition** — Elevated-temperature curves for tensile ultimate strength, tensile yield strength, tensile and compressive moduli, and Poisson's ratio are presented in Figures 6.3.3.1.1(a) and (b), as well as 6.3.3.1.4(a) and (b). Typical stress-strain and tangent-modulus curves are shown in Figures 6.3.3.1.6(a) through (d). Fatigue S/N curves are presented in Figures 6.3.3.1.8(a) through (d).

**Figure 6.3.3.0. Effect of temperature on the physical properties of Inconel 625.**

**MIL-HDBK-5H****1 December 1998****Table 6.3.3.0(b). Design Mechanical and Physical Properties of Inconel 625 Sheet and Plate**

Specification .....	AMS 5599									
Form .....	Sheet and plate									
Condition .....	Annealed									
Thickness, in. ....	≤0.062		0.063-0.109		0.110-0.140		0.141-0.187		0.188-0.250	0.251-1.000
Basis .....	A	B	A	B	A	B	A	B	S	S
Mechanical Properties:										
$F_{tu}$ , ksi:										
L .....	119	127	119	126	119	125	118	123	119	...
LT .....	120 <sup>a</sup>	128	120 <sup>a</sup>	127	120 <sup>a</sup>	126	119	124	120	120
$F_{ty}$ , ksi:										
L .....	56	62	55	61	54	60	53	59	59	...
LT .....	57	63	56	62	55	61	54	60	60	60
$F_{cy}$ , ksi:										
L .....	59	65	58	64	57	63	55	62	62	...
LT .....	59	66	58	65	57	64	56	63	63	...
$F_{su}$ , ksi .....	79	84	79	84	79	83	79	82	79	...
$F_{bru}$ , ksi:										
(e/D = 1.5) .....	202	216	202	214	202	212	201	209	202	...
(e/D = 2.0) .....	263	281	263	279	263	276	261	272	263	...
$F_{bry}^b$ , ksi:										
(e/D = 1.5) .....	88	97	86	95	84	94	83	92	92	...
(e/D = 2.0) .....	109	121	107	119	105	117	103	115	115	...
$e$ , percent (S-basis):										
LT .....	30	...	30	...	30	...	30	...	30	30
$E$ , 10 <sup>3</sup> ksi .....	29.8									
$E_c$ , 10 <sup>3</sup> ksi .....	29.8									
$G$ , 10 <sup>3</sup> ksi .....	11.8									
$\mu$ .....	0.28									
Physical Properties:										
$\omega$ , lb/in. <sup>3</sup> .....	0.305									
$C$ , $K$ , and $\alpha$ .....	See Figure 6.3.3.0									

a S-basis. The rounded  $T_{99}$  values are higher than specification values as follows:  $F_{tu}(\leq 0.062) = 123$  ksi,  $F_{tu}(0.063-0.109) = 122$  ksi, and  $F_{tu}(0.110-0.140) = 121$  ksi.

b Bearing values are “dry pin” values per Section 1.4.7.1.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 6.3.3.0(c). Design Mechanical and Physical Properties of Inconel 625 Bar**

Specification .....	AMS 5666			
Form .....	Bar			
Condition .....	Annealed			
Thickness or diameter, in. ....	0.500-0.999	1.000-1.999	2.000-2.999	3.000-3.999
Basis .....	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	120	120	120	120
ST .....	...	...	118	118
$F_{ty}$ , ksi:				
L .....	60	60	60	60
ST .....	...	...	57	57
$F_{cy}$ , ksi:				
L .....	60	59	56	53
ST .....	...	...	60	60
$F_{su}$ , ksi .....	79	79	79	79
$F_{bru}^a$ , ksi:				
(e/D = 1.5) .....	192	192	192	192
(e/D = 2.0) .....	234	234	234	234
$F_{bry}^a$ , ksi:				
(e/D = 1.5) .....	88	88	88	88
(e/D = 2.0) .....	102	102	102	102
$e$ , percent (S-basis):				
L .....	30	30	30	30
$E$ , $10^3$ ksi .....	29.8			
$E_c$ , $10^3$ ksi .....	29.8			
$G$ , $10^3$ ksi .....	11.8			
$\mu$ .....	0.28			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.305			
$C$ , $K$ , and $\alpha$ .....	See Figure 6.3.3.0			

a Bearing values are "dry pin" values per Section 1.4.7.1.

## MIL-HDBK-5H

1 December 1998




Figure 6.3.3.1.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of annealed Inconel 625 sheet and bar.




Figure 6.3.3.1.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of annealed Inconel 625 sheet and bar.



MIL-HDBK-5H  
1 December 1998




Figure 6.3.3.1.4(a). Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of annealed Inconel 625.






Figure 6.3.3.1.4(b). Effect of temperature on Poisson's ratio ( $\mu$ ) for annealed Inconel 625 bar.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 6.3.3.1.6(a). Typical tensile stress-strain curves for annealed Inconel 625 sheet at room and elevated temperatures.**




**Figure 6.3.3.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for annealed Inconel 625 sheet at room temperature.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 6.3.3.1.6(c). Typical tensile stress-strain curves for annealed Inconel 625 bar at room temperature.**




**Figure 6.3.3.1.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for annealed Inconel 625 bar at room temperature.**



## MIL-HDBK-5H

1 December 1998



**Figure 6.3.3.1.8(a). Best-fit S/N curves for annealed unnotched Inconel 625 bar, longitudinal direction.**

Correlative Information for Figure 6.3.3.1.8(a)

Product Form: Bar, 3/4-inch diameter

No. of Heats/Lots: 1

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                   133.2        73.8        RT

Equivalent Stress Equation:  
 $\log N_f = 24.49 - 9.62 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.42}$

Specimen Details: Unnotched  
                               0.250-inch diameter

Standard Deviation in log(Life) = 22.71 (1/ $S_{eq}$ )

Surface Condition: Longitudinally polished

Adjusted  $R^2$  = 90%

Reference:        6.3.3.1.8(a)


Sample Size = 27

Test Parameters:  
 Loading - Axial  
 Frequency - Unspecified  
 Temperature - RT  
 Environment - Air

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 6.3.3.1.8(b). Best-fit S/N curves for annealed notched Inconel 625 bar,  $K_t = 3.0$ , longitudinal direction.**

Correlative Information for Figure 6.3.3.1.8(b)

Product Form: Bar, 3/4-inch diameter

No. of Heats/Lots: 1

Properties:    TUS, ksi    TYS, ksi    Temp., °F  
                     133.2       73.8       RT

Equivalent Stress Equation:  
 $\log N_f = 19.08 - 7.70 \log (S_{eq})$   
 $S_{eq} = S_{max} (1-R)^{0.45}$

Specimen Details: V-Groove,  $K_t = 3.0$   
                              0.375-inch gross diameter  
                              0.250-inch net diameter  
                              0.013-inch root radius  
                              60° flank angle

Standard Deviation in  $\log(\text{Life})$  = 14.31 ( $1/S_{eq}$ )

Adjusted  $R^2$  = 92%

Sample Size = 26

Surface Condition: Polished

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]


Reference:        6.3.3.1.8(a)

Test Parameters:

Loading - Axial  
 Frequency - Unspecified  
 Temperature - RT  
 Atmosphere - Air

## MIL-HDBK-5H

1 December 1998



**Figure 6.3.3.1.8(c). Best-fit S/N curves for annealed unnotched Inconel 625 sheet, long-transverse direction.**

Correlative Information for Figure 6.3.3.1.8(c)

Product Form: Sheet, 0.093- and 0.125-inch thick

No. of Heats/Lots: 2

Properties:

TUS, ksi	TYS, ksi	Temp., °F
135.4	74.6	RT
136.7	69.8	

Equivalent Stress Equation:

$$\log N_f = 26.91 - 10.77 \log (S_{eq})$$

$$S_{eq} = S_{max} (1-R)^{0.43}$$

Standard Deviation in log(Life) = 37.39 (1/S<sub>eq</sub>)

Specimen Details: Unnotched  
0.500-inch wide  
0.250-inch wide

Adjusted R<sup>2</sup> = 75%

Surface Condition: As ground

Sample Size = 34

References: 6.3.3.1.8(a) and (b)

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

Test Parameters:

Loading - Axial


Frequency - Unspecified

Temperature - RT

Environment - Air

## MIL-HDBK-5H

1 December 1998



**Figure 6.3.3.1.8(d). Best-fit S/N curves for annealed notched Inconel 625 sheet,  $K_t = 3.0$ , long transverse direction.**

Correlative Information for Figure 6.3.3.1.8(d)

Product Form: Sheet, 0.093- and 0.125-inch thick

No. of Heats/Lots: 2

Properties:

TUS, ksi	TYS, ksi	Temp., °F
135.4	74.6	RT
136.7	69.8	

Equivalent Stress Equation:

$$\log N_f = 10.35 - 3.56 \log (S_{eq} - 22.89)$$

$$S_{eq} = S_{max} (1-R)^{0.64}$$

Standard Deviation in log(Life) = 10.52 (1/ $S_{eq}$ )

Specimen Details: Edge notched,  $K_t = 3.0$   
 0.625-inch gross width  
 0.030-inch root radius  
 0.375-inch net width  
 60° flank angle

Adjusted  $R^2$  = 96%

Sample Size = 37

Surface Condition: As ground

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

References: 6.3.3.1.8(a) and (b)

Test Parameters:

Loading - Axial  
 Frequency - Unspecified  
 Temperature - RT  
 Atmosphere - Air

**MIL-HDBK-5H****1 December 1998****6.3.4 INCONEL 706**

**6.3.4.0 Comments and Properties** — Inconel 706 is a vacuum-melted precipitation-hardened, nickel-base alloy with characteristics similar to Inconel 718 except that Inconel 706 has greatly improved machinability. The alloy has good formability and weldability. Like Inconel 718, Inconel 706 has excellent resistance to postweld strain-age cracking.

Depending upon choice of heat treatment, this alloy may be used for applications requiring either (1) high resistance to creep and stress rupture up to 1300°F or (2) high-tensile strength at cryogenic temperatures or elevated temperatures for short times. The creep-resistant heat treatment is characterized by an intermediate stabilizing treatment before precipitation hardening. Inconel 706 also has good resistance to oxidation and corrosion over a broad range of temperatures and environments.

Because of close relationship between heat treatment properties and application, the form and applications are listed with specifications in Table 6.3.4.0(a). Room-temperature mechanical and physical properties are in Table 6.3.4.0(b). The effect of temperature on physical properties is shown in Figure 6.3.4.0.

**Table 6.3.4.0(a). Material Specifications for Inconel 706**

Specification	Form	Application	
AMS 5605	Sheet, strip, and plate	Tensile	1800°F solution treated
AMS 5606	Sheet, strip, and plate	Creep-rupture	1750°F solution treated
AMS 5701	Bar, forging, and ring	Tensile	1800°F solution treated
AMS 5702	Bar, forging, and ring	Creep-rupture	1750°F solution treated
AMS 5703	Bar, forging, and ring	Creep-rupture	1750°F solution treated, stabilized and precipitation treated

**6.3.4.1 Solution-Treated and Aged Condition (Creep Rupture Heat Treatment)**—


Effect of temperature on mechanical properties is shown in Figures 6.3.4.1.1, 6.3.4.1.4, and 6.3.4.1.5. Typical tensile stress-strain curves are shown in Figure 6.3.4.1.6(a) and typical compressive stress-strain and tangent-modulus curves in Figure 6.3.4.1.6(b). A full-range tensile stress-strain curve is shown in Figure 6.3.4.1.6(c). Stress-rupture properties are specified at 1200°F; the appropriate specification should be consulted for detailed requirements.

**MIL-HDBK-5H****1 December 1998****Table 6.3.4.0(b). Design Mechanical and Physical Properties of Inconel 706**


Specification .....	AMS 5605		AMS 5606	AMS 5701		AMS 5702 and AMS 5703	
Form .....	Sheet, strip, and plate			Bar and forging			
Condition .....	Heat treated per indicated specification						
Thickness or diameter, in. ....	≤0.187	0.188-1.000	All	<2.500	2.500-4.000	<2.500	2.500-4.000
Basis .....	S	S	S	S	S	S	S
Mechanical Properties:							
$F_{tu}$ , ksi:							
L .....	...	...	...	170	170	170	165
LT .....	175	170	170	...	...	...	...
$F_{ty}$ , ksi:							
L .....	...	...	...	140	135	130	130
LT .....	145	140	135	...	...	...	...
$F_{cy}$ , ksi:							
L .....	...	...	...	146	141	136	136
LT .....	152	146	141	...	...	...	...
$F_{su}$ , ksi .....	109	106	106	106	106	106	103
$F_{bru}^a$ , ksi:							
(e/D = 1.5) .....	271	263	263	263	263	263	256
(e/D = 2.0) .....	344	334	334	334	334	334	325
$F_{bry}$ , ksi:							
(e/D = 1.5) .....	202	195	188	195	188	181	181
(e/D = 2.0) .....	243	234	226	234	226	218	218
$e$ , percent:							
L .....	...	...	...	12	12	12	12
LT .....	12	12	12	...	...	...	...
$RA$ , percent:							
L .....	...	...	...	15	15	15	15
$E$ , 10 <sup>3</sup> ksi .....	30.4						
$E_c$ , 10 <sup>3</sup> ksi .....	30.4						
$G$ , 10 <sup>3</sup> ksi .....	11.0						
$\mu$ .....	0.38						
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> .....	0.292						
$C$ , $K$ , and $\alpha$ .....	See Figure 6.3.4.0						

a Bearing values are “dry pin” values per Section 1.4.7.1.


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 6.3.4.0. Effect of temperature on the physical properties of solution-treated and aged Inconel 706.**



**Figure 6.3.4.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of solution treated and aged (creep rupture heat treatment) of Inconel 706.**

**MIL-HDBK-5H****1 December 1998**


**Figure 6.3.4.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of Inconel 706.**




**Figure 6.3.4.1.5. Effect of temperature on the elongation (e) of solution treated and aged Inconel 706 (creep rupture heat treatment).**



**MIL-HDBK-5H**  
**1 December 1998**




**Figure 6.3.4.1.6(a). Typical tensile stress-strain curves for solution-treated and aged Inconel 706 (creep rupture heat treatment) forged bar.**



**Figure 6.3.4.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for solution-treated and aged Inconel 706 (creep rupture heat treatment) forged bar.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 6.3.4.1.6(c). Typical tensile stress-strain curve (full range) for Inconel 706 bar and sheet at room temperature (creep rupture heat treatment).**

**MIL-HDBK-5H****1 December 1998****6.3.5 INCONEL 718**


**6.3.5.0 Comments and Properties** — Inconel 718 is a vacuum-melted, precipitation-hardened nickel-base alloy. It can be welded easily and excels in its resistance to strain-age cracking. It is also readily formable. Depending on choice of heat treatments, this alloy finds applications requiring either (1) high resistance to creep and stress rupture to 1300°F or (2) high strength at cryogenic temperatures. It also has good oxidation resistance up to 1800°F. Inconel 718 is available in all wrought forms and investment castings.

Because of the close relationship between heat treatment, properties, and applications, both the product form and application are listed with the specifications in Table 6.3.5.0(a). Room-temperature mechanical and physical properties are presented in Tables 6.3.5.0(b) through (d). The effect of temperature on physical properties is presented in Figure 6.3.5.0.

**Table 6.3.5.0(a). Material Specifications for Inconel 718**

Specification	Form	Application
AMS 5589	Tubing	Creep-rupture
AMS 5590	Tubing	Short-time
AMS 5596	Sheet, strip, plate	Creep-rupture
AMS 5597	Sheet, strip, plate	Short-time
AMS 5662, 5663	Bar, forging	Creep-rupture
AMS 5664	Bar, forging	Short-time
AMS 5383	Investment castings	Short-time

**6.3.5.1 Solution-Treated and Aged Condition** — Elevated-temperature curves are presented in Figures 6.3.5.1.1 and 6.3.5.1.4(a) through (c). Typical tensile and compressive stress-strain curves as well as typical compressive tangent-modulus curves for sheet and castings are shown in Figures 6.3.5.1.6(a) through (c). Figure 6.3.5.1.6(d) is a typical stress-strain curve (full range) for Inconel 718 investment casting. Creep and stress-rupture curves for forging are shown in Figures 6.3.5.1.7(a) through (e). Supplemental creep and stress-rupture information for forging is presented in Table 6.3.5.1.7. Fatigue S/N curves are presented in Figures 6.3.5.1.8(a) through (g). Fatigue-crack-propagation data for die forging and plate are presented in Figures 6.3.5.1.9(a) through (c).

**Figure 6.3.5.0. Effect of temperature on the physical properties of Inconel 718.**

**MIL-HDBK-5H**  
**1 December 1998**

**Table 6.3.5.0(b). Design Mechanical and Physical Properties of Inconel 718**

Specification . . . . .	AMS 5596				AMS 5597	AMS 5589	AMS 5590
	Sheet		Plate		Sheet and plate	Tubing	
	Solution treated and aged per indicated specification						
	0.010-0.187		0.188-0.249	0.250-1.000	0.010-1.000	O.D. > 0.125 Wall > 0.015	
Form . . . . .	A		B	S	S	S	S
Condition . . . . .							
Thickness, in. . . . .	0.010-0.187		0.188-0.249	0.250-1.000	0.010-1.000	O.D. > 0.125 Wall > 0.015	
Basis . . . . .	A	B	S	S	S	S	S
Mechanical Properties <sup>a</sup> :							
$F_{tu}$ , ksi:							
L . . . . .	180	192	180	...	...	185	170
LT . . . . .	180 <sup>c</sup>	191	180	180	180	...	...
$F_{ty}$ , ksi:							
L . . . . .	145	156	148	...	...	150	145
LT . . . . .	147	158	150	150	150	...	...
$F_{cy}$ , ksi:							
L . . . . .	155	167	158	...	...	...	...
LT . . . . .	158	170	161	...	...	...	...
$F_{su}$ , ksi . . . . .	124	132	124	...	...	...	...
$F_{bru}^b$ , ksi:							
(e/D = 1.5) . . . . .	291	309	291	...	...	...	...
(e/D = 2.0) . . . . .	380	403	380	...	...	...	...
$F_{bry}^b$ , ksi:							
(e/D = 1.5) . . . . .	208	223	212	...	...	...	...
(e/D = 2.0) . . . . .	241	259	246	...	...	...	...
$e$ , percent (S-basis):							
L . . . . .	...	...	...	...	...	12	15
LT . . . . .	12	...	12	12	12	...	...
$E$ , 10 <sup>3</sup> ksi . . . . .	29.4						
$E_c$ , 10 <sup>3</sup> ksi . . . . .	30.9						
$G$ , 10 <sup>3</sup> ksi . . . . .	11.4						
$\mu$ . . . . .	0.29						
Physical Properties:							
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.297						
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 6.3.5.0						

a Design allowables were based upon data from samples of material, supplied in the solution treated condition, which were aged to demonstrate heat treatment response by suppliers. Properties obtained by the user may be different, if the material has been formed or otherwise cold worked.

b Bearing values are "dry pin" values per Section 1.4.7.1.

c S-basis. The rounded  $T_{99}$  value is 183 ksi.

**MIL-HDBK-5H****1 December 1998****Table 6.3.5.0(c). Design Mechanical and Physical Properties of Inconel 718 Bar and Forging**

Specification	AMS 5662 and AMS 5663							AMS 5664		
Form	Bar						Forging	Bar	Forging	
Condition	Solution treated and aged per indicated specification									
Thickness, in.	0.250-1.000	1.001-1.500	1.501-2.000	2.001-2.500	2.501-3.000	3.001-4.000	4.001-5.000	≤5.000	≤10.000	≤10.000
Basis	S	S	S	S	S	S	S	S	S	S
Mechanical Properties:										
$F_{tu}$ , ksi:										
L	185	185	185	185	185	185	185	185	185	180
LT <sup>b</sup>	180	180	180	180	180	180	180	180	180	180
ST <sup>b</sup>	...	...	...	...	180	180	180	...	...	180
$F_{ty}$ , ksi:										
L	150	150	150	150	150	150	150	150	150	150
LT <sup>b</sup>	150	150	150	150	150	150	150	150	150	150
ST <sup>b</sup>	...	...	...	...	146	150	150	...	...	150
$F_{cy}$ , ksi:										
L	156	156	156	156	156	156	156	...	...	...
ST	...	...	...	156	156	156	156	...	...	...
$F_{su}$ , ksi	111	114	116	118	119	121	123	...	...	...
$F_{bru}^a$ , ksi:										
(e/D = 1.5)	309	309	309	309	309	309	309	...	...	...
(e/D = 2.0)	394	394	394	394	394	394	394	...	...	...
$F_{bry}^a$ , ksi:										
(e/D = 1.5)	216	216	216	216	216	216	216	...	...	...
(e/D = 2.0)	257	257	257	257	257	257	257	...	...	...
$e$ , percent:										
L	12	12	12	12	12	12	12	12	10	12
LT <sup>b</sup>	6	6	6	6	6	6	6	10	10	12
ST <sup>b</sup>	...	...	...	...	6	6	6	...	10	12
$RA$ , percent:										
L	15	15	15	15	15	15	15	15	12	15
LT <sup>b</sup>	8	8	8	8	8	8	8	12	12	15
ST <sup>b</sup>	...	...	...	...	8	8	8	...	12	15
$E$ , 10 <sup>3</sup> ksi:										
L	...									
LT	...									
$E_c$ , 10 <sup>3</sup> ksi:										
L	...									
LT	...									
$G$ , 10 <sup>3</sup> ksi	...									
$\mu$	...									
Physical Properties:										
$\omega$ , lb/in. <sup>3</sup>	0.297									
$C$ , $K$ , and $\alpha$	See Figure 6.3.5.0									

a Bearing values are "dry pin" values per Section 1.4.7.1.

b Applicable providing LT or ST direction is ≥ 2.500 inches.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 6.3.5.0(d). Design Mechanical and Physical Properties of Inconel 718 Investment Castings**

Specification .....	AMS 5383
Form .....	Investment Casting
Condition .....	ST
Location within casting .....	Any
Thickness, in. ....	≤0.500
Basis .....	S
Mechanical Properties:	
$F_{tu}$ , ksi .....	120
$F_{ty}$ , ksi .....	105
$F_{cy}$ , ksi .....	105
$F_{su}$ , ksi .....	88 <sup>a</sup>
$F_{bru}^b$ , ksi:	
(e/D = 1.5) .....	202
(e/D = 2.0) .....	248
$F_{bry}^b$ , ksi:	
(e/D = 1.5) .....	161
(e/D = 2.0) .....	188
$e$ , percent .....	3
$RA$ , percent .....	8
$E$ , 10 <sup>3</sup> ksi .....	29.4
$E_c$ , 10 <sup>3</sup> ksi .....	30.9
$G$ , 10 <sup>3</sup> ksi .....	11.4
$\mu$ .....	0.29
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.297
$C$ , $K$ , and $\alpha$ .....	See Figure 6.3.5.0

a Determined in accordance with ASTM Procedure B769.

b Bearing values are “dry pin” values per Section 1.4.7.1.

## MIL-HDBK-5H

1 December 1998




Figure 6.3.5.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and tensile yield strength ( $F_{ty}$ ) of solution-treated and aged Inconel 718.



MIL-HDBK-5H  
1 December 1998




Figure 6.3.5.1.4(a). Effect of temperature on dynamic tensile modulus (E) of solution-treated and aged Inconel 718.





Figure 6.3.5.1.4(b). Effect of temperature on dynamic shear modulus (G) of solution-treated and aged Inconel 718.




**MIL-HDBK-5H**  
**1 December 1998**




**Figure 6.3.5.1.4(c). Effect of temperature on Poisson's ratio ( $\mu$ ) for solution-treated and aged Inconel 718.**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 6.3.5.1.6(a). Typical tensile stress-strain, compressive stress-strain, and compressive tangent-modulus curves for solution-treated and aged Inconel 718 sheet (AMS 5596) at room temperature.**



**Figure 6.3.5.1.6(b). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for solution-treated and aged (creep-rupture application) Inconel 718 bar (AMS 5662 and AMS 5663) at room temperature.**

**MIL-HDBK-5H****1 December 1998**


**Figure 6.3.5.1.6(c). Typical tensile stress-strain, compressive stress-strain, and compressive tangent-modulus curves for solution treated and aged Inconel 718 investment casting (AMS 5383) at room temperature.**

**MIL-HDBK-5H****1 December 1998**

**Figure 6.3.5.1.6(d). Typical tensile stress-strain curve (full range) for solution treated and aged Inconel 718 investment casting (AMS 5383) at room temperature.**

## MIL-HDBK-5H

1 December 1998



**Figure 6.3.5.1.7(a). Average isothermal 0.10% creep curves for Inconel 718 forging.**

Correlative Information for Figure 6.3.5.1.7(a)

Makeup of Data Collection:

Heat Treatment: 2 [See Table 6.3.5.1.7(f)]  
 Number of Vendors = Unknown  
 Number of Lots = 2  
 Number of Test Laboratories = 1  
 Number of Tests = 32

Specimen Details:

Type - Unnotched round bar  
 Gage Length - N.A.  
 Gage Thickness - 1/4" - 3/8"

0.10 Percent Creep Equation:

$$\begin{aligned} \log t &= c + b_1 T + b_2 X + b_3 X^2 + b_4 X^3 \\ T &= ^\circ\text{R} \\ X &= \log(\text{stress, ksi}) \\ c &= 185.16 \\ b_1 &= 0.01778 \\ b_2 &= -255.25 \\ b_3 &= 146.28 \\ b_4 &= -28.65 \end{aligned}$$


Analysis Details:

Inverse Matrix = [See Table 6.3.5.1.7(f)]  
 Standard Deviation = 0.99  
 Standard Error of Estimate = 0.56

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 6.3.5.1.7(b). Average isothermal 0.20% creep curves for Inconel 718 forging.**

Correlative Information for Figure 6.3.5.1.7(b)

Makeup of Data Collection:

Heat Treatment: 2 [See Table 6.3.5.1.7(f)]  
 Number of Vendors = Unknown  
 Number of Lots = 2  
 Number of Test Laboratories = 1  
 Number of Tests = 31

Specimen Details:

Type - Unnotched round bar  
 Gage Length - N.A.  
 Gage Thickness - 1/4" - 3/8"

0.20 Percent Creep Equation:

$$\begin{aligned} \text{Log } t &= c + b_1 T + b_2 X + b_3 X^2 + b_4 X^3 \\ T &= ^\circ\text{R} \\ X &= \text{log (stress, ksi)} \\ c &= 185.67 \\ b_1 &= -0.01778 \\ b_2 &= -255.25 \\ b_3 &= 146.28 \\ b_4 &= -28.65 \end{aligned}$$

Analysis Details:


Inverse Matrix = [See Table 6.3.5.1.7(f)]  
 Standard Deviation = 0.98  
 Standard Error of Estimate = 0.41

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 6.3.5.1.7(c). Average isothermal 0.50% creep curves for Inconel 718 forging.**

Correlative Information for Figure 6.3.5.1.7(c)

Makeup of Data Collection:

Heat Treatment: 2 [See Table 6.3.5.1.7(f)]  
 Number of Vendors = Unknown  
 Number of Lots = 2  
 Number of Test Laboratories = 1  
 Number of Tests = 22

Specimen Details:

Type - Unnotched round bar  
 Gage Length - N.A.  
 Gage Thickness - 1/4" - 3/8"


0.50 Percent Creep Equation:

$$\begin{aligned} \text{Log } t &= c + b_1 T + b_2 X + b_3 X^2 + b_4 X^3 \\ T &= ^\circ\text{R} \\ X &= \log (\text{stress, ksi}) \\ c &= 185.75 \\ b_1 &= -0.01778 \\ b_2 &= -255.25 \\ b_3 &= 146.28 \\ b_4 &= -28.65 \end{aligned}$$

Analysis Details:

Inverse Matrix = [See Table 6.3.5.1.7(f)]  
 Standard Deviation = 1.10  
 Standard Error of Estimate = 0.34

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998****Figure 6.3.5.1.7(d). Average isothermal 5.00% creep curves for Inconel 718 forging.**Correlative Information for Figure 6.3.5.1.7(d)Makeup of Data Collection:

Heat Treatment: 2 [See Table 6.3.5.1.7(f)]  
 Number of Vendors = Unknown  
 Number of Lots = 2  
 Number of Test Laboratories = 1  
 Number of Tests = 24

Specimen Details:

Type - Unnotched round bar  
 Gage Length - N.A.  
 Gage Thickness - 1/4" - 3/8"

5.00 Percent Creep Equation:


$$\begin{aligned} \text{Log } t &= c + b_1 T + b_2 X + b_3 X^2 + b_4 X^3 \\ T &= ^\circ\text{R} \\ X &= \log (\text{stress, ksi}) \\ c &= 186.16 \\ b_1 &= -0.01778 \\ b_2 &= -255.25 \\ b_3 &= 146.28 \\ b_4 &= -28.65 \end{aligned}$$

Analysis Details:

Inverse Matrix = [See Table 6.3.5.1.7(f)]  
 Standard Deviation = 1.02  
 Standard Error of Estimate = 0.37

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



**MIL-HDBK-5H****1 December 1998****Figure 6.3.5.1.7(e). Average isothermal stress rupture curves for Inconel 718 forging.**Correlative Information for Figure 6.3.5.1.7(e)Makeup of Data Collection:

Heat Treatment: 2 [See Table 6.3.5.1.7(f)]  
 Number of Vendors = Unknown  
 Number of Lots = 7  
 Number of Test Laboratories = 2  
 Number of Tests = 162

Specimen Details:

Type - Unnotched round bar  
 Gage Length - N.A.  
 Gage Thickness - 1/4" - 3/8"

Stress Rupture Creep Equation:

$$\text{Log } t = c + b_1 T + b_2 X + b_3 X^2 + b_4 X^3$$

$T = ^\circ\text{R}$   
 $X = \log (\text{stress, ksi})$   
 $c = 186.27$   
 $b_1 = -0.01778$   
 $b_2 = -255.25$   
 $b_3 = 146.28$   
 $b_4 = -28.65$

Analysis Details:

Standard Deviation = 0.63  
 Standard Error of Estimate = 0.29  
 Within Heat Treatment Variance = 0.071  
 Ratio of Between to Within Heat Treatment  
 Variance = (at spec pt.) <0.10

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**Table 6.3.5.1.7. Supplemental Information on the Creep and Stress Rupture Properties of Inconel 718 Forging**


Heat Treatment Details				
Heat Treatment No.	Cycle No.	Temperature, °F	Time, Hours	Cool
2	1	1800	1	AC, WQ
	2	1325	8	FC (100°F/hr)
	3	1150	8	AC
21	1	1700-1850	1	AC
	2	1325	8	FC (100°F/hr)
	3	1150	8	AC

Stress Rupture Equation and Inverse Matrix for the Creep Stress = 0.10, 0.20, 0.50, and 5.00% and Stress Rupture Conditions

$$\log t = c + b_1T + b_2X + b_3X^2 + b_4X^3 + b_5Y_1 + b_6Y_2 + b_7Y_3 + b_8Y_4 + b_9Y_5$$

where  $Y_1 = 1$ ;  $Y_2, Y_3, Y_4, Y_5 = 0$  for Creep Strain = 0.10% Data  
 $Y_2 = 1$ ;  $Y_1, Y_3, Y_4, Y_5 = 0$  for Creep Strain = 0.20% Data  
 $Y_3 = 1$ ;  $Y_1, Y_2, Y_4, Y_5 = 0$  for Creep Strain = 0.50% Data  
 $Y_4 = 1$ ;  $Y_1, Y_2, Y_3, Y_5 = 0$  for Creep Strain = 5.00% Data  
 $Y_1, Y_2, Y_3, Y_4, Y_5 = 0$  for Stress Rupture Data

Column Row	1	2	3	4	5	6	7	8	9
1	1.809E+00	-1.108E-03	-1.978E+00	6.499E-01	-5.748E-02	-1.606E+00	-1.444E+00	-1.015E+00	-9.777E-01
2	-1.108E-03	6.834E-07	1.212E-03	-3.979E-04	3.517E-05	9.843E-04	8.852E-04	6.219E-04	5.993E-04
3	-1.978E+00	1.212E-03	3.482E+00	-1.657E+00	2.032E-01	1.634E+00	1.359E+00	6.886E-01	5.921E-01
4	6.499E-01	-3.979E-04	-1.657E+00	9.145E-01	-1.220E-01	-4.892E-01	-3.610E-01	-6.305E-02	3.594E-03
5	-5.748E-02	3.517E-05	2.032E-01	-1.220E-01	1.697E-02	3.801E-02	2.248E-02	-1.245E-02	-2.618E-02
6	-1.606E+00	9.843E-04	1.634E+00	-4.892E-01	3.801E-02	1.471E+00	1.303E+00	9.401E-01	9.124E-01
7	-1.444E+00	8.852E-04	1.359E+00	-3.610E-01	2.248E-02	1.303E+00	1.222E+00	8.806E-01	8.600E-01
8	-1.015E+00	6.219E-04	6.886E-01	-6.305E-02	-1.245E-02	9.401E-01	8.806E-01	7.491E-01	6.987E-01
9	-9.777E-01	5.993E-04	5.921E-01	3.594E-03	-2.618E-02	9.124E-01	8.600E-01	6.987E-01	1.195E+00

**MIL-HDBK-5H****1 December 1998**

**Figure 6.3.5.1.8(a). Best-fit S/N curves for unnotched Inconel 718 sheet at room temperature, long transverse direction.**

Correlative Information for Figure 6.3.5.1.8(a)

Product Form: Sheet, 0.066-inch and  
0.109-inch

<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp. °F</u>
	197.0	164.0	RT
	208.7	184.2	RT

Specimen Details: Unnotched  
0.30-inch net width  
0.5-inch net width

Heat Treatment: See AMS 5596

Surface Condition: #400 grit belt polished

References: 6.2.1.1.8 and 6.3.5.1.8(a)

Test Parameters:

Loading—Axial  
Frequency—Unspecified  
Temperature—RT  
Environment—Air

No. of Heats/Lots: 2

Equivalent Stress Equation:

$\log N_f = 8.63 - 2.07 \log (S_{eq} - 58.48)$

$S_{eq} = S_{max}(1-R)^{.58}$

Standard Deviation in Log (Life) = 26.73 (1/ $S_{eq}$ )


$R^2 = 90.3\%$

Sample Size = 53

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

## MIL-HDBK-5H

1 December 1998



**Figure 6.3.5.1.8(b). Best-fit S/N curves for notched,  $K_t = 3.0$ , Inconel 718 sheet at room temperature, long transverse direction.**

Correlative Information for Figure 6.3.5.1.8(b)

Product Form: Sheet, 0.066-inch and  
0.109-inch

<u>Properties</u> :	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>Temp, °F</u>
	197.0	164.0	RT
	208.7	184.2	RT

Specimen Details: Notched 60° V-Groove  
 $K_t = 3.0$   
 0.30-inch net width  
 0.22-inch root width  
 0.625-inch net width  
 0.030-inch root radius

Heat Treatment: See AMS 5596

Surface Condition: As machined

References: 6.2.1.1.8 and 6.3.5.1.8(a)

Test Parameters:

Loading—Axial  
 Frequency—Unspecified  
 Temperature—RT  
 Environment—Air


No. of Heats/Lots: 2

Equivalent Stress Equation:

$\log N_f = 8.17 - 2.23 \log (S_{eq} - 30.58)$   
 $S_{eq} = S_{max}(1-R)^{.68}$   
 Standard Deviation in Log (Life) = 14.07 (1/ $S_{eq}$ )  
 $R^2 = 93.7\%$

Sample Size = 49

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998**

**Figure 6.3.5.1.8(c). Best-fit S/N curves for unnotched Inconel 718 sheet at 1000 F, long transverse direction.**

Correlative Information for Figure 6.3.5.1.8(c)

Product Form: Sheet, 0.066-inch

Properties: TUS, ksi      TYS, ksi      Temp, °F  
165.0                      141.8                      1000

Specimen Details: Unnotched  
0.30-inch net width

Heat Treatment: See AMS 5596

Surface Condition: #400 grit belt polished

Reference: 6.2.1.1.8

Test Parameters:

Loading—Axial  
Frequency—60 Hz  
Temperature—1000 °F  
Environment—Air

No. of Heats/Lots: 1

Equivalent Stress Equation:

$\text{Log } N_f = 23.51 - 10.57 \text{ Log } (S_{eq} - 50)$

$S_{eq} = S_{max}(1-R)^{0.62}$

Standard Error of Estimate = 0.414

Standard Deviation in Life = 0.776


$R^2 = 71.5\%$

Sample Size = 21

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]





**MIL-HDBK-5H****1 December 1998**

**Figure 6.3.5.1.8(f). Best-fit S/N curves for unnotched Inconel 718 bar and plate at room temperature, longitudinal direction.**

Correlative Information for Figure 6.3.5.1.8(f)

Product Form: Bar, 0.75-inch diameter; plate, 0.5-, 0.75-, and 1.0-inch thick

Properties:

TUS, ksi	TYS, ksi	Temp, °F
204.4	177.7	RT
200.0	166.7	RT

Specimen Details: Unnotched  
0.250-inch diameter  
0.200-inch diameter

Heat Treatment: See AMS 5662 and AMS 5596

Surface Condition: Unspecified, RMS 8-11

References: 6.3.3.1.8(a) and 6.3.5.1.8(b)

Test Parameters:

Loading - Axial  
Frequency - Unspecified  
Temperature - RT  
Environment - Air

No. of Heats/Lots: 4

Equivalent Stress Equation:

$$\log N_f = 8.18 - 2.07 \log (S_{eq} - 63.0)$$

$$S_{eq} = S_a + 0.40 S_m$$

$$\text{Standard Deviation in Log (Life)} = 38.56 (1/S_{eq})$$

$$R^2 = 67.7\%$$


Sample Size = 44

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]



## MIL-HDBK-5H

1 December 1998



**Figure 6.3.5.1.8(g). Best-fit S/N curves for notched,  $K_t = 3.0$ , Inconel 718 bar at room temperature, longitudinal direction.**

Correlative Information for Figure 6.3.5.1.8(g)

Product Form: Bar, 0.75-inch diameter

Properties:  $T_{US}$ , ksi       $T_{YS}$ , ksi       $Temp$ , °F  
204.4                      177.7                      RT

Specimen Details: Notched, 60° V Notch  
0.252-inch diameter  
0.013-inch diameter

Heat Treatment: See AMS 5662 and AMS 5596

Surface Condition: Unspecified

Reference: 6.3.3.1.8(a)

Test Parameters:

Loading—Axial  
Frequency—Unspecified  
Temperature—RT  
Environment—Air

No. of Heats/Lots: 1

Equivalent Stress Equation:

$$\log N_f = 9.45 - 3.17 \log (S_{eq} - 8.6)$$


$$S_{eq} = S_a + 0.16 S_m$$

$$\text{Standard Deviation in Log (Life)} = 6.97 (1/S_{eq})$$

$$R^2 = 93.6\%$$

Sample Size = 31

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

**MIL-HDBK-5H****1 December 1998**


**Figure 6.3.5.1.9(a). Fatigue-crack-propagation data for Inconel 718 die forging (upset ratio = 5) and 0.5-inch thick plate. [References—6.3.5.1.9(a) through (e).]**

Specimen Thickness: 0.298-0.502 inch  
 Specimen Width: 1.153-2.000 inches  
 Specimen Type: C(T)

Environment: Lab air  
 Temperature: RT  
 Orientation: L-T and T-L

## MIL-HDBK-5H

1 December 1998




**Figure 6.3.5.1.9(b). Fatigue-crack-propagation data for Inconel 718 die forging (upset ratio = 5) and 0.5-inch thick plate. [References—6.3.5.1.9(b) and 6.3.5.1.9(d) through (g).]**

Specimen Thickness: 0.298-0.502 inch  
 Specimen Width: 1.157-2.001 inches  
 Specimen Type: C(T)

Environment: Lab air  
 Temperature: 800-1200 °F  
 Orientation: L-T and T-L

## MIL-HDBK-5H

1 December 1998



**Figure 6.3.5.1.9(c). Fatigue-crack-propagation data for Inconel 718 0.5-inch thick plate. [Reference—6.3.5.1.9(f).]**

Specimen Thickness: 0.298-0.479 inch  
 Specimen Width: 1.151-1.993 inches  
 Specimen Type: C(T)

Environment: Lab air  
 Temperature: 1000 °F  
 Orientation: L-T and T-L

**MIL-HDBK-5H****1 December 1998****6.3.6 INCONEL X-750**

**6.3.6.0 Comments and Properties** — Inconel X-750 is a high-strength oxidation-resistant nickel-base alloy. It is used for parts requiring high strength up to 1000°F or high creep strength up to 1500°F and for low-stressed parts operating up to 1900°F. It is hardenable by various combinations of solution treatment and aging, depending on its form and application. Inconel X-750 is available in all the usual wrought mill forms.

Inconel X-750 can be readily forged between 1900 and 2225°F; “hot-cold” working between 1200 and 1600°F is harmful and should be avoided. This alloy is readily formed but should be solution treated at 1925°F for 7 to 10 minutes after severe forming operations. It is somewhat more difficult to machine than austenitic stainless steels. Rough machining is easier in the solution-treated condition; finish machining in the partly or fully aged condition. Fusion welding is difficult for large section sizes and moderately difficult for small cross sections and sheet. It must be welded in the annealed or solution-treated condition; weldments should be stress relieved at 1650°F for 2 hours before aging. Nickel brazing, followed by precipitation heat treatment of the brazed assembly, results in strength nearly equal to fully heat-treated material.

Oxidation resistance of Inconel X-750 is good to 1900°F; but the beneficial effects of aging are lost above 1500°F. This alloy is subject to attack in sulfur-containing atmospheres.

A variety of heat treatments has been developed for Inconel X-750. Each provides special properties and renders the material in the best metallurgical condition for the intended application. Only two of these heat treatments, for applications requiring high strength up to 1100°F, are described below.

*Annealed and Aged for Sheet, Strip, and Plate* — Mill annealed plus 1300°F for 20 hours, and A.C. per AMS 5542.

*Equalized and Aged for Bar and Forging* — 1625°F for 4 hours, A.C., plus 1300°F for 24 hours, and A.C. per AMS 5667.

Other heat treatments are available for maximum creep-rupture strength.

Some material specifications for Inconel X-750 are shown in Table 6.3.6.0(a). Room-temperature mechanical and physical properties are shown in Table 6.3.6.0(b).

**Table 6.3.6.0(a). Material Specifications for Inconel X-750**

Specification	Form	Condition
AMS 5542	Sheet, strip, and plate	Annealed
AMS 5667	Bar and forging	Equalized

The effect of temperature on the physical properties of this alloy is shown in Figure 6.3.6.0.

**6.3.6.1 Annealed and Aged** — Elevated-temperature curves for tensile and yield ultimate strengths are shown in Figures 6.3.6.1.1 through 6.3.6.1.3.

**6.3.6.2 Equalized and Aged** — Elevated-temperature curves are presented in Figures 6.3.6.2.1(a) and (b), as well as 6.3.6.2.4(a) and (b).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 6.3.6.0(b). Design Mechanical and Physical Properties of Inconel X-750**

Specification .....	AMS 5542				AMS 5667	
Form .....	Strip	Sheet	Plate		Bars and forgings	
Condition .....	Annealed and aged				Equalized and aged	
Thickness or diameter, in. . .	≤0.009	≥0.010	0.010- 0.187	0.188- 4.000	<4.000	4.000- 10.000
Basis .....	S	S	S	S	S	S
Mechanical Properties:						
$F_{tu}$ , ksi:						
L .....	...	...	...	...	165	160
LT .....	150	155	165	155	...	...
$F_{ty}$ , ksi:						
L .....	...	...	...	...	105	100
LT .....	...	...	105	100	...	...
$F_{cy}$ , ksi:						
L .....	...	...	...	...	105	100
LT .....	...	...	105	100	...	...
$F_{su}$ , ksi .....	...	...	107	100	102	99
$F_{bru}$ , ksi:						
(e/D = 1.5) .....	...	...	247	232	247	240
(e/D = 2.0) .....	...	...	313	294	313	304
$F_{bry}$ , ksi:						
(e/D = 1.5) .....	...	...	157	150	157	150
(e/D = 2.0) .....	...	...	189	180	189	180
$e$ , percent:						
L .....	...	...	...	...	20	15
LT .....	...	15	20	20	...	...
RA, percent:						
L .....	...	...	...	...	25	17
$E$ , 10 <sup>3</sup> ksi .....	30.6					
$E_c$ , 10 <sup>3</sup> ksi .....	30.6					
$G$ , 10 <sup>3</sup> ksi .....	11.8					
$\mu$ .....	0.30					
Physical Properties:						
$\omega$ , lb/in. <sup>3</sup> .....	0.298					
$C$ , $K$ , and $\alpha$ .....	See Figure 6.3.6.0					

MIL-HDBK-5H  
1 December 1998




Figure 6.3.6.0. Effect of temperature on the physical properties of Inconel X-750.




Figure 6.3.6.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and tensile yield strength ( $F_{ty}$ ) of Inconel X-750 sheet and plate (AMS 5542).



MIL-HDBK-5H  
1 December 1998




Figure 6.3.6.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of Inconel X-750.




Figure 6.3.6.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of Inconel X-750.



## MIL-HDBK-5H

1 December 1998




Figure 6.3.6.2.1(a). Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) of Inconel X-750 bar (AMS 5667).




Figure 6.3.6.2.1(b). Effect of temperature on the tensile yield strength ( $F_{ty}$ ) of Inconel X-750 bar (AMS 5667).

MIL-HDBK-5H  
1 December 1998




Figure 6.3.6.2.4(a). Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of Inconel X-750.




Figure 6.3.6.2.4(b). Effect of temperature on the shear modulus (G) of Inconel X-750.

**MIL-HDBK-5H****1 December 1998****6.3.7 RENÉ 41**

**6.3.7.0 Comments and Properties** — René 41 is a vacuum-melted precipitation-hardening nickel-base alloy designed for highly stressed parts operating between 1200 and 1800°F. Its applications include afterburner parts, turbine castings, wheels, buckets, and high-temperature bolts and fasteners. René 41 is available in the form of sheet, bars, and forgings.

René 41 is forged between 1900 and 2150°F; small reductions must be made when breaking up an as-cast structure; cracking may be encountered in finishing below 1850°F. René 41 work hardens rapidly, and frequent anneals are required; to anneal, heat rapidly to 1950°F for 30 minutes and quench.

René 41 is difficult to machine. In the soft solution-annealed condition it is gummy; therefore, it should be in the fully aged condition for optimum machinability, and tungsten carbide cutting tools should be used. René 41 can be welded satisfactorily in the solution-treated condition; after welding, the parts should be solution treated for stress relief.

René 41 should not be exposed to temperatures above 2050°F during latter stages of hot working or during subsequent operations, otherwise severe intergranular cracking may be encountered.

The oxidation resistance of René 41 is good to 1800°F. Lengthy exposure above the aging temperature (1400 to 1650°F) results in loss of strength and room-temperature ductility.

Some material specifications for René 41 are shown in Table 6.3.7.0(a). Room temperature mechanical and physical properties are shown in Table 6.3.7.0(b). The effect of temperature on physical properties is shown in Figure 6.3.7.0.

**Table 6.3.7.0(a). Material Specifications for René 41**

Specification	Form	Condition
AMS 5545	Plate, sheet, and strip	Vacuum melted, solution treated
AMS 5712	Bar and forging	Vacuum melted, solution treated and aged
AMS 5713	Bar and forging	Vacuum melted, solution treated and aged

**6.3.7.1 Solution Treated at 1975 ° F and Aged at 1400 ° F Condition** — Tensile and stress-rupture requirements at elevated temperatures are specified for René 41. The appropriate specification should be consulted for detailed requirements. Other elevated-temperature data for René 41 in this condition are presented in Figures 6.3.7.1.1 through 6.3.7.1.5. A creep nomograph for René 41 alloy sheet is shown in Figure 6.3.7.1.7.

**MIL-HDBK-5H****1 December 1998****Table 6.3.7.0(b). Design Mechanical and Physical Properties of René 41**

Specification .....	AMS 5545				AMS 5712 and AMS 5713
	Sheet			Plate	Bar and forging
	Solution treated and aged (1400°F)				
	≤0.020	0.021-0.187		0.188-0.375	≤1.000
Basis .....	S	A <sup>a</sup>	B <sup>a</sup>	S	S
Mechanical Properties:					
$F_{tu}$ , ksi:					
L .....	...	170 <sup>b</sup>	185	...	170
LT .....	160	170 <sup>b</sup>	185	170	...
$F_{ty}$ , ksi:					
L .....	...	123	132	...	130
LT .....	120	123	132	130	...
$F_{cy}$ , ksi:					
L .....	...	132	142	...	133
LT .....	...	135	145	...	...
$F_{su}$ , ksi .....	...	105	114	105	110
$F_{bru}$ , ksi:					
(e/D = 1.5) .....	...	244	266	244	...
(e/D = 2.0) .....	...	310	338	310	...
$F_{bry}$ , ksi:					
(e/D = 1.5) .....	...	197	211	208	...
(e/D = 2.0) .....	...	245	263	259	...
$e$ , percent (S-basis):					
L .....	...	...	...	...	8
LT .....	6	10	...	10	...
$RA$ , percent (S-basis):					
L .....	...	...	...	...	10
$E$ , 10 <sup>3</sup> ksi .....	31.6				
$E_c$ , 10 <sup>3</sup> ksi .....	31.6				
$G$ , 10 <sup>3</sup> ksi .....	12.1				
$\mu$ .....	0.31				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> .....	0.298				
$C$ , $K$ , and $\alpha$ .....	See Figure 6.3.7.0				

a Design allowables were based upon data from samples of material, supplied in solution treated condition, which were aged to demonstrate heat treat response by suppliers. Properties obtained by the user may be different if the material has been formed or otherwise cold worked.

b S-basis. The rounded  $T_{99}$  value is 178 ksi.

MIL-HDBK-5H

1 December 1998






Figure 6.3.7.0. Effect of temperature on the physical properties of René 41.



**MIL-HDBK-5H**  
**1 December 1998**




**Figure 6.3.7.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of René 41.**




**Figure 6.3.7.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of René 41.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 6.3.7.1.3(a). Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) of René 41.**



**Figure 6.3.7.1.3(b). Effect of temperature on the bearing yield strength ( $F_{bry}$ ) of René 41.**

MIL-HDBK-5H  
1 December 1998




Figure 6.3.7.1.4. Effect of temperature on the tensile modulus (E) of René 41.





Figure 6.3.7.1.5. Effect of temperature on the elongation (e) of René 41 (>0.020 thickness) sheet.



## MIL-HDBK-5H

1 December 1998



**Figure 6.3.7.1.7. Typical creep properties of René 41 sheet.**

Correlative Information for Figure 6.3.7.1.7

Equation

Creep Strain, percent:

$$\epsilon = \left( 6.223 \times 10^7 \exp\left(-\frac{50760}{T}\right) \right) \left( \sigma^{0.3928 \exp\left(\frac{2554}{T}\right)} \right) \left( t^{4.1557 \exp\left(\frac{-3934}{T}\right)} \right)^a$$

Temperature (T) = Fahrenheit + 460

Example

Temp., T = 1600°F

Stress,  $\sigma$  = 7.5 ksi

Time, t = 10 hours

Creep Strain,  $\epsilon$  = 0.080

a This equation should only be used in the same temperature ranges indicated in the nomograph. Creep strains computed outside these temperature ranges may yield unreasonable values.

**MIL-HDBK-5H****1 December 1998****6.3.8 WASPALOY**

**6.3.8.0 Comments and Properties** — Waspaloy is a vacuum-melted precipitation-hardened nickel-base alloy which is strengthened by the precipitation of titanium and aluminum compounds and the solid-solution strengthening effects of chromium, molybdenum, and cobalt. The alloy is designed for highly stressed parts operating at temperatures up to 1550°F, such as aircraft gas turbine blades and discs and rocket engine parts. It is available in all the usual mill forms.

The optimum range for forging is 1900 to 2050°F. Avoid working the alloy below 1900°F due to danger of cracking and also decreasing the stress-rupture life. Sufficient soaking time between heating is necessary to ensure complete recrystallization; however, avoid excessive long-time soaking at the high forging temperature. Furnace atmospheres should be either neutral or slightly oxidizing to prevent carburization and to minimize scaling.

Waspaloy is relatively difficult to machine. Drilling, turning, etc., can best be accomplished in solution-treated and partially aged condition. Generally, carbide tools are preferred, and positive feeds are required to avoid work hardening. For finish machining, grinding is preferable.

Waspaloy is susceptible to hot cracking or “hot-shortness” above 2150°F; therefore, extreme care should be exercised in the design of weldments so that restraint can be minimized. Waspaloy should be welded in the annealed condition, with minimum heat input, and with rapid cooling by means of chill bars and gas backup. This alloy has good resistance to oxidation at temperatures up to 1750°F and to combustion products encountered in aircraft gas turbines.

Two heat treatments are used for this material. One is for optimum tensile strength (solution treated 1825 to 1900°F, stabilize 1550°F, 24 hours air cool, and age 16 hours at 1400°F air cool), and the other for stress-rupture properties (solution treated 1975°F, stabilized 1550°F, 24 hours air cool, age 1400°F, 16 hours air cool).

Some material specifications for Waspaloy are shown in Table 6.3.8.0(a). Room-temperature mechanical properties are shown in Table 6.3.8.0(b). Physical properties at room and elevated temperatures are shown in Figure 6.3.8.0.

**Table 6.3.8.0(a). Material Specifications for Waspaloy**

Specification	Form
AMS 5544	Plate, sheet, and strip
AMS 5704	Forgings
AMS 5706	Bar, forging, ring
AMS 5707	Bar, forging, ring
AMS 5708	Bar, forging, ring
AMS 5709	Bar, forging, ring <sup>a</sup>

a Primarily for applications requiring high stress-rupture strength.

**6.3.8.1 Aged Condition** — Stress rupture requirements at elevated temperatures are specified in material specifications. The appropriate specification should be consulted for detailed requirements. The effect of temperature on various mechanical properties is shown in Figures 6.3.8.1.1, 6.3.8.1.4, as well as 6.3.8.1.5(a) and (b). The effect of temperature on the Ramberg-Osgood parameter,  $n$  (tension), is shown in Figure 6.3.8.1.6(a). Typical tensile stress-strain curves are shown in Figure 6.3.8.1.6(b).

**MIL-HDBK-5H****1 December 1998****Table 6.3.8.0(b). Design Mechanical and Physical Properties of Waspaloy**

Specification . . . . .	AMS 5544		AMS 5704	AMS 5706 and AMS 5707
Form . . . . .	Sheet, strip, and plate		Forging	Bar, forging, and ring
Condition . . . . .	Solution, stabilization, and precipitation heat treated			
Thickness, in. . . . .	≤0.020	>0.020	≤3.500	≤3.500
Basis . . . . .	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L . . . . .	...	...	175	160
LT . . . . .	170	175	...	...
$F_{ty}$ , ksi:				
L . . . . .	...	...	120	110
LT . . . . .	110	115	...	...
$F_{cy}$ , ksi:				
L . . . . .	...	...	...	...
LT . . . . .	...	...	...	...
$F_{su}$ , ksi . . . . .	...	...	...	...
$F_{bru}$ , ksi:				
(e/D = 1.5) . . . . .	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...
$F_{bry}$ , ksi:				
(e/D = 1.5) . . . . .	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...
$e$ , percent:				
L . . . . .	...	...	15	15
LT . . . . .	15	20	...	...
$RA$ , percent:				
L . . . . .	...	...	18	18
$E$ , $10^3$ ksi . . . . .	30.6			
$E_c$ , $10^3$ ksi . . . . .	...			
$G$ , $10^3$ ksi . . . . .	...			
$\mu$ . . . . .	...			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.298			
$C$ , Btu/(lb)(°F) . . . . .	See Figure 6.3.8.0			
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft]	See Figure 6.3.8.0			
$\alpha$ , $10^{-6}$ in./in./°F . . . . .	See Figure 6.3.8.0			

MIL-HDBK-5H  
1 December 1998




Figure 6.3.8.0. Effect of temperature on the physical properties of Waspaloy.




Figure 6.3.8.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of Waspaloy.

MIL-HDBK-5H

1 December 1998




Figure 6.3.8.1.4. Effect of temperature on the modulus of elasticity (E) of Waspaloy.




Figure 6.3.8.1.5(a). Effect of temperature on elongation (e) of Waspaloy.



## MIL-HDBK-5H

1 December 1998




Figure 6.3.8.1.5(b). Effect of temperature on reduction in area (RA) of Waspaloy bar and forging.





Figure 6.3.8.1.6(a). Effect of temperature on Ramberg-Osgood parameter (n in tension) of Waspaloy.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 6.3.8.1.6(b). Typical tensile stress-strain curves for Waspaloy at room and elevated temperatures (all products).**

**MIL-HDBK-5H****1 December 1998****6.4 COBALT-BASE ALLOYS**

**6.4.0 GENERAL COMMENTS** — The use of cobalt in wrought heat-resistant alloys is usually limited to additions of cobalt to alloys of other bases. Very few of the heat-resistant alloys can be considered as cobalt base, since cobalt is seldom the predominating element. For airframe applications, some workability is usually required; the alloys considered in this section are limited to those available in wrought form.

**6.4.0.1 Metallurgical Considerations**

*Composition* — The common alloying elements for cobalt are chromium, nickel, carbon, molybdenum, and tungsten. Chromium is added to increase strength and oxidation resistance at very high temperatures; nickel to increase toughness; carbon to increase the hardness and strength, especially when combined with chromium and the other carbide formers, molybdenum and tungsten; molybdenum and tungsten also contribute to solid-solution strengthening.

Vacuum melting is not required for these alloys. For this reason, the cobalt-base alloys are often competitively priced with vacuum-melted nickel-base alloys although the price of cobalt is higher than that of nickel.

*Heat Treatment* — The cobalt-base alloys are heat treated with conventional equipment and fixtures such as those used with austenitic stainless steels. The use of good heat-treating practices is recommended, although this is not so critical as in the case of the nickel-based alloys.

**6.4.0.2 Manufacturing Considerations**

*Forging* — Because these alloys are designed to have very high strength at temperatures near the forging range, they require the use of heavy forging equipment. However, the forgeability of these alloys is good over a fairly wide range of temperatures. Hot-cold working is neither required nor recommended for these alloys.

*Cold Forming* — These alloys, when in the solution-treated condition, have excellent ductility and are readily cold formed. Because of their capacity for work hardening, they require higher forming pressures and frequent anneals.

*Machining* — These alloys are tough and they work harden rapidly; consequently, heavy-duty vibration-free machine tools, sharp cutting tools (high-speed steel or carbide tipped), and low cutting speeds are required.

*Welding* — The weldability of the cobalt-base alloys is comparable with that of the austenitic stainless steels. Welding may be accomplished by all commonly used welding processes. Large or complex weldments require stress relief.

*Brazing* — These alloys can be brazed using the same techniques and precautions applicable to stainless steels and nickel-base alloys. Alloys which contain aluminum or titanium require extremely dry, inert gas atmospheres, very high vacuum or a thin (0.002 to 0.0010-inch thick) nickel plating to prevent surface oxidation. It is also necessary to braze the material in the annealed condition and to keep the stresses low during brazing to avoid embrittlement, especially when brazing with low melting alloys.

**6.4.0.3 Special Precautions** — If the cobalt-base alloys have not been exposed to neutron radiation, no special safety precautions in handling are required. However, neutron irradiation creates a very



**MIL-HDBK-5H****1 December 1998**

dangerous radioactive isotope, cobalt 60, which has a half life of about 5.2 years. Special precautions must be employed to protect personnel from the radioactive material.

**6.4.1 L-605**

**6.4.1.0 Comments and Properties** — L-605, also known as Haynes Alloy 25, is a corrosion and heat-resistant cobalt-base alloy used for moderately stressed parts operating between 1000 and 1900°F. Its applications include gas turbine blades and rotors, combustion chambers, and afterburner parts. L-605 is not hardenable except by cold working and is usually used in the annealed condition. It is available in all the usual mill forms.

L-605 forges moderately well between 1900 and 2250°F. In the annealed condition, it has excellent formability at room temperature; severely formed parts should be annealed at 2225°F for 7 to 10 minutes. L-605 is difficult to machine. Its toughness and capacity for work hardening necessitate the use of sharp tools and low cutting speeds; high-speed steel or carbide cutting tools are recommended. L-605 can be fusion or resistance welded or brazed; large or complex fusion weldment should be stress relieved at 1300°F for 2 hours. This alloy has excellent oxidation resistance up to 1900°F.

Some material specifications for L-605 are shown in Table 6.4.1.0(a). Room-temperature mechanical and physical properties are shown in Table 6.4.1.0(b). The effect of temperature on physical properties is shown in Figure 6.4.1.0.

**Table 6.4.1.0(a). Material Specifications for L-605**

Specification	Form	Condition
AMS 5537	Sheet	Solution treated (annealed)
AMS 5759	Bar and forging	Solution treated (annealed)

**6.4.1.1 Solution Treated Condition** — Elevated temperature properties for this condition are shown in Figures 6.4.1.1.1 through 6.4.1.1.5. A creep nomograph is shown in Figure 6.4.1.1.7. Stress-rupture requirements at elevated temperatures are specified in material specifications. The appropriate specification should be consulted for detailed requirements.

**MIL-HDBK-5H****1 December 1998****Table 6.4.1.0(b). Design Mechanical and Physical Properties of L-605**

Table 6.4.1.0. Design Mechanical and Physical Properties of 2025				
Specification	AMS 5537			AMS 5759
Form	Sheet		Plate	Bar and forging
Condition	Solution treated			
Thickness, in.	0.010-0.187		0.188-0.375	≤1.000
Basis	A	B	S	S
Mechanical Properties:				
$F_u$ , ksi:				
L	126	131	...	125
LT	130	135	130	...
$F_y$ , ksi:				
L	57	62	...	45
LT	55 <sup>a</sup>	60	55	...
$F_{cy}$ , ksi:				
L	41	45	...	42
LT	56	61	...	...
$F_{su}$ , ksi	91	95	91	88
$F_{bru}$ , ksi:				
(e/D = 1.5)	186	193	186	...
(e/D = 2.0)	232	241	232	...
$F_{bry}$ , ksi:				
(e/D = 1.5)	88	96	88	...
(e/D = 2.0)	113	123	113	...
$e$ , percent (S-basis):				
L	...	...	...	30
LT	<sup>b</sup>	...	45	...
$E$ , 10 <sup>3</sup> ksi	32.6			
$E_c$ , 10 <sup>3</sup> ksi	32.6			
$G$ , 10 <sup>3</sup> ksi	12.6			
$\mu$	0.29			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup>	0.330			
$C$ , Btu/(lb)(°F)	0.090 (70-212°F)			
$C$ , $K$ , and $\alpha$	See Figure 6.4.1.0			

a S-basis. The rounded  $T_{99}$  value:  $F_y = 56$  ksi.b 30 -  $\leq 0.020$ ; 35 - 0.021 to 0.032; 40 - 0.033 to 0.043; 45 -  $\geq 0.043$ .

MIL-HDBK-5H  
1 December 1998






Figure 6.4.1.0. Effect of temperature on the physical properties of L-605.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 6.4.1.1.1. Effect of temperature on the tensile ultimate strength ( $F_{tu}$ ) and the tensile yield strength ( $F_{ty}$ ) of L-605.**




**Figure 6.4.1.1.2. Effect of temperature on the compressive yield strength ( $F_{cy}$ ) and the shear ultimate strength ( $F_{su}$ ) of L-605.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 6.4.1.1.3. Effect of temperature on the bearing ultimate strength ( $F_{bru}$ ) and the bearing yield strength ( $F_{bry}$ ) of L-605 sheet.**



**Figure 6.4.1.1.4(a). Effect of temperature on dynamic moduli ( $E$  and  $E_c$ ) of L-605 sheet.**

MIL-HDBK-5H  
1 December 1998




Figure 6.4.1.1.4(b). Effect of temperature on the shear modulus (G) of L-605 sheet.





Figure 6.4.1.1.5. Effect of temperature on the elongation (e) of L-605 (>0.020 thickness) sheet.



**MIL-HDBK-5H****1 December 1998****Figure 6.4.1.1.7. Typical creep properties of L-605 sheet.**Correlative Information for Figure 6.4.1.1.7

Equation

Creep Strain, percent:

$$\epsilon = \left( 3.516 \times 10^8 \exp\left(-\frac{56040}{T}\right) \right) \left( \sigma^{0.2791 \exp\left(\frac{3943}{T}\right)} \right) \left( t^{0.4172 \exp\left(\frac{413.4}{T}\right)} \right)^a$$

Temperature (T) = Fahrenheit + 460

Example

Temp., T = 1600°F

Stress,  $\sigma$  = 8 ksi

Time, t = 10 hours

Creep Strain,  $\epsilon$  = 0.091

- a This equation should only be used in the same temperature ranges indicated in the nomograph. Creep strains computed outside these temperature ranges may yield unreasonable values.

**MIL-HDBK-5H****1 December 1998****6.4.2 HS 188**

**6.4.2.0 Comments and Properties** — HS 188 is a corrosion- and heat-resistant cobalt-base alloy used for moderately stressed parts up to 2100°F. The alloy exhibits outstanding oxidation resistance up to 2100°F resulting from the addition of minute amounts of lanthanum to the alloy system. The alloy exhibits excellent post-aged ductility after prolonged heating of 1000 hours at temperatures up to 1600°F inclusive.

HS 188 is not hardenable except by cold working and is used in the solution-treated condition. The alloy can be forged and welded. Welding can be accomplished by both manual and automatic welding methods including electron beam, gas tungsten air, and resistance welding. Like other cobalt base alloys, machining is difficult necessitating the use of sharp tools and low cutting speeds; high speed steel or carbide cutting tools are recommended. Gas turbine applications include transition ducts, combustion cans, spray bars, flame-holders, and liners.

Material specifications for HS 188 are presented in Table 6.4.2.0(a). Room-temperature mechanical and physical properties are shown in Table 6.4.2.0(b). The effect of temperature on physical properties is shown in Figure 6.4.2.0.

**Table 6.4.2.0(a). Material Specifications for HS 188**

Specification	Form	Condition
AMS 5608	Sheet and plate	Solution treated (annealed)
AMS 5772	Bar and forging	Solution treated (annealed)

**6.4.2.1 Solution-Treated Condition** — Elevated-temperature properties are presented in Figures 6.4.2.1.1(a) and (b), 6.4.2.1.2, 6.4.2.1.4(a) through (c), and 6.4.2.1.5. Typical tensile stress-strain curves at room temperature are presented in Figure 6.4.2.1.6(a). Typical compressive stress-strain and tangent-modulus curves at room and elevated temperatures are presented in Figure 6.4.2.1.6(b). Strain control fatigue data for bar are presented in Figures 6.4.2.1.8(a) through (d).



**MIL-HDBK-5H**  
**1 December 1998**

**Table 6.4.2.0(b). Design Mechanical and Physical Properties of HS 188 Sheet**

Specification .....	AMS 5608	
Form .....	Sheet	
Condition .....	Solution Treated	
Thickness, in. ....	<0.020	0.020-0.187
Basis .....	S	S
Mechanical Properties:		
$F_{tu}$ , ksi:		
L .....	125	125
LT .....	125	125
$F_{ty}$ , ksi:		
L .....	57	57
LT .....	55	55
$F_{cy}$ , ksi:		
L .....	...	...
LT .....	55	55
$F_{su}$ , ksi .....	111	111
$F_{bru}$ , ksi:		
(e/D = 1.5) .....	...	...
(e/D = 2.0) .....	...	...
$F_{bry}$ , ksi:		
(e/D = 1.5) .....	...	...
(e/D = 2.0) .....	...	...
$e$ , percent:		
LT .....	40	45
$E$ , $10^3$ ksi .....	33.6	
$E_c$ , $10^3$ ksi .....	33.6	
$G$ , $10^3$ ksi .....	12.8	
$\mu$ .....	0.31	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> .....	0.324	
$C$ , $K$ , and $\alpha$ .....	See Figure 6.4.2.0	

MIL-HDBK-5H  
1 December 1998




Figure 6.4.2.0. Effect of temperature on the physical properties of HS 188.




Figure 6.4.2.1.1(a). Effect of temperature on tensile ultimate strength (F<sub>tu</sub>) of HS 188 sheet.

MIL-HDBK-5H  
1 December 1998




Figure 6.4.2.1.1(b). Effect of temperature on tensile yield strength ( $F_{ty}$ ) of HS 188 sheet.




Figure 6.4.2.1.2. Effect of temperature on compressive yield strength ( $F_{cy}$ ) of HS 188 sheet.

## MIL-HDBK-5H

1 December 1998




Figure 6.4.2.1.4(a). Effect of temperature on dynamic moduli (E and E<sub>c</sub>) of HS 188.



MIL-HDBK-5H  
1 December 1998




Figure 6.4.2.1.4(b). Effect of temperature on dynamic shear modulus (G) for HS 188.




Figure 6.4.2.1.4(c). Effect of temperature on Poisson's ratio ( $\mu$ ) for HS 188.

## MIL-HDBK-5H

1 December 1998




Figure 6.4.2.1.5. Effect of temperature on elongation (e) of HS 188 sheet.





Figure 6.4.2.1.6(a). Typical tensile stress-strain curves for HS 188 sheet at room temperature.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 6.4.2.1.6(b). Typical compressive stress-strain and compressive tangent-modulus curves for HS 188 sheet at various temperatures.**

MIL-HDBK-5H

1 December 1998




Figure 6.4.2.1.8(a). Best-fit  $\epsilon/N$  curve, cyclic stress-strain curve, and mean stress relaxation curve for HS 188 bar, longitudinal orientation at 800°F.



**MIL-HDBK-5H****1 December 1998**Correlative Information for Figure 6.4.2.1.8(a)Product Form/Thickness:

Bar/0.5-inch-thick diameter

Thermal Mechanical Processing History:

Solution annealed (AMS 5772)

Properties:

<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>E, ksi</u>	<u>Temp., °F</u>
102*	55*		75
		29,766	800

Stress-Strain Equations:

Cyclic (Companion Specimens)

Proportional Limit = 60 ksi

$$(\Delta\sigma/2) = 109 (\Delta\epsilon_p/2)^{0.06}$$

Mean Stress Relaxation

Inadequate data at low strain range  
values

Specimen Details:

Uniform gage test section

0.250-inch diameter

Reference: 3.8.1.1.8Test Parameters:

Strain Rate/Frequency - 20 cpm

Wave Form - Triangular

Temperature - 800 °F

Atmosphere - Air

No. of Heats/Lots: 2Equivalent Strain Equation:

$$\log N_f = 1.678 - 0.905 \log (\Delta\epsilon - 0.00572)$$

Standard Deviation of Log (Life) = 0.00176

(1/ε<sub>eq</sub>)Adjusted R<sup>2</sup> Statistic = 82%Sample Size = 18

[Caution: The equivalent stress model may  
provide unrealistic life predictions for stress  
ratios beyond those represented above.]

---

\* Minimum values from AMS 5772.

MIL-HDBK-5H  
1 December 1998





Figure 6.4.2.1.8(b). Best-fit  $\epsilon/N$  curve and cyclic stress-strain curve for HS 188 bar, longitudinal orientation at 1200°F.

**MIL-HDBK-5H****1 December 1998**Correlative Information for Figure 6.4.2.1.8(b)Product Form/Thickness:

Bar/1.5-inch-thick

Thermal Mechanical Processing History:

Solution annealed (AMS 5772)

Properties:

<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>E, ksi</u>	<u>Temp., °F</u>
120*	55*		75
		20,050	1200

Stress-Strain Equations:

Cyclic (Companion Specimens)

Proportional Limit = 45 ksi

$$(\Delta\sigma/2) = 293 (\Delta\epsilon_p/2)^{0.22}$$

Specimen Details:

Uniform gage test section

0.250-inch diameter

Reference: 3.8.1.1.8Test Parameters:

Strain Rate/Frequency - 20 cpm

Wave Form - Triangular

Temperature - 1200 °F

Atmosphere - Air

No. of Heats/Lots: 1Equivalent Strain Equation:

$$\log N_f = 1.073 - 0.925 \log (\Delta\epsilon - 0.00622)$$

$$\text{Standard Deviation of Log(Life)} = 0.00134 (1/\epsilon_{eq})$$

$$\text{Adjusted } R^2 \text{ Statistic} = 91\%$$

Sample Size = 14

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

---

\* Minimum values from AMS 5772.

MIL-HDBK-5H  
1 December 1998





Figure 6.4.2.1.8(c). Best-fit  $\epsilon/N$  curve and cyclic stress-strain curve for HS 188 bar, longitudinal orientation at 1600°F.

**MIL-HDBK-5H****1 December 1998**Correlative Information for Figure 6.4.2.1.8(c)Product Form/Thickness:

Bar/1.5-inch-thick

Thermal Mechanical Processing History:

Solution treated, water quenched (AMS 5772)

Properties:

<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>E, ksi</u>	<u>Temp., °F</u>
120*	55*		75
		22,406	1600

Stress-Strain Equations:

Cyclic (Companion Specimens)

Proportional Limit = 36 ksi

$$(\Delta\sigma/2) = 81.6 (\Delta\epsilon_p/2)^{0.094}$$

Specimen Details:

Uniform gage test section

0.250-inch diameter

Reference: 3.8.1.1.8Test Parameters:

Strain Rate/Frequency - 20 cpm

Wave Form - Triangular

Temperature - 1600 °F

Atmosphere - Air

No. of Heats/Lots: 1Equivalent Strain Equation:Log  $N_f$  = 0.011 - 1.343 log ( $\Delta\epsilon$ -0.00283)

Standard Deviation of Log(Life) = 0.116

Adjusted  $R^2$  Statistic = 96%Sample Size = 16

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

---

\* Minimum values from AMS 5772.

MIL-HDBK-5H  
1 December 1998




Figure 6.4.2.1.8(d). Best-fit  $\epsilon/N$  curve and cyclic stress-strain curve for HS 188 bar, longitudinal orientation at 1800°F.

**MIL-HDBK-5H****1 December 1998**Correlative Information for Figure 6.4.2.1.8(d)Product Form/Thickness:

Bar/1.5-inch-thick

Thermal Mechanical Processing History:

Solution treated, water quenched (AMS 5772)

Properties:

<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>E, ksi</u>	<u>Temp., °F</u>
120*	55*		75
		20,353	1800

Stress-Strain Equations:

Cyclic (Companion Specimens)

Proportional Limit = 23 ksi

$$(\Delta\sigma/2) = 66.3 (\Delta\epsilon_p/2)^{0.12}$$

Specimen Details:

Uniform gage test section

0.250-inch diameter

Reference: 3.8.1.1.8Test Parameters:

Strain Rate/Frequency - 20 cpm

Wave Form - Triangular

Temperature - 1800 °F

Atmosphere - Air

No. of Heats/Lots: 1Equivalent Strain Equation:Log  $N_f = 0.047 - 1.317 \log (\Delta\epsilon - 0.00239)$ 

Standard Deviation in Log(Life) = 0.0126

Adjusted  $R^2$  Statistic = 96%Sample Size = 15

[Caution: The equivalent stress model may provide unrealistic life predictions for stress ratios beyond those represented above.]

---

\* Minimum values from AMS 5772.

**MIL-HDBK-5H****1 December 1998****REFERENCES**

- 6.2.1.1.8 Blatherwick, A. A. and Cers, A., "Fatigue, Creep and Stress-Rupture Properties of Nicrotung, Super A-286, and Inconel 718", AFML-TR-65-4447 (June 1966) (MCIC 65927).
- 6.3.3.1.8(a) Ruff, P. E., "Effect of Manufacturing Processes on Structural Allowables—Phase II", AFWAL-TR-86-4120, Battelle (November 1986) (MIL-HDBK-5 Source M-656).
- 6.3.3.1.8(b) Deel, O. L., and Mindlin, H., "Engineering Data on New Aerospace Structural Materials", AFML-TR-71-249, Battelle (December 1971) (MIL-HDBK-5 Source M-465).
- 6.3.5.1.8(a) Ruff, P. E., "Effect of Manufacturing Processes on Structural Allowables—Phase I," AFWAL-TR-85-4128, Battelle (January 1986) (MIL-HDBK-5 Source M-654).
- 6.3.5.1.8(b) Korth, G. E. and Smokik, G. R., "Status Report of Physical and Mechanical Test Data of Alloy 718", EG&G Idaho Inc., TREE-1254 (March 1978) (MIL-HDBK-5 Source M-603).
- 6.3.5.1.9(a) James, L. A., "Heat-to-Heat and/or Melt Practice Variations in Crack Growth Behavior of Inconel 718", Mechanical Properties Test Data for Structural Materials, Quarterly Report for Period Ending October 31, 1977, Report ORNL-5349, pp. 196-199, Oak Ridge National Laboratory (December 1977).
- 6.3.5.1.9(b) Mills, W. J. and James, L. A., "Effect of Heat-Treatment on Elevated Temperature Fatigue-Crack Growth Behavior of Two Heats of Alloy 718", ASME Paper 78-WA-PVP-3 (December 1978).
- 6.3.5.1.9(c) James, L. A., "Investigation of Potential Product Form Effects Upon the Fatigue-Crack Growth Behavior of Alloy 718", Mechanical Properties Test Data for Structural Materials, Semiannual Progress Report for Period Ending July 31, 1979, Report ORNL/BRP-79/5, pp. 5.1-5.4, Oak Ridge National Laboratory (October 1979).
- 6.3.5.1.9(d) James, L. A., "The Effect of Product Form Upon Fatigue-Crack Growth Behavior in Alloy 718", Report HEDL-TME-80-11, Hanford Engineering Development Laboratory (March 1980).
- 6.3.5.1.9(e) James, L. A. and Mills, W. J., "Effect of Heat-Treatment and Heat-to-Heat Variations in the Fatigue-Crack Growth Response of Alloy 718—Phase I: Macroscopic Variation", Report HEDL-TME-80-9, Hanford Engineering Development Laboratory (March 1980).
- 6.3.5.1.9(f) James, L. A., "Fatigue-Crack Propagation Behavior of Inconel 718", Report HEDL-TME-75-80, Hanford Engineering Development Laboratory (September 1975).
- 6.3.5.1.9(g) James, L. A., "Heat-to-Heat and/or Melt Practice Variations in Crack Growth Behavior of Alloy 718", Mechanical Properties Test Data for Structural Materials, Quarterly Progress Report for Period Ending January 31, 1978, Report ORNL-5380, pp. 153-160, Oak Ridge National Laboratory (March 1978).



**CHAPTER 7****MISCELLANEOUS ALLOYS AND HYBRID MATERIALS****7.1 GENERAL**

This chapter contains the engineering properties and related characteristics of miscellaneous alloys and hybrid materials. In addition to the usual properties, some characteristics relating to the special uses of these alloys are described. For example, the electrical conductivity is reported for the bronzes and information is included on toxicity of particles of beryllium and its compounds, such as beryllium oxide.

The organization of this chapter is in sections by base metal and subdivided as shown in Table 7.1.

**Table 7.1. Miscellaneous Alloys Index**

Section	Designation
<b>7.2</b>	<b>Beryllium</b>
7.2.1	Standard Grade Beryllium
<b>7.3</b>	<b>Copper and Copper Alloys</b>
7.3.1	Manganese Bronzes
7.3.2	Copper Beryllium
<b>7.4</b>	<b>Multiphase Alloys</b>
7.4.1	MP35N Alloy
7.4.2	MP159 Alloy
<b>7.5</b>	<b>Aluminum Alloy Sheet Laminates</b>
7.5.1	2024-T3 Aramid Fiber Reinforced Sheet Laminate
7.5.2	7475-T761 Aramid Fiber Reinforced Sheet Laminate

**7.2 BERYLLIUM****7.2.0 GENERAL**

This section contains the engineering properties and related characteristics of beryllium used in aerospace structural applications. Beryllium is a lightweight, high modulus, moderate temperature capability metal that is used for specific aerospace applications. Structural designs utilizing beryllium sheet should allow for anisotropy, particularly the very low short transverse properties. Additional information on the fabrication of beryllium may be found in References 7.2.0(a) through (i).

**7.2.1 STANDARD GRADE BERYLLIUM**

**7.2.1.0 Comments and Properties** — Standard grade beryllium bars, rods, tubing, and machined shapes are produced from vacuum hot-pressed powder with 1½ percent maximum beryllium oxide content. These products are also available in numerous other compositions for special purposes but are not covered in this document. Sheet and plate are fabricated from vacuum hot-pressed powder with 2 percent maximum beryllium oxide content.

**MIL-HDBK-5H****1 December 1998****7.2.1.1 Manufacturing Considerations**

*Hot Shaping* — Beryllium hot-pressed block can be forged and rolled but requires temperatures of 700°F and higher because of brittleness. A temperature range of 1000 to 1400°F is recommended. Hot shaping procedures are given in more detail in Reference 7.2.0(b).

*Forming* — Beryllium sheet should be formed at 1300 to 1350°F, holding at temperature no more than 1.5 hours, for minimum springback. Forming above 1450°F will result in a reduction in strength.

*Machining* — Carbide tools are most often used in machining beryllium. Mechanical metal removal techniques generally cause microcracks and metallographic twins. Finishing cuts are usually 0.002 to 0.005 inch in depth to minimize surface damage. Although most machining operations are performed without coolant, to avoid contamination of the chips, the use of coolant can reduce the depth of damage and give longer tool life. See Reference 7.2.0(c) for more information. Finish machining should be followed by chemical etching at least 0.002-inch from the surface to remove machining damage. See References 7.2.0(h) and (i). A combination of 1350°F stress relief followed by an 0.0005-inch etch may be necessary for close-tolerance parts. Damage-free metal removal techniques include chemical milling and electrochemical machining. The drilling of sheet may lead to delamination and breakout unless the drillhead is of the controlled torque type and the drills are carbide burr type.

*Joining* — Parts may be joined mechanically by riveting, but only by squeeze riveting to avoid damage to the beryllium, by bolting, threading, or by press fitting specifically designed to avoid damage. Parts also may be joined by brazing, soldering, braze welding, adhesive bonding, and diffusion bonding. Fusion welding is not recommended. Brazing may be accomplished with zinc, aluminum-silicon, or silver-base filler metals. Many elements, including copper, may cause embrittlement when used as brazing filler metals. However, specific manufacturing techniques have been developed by various beryllium fabricators to use many of the common braze materials. For each method of joining specific detailed procedures must be followed, Reference 7.2.0(f).

*Surface Treatment* — A surface treatment such as chemical etching to remove the machined surface of metal is recommended to ensure the specified properties. All design allowables herein represent material so treated. This surface treatment is especially important when beryllium is to be mechanically joined. References 7.2.0(d), (h), and (i) contain information on etching solutions and procedures.

*Toxicity Hazard* — Particles of beryllium and its compounds, such as beryllium oxide, are toxic, so special precautions to prevent inhalation must be taken. References 7.2.1.1(a) through (e) outline the hazard and methods to control it.

*Specifications and Properties* — Material specifications for standard grade beryllium are presented in Table 7.2.1.0(a).

**Table 7.2.1.0(a). Material Specifications for Standard Grade Beryllium**

Specification	Form
AMS 7906	Bar, rod, tubing, and mechanical shapes
AMS 7902	Sheet and plate

**MIL-HDBK-5H****1 December 1998**

Room-temperature mechanical and physical properties are shown in Tables 7.2.1.0(b) and (c). Notch tensile test data are available in Reference 7.2.1.1(g). The effect of temperature on physical properties is shown in Figure 7.2.1.0.

**7.2.1.1 Hot-Pressed Condition** — The effect of temperature on the mechanical properties of hot-pressed beryllium is presented in Figures 7.2.1.1.1 and 7.2.1.1.4.


**Table 7.2.1.0(b). Design Mechanical and Physical Properties of Beryllium Bar, Rod, Tubing, and Mechanical Shapes**

Specification .....	AMS 7906
Form .....	Bar, rod, tubing, and machined shapes
Condition .....	Hot pressed (ground and etched)
Thickness or diameter, in. ....	...
Basis .....	S
Mechanical Properties:	
$F_{tu}$ , ksi:	
L .....	47
LT .....	47
$F_{ty}$ , ksi:	
L .....	35
LT .....	35
$F_{cy}$ , ksi:	
L .....	...
LT .....	...
$F_{su}$ , ksi .....	...
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$e$ , percent:	
L .....	2
LT .....	2
$E$ , $10^3$ ksi .....	42
$E_c$ , $10^3$ ksi .....	42
$G$ , $10^3$ ksi .....	20
$\mu$ .....	0.10
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.067
$C$ , $K$ , and $\alpha$ .....	See Figure 7.2.1.0


**MIL-HDBK-5H****1 December 1998****Table 7.2.1.0(c). Design Mechanical and Physical Properties of Beryllium Sheet and Plate**

Specification . . . . .	AMS 7902			
	Sheet	Plate		
	Stress relieved (ground and etched)			
	0.020-0.250	0.251-0.450	0.451-0.600	≥0.601
	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L . . . . .	70	65	60	40
LT . . . . .	70	65	60	40
$F_{ty}$ , ksi:				
L . . . . .	50	45	40	30
LT . . . . .	50	45	40	30
$F_{cy}$ , ksi:				
L . . . . .	...	...	...	...
LT . . . . .	...	...	...	...
$F_{su}$ , ksi . . . . .	...	...	...	...
$F_{bru}$ , ksi:				
(e/D = 1.5) . . . . .	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...
$F_{bry}$ , ksi:				
(e/D = 1.5) . . . . .	...	...	...	...
(e/D = 2.0) . . . . .	...	...	...	...
$e$ , percent:				
L . . . . .	10	4	3	1
LT . . . . .	10	4	3	1
$E$ , 10 <sup>3</sup> ksi . . . . .	42.5			
$E_c$ , 10 <sup>3</sup> ksi . . . . .	42.5			
$G$ , 10 <sup>3</sup> ksi . . . . .	20.0			
$\mu$ . . . . .	0.10 (L and LT)			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.067			
$C$ , $K$ , and $\alpha$ . . . . .	See Figure 7.2.1.0			


**MIL-HDBK-5H**  
**1 December 1998**



**Figure 7.2.1.0. Effect of temperature on the physical properties of beryllium (2% maximum BeO).**



**Figure 7.2.1.1.1. Effect of temperature on the tensile ultimate strength (F<sub>tu</sub>) and tensile yield strength (F<sub>ty</sub>) of hot-pressed beryllium bar, rod, tubing, and machined shapes.**

**MIL-HDBK-5H****1 December 1998**

**Figure 7.2.1.1.4. Effect of temperature on the tensile and compressive moduli (E and E<sub>c</sub>) of hot-pressed beryllium bar, rod, tubing, and machined shapes.**

**MIL-HDBK-5H****1 December 1998****7.3 COPPER AND COPPER ALLOYS****7.3.0 GENERAL**

The properties of major significance in designing with copper and copper alloys are electrical and thermal conductivity, corrosion resistance, and good bearing qualities (antigalling). Copper and copper alloys are non-magnetic and can be readily joined by welding, brazing and soldering. The use of copper alloys is usually predicated upon two or more of the above properties plus the ease of casting and hot and cold working into desirable shapes.

The thermally unstable range for copper and copper alloys generally begins somewhat above room temperature (150°F). Creep, stress relaxation and diminishing stress rupture strength are factors of concern above 150°F. Copper alloys frequently are used at temperatures up to 480°F. The range between 480 and 750°F is considered very high for copper alloys, since copper and many of its alloys begin to oxidize slightly above 350°F and protection may be required. Bronzes containing Al, Si, and Be oxidize to a lesser extent than the red copper alloys. Precipitation hardened alloys such as copper beryllium retain strength up to their aging temperatures of 500 to 750°F.

Copper alloys used for bearing and wear resistance applications include, in the order of their increasing strength and load-carrying capacity, copper-tin-lead, copper-tin, silicon bronze, manganese bronze, aluminum bronze, and copper beryllium. Copper beryllium and manganese bronzes are included in MIL-HDBK-5.

Copper-base bearing alloys are readily cast by a number of techniques: statically sand cast, centrifugally cast into tubular shapes, and continuously cast into various shapes. Tin bronze, sometimes called phosphor bronze because phosphorous is used to deoxidize the melt and improve castability, is a low-strength alloy. It is generally supplied as a static (sand) casting or centrifugal casting (tubular shapes from rotating graphite molds). Manganese bronze is considerably stronger than tin bronze, is easily cast in the foundry, has good toughness and is not heat treated. Aluminum bronze alloys, especially those with nickel, silicon, and manganese over 2 percent, respond to heat treatment, resulting in greater strength, and higher galling and fatigue limits than manganese bronze. Aluminum bronze is used in the static and centrifugal cast form or parts may be machined from wrought rod and bar stock. Copper beryllium is the highest strength copper-base bearing material, due to its response to precipitation hardening. Copper beryllium is also available in static and centrifugal cast form but is generally used as wrought shapes, such as extrusions, forgings, and mill shapes.

Copper beryllium, because of its high strength, is also useful as a spring material. In this application its high elastic limit, high fatigue strength as well as good electrical conductivity are significant. Copper beryllium resists softening up to 500°F, which is higher than other common copper alloys. Copper beryllium springs are usually fabricated from strip or wire. Consult References 7.3.0(a) through (c) for more information.

**MIL-HDBK-5H****1 December 1998****7.3.1 MANGANESE BRONZES**

**7.3.1.0 Comments and Properties** — The manganese bronzes are also known as the high-strength yellow brasses and leaded high-strength yellow brasses. These alloys contain zinc as the principal alloying element with smaller amounts of iron, aluminum, manganese, nickel, and lead present. These bronzes are easily cast.

Some material specifications for manganese bronzes are presented in Table 7.3.1.0(a). A cross index to CDA and former QQ-C-390 designations is presented in Table 7.3.1.0(b). Room-temperature mechanical properties are shown in Tables 7.3.1.0(c) and (d).

**Table 7.3.1.0(a). Material Specifications for Manganese Bronzes**

Specification	Form
AMS 4860	Casting
AMS 4862	Casting

**Table 7.3.1.0(b). Cross Index**

Copper Alloy UNS No.	CDA Alloy No.	Former QQ-C-390 Alloy No.
C86300	863	C7
C86500	865	C3



**MIL-HDBK-5H****1 December 1998****Table 7.3.1.0(c). Design Mechanical and Physical Properties of C86500 Manganese Bronze**

Specification .....	AMS 4860
Form .....	Sand and centrifugal casting
Condition .....	As cast
Location within casting .....	Any area
Basis .....	S
Mechanical Properties:	
$F_{tu}$ , ksi .....	65 <sup>a</sup>
$F_{ty}$ , ksi .....	25 <sup>a</sup>
$F_{cy}$ , ksi .....	...
$F_{su}$ , ksi .....	...
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$e$ , percent .....	20 <sup>a</sup>
$E$ , 10 <sup>3</sup> ksi .....	15.0
$E_c$ , 10 <sup>3</sup> ksi .....	...
$G$ , 10 <sup>3</sup> ksi .....	...
$\mu$ .....	...
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.301
$C$ , Btu/(lb)(°F) .....	0.09 (at 68°F)
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	50 (at 68°F)
$\alpha$ , 10 <sup>-6</sup> in./in/°F .....	11.3 (68 to 212°F)
Electrical conductivity, % IACS .....	22.0

a When specified, conformance to tensile property requirements is determined by testing specimens cut from casting.

**MIL-HDBK-5H****1 December 1998****Table 7.3.1.0(d). Design Mechanical and Physical Properties of C86300 Manganese Bronze**

Specification .....	AMS 4862
Form .....	Sand and centrifugal casting
Condition .....	As cast
Location within casting .....	Any area
Basis .....	S
Mechanical Properties:	
$F_{tu}$ , ksi .....	110 <sup>a</sup>
$F_{ty}$ , ksi .....	60 <sup>a</sup>
$F_{cy}$ , ksi .....	...
$F_{su}$ , ksi .....	...
$F_{bru}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$F_{bry}$ , ksi:	
(e/D = 1.5) .....	...
(e/D = 2.0) .....	...
$e$ , percent .....	12 <sup>a</sup>
$E$ , 10 <sup>3</sup> ksi .....	14.2
$E_c$ , 10 <sup>3</sup> ksi .....	...
$G$ , 10 <sup>3</sup> ksi .....	...
$\mu$ .....	...
Physical Properties:	
$\omega$ , lb/in. <sup>3</sup> .....	0.283
$C$ , Btu/(lb)(°F) .....	0.09 (at 68°F)
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] .....	20.5 (at 68°F)
$\alpha$ , 10 <sup>-6</sup> in./in/°F .....	12.0 (68 to 500°F)
Electrical conductivity, % IACS .....	8.0

a When specified, conformance to tensile property requirements is determined by testing specimens cut from casting.

**MIL-HDBK-5H****1 December 1998****7.3.2 COPPER BERYLLIUM**

**7.3.2.0 Comments and Properties** — Copper beryllium refers to a family of copper-base alloys containing beryllium and cobalt or nickel which cause the alloys to be precipitation hardenable. Data for only one high-strength alloy, designated C17200, which contains 1.90 percent (nominal) beryllium, are presented in this section. This alloy is suitable for parts requiring high strength, good wear, and corrosion resistance. Alloy C17200 is available in the form of rod, bar, shapes, mechanical tubing, strip, and casting.

*Manufacturing Considerations* — The heat treatable tempers of rod and bar are designated TB00 (AMS 4650) for solution-treated or TD04 (AMS 4651) for solution-treated plus cold worked conditions. After fabrication operations, the material may be strengthened by precipitation heat treatment (aging). Rod and bar are also available from the mill in the TF00 (AMS 4533) and TH04 (AMS 4534) conditions. Mechanical tubing is available from the mill in TF00 (AMS 4535) condition. Machining operations on rod, bar, and tubing are usually performed on material in the TF00 or (TH04) conditions. This eliminates the volumetric shrinkage of 0.02 percent, which occurs during precipitation hardening, as a factor in maintaining final dimensional tolerances. This material has good machinability in all conditions.

Strip is also available in the heat treatable condition. Parts are stamped or formed in a heat treatable temper and subsequently precipitation heat treated. For strip, the heat treatable tempers are designated TB00 (AMS 4530, ASTM B194), TD01 (ASTM B194), TD02 (AMS 4532, ASTM B194), and TD04 (ASTM B194), indicating a progressively greater amount of cold work by the mill. When parts produced from these tempers are precipitation heat treated by the user, the designations become TF00, TH01, TH02, and TH04, respectively. Strip is also available from the mill for the hardened conditions. Design values for these conditions are not included.

*Environmental Considerations* — The copper beryllium alloys have good corrosion resistance and are not susceptible to hydrogen embrittlement. The maximum service temperature for C17200 copper beryllium products is 500°F for up to 100 hours.

*Specifications and Properties* — A cross-index to previous and current temper designations for C17200 alloy is presented in Table 7.3.2.0(a).

**Table 7.3.2.0(a). Cross-Index to Previous and Current Temper Designations for C17200 Copper Beryllium**

Previous Temper	Current ASTM Temper
A	TB00
AT	TF00
¼H	TD01
¼HT	TH01
½H	TD02
½HT	TH02
H	TD04
HT	TH04

Material specifications for alloy C17200 are presented in Table 7.3.2.0(b). Room-temperature mechanical properties are shown in Tables 7.3.2.0(c) through (g). The effect of temperature on physical properties is depicted in Figure 7.3.2.0.

**MIL-HDBK-5H****1 December 1998****Table 7.3.2.0(b). Material Specifications for C17200 Copper Beryllium Alloy**

Specification	Form
ASTM B194	Strip (TB00, TD01, TD02, TD04)
AMS 4530	Strip (TB00)
AMS 4532	Strip (TD02)
AMS 4650	Bar, rod, shapes, and forgings (TB00)
AMS 4533	Bar and rod (TF00)
AMS 4535	Mechanical tubing (TF00)
AMS 4651	Bar and rod (TD04)
AMS 4534	Bar and rod (TH04)

The temper index for C17200 alloy is as follows:

<u>Section</u>	<u>Temper</u>
7.3.2.1	TF00
7.3.2.2	TH04

**7.3.2.1 TF00 Temper** — Typical tensile and compressive stress-strain and tangent-modulus curves are presented in Figures 7.3.2.1.6(a) and (b).

**7.3.2.2 TH04 Temper** — Typical tensile and compressive stress-strain and tangent-modulus curves are presented in Figure 7.3.2.2.6.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 7.3.2.0(c). Design Mechanical and Physical Properties of Copper Beryllium Strip**

Specification .....	ASTM B194 AMS 4530	ASTM B194	ASTM B194 AMS 4532	ASTM B194
Form .....	Strip			
Condition .....	TF00	TH01	TH02	TH04
Thickness, in. ....	≤0.188	≤0.188	≤0.188	≤0.188
Basis .....	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	165	175	185	190
LT .....	...	...	...	...
$F_{ty}$ , ksi:				
L .....	140	150	160	165
LT .....	...	...	...	...
$F_{cy}^a$ , ksi:				
L .....	140	150	160	165
LT .....	140	150	160	165
$F_{su}^a$ , ksi .....	90	90	92	95
$F_{bru}^a$ , ksi:				
(e/D = 1.5) .....	214	227	240	247
(e/D = 2.0) .....	280	297	314	323
$F_{bry}^a$ , ksi:				
(e/D = 1.5) .....	196	210	224	231
(e/D = 2.0) .....	210	225	240	247
$e$ , percent:				
L .....	3	2.5	1	1
$E$ , 10 <sup>3</sup> ksi .....	18.5			
$E_c$ , 10 <sup>3</sup> ksi .....	...			
$G$ , 10 <sup>3</sup> ksi .....	7.3			
$\mu$ .....	0.27			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.298			
$C$ , $K$ , and $\alpha$ .....	See Figure 7.3.2.0 for TF00 temper			

a These properties do not represent values derived from tests, but are estimates.

**MIL-HDBK-5H****1 December 1998****Table 7.3.2.0(d). Design Mechanical and Physical Properties of C17200 Copper Beryllium Rod and Bar**

Specification .....	AMS 4650 and AMS 4533				
Form .....	Rod and bar				
Condition .....	TF00				
Thickness, in. ....	≤ 1.500	1.501-2.000	2.001-3.000	3.001-3.500	3.501-4.000
Basis .....	S	S	S	S	S
Mechanical Properties:					
$F_{tu}$ , ksi:					
L .....	165	165	165	165	165
ST .....	...	158	158	158	158
$F_{ty}$ , ksi:					
L .....	140	140	140	140	140
ST .....	...	137	137	137	137
$F_{cy}$ , ksi:					
L .....	150	149	145	143	139
ST .....	...	142	142	142	142
$F_{su}$ , ksi .....	...	94	94	94	94
$F_{bru}^a$ , ksi:					
(e/D = 1.5) .....	226	226	226	226	226
(e/D = 2.0) .....	290	290	290	290	290
$F_{bry}^a$ , ksi:					
(e/D = 1.5) .....	200	200	200	200	200
(e/D = 2.0) .....	225	225	225	225	225
$e$ , percent:					
L .....	4 <sup>b</sup>	4 <sup>b</sup>	4 <sup>b</sup>	3	3
$E$ , 10 <sup>3</sup> ksi .....	18.5				
$E_c$ , 10 <sup>3</sup> ksi .....	18.7				
$G$ , 10 <sup>3</sup> ksi .....	7.3				
$\mu$ .....	0.27				
Physical Properties:					
$\omega$ , lb/in. <sup>3</sup> .....	0.298				
$C$ , $K$ , and $\alpha$ .....	See Figure 7.3.2.0				

a Bearing values are "dry pin" values per Section 1.4.7.1.

b AMS 4650 specifies  $e = 3$  percent.

**MIL-HDBK-5H****1 December 1998****Table 7.3.2.0(e). Design Mechanical and Physical Properties of C17200 Copper Beryllium Rod and Bar**

Specification .....	AMS 4651			
Form .....	Rod and bar			
Condition .....	TH04			
Thickness, in. ....	≤0.375	0.376-1.000	1.001-1.500	1.501-2.000
Basis .....	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	185	180	175	175
ST .....	...	...	...	169
$F_{ty}$ , ksi:				
L .....	145	145	145	145
ST .....	...	...	...	140
$F_{cy}$ , ksi:				
L .....	...	148	148	148
ST .....	...	...	...	154
$F_{su}$ , ksi .....	...	89	90	93
$F_{bru}^a$ , ksi:				
(e/D = 1.5) .....	...	242	235	235
(e/D = 2.0) .....	...	306	298	298
$F_{bry}^a$ , ksi:				
(e/D = 1.5) .....	...	207	207	207
(e/D = 2.0) .....	...	225	225	225
$e$ , percent:				
L .....	1	1	2	2
$E$ , $10^3$ ksi .....	18.5			
$E_c$ , $10^3$ ksi .....	18.7			
$G$ , $10^3$ ksi .....	7.3			
$\mu$ .....	0.27			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.298			
$C$ , $K$ , and $\alpha$ .....	...			

a Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998****Table 7.3.4.0(f). Design Mechanical and Physical Properties of C17200 Copper Beryllium Rod and Bar**

Specification . . . . .	AMS 4534											
Form . . . . .	Rod and bar											
Condition . . . . .	TH04											
Thickness, in. . . . .	$\leq 0.375$		0.376-0.999		1.000-1.499		1.500-1.999		2.000-2.499		2.500-3.000	
Basis . . . . .	A	B	A	B	A	B	A	B	A	B	A	B
Mechanical Properties:												
$F_{tu}$ , ksi:												
L . . . . .	182	188	180	186	177 <sup>a</sup>	184	177	183	175	181	172	178
ST . . . . .	...	...	...	...	...	...	167	173	168	174	167	173
$F_{ty}$ , ksi:												
L . . . . .	157	165	154	162	150 <sup>a</sup>	162	150	158	147	155	145	152
ST . . . . .	...	...	...	...	...	...	145	153	142	150	140	147
$F_{cy}$ , ksi:												
L . . . . .	...	...	157	166	153	164	153	162	150	158	148	155
ST . . . . .	...	...	...	...	...	...	160	168	156	165	154	162
$F_{su}$ , ksi . . . . .	...	...	89	92	91	95	94	97	95	98	94	96
$F_{bru}^b$ , ksi:												
(e/D = 1.5) . . . . .	...	...	242	250	238	247	238	246	235	243	231	239
(e/D = 2.0) . . . . .	...	...	306	317	302	313	302	312	298	308	293	303
$F_{bry}^b$ , ksi:												
(e/D = 1.5) . . . . .	...	...	220	231	214	228	214	226	210	221	207	217
(e/D = 2.0) . . . . .	...	...	239	251	233	248	233	245	228	240	225	236
$e$ , percent (S-basis):												
L . . . . .	3	...	3	...	3	...	3	...	3	...	3	...
$E$ , 10 <sup>3</sup> ksi . . . . .	18.5											
$E_c$ , 10 <sup>3</sup> ksi . . . . .	18.7											
$G$ , 10 <sup>3</sup> ksi . . . . .	7.3											
$\mu$ . . . . .	0.27											
Physical Properties:												
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.298											
$C$ , $K$ , and $\alpha$ . . . . .	...											

a S-basis. A values are  $F_{tu}(L) = 178$  ksi and  $F_{ty} = 152$  ksi.

b Bearing values are "dry pin" values per Section 1.4.7.1.




**MIL-HDBK-5H**  
**1 December 1998**


**Table 7.3.2.0(g). Design Mechanical and Physical Properties of C17200 Copper Beryllium Mechanical Tubing**

Specification .....	AMS 4535			
Form .....	Mechanical tubing			
Condition .....	TF00			
Outside Diameter, in. ....	$\leq 2.499$	2.500-12.000		
Wall Thickness, in. ....	$\leq 0.749$	0.750-2.000		
Basis .....	A	B	A	B
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	161	167	161	167
LT .....	...	...	157	163
$F_{ty}$ , ksi:				
L .....	126	136	126	136
LT .....	...	...	124	134
$F_{cy}$ , ksi:				
L .....	134	145	134	145
LT .....	...	...	135	146
$F_{su}$ , ksi .....	92	95	92	95
$F_{bru}^a$ , ksi:				
(e/D = 1.5) .....	228	237	228	237
(e/D = 2.0) .....	287	298	287	298
$F_{bry}^a$ , ksi:				
(e/D = 1.5) .....	183	197	183	197
(e/D = 2.0) .....	206	222	206	222
$e$ , percent (S-basis):				
L .....	3	...	3	...
$E$ , $10^3$ ksi .....	18.5			
$E_c$ , $10^3$ ksi .....	18.7			
$G$ , $10^3$ ksi .....	7.3			
$\mu$ .....	0.27			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.298			
$C$ , Btu/(lb)(°F) .....	See Figure 7.3.4.0			


a Bearing values are "dry pin" values per Section 1.4.7.1.

**MIL-HDBK-5H****1 December 1998**


**Figure 7.3.2.0. Effect of temperature on the physical properties of copper beryllium (TF00).**



**Figure 7.3.2.1.6(a). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for C17200 copper beryllium bar and rod in TF00 temper.**

**MIL-HDBK-5H****1 December 1998**

**Figure 7.3.2.1.6(b). Typical tensile and compressive stress-strain and compressive tangent-modulus curves for C17200 copper beryllium mechanical tubing in TF00 temper.**



**Figure 7.3.2.2.6. Typical tensile and compressive stress-strain and compressive tangent-modulus curves for C17200 copper beryllium bar and rod in TH04 temper.**

**MIL-HDBK-5H****1 December 1998****7.4 MULTIPHASE ALLOYS****7.4.0 GENERAL**

This section contains the engineering properties of the “Multiphase” alloys. These alloys, based on the quaternary of cobalt, nickel, chromium, and molybdenum, can be work-strengthened and aged to ultrahigh strengths with good ductility and corrosion resistance.

**7.4.1 MP35N ALLOY**

**7.4.1.0 Comments and Properties** — MP35N is a vacuum induction, vacuum arc remelted alloy which can be work-strengthened and aged to ultrahigh strengths. This alloy is suitable for parts requiring ultrahigh strength, good ductility and excellent corrosion and oxidation resistance up to 700°F.

*Manufacturing Considerations* — The work hardening characteristics of MP35N are similar to 304 stainless steel. Drawing, swaging, rolling, and shear forming are excellent deforming methods for work strengthening the alloy. The machinability of MP35N is similar to the nickel-base alloys.

*Environmental Considerations* — MP35N has excellent corrosion, crevice corrosion and stress corrosion resistance in seawater. Due to the passivity of MP35N, a galvanically active coating, such as aluminum or cadmium, may be required to prevent galvanic corrosion of aluminum joints. Initial tests have indicated that MP35N does not appear to be susceptible to hydrogen embrittlement.

Short time exposure to temperatures above 700°F causes a decrease in ductility (elongation and reduction of area) at temperature. Mechanical properties at room temperature are not affected significantly by unstressed exposure to temperatures up to 50 degrees below the aging temperature (1000 to 2000°F) for up to 100 hours.

*Heat Treatment* — After work strengthening, MP35N is aged at 1000 to 1200°F for 4 to 4½ hours and air cooled.

Material specifications for MP35N are presented in Table 7.4.1.0(a). The room-temperature mechanical and physical properties for MP35N are presented in Tables 7.4.1.0(b) and (c). The effect of temperature on physical properties is shown in Figure 7.4.1.0.

**Table 7.4.1.0(a). Material Specifications for MP35N Alloy**

Specification	Form
AMS 5844	Bar (solution treated, and cold drawn)
AMS 5845	Bar (solution treated, cold drawn and aged)

**7.4.1.1 Cold Worked and Aged Condition** — Elevated temperature curves for various mechanical properties are shown in Figures 7.4.1.1.1, 7.4.1.1.4 (a) and (b), and 7.4.1.1.5. Typical tensile stress-strain curves at room and elevated temperatures are shown in Figure 7.4.1.1.6.

**MIL-HDBK-5H****1 December 1998****Table 7.4.1.0(b). Design Mechanical and Physical Properties of MP35N Alloy Bar**

Specification .....	AMS 5845			
Form .....	Bar			
Condition .....	Solution treated, cold drawn, and aged			
Diameter, in. <sup>c</sup> .....	≤0.800		0.801- 1.000	1.001- 1.750
Basis .....	A	B	S	S
Mechanical Properties:				
$F_m$ , ksi:				
L .....	260 <sup>a</sup>	275	260	260
LT .....	...	...	...	...
$F_y$ , ksi:				
L .....	230 <sup>b</sup>	266	230	230
LT .....	...	...	...	...
$F_{cy}$ , ksi:				
L .....	...	...	...	...
LT .....	...	...	...	...
$F_{su}$ , ksi .....	145	147	145	...
$F_{bru}$ , ksi:				
(e/D = 1.5) .....	...	...	...	...
(e/D = 2.0) .....	...	...	...	...
$F_{bry}$ , ksi:				
(e/D = 1.5) .....	...	...	...	...
(e/D = 2.0) .....	...	...	...	...
$e$ , percent (S basis):				
L .....	8	...	8	8
$RA$ , percent (S basis):				
L .....	35	...	35	35
$E$ , 10 <sup>3</sup> ksi .....	34.0			
$E_c$ , 10 <sup>3</sup> ksi .....	...			
$G$ , 10 <sup>3</sup> ksi .....	11.7			
$\mu$ .....	...			
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.304			
$C$ , Btu/(lb)(°F) .....	0.18 (32 to 70°F)			
$K$ and $\alpha$ .....	See Figure 7.4.1.0			

a The A value of 266 ksi is higher than specification minimum.

b The A value of 256 ksi is higher than specification minimum.

c Tensile specimens are located at T/2 location for bars 0.800 inch and under in diameter or distance between parallel sides and at T/4 location of larger size bars. The strength of bar, especially large diameter, may vary significantly from center to surface; consequently, caution should be exercised in machining parts from bars over 0.800 inch in diameter since strengths may be lower than design values depending on depth of material removed from surface.

**MIL-HDBK-5H****1 December 1998****Table 7.4.1.0(c). Design Mechanical and Physical Properties of MP35N Alloy Bar**

Specification .....	AMS 5844	
Form .....	Bar	
Condition .....	Solution treated, cold drawn, and aged	
Diameter, in. <sup>a</sup> .....	≤1.000	1.001-1.750
Basis .....	S	S
Mechanical Properties:		
$F_m$ , ksi:		
L .....	260	260
LT .....	...	...
$F_{ty}$ , ksi:		
L .....	230	230
LT .....	...	...
$F_{cy}$ , ksi:		
L .....	...	...
LT .....	...	...
$F_{su}$ , ksi .....	145	...
$F_{bru}$ , ksi:		
(e/D = 1.5) .....	...	...
(e/D = 2.0) .....	...	...
$F_{bry}$ , ksi:		
(e/D = 1.5) .....	...	...
(e/D = 2.0) .....	...	...
$e$ , percent:		
L .....	8	8
$RA$ , percent:		
L .....	35	35
$E$ , 10 <sup>3</sup> ksi .....	34.0	
$E_c$ , 10 <sup>3</sup> ksi .....	...	
$G$ , 10 <sup>3</sup> ksi .....	11.7	
$\mu$ .....	...	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> .....	0.304	
$C$ , Btu/(lb)(°F) .....	0.18 (32 to 70°F)	
$K$ and $\alpha$ .....	See Figure 7.4.1.0	

<sup>a</sup> Tensile specimens are located at T/2 location for bars 0.800 inch and under in diameter or distance between parallel sides and at T/4 location for larger size bars. The strength of bar, especially large diameter may vary significantly from center to surface; consequently, caution should be exercised in machining parts from bars over 0.800 inch in diameter since strengths may be lower than design values depending on depth of material removed from surface.

MIL-HDBK-5H

1 December 1998




Figure 7.4.1.0. Effect of temperature on the physical properties of MP35N alloy.




Figure 7.4.1.1.1. Effect of temperature on the tensile ultimate strength (F<sub>tu</sub>) and the tensile yield strength (F<sub>ty</sub>) of cold worked and aged MP35N bar, F<sub>tu</sub> = 260 ksi.



MIL-HDBK-5H

1 December 1998




Figure 7.4.1.1.4(a). Effect of temperature on the dynamic tensile modulus (E) of MP35N alloy bar.




Figure 7.4.1.1.4(b). Effect of temperature on the dynamic shear modulus (G) of MP35N alloy bar.



MIL-HDBK-5H  
1 December 1998




Figure 7.4.1.1.5. Effect of temperature on the elongation (e) of cold worked and aged MP35N bar,  $F_{tu} = 260$  ksi.




Figure 7.4.1.1.6. Typical tensile stress-strain curves at room and elevated temperatures for cold worked and aged MP35N bar,  $F_{tu} = 260$  ksi.

**MIL-HDBK-5H****1 December 1998****7.4.2 MP159 ALLOY**

**7.4.2.0 Comments and Properties** — MP159 is a vacuum induction, vacuum arc remelted alloy, based on cobalt, nickel, chromium, iron, and molybdenum, which can be work-strengthened and aged to ultrahigh strength. This alloy is suitable for parts requiring ultrahigh strength, good ductility, and excellent corrosion and oxidation resistance up to 1100°F. The alloy maintains its ultrahigh strength very well at temperatures up to 1100°F.

*Manufacturing Considerations* — The work hardening characteristics of MP159 are similar to MP35N and 304 stainless steel. Drawing, swaging, rolling, and shear forming are excellent deforming methods for work strengthening the alloy. The machinability of MP159 is similar to MP35N and the nickel-base alloys.

*Environmental Considerations* — MP159 has excellent corrosion, crevice corrosion, and stress corrosion resistance in various hostile environments. Due to the passivity of MP159, a galvanically active coating, such as aluminum or cadmium, may be required to prevent galvanic corrosion of aluminum joints. Initial tests have indicated that MP159 does not appear to be susceptible to hydrogen embrittlement.

*Heat Treatment* — After work strengthening, MP159 is aged at 1200 to 1250°F ± 25°F for 4 to 4½ hours and air cooled.

Material specifications for MP159 are presented in Table 7.4.2.0(a). The room temperature mechanical and physical properties for MP159 are presented in Tables 7.4.2.0(b) and (c). The effect of temperature on thermal expansion is shown in Figure 7.4.2.0.

**Table 7.4.2.0(a). Material Specifications for MP159 Alloy**

Specification	Form
AMS 5842	Bar (solution treated and cold drawn)
AMS 5843	Bar (solution treated, cold drawn, and aged)

**7.4.2.1 Cold Worked and Aged Condition** — The effect of temperature on tension modulus of elasticity and shear modulus is presented in Figure 7.4.2.1.4. A typical stress-strain curve at room temperature is shown in Figure 7.4.2.1.6.

**MIL-HDBK-5H****1 December 1998****Table 7.4.2.0(b). Design Mechanical and Physical Properties of MP159 Alloy Bar**

Specification .....	AMS 5843				
Form .....	Bar				
Condition .....	Solution treated, cold drawn, and aged				
Diameter, in. <sup>a</sup> .....	≤0.500		0.501-0.800		0.801-1.750
Basis .....	A	B	A	B	S
<b>Mechanical Properties:</b>					
$F_{tu}$ , ksi:					
L .....	260 <sup>b</sup>	269	260 <sup>b</sup>	269	260
LT .....	...	...	...	...	...
$F_{ty}$ , ksi:					
L .....	250 <sup>c</sup>	262	250 <sup>c</sup>	262	250
LT .....	...	...	...	...	...
$F_{cy}$ , ksi:					
L .....	...	...	...	...	...
LT .....	...	...	...	...	...
$F_{su}$ , ksi .....	131	144	...	...	...
$F_{bru}$ , ksi:					
(e/D = 1.5) .....	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...
$F_{bry}$ , ksi:					
(e/D = 1.5) .....	...	...	...	...	...
(e/D = 2.0) .....	...	...	...	...	...
$e$ , percent (S basis):					
L .....	6	...	6	...	6
$RA$ , percent (S basis):					
L .....	32	...	32	...	32
$E$ , 10 <sup>3</sup> ksi .....	35.3				
$E_c$ , 10 <sup>3</sup> ksi .....	...				
$G$ , 10 <sup>3</sup> ksi .....	11.3				
$\mu$ .....	0.37 (solution treated condition)				
<b>Physical Properties:</b>					
$\omega$ , lb/in. <sup>3</sup> .....	0.302				
$C$ and $K$ .....	...				
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	See Figure 7.4.2.0				

a Tensile specimens are located at T/2 location for bars 0.800 inch and under in diameter or distance between parallel sides and at T/4 location for larger size bars. The strength of bar, especially large diameter, may vary machining parts from bars over 0.800-inch in diameter since strengths may be lower than design values depending on depth of material removed from surface.

b S-Basis. The rounded  $T_{99}$  value of 265 ksi is higher than specification minimum.

c S-Basis. The rounded  $T_{99}$  value of 253 ksi is higher than specification minimum.

**MIL-HDBK-5H****1 December 1998****Table 7.4.2.0(c). Design Mechanical and Physical Properties of MP159 Alloy Bar**

Specification .....	AMS 5842	
Form .....	Bar	
Condition .....	Solution treated, cold drawn, and aged	
Diameter, in. <sup>a</sup> .....	≤0.500	0.501-1.750
Basis .....	S	S
Mechanical Properties:		
$F_{tu}$ , ksi:		
L .....	260	260
LT .....	...	...
$F_{ty}$ , ksi:		
L .....	250	250
LT .....	...	...
$F_{cy}$ , ksi:		
L .....	...	...
LT .....	...	...
$F_{su}$ , ksi .....	131	...
$F_{bru}$ , ksi:		
(e/D = 1.5) .....	...	...
(e/D = 2.0) .....	...	...
$F_{bry}$ , ksi:		
(e/D = 1.5) .....	...	...
(e/D = 2.0) .....	...	...
$e$ , percent:		
L .....	6	6
$RA$ , percent:		
L .....	32	32
$E$ , 10 <sup>3</sup> ksi .....	35.3	
$E_c$ , 10 <sup>3</sup> ksi .....	...	
$G$ , 10 <sup>3</sup> ksi .....	11.3	
$\mu$ .....	0.37 (solution treated condition)	
Physical Properties:		
$\omega$ , lb/in. <sup>3</sup> .....	0.302	
$C$ and $K$ .....	...	
$\alpha$ , 10 <sup>-6</sup> in./in./°F .....	See Figure 7.4.2.0	

- a Tensile specimens are located at T/2 location for bars 0.800 inch and under in diameter or distance between parallel sides and at T/4 location for larger size bars. The strength of bar, especially large diameter may vary significantly from center to surface; consequently, caution should be exercised in machining parts from bars over 0.800 inch in diameter since strengths may be lower than design values depending on depth of material removed from surface.

## MIL-HDBK-5H

1 December 1998




Figure 7.4.2.0. Effect of temperature on thermal expansion ( $\alpha$ ) of MP159 alloy bar.





Figure 7.4.2.1.4. Effect of temperature on the tensile modulus (E) and shear modulus (G) of MP159 alloy bar.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 7.4.2.1.6. Typical tensile stress-strain curve at room temperature for cold worked and aged MP159 alloy bar.**



**MIL-HDBK-5H****1 December 1998****7.5 ALUMINUM ALLOY SHEET LAMINATES****7.5.0 GENERAL**

This section contains the engineering properties of aluminum alloy sheet laminates. These products consist of thin high-strength aluminum alloy sheets alternating with fiber layers impregnated with adhesive. These sheet laminates provide a very efficient structure for certain applications and exhibit excellent fatigue resistance.

Tensile and compressive properties for the aluminum alloy sheet laminates were determined using test specimens similar to those used for testing conventional aluminum alloy sheet with one exception. The Iosipescu shear specimen was the most appropriate configuration for the determination of shear strength. Shear yield strength and shear ultimate strength were determined using the Iosipescu test procedure. Shear yield strength was determined at 0.2% offset from load-deformation curves. Bearing tests were conducted according to ASTM E 238, which is applicable to conventional aluminum alloy products. Bearing specimens exhibited several different types of failure and bearing strength was influenced by failure mode. Consequently, a more suitable bearing test procedure for aramid fiber reinforced aluminum alloy sheet laminates is currently being developed. However, the design values for bearing strength determined according to ASTM E 238 are conservative and are considered suitable for design. These sheet laminates exhibit low elongation as measured by the tensile test. Consequently, a more realistic measure of ductility is total strain at failure,  $\epsilon_t$ , defined as the measure of strain determined from the tensile load-deformation curve at specimen failure. This measurement includes both elastic and plastic strains. The minimum total strain at failure value from the material specification shall be presented in the room temperature design allowable table. These sheet laminates are generally anisotropic. Therefore, design values for each grain orientation of the aluminum alloy sheet shall be presented for all mechanical properties, except  $F_{su}$  and  $F_{sy}$ . The longitudinal direction is parallel to the rolling direction of the aluminum alloy sheet or length of sheet laminate, while the long transverse direction is 90° to the longitudinal direction or parallel to the width of the sheet laminate. The design values for  $F_{cy}$ ,  $F_{sy}$ ,  $F_{su}$ ,  $F_{bry}$ , and  $F_{bru}$  were derived conventionally in accordance with the guidelines.

**7.5.1 2024-T3 ARAMID FIBER REINFORCED SHEET LAMINATE**

**7.5.1.0 Comments and Properties** — This product consists of thin 2024-T3 sheets alternating with aramid fiber layers embedded in a special resin. Nominal thickness of aluminum sheet is 0.012 inch with a prepreg nominal thickness of 0.0085 inch. The primary advantage of this product is the significant improvement in fatigue and fatigue crack growth properties compared to conventional aluminum alloy structures. The product also has good damping capacity and resistance to impact. Compared to 7475-T761 aramid fiber-reinforced sheet laminate, this product has better formability and damage tolerance characteristics.

*Manufacturing Considerations* — This product can be fabricated by conventional metal practices for machining, sawing, drilling, joining with fasteners and can be inspected by conventional procedures.

*Environmental Considerations* — This product has good corrosion resistance. The maximum service temperature is 200°F.

*Specification and Properties* — A material specification is presented in Table 7.5.1.0(a). Room-temperature mechanical properties are presented in Table 7.5.1.0(b).

**MIL-HDBK-5H****1 December 1998****Table 7.5.1.0(a). Material Specifications for 2024-T3  
Aramid Fiber Reinforced Sheet Laminate**

Specification	Form
AMS 4254	Sheet laminate

**7.5.1.1 T3 Temper**— Typical tensile and compressive stress-strain and tangent-modulus curves are shown in Figures 7.5.1.1.6(a) through (l).



## MIL-HDBK-5H

1 December 1998

**Table 7.5.1.0(b). Design Mechanical and Physical Properties of 2024-T3 Aluminum Alloy, Aramid Fiber Reinforced, Sheet Laminate**

Specification .....	AMS 4254			
Form .....	Aramid fiber reinforced sheet laminate			
Laminate lay-up .....	2/1	3/2	4/3	5/4
Nominal thickness, in. ....	0.032	0.053	0.074	0.094
Basis .....	S	S	S	S
Mechanical Properties:				
$F_{tu}$ , ksi:				
L .....	90	96	101	101
LT .....	48	44	43	42
$F_{ty}$ , ksi:				
L .....	48	49	49	49
LT .....	33	30	30	30
$F_{cy}$ , ksi:				
L .....	35	35	34	33
LT .....	33	30	30	30
$F_{su}^a$ , ksi .....	d	d	d	d
$F_{sy}^a$ , ksi .....	16	15	14	14
$F_{bru}^b$ , ksi:				
L (e/D = 1.5) .....	78	73	73	68
LT (e/D = 1.5) .....	89	84	80	75
L (e/D = 2.0) .....	93	86	83	77
LT (e/D = 2.0) .....	95	89	81	76
$F_{bry}^b$ , ksi:				
L (e/D = 1.5) .....	53	52	51	50
LT (e/D = 1.5) .....	56	52	52	52
L (e/D = 2.0) .....	63	63	61	59
LT (e/D = 2.0) .....	66	61	61	60
$\epsilon_t^c$ , percent:				
L .....	2	2	2	2
LT .....	12	12	12	14
$E$ , $10^3$ ksi:				
L .....	9.9	9.9	9.7	9.6
LT .....	8.1	7.5	7.1	7.0
$E_c$ , $10^3$ ksi:				
L .....	9.5	9.4	9.3	9.1
LT .....	8.0	7.5	7.2	7.0
$G$ , $10^3$ ksi:				
L .....	2.7	2.5	2.4	2.2
LT .....	2.6	2.4	2.4	2.2
$\mu$ :				
L .....	0.33	0.34	0.34	0.32
LT .....	0.29	0.27	0.26	0.25
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....	0.086	0.084	0.082	0.081
$C$ , $K$ , and $\alpha$ .....	...	...	...	...


a Shear values determined from data obtained using Iosipescu shear specimens.

b Bearing values are "dry pin" values per Section 1.4.7.1 determined in accordance with ASTM E238.


c Total (elastic plus plastic) strain at failure determined from stress-strain curve.

d Shear ultimate strengths not determinable due to excessive deflection of specimen.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 7.5.1.1.6(a). Typical tensile stress-strain curves for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**




**Figure 7.5.1.1.6(b). Typical tensile stress-strain curves for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 7.5.1.1.6(c). Typical tensile stress-strain curves for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**




**Figure 7.5.1.1.6(d). Typical tensile stress-strain curves for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 7.5.1.1.6(e). Typical compressive stress-strain and compressive tangent-modulus curves for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**




**Figure 7.5.1.1.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 7.5.1.1.6(g). Typical compressive stress-strain and compressive tangent-modulus curves for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**




**Figure 7.5.1.1.6(h). Typical compressive stress-strain and compressive tangent-modulus curves for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 7.5.1.1.6(i). Typical tensile stress-strain curves (full range) for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**




**Figure 7.5.1.1.6(j). Typical tensile stress-strain curves (full range) for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 7.5.1.1.6(k). Typical tensile stress-strain curves (full range) for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**



**Figure 7.5.1.1.6(l). Typical tensile stress-strain curves (full range) for 2024-T3 aluminum alloy, aramid fiber-reinforced, sheet laminate.**

**MIL-HDBK-5H****1 December 1998****7.5.2 7475-T761 ARAMID FIBER REINFORCED SHEET LAMINATE**

**7.5.2.0 Comments and Properties** — This product consists of thin 7475-T761 sheets alternating with aramid fiber layers embedded in a special resin. Nominal thickness of aluminum sheet is 0.012 inch with a prepreg nominal thickness of 0.0085 inch. The primary advantage of this product is the significant improvement in fatigue and fatigue crack growth properties compared to conventional aluminum alloy structures. The product also has good damping capacity and resistance to impact.

*Manufacturing Considerations* — This product can be fabricated by conventional metal practices for machining, sawing, drilling, joining with fasteners and can be inspected by conventional procedures.

*Environmental Considerations* — This product has good corrosion resistance. The maximum service temperature is 200°F.

*Specifications and Properties* — A material specification is presented in Table 7.5.2.0(a). Room-temperature mechanical properties are presented in Table 7.5.2.0(b).

**Table 7.5.2.0(a). Material Specifications for 7475-T761  
Aramid Fiber Reinforced Sheet Laminate**

Specification	Form
AMS 4302	Sheet laminate

**7.5.2.1 T761 Temper** — Tensile and compressive stress-strain and tangent modulus curves are shown in Figures 7.5.2.1.6(a) through (f). Full-range tensile stress-strain curves are presented in Figures 7.5.2.1.6(g) through (j).



**MIL-HDBK-5H****1 December 1998****Table 7.5.2.0(b). Design Mechanical and Physical Properties of 7475-T761 Aluminum Alloy, Aramid Fiber Reinforced, Sheet Laminate**


Specification . . . . .	AMS 4302			
Form . . . . .	Aramid fiber reinforced sheet laminate			
Laminate lay-up . . . . .	2/1	3/2	4/3	5/4
Nominal thickness, in. . . . .	0.032	0.053	0.074	0.094
Basis . . . . .	S	S	S	S
<b>Mechanical Properties:</b>				
$F_{tu}$ , ksi:				
L . . . . .	103	111	114	116
LT . . . . .	56	51	50	48
$F_{ty}$ , ksi:				
L . . . . .	76	82	82	84
LT . . . . .	48	43	42	40
$F_{cy}$ , ksi:				
L . . . . .	46	46	44	44
LT . . . . .	51	48	47	45
$F_{su}^a$ , ksi . . . . .	35	33	33	32
$F_{sy}^a$ , ksi . . . . .	24	23	22	21
$F_{bru}^b$ , ksi:				
L (e/D = 1.5) . . . . .	91	83	84	82
LT (e/D = 1.5) . . . . .	96	85	86	80
L (e/D = 2.0) . . . . .	104	87	88	84
LT (e/D = 2.0) . . . . .	108	88	86	80
$F_{bry}^b$ , ksi:				
L (e/D = 1.5) . . . . .	73	70	66	69
LT (e/D = 1.5) . . . . .	76	69	69	67
L (e/D = 2.0) . . . . .	83	81	77	79
LT (e/D = 2.0) . . . . .	84	76	75	72
$e_t^c$ , percent:				
L . . . . .	1.5	1.8	1.7	1.8
LT . . . . .	6.1	6.4	6.3	6.6
$E$ , $10^3$ ksi:				
L . . . . .	9.8	9.9	10.0	9.8
LT . . . . .	7.7	7.1	6.7	6.7
$E_c$ , $10^3$ ksi:				
L . . . . .	9.6	9.6	9.6	9.7
LT . . . . .	7.8	7.3	7.0	6.9
$G$ , $10^3$ ksi:				
L . . . . .	2.8	2.6	2.3	2.3
LT . . . . .	2.6	2.4	2.3	2.3
$\mu$ :				
L . . . . .	0.35	0.35	0.35	0.35
LT . . . . .	0.25	0.25	0.25	0.25
<b>Physical Properties:</b>				
$\omega$ , lb/in. <sup>3</sup> . . . . .	0.085	0.083	0.082	0.081
$C$ , $K$ , and $\alpha$ . . . . .	...	...	...	...

a Shear values determined from data obtained using Iosipescu shear specimens.


b Bearing values are "dry pin" values per Section 1.4.7.1 determined in accordance with ASTM E 238.

c Total (elastic plus plastic) strain at failure determined from stress-strain curve. Values are minimum but not included in AMS 4302.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 7.5.2.1.6(a). Typical tensile stress-strain curves for 7475-T761 aluminum alloy, aramid fiber-reinforced, sheet laminate.**




**Figure 7.5.2.1.6(b). Typical tensile stress-strain curves for 7475-T761 aluminum alloy, aramid fiber-reinforced, sheet laminate.**


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 7.5.2.1.6(c). Typical tensile stress-strain curves for 7475-T761 aluminum alloy, aramid fiber-reinforced, sheet laminate.**



**Figure 7.5.2.1.6(d). Typical compressive stress-strain and compressive tangent-modulus curves for 7475-T761 aluminum alloy, aramid fiber-reinforced, sheet laminate.**


**MIL-HDBK-5H****1 December 1998**

**Figure 7.5.2.1.6(e). Typical compressive stress-strain and compressive tangent-modulus curves for 7475-T761 aluminum alloy, aramid fiber-reinforced, sheet laminate.**




**Figure 7.5.2.1.6(f). Typical compressive stress-strain and compressive tangent-modulus curves for 7475-T761 aluminum alloy, aramid fiber-reinforced, sheet laminate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 7.5.2.1.6(g). Typical tensile stress-strain curves (full range) for 7475-T761 aluminum alloy, aramid fiber-reinforced, sheet laminate.**

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 7.5.2.1.6(h). Typical tensile stress-strain curves (full range) for 7475-T761 aluminum alloy, aramid fiber-reinforced, sheet laminate.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 7.5.2.1.6(i). Typical tensile stress-strain curves (full range) for 7475-T761 aluminum alloy, aramid fiber-reinforced, sheet laminate.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 7.5.2.1.6(j). Typical tensile stress-strain curves (full range) for 7475-T761 aluminum alloy, aramid fiber-reinforced, sheet laminate.**



**MIL-HDBK-5H****1 December 1998****REFERENCES**

- 7.2.0(a) Williams, R. F., and Ingels, S. E., "The Fabrication of Beryllium—Volume I: A Survey of Current Technology," NASA TM X-53453 (July 1966).
- 7.2.0(b) Williams, R. F., and Ingels, S. E., "The Fabrication of Beryllium Alloys—Volume II: Forming Techniques for Beryllium Alloys," NASA TM X-43453 (July 1966).
- 7.2.0(c) Williams, R. F., and Ingels, S. E., "The Fabrication of Beryllium—Volume III: Metal Removal Techniques," NASA TM X-53453 (August 1966).
- 7.2.0(d) Williams, R. F., and Ingels, S. E., "The Fabrication of Beryllium—Volume IV: Surface Treatments for Beryllium Alloys," NASA TM X-53453 (July 1966).
- 7.2.0(e) Williams, R. F., and Ingels, S. E., "The Fabrication of Beryllium—Volume V: Thermal Treatments for Beryllium Alloys," NASA TM X-53453 (July 1966).
- 7.2.0(f) Williams, R. F., and Ingels, S. E., "The Fabrication of Beryllium—Volume VI: Joining Techniques for Beryllium Alloys," NASA TM X-53453 (July 1966).
- 7.2.0(g) Stonehouse, A. J., and Marder, J. M., "Beryllium," ASM Metals Handbook, Tenth Edition, Vol. 2, pp. 683-687, 1990.
- 7.2.0(h) Hanafee, J. E., "Effect of Annealing and Etching on Machine Damage In Structural Beryllium," J. Applied Metal Working, Vol. 1, No. 3, pp. 41-51 (1980).
- 7.2.0(i) Corle, R. R., Leslie, W. W., and Brewer, A. W., "The Testing and Heat Treating of Beryllium for Machine Damage Removal," RFP-3084, Rockwell International, Rocky Flats Plant, DOE, Sept. 1981.
- 7.2.1.1(a) Breslen, A. U., and Harris, W. B., "Health Protection in Beryllium Facilities, Summary of Ten Years' Experience," U.S. Atomic Energy Commission, Health and Safety Laboratory, New York Operations Office, Report HASL-36 (May 1, 1958).
- 7.2.1.1(b) Breslen, A. U., and Harris, W. B., "Practical Ways to Collect Beryllium Dust," Air Engineering, 2(7), p. 34 (July 1960).
- 7.2.1.1(c) Cholak, J., et al., "Toxicity of Beryllium, Final Technical Engineering Report," ASD TR 62-7-665 (April 1962).
- 7.2.1.1(d) "Beryllium Disease and Its Control," AMA Arch. Ind. Health, 19(2), pp. 91-267 (February 1959).
- 7.2.1.1(e) Stokinger, H. E., "Beryllium, Its Industrial Hygiene Aspect," Academic Press (1966).
- 7.2.1.1(f) Rossman, M. D., Preuss, O. P., and Powers, M. B., *Beryllium-Biomedical and Environmental Aspects*, Williams and Wilkins, Baltimore, Hong Kong, London, Munich, San Francisco, Sydney, and Tokyo, 319 pages (1991).
- 7.2.1.1(g) Crawford, R. F., and Barnes, A. B., "Strength Efficiency and Design Data for Beryllium Structures," ASD TR 61-692 (1961).

**MIL-HDBK-5H**

**1 December 1998**

- 7.3.0(a) “The Selection and Application of Wrought Copper and Copper Alloy,” by the ASM Committee on Applications of Copper, ASM Metals Handbook, Vol. 1, 8th Edition, pp. 960-972 (1961).
- 7.3.0(b) “The Selection and Application of Copper Alloy Castings,” by the ASM Committee on Copper Alloy Castings, ASM Metals Handbook, Vol. 1, 8th Edition, pp. 972-983 (1961).
- 7.3.0(c) CDA Standard Handbook, “Part 2—Wrought Mill Producers Alloy Data,” and “Part 7—Cast Products Data,” Copper Development Association, New York.

**MIL-HDBK-5H****1 December 1998****CHAPTER 8****STRUCTURAL JOINTS**

This chapter, while comprising three major sections, primarily is concerned with joint allowables. Section 8.1 is concerned with mechanically fastened joints; Section 8.2, with metallurgical joints (various welding and brazing processes). Section 8.3 contains information for structural component data; it is concerned with bearings, pulleys, and cables.

With particular reference to Section 8.1, the introductory section (8.1.1) contains fastener indexes that can be used as a quick reference to locate a specific table of joint allowables. Following this introductory section are five sections comprising the five major fastener categories, as shown in Table 8.0.1.

**Table 8.0.1. Structural Joints Index (Fastener Type)**

Section	Fastener Type
8.1.2	Solid Rivets
8.1.2.1	Protruding head
8.1.2.2	Flush head
8.1.3	Blind fasteners
8.1.3.1	Protruding head
8.1.3.2	Flush head
8.1.4	Swaged collar fasteners
8.1.4.1	Protruding head
8.1.4.2	Flush head
8.1.5	Threaded fasteners
8.1.5.1	Protruding head
8.1.5.2	Flush head
8.1.6	Special fasteners
8.1.6.1	Fastener sleeves

In each of the five major sections, there are subsections that describe the factors to be considered in determining the strength of fasteners and joints. After each major section, pertinent tables are presented.

Similarly, Section 8.2 has an introductory section (8.2.1), followed by two major sections comprising different metallurgical joints as shown in Table 8.0.2.

**MIL-HDBK-5H****1 December 1998****Table 8.0.2. Structural Joints Index (Joining Methods)**

Section	Joining Methods
8.2.2	Welded joints
8.2.2.1	Fusion
8.2.2.2	Flush and pressure
8.2.2.3	Spot and seam
8.2.3	Brazing
8.2.3.1	Copper
8.2.3.2	Silver

Following each 4-digit section, applicable tables and figures for the particular section are presented.

## **8.1 MECHANICALLY FASTENED JOINTS**

To determine the strength of mechanically fastened joints, it is necessary to know the strength of the individual fasteners (both by itself, and when installed in various thicknesses of the various materials). In most cases, failures in such joints occur by tensile failure of the fasteners, shearing of the fasteners and by bearing and/or tearing of the sheet or plate.

**8.1.1 INTRODUCTION AND FASTENER INDEXES** — Five categories of mechanical fasteners are presently contained in this Handbook, generically defined as follows:

*Solid Rivets* — Solid rivets are defined as one piece fasteners installed by mechanically upsetting one end.

*Blind Fasteners* — Blind fasteners are usually multiple piece devices that can be installed in a joint which is accessible from one side only. When a blind fastener is being installed, a self-contained mechanical, chemical, or other feature forms an upset on its inaccessible or blind side. These fasteners must be destroyed to be removed. This fastener category includes such fasteners as blind rivets, blind bolts, etc.

*Swaged Collar Fasteners* — Swaged collar fasteners are multiple piece fasteners, usually consisting of a solid pin and a malleable collar which is swaged or formed onto the pin to clamp the joint. This fastener usually is permanently installed. This fastener class includes such fasteners as “Hi-Shear” rivets, “Lockbolts”, and “Cherrybucks”.

*Threaded Fasteners* — Fasteners in this category are considered to be any threaded part (or parts) that after assembly in a joint can be easily removed without damage to the fastener or to the material being joined. This classification includes bolts, screws, and a wide assortment of proprietary fasteners.

*Special Fasteners* — As the name implies, this category of fastener is less commonly used in primary aircraft structure than the four categories listed above. Examples of such fastening systems are sleeves, inserts, panel fasteners, etc.

In the following 3-digit sections, descriptive information is presented relative to the establishment of design allowables in joints containing these four categories of fasteners. Following each such section are the various tables of joint allowables or associated information for computing joint allowables as described.

**MIL-HDBK-5H****1 December 1998**

Tables 8.1.1(a) through (e) are fastener indexes that list the joint allowables tables for each fastener category. These indexes are provided to make it easier to locate the allowables table for a given fastener and sheet material combination. Each of the indexes generally is similarly structured in the following manner. The left-hand column describes the fastener by referring to the MS or NAS part number or to a vendor part number when the fastener is not covered by either series. The second column contains the table number for the allowables table for each fastener. The fastener column has been so arranged that when protruding head and countersunk head fasteners are included in a given fastener index table, the protruding head tables appear first in the second column. The third column identifies generally the base material of the fastener. Generic terms usually are used, such as steel, aluminum, titanium, etc. The fourth column identifies the specific sheet or plate material.

It is recommended that Section 9.4.1 be reviewed in its entirety since it contains detailed information on the generation and analysis of joint data that results in the joint allowables tables contained in this section.

**8.1.1.1 Fastener Shear Strengths** — Fastener shear strengths accepted and documented by the aerospace industry and government agencies are listed in Table 8.1.1.1. Some existing tables in MIL-HDBK-5 may reflect other values; however, new fastener proposals will be classified in accordance with the above-noted table.

**8.1.1.2 Edge Distance Requirements** — The joint allowables in MIL-HDBK-5 are based on joint tests having edge distances of twice the nominal hole diameter, 2D. Therefore, the allowables are applicable only to joints having 2D edge distance.

**MIL-HDBK-5H****1 December 1998****Table 8.1.1(a). Fastener Index for Solid Rivets**

Fastener Identification <sup>a</sup>	Table Number	Rivet Material	Sheet Material	Page No.
Rivet Hole Size	8.1.2(a)	...	...	8-10
Shear Strength of Solid Rivets	8.1.2(b)	...	...	8-11
Unit Bearing Strength	8.1.2.1(a)	...	...	8-12
Shear Strength Corection Factors	8.1.2.1(b)	Aluminum	...	8-13
NAS1198 (MC) <sup>b</sup>	8.1.2.1(c)	A-286	A-286	8-14
MS20427M (MC)	8.1.2.2(a)	Monel	AISI 301/302	8-15
MS20427M (D) <sup>b</sup>	8.1.2.2(b)	Monel	AISI 301/302	8-16
MS20426AD (D)	8.1.2.2(c)	Aluminum	Aluminum	8-17
MS20426D (D)	8.1.2.2(d)	Aluminum	Aluminum	8-18
MS20426DD (D)	8.1.2.2(e)	Aluminum	Aluminum	8-19
MS20426 (MC)	8.1.2.2(f)	Aluminum	Clad 2024-T42	8-20
MS20426B (MC)	8.1.2.2(g)	Aluminum	AZ31B-H24	8-21
MS20427M (MC)	8.1.2.2(h)	Monel	Com Pure Titanium	8-22
BRFS-D (MC)	8.1.2.2(i)	Aluminum	Clad 2024-T3	8-23
BRFS-AD (MC)	8.1.2.2(j)	Aluminum	Clad 2024-T3	8-24
BRFS-DD (MC)	8.1.2.2(k)	Aluminum	Clad 2024-T3	8-25
BRFS-T (MC)	8.1.2.2(l)	Ti-45Cb	Clad 7075-T6/Ti-6Al-4V	8-26
MS14218E	8.1.2.2(m)	Aluminum	Clad 2024-T3	8-27
NAS1097E (MC)	8.1.2.2(n)	Aluminum	Clad 2024-T3/7075-T6	8-28
MS14218AD (MC)	8.1.2.2(o)	Aluminum	Clad 2024-T3	8-29
MS14219E (MC)	8.1.2.2(p)	Aluminum	Clad 2024-T3	8-30
MS14219E (MC)	8.1.2.2(q)	Aluminum	Clad 7075-T6	8-31
MS20426E	8.1.2.2(r)	Aluminum	Clad 2024-T3	8-32
MS20426E	8.1.2.2(s)	Aluminum	Clad 7075-T3	8-33

a In some cases, entries in this table identify the subject matter in certain tables.

b MC, machine countersunk holes; D, dimpled holes.

**MIL-HDBK-5H****1 December 1998****Table 8.1.1(b). Fastener Index for Blind Fasteners**

Fastener Identification	Table Number	Fastener Sleeve Material	Sheet or Plate Material	Page No.
<u>Protruding-head, Friction-Lock Blind Rivets</u>				
CR 6636	8.1.3.1.1(a)	A-286	Various	8-35
MS20600M	8.1.3.1.1(b)	Monel	AISI 301	8-36
MS20600M	8.1.3.1.1(c)	Monel	Clad 2024-T3/7075-T6	8-37
MS20600AD and MS20602AD	8.1.3.1.1(d)	Aluminum	Clad 2024-T3	8-38
MS20600B	8.1.3.1.1(e)	Aluminum	AZ31B-H24	8-39
<u>Protruding-head, Mechanical-Lock Blind Rivets</u>				
NAS1398C	8.1.3.1.2(a)	A-286	Alloy Steel	8-40
CR 2643	8.1.3.1.2(a)	A-286	Alloy Steel	8-40
NAS1398 MS or MW	8.1.3.1.2(b)	Monel	AISI 301-½ Hard	8-41
NAS1398 MS or MW	8.1.3.1.2(c)	Monel	Clad 7075-T6	8-42
NAS1398B	8.1.3.1.2(d <sub>1</sub> )	Aluminum	Clad 2024-T3	8-43
NAS1398D	8.1.3.1.2(d <sub>1</sub> )	Aluminum	Clad 2024-T3	8-43
NAS1738B and NAS1738E	8.1.3.1.2(d <sub>2</sub> )	Aluminum	Clad 2024-T3	8-44
NAS1398B	8.1.3.1.2(e)	Aluminum	AZ31B-H24	8-45
NAS1738B and NAS1738E	8.1.3.1.2(e)	Aluminum	AZ31B-H24	8-45
CR 2A63	8.1.3.1.2(f)	Aluminum	Clad 2024-T81	8-46
CR 4623	8.1.3.1.2(g)	A-286	Clad 7075-T6	8-47
CR 4523	8.1.3.1.2(h)	Monel	Clad 7075-T6	8-48
NAS1720KE and NAS1720KE (L)	8.1.3.1.2(i)	Aluminum	Clad 7075-T6	8-49
NAS1720C and NAS1720C (L)	8.1.3.1.2(j)	A-286	Clad 2024-T3	8-50
M7885/2	8.1.3.1.2(k)	Aluminum	Clad 7075-T6	8-51
M7885/6	8.1.3.1.2(l)	Aluminum	Clad 2024-T3	8-52
AF3243	8.1.3.1.2(m)	Aluminum	Clad 2024-T3	8-53
HC3213	8.1.3.1.2(n)	Aluminum	Clad 2024-T3	8-54
HC6223	8.1.3.1.2(o)	Aluminum	Clad 2024-T3	8-55
HC6253	8.1.3.1.2(p)	Aluminum	Clad 2024-T3	8-56
<u>Flush-head, Friction-Lock Blind Rivets</u>				
CR 6626 (MC) <sup>a</sup>	8.1.3.2.1(a)	A-286	Various	8-57
MS20601M (MC)	8.1.3.2.1(b)	Monel	17-7PH (TH1050)	8-58
MS20601M (D) <sup>a</sup>	8.1.3.2.1(c)	Monel	AISI 301	8-59
MS20601M (MC)	8.1.3.2.1(d <sub>1</sub> )	Monel	AISI 301-Ann	8-60
MS20601M (MC)	8.1.3.2.1(d <sub>2</sub> )	Monel	AISI 301-¼ Hard	8-61
MS20601M (MC)	8.1.3.2.1(d <sub>3</sub> )	Monel	AISI 301-½ Hard	8-62
MS20601M (MC)	8.1.3.2.1(e)	Monel	7075-T6	8-63
MS20601AD and MS20603AD (MC)	8.1.3.2.1(f)	Aluminum	Clad 2024-T3	8-64
MS20601B (MC)	8.1.3.2.1(g)	Aluminum	AZ31B-H24	8-65

a MC, machine countersunk holes; D, dimpled holes.

**MIL-HDBK-5H****1 December 1998****Table 8.1.1(b). Fastener Index for Blind Fasteners—Continued**

Fastener Identification	Table Number	Fastener Sleeve Material	Sheet or Plate Material	Page No.
<u>Flush-head, Mechanical-Lock Spindle Blind Rivets</u>				
NAS1399C (MC)	8.1.3.2.2(a)	A-286	Alloy Steel	8-66
CR 2642 (MC)	8.1.3.2.2(a)	A-286	Alloy Steel	8-66
NAS1399 MS or MW (MC)	8.1.3.2.2(b)	Monel	AISI 301-½ Hard	8-67
NAS1291C (MC)	8.1.3.2.2(c)	A-286	Clad 7075-T6	8-68
NAS1399 MS or MW (MC)	8.1.3.2.2(d)	Monel	Clad 7075-T6	8-69
NAS1921M (MC)	8.1.3.2.2(e)	Monel	Clad 7075-T6	8-70
CR 2A62 (MC)	8.1.3.2.2(f)	Aluminum	Clad 2024-T81	8-71
NAS1921B (MC)	8.1.3.2.2(g)	Aluminum	Clad 7075-T6	8-72
NAS1399B (MC)	8.1.3.2.2(h)	Aluminum	Clad 2024-T3	8-73
NAS1399D (MC)	8.1.3.2.2(h)	Aluminum	Clad 2024-T3	8-73
NAS1739B and NAS1379E (MC)	8.1.3.2.2(i)	Aluminum	Clad 2024-T3	8-74
NAS1739B and NAS1739E (D)	8.1.3.2.2(i)	Aluminum	Clad 2024-T3	8-74
NAS1399B (MC)	8.1.3.2.2(j)	Aluminum	AZ31B-H24	8-75
NAS1739B and NAS1739E (MC)	8.1.3.2.2(j)	Aluminum	AZ31B-H24	8-75
CR 4622 (MC)	8.1.3.2.2(k)	A-286	Clad 7075-T6	8-76
CR 4522 (MC)	8.1.3.2.2(l)	Monel	Clad 7075-T6/T651	8-77
NAS1721KE and NAS1721KE (L) (MC)	8.1.3.2.2(m)	Aluminum	Clad 2024-T3	8-78
NAS1721C and NAS1721C (L) (MC)	8.1.3.2.2(n)	A-286	Clad 7075-T6	8-79
M 7885/3 (MC)	8.1.3.2.2(o)	Aluminum	Clad 2024-T3	8-80
M 7885/7 (MC)	8.1.3.2.2(p)	Aluminum	Clad 2024-T3	8-81
HC3212 (MC)	8.1.3.2.2(q)	Aluminum	Clad 2024-T3	8-82
MBC 4807 and MBC 4907	8.1.3.2.2(r)	Aluminum	Clad 2024-T3	8-83
MBC 4801 and MBC 4901	8.1.3.2.2(s)	Aluminum	Clad 2024-T3	8-84
HC6222	8.1.3.2.2(t)	Aluminum	Clad 2024-T3	8-85
HC6252	8.1.3.2.2(u)	Aluminum	Clad 2024-T3	8-86
<u>Flush-head Blind Bolts</u>				
MS21140 (MC)	8.1.3.2.3(a)	A-286	Clad 7075-T6/T651	8-87
MS90353 (MC)	8.1.3.2.3(b <sub>1</sub> )	Alloy Steel	Clad 2024-T3/T351	8-88
MS90353 (MC)	8.1.3.2.3(b <sub>2</sub> )	Alloy Steel	Clad or Bare 7075-T6 or T651	8-89
FF-200, FF-260 and FF-312 (MC)	8.1.3.2.3(c)	Alloy Steel	Clad 2024-T42/ 7075-T6	8-90
NS 100 (MC)	8.1.3.2.3(d)	Alloy Steel	Clad 7075-T6	8-91
SSHFA-200 and SSHFA-260(MC)	8.1.3.2.3(e)	Aluminum	Clad 2024-T42/ 7075-T6	8-92
PLT-150 (MC)	8.1.3.2.3(f)	Alloy Steel	Clad 7075-T6/T651	8-93
NAS1670L (MC)	8.1.3.2.3(g)	Alloy Steel	Clad 7075-T6/T651	8-94
NAS1674L (MC)	8.1.3.2.3(h)	Aluminum	Clad 7075-T6	8-95

a MC, machine countersunk holes; D, dimpled holes.



**MIL-HDBK-5H****1 December 1998****Table 8.1.1(c). Fastener Index for Swaged-Collar/Upset-Pin Fasteners**

Fastener Identification	Table Number	Fastener Pin Material	Sheet or Plate Material	Page No.
Ultimate Single-Shear and Tensile Strengths	8.1.4	Alloy Steel and Alum.	...	8-98
CSR 925	8.1.4.1(a)	Titanium	Clad 7075-T6	8-99
CSR 925	8.1.4.1(b)	Titanium	Clad 2024-T3	8-100
NAS1436-NAS1442 (MC) <sup>a</sup>	8.1.4.2(a)	Alloy Steel	Clad 7075-T6/T651	8-101
NAS7024-NAS7032 (MC)	8.1.4.2(b)	Alloy Steel	Clad 7075-T6/T651	8-102
CSR 924 (MC)	8.1.4.2(c)	Titanium	Clad 7075-T6	8-103
CSR 924 (MC)	8.1.4.2(d)	Titanium	Clad 2024-T3	8-104
HSR 201 (MC)	8.1.4.2(e)	A-286	Clad 7075-T6	8-105
HSR 101 (MC)	8.1.4.2(f)	Titanium	Clad 7075-T6	8-106
GPL 3SC-V (MC)	8.1.4.2(g)	Titanium	Clad 7075-T6	8-107
GPL 3SC-V (MC)	8.1.4.2(h)	Titanium	Clad 2024-T3	8-108
LGPL 2SC-V (MC)	8.1.4.2(i)	Titanium	Clad 7075-T6	8-109
LGPL 2SC-V (MC)	8.1.4.2(j)	Titanium	Clad 2024-T3	8-110

a MC, machine countersunk holes.

**Table 8.1.1(d). Fastener Index for Threaded Fasteners**

Fastener Identification <sup>a</sup>	Table Number	Fastener Sleeve Material	Sheet	Page No.
Single Shear Strength	8.1.5(a)	Steel	...	8-113
Tensile Strength	8.1.5(b <sub>1</sub> )	Steel	...	8-114
Tensile Strength	8.1.5(b <sub>2</sub> )	...	...	8-115
Unit Bearing Strength	8.1.5.1	Alloy Steel	...	8-116
AN 509 Screws (MC) <sup>b</sup>	8.1.5.2(a <sub>1</sub> )	Alloy Steel	Clad 2024-T3	8-117
AN 509 Screws (MC)	8.1.5.2(a <sub>2</sub> )	CRES	Clad 7075-T6	8-118
PBF 11 (MC)	8.1.5.2(b)	Alloy Steel	Ti-6Al-4V	8-119
TL 100 (MC)	8.1.5.2(c)		Clad 7075-T6	8-120
TLV 100 (MC)	8.1.5.2(d)	Titanium	Clad 7075-T6	8-121
HPB-V (MC)	8.1.5.2(e)	Titanium	Clad 7075-T6	8-122
KLBHV with KFN 600 (MC)	8.1.5.2(f)	Titanium	Clad 7075-T6	8-123
HL-61-70 (MC)	8.1.5.2(g)	CRES	Clad 7075-T6	8-124
HL-719-79 (MC)	8.1.5.2(h)	Alloy Steel	Clad 7075-T6	8-125
HL-11 (MC)	8.1.5.2(i)	Titanium	Clad 7075-T6	8-126
HL-911 (MC)	8.1.5.2(j)	Titanium	Clad 7075-T6	8-127
NAS4452S and KS 100-FV with NAS4445DD (MC)	8.1.5.2(k)	Alloy Steel or Titanium	Clad 7075-T6	8-128
HPG-V (MC)	8.1.5.2(l)	Titanium	Clad 7075-T6	8-129
NAS4452V with NAS4445 DD (MC)	8.1.5.2(m)	Titanium	Clad 7075-T6	8-130
HL18Pin, HL70 Collar (MC)	8.1.5.2(n)	Alloy Steel	Clad 7075-T6	8-131
HL19 Pin, HL70 Collar (MC)	8.1.5.2(o)	Alloy Steel	Clad 7075-T6	8-132

a In some cases entries in this table identify the subject matter in certain tables.

b MC, machine countersunk holes; D, dimpled holes.

**MIL-HDBK-5H****1 December 1998****Table 8.1.1(e). Fastener Index for Special Fasteners**

Fastener Identification	Table Number	Fastener Pin Material	Sheet or Plate Material	Page No.
ACRES Sleeves	...	A-286	Clad 7075-T6	8-133
MIL-B-8831/4 (MC) <sup>a</sup>	8.1.6.2(a)	Steel Pin, Aluminum Sleeve	Clad 7075-T6	8-134
MIL-B-8831/4 (MC)	8.1.6.2(b)	Steel Pin, Aluminum Sleeve	Clad 2024-T3	8-135

a MC, machine countersunk holes.

**Table 8.1.1.1. Fastener Shear Strengths**

F <sub>su</sub> , ksi	Examples of Current Alloys Which Meet Level <sup>a</sup>	Current Usage		
		Driven Rivets	Blind Fasteners	Solid Shank Fasteners
28	5056	X	X	
30	2117	X	X	
34	2017	X	X	
36	2219	X	X	
38	2017	X	X	
41	2024 and 7050-T73	X		
43	7050-T731	X	X	X
46	7075		X	
49	Monel	Undriven		
50	Ti/Cb	X		
55	Monel		X	
75	Alloy Steel and CRES		X	X
78	A-286			X
90	A-286	Undriven		
95	Alloy Steel, A-286, Ti-6Al-4V	X	X	X
108	Alloy Steel and Ti-6Al-2Sn			X
110	A-286			X
112	Alloy Steel		X	X
125	Alloy Steel and CRES			X
132	Alloy Steel			X
145	MP35N			X
156	Alloy Steel			X
180	Alloy Steel			X

a Different tempers and thermal treatments are used to obtain desired fastener shear strengths.

**MIL-HDBK-5H**  
**1 December 1998**

**8.1.2 SOLID RIVETS** — The recommended diameter dimensions of the upset head on solid rivets shall be at least 1.3 times the nominal shank diameter except for 7050 rivets which shall be at least 1.4 times the nominal shank diameter. Head heights shall be a minimum of 0.3 diameter. Shear strengths for driven rivets may be based on areas corresponding to the nominal hole diameter provided that the nominal hole diameter is not larger than the values listed in Table 8.1.2(a). If the nominal hole diameter is larger than the listed value, the listed value shall be used. Shear strength values for solid rivets of a number of rivet materials are given in Table 8.1.2(b).

**8.1.2.1 Protruding-Head Solid Rivet Joints** — The unit load at which shear or bearing type of failure occurs is calculated separately and the lower of the two governs the design.

The design bearing stress for various materials at both room and elevated temperatures is given in the strength properties stated for each alloy or group of alloys and is applicable to riveted joints wherein cylindrical holes are used and where  $t/D$  is greater than or equal to 0.18; where  $t/D$  is less than 0.18, tests to substantiate yield and ultimate bearing strengths must be performed. These bearing stresses are applicable only for the design of rigid joints where there is no possibility of relative motion of the parts joined without deformation of such parts. Design bearing stresses at low temperatures will be higher than those specified for room temperature; however, no quantitative data are available.

For convenience, “unit” sheet bearing strengths for rivets, based on a bearing stress of 100 ksi and nominal hole diameters, are given in Table 8.1.2.1(a).

In computing protruding-head rivet design shear strengths, the shear strength values obtained from Table 8.1.2(b) should be multiplied by the correction factors given in Table 8.1.2.1(b). This compensates for the reduction in rivet shear strength resulting from high bearing stresses on the rivet at  $t/D$  ratios less than 0.33 for single-shear joints and 0.67 for double-shear joints.

For those rivet material sheet material combinations where test data shows the above to be unconservative or for rivet materials other than those shown in Table 8.1.2(b), joint allowables should be established by test in accordance with Section 9.4. From such tests tabular presentation of ultimate load and yield load allowables are made.

Unless otherwise specified, yield load is defined in Section 9.4.1.3.3 as the load which results in a joint permanent set equal to  $0.04D$ , where  $D$  is the decimal equivalent of the hole diameter defined in Table 9.4.1.2(a).

Table 8.1.2.1(c) provides ultimate and yield strength data on protruding-head A-286 solid rivets in aged A-286 sheet, for a variety of conditions of exposure.

**8.1.2.2 Flush-Head Solid Rivet Joints** — Tables 8.1.2.2(a) through (s) contain joint allowables for various flush-head solid rivet/sheet material combinations. The allowable ultimate loads were established from test data using the average ultimate test load divided by a factor of 1.15. (See Section 9.4 for possible variations.) This factor is not applicable to shear strength cutoff values. Shear strength cutoff values may be either the procurement specification shear strength ( $S$  value) of the fastener, or if no specification exists, a statistical value determined from test results as described in Section 9.4.

Yield load allowables are established from test data. Unless otherwise specified, the yield load is defined in Section 9.4.1.3.3 as the load which results in a joint permanent set equal to  $0.04D$ , where  $D$  is the decimal equivalent of the hole diameter defined in Table 9.4.1.2(a).

**MIL-HDBK-5H****1 December 1998**

For machine countersunk joints, the sheet gage specified in the tables is that of the countersunk sheet. When the noncountersunk sheet is thinner than the countersunk sheet, the bearing allowable for the noncountersunk sheet-fastener combination should be computed, compared to the table value, and the lower of the two values selected. Increased attention should be paid to detail design in cases where  $t/D < 0.25$  because of possibly greater incidence of difficulty in service life.

**Table 8.1.2(a). Standard Rivet-Hole Drill Sizes and Nominal Hole Diameters**

Rivet Size, in.	1/16	3/32	1/8	5/32	3/16	1/4	5/16	3/8
Drill No. ....	51	41	30	21	11	F	P	W
Nominal Hole Diameter, in.	0.067	0.096	0.1285	0.159	0.191	0.257	0.323	0.386

**Table 8.1.2(b). Single Shear Strength of Solid Rivets<sup>a</sup>**

Undriven			Driven		Rivet Designation	Rivet Size							
Rivet Material	F <sub>su</sub> (ksi)		Rivet Material	F <sub>su</sub> <sup>c</sup> (ksi)		1/16	3/32	1/8	5/32	3/16	1/4	5/16	3/8
	Min	Max				Driven Single Shear Strength, lbs <sup>b</sup>							
5056-H32	24	n/a	5056-H321 <sup>d</sup>	28 <sup>e</sup>	B <sup>f</sup>	99	203	363	556	802	1450	2290	3275
2117-T4	26	n/a	2117-T3	30 <sup>e</sup>	AD	106	217	389	596	860	1555	2455	3510
2017-T4	35	42	2017-T3	38 <sup>e</sup>	D	134	275	493	755	1085	1970	3115	4445
2024-T4	37	n/a	2024-T31	41 <sup>g</sup>	DD	145	297	532	814	1175	2125	3360	4795
7050-T73	41	46	7050-T731 <sup>d</sup>	43 <sup>e</sup>	E <sup>h</sup>	152	311	558	854	1230	2230	3520	5030
Monel	49	59	Monel	52 <sup>e</sup>	M	183	376	674	1030	1490	2695	4260	6085
Ti-45Cb	50	59	Ti-45Cb	53 <sup>e</sup>	T	187	384	687	1050	1515	2745	4340	6200
A-286	85	95	A-286	90 <sup>e</sup>	-	317	651	1165	1785	2575	4665	7375	10500

a All rivets must be sufficiently driven to fill the rivet hole at the shear plane. Driving changes the rivet strength from the undriven to the driven condition and thus provides the above driven shear strengths.

b Based on nominal hole diameter specified in Table 8.1.2(a).

c Shear stresses are for the as driven condition on B-basis probability.

d The temper designations last digit (1), indicates recognition of strengthening derived from driving.

e The bucktail's minimum diameter is 1.5 times the nominal hole diameter in Table 8.1.2(a).

f Should not be exposed to temperatures over 150°F.

g Driven in the W (fresh or ice box) condition to minimum 1.4D bucktail diameter.

h E (or KE, as per NAS documents).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.2.1(a). Unit Bearing Strength of Sheet on Rivets,  $F_{br} = 100$  ksi**

Sheet thickness, in.	Unit Bearing Strength for Indicated Rivet Diameter, lbs							
	1/16	3/32	1/8	5/32	3/16	1/4	5/16	3/8
0.012 .....	80	...	...	...	...	...	...	...
0.016 .....	107	...	...	...	...	...	...	...
0.018 .....	121	173	...	...	...	...	...	...
0.020 .....	134	192	...	...	...	...	...	...
0.025 .....	168	240	321	...	...	...	...	...
0.032 .....	214	307	411	509	...	...	...	...
0.036 .....	241	346	462	572	688	...	...	...
0.040 .....	268	384	514	636	764	...	...	...
0.045 .....	302	432	578	716	860	...	...	...
0.050 .....	335	480	642	795	955	1285	...	...
0.063 .....	422	605	810	1002	1203	1619	2035	...
0.071 .....	476	682	912	1129	1356	1825	2293	2741
0.080 .....	536	768	1028	1272	1528	2056	2584	3088
0.090 .....	603	864	1156	1431	1719	2313	2907	3474
0.100 .....	670	960	1285	1590	1910	2570	3230	3860
0.125 .....	838	1200	1606	1988	2388	3212	4038	4825
0.160 .....	1072	1536	2056	2544	3056	4112	5168	6176
0.190 .....	1273	1824	2442	3021	3629	4883	6137	7334
0.250 .....	1670	2400	3210	3975	4775	6425	8075	9650

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.2.1(b). Shear Strength Correction Factors for Solid Protruding Head Rivets<sup>a</sup>**

Rivet Diameter, in.	1/16	3/32	1/8	5/32	3/16	1/4	5/16	3/8
Single-Shear Rivet Strength Factors								
Sheet thickness, in.:	0.964	...	...	...	...	...	...	...
0.016 .....	0.981	0.912	...	...	...	...	...	...
0.018 .....	0.995	0.933	...	...	...	...	...	...
0.020 .....	1.000	0.970	0.920	...	...	...	...	...
0.025 .....	...	1.000	0.964	0.925	...	...	...	...
0.032 .....	...	...	0.981	0.946	0.912	...	...	...
0.036 .....	...	...	0.995	0.964	0.933	...	...	...
0.040 .....	...	...	1.000	0.981	0.953	...	...	...
0.045 .....	...	...	...	0.995	0.970	0.920	...	...
0.050 .....	...	...	...	1.000	1.000	0.961	0.922	...
0.063 .....	...	...	...	...	...	0.979	0.944	0.909
0.071 .....	...	...	...	...	...	0.995	0.964	0.933
0.080 .....	...	...	...	...	...	1.000	0.981	0.953
0.090 .....	...	...	...	...	...	...	0.995	0.972
0.100 .....	...	...	...	...	...	...	1.000	1.000
0.125 .....	...	...	...	...	...	...	...	...
Double-Shear Rivet Strength Factors								
Sheet thickness, in.:	0.687	...	...	...	...	...	...	...
0.016 .....	0.744	0.518	...	...	...	...	...	...
0.018 .....	0.789	0.585	...	...	...	...	...	...
0.020 .....	0.870	0.708	0.545	...	...	...	...	...
0.025 .....	0.941	0.814	0.687	0.560	...	...	...	...
0.032 .....	0.969	0.857	0.744	0.630	0.518	...	...	...
0.036 .....	0.992	0.891	0.789	0.687	0.585	...	...	...
0.040 .....	1.000	0.924	0.834	0.744	0.653	...	...	...
0.045 .....	...	0.951	0.870	0.789	0.708	0.545	...	...
0.050 .....	...	1.000	0.937	0.872	0.808	0.679	0.550	...
0.063 .....	...	...	0.966	0.909	0.852	0.737	0.622	0.508
0.071 .....	...	...	0.992	0.941	0.891	0.789	0.687	0.585
0.080 .....	...	...	1.000	0.969	0.924	0.834	0.744	0.653
0.090 .....	...	...	...	0.992	0.951	0.870	0.789	0.708
0.100 .....	...	...	...	1.000	1.000	0.935	0.870	0.805
0.125 .....	...	...	...	...	...	0.992	0.941	0.891
0.160 .....	...	...	...	...	...	1.000	0.981	0.939
0.190 .....	...	...	...	...	...	...	1.000	1.000
0.250 .....	...	...	...	...	...	...	...	...

a Sheet thickness is that of the thinnest sheet in single-shear joints and the middle sheet in double-shear joints. Values based on tests of aluminum rivets, Reference 8.1(a).

**Table 8.1.2.1(c). Static Joint Strength of Protruding Head A-286 Solid Rivets in A-286 Alloy Sheet at Various Temperatures**

Rivet Type .....	NAS1198 ( $F_{su} = 90$ ksi)								
Sheet Material .....	A-286, solution treated and aged, $F_{tu} = 140$ ksi								
Temperature .....	Room Temperature			1200 °F, Stabilized 15 Minutes			1200 °F, Rapid Heating in 20 Seconds, Tested in 15 Seconds		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)
Sheet thickness, in.:	Ultimate Strength <sup>a</sup> , lbs.								
0.020 .....	478	...	...	331	...	...	470 <sup>b</sup>	...	...
0.025 .....	590	740	...	426	626	...	587 <sup>b</sup>	726 <sup>b</sup>	...
0.032 .....	745	932	1132	560	801	962	752 <sup>b</sup>	930 <sup>b</sup>	1117 <sup>b</sup>
0.040 .....	923	1152	1397	682	1002	1204	783	1164 <sup>b</sup>	1397 <sup>b</sup>
0.050 .....	1023	1428	1677	...	1044	1505	...	1198	1729 <sup>b</sup>
0.063 .....	1131	1578	1821	...	...	1507	...	...	...
0.071 .....	1170	1660	1909	...	...	...	...	...	...
0.080 .....	...	1752	2008	...	...	...	...	...	...
0.090 .....	...	1790	2118	...	...	...	...	...	...
0.100 .....	...	...	2229	...	...	...	...	...	...
0.125 .....	...	...	2504	...	...	...	...	...	...
0.160 .....	...	...	2580	...	...	...	...	...	...
Rivet shear strength <sup>c</sup> .....	1170	1790	2580	682	1044	1507	783	1198	1729
Sheet thickness, in.:	Yield Strength <sup>a,d</sup> , lbs.								
0.020 .....	447	...	...	300	...	...	300	...	...
0.025 .....	590	695	...	374	464	...	374	464	...
0.032 .....	745	932	974	479	593	713	478	593	712
0.040 .....	867	1152	1167	598	741	890	598	740	889
0.050 .....	938	1331	1407	...	925	1112	...	924	1110
0.063 .....	1031	1447	1649	...	...	1400	...	...	...
0.071 .....	1089	1518	1723	...	...	...	...	...	...
0.080 .....	...	1597	1806	...	...	...	...	...	...
0.090 .....	...	1686	1898	...	...	...	...	...	...
0.100 .....	...	...	1990	...	...	...	...	...	...
0.125 .....	...	...	2221	...	...	...	...	...	...
0.160 .....	...	...	2543	...	...	...	...	...	...

a Test data from which the yield and ultimate strengths were derived can be found in Reference 8.1.2.1.

b Yield value is less than 2/3 of indicated ultimate.

c Rivet shear strength is documented in NAS1198 as 90 ksi.

d Permanent set at yield load: 0.005 inch.

Note: Because of difficulties encountered upsetting countersunk head rivets in thin A-286 sheet, such conditions should be avoided in design.



**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.2.2(a). Static Joint Strength of 100° Flush Head Monel Solid Rivets in Machine-Countersunk Stainless Steel Sheet**

Rivet Type	MS20427M ( $F_{su} = 49$ ksi)									
Sheet Material	AISI 302-Annealed			AISI 301-¼ Hard			AISI 301-½ Hard AISI 301-Full Hard			
Rivet Diameter, in. (Nominal Hole Diameter, in.)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	3/32 (0.096)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)
Ultimate Strength, lbs										
Sheet thickness, in.:										
0.040	439 <sup>a</sup>	...	...	439	...	...	251	439	...	...
0.050	526 <sup>a</sup>	<sup>b</sup> 673 <sup>a</sup>	...	468	<sup>b</sup> 673	...	322	447	<sup>b</sup> 673	...
0.063	635 <sup>a</sup>	820 <sup>a</sup>	<sup>b</sup> ...	595	732	<sup>b</sup> ...	355	538	688	<sup>b</sup> ...
0.071	...	915 <sup>a</sup>	1110 <sup>a</sup>	635	830	990	...	615	741	984 <sup>b</sup>
0.080	...	973 <sup>a</sup>	1246 <sup>a</sup>	<sup>b</sup> ...	936	1118	<sup>b</sup> ...	635	850	995 <sup>b</sup>
0.090	...	...	1380 <sup>a</sup>	...	973	1255	...	...	973	1132
0.100	...	...	1400	...	...	1400	...	...	...	1280
0.125	...	...	...	...	...	...	...	...	...	1400
Rivet shear strength <sup>c</sup>	635	973	1400	635	973	1400	355	635	973	1400
Yield Strength <sup>d</sup> , lbs										
Sheet thickness, in.:										
0.040	259	...	...	368	...	...	212	324	...	...
0.050	324	402	...	442	570	...	293	360	498	...
0.063	408	506	...	492	686	...	355	480	557	...
0.071	...	570	685	561	714	958	...	561	630	780
0.080	...	643	771	...	764	1012	...	635	765	848
0.090	...	...	865	...	893	1062	...	...	893	1000
0.100	...	...	965	...	...	1160	...	...	...	1160
0.125	...	...	...	...	...	...	...	...	...	1400
Head height (ref.), in.	0.048	0.061	0.077	0.048	0.061	0.077	0.042	0.048	0.061	0.077

a Yield value is less than 2/3 of the indicated ultimate strength value.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Rivet shear strength is documented in MS20427M.

d Permanent set at yield load: 0.005 inch.

**Table 8.1.2.2(b). Static Joint Strength of 100° Flush Head Monel Solid Rivets in Dimpled Stainless Steel Sheet**

Rivet Type .....	MS20427M ( $F_{su} = 49$ ksi)										
Sheet Material .....	AISI 302 - annealed				AISI 301 - 1/4 hard			AISI 301 - 1/2 hard			
Rivet Diameter, in. ....	1/8	5/32	3/16	1/4	1/8	5/32	3/16	3/32	1/8	5/32	3/16
(Nominal Hole Diameter, in.) .....	(0.1285)	(0.159)	(0.191)	(0.257)	(0.1285)	(0.159)	(0.191)	(0.096)	(0.1285)	(0.159)	(0.191)
Ultimate Strength, lbs.											
Sheet thickness, in.:											
0.020 .....	348	...	...	...	497	...	...	348	497	...	...
0.025 .....	441	536	...	...	595	766	...	355	595	766	...
0.032 .....	568	698	846	...	635	931	1163	...	635	931	1163
0.040 .....	635	884	1046	1370	...	973	1382	...	...	973	1382
0.050 .....	...	973	1320	1730	...	...	1405	...	...	...	1405
0.063 .....	...	...	1405	2240	...	...	...	...	...	...	...
0.071 .....	...	...	...	2490	...	...	...	...	...	...	...
0.080 .....	...	...	...	2540	...	...	...	...	...	...	...
Rivet shear strength <sup>a</sup> .....	635	973	1405	2540	635	973	1405	355	635	973	1405
Yield Strength <sup>b</sup> , lbs.											
Sheet thickness, in.:											
0.020 .....	336	...	...	...	449	...	...	329	449	...	...
0.025 .....	427	518	...	...	533	681	...	355	533	681	...
0.032 .....	550	679	801	...	635	842	1049	...	635	842	1049
0.040 .....	635	856	1020	1326	...	973	1252	...	...	973	1252
0.050 .....	...	973	1280	1678	...	...	1405	...	...	...	1405
0.063 .....	...	...	1405	2140	...	...	...	...	...	...	...
0.071 .....	...	...	...	2420	...	...	...	...	...	...	...
0.080 .....	...	...	...	2540	...	...	...	...	...	...	...
Head height (max.), in. ....	0.048	0.061	0.077	0.103	0.048	0.061	0.077	0.042	0.048	0.061	0.077

a Rivet shear strength from Table 8.1.2(b).

b Permanent set at yield load: 0.005 inch.

**Table 8.1.2.2(c). Static Joint Strength of 100° Flush Head Aluminum Alloy (2117-T3) Solid Rivets in Dimpled Aluminum Alloy Sheet<sup>a,b</sup>**

Rivet Type .....	MS20426AD ( $F_{su} = 30$ ksi)								
Sheet Material .....	2024-T3 2024-T42 2024-T62 2024-T81	2024-T3 2024-T42	2024-T62 2024-T81	2024-T86 7075-T6					
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	3/32 (0.096)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	5/32 (0.159)	3/16 (0.191)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)
Ultimate Strength, lbs.									
Sheet thickness, in.:									
0.016 .....	177	...	...	...	...	...	...	...	...
0.020 .....	209	299	...	...	...	...	302	...	...
0.025 .....	217	360	474	...	462	...	383	462	...
0.032 .....	...	388	568	722	596	725	388	596	725
0.040 .....	...	...	596	839	...	862	...	...	862
0.050 .....	...	...	...	862	...	...	...	...	...
Rivet shear strength <sup>c</sup> .....	217	388	596	862	596	862	388	596	862
Yield Strength <sup>d</sup> , lbs.									
Sheet thickness, in.:									
0.016 .....	154	...	...	...	...	...	...	...	...
0.020 .....	184	257	...	...	...	...	257	...	...
0.025 .....	209	315	324	...	324	...	315	410	...
0.032 .....	...	367	430	512	430	512	367	525	640
0.040 .....	...	...	506	644	...	644	...	...	782
0.050 .....	...	...	...	757	...	...	...	...	...
Head height (max.), in. ....	0.036	0.042	0.055	0.070	0.055	0.070	0.042	0.055	0.070

a These allowables apply to double dimpled sheets and to the upper sheet dimpled into a machine-countersunk lower sheet. Sheet gage is that of the thinnest sheet for double dimpled joints and of the upper dimpled sheet for dimpled, machine-countersunk joints. The thickness of machine-countersunk sheet must be at least one tabulated gage thicker than the upper sheet. In no case shall allowables be obtained by extrapolation for gages other than those shown.

b Test data from which the yield strengths listed were derived and can be found in Reference 8.1.2.2.

c Rivet shear strength from Table 8.1.2(b).

d Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**Table 8.1.2.2(d). Static Joint Strength of 100° Flush Head Aluminum Alloy (2017-T3) Solid Rivets in Dimpled Aluminum Alloy Sheet<sup>a,b</sup>**

Rivet Type . . . . .	MS20426D ( $F_{su} = 38$ ksi)								
Sheet Material . . . . .	2024-T3 and 2024-T42			2024-T86 and 7075-T6			2024-T62 and 2024-T81		
Rivet Diameter, in. . . . .	5/32	3/16	1/4	5/32	3/16	1/4	5/32	3/16	1/4
(Nominal Hole Diameter, in.) . . . . .	(0.159)	(0.191)	(0.257)	(0.159)	(0.191)	(0.257)	(0.159)	(0.191)	(0.257)
Ultimate Strength, lbs.									
Sheet thickness, in.:									
0.025 . . . . .	419	...	...	530	...	...	419	...	...
0.032 . . . . .	600	681	...	672	822	...	600	681	...
0.040 . . . . .	738	905	845	755	1000	1108	738	905	1108
0.050 . . . . .	755	1090	1332	...	1090	1508	755	1090	1508
0.063 . . . . .	...	...	1695	...	...	1803	...	...	1803
0.071 . . . . .	...	...	1853	...	...	1930	...	...	1930
0.080 . . . . .	...	...	1970	...	...	1970	...	...	1970
Rivet shear strength <sup>c</sup> . . . . .	755	1090	1970	755	1090	1970	755	1090	1970
Yield Strength <sup>d</sup> , lbs.									
Sheet thickness, in.:									
0.025 . . . . .	336	...	...	450	...	...	336	...	...
0.032 . . . . .	483	546	...	581	...	...	483	546	...
0.040 . . . . .	589	730	845	675	705	978	589	730	845
0.050 . . . . .	681	888	1187	...	867	1508	681	888	1187
0.063 . . . . .	...	...	1415	...	1007	1803	...	...	1415
0.071 . . . . .	...	...	1656	...	...	1930	...	...	1656
0.080 . . . . .	...	...	1870	...	...	1970	...	...	1870
Head height (max.), in. . . . .	0.055	0.070	0.095	0.055	0.070	0.095	0.055	0.070	0.095

a These allowables apply to double dimpled sheets and to the upper sheet dimpled into a machine-countersunk lower sheet. Sheet gage is that of the thinnest sheet for double dimpled joints and of the upper dimpled sheet for dimpled, machine-countersunk joints. The thickness of machine-countersunk sheet must be at least one tabulated gage thicker than the upper sheet. In no case shall allowables be obtained by extrapolation for gages other than those shown.

b Test data from which the yield strengths listed were derived and can be found in Reference 8.1.2.2.

c Rivet shear strength from Table 8.1.2(b).

d Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.2.2(e). Static Joint Strength of 100° Flush Head Aluminum Alloy (2024-T31) Solid Rivets in Dimpled Aluminum Alloy Sheet<sup>a,b</sup>**

Rivet Type . . . . .	MS20426DD ( $F_{su} = 41$ ksi)					
Sheet Material . . . . .	2024-T3 2024-T42		2024-T62 2024-T81		2024-T86 7075-T6	
Rivet Diameter, in. . . . .	3/16	1/4	3/16	1/4	3/16	1/4
(Nominal Hole Diameter, in.) . .	(0.191)	(0.257)	(0.191)	(0.257)	(0.191)	(0.257)
Ultimate Strength, lbs.						
Sheet thickness, in.:						
0.032 . . . . .	744	...	786	...	786	...
0.040 . . . . .	941	879	982	1300	982	1300
0.050 . . . . .	1110	1359	1152	1705	1152	1705
0.063 . . . . .	1175	1727	1175	2010	1175	2010
0.071 . . . . .	...	1883	...	2125	...	2125
0.080 . . . . .	...	2025	...	...	...	...
0.090 . . . . .	...	2125	...	...	...	...
Rivet shear strength <sup>c</sup> . . . . .	1175	2125	1175	2125	1175	2125
Yield Strength <sup>d</sup> , lbs.						
Sheet thickness, in.:						
0.032 . . . . .	582	...	649	...	786	...
0.040 . . . . .	666	879	816	962	982	978
0.050 . . . . .	738	1308	961	1308	1152	1543
0.063 . . . . .	925	1564	1068	1564	1175	1958
0.071 . . . . .	...	1711	...	1711	...	2125
0.080 . . . . .	...	1928	...	...	...	...
0.090 . . . . .	...	2121	...	...	...	...
Head height (max.), in. . . . .	0.070	0.095	0.070	0.095	0.070	0.095

a These allowables apply to double dimpled sheets and to the upper sheet dimpled into a machine-countersunk lower sheet. Sheet gage is that of the thinnest sheet for double dimpled joints and of the upper dimpled sheet for dimpled, machine-countersunk joints. The thickness of machine-countersunk sheet must be at least one tabulated gage thicker than the upper sheet. In no case shall allowables be obtained by extrapolation for gages other than those shown.

b Test data from which the yield strengths listed were derived and can be found in Reference 8.1.2.2.

c Rivet shear strength from Table 8.1.2(b).

d Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.2.2(f). Static Joint Strength of 100° Flush Head Aluminum Alloy Solid Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	MS20426AD (2117-T3) ( $F_{su}$ = 30 ksi)				MS20426D (2017-T3) ( $F_{su}$ = 38 ksi)			MS20426DD (2024-T31) ( $F_{su}$ = 41 ksi)	
Sheet Material .....	Clad 2024-T42								
Rivet Diameter, in. .... (Nominal Hole Diameter, in.)	3/32 (0.096)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	5/32 (0.159)	3/16 (0.191)	1/4 (0.257)	3/16 (0.191)	1/4 (0.257)
Sheet thickness, in.:	Ultimate Strength <sup>a</sup> , lbs								
	0.032 .....	178	...	...	...	...	...	...	...
	0.040 .....	193	<sup>c</sup> 309	...	...	...	...	...	...
	0.050 .....	206	340	<sup>c</sup> 479	...	580 <sup>b</sup>	...	...	...
	0.063 .....	216	363	523	<sup>c</sup> 705	657 <sup>b</sup>	<sup>c</sup> 859 <sup>b</sup>	...	886
	0.071 .....	...	373	542	739	<sup>c</sup> 690	917 <sup>b</sup>	<sup>c</sup> ...	942
	0.080 .....	...	...	560	769	720	969 <sup>b</sup>	...	992
	0.090 .....	...	...	575	795	746	1015	1552 <sup>b</sup>	1035
	0.100 .....	...	...	...	818	...	1054	1640 <sup>b</sup>	<sup>c</sup> 1073
	0.125 .....	...	...	...	853	...	1090	1773	1131
	0.160 .....	...	...	...	...	...	...	1891	...
	0.190 .....	...	...	...	...	...	...	1970	...
	Rivet shear strength <sup>d</sup> .....	217	388	596	862	755	1090	1970	1175
Sheet thickness, in.:	Yield Strength <sup>a,e</sup> , lbs								
	0.032 .....	132	...	...	...	...	...	...	...
	0.040 .....	153	231	...	...	...	...	...	...
	0.050 .....	188	261	321	...	345	...	...	...
	0.063 .....	213	321	402	471	401	515	...	614
	0.071 .....	...	348	453	538	481	557	...	669
	0.080 .....	...	...	498	616	562	623	...	761
	0.090 .....	...	...	537	685	633	746	861	842
	0.100 .....	...	...	...	745	...	854	1017	913
	0.125 .....	...	...	...	836	...	1018	1313	1021
	0.160 .....	...	...	...	...	...	...	1574	...
	0.190 .....	...	...	...	...	...	...	1753	...
	Head height (ref.), in. ....	0.036	0.042	0.055	0.070	0.055	0.070	0.095	0.070

a Test data from which the yield and ultimate strength listed were derived can be found in Reference 8.1.2.2.

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Rivet shear strength is documented in MS20426.

e Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.2.2(g). Static Joint Strength of 100° Flush Head Aluminum Alloy (5056-H321) Solid Rivets in Machine-Countersunk Magnesium Alloy Sheet**

Rivet Type .....	MS20426B ( $F_{su} = 28$ ksi)				
Sheet Material .....	AZ31B-H24				
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .	3/32 (0.096)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	1/4 (0.257)
Ultimate Strength, lbs					
Sheet thickness, in.:					
0.032 .....	172 <sup>a</sup>	...	...	...	...
0.040 .....	180	<sup>b</sup> 304 <sup>a</sup>	...	...	...
0.050 .....	190	318	<sup>b</sup> 467 <sup>a</sup>	...	...
0.063 .....	203	337	490	<sup>b</sup> 679 <sup>a</sup>	...
0.071 .....	...	348	503	697 <sup>a</sup>	<sup>b</sup> ...
0.080 .....	...	360	519	715	...
0.090 .....	...	363	536	737	1244
0.100 .....	...	...	554	757	1271 <sup>b</sup>
0.125 .....	...	...	556	802	1343
0.160 .....	...	...	...	...	1440
0.190 .....	...	...	...	...	1450
Rivet shear strength <sup>c</sup> .....	203	363	556	802	1450
Yield Strength <sup>d</sup> , lbs					
Sheet thickness, in.:					
0.032 .....	104	...	...	...	...
0.040 .....	127	172	...	...	...
0.050 .....	152	214	268	...	...
0.063 .....	186	259	334	409	...
0.071 .....	...	287	369	459	...
0.080 .....	...	318	406	504	...
0.090 .....	...	353	450	555	792
0.100 .....	...	...	491	606	856
0.125 .....	...	...	556	735	1030
0.160 .....	...	...	...	...	1273
0.190 .....	...	...	...	...	1450
Head height (ref.), in. ....	0.036	0.042	0.055	0.070	0.095

a Yield value is less than 2/3 of the indicated ultimate strength value.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Rivet shear strength is documented in MS20426.

d Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

## MIL-HDBK-5H

1 December 1998

**Table 8.1.2.2(h). Static Joint Strength of 100° Flush Head Monel Solid Rivets in Machine-Countersunk Titanium Alloy Sheet**

Rivet Type .....	MS20427M ( $F_{su} = 49$ ksi)			
Sheet Material .....	Commercially Pure Titanium, $F_{tu} = 80$ ksi			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	1/4 (0.257)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.040 .....	531	...	...	...
0.050 .....	573	<sup>a</sup> 818	...	...
0.063 .....	626	885	<sup>a</sup> ...	...
0.071 .....	635	926	1242	...
0.080 .....	...	973	1302	<sup>a</sup> ...
0.090 .....	...	...	1360	...
0.100 .....	...	...	1400	2260
0.125 .....	...	...	...	2460 <sup>a</sup>
0.160 .....	...	...	...	2540
Rivet shear strength <sup>b</sup> .....	635	973	1400	2540
Yield Strength <sup>c</sup> , lbs				
Sheet thickness, in.:				
0.040 .....	376	...	...	...
0.050 .....	472	582	...	...
0.063 .....	598	736	...	...
0.071 .....	635	835	933	...
0.080 .....	...	945	1130	...
0.090 .....	...	...	1268	...
0.100 .....	...	...	1400	1860
0.125 .....	...	...	...	2340
0.160 .....	...	...	...	2540
Head height (max.), in. ....	0.048	0.061	0.077	0.103

a Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

b Rivet shear strength is documented in MS20427.

c Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.



**MIL-HDBK-5H****1 December 1998****Table 8.1.2.2(i). Static Joint Strength of 120° Flush Shear Head Aluminum Alloy (2017-T3) Solid Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	BRFS-D <sup>a</sup> ( $F_{su} = 38$ ksi)				
Sheet Material .....	Clad 2024-T3				
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b</sup> .	3/32 (0.096)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	1/4 (0.257)
Ultimate Strength, lbs					
Sheet thickness, in.:					
0.020 .....	139	...	...	...	...
0.025 .....	176	233	...	...	...
0.032 .....	226	300	367	...	...
0.040 .....	275	378	465	552	...
0.050 .....	...	477	585	697	930
0.063 .....	...	494	741	886	1182
0.071 .....	...	...	755	1005	1338
0.080 .....	...	...	...	1090	1513
0.090 .....	...	...	...	...	1711
0.100 .....	...	...	...	...	1902
0.125 .....	...	...	...	...	1970
Rivet shear strength <sup>c</sup> .....	275	494	755	1090	1970
Yield Strength <sup>d</sup> , lbs					
Sheet thickness, in.:					
0.020 .....	137	...	...	...	...
0.025 .....	171	229	...	...	...
0.032 .....	207	294	359	...	...
0.040 .....	231	357	453	547	...
0.050 .....	...	398	550	680	918
0.063 .....	...	451	614	814	1149
0.071 .....	...	...	655	857	1295
0.080 .....	...	...	...	914	1430
0.090 .....	...	...	...	...	1513
0.100 .....	...	...	...	...	1592
0.125 .....	...	...	...	...	1790
Head height (ref.), in. ....	0.018	0.023	0.030	0.039	0.049

a Data supplied by Briles Rivet Corp.

b Fasteners installed in hole diameters of 0.0975, 0.1285, 0.1615, 0.1945, 0.257, +0.0005, -0.001, respectively.

c Shear strength based on Table 8.1.2(b) and  $F_{su} = 38$  ksi.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.2.2(j). Static Joint Strength of 120° Flush Shear Head Aluminum Alloy (2117-T3) Solid Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	BRFS-AD <sup>a</sup> ( $F_{su} = 30$ ksi)				
Sheet Material .....	Clad 2024-T3				
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b</sup> .	3/32 (0.096)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	1/4 (0.257)
Ultimate Strength, lbs					
Sheet thickness, in.:					
0.020 .....	119	...	...	...	...
0.025 .....	144	201	...	...	...
0.032 .....	171	250	316	...	...
0.040 .....	204	292	386	474	...
0.050 .....	217	343	451	571	806
0.063 .....	...	388	536	675	987
0.071 .....	...	...	596	737	1073
0.080 .....	...	...	...	812	1169
0.090 .....	...	...	...	862	1278
0.100 .....	...	...	...	...	1371
0.125 .....	...	...	...	...	1550
Rivet shear strength <sup>c</sup> .....	217	388	596	862	1550
Yield Strength <sup>d</sup> , lbs					
Sheet thickness, in.:					
0.020 .....	119	...	...	...	...
0.025 .....	144	201	...	...	...
0.032 .....	171	250	316	...	...
0.040 .....	204	292	386	474	...
0.050 .....	217	343	451	571	806
0.063 .....	...	388	536	675	987
0.071 .....	...	...	596	737	1073
0.080 .....	...	...	...	812	1169
0.090 .....	...	...	...	862	1278
0.100 .....	...	...	...	...	1371
0.125 .....	...	...	...	...	1550
Head height (ref.), in. ....	0.018	0.023	0.030	0.039	0.049

a Data supplied by Briles Rivet Corp.

b Fasteners installed in hole diameters of 0.0975, 0.1285, 0.1615, 0.1945, 0.257, +0.0005, -0.001, respectively.

c Shear strength based on Table 8.1.2(b) and  $F_{su} = 38$  ksi.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.2.2(k). Static Joint Strength of 120° Flush Shear Head Aluminum Alloy (2024-T31) Solid Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	BRFS-DD <sup>a</sup> ( $F_{su} = 41$ ksi)	
Sheet Material .....	Clad 2024-T3	
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b</sup> ....	3/16 (0.191)	1/4 (0.257)
Ultimate Strength, lbs		
Sheet thickness, in.:		
0.040 .....	598	...
0.050 .....	772	1000
0.063 .....	994	1300
0.071 .....	1130	1480
0.080 .....	1180	1690
0.090 .....	...	1920
0.100 .....	...	2120
Rivet shear strength <sup>c</sup> .....	1180	2120
Yield Strength <sup>d</sup> , lbs		
Sheet thickness, in.:		
0.040 .....	598	...
0.050 .....	772	1000
0.063 .....	949	1300
0.071 .....	1000	1480
0.080 .....	1060	1680
0.090 .....	...	1760
0.100 .....	...	1850
Head height (ref.), in. ....	0.039	0.049

a Data supplied by Briles Rivet Corp.

b Fasteners installed in hole diameters of 0.1935 and 0.257,  $\pm 0.0005$ .c Shear strength based on Table 8.1.2(b) and  $F_{su} = 41$  ksi.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.2.2(l). Static Joint Strength of 120° Flush Shear Head Ti-45 Cb Solid Rivets in Machine-Countersunk Aluminum Alloy and Titanium Sheet**

Rivet Type . . . . .	BRFS-T <sup>a</sup> ( $F_{su} = 53$ ksi)					
Sheet Material . . . . .	Clad 7075-T6			Annealed Ti-6Al-4V		
Rivet Diameter, in. . . . . (Nominal Hole Diameter, in.) <sup>b</sup>	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)
Ultimate Strength, lbs						
Sheet thickness, in.:						
0.025 . . . . .	288	...	...	400	...	...
0.032 . . . . .	369	456	...	513	635	...
0.040 . . . . .	461	572	685	564	796	952
0.050 . . . . .	577	713	858	602	867	1190
0.063 . . . . .	610	891	1080	650	927	1270
0.071 . . . . .	628	914	1220	680	964	1310
0.080 . . . . .	649	939	1300	687	1005	1360
0.090 . . . . .	671	967	1330	...	1050	1420
0.100 . . . . .	687	996	1370	...	...	1470
0.125 . . . . .	...	1050	1450	...	...	1520
0.160 . . . . .	...	...	1520	...	...	...
Rivet shear strength <sup>c</sup> . . . . .	687	1050	1520	687	1050	1520
Yield Strength <sup>d</sup> , lbs						
Sheet thickness, in.:						
0.025 . . . . .	288	...	...	400	...	...
0.032 . . . . .	369	456	...	513	635	...
0.040 . . . . .	461	572	685	564	796	952
0.050 . . . . .	577	713	858	602	867	1190
0.063 . . . . .	610	891	1080	650	927	1270
0.071 . . . . .	628	914	1220	680	964	1310
0.080 . . . . .	649	939	1300	687	1005	1360
0.090 . . . . .	671	967	1330	...	1050	1420
0.100 . . . . .	687	996	1370	...	...	1470
0.125 . . . . .	...	1050	1450	...	...	1520
0.160 . . . . .	...	...	1520	...	...	...
Head height (ref.), in. . . . .	0.023	0.030	0.039	0.023	0.030	0.039

a Data supplied by Briles Rivet Corp.

b Allowables developed from tests with hole diameters noted, except 5/32 and 3/16 diameters were 0.161 and 0.1935  $\pm$  0.0005, respectively.c Rivet shear strength based on Table 8.1.2(b) and  $F_{su} = 53$  ksi.

d Permanent set at yield load: 4% of nominal hole diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.2.2(m). Static Joint Strength of 120° Flush Shear Head Aluminum Alloy (7050-T731) Solid Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	MS14218E <sup>a</sup> ( $F_{su} = 43$ ksi)						
Sheet Material .....	Clad 2024-T3						
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b</sup>	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	7/32 (0.228)	1/4 (0.257)	9/32 (0.290)	5/16 (0.323)
Ultimate Strength, lbs							
Sheet thickness, in.:							
0.025 .....	215	...	...	...	...	...	...
0.032 .....	307	<sup>c</sup> 346	...	...	...	...	...
0.040 .....	434	478	<sup>c</sup> 529	...	...	...	...
0.050 .....	508	673	732	<sup>c</sup> 806	...	...	...
0.063 .....	536	781	1045	1135	<sup>c</sup> 1200	1285	...
0.071 .....	554	803	1110	1365	1445	1530	<sup>c</sup> 1630
0.080 .....	558	827	1140	1565	1735	1835	1930 <sup>c</sup>
0.090 .....	...	854	1175	1605	1990	2200	2320
0.100 .....	...	...	1205	1645	2030	2525	2725
0.125 .....	...	...	1230	1740	2140	2650	3205
0.160 .....	...	...	...	1755	2230	2820	3400
0.190 .....	...	...	...	...	...	2840	3525
Rivet shear strength <sup>d</sup> .....	558	854	1230	1755	2230	2840	3525
Yield Strength <sup>e</sup> , lbs							
Sheet thickness, in.:							
0.025 .....	215	...	...	...	...	...	...
0.032 .....	307	346	...	...	...	...	...
0.040 .....	388	478	529	...	...	...	...
0.050 .....	487	601	721	806	...	...	...
0.063 .....	536	760	912	1085	1200	1285	...
0.071 .....	552	803	1030	1225	1377	1530	1630
0.080 .....	558	827	1140	1385	1554	1755	1930
0.090 .....	...	854	1175	1560	1750	1970	2200
0.100 .....	...	...	1205	1645	1950	2200	2445
0.125 .....	...	...	1230	1735	2140	2650	3060
0.160 .....	...	...	...	1755	2230	2810	3400
0.190 .....	...	...	...	...	...	2840	3525
Head height (ref.), in. ....	0.027	0.035	0.044	0.053	0.061	0.069	0.077

a Data supplied by Briles Rivet Corp.

b Allowables developed from tests with hole diameters noted, except 5/32, 3/16, and 5/16 diameters were 0.161, 0.1935, and 0.316, respectively. Hole tolerances were +0.0005-0.001 inch.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Shear strength based on Table 8.1.2(b) and  $F_{su} = 43$  ksi.

e Permanent set at yield load: 4% of nominal hole diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.2.2(n). Static Joint Strength of 100° Flush Shear Head Aluminum Alloy (7050-T73) Solid Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	NAS1097-E <sup>a</sup> ( $F_{su} = 41$ ksi)							
Sheet Material .....	Clad 2024-T3				Clad 7075-T6			
Nominal Rivet Diameter, in. . . (Nominal Hole Diameter, in.) <sup>b</sup>	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	1/4 (0.257)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	1/4 (0.257)
Ultimate Strength, lbs								
Sheet thickness, in.:								
0.025 .....	227	...	...	...	278	...	...	...
0.032 .....	326	<sup>c</sup> 367	...	...	354	<sup>c</sup> 441	...	...
0.040 .....	437	505	<sup>c</sup> 561	...	439	547	<sup>c</sup> 661	...
0.050 .....	466	679	773	<sup>c</sup> 908	456	674	823	<sup>c</sup> 1120
0.063 .....	485	717	1005	1275	477	700	980	1330 <sup>c</sup>
0.071 .....	497	731	1025	1500	490	716	999	1570
0.080 .....	507	747	1045	1750	505	734	1020	1760
0.090 .....	521	765	1065	1840	520	754	1045	1790
0.100 .....	531	781	1085	1870	531	774	1070	1825
0.125 .....	...	814	1135	1935	...	814	1130	1905
0.160 .....	...	...	1175	2030	...	...	1175	2020
0.190 .....	...	...	...	2110	...	...	...	2115
0.250 .....	...	...	...	2125	...	...	...	2125
Rivet shear strength <sup>d</sup> .....	531	814	1175	2125	531	814	1175	2125
Yield Strength <sup>e</sup> , lbs								
Sheet thickness, in.:								
0.025 .....	192	...	...	...	222	...	...	...
0.032 .....	283	311	...	...	307	356	...	...
0.040 .....	349	439	479	...	372	475	542	...
0.050 .....	398	538	674	767	398	572	724	894
0.063 .....	462	617	799	1105	431	612	836	1205
0.071 .....	497	665	857	1310	451	638	867	1400
0.080 .....	507	720	921	1400	474	666	900	1490
0.090 .....	521	765	995	1500	499	698	938	1540
0.100 .....	531	781	1065	1595	525	729	976	1595
0.125 .....	...	814	1135	1835	...	808	1070	1720
0.160 .....	...	...	1175	2030	...	...	1175	1895
0.190 .....	...	...	...	2110	...	...	...	2050
0.250 .....	...	...	...	2125	...	...	...	2125
Head height (ref.), in. ....	0.029	0.037	0.046	0.060	0.029	0.037	0.046	0.060

a Data supplied by Lockheed-Georgia Company.

b Fasteners installed in hole diameters of 0.130, 0.158, 0.191, and  $0.254 \pm 0.003$  inch, respectively.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Shear strength based on Table 8.1.2(b) and  $F_{su} = 41$  ksi.

e Permanent set at yield load: 4% of nominal hole diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.2.2(o). Static Joint Strength of 120° Flush Shear Head Aluminum Alloy (2117-T3) Solid Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	MS14218AD <sup>a</sup> ( $F_{su} = 30$ ksi)					
Sheet Material .....	Clad 2024-T3					
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b</sup>	3/32 (0.096)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	7/32 (0.228)	1/4 (0.257)
Ultimate Strength, lbs						
Sheet thickness, in.:						
0.020 .....	125	...	...	...	...	...
0.025 .....	153	<sup>c</sup> 212	...	...	...	...
0.032 .....	188	263	<sup>c</sup> 334	...	...	...
0.040 .....	216	322	408	<sup>c</sup> 498	...	...
0.050 .....	217	380	498	609	<sup>c</sup> 740	849
0.063 .....	...	388	588	751	910	1040 <sup>c</sup>
0.071 .....	...	...	596	817	1015	1155
0.080 .....	...	...	...	862	1125	1290
0.090 .....	...	...	...	...	1205	1425
0.100 .....	...	...	...	...	1225	1520
0.125 .....	...	...	...	...	...	1555
Rivet shear strength <sup>d</sup> .....	217	388	596	862	1225	1555
Yield Strength <sup>e</sup> , lbs						
Sheet thickness, in.:						
0.020 .....	125	...	...	...	...	...
0.025 .....	153	212	...	...	...	...
0.032 .....	188	263	334	...	...	...
0.040 .....	216	319	408	498	...	...
0.050 .....	217	370	492	609	740	849
0.063 .....	...	388	574	733	910	1040
0.071 .....	...	...	596	794	1005	1155
0.080 .....	...	...	...	842	1090	1275
0.090 .....	...	...	...	862	1180	1380
0.100 .....	...	...	...	...	1225	1480
0.125 .....	...	...	...	...	...	1555
Head height (ref.), in. ....	0.022	0.027	0.035	0.044	0.053	0.061

a Data supplied by Briles Rivet Corp.

b Load allowables developed from tests with hole diameters noted, except 3/32, 5/32, and 3/16 diameters were 0.098, 0.161, and 0.1935, respectively. Hole tolerance was +0.0005-0.001 inch.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Shear strength based on Table 8.1.2(b) and  $F_{su} = 30$  ksi.

e Permanent set at yield load: 4% of nominal hole diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.2.2(p). Static Joint Strength of 120° Flush Tension Type Head Aluminum Alloy (7050-T731) Solid Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	MS14219 E <sup>a</sup> ( $F_{su} = 43$ ksi)							
Sheet Material .....	Clad 2024-T3							
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b</sup>	3/32 (0.096)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	7/32 (0.228)	1/4 (0.257)	9/32 (0.290)	5/16 (0.523)
Ultimate Strength, lbs								
Sheet thickness, in.:								
0.032 .....	210	...	...	...	...	...	...	...
0.040 .....	279	<sup>c</sup> 339	...	...	...	...	...	...
0.050 .....	310	473	<sup>c</sup> 527	...	...	...	...	...
0.063 .....	311	538	743	<sup>c</sup> 819	...	...	...	...
0.071 .....	...	558	788	979	<sup>c</sup> 1065	...	...	...
0.080 .....	...	...	834	1105	1280	<sup>c</sup> ...	...	...
0.090 .....	...	...	854	1165	1520	1625	...	...
0.100 .....	...	...	...	1230	1605	1890	<sup>c</sup> 2020	2120
0.125 .....	...	...	...	...	1755	2145	2580	2965 <sup>c</sup>
0.160 .....	...	...	...	...	...	2230	2840	3415
0.190 .....	...	...	...	...	...	...	...	3525
Rivet shear strength <sup>d</sup> .....	311	588	854	1230	1755	2230	2840	3525
Yield Strength <sup>e</sup> , lbs								
Sheet thickness, in.:								
0.032 .....	210	...	...	...	...	...	...	...
0.040 .....	277	339	...	...	...	...	...	...
0.050 .....	301	468	527	...	...	...	...	...
0.063 .....	309	538	728	819	...	...	...	...
0.071 .....	...	543	788	979	1065	...	...	...
0.080 .....	...	...	823	1100	1280	...	...	...
0.090 .....	...	...	833	1165	1490	1625	...	...
0.100 .....	...	...	...	1190	1605	1875	2020	2120
0.125 .....	...	...	...	...	1705	2145	2580	2945
0.160 .....	...	...	...	...	...	2200	2765	3390
0.190 .....	...	...	...	...	...	...	...	3455
Head height (ref.), in. ....	0.034	0.041	0.053	0.068	0.077	0.090	0.100	0.104

a Data supplied by Briles Rivet Corp.

b Load allowables developed from tests with hole diameters noted, except 5/32, 3/16, and 5/16 diameter were 0.161, 0.1935, and 0.316, respectively. Hole tolerances were + 0.0005, -0.001 inch.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Rivet shear strength based on Table 8.1.2(b) and  $F_{su} = 43$  ksi.

e Permanent set at yield load: 4% of nominal hole diameter (Ref. 9.4.1.3.3).



**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.2.2(q). Static Joint Strength of 120° Flush Tension Type Head Aluminum Alloy (7050-T731) Solid Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	MS14219 E <sup>a</sup> ( $F_{su} = 43$ ksi)							
Sheet Material .....	Clad 7075-T6							
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b</sup>	3/32 (0.096)	1/8 (0.1285)	5/32 (0.159)	3/16 (0.191)	7/32 (0.228)	1/4 (0.257)	9/32 (0.290)	5/16 (0.523)
	Ultimate Strength, lbs							
Sheet thickness, in.:								
0.032 .....	272	...	...	...	...	...	...	...
0.040 .....	297	<sup>c</sup> 455	...	...	...	...	...	...
0.050 .....	311	522	<sup>c</sup> 704	...	...	...	...	...
0.063 .....	...	558	803	<sup>c</sup> 1065	...	...	...	...
0.071 .....	...	...	832	1140	<sup>c</sup> 1435	...	...	...
0.080 .....	...	...	854	1180	1600	<sup>c</sup> ...	...	...
0.090 .....	...	...	...	1220	1650	2030	...	...
0.100 .....	...	...	...	1230	1700	2090	<sup>c</sup> 2565	2860
0.125 .....	...	...	...	...	1755	2230	2740	<sup>c</sup> 3295
0.160 .....	...	...	...	...	...	...	2840	3525
Rivet shear strength <sup>d</sup> .....	311	558	854	1230	1755	2230	2840	3525
	Yield Strength <sup>e</sup> , lbs							
Sheet thickness, in.:								
0.032 .....	272	...	...	...	...	...	...	...
0.040 .....	296	455	...	...	...	...	...	...
0.050 .....	308	522	704	...	...	...	...	...
0.063 .....	...	550	802	1065	...	...	...	...
0.071 .....	...	...	823	1140	1435	...	...	...
0.080 .....	...	...	845	1170	1600	...	...	...
0.090 .....	...	...	...	1205	1650	2030	...	...
0.100 .....	...	...	...	1220	1685	2090	2565	2860
0.125 .....	...	...	...	...	1740	2195	2715	3295
0.160 .....	...	...	...	...	...	...	2815	3480
Head height (ref.), in. ....	0.034	0.041	0.053	0.068	0.077	0.090	0.100	0.104

a Data supplied by Briles Rivet Corp.

b Allowables developed from tests with hole diameters noted, except 3/32, 5/32, 3/16, and 5/16 diameters were 0.098, 0.161, 0.1935, and 0.316, respectively. Hole tolerances were +0.0005, -0.001 inch.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Rivet shear strength based on Table 8.1.2(b) and  $F_{su} = 43$  ksi.

e Permanent set at yield load: 4% of nominal hole diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.2.2(r). Static Joint Strength of Solid 100° Flush Head Aluminum Alloy (7050-T73) Solid Rivets in Machine Countersunk Aluminum Alloy Sheet**

Rivet Type .....	MS20426E ( $F_{su} = 41$ ksi) <sup>a</sup>			
Sheet Material .....	Clad 2024-T3			
Rivet Diameter, in. ....	1/8	5/32	3/16	1/4
(Nominal Hole Diameter, in.) <sup>b</sup> ....	(0.1285)	(0.159)	(0.191)	(0.257)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.040 .....	386	c ...	...	...
0.050 .....	419		...	...
0.063 .....	463	647	870	c ...
0.071 .....	491	680	910	
0.080 .....	521	718	955	...
0.090 .....	531	760	1005	1610
0.100 .....	...	802	1055	1680
0.125 .....	...	814	1175	1845
0.160 .....	...	...	...	2085
0.190 .....	...	...	...	2125
Rivet shear strength <sup>d</sup>	531	814	1175	2125
Yield Strength <sup>e</sup> , lbs				
Sheet thickness, in.:				
0.040 .....	262	...	...	...
0.050 .....	327	404	...	...
0.063 .....	412	510	612	...
0.071 .....	464	574	690	...
0.080 .....	517	647	777	...
0.090 .....	531	728	875	1175
0.100 .....	...	794	972	1310
0.125 .....	...	814	1160	1635
0.160 .....	...	...	...	2070
0.190 .....	...	...	...	2125
Head Height (ref.), in.	0.042	0.055	0.070	0.095

a Data supplied by Lockheed Ga. Co. and Air Force Materials Laboratory.

b Load allowables developed from tests with hole diameters of 0.130, 0.158, 0.191, and  $0.256 \pm 0.003$  inch.

c The values in the table above the horizontal line in each column are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires the specific approval of the procuring agency.

d Shear strength based on area computed from nominal hole diameters in Table 8.1.2(b) and  $F_{su} = 41$  ksi.

e Permanent set at yield load: 4% of the nominal hole diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.2.2 (s). Static Joint Strength of Solid 100° Flush Head Aluminum Alloy (7050-T73) Solid Rivets in Machine Countersunk Aluminum Alloy Sheet**

Rivet Type .....	MS20426E ( $F_{su} = 41$ ksi) <sup>a</sup>			
Sheet Material .....	Clad 7075-T6			
Rivet Diameter, in. ....	1/8	5/32	3/16	1/4
(Nominal Hole Diameter, in.) <sup>b</sup> ..	(0.1285)	(0.159)	(0.191)	(0.257)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.040 .....	318	...	...	...
0.050 .....	393	<sup>c</sup> 492	...	...
0.063 .....	440	606	<sup>c</sup> 745	...
0.071 .....	469	642	840	<sup>c</sup> ...
0.080 .....	502	683	898	...
0.090 .....	531	728	952	1430
0.100 .....	...	773	1005	1570 <sup>c</sup>
0.125 .....	...	814	1140	1755
0.160 .....	...	...	1175	2010
0.190 .....	...	...	...	2125
Rivet shear strength <sup>d</sup>	531	814	1175	2125
Yield Strength <sup>e</sup> , lbs				
Sheet thickness, in.:				
0.040 .....	257	...	...	...
0.050 .....	330	399	...	...
0.063 .....	423	515	607	...
0.071 .....	469	586	693	...
0.080 .....	502	666	789	...
0.090 .....	531	728	896	1175
0.100 .....	...	773	1005	1320
0.125 .....	...	814	1140	1680
0.160 .....	...	...	1175	2010
0.190 .....	...	...	...	2125
Head Height (ref.), in.	0.042	0.055	0.070	0.095

a Data supplied by Lockheed Ga. Co., Air Force Materials Laboratory, Allfast, Cherry Fasteners, Douglas Aircraft Co., and Huck Mfg. Co.

b Load allowables developed from tests with hole diameters of 0.130, 0.158, 0.191, and  $0.256 \pm 0.003$  inch.

c The values in the table above the horizontal line in each column are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires the specific approval of the procuring agency.

d Shear strength based on area computed from nominal hole diameters in Table 8.1.2(b) and  $F_{su} = 41$  ksi.

e Permanent set at yield load: 4% of the nominal hole diameter.

**MIL-HDBK-5H****1 December 1998**

**8.1.3 BLIND FASTENERS** — The strengths shown in the following tables are applicable only for the grip lengths and hole tolerances recommended by the respective fastener manufacturers. For some fastener systems, permanent set at yield load may be increased if hole sizes greater than those listed in the applicable table are used. This condition may exist even though the test hole size lies within the manufacturer's recommended hole size range (Reference 9.4.1.3.3).

The strength values were established from test data and are applicable to "joints" with  $e/D \geq 2.0$ . For joints with  $e/D$  ratios less than 2.0, tests to substantiate the use of yield and ultimate strength allowables must be made. Ultimate strength values of protruding- and flush-head blind fasteners were obtained as described in Section 9.4. The analyses included dividing the average ultimate load from test data by 1.15. This factor is not applicable to shear strength cutoff values which may be either the procurement specification shear strength ( $S$  values) of the fastener, or if no specification exists, a statistical value determined from test results as described in Section 9.4.

Unless otherwise specified, yield load is defined in Section 9.4.1.3.3 as the load which results in a joint permanent set equal to  $0.04D$ , where  $D$  is the decimal equivalent of the hole or fastener shank diameter, as defined in Table 9.4.1.2(a). Some tables are footnoted to show the previous criteria used for those particular tables.

For machine countersunk joints, the sheet gage specified in the tables is that of the countersunk sheet. When the noncountersunk sheet is thinner than the countersunk sheet, the bearing allowable for the noncountersunk sheet-fastener combination should be computed, compared to the table value, and the lower of the two values selected. Increased attention should be paid to detail design in cases where  $t/D < 0.25$  because of the possibility of unsatisfactory service life.

Joint allowable strengths of blind fasteners in double-dimpled or dimpled into machine countersunk applications should be established on the basis of specific tests acceptable to the procuring or certifying agency. In the absence of such data, allowables for blind fasteners in machine countersunk sheet may be used.

Reference should be made to the requirements of the applicable procuring or certifying agency relative to the use of blind fasteners such as the limitations of usage in design standard MS33522.

**8.1.3.1 Protruding-Head Blind Fasteners**

**8.1.3.1.1 Friction-Lock Blind Rivets** — Tables 8.1.3.1.1(a) through 8.1.3.1.1(e) contain joint allowables for various protruding-head, friction-lock blind rivet/sheet material combinations.

**8.1.3.1.2 Mechanical-Lock Spindle Blind Rivets** — Tables 8.1.3.1.2(a) through (p) contain joint allowables for various protruding-head, mechanical-lock spindle blind rivet/sheet material combinations.

**8.1.3.2 Flush-Head Blind Fasteners**

**8.1.3.2.1 Friction-Lock Blind Rivets** — Tables 8.1.3.2.1(a) through (g) contain joint allowables for various flush-head, friction-lock blind rivet/sheet material combinations.

**8.1.3.2.2 Mechanical-Lock Spindle Blind Rivets** — Tables 8.1.3.2.2(a) through (u) contain joint allowables for various flush-head, mechanical-lock spindle blind rivet/sheet material combinations.

**8.1.3.2.3 Flush-Head Blind Bolts** — Tables 8.1.3.2.3(a) through (h) contain joint allowables for various flush-head blind bolt/sheet material combinations.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.1(a). Static Joint Strength of Blind Protruding Head A-286 Rivets in Alloy Steels, Titanium Alloy and A-286 Alloy Sheet**

Rivet Type .....	CR 6636 <sup>a</sup> ( $F_{su} = 75$ ksi)			
Sheet Material .....	Alloy Steel, $F_{tu} = 125$ ksi, Titanium Alloys, $F_{tu} = 120$ ksi, and A-286 Alloy, $F_{tu} = 140$ ksi			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength <sup>b</sup> , lbs				
Sheet thickness, in.:				
0.008 .....	169	...	...	...
0.012 .....	290	341	...	...
0.016 .....	412	493	566	...
0.020 .....	532	645	748	924
0.025 .....	688	816	967	1221
0.032 .....	796	1050	1278	1650
0.040 .....	879	1233	1570	2129
0.050 .....	945	1354	1807	2673
0.063 .....	970	1461	1980	3168
0.071 .....	...	1490	2062	3350
0.080 .....	...	...	2150	3515
0.090 .....	...	...	...	3663
0.100 .....	...	...	...	3779
0.112 .....	...	...	...	3890
Rivet shear strength <sup>c</sup> .....	970	1490	2150	3890

a Data supplied by Cherry Fasteners.

b Yield strength is in excess of 80% of ultimate. This is based on a previous Navy "BuAer" definition that yield strength would not be considered to be critical if it exceeded 1.15 x 2.3 of design ultimate strength. There was no requirement for submission of the yield data for inclusion in ANC-5.

c Shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 75$  ksi.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.1(b). Static Joint Strength of Protruding Head Monel Rivets in Stainless Steel Sheet**

Rivet Type .....	MS20600M ( $F_{su} = 55$ ksi)							
Sheet Material .....	ANSI 301-Annealed				AISI 301-1/2 Hard			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) ..	1/8 (0.130)	5/32 (0.162)	3/16 (0.154)	1/4 (0.258)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength, lbs								
Sheet thickness, in.:								
0.010 .....	...	...	...	...	195	...	...	...
0.012 .....	...	...	...	...	225	287	...	...
0.016 .....	...	...	...	...	290	367	453	...
0.020 .....	332 <sup>a</sup>	...	...	...	358	450	552	774
0.025 .....	396 <sup>a</sup>	494 <sup>a</sup>	...	...	440	552	675	940
0.032 .....	472 <sup>a</sup>	627 <sup>a</sup>	768 <sup>a</sup>	...	522	690	1040	1163
0.040 .....	526 <sup>a</sup>	729 <sup>a</sup>	942 <sup>a</sup>	1290 <sup>a</sup>	580	810	1200	1430
0.050 .....	594 <sup>a</sup>	810 <sup>a</sup>	1070 <sup>a</sup>	1585 <sup>a</sup>	635	903	1325	1760
0.063 .....	681 <sup>a</sup>	919 <sup>a</sup>	1280 <sup>a</sup>	1875 <sup>a</sup>	678	980	1385	2090
0.071 .....	700 <sup>a</sup>	984 <sup>a</sup>	1370 <sup>a</sup>	1980 <sup>a</sup>	701	1013	1438	2220
0.080 .....	713	1055 <sup>a</sup>	1470 <sup>a</sup>	2110 <sup>a</sup>	713	1050	1486	2340
0.090 .....	...	1080 <sup>a</sup>	1530 <sup>a</sup>	2240 <sup>a</sup>	...	1081	1540	2450
0.100 .....	...	1090	1580	2380 <sup>a</sup>	...	1090	1580	2540
0.125 .....	...	...	...	2700 <sup>a</sup>	...	...	...	2710
0.160 .....	...	...	...	2855	...	...	...	2855
Rivet shear strength <sup>b</sup> .....	713	1090	1580	2855	713	1090	1580	2855
Yield Strength <sup>c</sup> , lbs								
Sheet thickness, in.:								
0.010 .....	...	...	...	...	195	...	...	...
0.012 .....	...	...	...	...	225	287	...	...
0.016 .....	...	...	...	...	290	367	453	...
0.020 .....	128	...	...	...	358	450	551	774
0.025 .....	160	199	...	...	440	552	675	940
0.032 .....	205	254	306	...	522	690	836	1163
0.040 .....	257	318	382	514	580	810	1040	1430
0.050 .....	321	397	477	642	635	903	1200	1760
0.063 .....	405	501	601	810	678	980	1325	2090
0.071 .....	456	564	678	912	701	1013	1385	2220
0.080 .....	514	635	764	1025	713	1050	1438	2340
0.090 .....	...	715	860	1155	...	1081	1486	2450
0.100 .....	...	795	955	1285	...	1090	1540	2540
0.125 .....	...	...	...	1605	...	...	...	2710
0.160 .....	...	...	...	2055	...	...	...	2855

a Yield value is less than 2/3 of the indicated ultimate strength value.

b Rivet shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 55$  ksi.

c Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.1(c). Static Joint Strength of Blind Protruding Head Monel Rivets in Aluminum Alloy Sheet**

Rivet Type .....	MS20600M ( $F_{su} = 55$ ksi)							
Sheet Material .....	2024-T3				7075-T6			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength, lbs								
Sheet thickness, in.:								
0.025 .....	268	...	...	...	297	...	...	...
0.032 .....	365	429	...	...	405	472	...	...
0.040 .....	478	569	650	...	485	631	720	...
0.050 .....	545	738	860	1070	545	747	955	1190
0.063 .....	622	844	1110	1430	622	844	1110	1590
0.071 .....	652	903	1180	1665	652	903	1180	1840
0.080 .....	684	968	1255	1910	684	968	1255	1940
0.090 .....	713	1010	1345	2060	713	1010	1345	2060
0.100 .....	...	1050	1415	2180	...	1050	1415	2180
0.125 .....	...	1090	1545	2480	...	1090	1545	2480
0.160 .....	...	...	1580	2735	...	...	1580	2735
0.190 .....	...	...	...	2855	...	...	...	2855
Rivet shear strength <sup>a</sup> .....	713	1090	1580	2855	713	1090	1580	2855
Yield Strength <sup>b</sup> , lbs								
Sheet thickness, in.:								
0.025 .....	234	...	...	...	272	...	...	...
0.032 .....	297	370	...	...	343	430	...	...
0.040 .....	368	460	556	...	425	533	644	...
0.050 .....	458	570	688	936	492	657	797	1090
0.063 .....	529	715	863	1170	529	759	996	1350
0.071 .....	552	786	970	1315	552	786	1075	1520
0.080 .....	577	818	1090	1470	577	818	1110	1700
0.090 .....	605	853	1155	1650	605	853	1155	1915
0.100 .....	...	888	1200	1830	...	888	1200	1970
0.125 .....	...	976	1300	2110	...	976	1300	2110
0.160 .....	...	...	1450	2310	...	...	1450	2310
0.190 .....	...	...	...	2480	...	...	...	2480

a Shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 55$  ksi.

b Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.1(d). Static Joint Strength of Blind Protruding Head Alloy (2117-T3) Rivets in Aluminum Alloy Sheet**

Rivet Type .....	MS20600AD and MS20602AD ( $F_{su} = 30$ ksi)			
Sheet Material .....	Clad 2024 T3			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.025 .....	233	...	...	...
0.032 .....	277	368	...	...
0.040 .....	321	425	544	...
0.050 .....	388	506	643	961
0.063 .....	...	596	753	1110
0.071 .....	...	...	823	1200
0.080 .....	...	...	862	1305
0.090 .....	...	...	...	1415
0.100 .....	...	...	...	1550
Rivet shear strength <sup>a</sup> .....	388	596	862	1550
Yield Strength <sup>b</sup> , lbs				
Sheet thickness, in.:				
0.025 .....	226	...	...	...
0.032 .....	264	356	...	...
0.040 .....	304	406	523	...
0.050 .....	362	475	610	925
0.063 .....	388	560	709	1058
0.071 .....	...	596	771	1135
0.080 .....	...	...	862	1230
0.090 .....	...	...	...	1330
0.100 .....	...	...	...	1450

a Rivet shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 30$  ksi.

b Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.



**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.1(e). Static Joint Strength of Blind Protruding Head Aluminum Alloy (5056) Rivets in Magnesium Alloy Sheet**

Rivet Type .....	MS20600B ( $F_{su} = 28$ ksi)			
Sheet Material .....	AZ31B-H24			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
	Ultimate Strength <sup>a</sup> , lbs			
Sheet thickness, in.:				
0.025 .....	178	...	...	...
0.032 .....	218	282	...	...
0.040 .....	256	339	420	...
0.050 .....	290	392	502	714
0.063 .....	330	449	584	870
0.071 .....	352	481	627	942
0.080 .....	363	512	667	1025
0.090 .....	...	550	714	1090
0.100 .....	...	556	757	1160
0.125 .....	...	...	802	1315
0.160 .....	...	...	...	1450
Rivet shear strength <sup>b</sup> .....	363	556	802	1450

a Yield strength is in excess of 80% of ultimate. This is based on a previous Navy "Bureau of Aeronautics" definition that yield strength was not considered to be critical if it exceeded  $1.15 \times 2/3$  of design ultimate strength. There was no requirement for submission of the yield data for inclusion in ANC-5.

b Shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 28$  ksi.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(a). Static Joint Strength of Blind Protruding Head Locked Spindle A-286 Rivets in Alloy Steel Sheet**

Rivet Type .....	NAS1398C <sup>a</sup> and NAS1398C, Code A <sup>b</sup> ( $F_{su}$ = 75 ksi)			CR 2643 <sup>a</sup> ( $F_{su}$ = 95 ksi)		
	Alloy Steel $F_{tu}$ = 180 ksi					
Rivet Diameter, in. .... (Nominal Hole Diameter, in.)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
	Ultimate Strength <sup>c</sup> , lbs					
Sheet thickness, in.:						
0.025 .....	697	...	...	697	...	...
0.032 .....	785	1112	...	807	1112	...
0.040 .....	860	1211	1628	911	1246	1639
0.050 .....	956	1325	1772	1043	1406	1833
0.063 .....	970	1480	1958	1215	1615	2090
0.071 .....	...	1490	2070	1230	1748	2240
0.080 .....	...	...	2150	...	1885	2420
0.090 .....	...	...	...	...	...	2610
0.100 .....	...	...	...	...	...	2720
Rivet shear strength .....	970 <sup>d</sup>	1490 <sup>d</sup>	2150 <sup>d</sup>	1230 <sup>e</sup>	1885 <sup>e</sup>	2720 <sup>e</sup>

a Data supplied by Cherry Fasteners.

b Confirmatory data supplied by Olympic Fastening Systems, Inc.

c Yield strength is in excess of 80% of ultimate. This is based on a previous Navy "Bureau of Aeronautics" definition that yield strength would not be considered to be critical if it exceeded  $1.15 \times 2/3$  of design ultimate strength. There was no requirement for submission of the yield data for inclusion in ANC-5.

d Rivet shear strength is documented in NAS1400.

e Shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 95$  ksi.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(b). Static Joint Strength of Blind Protruding Head Locked Spindle Monel Rivets in Stainless Steel Sheet**

Rivet Type .....	NAS1398 MS or MW <sup>a</sup> and NAS1398 MS or MW, Code A <sup>b</sup> ( $F_{su} = 55$ ksi)		
Sheet Material .....	AISI 301-1/2 Hard		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
	Ultimate Strength <sup>c</sup> , lbs		
Sheet thickness, in.:			
0.025 .....	462	...	...
0.032 .....	568	734	...
0.040 .....	594	870	1094
0.050 .....	632	915	1270
0.063 .....	678	971	1335
0.071 .....	706	1009	1380
0.080 .....	710	1048	1428
0.090 .....	...	1090	1532
0.100 .....	...	...	1580
Rivet shear strength <sup>d</sup> .....	710	1090	1580

a Data supplied by Cherry Fasteners.

b Confirmatory data supplied by Olympic Fastening Systems, Inc.

c Yield strength is in excess of 80% of ultimate strength. This is based on a previous Navy "Bureau of Aeronautics" definition that yield strength was not considered to be critical if it exceeded  $1.15 \times 2/3$  of design ultimate strength. There was no requirement for submission of the yield strength data for inclusion in ANC-5.

d Rivet shear strength is documented in NAS1400.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(c). Static Joint Strength of Blind Protruding Head Locked Spindle Monel Rivets in Aluminum Alloy Sheet**

Rivet Type .....	NAS1398 MS or MW <sup>a</sup> and NAS1398 MS or MW, Code A <sup>b</sup> ( $F_{su} = 55$ ksi)		
Sheet Material .....	Clad 7075-T6		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
	Ultimate Strength <sup>c</sup> , lbs		
Sheet thickness, in.:			
0.025 .....	318	...	...
0.032 .....	404	506	...
0.040 .....	466	624	774
0.050 .....	546	720	922
0.063 .....	647	845	1072
0.071 .....	710	921	1168
0.080 .....	...	1009	1272
0.090 .....	...	1090	1387
0.100 .....	...	...	1507
0.125 .....	...	...	1580
Rivet shear strength <sup>d</sup> .....	710	1090	1580

a Data supplied by Cherry Fasteners.

b Confirmatory data supplied by Olympic Fastening Systems, Inc.

c Yield strength is in excess of 80% of ultimate. This is based on a previous Navy "Bureau of Aeronautics" definition that yield strength would not be considered to be critical if it exceeded  $1.15 \times 1/3$  of design ultimate strength. There was no requirement for submission of the yield data for inclusion in ANC-5.

d Rivet shear strength is documented in NAS1400.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(d<sub>1</sub>). Static Joint Strength of Blind Protruding Head Locked Spindle Aluminum Alloy Rivets in Aluminum Alloy Sheet**

Rivet Type	NAS1398B <sup>a</sup> ( $F_{su}$ = 30 ksi)				NAS1398D <sup>a</sup> ( $F_{su}$ = 38 ksi)			
Sheet Material	Clad 2024-T3							
Rivet Diameter, in. (Nominal Hole Diameter, in.)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
	Ultimate Strength, lbs.							
Sheet thickness, in.:								
0.025	228	...	...	...	228	...	...	...
0.032	289	364	412	...	304	364	...	...
0.040	337	448	553	670	355	470	553	...
0.050	388	521	662	914	418	548	696	914
0.063	...	596	781	1145	494	647	816	1205
0.071	...	...	854	1240	...	710	894	1303
0.080	...	...	862	1350	...	755	975	1420
0.090	...	...	...	1475	...	...	1069	1545
0.100	...	...	...	1550	...	...	1090	1670
0.125	...	...	...	...	...	...	...	1970
Rivet shear strength <sup>b</sup>	388	596	862	1550	494	755	1090	1970

a Data supplied by Cherry Fasteners.

b Rivet shear strength documented in NAS1400.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.3.1.2(d<sub>2</sub>). Static Joint Strength of Blind Protruding Head Locked Spindle Aluminum Alloy Rivets in Aluminum Alloy Sheet**

Rivet Type .....	NAS1738B and NAS1738E <sup>a</sup> ( $F_{su} = 34$ ksi)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.144)	5/32 (0.178)	3/16 (0.207)
Ultimate Strength, lbs			
Sheet thickness, in.:			
0.025 .....	267	305	330
0.032 .....	368	428	473
0.040 .....	427	567	636
0.050 .....	480	650	815
0.063 .....	547 <sup>b</sup>	735	912
0.071 .....	554 <sup>b</sup>	785 <sup>b</sup>	976
0.080 .....	...	837 <sup>b</sup>	1042 <sup>b</sup>
0.090 .....	...	...	1115 <sup>b</sup>
0.100 .....	...	...	1128 <sup>b</sup>
Rivet shear strength <sup>c</sup> .....	554	837	1128
Yield Strength <sup>d</sup> , lbs			
Sheet thickness, in.:			
0.020 .....	185	213	228
0.025 .....	242	285	317
0.032 .....	298	386	433
0.040 .....	321	453	568
0.050 .....	336	489	625
0.063 .....	336	508	680
0.071 .....	336	508	684
0.080 .....	...	508	684
0.090 .....	...	...	684
0.100 .....	...	...	684

a Data supplied by Cherry Fasteners.

b Yield value is less than 2/3 of the indicated ultimate.

c Rivet shear strength was documented in NAS1740 prior to Revision (1), dated January 15, 1974.

d Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(e). Static Joint Strength of Blind Protruding Head Locked Spindle Aluminum Alloy Rivets in Magnesium Alloy Sheet**

Rivet Type .....	NAS1398B <sup>a</sup> ( $F_{su} = 30$ ksi)				NAS1738B and NAS1738E <sup>a</sup> ( $F_{su} = 34$ ksi)		
Sheet Material .....	AZ31B-H24						
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) ..	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)	1/8 (0.144)	5/32 (0.178)	3/16 (0.207)
	Ultimate Strength, lbs.						
Sheet thickness, in.:							
0.025 .....	163	...	...	...	202	...	...
0.032 .....	208	256	310	...	261	321	372
0.040 .....	255	324	388	519	325	401	465
0.050 .....	298	394	485	654	372	501	579
0.063 .....	352	461	588	822	425	570	708
0.071 .....	385	501	639	924	458	609	756
0.080 .....	388	550	695	1020	495	656	809
0.090 .....	...	596	755	1109	536 <sup>b</sup>	709	866
0.100 .....	...	...	820	1191	554 <sup>b</sup>	759	925
0.125 .....	...	...	862	1397	...	837 <sup>b</sup>	1072 <sup>b</sup>
0.160 .....	...	...	...	1550	...	...	1128 <sup>b</sup>
Rivet shear strength .....	388 <sup>c</sup>	596 <sup>c</sup>	862 <sup>c</sup>	1550 <sup>c</sup>	554 <sup>d</sup>	837 <sup>d</sup>	1128 <sup>d</sup>
	Yield Strength <sup>e</sup> , lbs.						
Sheet thickness, in.:							
0.025 .....	...	...	...	...	155	...	...
0.032 .....	...	...	...	...	198	243	282
0.040 .....	...	...	...	...	248	304	353
0.050 .....	...	...	...	...	302	380	441
0.063 .....	...	...	...	...	325	460	556
0.071 .....	...	...	...	...	336	478	614
0.080 .....	...	...	...	...	336	499	638
0.090 .....	...	...	...	...	336	508	664
0.100 .....	...	...	...	...	336	508	684
0.125 .....	...	...	...	...	...	508	684
0.160 .....	...	...	...	...	...	...	684

a Data supplied by Cherry Fasteners.

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Rivet shear strength is documented in NAS1400.

d Rivet shear strength was documented in NAS1740 prior to Revision (1), dated January 15, 1974.

e Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(f). Static Joint Strength of Blind Protruding Head Locked Spindle Aluminum Alloy (2219) Rivets in Aluminum Alloy Sheet**

Rivet Type .....	CR 2A63 <sup>a</sup> ( $F_{su} = 36$ ksi)		
Sheet Material .....	Clad 2024-T81		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Ultimate Strength, lbs			
Sheet thickness, in.			
0.025 .....	256	...	...
0.032 .....	295	404	...
0.040 .....	340	458	592
0.050 .....	395	527	675
0.063 .....	467	617	783
0.071 .....	478	672	848
0.080 .....	...	734	922
0.090 .....	...	741	1005
0.100 .....	...	...	1063
Rivet shear strength <sup>b</sup> .....	478	741	1063
Yield Strength <sup>c</sup> , lbs			
Sheet thickness, in.:			
0.025 .....	256	...	...
0.032 .....	295	404	...
0.040 .....	336	458	592
0.050 .....	383	521	675
0.063 .....	440	598	770
0.071 .....	445	646	827
0.080 .....	...	683	890
0.090 .....	...	690	963
0.100 .....	...	...	984

a Data supplied by Cherry Fasteners.

b Shear strength values based on indicated nominal hole diameters and  $F_{su} = 36$  ksi.

c Permanent set at yield load: 4% of nominal hole diameter (Ref. 9.4.1.3.3).



**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(g). Static Joint Strength of Blind Protruding Head Locked Spindle A-286 Rivets in Aluminum Alloy Sheet**

Rivet Type .....	CR4623 <sup>a</sup> ( $F_{su} = 75$ ksi)			
	Clad 7075-T6			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b</sup>	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Sheet thickness, in.:	Ultimate Strength, lbs.			
0.020 .....	237	...	...	...
0.025 .....	298	367	...	...
0.032 .....	385	478	566	...
0.040 .....	486	601	714	939
0.050 .....	610	757	902	1185
0.063 .....	772	958	1145	1505
0.071 .....	856	1080	1290	1705
0.080 .....	903	1220	1455	1925
0.090 .....	956	1340	1645	2175
0.100 .....	995	1405	1830	2425
0.125 .....	...	1545	2055	3035
0.160 .....	...	...	2215	3570
0.190 .....	...	...	...	3885
0.250 .....	...	...	...	3920
Rivet shear strength <sup>c</sup> .....	995	1545	2215	3920
Sheet thickness, in.:	Yield Strength <sup>d</sup> , lbs.			
0.020 .....	237	...	...	...
0.025 .....	296	367	...	...
0.032 .....	381	475	565	...
0.040 .....	478	594	709	938
0.050 .....	596	745	890	1180
0.063 .....	690	932	1125	1490
0.071 .....	747	1005	1270	1680
0.080 .....	812	1085	1385	1895
0.090 .....	857	1175	1495	2140
0.100 .....	879	1265	1600	2360
0.125 .....	...	1365	1870	2715
0.160 .....	...	...	1995	3215
0.190 .....	...	...	...	3425
0.250 .....	...	...	...	3690

a Data supplied by Cherry Fasteners.

b Allowable loads developed from test with hole diameters as listed.

c Fastener shear strength based on nominal hole diameters and  $F_{su} = 75$  ksi from data analysis.

d Permanent set at yield load: 4% of nominal hole diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(h). Static Joint Strength of Blind Protruding Head Locked Spindle Monel Rivets in Aluminum Alloy Sheet**

Rivet Type . . . . .	CR 4523 <sup>a</sup> ( $F_{su} = 65$ ksi)			
	Clad 7075-T6			
Rivet Diameter, in . . . . . (Nominal Hole Diameter, in.) <sup>b</sup>	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Sheet thickness, in.:	Ultimate Strength, lbs.			
0.020 . . . . .	221	...	...	...
0.025 . . . . .	284	344	...	...
0.032 . . . . .	373	456	533	...
0.040 . . . . .	475	582	684	878
0.050 . . . . .	602	740	875	1130
0.063 . . . . .	701	945	1120	1455
0.071 . . . . .	729	1055	1270	1655
0.080 . . . . .	760	1095	1440	1885
0.090 . . . . .	796	1140	1540	2135
0.100 . . . . .	831	1180	1590	2390
0.125 . . . . .	863	1290	1725	2760
0.160 . . . . .	...	1340	1905	3005
0.190 . . . . .	...	...	1920	3215
0.250 . . . . .	...	...	...	3400
Rivet shear strength <sup>c</sup> . . . . .	863	1340	1920	3400
Sheet thickness, in.:	Yield Strength <sup>d</sup> , lbs.			
0.020 . . . . .	221	...	...	...
0.025 . . . . .	279	344	...	...
0.032 . . . . .	360	447	530	...
0.040 . . . . .	453	561	667	878
0.050 . . . . .	569	706	841	1110
0.063 . . . . .	659	893	1065	1405
0.071 . . . . .	707	965	1205	1590
0.080 . . . . .	729	1035	1340	1795
0.090 . . . . .	752	1105	1430	2030
0.100 . . . . .	776	1135	1520	2260
0.125 . . . . .	834	1205	1645	2590
0.160 . . . . .	...	1305	1765	2880
0.190 . . . . .	...	...	1870	3015
0.250 . . . . .	...	...	...	3290

a Data supplied by Cherry Fasteners.

b Allowable loads developed from test with hole diameters as listed.

c Fastener shear strength based on nominal hole diameters and  $F_{su} = 65$  ksi from data analysis.

d Permanent set at yield load: 4% of nominal hole diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(i). Static Joint Strength of Blind Protruding Head Locked Spindle Aluminum Alloy (7050) Rivets in Aluminum Alloy Sheet**

Rivet Type .....	NAS 1720KE and NAS 1720KE( )L <sup>a,b</sup> ( $F_{su} = 33$ ksi)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>c</sup> .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Sheet thickness, in.:	Ultimate Strength, lbs.		
0.020 .....	174	...	...
0.025 .....	219	272	...
0.032 .....	282	350	417
0.040 .....	354	440	525
0.050 .....	376	552	659
0.063 .....	392	585	816
0.071 .....	402	597	831
0.080 .....	413	611	847
0.090 .....	425	626	866
0.100 .....	437	641	884
0.125 .....	450	680	929
0.160 .....	...	700	950
Rivet shear strength <sup>d</sup> .....	450	700	950
Sheet thickness, in.:	Yield Strength <sup>e</sup> , lbs.		
0.020 .....	174	...	...
0.025 .....	215	272	...
0.032 .....	261	340	417
0.040 .....	314	406	504
0.050 .....	366	489	603
0.063 .....	382	570	732
0.071 .....	391	582	809
0.080 .....	402	595	825
0.090 .....	414	610	843
0.100 .....	426	625	861
0.125 .....	450	662	905
0.160 .....	...	700	950

a Data supplied by Avdel Corp.

b Fasteners should not be used for structural applications where the t/D is less than 0.15.

c Loads developed from tests with hole diameters of 0.130, 0.162, and 0.194, +0.0005, -0.0000 inch.

d Rivet shear strength is documented in NAS 1722.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(i). Static Joint Strength of Blind Protruding Head Locked Spindle A-286 Rivets in Aluminum Alloy Sheet**

Rivet Type .....	NAS1720C and NAS1720C(L) <sup>a,b</sup> ( $F_{su} = 75$ ksi)		
Sheet Material .....	Clad 7075-T6		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>c</sup> ..	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Sheet thickness, in:	Ultimate Strength, lbs.		
0.025 .....	329	...	...
0.032 .....	399	528	...
0.040 .....	499	621	799
0.050 .....	625	778	930
0.063 .....	789	982	1170
0.071 .....	847	1105	1320
0.080 .....	870	1245	1490
0.090 .....	896	1320	1680
0.100 .....	921	1350	1865
0.125 .....	985	1430	1955
0.160 .....	1000	1500	2090
0.190 .....	...	...	2200
Rivet shear strength <sup>d</sup> .....	1000	1500	2200
Sheet thickness, in.:	Yield Strength <sup>e</sup> , lbs.		
0.025 .....	329	...	...
0.032 .....	390	386	...
0.040 .....	453	607	779
0.050 .....	531	704	895
0.063 .....	632	831	1045
0.071 .....	687	909	1140
0.080 .....	701	996	1245
0.090 .....	717	1070	1360
0.100 .....	733	1090	1475
0.125 .....	773	1140	1575
0.160 .....	829	1210	1655
0.190 .....	...	...	1730

a Data supplied by Avdel Corp.

b Fasteners should not be used for structural applications where the t/D is less than 0.15.

c Loads developed from tests with hole diameters of 0.130, 0.162, and 0.194,  $\pm 0.0001$  inch.

d Rivet shear strength is documented in NAS1722.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(k). Static Joint Strength of Blind Protruding Head Locked Spindle Aluminum Alloy Rivets in Aluminum Alloy Sheet**

Rivet Type .....	M 7885/2 <sup>a</sup> ( $F_{su} = 51$ ksi approx.)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. ....	1/8	5/32	3/16
(Nominal Hole Diameter, in.) <sup>b</sup> ....	(0.130)	(0.162)	(0.194)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.025 .....	249	...	...
0.032 .....	314	397	...
0.040 .....	387	489	593
0.050 .....	414	603	730
0.063 .....	443	644	882
0.071 .....	461	667	909
0.080 .....	481	692	939
0.090 .....	504	720	973
0.100 .....	526	748	1005
0.125 .....	582	818	1090
0.160 .....	661	916	1205
0.190 .....	664	1000	1305
0.250 .....	...	1030	1480
Rivet shear strength <sup>c</sup> .....	664	1030	1480
Yield Strength, lbs. <sup>d</sup>			
Sheet thickness, in.:			
0.025 .....	222	...	...
0.032 .....	275	353	...
0.040 .....	294	428	525
0.050 .....	312	457	628
0.063 .....	336	487	664
0.071 .....	351	505	686
0.080 .....	368	526	711
0.090 .....	386	549	738
0.100 .....	405	572	766
0.125 .....	451	629	834
0.160 .....	515	709	931
0.190 .....	570	778	1010
0.250 .....	...	916	1175

a Data supplied by Allfast Fastening Systems, Cherry Textron, John Hassall Inc., and Huck International Inc.

b Loads developed from tests with hole diameters of 0.130, 0.162, and 0.194,  $\pm 0.001$  inch.

c Rivet shear strength is documented in MIL-R-7885D.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(I). Static Joint Strength of Blind Protruding Head Locked Spindle Aluminum Alloy Rivets in Aluminum Alloy Sheet**

Rivet Type .....	M 7885/6 <sup>a</sup> ( $F_{su} = 51$ ksi approx.)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. ....	1/8	5/32	3/16
(Nominal Hole Diameter, in.) <sup>b</sup> ....	(0.144)	(0.178)	(0.207)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.032 .....	306	386	...
0.040 .....	376	473	557
0.050 .....	493	581	683
0.063 .....	527	758	847
0.071 .....	548	783	948
0.080 .....	571	812	1050
0.090 .....	597	844	1085
0.100 .....	623	876	1120
0.125 .....	688	956	1215
0.160 .....	778	1065	1345
0.190 .....	814	1160	1455
0.250 .....	...	1245	1680
0.312 .....	...	...	1685
Rivet shear strength <sup>c</sup> .....	814	1245	1685
Yield Strength, lbs. <sup>d</sup>			
Sheet thickness, in.:			
0.032 .....	306	386	...
0.040 .....	359	473	557
0.050 .....	412	553	683
0.063 .....	479	637	784
0.071 .....	492	719	844
0.080 .....	505	736	913
0.090 .....	521	755	989
0.100 .....	536	774	1010
0.125 .....	575	822	1065
0.160 .....	628	888	1140
0.190 .....	675	946	1210
0.250 .....	...	1060	1340
0.312 .....	...	...	1480

a Data supplied by Allfast Fastening Systems, Cherry Textron, John Hassall Inc., and Huck International, Inc.

b Loads developed from tests with hole diameters of 0.144, 0.178, and 0.207,  $\pm 0.001$  inch.

c Rivet shear strength is documented in MIL-R-7885D.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(m). Static Joint Strength of Blind Protruding Head Locked Spindle Aluminum Alloy Rivets in Aluminum Alloy Sheet**

Rivet Type .....	AF3243 <sup>a</sup> ( $F_{su} = 51$ ksi approx.)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. ....	1/8	5/32	3/16
(Nominal Hole Diameter, in.) <sup>b</sup> ....	(0.144)	(0.178)	(0.207)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.032 .....	306	386	...
0.040 .....	376	473	557
0.050 .....	493	581	683
0.063 .....	527	758	847
0.071 .....	548	783	948
0.080 .....	571	812	1050
0.090 .....	597	844	1085
0.100 .....	623	876	1120
0.125 .....	688	956	1215
0.160 .....	778	1065	1345
0.190 .....	814	1160	1455
0.250 .....	...	1245	1680
0.312 .....	...	...	1685
Rivet shear strength <sup>c</sup> .....	814	1245	1685
Yield Strength, lbs. <sup>d</sup>			
Sheet thickness, in.:			
0.032 .....	306	386	...
0.040 .....	376	473	557
0.050 .....	493	581	683
0.063 .....	527	758	847
0.071 .....	548	783	948
0.080 .....	571	812	1050
0.090 .....	597	844	1085
0.100 .....	623	876	1120
0.125 .....	688	956	1215
0.160 .....	778	1065	1345
0.190 .....	814	1160	1455
0.250 .....	...	1245	1680
0.312 .....	...	...	1685

a Data supplied by Allfast Fastening Systems.

b Loads developed from tests with hole diameters of 0.144, 0.178, and 0.207,  $\pm 0.001$  inch.

c Rivet shear strength is documented in MIL-R-7885D.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(n). Static Joint Strength of Blind Protruding Head Locked Spindle Aluminum Alloy Rivets in Aluminum Alloy Sheet**

Rivet Type .....	HC3213 <sup>a</sup> ( $F_{su} = 51$ ksi approx.)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. ....	1/8	5/32	3/16
(Nominal Hole Diameter, in.) <sup>b</sup> ....	(0.130)	(0.162)	(0.194)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.025 .....	249	...	...
0.032 .....	314	397	...
0.040 .....	387	489	593
0.050 .....	479 <sup>e</sup>	603	730
0.063 .....	538 <sup>e</sup>	753 <sup>e</sup>	908
0.071 .....	558 <sup>e</sup>	812 <sup>e</sup>	1015
0.080 .....	581 <sup>e</sup>	840 <sup>e</sup>	1140 <sup>e</sup>
0.090 .....	607 <sup>e</sup>	872 <sup>e</sup>	1180 <sup>e</sup>
0.100 .....	632 <sup>e</sup>	904 <sup>e</sup>	1220 <sup>e</sup>
0.125 .....	664 <sup>e</sup>	983 <sup>e</sup>	1315 <sup>e</sup>
0.160 .....	...	1030 <sup>e</sup>	1450 <sup>e</sup>
0.190 .....	...	...	1480 <sup>e</sup>
Rivet shear strength <sup>c</sup> .....	664	1030	1480
Yield Strength, lbs. <sup>d</sup>			
Sheet thickness, in.:			
0.025 .....	222	...	...
0.032 .....	275	353	...
0.040 .....	294	428	525
0.050 .....	312	457	628
0.063 .....	336	487	664
0.071 .....	351	505	686
0.080 .....	368	526	711
0.090 .....	386	549	738
0.100 .....	405	572	766
0.125 .....	451	629	834
0.160 .....	...	709	931
0.190 .....	...	...	1015

a Data supplied by Huck International Inc.

b Loads developed from tests with hole diameters of 0.130, 0.162, and 0.194,  $\pm 0.001$  inch.

c Rivet shear strength is documented in MIL-R-7885D.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

e Yield is less than 2/3 of indicated ultimate.



**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(o). Static Joint Strength of Protruding Head Locked Spindle Aluminum Alloy Blind Rivets in Aluminum Alloy Sheet**

Rivet Type .....	HC6223 <sup>a</sup> ( $F_{su} = 50$ ksi) Nominal		
Sheet and Plate Material .....	Clad 2024-T3		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Ultimate Strength, lbs			
Sheet thickness, in.:			
0.016 .....	...	...	...
0.020 .....	...	...	...
0.025 .....	272	...	...
0.032 .....	367	437	...
0.040 .....	427	573	661
0.050 .....	476	664	864
0.063 .....	539	743	975
0.071 .....	578	792	1033
0.080 .....	622	846	1099
0.090 .....	664	907	1171
0.100 .....	...	967	1244
0.125 .....	...	1030	1425
0.160 .....	...	...	1480
0.190 .....	...	...	...
Rivet shear strength <sup>b</sup> .....	664	1030	1480
Yield Strength <sup>c</sup> , lbs			
Sheet thickness, in.:			
0.016 .....	...	...	...
0.020 .....	...	...	...
0.025 .....	255	...	...
0.032 .....	320	406	...
0.040 .....	394	498	605
0.050 .....	417	613	743
0.063 .....	437	648	901
0.071 .....	449	664	920
0.080 .....	463	681	940
0.090 .....	478	700	963
0.100 .....	...	720	986
0.125 .....	...	768	1044
0.160 .....	...	...	1125
0.190 .....	...	...	...

a Data supplied by Huck International, Inc.

b Rivet shear strength is documented in MIL-R-7885D.

c Permanent set at yield load: 4% of nominal hole diameter (see 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.1.2(p). Static Joint Strength of Protruding Head Locked Spindle Aluminum Alloy Blind Rivets in Aluminum Alloy Sheet**

Rivet Type .....	HC6253 <sup>a</sup> ( $F_{su} = 50$ ksi)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) ....	1/8 (0.144)	5/32 (0.178)	3/16 (0.207)
Ultimate Strength, lbs			
Sheet thickness, in.:			
0.016 .....	...	...	...
0.020 .....	...	...	...
0.025 .....	...	...	...
0.032 .....	344	419	...
0.040 .....	436	532	613
0.050 .....	513	674	777
0.063 .....	559	789	992
0.071 .....	588	824	1055
0.080 .....	620	864	1101
0.090 .....	656	908	1152
0.100 .....	691	952	1204
0.125 .....	781	1063	1332
0.160 .....	814	1217	1512
0.190 .....	...	1245	1666
0.250 .....	...	...	1685
Rivet shear strength <sup>b</sup> .....	814	1245	1685
Yield Strength <sup>c</sup> , lbs			
Sheet thickness, in.:			
0.016 .....	...	...	...
0.020 .....	...	...	...
0.025 .....	...	...	...
0.032 .....	344 <sup>d</sup>	419 <sup>d</sup>	...
0.040 .....	403	532 <sup>d</sup>	613 <sup>d</sup>
0.050 .....	462	619	731
0.063 .....	523	715	879
0.071 .....	541	774	948
0.080 .....	560	805	1025
0.090 .....	583	832	1079
0.100 .....	605	859	1110
0.125 .....	660	928	1190
0.160 .....	738	1024	1302
0.190 .....	...	1270	1397
0.250 .....	...	...	1588

a Data supplied by Huck International, Inc.

b Rivet shear strength is documented in MIL-R-7885D.

c Permanent set at yield load: 4% of nominal hole diameter (see 9.4.1.3.3).

d Yield reduced to match ultimate strength.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.1(a). Static Joint Strength of Blind 100° Flush Head A-286 Rivets in Machine-Countersunk Alloy Steel, Titanium Alloy, and A-286 Alloy Sheet**

Rivet Type .....	CR 6626 <sup>a</sup> ( $F_{su} = 75$ ksi)			
Sheet Material .....	Alloy Steel, $F_{tu} = 125$ ksi, Titanium Alloy, $F_{tu} = 120$ ksi, and A-286 Alloy, $F_{tu} = 140$ ksi			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.040 .....	582 <sup>b</sup>	...	...	...
0.050 .....	693	<sup>c</sup> 898 <sup>b</sup>	...	...
0.063 .....	842	1082	<sup>c</sup> 1351 <sup>b</sup>	...
0.071 .....	891	1189	1478	<sup>c</sup> ...
0.080 .....	949	1303	1633	...
0.090 .....	970	1379	1798	2558 <sup>b</sup>
0.100 .....	...	1461	1916	2772 <sup>c</sup>
0.112 .....	...	1490	2026	3036
0.125 .....	...	...	2150	3333
0.140 .....	...	...	...	3531
0.160 .....	...	...	...	3795
0.190 .....	...	...	...	3890
Rivet shear strength <sup>d</sup> .....	970	1490	2150	3890
Yield Strength <sup>e</sup> , lbs				
Sheet thickness, in.:				
0.040 .....	355	...	...	...
0.050 .....	499	557	...	...
0.063 .....	681	784	858	...
0.071 .....	771	923	1031	...
0.080 .....	858	1082	1223	...
0.090 .....	920	1202	1424	1700
0.100 .....	...	1297	1643	1997
0.112 .....	...	1417	1779	2327
0.125 .....	...	...	1925	2690
0.140 .....	...	...	...	3053
0.160 .....	...	...	...	3432
0.190 .....	...	...	...	3845
Head height (ref.), in. ....	0.042	0.055	0.070	0.095

a Data supplied by Cherry Fasteners.

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Rivet shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 75$  ksi.

e Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**Table 8.1.3.2.1(b). Static Joint Strength of Blind 100° Flush Head Monel Rivets in Machine-Countersunk Stainless Steel**

Rivet Type .....	MS20601M (R.T. $F_{su}$ = 55 ksi)											
Sheet Material .....	17-7PH, TH 1050											
Temperature .....	Room				500°F				700°F			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength, lbs												
Sheet thickness, in.:												
0.040 .....	373 <sup>a</sup>	...	...	...	373 <sup>a</sup>	...	...	...	373 <sup>a</sup>	...	...	...
0.050 .....	429	<sup>b</sup> 574 <sup>a</sup>	...	...	429	<sup>b</sup> 574 <sup>a</sup>	...	...	429	<sup>b</sup> 574 <sup>a</sup>	...	...
0.063 .....	495	664	<sup>b</sup> 866 <sup>a</sup>	...	495	664	<sup>b</sup> 866 <sup>a</sup>	...	495	664	<sup>b</sup> 866 <sup>a</sup>	...
0.071 .....	535	714	924	<sup>b</sup> ...	535	714	924	<sup>b</sup> ...	535	714	924	<sup>b</sup> ...
0.080 .....	579	771	991	...	579	771	991	...	574	771	991	...
0.090 .....	630	833	1065	1615 <sup>a</sup>	625	833	1065	1615 <sup>a</sup>	590	833	1065	1615 <sup>a</sup>
0.100 .....	...	896	1140	1720	<sup>b</sup> ...	896	1140	1720	<sup>b</sup> ...	884	1140	1720 <sup>b</sup>
0.125 .....	...	...	1325	1970	...	...	1325	1970	...	904	1290	1970
0.160 .....	...	...	...	2320	...	...	...	2320	...	...	1305	2300
0.180 .....	...	...	...	2520	...	...	...	2500	...	...	...	2360
Rivet shear strength <sup>c</sup> .....	713	1090	1580	2855	648	993	1430	2590	590	904	1305	2360
Yield Strength <sup>d</sup> , lbs												
Sheet thickness, in.:												
0.040 .....	213	...	...	...	213	...	...	...	213	...	...	...
0.050 .....	303	332	...	...	303	332	...	...	303	332	...	...
0.063 .....	439	476	518	...	439	476	518	...	439	476	518	...
0.071 .....	528	569	621	...	528	569	621	...	528	569	621	...
0.080 .....	579	696	741	...	579	696	741	...	574	696	741	...
0.090 .....	630	833	910	1030	625	833	910	1030	590	833	910	1030
0.100 .....	...	896	1075	1212	...	896	1075	1212	...	884	1075	1212
0.125 .....	...	...	1325	1731	...	...	1325	1731	...	904	1290	1731
0.160 .....	...	...	...	2320	...	...	...	2320	...	...	1305	2300
0.180 .....	...	...	...	2520	...	...	...	2500	...	...	...	2360
Head height (ref.), in. ....	0.042	0.055	0.070	0.095	0.042	0.055	0.070	0.095	0.042	0.055	0.070	0.095

a Yield value is less than 2/3 of the indicated ultimate strength value.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Rivet shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su}$  values at 55 ksi, 50 ksi, and 45 ksi at room temperature, 500°F and 700°F, respectively.

d Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.1(c). Static Joint Strength of Blind 100° Flush Head Monel Rivets in Dimpled Stainless Steel Sheet**

Rivet Type .....	MS20601M ( $F_{su} = 55$ ksi)							
Sheet Material .....	AISI 301-Annealed				AISI 301-1/4 Hard			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength, lbs.								
Sheet thickness, in.:								
0.010 .....	224	...	...	...	277	377	...	...
0.012 .....	254	338	...	...	302	428	560	...
0.016 .....	313	412	519	...	358	485	632	...
0.020 .....	375	486	610	...	415	542	705	1135
0.025 .....	447	576	722	1045	482	642	808	1230
0.032 .....	516	705	876	1255	543	750	963	1400
0.040 .....	536	793	1055	1490	585	833	1110	1660
0.050 .....	565	825	1150 <sup>a</sup>	1790	628	910	1240	1930
0.063 .....	...	868	1200 <sup>a</sup>	2065	...	964	1330	2175
0.071 .....	...	...	...	2100	...	973	1375	2275
0.080 .....	...	...	...	2150	...	...	1405	2340
0.090 .....	...	...	...	2200	...	...	...	2440
0.100 .....	...	...	...	...	...	...	...	2510
Rivet shear strength <sup>b</sup>	635	973	1405	2540	635	973	1405	2540
Yield Strength <sup>a</sup> , lbs.								
Sheet thickness, in.:								
0.010 .....	188	...	...	...	244	291	...	...
0.012 .....	214	281	...	...	259	335	423	...
0.016 .....	270	352	438	...	333	428	535	...
0.020 .....	328	422	518	...	398	528	639	896
0.025 .....	397	506	627	873	443	612	774	1080
0.032 .....	498	627	770	1070	505	689	912	1330
0.040 .....	536	772	939	1310	576	779	1015	1590
0.050 .....	565	825	1150	1590	619	883	1145	1770
0.063 .....	...	868	1200	1970	...	954	1305	2000
0.071 .....	...	...	...	2100	...	973	1350	2140
0.080 .....	...	...	...	2150	...	...	1400	2305
0.090 .....	...	...	...	2200	...	...	...	2395
0.100 .....	...	...	...	...	...	...	...	2475
Head height (ref.), in. ....	0.042	0.055	0.070	0.095	0.042	0.055	0.070	0.095

a Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

b Rivet shear strength from Table 8.1.2(b).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.1(d<sub>1</sub>). Static Joint Strength of Blind 100° Flush Head Monel Rivets in Machine-Countersunk Stainless Steel Sheet**

Rivet Type .....	MS20601M ( $F_{su} = 55$ ksi)			
Sheet Material .....	AISI 301-Annealed			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.040 .....	469 <sup>a</sup>	...	...	...
0.050 .....	555 <sup>a</sup>	<sup>b</sup> 721 <sup>a</sup>	...	...
0.063 .....	...	864 <sup>a</sup>	<sup>b</sup> 1075 <sup>a</sup>	...
0.071 .....	...	...	1187 <sup>a</sup>	<sup>b</sup> ...
0.080 .....	...	...	...	...
0.090 .....	...	...	...	2040
Rivet shear strength <sup>c</sup> .....	713	1090	1580	2855 <sup>b</sup>
Yield Strength <sup>d</sup> , lbs				
Sheet thickness, in.:				
0.040 .....	231	...	...	...
0.050 .....	321	359	...	...
0.063 .....	...	500	566	...
0.071 .....	...	...	678	...
0.080 .....	...	...	...	...
0.090 .....	...	...	...	1135
Head height (ref.), in. ....	0.042	0.055	0.070	0.095

a Yield value is less than 2/3 of the indicated ultimate strength value.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Rivet shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 55$  ksi.

d Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**Table 8.1.3.2.1(d<sub>2</sub>). Static Joint Strength of Blind 100° Flush Head Monel Rivets in Machine-Countersunk Stainless Steel Sheet**

Rivet Type	MS20601M (R.T. $F_{su} = 55$ ksi)											
Sheet Material	AISI 301-¼ Hard											
Temperature	Room				500°F				700°F			
Rivet Diameter, in. (Nominal Hole Diameter, in.)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Sheet thickness, in.:	Ultimate Strength, lbs											
0.040	373 <sup>a</sup>	...	...	...	373 <sup>a</sup>	...	...	...	373 <sup>a</sup>	...	...	...
0.050	450	<sup>b</sup> 574 <sup>a</sup>	...	...	450 <sup>a</sup>	<sup>b</sup> 574 <sup>a</sup>	...	...	450 <sup>a</sup>	<sup>b</sup> 574 <sup>a</sup>	...	...
0.063	538	704	<sup>b</sup> 866 <sup>a</sup>	...	538	704 <sup>a</sup>	<sup>b</sup> 866 <sup>a</sup>	...	538	704 <sup>a</sup>	<sup>b</sup> 866 <sup>a</sup>	...
0.071	584	773	960	<sup>b</sup> ...	584	773	960 <sup>a</sup>	<sup>b</sup> ...	584	773	960 <sup>a</sup>	<sup>b</sup> ...
0.080	637	838	1065	...	637	838	1065 <sup>a</sup>	...	590	838	1065 <sup>a</sup>	...
0.090	695	910	1155	1645	648	910	1155	1645 <sup>a</sup>	...	904	1155	1645 <sup>a</sup>
0.100	713	984	1240	1800	<sup>b</sup> ...	984	1240	1800 <sup>a</sup>	<sup>b</sup> ...	...	1240	1800 <sup>a</sup> <sup>b</sup>
0.125	...	1090	1460	2135	...	993	1430	2135	...	...	1305	2135
0.160	...	...	1580	2550	...	...	...	2550	...	...	...	2360
0.180	...	...	...	2780	...	...	...	2590	...	...	...	...
Rivet shear strength <sup>c</sup>	713	1090	1580	2855	648	993	1430	2590	590	904	1305	2360
Sheet thickness, in.:	Yield Strength <sup>d</sup> , lbs											
0.040	231	...	...	...	192	...	...	...	192	...	...	...
0.050	336	359	...	...	279	298	...	...	279	298	...	...
0.063	459	531	566	...	425	440	471	...	425	440	471	...
0.071	530	625	698	...	525	546	576	...	525	546	576	...
0.080	607	725	835	...	607	683	690	...	590	683	690	...
0.090	693	832	966	1135	648	832	872	945	...	832	872	945
0.100	713	943	1095	1345	...	943	1060	1115	...	...	1060	1115
0.125	...	1090	1420	1815	...	993	1420	1670	...	...	1305	1670
0.160	...	...	1580	2430	...	...	...	2430	...	...	...	2360
0.180	...	...	...	2775	...	...	...	2590	...	...	...	...
Head height (ref.), in.	0.042	0.055	0.070	0.095	0.042	0.055	0.070	0.095	0.042	0.055	0.070	0.095

a Yield value is less than 2/3 of the indicated ultimate strength value.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Rivet shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 55$  ksi at R.T.,  $F_{su} = 50$  ksi at 500°F, and  $F_{su} = 45$  ksi at 700°F.

d Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**Table 8.1.3.2.1(d<sub>3</sub>). Static Joint Strength of Blind 100° Flush Head Monel Rivets in Machine-Countersunk Stainless Steel Sheet**

Rivet Type	MS20601M (R.T. $F_{su} = 55$ ksi)											
Sheet Material	AISI 301-½ Hard											
Temperature	Room				500°F				700°F			
Rivet Diameter, in. (Nominal Hole Diameter, in.)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength, lbs												
Sheet thickness, in.:												
0.040	350 <sup>a</sup>	...	...	...	350 <sup>a</sup>	...	...	...	350 <sup>a</sup>	...	...	...
0.050	444	<sup>b</sup> 540 <sup>a</sup>	...	...	444	<sup>b</sup> 540 <sup>a</sup>	...	...	444	<sup>b</sup> 540 <sup>a</sup>	...	...
0.063	538	694	<sup>b</sup> 821	...	538	694	<sup>b</sup> 821	...	538	694	<sup>b</sup> 821	...
0.071	584	773	935	<sup>b</sup> ...	584	773	935	<sup>b</sup> ...	575	773	935	<sup>b</sup> ...
0.080	637	838	1065	...	624	838	1065	...	586	838	1065	...
0.090	695	910	1155	1585	648	910	1155	1585	590	886	1155	1585
0.100	713	984	1240	1780	<sup>b</sup> ...	962	1240	1780	<sup>b</sup> ...	904	1240	1780 <sup>b</sup>
0.125	...	1090	1460	2135	...	993	1410	2135	...	...	1305	2135
0.160	...	...	1580	2550	...	...	1430	2500	...	...	...	2345
0.180	...	...	...	2780	...	...	...	2590	...	...	...	2360
Rivet shear strength <sup>c</sup>	713	1090	1580	2855	648	993	1430	2590	590	904	1305	2360
Yield Strength <sup>d</sup> , lbs												
Sheet thickness, in.:												
0.040	231	...	...	...	231	...	...	...	231	...	...	...
0.050	336	359	...	...	336	359	...	...	336	359	...	...
0.063	459	531	566	...	459	531	566	...	459	531	566	...
0.071	530	625	698	...	530	625	698	...	530	625	698	...
0.080	607	725	835	...	607	725	835	...	586	725	835	...
0.090	693	832	966	1135	648	832	966	1135	590	832	966	1135
0.100	713	943	1095	1345	...	943	1095	1345	...	904	1095	1345
0.125	...	1090	1420	1815	...	993	1410	1815	...	...	1305	1815
0.160	...	...	1580	2430	...	...	1430	2430	...	...	...	2345
0.180	...	...	...	2775	...	...	...	2590	...	...	...	2360
Head height (ref.), in.	0.042	0.055	0.070	0.095	0.042	0.055	0.070	0.095	0.042	0.055	0.070	0.095

a Yield value is less than 2/3 of the indicated ultimate strength value.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Rivet shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 55$  ksi at R.T.,  $F_{su} = 50$  ksi at 500°F, and  $F_{su} = 45$  ksi at 700°F.

d Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.



**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.1(e). Static Joint Strength of Blind 100° Flush-Head Monel Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	MS20601M ( $F_{su} = 55$ ksi)			
Sheet Material .....	7075-T6			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Sheet thickness, in.:	Ultimate Strength, lbs			
	320 <sup>a</sup>	...	...	...
	393	494 <sup>a</sup>	...	...
	487	612 <sup>a</sup>	747 <sup>a</sup>	...
	545	684	832 <sup>a</sup>	...
	565	766	930 <sup>a</sup>	...
	587	840	1040	1425 <sup>a</sup> <sup>b</sup>
	610	867	1150	1570 <sup>a</sup>
	...	937	1270	1940
	...	...	1385	2260
	...	...	...	2390
	713	1090	1580	2855
	Yield Strength <sup>d</sup> , lbs			
	146	...	...	...
	228	226	...	...
	395	369	343	...
	496	495	444	...
	526	640	615	...
	561	769	806	660
	595	811	1000	912
	...	918	1195	1560
	...	...	1375	2105
	...	...	...	2310
Head height (ref.), in. ....	0.042	0.055	0.070	0.095

a Yield value is less than 2/3 of the indicated ultimate strength value.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Rivet shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 55$  ksi.

d Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.1(f). Static Joint Strength of Blind 100° Flush Head Aluminum Alloy (2117-T3) Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	MS20601AD and MS20603AD ( $F_{su} = 30$ ksi)			
Sheet Material .....	Clad 2024-T3			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.040 .....	159	...	...	...
0.050 .....	236	<sup>a</sup> 258	...	...
0.063 .....	327	369	<sup>a</sup> 398	...
0.071 .....	360	439	485	<sup>a</sup> ...
0.080 .....	388	511	577	...
0.090 .....	...	561	684	795
0.100 .....	...	596	768	945 <sup>a</sup>
0.125 .....	...	...	862	1270
Rivet shear strength <sup>b</sup> .....	388	596	862	1550
Yield Strength <sup>c</sup> , lbs				
Sheet thickness, in.:				
0.040 .....	110	...	...	...
0.050 .....	198	185	...	...
0.063 .....	300	308	296	...
0.071 .....	336	384	391	...
0.080 .....	377	468	497	...
0.090 .....	...	524	614	621
0.100 .....	...	592	709	973
0.125 .....	...	...	862	1150
Head height (ref.), in. ....	0.042	0.055	0.070	0.095

a Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

b Rivet shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 30$  ksi.

c Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.1(g). Static Joint Strength of Blind 100° Flush Head Aluminum Alloy (5056-H321) Rivets in Machine-Countersunk Magnesium Alloy Sheet**

Rivet Type .....	MS20601B ( $F_{su} = 28$ ksi)			
Sheet Material .....	AZ31B-H24			
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.040 .....	167	...	...	...
0.050 .....	208	<sup>a</sup> 257	...	...
0.063 .....	262	324	<sup>a</sup> 390	...
0.071 .....	295	366	440	<sup>a</sup> ...
0.080 .....	333	413	495	...
0.090 .....	363	464	557	749
0.100 .....	...	516	620	833 <sup>a</sup>
0.125 .....	...	556	774	1040
0.160 .....	...	...	802	1332
0.190 .....	...	...	...	1450
Rivet shear strength <sup>b</sup> .....	363	556	802	1450
Yield Strength <sup>c</sup> , lbs				
Sheet thickness, in.:				
0.040 .....	158	...	...	...
0.050 .....	197	244	...	...
0.063 .....	248	308	370	...
0.071 .....	279	346	417	...
0.080 .....	315	391	469	...
0.090 .....	354	440	527	710
0.100 .....	...	489	587	789
0.125 .....	...	556	734	986
0.160 .....	...	...	802	1262
0.190 .....	...	...	...	1450
Head height (ref.), in. ....	0.042	0.055	0.070	0.095

a Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

b Rivet shear strength based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 28$  ksi.

c Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(a). Static Joint Strength of Blind 100° Flush Head Locked Spindle A-286 Rivets in Machine-Countersunk Alloy Steel Sheet**

Rivet Type . . . . .	NAS1399C <sup>a</sup> ( $F_{su} = 75$ ksi)			CR 2642 <sup>a</sup> ( $F_{su} = 95$ ksi)		
Sheet Material . . . . .	Alloy Steel, $F_u = 180$ ksi					
Rivet Diameter, in. . . . . (Nominal Hole Diameter, in.) . .	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Sheet thickness, in.:	Ultimate Strength, lbs.					
	380 <sup>b</sup>	...	...	380 <sup>b</sup>	...	...
	475 <sup>b</sup>	<sup>c</sup> 588 <sup>b</sup>	...	475	<sup>c</sup> 588 <sup>b</sup>	...
	698	741 <sup>b</sup>	<sup>c</sup> 890 <sup>b</sup>	698	741	<sup>c</sup> 890 <sup>b</sup>
	840	908	1004 <sup>b</sup>	<sup>c</sup> 840	908	1004 <sup>b</sup>
	970	1108	1171 <sup>b</sup>	1002	1108	1171
	...	1333	1438	1185	1333	1438
	...	1490	1710	1230	1559	1710
	...	...	2150	...	1885	2380
	...	...	...	...	...	2720
Rivet shear strength . . . . .	970 <sup>d</sup>	1490 <sup>d</sup>	2150 <sup>d</sup>	1230 <sup>e</sup>	1885 <sup>e</sup>	2720 <sup>e</sup>
Sheet thickness, in.:	Yield Strength <sup>f</sup> , lbs.					
	137	...	...	180	...	...
	292	219	...	320	278	...
	494	468	387	536	513	432
	614	620	570	665	675	628
	755	793	776	816	860	847
	...	983	1003	981	1063	1090
	...	1176	1236	1144	1267	1337
	...	...	1809	...	1777	1950
	...	...	...	...	...	2720
Head height (ref.), in. . . . .	0.042	0.055	0.070	0.042	0.055	0.070

a Data supplied by Cherry Fasteners.

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Rivet shear strength is documented in NAS1400.

e Shear strength is based on areas computed from nominal hole diameters in Table 8.1.2(a) and  $F_{su} = 95$  ksi.

f Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(b). Static Joint Strength of Blind 100° Flush Head Locked Spindle Monel Rivets in Machine-Countersunk Stainless Steel Sheet**

Rivet Type .....	NAS1399 MS or MW <sup>a</sup> ( $F_{su} = 55$ ksi)		
Sheet Material .....	AISI 301-1/2 Hard		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) ..	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Sheet thickness, in.:	Ultimate Strength, lbs.		
	287 <sup>b</sup>	...	...
	363	<sup>c</sup> 445 <sup>b</sup>	...
	491	569	<sup>c</sup> 671 <sup>b</sup>
	569	668	755 <sup>b</sup> <sup>c</sup>
	657	776	886
	710	898	1032
	...	1019	1182
	...	1090	1580
	Rivet shear strength <sup>d</sup> .....	710	1090
Sheet thickness, in.:	Yield Strength <sup>e</sup> , lbs.		
	163	...	...
	243	253	...
	348	384	401
	413	463	496
	487	554	606
	568	655	726
	...	753	846
	...	1004	1156
Head height (ref.), in. ....	0.042	0.055	0.070

a Data supplied by Cherry Fasteners.

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Rivet shear strength is documented in NAS1400.

e Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(c). Static Joint Strength of 100° Flush Head Locked Spindle A-286 Blind Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	NAS1921C <sup>a</sup> ( $F_{su} = 80$ ksi)		
Sheet Material .....	Clad 7075-T6		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Ultimate Strength, lbs			
Sheet thickness, in.			
0.050 .....	612 <sup>b</sup>	...	...
0.063 .....	749 <sup>b</sup>	956 <sup>b</sup>	...
0.071 .....	831 <sup>b</sup>	1060 <sup>b</sup>	...
0.080 .....	923 <sup>b</sup>	1180 <sup>b</sup>	1450 <sup>b</sup>
0.090 .....	1110 <sup>b</sup>	1305 <sup>b</sup>	1605 <sup>b</sup>
0.100 .....	1090 <sup>b</sup>	1435 <sup>b</sup>	1755 <sup>b</sup>
0.125 .....	...	1670 <sup>b</sup>	2130 <sup>b</sup>
0.160 .....	...	...	2400 <sup>b</sup>
Rivet shear strength <sup>c</sup> .....	1090	1670	2400
Yield Strength <sup>d</sup> , lbs			
Sheet thickness, in.:			
0.050 .....	365	...	...
0.063 .....	466	571	...
0.071 .....	528	649	...
0.080 .....	598	737	873
0.090 .....	639	835	990
0.100 .....	686	931	1105
0.125 .....	804	1065	1325
0.160 .....	...	...	1605
Head height (ref.), in. ....	0.042	0.055	0.070

a Data supplied by Huck Manufacturing Company.

b Yield value is less than 2/3 of indicated ultimate strength value.

c Rivet shear strength is documented in NAS1900.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3) (revised May 1, 1985 from the greater of 0.012 inch or 4% of nominal diameter).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(d). Static Joint Strength of Blind 100° Flush Head Locked Spindle Monel Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	NAS1399 MS or MW <sup>a</sup> ( $F_{su} = 55$ ksi)		
Sheet Material .....	Clad 7075-T6		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) ..	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.040 .....	323 <sup>b</sup>	...	...
0.050 .....	404 <sup>b</sup>	<sup>c</sup> 499 <sup>b</sup>	...
0.063 .....	500 <sup>b</sup>	631 <sup>b</sup>	<sup>c</sup> 757 <sup>b</sup>
0.071 .....	557	703 <sup>b</sup>	855 <sup>b</sup>
0.080 .....	610	784	958 <sup>b</sup>
0.090 .....	636	873	1065 <sup>b</sup>
0.100 .....	662	937	1175
0.125 .....	710	1015	1370
0.160 .....	...	1090	1505
0.190 .....	...	...	1580
Rivet shear strength <sup>d</sup> .....	710	1090	1580
Yield Strength <sup>e</sup> , lbs.			
Sheet thickness, in.:			
0.040 .....	139	...	...
0.050 .....	223	218	...
0.063 .....	331	353	351
0.071 .....	397	436	451
0.080 .....	472	529	563
0.090 .....	556	633	687
0.100 .....	562	737	811
0.125 .....	574	873	1120
0.160 .....	...	894	1260
0.190 .....	...	...	1280
Head height (ref.), in. ....	0.042	0.055	0.070

a Data supplied by Cherry Fasteners.

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Rivet shear strength is documented in NAS1400.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3) (revised May 1, 1985, from the greater of 0.005 inch or 2.5% of nominal diameter).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.3.2.2(e). Static Joint Strength of 100° Flush Head Locked Spindle Monel Blind Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	NAS 1921 M <sup>a</sup> ( $F_{su} = 75$ ksi)		
Sheet Material .....	Clad 7075-T6		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Ultimate Strength, lbs			
Sheet thickness, in.			
0.050 .....	595 <sup>b</sup>	...	...
0.063 .....	732 <sup>b</sup>	927 <sup>b</sup>	...
0.071 .....	816 <sup>b</sup>	1035 <sup>b</sup>	...
0.080 .....	913 <sup>b</sup>	1158 <sup>b</sup>	1400 <sup>b</sup>
0.090 .....	946 <sup>b</sup>	1289 <sup>b</sup>	1570 <sup>b</sup>
0.100 .....	980 <sup>b</sup>	1415 <sup>b</sup>	1720 <sup>b</sup>
0.125 .....	1020	1525 <sup>b</sup>	2055 <sup>b</sup>
0.160 .....	...	1565 <sup>b</sup>	2245 <sup>b</sup>
0.190 .....	...	...	2260
Rivet shear strength <sup>c</sup> .....	1020	1565	2260
Yield Strength <sup>d</sup> , lbs			
Sheet thickness, in.:			
0.050 .....	354	...	...
0.063 .....	447	554	...
0.071 .....	504	625	...
0.080 .....	569	707	843
0.090 .....	607	796	952
0.100 .....	626	885	1060
0.125 .....	686	972	1265
0.160 .....	...	1080	1430
0.190 .....	...	...	1540
Head height (ref.), in. ....	0.042	0.055	0.070

a Data supplied by Huck Manufacturing Company.

b Yield value is less than 2/3 of indicated ultimate strength value.

c Rivet shear strength is documented in NAS 1900.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3) (revised May 1, 1985 from the greater of 0.012 inch or 4% of nominal diameter).



**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.3.2.2(f). Static Joint Strength of Blind 100° Flush Head Aluminum Alloy (2219) Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	CR 2A62 <sup>a</sup> ( $F_{su} = 36$ ksi)		
Sheet Material .....	Clad 2024-T81		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Ultimate Strength, lbs			
Sheet thickness, in.			
0.050 .....	203	...	...
0.063 .....	289	319	...
0.071 .....	342	385	...
0.080 .....	393	461	503
0.090 .....	416	542	603
0.100 .....	439	610	701
0.125 .....	478	682	894
0.160 .....	...	741	1013
0.190 .....	...	...	1063
Rivet shear strength <sup>b</sup> .....	478	741	1063
Yield Strength <sup>c</sup> , lbs			
Sheet thickness, in.:			
0.050 .....	169	...	...
0.063 .....	247	267	...
0.071 .....	295	326	...
0.080 .....	349	394	423
0.090 .....	409	468	514
0.100 .....	424	544	603
0.125 .....	448	658	827
0.160 .....	...	670	960
0.190 .....	...	...	1002
Head height (ref.), in. ....	0.042	0.055	0.070

a Data supplied by Cherry Fasteners.

b Shear strength values are based on indicated nominal hole diameters and  $F_{su} = 36$  ksi.

c Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(g). Static Joint Strength of Blind 100° Flush Head Locked Aluminum Alloy Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	NAS1921B <sup>a</sup> ( $F_{su} = 36$ ksi)		
Sheet Material .....	Clad 7075-T6		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) ..	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.040 .....	171	...	...
0.050 .....	232	<sup>b</sup> 267	...
0.063 .....	313	366	<sup>b</sup> 411
0.071 .....	360	427	484
0.080 .....	416	498	566
0.090 .....	477	571	658
0.100 .....	494	647	748
0.125 .....	...	755	978
0.160 .....	...	...	1090
Rivet shear strength <sup>c</sup> .....	495	755	1090
Yield Strength <sup>d</sup> , lbs.			
Sheet thickness, in.:			
0.040 .....	110	...	...
0.050 .....	161	171	...
0.063 .....	247	254	270
0.071 .....	303	315	330
0.080 .....	354	395	399
0.090 .....	373	484	506
0.100 .....	393	549	611
0.125 .....	...	610	803
0.160 .....	...	...	906
Head height (ref.), in. ....	0.042	0.055	0.070

a Data supplied by Huck Manufacturing Company.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Rivet shear strength is documented in NAS1900.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3) (revised May 1, 1985, from the greater of 0.005 inch or 2.5% of nominal diameter).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(h). Static Joint Strength of Blind 100° Flush Head Locked Spindle Aluminum Alloy Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type . . . . .	NAS1399B <sup>a</sup> (5056) ( $F_{su}$ = 30 ksi)			NAS1399D <sup>a</sup> (2017) ( $F_{su}$ = 36 ksi)		
Sheet Material . . . . .	Clad 2024-T3					
Rivet Diameter, in. . . . . (Nominal Hole Diameter, in.)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Sheet thickness, in.:	Ultimate Strength, lbs.					
	149 <sup>b</sup>	...	...	149 <sup>b</sup>	...	...
	223 <sup>b</sup>	<sup>c</sup> 230 <sup>b</sup>	...	223 <sup>b</sup>	<sup>c</sup> 230 <sup>b</sup>	...
	310 <sup>b</sup>	349 <sup>b</sup>	<sup>c</sup> 356 <sup>b</sup>	319 <sup>b</sup>	349 <sup>b</sup>	<sup>c</sup> 356 <sup>b</sup>
	366	415 <sup>b</sup>	448 <sup>b</sup>	<sup>c</sup> 379 <sup>b</sup>	420 <sup>b</sup>	448 <sup>b</sup>
	388	492 <sup>b</sup>	544 <sup>b</sup>	423	506 <sup>b</sup>	547 <sup>b</sup>
	...	578	646 <sup>b</sup>	459	600 <sup>b</sup>	660 <sup>b</sup>
	...	596	751 <sup>b</sup>	494	652	775 <sup>b</sup>
	...	...	862	...	755	969
	...	...	...	...	...	1090
Rivet shear strength <sup>d</sup> . . . . .	388	596	862	494	755	1090
Sheet thickness, in.:	Yield Strength <sup>e</sup> , lbs.					
	72	...	...	72	...	...
	114	113	...	114	113	...
	197	182	170	197	182	170
	247	245	220	247	245	220
	304	316	304	304	316	304
	...	396	399	367	396	399
	...	473	493	431	473	493
	...	...	729	...	672	729
	...	...	...	...	...	1060
Head height (ref.), in. . . . .	0.042	0.055	0.070	0.042	0.055	0.070

a Data supplied by Cherry Fasteners.

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Rivet shear strength is documented in NAS1900.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3) (revised May 1, 1985, from the greater of 0.005 inch or 2.5% of nominal diameter).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.3.2.2(i). Static Joint Strength of Blind 100° Flush Head Locked Spindle Aluminum Alloy Rivets in Machine-Countersunk and Dimpled Aluminum Alloy Sheet**

Rivet Type .....	NAS1739B <sup>a</sup> and NAS1739E <sup>a,c</sup> ( $F_{su}$ = 34 ksi)			NAS1739B <sup>b</sup> and NAS1739E <sup>b,c</sup> ( $F_{su}$ = 34 ksi)			
Sheet Material .....	Clad 2024-T3						
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) ...	1/8 (0.144)	5/32 (0.178)	3/16 (0.207)	1/8 (0.144)	5/32 (0.178)	3/16 (0.207)	
Sheet thickness, in.:	Ultimate Strength, lbs.						
	...	...	...	246	334	418	
	...	...	...	281	376	465	
	212	...	...	330	436	536	
	266	<sup>d</sup> 326	...	386	506	616	
	344	410	<sup>d</sup> ...	456	592	716	
	441	533	606	546	703	845	
	504	608	696	<sup>d</sup> ...	771	926	
	554	693	794	...	837	1015	
	...	787	900	...	...	1110	
	...	837	1015	...	...	...	
	...	...	1128	...	...	...	
	Rivet shear strength <sup>e</sup> .....	554	837	1128	554	837	1128
	Sheet thickness, in.:	Yield Strength <sup>f</sup> , lbs.					
...		...	...	...	...	...	
...		...	...	...	...	...	
159		...	...	...	...	...	
212		247	...	...	...	...	
279		331	...	...	...	...	
365		437	492	...	...	...	
418		503	568	...	...	...	
448		577	654	...	...	...	
...		659	750	...	...	...	
...		689	845	...	...	...	
...		...	960	...	...	...	
Head height (ref.), in. ....		0.035	0.047	0.063	0.035	0.047	0.063

a Machine-countersunk holes.

b Dimpled holes. These allowables apply to double dimpled sheets and to the upper sheet dimpled into a machine-countersunk lower sheet. Sheet gauge is that of the thinnest sheet for double dimpled joints and of the upper dimpled, machine-countersunk joints. The thickness of the machine-countersunk sheet must be at least one tabulated gauge thicker than the upper sheet. In no case shall allowables be obtained by extrapolation for gauges other than those shown.

c Data supplied by Cherry Fasteners. Confirmatory data for machine-countersunk holes provided by Allfast Fastening Systems, Inc.

d The values in the table above the horizontal line in each column are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

e Rivet shear strength is documented in NAS1740.

f Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3) (revised May 1, 1985, from the greater of 0.005 inch or 2.5% of nominal diameter).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(j). Static Joint Strength of Blind 100° Flush Head Locked Spindle Aluminum Alloy Rivets in Machine-Countersunk Magnesium Alloy Sheet**

Rivet Type .....	NAS1399B <sup>a</sup> ( $F_{su} = 30$ ksi)				NAS1739B and NAS 1739E <sup>a</sup> ( $F_{su} = 34$ ksi)		
Sheet Material .....	AZ31B-H24						
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)	1/8 (0.144)	5/32 (0.178)	3/16 (0.207)
	Ultimate Strength, lbs.						
Sheet thickness, in.:							
0.032 .....	...	...	...	...	188 <sup>b</sup>	...	...
0.040 .....	178 <sup>b</sup>	...	...	...	235 <sup>b</sup>	<sup>c</sup> 292 <sup>b</sup>	...
0.050 .....	223 <sup>b</sup>	<sup>c</sup> 274 <sup>b</sup>	...	...	295	362 <sup>b</sup>	<sup>c</sup> ...
0.063 .....	292 <sup>b</sup>	349 <sup>b</sup>	<sup>c</sup> 418 <sup>b</sup>	...	371	457	530 <sup>b</sup>
0.071 .....	334 <sup>b</sup>	399 <sup>b</sup>	471 <sup>b</sup>	<sup>c</sup> ...	418	514	600 <sup>b</sup>
0.080 .....	383 <sup>b</sup>	459 <sup>b</sup>	536 <sup>b</sup>	...	471	580	671
0.090 .....	388	526 <sup>b</sup>	613 <sup>b</sup>	803 <sup>b</sup>	531	651	756
0.100 .....	...	593 <sup>b</sup>	693 <sup>b</sup>	892 <sup>b</sup>	<sup>c</sup> 554	725 <sup>b</sup>	843
0.125 .....	...	596	862	1153 <sup>b</sup>	...	837 <sup>b</sup>	1052 <sup>b</sup>
0.160 .....	...	...	...	1532 <sup>b</sup>	...	...	...
Rivet shear strength .....	388 <sup>d</sup>	596 <sup>d</sup>	862 <sup>d</sup>	1550 <sup>d</sup>	554 <sup>e</sup>	837 <sup>e</sup>	1128 <sup>e</sup>
	Yield Strength <sup>f</sup> , lbs.						
Sheet thickness, in.:							
0.032 .....	...	...	...	...	106	...	...
0.040 .....	49	...	...	...	147	164	...
0.050 .....	94	76	...	...	197	227	...
0.063 .....	158	152	128	...	262	307	340
0.071 .....	197	200	186	...	300	355	399
0.080 .....	242	254	250	...	314	414	462
0.090 .....	291	315	323	277	330	459	534
0.100 .....	...	375	396	376	336	478	608
0.125 .....	...	530	580	621	...	508	667
0.160 .....	...	...	...	968	...	...	...
Head height (ref.), in. ....	0.042	0.055	0.070	0.095	0.035	0.047	0.063

a Data supplied by Cherry Fasteners.

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Rivet shear strength is documented in NAS1400.

e Rivet shear strength is documented in NAS1740 dated March 1968.

f Permanent set at yield load: the greater of 0.005 inch or 2.5% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(k). Static Joint Strength of Blind 100° Flush Head Locked Spindle A-286 Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	CR 4622 <sup>a</sup> ( $F_{su} = 75$ ksi)			
Sheet Material .....	Clad 7075-T6			
Rivet Diameter ..... (Nominal Hole Diameter, in.) <sup>b</sup>	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)	1/4 (0.258)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.050 .....	595 <sup>c</sup>	...	...	...
0.063 .....	733 <sup>c</sup>	932 <sup>c</sup>	...	...
0.071 .....	817 <sup>c</sup>	1035 <sup>c</sup>	...	...
0.080 .....	913	1160 <sup>c</sup>	1410 <sup>c</sup>	...
0.090 .....	947	1290 <sup>c</sup>	1570 <sup>c</sup>	...
0.100 .....	982	1420	1725 <sup>c</sup>	2360 <sup>c</sup>
0.125 .....	995	1525	2060	2880 <sup>c</sup>
0.160 .....	...	1545	2215	3605
0.190 .....	...	...	...	3810
0.250 .....	...	...	...	3920
Rivet shear strength <sup>d</sup> .....	995	1545	2215	3920
Yield Strength <sup>e</sup> , lbs				
Sheet thickness, in.:				
0.050 .....	211	...	...	...
0.063 .....	348	339	...	...
0.071 .....	489	470	...	...
0.080 .....	608	620	574	...
0.090 .....	664	787	774	...
0.100 .....	720	947	970	853
0.125 .....	860	1120	1400	1505
0.160 .....	...	1365	1695	2410
0.190 .....	...	...	...	2740
0.250 .....	...	...	...	3405
Head height (ref.), in. ....	0.041	0.054	0.069	0.095

a Data supplied by Cherry Fasteners.

b Allowable loads developed from test with nominal hole diameters as listed.

c Yield value is less than 2/3 of the indicated ultimate strength value.

d Fastener shear strength based upon nominal hole diameters and  $F_{su} = 75$  ksi from data analysis.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(l). Static Joint Strength of Blind 100° Flush Head Locked Spindle Monel Rivets in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Rivet Type .....	CR 4522 <sup>a</sup> ( $F_{su} = 65$ ksi)			
Sheet and Plate Material .....	Clad 7075-T6 and T651			
Rivet Diameter .....	1/8	5/32	3/16	1/4
(Nominal Hole Diameter, in.) <sup>b</sup>	(0.130)	(0.162)	(0.194)	(0.258)
Ultimate Strength, lbs				
Sheet or plate thickness, in.:				
0.050 .....	529 <sup>c</sup>	...	...	...
0.063 .....	632 <sup>c</sup>	828 <sup>c</sup>	...	...
0.071 .....	694 <sup>c</sup>	906 <sup>c</sup>	...	...
0.080 .....	754	995 <sup>c</sup>	1240 <sup>c</sup>	...
0.090 .....	776	1095	1360 <sup>c</sup>	...
0.100 .....	797	1170	1475 <sup>c</sup>	...
0.125 .....	852	1240	1695	2485 <sup>c</sup>
0.160 .....	863	1335	1810	2975
0.190 .....	...	1340	1910	3105
0.250 .....	...	...	1920	3365
0.312 .....	...	...	...	3400
Rivet shear strength <sup>d</sup> .....	863	1340	1920	3400
Yield Strength <sup>e</sup> , lbs				
Sheet or plate thickness, in.:				
0.050 .....	169	...	...	...
0.063 .....	346	273	...	...
0.071 .....	454	408	...	...
0.080 .....	561	562	483	...
0.090 .....	621	732	688	...
0.100 .....	682	874	888	...
0.125 .....	833	1060	1300	1355
0.160 .....	863	1325	1615	2225
0.190 .....	...	1340	1885	2585
0.250 .....	...	...	1920	3300
0.312 .....	...	...	...	3400
Head height (ref.), in. ....	0.042	0.055	0.070	0.095

a Data supplied by Cherry Fasteners.

b Allowable loads developed from test with nominal hole diameters as listed.

c Yield value is less than 2/3 of the indicated ultimate strength value.

d Fastener shear strength based upon nominal hole diameters and  $F_{su} = 65$  ksi from data analysis.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.3.2.2(m). Static Joint Strength of Blind 100° Flush Head Locked Spindle Aluminum Alloy (7050) Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	NAS1721KE and NAS1721KE ( )L <sup>a</sup> ( $F_{SH} = 33$ ksi)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b</sup> ..	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Sheet thickness, in.: 0.040 ..... 0.050 ..... 0.063 ..... 0.071 ..... 0.080 ..... 0.090 ..... 0.100 ..... 0.125 ..... Rivet shear strength <sup>e</sup> .....	Ultimate Strength, lbs.		
	221 <sup>d</sup>	...	...
	277 <sup>d</sup>	342 <sup>d</sup>	...
	351	435 <sup>d</sup>	518 <sup>d</sup>
	396	491 <sup>d</sup>	586 <sup>d</sup>
	448	555	662 <sup>d</sup>
	450	626	747
	...	697	832
	...	700	950
	450	700	950
Sheet thickness, in.: 0.040 ..... 0.050 ..... 0.063 ..... 0.071 ..... 0.080 ..... 0.090 ..... 0.100 ..... 0.125 .....	Yield Strength <sup>f</sup> , lbs.		
	62	...	...
	150	99	...
	263	240	182
	333	327	287
	386	425	404
	403	534	534
	...	600	665
	...	653	874
Head height (ref.), in. ....	0.042	0.055	0.070

a Data supplied by Avdel Corp.

b Loads developed from tests with hole diameters of 0.130, 0.162, and 0.194,  $\pm 0.001$  inch.

c The values in the table above the horizontal line in each column are for knife-edge conditions, and the use of fasteners in this condition is undesirable. The use of knife-edge conditions in the design of military aircraft requires the specific approval of the procuring agency.

d Yield value is less than 2/3 of indicated ultimate value.

e Rivet shear strength is documented in NAS1722.

f Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).



**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(n). Static Joint Strength of Blind 100° Flush Head Locked Spindle A-286 Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	NAS1721C and NAS1721C( )L <sup>a</sup> ( $F_{su} = 75$ ksi)		
Sheet Material .....	Clad 7075-T6		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) .....	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.040 .....	454 <sup>d</sup>	...	...
0.050 .....	585 <sup>d</sup>	707 <sup>d</sup>	...
0.063 .....	751 <sup>d</sup>	919 <sup>d</sup>	1075 <sup>d</sup>
0.071 .....	853 <sup>d</sup>	1045 <sup>d</sup>	1230 <sup>d</sup>
0.080 .....	881 <sup>d</sup>	1190 <sup>d</sup>	1405 <sup>d</sup>
0.090 .....	896	1345 <sup>d</sup>	1595 <sup>d</sup>
0.100 .....	912	1365 <sup>d</sup>	1785 <sup>d</sup>
0.125 .....	951	1415	1970
0.160 .....	1000	1485	2055
0.190 .....	...	1500	2125
0.250 .....	...	...	2200
Rivet shear strength <sup>e</sup> .....	1000	1500	2200
Yield Strength <sup>f</sup> , lbs.			
Sheet thickness, in.:			
0.040 .....	77	...	...
0.050 .....	220	122	...
0.063 .....	375	352	246
0.071 .....	470	471	425
0.080 .....	578	604	585
0.090 .....	615	753	763
0.100 .....	641	902	942
0.125 .....	707	997	1330
0.160 .....	799	1110	1470
0.190 .....	...	1210	1585
0.250 .....	...	...	1820
Head height (ref.), in. ....	0.042	0.055	0.070

a Data supplied by Avdel Corp.

b Loads developed from tests with hole diameters of 0.130, 0.162, and 0.194,  $\pm 0.001$  inch.

c The values in the table above the horizontal line in each column are for knife-edge conditions and the use of fasteners in this condition is undesirable. The use of knife-edge conditions in the design of military aircraft requires the specific approval of the procuring agency.

d Yield value is less than 2/3 of indicated ultimate value.

e Rivet shear strength is documented in NAS1722.

f Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(o). Static Joint Strength of Blind 100° Flush Head Locked Spindle Aluminum Alloy Rivets in Machine Countersunk Aluminum Alloy Sheet**

Rivet Type .....	M7885/3 <sup>a</sup> ( $F_{su} = 51$ ksi approx.)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. ....	1/8	5/32	3/16
(Nominal Hole Diameter, in.) <sup>b</sup> .....	(0.130)	(0.162)	(0.194)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.040 .....	241 <sup>f</sup>	...	...
0.050 .....	290	<sup>c</sup> 375 <sup>f</sup>	...
0.063 .....	355	455	<sup>c</sup> 561 <sup>f</sup>
0.071 .....	394	505	620 <sup>c</sup>
0.080 .....	439	560	686
0.090 .....	471	622	760
0.100 .....	491	683	834
0.125 .....	543	764	1015
0.160 .....	616	855	1125
0.190 .....	664	932	1220
0.250 .....	...	1030	1405
0.312 .....	...	...	1480
Rivet shear strength <sup>d</sup> .....	664	1030	1480
Yield Strength, lbs. <sup>e</sup>			
Sheet thickness, in.:			
0.040 .....	155	...	...
0.050 .....	197	242	...
0.063 .....	252	310	366
0.071 .....	286	352	417
0.080 .....	325	400	474
0.090 .....	367	453	537
0.100 .....	390	506	600
0.125 .....	434	607	758
0.160 .....	495	683	897
0.190 .....	548	749	975
0.250 .....	...	880	1130
0.312 .....	...	...	1290
Head height (ref.), in. ....	0.042	0.055	0.070

a Data supplied by Allfast Fastening Systems, Cherry Textron, John Hassall Inc., and Huck Manufacturing Company.

b Loads developed from tests with hole diameters of 0.130, 0.162, and 0.194,  $\pm 0.001$  inch.

c The values of the table above the horizontal line in each column are for knife-edge conditions, and the use of fasteners in this condition is undesirable. The use of knife-edge conditions in the design of military aircraft requires the specific approval of the procuring agency.

d Rivet shear strength is documented in MIL-R-7885D.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

f Yield is less than 2/3 of indicated ultimate.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(p). Static Joint Strength of Blind 100° Flush Head Locked Spindle Aluminum Alloy Rivets in Machine Countersunk Aluminum Alloy Sheet**

Rivet Type .....	M7885/7 <sup>a</sup> ( $F_{su} = 51$ ksi approx.)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. ....	1/8	5/32	3/16
(Nominal Hole Diameter, in.) <sup>b</sup> ....	(0.144)	(0.178)	(0.207)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.032 .....	204	...	...
0.040 .....	249	<sup>c</sup> 315	...
0.050 .....	304	384	<sup>c</sup> ...
0.063 .....	376	472	557
0.071 .....	420	527	621
0.080 .....	469	588	692
0.090 .....	525	656	771
0.100 .....	580	725	851
0.125 .....	691	895	1049
0.160 .....	769	1072	1327
0.190 .....	814	1154	1462
0.250 .....	...	1245	1652
0.312 .....	...	...	1685
Rivet shear strength <sup>d</sup> .....	814	1245	1685
Yield Strength, lbs. <sup>e</sup>			
Sheet thickness, in.:			
0.032 .....	162	...	...
0.040 .....	202	250	...
0.050 .....	252	312	...
0.063 .....	318	393	457
0.071 .....	358	443	515
0.080 .....	400	499	580
0.090 .....	435	561	653
0.100 .....	470	615	725
0.125 .....	557	723	876
0.160 .....	679	875	1052
0.190 .....	784	1004	1203
0.250 .....	...	1264	1504
0.312 .....	...	...	1685
Head height (ref.), in. ....	0.035	0.047	0.063

a Data supplied by Allfast Fastening Systems, Cherry Textron, John Hassall Inc., and Huck Manufacturing Company.

b Loads developed from tests with hole diameters of 0.144, 0.178, and 0.207,  $\pm 0.001$  inch.

c The values of the table above the horizontal line in each column are for knife-edge conditions, and the use of fasteners in this condition is undesirable. The use of knife-edge conditions in the design of military aircraft requires the specific approval of the procuring agency.

d Rivet shear strength is documented in MIL-R-7885D.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(q). Static Joint Strength of Blind 100° Flush Head Locked Spindle Aluminum Alloy Rivets in Machine Countersunk Aluminum Alloy Sheet**

Rivet Type .....	HC3212 <sup>a</sup> ( $F_{su} = 51$ ksi approx.)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. ....	1/8	5/32	3/16
(Nominal Hole Diameter, in.) <sup>b</sup> .....	(0.130)	(0.162)	(0.194)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.040 .....	241	...	...
0.050 .....	290	<sup>c</sup> 375	...
0.063 .....	355	455	<sup>c</sup> 561
0.071 .....	394	505	620
0.080 .....	439	560	686
0.090 .....	488	622	760
0.100 .....	538	683	834
0.125 .....	631	837	1015
0.160 .....	664	999	1260
0.190 .....	...	1030	1420
0.250 .....	...	...	1480
Rivet shear strength <sup>d</sup> .....	664	1030	1480
Yield Strength, lbs. <sup>e</sup>			
Sheet thickness, in.:			
0.040 .....	169	...	...
0.050 .....	250	265	...
0.063 .....	355	395	417
0.071 .....	394	475	513
0.080 .....	427	560	621
0.090 .....	450	622	741
0.100 .....	473	664	834
0.125 .....	529	735	970
0.160 .....	609	834	1090
0.190 .....	...	919	1190
0.250 .....	...	...	1395
Head height (ref.), in. ....	0.042	0.055	0.070

a Data supplied by Huck International Inc.

b Loads developed from tests with hole diameters of 0.130, 0.162, and 0.194,  $\pm 0.001$  inch.

c The values of the table above the horizontal line in each column are for knife-edge conditions, and the use of fasteners in this condition is undesirable. The use of knife-edge conditions in the design of military aircraft requires the specific approval of the procuring activity.

d Rivet shear strength is documented in MIL-R-7885D.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(r). Static Joint Strength of Blind 100° Flush Head Locked Spindle 2014 Aluminum Alloy Rivets in Machine Countersunk Aluminum Alloy Sheet**

Rivet Type .....	MBC 4807 and 4907 ( $F_{su} = 33$ ksi approx.) <sup>a</sup>		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. ....	1/8	5/32	3/16
(Nominal Hole Diameter, in.) <sup>b</sup>	(0.130)	(0.162)	(0.194)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.040 .....	183	c	...
0.050 .....	243		...
0.063 .....	320	c	437
0.071 .....	368		508
0.080 .....	412		588
0.090 .....	435		677
0.100 .....	450		766
0.125 .....	...		937
0.160 .....	...		950
Rivet shear strength <sup>d</sup> .....	450	700	950
Yield Strength, lbs. <sup>e</sup>			
Sheet thickness, in.:			
0.040 .....	102	...	...
0.050 .....	173	160	...
0.063 .....	264	274	263
0.071 .....	309	345	347
0.080 .....	333	423	441
0.090 .....	360	486	546
0.100 .....	387	519	651
0.125 .....	...	602	765
0.160 .....	...	...	904
Head height (ref.), in. ....	0.041	0.053	0.068

a A product of Avdel Systems Ltd.

b Loads developed from tests with hole diameters of 0.130, 0.162, and 0.194, +/- 0.001 inch.

c The values in the table above the horizontal line in each column are for knife-edge conditions, and the use of fasteners in this condition is undesirable. The use of knife-edge conditions in the design of military aircraft requires the specific approval of the procuring agency.

d Rivet shear strength is documented in NAS 1722, and rivets meet the requirements of NAS 1721.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.3.2.2(s). Static Joint Strength of Blind Protruding Head Locked Spindle 2014 Aluminum Alloy Rivets in Aluminum Alloy Sheet**

Rivet Type .....	MBC 4801 and 4901 ( $F_{su} = 33$ ksi approx.) <sup>a</sup>		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b</sup> ..	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.025 .....	247	...	...
0.032 .....	284	389	...
0.040 .....	326	441	571
0.050 .....	378	507	650
0.063 .....	415	589	751
0.071 .....	437	617	814
0.080 .....	450	649	864
0.090 .....	...	684	906
0.100 .....	...	700	948
0.125 .....	...	...	950
Rivet shear strength <sup>c</sup> .....	450	700	950
Yield Strength, lbs. <sup>d</sup>			
Sheet thickness, in.:			
0.025 .....	238	...	...
0.032 .....	277	375	...
0.040 .....	321	431	552
0.050 .....	368	500	635
0.063 .....	381	572	743
0.071 .....	389	583	810
0.080 .....	399	594	828
0.090 .....	...	607	843
0.100 .....	...	619	858
0.125 .....	...	...	896

a A product of Avdel Systems Ltd.

b Loads developed from tests with hole diameters of 0.130, 0.162, and 0.194,  $\pm 0.001$  inch.

c Rivet shear strength is documented in NAS 1722, and rivets meet the requirements of NAS 1720.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(t). Static Joint Strength of 100° Flush Head Locked Spindle Aluminum Alloy Blind Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	HC6222 <sup>a</sup> ( $F_{su} = 50$ ksi) Nominal		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) ...	1/8 (0.130)	5/32 (0.162)	3/16 (0.194)
Ultimate Strength, lbs			
Sheet thickness, in.:			
0.040 .....	270 <sup>c</sup>	...	...
0.050 .....	317	420 <sup>c</sup>	...
0.063 .....	377	496	624 <sup>c</sup>
0.071 .....	414	542	680
0.080 .....	456	594	743
0.090 .....	503	652	812
0.100 .....	550	711	882
0.125 .....	664	856	1055
0.160 .....	...	1030	1299
0.190 .....	...	...	1480
0.250 .....	...	...	...
Rivet shear strength <sup>d</sup> .....	664	1030	1480
Yield Strength <sup>e</sup> , lbs			
Sheet thickness, in.:			
0.040 .....	196	237 <sup>b</sup>	...
0.050 .....	252	306	...
0.063 .....	323	395	464
0.071 .....	368	451	530
0.080 .....	417	512	605
0.090 .....	445	581	687
0.100 .....	459	650	770
0.125 .....	494	714	972
0.160 .....	...	775	1045
0.190 .....	...	...	1108
0.250 .....	...	...	...
Head height (ref.), in. ....	0.042	0.055	0.070

a Data supplied by Huck International, Inc.

b Yield value is less than 2/3 of the indicated ultimate.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Rivet shear strength is documented in MIL-R-7885D.

e Permanent set at yield load: 4% of nominal hole diameter (see 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.2(u). Static Joint Strength of 100° Flush Head Locked Spindle Aluminum Alloy Blind Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	HC6252 <sup>a</sup> ( $F_{su} = 50$ ksi)		
Sheet Material .....	Clad 2024-T3		
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) ..	1/8 (0.144)	5/32 (0.178)	3/16 (0.207)
Ultimate Strength, lbs			
Sheet thickness, in.:			
0.032 .....	265 <sup>b,c</sup>	...	...
0.040 .....	304	408 <sup>b,c</sup>	...
0.050 .....	352	467	...
0.063 .....	414	544	665 <sup>c</sup>
0.071 .....	452	591	720
0.080 .....	495	645	782
0.090 .....	543	704	851
0.100 .....	591	763	920
0.125 .....	701	911	1092
0.160 .....	814	1097	1332
0.190 .....	...	1237	1505
0.250 .....	...	1245	1685
Rivet shear strength <sup>d</sup> .....	814	1245	1685
Yield Strength <sup>e</sup> , lbs			
Sheet thickness, in.:			
0.032 .....	154	...	...
0.040 .....	214	240	...
0.050 .....	288	332	...
0.063 .....	384	451	500
0.071 .....	444	524	586
0.080 .....	494	607	682
0.090 .....	513	698	788
0.100 .....	531	758	895
0.125 .....	576	814	1048
0.160 .....	640	893	1139
0.190 .....	...	961	1218
0.250 .....	...	1096	1376
Head height (ref.), in. ....	0.035	0.047	0.063

a Data supplied by Huck International, Inc.

b Yield value is less than 2/3 of the indicated ultimate.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring activity.

d Rivet shear strength is documented in MIL-R-7885D.

e Permanent set at yield load: 4% of nominal hole diameter (see 9.4.1.3.3).



**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.3(a). Static Joint Strength of Blind 100° Flush Head A-286 Bolts in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type . . . . .	MS21140 <sup>a</sup> ( $F_{su} = 95$ ksi)				
Sheet and Plate Material . . . . .	Clad 7075-T6 and T651				
Fastener Diameter, in. . . . . (Nominal Shank Diameter, in.)	5/32 (0.163)	3/16 (0.198)	1/4 (0.259)	5/16 (0.311)	3/8 (0.373)
Ultimate Strength, lbs					
Sheet or plate thickness, in.:					
0.071 . . . . .	1165 <sup>b</sup>	...	...	...	...
0.080 . . . . .	1330 <sup>b</sup>	<sup>c</sup> 1600 <sup>b</sup>	...	...	...
0.090 . . . . .	1515 <sup>b</sup>	1805 <sup>b</sup>	<sup>c</sup> ...	...	...
0.100 . . . . .	1700 <sup>b</sup>	2020 <sup>b</sup>	2615 <sup>b</sup>	...	...
0.125 . . . . .	1980 <sup>b</sup>	2595 <sup>b</sup>	3295 <sup>b</sup>	<sup>c</sup> 3935 <sup>b</sup>	...
0.160 . . . . .	...	2925 <sup>b</sup>	4335 <sup>b</sup>	5080 <sup>b</sup>	<sup>c</sup> 6010 <sup>b</sup>
0.190 . . . . .	...	...	5005 <sup>b</sup>	6150 <sup>b</sup>	<sup>c</sup> 7205 <sup>b</sup>
0.200 . . . . .	...	...	...	6520 <sup>b</sup>	6580 <sup>b</sup>
0.250 . . . . .	...	...	...	7215 <sup>b</sup>	9810 <sup>b</sup>
0.312 . . . . .	...	...	...	...	10380 <sup>b</sup>
Fastener shear strength <sup>d</sup> . . . . .	1980	2925	5005	7215	10380
Yield Strength <sup>e</sup> , lbs					
Sheet or plate thickness, in.:					
0.071 . . . . .	478	...	...	...	...
0.080 . . . . .	584	627	...	...	...
0.090 . . . . .	702	730	...	...	...
0.100 . . . . .	819	901	1025	...	...
0.125 . . . . .	1115	1260	1435	1540	...
0.160 . . . . .	...	1760	2090	2285	2430
0.190 . . . . .	...	...	2655	2965	3235
0.200 . . . . .	...	...	...	3190	3510
0.250 . . . . .	...	...	...	4320	4860
0.312 . . . . .	...	...	...	...	6460
Head height (ref.), in. . . . .	0.074	0.082	0.108	0.140	0.168

a Data supplied by Huck Manufacturing Company.

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Fastener shear strength is documented in MIL-F-8975.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3) (revised May 1, 1986, from the greater of 0.012 inch or 4% of nominal diameter).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.3(b<sub>1</sub>). Static Joint Strength of Blind 100° Flush Head Alloy Steel Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type . . . . .	MS90353, MS90353S, and MS90353U <sup>a</sup> ( $F_{su} = 112$ ksi)				
Sheet and Plate Material . . . . .	Clad 2024-T3 and T351				
Fastener Diameter, in. . . . . (Nominal Shank Diameter, in.) .	5/32 (0.163)	3/16 (0.198)	1/4 (0.259)	5/16 (0.311)	3/8 (0.373)
Ultimate Strength, lbs					
Sheet or plate thickness, in.:					
0.071 . . . . .	1120 <sup>b</sup>	...	...	...	...
0.080 . . . . .	1305 <sup>b</sup>	<sup>c</sup> 1480 <sup>b</sup>	...	...	...
0.090 . . . . .	1510 <sup>b</sup>	1735 <sup>b</sup>	<sup>c</sup> ...	...	...
0.100 . . . . .	1740 <sup>b</sup>	2000 <sup>b</sup>	2380 <sup>b</sup>	...	...
0.125 . . . . .	2080 <sup>b</sup>	2670 <sup>b</sup>	3210 <sup>b</sup>	<sup>c</sup> 3625 <sup>b</sup>	...
0.160 . . . . .	2340 <sup>b</sup>	3195 <sup>b</sup>	4440 <sup>b</sup>	5060 <sup>b</sup>	<sup>c</sup> 5700 <sup>b</sup>
0.190 . . . . .	...	3450 <sup>b</sup>	5090 <sup>b</sup>	6310 <sup>b</sup>	7180 <sup>b</sup> <sup>c</sup>
0.250 . . . . .	...	...	5900 <sup>b</sup>	7860 <sup>b</sup>	9890 <sup>b</sup>
0.312 . . . . .	...	...	...	8500 <sup>b</sup>	11600 <sup>b</sup>
0.375 . . . . .	...	...	...	...	12200 <sup>b</sup>
Fastener shear strength <sup>d</sup> . . . . .	2340	3450	5900	8500	12200
Yield Strength <sup>e</sup> , lbs					
Sheet or plate thickness, in.:					
0.071 . . . . .	403	...	...	...	...
0.080 . . . . .	513	501	...	...	...
0.090 . . . . .	636	652	...	...	...
0.100 . . . . .	759	799	1045	...	...
0.125 . . . . .	989	1170	1525	1620	...
0.160 . . . . .	1170	1510	2200	2430	2610
0.190 . . . . .	...	1700	2700	3120	3440
0.250 . . . . .	...	...	3330	4170	5095
0.312 . . . . .	...	...	...	4955	6175
0.375 . . . . .	...	...	...	...	7135
Head height (ref.), in. . . . .	0.072	0.080	0.105	0.137	0.165

a Data supplied by Huck Manufacturing Company.

b Yield strength value is less than 2/3 of indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Fastener shear strength is documented in MIL-F-8117.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.3.2.3(b<sub>2</sub>). Static Joint Strength of Blind 100° Flush Head Alloy Steel Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Rivet Type .....	MS90353 <sup>a</sup> ( $F_{su} = 112$ ksi)				
Sheet and Plate Material .....	Clad or Bare 7075-T6 and T651				
Fastener Diameter, in. .... (Nominal Hole Diameter, in.) .	5/32 (0.163)	3/16 (0.198)	1/4 (0.259)	5/16 (0.311)	3/8 (0.373)
	Ultimate Strength, lbs				
Sheet or plate thickness, in.:					
0.071 .....	1360 <sup>c</sup>	...	...	...	...
0.080 .....	1535 <sup>c</sup>	<sup>b</sup> 1830 <sup>c</sup>	...	...	...
0.090 .....	1710 <sup>c</sup>	2090 <sup>c</sup>	<sup>b</sup> ...	...	...
0.100 .....	1880 <sup>c</sup>	2330 <sup>c</sup>	2970 <sup>c</sup>	...	...
0.125 .....	2200 <sup>c</sup>	2825 <sup>c</sup>	3805 <sup>c</sup>	<sup>b</sup> 4490 <sup>c</sup>	...
0.160 .....	2340	3365	4760 <sup>c</sup>	5850 <sup>c</sup>	<sup>b</sup> 6960 <sup>c</sup>
0.190 .....	...	3450	5370 <sup>c</sup>	6790 <sup>c</sup>	8310 <sup>c</sup> <sup>b</sup>
0.250 .....	...	...	5900	8290 <sup>c</sup>	10450 <sup>c</sup>
0.312 .....	...	...	...	8500	12200
0.375 .....	...	...	...	...	12200
Fastener shear strength <sup>d</sup> .....	2340	3450	5900	8500	12200
	Yield Strength <sup>e</sup> , lbs				
Sheet or plate thickness, in.:					
0.071 .....	557	...	...	...	...
0.080 .....	666	757	...	...	...
0.090 .....	787	875	...	...	...
0.100 .....	909	1025	1240	...	...
0.125 .....	1215	1395	1640	1860	...
0.160 .....	1640	1910	2315	2590	2850
0.190 .....	...	2355	2895	3290	3675
0.250 .....	...	...	4055	4680	5345
0.312 .....	...	...	...	6125	7075
0.375 .....	...	...	...	...	8830
Head height (ref.), in. ....	0.072	0.080	0.105	0.137	0.165

a Data supplied by Huck Manufacturing Company.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Yield value is less than 2/3 of indicated ultimate strength value.

d Fastener shear strength is documented in MIL-F-81177.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3) revised May 1, 1986, from the greater of 0.012 inch or 4% of nominal diameters.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.3(c). Static Joint Strength of Blind 100° Flush Head Alloy Steel Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type . . . . .	FF-200 <sup>a</sup>		FF-260 <sup>a</sup>		FF-312 <sup>a</sup>	
Sheet and Plate Material . . . . .	Clad 2024-T42	Clad 7075-T6	Clad 2024-T42	Clad 7075-T6	Clad 2024-T42	Clad 7075-T6
Fastener Diameter, in. . . . . (Nominal Shank Diameter, in.)	3/16 (0.198)	3/16 (0.198)	1/4 (0.259)	1/4 (0.259)	5/16 (0.311)	5/16 (0.311)
Ultimate Strength, lbs						
Sheet or plate thickness, in.:						
0.071 . . . . .	1220 <sup>b</sup>	1360 <sup>b</sup>	...	...	...	...
0.080 . . . . .	1380 <sup>b</sup>	1500 <sup>b</sup>	...	...	...	...
0.090 . . . . .	1520 <sup>b</sup>	1620 <sup>b</sup>	...	...	...	...
0.100 . . . . .	1650 <sup>b</sup>	1740 <sup>b</sup>	2250 <sup>b</sup>	2700 <sup>b</sup>	...	...
0.125 . . . . .	1890 <sup>b</sup>	1960	2940 <sup>b</sup>	3220 <sup>b</sup>	2720	3080 <sup>b</sup>
0.160 . . . . .	2160	2200	3390 <sup>b</sup>	3570 <sup>b</sup>	3600 <sup>b</sup>	3940 <sup>b</sup>
0.190 . . . . .	2400	2420	3730 <sup>b</sup>	2860 <sup>b</sup>	4490 <sup>b</sup>	4810 <sup>b</sup>
0.250 . . . . .	2620	2620	4260 <sup>b</sup>	4320	5550 <sup>b</sup>	6000 <sup>b</sup>
0.312 . . . . .	...	...	4500	4500	6000 <sup>b</sup>	...
Fastener shear strength <sup>d</sup>	2620	2620	4500	4500	6000	6000
Yield Strength <sup>e</sup> , lbs						
Sheet or plate thickness, in.:						
0.071 . . . . .	685	850	...	...	...	...
0.080 . . . . .	770	930	...	...	...	...
0.090 . . . . .	870	1025	...	...	...	...
0.100 . . . . .	980	1130	1120	1280	...	...
0.125 . . . . .	1200	1350	1380	1600	1440	1540
0.160 . . . . .	1500	1640	1700	2050	1820	1980
0.190 . . . . .	1800	1960	2010	2470	2200	2520
0.250 . . . . .	2400	2550	2600	3190	2950	3710
0.312 . . . . .	...	...	3200	3880	3690	...
Head height (ref.), in. . . . .	0.077		0.102		0.134	

a Data supplied by Monogram Aerospace Fasteners.

b Yield value is less than 2/3 of indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Fastener shear strength is documented in NAS1675.

e Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.3.2.3(d). Static Joint Strength of Blind 100° Flush Head Alloy Steel Fasteners in Machine-Countersunk Aluminum Alloy Sheet**

Fastener Type .....	NS 100 <sup>a</sup>		
Sheet Material .....	Clad 7075-T6		
Fastener Diameter, in. .... (Nominal Shank Diameter, in.)	5/32 (0.163)	3/16 (0.198)	1/4 (0.259)
	Ultimate Strength, lbs		
Sheet thickness, in.:			
0.063 .....	1085 <sup>b</sup>	...	...
0.071 .....	1295 <sup>b</sup>	<sup>c</sup> 1400 <sup>b</sup>	...
0.080 .....	1525 <sup>b</sup>	1710 <sup>b</sup>	<sup>c</sup> ...
0.090 .....	1695 <sup>b</sup>	2020 <sup>b</sup>	...
0.100 .....	1830 <sup>b</sup>	2335 <sup>b</sup>	2715 <sup>b</sup>
0.125 .....	2170 <sup>b</sup>	2745 <sup>b</sup>	<sup>c</sup> 3765 <sup>b</sup>
0.160 .....	2190	3325 <sup>b</sup>	4615 <sup>b</sup>
0.190 .....	...	3325 <sup>b</sup>	5280 <sup>b</sup>
0.250 .....	...	...	5690 <sup>b</sup>
Fastener shear strength <sup>d</sup> .....	2190	3325	5690
	Yield Strength <sup>e</sup> , lbs		
Sheet thickness, in.:			
0.063 .....	516	...	...
0.071 .....	602	690	...
0.080 .....	698	805	...
0.090 .....	804	936	...
0.100 .....	911	1065	1300
0.125 .....	1180	1390	1725
0.160 .....	1500	1835	2320
0.190 .....	...	2165	2830
0.250 .....	...	...	3725
Head height (ref.), in. ....	0.069	0.077	0.102

a Data supplied by Monogram Aerospace Fasteners.

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Fastener shear strength values are A basis from analysis of test data.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3) (revised May 1, 1985, from the greater of 0.012 inch or 4% of nominal diameter).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.3.2.3(e). Static Joint Strength of Blind 100° Flush Head Aluminum Alloy Fasteners in Machine-Countersunk Aluminum Alloy Sheet**

Fastener Type .....	SSHFA-200 <sup>a</sup> ( $F_{su} = 50$ ksi)		SSHFA-260 <sup>a</sup> ( $F_{su} = 50$ ksi)	
Sheet Material .....	Clad 2024-T42	Clad 7075-T6	Clad 2024-T42	Clad 7075-T6
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) .....	3/16 (0.198)	3/16 (0.198)	1/4 (0.259)	1/4 (0.259)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.050 .....	500	590	...	...
0.063 .....	640	750	<sup>b</sup> ...	...
0.071 .....	790	880	...	...
0.080 .....	1040	1060	1310	1480
0.090 .....	1270	1270	1480	1650 <sup>b</sup>
0.100 .....	1450	1450	1680	1850
0.125 .....	1550	1550	2010	2250
0.160 .....	...	...	2300	2650
0.190 .....	...	...	2520	...
0.250 .....	...	...	2650	...
Fastener shear strength <sup>c</sup> .....	1550	1550	2650	2650
Yield Strength <sup>d</sup> , lbs				
Sheet thickness, in.:				
0.050 .....	500	520	...	...
0.063 .....	630	700	...	...
0.071 .....	740	800	...	...
0.080 .....	860	915	940	1160
0.090 .....	990	1040	1080	1300
0.100 .....	1130	1180	1230	1460
0.125 .....	1340	1420	1550	1790
0.160 .....	...	...	1980	2240
0.190 .....	...	...	2420	...
0.250 .....	...	...	2650	...
Head height (ref.), in. ....	0.061	0.061	0.088	0.088

a Data supplied by Monogram Aerospace Fasteners.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Fastener shear strength is documented in NAS1675.

d Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.3(f). Static Joint Strength of Blind 100° Flush Head Alloy Steel Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type . . . . .	PLT-150 <sup>a</sup> ( $F_{su} = 112$ ksi) (H-11 Nut and screw, Inconel X-750 or A-286 Sleeve)			
Sheet or Plate Material . . . . .	Clad 7075-T6 and T651			
Fastener Diameter, in. . . . . (Nominal Shank Diameter, in.) . . . .	5/32 (0.163)	3/16 (0.198)	1/4 (0.259)	3/8 (0.373)
	Ultimate Strength, lbs			
Sheet or plate thickness, in.:				
0.063 . . . . .	1120 <sup>b</sup>	...	...	...
0.071 . . . . .	1320 <sup>b</sup>	<sup>c</sup> 1470 <sup>b</sup>	...	...
0.080 . . . . .	1550 <sup>b</sup>	1755 <sup>b</sup>	...	...
0.090 . . . . .	1730 <sup>b</sup>	2060 <sup>b</sup>	...	...
0.100 . . . . .	1885 <sup>b</sup>	2350 <sup>b</sup>	2820 <sup>b</sup>	...
0.125 . . . . .	2300 <sup>b</sup>	2850 <sup>b</sup>	3825 <sup>b</sup>	<sup>c</sup> ...
0.160 . . . . .	2340 <sup>b</sup>	3450 <sup>b</sup>	4790 <sup>b</sup>	6695 <sup>b</sup>
0.190 . . . . .	...	...	5570 <sup>b</sup>	8440 <sup>b</sup>
0.250 . . . . .	...	...	5900 <sup>b</sup>	10700 <sup>b</sup>
0.312 . . . . .	...	...	...	12250 <sup>b</sup>
Fastener shear strength <sup>d</sup> . . . . .	2340	3450	5900	12250
	Yield Strength <sup>e</sup> , lbs			
Sheet or plate thickness, in.:				
0.063 . . . . .	534	...	...	...
0.071 . . . . .	615	730	...	...
0.080 . . . . .	705	830	...	...
0.090 . . . . .	805	953	...	...
0.100 . . . . .	906	1075	1345	...
0.125 . . . . .	1235	1390	1750	...
0.160 . . . . .	1545	1910	2310	3160
0.190 . . . . .	...	...	2965	3850
0.250 . . . . .	...	...	3840	5395
0.312 . . . . .	...	...	...	6985
Head height (ref.), in. . . . .	0.069	0.077	0.102	0.160

a Data supplied by Voi-Shan Industries (Inconel X-750 Sleeve) and Monogram Aerospace Fasteners (A-286 Sleeve).

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Fastener shear strength based on area computed from nominal shank diameter in Table 9.4.1.2(a) and  $F_{su} = 112$  ksi.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3) (revised May 1, 1985, from the greater of 0.012 inch or 4% of nominal diameter).

**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.3(g). Static Joint Strength of Blind 100° Flush Head Alloy Steel Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type . . . . .	NAS1670-L <sup>a</sup>				
Sheet and Plate Material . . . . .	Clad 7075-T6 and T651				
Fastener Diameter, in. <sup>b</sup> . . . . . (Nominal Shank Diameter, in.)	5/32 (0.163)	3/16 (0.198)	1/4 (0.259)	5/16 (0.311)	3/8 (0.373)
Ultimate Strength, lbs					
Sheet or plate thickness, in.:					
0.063 . . . . .	1110 <sup>c</sup>	...	...	...	...
0.071 . . . . .	1230 <sup>c</sup>	<sup>d</sup> 1530 <sup>c</sup>	...	...	...
0.080 . . . . .	1365 <sup>c</sup>	1700 <sup>c</sup>	<sup>d</sup> ...	...	...
0.090 . . . . .	1525 <sup>c</sup>	1885 <sup>c</sup>	...	...	...
0.100 . . . . .	1678 <sup>c</sup>	2065 <sup>c</sup>	2800 <sup>c</sup>	...	...
0.125 . . . . .	1678	2530 <sup>c</sup>	3400 <sup>c</sup>	<sup>d</sup> 4165 <sup>c</sup>	...
0.160 . . . . .	1678	2620 <sup>c</sup>	4255 <sup>c</sup>	5190 <sup>c</sup>	<sup>d</sup> 6350 <sup>c</sup>
0.190 . . . . .	...	2620	4500 <sup>c</sup>	6000 <sup>c</sup>	7395 <sup>c</sup> <sup>d</sup>
0.250 . . . . .	...	...	4500	6000	9625 <sup>c</sup>
0.312 . . . . .	...	...	...	...	9750
0.375 . . . . .	...	...	...	...	9750
Fastener shear strength <sup>e</sup> . . . . .	1678	2620	4500	6000	9750
Yield Strength <sup>f</sup> , lbs					
Sheet or plate thickness, in.:					
0.063 . . . . .	500	...	...	...	...
0.071 . . . . .	601	647	...	...	...
0.080 . . . . .	711	788	...	...	...
0.090 . . . . .	802	941	...	...	...
0.100 . . . . .	887	1085	1255	...	...
0.125 . . . . .	1105	1340	1770	1930	...
0.160 . . . . .	1405	1700	2250	2720	3055
0.190 . . . . .	...	2020	2655	3200	3890
0.250 . . . . .	...	...	3480	4185	5020
0.312 . . . . .	...	...	...	...	6280
0.375 . . . . .	...	...	...	...	7520
Head height (ref.), in. . . . .	0.069	0.077	0.102	0.134	0.160

a Data supplied by Monogram Aerospace Fasteners.

b Fasteners installed in 0.165/0.166, 0.200/0.201, 0.261/0.262, 0.312/0.313, 0.375/0.376 inch holes.

c Yield value is less than 2/3 of the indicated ultimate strength value.

d Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

e Fastener shear strength is documented in NAS1675.

f Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).



**MIL-HDBK-5H****1 December 1998****Table 8.1.3.2.3(h). Static Joint Strength of Blind 100° Flush Head Aluminum Alloy Fasteners in Machine-Countersunk Aluminum Alloy Sheet**

Fastener Type .....	NAS1674-L <sup>a</sup>		
Sheet Material .....	Clad 7075-T6		
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) <sup>b</sup>	5/32 (0.163)	3/16 (0.198)	1/4 (0.259)
Ultimate Strength, lbs			
Sheet thickness, in.:			
0.050 .....	548 <sup>c</sup>	...	...
0.063 .....	756 <sup>c</sup>	853	...
0.071 .....	882 <sup>c</sup>	1010	...
0.080 .....	960	1185	...
0.090 .....	...	1375	1645
0.100 .....	...	1550	1900
0.125 .....	...	...	2535
0.160 .....	...	...	2650
Fastener shear strength <sup>d</sup> .....	960	1550	2650
Yield Strength <sup>e</sup> , lbs			
Sheet thickness, in.:			
0.050 .....	356	...	...
0.063 .....	481	666	...
0.071 .....	561	774	...
0.080 .....	650	892	...
0.090 .....	...	1025	1275
0.100 .....	...	1155	1450
0.125 .....	...	...	1880
0.160 .....	...	...	2480
Head height (ref.), in. ....	0.049	0.061	0.088

a Data supplied by Monogram Aerospace Fasteners.

b Fasteners installed in 0.165/0.166, 0.199/0.200, 0.260/0.261 inch holes.

c Yield value is less than 2/3 of the indicated ultimate strength value.

d Fastener shear strength is documented in NAS1675.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998**

**8.1.4 SWAGED COLLAR/UPSET-PIN FASTENERS** — The strengths shown in the following tables are applicable only when grip lengths and hole tolerances are as recommended by respective fastener manufacturers. For some fastener systems, permanent set at yield load may be increased if hole sizes greater than those listed in the applicable table are used. This condition may exist even though the test hole size lies within the manufacturer's recommended hole size range (refer to Section 9.4.1.3.3).

The ultimate allowable shear load for lockbolts and lockbolt stumps may be obtained from Table 8.1.4 for the appropriate shear stress level. Tensile strengths of lockbolts and lockbolt stumps also are contained in Table 8.1.4.

For lockbolts under combined loading of shear and tension installed in material having a thickness large enough to make the shear cutoff strength critical for shear loading, the following interaction equations are applicable:

$$\text{Steel lockbolts, } R_t + R_s^{10} = 1.0$$

$$7075\text{-T6 lockbolts, } R_t + R_s^5 = 1.0$$

where  $R_t$  and  $R_s$  are the ratios of applied load to allowable load in tension and shear, respectively.

Unless otherwise specified, yield load is defined in Section 9.4.1.3.3 as the load which results in a joint permanent set equal to 4% D, where D is the decimal equivalent of the fastener shank diameter, as defined in 9.4.1.2(a).

**8.1.4.1 Protruding-Head Swaged Collar Fastener Joints** — Tables 8.1.4.1(a) and (b) contain joint allowables for various protruding-head swaged collar fastener/sheet material combinations. It has been shown that protruding shear head (representative configurations are NAS 2406 to NAS 2412 and M43859/1) fastener joints may not develop the full bearing strength of joint material. Therefore, static allowable loads for protruding shear head fasteners must be established from test data using the criteria specified in Section 9.4.1. For shear joints with protruding tension head fasteners, the load per fastener at which shear or bearing type of failure occurs is calculated separately and the lower of the two governs the design. Allowable shear loads are obtained from Table 8.1.4.

The design bearing stresses for various materials at room and other temperatures are given in strength properties stated for each alloy or group of alloys, and are applicable to joints with pins in cylindrical holes and where  $t/D \geq 0.18$ . Where  $t/D < 0.18$ , tests to substantiate yield and ultimate bearing strengths must be performed. These bearing stresses are applicable only for design of rigid joints where there is no possibility of relative motion of the parts joined without deformation of such parts.

For convenience, "unit" sheet bearing strengths for pins, based on bearing stress of 100 ksi and nominal fastener diameters, are given in Table 8.1.5.1. The strength for a specific combination of fastener, sheet thickness, and sheet material is obtained by multiplying the proper "unit" strength by the ratio of material allowable bearing stress (ksi) to 100.

**8.1.4.2 Flush-Head Swaged Collar Fastener Joints** — Tables 8.1.4.2(a) through (j) contain joint allowables for various flush-head swaged collar fastener/sheet material combinations. The allowable loads for flush-head swaged collar fasteners were established from test data using the following criteria, unless otherwise noted in the footnotes of individual tables.

*Ultimate Load* — Average ultimate test load divided by a factor of 1.14, as defined in Section 9.4. This factor is not applicable to shear strength cutoff values which may be either the procurement specification shear strength (S value) of the fastener or, if no specification exists, a statistical value determined from test results as described in Section 9.4.

**MIL-HDBK-5H**  
**1 December 1998**

The allowable loads shown for flush-head swaged collar fasteners are applicable to joints having  $e/D$  equal to or greater than 2.0.

For machine countersunk joints, the sheet gage specified in the tables is that of countersunk sheet. When the noncountersunk sheet is thinner than the countersunk sheet, the bearing allowable for the noncountersunk sheet-fastener combination should be computed, compared to the table value, and the lower of the two values selected.

**Table 8.1.4. Ultimate Single-Shear and Tensile Strengths of Lockbolts and Lockbolt Stumps<sup>a</sup>**

Nominal Diameter (inches)	Heat Treated Alloy Steel <sup>b</sup> (160 ksi)			7075-T6 <sup>c</sup>		
	Single-Shear Strength, lbs.	Tensile Strength, lbs.		Single-Shear Strength, lbs.	Tensile Strength, lbs.	
		Tensile Type <sup>d</sup>	Shear Type <sup>e</sup>			Tensile Type <sup>d</sup>
		NAS 1456 thru 1462	NAS 1414 thru 1422			NAS 1516 thru 1522
		NAS 1465 thru 1472	NAS 1424 thru 1432			NAS 1525 thru 1532
	NAS 1475 thru 1482	NAS 1436 thru 1442	NAS 1535 thru 1542			
	NAS 1486 thru 1492	NAS 1446 thru 1452	NAS 1546 thru 1552			
	NAS 1496 thru 1502		NAS 1556 thru 1562			
5/32 .....	2007 <sup>f</sup> /1822 <sup>g</sup>	1100 <sup>f</sup>	705 <sup>g</sup>	960 <sup>f</sup>	740 <sup>f</sup>	
3/16 .....	2623	2210	1105	1260	1195	
1/4 .....	4660	4080	2040	2185	2200	
5/16 .....	7290	6500 <sup>d</sup>	3250	3450	3500	
3/8 .....	10490	10100 <sup>h</sup>	5050	4970	5455	

a Lockbolts are pull-gun driven; lockbolt stumps are hammer or squeeze driven.

b Used with 2024-T4 aluminum alloy collar, NAS 1080.

c Used with 6061-T6 aluminum alloy collar.

d Tensile type have a higher head and more grooves than the shear type and can be either protruding or 100° flush head.  
Strength value listed refers to lowest strength fastener configuration within this type.

e Shear type have shorter head and less grooves than the tensile type and can be either protruding or 100° flush head.  
Strength values listed refer to lowest strength fastener configuration within this type.

f Available as lockbolt only (0.164 dia. for #8 lockbolts).

g Available as lockbolt stump only (0.156 dia. for 5/32 stumps).

h Five groove design on lockbolts.

**MIL-HDBK-5H****1 December 1998****Table 8.1.4.1(a). Static Joint Strength of Protruding Shear Head Ti-6Al-4V Cherrybuck Fasteners in Aluminum Alloy Sheet**

Fastener Type .....	CSR 925 <sup>a</sup> ( $F_{su} = 95$ ksi)		
Sheet Material .....	Clad 7075-T6		
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) <sup>b</sup> ...	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.050 .....	995	...	...
0.063 .....	1227	1442	...
0.071 .....	1371	1607	...
0.080 .....	1532	1792	2415
0.090 .....	1711	2001	2688
0.100 .....	1890	2205	2960
0.125 .....	2007	2694	3641
0.160 .....	...	...	4595
0.190 .....	...	...	4660
Fastener shear strength <sup>c</sup> .....	2007	2694	4660
Yield Strength <sup>d</sup> , lbs.			
Sheet thickness, in.:			
0.050 .....	861	...	...
0.063 .....	1013	1225	...
0.071 .....	1107	1334	...
0.080 .....	1213	1455	2067
0.090 .....	1331	1592	2246
0.100 .....	1448	1727	2425
0.125 .....	1741	2068	2873
0.160 .....	...	...	3499
0.190 .....	...	...	4036

a Data supplied by Cherry Fasteners.

b Fasteners installed in clearance holes (0.0005" - 0.002") (Ref. Section 8.1.4).

c Fastener shear strength based on area computed from nominal shank diameters in Table 9.4.1.2(a) and  $F_{su} = 95$  ksi.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.4.1(b). Static Joint Strength of Protruding Shear Head Ti-6Al-4V Cherrybuck Fasteners in Aluminum Alloy Sheet**

Fastener Type .....	CSR 925 <sup>a</sup> ( $F_{su} = 95$ ksi)		
Sheet Material .....	Clad 2024-T3		
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) <sup>b</sup> ..	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.050 .....	807	...	...
0.063 .....	1020	1180	...
0.071 .....	1150	1335	...
0.080 .....	1300	1505	1970
0.090 .....	1465	1695	2220
0.100 .....	1630	1885	2470
0.125 .....	2007	2360	3095
0.160 .....	...	2694	3975
0.190 .....	...	...	4660
Fastener shear strength <sup>c</sup> .....	2007	2694	4660
Yield Strength <sup>d</sup> , lbs.			
Sheet thickness, in.:			
0.050 .....	619	...	...
0.063 .....	747	889	...
0.071 .....	827	981	...
0.080 .....	916	1085	1495
0.090 .....	1015	1200	1645
0.100 .....	1115	1315	1795
0.125 .....	1360	1600	2175
0.160 .....	...	2000	2705
0.190 .....	...	...	3155

a Data supplied by Cherry Fasteners.

b Fasteners installed in clearance holes (0.0005" - 0.002") (Ref. Section 8.1.4).

c Fastener shear strength based on area computed from nominal diameters in Table 9.4.1.2(a) and  $F_{su} = 95$  ksi.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.4.2(a). Static Joint Strength of 100° Flush Shear Head Alloy Steel Lockbolt Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type .....	NAS 1436-1442 <sup>a</sup> ( $F_{SH} = 95$ ksi)			
Sheet and Plate Material .....	Clad 7075-T6 and T651			
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) ..	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)
Ultimate Strength, lbs				
Sheet or plate thickness, in.:				
0.071 .....	1684	...	...	...
0.080 .....	1875	...	...	...
0.090 .....	2077	...	...	...
0.100 .....	2286	3075	...	...
0.125 .....	2620	3750	4811	...
0.160 .....	...	4625	5994 <sup>b</sup>	7350
0.190 .....	...	4650	6993	8554
0.250 .....	...	...	7300	10435
0.312 .....	...	...	...	10500
Fastener shear strength <sup>c</sup> .....	2620	4650	7300	10500
Yield Strength <sup>d</sup> , lbs				
Sheet or plate thickness, in.:				
0.071 .....	1405	...	...	...
0.080 .....	1598	...	...	...
0.090 .....	1717	...	...	...
0.100 .....	1850	2395	...	...
0.125 .....	2232	2790	3327	...
0.160 .....	...	3415	3851	5656
0.190 .....	...	3765	4666	6342
0.250 .....	...	...	5248	7910
0.312 .....	...	...	...	8946
Head height (max.), in. ....	0.049	0.063	0.071	0.081

a Data supplied by Huck Manufacturing Company.

b Yield value is less than 2/3 of the indicated ultimate strength value.

c Fastener shear strength is documented in NAS 1413.

d Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.4.2(b). Static Joint Strength of 100° Flush Shear/Tension Head Alloy Steel Lockbolt Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type . . . . .	NAS 7024-7032 <sup>a,b</sup> ( $F_{su} = 108$ ksi)					
Sheet and Plate Material . . . . .	Clad 7075-T6 and T651					
Fastener Diameter, in. . . . . (Nominal Shank Diameter, in.) .	1/8 (0.125)	5/32 (0.156)	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)
Ultimate Strength, lbs						
Sheet or plate thickness, in.:						
0.040 . . . . .	563	...	...	...	...	...
0.050 . . . . .	846 <sup>d</sup>	<sup>c</sup> 881	1071	...	...	...
0.063 . . . . .	1040 <sup>d</sup>	1341 <sup>d</sup>	1398	...	...	...
0.071 . . . . .	1147	1494 <sup>d</sup>	1743 <sup>d</sup>	2001	...	...
0.080 . . . . .	1231	1645 <sup>d</sup>	2083 <sup>d</sup>	2256	<sup>c</sup> ...	...
0.090 . . . . .	1289	1813	2288 <sup>d</sup>	2823	3071	...
0.100 . . . . .	1325	1921	2493 <sup>d</sup>	3390 <sup>d</sup>	3425	<sup>c</sup> 4225
0.125 . . . . .	...	2070	2878	4140 <sup>d</sup>	5200 <sup>d</sup>	5500 <sup>c</sup>
0.160 . . . . .	...	...	3060	4930	6490	8080 <sup>d</sup>
0.190 . . . . .	...	...	...	5280	7530	8725 <sup>d</sup>
0.250 . . . . .	...	...	...	5300	7870	10010
0.312 . . . . .	...	...	...	...	8220	11270
0.324 . . . . .	...	...	...	...	8280	11340
0.375 . . . . .	...	...	...	...	...	11620
0.433 . . . . .	...	...	...	...	...	11930
Fastener shear strength <sup>e</sup> . . . . .	1325	2070	3060	5300	8280	11930
Yield Strength <sup>f</sup> , lbs						
Sheet or plate thickness, in.:						
0.040 . . . . .	426	...	...	...	...	...
0.050 . . . . .	537	666	804	...	...	...
0.063 . . . . .	682	846	1024	...	...	...
0.071 . . . . .	770	957	1159	1508	...	...
0.080 . . . . .	870	1082	1311	1708	...	...
0.090 . . . . .	981	1221	1430	1931	2392	...
0.100 . . . . .	1092	1360	1649	2152	2669	3177
0.125 . . . . .	...	1705	2071	2709	3363	4010
0.160 . . . . .	...	...	2595	3486	4340	4975
0.190 . . . . .	...	...	...	4050	5170	5760
0.250 . . . . .	...	...	...	4140	6210	7340
0.312 . . . . .	...	...	...	...	7040	8730
0.324 . . . . .	...	...	...	...	7200	8810
0.375 . . . . .	...	...	...	...	...	9160
0.433 . . . . .	...	...	...	...	...	9560
Head height (ref.), in. . . . .	0.042	0.050	0.060	0.077	0.094	0.111

a Data supplied by Huck Manufacturing Company.

b Used with NAS1080K aluminum alloy collar.

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Yield value is less than 2/3 of indicated ultimate strength value.

e Fastener shear strength is documented in NAS1413.

f Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.



**MIL-HDBK-5H****1 December 1998****Table 8.1.4.2(c). Static Joint Strength of 100° Flush Shear Head Ti-6Al-4V Cherrybuck Fasteners in Machine-Countersunk Aluminum Alloy Sheet**

Fastener Type . . . . .	CSR 924 <sup>a</sup> ( $F_{su} = 95$ ksi)		
Sheet Material . . . . .	Clad 7075-T6		
Fastener Diameter, in. . . . . (Nominal Shank Diameter, in.) <sup>b</sup> . .	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.050 . . . . .	941	...	...
0.063 . . . . .	1207	1383	...
0.071 . . . . .	1385	1588	...
0.080 . . . . .	1557	1779	2281
0.090 . . . . .	1775	2050	2594
0.100 . . . . .	1876	2263	2919
0.125 . . . . .	1950	2542	3765
0.160 . . . . .	2007	2660	4387
0.190 . . . . .	...	2694	4525
0.250 . . . . .	...	...	4660
Fastener shear strength <sup>b</sup> . . . . .	2007	2694	4660
Yield Strength <sup>c</sup> , lbs.			
Sheet thickness, in.:			
0.050 . . . . .	659	...	...
0.063 . . . . .	887	985	...
0.071 . . . . .	1022	1148	...
0.080 . . . . .	1116	1325	1625
0.090 . . . . .	1189	1480	1894
0.100 . . . . .	1257	1545	2162
0.125 . . . . .	1393	1733	2619
0.160 . . . . .	1608	1978	2950
0.190 . . . . .	...	2191	3231
0.250 . . . . .	...	...	3794
Head height (ref.), in. . . . .	0.034	0.046	0.060

a Data supplied by Cherry Fasteners.

b Fastener shear strength based on area computed from nominal shank diameter in Table 9.4.1.2(a) and  $F_{su} = 95$  ksi.

c Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.4.2(d). Static Joint Strength of 100° Flush Shear Head Ti-6Al-4V Cherrybuck Fasteners in Machine-Countersunk Aluminum Alloy Sheet**

Fastener Type . . . . .	CSR 924 <sup>a</sup> ( $F_{su} = 95$ ksi)		
Sheet Material . . . . .	Clad 2024-T3		
Fastener Diameter, in. . . . . (Nominal Shank Diameter, in.) <sup>b</sup> . .	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)
Ultimate Strength, lbs.			
Sheet thickness, in.:			
0.050 . . . . .	737	...	...
0.063 . . . . .	1019	1118	...
0.071 . . . . .	1152	1319	...
0.080 . . . . .	1279 <sup>c</sup>	1509	1837
0.090 . . . . .	1419 <sup>c</sup>	1673 <sup>c</sup>	2168
0.100 . . . . .	1560 <sup>c</sup>	1834 <sup>c</sup>	2500
0.125 . . . . .	1898 <sup>c</sup>	2242 <sup>c</sup>	3036 <sup>c</sup>
0.160 . . . . .	2007 <sup>c</sup>	2680 <sup>c</sup>	3786 <sup>c</sup>
0.190 . . . . .	...	2694	4404 <sup>c</sup>
0.250 . . . . .	...	...	4660
Fastener shear strength <sup>d</sup> . . . . .	2007	2694	4660
Yield Strength <sup>e</sup> , lbs.			
Sheet thickness, in.:			
0.050 . . . . .	511	...	...
0.063 . . . . .	712	778	...
0.071 . . . . .	786	922	...
0.080 . . . . .	840	1039	1276
0.090 . . . . .	900	1109	1513
0.100 . . . . .	960	1178	1750
0.125 . . . . .	1110	1352	1979
0.160 . . . . .	1321	1596	2300
0.190 . . . . .	...	1805	2575
0.250 . . . . .	...	...	3125
Head height (ref.), in. . . . .	0.034	0.046	0.060

a Data supplied by Cherry Fasteners.

b Fasteners installed in clearance holes (0.0005 - 0.002) (Ref. Section 8.1.4).

c Yield load is less than 2/3 of indicated ultimate.

d Fastener shear strength based on area computed from nominal shank diameter in Table 9.4.1.2(a) and  $F_{su} = 95$  ksi.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.4.2(e). Static Joint Strength of 100° Flush Shear Head A-286 Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Fastener Type .....	HSR201 <sup>a</sup> ( $F_{su} = 95$ ksi)		
Sheet Material .....	7075-T6		
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) <sup>b</sup> ..	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)
Sheet thickness, in.: 0.050 ..... 0.063 ..... 0.071 ..... 0.080 ..... 0.090 ..... 0.100 ..... 0.125 ..... 0.160 ..... Fastener shear strength <sup>c</sup> .....	Ultimate Strength, lbs.		
	1055	1095	...
	1330	1545	2030
	1500	1740	2285
	1690	1955	2575
	1900	2200	2895
	2007	2445	3220
	...	2694	4025
	...	...	4660
	2007	2694	4660
Sheet thickness, in.: 0.050 ..... 0.063 ..... 0.071 ..... 0.080 ..... 0.090 ..... 0.100 ..... 0.125 ..... 0.160 .....	Yield Strength <sup>d</sup> , lbs.		
	835	870	...
	1055	1225	1605
	1185	1380	1810
	1340	1550	2040
	1505	1745	2295
	1675	1940	2550
	...	2420	3190
	...	...	4180
Head height (nom.), in. ....	0.040	0.046	0.060

a Data supplied by Hi-Shear Corporation.

b Hole Size: Fastener installed in 0.000 interference to 0.005 clearance (Ref. Section 8.1.4).

c Fastener shear strength based on area computed from nominal shank diameter in Table 9.4.1.2(a) and  $F_{su} = 95$  ksi.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.4.2(f). Static Joint Strength of 100° Flush Shear Head Ti-8Mo-8V-2Fe-3Al Rivets in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	HSR101 <sup>a</sup> ( $F_{su} = 95$ ksi)		
Sheet Material .....	7075-T6		
Rivet Diameter, in. .... (Nominal Shank Diameter, in.) <sup>b</sup> ..	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)
Sheet thickness, in.: 0.050 ..... 0.063 ..... 0.071 ..... 0.080 ..... 0.090 ..... 0.100 ..... 0.125 ..... 0.160 ..... Rivet shear strength <sup>c</sup> .....	Ultimate Strength, lbs.		
	1040	1205	...
	1310	1520	2000
	1480	1715	2255
	1665	1930	2540
	1875	2170	2855
	2007	2410	3175
	...	2694	3965
	...	...	4660
	2007	2694	4660
Sheet thickness, in.: 0.050 ..... 0.063 ..... 0.071 ..... 0.080 ..... 0.090 ..... 0.100 ..... 0.125 ..... 0.160 ..... Head height (nom.), in. ....	Yield Strength <sup>d</sup> , lbs.		
	797	921	...
	1005	1165	1530
	1130	1310	1725
	1275	1475	1945
	1435	1660	2185
	1595	1845	2430
	...	2310	3035
	...	...	3885
	0.040	0.046	0.060

a Data supplied by Hi-Shear Corporation.

b Hole Size: Fastener installed in 0.000 interference to 0.005 clearance (Ref. Section 8.1.4).

c Fastener shear strength based on area computed from nominal shank diameter in Table 9.4.1.2(a) and 1/4 = 0.250 and  $F_{su} = 95$  ksi.

d Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.4.2(g). Static Joint Strength of 100° Flush Shear Head Ti-6Al-4V Lockbolt Fasteners in Machine-Countersunk Aluminum Alloy Sheet**

Rivet Type .....	GPL3SC-V Pin <sup>a,b</sup> ( $F_{su} = 95$ ksi), 2SC-3C Collar			
Sheet Material .....	Clad 7075-T6			
Rivet Diameter, in. .... (Nominal Shank Diameter, in) <sup>c</sup> ...	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)
Ultimate Strength, lbs.				
Sheet thickness, in.:				
0.050 .....	1105	...	...	...
0.063 .....	1500	1800	...	...
0.071 .....	1740	2125	<sup>e</sup> 2430	...
0.080 .....	2020	2485	2865	3170
0.090 .....	2200	2885	3365	3780 <sup>e</sup>
0.100 .....	2355	3310	3865	4390
0.125 .....	2694	3945	5135	5880
0.160 .....	...	4660	6245	8005
0.190 .....	...	...	7010	8955
0.250 .....	...	...	7290	10490
Rivet shear strength <sup>d</sup> .....	2694	4660	7290	10490
Yield Strength <sup>f</sup> , lbs.				
Sheet thickness, in.:				
0.050 .....	948	...	...	...
0.063 .....	1160	1585	...	...
0.071 .....	1290	1755	2265	...
0.080 .....	1435	1945	2500	3090
0.090 .....	1600	2160	2765	3415
0.100 .....	1760	2375	3030	3740
0.125 .....	2095	2910	3705	4535
0.160 .....	...	3585	4640	5670
0.190 .....	...	...	5440	6635
0.250 .....	...	...	6270	8230
Head height (ref.), in. ....	0.048	0.063	0.070	0.081

a Data supplied by Huck Manufacturing Company and Voi-Shan Industries.

b Aluminum coated per NAS 4006.

c Hole Size: Fastener installed in 0.005" interference to 0.0005" clearance (Ref. Section 8.1.4).

d Fastener shear strength based on area computed from nominal shank diameter in Table 9.4.1.2(a) and 1/4 = 0.250 and  $F_{su} = 95$  ksi.

e Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

f Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.4.2(h). Static Joint Strength of 100° Flush Shear Head Ti-6Al-4V Lockbolt Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Rivet Type .....	GPL3SC-V Pin <sup>a,b</sup> ( $F_{su} = 95$ ksi), 2SC-3C Collar			
Sheet Material .....	Clad 2024-T3			
Rivet Diameter, in. .... (Nominal Shank Diameter, in.) <sup>c</sup> .	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)
Sheet thickness, in.:	Ultimate Strength, lbs.			
0.050 .....	938	...	...	...
0.063 .....	1255	1535	...	...
0.071 .....	1455	1795	<sup>f</sup> 2085	...
0.080 .....	1680	2085		2740
0.090 .....	1920 <sup>e</sup>	2410	2845	3230 <sup>f</sup>
0.100 .....	2080 <sup>e</sup>	2735	3245	3725
0.125 .....	2460 <sup>e</sup>	3470 <sup>e</sup>	4270	4930
0.160 .....	2694	4175 <sup>e</sup>	5505 <sup>e</sup>	6645
0.190 .....	...	4590 <sup>e</sup>	6260 <sup>e</sup>	7885 <sup>e</sup>
0.250 .....	...	4660	7230	9705 <sup>e</sup>
0.312 .....	...	...	7290	10490
0.375 .....	...	...	...	...
Rivet shear strength <sup>d</sup> .....	2694	4660	7290	10490
Sheet thickness, in.:	Yield Strength <sup>g</sup> , lbs.			
0.050 .....	777	...	...	...
0.063 .....	945	1285	...	...
0.071 .....	1050	1435	1810	...
0.080 .....	1140	1590	2030	2440
0.090 .....	1230	1760	2260	2750
0.100 .....	1320	1910	2475	3065
0.125 .....	1545	2205	2975	3705
0.160 .....	1860	2620	3495	4475
0.190 .....	...	2975	3935	5010
0.250 .....	...	3685	4820	6075
0.312 .....	...	...	5740	7175
Head height (ref.), in. ....	0.048	0.063	0.070	0.081

a Data supplied by Huck Manufacturing Company and Voi-Shan Industries.

b Aluminum coated per NAS 4006.

c Hole size: Fasteners installed in 0.005" interference to 0.0005" clearance (Ref. Section 8.1.4).

d Fastener shear strength based on area computed from nominal shank diameter in Table 9.4.1.2(a) and  $F_{su} = 95$  ksi.

e Yield load is less than 2/3 of indicated ultimate.

f Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

g Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.4.2(i). Static Joint Strength of 100° Flush Shear Head Ti-6Al-4V Lockbolt Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Rivet Type .....	LGPL2SC-V Pin <sup>a,b</sup> ( $F_{su} = 95$ ksi), 3SLC-C Collar			
Sheet Material .....	Clad 7075-T6			
Rivet Diameter, in. .... (Nominal Shank Diameter, in.) <sup>c</sup> .	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)
Sheet thickness, in.:	Ultimate Strength, lbs.			
0.050 .....	1040	...	...	...
0.063 .....	1370	1710	...	...
0.071 .....	1575	1980	<sup>e</sup> 2345	...
0.080 .....	1805	2280	2715	3105
0.090 .....	2060	2615	3130	3620 <sup>e</sup>
0.100 .....	2315	2950	3550	4130
0.125 .....	2590	3790	4605	5375
0.160 .....	2694	4430	6070	7150
0.190 .....	...	4660	6750	8660
0.250 .....	...	...	7290	10154
0.312 .....	...	...	...	10490
Rivet shear strength <sup>d</sup> .....	2694	4660	7290	10490
Sheet thickness, in.:	Yield Strength <sup>f</sup> , lbs.			
0.050 .....	948	...	...	...
0.063 .....	1160	1585	...	...
0.071 .....	1290	1755	2265	...
0.080 .....	1435	1945	2500	3090
0.090 .....	1600	2160	2765	3415
0.100 .....	1760	2375	3030	3740
0.125 .....	2095	2910	3705	4535
0.160 .....	2395	3585	4640	5670
0.190 .....	...	3900	5440	6635
0.250 .....	...	...	6270	8230
0.312 .....	...	...	...	9255
Head height (ref.), in. ....	0.048	0.063	0.070	0.081

a Data supplied by Huck Manufacturing Company and Voi-Shan Industries.

b Aluminum coated per NAS 4006.

c Hole size: Fasteners installed in 0.005" interference to 0.0005" clearance (Ref. Section 8.1.4).

d Fastener shear strength based on area computed from nominal shank diameter in Table 9.4.1.2(a) and  $F_{su} = 95$  ksi.

e Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

f Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.4.2(j). Static Joint Strength of 100° Flush Shear Head Ti-6Al-4V Lockbolt Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Rivet Type .....	LGPL2SC-V Pin <sup>a,b</sup> ( $F_{su} = 95$ ksi), 3SLC-C Collar			
Sheet Material .....	Clad 2024-T3			
Rivet Diameter, in. .... (Nominal Shank Diameter, in.) <sup>c</sup> .	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)
Sheet thickness, in.:	Ultimate Strength, lbs.			
0.050 .....	836	...	...	...
0.063 .....	1180	1350	...	...
0.071 .....	1395	1630	f 1775	...
0.080 .....	1640	1950		2270
0.090 .....	1900 <sup>e</sup>	2300	2595	2800 <sup>f</sup>
0.100 .....	2115 <sup>e</sup>	2650	3035	3335
0.125 .....	2340	3530 <sup>e</sup>	4140	4640
0.160 .....	2655	4000	5645 <sup>e</sup>	6500
0.190 .....	2694	4355	6085	8080 <sup>e</sup>
0.250 .....	...	4660	6965	9180
0.312 .....	...	...	7290	10270
0.375 .....	...	...	...	10490
Rivet shear strength <sup>d</sup> .....	2694	4660	7290	10490
Sheet thickness, in.:	Yield Strength <sup>g</sup> , lbs.			
0.050 .....	733	...	...	...
0.063 .....	901	1220	...	...
0.071 .....	1005	1360	1745	...
0.080 .....	1125	1515	1930	2270
0.090 .....	1250	1685	2140	2635
0.100 .....	1380	1855	2355	2895
0.125 .....	1640	2280	2895	3530
0.160 .....	1910	2795	3640	4430
0.190 .....	2140	3100	4230	5200
0.250 .....	...	3700	4985	6440
0.312 .....	...	...	5760	7375
0.375 .....	...	...	...	8325
Head height (ref.), in. ....	0.048	0.063	0.070	0.081

a Data supplied by Huck Manufacturing Company and Voi-Shan Industries.

b Aluminum coated per NAS 4006.

c Hole size: Fasteners installed in 0.0005" interference to 0.0005" clearance (Ref. Section 8.1.4).

d Fastener shear strength based on area computed from nominal shank diameter in Table 9.4.1.2(a) and  $F_{su} = 95$  ksi.

e Yield load is less than 2/3 of indicated ultimate.

f Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

g Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).



**MIL-HDBK-5H****1 December 1998**

**8.1.5 THREADED FASTENERS** — The strengths shown in the following tables are applicable only when grip lengths and hole tolerances are as recommended by the respective fastener manufacturers. For some fastener systems, permanent set at yield load may be increased if hole sizes greater than those listed in the applicable table are used. This condition may exist even though the test hole size lies within the manufacturer's recommended hole size range (refer to Section 9.4.1.3.3).

The ultimate single shear strength of threaded fasteners at full diameter is shown in Table 8.1.5(a). The ultimate tensile strength of threaded fasteners is shown in Tables 8.1.5(b<sub>1</sub>) and (b<sub>2</sub>). In both tables values shown are a product of the indicated strength and area, with the area based on the following:

*Shear* — Based on basic shank diameter.

*Tension* — Based on the nominal minor diameter of the thread as published in Table 2.21 of Handbook H-28.

For any given threaded fastener the allowable load shall be chosen using an appropriate category corresponding to minimum tensile strength, shear strength, or other requirements of the pertinent procurement specification.

It is recognized that some procurement specifications may provide higher tensile strengths than those reported in Tables 8.1.5(b<sub>1</sub>) and (b<sub>2</sub>), since they may be based on a larger effective area than shown in the table. The values listed herein have been judged acceptable for design, acknowledging that they may be slightly conservative since they are based on the nominal minor diameter area.

Unless otherwise specified, the yield load is defined in Section 9.4.1.3.3 for threaded fasteners as the load at which the joint permanent is set equal to 0.04D, where D is the decimal equivalent of the fastener shank diameter as defined in Table 9.4.1.2(a).

**8.1.5.1 Protruding-Head Threaded Fastener Joints** — It has been shown that protruding shear head (representative configuration is NAS 1982) fastener joints may not develop the full bearing strength of the joint material. Therefore, static allowable loads for protruding shear head fasteners must be established from test data using the criteria specified in Section 9.4.1. For shear joints with protruding tension head fasteners, the load per fastener at which shear or bearing type of failure occurs is separately calculated, and the lower of the two values so determined governs the design. Allowable shear loads may be obtained from Table 8.1.5(a).

The design bearing stresses for various materials at room and other temperatures are given in the properties for each alloy or group of alloys, and are applicable to joints with fasteners in cylindrical holds and where  $t/D \geq 0.18$ . Where  $t/D < 0.18$ , tests to substantiate yield and ultimate bearing strengths must be performed. These bearing stresses are applicable only for design of rigid joints where there is no possibility of relative motion of the parts joined without deformation of such parts.

For convenience, "unit" sheet bearing strengths for threaded fasteners, based on a strength of 100 ksi and nominal fastener diameters, are given in Table 8.1.5.1. The strength for a specific combination of fasteners, sheet thickness, and sheet material is obtained by multiplying the proper "unit" strength by the ratio of material allowable bearing stress (ksi) to 100.

The following interaction formula is applicable to AN3 series bolts under combined shear and tension loading:  $R_s^3 + R_t^2 = 1.0$ , where  $R_s$  and  $R_t$  are ratios of applied load to allowable load in shear and tension, respectively.

**MIL-HDBK-5H****1 December 1998**

**8.1.5.2 Flush-Head Threaded Fastener Joints** — Tables 8.1.5.2(a) through (o) contain joint allowables for various flush-head threaded fastener/sheet material combinations. Unless otherwise noted, the allowable loads for flush-head threaded fasteners were established from test data using the following criteria;

*Ultimate Load* — Average ultimate test load divided by a factor of 1.15, as defined in Chapter 9. This factor is not applicable to shear strength cutoff values which may be either procurement specification shear strength (S value) of the fastener or, if no specification exists, a statistical value determined from test results. It should coincide with shear values from Table 8.1.5(a).

The allowables shown for flush-head threaded fasteners are applicable to joints having  $e/D$  equal to or greater than 2.0.

For machine countersunk joints, the sheet gage specified in the tables is that of the countersunk sheet. When the noncountersunk sheet is thinner than the countersunk sheet, the bearing allowable for the noncountersunk sheet-fastener combination should be computed, compared to the table value, and the lower of the two values selected.

**Table 8.1.5(a). Ultimate Single Shear Strength of Threaded Fasteners**

Shear Stress of Fastener, ksi			35	38	75	90	95	108	125	132	145	156
Fastener Diameter		Basic Shank Area										
in.	Size <sup>a</sup>		Ultimate Single Shear Strength, lbs.									
0.112	#4	0.0098520	345	374	739	887	936	1060	1230	1300	1425	1535
0.125	1/8	0.012272	430	466	920	1105	1165	1325	1530	1620	1775	1910
0.138	#6	0.014957	523	568	1120	1345	1420	1615	1870	1970	2165	2330
0.156	5/32	0.019175	671	729	1435	1725	1820	2070	2395	2530	2780	2990
0.164	#8	0.021124	739	803	1580	1900	2005	2280	2640	2785	3060	3295
0.188	3/16	0.027612	966	1045	2070	2485	2620	2980	3450	3645	4005	4310
0.190	#10	0.028353	992	1075	2125	2550	2690	3060	3540	3740	4110	4420
0.216	#12	0.036644	1280	1390	2745	3295	3480	3955	4580	4840	5315	5720
0.219	7/32	0.037582	1315	1425	2815	3380	3570	4060	4700	4960	5445	5860
0.250	1/4	0.049087	1715	1865	3680	4420	4660	5300	6140	6480	7115	7660
0.312	5/16	0.076699	2680	2915	5750	6900	7290	8280	9590	10100	11100	11950
0.375	3/8	0.11045	3865	4200	8280	9935	10450	11900	13800	14550	16000	17200
0.438	7/16	0.15033	5260	5710	11250	13500	14250	16200	18750	19800	21750	23450
0.500	1/2	0.19635	6870	7460	14700	17650	18650	21200	24500	25900	28450	30600
0.562	9/16	0.24850	8700	9440	18600	22350	23600	26800	31050	32800	36000	38750
0.625	5/8	0.30680	10700	11650	23000	27600	29150	33100	38350	40500	44500	47900
0.750	3/4	0.44179	15450	16750	33100	39750	42000	47700	55200	58300	64000	68900
0.875	7/8	0.60132	21050	22850	45100	54100	57100	64900	75200	79400	87200	93800
1.000	1	0.78540	27450	29850	58900	70700	74600	84800	98200	103500	113500	122500
1.125	1-1/8	0.99402	34750	37750	74600	89500	94400	107000	124000	131000	144000	155000
1.250	1-1/4	1.2272	43000	46600	92000	110000	116500	132500	153000	162000	177500	191000
1.375	1-3/8	1.4849	52000	56400	111000	133500	141000	160000	185500	196000	215000	231500
1.500	1-1/2	1.7671	61800	67100	132500	159000	167500	190500	220500	233000	256000	275500

a Fractional equivalent or screw number.

**Table 8.1.5(b<sub>1</sub>). Ultimate Tensile Strength of Threaded Fasteners**

Tensile Stress of Fastener, ksi			55	62	62.5	125	140	160	180
Fastener Diameter		Nominal Minor Area <sup>d</sup>	MIL-S-7742						
in.	c		Ultimate Tensile Strength, lbs. <sup>a,b</sup>						
0.112	4-40	0.0050896	280	316	318	636	713	814	916
0.138	6-32	0.0076821	423	476	480	960	1075	1225	1380
0.164	8-32	0.012233	673	758	765	1525	1710	1955	2200
0.190	10-32	0.018074	994	1120	1130	2255	2530	2890	3250
0.250	1/4-28	0.033394	1835	2070	2085	4170	4680	5340	6010
0.312	5/16-24	0.053666	2950	3325	3350	6710	7510	8590	9660
0.375	3/8-24	0.082397	4530	5110	5150	10300	11500	13150	14800
0.438	7/16-20	0.11115	6110	6890	6950	13850	15550	17750	20000
0.500	1/2-20	0.15116	8310	9370	9450	18900	21150	24150	27200
0.562	9/16-18	0.19190	10550	11900	11950	23950	26850	30700	34500
0.625	5/8-18	0.24349	13350	15100	15200	30400	34050	38950	43800
0.750	3/4-16	0.35605	19550	22050	22250	44500	49800	57000	64100
0.875	7/8-14	0.48695	26750	30150	30400	60900	68200	77900	87700
1.000	1-12	0.63307	34800	39250	39550	79100	88600	101000	114000
1.125	1-1/8-12	0.82162	45200	50900	51400	102500	115000	131500	147500
1.250	1-1/4-12	1.0347	56900	64200	64700	129000	144500	165500	186000
1.375	1-3/8-12	1.2724	70000	78900	79500	159000	178000	203500	229000
1.500	1-1/2-12	1.5345	84400	95100	95900	191500	214500	245500	276000

a Values shown above heavy line are for 2A threads, all other values are for 3A threads.

b Nuts and fastener heads designed to develop the ultimate tensile strength of the fastener are required to develop the tabulated tension loads.

c Fractional equivalent or number and threads per inch.

d The tension fastener allowables above are based on the nominal minor diameter thread area for MIL-S-7742 threads from Table 2.2.1 of Handbook H-28.

**Table 8.1.5(b<sub>2</sub>). Ultimate Tensile Strength of Threaded Fasteners (Continued)**

Tensile Stress of Fastener, ksi			160	180	220	260
Fastener Diameter		Maximum Minor Area <sup>d</sup>	MIL-S-8879			
in.	c		Ultimate Tensile Strength, lbs. <sup>a,b</sup>			
0.112	4-40	0.0054367	869	979	1195	1410
0.138	6-32	0.0081553	1305	1465	1790	2120
0.164	8-32	0.012848	2055	2310	2825	3340
0.190	10-32	0.018602	2975	3345	4090	4840
0.250	1/4-28	0.034241	5480	6160	7530	8900
0.312	5/16-24	0.054905	8780	9880	12050	14250
0.375	3/8-24	0.083879	13400	15100	18450	21800
0.438	7/16-20	0.11323	18100	20350	24900	29400
0.500	1/2-20	0.15358	24550	27600	33750	39900
0.562	9/16-18	0.19502	31200	35100	42900	50700
0.625	5/8-18	0.24700	39500	44500	54300	64200
0.750	3/4-16	0.36082	57700	64900	79400	93800
0.875	7/8-14	0.49327	78900	88800	108500	128000
1.000	1-12	0.64156	102500	115500	141000	166500
1.125	1-1/8-12	0.83129	133000	149500	182500	216000
1.250	1-1/4-12	1.0456	167000	188000	230000	271500
1.375	1-3/8-12	1.2844	205500	231000	282500	333500
1.500	1-1/2-12	1.5477	247500	278500	340500	402000

a Values are for 3A threads.

b Nuts and fastener heads designed to develop the ultimate tensile strength of the fastener are required to develop the tabulated tension loads.

c Fractional equivalent or number and threads per inch.

d The tension fastener allowables above are based on the maximum minor diameter thread area for MIL-S-8879 threads from Tables II and III of MIL-S-8879.

**Table 8.1.5.1. Unit Bearing Strength of Sheet and Plate in Joints With Threaded Fasteners or Pins;  $F_{br} = 100$  ksi**

Fastener, Diameter, in.	Unit Bearing Strength of Sheet for Fastener Diameter Indicated, lbs. <sup>a</sup>													
	0.156	0.164	0.188	0.190	0.250	0.312	0.375	0.438	0.500	0.562	0.625	0.750	0.875	1.000
Thickness, in.														
0.032 .....	500	525	...	...	...	...	...	...	...	...	...	...	...	...
0.036 .....	563	590	675	684	...	...	...	...	...	...	...	...	...	...
0.040 .....	625	656	750	760	...	...	...	...	...	...	...	...	...	...
0.045 .....	704	738	845	855	...	...	...	...	...	...	...	...	...	...
0.050 .....	781	820	940	950	1250	...	...	...	...	...	...	...	...	...
0.063 .....	985	1033	1180	1197	1575	1969	...	...	...	...	...	...	...	...
0.071 .....	1110	1164	1330	1349	1775	2219	2662	...	...	...	...	...	...	...
0.080 .....	1250	1312	1500	1520	2000	2500	3000	3500	...	...	...	...	...	...
0.090 .....	1407	1476	1690	1710	2250	2812	3375	3938	4500	...	...	...	...	...
0.100 .....	1562	1640	1875	1900	2500	3125	3750	4375	5000	...	...	...	...	...
0.125 .....	1953	2050	2340	2375	3125	3906	4688	5469	6250	7030	7812	...	...	...
0.160 .....	2500	2624	3000	3040	4000	5000	6000	7000	8000	9000	10000	12000	...	...
0.200 .....	3125	3280	3750	3800	5000	6250	7500	8750	10000	11250	12500	15000	17500	20000
0.250 .....	3916	4100	4688	4750	6250	7812	9375	10940	12500	14060	15625	18750	21875	25000
0.312 .....	4867	5117	5866	5928	7800	9734	11700	13670	15600	17530	19500	23400	27300	31200
0.375 .....	5850	6150	7050	7125	9375	11700	14063	16425	18750	21075	23400	28125	32810	37500
0.500 .....	7800	8200	9400	9500	12500	15600	18750	21900	25000	28100	31250	37500	43750	50000
0.625 .....	9750	10250	11750	11875	15625	19500	23440	27375	31250	35125	39062	46875	54690	62500
0.750 .....	11700	12300	14100	14250	18750	23400	28125	32850	37500	42150	46875	56250	65625	75000
0.875 .....	13650	14350	16450	16625	21875	27300	32810	38325	43750	49175	56690	65625	76560	87500
1.000 .....	15600	16400	18800	19000	25000	31200	37600	43800	50000	56200	62500	75000	87500	100000

<sup>a</sup> Bearing strengths shown are based on nominal fastener diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(a<sub>1</sub>). Static Joint Strength of 100° Flush Head Alloy Steel Screws in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type . . . . .	AN509 <sup>b</sup> steel screw ( $F_{su} = 75$ ksi) w/MS20365 or equiv. steel nut				
Sheet and Plate Material . . . . .	Clad 2024-T3 and T351				
Fastener Diameter, in. . . . . (Nominal Shank Diameter, in.) .	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)	1/2 (0.500)
Ultimate Strength <sup>a</sup> , lbs					
Sheet or plate thickness, in.:					
0.080 . . . . .	1576 <sup>c</sup>	...	...	...	...
0.090 . . . . .	1726 <sup>c</sup>	<sup>d</sup> ...	...	...	...
0.100 . . . . .	1877 <sup>c</sup>	2567 <sup>c</sup>	...	...	...
0.125 . . . . .	2126 <sup>c</sup>	3054 <sup>c</sup>	<sup>d</sup> 3922 <sup>c</sup>	4579 <sup>c</sup>	...
0.160 . . . . .	...	3536 <sup>c</sup>	4722 <sup>c</sup>	5878 <sup>c</sup>	<sup>d</sup> ...
0.190 . . . . .	...	3682	5405 <sup>c</sup>	6872 <sup>c</sup>	9408 <sup>c</sup>
0.250 . . . . .	...	...	5750	8280 <sup>c</sup>	<sup>d</sup> 12201 <sup>c</sup>
0.312 . . . . .	...	...	...	8280 <sup>c</sup>	14141 <sup>c</sup>
0.375 . . . . .	...	...	...	...	14730
Fastener shear strength <sup>e</sup> . . . . .	2126	3682	5750	8280	14730
Yield Strength <sup>a,f</sup> , lbs					
Sheet or plate thickness, in.:					
0.080 . . . . .	903	...	...	...	...
0.090 . . . . .	989	...	...	...	...
0.100 . . . . .	1084	1490	...	...	...
0.125 . . . . .	1296	1748	2001	2559	...
0.160 . . . . .	1615	2116	2334	2939	...
0.190 . . . . .	...	2484	2702	3361	6012
0.250 . . . . .	...	...	3404	4197	7306
0.312 . . . . .	...	...	...	5092	8452
0.375 . . . . .	...	...	...	...	9996
Head height (ref.), in. . . . .	0.080	0.106	0.133	0.159	0.213

a Test data from which the yield and ultimate strengths were derived can be found in Reference 8.1.5.2.

b This fastener is no longer manufactured; do not specify for new designs.

c Yield value is less than 2/3 of the indicated ultimate strength value.

d Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

e Fastener shear strength based on area computed from nominal shank diameters in Table 9.4.1.2(a) and  $F_{su} = 75$  ksi.

f Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.5.2(a<sub>2</sub>). Static Joint Strength of 100° Flush Head Alloy Steel Screws in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type .....	AN509 <sup>b</sup> steel screw ( $F_{su} = 75$ ksi) w/MS20365 or equiv. steel nut				
Sheet and Plate Material .....	Clad 7075-T6 and T651				
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) .	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)	1/2 (0.500)
Ultimate Strength <sup>a</sup> , lbs					
Sheet or plate thickness, in.:					
0.080 .....	1632 <sup>c</sup>	...	...	...	...
0.090 .....	1762 <sup>c</sup>	<sup>d</sup> ...	...	...	...
0.100 .....	1892	2723 <sup>c</sup>	...	...	...
0.125 .....	2126	3109 <sup>c</sup>	<sup>d</sup> 4180 <sup>c</sup>	5216 <sup>c</sup>	...
0.160 .....	...	3551 <sup>c</sup>	4858 <sup>c</sup>	6193 <sup>c</sup>	<sup>d</sup> ...
0.190 .....	...	3682	5433 <sup>c</sup>	6996 <sup>c</sup>	...
0.250 .....	...	...	5750	8280 <sup>c</sup>	12421 <sup>c</sup>
0.312 .....	...	...	...	8280	14185 <sup>c</sup>
0.375 .....	...	...	...	...	14730
Fastener shear strength <sup>e</sup> .....	2126	3682	5750	8280	14730
Yield Strength <sup>a,f</sup> , lbs					
Sheet or plate thickness, in.:					
0.080 .....	965	...	...	...	...
0.090 .....	1063	...	...	...	...
0.100 .....	1179	1600	...	...	...
0.125 .....	1462	1895	2098	2699	...
0.160 .....	...	2363	2501	3088	...
0.190 .....	...	2926	3018	3601	...
0.250 .....	...	...	4312	4868	8041
0.312 .....	...	...	...	6624	9437
0.375 .....	...	...	...	...	11686
Head height (ref.), in. ....	0.080	0.106	0.133	0.159	0.213

a Test data from which the yield and ultimate strengths were derived can be found in Reference 8.1.5.2.

b This fastener is no longer manufactured; do not specify for new designs.

c Yield value is less than 2/3 of the indicated ultimate strength value.

d Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

e Fastener shear strength based on area computed from nominal shank diameters in Table 9.4.1.2(a) and  $F_{su} = 75$  ksi.

f Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.



**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(b). Static Joint Strength of 100° Flush Head Stainless Steel (PH13-8Mo-H1000) Fasteners in Machine-Countersunk Titanium Alloy Sheet and Plate**

Fastener Type .....	PBF 11 <sup>a</sup> ( $F_{su} = 125$ ksi)			
Sheet and Plate Material .....	Annealed Ti-6Al-4V			
Rivet Diameter, in. .... (Nominal Shank Diameter, in.) <sup>b</sup> ...	5/32 (0.164)	1/4 (0.250)	3/8 (0.375)	1/2 (0.500)
Ultimate Strength, lbs				
Sheet or plate thickness, in.:				
0.040 .....	1535	...	...	...
0.050 .....	1963	...	...	...
0.063 .....	2528	3656	...	...
0.071 .....	2640	4213	...	...
0.080 .....	...	4813	6820	...
0.090 .....	...	5438	7818	...
0.100 .....	...	6140	8775	11250
0.125 .....	...	...	11264	14575
0.160 .....	...	...	13810	19250
0.190 .....	...	...	...	23200
0.200 .....	...	...	...	24540
Fastener shear strength <sup>d</sup> .....	2640	6140	13810	24540
Yield Strength <sup>e</sup> , lbs				
Sheet or plate thickness, in.:				
0.040 .....	1237	...	...	...
0.050 .....	1543	...	...	...
0.063 .....	1947	2969	...	...
0.071 .....	2049	3350	...	...
0.080 .....	...	3756	5667	...
0.090 .....	...	4219	6370	...
0.100 .....	...	4600	7101	9500
0.125 .....	...	...	8789	11825
0.160 .....	...	...	10645	15025
0.190 .....	...	...	...	17825
0.200 .....	...	...	...	18400
Head height (nom.), in. ....	0.040	0.060	0.077	0.101

a Data supplied by Huck Manufacturing Company and PB Fasteners.

b Fasteners installed in clearance holes (0.0025-0.0030) (Ref. Section 8.1.5).

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Fastener shear strength based on areas computed from indicated nominal shank diameter  $F_{su} = 125$  ksi.

e Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.1.5.2(c). Static Joint Strength of 100° Flush Head Tapered Alloy Steel Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type .....	TL 100 <sup>a</sup> ( $F_{su} = 108$ ksi)					
Sheet and Plate Material .....	Clad 7075-T6 and T651					
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) ..	3/16 (0.1969)	1/4 (0.2585)	5/16 (0.3214)	3/8 (0.3860)	7/16 (0.4490)	1/2 (0.5122)
	Ultimate Strength, lbs					
Sheet or plate thickness, in.:						
0.100 .....	2435	...	...	...	...	...
0.125 .....	2913	3745	4443	...	...	...
0.160 .....	3290	4831	6017	7016	7993	...
0.190 .....	...	5269	7017	8511	9737	10900
0.250 .....	...	5670	8148	11120	13220	14890
0.285 .....	...	...	8760	11360	15000	17240
0.312 .....	...	...	...	11570	15280	19000
0.344 .....	...	...	...	11800	15560	19800
0.375 .....	...	...	...	12030	15820	20110
0.500 .....	...	...	...	12640	16870	21320
Fastener shear strength <sup>b</sup> .....	3290	5670	8760	12640	17100	22250
	Yield Strength <sup>c</sup> , lbs					
Sheet or plate thickness, in.:						
0.100 .....	1960	...	...	...	...	...
0.125 .....	2350	2990	3818	...	...	...
0.160 .....	2840	3550	4650	5650	6703	...
0.190 .....	...	3970	5308	6596	7806	9045
0.250 .....	...	4830	6450	8209	9903	11560
0.285 .....	...	...	7060	9090	10930	12840
0.312 .....	...	...	...	9680	11780	13930
0.344 .....	...	...	...	10010	12710	14930
0.375 .....	...	...	...	10430	13200	16000
0.500 .....	...	...	...	...	15160	18490
Head height (max.), in. ....	0.048	0.063	0.070	0.081	0.100	0.110

a Data supplied by Briles Manufacturing Company.

b Fastener shear strength based on areas computed from indicated nominal shank diameter and  $F_{su} = 108$  ksi.

c Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(d). Static Joint Strength of 100° Flush Head Tapered STA Ti-6Al-4V Fasteners in Machine-Countersunk Aluminum Alloy Sheet**

Fastener Type .....	TLV 10 <sup>a</sup> ( $F_{su} = 95$ ksi)			
Sheet Material .....	Clad 7075-T6			
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) ....	1/8 (0.1437)	5/32 (0.1688)	3/16 (0.1965)	1/4 (0.2583)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.032 .....	488	...	...	...
0.040 .....	610	<sup>b</sup> 713	826	...
0.050 .....	768	896	1050	<sup>b</sup> ...
0.063 .....	967	1145	1312	1730
0.071 .....	1120	1290	1491	1960 <sup>b</sup>
0.080 .....	1260	1470	1690	2223
0.090 .....	1377	1670	1910	2505
0.100 .....	1441	1845	2130	2800
0.125 .....	1530	2010	2580	3540
0.160 .....	1540	2125	2800	4410
0.190 .....	...	...	2880	4750
0.250 .....	...	...	...	4980
Fastener shear strength <sup>c</sup> .....	1540	2125	2880	4980
Yield Strength <sup>d</sup> , lbs				
Sheet thickness, in.:				
0.032 .....	488	...	...	...
0.040 .....	610	713	826	...
0.050 .....	753	890	1050	...
0.063 .....	925	1118	1301	1730
0.071 .....	1035	1240	1467	1960
0.080 .....	1138	1377	1637	2192
0.090 .....	1238	1522	1806	2455
0.100 .....	1321	1639	1976	2711
0.125 .....	1480	1880	2331	3304
0.160 .....	1540	2111	2683	3986
0.190 .....	...	...	2880	4437
0.250 .....	...	...	...	4980
Head height (max.), in. ....	0.033	0.041	0.048	0.063

a Data supplied by Lockheed Georgia Company.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Fastener shear strength based on areas computed from indicated nominal shank diameter and  $F_{su} = 95$  ksi.

d Permanent set at yield load: the greater of 0.012 inch or 4% of fractional diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(e). Static Joint Strength of 70° Flush Head Tapered Ti-6Al-4V Fasteners in Non-Matching Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type .....	HPB-V <sup>a</sup> ( $F_{su} = 95$ ksi)			
Sheet and Plate Material .....	Clad 7075-T6 and T651			
Fastener Diameter ..... (Nominal Shank Diameter, in.) <sup>b</sup> .....	3/16 (0.1976)	1/4 (0.2587)	5/16 (0.3211)	3/8 (0.3850)
Sheet Countersink Angle .....	82°	82°	82°	75°
Ultimate Strength, lbs				
Sheet or plate thickness, in.:				
0.063 .....	1355	...	...	...
0.071 .....	1554	2041	...	...
0.080 .....	1710	2296	...	...
0.090 .....	1847	2583	3207	...
0.100 .....	1984	2864	3567	4269
0.125 .....	2319	3293	4454	5336
0.160 .....	2792	3908	5176	6611
0.190 .....	2913	4444	5836	7396
0.250 .....	...	4993	7155	8968
0.312 .....	...	...	7692	10613
0.375 .....	...	...	...	11058
0.500 .....	...	...	...	11058
Fastener shear strength <sup>c</sup> .....	2913	4993	7692	11058
Yield Strength <sup>d</sup> , lbs				
Sheet or plate thickness, in.:				
0.063 .....	1269	...	...	...
0.071 .....	1429	1874	...	...
0.080 .....	1613	2108	...	...
0.090 .....	1812	2376	2949	...
0.100 .....	1995	2637	3279	3928
0.125 .....	2366	3299	4093	4906
0.160 .....	2718	3975	5217	6285
0.190 .....	2913	4397	5949	7441
0.250 .....	...	4993	6980	9042
0.312 .....	...	...	7692	10257
0.375 .....	...	...	...	11058
0.500 .....	...	...	...	11058
Head height (max.), in. ....	0.057	0.067	0.076	0.086

a Data supplied by PB Fasteners.

b Fasteners installed in interference holes (0.0015-0.0048) (Ref. Section 8.1.5).

c Fastener shear strength based on areas computed from the indicated nominal shank diameter and  $F_{su} = 95$  ksi.

d Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(f). Static Joint Strength of 100° Flush Shear Head Ti-6Al-4V Fasteners in Machine-Countersunk Aluminum Alloy Sheet**

Fastener Type . . . . .	KLBHV Pin ( $F_{su} = 95$ ksi), KFN 600 Nut <sup>a</sup>				
Sheet Material . . . . .	Clad 7075-T6				
Fastener Diameter, in. . . . . (Nominal Shank Diameter, in.) <sup>b</sup>	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)	5/16 (0.3125)	3/8 (0.375)
Ultimate Strength, lbs					
Sheet thickness, in.:					
0.040 . . . . .	748	...	...	...	...
0.050 . . . . .	987	<sup>c</sup> 1112	...	...	...
0.063 . . . . .	1291	1462	1813	...	...
0.071 . . . . .	1428	1679	2100	<sup>c</sup> ...	...
0.080 . . . . .	1571	1888	2438	2902	...
0.090 . . . . .	1722	2058	2794	3322	3867
0.100 . . . . .	1883	2231	3150	3810	4402
0.125 . . . . .	2007	2694	3725	4924	5724
0.160 . . . . .	...	...	4531	4901	7397
0.190 . . . . .	...	...	4660	6790	8452
0.200 . . . . .	...	...	...	7083	8789
0.250 . . . . .	...	...	...	7290	10490
Fastener shear strength <sup>d</sup> . . . . .	2007	2694	4660	7290	10490
Yield Strength <sup>e</sup> , lbs					
Sheet thickness, in.:					
0.040 . . . . .	594	...	...	...	...
0.050 . . . . .	740	859	...	...	...
0.063 . . . . .	931	1079	1419	...	...
0.071 . . . . .	1049	1213	1600	...	...
0.080 . . . . .	1176	1368	1806	2267	...
0.090 . . . . .	1283	1534	2031	2540	3052
0.100 . . . . .	1375	1675	2250	2824	3375
0.125 . . . . .	1606	1942	2813	3517	4219
0.160 . . . . .	...	...	3306	4455	5386
0.190 . . . . .	...	...	3725	4983	6385
0.200 . . . . .	...	...	...	5168	6581
0.250 . . . . .	...	...	...	6038	7636
Head height (ref.), in. . . . .	0.043	0.048	0.063	0.070	0.081

a Data supplied by Kaynar Manufacturing Co., Inc.

b Fasteners installed in interference holes (0.003-0.055) (Ref. 8.1.5).

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Fastener shear strength based on areas computed from indicated nominal shank diameter and  $F_{su} = 95$  ksi.

e Permanent set at yield load: 4% of the nominal diameter (Ref. 9.4.1.3.3).

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(g). Static Joint Strength of 100° Flush Shear AISI 431<sup>a</sup> Hi-Lok Fasteners in Aluminum Alloy Sheet and Plate**

Rivet Type . . . . .	HL 61 Pin ( $F_{su} = 125$ ksi), HL 70 Collar <sup>b</sup>			
Sheet and Plate Material . . . . .	Clad 7075-T6 and T651			
Rivet Diameter . . . . . (Nominal Shank Diameter, in.) . .	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)
Ultimate Strength, lbs				
Sheet or plate thickness, in.:				
0.090 . . . . .	2327	...	...	...
0.100 . . . . .	2430	3740	...	...
0.125 . . . . .	2695	4080	...	...
0.160 . . . . .	3070	4560	6500 <sup>c</sup>	...
0.190 . . . . .	3390	4970	7160	9100
0.250 . . . . .	3544	5800	8320	10230
0.312 . . . . .	...	6140	9590	11390
0.375 . . . . .	...	...	...	12580
0.500 . . . . .	...	...	...	13810
Fastener shear strength <sup>d</sup> . . . . .	3544	6140	9590	13810
Yield Strength <sup>e</sup> , lbs				
Sheet or plate thickness, in.:				
0.090 . . . . .	1840	...	...	...
0.100 . . . . .	1943	2900	...	...
0.125 . . . . .	2195	3240	...	...
0.160 . . . . .	2540	3700	4030	...
0.190 . . . . .	2840	4020	5430	7120
0.250 . . . . .	3110	4870	6590	8500
0.312 . . . . .	...	5350	7580	9700
0.375 . . . . .	...	...	7890	10410
0.500 . . . . .	...	...	...	12070
Head height (max.), in. . . . .	0.049	0.063	0.077	0.051

- a AISI 431 is prohibited from use in Air Force and Navy structure by MIL-STD-1568 and SD-24, respectively, because of its sensitivity to heat treatment. Use of fasteners made of this material in design of military aerospace structures requires the specific approval of the procuring agency.
- b Data supplied by Hi-Shear Corporation.
- c Yield value is less than 2/3 of the indicated ultimate strength value.
- d Fastener shear strength based on areas computed from the indicated nominal shank diameter and  $F_{su} = 125$  ksi.
- e Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(h). Static Joint Strength of 100° Flush Shear Head Alloy Steel Hi-Lok Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type .....	HL 719 Pin ( $F_{su} = 108$ ksi), HL 79 Collar <sup>a</sup>				
Sheet and Plate Material .....	7075-T6 and T651				
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) <sup>b</sup> ...	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)
Ultimate Strength, lbs					
Sheet or plate thickness, in.:					
0.040 .....	734	...	...	...	...
0.050 .....	1044	<sup>c</sup> 1131	...	...	...
0.063 .....	1384	1565	1813	...	...
0.071 .....	1518	1820	2216	...	...
0.080 .....	1668	1998	2594	2916	...
0.090 .....	1764	2193	3015	3532	3724
0.100 .....	1825	2345	3338	4059	4516
0.125 .....	1979	2524	3980	5229	6167
0.160 .....	2195	2774	4350	6347	7928
0.190 .....	...	2989	4634	6702	9087
0.250 .....	...	3062	5200	7512	9985
0.312 .....	...	...	5300	8146	10870
0.375 .....	...	...	...	8280	11760
Fastener shear strength <sup>d</sup> .....	2281	3062	5300	8280	11930
Yield Strength <sup>e</sup> , lbs					
Sheet or plate thickness, in.:					
0.040 .....	690	...	...	...	...
0.050 .....	861	1000	...	...	...
0.063 .....	1086	1261	1664	...	...
0.071 .....	1224	1421	1876	...	...
0.080 .....	1346	1601	2114	2647	...
0.090 .....	1478	1771	2378	2978	3578
0.100 .....	1610	1924	2642	3309	3976
0.125 .....	1845	2308	3210	4136	4970
0.160 .....	2022	2583	3920	5124	6362
0.190 .....	...	2750	4344	5886	7330
0.250 .....	...	3062	4785	6925	9160
0.312 .....	...	...	...	7496	10130
0.375 .....	...	...	...	8158	10820
Head height (nom.), in. ....	0.040	0.046	0.060	0.067	0.077

a Data supplied by Hi-Shear Corporation.

b Fasteners installed in interference holes (0.001-0.002) (Ref. Section 8.1.5).

c Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

d Fastener shear strength based on areas computed from indicated nominal shank diameter and  $F_{su} = 108$  ksi.

e Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(i). Static Joint Strength of 100° Flush Shear Head Ti-6Al-4V Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type . . . . .	HL 11 Pin ( $F_{su} = 95$ ksi), HL 70 Collar <sup>a</sup>			
Sheet and Plate Material . . . . .	Clad 7075-T6 and T651			
Fastener Diameter, in. . . . . (Nominal Shank Diameter, in.) . . . .	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)
Sheet or plate thickness, in.:	Ultimate Strength, lbs			
0.040 . . . . .	734	837	...	...
0.050 . . . . .	941	1083	<sup>b</sup> 1343	...
0.063 . . . . .	1207	1393	1762	<sup>b</sup> 2170
0.071 . . . . .	1385	1588	2012	2463 <sup>b</sup>
0.080 . . . . .	1557	1779	2281	2823
0.090 . . . . .	1775	2050	2594	3193
0.100 . . . . .	1876	2263	2919	3631
0.125 . . . . .	1950	2542	3765	4594
0.160 . . . . .	2007	2660	3970	5890
0.190 . . . . .	...	2694	4165	6105
0.250 . . . . .	...	...	4530	6580
0.312 . . . . .	...	...	4660	7050
0.375 . . . . .	...	...	...	7290
Fastener shear strength <sup>c</sup> . . . . .	2007	2694	4660	7290
Sheet or plate thickness, in.:	Yield Strength <sup>d</sup> , lbs			
0.040 . . . . .	674	794	...	...
0.050 . . . . .	835	982	1325	...
0.063 . . . . .	1038	1230	1655	2141
0.071 . . . . .	1130	1355	1813	2338
0.080 . . . . .	1230	1480	2062	2620
0.090 . . . . .	1342	1625	2250	2880
0.100 . . . . .	1440	1750	2470	3420
0.125 . . . . .	1670	2020	2930	3860
0.160 . . . . .	1891	2360	3480	4620
0.190 . . . . .	...	2560	3840	5150
0.250 . . . . .	...	...	4440	6170
0.312 . . . . .	...	...	4660	6900
0.375 . . . . .	...	...	...	7290
Head height (nom.), in. . . . .	0.040	0.046	0.060	0.067

a Data supplied by Hi-Shear Corporation.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Fastener shear strength based on areas computed from indicated nominal shank diameter and  $F_{su} = 95$  ksi.

d Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.



**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(j). Static Joint Strength of 100° Flush Shear Head Ti-6Al-6V-2Sn Fasteners in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type .....	HL 911 Pin ( $F_{su} = 108$ ksi), HL 70 Collar <sup>a</sup>				
Sheet and Plate Material .....	Clad 7075-T6 and T651				
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) .....	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)
Ultimate Strength, lbs					
Sheet or plate thickness, in.:					
0.040 .....	780	...	...	...	...
0.050 .....	982	<sup>b</sup> 1137	1456	...	...
0.063 .....	1264	1458	1863	<sup>b</sup> 2287	...
0.071 .....	1426	1642	2094	2570	<sup>b</sup> 3096
0.080 .....	1622	1866	2425	2920	3473 <sup>b</sup>
0.090 .....	1740	2105	2750	3339	3965
0.100 .....	1794	2310	3063	3777	4415
0.125 .....	1915	2455	3875	4770	5666
0.160 .....	2098	2660	4219	6181	7339
0.190 .....	2252	2840	4450	6483	8788
0.250 .....	2281	3062	4925	7067	9589
0.312 .....	...	...	5300	7670	10362
0.375 .....	...	...	...	8280	11079
0.500 .....	...	...	...	...	11930
Fastener shear strength <sup>c</sup> .....	2281	3062	5300	8280	11930
Yield Strength <sup>d</sup> , lbs					
Sheet or plate thickness, in.:					
0.040 .....	734	...	...	...	...
0.050 .....	882	1044	1394	...	...
0.063 .....	1076	1300	1750	2190	...
0.071 .....	1184	1406	1938	2472	2995
0.080 .....	1320	1540	2188	2774	3332
0.090 .....	1392	1680	2375	3066	3768
0.100 .....	1480	1810	2569	3358	4120
0.125 .....	1700	2085	3031	4010	5019
0.160 .....	1870	2380	3563	4818	6074
0.190 .....	1978	2530	3937	5354	6749
0.250 .....	2178	2740	4375	6269	8183
0.312 .....	...	...	4687	6883	9209
0.375 .....	...	...	...	7418	9870
0.500 .....	...	...	...	...	11039
Head height (nom.), in. ....	0.040	0.046	0.060	0.067	0.077

a Data supplied by Hi-Shear Corporation.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Fastener shear strength based on areas computed from indicated nominal shank diameter and  $F_{su} = 108$  ksi.

d Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(k). Static Joint Strength of 100° Flush Head Ti-6Al-6V-2Sn or Alloy Steel, Shear Type Fasteners in Machine-Countersunk Aluminum Alloy Sheet**

Fastener Type .....	NAS 4452S and KS 100-FV Pins <sup>a</sup> ( $F_{su} = 108$ ksi), NAS 4445DD Nut			
Sheet Material .....	7075-T6			
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) .....	1/8 (0.138)	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)
Ultimate Strength, lbs				
Sheet thickness, in.:				
0.040 .....	644	...	...	...
0.050 .....	857	976	1065	...
0.063 .....	1131	1305	1458	1750
0.071 .....	1268	1512	1697	2062 <sup>b</sup>
0.080 .....	1428	1703	1964	2406
0.090 .....	1499	1910	2227	2794
0.100 .....	1539	2084	2458	3181
0.125 .....	1615	2200	2848	4063
0.160 .....	...	2281	3036	4900
0.190 .....	...	...	3062	5113
0.250 .....	...	...	...	5300
Fastener shear strength <sup>c</sup> .....	1615	2281	3062	5300
Yield Strength <sup>d</sup> , lbs				
Sheet thickness, in.:				
0.040 .....	609	...	...	...
0.050 .....	766	906	1029	...
0.063 .....	946	1157	1325	1706
0.071 .....	1044	1278	1505	1956
0.080 .....	1152	1412	1668	2219
0.090 .....	1261	1555	1848	2500
0.100 .....	1320	1694	2014	2762
0.125 .....	1444	1904	2397	3350
0.160 .....	...	2106	2661	4100
0.190 .....	...	...	2845	4419
0.250 .....	...	...	...	4925
Head height (max.), in. ....	0.037	0.040	0.049	0.063

a Data supplied by Huck Manufacturing Company.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Fastener shear strength is documented in NAS 4444.

d Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(l). Static Joint Strength of 70° Flush Head Straight Shank Ti-6Al-4V Fasteners in Non-Matching Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type .....	HPT-V <sup>a</sup> ( $F_{su} = 95$ ksi)			
Sheet and Plate Material .....	Clad 7075-T6 and T651			
Fastener Diameter .....	3/16	1/4	5/16	3/8
(Nominal Shank Diameter, in.) <sup>b</sup> .....	(0.193)	(0.255)	(0.3175)	(0.380)
Sheet Countersink Angle .....	82°	82°	82°	75°
Ultimate Strength, lbs				
Sheet or plate thickness, in.:				
0.063 .....	1348	...	...	...
0.071 .....	1546	1970	...	...
0.080 .....	1704	2275	...	...
0.090 .....	1814	2580	3125	...
0.100 .....	1948	2873	3528	4100
0.125 .....	2265	3282	4465	5270
0.160 .....	2700	3868	5171	6642
0.190 .....	2779	4361	5826	7393
0.250 .....	...	4851	7056	8880
0.312 .....	...	...	7521	10396
0.375 .....	...	...	...	10774
Fastener shear strength <sup>c</sup> .....	2779	4851	7521	10774
Yield Strength <sup>d</sup> , lbs				
Sheet or plate thickness, in.:				
0.063 .....	1180	...	...	...
0.071 .....	1378	1651	...	...
0.080 .....	1590	1944	...	...
0.090 .....	1702	2321	2631	...
0.100 .....	1818	2620	3024	3350
0.125 .....	2112	3055	4133	4664
0.160 .....	2496	3601	4848	6209
0.190 .....	2734	4062	5413	6902
0.250 .....	...	4745	6552	8288
0.312 .....	...	7378	9631	...
0.375 .....	...	...	...	10584
Head height (max.), in. ....	0.060	0.070	0.080	0.090

a Data supplied by PB Fasteners.

b Fasteners installed in interference holes (0.0045-0.0055) (Ref. 8.1.5).

c Fastener shear strength based on areas computed from the indicated nominal shank diameter and  $F_{su} = 95$  ksi.

d Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(m). Static Joint Strength of 100° Flush Shear Head STA Ti-6Al-4V Fasteners in Machine-Countersunk Aluminum Alloy Sheet**

Fastener Type .....	NAS 4452V Pin ( $F_{su} = 95$ ksi), NAS 4445D Nut <sup>a</sup>				
Sheet Material .....	Clad 7075-T6				
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) ...	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)	3/8 (0.375)
Ultimate Strength, lbs					
Sheet or plate thickness, in.:					
0.040 .....	766	...	...	...	...
0.050 .....	1092	<sup>b</sup> 1173	...	...	...
0.063 .....	1450	1639	1886	...	...
0.071 .....	1633	1889	2290	<sup>b</sup> ...	...
0.080 .....	1805	2136	2710	3028	...
0.090 .....	1955	2368	3135	3651	...
0.100 .....	2007	2557	3515	4230	4669
0.125 .....	...	2694	4273	5485	6428
0.160 .....	...	...	4660	6776	8426
0.190 .....	...	...	...	7290	9708
0.250 .....	...	...	...	...	10490
Fastener shear strength <sup>c</sup> .....	2007	2694	4660	7290	10490
Yield Strength <sup>d</sup> , lbs					
Sheet thickness, in.:					
0.040 .....	712	...	...	...	...
0.050 .....	891	1034	...	...	...
0.063 .....	1103	1295	1712	...	...
0.071 .....	1223	1445	1932	...	...
0.080 .....	1349	1604	2169	2715	...
0.090 .....	1475	1768	2420	3056	...
0.100 .....	1489	1920	2658	3383	4082
0.125 .....	...	2241	3196	4145	5072
0.160 .....	...	...	3812	5076	6321
0.190 .....	...	...	...	5746	7265
0.250 .....	...	...	...	...	8802
Head height (max.), in. ....	0.040	0.049	0.063	0.077	0.091

a Data supplied by Huck Manufacturing Company.

b Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

c Fastener shear strength is documented in NAS 4444.

d Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(n). Static Joint Strength of Protruding Shear Head Alloy Steel Hi-Lok Fasteners in Aluminum Alloy Sheet**

Fastener Type .....	HL 18 Pin ( $F_{su} = 95$ ksi), HL 70 Collar <sup>a</sup>			
Sheet Material .....	Clad 7075-T6			
Fastener Diameter, in. .... (Nominal Shank Diameter, in.) <sup>b</sup> ...	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)
Sheet thickness, in.:	Ultimate Strength, lbs.			
0.050 .....	1078	...	...	...
0.063 .....	1353	1559	...	...
0.071 .....	1520	1776	...	...
0.080 .....	1718	1957	2593	...
0.090 .....	1890	2224	2937	...
0.100 .....	1930	2473	3250	4050
0.125 .....	2007	2580	4063	5075
0.160 .....	...	2694	4450	6509
0.190 .....	...	...	4620	6880
0.250 .....	...	...	4660	7290
Rivet shear strength <sup>c</sup> .....	2007	2694	4660	7290
Sheet thickness, in.:	Yield Strength <sup>d</sup> , lbs.			
0.050 .....	976	...	...	...
0.063 .....	1251	1426	...	...
0.071 .....	1430	1624	...	...
0.080 .....	1589	1848	2344	...
0.090 .....	1746	2065	2687	...
0.100 .....	1875	2242	3031	3660
0.125 .....	...	2563	3750	4734
0.160 .....	...	...	4406	6051
0.190 .....	...	...	...	6686

a Data supplied by Hi-Shear Corporation.

b Fasteners installed in clearance holes (0.0005-0.0025) (Ref. Section 8.1.5).

c Fastener shear strength based on areas computed from indicated nominal shank diameter and  $F_{su} = 95$  ksi.

d Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998****Table 8.1.5.2(o). Static Joint Strength of 100° Flush Shear Head Alloy Steel Hi-Lok Fasteners in Machine-Countersunk Aluminum Alloy Sheet**

Fastener Type . . . . .	HL 19 Pin ( $F_{su} = 95$ ksi), HL 70 Collar <sup>a</sup>			
Sheet Material . . . . .	Clad 7075-T6			
Fastener Diameter, in. . . . . (Nominal Shank Diameter, in.) <sup>b</sup> . . .	5/32 (0.164)	3/16 (0.190)	1/4 (0.250)	5/16 (0.312)
Sheet thickness, in.:	Ultimate Strength, lbs.			
0.050 . . . . .	968	...	...	...
0.063 . . . . .	1251	1408	...	...
0.071 . . . . .	1400	1606	...	...
0.080 . . . . .	1595	1823	2344	...
0.090 . . . . .	1815	2050	2675	...
0.100 . . . . .	1903	2300	3000	3660
0.125 . . . . .	2005	2570	3781	4685
0.160 . . . . .	...	2694	4420	6051
0.190 . . . . .	...	...	4625	6832
0.250 . . . . .	...	...	4660	7290
Rivet shear strength <sup>c</sup> . . . . .	2007	2694	4660	7290
Sheet thickness, in.:	Yield Strength <sup>d</sup> , lbs.			
0.050 . . . . .	839	...	...	...
0.063 . . . . .	1031	1191	...	...
0.071 . . . . .	1141	1336	...	...
0.080 . . . . .	1279	1480	2013	...
0.090 . . . . .	1416	1632	2219	...
0.100 . . . . .	1540	1805	2420	3143
0.125 . . . . .	1807	2173	3000	3777
0.160 . . . . .	...	2545	3670	4800
0.190 . . . . .	...	...	4144	5514
0.250 . . . . .	...	...	...	6686
Head height (nom.), in. . . . .	0.040	0.046	0.060	0.067

a Data supplied by Hi-Shear Corporation.

b Fasteners installed in clearance holes (0.0005-0.0025) (Ref. Section 8.1.5).

c Fastener shear strength based on areas computed from indicated nominal shank diameter and  $F_{su} = 95$  ksi.

d Permanent set at yield load: the greater of 0.012 inch or 4% of nominal diameter.

**MIL-HDBK-5H****1 December 1998**

**8.1.6 SPECIAL FASTENERS** — Due to the special nature of this classification of fastener, care must be exercised in their application. Consideration should be given to the proposed fastener application and its compatibility with data presented in this section. In particular, test and analysis methods used for fasteners in this section may necessarily be different than those used in preceding sections.

**8.1.6.1 Fastener Sleeves** — Fastener sleeves are precision-formed, tubular elements designed to replace oversize fasteners used in the repair of damaged or enlarged holes.

**8.1.6.1.1 A-286 ACRES Sleeves in 7075-T6 Aluminum Alloy Sheet and Plate** — Analysis of static lap joint data indicates that a single 100° low profile head, A-286 [ACRES Sleeve (part number JK5512C)] installed with titanium or steel Hi-Loks and alloy steel lockbolts (up to 108 ksi  $F_{su}$ ) provided static joint allowable shear loads equivalent to those developed by the above-noted fasteners when tested without sleeves. Fasteners and sleeves were installed to the same comparable hole tolerance and fit condition as fasteners when tested alone. The analysis was restricted to static lap joint data (in accordance with MIL-STD-1312 Test 4) and equivalency to fastener systems other than those listed above is not implied. Other properties such as tensile strength, preload, fatigue strength, and corrosion characteristics should be verified by test data. When using sleeves, knife-edge conditions should be avoided.

**8.1.6.2 Sleeve Bolts** — Tables 8.1.6.2(a) and (b) contain joint allowables for various sleeve bolt/sheet material combinations. Sleeve bolts are made of precision-formed aluminum alloy sleeve elements assembled on standard taper shank bolts. When the assembly is placed in a cylindrical hole and the bolt is drawn into the sleeve, the sleeve expands, thus filling the hole and causing an interference-fit condition.

The allowable loads were established from test data using the following criteria:

*Ultimate Load* — Average ultimate test load divided by a factor of 1.15, as defined in Section 9.4. This factor is not applicable to shear strength cutoff values which are defined by the procurement specification.

*Yield Load* — Average yield test load as defined in Section 9.4.1.3.3 and the load which results in a joint permanent set equal to 0.04D, where D is the hole size.

The allowable loads shown for flush-head fasteners are applicable to joints having  $e/D$  equal to or greater than 2.0.

For machine countersunk joints, the sheet gage specified in the tables herein is that of the countersunk sheet. When the noncountersunk sheet is thinner than the countersunk sheet, the bearing allowable for the noncountersunk sheet-fastener combination should be computed, compared to the table value, and the lower of the two values selected.

**MIL-HDBK-5H****1 December 1998****Table 8.1.6.2(a). Static Joint Strength of 100° Reduced Flush Head, Alloy Steel Pin, Aluminum Alloy Sleeve, Fastener in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type .....	MIL-B-8831/4 <sup>a</sup> ( $F_{su} = 108$ ksi)					
Sheet Material .....	Clad 7075-T6					
Fastener Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b,c</sup>	3/16 (0.2390)	1/4 (0.3032)	5/16 (0.3695)	3/8 (0.4350)	7/16 (0.5022)	1/2 (0.5735)
Sheet thickness, in.:	Ultimate Strength, lbs.					
0.100 .....	2585	...	...	...	...	...
0.125 .....	3205	4100	5035	...	...	...
0.160 .....	3290	5205	6385	7560	8790	...
0.190 .....	...	5670	7535	8925	10360	11900
0.250 .....	...	...	8760	11640	13495	15480
0.312 .....	...	...	...	12395	16195	19180
0.375 .....	...	...	...	12640	16625	21265
0.500 .....	...	...	...	...	17100	22250
Rivet shear strength <sup>d</sup> .....	3290	5670	8760	12640	17100	22250
Sheet thickness, in.:	Yield Strength <sup>e</sup> , lbs.					
0.100 .....	2080	...	...	...	...	...
0.125 .....	2570	3300	4075	...	...	...
0.160 .....	3255	4170	5135	6105	7125	...
0.190 .....	...	4915	6040	7175	8360	9635
0.250 .....	...	...	7855	9310	10825	12450
0.312 .....	...	...	...	11520	13375	15360
0.375 .....	...	...	...	12355	15620	18320
0.500 .....	...	...	...	...	...	21570
Sleeve head height (ref.), in. . .	0.062	0.075	0.082	0.093	0.115	0.120

a Data supplied by P.B. Fasteners.

b Nominal hole diameter based on  $\left( \frac{\text{max. expanded sleeve} - \text{min. hole}}{2} \right) + \text{min. hole}$  using larger expanded diameter from MIL-B-8831/4 dated 23 August 1982.

c Fasteners installed to interference levels of 0.0025-0.008 in.

d Fastener shear strength is documented in NAS 1724 as 108 ksi.

e Permanent set at yield load: 4% of nominal hole diameter (Ref. 9.4.1.3.3).



**MIL-HDBK-5H****1 December 1998****Table 8.1.6.2(b). Static Joint Strength of 100° Reduced Flush Head, Alloy Steel Pin, Aluminum Alloy Sleeve, Fastener in Machine-Countersunk Aluminum Alloy Sheet and Plate**

Fastener Type . . . . .	MIL-B-8831/4 <sup>a</sup> ( $F_{su} = 108$ ksi)					
Sheet Material . . . . .	Clad 2024-T3					
Fastener Diameter, in. . . . . (Nominal Hole Diameter, in.) <sup>b,c</sup>	3/16 (0.2390)	1/4 (0.3032)	5/16 (0.3695)	3/8 (0.4350)	7/16 (0.5022)	1/2 (0.5735)
Sheet thickness, in.:	Ultimate Strength, lbs.					
0.100 . . . . .	2175	...	...	...	...	...
0.125 . . . . .	2720	3450	4205	...	...	...
0.160 . . . . .	3290	4415	5380	6335	7315	...
0.190 . . . . .	...	5240	6390	7525	8685	9920
0.250 . . . . .	...	5480	7945	9895	11425	13050
0.312 . . . . .	...	5655	8165	11085	14260	16285
0.375 . . . . .	...	5670	8385	11345	14845	19070
0.500 . . . . .	...	...	8760	11865	15445	19755
0.625 . . . . .	...	...	...	12385	16045	20440
0.750 . . . . .	...	...	...	12640	16645	21225
0.875 . . . . .	...	...	...	...	17100	21805
1.000 . . . . .	...	...	...	...	...	22250
Rivet shear strength <sup>d</sup> . . . . .	3290	5670	8760	12640	17100	22250
Sheet thickness, in.:	Yield Strength <sup>e</sup> , lbs.					
0.100 . . . . .	1575	...	...	...	...	...
0.125 . . . . .	1880	2505	3200	...	...	...
0.160 . . . . .	2310	3050	3865	4720	5655	...
0.190 . . . . .	...	3515	4435	5395	6430	7595
0.250 . . . . .	...	4450	5570	6735	7980	9360
0.312 . . . . .	...	5055	6745	8115	9580	11185
0.375 . . . . .	...	5560	7460	9525	11205	13040
0.500 . . . . .	...	...	8680	11010	13655	16720
0.625 . . . . .	...	...	...	12385	15315	18625
0.750 . . . . .	...	...	...	12640	16645	20520
0.875 . . . . .	...	...	...	...	17100	21805
1.000 . . . . .	...	...	...	...	...	22250
Sleeve head height (ref.), in. . . .	0.062	0.075	0.082	0.093	0.115	0.120

a Data supplied by P.B. Fasteners.

b Nominal hole diameter based on  $\left( \frac{\text{max. expanded sleeve} - \text{min. hole}}{2} \right) + \text{min. hole}$  using larger expanded diameter from MIL-B-8831/4 dated 23 August 1982.

c Fasteners installed to interference levels of 0.002-0.008 in.

d Fastener shear strength is documented in NAS 1724 as 108 ksi.

e Permanent set at yield load: 4% of nominal hole diameter (Ref. 9.4.1.3.3).

## 8.2 METALLURGICAL JOINTS


In the design of metallurgical joints, the strength of the joining material (for example, weld metal) and the adjacent parent material must be considered. The joint should be analyzed on the basis of its loading, the specified allowable strengths, dimensions and geometry.

**8.2.1 INTRODUCTION AND DEFINITIONS** — The allowable strength for both the adjacent parent metal and the weld metal is given below in the particular section dealing with the method of forming used, and the material being joined. The following subparagraphs define certain joining processes.

*Welding* — Welding consists of joining two or more pieces of metal by applying heat, pressure or both, with or without filler material, to produce a localized union through fusion or recrystallization across the joint interface. Examples of common welding processes include: fusion [inert-gas, shielded-arc welding with tungsten electrode (TIG) and inert-gas shielded metal-arc welding using covered electrodes (MIG)], resistance (spot and seam), and flash. Several terms used in describing various sections of a welded joint are illustrated in Figure 8.2.1.

*Brazing* — Brazing consists of joining metals by the application of heat causing the flow of a thin layer, capillary thickness, of nonferrous filler metal into the space between the pieces. Bonding results from the intimate contact produced by the dissolution of a small amount of base metal in the molten filler metal, without fusion of the base metal.

**8.2.2 WELDED JOINTS** — The weld metal section of a joint should be analyzed on the basis of its loading, specified allowable strength, dimensions and geometry. The effects of the parent metal are to be accounted for as specified herein.



**Figure 8.2.1. Schematic diagram of weld and parent metal.**

**MIL-HDBK-5H****1 December 1998**

**8.2.2.1 Fusion Welding—Arc and Gas** — Section 9.4.2 contains a detailed discussion of one acceptable method of establishing fusion welding allowables. As stated in that section, other methods can be employed as approved by certifying agencies. The following subsections contain specific information for a number of materials.

**8.2.2.1.1 Strength of Fusion Welded Joints of Steel Alloys** — Allowable fusion weld-metal strengths of steel alloys are shown in Table 8.2.2.1.1(a). Design allowable stresses for the weld metal are based on 85 percent of the respective minimum tensile ultimate test values.

For steel joints welded after heat treatment, the allowable strengths near the weld are given in Tables 8.2.2.1.1(b) and (c).

**Table 8.2.2.1.1(a). Strength of Fusion Welded Joints of Steel Alloys**

Material	Heat Treatment Subsequent to Welding	Welding Rod or Electrode	$F_{su}$ , ksi	$F_{tu}$ , ksi
Carbon and alloy steels . .	None . . . . .	AMS 6457 . . . . .	32	51
		AWSA5.1 classes E6010 and E6013 . . . . .	32	51
Alloy steels . . . . .	None . . . . .	AMS 6452 . . . . .	43	72
Alloy steels . . . . .	Stress relieved . . . . .	AWSA5.5 class E10013 . . . . . MIL-E-22200/10, classes MIL- 10018-M1	50	85

**Table 8.2.2.1.1(b). Allowable Ultimate Tensile Stresses Near Fusion Welds in 4130, 4140, or 8630 Steels<sup>a</sup>**

Section Thickness ¼ inch or less	
Type of Joint	Ultimate Tensile Stress, ksi
Tapered joints of 30° or less <sup>b</sup> . . . . .	90
All others . . . . .	80

a Welded after heat treatment or normalized after weld.

b Gussets or plate inserts considered 0° taper with centerline.

**Table 8.2.2.1.1(c). Allowable Bending Modulus of Rupture Near Fusion Weld in 4130, 4140, 4340, or 8630 Steels<sup>a</sup>**

Type of Joint	Bending Modulus of Rupture, ksi
Tapered joints of 30° or less <sup>b</sup> . . . . .	$F_b$ from Figure 2.8.1.1 for $F_{tu} = 90$ ksi
All others . . . . .	0.9 of the values of $F_b$ from Figure 2.8.1.1 for $F_{tu} = 90$ ksi

a Welded after heat treatment or normalized after weld.

b Gussets or plate inserts considered 0° taper with centerline.

**MIL-HDBK-5H****1 December 1998**

For materials heat treated after welding, the allowable strength in the parent metal near a welded joint may equal the allowable strength for the material in the heat treated condition as given in the tables of design mechanical properties of the specific alloys; however, it should be noted that the weld metal allowables are based on 85 percent of these values.

**8.2.2.2 Flash and Pressure Welding**—The ultimate tensile allowable strength and bending allowable modulus of rupture for flash and pressure welds are given in Tables 8.2.2.2(a) and (b). A higher efficiency may be permitted in special cases by the applicable procuring or certifying agency upon approval of the manufacturer's process specification.

**8.2.2.3 Spot and Seam Welding**—Permission to use spot and seam welding on structural parts is governed by the requirements of the procuring or certifying agency. Table 8.2.2.3 gives the recommended allowable edge distance for spot and seam welds.

**8.2.2.3.1 Design Shear Strengths for Spot and Seam Welds in Uncoated Steels and Nickel and Cobalt Alloys**—The design shear strength for spot welds for these materials are given in Tables 8.2.2.3.1(a) and (b). The thickness ratio of the thickest sheet to the thinnest outer sheet in the combination should not exceed 4:1.

**8.2.2.3.1.1 Effects of Spot-Welds on the Parent Metal Strength of 300 Series Stainless Steel**—In applications of spot welding where ribs, intercostals, or doublers are attached to sheet, either at splices or at other joints on the sheet panels, the allowable ultimate strength of the spot-welded stainless steel sheet shall be determined by multiplying the ultimate tensile strength of the sheet (A or S-value) by the appropriate efficiency factors shown in Figures 8.2.2.3.1.1(a) through (c). Efficiencies for gages under 0.012 shall be determined by test.

**8.2.2.3.2 Design Shear Strengths for Spot and Seam Weldings in Aluminum Alloys**—The acceptable aluminum and aluminum alloy combinations for spot and seam welding are given in Table 8.2.2.3.2(a).

Design shear-strength for spot welds in aluminum alloys are given in Tables 8.2.2.3.2(b) and (c). The thickness ratio of the thickest to the thinnest outer sheet in the combination should not exceed 4:1.

Design shear-strength for spot-welded joints, based on tearing of the sheet, is given in Table 8.2.2.3.2(d) for some aluminum alloys, together with the "maximum" pitches that permit attainment of these strengths. Joints having larger pitches fail in the spot welds rather than by tearing of the sheet, and are governed by Tables 8.2.2.3.2(b) and (c). The design shear strengths listed are also applicable to seam welds.

**8.2.2.3.2.1 Effects of Spot Welds on Parent Metal Strength of Aluminum Alloys**—In applications of spot welding other than splices, where ribs, intercostals, or doublers are attached to sheet, the allowable ultimate strength of the spot-welded sheet may be determined by multiplying the ultimate tensile strength of the sheet (A or S-values) by the appropriate efficiency factor shown on Figure 8.2.2.3.2.1. Efficiencies for gages under 0.020 shall be determined by test.

**8.2.2.3.2.2 Fatigue Strength of Spot-Welded Joints in Aluminum Alloys**—The fatigue strength of spot-welded joints in aluminum alloy are given in Figures 8.2.2.3.2.2(a) through 8.2.2.3.2.2(e).

**8.2.2.3.3 Design Shear Strengths for Spot and Seam Welds in Magnesium Alloys**—Design shear-strength for spot welds in magnesium alloys are given in Table 8.2.2.3.3. The thickness ratio of the thickest sheet to the thinnest outer sheet in the combination should not exceed 4:1.

**MIL-HDBK-5H****1 December 1998**

**8.2.2.3.4 Design Shear Strengths for Spot and Seam Welds in Titanium and Titanium Alloys**—Design shear strength for spot welds in titanium and titanium alloys are given in Tables 8.2.2.3.4(a) and (b). The thickness ratio of the thickest sheet to the thinnest outer sheet in the combination should not exceed 4:1.

**Table 8.2.2.2(a). Allowable Ultimate Tensile Stress for Flash Welds in Steel Tubing**

Tubing	Allowable Ultimate Tensile Stress of Welds
Normalized tubing — not heat treated (including normalizing) after welding	$1.0 F_{tu}$ (based on $F_{tu}$ of normalized tubing)
Heat-treated tubing welded after heat treatment . . . . .	$1.0 F_{tu}$ (based on $F_{tu}$ of normalized tubing)
Tubing heat treated (including normalizing) after welding. $F_{tu}$ of unwelded material in heat-treated condition:	
< 100 ksi . . . . .	$0.9 F_{tu}$
100 to 150 ksi . . . . .	$0.6 F_{tu} + 30$
> 150 ksi . . . . .	$0.8 F_{tu}$

**Table 8.2.2.2(b). Allowable Bending Modulus of Rupture for Flash Welds in Steel Tubing**

Tubing	Allowable Bending Modulus of Rupture of Welds ( $F_b$ from Figure 2.8.1.1 using values of $F_{tu}$ listed)
Normalized tubing — not heat treated (including normalizing after welding)	$1.0 F_{tu}$ (based on $F_{tu}$ of normalized tubing)
Heat-treated tubing welded after heat treatment . . . . .	$1.0 F_{tu}$ (based on $F_{tu}$ of normalized tubing)
Tubing heat treated (including normalizing) after welding. $F_{tu}$ of unwelded material in heat-treated condition:	
< 100 ksi . . . . .	$0.9 F_{tu}$
100 to 150 ksi . . . . .	$0.6 F_{tu} + 30$
> 150 ksi . . . . .	$0.8 F_{tu}$

**MIL-HDBK-5H**  
**1 December 1998**


**Table 8.2.2.3. Recommended Minimum Edge Distance and Spacing for Spot-Welded Joints<sup>a</sup>**

Nominal Thickness <sup>b</sup> of Thinner Sheet, inch	Minimum Lap Joint <sup>c,d</sup> Edge Distance, inch	Minimum Spacing <sup>e</sup> , inch
0.016	0.19	0.19
0.020	0.20	0.30
0.025	0.22	0.38
0.032	0.25	0.46
0.040	0.28	0.52
0.050	0.31	0.58
0.063	0.38	0.67
0.071	0.41	0.73
0.080	0.44	0.79
0.090	0.47	0.89
0.100	0.50	1.00
0.125	0.56	1.25
0.160	0.69	1.60

a Reference Aluminum Association and American Welding Society Handbook.

b Intermediate gages will require interpolation between adjacent gages.

c Edge distances are measured materials in contact; this can be to a free edge or to a sheet metal radius where one material bends away from another. Edge distances less than those specified above may be used provided there is no expulsion of weld material or bulging of the edge of the sheet; however, these joints may have less static strength and shorter fatigue life.



d Minimum contacting overlap is twice the minimum edge distance.

e Less than minimum recommended spacing may cause shunting that leads to deterioration of weld strengths and joint life.

**MIL-HDBK-5H****1 December 1998****Table 8.2.2.3.1(a). Spot-Weld Design Shear Strength<sup>a,b</sup> in Thin Sheet and Foil for Uncoated Steels<sup>c</sup> and Nickel and Cobalt Alloys (Welding Specification MIL-W-6858)**

Thickness of Thinnest Outer Sheet, in.	Spots/inch		Material Ultimate Tensile Strength, ksi			
	Standard (Ns) <sup>d</sup>	Range <sup>e,f</sup>	Above 185	150 to 185	90 to 149	Below 90
			Design Shear Strength, pounds per linear inch (Xm)			
0.001	40	1-50	72	64	52	36
0.002	20	1-30	144	128	104	72
0.003	12	1-17	240	208	164	120
0.004	10	1-14	324	280	228	152
0.005	9	1-13	392	340	272	188
0.006	7	1-10	432	380	304	220
0.007	6	1-8	504	440	352	256
0.008	5	1-7	552	488	392	284

a Strength based on 80 percent of minimum values specified in Specification MIL-W-6858.

b The allowable tensile strength of spot-welds is 25 percent of the design shear strength. Higher values may be used, however, if these are substantiated by tests acceptable to the procuring or certifying agency.

c Refers to plain carbon steels containing not more than 0.15 percent carbon, austenitic, heat and corrosion resistant, and precipitation hardening steels. The reduction in strength of spot-welds due to the cumulative effects of time-temperature-stress factors is not greater than the reduction in strength of the parent metal.

d When the number of spots per inch is within 15 percent of the standard spot per inch requirement, the design shear strengths tabulated above shall apply.

e When the number of spots differs from the standard spots per inch by 15 percent or greater, but does not exceed the noted range of spots per inch, applicable design strength shall be determined as noted below:

$$\frac{X_m}{N_s} (K) N_r = X_r$$

where

X<sub>m</sub> = design shear strength in accordance with the above table

N<sub>s</sub> = standard spots per inch in accordance with the above table

N<sub>r</sub> = required spots per inch (production part)

X<sub>r</sub> = actual design shear strength requirement

K = 1.15 when number of spots per inch is reduced more than 15 percent of the standard spacing of the above table

K = 0.90 when number of spots is increased more than 15 percent of the standard spacing but within range of the tabular spacing.

f When the number of spots per inch is above the range indicated in the table, the design shear strength shall remain constant at the value obtained at the top of the range.

**MIL-HDBK-5H****1 December 1998****Table 8.2.2.3.1(b). Spot-Weld Design Shear Strength<sup>a,b</sup> in Panels for Uncoated Steels<sup>c</sup> and Nickel and Cobalt Alloys (Welding Specification MIL-W-6858)**

Material Ultimate Tensile Strength, ksi	Design Shear Strength, pounds per spot			
	Above 185	150 to 185	90 to 149	Below 90
Nominal thickness of thinner sheet, in.:				
0.009.....	160	140	104	80
0.010.....	196	164	128	92
0.012.....	280	220	160	120
0.016.....	384	320	236	172
0.018.....	472	392	272	200
0.020.....	508	424	312	224
0.022.....	584	488	360	264
0.025.....	696	580	424	320
0.028.....	820	684	508	372
0.032.....	1000	836	620	452
0.036.....	1200	1004	736	552
0.040.....	1400	1168	852	652
0.045.....	1680	1436	1028	804
0.050.....	1960	1700	1204	956
0.056.....	2304	2040	1416	1168
0.063.....	2840	2472	1688	1408
0.071.....	3360	2984	2028	1664
0.080.....	3880	3528	2404	1964
0.090.....	4480	4072	2812	2308
0.100.....	5040	4576	3200	2640
0.112.....	5600	5092	3636	3036
0.125.....	6228	5664	4052	3440

a Strength based on 80 percent of minimum values specified in Specification MIL-W-6858.


b The allowable tensile strength of spot-welds is 25 percent of the design shear strength. Higher values may be used, however, if these are substantiated by tests acceptable to the procuring or certifying agency.

c Refers to plain carbon steels containing not more than 0.15 percent carbon and to austenitic heat and corrosion resistant, precipitation hardening steels. The reduction in strength of spot-welds due to the cumulative effects of time-temperature-stress factors is not greater than the reduction in strength of the parent metal.




## MIL-HDBK-5H


1 December 1998



**Figure 8.2.2.3.1.1(a). Efficiency of the parent metal in tension for spot-welded AISI 301-A, and AISI 347-A, and AISI 301-1/4 stainless steel.**



**Figure 8.2.2.3.1.1(b). Efficiency of the parent metal in tension for spot-welding AISI 301-1/2H stainless steel.**

**MIL-HDBK-5H****1 December 1998**

**Figure 8.2.2.3.1.1(c). Efficiency of the parent metal in tension for spot-welded AISI 301-H stainless steel.**

**Table 8.2.2.3.2(a). Acceptable Aluminum and Aluminum Alloy Combination<sup>a</sup> for Spot and Seam Welding**

Specification . . . . .		AMS- QQ-A- 250/1	AMS- 4029 <sup>b</sup>	AMS- QQ-A- 250/3	AMS- QQ-A- 250/4 <sup>b</sup>	AMS- QQ-A- 250/5	AMS- QQ-A- 250/2	AMS- QQ-A- 250/8	AMS- QQ-A- 250/11	AMS- QQ-A- 250/12 <sup>b</sup>	AMS- QQ-A- 250/13 <sup>c</sup>
Material . . . . .		1100	Bare 2014	Clad 2014	Bare 2024	Clad 2024	3003	5052	6061	Bare 7075	Clad 7075
Specification	Material										
AMS-QQ-A-250/1	1100	...	...	...	...	...	...	...	...	...	...
AMS-4029	Bare 2014 <sup>b</sup>	...	*	*	*	...	...	...	...	*	...
AMS-QQ-A-250/3	Clad 2014	...	*	...	*	...	...	...	...	*	...
AMS-QQ-A-250/4	Bare 2024 <sup>b</sup>	...	*	*	*	...	...	...	...	*	...
AMS-QQ-A-250/5	Clad 2024	...	...	...	...	...	...	...	...	...	...
AMS-QQ-A-250/2	3003	...	...	...	...	...	...	...	...	...	...
AMS-QQ-A-250/8	5052	...	...	...	...	...	...	...	...	...	...
AMS-QQ-A-250/11	6061	...	...	...	...	...	...	...	...	...	...
AMS-QQ-A-250/12	Bare 7075 <sup>b</sup>	...	*	*	*	...	...	...	...	*	...
AMS-QQ-A-250/13	Clad 7075 <sup>b</sup>	...	...	...	...	...	...	...	...	...	...

a The various aluminum and aluminum-alloy materials referred to in this table may be spot-welded in any combinations except the combinations indicated by the asterisk(\*) in the table. The combinations indicated by the asterisk (\*) may be spot-welded only with the specific approval of the procuring or certifying agency.

b This table applies to construction of land- and carrier-based aircraft only. The welding of bare, high-strength alloys in construction of seaplanes and amphibians is prohibited unless specifically authorized by the procuring or certifying agency.

c Clad heat-treated and aged 7075 material in thicknesses less than 0.020 inch shall not be welded without specific approval of the procuring or certifying agency.

**MIL-HDBK-5H****1 December 1998****Table 8.2.2.3.2(b). Spot-Weld Design Shear Strength in Thin Sheet and Foil for Bare and Clad Aluminum Alloys<sup>a,b,c</sup> (Welding Specification MIL-W-6858)**

Thickness of Thinnest Outer Sheet, in.	Spots/inch		Material Ultimate Tensile Strength, ksi	
	Standard (Ns) <sup>d</sup>	Range <sup>e,f</sup>	56 and Above	Below 56
			Design Shear Strength, pounds per linear inch (Xm)	
0.001.....	40	1-50	24	16
0.002.....	20	1-30	48	32
0.003.....	12	1-17	80	52
0.004.....	10	1-14	108	72
0.005.....	9	1-13	132	92
0.006.....	7	1-10	148	100
0.007.....	6	1-8	168	112
0.008.....	5	1-7	188	128

a The reduction in strength of spot-welds due to the cumulative effects of time-temperature-stress factors is not greater than the reduction in strength of the parent metal.

b Strength based on 80 percent of minimum values specified in Specification MIL-W-6858.

c The allowable tensile strength of spot-welds is 25 percent of the design shear strength. Higher values may be used, however, if these are substantiated by tests acceptable to the procuring or certifying agency.

d When the number of spots per inch is within 15 percent of the standard spot per inch requirement, the design shear strengths tabulated above shall apply.

e When the number of spots differs from the standard spots per inch by 15 percent or greater, but does not exceed the noted range of spots per inch, applicable design strength shall be determined as noted below:

$$\frac{XM}{Ns} (K) Nr = Xr$$

where

Xm = design shear strength in accordance with the above table

Ns = standard spots per inch in accordance with the above table

Nr = required spots per inch (production part)

Xr = actual design shear strength requirement

K = 1.15 when number of spots per inch is reduced more than 15 percent of the standard spacing of the above table

K = 0.90 when number of spots is increased more than 15 percent of the standard spacing but within range of the tabular spacing.

f When the number of spots per inch is above the range indicated in the table, the design shear strength shall remain constant at the value obtained at the top of the range.

**MIL-HDBK-5H****1 December 1998****Table 8.2.2.3.2(c). Spot-Weld Design Shear Strength in Panels for Bare and Clad Aluminum Alloys<sup>a,b,c</sup> (Welding Specification MIL-W-6858)**

Material Ultimate Tensile Strength, ksi...	Design Shear Strength, pounds per spot			
	56 and Above	35 to 56	19.5 to 34.9	Below 19.5
Nominal thickness of thinner sheet, in.:				
0.010 .....	48	40	...	...
0.012 .....	60	52	24	16
0.016 .....	88	80	56	40
0.018 .....	100	92	68	52
0.020 .....	112	108	80	64
0.022 .....	128	124	96	76
0.025 .....	148	140	116	88
0.028 .....	172	164	140	108
0.032 .....	208	188	168	132
0.036 .....	244	220	204	156
0.040 .....	276	248	240	180
0.045 .....	324	296	280	208
0.050 .....	372	344	320	236
0.056 .....	444	412	380	272
0.063 .....	536	488	456	316
0.071 .....	660	576	516	360
0.080 .....	820	684	612	420
0.090 .....	1004	800	696	476
0.100 .....	1192	936	752	540
0.112 .....	1424	1072	800	588
0.125 .....	1696	1300	840	628
0.140 .....	2020	1538	...	...
0.160 .....	2496	1952	...	...
0.180 .....	2980	2400	...	...
0.190 .....	3228	2592	...	...
0.250 .....	5880	5120	...	...

a The reduction in strength of spot-welds due to the cumulative effects of time-temperature-stress factors is not greater than the reduction in strength of the parent metal.

b Strength based on 80 percent of minimum values specified in Specification MIL-W-6858.

c The allowable tensile strength of spot-welds is 25 percent of the design shear strength. Higher values may be used, however, if these are substantiated by tests acceptable to the procuring or certifying agency.

**Table 8.2.2.3.2(d). Maximum Static Strength of Spot-Welded Joints in Aluminum Alloys and Corresponding Maximum Design Spot-Weld Pitch<sup>a,b</sup>**


Material.....	Single Row Joints						Multiple Row Joints					
	7075-T6 clad		2024-T3 clad		6061-T6		7075-T6 clad		2024-T3 clad		6061-T6	
Thickness of Thinnest Sheet, in.	Strength, lbs/in.	Pitch, in.	Strength, lbs/in.	Pitch, in.	Strength, lbs/in.	Pitch, in.	Strength, lbs/in.	Pitch÷No. of Rows, in.	Strength, lbs/in.	Pitch÷No. of Rows, in.	Strength, lbs/in.	Pitch÷No. of Rows, in.
0.010.....	288	0.167	250	0.192	210	0.190	438	0.110	384	0.125	329	0.122
0.012.....	346	0.173	300	0.200	252	0.206	526	0.114	461	0.130	395	0.132
0.016.....	461	0.191	400	0.220	336	0.238	701	0.126	614	0.143	526	0.152
0.020.....	577	0.194	500	0.224	420	0.257	876	0.128	768	0.146	658	0.164
0.025.....	721	0.205	625	0.237	525	0.267	1095	0.135	960	0.154	822	0.170
0.032.....	923	0.225	800	0.260	672	0.280	1402	0.148	1229	0.169	1053	0.179
0.040.....	1059	0.261	918	0.301	778	0.319	1752	0.158	1536	0.180	1316	0.188
0.050.....	1230	0.302	1067	0.349	910	0.378	2190	0.170	1920	0.194	1645	0.209
0.063.....	1452	0.369	1259	0.426	1082	0.451	2759	0.194	2419	0.222	2073	0.235
0.071.....	1589	0.415	1378	0.479	1187	0.485	3110	0.212	2726	0.242	2336	0.247
0.080.....	1742	0.471	1511	0.543	1306	0.524	3504	0.234	3072	0.267	2632	0.260
0.090.....	1913	0.525	1660	0.605	1438	0.556	3942	0.255	3456	0.290	2961	0.270
0.100.....	2084	0.572	1808	0.659	1580	0.596	4380	0.272	3840	0.310	3290	0.284
0.112.....	2289	0.622	1986	0.717	1728	0.620	4906	0.290	4301	0.331	3685	0.291
0.125.....	2511	0.675	2179	0.788	1900	0.684	5475	0.310	4800	0.353	4112	0.316

a For multiple row joints row spacing is at minimum and same pitch in all rows.

b For pitches greater than those shown, strength is governed by Tables 8.2.2.3.2(b) and (c).

## MIL-HDBK-5H

1 December 1998



**Figure 8.2.2.3.2.1. Efficiency of the parent metal in tension for spot-welded aluminum alloys.**

MIL-HDBK-5H  
1 December 1998




Figure 8.2.2.3.2.2(a). Fatigue strength of spot-welded joints in aluminum alloy sheet. Load Ratio = 0.05 (static failure by tearing sheet).



MIL-HDBK-5H

1 December 1998




Figure 8.2.2.3.2.2(b). Fatigue strength of spot-welded joints in aluminum alloy sheet. Load Ratio = 0.05 (static failure by shear in the spot welds).

MIL-HDBK-5H

1 December 1998




Figure 8.2.2.3.2.2(c). Fatigue strength of triple row spot-welded lap joints in 6061-T6 aluminum alloy sheet. Load Ratio = 0.05.

MIL-HDBK-5H  
1 December 1998




Figure 8.2.2.3.2.2(d). Fatigue strength of spot-welded multiple row joints in aluminum alloy sheet. Load Ratio = 0.05 (static failure by shear in the spot welds).

## MIL-HDBK-5H

1 December 1998




Figure 8.2.2.3.2(e). Fatigue strength of triple row spot-welded lap joints in 6061-T6 aluminum alloy sheet. Load Ratio = 0.05 (static failure by tear in sheets).

**MIL-HDBK-5H****1 December 1998****Table 8.2.2.3.3. Spot-Weld Design Shear Strength in Panels for Magnesium Alloys<sup>a,b,c</sup> (Welding Specification MIL-W-6858)**

Material Ultimate Tensile Strength, ksi...	Design Shear Strength, pounds per spot	
	Greater than 19.5	Less than 19.5
Nominal thickness of thinner sheet, in.:		
0.012 .....	24	16
0.016 .....	56	40
0.018 .....	68	52
0.020 .....	80	64
0.022 .....	96	76
0.025 .....	116	88
0.028 .....	140	108
0.032 .....	168	132
0.036 .....	204	156
0.040 .....	240	180
0.045 .....	280	208
0.050 .....	320	236
0.056 .....	380	272
0.063 .....	456	316
0.071 .....	516	360
0.080 .....	612	420
0.090 .....	696	476
0.100 .....	752	540
0.112 .....	800	588
0.125 .....	840	628

a Strength based on 80 percent of minimum values specified in Specification MIL-W-6858.

b The allowable tensile strength of spot-welds is 25 percent of the design shear strength. Higher values may be used, however, if these are substantiated by tests acceptable to the procuring or certifying agency.

c Magnesium alloys AZ31B and HK31A may be spot-welded in any combination.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 8.2.2.3.4(a). Spot-Weld Design Shear Strength in Thin Sheet and Foils for Titanium and Titanium Alloys<sup>a,b,c</sup> (Welding Specification MIL-W-6858)**

Thickness of Thinnest Outer Sheet, in.	Spots/inch		Materials Ultimate Tensile Strength, ksi			
	Standard (Ns) <sup>d</sup>	Range <sup>e,f</sup>	Above 185	150 to 185	90 to 149	Below 90
			Design Shear Strength, pounds per linear inch (Xm)			
0.001 . . . . .	40	1-50	72	64	52	36
0.002 . . . . .	20	1-30	144	128	104	72
0.003 . . . . .	12	1-17	240	208	164	120
0.004 . . . . .	10	1-14	324	280	228	152
0.005 . . . . .	9	1-13	392	340	272	188
0.006 . . . . .	7	1-10	432	380	304	220
0.007 . . . . .	6	1-8	504	440	352	256
0.008 . . . . .	5	1-7	552	488	392	284

- a The reduction in strength of spot-welds due to the cumulative effects of time-temperature-stress factors is not greater than the reduction in strength of the parent metal.
- b Strength based on 80 percent of minimum values specified in Specification MIL-W-6858.
- c The allowable tensile strength of spot-welds is 25 percent of the design shear strength. Higher values may be used, however, if these are substantiated by tests acceptable to the procuring or certifying agency.
- d When the number of spots per inch is within 15 percent of the standard spot per inch requirement, the design shear strengths tabulated above shall apply.
- e When the number of spots differs from the standard spots per inch by 15 percent or greater, but does not exceed the noted range of spots per inch, applicable design strength shall be determined as noted below:

$$XM/Ns(K)Nr = Xr$$

where

Xm = design shear strength in accordance with the above table

Ns = standard spots per inch in accordance with the above table

Nr = required spots per inch (production part)

Xr = actual design shear strength requirement

K = 1.15 when number of spots per inch is reduced more than 15 percent of the standard spacing of the above table

K = 0.90 when number of spots is increased more than 15 percent of the standard spacing but within range of the tabular spacing.

- f When the number of spots per inch is above the range indicated in the table, the design shear strength shall remain constant at the value obtained at the top of the range.

**MIL-HDBK-5H****1 December 1998****Table 8.2.2.3.4(b). Spot-Weld Design Shear Strength in Panels for Titanium and Titanium Alloy<sup>a,b,c</sup> (Welding Specification MIL-W-6858)**

Material Ultimate Tensile Strength, ksi . . . . .	Design Shear Strength, pounds per spot	
	Above 100	100 and Below
Nominal thickness of thinner sheet, in.:		
0.010 . . . . .	164	128
0.012 . . . . .	220	160
0.016 . . . . .	320	236
0.018 . . . . .	392	272
0.020 . . . . .	424	312
0.022 . . . . .	488	360
0.025 . . . . .	580	424
0.028 . . . . .	684	508
0.032 . . . . .	836	620
0.036 . . . . .	1004	736
0.040 . . . . .	1168	852
0.045 . . . . .	1438	1028
0.050 . . . . .	1702	1204
0.056 . . . . .	2040	1416
0.063 . . . . .	2400	1688
0.071 . . . . .	2702	1914
0.080 . . . . .	3048	2160
0.090 . . . . .	3430	2435
0.100 . . . . .	3810	2702
0.112 . . . . .	4260	3030
0.125 . . . . .	4760	3380

a The reduction in strength of spot-welds due to the cumulative effects of time-temperature-stress factors is not greater than the reduction in strength of the parent metal.

b Strength based on 80 percent of minimum value specified in Specification MIL-W-6858.

c The allowable tensile strength of spot-welds is 25 percent of the design shear strength. Higher values may be used, however, if these are substantiated by tests acceptable to the procuring or certifying agency.

**MIL-HDBK-5H****1 December 1998****8.2.3 BRAZING**

**8.2.3.1 Copper Brazing** — The allowable shear strength for copper brazing of steel alloys shall be 15 ksi, for all conditions of heat treatment. Higher values may be allowed upon approval of the procuring or certifying agency.

The effect of the brazing process on the strength of the parent or base metal of steel alloys shall be considered in the structural design. Where copper furnace brazing is employed, the calculated allowable strength of the base metal which is subjected to the temperatures of the brazing process shall be in accordance with the following:

Material	Allowable Strength
Heat-treated material (including normalized) used in "as-brazed" condition	Mechanical properties of normalized material
Heat-treated material (including normalized) reheat-treated during or after brazing	Mechanical properties corresponding to heat treatment performed

**8.2.3.2 Silver Brazing** — Silver-brazed areas should not be subjected to temperatures exceeding 900°F. Silver brazing alloys are listed in specification QQ-B-654. Deviation from this specification may be allowed upon approval of the procuring or certifying agency.

The allowable shear strength for silver brazing of steel alloys shall be 15 ksi, provided that clearances or gaps between parts to be brazed do not exceed 0.010 in. Deviation from this specified allowable value may be allowed upon approval of the procuring or certifying agency.

The effect of silver brazing on the strength of the parent or base metal is the same as shown for copper brazing in Section 8.2.3.1.

**8.3 BEARINGS, PULLEYS, AND WIRE ROPE**

*Bearings* — Design, strengths, selection criteria, and other data for plain and antifriction bearings are found in AFSC Design Handbook AFSC DH-2-1, Chapters 3 and 6.

*Pulleys* — Pulley strengths and design data are to be utilized in accordance with Specification MIL-P-7034.

*Wire Rope* — Strengths and design data for wire rope are to be selected from the following specifications, whichever is appropriate: MIL-W-83420 or MIL-W-87161.



**MIL-HDBK-5H**

**1 December 1998**

**REFERENCES**

- 8.1(a) Hartman, E. C. and Westcoat, C., "The Shear Strength of Aluminum Alloy Driven Rivets as Affected by Increasing D/t Ratios," U.S. National Advisory Committee for Aeronautics, Technical Note No. 942, 23 pp (July 1944).
- 8.1.2.1 Fugazzi, G. R., "Results of Test Evaluation Program to Develop Design Joint Strength Load Allowable Values for A-286 Solid Rivets Under Room and Elevated Temperature Conditions," Almay Research and Testing Corporation Report No. G8058, 63 pp (November 1964).
- 8.1.2.2 "Report on Flush Riveted Joint Strength," Airworthiness Requirements Committee, A/C Industries Association of America, Inc., Airworthiness Project 12 (Revised May 25, 1948).
- 8.1.5.2 "Report on Flush Screw Joint Strength," Airworthiness Requirements Committee, A/C Industries Association of American, Inc., Airworthiness Project 20 (Revised April 6, 1953).

**MIL-HDBK-5H**  
**1 December 1998**

This page intentionally blank.

**MIL-HDBK-5H**  
**1 December 1998**

## **CHAPTER 9**

### **GUIDELINES FOR THE PRESENTATION OF DATA**

This chapter contains Guidelines for judging adequacy of data, procedures for analyzing data in determining property values for inclusion in previous chapters, and formats for submitting results of analyses to the MIL-HDBK-5 Coordination Group for approval.

The following subindex should be helpful in locating sections of these Guidelines applicable to various properties:

<b>Section</b>	<b>Subject</b>	<b>Page</b>
9.0	Summary	9-2
9.1	General	9-5
9.1.1	Introduction	9-5
9.1.2	Applicability	9-5
9.1.3	Approval Procedures	9-5
9.1.4	Documentation Requirements	9-5
9.1.5	Symbols and Definitions	9-6
9.1.6	Data Requirements for Incorporation of a New Product into MIL-HDBK-5	9-7
9.1.7	Procedure for the Submission of Mechanical Property Data	9-12
9.2	Room-Temperature Design Properties	9-18
9.2.1	Introduction	9-18
9.2.2	Designations and Symbols	9-18
9.2.3	Computational Procedures, General	9-21
9.2.4	Specifying the Population	9-23
9.2.5	Deciding Between Direct and Indirect Computation	9-25
9.2.6	Determining the Appropriate Computation Procedure	9-26
9.2.7	Direct Computation for the Normal Distribution	9-29
9.2.8	Direct Computation for the Weibull Distribution	9-31
9.2.9	Direct Computation for an Unknown Distribution	9-32
9.2.10	Computation of Derived Properties	9-33
9.2.11	Determining Design Allowables by Regression Analysis	9-37
9.2.12	Examples of Computational Procedures	9-41
9.2.13	Modulus of Elasticity and Poisson's Ratio	9-59
9.2.14	Physical Properties	9-59
9.2.15	Presentation of Room-Temperature Design Properties	9-60
9.3	Graphical Mechanical Property Data	9-65
9.3.1	Elevated Temperature Curves	9-65
9.3.2	Typical Stress-Strain, Compression Tangent-Modulus, and Full-Range Stress-Strain Curves	9-73
9.3.3	Biaxial Stress-Strain Behavior	9-90
9.3.4	Fatigue Data Analysis	9-92
9.3.5	Fatigue-Crack-Propagation Data	9-147
9.3.6	Creep and Creep-Rupture Data	9-150
9.4	Properties of Joints and Structures	9-169
9.4.1	Mechanically Fastened Joints	9-169
9.4.2	Fusion-Welded Joints	9-195
9.5	Miscellaneous Properties	9-206
9.5.1	Fracture Toughness	9-206
9.6	Statistical Procedures and Tables	9-213
9.6.1	Goodness-of-Fit Tests	9-213
9.6.2	Tests of Significance	9-217
9.6.3	Data-Regression Techniques	9-223
9.6.4	Tables	9-234
9.6.5	Estimation Procedures for the Weibull Distribution	9-257
References		9-260

**MIL-HDBK-5H**  
**1 December 1998**

## **9.0 SUMMARY**

The objective of this summary is to provide a global overview of Chapter 9 without defining specific statistical details. This overview will be most helpful to those unfamiliar with the statistical procedures used in MIL-HDBK-5 and to those who would like to learn more about the philosophy behind the MIL-HDBK-5 guidelines.

Chapter 9 is the “rule book” for MIL-HDBK-5. Since 1966, these guidelines have described statistical procedures used to calculate mechanical properties for alloys included in the Handbook. Recommended changes in the guidelines are reviewed first by the Guidelines and Emerging Materials Task Group (GEMTG) and later approved by the entire coordination committee. Recommended changes in statistical procedures within the guidelines are evaluated first by the Statistics Working Group (SWG), which supports the GEMTG. Similarly, recommended changes in fastener analysis procedures are examined by the Fastener Task Group (FTG) before approval by the coordination committee.

Chapter 9 is divided into 6 subchapters which cover the analysis methods used to define room and elevated temperature properties. The room temperature mechanical properties are tensile, compression, bearing, shear, fatigue, fracture toughness, elongation and elastic modulus. The elevated temperature properties are the same, except that creep and stress rupture properties are added to the list. Analysis procedures for fatigue, fatigue crack growth and mechanically fastened joints are also covered since these data are commonly used in aircraft design. The presentation of these data varies depending upon the data type. For instance, the room temperature mechanical properties (tensile, compression, bearing, shear, elongation and elastic modulus) are provided in a tabular format, while the fatigue, elevated temperature properties, and typical stress-strain curves are presented in graphical format.

Before an alloy can be considered for inclusion in MIL-HDBK-5, it must be covered by a commercial or government specification. There are two main reasons for this: (1) the alloy, and its method of manufacture, must be “reduced to standard practice” to increase confidence that the material, if obtained from different suppliers, will still demonstrate similar mechanical properties, and (2) specification minimum properties are included in MIL-HDBK-5 tables as design properties in situations where there are insufficient data to determine statistically based material design values.

The majority, by far, of the data in MIL-HDBK-5 are room temperature design properties: including tensile ( $F_{tu}$ ,  $F_{ty}$ ), shear ( $F_{su}$ ), compression ( $F_{cy}$ ), bearing strengths ( $F_{bru}$  and  $F_{bry}$ ), elongation and elastic modulus. Room temperature design properties are the primary focus in the Handbook because most aircraft, commercial and military, typically operate at near-ambient temperatures and because most material specifications include only room temperature property requirements.

Design minimum mechanical properties tabulated in MIL-HDBK-5 are calculated either by “direct” or “indirect” statistical procedures. The minimum sample size required for the direct computation of  $T_{99}$  and  $T_{90}$  values (from which A and B-basis design properties are established) is 100. These 100 observations must include data from at least 10 heats and lots (as defined in the next paragraph). A  $T_{99}$  value is a statistically computed, one-sided lower tolerance limit, representing a 95 percent confidence lower limit on the first percentile of the distribution. Similarly, a  $T_{90}$  value is a statistically computed, one-sided lower tolerance limit, representing a 95 percent lower confidence limit on the tenth percentile of the distribution. If the sample cannot be described by a normal or Weibull distribution, the  $T_{99}$  and  $T_{90}$  values must be computed by nonparametric (distribution free) means, which can only be done if there are at least 299 observations. In most cases, only minimum tensile ultimate and yield strength values are determined by the direct method.  $T_{90}$  values are not computed if there are insufficient data to compute  $T_{99}$  values, even though a much smaller sample size is required to compute nonparametric  $T_{90}$  values. This is because the general consensus within the MIL-HDBK-5 committee has been that a large number of observations (in the realm of 100) are needed

**MIL-HDBK-5H**  
**1 December 1998**

from a large number of heats and lots (e.g. 10) for a particular material to properly characterize the variability in strength of that product.

A lot represents all of the material of a specific chemical composition, heat treat condition or temper, and product form that has passed through all processing operations at the same time. Multiple lots can be obtained from a single heat. A heat of material, in the case of batch melting, is all of the material that is cast at the same time from the same furnace and is identified with the same heat number. In the case of continuous melting, a single heat of material is generally poured without interruption. The exception is for ingot metallurgy wrought aluminum products, where a single heat is commonly cast in sequential aluminum ingots, which are melted from a single furnace charge and poured in one or more drops without changes in the processing parameters (see Table 9.1.6.2).

Minimum compression, bearing, and shear strengths are typically determined through the indirect method. This is done to reduce cost, because as few as 10 data points (from 2 heats and 10 lots) can be used, in combination with “paired” direct properties to compute a design minimum value. In this indirect method, the compression, bearing, and shear strengths are paired with tensile values determined in the same region of the product to produce a ratio. Statistical analyses of these ratios are conducted to obtain lower bound estimates of the relationship between the primary property and the ratioed property. These ratios are then multiplied with the appropriate  $F_{tu}$  or  $F_{ty}$  in the Handbook to obtain the  $F_{su}$ ,  $F_{cy}$ ,  $F_{bru}$ ,  $F_{bry}$  values for shear, compression, and bearing (ultimate and yield), respectively.

Many mechanical property tables in the Handbook include data for specific grain directions and thickness ranges. This is done to better represent anisotropic materials, such as wrought products, that often display variations in mechanical properties as a function of grain direction and/or product thickness. Therefore, it is common practice to test for variability in mechanical properties as a function of product thickness. This is done through the use of regression analysis for both direct and indirect properties. If a regression is found to be significant, properties may be computed separately (without regression) for reduced thickness ranges.

To compliment the mechanical property tables, the Handbook also contains typical stress-strain curves. These curves are included to illustrate each material's yield behavior and to graphically display differences in yield behavior for different grain directions, tempers, etc. These curves are identified as typical because they are based upon only a few test points. Typical curves are shown for both tension and compression and are extended to just beyond the 0.2 percent yield stress. Each typical curve also contains a shape factor called the Ramberg-Osgood number ( $n$ ). These numbers can be used in conjunction with a material's elastic modulus to empirically develop a stress-strain curve. Typical tensile full-range stress-strain curves are also provided that illustrate deformation behavior from the proportional limit to fracture. In addition, compression tangent-modulus curves are provided to describe compression instability.

Effect of temperature and thermal exposure curves are included throughout the Handbook. For tensile properties, the curves are presented as a percentage of the room temperature design value. For these curves, there is a minimum data requirement and statistical procedures have been established to construct the curves. The creep rupture plots are shown as typical isothermal curves of stress versus time. The physical properties are shown as a function of temperature for each property, i.e., specific heat, thermal conductivity, etc. Physical properties are reported as average actual values, not a percentage of a room temperature value.

In addition to the mechanical properties, statistically based S/N fatigue curves are provided in the Handbook, since many airframe structures experience dynamic loading conditions. The statistical procedures are fairly rigorous. For example, the procedure describes how to treat outliers and run-outs (discontinued tests), and which models to use to best-fit a specific set of data. Each fatigue figure includes relevant

**MIL-HDBK-5H**  
**1 December 1998**

information such as  $K_t$ , R value, material properties, sample size and equivalent stress equation. Each figure should be closely examined by the user to properly identify the fatigue curves required for a particular design.

Design properties for mechanical fasteners and mechanically fastened elements are also included in MIL-HDBK-5. A unique analysis procedure has been developed for mechanical fasteners because fasteners generally do not develop the full bearing strength of materials in which they are installed. Realistic joint allowables are determined from test data using the statistical analysis procedures described in Chapter 9. There are four different types of fasteners for which design allowables must be determined, as described in Section 4.

The last section in the Handbook (Section 6) provides a detailed description of statistical procedures used in Chapter 9 for the analysis of data. Most of these procedures are backed up with examples and appropriate statistical tables.

**MIL-HDBK-5H**  
**1 December 1998**

## **9.1 GENERAL**

This section of the Guidelines covers general information. Information specific to individual properties can be found in pertinent sections.

**9.1.1 INTRODUCTION** — Design properties in MIL-HDBK-5 are used in the design of aerospace structures and elements. Thus, it is exceedingly important that the values presented in MIL-HDBK-5 reflect as accurately as possible the actual properties of the products covered.

Throughout the Guidelines, many types of statistical computations are referenced. Since these may not be familiar to all who may be analyzing data in the preparation of MIL-HDBK-5 proposals, a detailed description of each operation is required. To present the detailed description in the individual sections, however, would unnecessarily complicate the orderly presentation of the overall computational procedures. Therefore, the detailed description of the statistical techniques have been covered in Section 9.6.

**9.1.2 APPLICABILITY** — Minimum data requirements and analytical procedures defined in these Guidelines for establishment of MIL-HDBK-5 design properties and elevated temperature curves for these properties should be used to obtain approval of such values or curves when proposed to the MIL-HDBK-5 Coordination Group or a certifying agency. However, the minimum data requirements and analytical procedures are not mandatory; to the extent of precluding use of other analytical procedures which can be substantiated. Any exceptions or deviations must be reported when requesting approval of these values or curves by the Coordination Group or certifying agency.

**9.1.3 APPROVAL PROCEDURES** — The MIL-HDBK-5 Coordination Group (a voluntary, joint Government-Industry activity) meets twice yearly. At each meeting, this group acts upon proposed changes or additions to the document submitted in writing in advance of the meeting. The agenda is normally mailed to attendees four weeks prior to the meeting date, and the minutes four weeks following the meeting. Attachments for either the agenda or the minutes should be delivered to the Secretariat well in advance of the mailing date.

Attachments containing proposed changes or additions to the document shall include specific notations of changes or additions to be made; adequate documentation of supporting data; analytical procedures used (see Section 9.1.4); discussion of analysis of data; and a listing of exceptions or deviations from the requirements of these Guidelines.

Approval procedures for establishment of MIL-HDBK-5 equivalent design values are defined by the individual certifying agency.

**9.1.4 DOCUMENTATION REQUIREMENTS** — The purpose of adequate documentation of proposals submitted to the MIL-HDBK-5 Coordination Group is to permit an independent evaluation of proposals by each interested attendee and to provide a historical record of actions of the Coordination Group. For this reason, both supporting data and a description of analytical procedures employed must be made available to attendees, either as an integral portion of an attachment to the agenda or minutes, or by reference to other documents that may reasonably be expected to be in the possession of MIL-HDBK-5 Meeting attendees. A specific example of the latter would be certain reports of Government-sponsored research or material evaluations for which distribution included the MIL-HDBK-5 attendance list. In some cases involving large quantities of supporting data, it may suffice (at the discretion of the Coordination Group) to furnish a single copy of these data to the Secretariat, from whom they would be available to interested attendees.

**MIL-HDBK-5H****1 December 1998****9.1.5 SYMBOLS AND DEFINITIONS** (also see Sections 9.2.2, 9.3.4.2, 9.3.6.2, 9.4.1.2, 9.5.1.2, and 9.6) —

$\alpha$	—	Significance level; probability (risk) of erroneously rejecting the null hypothesis (see Section 9.6.2).
$\alpha_{99,90}$	—	Shape parameter estimates for a $T_{99}$ or $T_{90}$ tolerance bound based on an assumed three-parameter Weibull distribution.
$\alpha_{50}$	—	Shape parameter estimate for the Anderson-Darling goodness-of-fit test based on an assumed three-parameter Weibull distribution.
A	—	A-basis for mechanical property (see Section 9.2.2.1).
AD	—	Anderson-Darling test statistic, computed in goodness-of-fit tests for normality or Weibullness.
$\beta_{99,90}$	—	Scale parameter estimate for a $T_{99}$ or $T_{90}$ tolerance bound based on an assumed three-parameter Weibull distribution.
$\beta_{50}$	—	Scale parameter estimate for the Anderson-Darling goodness-of-fit test based on an assumed three-parameter Weibull distribution.
B	—	B-basis for mechanical property (see Section 9.2.2.1).
df	—	Degrees of freedom.
F	—	The ratio of two sample variances.
heat	—	All material identifiable to a single molten metal source. (All material from a heat is considered to have the same composition. A heat may yield one or more ingots. A heat may be divided into several lots by subsequent processing.)
$k_{99,90}$	—	The $T_{99}$ or $T_{90}$ tolerance limit factor for the normal distribution, based on 95 percent confidence and a sample of size n.
log	—	Base 10 logarithm.
lot	—	All material from a heat or single molten metal source of the same product type having the same thickness or configuration, and fabricated as a unit under the same conditions. If the material is heat treated, a lot is the above material processed through the required heat-treating operations as a unit.
ln	—	Natural (base e) logarithm.
n	—	Number of individual measurements or pairs of measurements; Ramberg-Osgood parameter.
r	—	Ratio of two paired measurements; rank of test point within a sample.
$\bar{r}$	—	Average ratio of paired measurements.
S	—	S-basis for mechanical property values (see Section 9.2.2.1).
s	—	Estimated population standard deviation.
$\tau_{99,90}$	—	Threshold estimates for a $T_{99}$ or $T_{90}$ tolerance bound based on an assumed three-parameter Weibull distribution.
$\tau_{50}$	—	Threshold estimate for the Anderson-Darling goodness-of-fit test based on an assumed three-parameter Weibull distribution.
t	—	Tolerance factor for the “t” distribution with the specified “confidence” and appropriate degrees of freedom.
$T_{90}$	—	Statistically based lower tolerance bound for a mechanical property such that at least 90 percent of the population is expected to exceed $T_{90}$ with 95 percent confidence.
$T_{99}$	—	Statistically based lower tolerance bound for a mechanical property such that at least 99 percent of the population is expected to exceed $T_{99}$ with 95 percent confidence.
$V_{99,90}$	—	The $T_{99}$ or $T_{90}$ tolerance limit factor for the three-parameter Weibull distribution, based on 95 percent confidence, a sample of size n, and a specified degree of upper tail censoring.
$X_i$	—	Value of an individual measurement.
$\bar{X}$	—	Average value of individual measurements.
$\Sigma$	—	The sum of.
'	—	Value determined by regression analysis.



**MIL-HDBK-5H**  
**1 December 1998**

**9.1.6 DATA REQUIREMENTS FOR INCORPORATION OF A NEW PRODUCT INTO MIL-HDBK-5** — This section specifies requirements for the incorporation of a new product into MIL-HDBK-5 on an S-basis (see Section 9.2.2.1 for definition). These requirements are applicable to each alloy, product form, and heat treat condition or temper. Sections 9.1.6.2 through 9.1.6.7 delineate requirements for a test program for the determination of mechanical property data suitable for computation of derived properties (see Section 9.2.10). A test matrix, based on these requirements, is shown in Table 9.1.6.

**9.1.6.1 Material Specification** — To be considered for inclusion in MIL-HDBK-5, a product must be covered by an industry specification (AMS specification issued by SAE Aerospace Materials Division or an ASTM standard published by the American Society for Testing and Materials), or a government specification (Military or Federal). If a public specification for the product is not available, action should be initiated to prepare a draft specification. Standard manufacturing procedures shall have been established for the fabrication and processing of production material before a draft specification is prepared. The draft specification shall describe a product which is commercially available on a production basis. An AMS draft specification should be submitted to the SAE Aerospace Materials Division and an ASTM standard should be transmitted to the American Society for Testing and Materials for publication. See Section 9.1.6.8 for requirements to substantiate the S-basis properties.

**9.1.6.2 Material** — The product used for the determination of mechanical properties suitable for use in the determination of minimum design (derived) values for incorporation into MIL-HDBK-5 shall be production material. The material shall have been produced using production facilities and standard fabrication and processing procedures. If a test program to determine requisite mechanical properties is initiated before a public specification describing this product is available, precautionary measures shall be taken to ensure that the product supplied for the test program conforms to the specification, when published, and represents production material.

Ten lots of material from at least two production heats, casts or melts for each product form and heat treat condition shall be tested to determine required mechanical properties. See Table 9.1.6.2 for definitions of heat, cast, and melt. A lot is defined as all material of a specific chemical composition, heat treat condition or temper, and product form which has been processed at the same time through all processing operations. Different sizes and configurations from a heat cast or melt shall be considered different lots. For a single lot of material, only one heat treat lot may be used to meet the ten-lot requirement. Thicknesses of the 10 lots to be tested shall span the thickness range of the product form covered by the material specification (or for the thickness range for which design values are to be established).

Dimensionally discrepant castings or special test configurations may be used for the development of derived properties with prior approval by the MIL-HDBK-5 Coordination Group, providing these castings meet the requirements of the applicable material specification. Design values for separately cast test specimens shall not be presented in MIL-HDBK-5.

**9.1.6.3 Test Specimens** — Mechanical property ratios are utilized in the analysis of data to determine minimum design values. Tensile yield in other than primary test direction, compressive yield, and bearing yield strengths are paired with the tensile yield strength in the primary test direction for each lot. Tensile ultimate in other than the primary test direction, shear ultimate, and bearing ultimate strengths are paired with the tensile ultimate strength in the primary test direction. See Table 9.2.10 for the primary testing direction for various products. Therefore, it is imperative that these test specimens be taken from the same sheet, plate, bar, extrusion, forging, or casting. Test specimens shall be located in close proximity. If coupons or specimens are machined prior to heat treatment, all specimens representing a lot shall be heat treated simultaneously in the same heat treat load through all heat treating operations. This procedure is necessary to provide precise mechanical property relationships (ratios).

**Table 9.1.6. Test Matrix to Provide Required Mechanical Property Data for Determination of Design Values for Derived Properties (on S-Basis)**

Lot Letter <sup>a,b,c</sup>	Test Specimen Requirements												
	TUS & TYS <sup>d,e,f,g</sup>			CYS <sup>d,e,g</sup>			SUS <sup>k</sup>			BUS & BYS <sup>j</sup> , e/D = 1.5		BUS & BYS <sup>j</sup> , e/D = 2.0	
	L	LT	ST <sup>h</sup>	L	LT	ST <sup>h</sup>	L	LT	ST <sup>h</sup>	L	LT <sup>h</sup>	L	LT <sup>h</sup>
A	2 <sup>i</sup>	2	2	2	2	2	2	2	2	2	2	2	2
B	2	2	2	2	2	2	2	2	2	2	2	2	2
C	2	2	2	2	2	2	2	2	2	2	2	2	2
D	2	2	2	2	2	2	2	2	2	2	2	2	2
E	2	2	2	2	2	2	2	2	2	2	2	2	2
F	2	2	2	2	2	2	2	2	2	2	2	2	2
G	2	2	2	2	2	2	2	2	2	2	2	2	2
H	2	2	2	2	2	2	2	2	2	2	2	2	2
I	2	2	2	2	2	2	2	2	2	2	2	2	2
J	2	2	2	2	2	2	2	2	2	2	2	2	2

a Ten lots, representing at least two production heats, or casts or melts, are required.

b Thicknesses of ten lots shall span thickness range of product form covered by material specification.

c For a single lot, multiple heat treat lots shall not be used to meet 10-lot requirement.

d If precision modulus values for  $E$  and  $E_c$  are not available, precision modulus tests should be conducted on three lots.

e Stress-strain data from at least three lots shall be submitted.

f Full-range tensile stress-strain data from at least one lot shall be submitted, but data from three or more lots are preferred.

g Products should also be tested in the 45° grain direction that are anticipated to have significantly different properties in this direction than the standard grain directions; these include materials such as aluminum-lithium alloys and Aramid fiber reinforced sheet laminate.

h As applicable, depending on product form and size.

i At least two specimens are recommended; however, a single test is acceptable if retesting can be accomplished to replace invalid tests.

j It is recommended that minimum sheet and strip selected for bearing tests comply with the t/D ratio (0.25-0.50) specified in ASTM E238. For failure modes, see Figure 9.4.1.7.2.

k It is recommended that sheet and strip  $\geq 0.050$  inch in thickness be selected for shear tests conducted according to ASTM B831. Shear testing of sheet  $< 0.050$  inch in thickness may result in invalid results due to buckling around the pin hole areas during testing.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.1.6.2. Definitions of Heat, Melt, and Cast**

Material	Heat, Melt, or Cast
Ingot Metallurgy Wrought Products Excluding Aluminum Alloys	A heat is material which, in the case of batch melting, is cast at the same time from the same furnace and is identified with the same heat number; or, in the case of continuous melting, is poured without interruption.
Ingot Metallurgy Wrought Aluminum Alloy Products	A cast consists of the sequential aluminum ingots which are melted from a single furnace charge and poured in one or more drops without changes in the processing parameters. (The cast number is for internal identification and is not reported.)
Powder Metallurgy Wrought Products Including Metal-Matrix Composites	A heat is a consolidated (vacuum hot pressed) billet having a distinct chemical composition.
Cast Alloy Products Including Metal-Matrix Composites	A melt is a single homogeneous batch of molten metal for which all processing has been completed and the temperature has been adjusted and made ready to pour castings. (For metal-matrix composites, the molten metal includes unmelted reinforcements such as particles, fibers, or whiskers.)

**MIL-HDBK-5H****1 December 1998**

Test specimens shall be located within the cross section of the product in accordance with the applicable material specification, or applicable sampling specification, such as AMS 2355, AMS 2370, and AMS 2371. Subsize tensile and compressive test specimens may be used when appropriate.

Test specimens shall be excised in longitudinal, long transverse, and short transverse (when applicable) grain directions. Mechanical properties shall also be obtained in the 45° grain direction for materials that are anticipated to have significantly different properties in this direction than the standard grain directions. For some product configurations, it may be impractical to obtain transverse bearing specimens. For aluminum die forgings, the longitudinal grain direction is defined as orientations parallel, within  $\pm 15^\circ$ , to the predominate grain flow. The long transverse grain direction is defined as perpendicular, within  $\pm 15^\circ$ , to the longitudinal (predominate) grain direction and parallel, within  $\pm 15^\circ$ , to the parting plane. (Both conditions must be met.) The short transverse grain direction is defined as perpendicular, within  $\pm 15^\circ$ , to the longitudinal (predominate) grain direction and perpendicular, within  $\pm 15^\circ$ , to the parting plane. (Both conditions must be met.) All three grain directions are applicable and tests shall be conducted.

Triplicate test specimens are preferred. Single test specimens may be acceptable for some products providing retesting can be performed when needed. Duplicate specimens are recommended as an economical compromise. Some variation in strength within a product is expected. The use of replicate specimens provides multiple mechanical property observations so that lot averages can be used to form paired mechanical property ratios. Mechanical property ratios formed from lot averages are more reliable than those formed from individual observations.

**9.1.6.4 Test Procedures** — All tests shall be performed in accordance with applicable ASTM specifications. The pin shear testing of aluminum alloys is covered by ASTM B 769. Grain orientations and loading directions for shear specimens are also specified in ASTM B 769. Published shear testing standards are not available for aluminum alloy sheet, strip, or thin extrusions or for products from other alloy systems. Bearing tests for products from all alloy systems shall be conducted in accordance with ASTM E 238 using “clean pin” test procedures. For aluminum alloy plate, bearing specimens are oriented flatwise and for aluminum alloy die and hand forgings, bearing specimens are oriented edgewise, as described in Section 3.1.2.1.1.

**9.1.6.5 Mechanical Properties** — Tensile, compression, shear, and bearing tests shall be conducted at room temperature to determine tensile yield and ultimate strengths, compressive yield strength, shear ultimate strength, and bearing yield and ultimate strengths for  $e/D = 1.5$  and  $e/D = 2.0$  for each grain direction and each lot of material. All data shall be identified by lot, or heat, or melt. For materials used exclusively in high temperature applications, such as gas turbine or rocket engines, the determination of design values for compression, shear, and bearing strengths may be waived by the MIL-HDBK-5 Coordination Group. In lieu of data for these properties, sufficient elevated temperature data for tensile yield and ultimate strengths, as well as modulus of elasticity, shall be submitted so that elevated temperature curves can be constructed. Data should be submitted for the useful temperature range of the product. See Section 9.3.1.1.1 for data requirements for elevated temperature curves.

**9.1.6.6 Modulus of Elasticity Data** — Tensile and compressive modulus of elasticity values shall be determined for at least three lots of material. Elastic modulus values are those obtained using a Class B-1 or better extensometer. The method of determining or verifying the classification of extensometers is identified in ASTM E 83. ASTM E 111 is the standard test method for the determination of Young’s Modulus, tangent modulus, and chord modulus of structural materials. A modulus value shall also be obtained for the 45 degree grain orientation for materials that are anticipated to have significantly different properties in this direction than the standard grain directions.

**MIL-HDBK-5H****1 December 1998**

**9.1.6.7 Other Data** — Room temperature, tensile, and compressive load-deformation curves or stress-strain data for each grain direction from at least three lots shall be provided. Room temperature, full-range, tensile load deformation curves or stress-strain data for each grain direction shall also be provided. Full-range stress-strain data shall be provided for at least one lot, but data for three lots are preferable. For heat resistant materials for which elevated temperature data for tensile yield and ultimate strengths are required, room and elevated temperature stress-strain data shall be provided. A precise density value in pounds per cubic inch shall be provided. Although not required, physical property data for coefficient of expansion, thermal conductivity, and specific heat should be submitted, when available. Also, information regarding manufacturing (fabrication and processing), environmental effects (corrosion resistance), heat treat condition and applicable specification shall be provided so that a comments and properties section can be prepared. Also, data for creep, stress rupture, fatigue crack propagation, fatigue and fracture toughness properties should be submitted whenever possible, especially when applicable specifications contain minimum property requirements, such as minimum fracture toughness values.

**9.1.6.8 Guideline Requirements for Specification Minimum Design Mechanical Properties** (S-basis) — A product must be covered by an industry specification prior to being considered for inclusion into MIL-HDBK-5 as indicated in 9.1.6.1. Within a specification, one of the basic requirements is to provide minimum properties (S-basis) which includes tension yield, tension ultimate, elongation and compression yield (when specified). As indicated in Section 9.2.2, the statistical significance to the S-basis properties is typically not known. However, it is known that minimum mechanical properties in the SAE/AMS specifications have been statistically justified in recent years (since ~ 1975) with a procedure contained in their documents. With that in mind, a procedure has been established to provide some level of statistical significance to these S-basis properties contained within the Handbook.

A material being submitted for inclusion into MIL-HDBK-5 shall include as part of the substantiation package the basis of the specification properties. This substantiation package should include the number of test samples, the number of lots, and the method of determining any property covered in the specification even if it is not to be reported in MIL-HDBK-5. This could include the development of minimum as well as maximum properties. Consideration must be made for the specified sizes, product forms, heat treatments and other variables affecting the physical and mechanical properties. It is also expected that the test material chemistry be in the nominal specification range and not tailored to the chemistry extremes.

It is recommended that the substantiation be based on a procedure similar to SAE/AMS in which the analysis of data or other appropriate documentation supports a statistical S-basis value where at least 99 percent of the population of values is expected to equal or exceed the minimum value with a confidence of 95 percent. Since only limited quantities of data are generally available for the basic mechanical properties (tension yield, tension ultimate, compression yield), it is recommended that at least 30 test samples from at least three heats or lots of material are provided for each thickness range or product form. The S-basis value may be computed by assuming the distribution of the sample population to be normal and using the following equation:

$$\text{Minimum } S = \bar{X} - s \cdot k_{99} \quad (9.1.6.8)$$

where

$\bar{X}$	=	sample mean
$s$	=	standard deviation
$k_{99}$	=	one-sided tolerance-limit factor corresponding to a proportion at least 0.99 of a normal distribution and a confidence coefficient of 0.95 based on the number of specimens (See Table 9.6.4.1).

**MIL-HDBK-5H**  
**1 December 1998**

When the tensile and compressive properties vary significantly with thickness, regression analysis should be used.

Although the establishment of an S-basis value should be based upon the statistically computed value, the S-basis value may be slightly lower, based on experience and judgement, to insure conservative values.

**9.1.7 PROCEDURE FOR THE SUBMISSION OF MECHANICAL PROPERTY DATA** — This section specifies the procedure for submission of mechanical property data for statistical analysis; specifically data supplied for the determination of  $T_{99}$  and  $T_{90}$  values for  $F_{tu}$  and  $F_{ty}$  and for data supplied to obtain derived property values for  $F_{cy}$ ,  $F_{su}$ ,  $F_{bru}$  and  $F_{bry}$ . The amount of data to be supplied for both of these are indicated in other sections of Chapter 9, such as Table 9.1.6 for derived property values. This section covers the format to submit the data in electronic form.

**9.1.7.1 Computer Software** — The data can be supplied on 3.5 or 5.25 inch disks for PC format or on 3.5 inch disks for Macintosh format. It is recommended that the software applications in Table 9.1.7.1 be used to construct the data files. Along with the floppy disk, provide a hard (paper) copy of the data contained on the disk and any other supporting documentation such as specimen dimensions, gage length etc. This information will be stored in the MIL-HDBK-5 archives for future reference.

**Table 9.1.7.1. Software Applications for Data Submission**

---

ASCII text editor

- Current Spreadsheet or Database Applications
  - The Chairman or Secretary of MIL-HDBK-5 can be contacted concerning software compatibility questions.
- 

The data supplied on these disks are to be supplied in English units. For example, physical dimensions should be reported in units of inches to the nearest thousandth of an inch (X.XXX), stress should be reported in units of ksi to the nearest one hundredth of a ksi (X.XX), strain is to be reported in percent to the nearest tenth of a percent (X.X) and modulus is to be reported in units of  $10^3$  ksi to the nearest tenth of a msi (X.X). If necessary, refer to Table 1.2.2 to convert to English units of measure.

**9.1.7.2 General Data Format** — Tables 9.1.7.2(a) and (b), for wrought and cast products respectively, show the information that should be supplied in electronic form along with the mechanical test results. The columns (or data fields), in order, will contain alloy type, specification number, temper/heat treatment, lot and/or heat number, product form, product thickness, specimen location, grain direction, and specimen number. Columns will be added towards the right of the specimen number and will contain the individual test results as discussed in Sections 9.1.7.3 and 9.1.7.4.

When specifying grain direction for wrought product strengths, etc., use the conventions identified in Table 9.1.6: L for longitudinal, LT for long transverse, and ST for short transverse. Products that are anticipated to have significantly different properties in directions other than those stated above should be tested in the appropriate directions and the results reported.

There are several types of product forms identified in the Handbook; therefore, the term product form should be properly defined and reported in this column. Examples for wrought products are sheet, plate, bar, and forging. Examples for cast products are sand casting, investment casting, and permanent mold casting. For cast products it is important to identify properties from designated or nondesignated areas.

**MIL-HDBK-5H****1 December 1998**

**9.1.7.3 Data Format for the Determination of A and B-Basis Values of  $F_u$  and  $F_{ty}$**  — The tensile test results that are to be reported for determination of A and B-basis properties are tensile ultimate strength (TUS), tensile yield strength (TYS), elongation (e), reduction of area (RA), and modulus. The results of these tests are to be reported as shown in Table 9.1.7.3 along with alloy designation, specification, lot and/or heat number, product thickness, grain direction, etc. as previously shown in Table 9.1.7.2. The number of tests required for determining A and B-basis properties are identified in Section 9.2.

**9.1.7.4 Data Format for Derived Property Values** — For the derived property values, several types of tests may be conducted such as tensile, compression, shear and bearing, as shown in Table 9.1.6. The results of these tests are to be reported as shown in Table 9.1.7.4 along with alloy designation, specification, lot and/or heat number, product thickness, grain direction, etc. as previously shown in Table 9.1.7.2. The ultimate strength properties are to be contained in one file as shown in Table 9.1.7.4(a) while the yield strength properties are to be contained in another file as shown in Table 9.1.7.4(b).

Generally, two tests are preferred (one required) for a given test type and product thickness. The results of these tests are to be reported in columns adjacent to each other. For example, TUS Test #1 and TUS Test #2 are on the same row for a given thickness and heat. An additional column should be created to report the specimen number for the second test. This column should be just to the left of the test result. The same procedure is to be used for the other properties. The abbreviations (see Section 1.2.2) for the other test types are CYS for compressive yield, SUS for shear ultimate, and BUS and BYS for bearing ultimate and bearing yield strengths, respectively. For the bearing properties, also identify the e/D ratio of either 1.5 or 2.0.

**9.1.7.5 Data Format for the Construction of Typical Stress-Strain Curves** — The tensile and compression stress-strain data should also be submitted in electronic form, if possible, so that typical tensile and compression stress-strain curves, compression tangent-modulus and typical tensile (full-range) curves can be constructed. In order to construct a typical stress-strain curve, the individual specimen curves must be documented up to slightly beyond the 0.2 percent offset yield strength. To construct a typical (full-range) stress-strain curve, the individual curves must be documented through to failure.

The data for the stress-strain curves must be supplied on a separate floppy disk from the mechanical property data. The data should be stored in a file which contains the load (or stress) in the first column and the displacement (or strain) in the second column. Each stress-strain pair should be identified with its corresponding specimen identification number.

For the load-displacement curves, the load should be reported in pounds (X.) and the displacement should be reported in units of thousandth of an inch (X.XXX). For stress-strain curves, the stress should be reported to the nearest hundredth of a ksi (X.XX) and strain should be reported to the nearest  $X.XX \times 10^{-6}$  units.

A hard copy of the load displacement curve should also be submitted for each stress-strain curve.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.1.7.2(a). General Data Format for Wrought Products**

Alloy Trade Name	Industry/ Government Specification No.	Temper/Heat Treatment	Lot and/or Heat No.	Product Form	Product Thickness (in.), or Area (in. <sup>2</sup> )	Speci- men Location	Grain Direc- tion	Specimen No.

**Table 9.1.7.2(b). General Data Format for Cast Products**

Alloy Trade Name	Industry/ Government Specification No.	Temper/Heat Treatment	Lot and/or Heat No.	Product Form	Product Thickness	Specimen Location (Designated, Nondesig- nated)	Specimen No.



**Table 9.1.7.3. Data Format for Determination of A and B-Basis Values of  $F_{tu}$  and  $F_{ty}$** 

Alloy Trade Name		Specimen No.	TUS ksi	TYS ksi	% E	% R	Elastic Modulus, msi
	The information to be entered between these two columns						
	depends upon the product form, see Table 9.1.7.2(a) or (b).						

**Table 9.1.7.4(a). Derived Ultimate Properties**

Alloy Trade Name		Specimen No.	TUS Test 1	TUS Test 2*	SUS Test 1	SUS Test 2*	BUS e/D=1.5 Test 1	BUS e/D=1.5 Test 2*	BUS e/D=2.0 Test 1	BUS e/D=2.0 Test 2*
	The information to be entered between these two									
	columns depends upon the product form, see Table 9.1.7.2(a) or (b).									

\* Two tests are preferred, only one is required.

**Table 9.1.7.4(b). Derived Yield Properties**

Alloy Trade Name		Specimen No.	TYS Test 1	TYS Test 2*	CYS Test 1	CYS Test 2*	BYS e/D=1.5 Test 1	BYS e/D=1.5 Test 2*	BYS e/D=2.0 Test 1	BYS e/D=2.0 Test 2*
	The information to be entered between these two									
	columns depends upon the product form, see Table 9.1.7.2(a) or (b).									

\* Two tests are preferred, only one is required.

**MIL-HDBK-5H**  
**1 December 1998**

## **9.2 ROOM-TEMPERATURE DESIGN PROPERTIES**

**9.2.1 INTRODUCTION** — This section contains detailed procedures for the determination of room-temperature design properties.

**9.2.2 DESIGNATIONS AND SYMBOLS** — Designations and Symbols presented in this section are applicable throughout the MIL-HDBK-5, but are particularly pertinent to computation and presentation of room-temperature mechanical properties.

**9.2.2.1 Data Basis** — There are four types of room-temperature mechanical properties included in MIL-HDBK-5. They are listed here, in order, from the least statistical confidence to the highest statistical confidence, as follows:

*Typical Basis* — A typical property value is an average value and has no statistical assurance associated with it.

*S-Basis* — This designation represents the specification minimum value specified by the governing industry specification (as issued by standardization groups such as SAE Aerospace Materials Division, ASTM, etc.) or federal or military standards for the material. (See MIL-STD-970 for order of preference of specifications.) For certain products heat treated by the user (for example, steels hardened and tempered to a designated  $F_m$ ), the S-basis value may reflect a specified quality-control requirement. Statistical assurance associated with this value is not known.

*B-Basis* — This designation indicates that at least 90 percent of the population of values is expected to equal or exceed the statistically calculated mechanical property value, with a confidence of 95 percent. This statistically calculated number is computed using the procedures specified in Section 9.2.

*A-Basis* — The lower value of either a statistically calculated number, or the specification minimum (S-basis). The statistically calculated number indicates that at least 99 percent of the population is expected to equal or exceed the statistically calculated mechanical property value with a confidence of 95 percent. This statistically calculated number is computed using the procedures specified in Section 9.2.

Sections 9.2.5, 9.2.7.1, 9.2.8.1, and 9.2.9.1 contain discussions of data requirements for direct computation of design properties based on current process capability of the majority of suppliers of a given material and product form. To assure that the A- and B-basis values, defined above, represent true current process capability of a material, all available original test data for current material that is produced and supplied to the appropriate government, industry, or equivalent company specifications are included in calculating these values. (However, to be considered for inclusion in MIL-HDBK-5, a material must be covered by an industry, Federal, or Military specification per Section 9.1.6.) Only positive proof of improper processing or testing is cause for exclusion of original test data, except that the number of tests per lot shall not exceed the usual frequency of testing for the product. It is recognized, however, that extensive acceptance testing resulting in elimination of low-strength material from the population may justify establishment of higher mechanical-property values for the remaining material. Since this is a function of both the type of product and the nature and frequency of the acceptance tests practiced by each company, it is impractical to attempt to include these considerations in this document.

Usually, only tensile ultimate and yield strengths in a specified testing direction are determined in such a manner that they can be termed A- and B-basis values, in accordance with definitions given above. Only tensile ultimate strength, tensile yield strength, elongation, and reduction of area (for some alloys) are normally specified in the governing specifications and can be termed S-basis values. However, ratioing procedures (described in Section 9.2.10) have been established, by which other property values such as

**MIL-HDBK-5H**  
**1 December 1998**

compression, shear, and bearing are computed to have approximately the same assurance levels as A-, B-, or S-basis values for tensile ultimate and yield strength. Property values determined in this manner are presented as having the same data basis as tensile ultimate and yield strengths in the same column of the table.

Current practice regarding the use of the above data bases in the presentation of room-temperature design properties is as follows:

- (1) Room-temperature design properties for tensile ultimate and yield strengths are presented as A- and B- or S-basis values. A-basis values that are higher than corresponding S-basis values are presented as footnotes in MIL-HDBK-5 property tables, and these A-basis values are not qualified for general use in design unless the specification requirements are increased to equal the A-basis value. However, A-basis values that are equal to or lower than corresponding S-basis values replace S-basis values in the document.
- (2) The S-basis value is used for elongation and reduction of area.
- (3) If an A-basis value is presented for a strength property, the corresponding B-basis value is also presented.
- (4) A- and B-basis values, when available, replace S-basis values, based upon item (1) conditions.
- (5) A- and B-basis values, based upon data representing samples of material supplied in the annealed, solution treated, or as-fabricated conditions, which were heat treated to demonstrate response to heat treatment by suppliers, are incorporated into MIL-HDBK-5 with an explanatory footnote. It is recognized that structural fabrication and processing can alter mechanical properties. The use of A- and B-basis values for structural design requires consideration of such effects. These material property values are derived from the statistically computed  $T_{99}$  and  $T_{90}$  values defined earlier.
- (6) Strength at room temperature after thermal exposure is presented graphically as a percentage of the tabulated design property.
- (7) Design data for all other properties, such as elastic modulus, Poisson's ratio, creep, fatigue, and physical properties, are presented on a typical basis unless indicated otherwise.

**9.2.2.2 Mechanical-Property Terms** — Mechanical properties that are presented as room-temperature design properties are listed in Table 9.2.2.2. It is important that use of a subscripted, capital letter “*F*” should be limited to designation of minimum values. Its use to designate an individual test value can lead to confusion and should be avoided in MIL-HDBK-5 data proposals.

The absence of a directionality symbol implies that the property value is applicable to each of the grain directions when the product dimensions exceed approximately 2.5 inches.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.2.2.2. Mechanical Property Terms**

Property	Units	Symbol	
		Room-Temperature Minimum Value	Individual or Typical Value
Tensile Ultimate Strength	ksi	$F_{tu}$	TUS
Tensile Yield Strength	ksi	$F_{ty}$	TYS
Compressive Yield Strength	ksi	$F_{cy}$	CYS
Shear Ultimate Strength	ksi	$F_{su}$	SUS
Shear Yield Strength*	ksi	$F_{sy}$	SYS
Bearing Ultimate Strength	ksi	$F_{bru}$	BUS
Bearing Yield Strength	ksi	$F_{bry}$	BYS
Elongation	percent	$e$	elong.
Total Strain at Failure*	percent	$e_t$	strain at failure
Reduction of Area	percent	$RA$	red. of area

\* As applicable.

The listed mechanical property symbols should be followed by one of the following additional symbols for wrought alloys, not castings.

- L — Longitudinal direction; parallel to the principal direction of flow in a worked metal.
- T — Transverse direction; perpendicular to the principal direction of flow in a worked metal; may be further defined as LT or ST.
- LT — Long-transverse direction; the transverse direction having the largest dimension, often called the “width” direction.
- ST — Short-transverse direction; the transverse direction having the smallest dimension, often called the “thickness” direction.

Values of  $F_{bru}$  and  $F_{bry}$  should indicate the appropriate edge distance/hole diameter (e/D) ratio. Design properties are presented for two such ratios: e/D = 1.5 and e/D = 2.0.

Data for use in establishing these properties should be based on ASTM standard testing practices. The test practice and any deviations therefrom should be reported when submitting proposals to the MIL-HDBK-5 Coordination Group for consideration.

**9.2.2.3 Statistical Terms** — Proper use of the following statistical terms and equations will alleviate misunderstanding in the presentation of data analyses:

**Population** — All potential measurements having certain independent characteristics in common, i.e., “all possible TUS(L) measurements for 17-7PH stainless steel sheet in TH1050 condition.”

**Sample** — A finite number of observations drawn from the population.

**Sample Mean** — Average of all observed values in the sample. It is an estimate of the population mean. A mean is indicated by a bar over the symbol for the value observed. Thus, the mean of  $n$  observations of TUS would be expressed as:

**MIL-HDBK-5H**  
**1 December 1998**

$$\overline{TUS} = \frac{TUS_1 + TUS_2 + \dots + TUS_n}{n} = \frac{\sum_{i=1}^n (TUS_i)}{n}$$

Sample Variance — The sum of the squared deviations from the sample mean, divided by  $n - 1$ , and, based on  $n$  observations of TUS, expressed as

$$s_{TUS}^2 = \frac{\sum_{i=1}^n (TUS_i - \overline{TUS})^2}{n - 1} = \frac{n \sum_{i=1}^n (TUS_i)^2 - \left( \sum_{i=1}^n TUS_i \right)^2}{n(n - 1)}$$

Sample Standard Deviation — An estimate of the population standard deviation; the square root of the sample variance, or

$$s_{TUS} = \sqrt{s_{TUS}^2}$$

Degrees of Freedom — Number of degrees of freedom for  $n$  sample values is defined as that number minus the number of constraints. For example, the standard deviation calculation contains one fixed value (the mean); therefore, it has  $n - 1$  degrees of freedom.

$T_{99}$  — At least 99 percent of the population of values is expected to equal or exceed this tolerance bound with a confidence of 95 percent.

$T_{90}$  — At least 90 percent of the population of values is expected to equal or exceed this tolerance bound with a confidence of 95 percent.

Probability — Ratio of possible number of favorable events to total possible number of equally likely events. Probability, as related to design properties, means that chances of a material-property measurement equaling or exceeding a certain value (the one-sided lower tolerance limit) is 99 percent in the case of a  $T_{99}$  value and 90 percent in the case of a  $T_{90}$  value.


Confidence — A specified degree of certainty that at least a given proportion of all future measurements can be expected to equal or exceed the lower tolerance limit. Degree of certainty is referred to as the confidence coefficient. For MIL-HDBK-5, the confidence coefficient is 95 percent which, as related to tolerance bounds for design properties, means that, in the long run over many future samples, 95 percent of conclusions regarding exceedance of  $T_{99}$  and  $T_{90}$  values would be true.

**9.2.3 COMPUTATIONAL PROCEDURES, GENERAL** — Procedures used to determine tolerance bounds for mechanical properties vary somewhat from one sample to another. All involve a number of steps that are best illustrated by the flowchart in Figure 9.2.3. These steps are summarized as follows:

- (1) Specify the population to which the property applies
- (2) Decide on the procedure for computing the property
- (3) Compute the property.

These steps are described in greater detail in Sections 9.2.4 through 9.2.11, and a number of examples of the several procedures are presented in Section 9.2.12.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 9.2.3. General procedures for determining design allowables.**



**MIL-HDBK-5H****1 December 1998**

**9.2.4 SPECIFYING THE POPULATION** — For computational purposes, definition of a population must be sufficiently restrictive to ensure that computed tolerance bounds for design properties are realistic and useful. This is done by establishing a range of products and test conditions for which a mechanical property can be characterized by a single statistical distribution. In most cases a homogeneous population of data for a measured test parameter should not include more than one alloy, heat-treated condition, or test temperature.

It is not necessarily obvious whether such a population may include more than one product form or size, grain direction or processing history. Strip, plate, bars, and forgings of one alloy may have essentially the same TYS, while for another material the TYS may differ greatly among those product forms. To resolve these questions, appropriate statistical tests of significance should be applied to the respective groups of data. These tests are described in detail in Section 9.6, and Section 9.2.12 presents examples of their use in MIL-HDBK-5 data analyses.

The step-by-step procedure for specifying the population is illustrated in Figure 9.2.4 and described in Section 9.2.4.1. This procedure is used to determine whether several available data sets may be combined for the purpose of computing design allowables. The procedure is applicable to data collections for which regression analysis is required as well as those for which regression is not required. In the latter case, an acceptability test is employed to eliminate unacceptable data sets. This procedure is described in Section 9.2.4.2. A corresponding acceptability test would be desirable for the regression setting; however, such a procedure has not yet been developed.

**9.2.4.1 Specification Procedure** — In most cases, these tests will provide a fairly clear-cut division between one population and another. For example, L and T properties either are or are not nearly identical. However, wrought product properties may sometimes vary continuously with some dimensional characteristic, such as thickness. It is necessary, therefore, to first test the data for the relationship between the property and the material dimension. Regression analysis procedures, which should be applied to each set of producer's data to determine if there is an effect due to a particular material dimension, are described in Section 9.6.3.

If any one of a group of data sets analyzed by regression shows a significant effect on properties due to the selected material dimension, all regressions should be tested for equality to determine whether the data sets may be combined and considered a homogeneous population. The procedure described in Section 9.6.3.3 should be used to perform this test.

If the regressions are accepted as equal, then  $T_{99}$  and  $T_{90}$  values can be calculated in one of two ways: (1) by regression; or (2) by dividing data into thickness ranges and calculating  $T_{99}$  and  $T_{90}$  values for each range. If the regressions are not equal,  $T_{99}$  and  $T_{90}$  values should be calculated separately for each data set and minimum  $T_{99}$  and  $T_{90}$  values determined for all data sets should be reported.

If none of the individual data sets (e.g. different producers) show significant regression due to the chosen material dimension, the different data sets should be tested for homogeneity using a k-sample Anderson-Darling test as described in Section 9.6.2.5. If data sets are found to be homogenous, data should be pooled and  $T_{99}$  and  $T_{90}$  values should be calculated using the single combined data set. If data from the various producers constitute more than one population, the following procedure should be used.

- (1) Data sets which do not comply to the minimum number of observations as stated in Sections 9.2.7.1, 9.2.8.1, and 9.2.9.1 data requirements should be excluded from any further evaluation until they meet the minimum requirements.

MIL-HDBK-5H  
1 December 1998




Figure 9.2.4. General procedures for specifying the population and calculating design allowables.

**MIL-HDBK-5H**  
**1 December 1998**

- (2) Each remaining data set should be tested for acceptability using the three-parameter Weibull acceptability test described in Section 9.2.4.2. If there is statistical evidence that one or more statistically distinct data sets do not meet the specification minimum value, the results will be brought to the Material Data Review Working Group where a decision will be made on whether or not these data sets should be included in the computation of material property values.
- (3) All remaining data sets should be tested for homogeneity using the k-sample Anderson-Darling test. If the data sets are found to be homogeneous,  $T_{99}$  and  $T_{90}$  values can be calculated using a single combined data set. If the populations are not homogeneous, material property values must be determined by calculating  $T_{99}$  and  $T_{90}$  values for each data set.

**9.2.4.2 Three-Parameter Weibull Acceptability Test** — The three-parameter Weibull acceptability test is designed to determine whether an acceptable proportion of a producer's population is likely to exceed the specification limit for corresponding material property. To carry out this test, an upper confidence bound (UCB) is calculated for the first percentile of the producer's population assuming that the population is distributed according to a three-parameter Weibull distribution. This UCB value is calculated in the same manner as a  $T_{99}$  value is calculated (in Section 9.2.8) with the following modifications:

- (1) In solving for the threshold  $\tau(\theta)$  (Section 9.6.5.1),  $\theta$  should be set equal to 0.90.
- (2) The value of  $V_{99}$  should be taken from Table 9.6.4.7 rather than Table 9.6.4.8 when using the formula for  $T_{99}$  (Equation [9.2.8.2,(e)]) to calculate the UCB value.

If UCB is greater than or equal to the specification limit, it is concluded that the producer's data is acceptable. If UCB is less than the specification limit, it is concluded (with a 5 percent risk of error) that the producer's data do not meet the specification minimum value.

In statistical terms, this method tests (at 5 percent significance level) the hypothesis that at least 99 percent of the producer's population is greater than the specification limit. If the hypothesis is not rejected (UCB greater than or equal to specification limit), then it is concluded that the producer's data is acceptable. If the hypothesis is rejected (UCB less than the specification limit), it is concluded that the producer's data is unacceptable.

This technique is applicable only when data have not been censored from the sample. It also assumes that the data are distributed according to a three-parameter Weibull distribution (although normally distributed data are also accommodated by this test). If the data sample is highly skewed, background data should be reviewed to determine whether the skewness is caused by a mixed population. If it is not, the Weibull test procedure can be applied. This test should be applied to both tensile yield and ultimate strengths (in appropriate grain directions), and if a producer's data is unacceptable for either property, that producer's data for both properties should be excluded for the purpose of computing  $T_{99}$  and  $T_{90}$  values.

**9.2.5 DECIDING BETWEEN DIRECT AND INDIRECT COMPUTATION** — The only room-temperature design properties that are regularly determined by direct computation are  $F_{tu}$  and  $F_{ty}$ . This procedure is usually limited to a specified or usual testing direction because there are seldom enough data available to determine properties in other test directions. Two rules govern the choice between direct and indirect computation:

- (1)  $F_{tu}$  and  $F_{ty}$  in the specified or usual testing direction may be determined by direct computation only.

**MIL-HDBK-5H****1 December 1998**

- (2)  $F_{tu}$  and  $F_{ty}$  in other testing directions (as well as  $F_{cy}$ ,  $F_{su}$ ,  $F_{bru}$ , and  $F_{bry}$  in all directions) may be determined by direct computation only if (a) the data are adequate to determine the distribution form and reliable estimates of population parameters, or (b) the sample includes 300 or more individual, representative observations of the property to be determined.

For example, assume that available data for a relatively new alloy comprise 50 observations of TUS in the specified testing direction. This sample is not considered large enough to determine the distribution form and reliable estimates of population mean and standard deviation. Since only direct computation is permitted in this instance, determination of  $T_{99}$  and  $T_{90}$  values must be postponed until a larger sample is available. However, these properties may be considered for presentation on the S basis at the discretion of the MIL-HDBK-5 Coordination Group, contingent on availability of an acceptable procurement specification for the material.

If the number of observations increases to 100, this quantity may be adequate to allow determination of  $T_{99}$  and  $T_{90}$ -values, provided data can be described by a normal or Weibull distribution. If the distribution cannot be described parametrically, at least 299 observations are required so that computation can proceed without knowledge of the distributional form.

If the above example involved observations of SUS instead of TUS, the same criteria would apply for direct computation. However,  $F_{su}$  could be determined by indirect computation with as few as ten paired observations of SUS and TUS (representing at least ten lots and two heats), provided  $F_{tu}$  has been established.

## **9.2.6 DETERMINING THE APPROPRIATE COMPUTATION PROCEDURE**

**9.2.6.1 Background** — Prior to 1984, lower tolerance bound mechanical properties ( $T_{99}$ ,  $T_{90}$ ) were established by one of two methods. If the sample population was found to be normally distributed by a chi-square test, then standard normal distribution computation procedures were used. Otherwise, non-parametric procedures were used.


In 1984, use of the normal distribution was supplemented by use of the three-parameter Weibull distribution to accommodate skewness in material properties. In addition, the chi-square test was replaced by the more sensitive Anderson-Darling goodness-of-fit test. Because the Anderson-Darling test is especially sensitive to departures in the tails from the candidate distribution (the very high and very low observations) in many situations, the Weibull distribution is often rejected, even when the model fit (by a probability plot) appears adequate in the lower values.

To permit computation of lower tolerance bounds in more of these cases, the Weibull approach was expanded to incorporate two different levels of upper-tail censoring and a last-resort conservative “backoff” option. Also, a modified version of the A-D test was developed which places more emphasis on the lower tail than the upper tail. In addition, because methods based on the normal distribution have intuitive appeal and are less computationally burdensome, a normal-based approach has been reinstated. This method is an adjusted version of the previously used normal method which was developed to protect against anti-conservatism due to undetected skewness. These methods were incorporated into the guidelines in 1995.

**9.2.6.2 Computation Procedures** — Current analysis procedures are defined in Figure 9.2.6. Three methods are permitted for the computation of the lower tolerance bounds ( $T_{99}$ ,  $T_{90}$ ): sequential Weibull procedure, adjusted normal procedure, and nonparametric procedure. The sequential Weibull procedure is applicable more frequently than the adjusted normal procedure. In addition, if more than one method can be applied, the sequential Weibull procedure often provides a higher lower tolerance bound.

## MIL-HDBK-5H

1 December 1998

Figure 9.2.6. Procedures for computation of  $T_{99}$  and  $T_{90}$ .

**MIL-HDBK-5H**  
**1 December 1998**

In what follows, certain procedures require artificial censoring of the measured data. That is, because the real engineering interest for design lies in lower percentiles of the distribution of a material's properties, some of the following procedures ignore a portion of the observations in the upper tail. Specifically, we use the notation  $X_{(1)} \leq X_{(2)} \leq \dots \leq X_{(n)}$  to denote the ordered sample, and will frequently refer to the censored sample:

$$X_{(1)} \leq X_{(2)} \leq \dots \leq X_{(r)},$$

where  $r/n$  represents the proportion of the sample which is uncensored. Alternatively,  $(1-r/n)$  represents the proportion of the sample which is censored. The terms  $r$  and  $n$  will be used throughout subsequent sections without redefinition. In the case of uncensored data,  $r=n$ .

When the sequential Weibull procedure is applied, a modified Anderson-Darling goodness-of-fit-test is conducted as described in 9.6.1.4 for the uncensored sample. If the assumption of Weibullness is not rejected, the lower tolerance bound should be computed using methods described in Section 9.2.8 for complete samples. (The risk that one may conclude erroneously that a true Weibull distribution is non-Weibull is set at 5 percent.) If the assumption of Weibullness is rejected for the complete sample, then the next step is to test the lower 80 percent of the data for Weibullness by trimming the top 20 percent of the measurements and applying a censored version of the Anderson-Darling test. Use the version of the test described in Section 9.6.1.4 for 20 percent censoring. If this test is not rejected, then the lower tolerance bounds should be computed using the methods described in 9.2.8 for 20 percent censoring. If the assumption of Weibullness is rejected here, then 50 percent censoring should be attempted, in the same manner as described for 20 percent censoring.

If the Weibull model is still rejected with 50 percent censoring, then a last resort conservative method should be attempted. This method decreases the initial Weibull threshold estimate while holding the shape and scale parameters constant, until the percentiles of the resulting model are sufficiently less than the sample percentiles. To avoid accepting an extremely inadequate fit, the decrease is limited to 0.5 ksi.

Section 9.6.1.6 describes the method for identifying a proper backoff (the decrease from the initial Weibull threshold estimate), denoted by  $\tau_{\text{backoff}}$ , for this method. If the appropriate backoff is less than or equal to 0.5 ksi, the lower tolerance bounds should be calculated by first computing bounds based on the complete sample as specified in Section 9.2.8, and then subtracting the  $\tau_{\text{backoff}}$  value. If an appropriate backoff less than or equal to 0.5 ksi is not identified, then the nonparametric procedures described in 9.2.9, or the adjusted normal procedure described in Section 9.2.7, should be considered.

If the adjusted normal analysis procedure is applied, the first step is to perform an Anderson-Darling goodness-of-fit test for normality as described in Section 9.6.1.2. If the assumption of normality is not rejected, the lower tolerance bounds may be computed using the methods described in Section 9.2.7. If the assumption of normality is rejected, the sequential Weibull procedures described in Section 9.2.8 or the nonparametric procedure described in Section 9.2.9 should be considered.

In those cases where sufficient data is available, one may choose to calculate the lower tolerance bounds by the nonparametric procedure. A  $T_{99}$  bound requires 299 data values and a  $T_{90}$  bound requires 29 data values.\* The nonparametric procedure is described in Section 9.2.9. If the sample size is too small for the nonparametric method, the sequential Weibull procedures described in Section 9.2.8 or the adjusted normal procedures described in Section 9.2.7, should be considered.

---

\* However, according to current guidelines, a  $T_{90}$  value cannot be calculated for inclusion in MIL-HDBK-5 with fewer than 100 data values. See Section 9.2.9.1.



**MIL-HDBK-5H**  
**1 December 1998**

In those cases where sample sizes are insufficient to apply the nonparametric method, and the goodness-of-fit tests will not allow application of the sequential Weibull or adjusted normal procedures, the lower tolerance bounds cannot be calculated.

**9.2.7 DIRECT COMPUTATION FOR THE NORMAL DISTRIBUTION** — This procedure should be used when a lower tolerance bound ( $T_{99}$ ,  $T_{90}$ ) is to be computed directly (not paired with another property for computational purposes) and the population may be interpreted to signify either the property measured (TUS, etc.) or some transformation of the measured value that is normally distributed. This procedure is applicable to  $F_{tu}$  and  $F_{ty}$ . It may also be used for  $F_{cy}$ ,  $F_{su}$ ,  $F_{bru}$ , and  $F_{bry}$  if sufficient quantity of data is available.

**9.2.7.1 Data Requirements** — Direct calculation of  $T_{99}$  and  $T_{90}$  values requires adequate data to determine (1) the form of distribution and (2) reliable estimates of the population mean and standard deviation. Prior experience with the material under consideration will help in determining sample size requirements. For a material, each population should be represented by a sample containing at least 100 observations. The sample shall include multiple lots, representing at least ten production heats, casts, or melts, from a majority of important producers. See Section 9.1.6.2 for definitions of lot, heat, cast, and melt. The sample should be distributed somewhat evenly over the size range applicable to the tolerance bound for the mechanical property. In order to avoid an undesirable biasing of the sample in favor of lots represented by more observations than other lots, the number of observations from each lot must be nearly equal.

Grouped data may be “ungrouped” and analyzed as described below, if grouped data are reported in intervals of 1 ksi or less. The uniform smoothing method for ungrouping grouped data should be used. For the uniform smoothing method, observations in an interval are spread uniformly over that interval. The  $i$ th observation in an interval is set equal to

$$a_i = L + \frac{i}{n + 1} (U - L) \quad i = 1, 2, \dots, n$$

where

- $n$  = the number of observations in the interval
- $L$  = the lower end point of the interval
- $U$  = the upper end point of the interval.

**9.2.7.2 Computational Procedure** — To compute the lower tolerance bounds for a normally distributed population, it is necessary to have (1) estimates of the mean and standard deviation of this population and (2) tables of one-sided\* tolerance-limit factors for the normal distribution. Means and standard deviations are computed from samples drawn from the population by a random process. Equations for computing the mean and standard deviation are presented in Section 9.2.2.3. One-sided tolerance-limit factors for the normal distribution are tabulated as functions of sample size and population proportion covered by the tolerance interval. Tolerance-limit factors are presented in Table 9.6.4.1.

---

\* At this point it is appropriate to distinguish between “one-sided” and “two-sided” tolerance factors, both of which are used in various stages of MIL-HDBK-5 analyses. A one-sided factor is used to establish a limit, above or below which it is predicted that at least some percentage of the values lie. A two-sided factor is used to establish an interval or range within which it is predicted that at least some percentage of the values lie. In both instances, a confidence is specified for the prediction. Thus, in determining a  $T_{99}$  value, one predicts, with 0.95 confidence, that at least 0.99 of the values in the population lie above the  $T_{99}$  value, and a one-sided tolerance factor is used in the prediction. See References 9.2.7.2(a) through (d).

**MIL-HDBK-5H**  
**1 December 1998**

With a suitable sample of size n, computation of the lower tolerance bounds is carried out by the use of the following formulas:

$$T_{99} = \bar{X} - (k_{99} - 0.1556 - 1.203q_{LB} + 2.858/n^{1/2}) s, \quad [9.2.7.2(a)]$$

$$T_{90} = \bar{X} - (k_{90} + 0.0338 - 0.202q_{LB}) s, \quad [9.2.7.2(b)]$$

where

- $\bar{X}$  = sample mean based on n observations
- s = sample standard deviation
- $k_{99}$  = one-sided tolerance-limit factor corresponding to a proportion at least 0.99 of a normal distribution and a confidence coefficient of 0.95
- $k_{90}$  = one-sided tolerance-limit factor corresponding to a proportion at least 0.90 of a normal distribution and a confidence coefficient of 0.95
- $q_{LB}$  = lower bound on skewness defined as

$$q_{LB} = \frac{q - 1.96 \left( \frac{6n(n-1)}{(n-2)(n+1)(n+3)} \right)^{1/2}}{\left( \frac{n-2}{(n(n-1))^{1/2}} \right)}$$

- q = sample skewness, defined as

$$q = \frac{n^2 \sum_{i=1}^n (x_i - \bar{x})^3}{(n-1)^3 s^3}.$$

The quantities added to the tolerance-limit factor,  $k_{99}$  and  $k_{90}$ , represent adjustments which were determined empirically to protect against anticonservatism even in the case of moderate negative skewness. Skewness is not easy to detect, and negative skewness in the underlying distribution can cause severely anticonservative estimates when using the normal model, even when the Anderson-Darling goodness-of-fit test is used to filter samples. These adjustments help to ensure that the lower tolerance bounds computed maintain a confidence level near 95 percent for underlying skewness as low as -1.0. For higher skewness, the procedure will produce significantly greater coverage.

If the variable that is normally distributed represents a transformation of the mechanical property, the lower tolerance bounds ( $T_{99}$ ,  $T_{90}$ ) computed by the above formulas must be transformed back to the original units in which the mechanical property is conventionally reported. When the computed  $T_{99}$  or  $T_{90}$  value results in a fractional number, the mechanical property value used in the room temperature tables is determined by rounding. Fractions greater than 0.75 usually are raised to the next larger integer while lesser decimal fractions are disregarded. However, the rounded  $T_{99}$  value is replaced in the mechanical properties tables with the S-basis value if the S-basis value is lower. In that case the rounded  $T_{99}$  value is included in a footnote.



**MIL-HDBK-5H**  
**1 December 1998**

**9.2.8 DIRECT COMPUTATION FOR THE WEIBULL DISTRIBUTION** — This procedure should be used when a mechanical property value is to be computed directly (not paired with another property for computational purposes) and the population may be interpreted to signify either the property measured (TUS, etc.) or some transformation of the measured value that follows a three-parameter Weibull distribution. This procedure is applicable to  $F_{tu}$  and  $F_{ty}$ . It may also be used for  $F_{cy}$ ,  $F_{su}$ ,  $F_{bru}$ , and  $F_{bry}$  if a sufficient quantity of data is available.

**9.2.8.1 Data Requirements** — Direct calculation of the lower tolerance bounds ( $T_{99}$ ,  $T_{90}$ ) requires adequate data to determine (1) form of the distribution and (2) reliable estimates of population threshold, shape, and scale parameters. Prior experience with the material under consideration will help determine sample size requirements. For a material, each population should be represented by a sample containing at least 100 observations that are distributed (parametrically) according to a three-parameter Weibull distribution. The sample should include multiple lots, representing at least ten production heats, casts, or melts, from a majority of important producers. The sample should be distributed somewhat evenly over the size range applicable to the property. In order to avoid an undesirable biasing of the sample in favor of lots represented by more observations than other lots, the number of observations from each lot must be nearly equal.

Grouped data may be “ungrouped” and analyzed as described below, if grouped data are reported in intervals of 1 ksi or less. The uniform smoothing method for ungrouping grouped data should be used. For the uniform smoothing method, observations in an interval are spread uniformly over that interval. The  $i$ th observation in an interval is set equal to

$$a_i = L + \frac{i}{n + 1} (U - L) \quad i = 1, 2, \dots, n$$

where

- $n$  = the number of observations in the interval
- $L$  = the lower end point of the interval
- $U$  = the upper end point of the interval.

**9.2.8.2. Computational Procedures** — In order to compute the lower tolerance bounds for a three-parameter Weibull population, it is necessary to have (1) an estimate of population threshold, (2) estimates of population shape and scale parameters, and (3) tables of one-sided tolerance limit factors for the three-parameter Weibull distribution. The method for estimating the population threshold based on complete or censored data (20 or 50 percent censoring) is presented in Section 9.6.5.1, and Section 9.6.5.2 contains the method for estimating population shape and scale parameters. Both of these procedures permit estimation with complete or censored data (20 or 50 percent censoring). A tabulation of tolerance limit factors by sample size, censoring level, and population proportion covered by the tolerance interval is presented in Table 9.6.4.8. For further information on these procedures and tabled values, see References 9.2.8(a) and 9.2.8(b).

Let  $X_1, \dots, X_n$  denote sample observations in any order and let  $X_{(1)}, \dots, X_{(n)}$  denote sample observations ordered from smallest to largest. The first step in calculating  $T_{99}$  and  $T_{90}$  for a three-parameter Weibull population is to obtain an estimate of the population threshold. The population threshold is theoretically the minimum achievable value for the property being measured. However, the real population is being empirically modeled by some Weibull population with a threshold. Since this empirical model is not perfect, there may be a small percentage of observations in the population that fall below the model threshold. Separate threshold estimates, denoted by  $\tau_{99}$  and  $\tau_{90}$ , will be obtained for  $T_{99}$  and  $T_{90}$  using the methods described in Section 9.6.5.1.

**MIL-HDBK-5H**  
**1 December 1998**

The second step in calculating mechanical properties for a three-parameter Weibull population is to obtain estimates of population shape and scale parameters for each property. Shape parameter estimates will be denoted by  $\beta_{99}$  and  $\beta_{90}$  and scale parameter estimates will be denoted by  $\alpha_{99}$  and  $\alpha_{90}$ . Estimation of shape and scale parameters is performed using a maximum likelihood procedure for the two-parameter Weibull distribution, after subtracting off the estimated threshold. (The two-parameter Weibull is equivalent to the three-parameter Weibull with threshold zero.)

Using the method outlined in Section 9.6.5.2, compute the maximum likelihood estimates of the shape and scale parameters for the censored or uncensored sample  $\{X_{(i)} - \tau_{99} : i=1, \dots, r\}$ , where  $r$  equals  $n$  for uncensored data and  $r$  represents the smallest integer greater than or equal to  $4n/5$  for 20 percent censoring and  $n/2$  for 50 percent censoring. Denote these estimates by  $\beta_{99}$  and  $\alpha_{99}$ , respectively. Using the same procedure, compute estimates  $\beta_{90}$  and  $\alpha_{90}$  based on the sample  $\{X_{(i)} - \tau_{90} : i=1, \dots, r\}$ .

With population parameter estimates discussed above at hand, the computation of the lower tolerance bounds is carried out by use of the formulas:

$$T_{99} = \tau_{99} + Q_{99} \exp \left[ - V_{99} / (\beta_{99} \sqrt{n}) \right],$$

$$T_{90} = \tau_{90} + Q_{90} \exp \left[ - V_{90} / (\beta_{90} \sqrt{n}) \right],$$

where

$$Q_{99} = \alpha_{99} (0.01005)^{1/\beta_{99}}$$

$$Q_{90} = \alpha_{90} (0.10536)^{1/\beta_{90}}$$

$$V_{99} = \text{the value in the } V_{99} \text{ column of Table 9.6.4.8 corresponding to a sample of size } n \text{ and the appropriate degree of censoring, and}$$

$$V_{90} = \text{the value in the } V_{90} \text{ column of Table 9.6.4.8 corresponding to a sample of size } n \text{ and the appropriate degree of censoring.}$$

Note that the level of censoring used in estimating the threshold, shape, and scale parameters must be used in determining  $V_{99}$  and  $V_{90}$ . Also, because this censoring level is determined by the goodness-of-fit test (9.6.1.4), the same censoring level is used for both  $T_{99}$  and  $T_{90}$ .

If the property that follows a three-parameter Weibull distribution represents a transformation, the lower tolerance bounds ( $T_{99}$ ,  $T_{90}$ ) computed by the above formulas must be transformed back to the original units in which the mechanical property is conventionally reported. When the computed  $T_{99}$  or  $T_{90}$  value results in a fractional number, the mechanical property used in the room temperature tables is determined by rounding. Fractions greater than 0.75 usually are raised to the next larger integer while lesser decimal fractions are disregarded. However, the rounded  $T_{99}$  value is replaced in the mechanical property tables with the  $S$  value if the  $S$  value is lower. In that case the rounded  $T_{99}$  value is included in a footnote.

**9.2.9 DIRECT COMPUTATION FOR AN UNKNOWN DISTRIBUTION** — This procedure should be used when a mechanical-property value is to be computed directly (not paired with another property for computational purposes) and the form of the distribution of population is unknown (not normal or three-parameter Weibull). Distribution should not be considered unknown (1) if tests show it to be nearly normal or three-parameter Weibull, (2) if it can be transformed to a nearly normal or three-parameter Weibull distribution, or (3) if it can be separated into nearly normal or three-parameter Weibull subpopulations. This procedure is applicable to  $F_{tu}$  and  $F_{ty}$ . It may also be used for  $F_{cy}$ ,  $F_{su}$ ,  $F_{bru}$ , and  $F_{bry}$  if sufficient quantity of data is available.

**9.2.9.1 Data Requirements** — Data must be adequate to assure that the sample is representative of the population. Although censoring is highly undesirable, parametric techniques will

**MIL-HDBK-5H**  
**1 December 1998**

“tolerate” a limited degree of censoring. In contrast, nonparametric techniques will not “tolerate” censoring. Determination of a  $T_{99}$  value requires at least 299 individual observations that represents 10 heats, casts, or melts, but additional data is very desirable. The selection of the number 299 is not arbitrary. Rather, 299 represents the smallest sample for which the lowest observation is a tolerance bound,  $T_{99}$ . For smaller samples,  $T_{99}$  is below the lowest observation and thus cannot be determined without knowledge of the form of population distribution. The lowest of 29 observations is a tolerance bound. The  $T_{90}$  value can be computed with a minimum of 29 observations provided these observations represent 10 heats, casts, or melts. However, the B-basis property is not included in the Handbook without the A-basis property. The requirement for number of heats or lots for the sample is comparable to that required for a parametric analysis.

**9.2.9.2 Computational Procedure** — Nonparametric (or distribution-free) data analysis assumes a random selection of test points and uses only the ranks of individual test points and the total number of test points. If test points have been deleted from a sample, the random basis is violated; consequently, this procedure must not be used when there is reason to suspect that the sample may have been censored.

As an example, assume that a sample consists of 299 test points selected in a random manner. The test point having the lowest value has rank 1, the test point having the next lowest value has rank 2, etc. Thus, an array of ranked test points might appear as follows:

<u>Rank of Test Point</u>	<u>Value of Test Point, ksi</u>
1	73.3
2	74.1
3	75.2
4	75.3
5	75.6
299	85.7

For each rank from a sample of size,  $n$ , it is possible to predict, with 0.95 confidence, the least fraction of population that exceeds the value of the test point having rank  $r$ . Since only two fractions, or probabilities, are of interest in determination of  $T_{99}$  and  $T_{90}$  values, only the ranks of test points having the probability and confidence of  $T_{99}$  and  $T_{90}$  values are presented in Table 9.6.4.2. To use this table with a sample size of 299, for example, one would designate the value of the lowest ( $r=1$ ) test measurement as  $T_{99}$  and the 22nd lowest ( $r=22$ ) test measurement as  $T_{90}$ . For sample sizes between tabulated values, interpolation is permissible. For sample sizes smaller than 299,  $T_{99}$  is smaller than the value of the lowest point and cannot be determined in this manner.

When the lower tolerance bound ( $T_{99}$  or  $T_{90}$ ) results in a fractional number, the actual mechanical property value used in the room temperature tables is determined by rounding. Fractions greater than 0.75 usually are raised to the next larger integer while less decimal fractions are disregarded. *However, the rounded  $T_{99}$  value is replaced in the mechanical property tables with the  $S$  value if the  $S$  value is lower.* In that case the rounded  $T_{99}$  value is included in a footnote.

**9.2.10 COMPUTATION OF DERIVED PROPERTIES** — Ideally, it is desirable to determine  $F_{cy}$ ,  $F_{su}$ ,  $F_{bru}$ ,  $F_{bry}$ , as well as  $F_{tu}$  and  $F_{ty}$  in other than specified test direction by direct computation as described in Sections 9.2.7 through 9.2.9, and, if sufficient quantity of data is available, direct computation procedures shall be used. Unfortunately, the cost of generating required data for these properties is usually prohibitive. Consequently, this section describes an indirect method of computation to determine the mechanical property values.

**MIL-HDBK-5H**  
**1 December 1998**

A derived property is a mechanical property value determined by its relationship to an established tensile property ( $F_{tu}$  or  $F_{ty}$ , A, B, or S-basis). This indirect method of computation is applicable to  $F_{tu}$  and  $F_{ty}$  in grain directions other than the specified testing direction, as delineated in the applicable material specification, and for all grain directions for  $F_{cy}$ ,  $F_{su}$ ,  $F_{bru}$ , and  $F_{bry}$ .

The procedure involves pairing of TUS, SUS, or BUS measurements with TUS measurements for which  $F_{tu}$  has been established or the pairing of TYS, CYS, and BYS measurements with TYS measurements for which  $F_{ty}$  has been established. Average values for each lot shall be used when more than one measurement per lot is available.

This technique is based on the premise that the mean ratio of paired observations representing related properties provides an estimate of the ratio of corresponding population means. The ratio consists of measurements of the property to be derived as the numerator and measurement of the established tensile property as the denominator. Thus, TUS or TYS in the specified testing direction always appears in the denominator of the ratio of observed values.

Grain direction to be used for the denominator is the specified test direction as delineated in the applicable material specification. For most materials, routine quality control (certification) tests are usually conducted only in one grain direction even though the specification may contain mechanical property requirements for two or three grain directions. For guidance, specified or primary test direction for different product forms of each alloy system is shown in Table 9.2.10.

**Table 9.2.10. Primary<sup>a</sup> Testing Direction for Various Alloy Systems**

Product Form	Carbon and Low Alloy Steels	Non-Heat Treatable Alum. Alloys	Heat Treatable Alum. Alloys	Magnesium Alloys	Titanium Alloys	Corrosion and Heat Resistant Alloys	Other Alloys
Sheet and Plate	LT	L	LT	L	<sup>d</sup>	LT	<sup>b</sup>
Bar	L	L	L	L	<sup>d</sup>	L	<sup>b</sup>
Tubing	L	L	L	L	L	L	<sup>b</sup>
Extrusion	L	L	L	L	<sup>d</sup>	L	<sup>b</sup>
Die Forging	<sup>b</sup>	L	L <sup>c</sup>	L	<sup>d</sup>	<sup>b</sup>	<sup>b</sup>
Hand Forging	<sup>b</sup>	LT	LT	LT	<sup>d</sup>	<sup>b</sup>	<sup>b</sup>

- a Although material specifications may contain mechanical-property requirements for two or three grain directions, the primary test direction indicates the grain direction which is tested regularly.
- b See applicable material specification.
- c Although material specifications require testing in both L and T directions, the T direction by definition includes all orientations not within  $\pm 15^\circ$  of parallel to grain flow. Hence, the L direction is preferred for analytical purposes.
- d Since there is no primary test direction for titanium alloys, mechanical property ratios shall be formed using strength values which represent the same grain directions in the numerator and denominator. The design allowable is computed as the product of the reduced ratio and the  $F_{ty}$  or  $F_{tu}$  value for the grain direction represented by the reduced ratio.

**9.2.10.1 Data Requirements** — Computation of a derived value for each significant test direction requires at least ten paired measurements from ten lots of material obtained from at least two production heats, casts, or melts for each product form and heat-treat condition or temper. See Section 9.1.6.2 for definitions of lot, heat, cast, and melt. If two lots are from the same heat, cast, or melt and have the same product form and thickness, they must be heat-treated separately in order to constitute two lots.

**MIL-HDBK-5H**  
**1 December 1998**

Therefore, it is recommended that two lots with the same product form and thickness come from a different heat, cast, or melt.

The thicknesses of the ten lots shall span the thickness range of product form covered by the material specification. Test specimens for paired ratios shall be located in close proximity and shall be taken from the same sheet, plate, bar, extrusion, forging, or casting. If coupons or specimens are machined prior to heat treatment, all coupons or specimens from the same lot shall be heat treated simultaneously in the same heat-treat load through all heat-treating operations. Some or all of the lots may be heat treated together provided they are of the same product form that represent different thicknesses or heats, casts, or melts.

In the cases where multiple observations are available from a single lot, the average of those observations shall be treated as an individual observation. Since some variation in strength may be expected from one specimen location to another, use of lot averages minimizes the effect of this variable.

Dimensionally discrepant castings or special test configurations, as approved by the MIL-HDBK-5 Coordination Group, may be used for a test program to obtain mechanical properties for determination of derived values, providing these castings meet the requirements of the applicable material specification. Separately cast bars are not acceptable for use in obtaining mechanical properties.

**9.2.10.2 Procedure** — Four basic steps are involved in determining design allowable properties by indirect computation:

- (1) Determine the ratios of paired observations for each lot of material.
- (2) Compute the statistics,  $\bar{r}$  and  $s$ , for the ratios of paired observations.
- (3) Determine the lower confidence interval estimate (reduced ratio) for the mean ratio.
- (4) Use the reduced ratio as the ratio of the derived to the established design allowable.

The ratio of two paired observations is obtained by dividing the measurement of the property to be derived [for example, CYS (LT) for heat-treatable aluminum sheet] by the measurement for established tensile property [for example, TYS (LT)] in the specified testing direction. Equations for computing average and standard deviation of the ratios are the same as those in Section 9.2.2.3.

The ratio of the two population means [for CYS (LT) and TYS (LT), respectively] is expected to exceed the lower confidence limit defined as

$$\bar{r} - t_{1-\alpha} s / \sqrt{n} \quad [9.2.10.2(a)]$$

where

- $n$  is the number of ratios
- $\bar{r}$  is the average of  $n$  ratios
- $s$  is the standard deviation of the ratios
- $t_{1-\alpha}$  is the  $1-\alpha$  fractile of the  $t$  distribution for  $n - 1$  degrees of freedom. At the risk level of  $\alpha = 0.05$ , the appropriate  $t$  value is  $t_{0.95}$ .

Since the lower confidence interval estimate is used as the ratio between the design allowable properties, the reduced ratio,  $R$ , may be defined as

$$R = \bar{r} - t_{0.95} s / \sqrt{n} \quad [9.2.10.2(b)]$$

Values of  $t_{0.95}$  for various degrees of freedom,  $n - 1$ , are tabulated in Table 9.6.4.5.

**MIL-HDBK-5H**  
**1 December 1998**

The reduced ratio may now be used to establish the design allowable for the property to be derived using the example of aluminum sheet,

$$R = \frac{F_{cy}(LT)}{F_{ty}(LT)} = \frac{\text{allowable to be derived}}{\text{established allowable in specified test direction}} .$$

The derived allowable property is computed by cross multiplying:

$$F_{cy}(LT) = R F_{ty}(LT) .$$

The basis (A, B, or S) for computed or derived property is assumed to be the same as the basis for  $F_{ty}$  or  $F_{tu}$  tensile property in the right-hand side of the equation. If only the S-basis (integer) properties are available to compute the derived properties, these values must be used. However, the unrounded S-basis  $F_{ty}$  or  $F_{tu}$  values computed with the method in Section 9.1.6.8 must be used to compute the derived properties if there are 100 or more observations representing 10 heats, casts, or melts. When there are 100 or more observations, and the  $T_{99}$  and  $T_{90}$  values can be computed for  $F_{ty}$  or  $F_{tu}$ , these unrounded values must be used to compute the derived property values to ensure the proper statistical confidence in the derived values. The lower of either the S-basis value computed from Section 9.1.6.8 or the  $T_{99}$  value must be used to compute the A-basis derived properties.

In a sample of ratios for a given product, effect of thickness on the ratio should be examined. If there is no effect of thickness, ratios for the various thicknesses can be pooled to compute the average and reduced ratio. If there is an effect of thickness, then a regression with thickness should be computed and the average and reduced ratios determined from the regression. See Section 9.2.11.2 for procedure.

When the computed design allowable results in a fractional number, actual design allowable value used in room temperature tables is determined in the following manner. Fractions greater than 0.75 usually are raised to the next larger integer while lesser decimal fractions are disregarded.

**9.2.10.3 Treatment of Grain Direction** — Tensile properties are usually listed according to grain direction in material specifications although some specifications do not indicate a grain direction, which implies isotropy. For MIL-HDBK-5, it is recommended that tension properties be shown for each grain direction. When the material is shown to be isotropic, then the same properties should be shown for each direction.

Compression properties are shown by grain direction similar to tension properties. An example of computing compression properties for heat treatable plate is shown below. The reduced ratio,  $R$ , for longitudinal grain direction, is determined from ratios,  $r$ , formed from paired observations for each lot of material,  $CYS(L)/TYS(LT)$ . Although a longitudinal ratio is being obtained, the divisor is long transverse because this is the specified testing direction (refer to Table 9.2.10). The reduced ratio,  $R$ , for long transverse grain direction, is determined from ratios,  $r$ , formed from paired observations for each lot of material,  $CYS(LT)/TYS(LT)$ . Similarly the reduced ratios,  $R$ , for short transverse grain direction, are determined from ratios,  $r$ , formed from paired observations for each lot of material,  $CYS(ST)/TYS(LT)$ . The ratios,  $r$ , determined in the above manner are used in conjunction with Equation 9.2.10.2(b) to obtain a reduced ratio,  $R$ , for each grain direction. Equating the reduced ratios, design property values are determined from the resulting relationships,

$$R = \frac{F_{cy}(L)}{F_{ty}(LT)}$$



**MIL-HDBK-5H**  
**1 December 1998**

or  $F_{cy}(L) = RF_{ty}(LT)$

similarly  $F_{cy}(LT) = RF_{ty}(LT)$

and  $F_{cy}(ST) = RF_{ty}(LT)$  .

Shear and bearing properties are usually shown without reference to grain direction. These properties shall be analyzed according to grain direction, and design properties shall be based on the lowest reduced ratio obtained for longitudinal, long transverse and short transverse (when applicable) directions. An exception is aluminum hand forgings for which shear values shall be presented according to grain direction.

In computing wrought product derived properties, paired ratios representing different grain directions shall not be combined in the determination of a reduced ratio. This is based on the premise that, if the ratio for two paired measurements is to provide an estimate of population mean ratio, then paired measurements must represent the same grain direction as that of the corresponding population means.

For aluminum die forgings, the longitudinal grain direction is defined as orientations parallel, within  $\pm 15^\circ$ , to the predominate grain flow. The long transverse grain direction is defined as perpendicular, within  $\pm 15^\circ$ , to the longitudinal (predominate) grain direction and parallel, within  $\pm 15^\circ$ , to the parting plane. (Both conditions must be met.) The short transverse grain direction is defined as perpendicular, within  $\pm 15^\circ$ , to the longitudinal (predominate) grain direction and perpendicular, within  $\pm 15^\circ$ , to the parting plane. (Both conditions must be met.) When possible, compression, bearing, and shear tests for three grain directions shall be conducted.


**9.2.10.4 Treatment of Test Specimen Location** — Testing specifications require a change in test specimen location from  $t/2$  for  $\leq 1.500$ - to  $t/4$  for  $> 1.500$ -inch thickness for certain products. Although this change in specimen location may result in  $t/4$  mechanical property ratios which are significantly different from  $t/2$  ratios (different populations), as for aluminum plate, the  $t/2$  and  $t/4$  mechanical property ratios should be treated together for analysis to determine derived properties.

**9.2.10.5 Treatment of Clad Aluminum Alloy Plate** — For clad aluminum alloy plate, 0.500 inch and greater in thickness, tensile properties are determined using round tensile specimens; consequently, tensile properties represent core material. To present design values which represent the average tensile properties across the thickness of the clad plate, an adjustment must be made in the tensile yield and ultimate strength values (S- or A- and B-basis), representing core strength, in the primary test direction(s). These strengths shall be reduced by a factor equal to twice the percentage of the nominal cladding thickness per side. These adjustments in the tensile yield and ultimate strengths shall be made prior to the computation of derived properties, except for short transverse properties. The following footnote, flagged to the appropriate thickness ranges, shall be incorporated into the design allowable table: "These values, except in the ST direction, have been adjusted to represent the average properties across the whole section, including X percent per side nominal cladding thickness."

**9.2.10.6 Proposals** — Proposals presented to the MIL-HDBK-5 Coordination Group should include (1) proposed new or revised table of room-temperature allowables, (2) raw data used in the analysis, and (3) analysis for the proposed design values.

**9.2.11 DETERMINING DESIGN ALLOWABLES BY REGRESSION ANALYSIS** — Procedures used to determine design allowables by regression analysis vary from sample to sample and all involve a number of decisions. These decisions are illustrated by a flowchart in Figure 9.2.11. Before employing regression

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 9.2.11. General procedures for determining design allowables when regression is required.**

analysis in the determination of material properties, one must ascertain that the average of property to be regressed varies continuously and linearly or quadratically with some dimensional parameter  $x$  (such as  $x = t$ ,  $1/t$ , etc., where  $t$  is thickness). If the variation of average is attributable to other causes, regression should not be used.

Regression analysis, as described herein, also assumes that residuals are normally distributed about the regression line. Residuals are the differences between observed data values and the values which are predicted by the fitted regression equation. Validity of this normality assumption should be evaluated by performing the Anderson-Darling test presented in Section 9.6.1.2.

The procedure for fitting a regression equation of the form,

$$TUS = a + bx,$$



**MIL-HDBK-5H**  
**1 December 1998**

or

$$(SUS/TUS) = a + bx,$$

or

$$(SUS/TUS) = a + bx + cx^2,$$

to  $n$  data points is described in Section 9.6.3. In addition to estimates for  $a$  and  $b$  (and possibly  $c$ ), this procedure produces two  $F$  statistics. One statistic ( $F_1$ ) tests the significance of regression. The other statistic ( $F_2$ ) tests the adequacy of a linear model for describing the relationship between the material property and the dimensional parameter. If  $F_2$  indicates a lack of fit of the model to the data, a transformation of the data may account for the nonlinearity. If  $F_1$  indicates an insignificant regression, one of the other appropriate analysis techniques, as described in Sections 9.2.7, 9.2.8, 9.2.9, or 9.2.10, should be used.

The steps involved in determining design allowables by regression analysis are as follows:

- (1) Express the property as a simple linear (or quadratic) function of the dimensional parameter and obtain estimates of the coefficient using the least squares regression procedure in Section 9.6.3.1 (or Section 9.6.3.2); for example

$$TUS = a + bx$$

or

$$(SUS/TUS) = a + bx + cx^2$$

where  $x$  is thickness or area and  $a$ ,  $b$ , and  $c$  are constants from the least squares equation.

- (2) Determine the root mean square error of regression ( $s_y$ ). A convenient equation for computing the root mean square error from large quantities of data is shown in Section 9.6.3.1.
- (3) At selected values of  $x$ , determine the allowable for the property by the procedures described in Sections 9.2.11.1 or 9.2.11.2.

The procedures described in this section permit the determination of design allowables only for specific values of  $x$ . When it is desired to present a single allowable covering a range of product thickness (for example, 1.001- to 2.000-inch plate), the lowest allowable for the range should be used. Thus, if  $TUS(LT)$  decreases continuously with increasing thickness, the  $TUS(LT)$  corresponding to  $x = 2.000$  inches would be presented in MIL-HDBK-5. If the decrease is large, a decrease in product thickness interval can be made: for example, by splitting the 1.001- to 2.000-inch interval into two intervals of 1.001 to 1.500 and 1.501 to 2.000 inches.

When the computed design allowable results in a fractional number, actual design allowable value used in room temperature tables is determined in the following manner. Fractions greater than 0.75 usually are raised to the next larger integer while lesser decimal fractions are disregarded.

**9.2.11.1 Direct Computational Procedure**—The direct computational procedure takes into account errors in the model estimates. If a linear relationship has been determined, compute  $T_{99}$  for  $F_m$  at  $x = x_o$ , using Equation [9.2.11.1(a)]

$$T_{99} = a + bx_o - k'_{99}s_y \quad [9.2.11.1(a)]$$

where  $a$ ,  $b$ , and  $s_y$  are computed in the regression of  $TUS$  data,  $k'_{99}$  is  $\sqrt{(1+\Delta)/n}$  times the 95th percentile of the noncentral  $t$  distribution with noncentrality parameter  $2.326/\sqrt{(1+\Delta)/n}$  and  $n - 2$  degrees of freedom, and

**MIL-HDBK-5H**  
**1 December 1998**

$$\Delta = \frac{(x_o - \Sigma x/n)^2}{\Sigma(x - \Sigma x/n)^2/n} \quad [9.2.11.1(b)]$$

The equation for computing a  $T_{90}$  is similar with  $k'_{90}$  being used in place of  $k'_{99}$ .  $k'_{90}$  is  $\sqrt{(1+\Delta)/n}$  times the 95th percentile of the noncentral t distribution with noncentrality parameter  $1.282/\sqrt{(1+\Delta)/n}$  and  $n-2$  degrees of freedom, where  $\Delta$  is defined above. If calculation of the appropriate noncentral t percentile is not possible, the following approximations to  $k'_{99}$  and  $k'_{90}$  may be used:

$$k'_{99} = 2.326 + \exp\{0.659 - 0.514 \ln(n) + (0.481 - 1.42/n)\ln(3.71 + \Delta) + 6.58/n\} \quad [9.2.11.1(c)]$$

$$k'_{90} = 1.282 + \exp\{0.595 - 0.508 \ln(n) + (0.486 - 0.986/n)\ln(1.82 + \Delta) + 4.62/n\}. \quad [9.2.11.1(d)]$$

These approximations are accurate to within 1.0 percent for  $n \geq 10$  and  $\Delta \leq 10$ . The square root of  $\Delta$  is the number of standard deviations between  $x_o$  and the arithmetic mean of the x-values. Thus, a  $\Delta$  value of 10 would represent an extreme  $x_o$  value, which is more than three standard deviations from the mean x-value.

If a quadratic relationship has been determined, calculate  $T_{99}$  for  $F_{tu}$  at  $x = x_o$  using Equation [9.2.11.1(e)]

$$T_{99} = a + bx_o + cx_o^2 - \left( t_{0.95, n-3, \frac{2.326}{\sqrt{Q}}} \right) \sqrt{Q} s_y \quad [9.2.11.1(e)]$$

where a, b, c,  $s_y$ , and Q are computed by quadratic regression, and the factor  $t_{0.95, n-3, \frac{2.326}{\sqrt{Q}}}$  is the 95th percentile of the noncentral t distribution with noncentrality parameter  $2.326/\sqrt{Q}$  and  $n-3$  degrees of freedom.

To calculate  $T_{90}$  in the presence of a quadratic relationship, use Equation 9.2.11.1(f)

$$T_{90} = a + bx_o + cx_o^2 - \left( t_{0.95, n-3, \frac{1.282}{\sqrt{Q}}} \right) \sqrt{Q} s_y \quad [9.2.11.1(f)]$$

where a, b, c,  $s_y$ , and Q are computed by quadratic regression, and the factor  $t_{0.95, n-3, \frac{1.282}{\sqrt{Q}}}$  is the 95th percentile of the noncentral t distribution with noncentrality parameter  $1.282/\sqrt{Q}$  and  $n-3$  degrees of freedom.\*

**9.2.11.2 Reduced Ratio Computational Procedure** — Regression may also be used to determine reduced ratios when an allowable for a property, such as SUS, is computed indirectly from an already established allowable for TUS. The following assumptions are inherent to the reduced ratio procedure:

- (1) The two properties must be distributed according to a bivariate normal distribution.
- (2) The coefficient of variation must be the same for the two properties within particular bounds.
- (3) The average of the ratio of the two properties must be well described by a linear function of the independent variable.

---

\* Note that critical values for the noncentral t distribution are not tabulated in MIL-HDBK-5.

**MIL-HDBK-5H**  
**1 December 1998**

It is also important that paired data be available over the entire range of the dimensional parameter for which there is data for the direct property (TUS). Note that the confidence level associated with allowables computed using the reduced ratio technique may be somewhat below 95 percent.

To compute the reduced ratio at  $x = x_o$ , in the case of linear regression, use Equation [9.2.11.2(a)],

$$\text{Reduced Ratio} = a + bx_o - (t_{0.95, n-2}) s_y \sqrt{\frac{1+\Delta}{n}} \quad [9.2.11.2(a)]$$

where  $\Delta$  is defined in Equation 9.2.11.1(b),  $a$ ,  $b$ , and  $s_y$  are computed in the regression of SUS/TUS data, and  $t_{0.95, n-2}$  is selected from Table 9.6.4.5 corresponding to  $n-2$  degrees of freedom. The allowable for  $F_{su}$  at  $x_o$  is then computed as the product of the reduced ratio and the established allowable for  $F_{tu}$ :

$$F_{su} = (\text{Reduced Ratio})(F_{tu}) .$$

To compute the reduced ratio at  $x = x_o$ , in the case of quadratic regression, use Equation [9.2.11.2(b)],

$$\text{Reduced Ratio} = a + bx_o + cx_o^2 - t_{0.95, n-3} s_y \sqrt{Q} \quad [9.2.11.2(b)]$$

where  $a$ ,  $b$ ,  $c$ ,  $s_y$ , and  $Q$  are computed in the quadratic regression of SUS/TUS data, and  $t_{0.95, n-3}$  is selected from Table 9.6.4.5 corresponding to  $n-3$  degrees of freedom.

The allowable for  $F_{su}$  at  $x_o$  is then computed as the product of the reduced ratio and the established allowable for  $F_{tu}$ :

$$F_{su} = (\text{Reduced Ratio})(F_{tu}) .$$

**9.2.12 EXAMPLES OF COMPUTATIONAL PROCEDURES** — It is appropriate to review computational procedures described in Sections 9.2.4 through 9.2.11. To do so, a hypothetical set of input data has been invented. In progressing through this example, flow charts of Figures 9.2.3, 9.2.4, 9.2.6, and 9.2.11 have been followed, and appropriate references to specific sections of the guidelines have been made.

It is assumed for this example that a quantity of quality assurance test data has been amassed, representing one long transverse tensile test per lot, plus other tests from a portion of the lots, at a frequency of one test per lot.

The example problems presented fall into two major categories. Problems I through VII illustrate techniques based on an assumed underlying normal distribution. Problems VIII through XII provide illustrations of techniques based on an assumed underlying three-parameter Weibull distribution.

The input data for these example problems are described below. Because entire data sets (as opposed to means and standard deviations) are required for Problems VIII through XII, the data points for groups (1) through (4) and group (6) have been reported in Tables 9.2.12(a) through (c).

**MIL-HDBK-5H****1 December 1998****Table 9.2.12(a). Group (1) Data Set for Example Problems in Section 9.2.12**

Group (1)				
139.608	146.534	147.442	151.229	153.792
140.638	146.651	147.489	151.234	153.844
140.711	146.667	147.497	151.283	153.846
140.988	146.699	147.653	151.323	153.855
141.873	146.710	147.752	151.388	153.914
141.940	146.714	147.765	151.425	153.992
142.105	146.766	147.785	151.428	154.021
142.478	146.825	147.803	151.433	154.064
142.597	146.857	147.911	151.471	154.068
142.694	146.876	147.942	151.557	154.077
143.309	146.941	147.952	151.599	154.110
143.502	146.944	147.961	151.609	154.128
143.620	146.970	147.980	151.628	154.149
143.644	147.087	148.001	151.641	154.219
143.674	147.198	148.012	151.670	154.242
143.720	147.284	148.029	151.785	154.297
143.844	147.291	148.038	151.837	154.359
143.865	147.326	148.048	151.876	154.382
143.867	147.334	148.049	151.962	154.508
143.997	147.353	148.051	151.992	154.541
144.221	148.686	148.059	152.015	154.571
144.320	148.691	148.074	152.037	154.781
144.463	148.695	148.091	152.081	154.858
144.508	148.701	148.118	152.101	155.012
144.612	148.714	148.122	152.143	155.077
144.651	148.724	148.197	152.150	155.102
144.837	148.854	148.201	152.151	155.116
144.864	148.868	148.236	152.157	155.231
144.890	148.884	148.267	152.199	155.267
144.973	148.891	148.292	152.207	155.311
145.076	148.919	148.304	152.270	155.336
145.110	148.952	148.334	152.332	155.359
145.122	148.957	148.339	152.352	155.386
145.165	148.982	148.355	152.448	155.422
145.214	149.016	148.368	152.656	155.469
145.229	149.045	148.567	152.736	155.604
145.270	149.103	148.584	152.802	155.627
145.277	149.107	148.620	152.840	155.641
145.325	149.158	148.678	152.882	155.785
145.399	149.180	148.684	152.907	155.823
145.416	149.183	150.194	152.920	155.863
145.577	149.187	150.310	152.929	155.904
145.600	149.321	150.315	153.007	156.078
145.693	149.416	150.340	153.029	156.088
145.709	149.473	150.377	153.049	156.379
145.721	149.571	150.415	153.102	156.616
145.741	149.581	150.423	153.118	156.716
145.872	149.605	150.427	153.206	156.740
145.921	149.605	150.459	153.279	156.924
145.925	149.606	150.579	153.286	157.053
145.966	149.653	150.722	153.296	157.341
145.978	149.707	150.731	153.298	157.357
146.069	149.731	150.739	153.478	157.614
146.136	149.755	150.773	153.504	157.763
146.220	149.798	150.830	153.543	157.980
146.285	149.810	151.019	153.576	158.021
146.301	149.812	151.042	153.648	158.154
146.367	149.894	151.075	153.695	158.518
146.479	149.996	151.111	153.707	159.377
146.500	150.124	151.211	153.715	162.717

**MIL-HDBK-5H****1 December 1998****Table 9.2.12(b). Group (3) Data Set for Example Problems in Section 9.2.12**

Group (3)				
121.438	126.276	128.823	131.254	133.841
121.614	126.342	128.846	131.325	133.843
121.757	126.388	128.868	131.388	133.893
122.077	126.430	128.966	131.439	133.898
122.109	126.449	128.983	131.444	133.912
122.494	126.535	128.989	131.469	133.922
122.503	126.606	129.029	131.477	133.934
122.543	126.665	129.035	131.677	133.948
122.632	126.668	129.052	131.690	134.089
123.082	126.673	129.083	131.731	134.134
123.101	126.696	129.117	131.754	134.179
123.193	126.727	129.136	131.786	134.194
123.238	126.822	129.148	131.808	134.249
123.296	126.863	129.321	131.816	134.339
123.474	126.877	129.413	131.906	134.351
123.527	126.907	129.434	131.975	134.361
123.616	126.919	129.546	131.977	134.689
123.694	126.972	129.560	132.138	134.747
123.755	126.999	129.596	132.189	134.776
123.770	127.114	129.654	132.223	134.779
123.825	127.140	129.709	132.282	134.873
124.025	127.203	129.715	132.286	134.874
124.055	127.300	129.784	132.296	134.883
124.083	127.322	129.788	132.380	134.890
124.105	127.337	129.891	132.393	134.969
124.121	127.383	129.899	132.436	135.027
124.171	127.387	129.938	132.470	135.064
124.176	127.420	129.940	132.482	135.191
124.223	127.474	130.007	132.511	135.499
124.373	127.579	130.020	132.514	135.513
124.681	127.607	130.070	132.558	135.518
124.691	127.677	130.206	132.564	135.532
124.718	127.695	130.225	132.595	135.545
124.778	127.710	130.237	132.703	135.661
124.793	127.741	130.351	132.718	135.754
124.920	127.761	130.427	132.762	135.836
124.934	127.811	130.457	132.805	135.920
125.000	127.841	130.499	132.849	135.921
125.018	127.859	130.526	132.851	135.944
125.070	127.859	130.528	132.869	136.027
125.070	127.889	130.586	132.952	136.030
125.150	127.946	130.599	133.024	136.032
125.152	128.010	130.624	133.031	136.050
125.247	128.016	130.684	133.049	136.112
125.279	128.153	130.710	133.096	136.149
125.295	128.203	130.765	133.159	136.154
125.350	128.288	130.772	133.166	136.160
125.370	128.309	130.797	133.224	136.204
125.433	128.323	130.895	133.438	136.217
125.531	128.332	131.003	133.441	136.348
125.535	128.341	131.008	133.508	136.855
125.714	128.452	131.040	133.581	136.883
125.717	128.640	131.103	133.592	137.087
125.801	128.672	131.104	133.595	137.115
125.915	128.699	131.125	133.622	137.163
126.083	128.719	131.158	133.683	137.484
126.128	128.723	131.175	133.749	137.618
126.129	128.752	131.176	133.763	137.653
126.194	128.795	131.192	133.768	138.335
126.276	128.819	131.195	133.774	139.141

**MIL-HDBK-5H****1 December 1998****Table 9.2.12(c). Groups (2), (4), and (6) Data Sets for Example Problems in Section 9.2.12**

<u>Group (2)</u>	<u>Group (4)</u>	<u>Group (6)</u>	
141.914	120.487	135.373	145.061
143.980	122.271	135.500	145.072
145.110	124.167	135.775	145.082
145.681	124.622	136.450	145.082
145.829	124.672	137.114	145.331
145.919	125.280	137.241	145.460
145.981	125.862	137.900	145.606
148.412	126.332	138.916	145.626
148.694	128.860	139.158	145.754
148.772	129.158	139.307	145.785
148.831	129.179	139.626	145.802
148.965	130.238	139.827	145.876
149.197	130.782	139.839	146.091
149.761	130.985	140.022	146.096
150.150	131.612	140.461	146.159
151.472	131.642	140.957	146.302
151.746	132.129	141.083	146.303
152.089	132.147	141.149	146.447
152.564	132.812	141.435	146.797
152.737	133.388	141.473	146.937
152.798	133.716	141.518	146.967
153.857	134.127	141.582	147.149
153.930	135.787	141.592	147.224
154.012	135.836	141.731	147.305
154.024	136.235	141.937	147.500
154.153	136.770	142.125	147.657
155.637	137.068	142.138	147.675
157.118	137.901	142.298	147.833
162.241	137.919	142.441	148.084
164.426	138.017	142.785	148.556
		142.838	148.708
		142.859	148.954
		143.141	148.988
		143.180	149.082
		143.397	149.123
		143.426	149.590
		143.444	149.831
		143.558	149.974
		143.722	150.325
		143.886	151.484
		144.200	151.523
		144.276	151.605
		144.313	152.086
		144.418	152.467
		144.465	152.646
		144.650	152.852
		144.672	153.164
		144.847	153.675
		144.901	155.492
		144.924	157.944

**MIL-HDBK-5H****1 December 1998****INFORMATION FOR EXAMPLE PROBLEMS**

Material Identification: Alloy X sheet, annealed.

Specified Testing Direction: Long Transverse (LT)

Specified Properties:

 $\leq 0.125$  inch — $F_{tu}$  (LT) = 140 ksi,  $F_{ty}$  (LT) = 115 ksi;

0.126-0.249 inch —

 $F_{tu}$  (LT) = 135 ksi,  $F_{ty}$  (LT) = 110 ksi.

Available Test Results:

Group (1). 300 observations of TUS(LT) for thickness range 0.020-0.125 inch from Supplier A; no variation with thickness. Go to Problems I, III, VIII, and X.

Group (2). 30 observations of TUS(LT) for thickness range 0.020-0.125 inch from Supplier B; no variation with thickness. Go to Problems I and VIII.

Group (3). 300 observations of TYS(LT) for thickness range 0.020-0.125 inch from Supplier A; no variation with thickness. Go to Problems II and IX.

Group (4). 30 observations of TYS(LT) for thickness range 0.020-0.125 inch from Supplier B; no variation with thickness. Go to Problems II and IX.

Group (5). 30 observations of SUS(LT) for thickness range 0.020-0.249 inch; apparent decrease in SUS(LT) on increasing thickness; observations may be paired with TUS(LT) if desired. Go to Problem VII.

Group (6). 100 observations of TUS(LT) for thickness range 0.126-0.249 inch; no variation with thickness. Go to Problems III and X.

**EXAMPLE PROBLEMS BASED ON AN  
ASSUMED UNDERLYING NORMAL DISTRIBUTION\***

**PROBLEM I**

*Should the data in Groups (1) and (2) be combined?*

Other Information: Neither property varies with thickness. Sample statistics are:

Subpopulation	n	$\bar{X}$ , ksi	s, ksi
Group (1) TUS (LT), 0.020 to 0.125	300	150.0	4.00
Group (2) TUS (LT), 0.020 to 0.125	30	151.0	5.00

(Refer to Sections 9.2.4 and 9.6.2.)

---

\* The statistical tests described in Problems I through III apply specifically to the case where normality can be assumed. The more general Anderson-Darling procedure described in Problem IV can be applied to normal as well as nonnormal distributions.

**MIL-HDBK-5H**  
**1 December 1998**

*Prob. I—Step 1. Test to determine whether the variances differ significantly:*

$$F = (s_1)^2/(s_2)^2 = (4.00)^2/(5.00)^2 = 0.64$$

Degrees of freedom, numerator =  $n_1 - 1 = 300 - 1 = 299$ .

Degrees of freedom, denominator =  $n_2 - 1 = 30 - 1 = 29$ .

$$F_{0.975}(299,29\text{df}) \text{ from Table 9.6.4.4} = 1.87 \text{ (approximately)}$$

$$1/F_{0.975} (29,299\text{df}) = 1/1.69 = 0.59$$

Since the computed value of  $F(0.64)$  lies within the 0.95 confidence interval (0.59 to 1.87), conclude the variances do not differ significantly.

*Prob. I—Step 2. Test to determine whether the averages differ significantly:*

Difference between averages  $D_{\bar{X}} = 150.0 - 151.0 = 1.0 \text{ ksi}$

$$u = t_{0.975} S_p \sqrt{\frac{n_1 + n_2}{n_1 n_2}}$$

Degrees of freedom =  $n_1 + n_2 - 2 = 300 + 30 - 2 = 328$

$t_{0.975} (328 \text{ df}) \text{ from Table 9.6.4.5} = 1.969$

$$S_p = \sqrt{\frac{(n_1 - 2) s_1^2 + (n_2 - 1) s_2^2}{n_1 + n_2 - 2}} = \sqrt{\frac{(300 - 1)(4.00)^2 + (30 - 1)(5.00)^2}{300 + 30 - 2}} = 4.10 \text{ ksi}$$

$$u = 1.969 \times 4.10 \times \sqrt{\frac{n_1 + n_2}{n_1 n_2}} = 1.969 \times 4.10 \times \sqrt{\frac{300 + 30}{300 \times 30}} = 1.54 \text{ ksi}$$

Since the observed difference between the averages,  $\bar{X}$  (1.0 ksi), is less than  $u$  (1.54 ksi), conclude the averages do not differ significantly.

*Prob. I—Step 3. Since there is no reason to conclude that the subpopulations represented by Groups (1) and (2) do not belong to the same population, combine these groups.*

Subpopulation	$\bar{n}$	$\bar{X}$ , ksi	$s$ , ksi
Group (1&2) TUS (LT), 0.020-0.125, Suppliers A and B	330	150.1	4.10

Go to Problem IV.



**MIL-HDBK-5H****1 December 1998****PROBLEM II**

*Should the data in Groups (3) and (4) be combined?*

Other Information: Neither property varies with thickness. Sample statistics are:

Subpopulation	n	$\bar{X}$ , ksi	s, ksi
Group (3) TYS (LT), 0.020-0.125, Supplier A	300	130.0	4.00
Group (4) TYS (LT), 0.020-0.125, Supplier B	30	131.0	5.00

The steps involved in this problem are identical to those in Problem I and similar conclusions were obtained from the input, namely, that Groups (3) and (4) should be combined. The sample statistics for the combined groups are:

Subpopulation	n	$\bar{X}$ , ksi	s, ksi
Group (3&4) TYS (LT), 0.020-0.125, Suppliers A and B	330	130.1	4.10

Go to Problem V.

**PROBLEM III**

*Should the data in Groups (1) and (6) be combined?*

Other Information: Neither property varies with thickness. Sample statistics are:

Subpopulation	n	$\bar{X}$ , ksi	s, ksi
Group (1) TUS (LT), 0.020-0.125	300	150.0	4.00
Group (6) TUS (LT), 0.126-0.249	100	145.0	4.47

*Prob. III—Step 1. Test to determine whether the variances differ significantly.*

$$F = (s_1)^2 / (s_2)^2 = (4.00)^2 / (4.47)^2 = 0.80$$

$$\text{Degrees of freedom, numerator} = n_1 - 1 = 300 - 1 = 299.$$

$$\text{Degrees of freedom, denominator} = n_6 - 1 = 100 - 1 = 99.$$

$$F_{0.975} (299, 99\text{df}) \text{ from Table 9.6.4.4} = 1.46 \text{ (approximately)}$$

$$1/F_{0.975} (99, 299\text{df}) = 1/1.43 = 0.700.$$

Since the computed value of F (0.80) lies within the 0.95 confidence interval (0.700 to 1.46), conclude that the variances do not differ significantly.

**MIL-HDBK-5H****1 December 1998**

*Prob. III—Step 2. Test to determine whether the averages differ significantly.*

Difference between averages,  $D_{\bar{x}} = (150.0 - 145.0) = 5.0$  ksi

$$u = t_{0.975} S_p \sqrt{\frac{n_1 + n_6}{n_1 n_6}}$$

Degrees of freedom =  $n_1 + n_6 - 2 = 300 + 100 - 2 = 398$ .

$t_{0.975}$  (398 df) from Table 9.6.4.5 = 1.968.

$$S_p = \sqrt{\frac{(n_1 - 1)s_1^2 + (n_6 - 1)s_6^2}{n_1 + n_6 - 2}} = \sqrt{\frac{(300 - 1)(4.00)^2 + (100 - 1)(4.47)^2}{300 + 100 - 2}} = 4.20 \text{ ksi}$$

$$u = (1.968)(4.20) \sqrt{\frac{n_1 + n_6}{n_1 n_6}} = (1.968)(4.20) \sqrt{\frac{300 + 100}{(300)(100)}} = 0.95 \text{ ksi}$$

Since the observed difference between the averages  $D_{\bar{x}}$  (5.0 ksi) is greater than  $u$  (0.95 ksi), conclude that the averages differ significantly and that the subpopulations represented by Groups (1) and (6) do not belong to the same population.

*Prob. III—Step 3. Do not combine the sample statistics for these groups.*

Go to Problem VI.

**PROBLEM IV**

*What computational method should be used for the combined observations of Groups (1) and (2)?*

Other Information: This property does not vary with thickness. Sample statistics for the combined observations are:

Population	n	$\bar{X}$ , ksi	s, ksi
Group (1&2) TUS (LT), 0.020-0.125	330	150.1	4.10

Form of the distribution has not been determined. (Refer to Sections 9.2.5, 9.2.6, 9.2.7, and 9.6.1.)

The sample is large enough to permit direct computation of A and B values. Consequently, the computational method will be determined by whether or not the observations are normally distributed.

*Prob. IV—Step 1. Test to determine whether the distribution is normal.* The Anderson-Darling test for normality will be employed in this example (see 9.6.1.2). Use the formula:

$$Z_{(i)} = (X_{(i)} - 150.1)/4.10,$$

**MIL-HDBK-5H****1 December 1998**

the values of  $Z_{(1)}, \dots, Z_{(330)}$  must be calculated. The first three values are  $Z_{(1)} = -2.56$ ,  $Z_{(2)} = -2.31$ , and  $Z_{(3)} = -2.29$ . Now  $F_0(Z_{(1)}), \dots, F_0(Z_{(330)})$  must be calculated by finding the area under the standard normal curve to the left of each  $Z$  value. The first three values are  $F_0(Z_{(1)}) = 0.0052$ ,  $F_0(Z_{(2)}) = 0.0104$ , and  $F_0(Z_{(3)}) = 0.0110$ .

The Anderson-Darling test statistic is then calculated as

$$AD = \left[ \sum_{i=1}^{330} \frac{1 - 2i}{330} [\ln(F_0(Z_{(i)})) + \ln(1 - F_0(Z_{(331-i)}))] \right] - 330 = 0.693.$$

The computed value of the test statistic is then compared to the critical value

$$0.750 = 0.752/[1 + 0.75/330 + 2.25/(330)^2]$$

Since the computed value of 0.693 is less than the critical value of 0.750, the hypothesis of normality is not rejected.

*Prob. IV—Step 2. Compute  $F_{tu}(LT)$ , 0.020 to 0.125, for Alloy X, using procedures for the normal distribution.*

Population	n	$\bar{X}$ , ksi	s, ksi
Group (1&2) TUS (LT), 0.020 to 0.125	330	150.1	4.10

$$k_A = 2.512$$

$$k_B = 1.410$$

$$F_{tu}(LT), A \text{ basis} = X - k_A s = 150.1 - 2.512 \times 4.10 = 139.8 \text{ or } 140 \text{ ksi (rounded per Section 9.2.10.2)}$$

$$F_{tu}(LT), B \text{ basis} = X - k_B s = 150.1 - 1.410 \times 4.10 = 144.3 \text{ or } 144 \text{ ksi (rounded per Section 9.2.10.2)}$$

**PROBLEM V**

*What computational method should be used for the combined observations of Groups (3) and (4)?*

Other Information: This property does not vary with thickness. Sample statistics for the combined observations are:

Population	n	$\bar{X}$ , ksi	s, ksi
Group (3&4) TYS(LT), 0.20 to 0.125	330	130.1	4.10

Form of the distribution has not been determined. (Refer to Sections 9.2.5, 9.2.6, 9.2.9, and 9.6.1.)

The sample is large enough to permit direct computation of A and B-values. Consequently, the computational method to be used will be determined by whether or not the observations are normally distributed.

*Prob. V—Step 1. Test to determine whether or not the distribution is normal.* The value of the Anderson-Darling test statistic for normality is 1.315 for Group (3&4). Since 1.315 is greater than the critical value of 0.750, the underlying distribution cannot be assumed to be normal. Thus, the underlying distribution will be treated as a three-parameter Weibull or an unknown distributional form.

**MIL-HDBK-5H****1 December 1998**

*Prob. V—Step 2. Compute  $F_y(LT)$ , 0.020-0.125, using procedures for the unknown distribution. This procedure requires the ranking of observations from lowest to highest. Referring to Table 9.6.4.2, it is found that for a sample size of 330, the lowest observation (rank = 1) is an A-value and the 24th lowest (rank = 24) is a B-value. The 24 lowest observations are shown below:*

Rank	TYS, ksi	Rank	TYS, ksi	Rank	TYS, ksi
1	120.5	9	122.5	17	123.5
2	121.4	10	122.5	18	123.5
3	121.6	11	122.6	19	123.6
4	121.8	12	123.1	20	123.7
5	122.1	13	123.1	21	123.8
6	122.1	14	123.2	22	123.8
7	122.3	15	123.2	23	123.8
8	122.5	16	123.3	24	124.0

Consequently, from these data the following allowables have been computed for Alloy X:

$F_y(LT)$ , A-basis = 120.5 ksi.

$F_y(LT)$ , B-basis = 124.0 ksi.

**PROBLEM VI**

*What computational procedure should be used for the observations in Group (6)?* The data in Group (6) represent a borderline situation. They cannot be combined with data for lesser thicknesses because there is significant difference between the TUS(LT) averages for the two thickness ranges, as shown in Problem III. The sample size is just barely adequate for direct computation if the distribution is found to be normal. If the distribution is not normal, the properties for this product would be presented on an S-basis, pending the accumulation of more data. The test for normality would be conducted as described in Problem IV, and will not be illustrated here.

**PROBLEM VII**

*What computational procedure should be used for the observations in Group (5)?*

Other Information: SUS(LT) decreases with increasing thickness, while TUS(LT) does not vary with thickness. Sample statistics are:

Population	n	$\bar{X}$ , ksi	s, ksi
Group (5) SUS(LT), 0.020 to 0.249	30	not determined	

The sample size for these data is too small to permit direct computation. Thus, the procedure that should be used is indirect computation by pairing observations of SUS(LT) with observations of TUS(LT). Also, since a thickness effect was suspected in the original data, a regression against thickness should be made and checked for significance. (Refer to Sections 9.2.10, 9.2.11, and 9.6.3.)

**MIL-HDBK-5H****1 December 1998**

*Prob. VII—Step 1. Pair SUS(LT) with TUS(LT).*

Ratios of SUS(LT)/TUS(LT) are as follows:

SUS(LT)/TUS(LT)	Thickness, inch	SUS(LT)/TUS(LT)	Thickness, inch
0.700	0.020	0.640	0.090
0.680	0.020	0.650	0.090
0.660	0.020	0.660	0.090
0.660	0.030	0.630	0.100
0.670	0.030	0.650	0.100
0.680	0.030	0.670	0.100
0.650	0.040	0.640	0.150
0.670	0.040	0.630	0.150
0.690	0.040	0.620	0.150
0.650	0.060	0.610	0.180
0.660	0.060	0.630	0.180
0.670	0.060	0.650	0.180
0.640	0.070	0.600	0.240
0.660	0.070	0.610	0.240
0.680	0.070	0.620	0.240

*Prob. VII—Step 2. Determine regression equation in the form  $[SUS(LT)/TUS(LT)]' = r' = a + bx$ , where  $x$  = thickness, using least-squares techniques. (Note—in this example, the letter  $r$ , rather than  $y$ , is used to denote the dependent variable and the prime (') is used to indicate that the ratio is determined by regression.) The following sums were obtained from analysis of the ratios plotted in Figure 9.2.12.*

Number of ratios,  $n = 30$

$\sum(x)$	= 2.94	$(\sum r)^2$	= 381.4209
$\sum(x^2)$	= 0.4260	$(\sum x)(\sum r)$	= 57.4182
$\sum(r)$	= 19.53	$S_{xx}$	= 0.1379
$\sum(r^2)$	= 12.7319	$S_{xr}$	= 0.0416
$\sum(xr)$	= 1.8723	$S_{rr}$	= 0.0179
$(\sum x)^2$	= 8.6436		


Referring to the equations presented in Section 9.6.3:

$$\text{Slope, } b = \frac{S_{xr}}{S_{xx}} = \frac{-0.0416}{0.1379} = -0.302$$

$$\text{Intercept, } a = \frac{\sum r - b(\sum x)}{n} = \frac{19.53 - (-0.302)(2.94)}{30} = 0.6806$$

## MIL-HDBK-5H

1 December 1998



**Figure 9.2.12. Ratios of input data for Problem VII.**

Standard Error of Estimate,

$$s_r' = \sqrt{\frac{S_{rr} - b^2 S_{xx}}{(n - 2)}}$$

$$= \sqrt{\frac{0.0179 - (-0.302)^2(0.1379)}{(30 - 2)}}$$

$$E = 0.014$$

The equation of the regression line is  $r' = 0.6806 - 0.302x$ .

The regression line is shown in Figure 9.2.12.

*Prob. VII—Step 3. Perform an analysis of variance to check the significance and linearity of the regression.*

Since there are 30 ratios, the analysis of variance approach rather than the method involving the computation of confidence limits on the slope term can be used to evaluate linearity.

The only information missing from Step 2 required for the analysis of variance is the values of T, or the summed values of r for each x. They are as follows:

**MIL-HDBK-5H**  
**1 December 1998**

$x_1$	$T_1$	$x_1$	$T_1$
0.02	2.04	0.09	1.95
0.03	2.01	0.10	1.95
0.04	2.01	0.15	1.89
0.06	1.98	0.18	1.89
0.07	1.98	0.24	1.83

Using these values, the analysis of variance, which is illustrated in Section 9.6.3.2, can be completed as follows:

Source of Variation	Sum of Squares	Degrees of Freedom	Mean Squares	$F_{calc}$
Regression	0.0126	1	0.0126	63.0
Error	0.0053	28	0.0002	
<hr/>				
Lack of Fit	0.0004	8	0.00005	0.208
Pure Error	0.0049	20	0.00024	
<hr/>				
Total	0.0179	29		

The second calculated F statistic of 0.208 with  $k - 2 = 8$  and  $n - k = 20$  degrees of freedom is less than the value of 2.45 from Table 9.6.4.9 corresponding to 8 numerator and 20 denominator degrees of freedom. Thus, the deviation from linearity is not significant. The first F statistic of 63.0 with 1 and 28 degrees of freedom is greater than the value of 4.20 from Table 9.6.4.9 corresponding to 1 numerator and 28 denominator degrees of freedom, so the slope of the regression is found to be significantly different from zero.

*Prob. VII—Step 4. Compute the reduced ratio for SUS(LT)/TUS(LT).* In performing this step, the reduced ratio will be computed at each of four thicknesses (0.020, 0.062, 0.125, and 0.249 inch). This is done by determining the lower confidence limit for the regression line at the desired thicknesses, using the equation from Section 9.2.11. The computation will be worked in detail for  $x_0 = 0.020$  inch:

$$\text{Reduced ratio} = [\text{SUS(LT)/TUS(LT)}]' - t_{0.95} s'_r \sqrt{\frac{1}{n} + \frac{(x_0 - \sum x/n)^2}{(\sum x^2) - (\sum x)^2/n}}$$

$$[\text{SUS(LT)/TUS(LT)}]' = r' = 0.681 - 0.302x_0 \text{ (from Step 2, Problem VII)} \\ = 0.681 - 0.302 \times 0.020 = 0.6746.$$

$$t_{0.95} \text{ (for } n - 2 = 30 - 2 = 28 \text{ degrees of freedom)} = 1.701 \text{ (from Table 9.6.4.5)}$$

$$s'_r = 0.014 \text{ (from Step 2)}$$

**MIL-HDBK-5H****1 December 1998**

$$\sqrt{\frac{1}{n} + \frac{(x_0 - \sum x/n)^2}{(\sum x^2) - (\sum x)^2/n}} = \sqrt{\frac{1}{30} + \frac{(0.020 - 2.94/30)^2}{0.4260 - 8.6436/30}} = 0.2783$$

Reduced ratio = 0.6746 - 1.701 x 0.014 x 0.2783 = 0.668.

The corresponding ratios for the other thicknesses are tabulated in Step 5. See Figure 9.2.12 for lower confidence limit curve.

*Prob. VII—Step 5. Compute  $F_{su}$ .* This computation will be illustrated for a thickness of 0.020 inch, using the reduced ratio from Step 4.

From Problem IV,

$F_{tu}(\text{LT})$	=	140 ksi (A-basis)
$F_{tu}(\text{LT})$	=	144 ksi (B-basis)
$F_{su}(\text{LT})$	=	Reduced Ratio x $F_{tu}(\text{LT})$
$F_{su}(\text{LT})(\text{A-Basis})$	=	0.668 x 140 = 93.5 ksi
$F_{su}(\text{LT})(\text{B-Basis})$	=	0.668 x 144 = 96.2 ksi.

For the four thicknesses listed,

t, inch	Reduced Ratio	$F_{su}(\text{LT}), \text{ksi}$		
		A-basis	B-basis	S-basis
0.020	0.668	93.5	96.2	...
0.062	0.657	92.0	94.6	...
0.125	0.638	89.3	91.9	...
0.249	0.595	...	...	80.3

Since  $F_{su}$  is shown to decrease with increasing thickness, only the lowest value applicable to the range should be presented in MIL-HDBK-5. By dividing the 0.020 to 0.125 thickness range into two ranges, a somewhat higher  $F_{su}(\text{LT})$  value may be presented for thinner material as shown below.

The results of the computations in Problems I through VII have produced the following results (fractions greater than 0.75 are raised to the next higher ksi, while less fractions are dropped):

Basis	Thickness, inch					
	<0.020	0.020-0.062		0.063-0.125		0.126-0.249
	S	A	B	A	B	S
$F_{tu}$ (LT), ksi	140	140	144	140	144	135
$F_{ty}$ (LT), ksi	115	120	124	120	124	110
$F_{su}$ , ksi	...	92	94	89	92	80

Since SUS(LT) data were not available for thickness <0.020 inch, a design value is not presented for this range.



**MIL-HDBK-5H****1 December 1998****EXAMPLE PROBLEMS BASED ON AN ASSUMED UNDERLYING  
THREE-PARAMETER WEIBULL DISTRIBUTION****PROBLEM VIII**

*Should the data in Groups (1) and (2) be combined?*

Other Information. Neither property varies with thickness. (Refer to Sections 9.2.4 and 9.6.2.)

The k-sample Anderson-Darling test will be employed in this example (see Section 9.6.2.5) to determine whether or not the data in Groups (1) and (2) should be combined. There are 328 distinct values in the combined data from both groups and these are ordered from least to greatest to obtain  $Z_{(1)}, \dots, Z_{(328)}$ . All values of  $h_j$  are equal to 1 except for  $h_{34} = 2$  and  $h_{160} = 2$ . Taking Group (2) to be the first ( $A_1$ )-sample and Group (1) to be the second ( $A_2$ )-sample, the first 24 Z-values are listed in the table below with the corresponding H- and F-values.

$Z_j$	$H_j$	$F_{ij}$	$Z_j$	$H_j$	$F_{ij}$	$Z_j$	$H_j$	$F_{ij}$
139.61	0.5	0	142.48	8.5	1	143.72	16.5	1
140.64	1.5	0	142.60	9.5	1	143.84	17.5	1
140.71	2.5	0	142.69	10.5	1	143.86	18.5	1
140.99	3.5	0	143.31	11.5	1	143.87	19.5	1
141.87	4.5	0	143.50	12.5	1	143.98	20.5	1.5
141.91	5.5	0.5	143.62	13.5	1	144.00	21.5	2
141.94	6.5	1	143.64	14.5	1	144.22	22.5	2
142.10	7.5	1	143.67	15.5	1	144.32	23.5	2

The k-sample Anderson-Darling test statistic is calculated as

$$ADK = \frac{1}{330(1)} \left[ \frac{1}{300} \sum_{j=1}^{328} h_j \frac{(330F_{1j} - 300H_j)^2}{H_j(330 - H_j) - 330h_j/4} + \frac{1}{30} \sum_{j=1}^{328} h_j \frac{(330F_{2j} - 30H_j)^2}{H_j(330 - H_j) - 330h_j/4} \right] = 0.821$$

The computed value of the test statistic is compared to the critical value of

$$2.488 = 1 + 0.759 \left( 1.645 + \frac{0.678}{\sqrt{1}} - \frac{0.362}{1} \right) .$$

Since the computed value of 0.821 is less than the critical value of 2.488, the hypothesis that the populations from which these groups were drawn are identical is not rejected. Thus Groups (1) and (2) will be combined for the computation of allowables.

Go to Problem XI.

**MIL-HDBK-5H****1 December 1998****PROBLEM IX**

*Should the data in Groups (3) and (4) be combined?*

Other Information: Neither property varies with thickness. (Refer to Sections 9.2.4 and 9.6.2.)

The value of the k-sample Anderson-Darling test statistic for Groups (3) and (4) is 2.147. Since 2.147 is less than the critical value of 2.488, the hypothesis that the populations from which these groups were drawn are identical is not rejected. Thus, Groups (3) and (4) will be combined for the computation of allowables.

Go to Problem XII.

**PROBLEM X**

*Should the data in Groups (1) and (6) be combined?*

Other Information: Neither property varies with thickness. (Refer to Sections 9.2.4 and 9.6.2.)

The k-sample Anderson-Darling test will be employed in this example (see Section 9.6.2.5). Taking Group (6) to be the first sample ( $A_1$ ) and Group (1) to be the second sample ( $A_2$ ), the k-sample Anderson-Darling test statistic is calculated as:

$$ADK = \frac{1}{400(1)} \left[ \frac{1}{100} \sum_{j=1}^{398} h_j \frac{(400 F_{1j} - 100 H_j)^2}{H_j(400 - H_j) 400 h_j/4} + \frac{1}{300} \sum_{j=1}^{398} h_j \frac{(400 F_{2j} - 300 H_j)^2}{H_j (400 - H_j) - 400 h_j/4} \right] = 44.195$$

Since the computed value of 44.195 is greater than the critical value of

$$2.486 = 1 + 0.758 \left( 1.645 + \frac{0.678}{\sqrt{1}} - \frac{0.362}{1} \right),$$

the hypothesis that the populations from which these groups are drawn are identical is rejected. Thus Groups (1) and (6) will not be combined for the calculation allowables.

**PROBLEM XI**

*What computational method should be used for the combined observations of Groups (1) and (2)?*

Other Information: This property does not vary with thickness.

Form of the distribution has not been determined. (Refer to Sections 9.2.5, 9.2.6, 9.2.8, and 9.6.1.4.)

The sample is large enough to permit direct computation of A and B-values. Consequently, the computational method will be determined by whether or not the observations may be assumed to follow a three-parameter Weibull distribution.

**MIL-HDBK-5H**  
**1 December 1998**

*Prob. XI—Step 1. Test to determine whether the distribution is a three-parameter Weibull distribution.* The Anderson-Darling test for three-parameter Weibullness will be employed in this example (see Section 9.6.1.4). Preliminary calculations give

$$\begin{aligned} K &= 88 & W_{50} &= 0.665 \\ \bar{X} &= 150.1 & S &= 4.10 \\ X_{(1)} &= 139.608 & H &= 139.6079 \\ L &= -259.9 \end{aligned}$$

$$R(\tau) = \frac{\sum_{i=89}^{262} L_i(\tau)}{\sum_{i=1}^{262} L_i(\tau)} \quad .$$

It can be verified that  $R(-259.9) > 0.665$  and  $R(139.6079) < 0.665$ . Solving the equation  $R(\tau) = 0.665$  with the initial interval  $(-259.9, 139.6079)$  gives  $\tau_{50} = 138.70$ . The function  $G_{50}(\beta_{50})$  then becomes

$$G_{50}(\beta_{50}) = \frac{1}{330} \sum_{i=1}^{330} \ln(X_i - 138.70) \left[ \left( \frac{X_i - 138.70}{\alpha_{50}} \right)^{\beta_{50}} - 1 \right] - \frac{1}{\beta_{50}}$$

where

$$\alpha_{50} = 10.53 \left[ \frac{1}{330} \sum_{i=1}^{330} \left( \frac{X_i - 138.70}{10.53} \right)^{\beta_{50}} \right]^{1/\beta_{50}}$$

Solving the equation  $G_{50}(\beta_{50}) = 0$  gives  $\beta_{50} = 3.02$  which in turn gives  $\alpha_{50} = 12.75$ .

The values of  $Z_{(1)}, \dots, Z_{(330)}$  are obtained using the formula

$$Z_i = \left( \frac{X_{(i)} - 138.70}{12.75} \right)^{3.02} \quad .$$

The first three Z-values are  $Z_{(1)} = 0.000345$ ,  $Z_{(2)} = 0.00339$ , and  $Z_{(3)} = 0.00378$ . The Anderson-Darling test statistic is calculated as

$$AD = \sum_{i=1}^{330} \frac{1 - 2i}{330} \left[ \ln(1 - \exp(-Z_{(i)})) + \ln(\exp(-Z_{(331-i)})) \right] - 330 = 0.491 \quad .$$

The computed value of the test statistic is compared to the critical value

**MIL-HDBK-5H****1 December 1998**

$$0.749 = 0.757/(1 + 1/5\sqrt{330})$$

Since the computed value of 0.491 is less than the critical value of 0.749, the hypothesis that the observations follow a three-parameter Weibull distribution is not rejected.

*Prob. XI—Step 2. Compute  $F_m$  (LT), 0.020-0.125, for Alloy X, using procedures for the three-parameter Weibull distribution. Preliminary calculations give*

$$\begin{array}{ll} K = 88 & W_A = 0.698 \\ W_\beta = 0.678 & \bar{X} = 150.1 \\ S = 4.10 & X_{(1)} = 139.608 \\ H = 139.6079 & L = -259.9 \end{array}$$

$$R(\tau) = \sum_{i=89}^{262} L_i(\tau) / \sum_{i=1}^{262} L_i(\tau)$$

Solving the equation  $R(\tau) = 0.698$  with the interval  $(-259.9, 139.6079)$  gives  $\tau_A = 136.43$ . Solving  $R(\tau) = 0.678$  gives  $\tau_B = 137.98$ .

Solving the equation  $G_A(\beta_A) = 0$  gives  $\beta_A = 3.63$  which in turn gives  $\alpha_A = 15.14$ . Solving the equation  $G_B(\beta_B) = 0$  gives  $\beta_B = 3.22$  which in turn gives  $\alpha_B = 13.52$ .

Using the formulas from 9.2.8.4 the allowables are calculated as follows:

$$\begin{aligned} Q_A &= 15.14 (0.01005)^{1/3.63} = 4.263 \\ Q_B &= 13.52 (0.10536)^{1/3.22} = 6.719 \\ A &= 136.43 + 4.263 \exp(-7.259/3.63 \sqrt{330}) = 140.2 \\ B &= 137.98 + 6.716 \exp(-4.103/3.22 \sqrt{330}) = 144.2 \end{aligned}$$

**PROBLEM XII**

*What computational method should be used for the combined observations of Groups (3) and (4)?*

Other Information: This property does not vary with thickness.

Form of the distribution has not been determined. (Refer to Sections 9.2.5, 9.2.6, 9.2.8, and 9.6.1.4.)

The sample is large enough to permit direct computation of A and B values. Consequently, the computational method will be determined by whether or not the observations may be assumed to follow a three-parameter Weibull distribution.

*Prob. XII—Step 1. Test to determine whether the distribution is a three-parameter Weibull distribution. The Anderson-Darling test for three-parameter Weibullness will be employed in this example (see Section 9.6.1.4). Preliminary calculations give*

$$\begin{array}{ll} K = 88 & \\ \bar{X} = 130.1 & W_{50} = 0.665 \\ X_{(1)} = 120.487 & S = 4.10 \\ L = -279.9 & H = 120.4869 \end{array}$$

**MIL-HDBK-5H****1 December 1998**

$$R(\tau) = \sum_{i=89}^{262} L_i(\tau) / \sum_{i=1}^{262} L_i(\tau)$$

Solving the equation  $R(\tau) = 0.665$  with initial interval  $(-279.9, 120.4869)$  gives  $\tau_{50} = 119.58$ . Solving the equation  $G_{50}(\beta_{50}) = 0$  gives  $\beta_{50} = 2.84$  which in turn gives  $\alpha_{50} = 11.81$ .

The values  $Z_{(1)}, \dots, Z_{(330)}$  are obtained using these estimates. The value of the Anderson-Darling test statistic is 1.392. Since the computed value of 1.392 is greater than the critical value of 0.749, the hypothesis that the observations follow a three-parameter Weibull distribution is rejected.

*Prob. XII—Step 2. Compute  $F_{\tau}(LT)$ , 0.020 to 0.125, using procedures for an unknown distribution. This computation has been carried out in Problem V, Step 2.*

**9.2.13 MODULUS OF ELASTICITY AND POISSON'S RATIO** — The following room-temperature elasticity values are presented in the room-temperature property tables as typical values:

Property	Units	Symbol	Recommended ASTM Test Procedures
Modulus of Elasticity			
In tension	1000 ksi	$E$	E 111
In compression	1000 ksi	$E_c$	E 111
In shear	1000 ksi	$G$	E 143
Poisson's Ratio	(Dimensionless)	$\mu$	E 132

If the material is not isotropic, the applicable test direction must be specified. Deviations from isotropy must be suspected if the experimentally determined Poisson's ratio differs from the value computed by the formula

$$\mu = \frac{E}{2G} - 1 \quad [9.2.13(a)]$$

where  $E$  is the average of  $E$  and  $E_c$ .

Given  $E$ ,  $E_c$ , and  $G$ ,  $\mu$  may be computed by this equation. Likewise, given  $E$ ,  $E_c$ , and  $\mu$ ,  $G$  may be computed from the equation:

$$G = \frac{E}{2(\mu + 1)} \quad [9.2.13(b)]$$

In the event  $E_c$  is not available,  $E$  may be substituted for  $E$  in the above equations to provide an estimate of either  $\mu$  or  $G$ .

**9.2.14 PHYSICAL PROPERTIES** — Density, specific heat, thermal conductivity, and mean coefficient of thermal expansion are physical properties normally included in MIL-HDBK-5. Physical properties are presented in the room-temperature property table if they are not presented in effect-of-temperature curves (see Section 9.3.1.4). The basis for physical properties is "typical". Table 9.2.14 displays units and symbols used in MIL-HDBK-5, and also recommended ASTM test procedures for measuring these properties. Since modifications of procedures are employed in measuring physical properties, methods used for values proposed for inclusion in MIL-HDBK-5 should be reported in the supporting data proposal. For specific heat

**MIL-HDBK-5H**  
**1 December 1998**

and thermal conductivity values reported in the room temperature property table, the reference temperature of measurement is also shown [for example, for 2017 aluminum the specific heat is 0.23 (at 212°F)]. For tabulated values of mean thermal expansion, temperature range of the coefficient is shown [for example, 12.5 (70 to 212°F)]. The reference temperature of 70°F is established as standard for mean coefficient of thermal expansion curves.

**Table 9.2.14. Units and Symbols Used to Present Physical Property Data and ASTM Test Procedures**

Property	Unit	Symbol	Recommended ASTM Test Procedures
Density	lb/in. <sup>3</sup>	$\omega$	C 693
Specific heat	Btu/lb-°F	$C$	D 2766
Thermal conductivity	Btu(hr-ft <sup>2</sup> -°F/ft)	$K$	C 714 <sup>a</sup>
Mean coefficient of thermal expansion	10 <sup>-6</sup> (in./in./°F)	$\alpha$	E 228

a ASTM C 714 is a test for thermal diffusivity from which thermal conductivity can be computed.

**9.2.15 PRESENTATION OF ROOM-TEMPERATURE DESIGN VALUES** — The proposal for the incorporation of design allowables into MIL-HDBK-5 shall contain supporting data and computations for all design properties. Depending on quantity and availability, data may be tabulated, plotted, or referenced (to readily available technical reports, specifications, etc.). Computations should indicate adequately the manner in which design values were computed and shall be presented in an orderly manner. Data sources shall be identified.

The table of room-temperature design values shall be presented in the format indicated in Figure 9.2.15(a) for conventional metallic materials. This format has been designed to accommodate most of these materials; however, some modifications may be required. For example, the format shown in Figure 9.2.15(b) shall be used for aluminum alloy sheet laminates which are generally anisotropic and have limited ductility. Design values for these hybrid materials are presented for several mechanical properties which differ from those shown for conventional metallic materials. Unused lines (for example, ST properties for sheet) are deleted. Guidance in the use of these formats may be obtained by examining tables throughout this document and by referral to the applicable procurement specification. The following instructions should be followed for the items located in Figure 9.2.15(a):

- (1) Table number: If this is a revision of an existing table, use the same table number; otherwise, use a new table number in the proper sequence.
- (2) Material designation: Use a numeric designation where available (for example, 7075 aluminum alloy). Avoid the use of trade names. Include products following the material designation, except products may be omitted from the title if there are many products covered by the table.
- (3) Specification: Refer to a public specification (industry, Military, or Federal), followed by a type or class designation, if appropriate. Do not refer to proprietary specifications.
- (4) Condition: Use a standard temper designation where applicable. Otherwise, use an easily recognized description, including pertinent details if these are not available in the reference specification. Examples: T651, TH1050, Aged (1400°F), Mill Annealed.
- (5) Cross-sectional area: Use only when applicable.

**MIL-HDBK-5H**  
**1 December 1998**

**Table ①. Design Mechanical and Physical Properties of (material designation) ②  
(products)**

Specification . . . . .	③			
Form . . . . .				
Condition (or Temper) . . . . .	④			
Cross-Sectional Area, in. <sup>2</sup> . . . . .		⑤		
Location Within Casting . . . . .		⑥		
Thickness or Diameter, in. . . . .		⑦		
Basis . . . . .	S	A	B ⑧	S
Mechanical Properties:				
$F_m$ , ksi:				
L . . . . .	120	120	124	
LT (or T) ⑨ . . . . .	...	... ⑩	...	
ST . . . . .				
$F_{ty}$ , ksi:				
L . . . . .				
LT (or T) . . . . .				
ST . . . . .				
$F_{cy}$ , ksi:				
L . . . . .				
LT (or T) . . . . .				
ST . . . . .				
$F_{su}$ , ksi . . . . .				
$F_{bru}$ , ksi:⑪				
(e/D = 1.5) . . . . .				
(e/D = 2.0) . . . . .				
$F_{bry}$ , ksi:				
(e/D = 1.5) . . . . .				
(e/D = 2.0) . . . . .				
$e$ , percent (S-basis):				
L . . . . .				
LT (or T) . . . . .				
ST . . . . .				
$RA$ , percent (S-basis):				
L . . . . .				
LT (or T) . . . . .				
ST . . . . .				
$E$ , 10 <sup>3</sup> ksi . . . . .				
$E_c$ , 10 <sup>3</sup> ksi . . . . .				
$G$ , 10 <sup>3</sup> ksi . . . . .				
$\mu$ . . . . .				
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> . . . . .	⑫			
$C$ , Btu/(lb)/(°F) . . . . .				
$K$ , Btu/[(hr)(ft <sup>2</sup> )(°F)/ft] . . . . .				
$\alpha$ , 10 <sup>-6</sup> in./in./°F . . . . .				

⑬ (footnotes)

**Figure 9.2.15(a). Format for room temperature property table.**

**MIL-HDBK-5H****1 December 1998****Table 7.5.X.X(b). Design Mechanical and Physical Properties of (sheet material designation) Aluminum Alloy, Aramid Fiber Reinforced, Sheet Laminate**

Specification .....	Aramid fiber reinforced sheet laminate			
Form .....	2/1	3/2	4/3	5/4
Laminate Lay-Up .....	0.032	0.053	0.074	0.094
Nominal Thickness, in. ....	S	S	S	S
Basis .....				
Mechanical Properties <sup>a</sup> :				
$F_{tu}$ , ksi:				
L .....				
LT .....				
$F_{ty}$ , ksi:				
L .....				
LT .....				
$F_{cy}$ , ksi:				
L .....				
LT .....				
$F_{su}$ , ksi .....				
$F_{sy}$ , ksi .....				
$F_{bru}$ , ksi:				
L (e/D = 1.5) .....				
LT (e/D = 1.5) .....				
L (e/D = 2.0) .....				
LT (e/D = 2.0) .....				
$F_{bry}$ , ksi:				
L (e/D = 1.5) .....				
LT (e/D = 1.5) .....				
L (e/D = 2.0) .....				
LT (e/D = 2.0) .....				
$\epsilon_r$ , percent:				
L .....				
LT .....				
$E$ , $10^3$ ksi:				
L .....				
LT .....				
$E_c$ , $10^3$ ksi:				
L .....				
LT .....				
$G$ , $10^3$ ksi:				
L .....				
LT .....				
$\mu$ :				
L .....				
LT .....				
Physical Properties:				
$\omega$ , lb/in. <sup>3</sup> .....				
C, K, and $\alpha$ .....				

a Design values were computed using nominal thickness of sheet laminate.

**Figure 9.2.15(b). Format for room temperature property table for aluminum alloy fiber reinforced sheet laminate.**



**MIL-HDBK-5H****1 December 1998**

- (6) Location within casting: Applicable only to castings. Specify “Non-designated area,” or “Designated area,” as applicable.
- (7) Design values shall be presented only for the thicknesses covered in the material specification.
- (8) Basis: For each product and size, use two columns covering A- and B-basis properties or one column covering S-basis properties. A-values that are higher than the corresponding S-values are presented only in footnotes to the table. In such instances, A-values are replaced by S-values in the body of the table. When A-values are presented for some properties and S-values are presented for other properties for the same product, values shall be shown in a column labeled A-basis, and individual S-values shall be identified by appropriate footnotes. Elongation, total strain at failure, and reduction of area values are presented on an S-basis only. When other properties are presented on an A- and B-basis, add “(S-basis)” after “ $e$ , percent,” or “ $\epsilon_t$ , percent” and “ $RA$ , percent.” For aluminum alloy die forgings,  $F_u$ ,  $F_{ty}$ , and  $e$  shall be shown on an S-basis only for transverse, T, grain direction. To explain, add the following footnote to these values, “Specification value. T tensile properties are presented on an S-basis only.” Design values for low alloy, quenched and tempered steels shall be presented on an S-basis only.
- (9) Grain direction: Show design values for grain directions “L, LT, and ST” or for grain directions “L and T” for the properties  $F_u$ ,  $F_{ty}$ ,  $F_{cy}$ ,  $e$ , and  $RA$ . For anisotropic materials, present design values for grain directions “L, 45°, and LT” for  $F_u$ ,  $F_{ty}$ , and  $F_{cy}$ . For aluminum alloy sheet laminates, show design values for L and LT grain directions of aluminum alloy sheet for all mechanical properties. Grain directions are not applicable to castings.

The T grain direction should be footnoted with the definition used in the specification identified at the top of the mechanical property table. For example, the T grain direction for aluminum die forgings covered in MIL, Federal and some AMS specifications should read as follows: “For die forgings, T indicates any grain direction not within  $\pm 15$  degrees of being parallel to the forging flow lines.” For the AMS specifications with the narrow definition for the T grain direction, the footnote should read as follows: “For die forgings, T indicates a grain direction within  $\pm 15$  degrees of being perpendicular to forging flow lines.” Specimens to test the transverse properties should be located as close to the short transverse direction as possible.

Transverse  $F_{cy}$  values for aluminum die forgings shall be shown as  $F_{cy}(T)$ . If the values are based upon short transverse or long transverse test data, add this information to the above footnote.

- (10) Missing values: For table entries that are missing or not applicable, show a series of three dots aligned with the numbers in that column.
- (11) Bearing values: Add footnote “Bearing values are dry pin values per Section 1.4.7.1” when bearing allowables are based on data from clean pin tests. Supporting information supplied with the proposal should describe the bearing test cleaning procedures used in testing.
- (12) Physical properties: Include a section for physical properties even if properties are not available. If physical property data are presented in an effect-of-temperature curve, use table entry, “See Figure X.X.X.0” to refer to the illustration.
- (13) Footnotes: Use footnotes to indicate anything unusual or restrictive concerning the property description, properties, or individual values; to present supplementary values; or to reference

**MIL-HDBK-5H**

**1 December 1998**

other tables or sections of text. When A-values have been replaced by S-values, the following wording is suggested: “S-basis. The rounded  $T_{99}$  values are as follows: (list values).”

In addition, the proposal shall contain supporting data and computations for all design properties. Depending on quantity and availability, data may be tabulated, plotted (by cumulative-probability curves or histograms), or referenced (to readily available technical reports, specifications, etc.). Computations should indicate adequately the manner in which design values were computed and shall be presented in an orderly manner. Data sources shall be identified.

**MIL-HDBK-5H**  
**1 December 1998**

## **9.3 GRAPHICAL MECHANICAL PROPERTY DATA**

**9.3.1 ELEVATED TEMPERATURE CURVES** — Effects of temperature and of thermal exposure on strength and certain other properties are presented graphically. Methods for determining these curves differ and are described below.

**9.3.1.1 Strength Properties** — Tensile ultimate and yield strengths, compressive yield strength, shear ultimate strength, and bearing ultimate and yield strengths at temperatures other than room temperature (80 °F) are shown as percentages of room-temperature value for that property. Use of percentage curves allows a single curve to be used in place of multiple curves when more than one room-temperature value is presented for a property, as for example, differing A- and B-design values for each of several thickness ranges. In instances where related properties differ in their response to temperature, additional curves are provided and are labeled to indicate specific properties and forms to which they apply.

No significance level is attached to these curves. For practical purposes, however, the product of a room-temperature A or B design value and an appropriate percentage value from the curve may be regarded as an A or B design value at the indicated temperature.

**9.3.1.1.1 Data Requirements** — An idealistic approach to the establishment of elevated temperature curves would be to have A-basis design values at a sufficient number of temperatures to define corresponding temperature curves on an A-basis. If such data were available, finished curves would be constructed by plotting A-values on a percentage scale and fairing in a smooth curve, and the procedures described in Section 9.3.1.1.2 would not be considered applicable. Unfortunately, the cost of generating the required data is prohibitive, and idealism must be tempered with practicality. For this reason, data requirements and the procedures described in Sections 9.3.1.1.2 and 9.3.1.1.3 allow some latitude to make fullest use of whatever data may be available.

These procedures, as described in the following sections, are intended both to establish the general shape of curves, and to adjust their scaling in such manner that the resulting product of a percentage value from the curve and a corresponding value from the room-temperature property table will yield a design value, at some designated temperature, that will be a good approximation of a directly computed design value at that temperature.

To establish the shape of an elevated-temperature curve, the sample shall include observations from at least five lots\* of material composed of at least two heats at each of several temperatures. Choice of temperatures shall be guided by probable range of service temperatures anticipated for the material, as well as by its metallurgical characteristics. For materials used at cryogenic temperatures, testing is normally conducted at -110, -320, and -423 °F; however, no attempt shall be made to extrapolate the curve below the lowest temperature for which adequate data are available. For elevated temperature applications, data should normally be available at temperature intervals from 200 to 300 °F except in regions of time-temperature-dependent metallurgical change, where temperature intervals of perhaps 100 to 150 °F are appropriate. Extrapolation beyond the range of temperatures covered by adequate data is not allowed.

For a number of alloys, most specifically heat-resisting alloys, procurement specifications may designate minimum property values at temperatures other than room temperature, and either A- or S-basis values may be available at both room temperature and secondary testing temperatures. When this is the case, the elevated temperature curve may be scaled by means of these values.

---

\* For single form and thickness, data from no more than one heat treat lot per heat may be used to meet the five lot requirement.

**MIL-HDBK-5H**  
**1 December 1998**

**9.3.1.1.2 Determination of Working Curves** — Working curves for each product form, heat treat condition, property, and grain direction should be constructed. Separate curves should be examined to determine if certain data can be combined. For example, it may be possible to combine data for sheet and plate, T73 and T7351 tempers, tensile and compressive yield strengths, or longitudinal and long transverse grain directions.

The dimensional units of these working curves shall be in terms of percentages of corresponding room-temperature value for the property. A percentage may be determined for each lot by dividing the average value of individual measurements (other than at room temperature) by the room-temperature average value for the same lot of material in the same testing direction (for isotropic materials, testing direction may be ignored), then multiplying by 100 to convert from a fraction to a percentage.

At each working temperature, the lower 95 percent confidence interval estimate (reduced ratio) of mean percentage shall be determined from percentage values for each lot at that temperature. Letting  $r$  equal percentage values,  $\bar{r}$  the average of these values, and  $n$  the number of such percentages, estimated standard deviation(s) and reduced ratio ( $R$ ) shall be determined from the equation:

$$s^2 = \sum(r - \bar{r})^2 / (n - 1) \quad [9.3.1.1.2(a)]$$

or 
$$s^2 = [\sum(r^2) - (\sum r)^2 / n] / (n - 1) \quad [9.3.1.1.2(b)]$$

and 
$$R = \bar{r} - t s / \sqrt{n} \quad [9.3.1.1.2(c)]$$


where  $t$  is 0.95 fractile of the  $t$  distribution corresponding to  $n-1$  degrees of freedom (see Table 9.6.4.5).

The working curve shall be a smooth curve drawn through 100 percent at room temperature and not higher than the computed values of  $R$  at each working temperature. When only room-temperature minima are applicable, no further adjustment of the working curve is required. However, when a secondary testing temperature is specified for the property, the working curve shall be lowered, if required, so that the product of percentage from this curve and a room-temperature  $S$ -value shall not exceed the  $S$ -value at the secondary testing temperature. In addition, if  $A$ -basis values have been established for this temperature, the working curve shall be lowered, if required, so that the product of the percentage from this curve and room temperature  $A$ -value shall not exceed the  $A$ -value at the secondary testing temperature.

Each working curve shall be labeled appropriately, designating product, property, and testing direction(s) covered by it. In addition, individual percentages, including  $R$  values and (if applicable) secondary  $A$  or  $S$ -values reduced to percentages, shall be plotted with the working curve. An example of a working curve is shown in Figure 9.3.1.1.2.

**9.3.1.1.3 Preparation of Finished Curves** — When two or more working curves are to be combined into a single curve, percentages shown in the finished curve shall represent the separate bound of all individual working curves used in its preparation. When corresponding working curves differ substantially in shape or scaling, it may be appropriate to prepare more than one finished curve (for example, separate curves for longitudinal and transverse testing directions). Finished curves shall not exhibit “humps”, such as might appear with a temperature range where aging takes place. Where such humps appear in working curves, these shall be leveled by means of horizontal line segments.


**MIL-HDBK-5H**  
**1 December 1998**




**Figure 9.3.1.1.2. Working curve drawn through reduced ratios converted to percentages.**

Finished curves shall be drawn in reproducible form on grids of 10 lines to the inch, with each tenth line accented. The ordinate shall normally be scaled in units of 20 percent per inch and shall be labeled “Percentage of Room Temperature Strength”. Abscissa shall be scaled in units of 100, 200, or 400°F per inch, as appropriate, and shall be labeled “Temperature, °F”. Both axes shall be annotated at intervals of 1 inch. Not more than two curves shall be drawn in a single figure, and these should be labeled clearly to distinguish between them. In addition, each figure shall carry a legend containing the words “strength at temperature”, together with exposure limits and other information that would limit the applicability of the curve.

An example of the finished percentage curve is shown in Figure 9.3.1.1.3(a). When practical, single percentage curves, representing  $F_{tu}$  and  $F_{ty}$  may be located on a single illustration as shown in Figure 9.3.1.1.3(b). Likewise, single curves representative of  $F_{cy}$  and  $F_{su}$  may be located on one illustration and curves for  $F_{bru}$  and  $F_{bry}$  may also be placed on a single illustration.



**Figure 9.3.1.1.3(a). Working curve from Figure 9.3.1.1.2 redrawn as finished curve.**




**Figure 9.3.1.1.3(b). Multiple percentage curves located on a single illustration.**

**9.3.1.2 Elongation and Reduction of Area** — Elongation and reduction of area are presented as “typical” values at each temperature. If ductility values follow a log-normal distribution, they should be converted to logarithms before averaging. In most cases, the median (middle-most value) will be

**MIL-HDBK-5H****1 December 1998**


nearly identical to the average determined in this manner. Ductility values are not converted to percentages of the room-temperature value. Hence, a best smooth curve drawn through the typical values at each temperature is merely redrawn without data points for presentation in the document, as shown in Figure 9.3.1.2. Separate curves may be required for products differing in ductility.



**Figure 9.3.1.2. Typical curve for elongation.**

As with strength data, care must be taken to avoid biasing the curve by the inclusion of large quantities of data from some lots and small quantities from others. Use of lot-average values in place of individual measurements is highly recommended.

**9.3.1.3 Modulus of Elasticity** — The elastic modulus may vary with test direction and product form. Data should be examined before plotting, and if differences are observed, separate working curves should be prepared for each variable. The percentage curve for modulus of elasticity is a best-fit smooth curve drawn through the average of all percentages at each temperature, where individual percentage values are obtained as described in Section 9.3.1.1.2. As with strength data, temperatures should be so selected that the shape of the curve is defined adequately. Figure 9.3.1.3 illustrates a finished percentage curve representing two moduli,  $E$  and  $E_c$ , for which working curves were similar enough to permit their combination into a single curve.



**Figure 9.3.1.3. Percentage curve representing two elastic moduli.**



**MIL-HDBK-5H**  
**1 December 1998**

**9.3.1.4 Physical Properties** — When data are adequate to present curves showing specific heat, thermal conductivity, and mean coefficient of thermal expansion over a range of temperatures, graphical presentation is used in place of tabular presentation described in Section 9.2.1.3. Working curves are first prepared for each property with the actual data plotted over the range of test temperatures.

Figure 9.3.1.4(a) shows a typical working curve. A best-fit smooth curve is drawn through the plotted points to depict the overall trend of data. The smooth curves from the specific heat, thermal conductivity, and thermal expansion working curves are then shown in a single figure as illustrated in Figure 9.3.1.4(b). The reference temperature for thermal expansion should be shown on the figure. In Figure





FIGURE 9.3.1.4(a). Typical working curve for thermal conductivity.

**Figure 9.3.1.4(a). Typical working curve for thermal conductivity.**



**Figure 9.3.1.4(b). Typical curves for physical properties.**

**MIL-HDBK-5H****1 December 1998**


9.3.1.4(b) the reference temperature of 70°F indicates that the mean coefficient of expansion between 70°F and the indicated temperature is plotted.

**9.3.1.5 Effect of Thermal Exposure on Room-Temperature Strength** — Curves described in this section are presented (1) when the material exhibits a decrease in room-temperature strength as a result of unstressed exposure to elevated temperatures, and (2) when data are not presented in the form of parametric curves (see “Complex-Exposure” in Section 9.3.1.6.2). Supporting data expressed as percentages of the “no-exposure” strength are plotted with percent of room-temperature strength as the ordinate and exposure temperature as the abscissa. Separate plots are required for each exposure time. Typical exposure times are ½, 10, 100, and 1000 hours. Design curves are drawn in the same manner as for effect of temperature on strength; humps that may appear in the design curve should be leveled off in drawing the final curve.

The following restrictions are placed on effect-of-exposure curves for strength properties at room temperature:

- (1) Percentage curves for a designated exposure temperature may not show increasing percentage values with increasing exposure time.
- (2) Percentage curves for a designated exposure time may not show increasing percentage values with increasing exposure temperature.

A typical effect-of-exposure curve is illustrated in Figure 9.3.1.5.



**Figure 9.3.1.5. Effect of exposure at elevated temperatures on room-temperature properties.**

**9.3.1.6 Effect of Thermal Exposure on Elevated Temperature Strength** — The effect of thermal exposure on elevated-temperature strength is presented in one of two manners, depending upon whether or not the exposure temperature equals the test temperature. In the case of simple exposure, exposure temperature and test temperature are assumed to be identical. For complex exposure, exposure temperature and test temperature need not be the same. When either of these curves is presented in MIL-HDBK-5, it includes all information normally presented in elevated temperature curves described in Section 9.3.1.1; thus, these curves replace the elevated temperature curves.

**9.3.1.6.1 Simple Exposure** — The curves are prepared in the same manner as basic elevated temperature curves described in Section 9.3.1.1. Separate design curves are prepared for each exposure time, and presented in a single figure. Typical exposure times for the curves are ½, 10, 100, and 1000 hours.




**MIL-HDBK-5H****1 December 1998**

The following additional restrictions are placed on effect-of-exposure curves for strength properties at elevated temperatures:

- (1) Percentage curves for a designated exposure (test) temperature may not show increasing percentage values with increasing exposure time.
- (2) Percentage curves for a designated exposure time may not show increasing percentage values with increasing exposure (test) temperature.

A typical set of curves for exposure at test temperature is illustrated in Figure 9.3.1.6.1.



**Figure 9.3.1.6.1. Simple-exposure curves.**

**9.3.1.6.2 Complex Exposure** — In these curves, thermal-exposure variables, time, and temperature are combined into an exposure parameter, which is plotted as the abscissa. The ordinate is expressed in the same manner as in effect-of-temperature curves. Separate percentage curves are presented for each test temperature. In addition, each figure contains a nomograph for use in converting exposure time and temperature to the exposure parameter.

The exposure parameter may be of the form  $P = (T_F + 460) (C + \log t)$ , where  $T_F$  is exposure temperature in degrees F,  $C$  is a constant, and  $t$  is exposure time in hours. There are a number of ways to determine the values of  $C$ . The simplest method is to select (by interpolation of test data) two exposure conditions that produce the same strength at some designated test temperature, set two parameters equal to each other, and solve for  $C$ . For example, assume that the following data are obtained:

**MIL-HDBK-5H**  
**1 December 1998**

Exposure		
Time, hr	Temp, °F	TUS at 400 °F, ksi
1000	400	80.0
1	500	83.0
10	500	78.0

Plot 500°F data as stress versus log time; a straight line between (83, log 1) and (78, log 10) crosses 80 ksi at log 4 (hours). Thus, 4 hours' exposure at 500°F is equal to 1000 hours' exposure at 400°F:

$$(400 + 460)(C + 3) = (500 + 450)(C + 0.602)$$

$$C = 20.$$

This exercise should be repeated for several pairs of exposure conditions to obtain an average value for C.


Alternatively, several equivalent exposure conditions may be plotted as log exposure time (ordinate) versus  $1/(T_F + 460)$  (abscissa). A best-fit straight line is drawn through the plotted points and its slope determined. C is then found from the relationship

$$C = m/(T_F + 460) - \log t,$$

where m is slope and  $1/(T_F + 460)$  and log t are coordinates of any point on the line. This method is amenable to data-regression procedures described in Section 9.6.4.3, from which a least-squares estimate of C is obtained.

Separate data plots are prepared for each test temperature, using percent of “no-exposure” room-temperature strength as the ordinate, and  $P = (T_F + 460)(C + \log t)$  as the abscissa. Design curves are then drawn as described in Section 9.3.1.1.2.

A typical complex-exposure curve is illustrated in Figure 9.3.1.6.2. It should be noted that the abscissa scale is not shown in the figure since the time-temperature nomograph is used directly to locate the position on the abscissa.



**Figure 9.3.1.6.2. Complex-exposure curves.**

**MIL-HDBK-5H**  
**1 December 1998**

### **9.3.2 TYPICAL STRESS-STRAIN, COMPRESSION TANGENT-MODULUS, AND FULL-RANGE STRESS-STRAIN CURVES**

**9.3.2.1 Introduction** — The stress-strain and tangent-modulus data appearing in MIL-HDBK-5 are described as “typical” stress-strain and compression tangent-modulus curves. The term typical indicates that representative stress-strain data for products covered have been adjusted to reflect precision typical values of the elastic modulus, and product average values of the 0.2 percent offset yield strength in tension or compression. Curves extend to strain somewhat beyond the 0.2 percent offset yield strength. Curves described as “full range” stress-strain curves are also included in MIL-HDBK-5. These curves extend through maximum load and beyond to rupture.

All curves will be prominently marked “typical”. With regard to tension data, only stress-strain curves are shown; however, compression data should include stress-strain curves and tangent-modulus curves. The Ramberg-Osgood  $n$  exponent should appear on all stress-strain curves if  $n$  is shown to apply in the approximate range from proportional limit to yield strength. The procedures and methods to be used are described in the following paragraphs.

Two alternative procedures are described for determining typical stress-strain curves.

- (1) The “strain-departure” method, which assumes no parametric relationship between stress and plastic strain, utilizes the full stress-strain curve.
- (2) The Ramberg-Osgood method, which assumes an exponential relationship between stress and plastic strain. Its use requires as few as two points from the original stress-strain curve, once the exponential relationship has been found to be applicable.

Generally, the two methods yield nearly identical results for those portions of the curve lying between proportional limit and yield stress. For plastic strains greater than about 0.002 in./in. and for bimetallic or clad products, only the strain-departure method is applicable.

Stress tangent-modulus curves may be derived graphically from compressive stress-strain curves, or computed, if the Ramberg-Osgood method is used.

**9.3.2.2 Data Requirements** — Preparation of each typical stress-strain curve requires (1) several representative original stress-strain curves, (2) average values for yield strength from original stress-strain curves, or, when available, product average values for yield strength, and (3) typical precision elastic-modulus values at test temperature.

Original stress-strain curves are utilized to obtain a representative curve shape which may be characterized by the Ramberg-Osgood parameter. The minimum number of original stress-strain curves required is dependent on the degree of variation from one curve to another. If curves are found to be similar in shape, and the range of products (thickness, etc.) is small, one curve from each of three plots should be adequate. Otherwise, the number of original curves should be increased as necessary to insure an adequate sampling.

Original stress-strain curves determined using an ASTM E 83 Class A extensometer (TUCKERMAN, Martens, etc.) are preferred for preparation of typical stress-strain curves up to 0.005-in./in. plastic strain or higher. When curves having this precision and accuracy are not available (particularly for full-range and elevated-temperature curves), curves determined using Class B-1 extensometers may be used as indicated in ASTM E 83.

**MIL-HDBK-5H****1 December 1998**

Product average values for yield strength, ultimate strength, and elongation are average values rounded to the nearest whole number determined from production lots of product form. Product average values represent current production capabilities; hence, these are supplied by producers.

Elastic modulus values are considered to be those obtained with Class B-1 or better extensometers as indicated in ASTM E 83. Typical values for elastic moduli at room temperature are tabulated in MIL-HDBK-5 room-temperature property tables. Values for these properties at other temperatures may be approximated by multiplying the room-temperature value by appropriate percentages from effect-of-temperature curves in MIL-HDBK-5. The modulus value used in constructing a stress-strain curve must agree with the value obtained from the room-temperature table value multiplied by the appropriate percentage from the elevated temperature curve.

For some materials, the shape of the stress-strain curve, yield strength, and elastic modulus vary with test direction. When this is the case, individual curves should be prepared for each test direction, and each curve should be labeled accordingly. Likewise, tensile and compressive stress-strain curves usually differ, and individual curves should be prepared for each type of loading. If two or more finished curves are found to be identical, they may be combined in presenting the finished curves.

The selection of test temperatures to be represented by typical stress-strain curves should be guided by the temperatures at which the product is typically used. In the absence of other information, these temperatures should include room temperature, other temperatures at which tensile properties are determined in conformance with the requirement of applicable procurement specifications, and appropriate temperatures within the useful application range for the product.

**9.3.2.3 Strain-Departure Method** — These steps, as illustrated in Table 9.3.2.3, should be followed to establish a typical tensile or compressive stress-strain curve using the strain-departure method:

- (1) The straight-line (modulus) portion of each curve should be extended as in Figure 9.3.2.3(a), and the 0.002 (0.2%) offset yield strength should be indicated.
- (2) At appropriate departures or offsets from the modulus line, load should be determined accurately, converted to stress, and recorded. Sufficient departure measurements should be made to accurately describe the curve to just beyond yield load for each load-strain curve.
- (3) At each strain departure, the stresses should be averaged.
- (4) When a product average yield strength value is available, the average stresses at each departure should be converted to product average stresses.
- (5) Elastic strains should be computed for each departure. (Elastic Strain equals Total Stress/Elastic Modulus.)
- (6) Elastic strains (computed) and plastic strains (departure) should be added to obtain total strain for each departure.

The following guidelines should be used to plot a typical stress-strain curve. The graph axis should be laid out such that there are 10 minor divisions for every major division with every tenth (major) division accented. The ordinate (Y-axis) is used for stress and should be scaled in units of ksi to the major division, as appropriate, to produce a total scale length of approximately 5 major divisions. The abscissa (X-axis) is used for total strain and should be scaled in units of in./in. to the major division, as appropriate, to produce a total scale length of approximately 6 major divisions.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.3.2.3. Example of Use of Strain Departures to Establish Typical Stress-Strain Curve as Described in Section 9.3.2.3.**

Departure (D) $\mu$ in./in.	Stress, ksi				Strain, $\mu$ in./in.		
	Test #1	Test #2	Test #3	Average <sup>a</sup> ( $\sigma_A$ )	Product Average <sup>b</sup> ( $\sigma_T$ )	Elastic <sup>c</sup> ( $\epsilon_E$ )	Total <sup>d</sup> ( $\epsilon_T$ )
0	43.81	42.75	41.20	42.59	42.63	4022	4022
20	49.77	48.81	45.14	47.91	47.95	4524	4544
40	51.41	50.98	47.82	50.17	50.12	4728	4768
100	54.31	53.96	51.24	53.17	53.22	5021	5121
500	60.16	60.37	57.10	59.21	59.27	5592	6092
1000	62.67	62.85	59.45	61.66	61.72	5823	6823
2000	64.95	65.06	61.80	63.94 <sup>f</sup>	64.00 <sup>e</sup>	6038	8038
2200	65.26	65.38	62.12	64.25	64.31	6067	8267

a Average of Tests 1, 2, and 3.


b  $\sigma_T = (\text{Product average yield strength} \div \text{average yield strength}) \times \sigma_A$ .

c  $\epsilon_E = \sigma_T / E$ .


d  $\epsilon_T = \epsilon_E + D$ .

e Product average yield strength.

f Average yield strength.



**Figure 9.3.2.3(a). Measuring loads by strain departure method.**




**Figure 9.3.2.3(b). Plotted data from Table 9.3.2.3.**

**MIL-HDBK-5H**  
**1 December 1998**

The final step is plotting the values in Table 9.3.2.3 to produce the typical stress-strain curve as shown in Figure 9.3.2.3(b). In addition to plotting the graphs by hand, they may be plotted with computer software programs. In the latter case, input the stress-strain pairs ( $\sigma_T$  and  $\epsilon_T$ ) from Table 9.3.2.3 into the computer and then curve fit the data. In all cases, the elastic section must be linear up to the proportional limit. It is recommended that the Ramberg-Osgood equation be used to fit the data from the proportional limit to just beyond the 0.2% yield stress. If not, a power-law polynomial second order may be used to fit the data points. The stress-strain curve should extend slightly beyond the 0.2% yield strength.

To complete the figure, the Ramberg-Osgood number from Section 9.3.2.4 and the typical yield strength (TYS) product average must be contained in a table within the figure. If more than one curve is contained in the figure, information such as the grain direction (L, LT, and ST), and/or temperature for each curve must be indicated in the figure. Figure 9.3.2.3(c) shows the proper format of a figure for presentation in Chapters 2 through 7.3.



**Figure 9.3.2.3(c). Typical stress-strain curves showing the proper presentation format.**

**9.3.2.4 Ramberg-Osgood Method** — This method, which is based on the work of Ramberg and Osgood [Reference 9.3.2.4(a)], and Hill [Reference 9.3.2.4(b)], assumes that an exponential relationship exists between stress and plastic strain, as expressed by

$$e_p = 0.002 \left( \frac{f}{f_{0.2ys}} \right)^n \quad [9.3.2.4(a)]$$

**MIL-HDBK-5H**  
**1 December 1998**

where

f is stress,  
 $f_{0.2ys}$  is the 0.2 percent yield stress,  
 $e_p$  is plastic strain,  
n is the Ramberg-Osgood parameter\*.

While this relationship may not be exact, it is sufficiently accurate for use up to the yield strength for many materials, but cannot be employed to compute full-range stress-strain curves.

Since total strain equals elastic strain plus plastic strain,

$$e_{total} = f/E + 0.002 \left( \frac{f}{f_{0.2ys}} \right)^n \quad [9.3.2.4(b)]$$

where E is the typical value of modulus of elasticity from the room-temperature property tables.

Equation 9.3.2.4(b) can be programmed for determination and plotting by a computer, given only values for E, n, and  $f_{0.2ys}$ . To obtain typical curves, TYS or CYS is used for  $f_{0.2ys}$ . TYS and CYS values are based on product averages when available; in other cases, average values from original stress-strain curves are used. The Ramberg-Osgood parameter, n, shall be determined analytically in development of typical stress-strain curves for MIL-HDBK-5.

As the first step in the analytical determination of n, a series of values of stress and strain departure (plastic strain) must be obtained from each original stress-strain curve. These may be determined by the method of strain-departure described in Section 9.3.2.3 or the alternate method outlined below:

- (1) Determine the indicated modulus of elasticity for the individual stress-strain curves.
- (2) For each curve, construct two lines parallel to the modulus line and intersecting the stress-strain curve at plastic strains of approximately 0.020 and 0.20 percent. The lines will bound the zone where stress-plastic strain pairs are determined. This zone also eliminates the small plastic strain region where nonlinearities in stress versus plastic strain sometimes exist.
- (3) Digitize each stress-strain curve over the range bounded in Step 2. A series of approximately ten to 12 pairs of stress-total pairs should be taken at nearly equal intervals within this range. A resolution of 0.25 ksi stress and 0.01 percent strain is desirable here.
- (4) Compute plastic strains from each collection of total strains, using the individual curve's modulus to subtract out elastic strains.

Once the stress and plastic strain values are tabulated for available stress-strain curves, it is possible to proceed with determination of the Ramberg-Osgood parameter. To determine n analytically, Equation 9.3.2.4(a) is rearranged to solve for stress, f, the dependent variable.

---

\* The Ramberg-Osgood parameter, n, should not be confused with the strain hardening coefficient, which is also denoted by the letter n. The one is the reciprocal of the other. Values of the Ramberg-Osgood parameter usually lie within the range of 2 to 40. It should be noted that an occasional practice in the aircraft industry, but not followed in MIL-HDBK-5, is to subtract a small increment of strain from Equation 9.3.2.4(a) in order to compensate for the existence of a proportional limit.

**MIL-HDBK-5H**  
**1 December 1998**

$$f = A e_p^{1/n} \quad [9.3.2.4(c)]$$

where

$$A = \frac{f_{0.2ys}}{(0.002)^{1/n}} \quad [9.3.2.4(d)]$$

Taking the natural logarithm of Equation 9.3.2.4(c), a transformed equation is obtained which can be analyzed by the method of linear least squares.

$$\ln f = \ln A + 1/n \ln e_p \quad [9.3.2.4(e)]$$

The solution for  $n$  is the same as that for a linear regression least-squares estimate of the slope,  $b$ , as shown in Section 9.6.3.1, Equation 9.6.3.1(d) where  $b = 1/n$ , therefore,

$$n = \frac{\sum x^2 - \frac{(\sum x)^2}{N}}{\sum xy - \frac{\sum x \sum y}{N}} \quad [9.3.2.4(f)]$$

where

$$x = \ln e_p$$

$$y = \ln f$$

$N$  = number of data points.

Correspondingly,  $A$  can be obtained from Equation 9.6.3.2(d) as

$$\ln A = \frac{\sum y - \frac{1}{n} \sum x}{N} \quad [9.3.2.4(g)]$$

Values for stress and strain departure may be input for solution of Equation 9.6.3.2(f) by either of two methods. In one method,  $x = \ln e_p$  and  $y = \ln f$  are input for each value of stress and strain departure for each stress-strain curve used in the analysis.  $N$  is the total number of points obtained from stress-departure analysis of all specimens from all heats that are analyzed. Care should be taken to ensure that the same number of data points are collected from each curve. In the other method, average stress ( $f$ ) is determined for all available curves at designated values of strain departure ( $e_p$ ). In this case,  $x$  and  $y$  in Equation 9.6.3.2(f) are  $\ln e_p$  and  $\ln f$ , respectively, and  $N$  is the number of strain departure points. Again, the same number of data points should be computed for each stress-strain curve.

Some investigators may analyze the results of each individual specimen by the method outlined by Equations 9.3.2.4(c) through (g) and record individual values of the parameter  $n$ . In these cases, an alternate approach must be used to combine results and establish  $n$ . This technique is called the method of computed strain-departure.

In the method of computed strain-departure, results from individual specimen analyses are used to compute stress levels [from Equation 9.3.2.4(c)] at specific strain-departure levels for all specimens. In so




**MIL-HDBK-5H****1 December 1998**

doing, the original data are used to analytically perform the method of strain-departure of Section 9.3.2.3 which should be used as a guideline for doing this analysis. Once these computed stress values are obtained, they can be used to calculate the exponent,  $n$ , by Equation 9.3.2.4(f) using either of the two methods that are described above for the case when data are recorded by the method of strain-departure.

An approximate value of the Ramberg-Osgood parameter can be found graphically, although this approach shall not be used to construct stress-strain curves for MIL-HDBK-5. Graphically determined stress-strain curves must be verified by computer analysis according to previously described techniques before inclusion in MIL-HDBK-5. A graphical procedure is described in the following paragraphs and is illustrated in Figure 9.3.2.4.

- (1) Plot at least three pairs of stress-plastic strain points from each original stress-strain curve on log-log graph paper. As illustrated in Figure 9.3.2.4(a), the ordinate is conventionally used for log stress, the abscissa is log plastic strain (strain departure method is described in Section 9.3.2.3), and the slope is  $1/n$ .
- (2) A straight line then is drawn through the plotted points and the slope ( $1/n$ ) is computed as shown in the figure.




**Figure 9.3.2.4. Graphical approximation of Ramberg-Osgood Parameter,  $n$ .**

When using the above-described approaches, it is recommended that a check be made to determine how well the value of  $n$  reproduces the stress-strain curve in the approximate range from the proportional limit (defined as 0.0001% in./in. plastic strain) to  $f_{0.2ys}$ . This can be done by constructing the stress-strain curve using Equation 9.3.2.4(b), and comparing an original stress-strain curve through the yield strength with the computed curve. In checking an original stress-strain curve with the computed curve, some judgment must be exercised in the vicinity of the proportional limit since the Ramberg-Osgood relationship may not precisely represent original stress-strain curves in this area. Stress deviations greater than about 5 percent between the two curves suggest that the Ramberg-Osgood relation is not applicable.

**9.3.2.5 Compression Tangent-Modulus Curves** — In deriving tangent-modulus curves graphically from typical compressive stress-strain curves, a number of points are marked off on the latter curves, particularly where the curve departs from linearity and in regions of greatest curvature. At each point on the curve, a line is drawn tangent to the curve as shown in Figure 9.3.2.5(a). The slope of each line is the

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 9.3.2.5(a). Determining tangent modulus and secant modulus.**

tangent modulus corresponding to the stress coordinate of the point of tangency. The Ramberg-Osgood relationship, Equation 9.3.2.4(b),

$$e_{\text{total}} = f/E + 0.002 \left( \frac{f}{f_{0.2\text{ys}}} \right)^n$$

also may be employed to determine the compression tangent-modulus curve.

Tangent modulus is the first derivative of stress with respect to strain,  $df/de$ , or

$$E_t = \frac{1}{\frac{1}{E} + \frac{0.002n}{f_{0.2\text{ys}}} \left( \frac{f}{f_{0.2\text{ys}}} \right)^{n-1}} \quad [9.3.2.5(a)]$$

This equation can be programmed for determination and plotting by a computer, given only values for  $E$ ,  $n$ , and  $f_{0.2\text{ys}}$ . To obtain typical curves, average CYS is used for  $f_{0.2\text{ys}}$ .

The following guidelines should be used to plot a compression tangent-modulus curve. The graph axis should be laid out such that there are 10 minor divisions for every major division with every tenth (major) division accented. The ordinate (Y-axis) scale is plotted in the same manner as that used for the stress-strain curves in Section 9.3.2.3. The abscissa (X-axis) scale is usually made equal to 2, 4, or 5 x  $10^3$  ksi per major division, depending on material, to produce a total scale length of approximately 6 major divisions.

**MIL-HDBK-5H**  
**1 December 1998**

The compression tangent-modulus curve is illustrated in Figure 9.3.2.5(b) where stress is plotted (on the ordinate) versus tangent modulus (on the abscissa). In addition to plotting the graphs by hand, they may be plotted with computer software programs. In the latter case, input the stress-modulus pairs ( $\sigma_T$  and  $E_t$ ) from Equation 9.3.2.5(a) into the computer or program the computer with the equation and then curve fit the data. If it will not lead to confusion, stress tangent-modulus curves may be superimposed on the corresponding stress-strain figures as illustrated in Figure 9.3.2.5(c). If, however, several stress-strain curves appear in one figure, it is advisable to present stress tangent-modulus curves in a separate figure, as illustrated in Figure 9.3.2.5(b).

The compression tangent-modulus curves for clad material should show a primary and secondary modulus as indicated in Figure 9.3.2.5(d). The stress-strain curves of clad material may indicate two modulus lines due to the cladding. The primary modulus is due to the combined modulus of both clad and base materials. However, the clad material is typically weaker than the base material and will yield at a low stress; therefore not contributing to the modulus at higher stresses. At this point, the secondary modulus becomes predominate. The compression tangent-modulus curves should show the primary and secondary modulus and indicated in Figure 9.3.2.5(d).


To complete the figure, the Ramberg-Osgood number from Section 9.3.2.4 must be contained in a table within the figure. If more than one tangent modulus curve is contained in the figure, information such as the grain direction (L, LT, and ST), and/or temperature for each curve must be indicated in the figure. Figures 9.3.2.5(b), (c), and (d) show the proper format for presentation in Chapters 2 through 7.

Stress-secant modulus curves are not presently used in MIL-HDBK-5. Secant or “chord” modulus is determined as illustrated in Figure 9.3.2.5(a) and is plotted in the same manner as the tangent modulus. The equation for secant modulus is:


$$E_s = \frac{f}{e} = \frac{f}{\frac{f}{E} + 0.002 \left( \frac{f}{f_y} \right)^n} \quad [9.3.2.5 (b)]$$

at the point of stress.

**MIL-HDBK-5H**  
**1 December 1998**




**Figure 9.3.2.5(b). Typical compressive tangent-modulus curves.**



**Figure 9.3.2.5(c). Typical compressive stress-strain and compressive tangent-modulus within the same figure.**

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 9.3.2.5(d). Typical compression tangent-modulus curves for clad aluminum alloy sheet showing the primary and secondary modulus.**

**9.3.2.6 Mathematical Representation of Stress-Strain Curves** — As an aid to computer analyses, the stress-strain curves for most materials can be represented mathematically. This method of representing stress-strain curves may be used for any stress-strain response that can be well characterized by the Ramberg-Osgood Method, and should be used as a supplement to a curve drawn by the Ramberg-Osgood Method.

To represent the stress-strain curves for a particular alloy using this method, a data summary like the one shown in Figure 9.3.2.6 should be constructed.

The parameters in the table are defined as follows:

**Tension**

- $n$  = Ramberg-Osgood parameter for small plastic strains in tension from the proportional limit up to the yield stress.
- $TYS$  = Typical yield stress in tension.
- $TUS$  = Typical ultimate stress in tension.

**Compression**

- $n_c$  = Ramberg-Osgood parameter for small plastic strains in compression up to the yield stress.
- $CYS$  = Typical yield stress in compression.

**MIL-HDBK-5H****1 December 1998****Table (table number). Typical Stress-Strain Parameters for (material designation)**

Temper/Product Form	Condition	Temper- ature, °F	Grain Direction	Tension			Compression	
				n	TYS, ksi	TUS	n <sub>c</sub>	CYS, ksi
T6 Clad Sheet	0.02-0.039 in. thickness	RT	L	32	57		17	57
			LT	17	57		13	60
	0.04-0.249 in. thickness		L	27	62		15	62
			LT	20	60		17	65
	½ hr. exposure	200 F	LT				9.5	60
	100 hr. exposure						8.0	62
	½ and 2 hr. exposure	300 F					4.0	54
	1000 hr. exposure						6.4	46
	½ hr. exposure	400 F					8.2	47
	100 hr. exposure						10	20
	1000 hr. exposure						6.0	16
	½ hr. exposure	500 F					7.0	22
	½ hr. exposure						4.3	9
	10 hr. exposure						6.0	8
	100 hr. exposure						13	7
	T62 Clad Plate	0.250 - 2.000 in. thickness	RT	L	29	64		27
LT				29	64		27	70
T651 Plate	0.250 - 2.000 in. thickness	RT	L	30	66		15	68
			LT	19	65		18	66
T6 Bar, Rod and Shapes	> 3 in. thickness	RT	L	31	62		25	60
T6 Forging		RT	L			70		
			LT			68		
T652 Hand Forging	2.001 - 3.000 in. thickness	RT	L	18	62	67	17	63
			LT	18	62	66	18	65
			ST	13	60		22	67
T6 Extrusion	0.125 - 0.499 in. thickness	RT	L	23	62		15	64
	> 0.500 in. thickness			26	68		14	72
T62 Extrusion	< 0.499 in. thickness	RT	L	29	64	71	17	68
			LT	29	64		32	68
T651X Extrusion	0.500 - 0.749 in. thickness	RT	L	32	64	74	16	68
			LT	18	64	70	18	68

**Figure 9.3.2.6. Example of stress-strain parameter table.**

**MIL-HDBK-5H**  
**1 December 1998**

Equation 9.3.2.4(a) shows the relationship between the plastic strain and stress values that hold for many materials up to that material's yield stress. The problem with this equation is that the Ramberg-Osgood parameter (n) typically changes for plastic strains greater than 0.002. Therefore, the variation of plastic strain typically must be expressed with two different equations. For stress values in the range between the proportional limit and yield stress, plastic strain can often be expressed by

$$e_p = 0.002 \left( f_1 / TYS \right)^{n_1} \quad [9.3.2.6(a)]$$

where

$f_1$  = any stress value between the proportional limit and tensile yield stress  
 TYS = the 0.2 percent typical yield stress  
 $e_p$  = the plastic strain.

In any tabular representation of these data for a given alloy (covering all production thickness and product forms), significant information may be missing. Therefore, only 50 percent of the data are required to be available before a table may be included in MIL-HDBK-5.

The data in this table may also be used to calculate other useful quantities. A table with all elements defined can be used to calculate the proportional limit in tension and compression, and the shear "yield" stress. Each of these calculations are covered below.

**Proportional Limit Stress in Tension and Compression.** If the proportional limit stress is equated with a plastic strain level of 0.0002 or a 0.02 percent deviation from linearity, and the Ramberg-Osgood relationship is found to be valid for small plastic strains, then the proportional limit stress ( $f_{p.l.}$ ) can be approximated from Equation 9.3.2.6(a) as follows:

$$f_{p.l.} = TYS \left( 0.10 \right)^{\frac{1}{n}} \quad [9.3.2.6(b)]$$

The same basic formulation could be used to define a proportional limit stress in compression, replacing TYS with CYS and n in tension with  $n_c$  in compression in Equation 9.3.2.6(b).

**Shear Yield Stress.** An estimate of the shear yield stress can be obtained from the equation:

$$F_{sy} = \frac{F_{ty}(L) + F_{ty}(LT) + F_{cy}(L) + F_{cy}(LT)}{4} \times \frac{2F_{su}}{F_{tu}(L) + F_{tu}(LT)} \quad [9.3.2.6(c)]$$

**MIL-HDBK-5H**  
**1 December 1998**

where

(p)	=	Primary load direction for shear
$F_{ty}(L)$	=	Tensile yield stress, longitudinal direction
$F_{ty}(LT)$	=	Tensile yield stress, long transverse direction
$F_{cy}(L)$	=	Compressive yield stress, longitudinal direction
$F_{cy}(LT)$	=	Compressive yield stress, long transverse direction
$F_{su}$	=	Shear ultimate stress
$F_{tu}(L)$	=	Tensile ultimate stress, longitudinal direction
$F_{tu}(LT)$	=	Tensile ultimate stress, long transverse direction.

**Compression Tangent Modulus Curves.** A mathematical procedure for construction of tangent modulus curves from compression stress-strain curves is given in Section 9.3.2.5. The compression stress-strain curve (up to the yield stress) may be constructed by adding the elastic strain component to the plastic strain component given in Equation 9.3.2.6(a). Calculation of the first derivative of stress with respect to strain gives tangent modulus values for specific values of total strain. Within MIL-HDBK-5 the tangent modulus curve is normally computed only up to the yield stress on the stress-strain curve. If tangent modulus values are desired at stress levels above the yield stress, a single function describing the relationship between stress and plastic strain over the range of interest should be used [rather than two separate functions as shown in Equations 9.3.2.6(a) and (b)].

**9.3.2.7 Minimum Stress-Strain and Stress Tangent-Modulus Curves** — Minimum stress-strain and stress tangent-modulus curves are not presented in MIL-HDBK-5, but these are sometimes required by the designer. Procedures for preparing minimum curves are identical to those for preparing typical curves, except for choice of yield-strength values. Product average, or average values of yield strength, are used to determine typical curves; minimum values ( $F_{ty}$  or  $F_{cy}$  A- or B-basis) are used to determine minimum curves. Average values of precision elastic modulus ( $E$  or  $E_c$ ) are used.

**9.3.2.8 Full-Range Tensile Stress-Strain Curves** — Preparation of each typical full-range tensile stress-strain curve requires (1) representative original full-range stress-strain curves, (2) product average values for ultimate strength, yield strength, and elongation, and (3) typical precision elastic-modulus values at test temperature. (See 9.3.2.2 for source and definition of product average values for ultimate strength, yield strength, and elongation as well as typical elastic-modulus values.) Full-range tensile stress-strain data for at least one lot of material shall be provided, but data from three lots are preferred. If data for less than three lots are submitted, the full-range stress-strain curve shall be labeled “BASED ON ONE LOT” or “BASED ON TWO LOTS”, as appropriate.

The procedure for developing typical full-range tensile stress-strain curves is based upon strain departures obtained from several original test curves, and the product average tensile strength, yield strength, and elongation established from production data. Properties of material tested for determining strain departures should be in reasonable agreement with the product average properties.

These steps, as illustrated in Table 9.3.2.8 and Figures 9.3.2.8(a) and (b), should be followed in developing typical full-range tensile stress-strain curves.



**MIL-HDBK-5H**  
**1 December 1998**

- (1) From each stress-strain test curve, measure strain departures (D) between the extension of the modulus line and the curve at stresses determined by taking appropriate percentages of the differences between ultimate stress and yield stress added to the yield stress.

$$f_{(1,n)} = \text{TYS} + \% (\text{TUS} - \text{TYS})$$

where TUS and TYS are values for each test. Also identify the proportional limit for each test. The proportional limit is defined as the stress level below, which the stress-strain curve is linear; as determined by  $f = E\epsilon$  where  $f$  is the stress,  $E$  is Young's Modulus, and  $\epsilon$  is the strain.

- (2) For departures beyond ultimate stress, the stresses are determined by taking the percentage of the difference between the fracture stress and ultimate stress and subtracting it from the ultimate stress.

$$f_{(1,n)} = \text{TUS} - (1 - \%) \cdot (\text{TUS} - \text{FS})$$

or

$$f_{(1,n)} = \text{FS} + \% (\text{TUS} - \text{FS})$$

where TUS and FS are values for each specimen.

- (3) For each percentage, average the stresses and strain departures,  $f_A$  and  $D_A$ , respectively.
- (4) Compute typical stresses between TYS and TUS using product average yield strengths.

$$f_T = \text{TYS}_{\text{Prod. Avg.}} + \% (\text{TUS}_{\text{Prod. Avg.}} - \text{TYS}_{\text{Prod. Avg.}})$$

- (5) Compute typical fracture stress,  $f_T(\text{FS})$ , as follows:

$$f_T(\text{FS}) = \frac{\text{TUS}_{\text{Prod. Avg.}}}{\text{TUS}_{\text{Avg.}}} f_{\text{Avg.}}(\text{FS})$$

- (6) Compute typical stresses between TUS and FS using product average ultimate strength and typical fracture stress.

$$f_T = \text{TUS}_{\text{Prod. Avg.}} - (1 - \%) \cdot (\text{TUS}_{\text{Prod. Avg.}} - f_T(\text{FS}))$$

or

$$f_T = f_T(\text{FS}) + \% (\text{TUS}_{\text{Prod. Avg.}} - f_T(\text{FS}))$$

**Table 9.3.2.8. Example of Strain-Departure Method to Establish Typical Full-Range Stress-Strain Curves**

Percent	Test 1		Test 2		Average		Typical			
	Stress, ksi $f_1$	Strain Departure <sup>c</sup> in./in. ( $D_1$ )	Stress, ksi $f_2$	Strain Departure <sup>c</sup> in./in. ( $D_2$ )	Stress, <sup>d</sup> ksi $f_A$	Strain Departure <sup>d</sup> in./in. ( $D_A$ )	Stress, ksi $f_T$	Strain Departure <sup>i</sup> in./in. ( $D_T$ )	Elastic Strain <sup>j</sup> in/in. ( $\epsilon_E$ )	Total Strain <sup>k</sup> in./in. ( $\epsilon_T$ )
<u>Yield Stress to Ultimate Stress</u>										
Proportional Limit (PL)	56.5		58.5		57.5 <sup>h</sup>		59.6 <sup>l</sup>	0.0000	0.0058	0.0058
0(TYS)	58.8 <sup>a</sup>	0.0020	60.9 <sup>a</sup>	0.0020	59.8	0.0020	62.0 <sup>e</sup>	0.0020	0.0061	0.0081
20	61.0 <sup>a</sup>	0.0106	63.0 <sup>a</sup>	0.0094	62.0	0.0100	64.0 <sup>e</sup>	0.0100	0.0063	0.0163
40	63.2 <sup>a</sup>	0.0204	65.2 <sup>a</sup>	0.0194	64.2	0.0199	66.0 <sup>e</sup>	0.0200	0.0065	0.0265
60	65.4 <sup>a</sup>	0.0302	67.4 <sup>a</sup>	0.0302	66.4	0.0302	68.0 <sup>e</sup>	0.0303	0.0067	0.0370
80	67.7 <sup>a</sup>	0.0452	69.5 <sup>a</sup>	0.0436	68.6	0.0444	70.0 <sup>e</sup>	0.0446	0.0069	0.0515
95	69.3 <sup>a</sup>	0.0640	71.1 <sup>a</sup>	0.0626	70.2	0.0633	71.5 <sup>e</sup>	0.0636	0.0070	0.0706
100(TUS)	69.9 <sup>a</sup>	0.0848	71.7 <sup>a</sup>	0.0838	70.8	0.0843	72.0 <sup>e</sup>	0.0847	0.0071	0.0918
<u>Ultimate Stress to Fracture Stress (FS)</u>										
100(TUS)	69.9 <sup>b</sup>	0.0848	71.7 <sup>b</sup>	0.0838	70.8	0.0843	72.0 <sup>g</sup>	0.0847	0.0071	0.0918
90	69.0 <sup>b</sup>	0.0962	70.9 <sup>b</sup>	0.1014	70.0	0.0988	71.1 <sup>g</sup>	0.0992	0.0070	0.1062
60	66.3 <sup>b</sup>	0.1058	68.5 <sup>b</sup>	0.1156	67.4	0.1107	68.5 <sup>g</sup>	0.1112	0.0067	0.1179
0(FS)	60.9 <sup>b</sup>	0.1210	63.7 <sup>b</sup>	0.1378	62.3	0.1294	63.4 <sup>f</sup>	0.1300	0.0062	0.1362
								(Elong.)		

a  $f_{1,n} = \text{TYS} + \% (\text{TUS} - \text{TYS})$  where TUS and TYS are values for each test.

b  $f_{1,n} = \text{TUS} - (1 - \%) \cdot (\text{TUS} - \text{FS})$  or  $f_{1,n} = \text{FS} + \% (\text{TUS} - \text{FS})$  where TUS and FS are values for each test.

c D = Departure (plastic strain) from modulus line at corresponding stresses.

d Averages (f and D) of Tests 1 and 2.

e  $f_T = \text{TYS}_{\text{Prod. Avg.}} + \% (\text{TUS}_{\text{Prod. Avg.}} - \text{TYS}_{\text{Prod. Avg.}})$ .

f  $f_T(\text{FS}) = (\text{TUS}_{\text{Prod. Avg.}} / \text{TUS}_{\text{Avg.}}) \cdot f_{\text{Avg.}}(\text{FS})$ .

g  $f_T = \text{TUS}_{\text{Prod. Avg.}} - (1 - \%) \cdot (\text{TUS}_{\text{Prod. Avg.}} - f_T(\text{FS}))$  or  $f_T = f_T(\text{FS}) + \% (\text{TUS}_{\text{Prod. Avg.}} - f_T(\text{FS}))$ .

h Average proportional limit.

i  $D_T = [((D_A - 0.002) \times (\text{Product Average Elongation} - 0.002)) \div (D_A \text{ at FS} - 0.002)] + 0.002$ .

j  $\epsilon_E = f_T \div E$  ( $E = 10.2 \times 10^3$  ksi in this example).

k  $\epsilon_T = D_T + \epsilon_E$ .

l  $f_T(\text{PL}) = (\text{TYS}_{\text{Prod. Avg.}} / \text{TYS}_{\text{Avg.}}) \cdot f_{\text{Avg.}}(\text{PL})$ .

MIL-HDBK-5H  
1 December 1998




Figure 9.3.2.8(a). Strain departure method for determining average full-range stress-strain curve.




Figure 9.3.2.8(b). Method of adjusting average to typical full-range stress-strain curve.

**MIL-HDBK-5H**  
**1 December 1998**

- (7) Adjust the average departures,  $D_A$ , to typical departures,  $D_T$ , as follows:

$$D_T = \frac{(D_A - 0.002)(\text{Prod. Avg. Elong.} - 0.002)}{(D_A \text{ at Fracture Stress} - 0.002)} + 0.002 \quad .$$

- (8) Compute elastic strains,  $\epsilon_E$ , by dividing typical stresses by typical modulus.

$$\epsilon_T = \frac{f_T}{E}$$

- (9) Obtain total strain,  $\epsilon_T$ , by adding  $D_T$  and  $\epsilon_E$ .

- (10) Calculate the average proportional limit from the stress-strain curves and compute the typical proportional limit.

$$f_T(\text{PL}) = \left( \text{TYS}_{\text{Prod. Avg.}} / \text{TYS}_{\text{Avg.}} \right) \cdot f_{\text{Avg.}}(\text{PL})$$

The final step is plotting the full-range stress-strain curves. The following guidelines should be followed to plot the stress-strain curve. There should be 10 minor divisions for every major division with every tenth (major) division accented. The ordinate (Y-axis) is used for stress and should be in units of 5, 10, 20, or 50 ksi to the major division. The abscissa (X-axis) is used for strain and should be in units of 0.01, 0.02, 0.05, or 0.1 in./in. to the major division.

In addition to plotting the graphs by hand, they may be plotted with computer software programs. In the latter case, input the stress-strain pairs ( $f_T$  and  $\epsilon_T$ ) from Table 9.3.2.8 into the computer and then curve fit the data. The elastic section must be linear up to the proportional limit. It is recommended that a power-law polynomial second order be used to fit the data from the proportional limit to fracture stress. The full-range stress-strain curve should be solid up to maximum stress and dashed from maximum stress to rupture. The fracture point should be indicated with an X. Only one typical full-range stress-strain figure should be plotted per page and should fill as much of the page as possible as illustrated in Figure 9.3.2.8(c). If more than one curve is contained in the figure, information such as the direction (ST, LT, and L), and/or temperature for each curve must be indicated.

**9.3.3 BIAXIAL STRESS-STRAIN BEHAVIOR** — Procedures for analyzing and presenting biaxial stress-strain properties may be added to the guidelines at a later date. In the interim, procedures described in Reference 9.3.3 may be used as a general guide.

MIL-HDBK-5H  
1 December 1998




Figure 9.3.2.8(c). Typical full-range curves drawn by the strain-departure method.

**MIL-HDBK-5H**  
**1 December 1998**

### **9.3.4 FATIGUE DATA ANALYSIS**

**9.3.4.1 Introduction** — Fatigue has been defined as “the process of progressive localized permanent structural change occurring in a material subjected to conditions that produce fluctuating stresses and strains at some point or points, and which may culminate in cracks or complete fracture after a sufficient number of fluctuations.”

For many years, tests have been performed on specimens having simple geometries in attempts to characterize the fatigue properties of particular materials. Fatigue tests have been conducted for many reasons. Basic fatigue-life information may be desired for design purposes, or to evaluate the differences between materials. The effects of heat treatments, mechanical working, or material orientation may also be studied through comparative fatigue testing.

Many types of machines and specimen designs have been used to develop fatigue data. Machine types include mechanical, electromechanical, hydraulic, and ultrasonic. Specimens have been designed for testing in cyclic tension and/or compression, bending, and torsion. Cyclic loading conditions have been produced by rotating bending, axial loading and cantilever bending. In- and out-of-phase biaxial and multiaxial fatigue conditions have also been examined using specially designed specimens. Tests have been conducted in a variety of simulated environments including temperatures ranging from cryogenic to near melting point levels. The fatigue data included in MIL-HDBK-5 are limited to constant-amplitude axial fatigue data on simple laboratory specimens tested according to ASTM E 606 [Reference 9.3.4.1(a)]. Data obtained under both strain control and load (stress) control are included. Figure 9.3.4.1(a) shows examples of trends for stress-life and strain-life fatigue data. Generally, stress-life data for unnotched specimens are limited to stress levels that produce intermediate-to-long fatigue lives because of unstable cyclic creep and tensile failure that can occur at high stress ratios in load-control testing. This phenomenon is shown in Figure 9.3.4.1(b). Strain-life curves are often focused on strain ranges that produce short-to-intermediate fatigue lives because of strain rate and frequency limitations which require long testing times to generate long-life fatigue data under strain control. However, there is no inherent limit to the life range that can be evaluated in strain-control testing.

For fatigue to occur, a material must undergo cyclic plasticity, at least on a localized level. The relationship between total strain, plastic strain, and elastic strain is shown in Figure 9.3.4.1(c). Low-cycle fatigue tests involve relatively high levels of cyclic plasticity. Intermediate-life fatigue tests usually involve plastic strains of the same order as the elastic strains. Long-life fatigue tests normally involve very low levels of cyclic plasticity. These trends are shown in Figure 9.3.4.1(d). In the MIL-HDBK-5 fatigue analysis guidelines, engineering strain is denoted as  $e$  and true or local strain is denoted as  $\epsilon$ . These symbols are used interchangeably within MIL-HDBK-5 for small strain values.

The limited plasticity involved in intermediate and long-life fatigue tests often results in a similar stress-strain response for both fully reversed strain-control and fully reversed load-control tests. A fatigue test, under strain control that produces a stable maximum stress of  $X$ , should produce (on the average) a fatigue life that is comparable to that obtained for a sample tested under load control at a maximum stress of  $X$ . Strictly speaking, the results are likely to be most comparable in terms of crack initiation life and not total life. If the comparison is made in terms of total life, the load-control results will tend to be more conservative than those generated by strain-control testing. When a specimen cracks in a test under strain control, it will usually display a decrease in maximum tensile load. Under load control, the maximum tensile load will remain constant but stress will increase as the crack grows, resulting in a shorter period of crack growth before the specimen fails.



MIL-HDBK-5H  
1 December 1998




Figure 9.3.4.1(a). Examples of stress-life and strain-life fatigue trends.

MIL-HDBK-5H  
1 December 1998




Figure 9.3.4.1(b). Example of cyclic creep phenomenon that can occur in a load control test with a high tensile mean stress [Reference 9.3.4.1(b)].





Figure 9.3.4.1(c). A typical hysteresis loop for a material tested in fatigue under strain control illustrating the relationship between stress and strain parameters.



MIL-HDBK-5H  
1 December 1998



**Figure 9.3.4.1(d). An example of a strain-life fatigue curve and the stress-strain response at short, intermediate, and long fatigue lives.**

A number of factors can significantly influence fatigue properties for a particular material—whether the data are developed under load or under strain control. The surface condition (such as surface roughness) of the test specimens is an important factor. The methods used for fabricating the specimens are also important—principally because such methods influence the state of surface residual stresses and residual stress profiles. Other factors such as mean stress or strain, specimen geometry (including notch type), heat treatment, environment, frequency and temperature can also be significant variables. In MIL-HDBK-5, fatigue data are always presented in separate displays for different theoretical stress concentration factors. However, data sets may be presented for various combinations of variables if preliminary analyses indicate that the data sets are compatible. In any case, it is very important to fully document both the input data and their resulting illustrations in MIL-HDBK-5 with regard to variables that can influence fatigue.

**9.3.4.2 Disclaimer** — The selection of the specific procedures and methods that are outlined in this guideline for fatigue data presentation should not be construed as an endorsement of these procedures and methods for life prediction of components. The selection was made for consistency in data presentation only. For the purpose of life prediction, other methods and models are also commonly employed. Depending on the material, component and loading history, other models may be more appropriate for the particular situation. It is beyond the scope of these guidelines to make recommendations with respect to a specific life prediction methodology (e.g., the construction of design allowable fatigue curves).

**9.3.4.3 Terminology** — The symbols and definitions used in analyzing and reporting fatigue data have been standardized by the American Society for Testing and Materials (ASTM). Most definitions of terms are consistent with those defined by the ASTM. However, some of the symbols and definitions differ and are noted with an asterisk (\*). The terms are listed in alphabetical order. In the definitions listed below, the term for load ( $P$ ) is taken to represent stress ( $S$ ), strain ( $\epsilon$  or  $e$ ), or any other expression or function of loading. The most common terms relating to fatigue loading are illustrated in Figure 9.3.4.3.

MIL-HDBK-5H  
1 December 1998




Figure 9.3.4.3. Typical fatigue loadings.

**MIL-HDBK-5H**  
**1 December 1998**

Alternating Load — See Loading Amplitude.

Confidence Interval — An interval estimate of a population parameter computed so that the statement “the population parameter lies in this interval” will be true, on the average, in a stated proportion of the times such statements are made.

Confidence Level (or Coefficient) — The stated portion of the time that the confidence interval is expected to include the population parameter.

Confidence Limits\* — The two numeric values that define a confidence interval.

Constant-Amplitude Loading — A loading in which all of the peak loads are equal and all of the valley loads are equal.

Constant-Life Fatigue Diagram — A plot (usually on Cartesian coordinates) of a family of curves, each of which is for a single fatigue life,  $N$ —relating  $S$ ,  $S_{\max}$ , and/or  $S_{\min}$  to the mean stress,  $S_m$ . Generally, the constant life fatigue diagram is derived from a family of  $S/N$  curves, each of which represents a different stress ratio ( $A$  or  $R$ ) for a 50 percent probability of survival. NOTE—MIL-HDBK-5 no longer presents fatigue data in the form of constant-life diagrams.

Cycle — Under constant-amplitude loading, the load varies from the minimum to the maximum and then to the minimum load (see Figure 9.3.4.3). The symbol  $n$  or  $N$  (see definition of fatigue life) is used to indicate the number of cycles.

Discontinued Test — See Runout.

Fatigue — The process of progressive localized permanent structural change occurring in a material subjected to conditions that produce fluctuating stresses and strains at some point or points, and which may culminate in cracks or complete fracture after a sufficient number of fluctuations. NOTE—fluctuations in stress and in time (frequency), as in the case of “random vibration”.

Fatigue Life —  $N$ —the number of cycles of stress or strain of a specified character that a given specimen sustains before failure of a specified nature occurs.

Fatigue Limit —  $S_f$ —the limiting value of the median fatigue strength as  $N$  becomes very large. NOTE—Certain materials and environments preclude the attainment of a fatigue limit. Values tabulated as “fatigue limits” in the literature are frequently (but not always) values of  $S_N$  for 50 percent survival at  $N$  cycles of stress in which  $S_m = 0$ .

Fatigue Loading — Periodic or non-periodic fluctuating loading applied to a test specimen or experienced by a structure in service (also known as cyclic loading).

Fatigue Notch Factor\* — The fatigue notch factor,  $K_f$  (also called fatigue strength reduction factor), is the ratio of the fatigue strength of a specimen with no stress concentration to the fatigue strength of a specimen with a stress concentration at the same number of cycles for the same conditions. NOTE—In specifying  $K_f$ , it is necessary to specify the geometry, mode of loading, and the values of  $S_{\max}$ ,  $S_m$ , and  $N$  for which it is computed.

---

\* Different from ASTM.

**MIL-HDBK-5H**  
**1 December 1998**

**Fatigue Notch Sensitivity** — The fatigue notch sensitivity,  $q$ , is a measure of the degree of agreement between  $K_f$  and  $K_t$ . NOTE—The definition of fatigue notch sensitivity is  $q = (K_f - 1)/(K_t - 1)$ .

**Hysteresis Diagram** — The stress-strain path during a fatigue cycle.

**Interrupted Test\*** — Tests which have been stopped before failure because of some mechanical problem, e.g., power failure, load or temperature spikes.

**Loading Amplitude** — The loading amplitude,  $P_a$ ,  $S_a$ , or  $\epsilon_a$  represents one-half of the range of a cycle (see Figure 9.3.4.3). (Also known as alternating load, alternating stress, or alternating strain.)

**Loading (Unloading) Rate** — The time rate of change in the monotonically increasing (decreasing) portion of the load-time function.

**Load Ratio** — The load ratio,  $R$ ,  $A$ , or  $R_\epsilon$ ,  $A_\epsilon$ , or  $R_\sigma$ ,  $A_\sigma$ , is the algebraic ratio of the two loading parameters of a cycle; the two most widely used ratios are

$$R = \frac{\text{minimum load}}{\text{maximum load}} = \frac{P_{\min}}{P_{\max}}$$

or

$$R_\sigma = \frac{S_{\min}}{S_{\max}}$$

or

$$R_\epsilon = \epsilon_{\min}/\epsilon_{\max}$$

and

$$A = \frac{\text{loading amplitude}}{\text{mean load}} = \frac{P_a}{P_m} \text{ or } \frac{S_a}{S_m}$$

$$A_\epsilon = \frac{\text{strain amplitude}}{\text{mean strain}} = \frac{\epsilon_a}{\epsilon_m} \text{ or } (\epsilon_{\max} - \epsilon_{\min})/(\epsilon_{\max} + \epsilon_{\min}) .$$

NOTE—Load ratios  $R$  or  $R_\epsilon$  are generally used in MIL-HDBK-5.

**Maximum Load** — The maximum load,  $P_{\max}$ ,  $S_{\max}$ ,  $\epsilon_{\max}$  is the load having the greatest algebraic value.

**Mean Load** — The mean load,  $P_m$ , is the algebraic average of the maximum and minimum loads in constant-amplitude loading:

**MIL-HDBK-5H**  
**1 December 1998**

$$P_m = \frac{P_{\max} + P_{\min}}{2},$$

or

$$S_m = \frac{S_{\max} + S_{\min}}{2},$$

or

$$\epsilon_m = \frac{\epsilon_{\max} + \epsilon_{\min}}{2},$$

or the integral average of the instantaneous load values.

**Median Fatigue Life** — The middlemost of the observed fatigue life values (arranged in order of magnitude) of the individual specimens in a group tested under identical conditions. In the case where an even number of specimens are tested, it is the average of the two middlemost values (based on log lives in MIL-HDBK-5). NOTE 1—The use of the sample median instead of the arithmetic mean (that is, the average) is usually preferred. NOTE 2—In the literature, the abbreviated term “fatigue life” usually has meant the median fatigue life of the group. However, when applied to a collection of data without further qualification, the term “fatigue life” is ambiguous.

**Median Fatigue Strength at N Cycles** — An estimate of the stress level at which 50 percent of the population would survive N cycles. NOTE—The estimate of the median fatigue strength is derived from a particular point of the fatigue-life distribution, since there is no test procedure by which a frequency distribution of fatigue strengths at N cycles can be directly observed. That is, one can not perform constant-life tests.

**Minimum Load** — The minimum load,  $P_{\min}$ ,  $S_{\min}$ , or  $\epsilon_{\min}$ , is the load having the least algebraic value.

**Outlier\*\*** —An experimental observation which deviates markedly from other observations in the sample. An outlier is often either an extreme value of the variability in the data, or the result of gross deviation in the material or experimental procedure.

**Peak**—The point at which the first derivative of the load-time history changes from a positive to a negative sign; the point of maximum load in constant-amplitude loading (see Figure 9.3.4.3).

**Precision\***—The degree of mutual agreement among individual measurements. Relative to a method of test, precision is the degree of mutual agreement among individual measurements made under prescribed like conditions. The lack of precision in a measurement may be characterized as the standard deviation of the errors in measurement.

**Range**—Range,  $\Delta P$ ,  $S_r$ ,  $\Delta \epsilon$ ,  $\epsilon_r$ ,  $\Delta \sigma$  is the algebraic difference between successive valley and peak loads (positive range or increasing load range) or between successive peak and valley loads (negative range or decreasing load range), see Figure 9.3.4.3. In constant-amplitude loading, for example, the range is given by  $\Delta P = P_{\max} - P_{\min}$ .

---

\* Different from ASTM.

**MIL-HDBK-5H**  
**1 December 1998**

**Residual\***—The difference between the observed fatigue (log) life and the fatigue (log) life estimated from the fatigue model at a particular stress/strain level.

**Runout\***—A test that has been terminated prior to failure. Runout tests are usually stopped at an arbitrary life value because of time and economic considerations. **NOTE**—Runout tests are useful for estimating a pseudo-fatigue-limit for a fatigue data sample.

**Sample**—The number of specimens selected from a population for test purposes. **NOTE**—The method of selecting the sample determines the population about which statistical inferences or generalization can be made.

**Sample Average (Arithmetic Mean)**—The sum of all the observed values in a sample divided by the sample size (number). It is a point estimate of the population mean.

**Sample Median**—The middle value when all observed values in a sample are arranged in order of magnitude if an odd number of samples are tested. If the sample size is even, it is the average of the two middlemost values. It is a point estimate of the population median, or 50 percentile point.

**Sample Standard Deviation\***—The standard deviation of the sample,  $s$ , is the square root of the sample variance. It is a point estimate of the standard deviation of a population, a measure of the “spread” of the frequency distribution of a population. **NOTE**—This value of  $s$  provides a statistic that is used in computing interval estimates and several test statistics.

**Sample Variance\***—Sample variance,  $s^2$ , is the sum of the squares of the differences between each observed value and the sample average divided by the sample size minus one. It is a point estimate of the population variance. **NOTE**—This value of  $s^2$  provides both an unbiased point estimate of the population variance and a statistic that is used on computing the interval estimates and several test statistics. Some texts define  $s^2$  as “the sum of the squared differences between each observed value and the sample average divided by the sample size”; however, this statistic underestimates the population variance, particularly for small sample sizes.

**Significant (Statistically significant)**—An effect or difference between populations is said to be present if the value of a test statistic is significant, that is, lies outside of predetermined limits. **NOTE**—An effect that is statistically significant may not have engineering importance.

**Significance Level**—The stated probability (risk) that a given test of significance will reject the hypothesis that a specified effect is absent when the hypothesis is true.

**S/N Curve for 50 Percent Survival\***—A curve fitted to the median values of fatigue life at each of several stress levels. It is an estimate of the relationship between applied stress and the number of cycles-to-failure that 50 percent of the population would survive. **NOTE 1**—This is a special case of the more general definition of S/N curve for P percent survival. **NOTE 2**—In the literature, the abbreviated term “S/N Curve” usually has meant either the S/N curve drawn through the mean (averages) or through the medians (50 percent values) for the fatigue life values. Since the term “S/N Curve” is ambiguous, it should be used only when described appropriately. **NOTE 3**—Mean S/N curves (based on log lives) are shown in MIL-HDBK-5.

---

\* Different from ASTM.

**MIL-HDBK-5H**  
**1 December 1998**

**S/N Diagram**—A plot of stress against the number of cycles to failure. The stress can be  $S_{\max}$ ,  $S_{\min}$ , or  $S_a$ . The diagram indicates the S/N relationship for a specified value of  $S_m$ , A, or R and a specified probability of survival. Typically, for N, a log scale (base 10) is used. Generally, for S, a linear scale is used, but a log scale is used occasionally. NOTE— $S_{\max}$ -versus-log N diagrams are used commonly in MIL-HDBK-5.

**Theoretical Stress Concentration Factor (or Stress Concentration Factor)**—This factor,  $K_t$ , is the ratio of the greatest stress to the nominal stress in the region of a notch (or other stress concentrator) as determined by the theory of elasticity (or by experimental procedures that give equivalent values). NOTE—The theory of plasticity should not be used to determine  $K_t$ .

**Tolerance Interval**—An interval computed so that it will include at least a stated percentage of the population with a stated probability.

**Tolerance Level**—The stated probability that the tolerance interval includes at least the stated percentage of the population. It is not the same as a confidence level, but the term confidence level is frequently associated with tolerance intervals.

**Tolerance Limits**—The two statistics that define a tolerance interval. (One value may be “minus infinity” or “plus infinity”.)

**Transition Fatigue Life\***—The point on a strain-life diagram where the elastic and plastic strains are equal.

**Waveform**—The shape of the peak-to-peak variation of a controlled mechanical test variable (for example, load, strain, displacement) as a function of time.

The following symbols are used frequently for the term covered by the preceding definitions. For stress, the use of S with appropriate lower case subscripts is preferred for general purposes; for mathematical analysis, the use of Greek symbols is generally preferred.

<u>Symbol</u>	<u>Term</u>
A	“A” ratio, loading amplitude/mean load; or area
$A_e$	strain “A” ratio, strain amplitude/mean strain
$A_i$	model parameter
D or d	diameter, or Durbin Watson statistic
E	modulus of elasticity in tension or compression
e	engineering strain
$\epsilon$	true or local strain
$\epsilon_{eq}^*$	equivalent strain

---

\* Different from ASTM.

**MIL-HDBK-5H**  
**1 December 1998**

$\epsilon_m$	mean strain, $(\epsilon_{\max} + \epsilon_{\min})/2$
$\epsilon_{\max}$	maximum strain
$\epsilon_{\min}$	minimum strain
$\Delta\epsilon$ or $\epsilon_r^*$	strain range, $\epsilon_{\max} - \epsilon_{\min}$
<u>Symbol</u>	<u>Term</u>
$\Delta\epsilon_e$	elastic strain range
$\Delta\epsilon_p$	plastic strain range
$K_f$	fatigue notch factor, or fatigue strength reduction factor
$K_t$	theoretical stress concentration factor
$\mu$	Poisson's ratio
$N$	fatigue life, number of cycles
$N_f$	fatigue life, cycles to failure
$N_i^*$	fatigue life, cycles to initiation
$N_t^*$	transition fatigue life where plastic and elastic strains are equal
$P$	load
$P_a$	load amplitude
$P_m$	mean load
$P_{\max}$	maximum load
$P_{\min}$	minimum load
$q$	fatigue notch sensitivity
$R$	load (stress) ratio, or residual (observed minus predicted value)
$R_\epsilon$	strain ratio, $\epsilon_{\min}/\epsilon_{\max}$
$S$	nominal or engineering stress
$s$	sample standard deviation
$s^2$	sample variance

---

\* Different from ASTM.



**MIL-HDBK-5H**  
**1 December 1998**

$S_a$	stress amplitude
$S_{eq}^*$	equivalent stress
$S_f$	fatigue limit
<u>Symbol</u>	<u>Term</u>
$S_m$	mean stress
$S_{max}$	maximum stress
$S_{min}$	minimum stress
SR	studentized residual
$\Delta S (S_r)^*$	stress range
TUS ( $S_u$ ) <sup>*</sup>	tensile ultimate strength
$\sigma$	true or local stress; or population standard deviation
$\sigma_x$	population standard deviation of x
$\sigma_x^2$	population variance of x
$\Delta\sigma$	true or local stress range.

**9.3.4.4 Data Requirements** — Both strain-controlled and load-controlled axial fatigue data can be considered for inclusion in MIL-HDBK-5. Constant amplitude test data are the primary focus. Well-documented, initial and/or periodic overstrain data may also be included. Data obtained under strain control are considered only for unnotched, uniform-gage-length specimens, while both notched and unnotched specimens are considered for load-control conditions.

Fatigue data generated under load control over a wide range of stress ranges and ratios can be acceptable. However, load-control experiments on unnotched samples can produce ratcheting failures rather than true fatigue failures. This can be a problem with materials that cyclically soften. In the absence of cyclic stress-strain data, the acceptability of short-life data obtained under load control on unnotched specimens can be difficult to evaluate. Therefore, results from specimens tested at a maximum stress level greater than the average tensile ultimate strength of the material should not be used. In addition, test results obtained under load control that have produced average fatigue lives on unnotched specimens of less than  $10^3$  cycles should be excluded. Short-life, load-control data generated on notched samples tested at high stress levels may be considered.

Fatigue data generated under strain control over a wide range of strain ratios and ranges can be acceptable also. High-strain-range tests producing low fatigue lives can be considered assuming that documented bending strains were held within ASTM E 606 limits and buckling failures were not produced. Documenting the stress response associated with each test result is important. The stress data that are

---

\* Different from ASTM.

**MIL-HDBK-5H**  
**1 December 1998**

reported should reflect the material's stable response, including effects of cyclic hardening or softening and of mean stress relaxation provided such data were obtained at other than  $R_\epsilon = -1$ . The normal convention is to report the stress values associated with one-half the material's fatigue life to crack initiation. Several criteria are commonly used to define crack initiation in a test under strain control. The primary requirements for inclusion in MIL-HDBK-5 are that the criteria be specific and applied consistently. If multiple sources of data are being considered, the potential problem of inconsistent crack initiation criteria must be addressed before that data are merged.

If strain-control data only are reported with fatigue test results obtained under strain control, these data must be supported by well-documented cyclic stress-strain curves and mean stress relaxation data for that specific material.

For fatigue experiments under load control, data are normally generated at specific stress ratios or mean stress levels. If the stress ratio is held constant, a fatigue curve is generated by performing a series of experiments at prescribed maximum stress levels such that the desired range of fatigue lives is achieved. If mean stress levels are held constant, a range of maximum stress levels is also used, but the stress ratio for each maximum stress level is different. Presentation of the latter type of data in a traditional  $S_{\max}$ -versus-log  $N_f$  display, with individual stress ratio curves, can be cumbersome because of the large number of stress ratios involved. For this reason, constant mean-stress fatigue data should be identified by mean stress level, even though they are plotted on a standard  $S_{\max}$ -versus-log  $N_f$  display. The illustrations should be clearly labeled to properly identify the mean-stress or stress-ratio levels.

To evaluate analytically the effects of stress or strain ratio on the fatigue performance of a particular material, it is recommended that data be available for at least three stress or strain ratios, or alternatively, three mean-stress or strain levels. Similarly, at least three stress or strain levels are recommended to evaluate the effects of mean stress on fatigue performance. In the case of data under strain control, a specific strain ratio or mean strain may not define a mean-stress level uniquely. For  $R_\epsilon = -1.0$  (mean strain = 0), the stress ratio is usually very close to  $R = -1.0$  (mean stress = 0)—if it is not, the data should be examined carefully for validity. For strain ratios greater than  $R_\epsilon = -1.0$ , the stress ratio is usually less than the strain ratio, and the difference is generally greater at the greatest strain ranges. For very large strain ranges in ductile materials, the stable stress ratio will approach  $R = -1.0$  (mean stress = 0), regardless of the strain ratio,  $R_\epsilon$ . Mean stress relaxation behavior is shown in Figure 9.3.4.4.

There should be at least six non-runout fatigue test results for each condition, and these data should be distributed over at least two orders of magnitude in fatigue life. These requirements are the minimum sample sizes normally required to consider developing a fatigue data display. Meeting the minimum data requirements does not ensure an acceptable set of fatigue curves. In cases involving highly scattered data, substantially larger sample sizes may be required to achieve a meaningful description of mean fatigue trends. The statistical procedures used to evaluate the significance of a fatigue data collection are described in Section 9.3.4.12.

**9.3.4.5 Fatigue Test Planning and Data Development** — In view of the above data requirements, fatigue data generated for inclusion in MIL-HDBK-5 should be the result of a well-planned test program. The following general discussion of fatigue test planning is based in large part on the concepts presented in References 9.3.4.5(a), (b), and (c). Those interested in the detailed aspects of fatigue test planning should refer to these and other sources. The discussion that follows pertains to fatigue testing under either load control or strain control.

MIL-HDBK-5H  
1 December 1998




Figure 9.3.4.4. Schematic of stabilized mean stress relaxation for different strain ranges at  $R_e = 0$ .

**MIL-HDBK-5H**  
**1 December 1998**

Traditionally, fatigue testing under load control has been performed to evaluate the fatigue performance of engineering materials and components subjected to numerous load fluctuations. Notched specimens are often used to evaluate the effect of stress concentrations upon fatigue life in load-control testing. The nominal stresses during load-control testing are generally below the materials yield strength and the resulting fatigue lives are usually greater than  $10^4$  cycles. Load-control tests with high mean-stress levels may develop unconstrained cyclic plasticity which may lead to ratcheting failures (see Figure 9.3.4.1(b)). Unless cyclic strains are monitored in load-control tests, it is not possible to know exactly when unconstrained cyclic plasticity will develop. In general, however, there are test conditions that should be avoided when operating under load control, as follows:

- (1) Unnotched-specimen fatigue tests in which fatigue lives less than  $10^3$  cycles to failure are expected.
- (2) Fatigue tests involving net-section maximum stresses greater than the yield strength or over 95 percent of the typical monotonic ultimate strength of the material.

Strain-controlled fatigue testing has emerged since the mid-1950s because the fatigue damage process was found to be highly dependent upon cumulative plastic deformation. Cycling a material between two strain limits can alter the material's stress-strain response (cyclic hardening or softening) compared to the monotonic response. Fatigue testing under strain control should be considered in cases where constrained inelastic cyclic strains may occur in the actual component. Strain control should also be used for any conditions where unconstrained cyclic plasticity may lead to ratcheting failures in load-control testing.

Fatigue data obtained under load control for use in MIL-HDBK-5 should be generated for at least three stress ratios. Fatigue lives ranging from approximately  $10^3$  to  $10^6$  cycles are most commonly of interest while the stress ratios chosen should normally span the range from about  $R = -1.0$  to  $0.50$  or greater.

Fatigue data obtained under strain control are commonly generated at  $R_\epsilon = -1.0$ . These data will be considered for MIL-HDBK-5, but generating data for at least two other strain ratios is also desirable.

The stabilized value of mean stress attained in a strain-control test at  $R_\epsilon$  greater than  $-1.0$  will be different from that observed at the beginning of the test for materials that undergo cyclic mean stress relaxation. The degree of stress relaxation will depend on strain range and strain ratio, the magnitude being greater at larger strain ranges or larger strain ratios. Complete relaxation to a zero mean stress is the limiting case. When testing at strain ratios greater than  $-1.0$ , it is appropriate to limit the strain ranges to values below those at which total cyclic mean-stress relaxation occurs.

The amount of cyclic stress relaxation also varies with the anticipated fatigue life. Large-strain-range, low-cycle tests usually exhibit the greatest mean stress relaxation. Because of this behavior, it is usually appropriate to run the positive mean strain experiments at strain ranges less than or equal to the level that produces complete mean stress relaxation.

A given series of fatigue tests conducted under strain control should be targeted to describe the useful life range for the material. The life range explored need only be limited on the low side by the maximum strain ranges that can be performed without specimen buckling problems, and on the high side by the maximum strain rates that are allowable, in combination with the permissible duration of individual tests. Life ranges of  $10$  to  $10^6$  cycles are reasonable to explore in strain-control tests with many materials and specimen geometries. Strain-control tests performed for inclusion in MIL-HDBK-5 should normally be conducted with symmetric waveforms, with no hold times at frequencies ranging from  $0.10$  to  $5$  Hz—depending on the response of extensometry and recording equipment. It is important to document the strain rates and conformance of the testing techniques with ASTM E 606 [Reference 9.3.4.1(a)].

**MIL-HDBK-5H**  
**1 December 1998**

Long-life fatigue tests are a special situation in strain-control testing because of the extended test periods that may be required, especially if maximum test frequencies must be kept at or below 1 Hz. For example, a test run at 1 Hz involving one million cycles requires about 11-1/2 days. Decreasing the duration of long-life, strain-control fatigue tests are desirable whenever possible; otherwise, a few tests in the  $10^6$  to  $10^7$  cycle range can take as much time as the rest of the life curve.

Switching from strain-control testing to load-control testing at a greater frequency at some point in the life of the specimen is becoming a common practice. This switch is typically done when the cyclic response is nominally elastic. Usually the frequency can be increased by a factor of 10 or more but even a factor of 2 or 3 is certainly worthwhile.

When the control mode and/or frequency are changed, certain criteria should be observed. When generating a strain-control fatigue curve, ranging from the short-life regime ( $10$  to  $10^3$  cycles) to the long-life regime ( $10^6$  to  $10^8$  cycles), the fatigue tests can be placed in three groups for consideration.

At the short-life end of the curve, the material response will typically vary throughout the test. In this regime, a significant amount of inelastic strain may be present, cyclic hardening or softening may occur as well as mean stress shifts. In short, no consistent relationships exist between stress and strain and, therefore, no control mode change is recommended in this life regime.

For intermediate life tests, some inelastic strain may be present and, for a period of time, the stress-strain relationship may vary. Generally, however, a stabilized, consistent relationship is eventually achieved. Under these conditions, it may be possible to switch the test mode to load control at a higher frequency.

In the long-life regime, very little inelastic strain will normally be present, and stress-strain stabilization is achieved very rapidly. Here, switching from the strain-control mode to the load-control mode can be accomplished.

The material behavior cited above can only be evaluated by starting all of the tests in the strain-control mode and then switching the mode and frequency when stabilized stress-strain behavior is achieved. An evaluation of the strain rate behavior of the material in the strain-control mode (within the normal response capabilities of the equipment) may be desirable to determine if the stress-strain relationship is likely to change when the frequency is changed.

In summary, do not switch control modes in the low life regime of the fatigue curve. When some inelastic strain is present, switching may be employed if stable stress-strain response can be obtained and a negligible strain rate effect at the test temperature and strain range of interest can be demonstrated (i.e., it can be shown that fatigue life and stress range are not influenced by loading rate). One very good check is to produce overlapping data points in this regime where some tests are run to failure in the strain-control mode while others are switched to high-frequency load-control mode after stabilization is obtained. This is necessary to provide assurance that the switching procedure is not influencing results.

At the very long-life end of the curve, the essentially elastic behavior of the material is most conducive to switching of control modes. The greatest benefit of the increased frequency can also be obtained here. If results have shown that switching is successful at the intermediate strain range level, then the probability of the long-life tests being at least as successful is high. If, however, the material exhibits a measurable inelastic strain and is slow to stabilize even after many cycles, caution should be exercised in making the decision for a control mode change.

When the determination that a test should be switched from strain control to load control has been made, the following sequence is recommended:

**MIL-HDBK-5H**  
**1 December 1998**

- (1) Note the maximum and minimum stabilized load levels.
- (2) Gradually reduce the strain range to zero. This process should take several cycles (at least 10). If a measurable inelastic strain is present, the strain range reduction should take sufficient cycles so the magnitudes of the maximum and minimum loads are reduced symmetrically.
- (3) At this point (strain range at zero) the load may or may not be at zero, depending on the conditions of strain ratio and strain range to which the specimen was exposed. If a residual load is present, the load should be adjusted to zero by carefully changing the strain level.
- (4) Next, the test system should be switched to the load-control mode and the test restarted. The strain-control cycling may have been performed using a triangular waveform. The higher frequency testing under load control generally employs a sine wave. The waveshape difference is only of secondary importance, and most machines can easily control a high frequency sine wave. The actual frequency used should be well within the capability of the test equipment so that the load can be accurately measured and controlled. Furthermore, care must be taken to avoid frequency effects, e.g., self-heating, and strain-rate effects. This is commonly a problem with tests involving a significant amount of inelastic strain.

When reproducing the maximum and minimum stresses that existed under strain-control testing, first introducing the mean load on the specimen and then gradually increasing the load range symmetrically from this point is generally preferred. Whatever procedures are used should be clearly defined and well documented.

The tendency of the load-control results to be slightly more conservative than those generated in strain-control testing is worth repeating. When a specimen develops a fatigue crack, a test that is being conducted under strain-control mode will generally exhibit a reduced tensile load as the crack propagates. Under load-control testing, the load remains constant and the crack will grow faster, resulting in a lesser life. For this reason, all data generated by this technique should be so noted and identified on data tables and graphs.

Essentially two steps are involved in the generation of a fatigue curve for a specific stress or strain ratio. First, the general shape of the curve should be determined. Nonreplicated fatigue tests completed at not more than four to six maximum stress levels are usually sufficient to define the basic shape of the curve above the fatigue limit. After the shape of the curve is found from test results, or estimated from fatigue data on similar materials, then the mean curve should be verified through carefully planned replicate fatigue tests.

If the lower maximum stress levels or strain ranges chosen result in nonfailures or runouts\*, do not repeat these stress levels while defining the general shape of the fatigue curve. Simply focus on relatively evenly spaced stress or strain levels that generally provide fatigue failures.

In performing these exploratory fatigue tests, obtaining the test specimens from a random sample that adequately represents the material is important. In that context, specimens should be taken from several different lots if possible. Particular care should also be given to minimizing nuisance variables such as test machine effects, frequency effects, surface finish irregularities, residual stress effects, or environmental

---

\* A specific fatigue cycle limit should be chosen as a runout point, and that limit should be used for all further tests on that material, regardless of the stress or strain ratio. For materials that typically display constant amplitude fatigue limits (many steels do), a runout limit as low as  $3 \times 10^6$  cycles may be satisfactory. Normally, however, a runout limit of  $10^7$  cycles is preferred, especially for materials that typically do not show a definite fatigue limit (many aluminums do not) and for experiments conducted at reasonably high cyclic frequencies ( $10^7$  cycles is accumulated in less than 4 days of continuous cycling at 30 Hz). Fatigue tests for cast metals are traditionally continued to  $2 \times 10^7$  cycles as a fatigue limit.

**MIL-HDBK-5H**  
**1 December 1998**

variations. Unfortunately, variables such as specimen fabrication can influence fatigue results to such an extent that the effect being studied is eclipsed. Composition, thermal-mechanical processing and the origin of the material should be well documented. The same type documentation should apply to the fabrication of the specimens. ASTM E 606 provides an example of a machining procedure in Appendix X3 [Reference 9.3.4.1(a)]. It is frequently referenced in machining specifications.

In addition, fabricating fatigue specimens also involves many special considerations. For example, simulating a component fabrication process for making the specimens may be desired, e.g., heat treating before or after machining. The specimens may be ground or lathe turned. A mechanical polish or electro-polish may be employed. Special processing such as shot peening, stress relieving, plating or coating may be used. All of these procedures (including their sequence) must be documented.

The formation of surface residual stresses should be recognized as one of the most influential effects of machining, although it is frequently overlooked. Any mechanical removal of material from the specimen can produce residual stresses on the surface. Even when special care is taken to remove material very gradually, residual stresses (either surface or profile) may approach the yield point of the material. Under certain conditions these stresses can have a dramatic effect on the fatigue life of the specimen. Whenever the test environment and strain range are such that these stresses are not dissipated, they can alter the stress on the surface of the specimen. Crack initiation and propagation life will therefore be affected. Machining processes for producing fatigue specimens, therefore, should be evaluated not only on the basis of machining tolerances and surface finish, but also on the magnitude, consistency, and profile of these residual stresses.

Fatigue tests that exhibit little inelastic strain are especially influenced by the procedures employed in specimen preparation. Test results in these intermediate- and long-life regimes can be very confusing and misleading if the residual stresses are not considered. These stresses should at least be measured and documented and, in some cases, it may be desirable to stress relieve or electro-polish the specimens.

After the general shape of the fatigue curve has been identified (as shown in Figure 9.3.4.5 for three different stress and strain ratios), replicate tests at specific stress or strain levels may be performed to improve the statistical definition of the fatigue curve. Normally, replications at three levels are sufficient, if no fatigue limit is anticipated (or no attempt is to be made to define one).

The replicated stress or strain levels should be selected to represent initial estimates (based on the exploratory experiments) that would be expected to provide average fatigue lives at the extremes of the life interval of interest and at an intermediate fatigue life. For example, if load-control tests are to be performed and the fatigue performance between  $10^4$  and  $10^6$  cycles to failure is of concern, select three maximum stress levels for each stress ratio that appear likely to provide average fatigue lives of about  $10^4$ ,  $10^5$ , and  $10^6$  cycles to failure, respectively.

Figure 9.3.4.5 illustrates this maximum stress and strain level selection process. As this figure suggests, specifying the levels with great precision is not necessary (or justified). The use of levels that have been established from exploratory testing may be appropriate. Use the same levels as those used on one of the exploratory tests if it results in a fatigue life near one of the life ranges of interest. The order of fatigue testing at these stress levels should be randomized for each series of replicates.



MIL-HDBK-5H  
1 December 1998





Figure 9.3.4.5. Schematic fatigue data displays (showing the initial exploratory tests as symbols and the strain levels subsequently chosen for replicate fatigue testing as bars; the length of the bars denoting observed data variability).



**MIL-HDBK-5H**  
**1 December 1998**

If further definition of the fatigue curve is desired in the long-life regime, replication at a fourth maximum stress level may be helpful\*. To select this stress level, examine the number of runouts obtained at the lowest of the three replicated stress levels. If the number of runouts is less than 50 percent at the lowest stress level, select another, somewhat lower stress level for replication (5 to 10 percent is suggested). Alternatively, if the number of runouts at the lowest of the three replicated stress levels is above 50 percent, select a fourth replicated stress level that is somewhat higher (again, 5 to 10 percent is suggested). Using such an approach, defining a fatigue limit stress at the selected runout level in clearly defined statistical terms will, in many cases, be possible.

The amount of replication required at each maximum stress level or strain range is the key remaining issue. Reference 9.3.4.5(a) recommends a minimum of 50 to 75 percent replication for design allowables data. This translates into two to four specimens at each stress or strain level. If the data displays minor variability, two specimens per level may be sufficient. If the data are highly variable, even four specimens per level may still not clearly define a statistically significant mean fatigue curve (see Section 9.3.4.12).

Adding the number of specimens recommended for curve shape definition and the number recommended for replication, the normal minimum number of fatigue tests per curve ranges from 8 to 16. Therefore, the development of fatigue curves for three stress or strain ratios for a fatigue data display in MIL-HDBK-5 might be based on 24 to 48 specimens. If additional stress or strain ratios are to be considered, the number of recommended tests would expand further, although fewer tests may be employed at these R-ratios.

More fatigue specimens are recommended for test in developing a fatigue data display for use in MIL-HDBK-5 than are actually required by current minimum data standards (see Section 9.3.4.4). This discrepancy exists primarily because the satisfaction of current minimum data standards does not ensure a statistically significant set of fatigue curves. The chance of producing a significant set of fatigue curves is much greater if the recommended fatigue test planning procedure is used and the designed test matrix is carefully completed.

Strain control fatigue data for a particular material must be accompanied by sufficient information to allow the construction of a cyclic stress-strain curve. Normally, such a curve can be constructed from stress-strain pairs recorded from stable hysteresis loops. Pairs obtained from a number of different tests covering a wide range of plastic strain ranges will allow construction of a complete cyclic stress-strain curve. Results from replicated incremental step tests may also be used to construct cyclic stress-strain tests [Reference 9.3.4.5(d)].

**9.3.4.6 Data Collection** — If a set of strain- or load-control data for a material of interest meet the minimum requirements, the data should be processed for analysis. Load-control data reports should clearly specify the net section stresses, stress ratios, and associated cycles to failure. Strain-control data reports should clearly specify the strain levels used, the stable stress response values, and the associated cycles to initiation and/or failure, along with a clear and concise definition of the failure criterion. Acceptable definitions of failure in a strain-control fatigue test report include:

- (1) Total specimen separation
- (2) Decrease of 50 percent in the maximum or stabilized tensile load value.

---

\* It is assumed here that long-life fatigue tests will be run in load control or started in strain control and switched to load control as discussed earlier.

**MIL-HDBK-5H**  
**1 December 1998**

Acceptable definitions of crack initiation in a strain-control fatigue test report include:

- (1) First significant deviation from the stabilized load range or a stabilized rate-of-change of the load range. Detection reliability is dependent upon the sensitivity of the monitoring equipment and consequently values as small as 1 to 5 percent are used in some cases, while values as great as 10 to 20 percent are used in other cases.
- (2) Verifiable results from a calibrated nondestructive inspection device, such as an electrical potential drop system.

The definition of crack initiation or failure used in a particular study must be clearly and quantitatively documented. Correlative information that is important for load or strain-control test data includes detailed specimen dimensions, fabrication procedures (and their sequence), surface finish, product form, environment, frequency, waveform, surface residual stresses, and temperature. Other useful information includes average material tensile properties, product dimensions, and manufacturer.

All fatigue data that are not listed as invalid by the author of the test report will be prepared for analysis, except for specimens tested at a maximum stress level greater than the average tensile ultimate strength of the material. The identity of different sources should be retained to determine whether combinations of data are appropriate. If all conditions from the different sources are virtually identical, the data should be analyzed together. Data should be identified as invalid if efforts in specimen preparation or testing efforts are discovered.

Runouts should be designated differently from failure data, since runouts are given special consideration in the regression analysis used to define mean fatigue curves. Runouts are generally defined as tests that have accumulated some predetermined number of cycles and have been subsequently stopped to reduce test time. Tests which have been stopped due to distinct problems encountered during testing are termed interrupted tests. Typical problems include power failures, temperature deviations, and load spikes. Interrupted tests are generally valid up until time at which the problem occurred. In this context, interrupted tests are treated the same as runouts in determining the mean fatigue-life trends of a data collection. However, if the interruption occurs long before expected failure of the specimen, the information contributed by the interrupted test is minimal, and the data point should be discarded.

Data from specimens which exhibit failures outside of the gage section may, in certain circumstances, be included in the analysis and treated as interrupted tests. Failures occurring just outside the gage section are essentially normal failures and should be included for analysis. In strain-control tests, however, the crack initiation is not sensed by the extensometer. Failures at threads, shoulders, or button heads may be indicative of a problem with the specimen design or test procedure.

Strain-control fatigue data must be accompanied by sufficient information to construct a cyclic stress-strain curve. The cyclic stress-strain curve may be established based on incremental stress-strain results or multiple specimen data for which stable stress amplitudes are defined for the complete range of strain ranges. The method used to define the cyclic stress-strain curve must be recorded so that it can be included in the correlative information along with the strain-life fatigue data displays.

**9.3.4.7 Analysis Procedures** — Once a collection of data is reviewed (see Section 9.3.4.6) and compiled for the material of interest, analysis of that data may begin. An outline of the analysis procedure that is normally followed is given in Figure 9.3.4.7. Each of the elements in the flow chart are discussed in the following sections.

MIL-HDBK-5H  
1 December 1998




Figure 9.3.4.7. Flow chart of general fatigue analysis procedure.

**MIL-HDBK-5H**  
**1 December 1998**

The same basic analysis procedure is used for strain- and load-control data except these data types are normally analyzed separately even if they represent the same material and product form. The only case where load- and strain-control data can be combined is the situation where some specimens have been switched from strain- to load-control testing. In this case, the load- and strain-control data may be analyzed on an equivalent strain basis. In all other cases, load-control data should be analyzed on an equivalent stress basis. Load-control data generated at different stress concentrations should always be analyzed separately.

**9.3.4.8 Fatigue Life Models** — To clarify the fatigue data trends for a specific stress or strain ratio, a linear regression model can be applied as follows:

$$\log(N_i \text{ or } N_f) = A_1 + A_2 \log(S_{\max} \text{ or } \Delta\epsilon). \quad [9.3.4.8(a)]$$

Note that fatigue life is specified as the dependent variable. The alternative approach, using stress or strain as the dependent variable, is sometimes used, but this procedure will not be employed in developing mean fatigue curves in MIL-HDBK-5. The use of fatigue life or, more specifically, logarithm (base 10) of fatigue life as the dependent variable will be used since stress or strain is the controlled parameter in a fatigue experiment, and the resultant fatigue life is a random variable.

If Equation 9.3.4.8(a) does not adequately describe long-life data trends, a nonlinear model (or a more complicated linear model) may be warranted. For example, long-life, load-control data might be modeled by the nonlinear expression

$$\log N_j = A_1 + A_2(S_{\max} - A_3) \quad [9.3.4.8(a)]$$

or by the more complicated equation [Reference 9.3.4.8]

$$\log N_f = A_1 + A_2 \log S_{\max} + A_3 \sqrt{\log S_{\max} + A_4} \quad [9.3.4.8(c)]$$

These more complex forms should only be employed in instances where they are warranted based on a distinct fatigue limit at long lives and when the simpler linear model was inadequate.

Standard least squares regression analysis and the procedure for detecting outliers in Section 9.3.4.11 require that the variance be relatively constant at all fatigue life values. Traditionally, the logarithm of fatigue life is approximated by a normal distribution. However, the variability or scatter of fatigue life is generally not constant, but increases with increasing fatigue life. To ensure the reliable use of the outlier detection procedure, a weighting scheme designed to produce a more uniform distribution of residuals is suggested in Section 9.3.4.10.

**9.3.4.9 Evaluation of Mean Stress and Strain Effects**—Commonly, load-controlled fatigue data generated over a range of stress ratios can be represented by the following equivalent stress-fatigue life formulation:

$$\log N_f = A_1 + A_2 \log (S_{eq} - A_4) \quad [9.3.4.9(a)]$$

where

$$S_{eq} = (\Delta S)^{A_3} (S_{\max})^{1-A_3}$$

$$S_{eq} = S_{\max} (1 - R)^{A_3}$$

**MIL-HDBK-5H**  
**1 December 1998**

The equivalent stress model (and the related equivalent strain model) are derived from Reference 9.3.4.9(a).

Equation 9.3.4.9(a) is nonlinear in its general form and must, therefore, normally be optimized through use of a nonlinear regression package. However, the above equation can be solved through a linear analysis, if  $A_3$  and  $A_4$  are optimized through an iterative solution. The parameter  $A_3$  normally lies in the range of 0.30 to 0.70, while  $A_4$  represents, in essence, the fatigue limit stress. In cases where the optimum value of  $A_4$  is negative or insignificant, it should be omitted. Unnotched data, especially aluminum alloy data, can frequently be represented without using the nonlinear  $A_4$  term. Parameter optimization is discussed more thoroughly in Section 9.3.4.10.

If  $A_4$  is zero or set equal to zero, Equation 9.3.4.9(a) becomes linear in  $\log S_{\max}$  and  $\log (1-R)$ , and it can be written as follows:

$$\log N_f = A_1 + A_2 \log S_{\max} + B \log (1-R) \quad [9.3.4.9(b)]$$

where  $B = A_2 A_3$ . Thus, if  $A_4$  is zero, then

$$A_3 = B/A_2$$

Strain-controlled fatigue data generated over a range of strain ratios often can be consolidated by the following equivalent strain formulation:

$$\log N_f = A_1 + A_2 \log (\epsilon_{eq} - A_4) \quad [9.3.4.9(c)]$$

where

$$\epsilon_{eq} = (\Delta\epsilon)^{A_3} (S_{\max}/E)^{1-A_3} .$$

Note that Equation 9.3.4.9(c) is very similar in form to Equation 9.3.4.9(a). It is important to note, however, that the maximum stress value used in Equation 9.3.4.9(c) is not a controlled quantity. It is a measured quantity and its magnitude depends primarily on the amount of cyclic softening or hardening that occurs in combination with mean stress relaxation. Although  $S_{\max}$  can be predicted with reasonable accuracy if the cyclic response of the material is well established, using the stable measured values of  $S_{\max}$ , when analyzing strain-control data for presentation in MIL-HDBK-5, is preferred.

The equivalent stress and strain approaches are very useful for computing mean fatigue life estimates for conditions intermediate to those for which the test data have been generated. Caution should be used, however, in making life predictions for stress/strain conditions beyond the range of those represented in the data base. Also, when only two stress/strain ratios are used in the equivalence formulation, fatigue life estimates at conditions other than those two ratios (either intermediate or beyond) may be unreliable.

If the basic formulations just described do not realistically represent the data, alternative equivalent stress or strain formulations should be considered. Two formulations [References 9.3.4.9(a) and (b)], in particular, may apply in these specific instances where equivalent stress is defined as:

$$S_{eq} = S_a + A_3 S_m \quad [9.3.4.9(d)]$$

or

**MIL-HDBK-5H**  
**1 December 1998**

$$S_{eq} = S_a + S_m^{A_3} \quad [9.3.4.9(e)]$$

and equivalent strain is defined as:

$$\epsilon_{eq} = \epsilon_a + A_3 S_m/E \quad [9.3.4.9(f)]$$

or

$$\epsilon_{eq} = \epsilon_a + (S_m/E)^{A_3} \quad [9.3.4.9(g)]$$

where

$S_{eq}$  = equivalent stress  
 $\epsilon_{eq}$  = equivalent strain  
 $S_a$  = alternating stress  
 $S_m$  = mean stress  
 $\epsilon_a$  = alternating strain  
 $E$  = elastic modulus (from each test result).

Other data consolidation parameters may also be used provided they do not violate other guideline requirements, and they can be proven adequate. Adequacy may be assessed by employing the procedures described in Section 9.3.4.12.

To evaluate the adequacy of one equivalent stress or strain formulation compared to another, it is also useful to construct a plot of residuals versus stress or strain identifying individual stress or strain ratios. In this way the usefulness of a given formulation for modeling stress or strain ratio effects is visually apparent.

**9.3.4.10 Estimation of Fatigue-Life Model Parameters** — The fatigue-life model parameters are estimated to obtain the best-fit S/N or  $\epsilon$ /N curve for the data. The procedure used to determine the parameters includes a statistical method for adjusting the fatigue model for the nonconstant variance commonly observed in long-life fatigue data. The motivation for this adjustment is the fact that constant variance is an inherent assumption in least squares regression analysis. To estimate the parameters in Equation 9.3.4.9(a) or Equation 9.3.4.9(c) and adjust the model to incorporate nonuniform variance, the following six-step procedure is performed.


**Step 1 - Initial Parameter Estimates.** If  $A_4$  is assumed to be zero, then a linear least squares regression analysis is performed to obtain the initial parameter estimates for  $A_1$ ,  $A_2$ , and  $A_3$ . If  $A_4$  is to be estimated from the data, a nonlinear least squares regression analysis is performed to obtain the initial parameter estimates for  $A_1$ ,  $A_2$ ,  $A_3$ , and  $A_4$ . Runout observations above the minimum equivalent stress (strain) at which a failure occurred should be included in the calculation of the initial parameter estimates and residuals.

To facilitate convergence of the nonlinear least squares fit when  $A_4$  is to be estimated from the data, the following procedure may be used to obtain starting values. Set  $A_3$  equal to 0.5 and calculate equivalent stress (strain) values for each observation. Set  $A_4$  equal to one-half the smallest equivalent stress (strain) not

**MIL-HDBK-5H**  
**1 December 1998**

associated with a runout. Using these values of  $A_3$  and  $A_4$  as constants, obtain least squares estimates of  $A_1$  and  $A_2$  using a linear regression routine.

Step 2 - Fitting the Variability Model. The magnitude of the residuals from these fatigue-life models typically increases with decreasing stress or strain as illustrated in Figure 9.3.4.10(a). The residuals plotted are the observed  $\log(\text{life})$  values minus the predicted  $\log(\text{life})$  values.



**Figure 9.3.4.10(a). Example plot showing increasing magnitude of residuals with decreasing stress/strain levels.**

To evaluate the fatigue-life model for nonuniform variance, it is useful to construct a model to estimate the standard deviation of  $\log(\text{life})$  as a function of equivalent stress (strain). If there is nonuniform variance, such a model can then be used to perform a weighted regression to estimate the fatigue life model parameters where the weight for each observations inversely proportional to its estimated variance.

The suggested standard deviation model is

$$\frac{|R|}{\sqrt{2/\pi}} = \sigma_o + \sigma_1 \left[ \frac{1}{S_{eq}} \right] = g(S_{eq}) \quad [9.3.4.10(a)]$$

$$\frac{|R|}{\sqrt{2/\pi}} = \sigma_o + \sigma_1 \left[ \frac{1}{\epsilon_{eq}} \right] = h(\epsilon_{eq})$$


where  $R$  (observed  $\log(\text{life})$  minus predicted  $\log(\text{life})$ ) represents the residuals from the fatigue life model fitted in Step 1. This model assumes that the standard deviation of  $\log(\text{life})$  is a linear function of the

**MIL-HDBK-5H****1 December 1998**

reciprocal of equivalent stress (strain). The absolute values of the residuals are divided by  $\sqrt{2/\pi}$  so that  $g(S_{eq})$  or  $h(\epsilon_{eq})$  is an estimate of the standard deviation of  $\log(\text{life})$ .

The intercept,  $\sigma_0$ , and the slope,  $\sigma_1$ , are first estimated by ordinary least squares. If the least squares estimate of  $\sigma_0$  is negative,  $\sigma_0$  should be set to zero and  $\sigma_1$  should be estimated by performing a least squares regression through the origin (no intercept term). A 90 percent confidence interval for  $\sigma_1$  should also be obtained. If the lower bound of the confidence interval for  $\sigma_1$  is positive, there is evidence of nonuniform variance and one should proceed to Step 3A. If the confidence interval for  $\sigma_1$  contains zero, there is no evidence of nonuniform variance and one should proceed to Step 3B. If the upper bound of the confidence interval for  $\sigma_1$  is negative, this indicates abnormal behavior requiring further examination of the data set before proceeding with the analysis.

Figure 9.3.4.10(b) is a plot of the absolute values of the residuals from Figure 9.3.4.10(a) versus the reciprocal of equivalent stress. The slope and vertical intercept of the least squares line displayed in this plot are the estimated parameters  $\sigma_1$  and  $\sigma_0$ .



**Figure 9.3.4.10(b). Example plot showing the magnitude of the residuals versus the inverse of equivalent stress/strain levels.**

Step 3A - Fitting the Weighted Fatigue Model. Adjust the fatigue model for nonconstant variance by dividing each term in the model by  $g(S_{eq})$  or  $h(\epsilon_{eq})$ , the estimated standard deviation of the dependent regression variable. If the four-parameter fatigue model is being used, the adjusted model becomes



**MIL-HDBK-5H**  
**1 December 1998**

$$\left[ \frac{\log(N)}{g(S_{eq})} \right] = A_1 \left[ \frac{1}{g(S_{eq})} \right] + A_2 \left[ \frac{\log(S_{eq} - A_4)}{g(S_{eq})} \right]$$

or

[9.3.4.10(b)]

$$\left[ \frac{\log(N)}{g(\epsilon_{eq})} \right] = A_1 \left[ \frac{1}{g(\epsilon_{eq})} \right] + A_2 \left[ \frac{\log(\epsilon_{eq} - A_4)}{g(\epsilon_{eq})} \right]$$

where  $S_{eq}$  and  $\epsilon_{eq}$  are defined in Equations 9.3.4.9(a) and 9.3.4.9(c). Perform a nonlinear least squares regression analysis (no intercept) using the adjusted model to obtain new estimates of  $A_1$ ,  $A_2$ ,  $A_3$ , and  $A_4$ . When performing this regression, all runouts above the minimum  $S_{eq}$  or  $\epsilon_{eq}$  at which a failure occurred should be included in the analysis and treated as failures. The inclusion of runouts in this step should be determined based on equivalent stress (strain) values using the value of  $A_3$  estimated in Step 1. Assuming that the equivalent stress/strain model is valid, this qualifying stress/strain level allows the use of all runouts above stresses or strains at which failures have been observed. Below this level, there is no statistical evidence that discontinued tests would have failed. Therefore, runouts below the minimum  $S_{eq}$  or  $\epsilon_{eq}$  value at which a failure occurred are not assigned finite life values in estimating the parameters.

It should be noted that the regression analysis performed using the adjusted model [Equation 9.3.4.10(b)] is equivalent to performing a weighted least squares regression analysis using the original fatigue life model [Equation 9.3.4.9(c)] and weights equal to  $1/g^2(S_{eq})$  or  $1/g^2(\epsilon_{eq})$ . Also, it may be desirable in certain situations to fit alternative standard deviation models to the residuals from Step 1. In this case, simply redefine  $g(S_{eq})$  or  $g(\epsilon_{eq})$  to be equal to the desired model and follow Steps 1 through 3 above. Upon completion of Step 3A, proceed to Step 4.

**Step 3B - Fitting the Unweighted Fatigue Model.** Using the initial estimate of  $A_3$  obtained in Step 1, calculate equivalent stress (strain) values for all observations including runouts. All runouts above the minimum equivalent stress (strain) at which a failure occurred should be included in the analysis and treated as failures. (See Step 3A for an explanation of this rationale.) Using the same regression techniques employed in Step 1, obtain least squares estimates of the parameters  $A_1$ ,  $A_2$ ,  $A_3$ , and  $A_4$ .

**Step 4 - Testing the Significance of Model Parameters.** Obtain a 90 percent confidence interval for  $A_4$ . If the lower bound of the confidence interval is negative, there is no evidence that  $A_4$  is different from zero. In this case, assume  $A_4$  is equal to zero and repeat Step 3A or 3B, eliminating  $A_4$  from the model.

Next, obtain a 90 percent confidence interval for  $A_2$ . If the upper bound of the confidence interval is negative, this indicates that the relationship between  $\log(\text{life})$  and equivalent stress (strain) is significant. If the upper bound of the confidence interval is positive, there is no evidence of a significant relationship between  $\log(\text{life})$  and equivalent stress (strain) and the data set should be examined further before proceeding with the analysis.

**Step 5 - Re-estimating  $A_1$  and  $A_2$ .** If a weighted least squares analysis was performed in Step 3A,  $A_1$  and  $A_2$  should be re-estimated to include the effect of the new value of  $A_3$  on the calculation of weights and the inclusion of runouts. First, recompute the weights  $g(S_{eq})$  or  $g(\epsilon_{eq})$  using the value of  $A_3$  obtained in Step 3A. Then perform a linear regression (no intercept) to obtain updated estimates of  $A_1$  and  $A_2$  in Equation 9.3.4.10(b) treating  $A_3$  as a constant. The inclusion of runouts in this linear regression should be determined based on equivalent stress (strain) values using the value of  $A_3$  obtained in Step 3A.

**MIL-HDBK-5H**  
**1 December 1998**

Step 6 - Estimating the Standard Deviation and Calculating Standardized Residuals. The method for estimating the “standard deviation of log(life)” (SD) depends on whether there is evidence of nonuniform variance in the fatigue life data. If an unweighted regression was performed in Step 3B to obtain the model parameters, SD should be set equal to the root mean square error (RMSE) associated with the fitted and unweighted fatigue life model. In this case, SD may be calculated as

$$SD = RMSE = \sqrt{\sum_{i=1}^n R_i^2 / (n-k)} \quad [9.3.4.10(c)]$$

where k is the number of parameters estimated in Step 3, and

$$R_i = \log N_i - \log \hat{N}_i \quad [9.3.4.10(d)]$$

where  $R_i$  is the residual,  $\log N_i$  is the logarithm of observed number of cycles, and  $\log \hat{N}_i$  is the logarithm of predicted number of cycles associated with the  $i$ th observation.

If a weighted regression was performed in Step 3A to obtain the model parameters, SD should be reported as linear function of the reciprocal of equivalent stress (strain). This function should be obtained by multiplying the fitted standard deviation model  $g(S_{eq})$  or  $g(\epsilon_{eq})$  from Step 2 by the root mean square error (RMSE) associated with the fitted and weighted fatigue life model to obtain an updated standard deviation model. In this case, SD may be calculated as

$$SD = RMSE * (\sigma_0 + \sigma_1 / S_{eq})$$

or

$$SD = RMSE * (\sigma_0 + \sigma_1 / \epsilon_{eq})$$

where

$$RMSE = \sqrt{\sum_{i=1}^n WR_i^2 / (n - k)} \quad [9.3.4.10(f)]$$

k is the number of parameters estimated in Step 3, and

$$WR_i = \frac{\log N_i - \log \hat{N}_i}{g(S_{eq,i} \text{ or } \epsilon_{eq,i})} \quad [9.3.4.10(g)]$$

**MIL-HDBK-5H**  
**1 December 1998**


with  $WR_i$  denoting the weighted residual and  $S_{eq,i}(\epsilon_{eq,i})$  the equivalent stress (strain) associated with the  $i$ th observation.

As a final step associated with the estimation of fatigue life model parameters, standardized residuals should be calculated for use in the judging the appropriateness of the fitted model. Standardized residuals are calculated as

$$SR_i = R_i/SD \quad [9.3.4.10(h)]$$

where the form of the residual  $R_i$  is given in Equation 9.3.4.10(d) and the estimated standard deviation  $SD$  is given by either Equation 9.3.4.10(c) or Equation 9.3.4.10(e).

Figure 9.3.4.10(c) is a plot of the standardized residuals for the same data plotted in Figure 9.3.4.10(b) but based on a standard deviation model to correct the nonuniform variance. Note that the pattern of nonconstant variance has been eliminated.



**Figure 9.3.4.10(c). Example plot showing constant variance of standardized residuals.**

Note - When performing any of the regression analyses described above to estimate the parameters  $A_1$ ,  $A_2$ ,  $A_3$ , and  $A_4$ , the estimate of  $A_4$  should be restricted to be greater than or equal to zero. Some regression programs allow such restrictions as an option. If such an option is not available and if the estimate of  $A_4$  is negative, set  $A_4$  equal to zero and refit the model treating  $A_4$  as a constant. Also note that the parameter estimates obtained from the regression analysis of Step 3A or 3B need not

**MIL-HDBK-5H**  
**1 December 1998**

necessarily be reported as the final parameter estimates. If the data set includes runout observations, final estimates of the  $A_1$  and  $A_2$  parameters may be calculated using the maximum likelihood techniques presented in Section 9.3.4.14, provided that software for performing this procedure is available.

**9.3.4.11 Treatment of Outliers** — An outlying observation (or outlier) is one that appears to deviate markedly from other observations in the sample in which it occurs. Outliers may essentially be classified into two groups:

- (1) An extreme value of the random variable inherent in the data (in this case fatigue life). If this is true, the value should be retained in future analyses.
- (2) An unusual result caused by a gross deviation in material or prescribed experimental procedure or an error in calculating or recording any experimental data.

An outlier of the second type is sometimes correctable by a review of the test sample and/or test records, which may provide sufficient evidence for rejection of the observation. An outlying value from a failure that occurred in the fillet of an unnotched fatigue test sample is an example of a potentially rejectable result based on physical evidence alone. The more difficult case is one where an observation is an obvious outlier and no physical reasons can be identified to justify its exclusion.

Assuming uniform variance in the standardized residuals over the complete range in equivalent stress or strain, the problem of identifying certain observations as potential outliers should be addressed as follows. Calculate the studentized residuals,

$$T_i = \frac{SR_i}{(1 - h_i)^{1/2}} \left[ \frac{RMSE}{RMSE(i)} \right]$$

for  $i = 1, \dots, n$  where  $SR_i$  is the standardized residual from Equation 9.3.4.10(h),  $RMSE$  is the root mean square error based on the entire sample as calculated in either Equation 9.3.4.10(c) or Equation 9.3.4.10(f), and  $RMSE(i)$  is the root mean square error based on the sample which excludes the  $i$ th observation as calculated by either Equation 9.3.4.10(c) or Equation 9.3.4.10(f).

The value  $h_i$  is calculated using the formula

$$h_i = \frac{X_{1i}^2 \left( \sum X_{2j}^2 \right) - 2 X_{1i} X_{2i} \left( \sum X_{1j} X_{2j} \right) + X_{2i}^2 \left( \sum X_{1j}^2 \right)}{\left( \sum X_{1j}^2 \right) \left( \sum X_{2j}^2 \right) - \left( \sum X_{1j} X_{2j} \right)^2}$$

where  $X_{1i}$  is the value of  $1/SD$  for the  $i$ th specimen,  $X_{2i}$  is the value of  $\log(S_{eq}-A_4)/SD$  for the  $i$ th specimen and all summations are over  $j = 1, \dots, n$ . Note that

$$RMSE^2(i) = \frac{(n - k)RMSE^2 - SR_i^2/(1 - h_i)}{(n - k - 1)}$$

**MIL-HDBK-5H**  
**1 December 1998**

where RMSE is the root mean square error based on the entire sample as calculated in either Equation 9.3.4.10(c) or Equation 9.3.4.10(f) and  $k$  is the number of parameters estimated in Step 3 of Section 9.3.4.10.

It can be shown that each  $T_i$  has a central  $t$  distribution with  $n-k-1$  degrees of freedom. Applying the Bonferroni inequality [Reference 9.3.4.11] to obtain a conservative critical value leads to the following outlier test. Calculate the maximum absolute studentized residual

$$G = \max [T_i]$$

and declare the data value corresponding to  $G$  to be an outlier if

$$G > t(\alpha/2n, n - k - 1)$$

where  $t(\alpha/2n, n-k-1)$  is the upper  $\alpha/2n$  percentile point of the central  $t$  distribution with  $n-k-1$  degrees of freedom and  $\alpha$  represents the significance level of the outlier test. Under the hypothesis that no outliers are present in the data, the probability is less than  $\alpha$  that the data value corresponding to  $G$  will be falsely declared an outlier.

In applying this test to fatigue life data, a significance level of  $\alpha = 0.05$  is used and the test is first applied to the entire sample. If an outlier is detected, the outlying observation is removed from the sample and the entire analysis is repeated on the smaller sample of  $n-1$  observations starting with Step 1 of Section 9.3.4.10. (When a nonlinear least squares fit is performed in Step 1, use the current estimates for  $A_1$ ,  $A_2$ ,  $A_3$ , and  $A_4$  as starting values rather than following the starting value algorithm.) This process of removing outliers and repeating the analysis continues until no outliers are detected in the remaining sample. For strain-control data, apply the procedure described above replacing  $S_{eq}$  with  $\epsilon_{eq}$  throughout.


The data analyst may also wish to carry out the outlier test procedure using a significance level of  $\alpha = 0.20$  in order to identify additional observations that may warrant investigation. To identify even more suspect observations, a larger significance level may be used. Any data values identified by this procedure should be examined but retained in the data set unless physical evidence justifies their exclusion.

**9.3.4.12 Assessment of the Fatigue Life Model** — The fit of the fatigue model S/N curve to the data may be assessed in two ways—the adequacy of the equivalent stress/strain model and the adequacy of the fatigue life model. The equivalent stress model lack of fit test and the overall lack of fit test described below provide a reasonable assessment of the fatigue life model.

When three or more stress (strain) ratios are used, the fit of the equivalent stress (strain) model may be tested by determining the relationship between the standardized residuals from Equation 9.3.4.10(h) and stress (strain) ratio. A difference in the means of the standardized residuals at each stress (strain) ratio indicates that the equivalent stress (strain) model is inadequate. To determine whether or not there is a statistically significant difference in the means of the standardized residuals at each stress (strain) ratio, an analysis of variance should be performed on the standardized residuals using stress (strain) ratio as the treatment variable. A statistical F-test should be used to determine if the effect of stress ratio is significant at the 5 percent level [Reference 9.3.4.12]. The equivalent stress (strain) model should be considered inadequate when the effect of stress (strain) ratio is significant according to the statistical F-test.

**MIL-HDBK-5H****1 December 1998**

The plot of the standardized residuals versus stress ratio shown in Figure 9.3.4.12(a) illustrates such a relationship between the standardized residuals and stress ratio. Since there would be no such relationship if the equivalent stress model were adequate, the plot indicates that the equivalent stress model must have been misspecified in this case. In addition to the lack of fit shown by differences in standardized residual means, other types of lack of fit could exist. Therefore, it would be prudent to examine stress-life plots in addition to performing the statistical test for lack of fit of the equivalent stress model.



**Figure 9.3.4.12(a). Standardized residuals versus stress ratio.**

If the equivalent stress (strain) model is inappropriate, then a new equivalent stress (strain) model should be selected. When a suitable stress (strain) model is not available, an alternative strategy is to present the data with best fit regression lines for each stress (strain) ratio. To be acceptable, each curve must meet minimum data requirements and satisfy significance checks as discussed in Section 9.3.4.10. This approach is less desirable than the equivalent stress (strain) modeling approach because it requires the estimation of fatigue trends using a graphical technique for intermediate conditions where no data exist. It should, therefore, be used only in cases where significant fatigue data collections cannot be handled by standard procedures.

Once an equivalent stress (strain) model has been found that describes the general fatigue data trends for all stress (strain) ratios, an overall test of the fit of the fatigue model should be performed. The stress-life plot shown in Figure 9.3.4.12(b) is characteristic of an overall lack of fit. To identify such a lack of fit, the Durbin-Watson test may be used [Reference 9.3.4.12]. The statistic  $D$  should be computed according to the formula

$$D_i = \frac{\sum_{i=2}^n (SR_i - SR_{i-1})^2}{\sum_{i=1}^n SR_i^2} \quad [9.3.4.12(a)]$$

MIL-HDBK-5H  
1 December 1998




Figure 9.3.4.12(b). Stress-life plot showing lack of fit.

where  $SR_i$  is the  $i$ th standardized residual [Equation 9.3.4.10(h)] ordered by increasing values of equivalent stress(strain). If

$$D < 2 - 4.73/n^{0.555} \quad [9.3.4.12(b)]$$


conclude that there is a significant lack of fit at the 5 percent significance level. This equation was derived from the conservative critical value ( $d_c$ ) reported in Table A.6 of Montgomery and Peck [Reference 9.3.4.12]. When an overall lack of fit is determined from this test, the modeling procedure should be repeated with a more appropriate fatigue model.

**9.3.4.13 Data Set Combination** — In many cases, data from different sources, orientations, etc., may need to be combined for analysis. When data set combinations of this sort are performed, the validity of the combination should be tested with the method described below. The test is similar to that used to determine the adequacy of the equivalent stress (strain) model in the previous section.

If there is a relationship between the standardized residuals from Equation 9.3.4.10(h) and the data set from which they were obtained, such as that shown in Figure 9.3.4.13, then the data sets should normally not be combined. To determine whether or not the mean of the standardized residuals is significantly different for any of the data sets, an analysis of variance should be performed on the standardized residuals using data set as the treatment variable. The analysis of variance F-test should be used to determine if the combined data sets are significantly different at the 5 percent level.

## MIL-HDBK-5H

1 December 1998



**Figure 9.3.4.13. Standardized residual plot showing different mean trends between data sets.**

When the data sets are found to be significantly different, at least one of the data sets should normally be removed from the data set combination. In this situation, the data analyst may wish to apply a standard multiple comparison procedure to the standardized residual data to determine which standardized residual means are significantly different from the others. For a discussion of standard multiple comparison procedures, see pages 185-201 of Winer [Reference 9.3.4.13].

There may be situations where differences between data sets are found to be statistically significant, yet these differences are so small as to be unimportant from an engineering standpoint. If a particular analysis reveals such a case, exceptions may be taken, if clearly noted and explained in the fatigue data proposal.

**9.3.4.14 Treatment of Runouts** — It is difficult to incorporate information from runouts (or interrupted tests) when using the least squares criterion to fit fatigue life models to data since the failure times for these observations are not known. The runouts must be either ignored or treated as failures and neither of these alternatives adequately incorporates the information contained in the runout observations. Both of these approaches tend to produce smaller predicted lives at a given equivalent stress (strain) value than is appropriate. The treatment of runouts presented below is more appropriate but requires that two of the fatigue life model parameters be estimated by maximum likelihood techniques rather than by least squares procedures.

The maximum likelihood procedure is employed to obtain new estimates for the parameters  $A_1$  and  $A_2$  in Equation 9.3.4.9(a) or 9.3.4.9(c). For the purpose of this analysis, fatigue life (cycles to failure) is



**MIL-HDBK-5H**  
**1 December 1998**

assumed to be log normally distributed and the parameters  $A_3$  and  $A_4$  are considered to be constants which are equal to the values obtained using the procedures of Section 9.3.4.10.

The estimated values of  $A_1$  and  $A_2$  obtained previously are used as initial values. The maximum likelihood procedure then determines the values of  $A_1$  and  $A_2$  which maximize the log-likelihood function

$$L(A_1, A_2, \sigma) = \sum_{i=1}^n (1 - d_i) [\log(f(w_i)/\sigma)] + d_i \log S(w_i)$$

where

$$f(w) = \frac{1}{\sqrt{2\pi}} \exp \left[ -\frac{w^2}{2} \right]$$

is the standard normal density function,

$$S(w) = \int_w^{\infty} f(t) dt$$

is the survival function for the standard normal distribution,  $d_i$  is equal to 1 if the  $i$ th observation is a runout and zero otherwise,  $\sigma$  is a scale parameter to be estimated, and

$$w_i = \left[ \frac{\log(N)}{SD} \right] - A_1 \left[ \frac{1}{SD} \right] - A_2 \left[ \frac{\log(S_{eq} - A_4)}{SD} \right]$$

where  $N$  is the cycles to failure and  $SD$  is the standard deviation for the  $i$ th observation as calculated from Equation 9.3.4.10(c) or Equation 9.3.4.10(e).

For more information on the maximum likelihood procedure, see Reference 9.3.4.14(a). For use in standard data analysis, the maximum likelihood procedure is conveniently implemented in some statistical software packages such as SAS [see Reference 9.3.4.14(b)].

When runouts are present, the fitted curve produced by maximum likelihood will generally predict longer average cycles to failure at given equivalent stress (strain) values than the fitted curve produced by least squares. Although it would be desirable to update all of the parameters in the fatigue model with maximum likelihood, algorithms to perform maximum likelihood on nonlinear models are not readily available. For this reason, the least squares estimates of the parameters  $A_3$  and  $A_4$  must be used.

**9.3.4.15 Recognition of Time Dependent Effects** — All prior discussion has been based on the assumption that time dependent effects in the fatigue data sample of interest are negligible. When dealing with elevated temperature fatigue properties of materials (or room temperature fatigue properties in a corrosive environment, for example), this assumption may not be realistic. Analysis methods that are approved for use in MIL-HDBK-5 do not account for time-dependent effects. Therefore, every effort must be made to identify data that embody significant time-dependent effects.

**MIL-HDBK-5H**  
**1 December 1998**

There are no absolute methods presently available for sensing time-dependent effects in fatigue data; however, there are some useful approximation techniques. One of the more useful approaches applied to “suspect” data is to include time-dependent terms in the regression model. If the terms are significant, there is reason to believe that the population contains time dependent data. Subdividing the data into subsets that do not show time dependent effect may be possible. If this is not possible, the data set should either be rejected or included with a disclaimer restricting usage of the data to predict performance at other frequencies or temperatures.

One other possible indicator of time dependent effects is an abnormal equivalent stress (strain) model. If data for different stress or strain ratios do not fit the customary models (as described in Section 9.3.4.9), or abnormal optimum parameters are defined the problem may be caused by time dependent effects. In the case of the primary equivalent stress (strain) formulation equation the exponent normally is between zero and one. If the  $A_3$  exponent approaches or exceeds one, the influence of maximum stress on fatigue life is negligible. This is a very unusual result that usually indicates problems with the data sample. The problem may result from mixed sources, where the data from each source were generated at different stress (strain) ratios. Rejection of such data sets is discussed in Section 9.3.4.13. In the case of the primary equivalent stress model [Equation 9.3.4.9(a)], if the exponent ( $A_3$ ) approaches or is less than zero, it indicates the influence of maximum stress on fatigue life is “too strong”. This result implies that creep is affecting the data.

If data are available for a material at a range of different temperatures it may be possible to analyze these sets separately and make comparisons between best-fit mean trend lines for increasing temperatures. If the different mean trend lines are not consistent with the higher-temperature curves converging or diverging from the lower-temperature curves, there is probably a significant time-dependent effect in the data. The suspect data should either be excluded or included with a disclaimer as previously cited. If data are excluded for time-dependent effects, the preliminary analyses of those data should be included in the data proposal and reasons for their exclusion should be given.

**9.3.4.16 Presentation of Fatigue Analysis Results** — Separate data presentations are made for strain-controlled and load-controlled data. The only case where load-controlled data can be presented with strain-controlled data is when long-life tests have been switched from strain to load control in accordance with recommended procedures (see Section 9.3.4.5). Separate plots should be constructed for each material, notch concentration (in the case of load-controlled data), temperature, or other documented parameters that have been demonstrated to cause significant variations in fatigue behavior.

Load-controlled data presentations should consist of a family of at least three stress ratio or mean stress curves, with at least six data points per curve covering two orders of magnitude in life. (See exceptions noted in Section 9.3.4.4). The basic data should be included on each plot, with separate symbols used for each stress ratio or mean stress. Runouts should be identified with an arrow ( $\rightarrow$ ). The analytically defined mean S/N curves for each stress ratio or mean stress should also be included on each plot. These curves should not be extrapolated beyond existing data.

The fatigue curve for each stress ratio should be constructed based on the following criteria:

- (1) The curve should start at the greatest maximum stress for that specific stress ratio. Unnotched fatigue curves should not extend above the average tensile ultimate strength of the material.
- (2) The curve shall terminate at the lowest maximum stress or longest life value, whichever is most limiting for that specific stress ratio.

**MIL-HDBK-5H**  
**1 December 1998**

In addition to the stress-life plot [such as shown in Figure 9.3.4.17(h)], a tabulation of test and material conditions should also be included. At a minimum the following information should be included with an S/N plot:

- (1) Material
- (2) Product Form, Grain Direction, Thickness, Processing History, Fabrication Sequence
- (3) Test Parameters
  - Loading
  - Test Frequency
  - Temperature
  - Environment
- (4) Average Tensile Properties
- (5) Specimen Details
  - Notch Description
  - Specimen Dimensions
- (6) Surface Condition/Surface Residual Stresses/Finish
  - Finish
  - Residual Stress Data
- (7) Equivalent Stress Equation
  - Life Equation With Parameter Estimates
  - Standard Deviation of log(Life)
  - Adjusted R-Squared Statistic
  - Sample Size
- (8) Reference Numbers
- (9) No. of Heats/Lots

The following cautionary note should be included with each equivalent stress equation: [Caution: The equivalent stress model may provide unrealistic life predictions for maximum stresses and stress ratios beyond those represented above.] In calculating the “standard deviation of log(life)” and the adjusted R-squared statistic, all quantities should be computed using the final estimates of the fatigue model parameters and excluding runout observations.

The method for reporting the “standard deviation of log(life)” (SD) depends on whether there is evidence of nonuniform variance in the fatigue life data. If an unweighted fatigue model was fitted to the data, the single SD value from Equation 9.3.4.10(c) should be reported. If a weighted fatigue model was fitted to the data, SD should be reported as the linear function of the reciprocal of equivalent stress (strain) as calculated from Equation 9.3.4.10(e).

If an unweighted fatigue life model was fitted to the data, the adjusted R-squared statistic may be calculated as

$$R^2 = 1 - (\text{RMSE})^2/(\text{RTE})^2 \quad [9.3.4.16(a)]$$

where

$$\text{RTE} = \sqrt{\sum_{i=1}^n D_i^2 / (n - 1)}$$

**MIL-HDBK-5H**  
**1 December 1998**

$$D_i = \log(N_i) - \overline{\log(N)}$$

$$\overline{\log(N)} = \frac{1}{n} \sum_{i=1}^n \log(N_i)$$

and RMSE is calculated in Equation 9.3.4.10(c). If a weighted fatigue life model was fitted to the data, the adjusted R-squared statistic may be calculated as

$$R^2 = 1 - (\text{RMSE})^2 / (\text{RTE})^2 \quad [9.3.4.16(b)]$$

where

$$\text{RTE} = \sqrt{\sum_{i=1}^n \text{WD}_i^2 / (n - 1)}$$

$$\text{WD}_i = \frac{\log(N_i) - \overline{\log(N)}}{g(S_{\text{eq},i} \text{ or } \epsilon_{\text{eq},i})}$$

$$\overline{\log(N)} = \frac{\sum_{i=1}^n \log(N_i) / g(S_{\text{eq},i} \text{ or } \epsilon_{\text{eq},i})}{\sum_{i=1}^n (1/g(S_{\text{eq},i} \text{ or } \epsilon_{\text{eq},i}))}$$

and RMSE is as calculated in Equation 9.3.4.10(f).

Strain-controlled data presentations should consist of a plot of log(strain range) versus log(life) and a separate graph displaying the monotonic and cyclic stress-strain response for the material. Normally the fatigue curves should be based on at least six data points for each of three or more strain ratios, and the data should cover at least two orders of magnitude in life. As with the load-controlled data, the individual data points should be included on each plot, with separate symbols used for each strain ratio. If runouts are included in the data, they should be identified with an arrow ( $\rightarrow$ ). Data points that are based on tests that were switched from strain to load control should be identified clearly. The mean curves should extend from slightly above the greatest strain value to slightly below the least strain value.

Plotting the strain-life curves for different strain ratios is not as straightforward as plotting stress-life curves. The equivalent strain models cannot be written explicitly in terms of  $R_\epsilon$ . Therefore, other information must be used to model the data trends for the various strain ratios. The mean-stress relaxation behavior for each strain ratio must be identified and mathematically defined. In general, the onset of mean stress relaxation occurs at smaller strain amplitudes for larger strain ratios. This behavior is shown in the mean stress relaxation plot of Figure 9.3.4.16(a). The elastic response (dashed lines) predicts much higher

**MIL-HDBK-5H**  
**1 December 1998**

mean stresses than those actually observed, suggesting that mean stress relaxation has occurred. The regression line correlating the relaxed mean stresses with strain amplitude intersects the elastic response lines at larger strain amplitudes for smaller strain ratios. The elastic response line for the higher strain ratio ( $R_\epsilon = 0.6$ ) intersects the mean stress relaxation line at approximately  $\Delta\epsilon/2 = 0.0007$ . The elastic response line for the lower strain ratio ( $R_\epsilon = 0.0$ ) intersects the mean stress relaxation at approximately  $\Delta\epsilon/2 = 0.002$ . This information can be used to construct reasonable mean curves for each strain ratio for which fatigue data are available.

Considering the primary equivalent strain relation [Equation 9.3.4.9(c)]

$$\epsilon_{eq} = (\Delta\epsilon)^{A_3} (S_{max}/E)^{1 - A_3} ,$$

$S_{max}$  can be written as

$$S_{max} = S_m + S_a$$

where  $S_m$  is the relaxed mean stress and  $S_a$  is the stress amplitude found from the cyclic stress-strain curve. Given the mean stress relaxation data, both  $S_m$  and  $S_a$  can be estimated for a particular strain amplitude and strain ratio. Once  $S_{max}$  is defined, based on  $S_a$  and  $S_m$ ,  $\epsilon_{eq}$  can be calculated and a fatigue life can be determined. Through this procedure an approximate mean curve can be constructed for each strain ratio as shown in Figure 9.3.4.16(a).

If the stress amplitude ( $S_a$ ) and the mean stress relaxation pattern can reasonably be assumed to be independent of strain ratio, the following procedure may be used to construct mean curves for each strain ratio by expressing  $S_a$  as a function of the strain range and  $S_m$  as a function of strain range and strain ratio. Using the data corresponding to a strain ratio of  $R_\epsilon = -1$  only, fit the regression equation

$$\log(S_{max}) = \alpha_1 + \beta_1 \log (\Delta\epsilon/2 - S_{max}/E)$$

In some cases it may be necessary to exclude small plastic strain observations from the regression, because of the scatter (and likely unreliability) in these values. In other words, it is recommended that the cyclic stress-strain curve be defined, through at least squares regression treating stress as the dependent variable, with consideration given to a cutoff in cyclic plastic strain. A cutoff of approximately 0.0001 in plastic strain amplitude is often useful.

Assuming that stress amplitude is independent of strain ratio and provided that the estimate of the parameter  $\beta_1$  is greater than zero, a mean value for stress amplitude can be determined as a function of strain range by solving the formula

$$S_a / \bar{E} + (S_a/k)^{\frac{1}{n}} = \Delta\epsilon/2 \quad [9.3.4.16(c)]$$

for  $S_a$  where  $E$  is the average elastic modulus for all specimens tested and

$$n = \beta_1 \text{ and } k = A \log (\alpha_1) .$$

If the estimate of the parameter  $\beta_1$  is less than or equal to zero, the data set should be examined further before proceeding with the analysis.

MIL-HDBK-5H  
1 December 1998




Figure 9.3.4.16(a). Example strain-life, cycle stress-strain, and mean stress relaxation curves.

**MIL-HDBK-5H**  
**1 December 1998**

Using the data corresponding to all strain ratios other than  $R_\epsilon = -1$ , fit the regression equation

$$S_m = \alpha_2 + \beta_2 (\Delta\epsilon/2)$$

using weighed least squares to give higher weight to the observations which exhibit partial mean stress relaxation. If there is no way to directly calculate  $S_m$  from the data reported in the data set, an  $S_m$  value for use in fitting the above regression equation may be calculated by solving Equation 9.3.4.16(c) for  $S_a$  and subtracting this value from the reported  $S_{max}$  value. The weighting function

$$w = \left( |S_m|/S^* \right) \left( 1 - S_m/S^* \right)^2$$

where

$$S^* = \left[ (1 + R_\epsilon) / (1 - R_\epsilon) \right] E (\Delta\epsilon/2)$$

appears to work well in general. Assuming that the mean stress relaxation pattern is independent of strain ratio and provided that the estimate of the parameter  $\beta_2$  is less than zero, a mean value for  $S_m$  can be determined as a function of strain range and strain ratio according to the formula

$$S_m = \alpha_2 + \begin{cases} \beta_3(\Delta\epsilon/2) & (\Delta\epsilon/2) \leq \alpha_2/(\beta_3 - \beta_2) \\ \beta_2(\Delta\epsilon/2) & \alpha_2/(\beta_3 - \beta_2) \leq \Delta\epsilon/2 \leq -\alpha_2/\beta_2 \\ 0 & -\alpha_2/\beta_2 \leq (\Delta\epsilon/2) \end{cases}$$

where

$$\beta_3 = \left[ (1 + R_\epsilon) / (1 - R_\epsilon) \right] \bar{E} \quad .$$

If the estimate of parameter  $\beta_2$  is greater than or equal to zero, the data set should be examined further before proceeding with the analysis.

Mean curves determined according to the above procedures exhibit the following characteristics:

- (1) At large strain ranges, enough plastic strain is available to relax at the mean stress to zero, regardless of the strain ratio. Therefore, all strain ratios result in equivalent predicted fatigue lives.
- (2) At strain ranges corresponding to mean stresses represented by the relaxation regression line, strain ratios other than  $R_\epsilon = -1$  (zero mean stress) result in equivalent predicted fatigue lives.
- (3) At low strain ranges, the individual strain ratios assume their elastic mean stress response and diverge from each other.

The above procedure is used for plotting the strain-life curves in MIL-HDBK-5 when multiple strain ratios are involved.\* The curves generally represent the mean data trends closely.

---

\* In the general case, data generated at different strain ratios will not necessarily follow the same mean stress relaxation pattern. If different patterns for each strain ratio are evident in a particular case, it is suggested that a family of mean stress relaxation curves be constructed.

**MIL-HDBK-5H**  
**1 December 1998**

In addition to the strain-life plot, stress-strain curves and mean stress relaxation curves should be presented as shown in Figure 9.3.4.16(a). A tabulation of test and material conditions should also be included as shown in Figure 9.3.4.16(b). This information should include:

- (1) Material
- (2) Product Form, Grain Direction, Thickness, Processing History, Fabrication Sequence
- (3) Test Parameters
  - Strain Rate and/or Frequency
  - Wave Form
  - Temperature
  - Environment
- (4) Average Tensile Properties
- (5) Stress-Strain Equation
  - Monotonic (if available and appropriate) - Cyclic
- (6) Specimen Details
  - Specimen Type
  - Specimen Dimensions
  - Fabrication Sequence
- (7) Surface Condition/Surface Residual Stresses/Finish
  - Finish
  - Residual Stress Data

Correlative Information for Figure 9.3.4.16(a)

<u>Product Form:</u>	Die forging, 2-inch thick			<u>Reference:</u>	3.4.5.6.8(a)
<u>Thermal Mechanical Processing History:</u>	Annealed at 1800°F, water quench			<u>Test Parameters:</u>	Strain Rate/Frequency - 180 cpm Wave Form - Sinusoidal Temperature - 250°F Atmosphere - Air
<u>Properties:</u>	<u>TUS, ksi</u>	<u>TYS, ksi</u>	<u>E, ksi</u>	<u>Temp., °F</u>	<u>No. of Heats/Lots:</u> 2
	155-160	135-140	29,000	250	
<u>Stress-Strain Equations:</u>	Monotonic			<u>Equivalent Strain Equation:</u>	Log N <sub>f</sub> = -6.56-4.20 log (ε <sub>eq</sub> -0.0022) ε <sub>eq</sub> = (Δε) <sup>0.46</sup> (S <sub>max</sub> /E) <sup>0.54</sup> Standard Deviation of log(Life) = 0.123 Adjusted R <sup>2</sup> Statistic = 93%
	Proportional Limit = 111 ksi σ = 289 (ε <sub>p</sub> ) <sup>0.138</sup>				
	Cyclic (Companion Specimens)				
	Proportional Limit = 92 ksi (Δε/2) = 156 (Δε <sub>p</sub> /2) <sup>0.046</sup>				
	Mean Stress Relaxation				
	σ <sub>m</sub> = 114.0-24562(Δε/2)				
<u>Specimen Details:</u>	Uniform gage test section 0.250-inch diameter Polished with increasingly finer grits of emery paper to surface roughness of 10 RMS with polishing marks longitudinal.			<u>Sample Size</u> = 33	[Caution: The equivalent strain model may provide unrealistic life predictions for strain ratios and ranges beyond those represented above.]

**Figure 9.3.4.16(b). Example of correlative information and analysis results for a strain control fatigue data presentation.**



**MIL-HDBK-5H**  
**1 December 1998**

- (8) Equivalent Strain Equation
  - Life Equation with Parameter Estimates
  - Standard Deviation of log(Life)
  - Adjusted R-Squared Statistic
  - Sample Size
- (9) Reference Numbers
- (10) No. of Heats/Lots.

The following cautionary note should be included with each equivalent strain equation: [Caution: The equivalent strain model may provide unrealistic life predictions for strain ratios and ranges beyond those represented above.]

### **9.3.4.17 Example Problems —**

#### **Example 1. Strain Control**

A collection of iron alloy bar strain-controlled fatigue data at 70°F is given in Table 9.3.4.17. The required steps for the analysis of the data set are presented below. The guideline sections relating to each step in the analysis are noted.

Data Requirements (See Section 9.3.4.4) — The data set includes three strain ratios ( $R_\epsilon = -1.0, 0.0, 0.6$ ) each consisting of at least eight nonrunout data points. This satisfies the minimum recommended sample size for analysis. Two runouts ( $N_f = 10^5$  and  $10^6$  at  $R_\epsilon = -1$  are included in the data set.

Data Collection (See Section 9.3.4.6)—The specimen design for the test program is reported as uniform-gage section with a diameter of 0.20 inches. Failure is defined as complete separation. The tensile properties are presented in the correlative information. No information is available regarding the fabrication sequence for the specimens. Fabrication information is important, although in this case it is not considered sufficient cause to reject the data set for analysis. The test data at the  $R_\epsilon = -1.0$  strain ratio provide information regarding this material's cyclic stress-strain response. The cyclic stress-strain curve constructed from the data is shown in Figure 9.3.4.17(a). The monotonic curve (dashed) is estimated from the reported yield and ultimate strengths.

Evaluation of Mean Stress and Strain Effects (See Section 9.3.4.9)—The data set consists of three strain ratios and therefore an equivalent-strain formulation is used to consolidate the data on the basis of equivalent strain. Equation 9.3.4.9(c),

$$\log N_f = A_1 + A_2 \log (\epsilon_{eq} - A_4)$$

where

$$\epsilon_{eq} = (\Delta\epsilon)^{A_3} (S_{max}/E)^{1 - A_3} ,$$

is the initial model attempted for fitting the data and proves to be adequate throughout the analysis.


**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.3.4.17. Iron Alloy Strain-Controlled Fatigue Data at 70°F**

Specimen Number	$\Delta\epsilon$	$S_{\max}$ (ksi)	Cycles to Failure	Strain Ratio
1	0.600	71.1	10223	-1.00
2	0.600	77.8	10396	-1.00
3	0.600	79.2	8180	-1.00
4	0.970	117.2	605	-1.00
5	1.000	110.7	672	-1.00
6	1.000	112.8	642	-1.00
7	1.500	126.9	209	-1.00
8	1.500	127.1	340	-1.00
9	0.600	116.6	3958	0.0
10	0.600	124.2	3895	0.0
11	0.597	118.2	3919	0.0
12	0.600	128.3	4050	0.0
13	0.600	122.6	2470	0.0
14	0.400	106.4	16388	0.0
15	0.393	101.9	22896	0.0
16	0.400	102.1	15388	0.0
17	0.400	93.7	38648	0.0
18	0.400	101.2	11960	0.0
19	0.750	139.4	1099	0.60
20	0.750	137.3	1544	0.60
21	0.750	113.0	966	0.60
22	0.500	124.5	4665	0.60
23	0.500	140.6	4342	0.60
24	0.500	138.4	4240	0.60
25	0.400	158.0	7460	0.60
26	0.400	146.1	11134	0.60
27	0.400	119.1	10876	0.60
28	0.440	65.8	100000*	-1.00
29	0.330	50.0	1000000*	-1.00

\* Did not fail.

MIL-HDBK-5H  
1 December 1998



**Figure 9.3.4.17(a). Stable cyclic and monotonic stress-strain curves for iron alloy at 70°F.**


Estimation of Fatigue Life Model Parameters - Least Squares (See Section 9.3.4.10)—The initial least-squares regression results in the following fatigue-life equation parameters:

$$\begin{aligned}
 A_1 &= -4.62 \\
 A_2 &= -3.28 \\
 A_3 &= 0.610 \\
 A_4 &= 0.00198.
 \end{aligned}$$

A plot of the residuals for the fatigue model using these parameters is shown in Figure 9.3.4.17(b). These residuals do not exhibit the characteristic pattern of increasing residual magnitudes with decreasing equivalent strain levels shown in Figure 9.3.4.10(a). Rather, the variance appears to be relatively uniform. During Step 2 of the parameter estimation procedure, a negative, but insignificant, estimate of the residual model slope,  $\sigma_1$ , was obtained. This result indicates the residuals are already uniformly distributed and a constant variance model can be used. The constant variance model, in effect, does not weight the fatigue life model, so the initial parameter estimates are retained.

## MIL-HDBK-5H

1 December 1998



**Figure 9.3.4.17(b). Residual plot of fatigue-life model for initial parameter estimates.**

Treatment of Outliers (See Section 9.3.4.11) — After the data have been checked for uniformity of variance, they can be screened to determine if any outliers are present. The critical studentized residual at the 5 percent significance level for this sample of 27 observations is found to be 3.53. Any of the observations with the absolute value of the studentized residuals being greater than 3.53 would be considered outliers. The largest studentized residual from the data was 2.09; therefore, none of the observations are identified as statistically significant outliers.

Assessment of the Fatigue Life Model (See Section 9.3.4.12) — The equivalent strain formulation is marginally acceptable at the 5 percent level. The lack of fit test for the fatigue-life model results in a Durbin-Watson D statistic of 1.042. The critical value of D for a sample size of 27 is 1.241 [Equation 9.3.4.12(b)].

Since the Durbin-Watson statistic is less than the critical value, the equivalent strain model must be considered questionable in terms of its compensation for effects of strain ratio. However, no other model was found to perform better and a review of the plotted data revealed very low scatter compared to the predicted trends. Therefore, engineering judgement was used, and the proposed model was accepted.

Data Set Combination (See Section 9.3.4.13) — All of the data for this analysis came from a single source; therefore, this test is not applicable.

Treatment of Runouts (See Section 9.3.4.14) — The data set being considered includes two runout observations. The parameters  $A_1$  and  $A_2$  are therefore reestimated using the maximum likelihood regression to account for censored life values. The maximum likelihood estimates are:

**MIL-HDBK-5H****1 December 1998**

$$\begin{aligned}
 A_1 &= -5.07 \\
 A_2 &= -3.47 \\
 A_3 &= 0.610 \\
 A_4 &= 0.00198.
 \end{aligned}$$

The change in parameters  $A_1$  and  $A_2$  shift the predicted lives to greater values than the least squares parameter estimates.

Presentation of Fatigue Analysis Results (See Section 9.3.4.16) — The presentation of the strain-life curve and correlative information shown in Figure 9.3.4.17(c) is typical of a MIL-HDBK-5 strain-control fatigue data proposal. Regarding the mean stress relaxation plot, note that a single regression has been performed to represent both the  $R_\epsilon = 0.6$  and  $R_\epsilon = 0.0$  strain ratios. Although it would be expected that higher strain ratios would result in higher stabilized mean stresses, the limited amount of data precludes performing separate regressions for each strain ratio. It can be seen from the strain-life plot that using the single regression does represent the mean fatigue trends fairly well.

**Example 2. Load Control**

A large collection of 300M alloy die forging fatigue data is presented in Figure 9.3.4.17(d). The required steps for the analysis of the data set are presented below.

Data Requirements (See Section 9.3.4.4)—The data set consists of four stress ratios ( $R = -1.0, -0.33, 0.05, 0.2$ ). Each stress ratio includes at least twenty-three nonrunout observations, easily satisfying the minimum sample size requirement of six tests per stress ratio.

Data Collection (See Section 9.3.4.6) — The data shown in Figure 9.3.4.17(d) were compiled from four sources. Each source reports the results of fatigue testing programs conducted within two years of each other (1968-1970).

The failure criteria for all tests is reported as complete separation of the specimen. Those tests which did not fail are identified on the S/N plot with an arrow ( $\rightarrow$ ). These runout observations are treated differently in the regression analysis which define the mean fatigue curves (see Section 9.3.4.14).

Evaluation of Mean Stress and Strain Effects (See Section 9.3.4.9)—The collection of data consists of four stress ratios, and therefore, an equivalent-stress formation was used to consolidate the data. Equation 9.3.4.9(a),

$$\log N_f = A_1 + A_2 \log (S_{eq} - A_4)$$

where

$$S_{eq} = S_{max}(1 - R)^{A_3},$$

is the initial model attempted for fitting the data, and it proved adequate throughout the analysis.

Estimation of Fatigue Life Model Parameters — Least Squares (See Section 9.3.4.10) — The initial least-squares regression (runouts excluded) results in the following fatigue-life equation parameters:

$$\begin{aligned}
 A_1 &= 23.7 \\
 A_2 &= -8.41 \\
 A_3 &= 0.366 \\
 A_4 &= 0.0.
 \end{aligned}$$

MIL-HDBK-5H  
1 December 1998




Figure 9.3.4.17(c).  $\epsilon/N$  curve and correlative information for iron alloy at 700°F.

**MIL-HDBK-5H****1 December 1998**Correlative Information for Figure 9.3.4.17(c)Product Form: Bar, 1-inch thickReference: 3.4.5.6.8(a)Thermal Mechanical Processing History:

Not available

Test Parameters:

Strain Rate/Frequency - 180 cpm

Wave Form - Sinusoidal

Temperature - 70 °F

Properties:

TUS, ksi	TYS, ksi	E, ksi	Temp., °F
175-180	150-155	27,500	70

No. of Heats/Lots: 4Stress-Strain Equations:

Monotonic

Proportional Limit = 150 ksi

 $\sigma = 280 (\epsilon_p)^{0.12}$ 

Cyclic (Companion Specimens)

Proportional Limit = 105 ksi (est.)

 $(\Delta\sigma/2) = 196 (\Delta\epsilon_p/2)^{0.076}$ 

Mean Stress Relaxation

 $\sigma_m = 125.4 - 25666(\Delta\epsilon/2)$ Equivalent Strain Equation: $\log N = -5.07 - 3.47 \log (\epsilon_{eq} - 0.00198)$  $\epsilon_{eq} = (\Delta\epsilon)^{0.61} (S_{max}/E)^{0.39}$ 

Standard Deviation of log(Life) = 0.111

Adjusted R<sup>2</sup> Statistic = 96%Sample Size = 29

[Caution: The equivalent strain model may provide unrealistic life predictions for strain ratios and ranges beyond those represented above.]

Specimen Details:


Uniform gage test section

0.200-inch diameter

**Figure 9.3.4.17(c).  $\epsilon/N$  curve and correlative information for iron alloy at 700°F — Continued.**

## MIL-HDBK-5H

1 December 1998



**Figure 9.3.4.17(d). S/N plot of unnotched 300M die forging fatigue data, transverse orientation.**

The fatigue-limit parameter ( $A_4$ ) of zero seems somewhat inconsistent with the data shown in Figure 9.3.4.17(d). A visual examination of the S/N plot reveals a tendency for the data to asymptotically approach some limiting value. The zero fatigue limit term suggests that some problem may exist within the data collection. A plot of the residuals for the fatigue model using these parameters is shown in Figure 9.3.4.17(e).

The parameters obtained after the model is adjusted for nonconstant variance are:

$$A_1 = 23.4$$

$$A_2 = -8.38$$

$$A_3 = 0.40$$

$$A_4 = 13.5.$$

Note that a fatigue limit term of 13 ksi has now been estimated. However, a check on the significance of the  $A_4$  term revealed that it was clearly insignificant. All of the runouts in the data collection were above this equivalent stress level and, therefore, all runouts were used in the regression procedure. A plot of the residuals after the fatigue life model has been adjusted is shown in Figure 9.3.4.17(f). Note the relative shift in the magnitude of the residuals at the higher and lower  $S_{eq}$  values compared to Figure 9.3.4.17(e).

Treatment of Outliers (See Section 9.3.4.11) — None of the observations were identified as outliers. The critical studentized residual at the 5 percent significance level for this data set of 114 observations is 3.63. The largest standardized residual was 3.23, resulting from a runout observation.



MIL-HDBK-5H

1 December 1998




Figure 9.3.4.17(e). Residual plot before model has been adjusted for nonconstant variance.





Figure 9.3.4.17(f). Standardized residual plot after model has adjusted for nonconstant variance.

## MIL-HDBK-5H

1 December 1998

Assessment of the Fatigue Life Model (See Section 9.3.4.12) — The equivalent stress model is not able to consolidate the  $R = -0.33$  stress ratio with the other stress ratios. The F-test performed on the residuals of the stress ratios proves significant at the 5 percent level for  $R = -0.33$ . This indicates that the mean of the residuals for  $R = -0.33$  differs significantly from the mean of the residuals from the other ratios. The plot of stress ratios versus residuals, as shown in Figure 9.3.4.17(g), illustrates that the mean of the residuals for  $R = -0.33$  is significantly different than those for the other stress ratios. A close examination of the original S/N plot shown in Figure 9.3.4.17(d) reveals that the  $R = -0.33$  data tend to overlap the  $R = -1.0$  data: at the lower maximum stress levels (about 100 ksi), the  $R = -1.00$  data actually show longer average fatigue lives than do the  $R = -0.33$  data, when the reverse would be expected. The Durbin-Watson D statistic for determining lack of fit is 1.61, indicating a poor fit of the model to the data. The critical value of D for a sample of 114 observations [Equation 9.4.3.12(b)] is 1.66.



**Figure 9.3.4.17(g). Residual plot of stress ratios. Note the low mean value of  $R = -0.33$ .**

This incompatibility among stress ratios indicates that either a problem exists with the data or with the assumed equivalent stress model. The data sources were re-examined to possibly determine if some difference in specimen preparation or testing procedure among the sources may have caused the inconsistencies. Unfortunately, no significant differences were discovered that would provide sufficient reason to exclude the suspect  $R = -0.33$  data due to testing methods alone. The problem is confounded because all of the  $R = -0.33$  data comes from a single source which does not include other stress ratios. This precludes examining source to source variability.

In situations such as this where a data set for a single source is determined to statistically deviate from the fatigue trends exhibited by the bulk of the data, it should be evaluated for exclusion. Engineering judgement suggests that the  $R = -0.33$  data be excluded from the data collection based on the following:

- (1) Unrealistic fatigue limit
- (2) Lack of fit for fatigue life model based upon Durbin-Watson statistic
- (3) Stress ratio incompatibility.

**MIL-HDBK-5H****1 December 1998**

The modified data collection is now reanalyzed. For the sake of brevity, the details of the analysis procedure for Sections 9.3.4.4 (Data Requirements) through 9.3.4.11 (Treatment of Runouts) will be omitted. It is interesting to note, however, that the fatigue limit term ( $A_4$ ) resulting from the least squares regression with the  $R = -0.33$  data excluded is 94.2 ksi. This result more realistically represents the longer life fatigue trends compared to the previous (insignificant) estimate of 13.5 ksi. With the suspect data removed, the equivalent stress model is determined to be acceptable at the 5 percent level. The Durbin-Watson D statistic also is increased to 2.18 indicating that the model now provides an adequate fit to the data.

Dataset Combination (See Section 9.3.4.13) — With the exclusion of the source containing the  $R = -0.33$  data, the remaining data set combination is determined acceptable at the 5 percent level.

Treatment of Runouts (See Section 9.3.4.14) — The data collection includes seven runout observations. The maximum likelihood procedure has the effect of essentially shifting these runouts to the fatigue lives at which they most likely would have failed. The resulting fatigue life model parameters should reflect the slight increase in estimated fatigue life over the least squares parameters, particularly in the long life region. In general, the maximum likelihood regression will result in a higher intercept term ( $A_1$ ) and a steeper (more negative) slope ( $A_2$ ). The  $A_3$  and  $A_4$  terms are taken as constants to reduce the problem to a linear analysis.

The parameters resulting from the least squares regression are:

$$\begin{aligned} A_1 &= 14.54 \\ A_2 &= -5.04 \\ A_3 &= 0.385 \\ A_4 &= 94.2. \end{aligned}$$

The maximum likelihood parameters conform to the expected trends for  $A_1$  and  $A_2$ :


$$\begin{aligned} A_1 &= 14.79 \\ A_2 &= -5.16 \\ A_3 &= 0.385 \\ A_4 &= 94.2. \end{aligned}$$

Note the increase in  $A_1$  and the decrease (more negative slope) in  $A_2$ .

Presentation of Fatigue Analysis Results (See Section 9.3.4.16)—The stress-life curve and correlative information shown in Figure 9.3.4.17(h) is typical of a MIL-HDBK-5 load-control fatigue data proposal.

## MIL-HDBK-5H

1 December 1998



**Figure X.X.X.X.X. Best-fit S/N curves for unnotched 300M alloy forging  $F_{tu} = 280$  ksi, transverse orientation.**

Correlative Information for Figure X.X.X.X.X

Product Forms: Forged billet, uncertain size  
Die forging, 6-1/2 x 20 inches  
6-inch RCS billet  
1-1/4 x 8-inch forged bar  
all CEVM

Test Parameters:  
Loading - Axial  
Frequency - 1800 - 2000 cpm  
Temperature - RT  
Environment - Air

Properties: TUS, ksi    TYS, ksi    Temp., °F  
272-294    226-243    RT

No. of Heats/Lots: 5

Specimen Details: Unnotched  
0.200-0.250-inch diameter

Equivalent Stress Equation:  
 $\log N_f = 14.8 - 5.2 \log (S_{eq} - 94.2)$   
 $S_{eq} = S_{max}(1-R)^{0.38}$   
Standard Deviation of  $\log(\text{Life}) = 65.8 / (S_{eq})$   
Adjusted  $R^2$  Statistic = 87%

Surface Condition: Heat treat and finish grind  
to a finish of 63 RMS or  
better with light grinding  
parallel to specimen length,  
stress relieve.

Sample Size = 90

[Caution: The equivalent stress model may  
provide unrealistic life predictions for stress  
ratios and maximum stress beyond those  
represented above.]

References: 2.3.1.2.8(c), (d), (e)

**Figure 9.3.4.17(h). Example S/N curve and correlative information.**

**MIL-HDBK-5H**  
**1 December 1998**

### **9.3.5 FATIGUE-CRACK-PROPAGATION DATA**

**9.3.5.1 General** — Fatigue-crack-propagation data, recorded in the form of crack-length measurements and cycle counts ( $a_i, N_i$ ) can be presented as crack-growth curve drawn through the data points as shown in Figure 9.3.5.1(a).

Although data presented in this form indicate general trends, they are not generally useful for design purposes since a variety of stress levels, stress ratios, initial crack conditions, and environmental conditions are encountered.

It has been found convenient to model fatigue-crack-propagation damage behavior as rate process and formulate a dependent variable based on the slope of this growth curve, or an approximation to it, namely,

$$\frac{da}{dN} \approx \frac{\Delta a}{\Delta N} \quad [9.3.5.1(a)]$$

Results obtained from the theory of linear elastic fracture mechanics have suggested that rate process at the crack tip might be represented as a function of a stress-intensity factor,  $K$ , which, in general form, may be written as

$$K = S\sqrt{a} \, g(a,w) \quad , \quad [9.3.5.1(b)]$$

where  $g(a,w)$  is a geometric scaling function dependent on crack and specimen geometry, and  $S$  is nominal stress. As a result, the independent variable is usually considered as some function of  $K$ . At present, in MIL-HDBK-5 the independent variable is considered to be simply the range of the stress intensity factor,  $\Delta K$ , and data are considered to be parametric on the stress ratio,  $R$ , such that Equation 1.4.13.3(b) becomes

$$da/dN \approx \Delta a/\Delta N = g(\Delta K, R) \quad , \quad [9.3.5.1(c)]$$

where  $\Delta K = K_{\max} - K_{\min}$ . Values of maximum and minimum stress intensity factors,  $K_{\max}$  and  $K_{\min}$ , respectively, are computed with Equation 9.3.5.1(b) using respective maximum and minimum cyclic stresses.

A crack growth rate curve, as shown in Figure 9.3.5.1(b), is obtained by plotting the locus of points  $(da/dN, \Delta K)$  derived from the crack-growth curve [see Figure 9.3.5.1(a)] at selected values of crack length,  $a$ . Crack-growth-rate curves are generally plotted on log-log coordinates.

Within the general curve shape described above, systematic variations in data point locations are observed. When data from tests conducted at several different stress ratios are present, the plot of crack-growth rate versus stress-intensity-factor range will be layered into distinct bands. Layering of data points may also occur as a result of variation in such parameters as test frequency, environment, temperature, and specimen grain direction.

**9.3.5.2 Data Generation and Interpretation** — Fatigue-crack-propagation data may be generated by several types of fracture mechanics test specimens. The principal criteria for acceptance of data are twofold. One is that a valid stress-intensity-factor formulation be available for the specimen; the other is that nominal net-section stresses, as calculated by concepts of elementary strength of materials, be less than

MIL-HDBK-5H  
1 December 1998




Figure 9.3.5.1(a). Crack-growth curve.




Figure 9.3.5.1(b). Crack-growth-rate curve.


**MIL-HDBK-5H****1 December 1998**

eighty percent (80%) of the tensile yield strength of the material. ASTM E 647 provides detailed guidance on specimen designs and testing procedures.

Basic data are generated as crack lengths,  $a$ , and associated cycle counts,  $N$ . These data are interpreted as crack-growth rates determined as slopes, or average slopes, of sequential subsets of data. For MIL-HDBK-5,  $da/dN$  is calculated as the weighted average incremental slope approximation.

$$\left(\frac{da}{dN}\right) \approx \left(\frac{\Delta a}{\Delta N}\right)_{i-1} + \frac{N_i - N_{i-1}}{(N_{i+1} - N_{i-1})} \left[ \left(\frac{\Delta a}{\Delta N}\right)_i - \left(\frac{\Delta a}{\Delta N}\right)_{i-1} \right] \quad i=2, \dots, n-1 \quad [(9.3.5.2)]$$

from the measured crack-growth data as illustrated in Figure 9.3.5.2. However, alternative methods, such as polynomial fitting of the  $a$  versus  $N$  curve, are acceptable for computation of  $da/dN$  values. By this indexing and calculating procedure “ $n$ ” measurements provide “ $n-2$ ” slope or rate values at all but first and last measurement points. The directly associated stress-intensity factor for each slope computation is computed in accordance with Equation 9.3.5.1(b).



**Figure 9.3.5.2. Analytical definition of crack-growth rate calculation.**

**9.3.5.3 Data Requirements** — In order to establish a positive trend in rate behavior, it is recommended that rate data be generated over a range of at least two orders of magnitude. In general, this will be associated with a domain of stress-intensity-factor range from one half to a full order of magnitude. Good experimental techniques coupled with this data-range criterion should provide a concise and consistent data display for linear or other analysis.

**MIL-HDBK-5H****1 December 1998**

When planning experimental programs to achieve the best, most complete derivation of fatigue-crack-propagation data, the range of  $\Delta K$  over which tests are conducted should include those which will provide crack-growth rates as low as  $10^{-8}$  inches/cycle. Furthermore, if possible, multiple heats of material should be included. Ideally, to properly document the effects of stress ratio, FCP data should also be generated over a range of R ratios (0.1, 0.4, and 0.7 are typically good values). If data representing negative R ratios are available, they should also be included.

**9.3.5.4 Reporting** — Reporting of basic crack-growth data shall be as complete as possible. In addition to reporting cyclic loading conditions, such as maximum cyclic load and/or stress levels, stress ratio, test frequency, and specimen dimensions, it is particularly important to identify environmental conditions associated with the tests. The number of specimens and number of respective heats should also be identified. Table 9.3.5.4 serves as an example of the type of information which should be available (or at least is desirable) for each collection of FCP data.

**9.3.5.5 Preparation of FCP Data Proposals** — When preparing FCP data proposals for submittal to MIL-HDBK-5 Coordination Group, several steps must be taken. First, various factors potentially influencing crack-propagation rates should be documented in a FCP Data Proposal as shown in Table 9.3.5.4. Second, data for individual test conditions should be plotted and compared so that a determination can be made as to whether combinations of test conditions are appropriate. If data are available for a range of specimen thicknesses, it may be desirable to treat such data in separate plots, if FCP rate behavior is influenced by thickness. Similarly, potential effects of environment, buckling restraints, specimen width, specimen type, crack orientation, temperature, and frequency should be evaluated; and, where visible differences in FCP rate trends exist, separate plots must be developed. In some cases, it may be necessary (or helpful) to include working figures of trial combinations of FCP data so that reviewers of the data proposal can more easily see reasons for particular data combinations. If a collection of FCP data (involving one or more figures) is approved, working curves and background data sheet will be retained in MIL-HDBK-5 files and only the final data plot will be incorporated in the Handbook.

**9.3.5.6 Data Presentations** — Fatigue crack-propagation data are presented in the Handbook on double logarithmic graphical displays of crack-growth rate,  $da/dN$ ,  $\mu\text{-in./cycle}$ , versus stress-intensity factor range,  $\Delta K$ . Data points are presented along with a visually best-fit line judged to be most representative of the median behavior of those data. A sample display is presented in Figure 9.3.5.6.

Since data are not necessarily generated at predesignated stress ratio levels, stress ratio increments which are used on a given display are selected to present the most complete portrayal of available data. Data are summarized in graphical displays in the appropriate chapters of MIL-HDBK-5.

**9.3.6 CREEP AND CREEP-RUPTURE DATA**

**9.3.6.1 Introduction** — Creep is defined as time-dependent deformation of a material under an applied load. It is usually regarded as an elevated temperature phenomenon, although some materials creep at room temperature. If permitted to continue indefinitely, creep terminates in rupture. (First stage or logarithmic creep exhibited by many materials at lower temperatures is not the subject of this section.) Creep in service usually occurs under varying conditions of temperature and complex (multiaxial) stress, leading to an infinite number of stress-temperature-time combinations. Creep data for use in general design are usually obtained under conditions of constant uniform temperature and uniaxial stress. This type of data is the subject of this section.



**MIL-HDBK-5H****1 December 1998****Table 9.3.5.4. Sample Listing of Fatigue-Crack-Propagation Background Data**

Materials:	Ti-6Al-4V Titanium		
Alloy Designation or Specification:	MIL-T-9046, Type III, Composition C		
Product Form:	Plate		
Heat Treatment:	Mill Annealed		
Heat Number(s):	Ingot 295338		
Chemistry (% by weight):	C	0.02	
	N	0.010	
	Fe	0.18	
	Al	6.4	
	V	4.2	
	O	0.127	
	H	81 (PPM)	
Data Source(s):	Feddersen, C. E., and Hyler, W. S., "Fracture and Fatigue-Crack Propagation Characteristics of 1/4 Inch Mill Annealed Ti-6Al-4V Titanium Alloy Plate", Report No. G9706, Battelle (1971).		
Specimen Description:			
Type:	M(T) Panel		
Thickness:	0.250 inch		
Width:	9, 16, 32 inches		
Crack Orientation:	L-T		
Location w-r-t Product Thickness:	Through-thickness specimen		
Surface Finish:	Not Indicated		
Test Conditions:			
No. of Specimens:	9	7	6
Maximum <u>Stress</u> or Load:	5, 10, 30 ksi	5, 10, 30, 50 ksi	10, 30, 50 ksi
Stress Ratio:	0.10	0.40	0.70
Cyclic Frequency:	1-25 Hz		
Environment:	50% relative humidity		
Temperature:	68 ± 2°F		
Buckling Restraints?:	Yes		
Crack Monitoring Technique:	Optical		
Additional Comments:	<ol style="list-style-type: none"> <li>1. Frequency was varied from 1 to 25 Hz according to the magnitude of stress range, no frequency effects were noted in this environment.</li> <li>2. From 20 to 70 crack readings were made on each specimen.</li> <li>3. No panel width effects on FCP rates were evident.</li> </ol>		

MIL-HDBK-5H

1 December 1998




Figure X.X.X.X.X. Typical-crack-propagation data for 0.090-inch-thick, 7075-T6 aluminum alloy sheet with buckling restraint. [References 3.7.4.1.9(a) through (e)].

Specimen Thickness:	0.090 inch	Environment:	Lab Air
Specimen Width:	1-1/2 - 12 inches	Temperature:	RT
Specimen Type:	M(T)	Orientation:	L-T

Figure 9.3.5.6. Sample display of fatigue-crack-propagation-rate data.

**MIL-HDBK-5H****1 December 1998**

**9.3.6.2 Terminology** — The definitions presented below will be helpful in preparing creep-rupture data for inclusion in MIL-HDBK-5.

**Creep**—The time-dependent deformation of a solid resulting from force.

**Note 1**—Creep tests are usually made at constant load and temperature. For tests on metals, initial loading strain, however defined, is not included.

**Note 2**—This change in strain is sometimes referred to as creep strain.

**Primary Creep**—Creep occurring at a diminishing rate, sometimes called initial stage of creep.

**Secondary Creep**—Creep occurring at a constant rate, sometimes called second stage creep.

**Tertiary Creep**—Creep occurring at an accelerating rate, sometimes called third stage creep.

**Creep Test**—A creep test has the objective of measuring deformation and deformation rates at stresses usually well below those which would result in fracture during the time of testing.

**Creep-Rupture Test**—A creep-rupture test is one in which progressive specimen deformation and time for rupture are measured. In general, deformation is much larger than that developed during a creep test.

**Stress-Rupture Test**—A stress-rupture test is one in which time for rupture is measured, no deformation measurement being made during the test.

**Total Strain**—Total strain at any given time, including initial loading strain (which may include plastic strain in addition to elastic strain) and creep strain, but not including thermal expansion.

**Loading Strain**—Loading strain is the change in strain during the time interval from the start of loading to the instant of full-load application, sometimes called initial strain.

**Plastic Strain During Loading**—Plastic strain during loading is the portion of the strain during loading determined as the offset from the linear portion to the end of a stress-strain curve made during load application.

**Creep-Strain**—The time-dependent part of the strain resulting from stress, excluding initial loading strain and thermal expansion.

**Total Plastic Strain**—Total plastic strain at a specified time is equal to the sum of plastic strain during loading plus creep.

**Creep Stress**—The constant load divided by the original cross-sectional area of the specimen.

**Elapsed Time**—The time interval from application of the creep stress to a specified observation.


**Creep-Rupture Strength**—Stress that will cause fracture in a creep test at a given time, in a specified constant environment. Note: This is sometimes referred to as the stress-rupture strength.

**Creep Strength**—Stress that causes a given creep in a creep test at a given time in a specified constant environment.

**MIL-HDBK-5H****1 December 1998**

**Rate of Creep**—The slope of the creep-time curve at a given time determined from a Cartesian plot.

**Creep-Rupture Curve**—Results of material tests under constant load and temperature; usually plotted as strain versus time to rupture. A typical plot of creep-rupture data is shown in Figure 9.3.6.2. The strain indicated in this curve includes both initial deformation due to loading and plastic strain due to creep.



**Figure 9.3.6.2. Typical creep-rupture curve.**

**Master Creep Equation**—An equation expressing combinations of stress, temperature, time and creep, or a set of equations expressing combinations of stress, temperature and time for given levels of creep.

**Master Rupture Equation**—An equation expressing combinations of stress, temperature, and time that cause complete separation (fracture or rupture) of the specimen.

**Isothermal Lines**—Lines of uniform temperature on a creep or stress-rupture curve.

**Isostrain Lines**—Lines representing constant levels of creep.

**9.3.6.3 Data Generation** — The following paragraphs provide guidelines on testing methods and designing an experimental matrix for developing creep and creep-rupture data.

**Test Methods**—Test methods must conform to ASTM E-139. However, it is recognized that this standard allows considerable latitude in procedures such that both level and scatter results can be significantly affected.

In case of significant difference in results from different testing sources, the following should be evaluated:

Material Condition (see Section 9.3.6.4)

Specimen Dimensions and Configuration (geometry effect)

Specimen Surface Preparation (residual stresses)

**MIL-HDBK-5H**  
**1 December 1998**

Specimen Alignment (concentricity, fixturing, load train, and loading method)

Temperature Control (number, type, and location of sensors, reference junction temperature control, monitoring and recording)

Extensometers (type, fixturing, and recording)

Strain Recording (records inelastic strain on loading and creates a record to be evaluated for test stability)

Documentation (testing procedures)

General Laboratory Conditions, Personnel Qualifications, Calibration Intervals.

The submitter of a proposal should be prepared to provide documentation sufficient to permit a comparative evaluation of data. Inability to do so may cause rejection of some associated data, or the entire proposal.

*Design of Experiments*—A design of experiments approach to creep data development is highly recommended because it provides the maximum amount of useful data for the least expenditure of time and testing funds. If such an approach is not used, it is likely that several times as many test data will not serve as well in developing desired mathematical models of creep behavior as data developed through design of experiments. This section is devoted to a description of design of experiments approach which can be used to develop regression models to mathematically portray creep rupture life and creep as a function of temperature and stress.

One method for planning testing is to develop a test layout in matrix form, with temperatures in rows and expected creep lives in columns. Then, through testing, simply fill out blocks within the matrix. There should be a minimum of eight observations per isothermal line, or twenty observations per Larson-Miller or other regression model. This insures coverage of all conditions of interest. Further explanation of this method, by way of an example, is provided in Section 9.3.6.8.

*Choosing the Number of Temperatures and Life Intervals*—Before the test matrix can be formed, interval sizes must be considered, first for temperature and then life.

- (a) Temperature—A range of temperatures is usually required. For example, if experiments must range from 1000°F through 1500°F, a choice must be made whether to perform tests at six levels (1000°F, 1100°F, 1200°F, 1300°F, 1400°F, 1500°F), or maybe at three levels (1000°F, 1300°F, 1500°F). The decision can be quite complicated and based on such phenomena as:
  - (1) The relative closeness of the isothermal lines
  - (2) Parallel or divergent isothermal lines
  - (3) The precipitation of secondary phases within the life ranges of interest.

However, this selection can be greatly simplified with very little user risk. Start with the lowest temperature, and then choose the next temperature line such that at least one level of testing stress, on log stress-log life plot, will be common to both temperatures. Then, proceed to the next temperature line, etc., ensuring like stress values on adjacent temperature levels.

- (b) Life—Divide a log-life cycle into four equidistant segments. For example, between 100 hours and 1000 hours, the divisions would be approximately 180 hours, 320 hours, and 560 hours on the log-life scale. These divisions are far enough apart to insure a well-defined curve and a

**MIL-HDBK-5H****1 December 1998**

minimum overlap of data. To convert from temperature and life desired to temperature and test stress requires that there be some prior knowledge of this relationship. If there is no prior knowledge, a series of “probe” tests must be made to locate the isothermal lines on a log-log plot.

*Choosing the Number of Heats*—Batch variations in chemistry, heat treating, etc., can cause considerable variations in the mechanical properties of an alloy. This difference is referred to as heat-to-heat components, as opposed to within-heat components of variance.\* Heat-to-heat standard deviation is usually 50 to 70 percent of within-heat standard deviation. The root sum square of the two components of variance produces a measure of scatter about the regression that, when added to curve fitting error, gives the regression parameter called SEE (Standard Error of Estimate). SEE is a product of regression analysis; it is rarely determined as defined above. It is this parameter which fixes design minimums about the regression estimates of the typical or mean values.

To make a mathematically sound decision on the minimum number of heats that should be used in a given analysis, it is necessary that an estimate of heat-to-heat and within-heat variance be known. This can usually be estimated from like alloys, or calculated from development data. Simulation has shown the following minimum number of heats to be satisfactory:

- (1) When the heat-to-heat component of variance is less than 25 percent of within-heat variance, use two heats equally.
- (2) When the heat-to-heat component of variance is between 25-65 percent of within-heat variance, use three heats equally.
- (3) When the heat-to-heat component of variance is greater than 65 percent of within-heat variance, use five heats equally.

Heats should be distributed randomly and essentially equally throughout the test matrix to insure an unbiased heat distribution.

When regression models are developed from data that were not taken from an experimental model, heats are rarely chosen randomly. Therefore, unless there are large samples of data in all areas of the regression matrix, this imbalance of heat sample sizes must be accounted for as described in Section 9.3.6.5. Order of testing must also be randomized so that any time-, operator-, or machine-oriented effects are randomly distributed within the test matrix as described in Reference 9.3.6.3.

**9.3.6.4 Data Collection and Interpretation**—After a desired group of creep and/or creep-rupture data have been experimentally developed or isolated in preproduction files, it is necessary to carefully collect and interpret these data in accordance with the following guidelines:

*Data Collection*—For isostrain creep, collected data will include stress, temperature, modulus and plastic strain on initial loading, and strain-time pairs sufficient to define a curve. While strain-time pairs will be only those for the isostrain of interest, after inelastic strain on loading has been included in the reported strain, it may be that reported data may not correspond to isostrain levels. Consequently, isostrain-time pairs may be read from a smooth curve drawn through the values recorded during the test.

---

\* The within heat variance is the pooled variability of data from all heats, where the variability for each heat is calculated about its own average regression line. The heat-to-heat variance is calculated from the variability of each heat's average regression line about the overall average regression line of all heats. All heat average curves are assumed to be parallel in log life.

**MIL-HDBK-5H**  
**1 December 1998**

For rupture, collected data will include stress, temperature, time-to-rupture, percent elongation, and reduction of area. Percent elongation and reduction of area can then be used to define rupture ductility curves or equations.

*Data Interpretation*—State-of-the-art for interpreting these types of creep and rupture data requires that a certain amount of judgment be allowed. The general approach will be to optimize one of several empirical equations that best follows the trend of data, using life (or time) as the dependent variable. Independent variables will include stress and temperature for rupture and isostrain creep curves, and will also include strain for isostrain creep curves.

Rupture ductility can be an exception to the above because of complex behavior and data scatter. At least a cautionary note should be given in the introductory material on times and temperatures included in rupture data. Some materials exhibit such low elongation in certain time-temperature regions that normal, reasonable values of design creep strain cannot be achieved without risk of fracture.

Interpretation of creep and rupture data should also include variables that are reflected in background data reporting requirements (discussed in the next subsection). Depending on the information content of the data, and the type of variable, it may be desirable to develop a series of equations, or to include additional physical variables in the regression analysis. The proposal should demonstrate that these additional variables have been evaluated and appropriately treated in the analysis.

The individual interpreting the data should also take note of the following special types of data, and consider the following recommendations on their use:

*Specification Data*—Virtually all alloys used for high-temperature applications are controlled and purchased by a process control variable generally called “spec point”. Therefore, there will often be large quantities of data available from quality control data records at the specification condition. Data will contain many heats, and serve as an excellent measurement source of scatter. Therefore, in regression modeling, specification data are often the major source of scatter measurements. Slope measurements must come from the experimental design matrix.

Specification data can also be used to (1) determine, through analysis-of-variance techniques, fractions of scatter due to heat-to-heat variations, etc., (2) determine, through distribution analysis, if data are normal, log normal, etc., and (3) find out, if data are not normal, what transformation is required.

*Outliers*—These can be excluded only if tests are demonstrably invalid, or if the effect on the equation and statistical parameters is unreasonable. Since exclusion of outliers normally involves a certain degree of judgment, it should only be done by a knowledgeable, experienced individual.

*Discontinued Tests*—These can be included if longer lived, or excluded if shorter lived, than average life of the data subset (lot, section thickness, etc.) to which they belong. (Also, see censored distributions in Section 9.3.6.5 on Data Analysis Procedures.)

*Stepped-Tests*—If load on the specimen had been increased or decreased after initial loading, this test result shall be excluded.

*Truncating Data*—Certain equations, notably parametrics, often do not properly represent a mix of shorter and longer time data. These equations can severely overpredict creep and rupture lives less than ten to thirty hours. Similarly a preponderance of short time data can cause long lives to be overpredicted. Eliminating such data requires truncating the data (or subset). This is done by



**MIL-HDBK-5H**  
**1 December 1998**

removing all data above (or below) a fixed stress level, even though normally acceptable data are excluded.

**Background Data Reporting**—The significance and reliability of creep data generated at elevated temperatures for heat-resistant alloys are, to a major extent, a function of detailed factors which relate to the material, its processing, and its testing. Hence, it is necessary to evaluate not only the property data, but also correlative information concerning these factors.

It is not possible to specify individual items of correlative information, or the minimum thereof, which must be provided with elevated temperature property data to make those data properly meaningful. Individual alloy systems, product forms, and testing practices can all be quite unique with regard to associated information which should be provided with the data. A certain minimum amount of information is required for all data, including:

- (1) Identity of alloy
- (2) Chemical composition of the specific material tested
- (3) Form of product (sheet, forging, etc.)
- (4) Heat-treatment condition
- (5) Producer(s)
- (6) Specification to which product was produced (AMS specifications are normally considered standard\*)
- (7) Date when part was made.

Lack of such information is sufficient basis for rejection of a particular data set.

In addition, it is vital that the individual submitting data consider those factors which contribute to uniqueness of the alloy, processing, and/or testing, and give thought to information which is pertinent to that uniqueness. Thus, grain size can be a significant variable, not only between cast turbine blades, but within a single blade. Thermomechanical working processes may result in significantly different properties (not only higher, but lower as well); and test specimen design can affect resultant data. It is mandatory that knowledgeable personnel be involved when data are submitted for evaluation and potential use. Any correlative data that can be provided will aid the analyst in identifying valid reasons for rejection of data which may not fit the trends of other data (outliers). Such apparent outliers may be indicated through analysis of between-heat variance as described in Section 9.3.6.5.

These examples illustrate the need for adequate information:

- (1) Creep-rupture specimens are being machined from cast high-strength, nickel-base alloy turbine blades. At center span location, specimens are 0.070- to 0.090-inch diameter, while at the trailing edge, specimens are flat and 0.020-inch thick. Flat specimens are typically about one Larson-Miller parameter weaker than round specimens, which is attributable both to thickness effects of the thin specimens and to finer grain size at the trailing edge. In addition, trailing edge

---

\* Company specification data may be included with federal, military, and industry specification data if it is properly documented and can be shown to compare favorably in creep or stress-rupture behavior.



**MIL-HDBK-5H****1 December 1998**

specimens exhibit more scatter. Hence, availability of associated information is vital when considering data from specimens machined from cast turbine blades.

- (2) Comparison of creep-rupture properties of Waspaloy and Superwaspaloy shows that the latter is much weaker at temperatures approaching the upper bounds of utility of the alloy. The significantly lower properties at higher temperatures are attributed to a finer grain size of Superwaspaloy and also to a recovery process that may well be occurring at these temperatures. This alloy is subjected to extensive thermomechanical working, and some strengthening gained by the associated warm working is lost at higher testing temperatures. This effect clearly indicates that processing history significantly affects levels of mechanical properties and, hence, must be adequately documented when property data are submitted.

**9.3.6.5 Data Analysis Procedures** — After an acceptable data collection has been obtained and interpreted, it is possible to proceed in analyzing those data and developing mathematical models of creep and creep-rupture behavior. The objective of the procedures described in the following paragraphs is to calculate creep and rupture life as a function of test conditions and other significant variables. This calculation is done to provide an average curve and a measure of expected variability about the average. The approach that is discussed involves regression analysis to optimize the fit of an equation to the data set. Linear regression analysis is described in Section 9.6.3. The following information provides guidelines in the application of regression analysis to creep and rupture data and recommends approaches to specific problems that are frequently encountered.

*General*—It is assumed that life or time is the dependent variable for rupture or isostrain creep equation analysis, respectively, and logarithmic transformation of the dependent variable is normally distributed.

The data set will nearly always contain a variety of stresses and temperatures. If the data set is the product of a very well-balanced test design (see Section 9.3.6.3), good results may be obtained by independently fitting each temperature. Since this type of data set is often not available, and the approach sacrifices the opportunity for interpolation, the discussion will assume that at least temperature and stress are used as independent variables.

In order to achieve good results, it may be necessary to consider other variables. Some variables are continuous physical variables that are incorporated into regression variables, e.g., section size. Other variables may occur as discrete subsets that require modifying the regression analysis (this is discussed under Subsets of Data). In such cases, it may be necessary to group data per subset for data reporting if regression analysis cannot easily accommodate the observed subsets.

*Selection of Equations*—For isostrain and rupture time, as a function of stress and temperature, a number of relationships have been proposed. Some useful ones are:

- (1)  $\log t = c + b_1/T + b_2X/T + b_3X^2/T + b_4X^3/T$
- (2)  $\log t = c + b_1/T + b_2X + b_3X^2 + b_4X^3$
- (3)  $\log t = c + b_1 T + b_2X + b_3X^2 + b_4X^3$
- (4)  $\log t = c + (T-T_a)(b_1 + b_2X + b_3X^2 + b_4X^3)$ .

These are the Larson-Miller, Dorn, Manson-Succop, and Manson-Haferd, respectively, where

- $c$  = the regression constant
- $b_1$  = coefficients ( $b_1$  through  $b_4$ )
- $t$  = time
- $T$  = absolute temperature ( $T_a$  is the temperature of convergence of the isostress lines)
- $X$  =  $\log S$  (stress).

**MIL-HDBK-5H**  
**1 December 1998**

While all forms may be used to model a data set with varying degrees of goodness of fit, experience and practice indicate the Larson-Miller relationship adequately models most materials, and is usually the preferred equation form.

If data for a given material is available at a variety of creep strain levels as well as the stress rupture point, only one model should be used to describe data trends for each strain level. The decision as to which of the four customary models is chosen should be based on a comparative analysis of data for the most comprehensive data collection, whether that collection be for a specific creep strain level or stress rupture point. In addition, the constant term found in the optimum analysis should be held the same for all creep strain levels. If this is done, it will be possible to construct a composite plot of stress versus parameter for all creep strain levels and the stress-rupture level.

If none of these standard forms satisfactorily follows data trends, various combinations of stress and temperature may be tried. For example, terms can be selected from a matrix obtained using cross products of  $T^{-1}$ ,  $T^0$ ,  $T^1$  with  $S^{-1}$ ,  $S^0$  and  $S^1$ . Methods for generalizing and applying these equations are discussed in Reference 9.3.6.5.

The exact form of the functions should reflect data and reasonable boundary conditions. Quadratic, quartic, etc., can be expected to give poor boundary conditions, e.g., zero life at zero stress, and should be avoided. Extrapolation by users of the equation is inevitable (though it is not recommended), so other general equations must be checked for unusual behavior beyond the data—this can be done, in many cases, by differentiating to obtain maxima and minima. In general, short times should give strengths approximately corresponding to tensile yield and ultimate strength; zero stress should predict infinite life.

Metallurgical instabilities and transition regions may present difficulties in some analyses. Methods for handling such problems have been discussed in Reference 9.3.6.5.

*Optimum Fit*—Guidelines for an optimum fit are:

- (1) Minimum number of terms. With two independent variables,  $\sigma$  and  $T$ , six regression variables are reasonable, each additional physical variable allowing two additional regression variables.
- (2) Reasonable curve characteristics for material behavior, including extrapolation.
- (3) Minimum standard error and maximum correlation coefficient (as long as 1 and 2 are not violated). Standard errors are typically between 0.1 and 0.2.
- (4) Uniform deviations (see a later paragraph on Weights for a brief discussion of nonuniform deviations and their analytical treatment).

*Subsets of Data*—A non-normal or multimodal population, or an excessive standard error may indicate the presence of subsets. However, an apparently typical data set may contain subsets that should receive special consideration.

One type can be treated by adding physical variables to the regression analysis. For example, different thicknesses of sheet material may give different average lives. Including sheet thickness in the regression should not only improve fit but also avoid the risk of misrepresenting behavior of the material. Section thickness, distance from surface, and grain size are other examples of subsets that can be treated as regression variables. Section thickness and distance from surface refer to location of the specimen in terms of geometry of the original material, e.g., finish work thickness, final heat thickness, etc.

**MIL-HDBK-5H****1 December 1998**

A second type is not typically subject to use as a regression variable. Examples of these are orientation (L, LT, and ST), or different heats (chemistry). A decision must be made whether to treat these as unique subsets to be analyzed separately (if properties are different) or as randomly distributed subsets. Orientation will usually be analyzed separately, while heats will usually be randomly distributed subsets. Other methods (e.g., fixed intercept, centered above mean values for each creep level) may be more suited for a given data set and may be tried. The specific procedure used must be indicated in the data package.

The theory of treatment of randomly distributed subsets has been developed in Reference 9.3.6.3, while application to lots of material (actually “heats” in chemistry) is considered in Reference 9.3.6.5. Treating subsets as random affects calculation of both average curve and standard error. While effect on standard error may become insignificant as the number of subsets exceeds ten (depending on the relative contribution to total standard error), effect on the trend of the calculated average remains. Lots whose average lives are uniformly displaced (parallel) in logarithm of life, or are not significantly non-parallel, are discussed in Reference 9.3.6.5. There is no known published reference for treating non-parallel lots. Data permitting, individual lots can be fitted, within-lot variances pooled, and average and variance of lot averages calculated for selected stress-temperature combinations. After calculating total variance and desired lower level tolerance limit\* (X-ks) at each stress level, curves can be drawn and, if desired, equations be fit to X's and (X-ks)'s. It should be noted that the equation for (X-ks) is not likely to properly reflect uncertainty in coefficients obtained by normal fitting procedures. Alternately, all data for non-parallel lots can be pooled and variance weighted, providing sufficient lots are represented and average curve is reasonably similar to the first approach.

*Consistency in Creep and Stress Rupture Trends*—When creep data are somewhat limited, an independent analysis of each creep strain level may produce inconsistent trends between different creep strain levels and stress rupture mean curve. There may be cases where very minor extrapolations will produce creep curves that cross over each other or the stress rupture curve. In some instances, this problem can be eliminated, without a significant loss in quality of fit at each creep strain level, by forcing a prescribed relationship to exist between creep curves and stress rupture curve. Parallelism in log(time) is the simplest relationship that can be assumed, but it is also a relationship that is often supported by data trends. A linearly increasing or decreasing separation of creep curves and stress rupture curve in log(time) as a function of stress is also a possibility, but it takes a large quantity of data to verify such trends. If large quantities of data are available, then it is generally preferable to analyze each creep strain level individually. Therefore, about the only practical relationship to assume between individual creep curves and the stress rupture curve is parallelism in log(time).

Parallelism in log(time) can be achieved through the addition of a dummy variable to the stress rupture equation for each creep strain level being added to the regression analysis. For example, in the case of the Larson-Miller equation, which (in its third order form) is normally written as

$$\log t = c + b_1/T + b_2X/T + b_3 X^2/T + b_4 X^3/T,$$

where

t = time, hrs

T = absolute temperature, °R

X = log (stress), ksi,

---

\* Tolerance limits used here are one-sided and are normally developed for tolerance levels of 90 or 99 percent at a confidence level of 95 percent.

**MIL-HDBK-5H**  
**1 December 1998**

the equation can be modified to include additional terms for each creep level, as follows

$$\log t = c + b_1/T + b_2X/T + b_3X^2/T + b_4X^3/T + b_5 Y_1 + b_6 Y_2 + \dots b_{4+i} Y_i$$

where the value of  $Y_i$  new terms are either 0 or 1. If a creep strain level 1 data point is considered,  $Y_1 = 1$  and all other  $Y$ 's are 0. Similarly, if a creep strain level 2 data point is considered,  $Y_2 = 1$  and all other  $Y$ 's are 0. If a stress rupture data point is considered, all the  $Y$ 's are 0. In this way, the optimized values of additional  $b$ 's represent average  $A$  in  $\log(\text{time})$  that each creep curve falls below the stress rupture curve.

The usefulness of such an approach must be verified through an examination of quality of fit for each creep strain level compared to raw data trends.

*Weights*—Rupture and isostrain creep curves will not normally require weights to obtain uniform variables. Analysis, including strain as a variable, frequently will. Variables other than strain, temperature, and stress will require evaluation for uniform variance. Reference 9.3.6.5 provides further discussion of weighting.

*Rejection of Analyses*—Regression analyses of specific creep or stress-rupture data sets should normally be rejected if the  $R^2$  statistic for analysis is <75 percent, or there are fewer data than five times the number of temperature levels, or there are <20 data points total available for regression.

If data for several different creep strain levels are analyzed in combination with stress rupture data,  $R^2$  levels below 75 percent for one or two creep strain levels may be acceptable, if the overall  $R^2$  exceeds 75 percent. Separate analyses of low creep strain data may show relatively high variation with  $R^2$  values below 75 percent. In these cases, if there are sufficient data to produce significant regression coefficients at a 95 percent confidence level, the result may still be acceptable for inclusion in MIL-HDBK-5.

**9.3.6.6 Preparation of Creep-Rupture Data Proposals** — Creep-rupture proposals developed for review and possible inclusion in MIL-HDBK-5 should contain the following information and meet associated criteria.

*Data Reporting*—The background information shall meet the requirements of Section 9.3.6.4. Test results shall be listed in a manner such that all data are identifiable in terms of material and test background information as well as test conditions used in generating data (see Section 9.3.6.7 for an example).

*Analysis Reporting*—The analysis report will display the following (see Section 9.3.6.5 for details);

- (a) Trials—Equations tried and reason for ejecting.
- (b) Data rejected—Reason.
- (c) Best-fit details—Listing of data, calculated values, and deviations. All data are to be clearly traceable in terms of data reporting requirements.
- (d) Standard error or total variance and correlation coefficient.
- (e) Subset variance—If random subsets are used, report both the pooled within-subset variance and the between-subset variances as well as the total variances.
- (f) Constants—Report the average regression constant and regression constants for any subsets.

**MIL-HDBK-5H****1 December 1998**

- (g) Coefficients—Report the numerical value of the coefficient of each regression variable and its standard error.
- (h) Equation—Exhibit the equation used; with the coefficients,  $b_1$ , traceable to the numerical listing in above item (g).
- (i) Deviation—Exhibit plots of deviations in life versus calculated life for each temperature and, as far as possible, identify according to subsets. It is also possible to provide a summary table of deviations. As an example of isostrain creep or rupture, divide the life range of data in five equal logarithmic increments and, for each temperature, give the algebraic sum of deviation with that increment. If random subsets are used, deviations summed are to be those from within the respective subsets.
- (j) Data and Curve Comparison—Display data against the calculated average curve. Encode data with symbols as the deviation plots. Scale coordinates such that the curves have an apparent slope of about -1.0. Use scales appropriate for the most significant form of the regression variable, usually  $\log(\text{stress})$  versus  $\log(\text{life})$ , with life (dependent variable) on the abscissa and stress on the ordinate.
- (k) Curve Extrapolation Tests—Exhibit the average curve from one to 105 hours for corresponding temperature levels. Representative curves may be used including extreme values of independent variables represented in data. Further, calculation of desired tolerance limit (e.g., probability level) should be performed to assist in determining validity of the extrapolation.

The above recommendations apply to incorporation of new creep and/or stress-rupture curves in MIL-HDBK-5. The use of creep nomographs has been discontinued. Creep nomographs in MIL-HDBK-5 will be replaced as data are reanalyzed and new analytically defined creep and stress rupture curves are developed.


**9.3.6.7 Data Presentation** — The presentation for MIL-HDBK-5 will include one or more pages of correlative information, equations, and curves as needed. Requirements on each will vary with the problem and should be reasonably obvious from data, background information, and analytical results.

An example of a typical data presentation is shown in Figure 9.3.6.7. Note that raw data are displayed along with mean trend lines, on a semi-logarithmic plot of stress versus time. Supportive data describing alloy, specimen details, and analysis results are also presented. Table 9.3.6.7 provides even more detailed, but necessary, information on such factors as heat treatment details and inverse matrix (which can be used in conjunction with other analysis results to compute lower level tolerance limits for the data).

Some creep data are still presented in creep nomographs. For these cases, the analysis and presentation were based primarily on Reference 1.4.8.2(b). The presentation of creep data in the form of a nomograph is not in compliance with the above guidelines. Therefore, these creep nomographs will be replaced in the near future.

## MIL-HDBK-5H

1 December 1998



**Figure 9.3.6.7. Average isothermal stress rupture curves for alloy XYZ forging.**

Correlative Information for Figure 9.3.6.7(a)

Makeup of Data Collection:

Public Specifications—AMS 5663  
 Heat Treatment—2, 21 [See Table 9.3.6.7(a)]  
 Number of Vendors—Not specified  
 Number of Heats—7  
 Number of Test Laboratories = 3  
 Number of Tests = 347

Specimen Description:

Type—Unnotched round bar  
 Gage Length—N.A.  
 Gage Thickness—1/4"—3/8"

Stress Rupture Equation:

$$\begin{aligned} \log t &= c + b_1 T + b_2 X + b_3 X^2 + b_4 X^3 \\ T &= ^\circ\text{R}, X = \log(\text{stress, ksi}) \\ c &= 186.27 \\ b_1 &= -0.01778 \\ b_2 &= -255.25 \\ b_3 &= 146.28 \\ b_4 &= -28.65 \end{aligned}$$

Analysis Details:

Inverse Matrix—See Table 9.3.6.7(a)  
 Standard Deviation = 0.63  
 Standard Error of Estimate = 0.29  
 Within Heat Variance = 0.071  
 Ratio of Between to Within Heat  
 Variance = (at spec pt.) < 0.10

**Table 9.3.6.7. Supplemental Data Pertaining to the Stress Rupture Behavior of Alloy XYZ Forging**

Heat Treatment Details				
Heat Treatment No.	Cycle No.	Temperature, °F	Time, Hours	Cool
2	1	1800	1	AC, WQ
	2	1325	8	FC (100 °F/hr)
	3	1150	8	AC
21	1	1700-1850	1	AC
	2	1325	8	FC (100 °F/hr)
	3	1150	8	AC

Stress Rupture Equation and Inverse Matrix for the Creep Stress =  
0.10, 0.20, 0.50, and 5.00% and Stress Rupture Conditions

$$\log t = c + b_1T + b_2X + b_3X^2 + b_4X^3 + b_5Y_1 + b_6Y_2 + b_7Y_3 + b_8Y_4 + b_9Y_5$$

where

$Y_1$	=	1; $Y_2, Y_3, Y_4, Y_5 = 0$ for Creep Strain = 0.10% Data
$Y_2$	=	1; $Y_1, Y_3, Y_4, Y_5 = 0$ for Creep Strain = 0.20% Data
$Y_3$	=	1; $Y_1, Y_2, Y_4, Y_5 = 0$ for Creep Strain = 0.50% Data
$Y_4$	=	1; $Y_1, Y_2, Y_3, Y_5 = 0$ for Creep Strain = 5.00% Data
		$Y_1, Y_2, Y_3, Y_4, Y_5 = 0$ for Stress Rupture Data

Column Row	1	2	3	4	5	6	7	8	9
1	1.809E+00	-1.108E-03	-1.978E+00	6.499E-01	-5.748E-02	-1.606E+00	-1.444E+00	-1.015E+00	-9.777E-01
2	-1.108E-03	6.834E-07	1.212E-03	-3.979E-04	3.517E-05	9.843E-04	8.852E-04	6.219E-04	5.993E-04
3	-1.978E+00	1.212E-03	3.482E+00	-1.657E+00	2.032E-01	1.634E+00	1.359E+00	6.886E-01	5.921E-01
4	6.499E-01	-3.979E-04	-1.657E+00	9.145E-01	-1.220E-01	-4.892E-01	-3.610E-01	-6.305E-02	3.594E-03
5	-5.748E-02	3.517E-05	2.032E-01	-1.220E-01	1.697E-02	3.801E-02	2.248E-02	-1.245E-02	-2.618E-02
6	-1.606E+00	9.843E-04	1.634E+00	-4.892E-01	3.801E-02	1.471E+00	1.303E+00	9.401E-01	9.124E-01
7	-1.444E+00	8.852E-04	1.359E+00	-3.610E-01	2.248E-02	1.303E+00	1.222E+00	8.806E-01	8.600E-01
8	-1.015E+00	6.219E-04	6.886E-01	-6.305E-02	-1.245E-02	9.401E-01	8.806E-01	7.491E-01	6.987E-01
9	-9.777E-01	5.993E-04	5.921E-01	3.594E-03	-2.618E-02	9.124E-01	8.600E-01	6.987E-01	1.195E+00




**MIL-HDBK-5H****1 December 1998**

**9.3.6.8 An Example of the Use of Experimental Design for the Purpose of Developing Regression Models** — By a slight chemical change and modification of heat, the former Alloy 325 is now believed to have an increased stress-rupture life of 20 percent to 30 percent. It is desired to fully characterize these properties over the 1600 to 1900°F range. Average creep life is to be from 10 hours to 1,000 hours.

Nineteen stress rupture tests from two heats of new alloy averaged 37.4 hours at 30 ksi/1800°F,  $s(\log 10) = 0.150$ . Figure 9.3.6.8(a) is a log-log mean life plot of predicted stress rupture properties of modified Alloy 325 based on a predicted value. A 1750°F line has been added to the original plot. From this log-log plot, it can be seen that only three temperatures need to be tested because there are stress levels in common with the 1600°F line, and the same is true for the 1750°F and 1900°F lines.

Next, three temperature lines are bracketed with the 10-hours to 1000-hours life range. See Figure 9.3.6.8(b). Stress levels are then chosen to give the desired life. There are 25 tests required with this procedure. All 25 could be run, or 3 tests could be randomly eliminated from the center cells of the matrix (see circled cells). If 3 are deleted this would leave 22 tests, which are near the minimum of 20. These tests could be conducted and these data added to the 19 specific data points at 30 ksi/1800°F. This quantity would constitute the data set. Table 9.3.6.8 shows the results of a simulated sampling.

A Larson-Miller analysis of data produced the curves in Figures 9.3.6.8(c) and (d). Data plotted with the temperature lines of Figure 9.3.6.8(d) confirm a good fit over the range of data. The approach described in this example can be used for any creep or rupture experimental design.




**Figure 9.3.6.8(a). Estimated stress rupture curves for Alloy 325 (MOD).**



[illegible]

**Figure 9.3.6.8(b). Experimental design matrix for creep rupture.**



**Figure 9.3.6.8(c). Alloy 325 (MOD) stress rupture typical life.**

## MIL-HDBK-5H

1 December 1998




Figure 9.3.6.8(d). Alloy 325 (MOD) stress rupture typical life.

Table 9.3.6.8. Results of Simulated Sampling of Creep-Rupture Data

ksi	1600°F	ksi	1750°F	ksi	1900°F
63	19.0 hrs.	42	8.8 hrs.	25	27.6 hrs.
59	11.1 hrs.	39	35.5 hrs.	22	23.9 hrs.
54	36.3 hrs.	36	52.3 hrs.	17	65.4 hrs.
52	170.7 hrs.	32	71.8 hrs.	15	140.3 hrs.
45	148.0 hrs.	29	121.9 hrs.	12	257.5 hrs.
42	376.0 hrs.	27	355.9 hrs.	10	623.5 hrs.
39	806.9 hrs.	22	389.0 hrs.	*	
36	878.0 hrs.	20	2912.4 hrs.	*	

\*No interest.

SPECIFICATION DATA  
@ 30 KSI 1800°F

Hours

41.4	33.1	70.5	36.1
16.5	27.4	37.5	34.9
35.0	33.4	48.6	74.2
33.6	51.3	29.0	47.5
32.6	42.7	26.4	

(n = 19,  $\bar{X}$  = 37.4, s(log 10) = 0.150)

**MIL-HDBK-5H**  
**1 December 1998**

## **9.4 PROPERTIES OF JOINTS AND STRUCTURES**

### **9.4.1 MECHANICALLY FASTENED JOINTS**

**9.4.1.1 Introduction** — Some mechanical fasteners will not develop full bearing strengths of materials in which they are installed. Joint allowables for these fasteners must therefore be determined from test data. Fasteners for which allowable loads must be determined are: (1) flush-head fasteners in dimpled or countersunk sheet, (2) fasteners with hollow or multiple-piece shanks, (3) protruding-head fasteners with shear-type heads\*, and (4) protruding-head bolts and rivets when thickness-to-diameter ratio ( $t/D$ ) is less than 0.18.

These guidelines define data generation (quality/quantity), analysis methods, and presentation format applicable to mechanically fastened joint allowables. They reflect a need to (1) ensure that the aerospace industry is interested in new fastener systems which are incorporated in MIL-HDBK-5, and (2) ensure that confirmatory data to substantiate allowable loads meet certain stated requirements that simplify the process of acceptance through coordination. To accomplish these needs, fastener systems proposed for inclusion in MIL-HDBK-5 may be introduced (sponsored) by airlines, airframe or engine prime contractors, and Government agencies (DoD, FAA, or NASA); i.e., one of the users. When introducing a new fastener, the sponsoring organization shall supply information specified in Section 9.4.1.7.1. The sponsoring organization is also expected to review the test program plan, actual testing, and data analysis. At least 25 percent of the specimen fabrication and testing shall be performed at a second facility. It also is expected that fasteners and fastener materials will be obtained from three production runs per diameter as documented in the report. The sponsoring organization shall submit a report documenting design allowables to MIL-HDBK-5 Coordination Group for evaluation. (See Section 9.4.1.7.2.)

Proposals not meeting the requirements described herein will be rejected or require more time-consuming evaluation, inevitably delaying approval and release of proposed allowables. Therefore, use of these guidelines in preparing proposals for MIL-HDBK-5 is essential.

In case of conflict, provisions of this document take precedence over reference documents for any tests or analyses made to provide, substantiate, or revise MIL-HDBK-5 fastener allowables.

**9.4.1.2 Definitions** — Terms used in Section 9.4.1 vary among users of this Handbook. To provide consistency, these terms are defined herein in accordance with the intent of MIL-HDBK-5.

- (a) **Deformable Shank Fasteners**—A fastener whose shank is deformed in the grip area during normal installation processes.
- (b) **Nominal Hole Diameters**—Nominal hole diameters for deformable shank fasteners shall be according to Table 9.4.1.2. When tests are made with hole diameters other than those tabulated, hole sizes used shall be noted in the report and on the proposed joint allowables table.
- (c) **Nondeformable Shank Fasteners**—A fastener whose shank does not deform in the grip area during normal installation processes.
- (d) **Nominal Shank Diameter**—Nominal shank diameter of fasteners with shank diameters equal to those used for standard size bolts and screws (NAS 618 sizes) shall be the decimal equivalents of stated fractional or numbered sizes. These diameters are those listed in the

---

\* For example, protruding-head fasteners with reduced head heights similar to those shown for NAS 529 rivets.

**MIL-HDBK-5H**  
**1 December 1998**

fourth column of Table 9.4.1.2. Nominal shank diameters for nondeformable shank blind fasteners are listed in the fifth column of Table 9.4.1.2. Nominal shank diameters for other fasteners shall be the average of required maximum and minimum shank diameters.

There are many generically named fasteners for which joint allowables are provided. These fasteners are listed below, followed by the letter H or S. H signifies that, in the analysis, nominal hole diameter (as described above) is used. S signifies that, in the analysis, nominal shank diameter is used.

- (a) Solid rivets and blind fasteners whose shanks deform during installation. (H)
- (b) Solid rivets and blind fasteners whose shanks do not deform during installation. (S)
- (c) Threaded and swaged-collar fasteners whose shanks do not deform during installation. (S)
- (d) AR interference-fit and close-tolerance fasteners. (S)


**Table 9.4.1.2. Nominal Hole and Shank Diameters, Inches**

Fastener Size, Functional or Numbered	Deformable Shank Fasteners Nominal Hole Diameter		Nondeformable Shank Fasteners Nominal Shank Diameter <sup>a</sup>	
	Solid Rivets	Blind Fasteners	Solid Shank Fasteners	Blind Fasteners
1/16	0.067	...	...	...
3/32	0.096	0.098		
#4	...	...	0.112	...
1/8	0.1285	0.130 0.144	0.125	...
#6	...	...	0.138	...
5/32	0.159	0.162 0.178	0.156	0.163
#8	...	...	0.164	...
3/16	0.191	0.194 0.207	0.188	0.198
#10	...	...	0.190	...
#12	...	...	0.216	...
7/32	...	...	0.219	...
1/4	0.257	0.258 0.273	0.250	0.259
5/16	0.323		0.312	0.311
3/8	0.386	...	0.375	0.373
7/16	...	...	0.438	0.436
1/2	...	...	0.500	0.497
9/16	...	...	0.562	...
5/8	...	...	0.625	...
3/4	...	...	0.750	...
7/8	...	...	0.875	...
1	...	...	1.000	...
1-1/8	...	...	1.125	...
1-1/4	...	...	1.250	...
1-3/8	...	...	1.375	...
1-1/2	...	...	1.500	...

<sup>a</sup> In order to standardize test and analysis procedures, nondeformable shank fasteners shall be installed in net fit  $\pm 0.0005$  inch holes.

**MIL-HDBK-5H****1 December 1998**

**9.4.1.3 Data Generation** — Development of mechanically fastened joint allowables from test data usually is accomplished with the aid of graphic analysis. Coordinates of the graph are  $P/D^2$  and  $t/D$ , where  $P$  is subscripted  $P_u$  for ultimate load and  $P_y$  for yield load. The analysis assumes that design of a line of fasteners (a given configuration, material, and range of diameters) is proportional so that, when data from tests are plotted with the above coordinates, all data for all diameters can be represented by a single design curve. A schematic diagram of such a design curve for ultimate load is shown in Figure 9.4.1.3.



**Figure 9.4.1.3. Schematic diagram of  $P_u/D^2$  versus  $t/D$ .**

Note there are three regions to the curve as follows:

Region 1, in which the joint failure mode is by sheet bearing.

Region 2, which is a transition failure zone in which failure may be by other means, such as head pulling through sheet, tension or shear of the fastener head, etc.

Region 3, in which the joint failure mode is by fastener shear.

The design curve shall be constructed so that all data fall to the left and above.

Data required for determining mechanically fastened joint allowables are based on results of single-shear lap-joint tests over the three regions described above, and fastener shear tests (usually, double shear tests in hardened steel test plates or fixtures). For driven rivets and blind fasteners, the single-shear lap-joint test in hardened steel test plates may be used to obtain shear strength or cutoff (Region 3). It is preferred, however, that shear strength be obtained from double shear tests of the fastener. Fastener system tensile strength data are required for all fasteners except solid and blind rivets (see Section 9.4.1.4.2). Sheet tensile test data also are necessary (see Section 9.4.1.4.5).


**9.4.1.3.1 Testing Equipment and Procedures** — Room-temperature testing equipment and procedures should comply with the provisions of MIL-STD-1312, Tests 4, 13, and 20 [References 9.4.1.3.1(a) through (c) for both single- and double-shear tests.

**9.4.1.3.2 Specimen Design Configuration** — Specimen design should be as provided in MIL-STD-1312, Test 4, Figure 1, Reference 9.4.1.3.1(a).

**MIL-HDBK-5H**  
**1 December 1998**

**9.4.1.3.3 Yield Load Definition** — Joint yield loads for all fasteners are defined as loads which result in  $0.04D$  permanent set in the joint when the fastener is tested in nominal hole size as defined in Table 9.4.1.2. For some fastening systems, tests in larger hole sizes, although within manufacturer's recommended hole size limits, may result in joint permanent sets greater than  $0.04D^*$  at yield load.

**9.4.1.3.4 Yield Load Determination** — The preferred method of determining yield load is by the secondary modulus method.\*\* To obtain secondary modulus line, during the test the joint is unloaded from a load close to, and preferably above, estimated yield load to a load value in the range of about 10 to 20 percent of estimated yield load. The joint then is reloaded and secondary modulus is the slope of this second loading line. This procedure is described in Reference 9.4.1.3.1(a) and is illustrated in Figures 9.4.1.3.4(a) through (e).



**Figure 9.4.1.3.4(a). Illustration of secondary-modulus method of yield strength determination.**


- (1) Reduce load to 10-20 percent of yield load.
- (2) Secondary-modulus line. The straight part of the loading side of the secondary-modulus loop indicating elastic behavior.
- (3) Offset line. A line parallel to the secondary-modulus line.
- (4) Offset. Equal to permanent set value specified in Section 9.4.1.3.3.

If curves similar to Curves A and B in Figure 9.4.1.3.4(b) are obtained early in the test program, strain hardening will be presumed. In that case, unloading should be delayed in subsequent tests until after anticipated yield load. Curves showing strain hardening may be extrapolated a reasonable amount to determine yield load by the secondary modulus method as shown.

The initial loading line is used to establish the intersection with the abscissa from which to measure yield offset. At times, minor irregularities occur on initial loading which necessitates redrawing of the lower part of the curve as a continuation of the normal curve, as shown in Curves C and D of Figure 9.4.1.3.4(c).


\* Or previous yield load criteria used prior to 1973. Applicable yield criteria are noted in footnote for design allowable table.

\*\* The primary modulus line has been used in the past, on occasion. It is the slope of the initial loading line and frequently is observed to have greater variability than the secondary modulus line.



**Figure 9.4.1.3.4(b). Sample secondary modulus load-deflection curves.**

- (1) Offset per 9.4.1.3.3.
- (2) Joint yield strength.



**Figure 9.4.1.3.4(c). Sample secondary-modulus load-deflection curves.**

- (1) Offset per 9.4.1.3.3.
- (2) Joint yield strength.
- (3) Disregarded irregularities, per 9.4.1.3.

## MIL-HDBK-5H

### 1 December 1998

Unusually shaped curves are sometimes obtained. Typical of these are the illustrations in Figure 9.4.1.3.4(d). Data which are typified by Curves A or B are unacceptable for analysis. When the secondary modulus has a straight-line portion of recognizable length, do as shown in Curve C. When the secondary curve has two straight parts, but is more in question (as in Curve D), and there are satisfactory curves available from similar group test specimens, use the slope which approximates other curves. Otherwise, the more conservative (steepest) shall be used. An acceptable alternate is to draw a straight line between end points of the off-loading-reloading loop and consider this as the secondary modulus line, as shown in Figure 9.4.1.3.4(e). The primary modulus method may be used as a last resort, if there is no straight-line portion or usable loop in the secondary modulus curve.

**9.4.1.4 Quantity and Distribution of Test Data** — This section delineates required data to develop the design curve shown schematically in Figure 9.4.1.3. There are three facets to consider, which are described in following subsections: (1) shear strength of the fastener, Region 3; (2) shear critical strength, bearing and transition regions, Regions 1 and 2; and (3) tensile properties of sheet and plate material used in the joint.

A fourth subsection is concerned with the case when data are required for certification purposes (not for use in MIL-HDBK-5) for a specific thickness and fastener diameter.

**9.4.1.4.1 Shear Strength of Fastener** — Although many fasteners for which joint allowables are given in MIL-HDBK-5 are covered by MIL and NAS specifications (which provide for minimum shear strength values), many proprietary fasteners are listed wherein minimum shear strength values are established by the manufacturer. In either case, sufficient testing is necessary to establish minimum values. The intent of this subsection is to provide minimum test requirements to document shear strength of fasteners appearing in MIL-HDBK-5, regardless of specification source.


Shear strengths shall be determined from shear-critical single-shear test results or double-shear test results. Double-shear test results performed in accordance with MIL-STD-1312, Test 13, are preferred over single-shear results, except for blind fasteners and driven rivets. For these latter fasteners, shear-critical tests shall be conducted with all components in the installed condition in hardened steel test plates. MIL-STD-1312, Test 20, is the preferred test method. Furthermore, when fasteners of a given configuration and material are identical in every respect except for head size and shape, fastener shear test data are necessary only on one head style.

The minimum quantity of shear tests required for each fastener diameter for which allowables are to be established is 15. Fasteners for each diameter shall be selected from at least three production lots that represent at least two heats of the fastener component materials.

Fasteners developed from materials not previously used for fastener applications will require additional testing in order to determine statistically reliable minimum shear strengths. Test values should be developed in accordance with the test methods noted above using hole sizes specified in those methods or Table 9.4.1.2, as appropriate. Test values shall represent a minimum of 10 tests from each of 10 production lots made of at least 3 heats of material (100 tests). Fasteners tested should be evenly distributed over the diameter range under consideration with grip ranging from 2 to 3 diameters for solid and blind rivets and any appropriate length for solid shank fasteners. Shear strength ( $F_{su}$ ) should be computed based on hole size for solid and blind rivets and measured shank diameter for non-hole filling blind fasteners and pins. Data shall be checked for normality and if distribution is found to be normal:




MIL-HDBK-5H  
1 December 1998



**Figure 9.4.1.3.4(d). Sample secondary-modulus load-deflection curves.**

- (1) Offset, per 9.4.1.3.3
- (2) Joint yield strength.
- (3) Disregarded irregularities, per 9.4.1.3.4.
- (4) Disregarded second slope in secondary-modulus curve.

**MIL-HDBK-5H****1 December 1998**

**Figure 9.4.1.3.4(e). Sample alternative secondary-modulus load-deflection curve.**

- (1) Offset, per Section 9.4.1.3.3
- (2) Joint yield strength.
- (3) Alternative secondary-modulus line.

- (a) For solid driven rivets, compute the B-value and select the next lower shear strength from Table 8.1.1.1, if it is within 2 ksi of the computed value. If the computed B value is more than 2 ksi above the next lower value in Table 8.1.1.1, a new value may be proposed.
- (b) For other fasteners, compute the A-value and select the next lower shear strength from Table 8.1.1.1. If the computed A-value is more than 5 ksi above the next lower value in Table 8.1.1.1, a new value may be proposed.

If analysis of data shows a non-normal distribution, obtain additional observations (as required) and employ the nonparametric procedure described in Section 9.2.8.2. Minimum shear strength shall then be selected as described in (a) and (b) above.

**9.4.1.4.2 Tensile Strength of Fastener** — Tensile strength shall be determined for all fastener systems except solid and blind rivets from tests performed in accordance with MIL-STD-1312, Test 8. Tensile test requirements and analytical methods shall be the same as for shear strength determination (see Section 9.4.1.4.1).

**9.4.1.4.3 Assembled Joint Strength** — The requirement for data from two fabricating and testing sources applies to assembled joint strength. Approximately 75 percent of required data shall come from one source; the remainder from a second source. Data shall cover the  $t/D$  range that results in bearing, transitional and shear-type failures as shown in Figure 9.4.1.3(a). It is suggested that the second source concentrate testing in the bearing and transition regions. Selection of sheet thickness shall be made in such a way that, for each fastener diameter, an even distribution of data is achieved over the  $t/D$  (thickness/diameter) range with about 20 percent of the data taken at  $t/D$  values for which joint failure will be by fastener shear (not applicable to dimpled joints). Sheet thickness/fastener grip combinations shall be selected to include a uniform distribution of minimum and maximum grip conditions throughout the  $t/D$  range tested.

**MIL-HDBK-5H**  
**1 December 1998**

Specimen fabrication and testing shall be allocated to provide data from each source, distributed across the sheet critical and transition ranges.

**9.4.1.4.4 Sheet Critical Strength** — The requirement for data from two fabricating and testing sources applies to sheet critical strength. Approximately 75 percent of required data shall come from one source; the remainder from a second source. The data will cover the t/D range that results in bearing, transitional and shear-type failures as shown in Figure 9.4.1.3. It is suggested that the second source concentrate testing in the bearing and transition regions. Selection of sheet thickness shall be made in such a way that an even distribution of data is achieved over the t/D (thickness/diameter) range with about 20 percent of the data taken at t/D values for which joint failures will be by fastener shear (not applicable to dimpled joints).

All diameters of a given fastener for which joint allowable loads are established shall be included in the test plan. Since a fastener line usually comprises 2 to 5 more diameters, quantity of joint specimens to be tested will be expected to vary, depending upon number of fastener diameters. Quantity of data shall include results from at least the following valid tests: two diameters, 40 tests; three diameters, 55 tests; four diameters, 70 tests; five diameters, 85 tests. In allocating test joint specimens among fastener diameters, for a three- or four-diameter fastener line a larger quantity of specimens shall be used for the largest and smallest diameters with somewhat less testing for intermediate diameter(s). In the case of a five-diameter fastener line, larger quantities of specimens should be allocated to the largest, middlemost, and smallest diameters with somewhat less testing for the two remaining intermediate diameters. For each diameter and t/D combination tested, a minimum of three specimens should be used.

In the sheet critical range, fasteners with different head shapes, head sizes (NAS 1097, MS 29694, or MS 20426), material, or heat treatment will be considered different fasteners and shall require separate tests. Sheet materials with different heat treatments or compositions will be considered different materials and also shall require separate tests. In the case of aluminum alloys, data obtained with clad sheet may be used to determine allowables for clad and bare sheet; however, allowables obtained from tests on bare sheet can be used only to determine allowables for bare sheet. In the case of all sheet materials, data from tests using sheet at one heat-treat level may be used to determine allowables for sheet having higher strength heat treatments. However, the reverse is not permissible.

**9.4.1.4.5 Tensile Properties of Joint Materials** — At least three sheet tension test results as required by MIL-STD-1312, Test 4, shall be provided for each sheet or plate used to make single-shear test specimens described in the previous subsection. Tensile ultimate and yield strengths and percent elongation shall be reported in accordance with ASTM E 8. Grain direction shall be that applicable to the procurement specification tensile test requirements. Tabulated data shall identify single-shear specimens made from sheet to which each group of sheet-tension specimens apply by appropriate coding.

**9.4.1.4.6 Joint Allowable Loads for Limited Thickness Material** — In the event that joint allowable loads for a limited range of thickness or diameter required for procuring or regulatory agency (one such case would be where t/D is less than 0.18 for protruding head fasteners), a much smaller quantity of data is required than described in Section 9.4.1.4.2. As a minimum, this could require development of allowables for one thickness and one diameter of a given fastener. In this case, data shall consist of the results from 15 lap-joint tests and if practical shall represent at least three production lots of fasteners.

**9.4.1.4.7 Fastener Systems With Limited Grip Lengths** — Should a static joint strength table be desired for a fastener system produced in a limited range of grip lengths, the following procedure shall be followed:

- (1) Sponsorship (see Section 9.4.1.7.1), including a specification and standards page, shall be required.

**MIL-HDBK-5H**  
**1 December 1998**

- (2) Test all diameters (at least 2) through the full grip range (a minimum of 3 grip lengths above knife-edge) shown on the standards page.
- (3) Test a minimum of 5 specimens per t/D ratio (3 from the prime source and 2 from the second source).
- (4) To the extent possible, the distribution of minimum/maximum grip combinations and fabrication testing allocation specified in Section 9.4.1.4.2 shall be observed.
- (5) Analyze the data using a conservative application of the standard approach (possibly requiring all test data points to be above the average ultimate -5 percent or average yield -10 percent lines in cases of extreme data scatter).
- (6) Use the standard design allowables presentation except:
  - (a) Don't show fastener shear strength unless shear failures are obtained in the test program.
  - (b) In a box, located prominently within the table, place the following information.

THIS FASTENER IS ONLY MANUFACTURED  
 IN LIMITED GRIP LENGTHS. IT HAS ONLY  
 BEEN TESTED IN THE SHEET GAGES  
 SHOWN IN THIS TABLE. DESIGN DATA  
 FOR SHEET GAGES OR DIAMETERS OTHER  
 THAN THOSE SHOWN HERE CANNOT BE  
 EXTRAPOLATED.

- (7) Additional test data and a new part number may be required if available diameters and/or grip lengths are extended in the future.

**9.4.1.4.8 Confirmatory Data** — If a manufacturer wishes the company name to be added to the footnote of an existing table as a supplier of confirmatory data, the following procedure shall be used:

- (1) Repeat, in total (quantities and conditions), the original test program from which the table was developed.
- (2) Utilizing the test report from the original supplier of the test data, plot the average ultimate strength +10 percent and -5 percent, ultimate load design lines, and average yield strength  $\pm 10$  percent lines.
- (3) Utilizing these plots, plot the average data points and the lowest ultimate data point from each t/D combination tested by the supplier of confirmatory data.
- (4) If all plotted average points fall within or above the plotted bands, and all lowest ultimate values fall above the design ultimate line, then the new product has the same allowable load values as the original fastener tested and can be included in the table.
- (5) The existing design allowable table shall be modified in accordance with Item 17(c) of Section 9.4.1.6.

**MIL-HDBK-5H**  
**1 December 1998**

If a manufacturer wishes the company name to be added to the footnote of an existing design allowable table with four or more diameters as a supplier of confirmatory data but does not produce or market the fastener in all diameters contained in the design allowable table, the following procedure shall be used:

- (1) Test at least three successive diameters including the smallest diameter in the design allowable table, or test at least three successive diameters including the largest diameter in the design allowable table. Quantities shall be the same as for the original test program.
- (2) Utilizing the test report from the original supplier of the test data, plot the average ultimate strength +10 percent and -5 percent, ultimate load design lines, and average yield strength  $\pm 10$  percent lines.
- (3) Utilizing these plots, plot the average data points and the lowest ultimate data point from each t/D combination tested by the supplier of confirmatory data.
- (4) If all plotted average points fall within or above the plotted bands, and all lowest ultimate values fall above the design ultimate line, then the new product has the same allowable load values for the fastener diameters tested as the original fastener tested and can be included in the table.
- (5) Add the following footnote to the design allowable table: "Confirmatory data provided by XYZ Company." Flag this footnote to supplier's part number and applicable fastener diameters.

#### **9.4.1.5 Analysis of Test Data**

**9.4.1.5.1 Shear Strength of Fastener** — Each group of double-shear or single-shear results for a specific fastener type, size, and material shall be analyzed to determine an A-value, except driven rivets which shall be analyzed to obtain a B-value. The lower limit shall be calculated using one of the following formulas:

$$L = \bar{x} - k \sqrt{\frac{\sum(x - \bar{x})^2}{n - 1}} \quad [9.4.1.5.1(a)]$$

$$L = \bar{x} - k \sqrt{\frac{\sum x^2 - (\sum x)^2/n}{n - 1}} \quad [9.4.1.5.1(b)]$$

$$L = \bar{x} - k \sqrt{\frac{n \sum x^2 - (\sum x)^2}{n(n - 1)}} \quad [9.4.1.5.1(c)]$$

where

- x = individual observed test result in terms of load
- n = number of observed test results
- L = lower tolerance limit corresponding to either the A- or B-basis
- $\bar{x}$  = average of test results =  $(\sum x)/n$
- $\sum$  = summation of all values of the indicated quantity
- k = factor from Table 9.6.4.1 applicable to either the A- or B-basis.

**MIL-HDBK-5H**  
**1 December 1998**

The calculated L values shall be equal to or greater than the values in Table 8.1.5(a) (for the appropriate stress level) and the specification value. (That is, the computed L value for a 0.190 diameter, 95 ksi fastener shall be greater than, or equal to, the allowable load value of 2,694 pounds.) The allowable load shall be the lower of the appropriate Table 8.1.5(a) value or the specification value.

If Table 8.1.5(a) is not applicable (i.e., driven rivets, blind fasteners, and fasteners without shear-load requirements in the specification), the L values shall be converted to stresses for each diameter using nominal shank areas for S fasteners and nominal hole areas for H fasteners.

The allowable stress for the fastener system shall be established as the lowest of the above calculated stresses, or the specification stress value, whichever is lower. Allowable fastener shear strength shall be the product of this stress and the appropriate (H or S) areas used above.

The shear strengths so calculated shall be clearly identified as either 90 percent (B-value) or 99 percent (A-value) allowables.

**9.4.1.5.2 Sheet Critical and Transition Critical Strengths**—The analysis of data in the bearing and transitional regions provides design allowable curves for yield and ultimate strength where sheet or plate material of the joint is generally critical. To accomplish the analysis, tables and graphs are required as detailed in this subsection. The use of computer programs to analyze data and to prepare tables of calculations and figures, as next described, is acceptable. However, all tables and figures subsequently described should be illustrated in the report. When using a computer for analysis, some engineering judgements may be necessary for certain data sets in the transition thickness range.

- (a) **Presentation and Analysis of Basic Test Data**—The values of the functions  $t/D$ ,  $P_u/D^2$ , and  $P_y/D^2$  shall be calculated from the basic  $t$ ,  $D$ ,  $P_u$ , and  $P_y$  test data obtained on each specimen tested, using the values defined below:

$t$  = measured sheet thickness, inch, for thinnest sheet gage of combination

$D$  = measured hole diameter, inch, for H-type fasteners, nominal shank diameter for S-type fasteners as defined in Section 9.4.1.2

$P_u$  = test ultimate load, pounds per fastener

$P_y$  = test yield load, determined per Section 9.4.1.3.4, pounds per transfer.

A suggested format for reporting the basic data and the computed values of  $t/D$ ,  $P_u/D^2$ , and  $P_y/D^2$  is shown in Figure 9.4.1.5.2(a). The average  $P_u/D^2$  and  $P_y/D^2$  for each fastener diameter at each  $t/D$  shall be indicated in the table.

Computation of $P/D^2$ and $t/D$ from Basic Data									
Test Specimen No.	D Diameter	$D^2$	t Gage	$t/D$	Yield Load, $P_y$	$\frac{P_y}{10^4 D^2}$	Ultimate Load, $P_u$	$\frac{P_u}{10^4 D^2}$	Type of Failure

$t$ ,  $D$ ,  $P_u$ , and  $P_y$ , per Section 9.4.1.5.2.

**Figure 9.4.1.5.2(a). Suggested tabular layout for basic data and computer  $P/D^2$  and  $t/D$  data.**

**MIL-HDBK-5H**  
**1 December 1998**

- (b) Graphical Analysis to Determine Average Ultimate and Yield Load Curves—The general assumption inherent in a  $P/D^2$  versus  $t/D$  analysis procedures is that the dimensions of a fastener system are proportional to the fastener diameter. Therefore, a graph of the average  $P_u/D^2$  and  $P_y/D^2$  values for each  $t/D$  tested is expected to yield a compact band of data points through which single ultimate and yield load curves can be drawn. This portion of the graphical analysis is to establish the all-diameters average curves; or if the data requires, establish more than one average curve for yield and ultimate loads for groups of fastener diameters. The suggested format for these graphical presentations is shown in Figure 9.4.1.5.2(b).


Using different symbols (suitably identified on the graphs) for each fastener diameter, the average  $P_u/D^2$  values for all diameters tested shall be plotted as a function of  $t/D$  on a single graph. Sheet critical and transitional regional failures are to be plotted using symbols with an open form (i.e.,  $\circ$ ,  $\triangle$ , etc.). Fastener shear failures are plotted with the same symbols, but in closed form (i.e.,  $\bullet$ ,  $\blacktriangle$ , etc.). Similarly, the average  $P_y/D^2$  values shall be plotted as a function of  $t/D$  on a single graph. When applicable the data from the two sources shall be identified. In both cases, the resultant collection of data will be analyzed to establish average ultimate-load and yield-load curves. In the case of ultimate-load curve, consideration will be given to all test data for which joint failure was by failure modes other than fastener shear. The resultant average curves may be straight lines, a series of straight lines, or a smooth curve.

In constructing average ultimate- and yield-load curves in the low  $t/D$  region, which may include some data taken where the countersink extends into the second sheet, curves will be projected linearly downward, generally toward the 0-0 coordinate point. Such construction may ignore certain data that suggests the possibility of higher allowables. It is done in this manner to insure conservative design allowables in the near knife-edge condition.

The average curve (yield or ultimate load) represents the average of all plotted results and also represents reasonably the average curve for each diameter tested. The suggested test for reasonableness is that all of the plotted average ultimate load points shall fall in a band  $\pm 10$  percent,  $-5$  percent of average curve for all diameters, and plotted average yield load points shall fall in a band  $\pm 10$  percent of all average curve for all diameters. These lines should appear on the graphs. See Figures 9.4.1.5.2(c) and (d).

Individual graphs for each diameter will be provided that show average yield and ultimate load points at each  $t/D$  tested and lines representing the  $\pm 10$  percent band for yield and  $+10$ ,  $-5$  percent band for ultimate. See Figure 9.4.1.5.2(e). In the event that any of individual diameter average values fall outside the band, the following apply: (1) for fastener diameters whose individual averages lie all or partly above the band, use the average curve obtained for all fasteners, (2) for fastener diameters whose individual averages lie all or partly below the band, use the lowest portions of the individual diameter average curve and the all-diameter average curve.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 9.4.1.5.2(b). Suggested coordinates for graphical presentation of joint allowables data.**



MIL-HDBK-5H  
1 December 1998




Figure 9.4.1.5.2(c). Average ultimate-load analysis.

MIL-HDBK-5H  
1 December 1998




Figure 9.4.1.5.2(d). Average yield-load analysis.

MIL-HDBK-5H  
1 December 1998




Figure 9.4.1.5.2(e). Average test data for 5/32-diameter fastener.

**MIL-HDBK-5H**  
**1 December 1998**

In the event that the dispersion pattern of average  $P_u/D^2$  versus  $t/D$  (or  $P_y/D^2$  versus  $t/D$ ) graphs suggest that two adjacent fastener diameters can be grouped to form one average curve and the remaining average curve, this can be done; however, appropriate percentage bands should be indicated on the various graphs.

On graphs containing all of the average  $P_u/D^2$  versus  $t/D$  data (or  $P_y/D^2$  versus  $t/D$  data), each line should be clearly labeled as to its significance. Also to be shown on these graphs are one or more horizontal lines representing fastener shear strength (more than one line occurs when shear strength in pounds is not proportional to shank area) and allowable sheet or plate ultimate bearing strength and bearing yield strength lines. For materials where bearing properties vary with thickness, bearing strengths plotted shall include the lowest value in the applicable thickness range and the values used shall be the S or A values.

The nonshear-critical test data indicated above will include all data below the fastener shear strength line and all data for joints that failed in sheet bearing, pullout, head failure, combinations of shear, or any other mode of failure, other than shear of fastener shanks, even though same data may lie above the fastener shear strength line. All shear-critical data must be above the fastener shear strength line. The curves shall not extend beyond the tested  $t/D$  range.

- (c) Graphical Analysis to Determine Ultimate and Yield Load Design Allowable Curves—Three graphs are to be provided for this analysis. The first two graphs contain test data and analysis; the third graph contains final design allowable curves as described below.

On a single graph, plot all  $P_u/D^2$  individual test data for all diameters as a function of  $t/D$ , using the same symbols for each diameter as used on the previous graphs. Data from the two sources shall be suitably identified. Draw on the graph the average ultimate load curve, or curves, obtained as described above. Also show the shear cutoff line(s). Construct the tentative design allowable line(s), which is the average curve/1.15. In this construction, the shear cutoff line is not divided by 1.15 since it is the design-allowable curve.

The tentative ultimate-load design-allowable curve(s) is compared with the test data. If the data all lie above the curve(s), the tentative curve is the design allowable curve. If some data lie below the tentative curve(s), they shall be reduced as necessary so that none of the plotted test data points are below the applicable curve. This reduced curve(s) is the ultimate-load design allowable curve, subject to one further possible limitation discussed below. Label all curves with the applicable fastener diameters. See Figure 9.4.1.5.2(f).

On a single graph, plot all of the  $P_y/D^2$  individual test data for all diameters as a function of  $t/D$ , using the same symbols for each diameter as used on previous graphs, identifying both test sources. Show on the graph the average yield-load curve(s) obtained as described in Section 9.4.1.5.2(b). This curve(s) is the yield-load allowable design curve(s) and should be with the applicable fastener diameters. See Figure 9.4.1.5.2(g).

The calculations that lead to tabular presentations in MIL-HDBK-5 are based on design allowable curves described above, subject to one further check. That check is provided in a final graph, included in the analysis. The graph, a sample of which is shown in Figure 9.4.1.5.2(h), contains the design-allowable curves for ultimate and yield load, obtained as described above, without the inclusion of plotted data. Also shown on the graph are sheet-bearing ultimate and sheet-bearing yield lines, which are minimum strengths for the thickness range encompassing the data. If these sheet-bearing lines fall partly below the design curves in the sheet-critical  $t/D$  range, they become the design curve in those regions.

MIL-HDBK-5H  
1 December 1998




Figure 9.4.1.5.2(f). Establishment of design curve for ultimate load.

MIL-HDBK-5H  
1 December 1998




Figure 9.4.1.5.2(g). Establishment of design curve for yield load.

MIL-HDBK-5H  
1 December 1998




Figure 9.4.1.5.2(h). Relationship bearing strengths of sheet to design curves.



**MIL-HDBK-5H****1 December 1998**

All curves on this graph are to be clearly labeled. Those segments of the bearing ultimate line, average ultimate load/1.15 curve(s), and shear cutoff that provide the lower bound and, thus, the design-allowable curve, shall be indicated. Similarly, those segments of the bearing yield line and average yield load curve(s) that provide the lower bound and, thus, the design-allowable curve for the yield load shall be indicated.

**9.4.1.5.3 Calculation of Allowable Loads** — On the basis of lower bound curves described above, the allowable ultimate loads and allowable yield loads shall be calculated for each thickness and diameter combination for which allowable yield loads are required. Allowable loads shall not be calculated for thickness/diameter combinations below the  $t/D$  range tested, or for diameters not tested.

In these calculations, thickness (per Section 9.4.1.6, Note 11), and diameters to be used shall be the nominal shank diameter (per Section 9.4.1.2) for S-Type fasteners and recommended nominal hole diameters (per Section 9.4.1.2) for H-type fasteners. Figure 9.4.1.5.3 shows a suggested format for this set of calculations.

Computation of Allowables from Design Curves								
D	D <sup>2</sup>	t	t/D		P <sub>y</sub> /10 <sup>4</sup> D <sup>2</sup>	P <sub>y</sub>	P <sub>u</sub> /10 <sup>4</sup> D <sup>2</sup>	P <sub>u</sub>

D, t,  $P_u$ , and  $P_y$ , as described in 9.4.1.5.2.

**Figure 9.4.1.5.3. Suggested tabular layout for computing allowables from design curves.**

The analysis of joint allowable load data for the case where data are required for procuring or regulatory agency (not for use in MIL-HDBK-5) for a limited range of sheet thickness and fastener diameter is as follows. An analysis similar to that described in Section 9.4.1.5.2 is required for data over the limited  $t/D$  range evaluated. In the special case where one sheet thickness and one fastener diameter have been tested in accordance with the requirements of Section 9.4.1.4.4, data shall be analyzed as follows: the ultimate-load calculations shall be made utilizing statistical formulas listed in Section 9.4.1.5.1, where the  $k$  value is obtained from Table 9.6.4.1 for the appropriate number of test values ( $n$ ) and 99 percent probability ( $A$ ) value at a 95 percent confidence. These ultimate-load values shall be compared with values computed from bearing ultimate strengths of joint material. In each comparison, the lower of either (1) statistical value computed from joint test data, (2) average ultimate load divided by 1.15, (3) computed bearing strength, or (4) fastener shear strength, shall be the ultimate-load design allowable. The yield-load design allowable shall be selected as the lesser of the average yield load or the value computed from the bearing yield strength of the joint material.

The load values so calculated will be rounded to three or four significant figures as follows:

- (1) Load values less than 1000 will be rounded to 3 figures (load values less than 100, 2 figures).
- (2) Load values greater than 1000 will be rounded to 4 figures. The fourth figure will be a 0 or 5.

**9.4.1.6 Presentation Format** — The final table of allowable loads will be presented in a format suitable for use in MIL-HDBK-5, as illustrated in Figure 9.4.1.6. The following notes apply to the circled numbers in Figure 9.4.1.6.



**MIL-HDBK-5H**  
**1 December 1998**

**Table XXXX(b). Static Joint Strength of Flush Head 6061-T8 Aluminum Alloy Rivets in Machine-⑤ Countersunk Clad ⑥ Aluminum Alloy Sheet**

Rivet Type ⑦ .....	NASXXXX <sup>a</sup> ( $F_{su}$ = AAA ksi) ⑧				
Sheet Material .....	Clad 7075-T6 ⑨				
Rivet Diameter, in. .... (Nominal Hole Diameter, in.) <sup>b</sup> .....	3/32 ⑩ (0.096)	1/8 ⑩ (0.1285)	5/32 ⑩ (0.159)	3/16 ⑩ (0.191)	1/4 ⑩ (0.257)
Ultimate Strength, lbs					
Sheet thickness:					
0.032 .....	⑫ 182 <sup>c</sup>	...	...	...	...
0.040 .....	227	<sup>d</sup> ⑫ 304	...	...	...
0.050 .....	246	381	<sup>d</sup> ⑫ 471	...	...
0.063 .....	...	441	594	<sup>d</sup> ⑫ 714	...
0.071 ⑪ .....	...	...	670	805	<sup>d</sup> ...
0.080 .....	...	...	675	907	... ⑯
0.090 .....	...	...	...	974	⑫ 1375
0.100 .....	...	...	...	...	1525 <sup>d</sup>
0.125 .....	...	...	...	...	1765
Fastener shear strength <sup>c</sup> ⑬ .....	246 ⑭	441 ⑭	675 ⑭	974 ⑭	1765 ⑭
Yield Strength <sup>f</sup> , lbs					
Sheet thickness, in.:					
0.032 .....	119 ⑮	...	...	...	...
0.040 .....	188	224 ⑮	...	...	...
0.050 .....	246	307	349 ⑮	...	...
0.063 .....	...	414	481	539 ⑮	...
0.071 ⑪ .....	...	...	563	637	...
0.080 .....	...	...	655	748	...
0.090 .....	...	...	...	870	1060 ⑮
0.100 .....	...	...	...	...	1230
0.125 .....	...	...	...	...	1640
Fastener tensile strength <sup>g</sup> , lbs ⑰ .....	275	495	755	1090	1975
Head height (ref.), in. ⑱ .....	0.039	0.049	0.059	0.070	0.091

a Data supplied by ABC Corporation and DEF Company, Confirmatory data provided by XYZ Company.

b Fasteners installed in clearance holes (.00XX-.00YY) (Ref. 8.1.X).

c Yield value is less than 2/3 of indicated ultimate strength value.

⑰ d Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.

e Rivet shear strength is documented in NAS XXZZ as AAA ksi.

f Permanent set at yield load: 4% of nominal diameter (Ref. 9.4.1.3.3).

g System maximum tensile strength as tested in steel fixture.

NOTE: See Section 9.4.1.6 for format recommendations indicated by circled numbers.

**Figure 9.4.1.6. Sample format for MIL-HDBK-5 allowable joint strength at 70°F.**

**MIL-HDBK-5H****1 December 1998**

- (1) Omit table number. (Secretariat will assign table number.)
- (2) Head type: 100° Flush Head, 100° Flush Shear Head, Protruding Head, Protruding Shear Head, etc. The shear designation is applied to 100° or protruding head fasteners with heads similar in size to those on Hi-Shear rivets, shear-type lock-bolts, shear-head Hi-Lok, Taper-Lok, or similar fasteners.
- (3) Fastener material: steel, aluminum alloy, Monel, A286, nickel alloy, etc.
- (4) Type of fastener: blind rivet, rivet, bolt, blind bolt, screw, tapered fastener, etc.
- (5) Type of hole: machine countersunk or dimpled. (Omit for protruding head fasteners.)
- (6) Sheet material: consistent with other MIL-HDBK-5 tables.
- (7) "Rivet" for blind or conventional rivets, "Fastener" for other type fasteners.
- (8) Add footnote indicator to part numbers and indicate in a footnote the vendor(s) whose part number is shown if the fastener is not covered by an MS or NAS part number. Include fastener shear strength, material temper, and nut or collar identification.
- (9) Sheet or plate material and heat treatment or condition.
- (10) Nominal fastener diameter. For H-category fasteners, show nominal fractional hole size and, in parentheses, show actual nominal hole size in decimal equivalent. For S-category fasteners, show nominal fractional shank diameter and, in parentheses, show actual fastener shank diameter in decimals [i.e., a 1/8-inch-diameter NAS1740 rivet would be listed as 1/8 (0.144)].
- (11) Select standard sheet and plate thickness from the following:

0.008	0.016	0.032	0.063	0.090	0.160	0.312	0.625
0.010	0.020	0.040	0.071	0.100	0.190	0.375	0.750
0.012	0.025	0.050	0.080	0.125	0.250	0.500	0.875
- (12) Present design allowable values starting at first sheet thickness below knife-edge condition and continuing through the first value equal to or greater than shear strength value. Allowable loads shall not exceed shear strength. Add footnote indicator to ultimate strength values when yield is less than two-thirds of ultimate loads as indicated in Item (17).
- (13) Use the words: "Rivet shear strength" or "Fastener shear strength" conforming to Item (7) nomenclature.
- (14) Fastener single-shear allowable loads in pounds.
- (15) Present yield strength values for the same thickness and diameters for which ultimate strength values are provided.
- (16) For those countersunk head fasteners for which design values are applicable to thin sheet thicknesses, such that the countersink extends into the bottom sheet, a horizontal line shall be drawn in each column of the joint allowables table above the first ultimate strength design

**MIL-HDBK-5H**  
**1 December 1998**

value for which the countersink still is contained within the top sheet. For these cases, footnote (f) will be used, as indicated in Item (17).

- (17) Add all applicable footnotes from the list of standard notes shown below. All footnotes shall be designated by lower case letters.
- (a) “Yield value is less than two-thirds of the indicated ultimate strength value.” (Place footnote indicator next to applicable ultimate strength value.)
  - (b) “These allowables apply to double-dimpled sheets and to the upper sheet dimpled into a machine-countersunk sheet. The thickness of the machine-countersunk sheet must be at least one tabulated gage thicker than the upper dimpled sheet.” (Place footnote indicator next to the words “Ultimate Strength, lbs” at the top of the table.)
  - (c) “Data supplied by ABC Corporation.” When applicable add: “Confirmatory data provided by XYZ Company.” (Place footnote indicator next to part number.)
  - (d) “Shear strength based on areas computed from nominal hole diameters or nominal shank diameters, as applicable (indicate Table 8.1.2(a), or list hole diameters), and  $F_{su}$  = (indicate shear strength).” Indicate the source of the shear strength (MIL or NAS specifications or data analysis). The footnote indicator is placed next to the words “Fastener shear strength” indicated by Item 13 above. The shear strength shall not be greater than the strength required in the controlling specification or standard.
  - (e) “Allowables based on nominal hole diameters of (list hole diameters).” This footnote is used when shear strength is controlled by MIL or NAS specifications, and Table 8.1.2(a) hole diameters are not used.
  - (f) “Values above line are for knife-edge condition and the use of fasteners in this condition is undesirable. The use of knife-edge condition in design of military aircraft requires specific approval of the procuring agency.”
  - (g) “Permanent set at yield load: 4% of nominal diameter (see Section 9.4.1.3.3).”
  - (h) “Fasteners installed in clearance (or interference) holes.” Indicate actual range of fastener-hole fits (interference-clearance) from test program.
  - (i) “System maximum tensile strength as tested in steel fixture.” This footnote is used when table contains fastener tensile strength values. (Place footnote indicator next to the words “Fastener tensile strength, lbs”.)
- (18) When applicable, add line below yield strength section to present “Fastener tensile strength, lbs”. List the appropriate value for each fastener diameter.
- (19) For flush head fasteners, add line below yield strength section to present “Head height (ref.), in.” List appropriate value for each fastener diameter.

**MIL-HDBK-5H****1 December 1998****9.4.1.7 Required Information —**

**9.4.1.7.1 Introduction to New Fastener** — When introducing a new fastener for possible inclusion in MIL-HDBK-5, sponsor shall submit a written request (on company letterhead) to Chairman, MIL-HDBK-5 Coordination Group, providing the following information:

- (1) A description of the fastener such as: (a) type of fastener (driven rivet, blind fastener, swaged collar, etc.), (b) fastener material (alloy and temper), (c) unique or new features, (d) nominal sizes and actual diameters, and (e) part drawings and functional description.
- (2) Reason for fastener usage or intended usage such as: (a) higher strength, (b) higher or lower temperature capability, (c) improved fatigue performance, and (d) lower installed cost.
- (3) Development and use status. (It is not required that the fastener system actually be in use on production airframe structure, but there should be a high level of interest and an intent to use the fastener.) (a) What are current or planned airframe applications? (b) How long has the fastener been produced on a production (nonexperimental) basis? Include preliminary lap joint test data that demonstrates that sufficient diameters and grips are available to conduct a design allowable test program (i.e., data for at least one test for each diameter/grip combination contained in the proposed test plan).
- (4) Specification status. Under what type of specification is the fastener covered (MS, NAS, airframe or fastener company standard)?
- (5) In what sheet or plate material will the fastener be installed? (The proposed allowables should be for the same or similar sheet or plate material that the sponsor is using or plans to use.)
- (6) Shank deformation. Does shank deform during installation? Verification is desirable. (a) If a blind fastener, is it hole filling or nonhole filling? Verification of hole fill is desirable. (b) If a solid shank fastener, are design values to be presented for clearance or interference holes?
- (7) Has the sponsor conducted any testing on the fastener system (especially joint allowables) and will the sponsor provide data to the MIL-HDBK-5 Coordination Group?
- (8) Has the sponsor reviewed (or will the sponsor review) test program plan, actual testing, analysis of data, and specifications?

**9.4.1.7.2 Final Report** — A report will be submitted to MIL-HDBK-5 Coordination Group summarizing the test program, results, analysis, and suggested table of joint allowables for MIL-HDBK-5. The following information will be provided in the report:

- (1) A description of sheet and plate material with heat-treatment details and mechanical property test data for each sheet thickness used in the program in accordance with the requirements of Section 9.4.1.4.5.
- (2) A description of fastener, including drawings and specifications. If the fastener is not covered by a government or industry specification, a copy of an appropriate draft specification will be attached to the report.
- (3) A statement of compliance with MIL-STD-1312, including a detailed statement of any differences from this standard.

**MIL-HDBK-5H**  
**1 December 1998**

- (4) Basic test data [see Figure 9.4.1.5.2(a)], including that required in References 9.4.1.3(a), (b), (c), and representative load deflection curves.
- (5) Values for fastener shear calculation:  $L$ ,  $x$ ,  $k$ ,  $n$ , and either  $\Sigma(x - \bar{x})^2$  or both  $[\Sigma \bar{x}]$  and  $[\Sigma(\bar{x})^2]$  defined in Section 9.4.1.5.1 and fastener shear stress curves, if applicable.
- (6) Designation of allowable shear strength reliability (90 or 99 percent value).
- (7) Calculated  $t/D$ ,  $P_u/D^2$ , and  $P_y/D^2$  values [see Figure 9.4.1.5.2(a) for sample format].
- (8) Seven or more graphs, as required, of  $P/D^2$  versus  $t/D$ , as described in detail in Section 9.4.1.5.2, including the proposed design allowable curves for yield and ultimate load.
- (9) Calculations of allowable loads (see Figure 9.4.1.5.3 for sample format).
- (10) The suggested allowable load tables in the format shown in Section 9.4.1.6.
- (11) Failure identification code for failure of each fastener and/or joint is required, as shown in Figure 9.4.1.7.2. If failure is unique or not covered in the figure, so indicate.
- (12) Off-set used to obtain yield data.
- (13) Draft, in NAS or MS format, of specification for applicable fastener system.

**9.4.1.7.3 Sample Fasteners** — At time of approval of a fastener static joint strength proposal, fastener manufacturer shall submit, to the Chairman, MIL-HDBK-5 Coordination Group, 10 fasteners each from maximum and minimum diameter and grip size tested in the allowables program. These 40 samples shall be from the same production lots as those used in the test program. Samples shall be packaged suitable for storage with full identification of contents on the container. The information may also include any storage time limitation due to coating or lubricant life.


## **9.4.2 FUSION-WELDED JOINTS**

**9.4.2.1 Introduction** — The purpose of this section of the guidelines is to provide a uniform procedure by which reliable design data on welded joints can be developed for use within the aerospace industry. Unlike most other guidelines procedures, for which reasonably complete concurrence has been found among the users of MIL-HDBK-5, those relating to fusion-welding allowables are still subject to interpretation by users in view of their own welding processes. An additional consideration is that fusion-welding allowables are highly process-dependent. Design values will not be presented in MIL-HDBK-5 since their application will be limited to the process represented by data from which the allowables were derived. Consequently, it is the purpose of these guidelines to describe one of possibly many valid procedures, without excluding other procedures that may be authorized for determination of fusion-welding allowables. Basis for this discussion is presented in Reference 9.4.2.1.


These guidelines generally reflect procedures currently used within the aerospace industry. They are applicable to all types of weldable materials and welding processes. However, recommended test coupon configurations and testing methods described herein have been limited to those used in evaluation of butt-type joints.

**MIL-HDBK-5H**  
**1 December 1998**


**1. SHEET FAILURE**




(a) Bearing Deformation of Hole




(b) Tearing of Sheet Allowing Fastener Pull-Through, Head Pull-Through or Nut Collar of Formed Head Pull-Through



(c) Tearing of Sheet at Edge Margin



(d) Shear Out of Sheet Through Edge Margin




(e) Hoop Tension Failure of Sheet


**2. FASTENER HEAD FAILURE**




(a) Head Dished in Tension



(b) Partial Shear Failure of Head



(c) Shear Failure of Head




(d) Tensile Failure at Head to Shank Junction


**Figure 9.4.1.7.2. Failure identification code.**

**MIL-HDBK-5H**  
**1 December 1998**

**3. FASTENER NUT OR  
 FORMED HEAD FAILURE**



**4. FASTENER SHANK FAILURE**



**5. FASTENER SHANK SHEAR FAILURE**



**Shear at Midgrip**

**Figure 9.4.1.7.2. Failure identification code—Continued.**

**MIL-HDBK-5H**  
**1 December 1998**

A distinction is made in properties of weldments between those applicable to design and those used for welding development and process control. These guidelines are concerned with those properties applicable to design.

The approach followed establishes coupon-derived design properties for weldments produced under known and defined conditions. Appropriate analysis must be conducted to adapt coupon-derived data to design of the structure being considered. This is accomplished by determining the state of stress for the component joint, and/or by relating structural hardware test results to coupon-derived design properties. This approach is consistent with techniques used to obtain design data for MIL-HDBK-5, as defined in other sections of these guidelines.

Current military welding specifications do not contain adequate requirements for defining a meaningful population of weldments. Due to this lack of applicable industry-wide specifications, the necessary specification information must be presented with coupon-derived weldment design data.

Throughout the guidelines and in preparation of data, definitions of the American Welding Society will be used for terms relating to welding. The definitions utilized in MIL-HDBK-5 and in other sections of these guidelines will be used for other terms relating to material properties and statistical treatment of data.

**9.4.2.2 Population Definition** — Determination and presentation of properties of weldments requires adequate definition of pertinent welding parameters, including a description of base materials, welding process variables, and weld character. The most significant variables considered are divided into three basic categories: base materials, welding process variables, and weld character (see Figure 9.4.2.2). Variables listed are the minimum that must be identified and required by the specification.

In summary, the primary concern of population definition for weldments is to describe welding conditions in a manner that will assure reproducibility of this same population and will be sufficiently detailed to allow proper data analysis.

**9.4.2.2.1 Base Materials** — Base material variables include appropriate stipulation of alloy, composition form, preweld and postweld heat treat conditions, filler material, and material thickness.

**9.4.2.2.2 Welding Process Variables** — The most difficult aspect is establishing welding variables. The variables must be sufficiently detailed to represent the population of weldments produced, as well as to assure reproducibility of welds within this population. Appropriate selection of variables to be stipulated must be based on an interpretation of their effect on weldment properties and desirability of control. Using the variable of thermal control tooling as an example, it may be found that various types of tooling influence tensile properties of a weld joint by their effect on cooling rate. However, the difficulty in adequately describing thermal-control tooling for more than a single application makes it desirable to treat tooling as a random and uncontrolled variable. This same judgment of effect on properties and desirability of control must be made for each welding process variable.

**9.4.2.2.3 Weld Character** — Appropriate levels of weld character must be prescribed in order to define a population of weldments. This includes a description of internal and external quality levels, as well as minimum joint strength requirements. In most specifications there are several weld classes which identify in detail the quality level requirements. In addition, means of determining weldment characteristics are established by stipulation of both nondestructive and destructive test methods.



**MIL-HDBK-5H**  
**1 December 1998**

<u>BASE MATERIAL</u>			
Alloy, Composition, Form, Pre- and Post-Weld Heat Treat Condition, Material Thickness, Filler Material			
<u>WELDING PROCESS VARIABLES</u>			
<u>Joint Preparation</u>	<u>Tooling</u>	<u>Welding Conditions</u>	<u>Weld Repair</u>
Joint Type	Alignment	Welding Process	Number of Repairs
Edge Preparation	Restraint	Welding Method	Type of Repair
Cleaning	Thermal Control	Welding Position	
		Heat Input (Weld Setting)	
		Preheat	
		Interpass Temperature	
		Shielding Gas	
<u>WELD CHARACTER</u>			
<u>Inspection Methods</u>		<u>Acceptance Levels</u>	
NDT		External	
Visual		Underfill and Undercut	
Radiographic		Cracks	
Magnetic Particle		Pores	
Ultrasonic		Reinforcements	
DT		Internal	
Transverse Tensile Test		Pores	
		Inclusions	
		Cracks	
		Tensile Properties	
		Minimum and Minimum Average	

**Figure 9.4.2.2. Summary of population definition considerations.**

**9.4.2.3 Data Generation** — Data generation involves developing a testing program based on considerations of design data requirements, population definition, subpopulation definition, welding procedures, testing procedures, and minimum test data requirements. Data generation is in two parts:

- (1) Determination of the properties of weld coupons cut from simple panels welded in accordance with a welding process specification.
- (2) Determination of the strength of welded structural components and the relation between the structural component strength and the coupon strength determined in (1).

**9.4.2.3.1 Design Data Requirements (Coupons)** — The type of data required (i.e., tension, shear, fatigue, etc.) and general welding conditions of interest must be established first.

**MIL-HDBK-5H**  
**1 December 1998**

**BASE MATERIAL**

Alloy: 6061 Aluminum per AMS-QQ-A-250/11  
 Form: Sheet  
 Preweld Heat Treat Condition: T4 or T6  
 Postweld Heat Treat Condition: As-Welded  
 Material Thickness: 0.09 inch  
 Filler Material: 4043 per QQ-B-655

**WELDING VARIABLES**

Joint Preparation  
     Joint Type: Butt  
     Edge Preparation: Square Groove  
     Cleaning: Deoxidize, solvent wipe and hand scrape  
 Tooling: None Specified  
 Welding Conditions  
     Process: Mechanized GTA  
 Sequence: Single Pass  
 Position: Flat  
 Heat Input: Not Specified  
 Weld Repair: None

**WELDMENT QUALITY**

Inspection Methods  
     Visual  
     Radiographic, Mil-Std-453  
     Penetrant, Mil-I-6866  
 Acceptance Levels  
     External  
         Weld Beads: Removed Flush  
         Underfill and Undercut: None Allowed  
         Cracks: None Allowed  
         Pores: \*Maximum size 0.02-inch, one per inch  
         Mismatch: 10% of Thickness Maximum  
     Internal  
         Pores and Inclusions: \*Maximum Size 50% T or 0.12 inch whichever is lesser.  
                                     Maximum accumulated amount less than 2% of cross  
                                     section area.

\*Sharp-tailed or crack-like indications not allowed, appropriate acceptance levels will be added.

**Figure 9.4.2.3.2. Example population definition.**

**9.4.2.3.2 Basic Population Definition** — A basic population definition is selected, satisfying the general welding conditions previously established. The procedure for population definition requires a detailed review of applicable welding conditions to select a single population which will provide data consistent with requirements of the specification. The example shown in Figure 9.4.2.3.2 for 6061 aluminum weldments is typical of a basic population definition. In this example, tooling and heat input have not been specified.

**MIL-HDBK-5H**  
**1 December 1998**

**9.4.2.3.3 Subpopulation Definition** — Appropriate subpopulations must be selected. Obvious subpopulations or associated populations in Figure 9.4.2.3.2 would be alternative weld/heat treating sequences, filler materials, welding processes, weld repair, joint thickness, and weld classes (quality level). Selection of these preplanned subpopulations is dependent upon previous knowledge of their potential effect on weldment properties. However, those mentioned are most frequently encountered subpopulations required.

**9.4.2.3.4 Welding Procedure** — The variables defining the selected basic and subpopulations must be controlled within (but no better than) their prescribed ranges during test program welding. This requires welding in accordance with a referenced specification and any additional requirements which may limit the population. The generation of data requires that welding be conducted under production conditions rather than closely controlled laboratory conditions. Data for development of design properties must realistically represent the variation allowed in referenced specification and/or supplemental requirements for each variable.

Weldments from which data are generated should represent the product of several welders, welding machines, and weld setups. It is advisable to select test samples from weldments produced at different times by different operators guided only by specified requirements.


**9.4.2.3.5 Coupon Preparation** — Two types of transverse-weld tensile coupon configurations are recommended. Use flat coupons for materials up to 0.5-inch thickness. For weld joint thicknesses greater than 0.5-inch, round coupons are recommended. These two configurations are shown in Figure 9.4.2.3.5(a) and (b), respectively. Exact specimen dimensions are dependent on thickness of the weldment being evaluated, but geometric similitude is maintained within each type of specimen. Appropriate dimensions are given for the reduced test section of each coupon. The dimensions of gripping areas at each end are optional and may be modified to accommodate standard test fixtures.

Remove the weld heads from all flat coupons unless standards have been established regarding weld reinforcement configuration. When data are required for welds with reinforcements intact, their configurations must be specified. When round coupons are used in thick weldments, location within the weldment becomes an additional variable which must be described and associated with data.


At present, coupon configuration requirements for evaluation of properties other than transverse tensile have not been sufficiently defined to be utilized on an industry-wide basis. Due to the nature of fatigue testing, no specific test configurations are recommended. Configurations selected according to standard base metal practices have been used and may be satisfactory. Weld reinforcements are of particular significance in fatigue testing, and should be removed or specified in detail, together with a description of the coupon used.

Fracture toughness coupons should conform to the latest requirements defined by ASTM E 399, Reference 9.5.1.4.1. Crack location with respect to weldment is of particular importance, and the criteria for validity of specimen must be met. Coupons used for evaluation of other weldment properties, such as fillet-weld shear strength and creep or stress rupture, also require definition in order to be used for design strengths.

**MIL-HDBK-5H**  
**1 December 1998**



**Figure 9.4.2.3.5(a). Flat transverse-weld tensile coupon.**



**Figure 9.4.2.3.5(b). Round transverse-weld tensile coupon.**

**MIL-HDBK-5H**  
**1 December 1998**

**9.4.2.3.6 Testing Procedures**—Availability of accepted test methods for base metal evaluation, as evidenced by federal and ASTM standards, has resulted in their general application to testing of weldments. These standards control test equipment, data accuracy, and loading rates. Reference to existing base metal test methods are generally considered satisfactory for mechanical property testing of weldments except for configuration definition. The testing practice and any deviations should be reported when data samples are generated. In no case may a test result be discarded on the basis of a defect found after final inspection—for example, during post-test examination of fractured surfaces.

**9.4.2.3.7 Minimum Data Requirements**—The data sample must be adequate to determine form and distribution of the population from which it was drawn. If the weldment population definition is broad and allows considerable latitude in the range of parameters defined, it is obvious that larger sample sizes will be required. Certain minimum requirements can be stated, however, based on statistical considerations.

For data to be directly analyzed on a statistical basis, a typical weldment population exhibiting nearly normal distribution characteristics should be represented by a sample containing a minimum of 50 random observations. These observations should include at least 10 subsamples representing random variables such as base material lots, filler material lots, weld processing variables, and weld machine operators and setups.

Direct analysis of a data sample not normally distributed requires at least 300 observations to establish a minimum value on an A-basis. A B-value may be established from the smaller sample defined above. As in the previous case, the observations should be representative of the total population.

At least 10 pairs of measurements should be used for indirect analysis based on derived ratios. These paired observations should represent a range of variables in the specified population. If broad ranges in parameters are involved, additional observations may be required.

**9.4.2.3.8 Sample Requirements**—Due to the number of variables inherent in a welding process, it is advisable to make as broad a sampling as practicable within the population definition. The range of material and processing parameters included in the sample will obviously influence sample size. The total number of observations should be sufficient to identify factors that may be significant within the population, such as joint thickness, weld repair, filler material, and heat-treat condition.

**9.4.2.4 Data Analysis**—Certain concepts have been used for base-metal analyses which lend themselves to analysis techniques for weldments. The procedures described in other sections of the guidelines are used as a basis for analysis of mechanical property data for weldments in order to obtain A- and B-values. The procedures involve either direct statistical analysis of weldment data when sufficient data exist, or an indirect statistical analysis of ratios of paired properties.

The data samples required for direct statistical analysis will usually limit its use to tensile ultimate strength of weldment coupons. The indirect analysis may be used to derive other properties of interest using smaller samples. One example is to derive the minimum shear strength for the cases where only tensile distribution is known; one would operate on the ratio SUS/TUS in this case.

The indirect computation method also provides a tool for rational development of weld factors to be used in translating coupon-derived minimum properties to hardware design. In this case, ratio of hardware failure stress to control coupon failure stress is used.

**9.4.2.5 Data Presentation**—A minimum number of welding conditions should be shown in the data presentation for each basic population of weldments considered. These would include conditions of major significance to potential users of the data. In the population definition discussion, many potential

**MIL-HDBK-5H****1 December 1998**

welding variables were discussed. Among these variables, the following variables are the minimum that should always be specified where applicable:

- (1) Alloys
- (2) Weld-heat-treat conditions
- (3) Filler materials
- (4) Welding processes
- (5) Weld repairs
- (6) Joint thicknesses
- (7) Joint types
- (8) Weld quality levels
- (9) Welding methods, i.e., manual or mechanized.

Since data presented are based on coupon-derived results, it is also necessary to provide comments on use of data in structural design.

**9.4.2.5.1 Additional Information** — When weldment data are presented, they should include comments to aid designers in selecting appropriate welding processes or conditions. In addition, comments alerting a designer to possible fabrication problems or environmental effects should be included. These may include:

- (1) Potential weld heat-treating sequences for the alloy
- (2) Applicable welding methods
- (3) Comments on weldment properties
- (4) Discussion of pertinent welding process variables, such as heat input sensitivity or restrictions, preheat requirements, atmospheric contamination, and significant metallurgical phenomena.

**9.4.2.5.2 Room-Temperature Properties** — Data on room-temperature properties of weldments are presented in tabular form illustrated in Figure 9.4.2.5.2. The figure describes base material, welding variables, and weld character conditions that the data represent, as well as properties of interest. Precautionary notes for use of data in design are presented in footnotes and are discussed in Section 9.4.2.5.4.

**9.4.2.5.3 Data on Effect of Temperature** — A typical effect-of-temperature curve of weldment properties is shown in Figure 9.4.2.5.3. This type of curve should be presented in conjunction with room-temperature properties, referencing welding conditions and precautionary notes of the room-temperature case.

**9.4.2.5.4 Use of Design Data** — In footnotes to coupon-derived design data, it is necessary to present precautionary notes on the use of data in structural design. It is recognized that structures may not fail under load in the same manner as a coupon. This lack of one-to-one correlation may be due to differences either in weldment character resulting from potentially higher variability of production welding, or state of stress. Coupon-structure ratios are used to account for these differences.

The coupon-derived basic weld allowable accounts for a sizeable portion of the variability in welded joints; coupon-structure ratio accounts for the remainder. Since the state of stress (and to some extent, distribution of stress) is accounted for in the coupon-structure ratio, it is probable that each general structural configuration will have a unique coupon-structure ratio. For example, the coupon-structure ratio for a tank which must resist internal pressure would be different from the ratio for a welded joint in a sandwich panel.

**MIL-HDBK-5H**  
**1 December 1998**


Material	Material Thickness	Weld Joint Type	Filler Wire Alloy	Heat Treat After Welding	Properties				Other Properties or → → Welding Conditions
					F <sub>tu</sub> 2		F <sub>tu</sub> 3		
					A	B	A	B	
6061-T4	Up to 0.30 Above 0.30	Sq. Butt Groove	4043 4043	Aged to T6					
6061-T4 6061-T6	Up to 0.30 Above 0.30	Sq. Butt Groove	4043 4043	As- Welded					
6061-F	Up to 0.30 Above 0.30	Sq. Butt Groove	4043 4043	Sol. Ht and Age to T6					

<sup>1</sup> These coupon-derived properties are subject to the usage limitations discussed under "Use of Design Data."

<sup>2</sup> For the following welding conditions -----

<sup>3</sup> For the following welding conditions -----

**Figure 9.4.2.5.2. Typical format for presentation of room-temperature properties of weldments.**



**Figure 9.4.2.5.3. Typical effect of temperature presentation.**



**MIL-HDBK-5H****1 December 1998****9.5 MISCELLANEOUS PROPERTIES****9.5.1 FRACTURE TOUGHNESS**

**9.5.1.1 Introduction** — Fracture toughness of a material is its ability to resist flaw propagation and fracture. This characteristic is a generic quality, somewhat elusive to assess quantitatively. Of several measures of fracture toughness which have evolved for appraising the sensitivity of metals to the presence of small flaws, those based on crack stress or strain analysis appear to be more meaningful for use in design applications. Significant quantification of fracture and flaw propagation behavior of high-strength metals has been achieved through the concept of stress intensity factors. Typical room-temperature values and effect-of-temperature curves for critical stress intensity factors are presented in MIL-HDBK-5 for “information only” where data are available. Basic concepts, testing considerations, and interpretations of fracture toughness are briefly described in the following subsections.

**9.5.1.2 Nomenclature** — The following definitions are provided for discussion of fracture toughness:

**Plane Strain** — The stress state in which all strains occur only in the principal loading plane. No strains occur out of the plane, i.e.,  $\epsilon_z = 0$ , and  $\sigma_z \neq 0$ .

**Plane Stress** — The stress state in which all stresses occur only in the principal loading plane. No stresses occur out of the plane, i.e.,  $\sigma_z = 0$ , and  $\epsilon_z \neq 0$ .

**Stress Intensity Factor** — A physical quantity describing the severity of a flaw in the stress field of a loaded structural element. The gross stress in the material and flaw size are characterized parametrically by the stress intensity factor,

$$K = f\sqrt{a} Y, \text{ ksi} \cdot \text{in.}^{1/2} \quad [9.5.1.2]$$

where

$f$  = stress applied to the gross section including the flaw, ksi

$a$  = measure of flaw size, inches

$Y$  = factor relating component geometry and flaw size, non-dimensional. See Reference 1.4.12.2.1(a) for values.

Roman numeral subscripts I, II, and III on  $K$  are utilized to denote opening, sliding, and tearing modes, respectively, of flaw enlargement. Mode I has been evaluated almost exclusively in current data generation programs.

**Critical Stress Intensity Factor** — A limiting value of the stress intensity factor beyond which continued flaw propagation and/or fracture may be expected. This value is dependent on material and may vary with type of loading and conditions of use.


**Plane-Strain Fracture Toughness** — A generic term now generally adopted for the critical plane-strain stress intensity factor characteristic of plane-strain fracture, symbolically denoted  $K_{Ic}$ . This is because in current fracture testing practices, such as ASTM E 399, specification of the slowly increasing load test of specimen materials in the plane-strain stress state and in opening mode (I) has been dominant.



**MIL-HDBK-5H**  
**1 December 1998**

**Plane-Stress and Transitional Fracture Toughness** — A generic term denoting the critical stress intensity factor associated with fracture behavior under nonplane-strain conditions. Because of plasticity effects and stable crack growth which can be encountered prior to fracture under these conditions, designation of a specific value is dependent on the stage of crack growth detected during testing. Residual strength or apparent fracture toughness is a special case of plane-stress and transitional fracture toughness wherein the reference crack length is the initial pre-existing crack length and subsequent crack growth during the test is neglected.

**9.5.1.3 Significance of Stress State** — A primary factor in fracture behavior of a material is stress state, i.e., plane-stress or plane-strain. In accord with previous definitions, these stress states may be interpreted mechanically as a size or thickness effect within the material. The ideal plane-stress condition occurs in the two-dimensional ( $\sigma_z = 0$ ) case, in which all stresses are restricted to one plane. Material can accommodate extensive plastic deformation adjacent to the flaw prior to fracture, and at fracture exhibit a relatively high K value, as computed by a relationship such as Equation 9.5.1.2. At the opposite extreme is the ideal plane-strain case, in which the third dimension is of infinite extent so that bulk restraint of the material permits no out-of-plane strains. As a result, plastic deformation is restricted and the material fractures in a nearly elastic manner at a relatively low K value. In real materials, these ideal extremes can be closely approximated by “quasi” conditions of “thin” and “thick” bodies. Variation in stress intensity at fracture over these extremes, and the transition stage between, may be represented as in Figure 9.5.1.3.



**Figure 9.5.1.3. Variation of fracture toughness with thickness or stress state (size effect).**

**9.5.1.4 Plane-Strain Fracture Toughness** — For materials which are inherently brittle, or for structure and flaw configurations which are in triaxial tension due to their thickness or bulk restraint, quasi-plane-strain-stress conditions can be obtained in a finite-sized structural element. Triaxial stress state implicit to plane strain effectively embrittles the material by providing maximum restraint against plastic deformation. In this condition, component behavior is essentially elastic until fracture stress is reached and

**MIL-HDBK-5H**  
**1 December 1998**

is readily amenable to analysis in terms of elastic fracture mechanics. This mode of fracture is frequently characteristic of the very high strength metals.

**9.5.1.4.1 Data Generation and Interpretation** — While a wide variety of fracture specimens are available for specified testing objectives, the notch-bend specimen and compact specimen generally offer the greatest convenience and material economics for testing. Details of recommended testing practice are presented in Reference 9.5.1.4.1.

**9.5.1.4.2 Data Presentation** — Room temperature values of  $K_{Ic}$  are tabulated in the introductory comments for each chapter. This table shall include the range (minimum, average, and maximum) in  $K_{Ic}$  values, alloy, product form, heat treat condition, TYS range, product thickness, number of test specimens, number of lots, test specimen thickness range, and grain direction represented by data. Where data are available, effect of temperature on  $K_{Ic}$  is presented graphically in the appropriate alloy section. It is preferable that data incorporated in MIL-HDBK-5 represent a minimum of three specimens each from a minimum of five lots of material for each test direction.

**9.5.1.4.3 Data Requirements** — For materials covered by public specifications that include minimum fracture toughness requirements, at least three specimens each from a minimum of ten lots of material for each test direction (at least 30 observations total) are required for inclusion in MIL-HDBK-5.

**9.5.1.5 Plane-Stress and Transitional-Fracture Toughness** — In ductile materials and relatively thin structural elements, stress state may approach plane-stress conditions. As a result, crack tip plasticity and stable-crack growth may be expected in cracked structural components under load prior to reaching a critical stress-intensity factor value. Furthermore, due to the interaction of plasticity and geometry, characteristic fracture toughness of a material may vary with the stress state, as illustrated in Figure 9.5.1.3.

It is convenient to consider critical stress-intensity factor values, varying with thickness or stress state, as indices of crack-damage resistance. The stress-intensity factor can be used as a consistent measure of crack damage, not only for fracture instability, but also for other levels of crack damage severity, provided the damage is consistently specified and detected. This concept implies that plane-stress and transitional-fracture toughness of metallic materials, while not necessarily a fixed value for the material, is a characteristic value for a given product form, thickness, grain direction, temperature, and strain rate.

**9.5.1.5.1 Data Generation and Interpretation** — Because of the complexity of crack behavior in plane-stress and transitional-stress states, test methods for evaluating material toughness have not been completely standardized; however, several useful methods do exist. Although each configuration generates nearly consistent results when data are properly evaluated, it is recommended that each general flaw configuration be interpreted and applied within its own design context.



*Middle-Tension Panels* — Because it simulates typical crack conditions in thin-sheet structures, the center-through cracked tension panel is a popular testing configuration for evaluating crack behavior. This specimen is illustrated in Figure 9.5.1.5.1(a).

The crack-tip plasticity and slow-stable growth of the crack which are attendant to plane-stress or transitional stress state conditions may cause a deviation from abrupt fracture which is normally associated with crack extension under ideal plane conditions, as illustrated in Figure 9.5.1.5.1(b).

Two limiting damage levels are noted in this figure. Point O is the threshold or onset of slow, stable tear where the crack slowly extends after reaching a threshold stress level. Point C is fracture instability. Both levels of crack damage can be associated with a different stress intensity factor, or damage index, for

**MIL-HDBK-5H**  
**1 December 1998**

product forms and thicknesses of interest. These damage levels can be identified either directly with the  $K$  value as determined from instantaneous stress-crack length coordinate dimensions at these points, or approximately by the coordinates of Point A, which is residual strength, or apparent toughness concept of relating initial crack length to final fracture stress.



**Figure 9.5.1.5.1(a). Middle-tension panel. Figure 9.5.1.5.1(b). Crack growth curve.**

The stress intensity factor,  $K$ , associated with any of these damage levels is determined from Equation 9.5.1.2 where, for this configuration,

$$a = \text{half-length of crack}$$

$$Y = (\pi \sec \pi a/W)^{1/2}.$$

The locus of data points can be represented by a parametric stress-intensity factor curve, as shown in Figure 9.5.1.5.1(c), where each curve represents a different stress-intensity factor formulation. The slow growth curve is superimposed on this figure to illustrate the general relationship between the threshold of stable crack extension, apparent instability, and fracture instability for a typical crack.


Because of experimental difficulties associated with precise detection of threshold and instability points, points O and C, apparent toughness, or residual strength concept of crack damage is used in this presentation. This is the locus of data points "A", noted in Figure 9.5.1.5.1(b), which determine apparent fracture toughness.

$$K_{app} = f_c \left( \pi a_o \sec \pi a_o / W \right)^{1/2} . \quad [9.5.1.5.1]$$

See Reference 9.5.1.5.2 for additional information.

## MIL-HDBK-5H

1 December 1998



**Figure 9.5.1.5.1(c). Stress intensity factor curves as parametric indices of crack damage.**

**9.5.1.5.2 Criteria for Calculating Apparent Toughness**— Since precise definitions of damage mechanisms and their associated instability conditions have not been devised for crack behavior in plane-stress and transitional stress states, only general constraints can be suggested for screening data. To assure that crack damage or fracture instability occurs under predominantly linear elastic conditions the basic criterion is that net section stress must be less than 80 percent of tensile yield strength, TYS, actually representative of that material. Additional criteria may be imposed by stress and boundary constraints characteristic to specific specimen configurations.

*Middle-Tension Panels* — To maintain consistency with the Damage Tolerant Design Handbook, a related strength of materials document for Air Force contractors, a singular criterion,

$$f_c \leq 0.8 \text{ (TYS)} (1 - 2a/W) \quad [9.5.1.5.2]$$

corresponding to the above net section stress requirement, is imposed on fracture data from center-cracked tension panels. Data which satisfy this criterion are used with Equation 9.5.1.5.1 to define apparent fracture toughness.


The validity of elastic fracture in a given set of data may also be substantiated by additional tests conducted to demonstrate that elastic fracture conditions have been achieved and that the associated  $K$  value is nearly constant. For example, once a tentative value of  $K_{app}$  has been determined, it can be confirmed by testing additional panels of larger width (at least 50 percent larger) with the same initial crack length, or by testing the same panel width containing a smaller initial crack length (approximately two-thirds of the

**MIL-HDBK-5H**  
**1 December 1998**

previous). These additional  $K_{app}$  values must confirm to the original tentative value. In any case, it is recommended that tests can be conducted at a variety of crack lengths and panel widths whenever practical to obtain a more complete characterization of panel behavior.

**9.5.1.5.3 Data Presentation** — Plane stress and transitional fracture toughness data and other crack damage information are presented in each alloy chapter. Data are categorized by product form, grain direction, thickness (or thickness range), temperature, and strain rate. The presentation format is dependent upon the flaw and structural configuration as described in the following paragraphs.

*Middle-Tension Panel Data* — Apparent fracture instability data for middle-tension panels are presented on the graphical format of maximum gross stress versus initial crack length as illustrated in Figure 9.5.1.5.3. These data plots are presented as information and not as design allowables; hence, additional testing is necessary to substantiate design allowables over the range of crack lengths of interest.



**Figure 9.5.1.5.3. Format for the presentation of middle-tension panel data.**

The data in such graphical display satisfy the screening criterion of Equation 9.5.1.5.2.

The apparent stability fracture toughness value  $K_{app}$  associated with each curve is a simple average of test values determined according to Equation 9.5.1.5.1.

The average apparent toughness curve is presented over a range extending from the short crack length associated with a net section stress of 80 percent of tensile yield strength to either the largest crack length contained in the data, or one-third the panel width, whichever is greater.

Since slow, stable tear may occur during the loading of a cracked panel, an approximate measure of crack extension possible prior to fracture is useful to assess conditions of fracture instability. Where data are available, the average ratio,  $\Delta(2a)/(2a_0)$ , of crack extension prior to fracture to initial crack length is indicated in the field of the graphical display. This ratio is determined through

$$\frac{\Delta 2a}{2a_0} = \frac{2a_c - 2a_0}{2a_0} = \frac{a_c}{a_0} - 1 = \left( \frac{K_c^2}{K_{app}^2} \right) - 1,$$

**MIL-HDBK-5H**  
**1 December 1998**

where

$$K_c = f_c (\pi a_c \sec \pi a_c / W)^{1/2}$$

is the average stress intensity factor associated with critical fracture instability as determined by the reporting investigator.

Where data for a material include a thickness range from essentially plane stress to plane strain fracture toughness data will be summarized also as a display of thickness effect similar to Figure 9.5.1.3. From this figure, K values for the appropriate thickness, t, can be selected and residual strength curve similar to Figure 9.5.1.5.3 can be constructed.

At present, since these are not design allowable data, requirements on the quantity of information necessary will not be specified. Data displays will be prepared for those materials, product forms and thicknesses where a sufficient number of tests at various crack and specimen sizes are available to establish a distinct trend. Correlative information will be appended below such graphical displays to indicate range of test panel sizes, crack lengths, and number of heats or lots of the material from which determination of  $K_{app}$  was determined.

**9.5.1.5.4 Required Reporting and Documentation** — To assure proper evaluation of plane stress and traditional fracture toughness data, adequate documentation of test results must be included with any data submittals for MIL-HDBK-5. The minimum quantity of experimental information considered appropriate for data proposals on the subject is described in the following subsections.

*Middle-Tension Panels* — To identify the material tested, it is necessary to report alloy temper, product form, and grain directions being tested. Reference tensile properties, actually representative of specimen or material lot (i.e., not specification or MIL-HDBK-5 A and B values), are also necessary information. These shall include yield strength, ultimate strength, and elongation.

The specimen configuration is described by measured thickness, panel width, and free length between grips. The minimum flaw details to be reported are fatigue stress levels used in generating the fatigue crack and length of the fatigue crack existent prior to the rising load fracture test.

The test procedure shall be described briefly, identifying environment (temperature, humidity, salinity, etc.), loading rate, and the mode of buckling restraint.

The report of test results shall include maximum load and stress, and estimated critical crack length (indicate method of detection, such as visual observation, film record, or compliance calibration). It is recommended that whenever practical, a record of load versus crack length be obtained to assess slow stable crack extension prior to fracture.

**MIL-HDBK-5H**  
**1 December 1998**

## **9.6 STATISTICAL PROCEDURES AND TABLES**

This section includes a number of statistical aids for use in preparation of data for MIL-HDBK-5. These aids are intended to supplement, not to replace, the basic procedure described elsewhere in these Guidelines.

Many different statistical techniques may be useful in analysis of mechanical-property data. This section presents brief descriptions of procedures that will be used most frequently in this application. More detailed descriptions of these and other statistical techniques and tables in their various forms can be found in a number of workbooks and texts; Reference 9.6 is a particularly useful one.

When procedures other than those described below are employed in preparation of data proposals, they should be described adequately in the proposal.

### **9.6.1 GOODNESS-OF-FIT TESTS**

**9.6.1.1 Introduction** — The computational procedure selected to establish design-allowable values by statistical techniques is dependent upon distribution of strength measurements in the available sample. The most frequently used parametric procedures involve the use of normal distributions or three-parameter Weibull distributions. As noted previously, references to normal or Weibull distributions shall be interpreted as applying either to original measurements or to an appropriate transformation of them. This section contains a discussion and illustration of methods used to establish whether or not a population follows a normal or Weibull distribution.

Two goodness-of-fit test procedures are described below. The purpose of each is to indicate whether an initial distribution assumption should be rejected. The methods presented are based on the “Anderson-Darling” goodness-of-fit test statistic for testing normality (in Section 9.6.1.2) or three-parameter Weibullness (in Section 9.6.1.4). These tests are objective and indicate (at 5 percent risk of error) whether the sample is drawn from the tested distribution. Unfortunately, these tests may reject the hypothesis of normality or Weibullness even though the distribution may provide a reasonable approximation within the lower tail. Consequently, some subjective reasoning is employed after using a goodness-of-fit test.

After a goodness-of-fit test has been performed (especially if the distributional assumption has been rejected), it is often useful to form a cumulative probability plot of data to graphically illustrate the degree to which the assumed distribution fits the data. Methods for development of both normal probability plots (in Section 9.6.1.3) and Weibull probability plots (in Section 9.6.1.5) are presented.

In what follows, sample size is denoted by  $n$ , sample observations by  $X_1, \dots, X_n$ , and sample observations ordered from least to greatest by  $X_{(1)}, \dots, X_{(n)}$ . Obviously, the assumption is made that the data are ungrouped.

**9.6.1.2 “Anderson-Darling” Test for Normality** — The “Anderson-Darling” test for normality is used to determine whether the curve which fits a given set of data can be approximated by a normal curve. The essence of the test is a numerical comparison of the cumulative distribution function for observed data with that for the fitted normal curve over the entire range of the property being measured. Let

$$Z_{(i)} = (X_{(i)} - \bar{X})/s \quad i = 1, \dots, n$$

**MIL-HDBK-5H**  
**1 December 1998**

where  $X_{(i)}$  is the  $i^{\text{th}}$  smallest sample observation,  $\bar{X}$  is the sample average, and  $s$  is the sample standard deviation. Equations for computing sample statistics are presented in Section 9.2.2.3.

The “Anderson-Darling” test statistic is

$$AD = \left[ \sum_{i=1}^n \frac{1 - 2i}{n} \left[ \ln \left( F_0(Z_{(i)}) \right) + \ln \left( 1 - F_0(Z_{(n+1-i)}) \right) \right] \right] - n$$

where  $F_0$  is the standard normal distribution function\*. If

$$AD > 0.752 / (1 + 0.75/n + 2.25/n^2)$$

one may conclude (at 5 percent risk of error) that the population from which the sample was drawn is not normally distributed. Otherwise, the hypothesis that the population is normally distributed is not rejected. For further information on this test procedure, see References 9.6.1.2(a) and (b).

The same procedure can be used to test the normality of the residuals

$$e_i = y_i - (a + bx_i) \quad i = 1, \dots, n$$

from a regression (see Section 9.6.3) assuming uniformity of variance of the residuals over the range of the independent variable. When calculating the test statistic AD, define

$$Z_{(i)} = e_{(i)} / s_y \quad i = 1, \dots, n$$

where  $e_{(i)}$ ,  $i = 1, \dots, n$  are the ordered residuals from smallest to largest and  $s_y$  is the root mean square error of the regression defined in Section 9.6.3.1. The justification for this procedure may be found in Reference 9.6.1.2(c).

**9.6.1.3 Normal Probability Plot** — To graphically illustrate the degree to which a normal distribution fits a set of data, the use of arithmetic probability paper is recommended. Logarithmic probability paper may be used to determine whether the distribution of data could be made normal by logarithmic transformation. One axis is scaled in units of the property measured, and the other is a non-linear scale of probability.

If there are relatively few data points, all of them may be plotted individually on the chart. With larger samples, it is only necessary to plot enough points to define the curve.

The rank of each point selected for plotting is equal to the number of lower test points plus plotted point plus one half the number of other points equal to plotted point. Cumulative probability (P), in percent, is equal to the rank times 100, divided by one more than the total number of test points:

---

\* The standard normal distribution function  $F_0$  is that function such that  $F_0(x)$  is equal to the area under the standard normal curve to the left of the value  $x$ .



**MIL-HDBK-5H**  
**1 December 1998**

$$P \text{ (in percent)} = \frac{(\text{rank})(100)}{n + 1} \quad [9.6.1.3]$$

The measured value of each test point is plotted versus its cumulative probability and a straight line is drawn to represent the normal distribution. This line may be established by plotting any two points from the normal distribution curve for  $\bar{X}$  and  $s$  (for example,  $\bar{X} - 3s$  at 0.13 percent probability, and  $\bar{X} + 3s$  at 99.87 percent probability) and connecting these two points.

The plotted points should finally be compared with the line to determine whether there appears to be a reasonably good fit. With sample sizes on the order of 100 test points, only those points lying between about 10 and 90 percent probability should be considered in making this evaluation. With sample sizes of 1000 test points, these limits can be extended to about 1 and 99 percent.

If normal probability paper is unavailable, a normal probability plot may be formed by plotting the measured value of each test point versus  $\bar{X} + s F_o^{-1}(P/100)$  where  $F_o^{-1}$  is the inverse standard normal cumulative distribution function.\* The line representing the fitted normal distribution is the line passing through the points with equal horizontal and vertical coordinates. If the horizontal axis is labeled with cumulative probabilities (P values) rather than  $F_o^{-1}(P/100)$  values, the plot will be identical to a plot formed on normal probability paper.

**9.6.1.4 Modified “Anderson-Darling” Test for Weibullness** — The “Anderson-Darling” test for three-parameter Weibullness is used to determine whether the curve which fits a given set of data can be approximated by a three-parameter Weibull curve. The essence of the test is a numerical comparison of the cumulative distribution function for observed data with that for a fitted Weibull curve over the entire range of property being measured. This test differs from the original version of the Anderson-Darling test in that it emphasizes the lower tail. This method can be applied with complete or censored data.

The first two steps produce estimates of the parameters of a three-parameter Weibull distribution. Be sure to acknowledge the appropriate degree of censoring in computing the threshold, shape, and scale parameters as described in sections 9.6.5.1 and 9.6.5.2. Using the procedure outlined in 9.6.5.1, compute the threshold for the goodness-of-fit test,  $\tau_{50}$ . Then, using the method described in 9.6.5.2, compute the maximum likelihood estimates of the shape and scale parameters for  $\{X_{(i)} - \tau_{50} : i=1, \dots, r\}$  where  $r$  equals  $n$  for the uncensored data and  $r$  represents the smallest integer greater than or equal to  $4n/5$  for 20 percent censoring and  $n/2$  for 50 percent censoring. Denote these estimates by  $\beta_{50}$  and  $\alpha_{50}$ , respectively. Calculate the (censored or uncensored) A-D statistic by the following steps. For  $i=1, \dots, r$ , let

$$F_i = 1 - \exp \left( - \left( \frac{X_{(i)} - \tau_{50}}{\alpha_{50}} \right)^{\beta_{50}} \right),$$

let  $F_{n+1} = 1$ , and let

$$C_i = \frac{2i-1}{n}.$$

---

\* The point  $F_o^{-1}(P/100)$  is that value such that the area under the standard normal curve to the left of  $F_o^{-1}(P/100)$  is  $P/100$ .

**MIL-HDBK-5H**  
**1 December 1998**

Define the A-D statistic as

$$AD = -\sum_{i=1}^r (C_i \ln F_i - 2F_i) + \frac{r^2}{n} \ln F_{r+1} - 2r F_{r+1} + \frac{n}{2} F_{r+1}^2 - \frac{n}{2} F_1^2.$$

If

$$AD \geq \begin{cases} 0.3951 + 4.186 \times 10^{-5} n & \text{(Uncensored)} \\ 0.2603 + 4.182 \times 10^{-5} n & \text{(20 percent censored)} \\ 0.1761 + 1.842 \times 10^{-5} n & \text{(50 percent censored)} \end{cases} \quad [9.6.1.4]$$

one may conclude (at 5 percent risk of error) that the population from which the sample was drawn is not a three-parameter Weibull population. Otherwise, the hypothesis that the population is a three-parameter Weibull population is not rejected. Equation 9.6.1.4 was derived under the assumption that the threshold parameter is estimated, not known. For further information on this test procedure, see Reference 9.6.1.2(a).

**9.6.1.5 Weibull Probability Plot** — To graphically illustrate the degree to which a three-parameter Weibull distribution fits a set of data, the following procedure for creation of a Weibull probability plot is recommended. If there are relatively few data points, all of them may be plotted individually. With larger samples, it is only necessary to plot enough points to define the curve.

The rank of each point selected for plotting is the number of lower test points plus the plotted point plus one-half the number of other test points equal to the plotted point. Its cumulative probability,  $P$  (in percent), is equal to the rank multiplied by 100, divided by one more than the total number of test points:

$$P \text{ (in percent)} = \frac{(\text{rank})(100)}{n + 1}$$

The measured value of each test point is plotted versus  $F^{-1}(P/100)$  where

$$F^{-1}(P/100) = \tau_{50} + \alpha_{50} \left[ -\ln(1 - (P/100)) \right]^{\frac{1}{\beta_{50}}}$$

and  $\tau_{50}$ ,  $\alpha_{50}$ , and  $\beta_{50}$  are population parameter estimates obtained according to the procedures outlined in Section 9.6.5. A straight line is drawn to represent the fitted Weibull distribution. This line may be established by plotting any two points with equal vertical and horizontal coordinates and drawing a line through these two points. If the horizontal axis is labeled with cumulative probabilities rather than  $F^{-1}$  values, the plot will take the same form as the normal probability plot of Section 9.6.1.3.

The plotted points should finally be compared with the line to determine whether there appears to be a reasonably good fit. With sample sizes on the order of 100 test points, only those points lying between about 10 and 90 percent probability should be considered in making this evaluation. With sample sizes of 1000 test points, these limits can be extended to about 1 and 99 percent.

**9.6.1.6 Identifying Proper Backoff for Weibull Method** — Begin with the estimates  $\tau_{50}$ ,  $\alpha_{50}$ , and  $\beta_{50}$  obtained according to the procedures outlined in Section 9.6.5. Let  $F_{\tau}(x)$  represent the cumula-

**MIL-HDBK-5H**  
**1 December 1998**

tive distribution function of the three-parameter Weibull distribution with threshold parameter  $\tau$ , and scale and shape parameters,  $\alpha_{50}$  and  $\beta_{50}$ , respectively:

$$F_{\tau}(x) = 1 - \exp\left(-\left(\frac{x-\tau}{\alpha_{50}}\right)^{\beta_{50}}\right).$$

Define the special “backoff” Anderson Darling statistic by

$$ADB(\tau) = n \sum_{i=1}^n \left[ \left( \frac{i}{n} \right)^2 (\ln b_i - \ln a_i) - \frac{2i}{n} (b_i - a_i) + \frac{1}{2} (b_i^2 - a_i^2) \right],$$

where  $a_i = \min\{F_{\tau}(x_{(i)}), i/n\}$ ,  $b_i = \min\{F_{\tau}(x_{(i+1)}), i/n\}$  for  $i < n$ , and  $b_n = 1$ . Let  $\tau_{\text{backoff}}$  be the smallest value among 0.1, 0.2, 0.3, 0.4, and 0.5 such that

$$ADB(\tau_{50} - \tau_{\text{backoff}}) < 0.0359 + 1.2 \times 10^{-5} n. \quad [9.6.1.5]$$

If none of the five values satisfies Equation 9.6.1.5, the backoff procedure cannot be used to compute  $T_{99}$  and  $T_{90}$ . Otherwise,  $\tau_{\text{backoff}}$  is subtracted from  $T_{99}$  and  $T_{90}$  as calculated from the complete sample.

## 9.6.2 TESTS OF SIGNIFICANCE

**9.6.2.1 Introduction** — A test of significance is employed to make a decision on a statistical basis. In this section, three tests (“F” test, “t” test, and k-sample Anderson-Darling test) are described for use in determining whether the populations from which two or more samples are drawn are identical.

Assuming an underlying normal distribution, “F” and “t” tests may be used in the case of two samples. The “F” test is used first to determine whether the two sample variances differ significantly or not (with a 5 percent risk of error). If the two sample variances do not differ significantly, the “t” test is used to determine whether the two sample means differ significantly. If either the two sample variances or the two sample means differ significantly (with a 5 percent risk of error), one may conclude (with a 9.75 percent joint risk error) that the populations from which the two samples were drawn are not identical. Otherwise, the hypothesis that the two populations are identical is not rejected. The tests given are exact when:

- (1) The observations within each sample are taken randomly from a single population of possible observations, and
- (2) The characteristic measured is normally distributed within this population.

To carry out a similar procedure without requiring the assumption of an underlying normal distribution, or if three or more samples are to be compared, the k-sample Anderson-Darling test should be employed. This test is a nonparametric procedure and simply tests the hypothesis that populations from which the samples are drawn are identical.

**9.6.2.2 Definitions** — Location and dispersion parameters are defined in Section 9.2.2.3, and these terms are used in various parts of the Guidelines. The following definitions apply specifically to tests in this section:

**MIL-HDBK-5H****1 December 1998**

Significance Level (As Used Here) — Risk of concluding that two samples were drawn from different populations when, in fact, they were drawn from the same population. A significance level of  $\alpha = 0.05$  is employed through these Guidelines.\*

Confidence Interval Estimate — Range of values, computed with the sample that is expected to include the population variance or mean.

Degrees of Freedom — Number of independent comparisons afforded by a sample.

**9.6.2.3 The F Test** — The F test is used to determine whether the strength of two products differs with regard to variability.

Consider two products, A and B. These might represent two different processes, thickness ranges, or test directions. The statistics for the samples drawn from these products are:

	<u>Product A</u>	<u>Product B</u>
Sample size	$n_A$	$n_B$
Sample standard deviation	$s_A$	$s_B$
Sample mean	$\bar{X}_A$	$\bar{X}_B$

F is the ratio of the two sample variances, thus,

$$F = s_A^2 / s_B^2 \quad [9.6.2.3]$$

If the true variances of Products A and B are identical at a significance level of  $\alpha = 0.05$ , F should lie within the interval defined by

$F_{0.975}$  (for  $n_A - 1$  and  $n_B - 1$  degrees of freedom),

and

$1/F_{0.975}$  (for  $n_B - 1$  and  $n_A - 1$  degrees for freedom).\*\*

If F does not lie within this interval, it can be concluded that the two products differ with regard to their variability. Values of  $F_{0.975}$  are presented in Table 9.6.4.4.

**9.6.2.3.1 Example of Test Computation** — The following sample statistics are reported:

	<u>Product A</u>	<u>Product B</u>
Sample size	20	30
Sample standard deviation, ksi	4.0	5.0
Sample mean, ksi	100.0	102.0

---

\* This is appropriate, since a confidence level  $1 - \alpha = 0.95$  is used in establishing  $T_{99}$  and  $T_{90}$  values.

\*\* Since a two-sided interval is being defined for the population variance, the fractile of the F distribution corresponding to  $1 - \alpha/2$  should be used, i.e.,  $F_{0.975}$ .

**MIL-HDBK-5H**  
**1 December 1998**

Perform an F test as follows:

$$F = s_A^2 / s_B^2 = 4^2 / 5^2 = 0.64$$

$$df = n_A - 1 = 19$$

$$n_B - 1 = 29$$

$$F_{0.975 (19,29)} = 2.2$$

$$1/F_{0.975 (29,19)} = 1/2.40 = 0.42$$

} From Table 9.6.4.4

Since 0.64 lies within the interval of 0.42 to 2.23 one can conclude that there is no reason to believe that Products A and B differ with regard to their variability.

**9.6.2.4 The t Test** — The t test is used to determine whether two products differ with regard to average strength. If they do, one may conclude that the two products do not belong to the same population.

In making the t test, it is assumed that the variances of two products are nearly equal, as first determined from the F test. If the F test shows that the variances are significantly different, there is no need to conduct the t test.

Consider the same products, A and B. The statistics for samples drawn from these products are:

	<u>Product A</u>	<u>Product B</u>
Sample size	$n_A$	$n_B$
Sample standard deviation	$s_A$	$s_B$
Sample mean	$\bar{X}_A$	$\bar{X}_B$

$D_{\bar{x}}$  is the absolute difference between the two sample means.

$$D_{\bar{x}} = | \bar{X}_A - \bar{X}_B | \quad [9.6.2.4(a)]$$

If the true means of products A and B are identical,  $D_{\bar{x}}$  should not exceed  $u$ , which is determined as indicated by the following equation for a significance level of  $\alpha = 0.05$ .

$$u = t_{0.975} s_p \sqrt{\frac{n_A + n_B}{n_A n_B}} \quad [9.6.2.4(b)]$$

where

$t_{0.975}$  has  $n_A + n_B - 2$  degrees of freedom\*

---

\* Since a two-sided interval is being defined from the population means, the fractile of the t distribution corresponding to  $1-\alpha/2$  should be used, i.e.,  $t_{0.975}$ .

**MIL-HDBK-5H**  
**1 December 1998**

and

$$s_p = \sqrt{\frac{(n_A - 1)s_A^2 + (n_B - 1)s_B^2}{n_A + n_B - 2}} \quad [9.6.2.4(c)]$$

Values of  $t_{0.975}$  are found in Table 9.6.4.5.

**9.6.2.4.1 Example of Test Computation**—The following sample statistics are the same as those in Section 9.6.2.3.1:

	<u>Product A</u>	<u>Product B</u>
Sample size	20	30
Sample standard deviation, ksi	4.0	5.0
Sample mean, ksi	100.0	102.0

It was determined in Section 9.6.2.3.1 that the variances of Products A and B do not differ significantly. The t test computations to test the sample means are:

$$df = n_A + n_B - 2 = 48$$

$t_{0.975}$  (for 48 df) = 2.011 (from Table 9.6.4.5)

$$s_p = \sqrt{\frac{(n_A - 1)s_A^2 + (n_B - 1)s_B^2}{n_A + n_B - 2}} = \sqrt{\frac{(19)(4)^2 + (29)(5)^2}{48}} = 4.63 \text{ ksi}$$

$$\sqrt{\frac{n_A + n_B}{n_A n_B}} = \sqrt{\frac{20 + 30}{(20)(30)}} = 0.2887$$

$$u = t_{0.975} s_p \sqrt{\frac{n_A + n_B}{n_A n_B}} = (2.011)(4.63)(0.2887) = 2.7 \text{ ksi}$$

$$D_{\bar{x}} = |\bar{X}_A - \bar{X}_B| = 2.0 \text{ ksi}$$

Since  $D_{\bar{x}}$  (2.0) is not greater than  $u$  (2.7), it may be concluded that there is no reason to believe that Products A and B differ with regard to their average strength. On the basis of both tests in this example, the conclusion would be that the two products were drawn from the same population.

**9.6.2.5 The k-Sample Anderson-Darling Test**—The k-sample Anderson-Darling test is designed to test the hypothesis that populations from which two or more independent random samples were drawn are identical. The test is appropriately applied to determine whether two or more products differ with regard to strength distributions. The test is a nonparametric statistical procedure and, thus, requires no assumptions other than the samples are true independent random samples from their respective populations.

**MIL-HDBK-5H**  
**1 December 1998**

Consider the products  $A_1, A_2, \dots, A_k$ . Let  $X_{11}, X_{12}, \dots, X_{1n_1}$  denote a sample of  $n_1$  data points from product  $A_1$ , let  $X_{21}, X_{22}, \dots, X_{2n_2}$  denote a sample of the  $n_2$  data points from product  $A_2$ , and so forth. Furthermore, let  $N = n_1 + n_2 + \dots + n_k$  represent the total number of data points in the combined samples.

Let  $L$  denote the total number of distinct data points in the combined samples and  $Z_{(1)}, Z_{(2)}, \dots, Z_{(L)}$  denote the distinct values in the combined data set ordered from least to greatest. The  $k$ -sample Anderson-Darling statistic is defined by

$$ADK = \frac{N-1}{N^2(k-1)} \sum_{i=1}^k \left[ \frac{1}{n_i} \sum_{j=1}^L h_j \frac{(NF_{ij} - n_i H_j)^2}{H_j(N - H_j) - Nh_j/4} \right]$$

where

$h_j$  = the number of values in the combined samples equal to  $Z_{(j)}$

$H_j$  = the number of values in the combined samples less than  $Z_{(j)}$  plus one-half the number of values in the combined samples equal to  $Z_{(j)}$

and

$F_{ij}$  = the number of values in sample corresponding to product  $A_i$  which are less than  $Z_{(j)}$  plus one-half the number of values in the sample corresponding to product  $A_i$  which are equal to  $Z_{(j)}$ .

Under the hypothesis of no differences in the sampled populations, the mean of ADK is approximately one and the variance is approximately

$$\sigma_N^2 = \text{Var}(ADK) = \frac{aN^3 + bN^2 + cN + d}{(k-1)^2 (N-1) (N-2) (N-3)}$$

with

$$\begin{aligned} a &= (4g - 6)(k - 1) + (10 - 6g)S \\ b &= (2g - 4)k^2 + 8Tk + (2g - 14T - 4)S - 8T + 4g - 6 \\ c &= (6T + 2g - 2)k^2 + (4T - 4g + 6)k + (2T - 6)S + 4T \\ d &= (2T + 6)k^2 - 4Tk \end{aligned}$$

where

$$S = \sum_{i=1}^k \frac{1}{n_i}$$

**MIL-HDBK-5H**  
**1 December 1998**

$$T = \sum_{i=1}^{N-1} \frac{1}{i}$$

and

$$g = \sum_{i=1}^{N-2} \sum_{j=i+1}^{N-1} \frac{1}{(N-i)j}$$

If

$$ADK \geq 1 + \sigma_N \left[ 1.645 + \frac{0.678}{\sqrt{k-1}} - \frac{0.362}{k-1} \right]$$

one may conclude (with a 5 percent risk error) that samples were drawn from different populations. Otherwise, the hypothesis that samples were selected from identical populations is not rejected. For more information on the k-sample Anderson-Darling test, see Reference 9.6.2.5.

**9.6.3 DATA-REGRESSION TECHNIQUES** — When it is suspected that the average of one measured value varies linearly or curvilinearly with some other measured value, a regression is often employed to investigate and describe the relationship between the two quantities. Examples are effect of thickness on TUS, effect of temperature on TUS, and effect of stress on cycles or time to rupture. Mathematical techniques for performing a simple linear regression analysis are contained in Section 9.6.3.1. Mathematical techniques for performing a quadratic regression analysis are contained in 9.6.3.2. Statistical tests to determine whether or not a straight line adequately describes the data are described in Section 9.6.3.3 and a test for equality of several regression lines is presented in Section 9.6.3.4. An example is presented in Section 9.6.3.5 using hypothetical data to illustrate many of the regression calculations. Figure 9.6.3 provides guidance in choosing an appropriate regression analysis to use for calculating design allowables.

Since least-squares regression is a general analytical tool used for multiple purposes, further instructions for use of the computed best-fit equation and standard deviation are given elsewhere in the Guidelines. It should be pointed out, however, that this technique is sometimes employed with transformed variables; that is, it may be necessary to work with  $\log(TUS)$ ,  $t^2$ , or  $1/(T + 460)$ , for example. When this is the case, the analyst must remember to transform variables back to the original engineering units after final computations.

**9.6.3.1 Least-Squares Linear Regressions** — Linear regression is appropriate when there is an approximate linear relationship between two measurable characteristics. Such a relationship is expressed algebraically by an equation that, in the case of two measurable characteristics  $x$  and  $y$ , has the form



MIL-HDBK-5H  
1 December 1998




Figure 9.6.3. General procedures for performing a regression analysis in order to calculate design allowables.

**MIL-HDBK-5H**  
**1 December 1998**

$$y = \alpha + \beta x + \epsilon \quad [9.6.3.1(a)]$$

where

$x$  = independent variable

$y$  = dependent variable

$\alpha$  = true intercept of the regression equation

$\beta$  = true slope of the regression equation

$\epsilon$  = measurement or experimental error by which  $y$  differs from the ideal linear relationship.

Aside from the error term,  $\epsilon$ , this is the equation of a straight line. The parameter  $\alpha$  determines the point where this line intersects the  $y$ -axis, and the  $\beta$  represents its slope. The variable  $x$  and  $y$  may represent either direct measurements or some transformation measurements of the characteristics under consideration.

Knowing or assuming such an approximate linear relationship, the problem becomes one of estimating the parameters  $\alpha$  and  $\beta$  of the regression equations. It is necessary to have a random sample consisting of  $n$  pairs of observations, which is denoted by  $(x_1, y_1), (x_2, y_2), \dots, (x_n, y_n)$ . Such a sample can be represented graphically by  $n$  points plotted on a coordinate system, in which  $x$  is plotted horizontally and  $y$  vertically. A subjective solution can be obtained by drawing a line that, by visual inspection, appears to fit the points satisfactorily. An objective solution is given by the method of least squares.

The method of least squares is a numerical procedure for obtaining a line having the property that the sum of squares of vertical deviations of the sample points from this line is less than that for any other line. In this analysis, the least-squares line is represented by the equation

$$\hat{y} = a + bx \quad , \quad [9.6.3.1(b)]$$

in which

$\hat{y}$  = predicted value of  $y$  for any value of  $x$   
 $a$  and  $b$  = estimates of the parameters  $\alpha$  and  $\beta$  in the true regression equation obtained by the least squares method presented below.

It can be shown with the aid of calculus that the values of  $a$  and  $b$  that minimize the sum of squares of the vertical deviations are given by the formulas:

$$a = \frac{\sum y - b \sum x}{n} \quad [9.6.3.1(c)]$$

$$b = \frac{S_{xy}}{S_{xx}} \quad [9.6.3.1(d)]$$

where

$$S_{xy} = \sum xy - \frac{\sum x \sum y}{n} \quad , \quad [9.6.3.1(e)]$$

and

**MIL-HDBK-5H**  
**1 December 1998**

$$S_{xx} = \sum x^2 - \frac{(\sum x)^2}{n} \quad [9.6.3.1(f)]$$

The root mean square error of y is expressed as

$$S_y = \sqrt{\frac{\sum (y - \hat{y})^2}{n - 2}} \quad [9.6.3.1(g)]$$

where  $\hat{y}$  is the predicted value of y defined above. This quantity is an estimate of the standard deviation of the distribution of y about the regression line. A convenient computational formula for  $s_y$  is

$$s_y = \sqrt{\frac{S_{yy} - b^2 S_{xx}}{n - 2}} \quad [9.6.3.1(h)]$$

where

$$S_{yy} = \sum y^2 - \frac{(\sum y)^2}{n} \quad [9.6.3.1(i)]$$

The quantity  $R^2 = (b^2 S_{xx})/S_{yy}$  measures the proportion of total variation in the y data, about its average, that is explained by the regression. An  $R^2$  equal to 1 indicates that the regression model describes the data perfectly, which is rare in practice.  $R^2$  provides a rough idea of how well data is described by a linear regression. A more precise determination of the adequacy of a linear regression is discussed in Section 9.6.3.3.

**9.6.3.2 Least-Squares Quadratic Regression**—Quadratic regression is appropriate when there is an approximate quadratic relationship between two measurable characteristics. Such a relationship is expressed algebraically by an equation that, in the case of two measurable characteristics x and y, has the form

$$y = \alpha + \beta x + \gamma x^2 + \varepsilon \quad ,$$

where

x = independent variable

y = dependent variable

$\alpha$  = true intercept of the regression equation

$\beta$  = true coefficient of the linear term in the regression equation

$\gamma$  = true coefficient of the quadratic term in the regression equation

$\varepsilon$  = measurement or experimental error by which y differs from the ideal linear relationship.

Aside from the error term,  $\varepsilon$ , this is the equation of a parabola. The parameter  $\alpha$  determines the point where this curve intersects the y-axis. The variable x and y may represent either direct measurements or some transformation measurements of the characteristics under consideration.

**MIL-HDBK-5H**  
**1 December 1998**

Knowing or assuming such an approximately quadratic relationship, the problem becomes one of estimating the parameters  $\alpha$ ,  $\beta$ , and  $\gamma$  of the regression equation. It is necessary to have a random sample consisting of  $n$  pairs of observations, which is denoted by  $(x_1, y_1)$ ,  $(x_2, y_2)$ , ...,  $(x_n, y_n)$ . Such a sample can be represented graphically by  $n$  points plotted on a coordinate system, in which  $x$  is plotted horizontally,  $y$  vertically. A subjective solution can be obtained by drawing a curve that, by visual inspection, appears to fit the points satisfactorily. An objective solution is given by the method of least squares.

The method of least squares is a numerical procedure for obtaining a second-degree polynomial having the property that the sum of squares of vertical deviations of the sample points from this curve is less than that for any other second-degree polynomial. In this analysis, the least squares curve is represented by the equation

$$\hat{y} = a + bx + cx^2, \quad [9.6.3.2(a)]$$

in which

$\hat{y}$  = predicted value of  $y$  for any value of  $x$

$a$ ,  $b$ , and  $c$  = estimates of the parameters  $\alpha$ ,  $\beta$  and  $\gamma$  in the true regression equation obtained by the least squares method presented below.

It can be shown with the aid of calculus that the values of  $a$ ,  $b$ , and  $c$  that minimize the sum of squares of the vertical deviations are given by the formulas:

$$c = \frac{(\sum X_2 Y)(\sum X_1^2) - (\sum X_1 Y)(\sum X_1 X_2)}{D} \quad [9.6.3.2(b)]$$

$$b = \frac{(\sum X_1 Y)(\sum X_2^2) - (\sum X_2 Y)(\sum X_1 X_2)}{D}$$

$$a = \bar{y} - b \left( \sum \frac{x}{n} \right) - c \left( \sum \frac{x^2}{n} \right)$$

where

$$D = (\sum X_1^2)(\sum X_2^2) - (\sum X_1 X_2)^2 \quad [9.6.3.2(c)]$$

and where  $X_1 = x - \Sigma x/n$ ,  $X_2 = x^2 - \Sigma x^2/n$ ,  $Y = y - \Sigma y/n$ , all symbols being summed are subscripted by  $i$ , and all summations are over  $i=1$  to  $n$ .

The root mean square error of  $y$  is expressed as

**MIL-HDBK-5H**  
**1 December 1998**

$$s_y = \sqrt{\frac{\sum (y - \hat{y})^2}{n - 3}} \quad [9.6.3.2(d)]$$

where  $\hat{y}$  is the predicted value of  $y$  defined above. This quantity is an estimate of the standard deviation of the distribution of  $y$  about the regression curve. A convenient computational formula for  $s_y$  is

$$s_y = \sqrt{(\sum Y^2 - b \sum X_1 Y - c \sum X_2 Y) / (n - 3)} \quad [9.6.3.2(e)]$$

The quantity  $R^2 = 1 - (n - 3) s_y^2 / \sum Y^2$  measures the proportion of total variation in the  $y$  data, about its average, that is explained by the regression. An  $R^2$  equal to 1 indicates that the regression model describes the data perfectly, which is rare in practice.  $R^2$  provides a rough idea of how well the data are described by a quadratic regression.

Another quantity,  $Q$ , is required to compute allowables by quadratic regression analysis.  $Q$  is defined as

$$Q = q_1 + 2q_2x_0 + (2q_3 + q_4)x_0^2 + 2q_5x_0^3 + q_6x_0^4 \quad [9.6.3.2(f)]$$

where  $x_0$  is the value of the independent variable for which the allowable is being calculated and  $q_1, q_2, q_3, q_4, q_5$  and  $q_6$  are defined to be elements of the inverse of the matrix  $X'X$  as follows:

$$(X'X)^{-1} = \begin{bmatrix} q_1 & q_2 & q_3 \\ q_2 & q_4 & q_5 \\ q_3 & q_5 & q_6 \end{bmatrix} \quad [9.6.3.2(g)]$$

with

$$X'X = \begin{bmatrix} n & \sum x_i & \sum x_i^2 \\ \sum x_i & \sum x_i^2 & \sum x_i^3 \\ \sum x_i^2 & \sum x_i^3 & \sum x_i^4 \end{bmatrix} . \quad [9.6.3.2(h)]$$

**9.6.3.3 Tests for Adequacy of a Regression** — It is possible that the relationship between dependent variable  $y$  and independent variable  $x$  may not be approximately linear. In that case, a straight line would not “fit” the data very well. It is also possible that the relationships between  $x$  and  $y$ , although approximately linear, may not be very strong. In such a case, estimated slope parameter  $b$  would not be significantly different from zero. Both the lack of fit and the significance of a linear regression equation can be evaluated through an analysis of variance as described in this section.

**MIL-HDBK-5H**  
**1 December 1998**

The analysis of variance for testing lack of fit and significance of regression is based on the assumption that measurement errors,  $\epsilon_i$ , in the approximate linear relationship between  $y_i$  and  $x_i$ , i.e.,

$$\epsilon_i = y_i - (\alpha + \beta x_i) \quad i = 1, \dots, n$$

are independent and normally distributed with an overall mean of zero and a constant variance of  $\sigma^2$ . Assuming uniformity of variance of measurement errors over the range of the independent variable, the normality assumption concerning unobservable  $\epsilon_i$  can be checked by performing the Anderson-Darling test for normality on the observable residuals

$$e_i = y_i - (a + bx_i) \quad i = 1, \dots, n$$

where  $a$  and  $b$  are the least squares estimates of  $\alpha$  and  $\beta$ . See Section 9.6.1.2 for more details. By plotting the residuals  $e_i$  against the respective  $x_i$ , an informal check on the assumption of constant variance  $\sigma^2$  is possible as well. In such a plot residuals should vary approximately equally over the range of  $x_i$  values.

The analysis of variance table for testing the lack of fit and significance of a linear regression is shown below. The sums of squares for the three primary lines of the analysis of variance table (Regression, Error, and Total) are calculated using quantities defined in Section 9.6.3.1:

Source of Variation	Degrees of Freedom, (Linear)	Sum of Square, SS	Mean Squares, MS	$F_{\text{calc}}$
Regression	1	SSR	MSR	$F_1$
Error	n-2	SSE	MSE	
Lack of Fit	k-2	SSLF	MSLF	$F_2$
Pure Error	n-k	SSPE	MSPE	
Total	n-1	SST		

$$\begin{aligned} \text{SSR} &= b^2 S_{xx} \\ \text{SST} &= S_{yy} \\ \text{SSE} &= \text{SST} - \text{SSR}. \end{aligned}$$

If the multiple observations at one or more values of the independent variable  $x$  are available, and observations are made at three or more distinct  $x$  values, then it is possible to evaluate the adequacy of a line in describing the relationship between  $x$  and  $y$ . The notation in testing for this lack of fit is summarized in the analysis of variance table above. Let  $Y_{ij}$  denote the  $j^{\text{th}}$  data value at the  $i^{\text{th}}$   $x$  level,  $k$  represent the number of distinct  $x$  levels for which there is data, and  $n_i$  represent the number of data values at the  $i^{\text{th}}$   $x$  level. Denote the total of the observations at the  $i^{\text{th}}$   $x$  level by

$$T_i = \sum_{j=1}^{n_i} Y_{ij} \quad \text{for } i = 1, \dots, k$$

and note that

**MIL-HDBK-5H**  
**1 December 1998**

$$n = \sum_{i=1}^k n_i$$

is used to denote the total number of observations. The lack of fit and pure error sums of squares are computed as

$$SSLF = \sum_{i=1}^k \left( T_i^2 / n_i \right) - (\Sigma y)^2 / n - SSR$$

and

$$SSPE = SSE - SSLF \quad .$$

The sums of squares are divided by the corresponding degrees of freedom to compute mean squares as shown below:

$$\begin{aligned} MSR &= SSR \\ MSE &= SSE / (n - 2) \\ MSLF &= SSLF / (k - 2) \\ MSPE &= SSPE / (n - k) \quad . \end{aligned}$$

These mean squares are used to compute two F statistics which test for lack of fit and significance of regression. (Note: If there is only one data value for each x level, i.e.,  $n_i = 1$  for  $i = 1, 2, \dots, k$ , or if  $k \leq 2$ , then it is not possible to test for lack of fit.)

The two F statistics,  $F_1$  and  $F_2$ , are defined as ratios of the mean squares as specified below:

$$\begin{aligned} F_1 &= MSR / MSE \\ F_2 &= MSLF / MSPE. \end{aligned}$$

$F_2$  and Table 9.6.4.9 are used to test for lack of fit. If  $F_2$  is greater than the 95th percentile of F distribution with  $k - 2$  numerator degrees of freedom and  $n - k$  denominator degrees of freedom (from Table 9.6.4.9), then there is significant lack of fit. In this case it may be concluded (with a 5 percent risk of error) that linear regression does not adequately describe the relationship between x and y. Otherwise, lack of fit can be considered insignificant and a linear regression model can be assumed.

If lack of fit is not significant, the significance of regression may be tested using  $F_1$  and Table 9.6.4.9. If  $F_1$  is greater than the 95th percentile of F distribution with 1 numerator degree of freedom and  $n - 2$  denominator degrees of freedom (from Table 9.6.4.9), then regression is significant. Otherwise, regression is not significant and x is considered to have little or no predictive value for y.

**9.6.3.4 Testing for Equality of Several Regressions** — The procedure presented in this section is designed to test the hypothesis that the true regression equations corresponding to two or more independent data sets are equal (linear or quadratic). It is appropriately applied to test the equality of several regressions in determining whether corresponding data sets should be combined for the purpose of calculating design allowables. To test k regressions for equality, the following procedure should be performed.

Perform separate regression analyses for each data set. The same model form should be used in all regressions (all linear or all quadratic). Add error sum of squares (SSE) values from each of the separate

**MIL-HDBK-5H****1 December 1998**

regressions to obtain SSE(F), the error sum of squares for the full model which allows separate slope and intercept parameters for each data set. Then fit a single regression to the combined data from all data sets to obtain SSE(R), error sum of squares for the reduced model which contains a single set of coefficients a and b (and c for quadratic models) which apply to all data sets. The F statistic for testing the equality of the k regressions is

$$F = \frac{SSE(R) - SSE(F)}{2(k - 1)} \div \frac{SSE(F)}{n - 2k}$$

for simple linear models, and

$$F = \frac{SSE(R) - SSE(F)}{3(k - 1)} \div \frac{SSE(F)}{n - 3k}$$

for quadratic models, where n denotes total number of observations in all k data sets combined. In the linear case, if F is greater than the 95th percentile of the F distribution with 2(k - 1) numerator degrees of freedom and n - 2k denominator degrees of freedom (from Table 9.6.4.9), the hypothesis that the regressions are equal is rejected. In the quadratic case, if F is greater than the 95th percentile of the F distribution with 3(k - 1) numerator degrees of freedom, and n - 3k denominator degrees of freedom, the hypothesis that the regressions are equal is rejected. See Reference 9.6.3.3 for more detail.

**9.6.3.5 Example of Computations** — In this example, x represents thickness and y represents the TYS values determined from a group of tensile tests. Values of x and y are as follows:

X	Y
0.100	121
0.100	119
0.200	114
0.200	108
0.300	112
0.300	108
0.400	112
0.400	106
0.500	101
0.500	99

From these data, the following quantities may be calculated:

n	= 10	(Σx) <sup>2</sup>	= 9
Σx	= 3	(Σy) <sup>2</sup>	= 121000
Σy	= 1100.0	(Σx)(Σy)	= 3300
Σx <sup>2</sup>	= 1.1	S <sub>xx</sub>	= 0.20
Σy <sup>2</sup>	= 121452	S <sub>xy</sub>	= -8.4
Σxy	= 321.6	S <sub>yy</sub>	= 452.



**MIL-HDBK-5H**  
**1 December 1998**

The slope of the regression line is:

$$b = \frac{S_{xy}}{S_{xx}} = \frac{-8.4}{0.20} = -42 \quad .$$

The y-intercept of the regression line is:

$$a = \frac{\Sigma y - b \Sigma x}{n} = \frac{1100}{10} - \frac{(-42)(3)}{10} = 110 + 12.6 = 122.6 \quad .$$

Thus the final equation of the least squares regression line is:

$$\hat{y} = a + b x = 122.6 - 42x \quad .$$

The total of the y data at each x level is needed to calculate lack of fit and pure error sums of squares. These totals are as follows:

$x_i$	$T_i$
0.1	240
0.2	222
0.3	220
0.4	218
0.5	200

There are data values at  $k = 5$  different x levels, with  $n_i = 2$  values at each level and

$$\sum_{i=1}^k (T_i^2/n_i) = \frac{(240)^2}{2} + \dots + \frac{(200)^2}{2} = 121404 \quad .$$

Thus,

$$SSLF = 121404 - (1100)^2/10 - 352.8 = 51.2$$

and

$$SSPE = 99.2 - 51.2 = 48.$$

The mean square values are computed by dividing corresponding sums of squares by their degrees of freedom. The  $F_1$  and  $F_2$  statistics are then calculated as ratios of mean squares. The analysis of variance table is shown below.

**MIL-HDBK-5H**  
**1 December 1998**

Source of Variation	Degree of Freedom, DF	Sum of Square, SS	Mean Squares, MS	F <sub>calc</sub>
Regression	1	352.8	352.8	F <sub>1</sub> = 28.5
Error	8	99.2	12.4	
Lack of Fit	3	51.2	17.07	F <sub>2</sub> = 1.78
Pure Error	5	48.0	9.6	
Total	9	452.0		

Using this equation, the following values of  $\hat{y}$  may be computed for the values of x listed previously.

x	$\hat{y}$
0.100	118.4
0.200	114.2
0.300	110.0
0.400	105.8
0.500	101.6

The root mean square error is computed as follows:

$$S_y = \sqrt{\frac{\Sigma(y - \hat{y})^2}{n - 2}} = \sqrt{\frac{99.2}{8}}$$

or

$$S_y = \sqrt{\frac{S_{yy} - b^2 S_{xx}}{n - 2}} = \sqrt{\frac{452 - (-42)^2(0.2)}{8}} = 3.52$$

R<sup>2</sup> is computed as follows:

$$R^2 = \frac{b^2 S_{xx}}{S_{yy}} = \frac{(-42)^2(0.2)}{452} = 0.78$$

Thus, 78 percent of the variability in the y data about its average is explained by the linear relationship between y and x.

**MIL-HDBK-5H**  
**1 December 1998**

The sum of squares for the regression, total and error lines are computed as follows:

$$SSR = (-42)^2 (0.20) = 352.8$$

$$SST = 452$$

$$SSE = 452 - 352.8 = 99.2.$$

The  $F_2$  value of 1.78 with  $k - 2 = 3$  and  $n - k = 5$  degrees of freedom is less than the value of 5.41 from Table 9.6.4.9 corresponding to 3 numerator and 5 denominator degrees of freedom. This indicates that lack of fit can be considered insignificant. Thus, it is reasonable to assume that a linear regression adequately describes the data. The  $F_1$  value of 28.5 with 1 and  $n - 2 = 8$  degrees of freedom is greater than the value of 5.32 from Table 9.6.4.9 corresponding to 1 numerator and 8 denominator degrees of freedom, so the slope of the regression is found to be significantly different from zero.

**9.6.4 TABLES** — In this section a number of tables of statistical values that are required for analyses described in the Guidelines are presented. For tables containing various fractiles or confidence levels, only applicable portions are reproduced herein. Table 9.6.4.1 was reproduced by permission from Reference 9.6.4.1. Table 9.6.4.2 was computed specifically for MIL-HDBK-5. Tables 9.6.4.3 through 9.6.4.7 and Table 9.6.4.9 were reproduced or adapted from tables in Reference 9.6, with the addition of a few individual values from various sources. Tables 9.6.4.8 and 9.6.4.10 were computed specifically for MIL-HDBK-5.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.1. One-Sided Tolerance Limit Factors<sup>a</sup>, k, for the Normal Distribution, 0.95 Confidence, and n-1 Degrees of Freedom**

Note: use values for P = 0.99 to determine T<sub>99</sub>

use values for P = 0.90 to determine T<sub>90</sub>

n	P = 0.90	P = 0.99	n	P = 0.90	P = 0.99
2	20.581	37.094	31	1.767	3.048
3	6.155	10.553	32	1.758	3.034
4	4.162	7.042	33	1.749	3.020
5	3.407	5.741	34	1.740	3.007
6	3.006	5.062	35	1.732	2.995
7	2.755	4.642	36	1.725	2.983
8	2.582	4.354	37	1.717	2.972
9	2.454	4.143	38	1.710	2.961
10	2.355	3.981	39	1.704	2.951
11	2.275	3.852	40	1.697	2.941
12	2.210	3.747	41	1.691	2.932
13	2.155	3.659	42	1.685	2.923
14	2.109	3.585	43	1.680	2.914
15	2.068	3.520	44	1.674	2.906
16	2.033	3.464	45	1.669	2.898
17	2.002	3.414	46	1.664	2.890
18	1.974	3.370	47	1.659	2.883
19	1.949	3.331	48	1.654	2.876
20	1.926	3.295	49	1.650	2.869
21	1.905	3.263	50	1.646	2.862
22	1.886	3.233	51	1.641	2.856
23	1.869	3.206	52	1.637	2.850
24	1.853	3.181	53	1.633	2.844
25	1.838	3.158	54	1.630	2.838
26	1.824	3.136	55	1.626	2.833
27	1.811	3.116	56	1.622	2.827
28	1.799	3.098	57	1.619	2.822
29	1.788	3.080	58	1.615	2.817
30	1.777	3.064	59	1.612	2.812
			60	1.609	2.807

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.1. One-Sided Tolerance Limit Factors<sup>a</sup>, k, for the Normal Distribution, 0.95 Confidence, and n-1 Degrees of Freedom (continued)**

n	P = 0.90	P = 0.99	n	P = 0.90	P = 0.99
61	1.606	2.802	91	1.540	2.704
62	1.603	2.798	92	1.538	2.701
63	1.600	2.793	93	1.537	2.699
64	1.597	2.789	94	1.535	2.697
65	1.594	2.785	95	1.534	2.695
66	1.591	2.781	96	1.532	2.692
67	1.589	2.777	97	1.531	2.690
68	1.586	2.773	98	1.530	2.688
69	1.584	2.769	99	1.528	2.686
70	1.581	2.765	100	1.527	2.684
71	1.579	2.762	101	1.525	2.682
72	1.576	2.758	102	1.524	2.680
73	1.574	2.755	103	1.523	2.678
74	1.572	2.751	104	1.521	2.676
75	1.570	2.748	105	1.520	2.674
76	1.568	2.745	106	1.519	2.672
77	1.565	2.742	107	1.518	2.671
78	1.563	2.739	108	1.517	2.669
79	1.561	2.736	109	1.515	2.667
80	1.559	2.733	110	1.514	2.665
81	1.557	2.730	111	1.513	2.663
82	1.556	2.727	112	1.512	2.662
83	1.554	2.724	113	1.511	2.660
84	1.552	2.721	114	1.510	2.658
85	1.550	2.719	115	1.508	2.657
86	1.548	2.716	116	1.507	2.655
87	1.547	2.714	117	1.506	2.654
88	1.545	2.711	118	1.505	2.652
89	1.543	2.709	119	1.504	2.651
90	1.542	2.706	120	1.503	2.649

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.1. One-Sided Tolerance Limit Factors<sup>a</sup>, k, for the Normal Distribution, 0.95 Confidence, and n-1 Degrees of Freedom (continued)**

n	P = 0.90	P = 0.99	n	P = 0.90	P = 0.99
121	1.502	2.648	151	1.477	2.610
122	1.501	2.646	152	1.476	2.609
123	1.500	2.645	153	1.476	2.608
124	1.499	2.643	154	1.475	2.607
125	1.498	2.642	155	1.474	2.606
126	1.497	2.640	156	1.474	2.605
127	1.496	2.639	157	1.473	2.604
128	1.496	2.638	158	1.472	2.603
129	1.495	2.636	159	1.472	2.602
130	1.494	2.635	160	1.471	2.601
131	1.493	2.634	161	1.470	2.600
132	1.492	2.632	162	1.470	2.600
133	1.491	2.631	163	1.469	2.599
134	1.490	2.630	164	1.469	2.598
135	1.489	2.628	165	1.468	2.597
136	1.489	2.627	166	1.467	2.596
137	1.488	2.626	167	1.467	2.595
138	1.487	2.625	168	1.466	2.594
139	1.486	2.624	169	1.466	2.593
140	1.485	2.622	170	1.465	2.592
141	1.485	2.621	171	1.464	2.592
142	1.484	2.620	172	1.464	2.591
143	1.483	2.619	173	1.463	2.590
144	1.482	2.618	174	1.463	2.589
145	1.481	2.617	175	1.462	2.588
146	1.481	2.616	176	1.462	2.587
147	1.480	2.615	177	1.461	2.587
148	1.479	2.613	178	1.460	2.586
149	1.479	2.612	179	1.460	2.585
150	1.478	2.611	180	1.459	2.584

**MIL-HDBK-5H****1 December 1998****Table 9.6.4.1. One-Sided Tolerance Limit Factors<sup>a</sup>, k, for the Normal Distribution, 0.95 Confidence, and n-1 Degrees of Freedom (continued)**

n	P = 0.90	P = 0.99	n	P = 0.90	P = 0.99
181	1.459	2.583	255	1.429	2.540
182	1.458	2.583	260	1.428	2.537
183	1.458	2.583	265	1.426	2.535
184	1.457	2.581	270	1.425	2.533
185	1.457	2.580	275	1.423	2.531
186	1.456	2.580	280	1.422	2.529
187	1.456	2.579	285	1.421	2.527
188	1.455	2.578	290	1.419	2.525
189	1.455	2.577	295	1.418	2.524
190	1.454	2.577	300	1.417	2.522
191	1.454	2.576	305	1.416	2.520
192	1.453	2.575	310	1.415	2.518
193	1.453	2.575	315	1.413	2.517
194	1.452	2.574	320	1.412	2.515
195	1.452	2.573	325	1.411	2.514
196	1.451	2.572	330	1.410	2.512
197	1.451	2.572	335	1.409	2.511
198	1.450	2.571	340	1.408	2.509
199	1.450	2.570	345	1.407	2.508
200	1.450	2.570	350	1.406	2.506
205	1.447	2.566	355	1.405	2.505
210	1.445	2.563	360	1.404	2.504
215	1.443	2.560	365	1.404	2.502
220	1.441	2.557	370	1.403	2.501
225	1.439	2.555	375	1.402	2.500
230	1.437	2.552	380	1.401	2.499
235	1.436	2.549	385	1.400	2.498
240	1.434	2.547	390	1.399	2.496
245	1.432	2.544	395	1.399	2.495
250	1.431	2.542	400	1.398	2.494

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.1. One-Sided Tolerance Limit Factors<sup>a</sup>, k, for the Normal Distribution, 0.95 Confidence, and n-1 Degrees of Freedom (continued)**

n	P = 0.90	P = 0.99	n	P = 0.90	P = 0.99
425	1.394	2.489	800	1.363	2.443
450	1.391	2.484	825	1.361	2.441
475	1.388	2.480	850	1.360	2.439
500	1.385	2.475	875	1.359	2.438
525	1.382	2.472	900	1.358	2.436
550	1.380	2.468	925	1.357	2.434
575	1.378	2.465	950	1.356	2.433
600	1.376	2.462	975	1.355	2.432
625	1.374	2.459	1000	1.354	2.430
650	1.372	2.456	1500	1.340	2.411
675	1.370	2.454	2000	1.332	2.399
700	1.368	2.451	3000	1.323	2.385
725	1.367	2.449	5000	1.313	2.372
750	1.365	2.447	10000	1.304	2.358
775	1.364	2.445	∞	1.282	2.326

a The following equations may be used to compute k factors in lieu of using table values:

$$k_{99} = 2.326 + \exp [1.34 - 0.522 \ln(n) + 3.87/n]$$

$$k_{90} = 1.282 + \exp [0.958 - 0.520 \ln(n) + 3.19/n]$$

These approximations are accurate to within 0.2% of the table values for n greater than or equal to 16.



**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.2. Ranks, r, of Observations, n, for an Unknown Distribution Having the Probability and Confidence of T<sub>99</sub> and T<sub>90</sub> Values**

T <sub>99</sub> Value						T <sub>90</sub> Value					
n	r <sub>99</sub>	n	r <sub>99</sub>	n	r <sub>99</sub>	n	r <sub>90</sub>	n	r <sub>90</sub>	n	r <sub>90</sub>
≤ 298	a	4635	36	8643	72	≤ 28	b	638	52	2693	340
299	1	4749	37	8753	73	29	1	660	54	3797	350
473	2	4862	38	8862	74	46	2	682	56	3901	360
628	3	4975	39	8972	75	61	3	704	58	4005	370
773	4	5088	40	9081	76	76	4	726	60	4109	380
913	5	5201	41	9190	77	89	5	781	65	4213	390
1049	6	5314	42	9300	78	103	6	836	70	4317	400
1182	7	5427	43	9409	79	116	7	890	75	4421	410
1312	8	5539	44	9518	80	129	8	945	80	4525	420
1441	9	5651	45	9627	81	142	9	999	85	4629	430
1568	10	5764	46	9736	82	154	10	1053	90	4733	440
1693	11	5876	47	9845	83	167	11	1107	95	4836	450
1818	12	5988	48	9954	84	179	12	1161	100	4940	460
1941	13	6099	49	10063	85	191	13	1269	110	5044	470
2064	14	6211	50	10172	86	203	14	1376	120	5147	480
2185	15	6323	51	10281	87	215	15	1483	130	5251	490
2305	15	6434	52	10390	88	227	16	1590	140	5354	500
2425	16	6545	53	10498	89	239	17	1696	150	5613	525
2546	18	6657	54	10607	90	251	18	1803	160	5871	550
2665	19	6768	55	10716	91	263	19	1909	170	6130	575
2784	20	6879	56	10824	92	275	20	2015	180	6388	600
2902	21	6990	57	10933	93	298	22	2120	190	6645	625
3020	22	7100	58	11041	94	321	24	2226	200	6903	650
3137	23	7211	59	11150	95	345	26	2331	210	7161	675
3254	24	7322	60	11258	96	368	28	2437	220	7418	700
3371	25	7432	61	11366	97	391	30	2542	230	7727	730
3487	26	7543	62	11475	98	413	32	2647	240	8036	760
3603	27	7653	63	11583	99	436	34	2752	250	8344	790
3719	28	7763	64	11691	100	459	36	2857	260	8652	820
3834	29	7874	65			481	38	2962	270	8960	850
3949	30	7984	66			504	40	3066	280	9268	880
4064	31	8094	67			526	42	3171	290	9576	910
4179	32	8204	68			549	44	3276	300	9884	940
4293	33	8314	69			571	46	3380	310	10191	970
4407	34	8423	70			593	48	3484	320	10499	1000
4521	35	8533	71			615	50	3589	330		

a T<sub>99</sub> value is lower than value of lowest observation.

b T<sub>90</sub> value is lower than value of lowest observation.

The following equations may be used to compute ranks in lieu of using table values or for n values greater than these presented in the table:

$$r_{99} = n/100 - 1.645\sqrt{99n/10000} + 0.29 + 19.1/n, \text{ for } n \geq 299$$

rounded to the nearest integer. For n less than 299, the T<sub>99</sub> value does not exist. This approximation is exact for all but 23 values of n in the range of the table (299 ≤ n ≤ 11691), which is an error rate of about 0.2%. For this small percentage of n values, the approximation gives an r value 1 below the actual r, resulting in a conservative T<sub>99</sub> value. For T<sub>90</sub> values, the approximation is

**MIL-HDBK-5H**  
**1 December 1998**

$$r_{90} = n/10 - 1.645\sqrt{9n/100} + 0.23, \text{ for } n \geq 29$$

rounded to the nearest integer. For  $n$  less than 29, the  $T_{90}$  value does not exist. The approximation is exact for all but 12 values of  $n$  in the range of the table ( $29 \leq n \leq 10499$ ), and errs conservatively by one rank for this small percentage (0.1%).

**Table 9.6.4.3. 0.95 Fractiles<sup>a</sup> of the Chi-Squared Distribution Associated with df Degrees of Freedom**

df	$\chi^2_{0.95}$	df	$\chi^2_{0.95}$
1	3.84	16	26.30
2	5.99	17	27.59
3	7.81	18	28.87
4	9.49	19	30.14
5	11.07	20	31.41
6	12.59	21	32.67
7	14.07	22	33.92
8	15.51	23	35.17
9	16.92	24	36.42
10	18.31	25	37.65
11	19.68	26	38.88
12	21.03	27	40.11
13	22.36	28	41.34
14	23.68	29	42.56
15	25.00	30	43.77

a The following equation may be used to compute 0.95 fractiles of the Chi-Squared distribution in lieu of using table values:

$$\chi^2_{0.95} = \gamma \left( 1 - \frac{2}{9\gamma} + 1.645\sqrt{\frac{2}{9\gamma}} \right)^3 + \frac{9}{100\gamma}$$

where  $\gamma$  is the degrees of freedom (df). This approximation is accurate to within 0.2% of the table values. See Reference 9.6.4.3.

**Table 9.6.4.4. 0.975 Fractiles<sup>a</sup> of the F Distribution Associated with  $n_1$  and  $n_2$  Degrees of Freedom,  $F_{.975}(n_1, n_2)$** 

$n_2^b$	$n_1$ , degrees of freedom for numerator																		
	1	2	3	4	5	6	7	8	9	10	12	15	20	24	30	40	60	120	$\infty$
1	647.8	799.5	864.2	899.6	921.8	937.1	948.2	956.7	963.3	968.6	976.7	984.9	993.1	997.2	1001	1006	1010	1014	1018
2	38.51	39.00	39.17	39.25	39.30	39.33	39.36	39.37	39.39	39.40	39.41	39.43	39.45	39.46	39.45	39.47	39.48	39.99	39.50
3	17.44	16.04	15.44	15.10	14.88	14.73	14.62	14.54	14.47	14.42	14.34	14.25	14.17	14.12	14.08	14.04	13.99	13.95	13.90
4	12.22	10.65	9.98	9.60	9.36	9.20	9.07	8.98	8.90	8.84	8.75	8.66	8.56	8.51	8.46	8.41	8.36	8.31	8.26
5	10.01	8.43	7.76	7.39	7.15	6.98	6.85	6.76	6.68	6.62	6.52	6.43	6.33	6.28	6.23	6.18	6.12	6.07	6.02
6	8.81	7.26	6.60	6.23	5.99	5.82	5.70	5.60	5.52	5.46	5.37	5.27	5.17	5.12	5.07	5.01	4.96	4.90	4.85
7	8.07	6.54	5.89	5.52	5.29	5.12	4.99	4.90	4.82	4.76	4.67	4.57	4.47	4.42	4.36	4.31	4.25	4.20	4.14
8	7.57	6.06	5.42	5.05	4.82	4.65	4.53	4.43	4.36	4.30	4.20	4.10	4.00	3.95	3.89	3.84	3.78	3.73	3.67
9	7.21	5.71	5.08	4.72	4.48	4.32	4.20	4.10	4.03	3.96	3.87	3.77	3.67	3.61	3.56	3.51	3.45	3.39	3.33
10	6.94	5.46	4.83	4.47	4.24	4.07	3.95	3.85	3.78	3.72	3.62	3.52	3.42	3.37	3.31	3.26	3.20	3.14	3.08
11	6.72	5.26	4.63	4.28	4.04	3.88	3.76	3.66	3.59	3.53	3.43	3.33	3.23	3.17	3.12	3.06	3.00	2.94	2.88
12	6.55	5.10	4.47	4.12	3.89	3.73	3.61	3.51	3.44	3.37	3.28	3.18	3.07	3.02	2.96	2.91	2.85	2.79	2.72
13	6.41	4.97	4.35	4.00	3.77	3.60	3.48	3.39	3.31	3.25	3.15	3.05	2.95	2.89	2.84	2.78	2.72	2.66	2.60
14	6.30	4.86	4.24	3.89	3.66	3.50	3.38	3.29	3.21	3.15	3.05	2.95	2.84	2.79	2.73	2.67	2.61	2.55	2.49
15	6.20	4.77	4.15	3.80	3.58	3.41	3.29	3.20	3.12	3.06	2.96	2.86	2.76	2.70	2.64	2.59	2.52	2.46	2.40
16	6.12	4.69	4.08	3.73	3.50	3.34	3.22	3.12	3.05	2.99	2.89	2.79	2.68	2.63	2.57	2.51	2.45	2.38	2.32
17	6.04	4.62	4.01	3.66	3.44	3.28	3.16	3.06	2.98	2.92	2.82	2.72	2.62	2.56	2.50	2.44	2.38	2.32	2.25
18	5.98	4.56	3.95	3.61	3.38	3.22	3.10	3.01	2.93	2.87	2.77	2.67	2.56	2.50	2.44	2.38	2.32	2.26	2.19
19	5.92	4.51	3.90	3.56	3.33	3.17	3.05	2.96	2.88	2.82	2.72	2.62	2.51	2.45	2.39	2.33	2.27	2.20	2.13
20	5.87	4.46	3.86	3.51	3.29	3.13	3.01	2.91	2.84	2.77	2.68	2.57	2.46	2.41	2.36	2.29	2.22	2.16	2.09
21	5.83	4.42	3.82	3.48	3.25	3.09	2.97	2.87	2.80	2.73	2.64	2.53	2.42	2.37	2.31	2.25	2.18	2.11	2.04
22	5.79	4.38	3.78	3.44	3.22	3.05	2.93	2.84	2.76	2.70	2.60	2.50	2.39	2.33	2.27	2.21	2.14	2.08	2.00
23	5.75	4.25	3.75	3.41	3.18	3.02	2.90	2.81	2.73	2.67	2.57	2.47	2.36	2.30	2.24	2.18	2.11	2.04	1.97
24	5.72	4.32	3.72	3.38	3.15	2.99	2.87	2.78	2.70	2.64	2.54	2.44	2.33	2.27	2.21	2.15	2.08	2.01	1.94
25	5.69	4.29	3.69	3.35	3.13	2.97	2.85	2.75	2.68	2.61	2.51	2.41	2.30	2.24	2.18	2.12	2.05	1.98	1.91
26	5.66	4.27	3.67	3.33	3.10	2.94	2.82	2.73	2.65	2.59	2.49	2.39	2.28	2.22	2.16	2.09	2.03	1.95	1.88
27	5.63	4.24	3.65	3.31	3.08	2.92	2.80	2.71	2.63	2.57	2.47	2.36	2.25	2.19	2.13	2.07	2.00	1.93	1.85
28	5.61	4.22	3.63	3.29	3.06	2.90	2.78	2.69	2.61	2.55	2.45	2.34	2.23	2.17	2.11	2.06	1.98	1.91	1.83
29	5.59	4.20	3.61	3.27	3.04	2.88	2.76	2.67	2.59	2.53	2.43	2.32	2.21	2.15	2.09	2.03	1.96	1.89	1.81
30	5.57	4.18	3.59	3.25	3.03	2.87	2.75	2.65	2.57	2.51	2.41	2.31	2.20	2.14	2.07	2.01	1.94	1.87	1.79
40	5.42	4.05	3.46	3.13	2.90	2.74	2.62	2.53	2.45	2.39	2.29	2.18	2.07	2.01	1.94	1.88	1.80	1.72	1.64
60	5.29	3.93	3.34	3.01	2.79	2.63	2.51	2.41	2.33	2.27	2.17	2.06	1.94	1.88	1.82	1.74	1.67	1.58	1.48
120	5.15	3.80	3.23	2.89	2.67	2.52	2.39	2.30	2.22	2.16	2.05	1.94	1.82	1.76	1.69	1.61	1.53	1.43	1.31
$\infty$	5.02	3.69	3.12	2.79	2.57	2.41	2.29	2.19	2.11	2.05	1.94	1.83	1.71	1.64	1.57	1.48	1.39	1.27	1.00

a See following page for footnote.

b  $n_2$  = degrees of freedom for denominator

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.4. 0.975 Fractiles<sup>a</sup> of the F Distribution Associated with  $n_1$  and  $n_2$  degrees of Freedom  $F_{.975}(n_1, n_2)$**

a The following equation may be used to compute 0.975 fractiles of the F distribution in lieu of using table values:

$$F_{.975} \approx \exp \left[ 2\delta \left( 1 + \frac{z^2 - 1}{3} - \frac{4\sigma^2}{3} \right) + 2\sigma z \left( 1 + \frac{\sigma^2(z^2 - 3)}{6} \right)^{1/2} \right]$$

where

$$\begin{aligned} z &= 1.96 \\ \delta &= 0.5 (1/\gamma_2 - 1) - 1(\gamma_1 - 1) \\ \sigma^2 &= 0.5 (1/\gamma_2 - 1) - 1(\gamma_1 - 1) \\ \gamma_1 &= \text{degrees of freedom for numerator} \\ \gamma_2 &= \text{degrees of freedom for denominator.} \end{aligned}$$

This approximation is accurate to within 0.4% for  $\gamma_1 \geq 10$  and  $\gamma_2 \geq 16$ . See Reference 9.6.4.4.

**Table 9.6.4.5. 0.95 and 0.975 Fractiles<sup>a</sup> of the t Distribution Associated with df Degrees of Freedom**

df	$t_{.95}$	$t_{.975}$	df	$t_{.95}$	$t_{.975}$
1	6.314	12.706	21	1.721	2.080
2	2.920	4.303	22	1.717	2.074
3	2.353	3.182	23	1.714	2.069
4	2.132	2.776	24	1.711	2.064
5	2.015	2.571	25	1.708	2.060
6	1.943	2.447	26	1.706	2.056
7	1.895	2.365	27	1.703	2.052
8	1.860	2.306	28	1.701	2.048
9	1.833	2.262	29	1.699	2.045
10	1.812	2.228	30	1.697	2.042
11	1.796	2.201	40	1.684	2.021
12	1.782	2.179	50	1.676	2.009
13	1.771	2.160	60	1.671	2.000
14	1.761	2.145	80	1.664	1.990
15	1.753	2.131	100	1.660	1.984
16	1.746	2.120	120	1.658	1.980
17	1.740	2.110	200	1.653	1.972
18	1.734	2.101	500	1.648	1.965
19	1.729	2.093	$\infty$	1.645	1.960
20	1.725	2.086			

a The following equations may be used to compute 0.95 and 0.975 fractiles of the t distribution in lieu of using table values:

$$\begin{aligned} t_{.95} &\approx 1.645 + \exp [0.377 - 0.990 \ln(\gamma) + 1.15/\gamma] \\ t_{.975} &\approx 1.96 + \exp [0.779 - 0.980 \ln(\gamma) + 1.57/\gamma] \end{aligned}$$

where  $\gamma$  is the degrees of freedom (df). These approximations are accurate to within 0.5% for  $\gamma \geq 4$ .

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.6. Area Under the Normal Curve from  $-\infty$  to the Mean +  $Z_p$  Standard Deviations<sup>a,b</sup>**

$Z_p$	0.00	0.01	0.02	0.03	0.04	0.05	0.06	0.07	0.08	0.09
.0	.5000	.5040	.5080	.5120	.5160	.5199	.5239	.5279	.5319	.5359
.1	.5398	.5438	.5478	.5517	.5557	.5596	.5636	.5675	.5714	.5753
.2	.5793	.5832	.5871	.5910	.5948	.5987	.6026	.6064	.6103	.6141
.3	.6179	.6217	.6255	.6293	.6331	.6368	.6406	.6443	.6480	.6517
.4	.6554	.6591	.6628	.6664	.6700	.6736	.6772	.6808	.6844	.6879
.5	.6915	.6950	.6985	.7019	.7054	.7088	.7123	.7157	.7190	.7224
.6	.7257	.7291	.7324	.7357	.7389	.7422	.7454	.7486	.7517	.7549
.7	.7580	.7611	.7642	.7673	.7704	.7734	.7764	.7794	.7823	.7852
.8	.7881	.7910	.7939	.7967	.7995	.8023	.8051	.8078	.8106	.8133
.9	.8159	.8186	.8212	.8238	.8264	.8289	.8315	.8340	.8365	.8389
1.0	.8413	.8438	.8461	.8485	.8508	.8531	.8554	.8577	.8599	.8621
1.1	.8643	.8665	.8686	.8708	.8729	.8749	.8770	.8790	.8810	.8820
1.2	.8849	.8869	.8888	.8907	.8925	.8944	.8962	.8980	.8997	.9015
1.3	.9032	.9049	.9066	.9082	.9099	.9115	.9131	.9147	.9162	.9177
1.4	.9192	.9207	.9222	.9236	.9251	.9265	.9279	.9292	.9306	.9319
1.5	.9332	.9345	.9357	.9370	.9382	.9394	.9406	.9418	.9429	.9441
1.6	.9452	.9463	.9474	.9484	.9495	.9505	.9515	.9525	.9535	.9545
1.7	.9554	.9564	.9573	.9582	.9591	.9599	.9608	.9616	.9625	.9633
1.8	.9641	.9649	.9656	.9664	.9671	.9678	.9686	.9693	.9699	.9706
1.9	.9713	.9719	.9726	.9732	.9738	.9744	.9750	.9756	.9761	.9767
2.0	.9772	.9778	.9783	.9788	.9793	.9798	.9803	.9808	.9812	.9817
2.1	.9821	.9826	.9830	.9834	.9838	.9842	.9846	.9850	.9854	.9857
2.2	.9861	.9864	.9868	.9871	.9875	.9878	.9881	.9884	.9887	.9890
2.3	.9893	.9896	.9898	.9901	.9904	.9906	.9909	.9911	.9913	.9916
2.4	.9918	.9920	.9922	.9925	.9927	.9929	.9931	.9932	.9934	.9936
2.5	.9938	.9940	.9941	.9943	.9945	.9946	.9948	.9949	.9951	.9952
2.6	.9953	.9955	.9956	.9957	.9959	.9960	.9961	.9962	.9963	.9964
2.7	.9965	.9966	.9967	.9968	.9969	.9970	.9971	.9972	.9973	.9974
2.8	.9974	.9975	.9976	.9977	.9977	.9978	.9979	.9979	.9980	.9981
2.9	.9981	.9982	.9982	.9983	.9984	.9984	.9985	.9985	.9986	.9986
3.0	.9987	.9987	.9987	.9988	.9988	.9989	.9989	.9989	.9990	.9990
3.1	.9990	.9991	.9991	.9991	.9992	.9992	.9992	.9992	.9993	.9993
3.2	.9993	.9993	.9994	.9994	.9994	.9994	.9994	.9995	.9995	.9995
3.3	.9995	.9995	.9995	.9996	.9996	.9996	.9996	.9996	.9996	.9997
3.4	.9997	.9997	.9997	.9997	.9997	.9997	.9997	.9997	.9997	.9998

a For negative values of  $Z_p$ , subtract the tabular value from unity.

b The following equation may be used to compute the probabilities in lieu of using table values:

$$p \approx 0.5 \{ 1 - [1 + (A + BZ_p)^C]^D + [1 + (A - BZ_p)^C]^D \}$$

where

$$A = 0.644693$$

$$B = 0.161984$$

$$C = 4.874$$

$$D = -6.158$$

This approximation is accurate to within 0.07% of the true probabilities, see Reference 9.6.4.3.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.7. One-Sided Tolerance-Limit Factors for the Three-Parameter Weibull Acceptability Test with 95 Percent Confidence**

Sample Size	$V_{99}$
10	-4.46
15	-4.77
20	-4.98
25	-5.12
30	-5.23
35	-5.32
40	-5.40
50	-5.51
75	-5.71
100	-5.82
150	-5.97
200	-6.05
300	-6.17
400	-6.23
500	-6.27
750	-6.29
1,000	-6.34
2,000	-6.39
5,000	-6.51
10,000	-6.55
$\infty$	-6.65

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.8. One-Sided Tolerance Factors for the Three-Parameter Weibull Distribution with 95 Percent Confidence**

N	V <sub>99</sub> for T <sub>99</sub>			V <sub>90</sub> for T <sub>90</sub>		
	Uncensored	20% Censored	50% Censored	Uncensored	20% Censored	50% Censored
10	12.330	16.508	29.921	6.763	8.466	13.182
11	11.885	15.700	27.134	6.529	8.067	12.004
12	11.520	15.053	25.086	6.337	7.747	11.138
13	11.214	14.522	23.514	6.177	7.485	10.474
14	10.955	14.078	22.266	6.040	7.266	9.946
15	10.730	13.700	21.251	5.922	7.079	9.516
16	10.535	13.374	20.406	5.820	6.918	9.159
17	10.362	13.090	19.692	5.729	6.778	8.857
18	10.208	12.840	19.080	5.649	6.655	8.597
19	10.071	12.617	18.548	5.577	6.545	8.372
20	9.946	12.417	18.082	5.512	6.447	8.174
21	9.834	12.238	17.669	5.453	6.358	8.000
22	9.731	12.074	17.300	5.399	6.278	7.843
23	9.636	11.926	16.969	5.349	6.204	7.703
24	9.549	11.789	16.670	5.304	6.137	7.577
25	9.469	11.664	16.398	5.262	6.075	7.461
26	9.394	11.548	16.150	5.223	6.018	7.356
27	9.325	11.441	15.922	5.187	5.966	7.260
28	9.260	11.341	15.712	5.153	5.916	7.171
29	9.199	11.248	15.518	5.121	5.870	7.088
30	9.142	11.160	15.338	5.091	5.828	7.012
31	9.089	11.078	15.170	5.063	5.787	6.941
32	9.038	11.002	15.014	5.037	5.750	6.875
33	8.990	10.929	14.868	5.012	5.714	6.813
34	8.945	10.861	14.730	4.989	5.680	6.754
35	8.902	10.796	14.601	4.966	5.648	6.700
36	8.862	10.735	14.479	4.945	5.618	6.648
37	8.823	10.676	14.364	4.925	5.590	6.599
38	8.786	10.621	14.256	4.906	5.562	6.553
39	8.751	10.568	14.153	4.887	5.537	6.510
40	8.717	10.518	14.055	4.870	5.512	6.468
41	8.685	10.470	13.962	4.853	5.488	6.429
42	8.654	10.424	13.873	4.837	5.466	6.391
43	8.624	10.380	13.789	4.822	5.444	6.356
44	8.596	10.338	13.708	4.807	5.423	6.321
45	8.569	10.298	13.631	4.793	5.404	6.289
46	8.543	10.259	13.558	4.779	5.385	6.258
47	8.517	10.221	13.487	4.766	5.366	6.228
48	8.493	10.186	13.419	4.753	5.349	6.199

**MIL-HDBK-5H****1 December 1998****Table 9.6.4.8. One-Sided Tolerance Factors for the Three-Parameter Weibull Distribution with 95 Percent Confidence (Continued)**

N	V <sub>99</sub> for T <sub>99</sub>			V <sub>90</sub> for T <sub>90</sub>		
	Uncensored	20% Censored	50% Censored	Uncensored	20% Censored	50% Censored
49	8.469	10.151	13.354	4.741	5.332	6.171
50	8.447	10.118	13.292	4.729	5.315	6.145
51	8.425	10.086	13.232	4.718	5.300	6.119
52	8.404	10.055	13.174	4.707	5.284	6.095
53	8.383	10.025	13.118	4.696	5.270	6.071
54	8.364	9.996	13.064	4.686	5.255	6.048
55	8.344	9.968	13.012	4.676	5.242	6.026
56	8.326	9.940	12.962	4.666	5.228	6.005
57	8.308	9.914	12.914	4.657	5.216	5.985
58	8.290	9.889	12.867	4.648	5.203	5.965
59	8.273	9.864	12.822	4.639	5.191	5.946
60	8.257	9.840	12.778	4.631	5.179	5.927
61	8.241	9.817	12.735	4.622	5.168	5.909
62	8.225	9.794	12.694	4.614	5.157	5.892
63	8.210	9.772	12.654	4.606	5.146	5.875
64	8.195	9.751	12.615	4.599	5.135	5.858
65	8.181	9.730	12.577	4.591	5.125	5.842
66	8.167	9.709	12.541	4.584	5.115	5.827
67	8.153	9.690	12.505	4.577	5.106	5.811
68	8.140	9.671	12.470	4.570	5.096	5.797
69	8.127	9.652	12.436	4.563	5.087	5.782
70	8.114	9.634	12.404	4.557	5.078	5.769
71	8.102	9.616	12.372	4.550	5.069	5.755
72	8.090	9.598	12.340	4.544	5.061	5.742
73	8.078	9.581	12.310	4.538	5.053	5.729
74	8.067	9.565	12.280	4.532	5.044	5.716
75	8.055	9.549	12.252	4.526	5.036	5.704
76	8.044	9.533	12.223	4.520	5.029	5.692
77	8.034	9.517	12.196	4.515	5.021	5.681
78	8.023	9.502	12.169	4.509	5.014	5.669
79	8.013	9.487	12.143	4.504	5.006	5.658
80	8.003	9.473	12.117	4.499	4.999	5.647
81	7.993	9.459	12.092	4.494	4.992	5.637
82	7.983	9.445	12.067	4.489	4.986	5.626
83	7.974	9.431	12.043	4.484	4.979	5.616
84	7.964	9.418	12.020	4.479	4.973	5.606
85	7.955	9.405	11.997	4.474	4.966	5.596
86	7.946	9.392	11.975	4.470	4.960	5.587
87	7.938	9.380	11.952	4.465	4.954	5.578
88	7.929	9.367	11.931	4.461	4.948	5.568
89	7.921	9.355	11.910	4.456	4.942	5.559



**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.8. One-Sided Tolerance Factors for the Three-Parameter Weibull Distribution with 95 Percent Confidence (Continued)**

N	V <sub>99</sub> for T <sub>99</sub>			V <sub>90</sub> for T <sub>90</sub>		
	Uncensored	20% Censored	50% Censored	Uncensored	20% Censored	50% Censored
90	7.912	9.344	11.889	4.452	4.936	5.551
91	7.904	9.332	11.869	4.448	4.930	5.542
92	7.896	9.321	11.849	4.444	4.925	5.534
93	7.888	9.309	11.829	4.440	4.919	5.525
94	7.881	9.298	11.810	4.436	4.914	5.517
95	7.873	9.288	11.791	4.432	4.909	5.509
96	7.866	9.277	11.773	4.428	4.904	5.502
97	7.859	9.267	11.755	4.424	4.899	5.494
98	7.851	9.257	11.737	4.420	4.894	5.486
99	7.844	9.247	11.720	4.417	4.889	5.479
100	7.837	9.237	11.703	4.413	4.884	5.472
102	7.824	9.217	11.669	4.406	4.874	5.458
104	7.811	9.199	11.637	4.399	4.865	5.444
106	7.798	9.181	11.606	4.393	4.857	5.431
108	7.786	9.163	11.576	4.387	4.848	5.418
110	7.774	9.146	11.546	4.380	4.840	5.406
112	7.762	9.130	11.518	4.374	4.832	5.394
114	7.751	9.114	11.491	4.369	4.824	5.382
116	7.740	9.099	11.464	4.363	4.816	5.371
118	7.729	9.084	11.439	4.357	4.809	5.360
120	7.719	9.069	11.414	4.352	4.802	5.349
122	7.709	9.055	11.389	4.347	4.795	5.339
124	7.699	9.041	11.366	4.342	4.788	5.329
126	7.690	9.028	11.343	4.337	4.782	5.319
128	7.680	9.015	11.320	4.332	4.775	5.310
130	7.671	9.002	11.299	4.327	4.769	5.301
132	7.663	8.989	11.278	4.323	4.763	5.292
134	7.654	8.977	11.257	4.318	4.757	5.283
136	7.646	8.965	11.237	4.314	4.751	5.275
138	7.637	8.954	11.217	4.310	4.746	5.266
140	7.629	8.943	11.198	4.306	4.740	5.258
142	7.622	8.932	11.180	4.302	4.735	5.250
144	7.614	8.921	11.161	4.298	4.730	5.243
146	7.606	8.910	11.144	4.294	4.724	5.235
148	7.599	8.900	11.126	4.290	4.719	5.228
150	7.592	8.890	11.109	4.286	4.715	5.221
152	7.585	8.880	11.093	4.283	4.710	5.214
154	7.578	8.871	11.077	4.279	4.705	5.207
156	7.571	8.861	11.061	4.276	4.700	5.200
158	7.565	8.852	11.045	4.272	4.696	5.194
160	7.558	8.843	11.030	4.269	4.692	5.187

**MIL-HDBK-5H****1 December 1998****Table 9.6.4.8. One-Sided Tolerance Factors for the Three-Parameter Weibull Distribution with 95 Percent Confidence (Continued)**

N	V <sub>99</sub> for T <sub>99</sub>			V <sub>90</sub> for T <sub>90</sub>		
	Uncensored	20% Censored	50% Censored	Uncensored	20% Censored	50% Censored
162	7.552	8.834	11.015	4.266	4.687	5.181
164	7.546	8.826	11.001	4.263	4.683	5.175
166	7.540	8.817	10.987	4.260	4.679	5.169
168	7.534	8.809	10.973	4.257	4.675	5.163
170	7.528	8.801	10.959	4.254	4.671	5.157
172	7.522	8.793	10.946	4.251	4.667	5.151
174	7.517	8.785	10.932	4.248	4.663	5.146
176	7.511	8.777	10.920	4.245	4.659	5.140
178	7.506	8.770	10.907	4.242	4.656	5.135
180	7.501	8.762	10.894	4.239	4.652	5.130
182	7.495	8.755	10.882	4.237	4.649	5.125
184	7.490	8.748	10.870	4.234	4.645	5.120
186	7.485	8.741	10.859	4.231	4.642	5.115
188	7.480	8.734	10.847	4.229	4.638	5.110
190	7.475	8.727	10.836	4.226	4.635	5.105
192	7.471	8.720	10.825	4.224	4.632	5.100
194	7.466	8.714	10.814	4.221	4.629	5.096
196	7.461	8.707	10.803	4.219	4.625	5.091
198	7.457	8.701	10.793	4.217	4.622	5.087
200	7.452	8.695	10.782	4.214	4.619	5.082
204	7.443	8.683	10.762	4.210	4.613	5.074
208	7.435	8.671	10.742	4.206	4.608	5.066
212	7.427	8.659	10.724	4.201	4.602	5.058
216	7.419	8.648	10.705	4.197	4.597	5.050
220	7.411	8.638	10.687	4.193	4.591	5.042
224	7.404	8.627	10.670	4.189	4.586	5.035
228	7.396	8.617	10.653	4.186	4.581	5.028
232	7.389	8.607	10.637	4.182	4.576	5.021
236	7.382	8.597	10.621	4.178	4.572	5.014
240	7.375	8.588	10.606	4.175	4.567	5.008
244	7.369	8.579	10.591	4.171	4.563	5.002
248	7.363	8.570	10.576	4.168	4.559	4.995
252	7.356	8.562	10.562	4.165	4.554	4.990
256	7.350	8.553	10.548	4.162	4.550	4.984
260	7.344	8.545	10.535	4.159	4.546	4.978
264	7.339	8.537	10.522	4.156	4.542	4.972
268	7.333	8.529	10.509	4.153	4.539	4.967
272	7.327	8.522	10.497	4.150	4.535	4.962
276	7.322	8.514	10.485	4.147	4.531	4.957
280	7.317	8.507	10.473	4.145	4.528	4.952
284	7.312	8.500	10.461	4.142	4.524	4.947

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.8. One-Sided Tolerance Factors for the Three-Parameter Weibull Distribution with 95 Percent Confidence (Continued)**

N	V <sub>99</sub> for T <sub>99</sub>			V <sub>90</sub> for T <sub>90</sub>		
	Uncensored	20% Censored	50% Censored	Uncensored	20% Censored	50% Censored
288	7.307	8.493	10.450	4.139	4.521	4.942
292	7.302	8.486	10.439	4.137	4.518	4.937
296	7.297	8.479	10.428	4.134	4.514	4.933
300	7.292	8.473	10.417	4.132	4.511	4.928
310	7.281	8.457	10.392	4.126	4.504	4.917
320	7.270	8.442	10.368	4.121	4.496	4.907
330	7.260	8.428	10.345	4.115	4.489	4.898
340	7.250	8.415	10.323	4.110	4.483	4.888
350	7.241	8.402	10.302	4.106	4.477	4.880
360	7.232	8.390	10.282	4.101	4.471	4.871
370	7.223	8.378	10.263	4.097	4.465	4.863
380	7.215	8.367	10.245	4.092	4.459	4.855
390	7.207	8.356	10.227	4.088	4.454	4.848
400	7.200	8.346	10.211	4.084	4.449	4.841
425	7.182	8.321	10.172	4.075	4.437	4.825
450	7.166	8.299	10.136	4.067	4.427	4.810
475	7.151	8.279	10.104	4.060	4.417	4.796
500	7.138	8.261	10.074	4.053	4.408	4.783
525	7.125	8.244	10.047	4.046	4.400	4.772
550	7.114	8.228	10.021	4.040	4.392	4.761
575	7.103	8.213	9.997	4.035	4.385	4.751
600	7.093	8.199	9.975	4.030	4.378	4.742
625	7.083	8.186	9.955	4.025	4.372	4.733
650	7.074	8.174	9.935	4.020	4.366	4.725
675	7.066	8.162	9.917	4.016	4.360	4.717
700	7.058	8.152	9.900	4.012	4.355	4.710
725	7.050	8.141	9.884	4.008	4.350	4.703
750	7.043	8.132	9.868	4.004	4.345	4.697
775	7.037	8.123	9.854	4.001	4.341	4.690
800	7.030	8.114	9.840	3.998	4.337	4.685
825	7.024	8.106	9.827	3.994	4.332	4.679
850	7.018	8.098	9.814	3.991	4.329	4.674
875	7.013	8.090	9.802	3.989	4.325	4.669
900	7.007	8.083	9.791	3.986	4.321	4.664
925	7.002	8.076	9.780	3.983	4.318	4.659
950	6.997	8.069	9.769	3.981	4.315	4.655
975	6.993	8.063	9.759	3.978	4.312	4.651
1000	6.988	8.057	9.750	3.976	4.309	4.646
1100	6.972	8.034	9.714	3.968	4.298	4.632
1200	6.957	8.015	9.684	3.960	4.288	4.619
1300	6.945	7.998	9.657	3.954	4.280	4.608

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.8. One-Sided Tolerance Factors for the Three-Parameter Weibull Distribution with 95 Percent Confidence (Continued)**

N	V <sub>99</sub> for T <sub>99</sub>			V <sub>90</sub> for T <sub>90</sub>		
	Uncensored	20% Censored	50% Censored	Uncensored	20% Censored	50% Censored
1400	6.934	7.983	9.633	3.948	4.273	4.597
1500	6.924	7.969	9.612	3.943	4.266	4.589
1600	6.914	7.957	9.593	3.938	4.260	4.580
1700	6.906	7.946	9.575	3.934	4.255	4.573
1800	6.899	7.936	9.560	3.930	4.250	4.567
1900	6.892	7.926	9.545	3.927	4.246	4.560
2000	6.886	7.918	9.532	3.923	4.241	4.555
3000	6.841	7.858	9.438	3.901	4.212	4.515
4000	6.815	7.822	9.383	3.887	4.195	4.492
5000	6.797	7.798	9.346	3.878	4.183	4.477
6000	6.784	7.781	9.319	3.871	4.175	4.465
7000	6.773	7.767	9.298	3.866	4.168	4.456
8000	6.765	7.756	9.281	3.862	4.163	4.449
9000	6.758	7.747	9.267	3.859	4.159	4.443
10000	6.753	7.739	9.255	3.856	4.155	4.438
15000	6.733	7.713	9.215	3.846	4.142	4.422
20000	6.722	7.698	9.192	3.840	4.135	4.412
25000	6.714	7.688	9.176	3.836	4.130	4.405
30000	6.708	7.680	9.164	3.833	4.126	4.400

The values provided in Table 9.6.4.8 are calculated by the following formula:

$$d^{-1} \left\{ c k_n \frac{(a_{11} + 2a_{01}g(p) + a_{00}g(p)^2 + c^2(a_{01}^2 - a_{00}a_{11})/n)^{1/2}}{1 - c^2 a_{00}/n} + n^{1/2} \left[ g(p) - k_n \frac{g(p) + c^2 a_{01}/n}{1 - c^2 a_{00}/n} \right] \right\}$$

where  $d=0.7796968$ ,  $c=1.645$ ,  $k_n=(n/(n-1))^{1/2}$ ,  $p$  is the percentile being estimated ( $T_{99}$ :  $p=0.01$ ,  $T_{90}$ :  $p=0.10$ ), and  $g(p)=0.45 + 0.7797 \ln(-\ln(1-p))$ . The constants  $a_{00}$ ,  $a_{01}$ , and  $a_{11}$  depend on the level of censoring, and are given below. The statistical methodology employed here is discussed in detail in Reference 9.6.4.8.

Constant	Uncensored	20% Censored	50% Censored
$a_{00}$	0.6079	0.9282	1.7162
$a_{01}$	-0.4740	-0.4562	-0.0428
$a_{11}$	0.9775	0.9841	1.2169

**Table 9.6.4.9. 0.950 Fractiles of the F Distribution Associated with  $n_1$  and  $n_2$  Degrees of Freedom**

$n_2^a$	$n_1$ , degrees of freedom for numerator																		
	1	2	3	4	5	6	7	8	9	10	12	15	20	24	30	40	60	120	$\infty$
1	161.4	199.5	215.7	224.6	230.2	234.0	236.8	238.9	240.5	241.9	243.9	245.9	248.0	249.0	250.1	251.1	252.2	253.2	254.3
2	18.51	19.00	19.16	19.25	19.30	19.33	19.35	19.37	19.38	19.40	19.41	19.43	19.45	19.45	19.46	19.47	19.48	19.49	19.51
3	10.13	9.55	9.28	9.12	9.01	8.94	8.89	8.85	8.81	8.79	8.74	8.70	8.66	8.64	8.62	8.59	8.57	8.55	8.53
4	7.71	6.94	6.59	6.39	6.26	6.16	6.09	6.04	6.00	5.96	5.91	5.86	5.80	5.77	5.75	5.72	5.69	5.66	5.63
5	6.61	5.79	5.41	5.19	5.05	4.95	4.88	4.82	4.77	4.74	4.68	4.62	4.56	4.53	4.50	4.46	4.43	4.40	4.37
6	5.99	5.14	4.76	4.53	4.39	4.28	4.21	4.15	4.10	4.06	4.00	3.94	3.87	3.84	3.81	3.77	3.74	3.70	3.67
7	5.59	4.74	4.35	4.12	3.97	3.87	3.79	3.73	3.68	3.64	3.57	3.51	3.44	3.41	3.38	3.34	3.30	3.27	3.23
8	5.32	4.46	4.07	3.84	3.69	3.58	3.50	3.44	3.39	3.35	3.28	3.22	2.15	3.12	3.08	3.04	3.01	2.97	2.93
9	5.12	4.26	3.86	3.63	3.48	3.37	3.29	3.23	3.18	3.14	3.07	3.01	2.94	2.90	2.86	2.83	2.79	2.75	2.71
10	4.96	4.10	3.71	3.48	3.33	3.22	3.14	3.07	3.02	2.98	2.91	2.85	2.77	2.74	2.70	2.66	2.62	2.58	2.54
11	4.84	3.98	3.59	3.36	3.20	3.09	3.01	2.95	2.90	2.85	2.79	2.72	2.65	2.61	2.57	2.53	2.49	2.45	2.40
12	4.75	3.89	3.49	3.26	3.11	3.00	2.91	2.85	2.80	2.75	2.69	2.62	2.54	2.51	2.47	2.43	2.38	2.34	2.30
13	4.67	3.81	3.41	3.18	3.03	2.92	2.83	2.77	2.71	2.67	2.60	2.53	2.46	2.42	2.38	2.34	2.30	2.25	2.21
14	4.60	3.74	3.34	3.11	2.96	2.85	2.76	2.70	2.65	2.60	2.53	2.46	2.39	2.35	2.31	2.27	2.22	2.18	2.13
15	4.54	3.68	3.29	3.06	2.90	2.79	2.71	2.64	2.59	2.54	2.48	2.40	2.33	2.29	2.25	2.20	2.16	2.11	2.07
16	4.49	3.63	3.24	3.01	2.85	2.74	2.66	2.59	2.54	2.49	2.42	2.35	2.28	2.24	2.19	2.15	2.11	2.06	2.01
17	4.45	3.59	3.20	2.96	2.81	2.70	2.61	2.55	2.49	2.45	2.38	2.31	2.23	2.19	2.15	2.10	2.06	2.01	1.96
18	4.41	3.55	3.16	2.93	2.77	2.66	2.58	2.51	2.46	2.41	2.34	2.27	2.19	2.15	2.11	2.06	2.02	1.97	1.92
19	4.38	3.52	3.13	2.90	2.74	2.63	2.54	2.48	2.42	2.38	2.31	2.23	2.16	2.11	2.07	2.03	1.98	1.93	1.88
20	4.35	3.49	3.10	2.87	2.71	2.60	2.51	2.45	2.39	2.35	2.28	2.20	2.12	2.08	2.04	1.99	1.95	1.90	1.84
21	4.32	3.47	3.07	2.84	2.68	2.57	2.49	2.42	2.37	2.32	2.25	2.18	2.10	2.05	2.01	1.96	1.92	1.87	1.81
22	4.30	3.44	3.05	2.82	2.66	2.55	2.46	2.40	2.34	2.30	2.23	2.15	2.07	2.03	1.98	1.94	1.89	1.84	1.78
23	4.28	3.42	3.03	2.80	2.64	2.53	2.44	2.37	2.32	2.27	2.20	2.13	2.05	2.01	1.96	1.91	1.86	1.81	1.76
24	4.26	3.40	3.01	2.78	2.62	2.51	2.42	2.36	2.30	2.25	2.18	2.11	2.03	1.98	1.94	1.89	1.84	1.79	1.73
25	4.24	3.39	2.99	2.76	2.60	2.49	2.40	2.34	2.28	2.24	2.16	2.09	2.01	1.96	1.92	1.87	1.82	1.77	1.71
26	4.23	3.37	2.98	2.74	2.59	2.47	2.39	2.32	2.27	2.22	2.15	2.07	1.99	1.95	1.90	1.85	1.80	1.75	1.69
27	4.21	3.35	2.96	2.73	2.57	2.46	2.37	2.31	2.25	2.20	2.13	2.06	1.97	1.93	1.88	1.84	1.79	1.73	1.67
28	4.20	3.34	2.95	2.71	2.56	2.45	2.36	2.29	2.24	2.19	2.12	2.04	1.96	1.91	1.87	1.82	1.77	1.71	1.65
29	4.18	3.33	2.93	2.70	2.55	2.43	2.35	2.28	2.22	2.18	2.10	2.03	1.94	1.90	1.85	1.81	1.75	1.70	1.64
30	4.17	3.32	2.92	2.69	2.53	2.42	2.33	2.27	2.21	2.16	2.09	2.01	1.93	1.89	1.84	1.79	1.74	1.68	1.62
40	4.08	3.23	2.84	2.61	2.45	2.34	2.25	2.18	2.12	2.08	2.00	1.92	1.84	1.79	1.74	1.69	1.64	1.58	1.51
60	4.00	3.15	2.76	2.53	2.37	2.25	2.17	2.10	2.04	1.99	1.92	1.84	1.75	1.70	1.65	1.59	1.53	1.47	1.39
120	3.92	3.07	2.68	2.45	2.29	2.18	2.09	2.02	1.96	1.91	1.83	1.75	1.66	1.61	1.55	1.50	1.43	1.35	1.25
$\infty$	3.84	3.00	2.61	2.37	2.21	2.10	2.01	1.94	1.88	1.83	1.75	1.67	1.57	1.52	1.46	1.39	1.32	1.22	1.00

a  $n_2$  = degrees of freedom for denominator.

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.10.  $\gamma$ -values for Computing Threshold of Three-Parameter Weibull Distribution**

n	Anderson-Darling Test		$T_{90}$			$T_{99}$		
	Uncensored or 20% Censored	50% Censored	Uncensored	20% Censored	50% Censored	Uncensored	20% Censored	50% Censored
	$\gamma_{50,0}$ or $\gamma_{50,20}$	$\gamma_{50,50}$	$\gamma_{90,0}$	$\gamma_{90,20}$	$\gamma_{90,50}$	$\gamma_{99,0}$	$\gamma_{99,20}$	$\gamma_{99,50}$
10	0.50000	.	0.79644	0.85391	.	0.85162	0.86596	.
15	0.60692	0.50000	0.75277	0.78329	0.97146	0.81292	0.81934	0.86090
20	0.62147	0.57859	0.73316	0.75477	0.91726	0.79728	0.80072	0.83039
25	0.63033	0.60692	0.72186	0.73795	0.86979	0.78583	0.78741	0.80818
30	0.64057	0.62147	0.71316	0.72479	0.83400	0.77155	0.77185	0.79208
35	0.64379	0.62147	0.70831	0.71771	0.81708	0.76529	0.76477	0.78734
40	0.64630	0.63033	0.70472	0.71247	0.79441	0.76006	0.75893	0.77634
45	0.64997	0.63629	0.70113	0.70736	0.77717	0.75255	0.75101	0.76759
50	0.65135	0.64057	0.69900	0.70434	0.76374	0.74903	0.74714	0.76046
55	0.65252	0.64379	0.69724	0.70187	0.75306	0.74592	0.74376	0.75451
60	0.65440	0.64630	0.69522	0.69914	0.74440	0.74113	0.73882	0.74947
65	0.65516	0.64630	0.69401	0.69748	0.73985	0.73881	0.73632	0.74809
70	0.65583	0.64832	0.69296	0.69605	0.73347	0.73670	0.73406	0.74395
75	0.65697	0.64997	0.69163	0.69433	0.72810	0.73331	0.73062	0.74033
80	0.65745	0.65135	0.69084	0.69327	0.72352	0.73164	0.72885	0.73713
85	0.65789	0.65252	0.69013	0.69233	0.71959	0.73009	0.72721	0.73428
90	0.65865	0.65353	0.68917	0.69113	0.71618	0.72753	0.72464	0.73172
95	0.65898	0.65353	0.68860	0.69040	0.71433	0.72625	0.72330	0.73107
100	0.65929	0.65440	0.68808	0.68973	0.71157	0.72505	0.72206	0.72882
105	0.65983	0.65516	0.68735	0.68884	0.70912	0.72303	0.72004	0.72678
110	0.66007	0.65583	0.68692	0.68829	0.70694	0.72201	0.71899	0.72491
115	0.66030	0.65643	0.68652	0.68779	0.70499	0.72105	0.71799	0.72319
120	0.66071	0.65697	0.68593	0.68709	0.70323	0.71940	0.71636	0.72160
125	0.66090	0.65697	0.68559	0.68667	0.70229	0.71857	0.71551	0.72122
130	0.66107	0.65745	0.68528	0.68628	0.70079	0.71778	0.71469	0.71978
135	0.66139	0.65789	0.68479	0.68571	0.69942	0.71640	0.71334	0.71844
140	0.66154	0.65828	0.68452	0.68537	0.69817	0.71570	0.71263	0.71718
145	0.66167	0.65865	0.68425	0.68506	0.69702	0.71503	0.71195	0.71601
150	0.66193	0.65898	0.68385	0.68459	0.69597	0.71385	0.71080	0.71491
155	0.66205	0.65898	0.68361	0.68431	0.69541	0.71325	0.71019	0.71466
160	0.66216	0.65929	0.68339	0.68404	0.69448	0.71268	0.70961	0.71364
165	0.66237	0.65957	0.68304	0.68365	0.69361	0.71166	0.70862	0.71268
170	0.66247	0.65983	0.68284	0.68341	0.69281	0.71114	0.70810	0.71177
175	0.66256	0.66007	0.68266	0.68319	0.69206	0.71064	0.70760	0.71091
180	0.66273	0.66030	0.68235	0.68285	0.69135	0.70975	0.70673	0.71010
185	0.66282	0.66030	0.68218	0.68265	0.69100	0.70930	0.70628	0.70992
190	0.66289	0.66051	0.68201	0.68245	0.69036	0.70886	0.70584	0.70915
195	0.66304	0.66071	0.68174	0.68215	0.68977	0.70806	0.70507	0.70842
200	0.66311	0.66090	0.68159	0.68198	0.68921	0.70766	0.70467	0.70773
205	0.66318	0.66107	0.68145	0.68181	0.68868	0.70727	0.70428	0.70706
210	0.66331	0.66123	0.68121	0.68155	0.68818	0.70656	0.70360	0.70643
215	0.66337	0.66123	0.68108	0.68140	0.68793	0.70620	0.70324	0.70630
220	0.66342	0.66139	0.68095	0.68125	0.68747	0.70585	0.70289	0.70570
225	0.66353	0.66154	0.68073	0.68101	0.68704	0.70521	0.70228	0.70512
230	0.66358	0.66167	0.68061	0.68088	0.68663	0.70489	0.70196	0.70456
235	0.66364	0.66181	0.68049	0.68075	0.68623	0.70457	0.70165	0.70403
240	0.66373	0.66193	0.68030	0.68053	0.68586	0.70399	0.70109	0.70352
245	0.66378	0.66193	0.68019	0.68041	0.68568	0.70370	0.70080	0.70342
250	0.66382	0.66205	0.68009	0.68029	0.68533	0.70341	0.70052	0.70293
255	0.66391	0.66216	0.67991	0.68010	0.68500	0.70288	0.70002	0.70246
260	0.66395	0.66227	0.67981	0.67999	0.68468	0.70261	0.69975	0.70200

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.10.  $\gamma$ -values for Computing Threshold of Three-Parameter Weibull Distribution (Continued)**

n	Anderson-Darling Test		$T_{90}$			$T_{99}$		
	Uncensored or 20% Censored	50% Censored	Uncensored	20% Censored	50% Censored	Uncensored	20% Censored	50% Censored
	$\gamma_{50,0}$ or $\gamma_{50,20}$	$\gamma_{50,50}$	$\gamma_{90,0}$	$\gamma_{90,20}$	$\gamma_{90,50}$	$\gamma_{99,0}$	$\gamma_{99,20}$	$\gamma_{99,50}$
265	0.66399	0.66237	0.67971	0.67989	0.68438	0.70235	0.69949	0.70157
270	0.66406	0.66247	0.67955	0.67971	0.68409	0.70186	0.69903	0.70114
275	0.66410	0.66247	0.67946	0.67961	0.68396	0.70161	0.69879	0.70106
280	0.66413	0.66256	0.67937	0.67951	0.68368	0.70137	0.69855	0.70066
285	0.66420	0.66265	0.67922	0.67935	0.68342	0.70093	0.69813	0.70026
290	0.66423	0.66273	0.67914	0.67926	0.68317	0.70070	0.69790	0.69988
295	0.66426	0.66282	0.67906	0.67917	0.68293	0.70047	0.69768	0.69951
300	0.66433	0.66289	0.67892	0.67902	0.68269	0.70006	0.69729	0.69916
310	0.66438	0.66297	0.67877	0.67886	0.68237	0.69964	0.69688	0.69875
320	0.66446	0.66311	0.67857	0.67864	0.68195	0.69906	0.69633	0.69809
330	0.66454	0.66324	0.67838	0.67844	0.68156	0.69851	0.69580	0.69747
340	0.66459	0.66331	0.67825	0.67830	0.68130	0.69815	0.69545	0.69711
350	0.66466	0.66342	0.67807	0.67811	0.68095	0.69764	0.69497	0.69654
360	0.66472	0.66353	0.67790	0.67794	0.68063	0.69716	0.69451	0.69600
370	0.66476	0.66358	0.67779	0.67781	0.68041	0.69684	0.69420	0.69570
380	0.66482	0.66368	0.67764	0.67765	0.68012	0.69639	0.69378	0.69520
390	0.66487	0.66378	0.67749	0.67749	0.67984	0.69596	0.69337	0.69472
400	0.66490	0.66382	0.67739	0.67739	0.67965	0.69568	0.69310	0.69446
425	0.66501	0.66399	0.67707	0.67706	0.67912	0.69477	0.69224	0.69356
450	0.66511	0.66417	0.67678	0.67675	0.67858	0.69395	0.69146	0.69258
475	0.66519	0.66430	0.67655	0.67651	0.67816	0.69328	0.69083	0.69185
500	0.66526	0.66441	0.67631	0.67626	0.67778	0.69258	0.69017	0.69117
525	0.66534	0.66452	0.67608	0.67602	0.67743	0.69193	0.68955	0.69054
550	0.66539	0.66461	0.67589	0.67583	0.67711	0.69140	0.68906	0.68995
575	0.66545	0.66470	0.67569	0.67562	0.67682	0.69083	0.68852	0.68940
600	0.66550	0.66480	0.67551	0.67543	0.67652	0.69030	0.68802	0.68879
625	0.66554	0.66487	0.67536	0.67528	0.67627	0.68986	0.68762	0.68832
650	0.66559	0.66494	0.67519	0.67511	0.67604	0.68939	0.68718	0.68788
675	0.66563	0.66500	0.67503	0.67495	0.67583	0.68895	0.68676	0.68746
700	0.66567	0.66506	0.67490	0.67481	0.67563	0.68859	0.68642	0.68706
725	0.66570	0.66511	0.67476	0.67467	0.67545	0.68819	0.68605	0.68669
750	0.66574	0.66517	0.67463	0.67454	0.67524	0.68781	0.68570	0.68626
775	0.66576	0.66522	0.67452	0.67442	0.67508	0.68750	0.68541	0.68593
800	0.66579	0.66526	0.67440	0.67430	0.67493	0.68715	0.68509	0.68561
825	0.66582	0.66531	0.67428	0.67418	0.67478	0.68683	0.68479	0.68531
850	0.66584	0.66534	0.67419	0.67409	0.67464	0.68656	0.68454	0.68502
875	0.66587	0.66538	0.67408	0.67398	0.67451	0.68626	0.68426	0.68474
900	0.66589	0.66542	0.67398	0.67387	0.67437	0.68597	0.68400	0.68442
925	0.66591	0.66546	0.67389	0.67379	0.67425	0.68573	0.68377	0.68417
950	0.66593	0.66549	0.67380	0.67369	0.67414	0.68547	0.68353	0.68393
975	0.66595	0.66552	0.67371	0.67360	0.67403	0.68521	0.68330	0.68369
1000	0.66597	0.66554	0.67363	0.67353	0.67393	0.68500	0.68310	0.68347
1000	0.66597	0.66554	0.67363	0.67353	0.67393	0.68500	0.68310	0.68347
1100	0.66603	0.66565	0.67332	0.67322	0.67354	0.68414	0.68231	0.68262
1200	0.66609	0.66574	0.67305	0.67295	0.67321	0.68339	0.68162	0.68188
1300	0.66613	0.66581	0.67282	0.67271	0.67294	0.68275	0.68103	0.68126
1400	0.66617	0.66587	0.67261	0.67250	0.67269	0.68216	0.68049	0.68069
1500	0.66620	0.66592	0.67241	0.67231	0.67246	0.68162	0.68000	0.68017
1600	0.66623	0.66597	0.67225	0.67214	0.67227	0.68116	0.67958	0.67973
1700	0.66626	0.66601	0.67209	0.67198	0.67209	0.68072	0.67918	0.67931
1800	0.66628	0.66605	0.67194	0.67184	0.67193	0.68032	0.67882	0.67893

**MIL-HDBK-5H**  
**1 December 1998**

**Table 9.6.4.10.  $\gamma$ -values for Computing Threshold of Three-Parameter Weibull Distribution (Continued)**

n	Anderson-Darling Test		$T_{90}$			$T_{99}$		
	Uncensored or 20% Censored	50% Censored	Uncensored	20% Censored	50% Censored	Uncensored	20% Censored	50% Censored
	$\gamma_{50,0}$ or $\gamma_{50,20}$	$\gamma_{50,50}$	$\gamma_{90,0}$	$\gamma_{90,20}$	$\gamma_{90,50}$	$\gamma_{99,0}$	$\gamma_{99,20}$	$\gamma_{99,50}$
1900	0.66630	0.66608	0.67181	0.67171	0.67179	0.67997	0.67849	0.67859
2000	0.66632	0.66611	0.67168	0.67158	0.67165	0.67963	0.67819	0.67827
2000	0.66632	0.66611	0.67168	0.67158	0.67165	0.67963	0.67819	0.67827
3000	0.66643	0.66630	0.67080	0.67071	0.67072	0.67725	0.67604	0.67604
4000	0.66649	0.66639	0.67027	0.67019	0.67017	0.67584	0.67477	0.67474
5000	0.66653	0.66644	0.66990	0.66983	0.66981	0.67487	0.67390	0.67385
6000	0.66655	0.66648	0.66963	0.66956	0.66953	0.67415	0.67326	0.67321
7000	0.66657	0.66651	0.66942	0.66935	0.66933	0.67360	0.67277	0.67271
8000	0.66658	0.66653	0.66924	0.66919	0.66916	0.67315	0.67237	0.67230
9000	0.66659	0.66654	0.66910	0.66905	0.66902	0.67278	0.67204	0.67197
10000	0.66660	0.66656	0.66898	0.66893	0.66890	0.67247	0.67176	0.67169

The values of  $\gamma$  in Table 9.6.4.10 can be derived as percentiles of the beta distribution as follows. Let  $k$  be the greatest integer less than or equal to the minimum of  $4n/15$  and  $(1-p)n/3$ , where  $n$  represents the sample size and  $p$  represents the proportion of the sample being censored. When determining the  $\gamma$  value for an Anderson-Darling test (when calculating  $\tau_{50}$ ), let  $\theta=0.50$ . When calculating  $\tau_{90}$  or  $\tau_{99}$  let

$$\theta = \frac{\exp(M)}{1 + \exp(M)}$$

where

$$M = \begin{cases} \frac{0.425384 - 0.74068p + 8.12668/n}{0.58478 - 0.97165p} & \text{for calculating } \tau_{90} \\ \frac{1.778 + 2.748/\sqrt{n} + p(7.051/\sqrt{n} - 1.253)}{0.959} & \text{for calculating } \tau_{99}. \end{cases}$$

The value of  $\gamma$  in Table 9.6.4.10 represents the  $\theta$ th percentile of the beta distribution with parameters  $2k-2$  and  $k$ .

Note: The sequential Weibull procedure which makes use of Table 9.6.4.10 has only been validated for sample sizes between 50 and 1000.



**MIL-HDBK-5H**  
**1 December 1998**

**9.6.5 ESTIMATION PROCEDURES FOR THE WEIBULL DISTRIBUTION** — This section describes procedures required for modeling data with the three-parameter Weibull distribution. Section 9.6.5.1 describes a method for estimating the threshold parameter,  $\tau$ . Section 9.6.5.2 describes a method for estimating the shape and scale parameters,  $\beta$  and  $\alpha$ , respectively. Both methods permit estimation with upper-tail censored data. For a good exposition of such procedures, see Reference 9.6.1.2(a).

**9.6.5.1 Estimating the Weibull Population Threshold** — This section describes a method for estimating the threshold of a three-parameter Weibull distribution. The same approach is taken for estimating the threshold, whether the purpose is to test goodness-of-fit (Section 9.6.1.4), or to directly calculate  $T_{99}$  or  $T_{90}$  values (Section 9.2.8). This method applies to uncensored and upper-tail censored data; however, different columns of Table 9.6.4.10 are used. (References 9.2.8(a) and 9.2.8(b) provide details of this method for uncensored data.)

Let  $K$  equal the greatest integer less than or equal to  $\min \{4n/15, (1-p)n/3\}$ , where  $p$  represents the proportion of the upper tail that is censored ( $p$  equals 0, 0.2, or 0.5). Define the function  $R(\tau)$  by

$$R(\tau) = \frac{\sum_{i=K+1}^{3K-2} L_i(\tau)}{\sum_{i=1}^{3K-2} L_i(\tau)}$$

where

$$L_i(\tau) = \frac{1}{D_i} \left[ \ln(X_{(i+1)} - \tau) - \ln(X_{(i)} - \tau) \right]$$

with

$$D_1 = n \ln \left( 1 + \frac{1}{n-1} \right),$$

$$D_2 = \binom{n}{2} \ln \left( 1 + \frac{1}{n(n-2)} \right),$$

$$D_3 = \binom{n}{3} \ln \left( 1 + \frac{2n-3}{(n-1)^3(n-3)} \right),$$

$$D_4 = \binom{n}{4} \ln \left( 1 + \frac{6n^4 - 48n^3 + 140n^2 - 176n + 81}{n(n-4)(n-2)^6} \right),$$

and

$$D_i = \ln \left[ -\ln \left( 1 - \frac{i+0.5}{n+0.25} \right) \right] - \ln \left[ -\ln \left( 1 - \frac{i-0.5}{n+0.25} \right) \right]$$

**MIL-HDBK-5H**  
**1 December 1998**

for  $i=5,6,\dots,3K-2$ . Finally, let  $\bar{X}$  and  $S$  represent the sample mean and sample standard deviation, respectively.

Determine  $\gamma$  using the appropriate column of Table 9.6.4.10. The first set of columns in Table 9.6.4.10 is provided for estimating the threshold,  $\tau_{50}$ , associated with the Anderson-Darling goodness-of-fit test described in Section 9.6.1.4. The second and third sets of columns are provided for estimating  $\tau_{99}$  and  $\tau_{90}$ , which are needed to determine  $T_{99}$  and  $T_{90}$ , as described in Section 9.2.8. Each set of columns includes a column for uncensored data, 20 percent upper-tail censored data, and 50 percent upper-tail censored data.

The estimated threshold parameter,  $\tau$ , is the solution to the equation  $R(\tau) = \gamma$ . The function  $R(\tau)$  is a monotonically decreasing continuous function of  $\tau$ . A simple method for finding the solution is as follows. Start with  $L = \min(0, \bar{X} - 100S)$  and  $H = 0.999999X_{(1)}$ . If  $R(L) \leq \gamma$ , then set  $\tau = L$  or if  $R(H) \geq \gamma$  then set  $\tau = H$ . Otherwise reduce the  $(L,H)$  interval by calculating  $M = (L+H)/2$  and setting  $L = M$  if  $R(M) \geq \gamma$  or by setting  $H = M$  if  $R(M) < \gamma$ . If  $H - L \leq 2\bar{X}/10^6$ , then set  $\tau = M$  and stop. Otherwise, reduce the  $(L,H)$  interval again.

**9.6.5.2 Estimating the Shape and Scale Parameters for the Weibull Distribution** — This section describes a method for estimation of the shape and scale parameters of the two-parameter Weibull distribution based on data which may be censored in the upper tail. Estimates of the shape and scale parameters are based on the original data corrected for the estimated threshold,  $\tau$ . That is, the calculations in this section are performed based on  $Z_{(1)}, \dots, Z_{(n)}$ , where  $Z_{(i)} = X_{(i)} - \tau$ , with  $\tau$  estimated as in Section 9.6.5.1. The assumption is made here that if the data are censored, then only the  $r$  smallest observations in the sample are observed ( $1 \leq r \leq n$ ), where  $r$  is some pre-specified number (often based on a percentage); this is called Type II censoring. Thus, the input to this procedure is a total sample size,  $n$ , a censored sample size,  $r$ , and the sample remaining after censoring  $Z_{(1)}, \dots, Z_{(r)}$ . Define

$$g(\beta) = \frac{\sum_{i=1}^r Z_{(i)}^{\beta} \ln Z_{(i)} + (n-r) Z_{(r)}^{\beta} \ln Z_{(r)}}{\sum_{i=1}^r Z_{(i)}^{\beta} + (n-r) Z_{(r)}^{\beta}} - \frac{1}{\beta} - \frac{1}{r} \sum_{i=1}^r \ln Z_{(i)}$$

**Note:** When implementing the equation for  $g(\beta)$  in software, it may be necessary to divide each  $Z$  term that is raised to the  $\beta$  power by a normalizing factor,  $C$ , in order to avoid computational difficulties. The factor,  $C$ , can be any type of average calculated from the  $Z$  values (e.g., geometric mean of the uncensored  $Z$  values). Because the  $C$ -factor algebraically cancels out of the equation for  $g(\beta)$ , its use does not change the meaning of the equation in any way.

The shape parameter estimate,  $\beta$ , is the solution to the equation  $g(\beta) = 0$ . The function  $g(\beta)$  is a monotonically increasing continuous function of  $\beta$ . A simple method for finding the solution is as follows. Let  $S_y$  denote the standard deviation of  $Y_1, \dots, Y_r$  where  $Y_i = \ln(Z_i)$  for  $i=1, \dots, r$ . Calculate  $I = 1.28/S_y$  as an initial guess at the solution and calculate  $g(I)$ . If  $g(I) > 0$ , then find the smallest positive integer  $k$  such that  $g(I/2^k) < 0$  and let  $L = I/2^k$  and  $H = I/2^{k-1}$ . If  $g(I) < 0$ , then find the smallest positive integer  $k$  such that  $g(2^k I) > 0$  and let  $L = 2^{k-1} I$ , and  $H = 2^k I$ . Reduce the  $(L,H)$  interval by calculating  $M = (L+H)/2$  and setting  $L = M$  if  $g(M) \leq 0$  and/or by setting  $H = M$  if  $g(M) \geq 0$ . If  $H-L \leq 2I/10^6$ , then set  $\beta = M$  and stop. Otherwise, reduce the  $(L,H)$  interval again.

**MIL-HDBK-5H**  
**1 December 1998**

Once  $\beta$  has been determined, the scale parameter estimate is defined by

$$\alpha = \left( \frac{1}{r} \left( \sum_{i=1}^r Z_{(i)}^{\beta} + (n-r) Z_{(r)}^{\beta} \right) \right)^{\frac{1}{\beta}}.$$

## REFERENCES

- 9.2.7.2(a) Weissberg, A., and Beatty, G. H., "Tables of Tolerance-Limit Factors for Normal Distributors", Battelle Memorial Institute (December 1969).
- 9.2.7.2(b) Owen, D. B., "Tables of Factors for One-Sided Tolerance Limits for a Normal Distribution", Sandia Corporation (April 1958).
- 9.2.7.2(c) Owen, D. B., *Handbook of Statistical Tables*, Addison-Wesley (1962).
- 9.2.7.2(d) Guenther, W. C., *Concepts of Statistical Inference*, McGraw-Hill (1965).
- 9.2.8(a) Jones, R. A., and Scholz, F. W., "A and B-Allowables for the Three Parameter Weibull Distribution", Boeing Computer Services Company Technical Report No. 10 (October 1983).
- 9.2.8(b) Jones, R. A., and Scholz, F. W., "Tolerance Limits for the Three Parameter Weibull Distribution", Boeing Computer Service Company Technical Report No. 11 (1983).
- 9.3.2.4(a) Ramberg, W., and Osgood, W. R., "Description of Stress Strain Curves by Three Parameters", National Advisory Committee for Aeronautics, Technical Note 902 (July 1943).
- 9.3.2.4(b) Hill, H. N., "Determination of Stress-Strain Relations from Offset Yield Strength Values", National Advisory Committee for Aeronautics, Technical Note 927 (February 1944).
- 9.3.3 Burt, C. W., et al., "Mechanical Properties of Aerospace Structural Alloys Under Biaxial-Stress Conditions", AFML-TR-66-229 (August 1966).
- 9.3.4.1(a) "Constant-Amplitude Low-Cycle Fatigue Testing", ASTM Standard Recommended Practice E606.
- 9.3.4.1(b) Landgraf, R. W., "The Resistance of Metals to Cyclic Deformation", Achievement of High Fatigue Resistance in Metals and Alloys, ASTM STP 467, 1970, pp. 3-36.
- 9.3.4.5(a) "Manual on Statistical Planning and Analysis for Fatigue Experiments", ASTM STP 588 (1975).
- 9.3.4.5(b) "Statistical Analysis of Linear or Linearized Stress Life (S-N) and Strain Life ( $\epsilon$ -N) Data", ASTM Standard Practice E739.
- 9.3.4.5(c) ASTM Special Technical Publication No. 91-A, "A Guide for Fatigue Testing and the Statistical Analysis of Fatigue Data", Supplement to Manual on Fatigue Testing, STP No. 91 (1963).

**MIL-HDBK-5H**  
**1 December 1998**

- 9.3.4.5(d) Landgraf, R. W., Morrow, J., and Endo, T., "Determination of the Cyclic Stress-Strain Curve", *Journal of Materials*, JMLSA, Vol. 4, No. 1, March 1969, pp. 176-188.
- 9.3.4.8 Sjodahl, L. H., "Extensions of the Multiple Heat Regression Technique Using Centered Data for Individual Heats", *Progress in Analysis of Fatigue and Stress Rupture (Data)*, MPC-Vol. 23, 1984, pp. 47-86.
- 9.3.4.9(a) Walker, E. K., "The Effect of Stress Ratio During Crack Propagation and Fatigue for 2024-T3 and 7075-T6 Aluminum", *Effect of Environment and Complex Load History on Fatigue Life*, ASTM STP 462 (1970) pp. 1-14.
- 9.3.4.9(b) Stulen, F. L., "Fatigue Life Data Displayed by a Single Quantity Relating Alternating and Mean Stresses", AFML-TR-65-121 (1965).
- 9.3.4.9(c) Topper, T. H., and Sandor, B. I., "Effects of Mean Stress and Prestrain on Fatigue-Damage Summation", *Effects of Environment and Complex Load History on Fatigue Life*, ASTM STP 462, 1970, pp. 93-104.
- 9.3.4.11 Snedecor, G. W., and Cochran, W. G., *Statistical Methods*, Seventh Edition, The Iowa State University Press, Ames, Iowa (1980), pp. 115-116.
- 9.3.4.12 Montgomery, D. C., and Peck, E. A., *Introduction to Linear Regression Analysis*, Wiley, New York (1982).
- 9.3.4.13 Winer, B. J., *Statistic Principles in Experimental Design*, 2nd Ed., McGraw-Hill, New York (1971).
- 9.3.4.14(a) Kalbfleisch, J. D., and Prentice, R. L., *The Statistical Analysis of Failure Time Data*, Wiley, New York (1982).
- 9.3.4.14(b) *SAS Users Guide: Statistical Version 5 ed.*, Cary, N.C.: SAS Institute, Inc. (1985).
- 9.3.6.3 Mandel, J., and Paule, R., "Interlaboratory Evaluation of a Material With Unequal Numbers of Replicates", *Analytical Chemistry*, Vol. 42, No. 11, pp. 1194-1197 (September 1979), correction in Vol. 43, No. 10 (August 1971).
- 9.3.6.5 "Characterization of Materials for Service at Elevated Temperatures", Report No. MPC-7, Presented at 1978 ASME/CSME Montreal Pressure Vessel and Piping Conference, Montreal, Quebec, Canada (June 25-29, 1978).
- 9.4.1.3.1(a) "Military Standard, Fasteners, Test Methods, Test 4, Joint Shear Strength", MIL-STD-1312.
- 9.4.1.3.1(b) "Military Standard, Fasteners, Test Methods, Test 13, Double Shear Test", MIL-STD-1312.
- 9.4.1.3.1(c) "Military Standard, Fasteners, Test Methods, Test 20, Single Shear Test", MIL-STD-1312.
- 9.4.2.1 Hood, D., et al., "An Investigation of the Generation and Utilization of Engineering Data on Weldments", AFML-TR-68-268 (October 1968).

**MIL-HDBK-5H**  
**1 December 1998**

- 9.5.1.4.1 “Standard Method of Test for Plane-Strain Fracture Toughness of Metallic Materials”, ASTM E399.
- 9.5.1.5.1 Feddersen, C. E., “Evaluation and Prediction of the Residual Strength of Center-Cracked Tension Panels”, Damage Tolerance in Aircraft Structures, ASTM STP 486, American Society for Testing and Materials (1971).
- 9.6 Natrella, M. G., *Experimental Statistics*, National Bureau of Standards Handbook 91 (August 1, 1963).
- 9.6.1.2(a) Lawless, J. F., *Statistical Models and Methods for Lifetime Data*, John Wiley and Sons (1982), pp. 452-460.
- 9.6.1.2(b) D’Agostina, R. B. and Stephens, M. A., “Goodness-of-Fit Techniques,” Marcel Dekker, p. 123 (1987).
- 9.6.1.2(c) Pierce, D. A., and Kopecky, K. J., “Testing Goodness of Fit for the Distribution of Errors in Regression Models”, *Biometrika*, 66, pp. 1-5 (1979).
- 9.6.2.5 Scholz, F. W., and Stephens, M. A., “K-Sample Anderson-Darling Tests”, J. Amer. Statist. Assoc., 82, pp. 918-924 (Sept. 1987).
- 9.6.3.3 Neter, J., and Wasserman, W., “Applied Linear Statistical Models”, Richard D. Irwin (1974), pp. 160-165.
- 9.6.4.1 Owen, D. B., “Factors for One-Sided Tolerance Limits and for Variables and Sampling Plans”, Sandia Corporation Monograph SCR-607 (March 1963).
- 9.6.4.3 Johnson, N. L., and Kotz, S., *Distributions in Statistics—Continuous Univariate Distributions—I*, John Wiley & Sons, p. 176 (1970).
- 9.6.4.4 Abramovitz, M., and Stegun, I. A., *Handbook of Mathematical Functions*, National Bureau of Standards, AMS 55, pp. 927, 945, 947 (1970).
- 9.6.4.8 Jones, R. A., Osslander, M., Scholz, F. W., and Shorack, G. R., “Tolerance Bounds for Log-Gamma Regression Models”, *Technometrics*, Vol. 27, No. 2, pp. 109-118 (May 1985).
- 9.6.5.1 Press, W.H., Tenholksy, S.A., Vetterling, W.T., and Flannery, B.P., *Numerical Recipes in C, The Art of Scientific Computing*, Second Edition, Cambridge University Press, pp. 226-228 (1992).

**MIL-HDBK-5H**  
**1 December 1998**

This page intentionally blank.

**MIL-HDBK-5H****1 December 1998****APPENDIX A****A.0 GLOSSARY****A.1 ABBREVIATIONS** (also see Sections 1.2.1, 9.2.2, 9.3.4.3, 9.3.6.2, 9.4.1.2, 9.5.1.2, and 9.6).

a	— Amplitude; crack or flaw dimension; measure of flaw size, inches.
$a_c$	— Critical half crack length.
$a_o$	— Initial half crack length.
A	— Area of cross section, square inches; ratio of alternating stress to mean stress; subscript “axial”; A basis for mechanical-property values (see Section 1.4.1.1 or Section 9.2.2.1); “A” ratio, loading amplitude/mean load; or area.
$A_e$	— Strain “A” ratio, strain amplitude/mean strain.
$A_i$	— Model parameter.
AD	— Anderson-Darling test statistic, computed in goodness-of-fit tests for normality or Weibullness.
AISI	— American Iron and Steel Institute.
AMS	— Aerospace Materials Specification (published by Society of Automotive Engineers, Inc.).
Ann	— Annealed.
AN	— Air Force-Navy Aeronautical Standard.
ASTM	— American Society for Testing and Materials.
b	— Width of sections; subscript “bending”.
br	— Subscript “bearing”.
B	— Biaxial ratio (see Equation 1.3.2.8); B-basis for mechanical-property values (see Section 1.4.1.1 or Section 9.2.2.1).
Btu	— British thermal unit(s).
BUS	— Individual or typical bearing ultimate strength.
BYS	— Individual or typical bearing yield strength.
c	— Fixity coefficient for columns; subscript “compression”.
cpm	— Cycles per minute.
C	— Specific heat; Celsius; Constant.
CEM	— Consumable electrode melted.
CRES	— Corrosion resistant steel (stainless steel).
C(T)	— Compact tension.
CYS	— Individual or typical compressive yield strength.
d	— Mathematical operator denoting differential.
D or d	— Diameter, or Durbin Watson statistic; hole or fastener diameter; dimpled hole.
df	— Degrees of freedom.
e	— Elongation in percent, a measure of the ductility of a material based on a tension test; unit deformation or strain; subscript “fatigue or endurance”; the minimum distance from a hole, center to the edge of the sheet; Engineering strain.
$e_e$	— Elastic strain.
$e_p$	— Plastic strain.
$e/D$	— Ratio of edge distance (center of the hole to edge of the sheet) to hole diameter (bearing strength).
E	— Modulus of elasticity in tension or compression; average ratio of stress to strain for stress below proportional limit.
$E_c$	— Modulus of elasticity in compression; average ratio of stress to strain below proportional limit.

**MIL-HDBK-5H****1 December 1998**

$E_s$	— Secant modulus of elasticity, Eq. 9.3.2.5b.
$E_t$	— Tangent modulus of elasticity.
ELI	— Extra low interstitial (grade of titanium alloy).
ER	— Equivalent round.
ESR	— Electro-slag remelted.
$f$	— Internal (or calculated) tension stress; stress applied to the gross flawed section; creep stress.
$f_b$	— Internal (or calculated) primary bending stress.
$f_c$	— Internal (or calculated) compressive stress; maximum stress at fracture: gross stress limit (for screening elastic fracture data).
$f_{pl}$	— Proportional limit.
$f_s$	— Internal (or calculated) shear stress.
$f_t$	— Internal (or calculated) tensile stress.
ft	— Foot; feet.
$F$	— Design stress; Fahrenheit; Ratio of two sample variances.
$F_A$	— Design axial stress.
$F_b$	— Design bending stress; modulus of rupture in bending.
$F_{bru}$	— Design ultimate bearing stress.
$F_{bry}$	— Design bearing yield stress.
$F_c$	— Design column stress.
$F_{cc}$	— Design crushing or crippling stress (upper limit of column stress for local failure).
$F_{cu}$	— Design ultimate compressive stress.
$F_{cy}$	— Design compressive yield stress at which permanent strain equals 0.002.
$F_H$	— Design hoop stress.
$F_s$	— Design shear stress.
$F_{sp}$	— Design proportional limit in shear.
$F_{st}$	— Design modulus of rupture in torsion.
$F_{su}$	— Design ultimate stress in pure shear (this value represents the average shear stress over the cross section).
$F_{sy}$	— Design shear yield stress.
$F_{tp}$	— Design proportional limit in tension.
$F_{tu}$	— Design tensile ultimate stress.
$F_{ty}$	— Design tensile yield stress at which permanent strain equals 0.002.
$g$	— Gram(s).
$G$	— Modulus of rigidity (shear modulus).
Gpa	— Gigapascal(s).
hr	— Hour(s).
H	— Subscript “hoop”.
HIP	— Hot isostatically pressed.
$i$	— Slope (due to bending) of neutral plane of a beam, in radians (1 radian = 57.3 degrees).
in.	— Inch(es).
$I$	— Axial moment of inertia.
$J$	— Torsion constant (= $I_p$ for round tubes); Joule.
$k$	— Tolerance limit factor for the normal distribution and the specified probability, confidence, and degrees of freedom; Strain at unit stress.
$k_{99}, k_{90}$	— One-sided tolerance limit factor for $T_{99}$ and $T_{90}$ , respectively (see Section 9.2.7.2).
$k_{A,B}$	— K to A basis or B basis, respectively (see Section 9.2.7.2).
ksi	— Kips (1,000 pounds) per square inch.
$K$	— A constant, generally empirical; thermal conductivity; stress intensity; Kelvin; correction factor.
$K_{app}$	— Apparent plane stress fracture toughness or residual strength.



**MIL-HDBK-5H****1 December 1998**

$K_c$	— Critical plane stress fracture toughness, a measure of fracture toughness at point of crack growth instability.
$K_f$	— Fatigue notch factor, or fatigue strength reduction factor.
$K_{Ic}$	— Plane strain fracture toughness.
$K_N$	— Empirically calculated fatigue notch factor.
$K_t$	— Theoretical stress concentration factor.
lb	— Pound.
ln	— Natural (base e) logarithm.
log	— Base 10 logarithm.
L	— Length; subscript “lateral”; longitudinal (grain direction).
LT	— Long transverse (grain direction).
m	— Subscript “mean”; metre; slope.
mm	— Millimeter(s).
M	— Applied moment or couple, usually a bending moment.
$M_c$	— Machine countersunk.
Mg	— Megagram(s).
MIG	— Metal-inert-gas (welding).
MPa	— Megapascal(s).
MS	— Military Standard.
M.S.	— Margin of safety.
M(T)	— Middle tension.
n	— Number of individual measurements or pairs of measurements; subscript “normal”; cycles applied to failure; shape parameter for the standard stress-strain curve (Ramberg-Osgood parameter); number of fatigue cycles endured.
N	— Fatigue life, number of cycles to failure; Newton; normalized.
$N_f$	— Fatigue life, cycles to failure.
$N_i^*$	— Fatigue life, cycles to initiation.
$N_t^*$	— Transition fatigue life where plastic and elastic strains are equal.
NAS	— National Aerospace Standard.
p	— Subscript “polar”; subscript “proportional limit”.
psi	— Pounds per square inch.
P	— Load; applied load (total, not unit, load); exposure parameter; probability.
$P_a$	— Load amplitude.
$P_m$	— Mean load.
$P_{max}$	— Maximum load.
$P_{min}$	— Minimum load.
Pu	— Test ultimate load, pounds per fastener.
Py	— Test yield load, pounds per fastener.
q	— Fatigue notch sensitivity.
Q	— Static moment of a cross section.
Q&T	— Quenched and tempered.
r	— Radius; root radius; reduced ratio (regression analysis); ratio of two pair measurements; rank of test point within a sample.
$\bar{r}$	— average ratio of paired measurements.
R	— Load (stress) ratio, or residual (observed minus predicted value); stress ratio, ratio of minimum stress to maximum stress in a fatigue cycle; reduced ratio.
$R_b$	— Stress ratio in bending.
$R_c$	— Stress ratio in compression; Rockwell hardness - C scale.

---

\* Different from ASTM.

**MIL-HDBK-5H****1 December 1998**

$R_{\epsilon}$	— Strain ratio, $\epsilon_{\min}/\epsilon_{\max}$ .
$R_s$	— Stress ratio in shear or torsion; ratio of applied load to allowable shear load.
$R_t$	— Ratio of applied load to allowable tension load.
RA	— Reduction of area.
R.H.	— Relative humidity.
RMS	— Root-mean-square (surface finish).
RT	— Room temperature.
s	— Estimated population standard deviation; sample standard deviation; subscript “shear”.
$s^2$	— Sample variance.
S	— Shear force; nominal engineering stress, fatigue; S-basis for mechanical-property values (see Section 1.4.1.1).
$S_a$	— Stress amplitude, fatigue.
$S_e$	— Fatigue limit.
$S_{eq}^*$	— Equivalent stress.
$S_f$	— Fatigue limit.
$S_m$	— Mean stress, fatigue.
$S_{\max}$	— Highest algebraic value of stress in the stress cycle.
$S_{\min}$	— Lowest algebraic value of stress in the stress cycle.
$S_r$	— Algebraic difference between the maximum and minimum stresses in one cycle.
$S_y$	— Root mean square error.
SAE	— Society of Automotive Engineers.
SCC	— Stress-corrosion cracking.
SEE	— Estimate population standard error of estimate.
SR	— Studentized residual.
ST	— Short transverse (grain direction).
STA	— Solution treated and aged.
SUS	— Individual or typical shear ultimate strength.
SYS	— Individual or typical shear yield strength.
t	— Thickness; subscript “tension”; exposure time; elapsed time; tolerance factor for the “t” distribution with the specified probability and appropriate degrees of freedom.
T	— Transverse direction; applied torsional moment; transverse (grain direction); subscript “transverse”.
$T_F$	— Exposure temperature.
$T_{90}$	— Statistically based lower tolerance bound for a mechanical property such that at least 90 percent of the population is expected to exceed $T_{90}$ with 95 percent confidence.
$T_{99}$	— Statistically based lower tolerance bound for a mechanical property such that at least 99 percent of the population is expected to exceed $T_{99}$ with 95 percent confidence.
TIG	— Tungsten-inert-gas (welding).
TUS	— Individual or typical tensile ultimate strength.
$TUS(S_u)^*$	— Tensile ultimate strength.
TYS	— Individual or typical tensile yield strength.
u	— Subscript “ultimate”.
U	— Factor of utilization.
$V_{99}, V_{90}$	— The tolerance limit factor corresponding to $T_{99}, T_{90}$ for the three-parameter Weibull distribution, based on a 95 percent confidence level and a sample of size n.
W	— Width of center-through-cracked tension panel; Watt.
$\bar{x}$	— Distance along a coordinate axis.
x	— Sample mean based upon n observations.

\* Different from ASTM.

**MIL-HDBK-5H****1 December 1998**

X	— Value of an individual measurement; average value of individual measurements.
y	— Deflection (due to bending) of elastic curve of a beam; distance from neutral axis to given fiber; subscript “yield”; distance along a coordinate axis.
Y	— Nondimensional factor relating component geometry and flaw size. See Reference 1.4.12.2.1(a) for values.
z	— Distance along a coordinate axis.
Z	— Section modulus, I/y.

**A.2 SYMBOLS** (also see Sections 1.2.1, 9.2.2, 9.3.4.3, 9.3.6.2, 9.4.1.2, 9.5.1.2, and 9.6).

$\alpha$	— (1) Coefficient of thermal expansion, mean; constant. (2) Significance level; probability (risk of erroneously rejecting the null hypothesis (see Section 9.6.2)).
$\alpha_{99}, \alpha_{90}$	— Shape parameter estimates for a $T_{99}$ or $T_{90}$ value based on an assumed three-parameter Weibull distribution.
$\alpha_{50}$	— Shape parameter estimate for the Anderson-Darling goodness-of-fit test based on an assumed three-parameter Weibull distribution.
$\beta$	— Constant.
$\beta_{99}, \beta_{90}$	— Scale parameter estimate for a $T_{99}$ or $T_{90}$ value based on an assumed three-parameter Weibull distribution.
$\beta_{50}$	— Scale parameter estimate for the Anderson-Darling goodness-of-fit test based on an assumed three-parameter Weibull distribution.
$\Delta\epsilon$ or $\epsilon_r^*$	— strain range, $\epsilon_{\max} - \epsilon_{\min}$ .
$\Delta\epsilon_e$	— Elastic strain range.
$\Delta\epsilon_p$	— Plastic strain range.
$\Delta S (S_r)^*$	— Stress range.
$\Delta\sigma$	— True or local stress range.
$\epsilon$	— True or local strain.
$\epsilon_{eq}^*$	— Equivalent strain.
$\epsilon_m$	— Mean strain, $(\epsilon_{\max} + \epsilon_{\min})/2$ .
$\epsilon_{\max}$	— Maximum strain.
$\epsilon_{\min}$	— Minimum strain.
$\epsilon_t$	— Total (elastic plus plastic) strain at failure determined from tensile stress-strain curve.
$\delta$	— Deflection.
$\Phi$	— Angular deflection.
$\rho$	— Radius of gyration; Neuber constant (block length).
$\mu$	— Poisson's ratio.
$\sigma$	— True or local stress; or population standard deviation.
$\sigma_x$	— Population standard deviation of x.
$\sigma_x^2$	— Population variance of x.
$\tau_{99}, \tau_{90}$	— Threshold estimates for a $T_{99}$ or $T_{90}$ value based on an assumed three-parameter Weibull distribution.
$\tau_{50}$	— Threshold estimate for the Anderson-Darling goodness-of-fit test based on an assumed three-parameter Weibull distribution.
$\omega$	— Density; flank angle.
$\infty$	— Infinity.
$\Sigma$	— The sum of.
'	— Superscript that denotes value determined by regression analysis.

\* Different from ASTM.

**MIL-HDBK-5H****1 December 1998****A.3 DEFINITIONS** (also see Sections 1.2.1, 9.2.2, 9.3.6.2, 9.4.1.2, 9.5.1.2 and 9.6).

*A-Basis*.—The lower of either a statistically calculated number, or the specification minimum (S-basis). The statistically calculated number indicates that at least 99 percent of the population of values is expected to equal or exceed the A-basis mechanical design property, with a confidence of 95 percent.

*Alternating Load*.—See Loading Amplitude.

*B-Basis*.—At least 90 percent of the population of values is expected to equal or exceed the B-basis mechanical property allowable, with a confidence of 95 percent.

*Cast*.—Cast consists of the sequential ingots which are melted from a single furnace charge and poured in one or more drops without changes in the processing parameters. (The cast number is for internal identification and is not reported.) (See Table 9.1.6.1).

*Casting*.—One or more parts which are melted from a single furnace charge and poured in one or more molds without changes in the processing parameters. (The cast number is for internal identification and is not reported.) (See Table 9.1.6.1).

*Confidence*.—A specified degree of certainty that at least a given proportion of all future measurements can be expected to equal or exceed the lower tolerance limit. Degree of certainty is referred to as the confidence coefficient. For MIL-HDBK-5, the confidence coefficient is 95 percent which, as related to design properties, means that, in the long run over many future samples, 95 percent of conclusions regarding exceedance of A and B-values would be true.

*Confidence Interval*.—An interval estimate of a population parameter computed so that the statement “the population parameter lies in this interval” will be true, on the average, in a stated proportion of the times such statements are made.

*Confidence Interval Estimate*.—Range of values, computed with the sample that is expected to include the population variance or mean.

*Confidence Level (or Coefficient)*.—The stated portion of the time the confidence interval is expected to include the population parameter.

*Confidence Limits\**.—The two numeric values that define a confidence interval.

*Constant-Amplitude Loading*.—A loading in which all of the peak loads are equal and all of the valley loads are equal.

*Constant-Life Fatigue Diagram*.—A plot (usually on Cartesian coordinates) of a family of curves, each of which is for a single fatigue life,  $N$ —relating  $S$ ,  $S_{\max}$ , and/or  $S_{\min}$  to the mean stress,  $S_m$ . Generally, the constant life fatigue diagram is derived from a family of  $S/N$  curves, each of which represents a different stress ratio (A or R) for a 50 percent probability of survival. NOTE—MIL-HDBK-5 no longer presents fatigue data in the form of constant-life diagrams.

*Creep*.—The time-dependent deformation of a solid resulting from force.

---


\* Different from ASTM.

**MIL-HDBK-5H****1 December 1998**

Note 1—Creep tests are usually made at constant load and temperature. For tests on metals, initial loading strain, however defined, is not included.

Note 2—This change in strain is sometimes referred to as creep strain.

*Creep-Rupture Curve.*—Results of material tests under constant load and temperature; usually plotted as strain versus time to rupture. A typical plot of creep-rupture data is shown in Figure 9.3.6.2. The strain indicated in this curve includes both initial deformation due to loading and plastic strain due to creep.



**Figure A.1. Typical creep-rupture curve.**

*Creep-Rupture Strength.*—Stress that will cause fracture in a creep test at a given time, in a specified constant environment. Note: This is sometimes referred to as the stress-rupture strength.

*Creep-Rupture Test.*—A creep-rupture test is one in which progressive specimen deformation and time for rupture are measured. In general, deformation is much larger than that developed during a creep test.

*Creep-Strain.*—The time-dependent part of the strain resulting from stress, excluding initial loading strain and thermal expansion.

*Creep Strength.*—Stress that causes a given creep in a creep test at a given time in a specified constant environment.

*Creep Stress.*—The constant load divided by the original cross-sectional area of the specimen.

*Creep Test.*—A creep test has the objective of measuring deformation and deformation rates at stresses usually well below those which would result in fracture during the time of testing.

*Critical Stress Intensity Factor.*—A limiting value of the stress intensity factor beyond which continued flaw propagation and/or fracture may be expected. This value is dependent on material and may vary with type of loading and conditions of use.

*Cycle.*—Under constant-amplitude loading, the load varies from the minimum to the maximum and then to the minimum load (see Figure 9.3.4.3). The symbol  $n$  or  $N$  (see definition of fatigue life) is used to indicate the number of cycles.

**MIL-HDBK-5H****1 December 1998**

*Deformable Shank Fasteners.*—A fastener whose shank is deformed in the grip area during normal installation processes.

*Degree of Freedom.*—Number of degrees of freedom for  $n$  variables may be defined as number of variables minus number of constraints between them. Since the standard deviation calculation contains one fixed value (the mean) it has  $n - 1$  degrees of freedom.

*Degrees of Freedom.*—Number of independent comparisons afforded by a sample.

*Discontinued Test.*—See Runout.

*Elapsed Time.*—The time interval from application of the creep stress to a specified observation.

*Fatigue.*—The process of progressive localized permanent structural change occurring in a material subjected to conditions that produce fluctuating stresses and strains at some point or points, and which may culminate in cracks or complete fracture after a sufficient number of fluctuations. NOTE—fluctuations in stress and in time (frequency), as in the case of “random vibration”.

*Fatigue Life.*— $N$ —the number of cycles of stress or strain of a specified character that a given specimen sustains before failure of a specified nature occurs.

*Fatigue Limit.*— $S_f$ —the limiting value of the median fatigue strength as  $N$  becomes very large. NOTE—Certain materials and environments preclude the attainment of a fatigue limit. Values tabulated as “fatigue limits” in the literature are frequently (but not always) values of  $S_N$  for 50 percent survival at  $N$  cycles of stress in which  $S_m = 0$ .

*Fatigue Loading.*—Periodic or non-periodic fluctuating loading applied to a test specimen or experienced by a structure in service (also known as cyclic loading).

*Fatigue Notch Factor\**.—The fatigue notch factor,  $K_f$  (also called fatigue strength reduction factor), is the ratio of the fatigue strength of a specimen with no stress concentration to the fatigue strength of a specimen with a stress concentration at the same number of cycles for the same conditions. NOTE—In specifying  $K_f$ , it is necessary to specify the geometry, mode of loading, and the values of  $S_{max}$ ,  $S_m$ , and  $N$  for which it is computed.

*Fatigue Notch Sensitivity.*—The fatigue notch sensitivity,  $q$ , is a measure of the degree of agreement between  $K_f$  and  $K_t$ . NOTE—the definition of fatigue notch sensitivity is  $q = (K_f - 1)/(K_t - 1)$ .

*Heat.*—All material identifiable to a single molten metal source. (All material from a heat is considered to have the same composition. A heat may yield one or more ingots. A heat may be divided into several lots by subsequent processing.)

*Heat.*—Heat is material which, in the case of batch melting, is cast at the same time from the same furnace and is identified with the same heat number; or, in the case of continuous melting, is poured without interruption. (See Table 9.1.6.2)

*Heat.*—Heat is a consolidated (vacuum hot pressed) billet having a distinct chemical composition. (See Table 9.1.6.2)

---

\* Different from ASTM.

**MIL-HDBK-5H**  
**1 December 1998**

*Hysteresis Diagram.*—The stress-strain path during a fatigue cycle.

*Isostrain Lines.*—Lines representing constant levels of creep.

*Isothermal Lines.*—Lines of uniform temperature on a creep or stress-rupture curve.

*Interrupted Test\*.*—Tests which have been stopped before failure because of some mechanical problem, e.g., power failure, load or temperature spikes.

*Loading Amplitude.*—The loading amplitude,  $P_a$ ,  $S_a$ , or  $\epsilon_a$  represents one-half of the range of a cycle (see Figure 9.3.4.3). (Also known as alternating load, alternating stress, or alternating strain.)

*Loading Strain.*—Loading strain is the change in strain during the time interval from the start of loading to the instant of full-load application, sometimes called initial strain.

*Loading (Unloading) Rate.*—The time rate of change in the monotonically increasing (decreasing) portion of the load-time function.

*Load Ratio.*—The load ratio,  $R$ ,  $A$ , or  $R_\epsilon$ ,  $A_\epsilon$ , or  $R_\sigma$ ,  $A_\sigma$ , is the algebraic ratio of the two loading parameters of a cycle; the two most widely used ratios are

$$R = \frac{\text{minimum load}}{\text{maximum load}} = \frac{P_{\min}}{P_{\max}}$$

or

$$R_\sigma = \frac{S_{\min}}{S_{\max}}$$

or

$$R_\epsilon = \epsilon_{\min} / \epsilon_{\max}$$

and

$$A = \frac{\text{loading amplitude}}{\text{mean load}} = \frac{P_a}{P_m} \text{ or } \frac{S_a}{S_M}$$

$$A_\epsilon = \frac{\text{strain amplitude}}{\text{mean strain}} = \frac{\epsilon_a}{\epsilon_M} \text{ or } (\epsilon_{\max} - \epsilon_{\min}) / (\epsilon_{\max} + \epsilon_{\min}) .$$

NOTE—load ratios  $R$  or  $R_\epsilon$  are generally used in MIL-HDBK-5.

---

\* Different from ASTM.

**MIL-HDBK-5H****1 December 1998**

*Longitudinal Direction.*—Parallel to the principal direction of flow in a worked metal. For die forgings this direction is within  $\pm 15^\circ$  of the predominate grain flow.

*Long-Transverse Direction.*—The transverse direction having the largest dimension, often called the “width” direction. For die forgings this direction is within  $\pm 15^\circ$  of the longitudinal (predominate) grain direction and parallel, within  $\pm 15^\circ$ , to the parting plane. (Both conditions must be met.)

*Lot.*—All material from a heat or single molten metal source of the same product type having the same thickness or configuration, and fabricated as a unit under the same conditions. If the material is heat treated, a lot is the above material processed through the required heat-treating operations as a unit.

*Master Creep Equation.*—An equation expressing combinations of stress, temperature, time and creep, or a set of equations expressing combinations of stress, temperature and time for given levels of creep.

*Master Rupture Equation.*—An equation expressing combinations of stress, temperature, and time that cause complete separation (fracture or rupture) of the specimen.

*Maximum Load.*—The maximum load,  $P_{\max}$ ,  $S_{\max}$ ,  $\epsilon_{\max}$  is the load having the greatest algebraic value.

*Mean Load.*—The mean load,  $P_m$ , is the algebraic average of the maximum and minimum loads in constant-amplitude loading:

$$P_m = \frac{P_{\max} + P_{\min}}{2}, \text{ or}$$

$$S_m = \frac{S_{\max} + S_{\min}}{2}, \text{ or}$$

$$\epsilon_m = \frac{\epsilon_{\max} + \epsilon_{\min}}{2},$$

or the integral average of the instantaneous load values.

*Median Fatigue Life.*—The middlemost of the observed fatigue life values (arranged in order of magnitude) of the individual specimens in a group tested under identical conditions. In the case where an even number of specimens are tested, it is the average of the two middlemost values (based on log lives in MIL-HDBK-5). NOTE 1—The use of the sample median instead of the arithmetic mean (that is, the average) is usually preferred. NOTE 2—In the literature, the abbreviated term “fatigue life” usually has meant the median fatigue life of the group. However, when applied to a collection of data without further qualification, the term “fatigue life” is ambiguous.

*Median Fatigue Strength at N Cycles.*—An estimate of the stress level at which 50 percent of the population would survive N cycles. NOTE—The estimate of the median fatigue strength is derived from a particular point of the fatigue-life distribution, since there is no test procedure by which a frequency distribution of fatigue strengths at N cycles can be directly observed. That is, one can not perform constant-life tests.



**MIL-HDBK-5H****1 December 1998**

*Melt.*—Melt is a single homogeneous batch of molten metal for which all processing has been completed and the temperature has been adjusted and made ready to pour castings. (For metal-matrix composites, the molten metal includes unmelted reinforcements such as particles, fibers, or whiskers.) (See Table 9.1.6.2)

*Minimum Load.*—The minimum load,  $P_{\min}$ ,  $S_{\min}$ , or  $\epsilon_{\min}$ , is the load having the least algebraic value.

*Nominal Hole Diameters.*—Nominal hole diameters for deformable shank fasteners shall be according to Table 9.4.1.2(a). When tests are made with hole diameters other than those tabulated, hole sizes used shall be noted in the report and on the proposed joint allowables table.

*Nominal Shank Diameter.*—Nominal shank diameter of fasteners with shank diameters equal to those used for standard size bolts and screws (NAS 618 sizes) shall be the decimal equivalents of stated fractional or numbered sizes. These diameters are those listed in the fourth column of Table 9.4.1.2. Nominal shank diameters for nondeformable shank blind fasteners are listed in the fifth column of Table 9.4.1.2. Nominal shank diameters for other fasteners shall be the average of required maximum and minimum shank diameters.

*Nondeformable Shank Fasteners.*—A fastener whose shank does not deform in the grip area during normal installation processes.

*Outlier\**—An experimental observation which deviates markedly from other observations in the sample. An outlier is often either an extreme value of the variability in the data, or the result of gross deviation in the material or experimental procedure.

*Peak.*—The point at which the first derivative of the load-time history changes from a positive to a negative sign; the point of maximum load in constant-amplitude loading (see Figure 9.3.4.3).

*Plane Strain.*—The stress state in which all strains occur only in the principal loading plane. No strains occur out of the plane, i.e.,  $\epsilon_z = 0$ , and  $\sigma_z \neq 0$ .

*Plane Stress.*—The stress state in which all stresses occur only in the principal loading plane. No stresses occur out of the plane, i.e.,  $\sigma_z = 0$ , and  $\epsilon_z \neq 0$ .

*Plastic Strain During Loading.*—Plastic strain during loading is the portion of the strain during loading determined as the offset from the linear portion to the end of a stress-strain curve made during load application.

*Plane-Strain Fracture Toughness.*—A generic term now generally adopted for the critical plane-strain stress intensity factor characteristic of plane-strain fracture, symbolically denoted  $K_{Ic}$ . This is because in current fracture testing practices, specification of the slowly increasing load test of specimen materials in the plane-strain stress state and in opening mode (I) has been dominant.

*Plane-Stress and Transitional Fracture Toughness.*—A generic term denoting the critical stress intensity factor associated with fracture behavior under nonplane-strain conditions. Because of plasticity effects and stable crack growth which can be encountered prior to fracture under these conditions, designation of a specific value is dependent on the stage of crack growth detected during testing. Residual strength or apparent fracture toughness is a special case of plane-stress and transitional fracture toughness wherein the reference crack length is the initial pre-existing crack length and subsequent crack growth during the test is neglected.

---

\* Different from ASTM.

**MIL-HDBK-5H****1 December 1998**

*Population.*—All potential measurements having certain independent characteristics in common; i.e., “all possible TUS(L) measurements for 17-7PH stainless steel sheet in TH1050 condition”.

*Precision.\**—The degree of mutual agreement among individual measurements. Relative to a method of test, precision is the degree of mutual agreement among individual measurements made under prescribed like conditions. The lack of precision in a measurement may be characterized as the standard deviation of the errors in measurement.

*Primary Creep.*—Creep occurring at a diminishing rate, sometimes called initial stage of creep.

*Probability.*—Ratio of possible number of favorable events to total possible number of equally likely events. For example, if a coin is tossed, the probability of heads is one-half (or 50 percent) because heads can occur one way and the total possible events are two, either heads or tails. Similarly, the probability of throwing a three or greater on a die is 4/6 or 66.7 percent. Probability, as related to design allowables, means that chances of a material-property measurement equaling or exceeding a certain value (the one-sided lower tolerance limit) is 99 percent in the case of a A-basis value and 90 percent in the case of a B-basis value.

*Range.*—Range,  $\Delta P$ ,  $S_r$ ,  $\Delta\epsilon$ ,  $\epsilon_r$ ,  $\Delta\sigma$  is the algebraic difference between successive valley and peak loads (positive range or increasing load range) or between successive peak and valley loads (negative range or decreasing load range), see Figure 9.3.4.3. In constant-amplitude loading, for example, the range is given by  $\Delta P = P_{\max} - P_{\min}$ .

*Rate of Creep.*—The slope of the creep-time curve at a given time determined from a Cartesian plot.

*Residual.\**—The difference between the observed fatigue (log) life and the fatigue (log) life estimated from the fatigue model at a particular stress/strain level.

*Runout.\**—A test that has been terminated prior to failure. Runout tests are usually stopped at an arbitrary life value because of time and economic considerations. NOTE—Runout tests are useful for estimating a pseudo-fatigue-limit for a fatigue data sample.

*Sample.*—A finite number of observations drawn from the population.

*Sample.*—The number of specimens selected from a population for test purposes. NOTE—The method of selecting the sample determines the population about which statistical inferences or generalization can be made.

*Sample Average (Arithmetic Mean).*—The sum of all the observed values in a sample divided by the sample size (number). It is a point estimate of the population mean.

*Sample Mean.*—Average of all observed values in the sample. It is an estimate of population mean. A mean is indicated by a bar over the symbol for the value observed. Thus, the mean of n observations of TUS would be expressed as:

$$\overline{\text{TUS}} = \frac{\text{TUS}_1 + \text{TUS}_2 + \dots + \text{TUS}_n}{n} = \frac{\sum_{i=1}^n (\text{TUS}_i)}{n}$$

---

\* Different from ASTM.

**MIL-HDBK-5H****1 December 1998**

*Sample Median.*—Value of the middle-most observation. If the sample is nearly normally distributed, the sample median is also an estimate of the population mean.

*Sample Median.*—The middle value when all observed values in a sample are arranged in order of magnitude if an odd number of samples are tested. If the sample size is even, it is the average of the two middlemost values. It is a point estimate of the population median, or 50 percentile point.

*Sample Point Deviation.*—The difference between an observed value and the sample mean.

*Sample Standard Deviation.\**—The standard deviation of the sample,  $s$ , is the square root of the sample variance. It is a point estimate of the standard deviation of a population, a measure of the "spread" of the frequency distribution of a population. NOTE—This value of  $s$  provides a statistic that is used in computing interval estimates and several test statistics.

*Sample Variance.\**—Sample variance,  $s^2$ , is the sum of the squares of the differences between each observed value and the sample average divided by the sample size minus one. It is a point estimate of the population variance. NOTE—This value of  $s^2$  provides both an unbiased point estimate of the population variance and a statistic that is used on computing the interval estimates and several test statistics. Some texts define  $s^2$  as "the sum of the squared differences between each observed value and the sample average divided by the sample size", however, this statistic underestimates the population variance, particularly for small sample sizes.

*Sample Variance.*—The sum of the squared deviations, divided by  $n - 1$ , and, based on  $n$  observations of TUS, expressed as

$$S_{\text{TUS}}^2 = \frac{\sum_{i=1}^n (\text{TUS}_i - \overline{\text{TUS}})^2}{n - 1} = \frac{n \sum_{i=1}^n (\text{TUS}_i)^2 - \left( \sum_{i=1}^n \text{TUS}_i \right)^2}{n(n - 1)}$$

*S-Basis.*—The S-value is the minimum property value specified by the governing industry specification (as issued by standardization groups such as SAE Aerospace Materials Division, ASTM, etc.) or federal or military standards for the material. (See MIL-STD-970 for order of preference for specifications.) For certain products heat treated by the user (for example, steels hardened and tempered to a designated  $F_{ut}$ ), the S-value may reflect a specified quality-control requirement. Statistical assurance associated with this value is not known.

*Secondary Creep.*—Creep occurring at a constant rate, sometimes called second stage creep.

*Short-Transverse Direction.*—The transverse direction having the smallest dimension, often called the "thickness" direction. For die forgings this direction is within  $\pm 15^\circ$  of the longitudinal (predominate) grain direction and perpendicular, within  $\pm 15^\circ$ , to the parting plane. (Both conditions must be met.) When possible, short transverse specimens shall be taken across the parting plane.

---

\* Different from ASTM.

**MIL-HDBK-5H****1 December 1998**

*Significance Level (As Used Here).*—Risk of concluding that two samples were drawn from different populations when, in fact, they were drawn from the same population. A significance level of  $\alpha = 0.05$  is employed through these Guidelines.\*

*Significance Level.*—The stated probability (risk) that a given test of significance will reject the hypothesis that a specified effect is absent when the hypothesis is true.

*Significant (Statistically Significant).*—An effect or difference between populations is said to be present if the value of a test statistic is significant, that is, lies outside of predetermined limits. NOTE—An effect that is statistically significant may not have engineering importance.

*S/N Curve for 50 Percent Survival.\*\**—A curve fitted to the median values of fatigue life at each of several stress levels. It is an estimate of the relationship between applied stress and the number of cycles-to-failure that 50 percent of the population would survive. NOTE 1—This is a special case of the more general definition of S/N curve for P percent survival. NOTE 2—In the literature, the abbreviated term “S/N Curve” usually has meant either the S/N curve drawn through the mean (averages) or through the medians (50 percent values) for the fatigue life values. Since the term “S/N Curve” is ambiguous, it should be used only when described appropriately. NOTE 3—Mean S/N curves (based on log lives) are shown in MIL-HDBK-5.

*S/N Diagram.*—A plot of stress against the number of cycles to failure. The stress can be  $S_{\max}$ ,  $S_{\min}$ , or  $S_a$ . The diagram indicates the S/N relationship for a specified value of  $S_m$ , A, or R and a specified probability of survival. Typically, for N, a log scale (base 10) is used. Generally, for S, a linear scale is used, but a log scale is used occasionally. NOTE— $S_{\max}$ -versus-log N diagrams are used commonly in MIL-HDBK-5.

*Standard Deviation.*—An estimate of the population standard deviation; the square root of the variance, or

$$S_{TUS} = \sqrt{\frac{\sum_{i=1}^n (TUS_i - \overline{TUS})^2}{n - 1}} = \sqrt{\frac{n \sum_{i=1}^n (TUS_i)^2 - \sum_{i=1}^n (TUS_i)^2}{n(n - 1)}}$$

*Stress Intensity Factor.*—A physical quantity describing the severity of a flaw in the stress field of a loaded structural element. The gross stress in the material and flaw size are characterized parametrically by the stress intensity factor,

$$K = f\sqrt{a} Y, \text{ ksi} \cdot \text{in.}^{1/2} \quad [9.5.1.2]$$

*Stress-Rupture Test*—A stress-rupture test is one in which time for rupture is measured, no deformation measurement being made during the test.

*Tertiary Creep.*—Creep occurring at an accelerating rate, sometimes called third stage creep.

*Theoretical Stress Concentration Factor (or Stress Concentration Factor).*—This factor,  $K_t$ , is the ratio of the nominal stress to the greatest stress in the region of a notch (or other stress concentrator) as determined

---

\* This is appropriate, since a confidence level of  $1 - \alpha = 0.95$  is used in establishing A and B-values.

\*\* Different from ASTM.

**MIL-HDBK-5H**  
**1 December 1998**

by the theory of elasticity (or by experimental procedures that give equivalent values). NOTE—The theory of plasticity should not be used to determine  $K_t$ .

*Tolerance Interval.*—An interval computed so that it will include at least a stated percentage of the population with a stated probability.

*Tolerance Level.*—The stated probability that the tolerance interval includes at least the stated percentage of the population. It is not the same as a confidence level, but the term confidence level is frequently associated with tolerance intervals.

*Tolerance Limits.*—The two statistics that define a tolerance interval. (One value may be “minus infinity” or “plus infinity”.)

*Total Plastic Strain.*—Total plastic strain at a specified time is equal to the sum of plastic strain during loading plus creep.

*Total Strain.*—Total strain at any given time, including initial loading strain (which may include plastic strain in addition to elastic strain) and creep strain, but not including thermal expansion.

*Transition Fatigue Life.\**—The point on a strain-life diagram where the elastic and plastic strains are equal.

*Transverse Direction.*—Perpendicular to the principal direction of flow in a worked metal; may be defined as T, LT or ST.

*Typical Basis.*—A typical property value is an average value and has no statistical assurance associated with it.

*Waveform.*—The shape of the peak-to-peak variation of a controlled mechanical test variable (for example, load, strain, displacement) as a function of time.

---

\* Different from ASTM.

**MIL-HDBK-5H**  
**1 December 1998**

This page intentionally blank.

**MIL-HDBK-5H****1 December 1998****APPENDIX B****B.0 Alloy Index**

<b>Alloy Name</b>	<b>Form</b>	<b>Specification</b>	<b>Section</b>
250	Bar	AMS 6512	2.5.1
250	Sheet and Plate	AMS 6520	2.5.1
354.0	Casting	MIL-A-21180	3.9.1
355.0	Permanent Mold Casting	AMS 4281	3.9.2
356.0	Sand Casting	AMS 4217	3.9.4
356.0	Investment Casting	AMS 4260	3.9.4
356.0	Permanent Mold Casting	AMS 4284	3.9.4
359.0	Casting	MIL-A-21180	3.9.8
2014	Bare Sheet and Plate	AMS 4028	3.2.1
2014	Bare Sheet and Plate	AMS 4029	3.2.1
2014	Bar and Rod, Rolled or Cold Finished	AMS 4121	3.2.1
2014	Forging	AMS 4133	3.2.1
2014	Extrusion	AMS 4153	3.2.1
2014	Forging	MIL-A-22771	3.2.1
2014	Extruded Bar, Rod and Shapes	AMS-QQ-A-200/2	3.2.1
2014	Rolled or Drawn Bar, Rod and Shapes	AMS-QQ-A-225/4	3.2.1
2014	Clad Sheet and Plate	AMS-QQ-A-250/3	3.2.1
2014	Forging	QQ-A-367	3.2.1
2017	Bar and Rod, Rolled or Cold-Finished	AMS 4118	3.2.2
2017	Rolled Bar and Rod	AMS-QQ-A-225/5	3.2.2
2024	Bare Sheet and Plate	AMS 4035	3.2.3
2024	Bare Sheet and Plate	AMS 4037	3.2.3
2024	Tubing, Hydraulic, Seamless, Drawn	AMS 4086	3.2.3
2024	Bar and Rod, Rolled or Cold-Finished	AMS 4120	3.2.3
2024	Extrusion	AMS 4152	3.2.3
2024	Extrusion	AMS 4164	3.2.3
2024	Extrusion	AMS 4165	3.2.3
2024	Extruded Bar, Rod and Shapes	AMS-QQ-A-200/3	3.2.3
2024	Rolled or Drawn Bar, Rod and Wire	AMS-QQ-A-225/6	3.2.3
2024	Bare Sheet and Plate	AMS-QQ-A-250/4	3.2.3
2024	Clad Sheet and Plate	AMS-QQ-A-250/5	3.2.3
2024	Tubing	WW-T-700/3	3.2.3
2025	Die Forging	AMS 4130	3.2.4
2090	Sheet	AMS 4251	3.2.5
2124	Plate	AMS 4101	3.2.6
2124	Plate	AMS-QQ-A-250/29	3.2.6
2219	Sheet and Plate	AMS 4031	3.2.7
2219	Hand Forging	AMS 4144	3.2.7
2219	Extrusion	AMS 4162	3.2.7
2219	Extrusion	AMS 4163	3.2.7
2219	Sheet and Plate	AMS-QQ-A-250/30	3.2.7
2519	Plate	MIL-A-46192	3.2.8
2524	Sheet and Plate	AMS 4296	3.2.9
2618	Die and Hand Forgings	AMS 4132	3.2.10
2618	Die Forging	MIL-A-22771	3.2.10
2618	Forging	QQ-A-367	3.2.10

Key: Underline indicates inactive for new design.

**MIL-HDBK-5H****1 December 1998**

<b>Alloy Name</b>	<b>Form</b>	<b>Specification</b>	<b>Section</b>
4130	Bar and Forging	AMS 6348	2.3.1
4130	Sheet, Strip and Plate	AMS 6350	2.3.1
4130	Sheet, Strip and Plate	AMS 6351	2.3.1
4130	Tubing	AMS 6361	2.3.1
4130	Tubing	AMS 6362	2.3.1
4130	Bar and Forging	AMS 6370	2.3.1
4130	Tubing	AMS 6371	2.3.1
4130	Tubing	AMS 6373	2.3.1
4130	Tubing	AMS 6374	2.3.1
4130	Bar and Forging	AMS 6528	2.3.1
4130	Sheet, Strip and Plate	MIL-S-18729	2.3.1
4130	Bar and Forging	MIL-S-6758	2.3.1
4130	Tubing	MIL-T-6736	2.3.1
4135	Sheet, Strip and Plate	AMS 6352	2.3.1
4135	Tubing	AMS 6365	2.3.1
4135	Tubing	AMS 6372	2.3.1
4135	Tubing	MIL-T-6735	2.3.1
4140	Bar and Forging	AMS 6349	2.3.1
4140	Tubing	AMS 6381	2.3.1
4140	Bar and Forging	AMS 6382	2.3.1
4140	Tubing	AMS 6390	2.3.1
4140	Sheet, Strip and Plate	AMS 6395	2.3.1
4140	Bar and Forging	AMS 6529	2.3.1
4140	Bar and Forging	MIL-S-5626	2.3.1
4340	Sheet, Strip and Plate	AMS 6359	2.3.1
4340	Bar and Forging	AMS 6414	2.3.1
4340	Tubing	AMS 6414	2.3.1
4340	Bar and Forging	AMS 6415	2.3.1
4340	Tubing	AMS 6415	2.3.1
4340	Sheet, Strip and Plate	AMS 6454	2.3.1
4340	Bar and Forging	MIL-S-5000	2.3.1
4340	Tubing	MIL-S-8844	2.3.1
4340	Bar and Forging	MIL-S-8844	2.3.1
5052	Sheet and Plate	AMS 4015	3.5.1
5052	Sheet and Plate	AMS 4016	3.5.1
5052	Sheet and Plate	AMS 4017	3.5.1
5052	Sheet and Plate	AMS-QQ-A-250/8	3.5.1
5083	Bare Sheet and Plate	AMS 4056	3.5.2
5083	Extruded Bar, Rod and Shapes	AMS-QQ-A-200/4	3.5.2
5083	Bare Sheet and Plate	AMS-QQ-A-250/6	3.5.2
5086	Extruded Bar, Rod and Shapes	AMS-QQ-A-200/5	3.5.3
5086	Sheet and Plate	AMS-QQ-A-250/7	3.5.3
5454	Extruded Bar, Rod and Shapes	AMS-QQ-A-200/6	3.5.4
5454	Sheet and Plate	AMS-QQ-A-250/10	3.5.4
5456	Extruded Bar, Rod and Shapes	AMS-QQ-A-200/7	3.5.5
5456	Sheet and Plate	AMS-QQ-A-250/9	3.5.5
6061	Sheet and Plate	AMS 4025	3.6.2
6061	Sheet and Plate	AMS 4026	3.6.2
6061	Sheet and Plate	AMS 4027	3.6.2
6061	Tubing Seamless, Drawn	AMS 4080	3.6.2
6061	Tubing Seamless, Drawn	AMS 4082	3.6.2
6061	Bar and Rod, Rolled or Cold Finished	AMS 4115	3.6.2
6061	Bar and Rod, Cold Finished	AMS 4116	3.6.2
6061	Bar and Rod, Rolled or Cold Finished	AMS 4117	3.6.2
6061	Forging	AMS 4127	3.6.2

Key: Underline indicates inactive for new design.



**MIL-HDBK-5H**  
**1 December 1998**

<b>Alloy Name</b>	<b>Form</b>	<b>Specification</b>	<b>Section</b>
6061	Extrusion	AMS 4160	3.6.2
6061	Extrusion	AMS 4161	3.6.2
6061	Extrusion	AMS 4172	3.6.2
6061	Hand Forging	AMS 4248	3.6.2
6061	Forging	MIL-A-22771	3.6.2
6061	Pipe	MIL-P-25995	3.6.2
6061	Extruded Rod, Bar Shapes and Tubing	AMS-QQ-A-200/8	3.6.2
6061	Rolled Bar, Rod and Shapes	AMS-QQ-A-225/8	3.6.2
6061	Sheet and Plate	AMS-QQ-A-250/11	3.6.2
6061	Forging	QQ-A-367	3.6.2
6061	Tubing Seamless, Drawn	WW-T-700/6	3.6.2
6151	Die Forging	AMS 4125	3.6.3
6151	Forging	MIL-A-22771	3.6.3
7010	Plate	AMS 4204	3.7.1
7010	Plate	AMS 4205	3.7.1
7050	Bare Plate	AMS 4050	3.7.3
7050	Die Forging	AMS 4107	3.7.3
7050	Hand Forging	AMS 4108	3.7.3
7050	Bare Plate	AMS 4201	3.7.3
7050	Die Forging	AMS 4333	3.7.3
7050	Extruded Shape	AMS 4340	3.7.3
7050	Extruded Shape	AMS 4341	3.7.3
7050	Extruded Shape	AMS 4342	3.7.3
7050	Forging	MIL-A-22771	3.7.3
7075	Bare Sheet and Plate	AMS 4044	3.7.4
7075	Bare Sheet and Plate	AMS 4045	3.7.4
7075	Clad Sheet and Plate	AMS 4049	3.7.4
7075	Bare Plate	AMS 4078	3.7.4
7075	Bar and Rod, Rolled or Cold Finished	AMS 4122	3.7.4
7075	Bar and Rod, Rolled or Cold Finished	AMS 4123	3.7.4
7075	Bar and Rod, Rolled or Cold Finished	AMS 4124	3.7.4
7075	Forging	AMS 4126	3.7.4
7075	Die Forging	AMS 4141	3.7.4
7075	Forging	AMS 4147	3.7.4
7075	Bar and Rod, Rolled or Cold Finished	AMS 4186	3.7.4
7075	Bar and Rod, Rolled or Cold Finished	AMS 4187	3.7.4
7075	Forging	MIL-A-22771	3.7.4
7075	Extruded Bar, Rod and Shapes	AMS-QQ-A-200/11, 15	3.7.4
7075	Rolled or Drawn Bar and Rod	AMS-QQ-A-225/9	3.7.4
7075	Bare Sheet and Plate	AMS-QQ-A-250/12, 24	3.7.4
7075	Clad Sheet and Plate	AMS-QQ-A-250/13, 25	3.7.4
7075	Forging	QQ-A-367	3.7.4
7150	Bare Plate	AMS 4252 (T7751)	3.7.5
7150	Bare Plate	AMS 4306 (T6151)	3.7.5
7150	Extrusion	AMS 4307 (T61511)	3.7.5
7150	Extrusion	AMS 4345 (T77511)	3.7.5
7175	Die Forging	AMS 4148 (T66)	3.7.6
7175	Die and Hand Forging	AMS 4149 (T74)	3.7.6
7175	Hand Forging	AMS 4179 (T7452)	3.7.6
7175	Extrusion	AMS 4344 (T73511)	3.7.6
7175	Forging	MIL-A-22771	3.7.6
7249	Hand Forging	AMS 4334	3.7.7
7475	Bare Sheet	AMS 4084 (T61)	3.7.8
7475	Bare Sheet	AMS 4085 (T761)	3.7.8
7475	Bare Plate	AMS 4089 (T7651)	3.7.8

Key: Underline indicates inactive for new design.

**MIL-HDBK-5H**  
**1 December 1998**

<b>Alloy Name</b>	<b>Form</b>	<b>Specification</b>	<b>Section</b>
7475	Bare Plate	AMS 4090 (T651)	3.7.8
7475	Clad Sheet	AMS 4100 (T761)	3.7.8
7475	Bare Plate	AMS 4202 (T7351)	3.7.8
7475	Clad Sheet	AMS 4207 (T61)	3.7.8
8630	Bar and Forging	AMS 6280	2.3.1
8630	Tubing	AMS 6281	2.3.1
8630	Sheet, Strip and Plate	AMS 6355	2.3.1
8630	Sheet, Strip and Plate	MIL-S-18728	2.3.1
8630	Bar and Forging	MIL-S-6050	2.3.1
8735	Tubing	AMS 6282	2.3.1
8735	Bar and Forging	AMS 6320	2.3.1
8735	Sheet, Strip and Plate	AMS 6357	2.3.1
8740	Bar and Forging	AMS 6322	2.3.1
8740	Tubing	AMS 6323	2.3.1
8740	Bar and Forging	AMS 6327	2.3.1
8740	Sheet, Strip and Plate	AMS 6358	2.3.1
8740	Bar and Forging	MIL-S-6049	2.3.1
15-5PH	Investment Casting	AMS 5400	2.6.6
15-5PH	Bar, Forging, Ring and Extrusion (CEVM)	AMS 5659	2.6.6
15-5PH	Sheet, Strip and Plate (CEVM)	AMS 5862	2.6.6
17-4PH	Investment Casting (H1100)	AMS 5342	2.6.8
17-4PH	Investment Casting (H1000)	AMS 5343	2.6.8
17-4PH	Investment Casting (H900)	AMS 5344	2.6.8
17-4PH	Sheet, Strip and Plate	AMS 5604	2.6.8
17-4PH	Bar, Forging and Ring	AMS 5643	2.6.8
17-7PH	Plate, Sheet and Strip	AMS 5528	2.6.9
17-7PH	Plate, Sheet and Strip	MIL-S-25043	2.6.9
2024-T3 ARAMID Fiber Reinforced	Sheet Laminate	AMS 4254	7.5.1
280 (300)	Bar	AMS 6514	2.5.1
280 (300)	Sheet and Plate	AMS 6521	2.5.1
300M (0.42C)	Bar and Forging	AMS 6257	2.3.1
300M (0.42C)	Tubing	AMS 6257	2.3.1
300M (0.42C)	Bar and Forging	AMS 6419	2.3.1
300M (0.42C)	Tubing	AMS 6419	2.3.1
300M (0.4C)	Bar and Forging	AMS 6417	2.3.1
300M (0.4C)	Tubing	AMS 6417	2.3.1
4130 - N	Tubing	AMS 6360	2.3.1
4330V	Bar and Forging	AMS 6411	2.3.1
4330V	Tubing	AMS 6411	2.3.1
4330V	Bar and Forging	AMS 6427	2.3.1
4330V	Tubing	AMS 6427	2.3.1
4335V	Bar and Forging	AMS 6429	2.3.1
4335V	Tubing	AMS 6429	2.3.1
4335V	Bar and Forging	AMS 6430	2.3.1
4335V	Tubing	AMS 6430	2.3.1
4335V	Sheet, Strip and Plate	AMS 6433	2.3.1
4335V	Sheet, Strip and Plate	AMS 6435	2.3.1
5Cr-Mo-V	Sheet, Strip and Plate	AMS 6437	2.4.1
5Cr-Mo-V	Bar and Forging (CEVM)	AMS 6487	2.4.1
5Cr-Mo-V	Bar and Forging	AMS 6488	2.4.1
6013-T4	Sheet	AMS 4216	3.6.1
6013-T6	Sheet	AMS 4347	3.6.1
7049/7149	Forging	AMS 4111	3.7.2
7049/7149	Extrusion	AMS 4157	3.7.2
7049/7149	Plate	AMS 4200	3.7.2

Key: Underline indicates inactive for new design.

**MIL-HDBK-5H**  
**1 December 1998**

<b>Alloy Name</b>	<b>Form</b>	<b>Specification</b>	<b>Section</b>
7049/7149	Forging	AMS 4320	3.7.2
7049/7149	Extrusion	AMS 4343	3.7.2
7049/7149	Forging	MIL-A-22771	3.7.2
7049/7149	Forging	QQ-A-367	3.7.2
7475-T761 ARAMID Fiber Reinforced	Sheet Laminate	AMS 4302	7.5.2
9Ni-4Co-0.20C	Sheet, Strip and Plate	AMS 6523	2.4.2
9Ni-4Co-0.20C	Sheet, Strip and Plate	AMS 6524	2.4.3
9Ni-4Co-0.20C	Bar and Forging, Tubing	AMS 6526	2.4.3
A201.0	Casting (T7 Temper)	MIL-A-21180	3.8.1
A-286	Sheet, Strip and Plate	AMS 5525	6.2.1
A-286	Bar, Forging, Tubing and Ring	AMS 5731	6.2.1
A-286	Bar, Forging, Tubing and Ring	AMS 5732	6.2.1
A-286	Bar, Forging and Tubing	AMS 5734	6.2.1
A-286	Bar, Forging and Tubing	AMS 5737	6.2.1
A356.0	Casting	AMS 4218	3.9.5
A356.0	Casting	MIL-A-21180	3.9.5
A357.0	Casting	MIL-A-21180	3.9.6
AerMet 100	Bar and Forging	AMS 6478	2.5.3
AerMet 100	Bar and Forging	AMS 6532	2.5.3
AF1410	Bar and Forging	AMS 6527	2.5.2
AISI 1025	Sheet, Strip, and Plate	AMS 5046	2.2.1
AISI 1025	Bar	MIL-S-7079, Comp. 3	2.2.1
AISI 1025	Sheet and Strip	MIL-S-7952	2.2.1
AISI 1025	Tubing	MIL-T-5066	2.2.1
AISI 1025 - N	Seamless Tubing	AMS 5075	2.2.1
AISI 1025 - N	Tubing	AMS 5077	2.2.1
AISI 301	Sheet and Strip	AMS 5517	2.7.1
AISI 301	Sheet and Strip	AMS 5518	2.7.1
AISI 301	Sheet and Strip	AMS 5519	2.7.1
AISI 301	Plate, Sheet and Strip	MIL-S-5059	2.7.1
Alloy 188	Sheet and Plate	AMS 5608	6.4.2
Alloy 188	Bar and Forging	AMS 5772	6.4.2
AM100A	Investment Casting	AMS 4455	4.3.1
AM100A	Permanent Mold Casting	AMS 4483	4.3.1
AM100A	Casting	MIL-M-46062	4.3.1
AM-350	Sheet and Strip	AMS 5548	2.6.1
AM-355	Sheet and Strip	AMS 5547	2.6.2
AM-355	Plate	AMS 5549	2.6.2
AM-355	Bar, Forging and Forging Stock	AMS 5743	2.6.2
AZ31B	Sheet and Plate	AMS 4375	4.2.1
AZ31B	Plate	AMS 4376	4.2.1
AZ31B	Sheet and Plate	AMS 4377	4.2.1
AZ31B	Forging	ASTM B 91	4.2.1
AZ31B	Extrusion	ASTM B 107	4.2.1
AZ61A	Extrusion	AMS 4350	4.2.2
AZ61A	Forging	ASTM B 91	4.2.2
AZ91C/AZ91E	Sand Casting	AMS 4437	4.3.2
AZ91C/AZ91E	Sand Casting	AMS 4446	4.3.2
AZ91C/AZ91E	Investment Casting	AMS 4452	4.3.2
AZ91C/AZ91E	Casting	MIL-M-46062	4.3.2
AZ92A	Sand Casting	AMS 4434	4.3.3
AZ92A	Permanent Mold Casting	AMS 4484	4.3.3
AZ92A	Casting	MIL-M-46062	4.3.3
C355.0	Casting	MIL-A-21180	3.9.3
Copper Beryllium	Strip (TB00)	AMS 4530	7.3.2

Key: Underline indicates inactive for new design.

**MIL-HDBK-5H****1 December 1998**

<b>Alloy Name</b>	<b>Form</b>	<b>Specification</b>	<b>Section</b>
Copper Beryllium	Strip (TD02)	AMS 4532	7.3.2
Copper Beryllium	Bar and Rod (TF00)	AMS 4533	7.3.2
Copper Beryllium	Bar and Rod (TH04)	AMS 4534	7.3.2
Copper Beryllium	Mechanical tubing (TF00)	AMS 4535	7.3.2
Copper Beryllium	Bar, Rod, Shapes and Forging (TB00)	AMS 4650	7.3.2
Copper Beryllium	Bar and Rod (TD04)	AMS 4651	7.3.2
Copper Beryllium	Sheet (TB00, TD01, TD02, TD04)	ASTM B 194	7.3.2
CP Titanium	Sheet, Strip and Plate	AMS 4900	5.2.1
CP Titanium	Sheet, Strip and Plate	AMS 4901	5.2.1
CP Titanium	Sheet, Strip and Plate	AMS 4902	5.2.1
CP Titanium	Bar	AMS 4921	5.2.1
CP Titanium	Extruded Bars and Shapes	MIL-T-81556	5.2.1
CP Titanium	Sheet, Strip and Plate	MIL-T-9046	5.2.1
CP Titanium	Bar	MIL-T-9047	5.2.1
Custom 450	Bar, Forging, Tubing, Wire and Ring (air melted)	AMS 5763	2.6.3
Custom 450	Bar, Forging, Tubing, Wire and Ring (CEM)	AMS 5773	2.6.3
Custom 455	Tubing (welded)	AMS 5578	2.6.4
Custom 455	Bar and Forging	AMS 5617	2.6.4
D357.0	Sand Composite Casting	AMS 4241	3.9.7
D6AC	Bar and Forging	AMS 6431	2.3.1
D6AC	Tubing	AMS 6431	2.3.1
D6AC	Bar and Forging	MIL-S-8949	2.3.1
D6AC	Sheet, Strip and Plate	MIL-S-8949	2.3.1
EZ33A	Sand Casting	AMS 4442	4.3.4
Hastelloy X	Sheet and Plate	AMS 5536	6.3.1
Hastelloy X	Bar and Forging	AMS 5754	6.3.1
Hy-Tuf	Bar and Forging	AMS 6418	2.3.1
Hy-Tuf	Tubing	AMS 6418	2.3.1
Hy-Tuf	Bar and Forging	AMS 6425	2.3.1
Hy-Tuf	Tubing	AMS 6425	2.3.1
Inconel 718	Investment Casting	AMS 5383	6.3.5
Inconel 718	Tubing; Creep Rupture	AMS 5589	6.3.5
Inconel 718	Tubing; Short-Time	AMS 5590	6.3.5
Inconel 718	Sheet, Strip and Plate; Creep Rupture	AMS 5596	6.3.5
Inconel 718	Sheet, Strip and Plate; Short-Time	AMS 5597	6.3.5
Inconel 718	Bar and Forging; Creep Rupture	AMS 5662	6.3.5
Inconel 718	Bar and Forging; Creep Rupture	AMS 5663	6.3.5
Inconel 718	Bar and Forging; Short-Time	AMS 5664	6.3.5
Inconel Alloy 600	Plate, Sheet and Strip	AMS 5540	6.3.2
Inconel Alloy 600	Tubing, Seamless	AMS 5580	6.3.2
Inconel Alloy 600	Bar and Rod	ASTM B 166	6.3.2
Inconel Alloy 600	Forging	ASTM B 564	6.3.2
Inconel Alloy 625	Sheet, Strip and Plate	AMS 5599	6.3.3
Inconel Alloy 625	Bar, Forging and Ring	AMS 5666	6.3.3
Inconel Alloy 706	Sheet, Strip and Plate	AMS 5605	6.3.4
Inconel Alloy 706	Sheet, Strip and Plate	AMS 5606	6.3.4
Inconel Alloy 706	Bar, Forging and Ring	AMS 5701	6.3.4
Inconel Alloy 706	Bar, Forging and Ring	AMS 5702	6.3.4
Inconel Alloy 706	Bar, Forging and Ring	AMS 5703	6.3.4
Inconel Alloy X-750	Sheet, Strip and Plate; Annealed	AMS 5542	6.3.6
Inconel Alloy X-750	Bar and Forging; Equalized	AMS 5667	6.3.6
L-605	Sheet	AMS 5537	6.4.1
L-605	Bar and Forging	AMS 5759	6.4.1
Manganese Bronzes	Casting	AMS 4860	7.3.1
Manganese Bronzes	Casting	AMS 4862	7.3.1

Key: Underline indicates inactive for new design.

**MIL-HDBK-5H****1 December 1998**

<b>Alloy Name</b>	<b>Form</b>	<b>Specification</b>	<b>Section</b>
MP159 Alloy	Bar (solution treated and cold drawn)	AMS 5842	7.4.2
MP159 Alloy	Bar (solution treated, cold drawn and aged)	AMS 5843	7.4.2
MP35N Alloy	Bar (solution treated and cold drawn)	AMS 5844	7.4.1
MP35N Alloy	Bar (solution treated, cold drawn and aged)	AMS 5845	7.4.1
N-155	Sheet	AMS 5532	6.2.2
N-155	Tubing (welded)	AMS 5585	6.2.2
N-155	Bar and Forging	AMS 5768	6.2.2
N-155	Bar and Forging	AMS 5769	6.2.2
PH13-8Mo	Bar, Forging Ring and Extrusion (VIM+CEVM)	AMS 5629	2.6.5
PH15-7Mo	Plate, Sheet and Strip	AMS 5520	2.6.7
QE22A Magnesium	Sand Casting	AMS 4418	4.3.5
QE22A Magnesium	Sand Casting	MIL-M-46062	4.3.5
René 41	Plate, Sheet and Strip	AMS 5545	6.3.7
René 41	Bar and Forging	AMS 5713	6.3.7
René 41 - STA	Bar and Forging	AMS 5712	6.3.7
Standard Grade Beryllium	Sheet and Plate	AMS 7902	7.2.1
Standard Grade Beryllium	Bar, Rod, Tubing and Machined Shapes	AMS 7906	7.2.1
Ti-10V-2Fe-3Al (Ti-10-2-3)	Forging	AMS 4983	5.5.3
Ti-10V-2Fe-3Al (Ti-10-2-3)	Forging	AMS 4984	5.5.3
Ti-10V-2Fe-3Al (Ti-10-2-3)	Forging	AMS 4986	5.5.3
Ti-13V-11Cr-3Al	Sheet, Strip and Plate	MIL-T-9046	5.5.1
Ti-13V-11Cr-3Al	Bar	MIL-T-9047	5.5.1
Ti-15V-3Cr-3Sn-3Al (Ti-15-3-3-3)	Sheet and Strip	AMS 4914	5.5.2
Ti-5Al-2.5Sn	Sheet, Strip and Plate	AMS 4910	5.3.1
Ti-5Al-2.5Sn	Bar	AMS 4926	5.3.1
Ti-5Al-2.5Sn	Forging	AMS 4966	5.3.1
Ti-5Al-2.5Sn	Extruded Bar and Shapes	MIL-T-81556	5.3.1
Ti-5Al-2.5Sn	Sheet, Strip and Plate	MIL-T-9046	5.3.1
Ti-5Al-2.5Sn	Bar	MIL-T-9047	5.3.1
Ti-6Al-2Sn-4Zr-2Mo	Sheet, Strip and Plate	AMS 4919	5.3.3
Ti-6Al-2Sn-4Zr-2Mo	Bar	AMS 4975	5.3.3
Ti-6Al-2Sn-4Zr-2Mo	Forging	AMS 4976	5.3.3
Ti-6Al-2Sn-4Zr-2Mo	Sheet and Strip	MIL-T-9046	5.3.3
Ti-6Al-4V	Sheet, Strip and Plate	AMS 4911	5.4.1
Ti-6Al-4V	Die Forging	AMS 4920	5.4.1
Ti-6Al-4V	Bar and Die Forging	AMS 4928	5.4.1
Ti-6Al-4V	Extrusion	AMS 4934	5.4.1
Ti-6Al-4V	Extrusion	AMS 4935	5.4.1
Ti-6Al-4V	Casting	AMS 4962	5.4.1
Ti-6Al-4V	Bar	AMS 4967	5.4.1
Ti-6Al-4V	Sheet, Strip and Plate	MIL-T-9046	5.4.1
Ti-6Al-4V	Bar	MIL-T-9047	5.4.1
Ti6Al-6V-2Sn	Sheet, Strip and Plate	AMS 4918	5.4.2
Ti6Al-6V-2Sn	Bar and Forging	AMS 4971	5.4.2
Ti6Al-6V-2Sn	Bar and Forging	AMS 4978	5.4.2
Ti6Al-6V-2Sn	Bar and Forging	AMS 4979	5.4.2
Ti6Al-6V-2Sn	Extruded Bar and Shapes	MIL-T-81556	5.4.2
Ti6Al-6V-2Sn	Sheet, Strip and Plate	MIL-T-9046	5.4.2
Ti-8Al-1Mo-1V	Sheet, Strip and Plate	AMS 4915	5.3.2
Ti-8Al-1Mo-1V	Sheet, Strip and Plate	AMS 4916	5.3.2
Ti-8Al-1Mo-1V	Forging	AMS 4973	5.3.2
Ti-8Al-1Mo-1V	Sheet, Strip and Plate	MIL-T-9046	5.3.2
Ti-8Al-1Mo-1V	Bar	MIL-T-9047	5.3.2
Waspaloy	Plate, Sheet and Strip	AMS 5544	6.3.8
Waspaloy	Forging	AMS 5704	6.3.8

Key: Underline indicates inactive for new design.

**MIL-HDBK-5H****1 December 1998**

<b>Alloy Name</b>	<b>Form</b>	<b>Specification</b>	<b>Section</b>
Waspaloy	Bar, Forgings and Ring	AMS 5706	6.3.8
Waspaloy	Bar, Forgings and Ring	AMS 5707	6.3.8
Waspaloy	Bar, Forgings and Ring	AMS 5708	6.3.8
Waspaloy	Bar, Forgings and Ring	AMS 5709	6.3.8
ZE41A Magnesium	Sand Casting	AMS 4439	4.3.6
ZK60A-F	Extrusion	ASTM B 107	4.2.3
ZK60A-T5	Extrusion	AMS 4352	4.2.3
ZK60A-T5	Die and Hand Forging	AMS 4362	4.2.3

**MIL-HDBK-5H**  
**1 December 1998**

***APPENDIX C***

**C.0 Specification Index**

<b>Specification</b>	<b>Alloy Name</b>	<b>Form/Application</b>	<b>Section</b>
AMS 4015	5052	Sheet and Plate	3.5.1
AMS 4016	5052	Sheet and Plate	3.5.1
AMS 4017	5052	Sheet and Plate	3.5.1
AMS 4025	6061	Sheet and Plate	3.6.2
AMS 4026	6061	Sheet and Plate	3.6.2
AMS 4027	6061	Sheet and Plate	3.6.2
AMS 4028	2014	Bare Sheet and Plate	3.2.1
AMS 4029	2014	Bare Sheet and Plate	3.2.1
AMS 4031	2219	Sheet and Plate	3.2.7
AMS 4035	2024	Bare Sheet and Plate	3.2.3
AMS 4037	2024	Bare Sheet and Plate	3.2.3
AMS 4044	7075	Bare Sheet and Plate	3.7.4
AMS 4045	7075	Bare Sheet and Plate	3.7.4
AMS 4049	7075	Clad Sheet and Plate	3.7.4
AMS 4050	7050	Bare Plate	3.7.3
AMS 4056	5083	Bare Sheet and Plate	3.5.2
AMS 4078	7075	Bare Plate	3.7.4
AMS 4080	6061	Tubing Seamless, Drawn	3.6.2
AMS 4082	6061	Tubing Seamless, Drawn	3.6.2
AMS 4084 (T61)	7475	Bare Sheet	3.7.8
AMS 4085 (T761)	7475	Bare Sheet	3.7.8
AMS 4086	2024	Tubing, Hydraulic, Seamless, Drawn	3.2.3
AMS 4089 (T7651)	7475	Bare Plate	3.7.8
AMS 4090 (T651)	7475	Bare Plate	3.7.8
AMS 4100 (T761)	7475	Clad Sheet	3.7.8
AMS 4101	2124	Plate	3.2.6
AMS 4107	7050	Die Forging	3.7.3
AMS 4108	7050	Hand Forging	3.7.3
AMS 4111	7049/7149	Forging	3.7.2
AMS 4115	6061	Bar and Rod, Rolled or Cold Finished	3.6.2
AMS 4116	6061	Bar and Rod, Cold Finished	3.6.2
AMS 4117	6061	Bar and Rod, Rolled or Cold Finished	3.6.2
AMS 4118	2017	Bar and Rod, Rolled or Cold-Finished	3.2.2
AMS 4120	2024	Bar and Rod, Rolled or Cold-Finished	3.2.3
AMS 4121	2014	Bar and Rod, Rolled or Cold Finished	3.2.1
AMS 4122	7075	Bar and Rod, Rolled or Cold Finished	3.7.4
AMS 4123	7075	Bar and Rod, Rolled or Cold Finished	3.7.4
AMS 4124	7075	Bar and Rod, Rolled or Cold Finished	3.7.4
AMS 4125	6151	Die Forging	3.6.3
AMS 4126	7075	Forging	3.7.4
AMS 4127	6061	Forging	3.6.2
AMS 4130	2025	Die Forging	3.2.4
AMS 4132	2618	Die and Hand Forgings	3.2.10
AMS 4133	2014	Forging	3.2.1

Key: Underline indicates inactive for new design.



**MIL-HDBK-5H**  
**1 December 1998**

<b>Specification</b>	<b>Alloy Name</b>	<b>Form/Application</b>	<b>Section</b>
AMS 4141	7075	Die Forging	3.7.4
AMS 4144	2219	Hand Forging	3.2.7
AMS 4147	7075	Forging	3.7.4
AMS 4148 (T66)	7175	Die Forging	3.7.6
AMS 4149 (T74)	7175	Die and Hand Forging	3.7.6
AMS 4152	2024	Extrusion	3.2.3
AMS 4153	2014	Extrusion	3.2.1
AMS 4157	7049/7149	Extrusion	3.7.2
AMS 4160	6061	Extrusion	3.6.2
AMS 4161	6061	Extrusion	3.6.2
AMS 4162	2219	Extrusion	3.2.7
AMS 4163	2219	Extrusion	3.2.7
AMS 4164	2024	Extrusion	3.2.3
AMS 4165	2024	Extrusion	3.2.3
AMS 4172	6061	Extrusion	3.6.2
AMS 4179 (T7452)	7175	Hand Forging	3.7.6
AMS 4186	7075	Bar and Rod, Rolled or Cold Finished	3.7.4
AMS 4187	7075	Bar and Rod, Rolled or Cold Finished	3.7.4
AMS 4200	7049/7149	Plate	3.7.2
AMS 4201	7050	Bare Plate	3.7.3
AMS 4202 (T7351)	7475	Bare Plate	3.7.8
AMS 4204	7010	Plate	3.7.1
AMS 4205	7010	Plate	3.7.1
AMS 4207 (T61)	7475	Clad Sheet	3.7.8
AMS 4216	6013 (T4)	Sheet	3.6.1
AMS 4217	356.0	Sand Casting	3.9.4
AMS 4218	A356.0	Casting	3.9.5
AMS 4241	D357.0	Sand Composite Casting	3.9.7
AMS 4248	6061	Hand Forging	3.6.2
AMS 4251	2090	Sheet	3.2.5
AMS 4252 (T7751)	7150	Bare Plate	3.7.5
AMS 4254	2024-T3 ARAMID Fiber Reinforced	Sheet Laminate	7.5.1
AMS 4260	356.0	Investment Casting	3.9.4
AMS 4281	355.0	Permanent Mold Casting	3.9.2
AMS 4284	356.0	Permanent Mold Casting	3.9.4
AMS 4296	2524-T3	Sheet and Plate	3.2.9
AMS 4302	7475-T761 ARAMID Fiber Reinforced	Sheet Laminate	7.5.2
AMS 4306 (T6151)	7150	Bare Plate	3.7.5
AMS 4307 (T61511)	7150	Extrusion	3.7.5
AMS 4320	7049/7149	Forging	3.7.2
AMS 4333	7050	Die Forging	3.7.3
AMS 4334	7249	Hand Forging	3.7.7
AMS 4340	7050	Extruded Shape	3.7.3
AMS 4341	7050	Extruded Shape	3.7.3
AMS 4342	7050	Extruded Shape	3.7.3
AMS 4343	7049/7149	Extrusion	3.7.2
AMS 4344 (T73511)	7175	Extrusion	3.7.6
AMS 4345 (T77511)	7150	Extrusion	3.7.5
AMS 4347	6013 (T6)	Sheet	3.6.1
AMS 4350	AZ61A	Extrusion	4.2.2
AMS 4352	ZK60A-T5	Extrusion	4.2.3
AMS 4362	ZK60A-T5	Die and Hand Forging	4.2.3
AMS 4375	AZ31B	Sheet and Plate	4.2.1
AMS 4376	AZ31B	Plate	4.2.1

Key: Underline indicates inactive for new design.



**MIL-HDBK-5H****1 December 1998**

<b>Specification</b>	<b>Alloy Name</b>	<b>Form/Application</b>	<b>Section</b>
AMS 4377	AZ31B	Sheet and Plate	4.2.1
AMS 4418	QE22A Magnesium	Sand Casting	4.3.5
AMS 4434	AZ92A	Sand Casting	4.3.3
AMS 4437	AZ91C/AZ91E	Sand Casting	4.3.2
AMS 4439	ZE41A Magnesium	Sand Casting	4.3.6
AMS 4442	EZ33A	Sand Casting	4.3.4
AMS 4446	AZ91C/AZ91E	Sand Casting	4.3.2
AMS 4452	AZ91C/AZ91E	Investment Casting	4.3.2
AMS 4455	AM100A	Investment Casting	4.3.1
AMS 4483	AM100A	Permanent Mold Casting	4.3.1
AMS 4484	AZ92A	Permanent Mold Casting	4.3.3
AMS 4530	Copper Beryllium	Strip (TB00)	7.3.2
AMS 4532	Copper Beryllium	Strip (TD02)	7.3.2
AMS 4533	Copper Beryllium	Bar and Rod (TF00)	7.3.2
AMS 4534	Copper Beryllium	Bar and Rod (TH04)	7.3.2
AMS 4535	Copper Beryllium	Mechanical tubing (TF00)	7.3.2
AMS 4650	Copper Beryllium	Bar, Rod, Shapes and Forging (TB00)	7.3.2
AMS 4651	Copper Beryllium	Bar and Rod (TD04)	7.3.2
AMS 4860	Manganese Bronzes	Casting	7.3.1
AMS 4862	Manganese Bronzes	Casting	7.3.1
AMS 4900	CP Titanium	Sheet, Strip and Plate	5.2.1
AMS 4901	CP Titanium	Sheet, Strip and Plate	5.2.1
AMS 4902	CP Titanium	Sheet, Strip and Plate	5.2.1
AMS 4910	Ti-5Al-2.5Sn	Sheet, Strip and Plate	5.3.1
AMS 4911	Ti-6Al-4V	Sheet, Strip and Plate	5.4.1
AMS 4914	Ti-15V-3Cr-3Sn-3Al (Ti-15-3)-3-3	Sheet and Strip	5.5.2
AMS 4915	Ti-8Al-1Mo-1V	Sheet, Strip and Plate	5.3.2
AMS 4916	Ti-8Al-1Mo-1V	Sheet, Strip and Plate	5.3.2
AMS 4918	Ti6Al-6V-2Sn	Sheet, Strip and Plate	5.4.2
AMS 4919	Ti-6Al-2Sn-4Zr-2Mo	Sheet, Strip and Plate	5.3.3
AMS 4920	Ti-6Al-4V	Die Forging	5.4.1
AMS 4921	CP Titanium	Bar	5.2.1
AMS 4926	Ti-5Al-2.5Sn	Bar	5.3.1
AMS 4928	Ti-6Al-4V	Bar and Die Forging	5.4.1
AMS 4934	Ti-6Al-4V	Extrusion	5.4.1
AMS 4935	Ti-6Al-4V	Extrusion	5.4.1
AMS 4962	Ti-6Al-4V	Casting	5.4.1
AMS 4966	Ti-5Al-2.5Sn	Forging	5.3.1
AMS 4967	Ti-6Al-4V	Bar	5.4.1
AMS 4971	Ti6Al-6V-2Sn	Bar and Forging	5.4.2
AMS 4973	Ti-8Al-1Mo-1V	Forging	5.3.2
AMS 4975	Ti-6Al-2Sn-4Zr-2Mo	Bar	5.3.3
AMS 4976	Ti-6Al-2Sn-4Zr-2Mo	Forging	5.3.3
AMS 4978	Ti6Al-6V-2Sn	Bar and Forging	5.4.2
AMS 4979	Ti6Al-6V-2Sn	Bar and Forging	5.4.2
AMS 4983	Ti-10V-2Fe-3Al (Ti-10-2-3)	Forging	5.5.3
AMS 4984	Ti-10V-2Fe-3Al (Ti-10-2-3)	Forging	5.5.3
AMS 4986	Ti-10V-2Fe-3Al (Ti-10-2-3)	Forging	5.5.3
AMS 5046	AISI 1025	Sheet, Strip, and Plate	2.2.1
AMS 5075	AISI 1025 - N	Seamless Tubing	2.2.1
AMS 5077	AISI 1025 - N	Tubing	2.2.1
AMS 5342	17-4PH	Investment Casting (H1100)	2.6.8
AMS 5343	17-4PH	Investment Casting (H1000)	2.6.8
AMS 5344	17-4PH	Investment Casting (H900)	2.6.8
AMS 5383	Inconel 718	Investment Casting	6.3.5

Key: Underline indicates inactive for new design.

**MIL-HDBK-5H**  
**1 December 1998**

<b>Specification</b>	<b>Alloy Name</b>	<b>Form/Application</b>	<b>Section</b>
AMS 5400	15-5PH	Investment Casting	2.6.6
AMS 5517	AISI 301	Sheet and Strip	2.7.1
AMS 5518	AISI 301	Sheet and Strip	2.7.1
AMS 5519	AISI 301	Sheet and Strip	2.7.1
AMS 5520	PH15-7Mo	Plate, Sheet and Strip	2.6.7
AMS 5525	A-286	Sheet, Strip and Plate	6.2.1
AMS 5528	17-7PH	Plate, Sheet and Strip	2.6.9
AMS 5532	N-155	Sheet	6.2.2
AMS 5536	Hastelloy X	Sheet and Plate	6.3.1
AMS 5537	L-605	Sheet	6.4.1
AMS 5540	Inconel Alloy 600	Plate, Sheet and Strip	6.3.2
AMS 5542	Inconel Alloy X-750	Sheet, Strip and Plate; Annealed	6.3.6
AMS 5544	Waspaloy	Plate, Sheet and Strip	6.3.8
AMS 5545	René 41	Plate, Sheet and Strip	6.3.7
AMS 5547	AM-355	Sheet and Strip	2.6.2
AMS 5548	AM-350	Sheet and Strip	2.6.1
AMS 5549	AM-355	Plate	2.6.2
AMS 5578	Custom 455	Tubing (welded)	2.6.4
AMS 5580	Inconel Alloy 600	Tubing, Seamless	6.3.2
AMS 5585	N-155	Tubing (welded)	6.2.2
AMS 5589	Inconel 718	Tubing; Creep Rupture	6.3.5
AMS 5590	Inconel 718	Tubing; Short-Time	6.3.5
AMS 5596	Inconel 718	Sheet, Strip and Plate; Creep Rupture	6.3.5
AMS 5597	Inconel 718	Sheet, Strip and Plate; Short-Time	6.3.5
AMS 5599	Inconel Alloy 625	Sheet, Strip and Plate	6.3.3
AMS 5604	17-4PH	Sheet, Strip and Plate	2.6.8
AMS 5605	Inconel Alloy 706	Sheet, Strip and Plate	6.3.4
AMS 5606	Inconel Alloy 706	Sheet, Strip and Plate	6.3.4
AMS 5608	Alloy 188	Sheet and Plate	6.4.2
AMS 5617	Custom 455	Bar and Forging	2.6.4
AMS 5629	PH13-8Mo	Bar, Forging Ring and Extrusion (VIM+CEVM)	2.6.5
AMS 5643	17-4PH	Bar, Forging and Ring	2.6.8
AMS 5659	15-5PH	Bar, Forging, Ring and Extrusion (CEVM)	2.6.6
AMS 5662	Inconel 718	Bar and Forging; Creep Rupture	6.3.5
AMS 5663	Inconel 718	Bar and Forging; Creep Rupture	6.3.5
AMS 5664	Inconel 718	Bar and Forging; Short-Time	6.3.5
AMS 5666	Inconel Alloy 625	Bar, Forging and Ring	6.3.3
AMS 5667	Inconel Alloy X-750	Bar and Forging; Equalized	6.3.6
AMS 5701	Inconel Alloy 706	Bar, Forging and Ring	6.3.4
AMS 5702	Inconel Alloy 706	Bar, Forging and Ring	6.3.4
AMS 5703	Inconel Alloy 706	Bar, Forging and Ring	6.3.4
AMS 5704	Waspaloy	Forging	6.3.8
AMS 5706	Waspaloy	Bar, Forgings and Ring	6.3.8
AMS 5707	Waspaloy	Bar, Forgings and Ring	6.3.8
AMS 5708	Waspaloy	Bar, Forgings and Ring	6.3.8
AMS 5709	Waspaloy	Bar, Forgings and Ring	6.3.8
AMS 5712	René 41 - STA	Bar and Forging	6.3.7
AMS 5713	René 41	Bar and Forging	6.3.7
AMS 5731	A-286	Bar, Forging, Tubing and Ring	6.2.1
AMS 5732	A-286	Bar, Forging, Tubing and Ring	6.2.1
AMS 5734	A-286	Bar, Forging and Tubing	6.2.1
AMS 5737	A-286	Bar, Forging and Tubing	6.2.1
AMS 5743	AM-355	Bar, Forging and Forging Stock	2.6.2
AMS 5754	Hastelloy X	Bar and Forging	6.3.1
AMS 5759	L-605	Bar and Forging	6.4.1

Key: Underline indicates inactive for new design.

**MIL-HDBK-5H****1 December 1998**

<b>Specification</b>	<b>Alloy Name</b>	<b>Form/Application</b>	<b>Section</b>
AMS 5763	Custom 450	Bar, Forging, Tubing, Wire and Ring (air melted)	2.6.3
AMS 5768	N-155	Bar and Forging	6.2.2
AMS 5769	N-155	Bar and Forging	6.2.2
AMS 5772	Alloy 188	Bar and Forging	6.4.2
AMS 5773	Custom 450	Bar, Forging, Tubing, Wire and Ring (CEM)	2.6.3
AMS 5842	MP159 Alloy	Bar (solution treated and cold drawn)	7.4.2
AMS 5843	MP159 Alloy	Bar (solution treated, cold drawn and aged)	7.4.2
AMS 5844	MP35N Alloy	Bar (solution treated and cold drawn)	7.4.1
AMS 5845	MP35N Alloy	Bar (solution treated, cold drawn and aged)	7.4.1
AMS 5862	15-5PH	Sheet, Strip and Plate (CEVM)	2.6.6
AMS 6257	300M (0.42C)	Bar and Forging	2.3.1
AMS 6257	300M (0.42C)	Tubing	2.3.1
AMS 6280	8630	Bar and Forging	2.3.1
AMS 6281	8630	Tubing	2.3.1
AMS 6282	8735	Tubing	2.3.1
AMS 6320	8735	Bar and Forging	2.3.1
AMS 6322	8740	Bar and Forging	2.3.1
AMS 6323	8740	Tubing	2.3.1
AMS 6327	8740	Bar and Forging	2.3.1
AMS 6348	4130	Bar and Forging	2.3.1
AMS 6349	4140	Bar and Forging	2.3.1
AMS 6350	4130	Sheet, Strip and Plate	2.3.1
AMS 6351	4130	Sheet, Strip and Plate	2.3.1
AMS 6352	4135	Sheet, Strip and Plate	2.3.1
AMS 6355	8630	Sheet, Strip and Plate	2.3.1
AMS 6357	8735	Sheet, Strip and Plate	2.3.1
AMS 6358	8740	Sheet, Strip and Plate	2.3.1
AMS 6359	4340	Sheet, Strip and Plate	2.3.1
AMS 6360	4130 - N	Tubing (normalized)	2.3.1
AMS 6361	4130	Tubing	2.3.1
AMS 6362	4130	Tubing	2.3.1
AMS 6365	4135	Tubing	2.3.1
AMS 6370	4130	Bar and Forging	2.3.1
AMS 6371	4130	Tubing	2.3.1
AMS 6372	4135	Tubing	2.3.1
AMS 6373	4130	Tubing	2.3.1
AMS 6374	4130	Tubing	2.3.1
AMS 6381	4140	Tubing	2.3.1
AMS 6382	4140	Bar and Forging	2.3.1
AMS 6390	4140	Tubing	2.3.1
AMS 6395	4140	Sheet, Strip and Plate	2.3.1
AMS 6411	4330V	Bar and Forging	2.3.1
AMS 6411	4330V	Tubing	2.3.1
AMS 6414	4340	Bar and Forging	2.3.1
AMS 6414	4340	Tubing	2.3.1
AMS 6415	4340	Bar and Forging	2.3.1
AMS 6415	4340	Tubing	2.3.1
AMS 6417	300M (0.4C)	Bar and Forging	2.3.1
AMS 6417	300M (0.4C)	Tubing	2.3.1
AMS 6418	Hy-Tuf	Bar and Forging	2.3.1
AMS 6418	Hy-Tuf	Tubing	2.3.1
AMS 6419	300M (0.42C)	Bar and Forging	2.3.1
AMS 6419	300M (0.42C)	Tubing	2.3.1
AMS 6425	Hy-Tuf	Bar and Forging	2.3.1
AMS 6425	Hy-Tuf	Tubing	2.3.1

Key: Underline indicates inactive for new design.

**MIL-HDBK-5H****1 December 1998**

<b>Specification</b>	<b>Alloy Name</b>	<b>Form/Application</b>	<b>Section</b>
AMS 6427	4330V	Bar and Forging	2.3.1
AMS 6427	4330V	Tubing	2.3.1
AMS 6429	4335V	Bar and Forging	2.3.1
AMS 6429	4335V	Tubing	2.3.1
AMS 6430	4335V	Bar and Forging	2.3.1
AMS 6430	4335V	Tubing	2.3.1
AMS 6431	D6AC	Bar and Forging	2.3.1
AMS 6431	D6AC	Tubing	2.3.1
AMS 6433	4335V	Sheet, Strip and Plate	2.3.1
AMS 6435	4335V	Sheet, Strip and Plate	2.3.1
AMS 6437	5Cr-Mo-V	Sheet, Strip and Plate	2.4.1
AMS 6454	4340	Sheet, Strip and Plate	2.3.1
AMS 6478	AerMet 100	Bar and Forging	2.5.3
AMS 6487	5Cr-Mo-V	Bar and Forging (CEVM)	2.4.1
AMS 6488	5Cr-Mo-V	Bar and Forging	2.4.1
AMS 6512	250	Bar	2.5.1
AMS 6514	280 (300)	Bar	2.5.1
AMS 6520	250	Sheet and Plate	2.5.1
AMS 6521	280 (300)	Sheet and Plate	2.5.1
AMS 6523	9Ni-4Co-0.20C	Sheet, Strip and Plate	2.4.2
AMS 6524	9Ni-4Co-0.20C	Sheet, Strip and Plate	2.4.3
AMS 6526	9Ni-4Co-0.20C	Bar and Forging, Tubing	2.4.3
AMS 6527	AF1410	Bar and Forging	2.5.2
AMS 6528	4130	Bar and Forging	2.3.1
AMS 6529	4140	Bar and Forging	2.3.1
AMS 6532	AerMet 100	Bar and Forging	2.5.3
AMS 7902	Standard Grade Beryllium	Sheet and Plate	7.2.1
AMS 7906	Standard Grade Beryllium	Bar, Rod, Tubing and Machined Shapes	7.2.1
AMS-QQ-A-200/2	2014	Extruded Bar, Rod and Shapes	3.2.1
AMS-QQ-A-200/3	2024	Extruded Bar, Rod and Shapes	3.2.3
AMS-QQ-A-200/4	5083	Extruded Bar, Rod and Shapes	3.5.2
AMS-QQ-A-200/5	5086	Extruded Bar, Rod and Shapes	3.5.3
AMS-QQ-A-200/6	5454	Extruded Bar, Rod and Shapes	3.5.4
AMS-QQ-A-200/7	5456	Extruded Bar, Rod and Shapes	3.5.5
AMS-QQ-A-200/8	6061	Extruded Rod, Bar Shapes and Tubing	3.6.2
AMS-QQ-A-200/11, 15	7075	Extruded Bar, Rod and Shapes	3.7.4
AMS-QQ-A-225/4	2014	Rolled or Drawn Bar, Rod and Shapes	3.2.1
AMS-QQ-A-225/5	2017	Rolled Bar and Rod	3.2.2
AMS-QQ-A-225/6	2024	Rolled or Drawn Bar, Rod and Wire	3.2.3
AMS-QQ-A-225/8	6061	Rolled Bar, Rod and Shapes	3.6.2
AMS-QQ-A-225/9	7075	Rolled or Drawn Bar and Rod	3.7.4
AMS-QQ-A-250/3	2014	Clad Sheet and Plate	3.2.1
AMS-QQ-A-250/4	2024	Bare Sheet and Plate	3.2.3
AMS-QQ-A-250/5	2024	Clad Sheet and Plate	3.2.3
AMS-QQ-A-250/6	5083	Bare Sheet and Plate	3.5.2
AMS-QQ-A-250/7	5086	Sheet and Plate	3.5.3
AMS-QQ-A-250/8	5052	Sheet and Plate	3.5.1
AMS-QQ-A-250/9	5456	Sheet and Plate	3.5.5
AMS-QQ-A-250/10	5454	Sheet and Plate	3.5.4
AMS-QQ-A-250/11	6061	Sheet and Plate	3.6.2
AMS-QQ-A-250/12, 24	7075	Bare Sheet and Plate	3.7.4
AMS-QQ-A-250/13, 25	7075	Clad Sheet and Plate	3.7.4
AMS-QQ-A-250/29	2124	Plate	3.2.6
AMS-QQ-A-250/30	2219	Sheet and Plate	3.2.7
ASTM B 91	AZ31B	Forging	4.2.1

Key: Underline indicates inactive for new design.

**MIL-HDBK-5H****1 December 1998**

<b>Specification</b>	<b>Alloy Name</b>	<b>Form/Application</b>	<b>Section</b>
ASTM B 91	AZ61A	Forging	4.2.2
ASTM B 107	ZK60A-F	Extrusion	4.2.3
ASTM B 107	AZ31B	Extrusion	4.2.1
ASTM B 166	Inconel Alloy 600	Bar and Rod	6.3.2
ASTM B 194	Copper Beryllium	Sheet (TB00, TD01, TD02, TD04)	7.3.2
ASTM B 564	Inconel Alloy 600	Forging	6.3.2
MIL-A-21180	A201.0	Casting (T7 Temper)	3.8.1
MIL-A-21180	354.0	Casting	3.9.1
MIL-A-21180	C355.0	Casting	3.9.3
MIL-A-21180	A356.0	Casting	3.9.5
MIL-A-21180	A357.0	Casting	3.9.6
MIL-A-21180	359.0	Casting	3.9.8
MIL-A-22771	2014	Forging	3.2.1
MIL-A-22771	2618	Die Forging	3.2.10
MIL-A-22771	6061	Forging	3.6.2
MIL-A-22771	6151	Forging	3.6.3
MIL-A-22771	7049/7149	Forging	3.7.2
MIL-A-22771	7050	Forging	3.7.3
MIL-A-22771	7075	Forging	3.7.4
MIL-A-22771	7175	Forging	3.7.6
MIL-A-46192	2519	Plate	3.2.8
MIL-M-46062	AM100A	Casting	4.3.1
MIL-M-46062	AZ91C/AZ91E	Casting	4.3.2
MIL-M-46062	AZ92A	Casting	4.3.3
MIL-M-46062	QE22A Magnesium	Sand Casting	4.3.5
MIL-P-25995	6061	Pipe	3.6.2
MIL-S-18728	8630	Sheet, Strip and Plate	2.3.1
MIL-S-18729	4130	Sheet, Strip and Plate	2.3.1
MIL-S-25043	17-7PH	Plate, Sheet and Strip	2.6.9
MIL-S-5000	4340	Bar and Forging	2.3.1
MIL-S-5059	AISI 301	Plate, Sheet and Strip	2.7.1
MIL-S-5626	4140	Bar and Forging	2.3.1
MIL-S-6049	8740	Bar and Forging	2.3.1
MIL-S-6050	8630	Bar and Forging	2.3.1
MIL-S-6758	4130	Bar and Forging	2.3.1
MIL-S-7079, Comp. 3	AISI 1025	Bar	2.2.1
MIL-S-7952	AISI 1025	Sheet and Strip	2.2.1
MIL-S-8844	4340	Tubing	2.3.1
MIL-S-8844	4340	Bar and Forging	2.3.1
MIL-S-8949	D6AC	Bar and Forging	2.3.1
MIL-S-8949	D6AC	Sheet, Strip and Plate	2.3.1
MIL-T-5066	AISI 1025	Tubing	2.2.1
MIL-T-6735	4135	Tubing	2.3.1
MIL-T-6736	4130	Tubing	2.3.1
MIL-T-81556	CP Titanium	Extruded Bars and Shapes	5.2.1
MIL-T-81556	Ti-5Al-2.5Sn	Extruded Bar and Shapes	5.3.1
MIL-T-81556	Ti6Al-6V-2Sn	Extruded Bar and Shapes	5.4.2
MIL-T-9046	CP Titanium	Sheet, Strip and Plate	5.2.1
MIL-T-9046	Ti-5Al-2.5Sn	Sheet, Strip and Plate	5.3.1
MIL-T-9046	Ti-8Al-1Mo-1V	Sheet, Strip and Plate	5.3.2
MIL-T-9046	Ti-6Al-2Sn-4Zr-2Mo	Sheet and Strip	5.3.3
MIL-T-9046	Ti-6Al-4V	Sheet, Strip and Plate	5.4.1
MIL-T-9046	Ti6Al-6V-2Sn	Sheet, Strip and Plate	5.4.2
MIL-T-9046	Ti-13V-11Cr-3Al	Sheet, Strip and Plate	5.5.1
MIL-T-9047	CP Titanium	Bar	5.2.1

Key: Underline indicates inactive for new design.

**MIL-HDBK-5H****1 December 1998**

<b>Specification</b>	<b>Alloy Name</b>	<b>Form/Application</b>	<b>Section</b>
MIL-T-9047	Ti-5Al-2.5Sn	Bar	5.3.1
MIL-T-9047	Ti-8Al-1Mo-1V	Bar	5.3.2
MIL-T-9047	Ti-6Al-4V	Bar	5.4.1
MIL-T-9047	Ti-13V-11Cr-3Al	Bar	5.5.1
QQ-A-367	2014	Forging	3.2.1
QQ-A-367	2618	Forging	3.2.10
QQ-A-367	6061	Forging	3.6.2
QQ-A-367	7049/7149	Forging	3.7.2
QQ-A-367	7075	Forging	3.7.4
WW-T-700/3	2024	Tubing	3.2.3
WW-T-700/6	6061	Tubing Seamless, Drawn	3.6.2

**APPENDIX D****D.0 Subject Index**

- A-Basis, 1-9, 9-18, 9-65
- AMS, 9-7
- Anderson-Darling Test
  - k-Sample Test, 9-23, 9-217
  - Normality, 9-26, 9-28, 9-210
  - Weibullness, 9-26, 9-28, 9-212
- Applicability of Procedures, 9-5
- Approval Procedures, 9-5
- ASTM, 1-9, 9-7, 9-10, 9-59, 9-73, 9-89, 9-92, 9-151, 9-198
  - ASTM B 769, 9-10
  - ASTM C 693, 9-60
  - ASTM C 714, 9-60
  - ASTM D 2766, 9-60
  - ASTM E 8, 1-10, 1-174
  - ASTM E 83, 9-73
  - ASTM E 111, 9-59
  - ASTM E 132, 9-59
  - ASTM E 139, 9-151
  - ASTM E 143, 9-59
  - ASTM E 228, 9-60
  - ASTM E 238, 1-14, 9-10
  - ASTM E 399, 9-203
  - ASTM E 606, 9-89, 9-100, 9-103, 9-106
  - ASTM E 647, 9-144
- B-Basis, 1-9, 9-18
- Bearing Properties, 1-14
- Bearing Test Procedures, 9-10
- Biaxial Properties, 1-19
  - Modulus of Elasticity, 1-20
  - Ultimate Stress, 1-21
  - Yield Stress, 1-20
- Biaxial Stress-Strain Curves, 9-87
- Brittle Fracture, 1-21
  - Analysis, 1-22
- Cast, Definition of, 9-9
- Chi-Squared Distribution Values, 9-236
- Clad Aluminum Alloy Plate, 9-37
- Coefficient of Thermal Expansion, 9-59
- Columns, 1-31
  - Primary Instability, 1-31
  - Stable Sections, 1-31
  - Yield Stress, 1-32
- Combinability of Populations, 9-210
  - Anderson-Darling k-Sample Test, 9-214, 9-217
  - F-Test, 9-214, 9-215
  - t-Test, 9-214, 9-216
- Compressive Properties, 1-13
- Computational Procedures
  - Derived Properties, 9-33, 9-35, 9-39, 9-40
  - Normal Distribution 9-29
  - Unknown Distribution, 9-32
  - Weibull Distribution, 9-31
- Confidence, 9-21
- Confidence Interval, 9-92, 9-215
- Confidence Level, 9-92
- Confidence Limit, 9-94
- Creep/Stress Rupture, 1-15, 9-147
  - Data Analysis, 9-154, 9-156
  - Data Generation, 9-149, 9-151
  - Data Requirements, 9-151, 9-153
  - Definitions, 9-154
  - Example Problems, 9-163
  - Presentation of Data, 9-160
  - Terminology, 9-150
  - Test Planning, 9-152
- Data Basis, 9-18, 9-63
- Data Generation
  - Creep/Stress Rupture, 9-151
  - Fatigue, 9-108
  - Fatigue Crack Growth, 9-144
  - Fracture Toughness, 9-205
  - Fusion-Welded Joints, 9-196
  - Mechanically Fastened Joints, 9-168
  - Mechanical Properties, 9-10
  - Stress-Strain, 9-73
- Data Presentation
  - Creep-Rupture, 9-160
  - Elevated Temperature Curves, 9-66
  - Fatigue, 9-125
  - Fatigue Crack Propagation, 1-27, 9-147
  - Fracture Toughness, 9-208
  - Fusion-Welded Joints, 9-200
  - Mechanically Fastened Joints, 9-187
  - Room-Temperature Design Values, 9-60
  - Typical (Full-Range) Stress-Strain, 9-83
  - Typical Stress-Strain, 9-76
- Data Requirements
  - Creep/Stress Rupture, 9-151
  - Derived Properties, 9-34
  - Directly Calculated, 9-7



**MIL-HDBK-5H****1 December 1998**

- Elevated Temperature Properties, 9-65
- Fatigue, 9-100
- Fatigue Crack Growth, 9-146
- Fusion-Welded Joints, 9-196
- Mechanically Fastened Joints, 9-171
- Mechanical Properties, 9-12, 9-29, 9-34
- New Materials, 9-7
- Normal Distribution, 9-29
- Physical Properties, 9-11
- Stress-Strain, 9-73
- Unknown Distribution, 9-32
- Weibull Distribution, 9-31
- Definition of Terms
  - Creep/Stress Rupture, 9-154
  - Fatigue, 9-98
  - Fracture Toughness, 9-203
  - Mechanically Fastened Joints, 9-166
  - Mechanical Properties, 9-19
  - Statistics, 9-20, 9-92, 9-214
- Degrees of Freedom, 9-21, 9-215
- Density, 9-11, 9-59
- Derived Properties, 1-9, 9-33
- Design Mechanical Properties
  - By Regression, 9-37
  - Determining Form of Distribution, 9-25
  - Determining Population, 9-23
  - Direct Computation,
    - Non Parametric, 9-33
    - Normal, 9-29
    - Weibull, 9-31
  - Example Problems, 9-41
  - General Procedures, 9-21
  - Presentation, 9-60
- Dimensionally Discrepant Castings, 9-10
- Direct Computation of Allowables
  - Normal Distribution, 9-29
  - Unknown Distribution, 9-33
  - Weibull Distribution, 9-31
- Distribution, Form of, 9-26
- Documentation Requirements, 9-5
- Elastic Properties, 9-59
- Elevated Temperature Curves, 1-9, 9-65
  - Data Requirements, 9-65
  - Presentation, 9-66
  - Working Curves, 9-66
- Environmental Effects, 1-23
- Elongation, 1-12, 9-63, 9-67
- Examples of Computation Procedures
  - Complex Exposure, 9-71
  - Creep/Stress Rupture, 9-163
  - Design Allowables, 9-41
  - Fatigue, 9-132
  - F-Test, 9-215
  - Linear Regression, 9-227
  - Strain-Departure Method, 9-74, 9-84
  - t-Test, 9-216
- F-Distribution Fractiles, 9-237, 9-247
- F-Test, 9-215
- Fasteners
  - H-Type, 9-189
  - S-Type, 9-189
- Fatigue, 9-87
  - Data Analysis, 9-109
  - Data Generation, 9-108
  - Data Requirements, 9-100
  - Definitions, 9-98
  - Example Problems, 9-132
  - Life Models, 9-111
  - Presentation of Data, 9-125
  - Properties, 1-17
  - Terminology, 9-92
  - Test Planning, 9-101
  - Time Dependent Effects, 9-124
- Fatigue Crack Growth, 1-25, 9-144
  - Crack-Propogation Analysis, 1-26
  - Data Analysis, 9-144
  - Data Generation, 9-144
  - Data Requirements, 9-146
  - Presentation of Data, 1-26, 9-147
- Forgings, Definition of Grain Directions in, 9-10
- Fracture Strength, 1-21
  - Analysis, 1-22, 1-24
  - Apparent Fracture Toughness, 1-25
  - Brittle Fracture, 1-21
  - Center-Cracked Tension Panels, 1-25
  - Critical Plane-Strain, 1-22
  - Environmental, 1-23
  - Plane Stress, 1-23
  - Transitional Stress States, 1-23
- Fracture Toughness, 9-203
  - Critical Plain-Strain, 1-22
  - Data Analysis, 9-205
  - Data Generation, 9-205
  - Definitions, 9-203
  - Presentation of Data, 9-208
- Full-Range Stress-Strain Curves, 9-83
- Fusion-Welded Joints, 9-192
  - Data Analysis, 9-200
  - Data Generation, 9-196
  - Data Requirements, 9-196
  - Presentation of Data, 9-200
- Goodness-of-Fit Tests, 9-210
  - Normality, 9-210
  - Weibullness, 9-212



**MIL-HDBK-5H****1 December 1998**

- Grain Direction, Treatment of, 9-10, 9-34, 9-36
- Grouped Data Analysis, 9-29
- Heat Requirements, 9-7, 9-9
- Indirect Design Allowables, 9-35
- Instability, 1-30
  - Bending, 1-31
  - Combined Loadings, 1-31
  - Compression, 1-31
- International System of Units, 1-5
- k-Sample Anderson-Darling Test, 9-23, 9-217
- Larson-Miller Analysis, 9-163
- Location of Test Specimens, 9-10
- Lot Requirements, 9-7, 9-10, 9-11, 9-73, 9-83
- Material Failures, 1-29
  - Bearing, 1-29
  - Bending, 1-29
  - Combined Stress, 1-30
  - Compression, 1-29
  - Fatigue, 1-30
  - Shear, 1-29
  - Stress Concentrations, 1-30
  - Tension, 1-29
- Material Specifications, 9-7, 9-18
- Maximum Likelihood Estimation, 9-123
- Mean Stress/Strain Effects, Evaluation of, 9-111
- Mechanical Properties
  - Computation of Design Allowables, 9-18
  - Derived Properties, 9-33
  - Example Problems, 9-41
  - Presentation, 9-60
  - Terminology for, 9-19
  - Test Matrix, 9-8
- Mechanically Fastened Joints, 9-166
  - Data Analysis, 9-176
  - Data Generation, 9-168
  - Data Requirements, 9-171
  - Definitions, 9-166
  - Presentation of Data, 9-187
- Melt, Definition of, 9-9
- Metallurgical Instability, 1-19
- MIL-STD-1312, 9-168, 9-171, 9-191
- Modulus of Elasticity, 1-11, 9-59, 9-68
- Modulus of Rigidity, 1-13
- Nonparametric Data Analysis, 9-33
- Normal Curve Statistics, 9-230
- Normality, Assessment of, 9-210
- Outliers, Treatment of, 9-119
- Physical Properties, 9-59, 9-69
- Poisson's Ratio, 1-10, 9-59
- Precision Modulus Data, 9-10
- Presentation of Data
  - Creep/Stress Rupture, 9-160
  - Design Allowables, 9-60
  - Effect of Temperature Curves, 9-66
  - Fatigue, 9-125
  - Fatigue Crack Growth, 9-147
  - Fracture Toughness, 9-208
  - Fusion-Welded Joints, 9-200
  - Mechanically Fastened Joints, 9-187
  - Physical Properties, 9-59
  - Primary Test Direction, 9-34
  - Probability, 9-21
  - Probability Plots
    - Normal, 9-211
    - Weibull, 9-213
  - Proportional Limit
    - Shear, 1-13
    - Tensile, 1-12
  - Ramberg-Osgood Method, 9-76
  - Rank Values for A- and B-Basis, 9-34, 9-235
  - Ratioing of Mechanical Properties, 9-34
  - Reduced Ratios
    - By Regression, 9-37
    - Direct Computation, 9-34
  - Reduction in Area, 1-10, 1-12, 9-63, 9-67
  - References, 9-253
  - Regression, 9-219
    - Determining Design Allowables, 9-37
    - Determining Reduced Ratios, 9-40
    - Example Computations, 9-227
    - Least Squares, 9-219
    - Tests for Adequacy of, 9-224
  - Runouts, Treatment of, 9-123
  - S-Basis, 1-8, 9-18, 9-60
  - Separately Cast Test Bars, 9-9
  - Shear Properties, 1-13
  - Shear Test Procedures, 9-10
  - Significance, 9-215
  - Specific Heat, 9-59
  - Specifying the Population, 9-23, 9-197
  - Statistics
    - Symbols, 9-6, 9-98
    - Terms/Definitions, 9-20, 9-92, 9-214
  - Strain
    - Normal, 1-10
    - Poisson's Ratio, 1-10
    - Principal, 1-10
    - Rate, 1-10
    - Shear, 1-10
  - Strain Departure Method, 9-74
  - Stress
    - Normal, 1-9
    - Principal, 1-9
    - Shear, 1-9

# MIL-HDBK-5H

1 December 1998

- State of, 1-9
- Stress-Strain Curves, 9-73
  - Biaxial, 9-87
  - Data Requirements, 9-73
  - Example Computation, 9-75, 9-84
  - Full-Range, 9-83
  - Presentation, 9-76, 9-83
  - Typical, 9-76
- Stress-Tangent Modulus Curves, 9-83
- Symbols and Definitions
  - Creep/Stress Rupture, 9-150
  - Fatigue, 9-98
  - Fatigue Crack Growth, 9-144
  - Fracture Toughness, 9-203
  - General, 1-2, 9-6
  - Mechanically Fastened Joints, 9-166
  - Mechanical Properties, 9-19
  - Statistics, 9-6, 9-20, 9-92, 9-98, 9-214
- t-Distribution Fractiles, 9-238
- t-Test, 9-216
- Tangent Modulus Curves, 9-79
- Temperature Effects, 1-15
- Tensile Proportional Limit, 1-12
- Tensile Yield Stress, 1-12
- Terminology
  - Creep Rupture, 9-150
  - Fatigue, 1-17, 9-92
  - Mechanical Property, 9-19
- Test Specimens
  - Duplication, 9-10
  - Location, 9-7, 9-37
  - Orientation, 9-10, 9-34
  - Primary Test Direction, 9-34
- Testing Procedures
  - Bearing, 9-10
  - Creep/Stress Rupture, 9-152
  - Elastic Properties, 9-59
  - Fatigue, 9-101
  - Fatigue Crack Growth, 9-144
  - Fusion-Welded Joints, 9-200
  - Mechanically Fastened Joints, 9-168
  - Physical Properties, 9-59
  - Shear, 9-10
  - Stress-Strain, 9-73
- Tests of Significance, 9-214
  - Definitions, 9-214
  - F-Test, 9-215
  - t-Test, 9-216
- Thermal Conductivity, 9-59
- Thermal Exposure, 9-70
  - Complex, 9-71
  - Simple, 9-70
- Tolerance Bounds
  - $T_{90}$ , 9-6, 9-21
  - $T_{99}$ , 9-6, 9-21
- Tolerance Interval, 9-98
- Tolerance Level, 9-98
- Tolerance Limit Factors
  - Normal, One-Sided, 9-230
  - Weibull, One-Sided, 9-240, 9-241
- Typical Basis, 9-18, 9-65, 9-73
- Ultimate Bearing Stress, 1-15
- Ultimate Compression Stress, 1-13
- Ultimate Tensile Stress, 1-12
- Weibull Acceptability Test, 9-25
- Weibull Distribution Allowables, 9-29
- Weibullness, Assessment of, 9-212
- Working Curves, Determination of, 9-66
- Yield Bearing Stress, 1-14
- Yield Stress
  - Column, 1-32
  - Bearing, 1-14
  - Tensile, 1-12

**MIL-HDBK-5H**  
**1 December 1998**

***APPENDIX E***

**E.0 Figure Index**

<b>Figure No.</b>	<b>Current Form</b>
1.4.4.1	Scanned
1.4.8.2.1(a)	Scanned
1.4.8.2.1(b)	Scanned
1.4.9.3(a)	Scanned
1.4.11.1	Scanned
1.4.11.3	Scanned
1.4.12.2	Scanned
1.4.12.3	Scanned
1.4.12.4	Scanned
1.4.12.4.1	Scanned
1.4.13.2(a)	Scanned
1.4.13.2(b)	Scanned
1.4.13.4	Scanned
1.6.2.2	Scanned
1.6.4.4(a)	Vector Graphics
1.6.4.4(b)	Vector Graphics
1.6.4.4(c)	Vector Graphics
1.6.4.4(d)	Vector Graphics
1.6.4.4(e)	Vector Graphics
1.6.4.4(f)	Vector Graphics
1.6.4.4(g)	Vector Graphics
1.6.4.4(h)	Vector Graphics
1.6.4.4(i)	Vector Graphics
2.2.1.0	Vector Graphics
2.3.0.2	Scanned
2.3.1.0	Vector Graphics
2.3.1.1.1	Vector Graphics
2.3.1.1.2	Vector Graphics
2.3.1.1.3	Vector Graphics
2.3.1.1.4	Vector Graphics
2.3.1.2.6(a)	Scanned
2.3.1.2.6(b)	Vector Graphics
2.3.1.2.6(c)	Vector Graphics
2.3.1.2.8(a)	Scanned
2.3.1.2.8(b)	Scanned
2.3.1.2.8(c)	Scanned
2.3.1.2.8(d)	Scanned
2.3.1.2.8(e)	Scanned
2.3.1.2.8(f)	Scanned
2.3.1.2.8(g)	Scanned
2.3.1.2.8(h)	Scanned
2.3.1.3.6(a)	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
2.3.1.3.6(b)	Vector Graphics
2.3.1.3.6(c)	Vector Graphics
2.3.1.3.6(d)	Scanned
2.3.1.3.6(e)	Vector Graphics
2.3.1.3.6(f)	Vector Graphics
2.3.1.3.6(g)	Vector Graphics
2.3.1.3.8(a)	Scanned
2.3.1.3.8(b)	Scanned
2.3.1.3.8(c)	Scanned
2.3.1.3.8(d)	Scanned
2.3.1.3.8(e)	Scanned
2.3.1.3.8(f)	Scanned
2.3.1.3.8(g)	Scanned
2.3.1.3.8(h)	Scanned
2.3.1.3.8(i)	Scanned
2.3.1.3.8(j)	Scanned
2.3.1.3.8(k)	Scanned
2.3.1.3.8(l)	Scanned
2.3.1.3.8(m)	Scanned
2.3.1.3.8(n)	Scanned
2.3.1.3.8(o)	Scanned
2.3.1.4.8(a)	Scanned
2.3.1.4.8(b)	Scanned
2.3.1.4.8(c)	Scanned
2.3.1.4.8(d)	Scanned
2.3.1.4.9	Scanned
2.3.1.5.9	Scanned
2.4.1.0	Vector Graphics
2.4.1.1.1(a)	Vector Graphics
2.4.1.1.1(b)	Vector Graphics
2.4.1.1.2(a)	Vector Graphics
2.4.1.1.2(b)	Vector Graphics
2.4.1.1.3(a)	Vector Graphics
2.4.1.1.3(b)	Vector Graphics
2.4.1.1.4	Vector Graphics
2.4.2.0	Vector Graphics
2.4.2.1.1	Vector Graphics
2.4.2.1.2	Vector Graphics
2.4.2.1.4	Vector Graphics
2.4.2.1.6(a)	Vector Graphics
2.4.2.1.6(b)	Vector Graphics
2.4.3.0	Vector Graphics
2.4.3.1.1	Vector Graphics
2.4.3.1.2	Vector Graphics
2.4.3.1.3	Vector Graphics
2.4.3.1.4	Vector Graphics
2.4.3.1.6(a)	Vector Graphics
2.4.3.1.6(b)	Vector Graphics
2.4.3.1.6(c)	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
2.4.3.1.6(d)	Vector Graphics
2.4.3.1.8	Scanned
2.5.0.2(a)	Vector Graphics
2.5.1.0	Vector Graphics
2.5.1.1.1	Vector Graphics
2.5.1.1.2	Vector Graphics
2.5.1.1.3	Vector Graphics
2.5.1.1.4	Vector Graphics
2.5.1.1.6(a)	Vector Graphics
2.5.1.1.6(b)	Vector Graphics
2.5.1.1.6(c)	Vector Graphics
2.5.1.1.6(d)	Vector Graphics
2.5.1.1.6(e)	Scanned
2.5.2.1.6(a)	Scanned
2.5.2.1.6(b)	Scanned
2.5.3.1.6(a)	Scanned
2.5.3.1.6(b)	Vector Graphics
2.5.3.1.6(c)	Vector Graphics
2.5.3.2.6(a)	Vector Graphics
2.5.3.2.6(b)	Vector Graphics
2.5.3.2.6(c)	Vector Graphics
2.6.1.0	Scanned
2.6.1.1.1	Scanned
2.6.1.1.2	Scanned
2.6.1.1.3	Scanned
2.6.1.1.4	Scanned
2.6.1.1.6(a)	Vector Graphics
2.6.1.1.6(b)	Vector Graphics
2.6.2.0	Scanned
2.6.2.1.1	Scanned
2.6.2.1.2	Vector Graphics
2.6.2.1.3	Scanned
2.6.2.1.4	Vector Graphics
2.6.3.0	Vector Graphics
2.6.3.1.1	Vector Graphics
2.6.3.1.2	Vector Graphics
2.6.3.1.5	Vector Graphics
2.6.3.1.6	Vector Graphics
2.6.3.1.8	Scanned
2.6.3.2.1	Vector Graphics
2.6.3.2.2	Vector Graphics
2.6.3.2.5	Vector Graphics
2.6.3.2.6	Vector Graphics
2.6.3.2.8	Scanned
2.6.4.0	Vector Graphics
2.6.4.1.1	Vector Graphics
2.6.4.1.2	Vector Graphics
2.6.4.1.5	Vector Graphics
2.6.4.1.6	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
2.6.4.1.8(a)	Scanned
2.6.4.1.8(b)	Scanned
2.6.4.2.1	Vector Graphics
2.6.4.2.2	Vector Graphics
2.6.4.2.5	Scanned
2.6.4.2.6	Vector Graphics
2.6.4.2.8	Scanned
2.6.5.0	Vector Graphics
2.6.5.1.1	Vector Graphics
2.6.5.1.6(a)	Vector Graphics
2.6.5.1.6(b)	Vector Graphics
2.6.5.1.6(c)	Vector Graphics
2.6.5.1.8(a)	Scanned
2.6.5.1.8(b)	Vector Graphics
2.6.5.1.8(c)	Scanned
2.6.6.0	Vector Graphics
2.6.6.1.1	Vector Graphics
2.6.6.1.4	Vector Graphics
2.6.6.1.6(a)	Vector Graphics
2.6.6.1.6(b)	
2.6.6.1.6(c)	Vector Graphics
2.6.6.2.2	Vector Graphics
2.6.6.2.6(a)	Scanned
2.6.6.2.6(b)	Vector Graphics
2.6.6.2.8(a)	Vector Graphics
2.6.6.2.8(b)	Vector Graphics
2.6.6.2.8(c)	Vector Graphics
2.6.6.3.2	Scanned
2.6.6.3.6	Scanned
2.6.7.0	Vector Graphics
2.6.7.1.1	Scanned
2.6.7.1.4	Scanned
2.6.7.1.6(a)	Scanned
2.6.7.1.6(b)	Scanned
2.6.7.1.6(c)	Scanned
2.6.7.1.8(a)	Scanned
2.6.7.1.8(b)	Scanned
2.6.7.1.8(c)	Scanned
2.6.7.1.8(d)	Scanned
2.6.7.1.8(e)	Scanned
2.6.7.1.8(f)	Scanned
2.6.8.0	Vector Graphics
2.6.8.1.2	Vector Graphics
2.6.8.1.3	Vector Graphics
2.6.8.1.4	Vector Graphics
2.6.8.1.8(a)	Scanned
2.6.8.1.8(b)	Scanned
2.6.8.1.8(c)	Scanned
2.6.8.2.1	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
2.6.8.2.6(a)	Vector Graphics
2.6.8.2.6(b)	Vector Graphics
2.6.8.3.6(a)	Vector Graphics
2.6.8.3.6(b)	Vector Graphics
2.6.8.4.8	Scanned
2.6.8.5.8	Scanned
2.6.8.6.1	Vector Graphics
2.6.9.0	Vector Graphics
2.6.9.1.1	Vector Graphics
2.6.9.1.2	Vector Graphics
2.6.9.1.4(a)	Vector Graphics
2.6.9.1.4(b)	Vector Graphics
2.6.9.1.6(a)	Vector Graphics
2.6.9.1.6(b)	Vector Graphics
2.6.9.1.6(c)	Vector Graphics
2.7.1.0	Vector Graphics
2.7.1.1.1(a)	Vector Graphics
2.7.1.1.1(b)	Vector Graphics
2.7.1.2.6(a)	Vector Graphics
2.7.1.2.6(b)	Vector Graphics
2.7.1.3.1	Vector Graphics
2.7.1.3.2	Vector Graphics
2.7.1.3.3	Vector Graphics
2.7.1.3.4	Vector Graphics
2.7.1.3.6(a)	Vector Graphics
2.7.1.3.6(b)	Vector Graphics
2.7.1.4.6(a)	Vector Graphics
2.7.1.4.6(b)	Vector Graphics
2.7.1.5.1	Vector Graphics
2.7.1.5.2(a)	Vector Graphics
2.7.1.5.2(b)	Vector Graphics
2.7.1.5.3	Vector Graphics
2.7.1.5.4	Vector Graphics
2.7.1.5.6(a)	Vector Graphics
2.7.1.5.6(b)	Vector Graphics
2.7.1.5.6(c)	Vector Graphics
2.7.1.5.6(d)	Vector Graphics
2.8.1.1(a)	Vector Graphics
2.8.1.1(b)	Vector Graphics
2.8.3.2(a)	Vector Graphics
2.8.3.2(b)	Vector Graphics
2.8.3.2(c)	Vector Graphics
2.8.3.2(d)	Scanned
2.8.3.2(e)	Scanned
2.8.3.2(f)	Vector Graphics
2.8.3.2(g)	Scanned
2.8.3.2(h)	Scanned
2.8.3.2(i)	Vector Graphics
2.8.3.2(j)	Scanned

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
3.1.2.1.1(a)	Scanned
3.1.2.1.1(b)	Scanned
3.1.2.1.1(c)	Scanned
3.2.1.0	Vector Graphics
3.2.1.1.1(a)	Scanned
3.2.1.1.1(b)	Vector Graphics
3.2.1.1.1(c)	Vector Graphics
3.2.1.1.1(d)	Vector Graphics
3.2.1.1.1(e)	Vector Graphics
3.2.1.1.1(f)	Vector Graphics
3.2.1.1.2(a)	Vector Graphics
3.2.1.1.2(b)	Vector Graphics
3.2.1.1.3(a)	Vector Graphics
3.2.1.1.3(b)	Vector Graphics
3.2.1.1.4	Scanned
3.2.1.1.5(a)	Vector Graphics
3.2.1.1.5(b)	Vector Graphics
3.2.1.1.6(a)	Vector Graphics
3.2.1.1.6(b)	Vector Graphics
3.2.1.1.6(c)	Vector Graphics
3.2.1.1.6(d)	Vector Graphics
3.2.1.1.6(e)	Vector Graphics
3.2.1.1.6(f)	Vector Graphics
3.2.1.1.6(g)	Vector Graphics
3.2.1.1.6(h)	Vector Graphics
3.2.1.1.6(i)	Vector Graphics
3.2.1.1.6(j)	Vector Graphics
3.2.1.1.6(k)	Vector Graphics
3.2.1.1.6(l)	Vector Graphics
3.2.1.1.6(m)	Vector Graphics
3.2.1.1.6(n)	Vector Graphics
3.2.1.1.6(o)	Vector Graphics
3.2.1.1.6(p)	Vector Graphics
3.2.1.1.6(q)	Vector Graphics
3.2.1.1.6(r)	Vector Graphics
3.2.1.1.6(s)	Vector Graphics
3.2.1.1.6(t)	Vector Graphics
3.2.1.1.6(u)	Vector Graphics
3.2.1.1.6(v)	Vector Graphics
3.2.1.1.8(a)	Scanned
3.2.1.1.8(b)	Scanned
3.2.1.1.8(c)	Scanned
3.2.1.1.8(d)	Scanned
3.2.1.1.8(e)	Scanned
3.2.2.0	Vector Graphics
3.2.2.1.4	Vector Graphics
3.2.3.0	Vector Graphics
3.2.3.1.1(a)	Vector Graphics
3.2.3.1.1(b)	Vector Graphics



**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
3.2.3.1.1(c)	Vector Graphics
3.2.3.1.1(d)	Vector Graphics
3.2.3.1.1(e)	Vector Graphics
3.2.3.1.1(f)	Vector Graphics
3.2.3.1.2(a)	Vector Graphics
3.2.3.1.2(b)	Vector Graphics
3.2.3.1.3(a)	Vector Graphics
3.2.3.1.3(b)	Vector Graphics
3.2.3.1.4	Scanned
3.2.3.1.5(a)	Vector Graphics
3.2.3.1.5(b)	Vector Graphics
3.2.3.1.6(a)	Vector Graphics
3.2.3.1.6(b)	Vector Graphics
3.2.3.1.6(c)	Vector Graphics
3.2.3.1.6(d)	Vector Graphics
3.2.3.1.6(e)	Vector Graphics
3.2.3.1.6(f)	Vector Graphics
3.2.3.1.6(g)	Vector Graphics
3.2.3.1.6(h)	Vector Graphics
3.2.3.1.6(i)	Vector Graphics
3.2.3.1.6(j)	Vector Graphics
3.2.3.1.6(k)	
3.2.3.1.6(l)	Vector Graphics
3.2.3.1.6(m)	Vector Graphics
3.2.3.1.6(n)	Vector Graphics
3.2.3.1.6(o)	Vector Graphics
3.2.3.1.6(p)	Vector Graphics
3.2.3.1.6(q)	Vector Graphics
3.2.3.1.6(r)	Vector Graphics
3.2.3.1.6(s)	Vector Graphics
3.2.3.1.6(t)	Vector Graphics
3.2.3.1.6(u)	Vector Graphics
3.2.3.1.6(v)	Vector Graphics
3.2.3.1.6(w)	Vector Graphics
3.2.3.1.6(x)	Vector Graphics
3.2.3.1.6(y)	Vector Graphics
3.2.3.1.6(z)	Vector Graphics
3.2.3.1.6(aa)	Vector Graphics
3.2.3.1.8(a)	Scanned
3.2.3.1.8(b)	Scanned
3.2.3.1.8(c)	Scanned
3.2.3.1.8(d)	Scanned
3.2.3.1.8(e)	Scanned
3.2.3.1.8(f)	Scanned
3.2.3.1.8(g)	Scanned
3.2.3.1.8(h)	Scanned
3.2.3.1.8(i)	Scanned
3.2.3.3.1(a)	Vector Graphics
3.2.3.3.1(b)	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
3.2.3.3.1(c)	Vector Graphics
3.2.3.3.1(d)	Vector Graphics
3.2.3.3.5(a)	Vector Graphics
3.2.3.3.5(b)	Vector Graphics
3.2.3.3.6(a)	Vector Graphics
3.2.3.3.6(b)	Vector Graphics
3.2.3.3.6(c)	Vector Graphics
3.2.3.3.6(d)	Vector Graphics
3.2.3.3.6(e)	Vector Graphics
3.2.3.4.1(a)	Vector Graphics
3.2.3.4.1(b)	Vector Graphics
3.2.3.4.1(c)	Vector Graphics
3.2.3.4.1(d)	Vector Graphics
3.2.3.4.1(e)	Scanned
3.2.3.4.1(f)	Scanned
3.2.3.4.2(a)	Vector Graphics
3.2.3.4.2(b)	Vector Graphics
3.2.3.4.3(a)	Vector Graphics
3.2.3.4.3(b)	Vector Graphics
3.2.3.4.5(a)	Vector Graphics
3.2.3.4.5(b)	Vector Graphics
3.2.3.4.6(a)	Vector Graphics
3.2.3.4.6(b)	Vector Graphics
3.2.3.4.6(c)	Vector Graphics
3.2.3.4.6(d)	Vector Graphics
3.2.3.4.6(e)	Vector Graphics
3.2.3.4.6(f)	Vector Graphics
3.2.3.4.6(g)	Vector Graphics
3.2.3.4.6(h)	Vector Graphics
3.2.3.4.6(i)	Vector Graphics
3.2.3.4.6(j)	Vector Graphics
3.2.3.5.1(a)	Vector Graphics
3.2.3.5.1(b)	Vector Graphics
3.2.3.5.1(c)	Vector Graphics
3.2.3.5.1(d)	Vector Graphics
3.2.3.5.2(a)	Vector Graphics
3.2.3.5.2(b)	Vector Graphics
3.2.3.5.3(a)	Vector Graphics
3.2.3.5.3(b)	Vector Graphics
3.2.3.5.3(c)	Vector Graphics
3.2.3.5.5(a)	Scanned
3.2.3.5.5(b)	Scanned
3.2.3.5.6(a)	Vector Graphics
3.2.3.5.6(b)	Vector Graphics
3.2.3.5.6(c)	Vector Graphics
3.2.3.5.6(d)	Vector Graphics
3.2.3.5.10(a)	Scanned
3.2.3.5.10(b)	Scanned
3.2.4.0	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
3.2.5.1.6(a)	Vector Graphics
3.2.5.1.6(b)	Vector Graphics
3.2.6.1.1(a)	Vector Graphics
3.2.6.1.1(b)	Vector Graphics
3.2.6.1.6(a)	Scanned
3.2.6.1.6(b)	Scanned
3.2.6.1.9(a)	Scanned
3.2.6.1.9(b)	Scanned
3.2.6.1.9(c)	Scanned
3.2.6.1.9(d)	Scanned
3.2.6.1.9(e)	Scanned
3.2.7.0	Vector Graphics
3.2.7.1.1(a)	Vector Graphics
3.2.7.1.1(b)	Vector Graphics
3.2.7.1.6(a)	Vector Graphics
3.2.7.1.6(b)	Vector Graphics
3.2.7.2.1(a)	Vector Graphics
3.2.7.2.1(b)	Vector Graphics
3.2.7.2.6(a)	Vector Graphics
3.2.7.2.6(b)	Vector Graphics
3.2.7.2.8(a)	Scanned
3.2.7.2.8(b)	Scanned
3.2.7.2.8(c)	Scanned
3.2.7.2.8(d)	Scanned
3.2.7.3.6(a)	Vector Graphics
3.2.7.3.6(b)	Vector Graphics
3.2.7.3.6(c)	Vector Graphics
3.2.7.3.6(d)	Vector Graphics
3.2.7.3.6(e)	Vector Graphics
3.2.7.4.1(a)	Vector Graphics
3.2.7.4.1(b)	Vector Graphics
3.2.7.4.6(a)	Vector Graphics
3.2.7.4.6(b)	Vector Graphics
3.2.7.4.6(c)	Vector Graphics
3.2.7.4.6(d)	Vector Graphics
3.2.7.4.6(e)	Vector Graphics
3.2.8.1.6(a)	Vector Graphics
3.2.8.1.6(b)	Vector Graphics
3.2.10.0	Vector Graphics
3.2.10.1.1(a)	Vector Graphics
3.2.10.1.1(b)	Vector Graphics
3.2.10.1.1(c)	Vector Graphics
3.2.10.1.1(d)	Vector Graphics
3.2.10.1.2	Vector Graphics
3.2.10.1.3	Vector Graphics
3.2.10.1.4	Vector Graphics
3.2.10.1.5	Vector Graphics
3.2.10.1.6(a)	Vector Graphics
3.2.10.1.6(b)	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
3.5.1.0	Vector Graphics
3.5.1.1.1	Vector Graphics
3.5.1.1.4	Vector Graphics
3.5.1.1.5	Vector Graphics
3.5.1.3.1(a)	Vector Graphics
3.5.1.3.1(b)	Vector Graphics
3.5.1.3.1(c)	Vector Graphics
3.5.1.3.1(d)	Vector Graphics
3.5.1.3.5(a)	Vector Graphics
3.5.1.3.5(b)	Vector Graphics
3.5.1.5.1(a)	Vector Graphics
3.5.1.5.1(b)	Vector Graphics
3.5.1.5.1(c)	Vector Graphics
3.5.1.5.1(d)	Vector Graphics
3.5.1.5.5(a)	Vector Graphics
3.5.1.5.5(b)	Vector Graphics
3.5.2.0	Vector Graphics
3.5.2.1.6(a)	Vector Graphics
3.5.2.1.6(b)	Vector Graphics
3.5.2.1.6(c)	Vector Graphics
3.5.3.1.6(a)	Vector Graphics
3.5.3.1.6(b)	Vector Graphics
3.5.3.1.6(c)	Vector Graphics
3.5.3.2.6(a)	Vector Graphics
3.5.3.2.6(b)	Vector Graphics
3.5.3.2.6(c)	Vector Graphics
3.5.3.3.6(a)	Vector Graphics
3.5.3.3.6(b)	Vector Graphics
3.5.3.3.6(c)	Vector Graphics
3.5.3.4.6	Vector Graphics
3.5.3.7.6	Vector Graphics
3.5.4.1.6	Vector Graphics
3.5.4.2.6	Vector Graphics
3.5.4.3.6(a)	Vector Graphics
3.5.4.3.6(b)	Vector Graphics
3.5.5.0	Vector Graphics
3.5.5.1.6(a)	Vector Graphics
3.5.5.1.6(b)	Vector Graphics
3.5.5.2.6	Vector Graphics
3.5.5.4.6	Vector Graphics
3.6.1.1.6(a)	Vector Graphics
3.6.1.1.6(b)	Vector Graphics
3.6.2.0	Vector Graphics
3.6.2.2.1(a)	Vector Graphics
3.6.2.2.1(b)	Vector Graphics
3.6.2.2.1(c)	Vector Graphics
3.6.2.2.1(d)	Vector Graphics
3.6.2.2.4	Vector Graphics
3.6.2.2.5(a)	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
3.6.2.2.5(b)	Vector Graphics
3.6.2.2.6(a)	Vector Graphics
3.6.2.2.6(b)	Vector Graphics
3.6.2.2.6(c)	Vector Graphics
3.6.2.2.6(d)	Vector Graphics
3.6.2.2.6(e)	Vector Graphics
3.6.2.2.6(f)	Vector Graphics
3.6.2.2.6(g)	Vector Graphics
3.6.2.2.6(h)	Vector Graphics
3.6.2.2.6(i)	Vector Graphics
3.6.2.2.6(j)	Vector Graphics
3.6.2.2.6(k)	Vector Graphics
3.6.2.2.6(l)	Vector Graphics
3.6.2.2.6(m)	Vector Graphics
3.6.2.2.6(n)	Vector Graphics
3.6.2.2.6(o)	Vector Graphics
3.6.2.2.8	Vector Graphics
3.6.3.0	Vector Graphics
3.7.1.1.1	Vector Graphics
3.7.1.1.6(a)	Vector Graphics
3.7.1.1.6(b)	Vector Graphics
3.7.1.1.6(c)	Vector Graphics
3.7.1.1.6(d)	Vector Graphics
3.7.1.2.6(a)	Vector Graphics
3.7.1.2.6(b)	Vector Graphics
3.7.1.2.6(c)	Vector Graphics
3.7.1.2.6(d)	Vector Graphics
3.7.2.1.1	Vector Graphics
3.7.2.1.6(a)	Vector Graphics
3.7.2.1.6(b)	Vector Graphics
3.7.2.1.6(c)	Vector Graphics
3.7.2.1.6(d)	Vector Graphics
3.7.2.1.6(e)	Vector Graphics
3.7.2.1.6(f)	Vector Graphics
3.7.2.1.6(g)	Vector Graphics
3.7.2.1.8(a)	Scanned
3.7.2.1.8(b)	Scanned
3.7.2.1.8(c)	Scanned
3.7.2.1.8(d)	Scanned
3.7.2.1.8(e)	Scanned
3.7.2.1.8(f)	Scanned
3.7.2.1.8(g)	Scanned
3.7.3.1.6(a)	Vector Graphics
3.7.3.1.6(b)	Vector Graphics
3.7.3.1.6(c)	Vector Graphics
3.7.3.1.6(d)	Vector Graphics
3.7.3.1.8(a)	Scanned
3.7.3.1.8(b)	Scanned
3.7.3.2.1	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
3.7.3.2.6(a)	Vector Graphics
3.7.3.2.6(b)	Vector Graphics
3.7.3.2.6(c)	Vector Graphics
3.7.3.2.6(d)	Vector Graphics
3.7.3.2.6(e)	Vector Graphics
3.7.3.2.6(f)	Vector Graphics
3.7.3.2.6(g)	Vector Graphics
3.7.3.2.6(h)	Vector Graphics
3.7.3.2.6(i)	Vector Graphics
3.7.3.2.6(j)	Vector Graphics
3.7.3.2.8(a)	Scanned
3.7.3.2.8(b)	Scanned
3.7.3.2.8(c)	Scanned
3.7.3.2.8(d)	Scanned
3.7.3.2.8(e)	Scanned
3.7.3.2.8(f)	Scanned
3.7.3.2.8(g)	Scanned
3.7.3.2.8(h)	Scanned
3.7.3.2.8(i)	Scanned
3.7.3.2.9(a)	Scanned
3.7.3.2.9(b)	Scanned
3.7.3.2.9(c)	Scanned
3.7.3.3.6(a)	Vector Graphics
3.7.3.3.6(b)	Vector Graphics
3.7.3.3.6(c)	Vector Graphics
3.7.3.3.6(d)	Vector Graphics
3.7.3.3.6(e)	Vector Graphics
3.7.3.3.6(f)	Vector Graphics
3.7.3.3.8(a)	Scanned
3.7.3.3.8(b)	Scanned
3.7.4.0	Vector Graphics
3.7.4.1.1(a)	Scanned
3.7.4.1.1(b)	Scanned
3.7.4.1.1(c)	Vector Graphics
3.7.4.1.1(d)	Vector Graphics
3.7.4.1.2(a)	Vector Graphics
3.7.4.1.2(b)	Vector Graphics
3.7.4.1.3(a)	Vector Graphics
3.7.4.1.3(b)	Vector Graphics
3.7.4.1.4	Vector Graphics
3.7.4.1.5(a)	Vector Graphics
3.7.4.1.5(b)	Vector Graphics
3.7.4.1.6(a)	Vector Graphics
3.7.4.1.6(b)	Vector Graphics
3.7.4.1.6(c)	Vector Graphics
3.7.4.1.6(d)	Vector Graphics
3.7.4.1.6(e)	Vector Graphics
3.7.4.1.6(f)	Vector Graphics
3.7.4.1.6(g)	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
3.7.4.1.6(h)	Vector Graphics
3.7.4.1.6(i)	Vector Graphics
3.7.4.1.6(j)	Vector Graphics
3.7.4.1.6(k)	Vector Graphics
3.7.4.1.6(l)	Vector Graphics
3.7.4.1.6(m)	Vector Graphics
3.7.4.1.6(n)	Vector Graphics
3.7.4.1.6(o)	Vector Graphics
3.7.4.1.6(p)	Vector Graphics
3.7.4.1.6(q)	Vector Graphics
3.7.4.1.8(a)	Scanned
3.7.4.1.8(b)	Scanned
3.7.4.1.8(c)	Scanned
3.7.4.1.8(d)	Scanned
3.7.4.1.8(e)	Scanned
3.7.4.1.8(f)	Scanned
3.7.4.1.8(g)	Scanned
3.7.4.1.8(h)	Scanned
3.7.4.1.9	Scanned
3.7.4.1.10(a)	Scanned
3.7.4.1.10(b)	Scanned
3.7.4.1.10(c)	Scanned
3.7.4.1.10(d)	Scanned
3.7.4.1.10(e)	Scanned
3.7.4.1.10(f)	Scanned
3.7.4.1.10(g)	Scanned
3.7.4.1.10(h)	Scanned
3.7.4.2.6(a)	Vector Graphics
3.7.4.2.6(b)	Vector Graphics
3.7.4.2.6(c)	Vector Graphics
3.7.4.2.6(d)	Vector Graphics
3.7.4.2.6(e)	Vector Graphics
3.7.4.2.6(f)	Vector Graphics
3.7.4.2.9(a)	Scanned
3.7.4.2.9(b)	Scanned
3.7.4.2.9(c)	Scanned
3.7.4.2.10(a)	Scanned
3.7.4.2.10(b)	Scanned
3.7.5.1.6(a)	Vector Graphics
3.7.5.1.6(b)	Vector Graphics
3.7.5.1.6(c)	Vector Graphics
3.7.5.1.6(d)	Vector Graphics
3.7.5.2.6(a)	Vector Graphics
3.7.5.2.6(b)	Vector Graphics
3.7.5.2.6(c)	Vector Graphics
3.7.5.2.6(d)	Vector Graphics
3.7.5.2.8(a)	Scanned
3.7.5.2.8(b)	Scanned
3.7.5.2.8(c)	Scanned

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
3.7.6.1.6(a)	Vector Graphics
3.7.6.1.6(b)	Vector Graphics
3.7.6.1.8(a)	Scanned
3.7.6.1.8(b)	Scanned
3.7.6.1.8(c)	Scanned
3.7.6.1.8(d)	Scanned
3.7.6.2.6(a)	Vector Graphics
3.7.6.2.6(b)	Vector Graphics
3.7.6.2.6(c)	Vector Graphics
3.7.6.2.6(d)	Vector Graphics
3.7.6.2.6(e)	Vector Graphics
3.7.6.2.6(f)	Vector Graphics
3.7.6.2.8(a)	Scanned
3.7.6.2.8(b)	Scanned
3.7.7.1.6(a)	Vector Graphics
3.7.7.1.6(b)	Vector Graphics
3.7.7.1.6(c)	Vector Graphics
3.7.8.1.6(a)	Vector Graphics
3.7.8.1.6(b)	Vector Graphics
3.7.8.1.6(c)	Vector Graphics
3.7.8.1.6(d)	Vector Graphics
3.7.8.1.6(e)	Vector Graphics
3.7.8.1.6(f)	Vector Graphics
3.7.8.1.6(g)	Vector Graphics
3.7.8.1.8(a)	Scanned
3.7.8.1.8(b)	Scanned
3.7.8.1.8(c)	Scanned
3.7.8.1.10(a)	Scanned
3.7.8.1.10(b)	Scanned
3.7.8.1.10(c)	Scanned
3.7.8.1.10(d)	Scanned
3.7.8.2.6(a)	Vector Graphics
3.7.8.2.6(b)	Vector Graphics
3.7.8.2.8(a)	Scanned
3.7.8.2.8(b)	Scanned
3.7.8.2.9(a)	Scanned
3.7.8.2.9(b)	Scanned
3.7.8.3.6(a)	Vector Graphics
3.7.8.3.6(b)	Vector Graphics
3.7.8.3.6(c)	Vector Graphics
3.7.8.3.6(d)	Vector Graphics
3.7.8.3.6(e)	Vector Graphics
3.7.8.3.6(f)	Vector Graphics
3.7.8.3.6(g)	Vector Graphics
3.7.8.3.6(h)	Vector Graphics
3.7.8.3.6(i)	Vector Graphics
3.7.8.3.6(j)	Vector Graphics
3.7.8.3.6(k)	Vector Graphics
3.7.8.3.6(l)	Vector Graphics



**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
3.7.8.3.10(a)	Scanned
3.7.8.3.10(b)	Scanned
3.8.1.0	Vector Graphics
3.8.1.1.6	Vector Graphics
3.8.1.1.8(a)	Scanned
3.8.1.1.8(b)	Scanned
3.8.1.1.8(c)	Scanned
3.9.2.0	Vector Graphics
3.9.4.0	Vector Graphics
3.9.5.1.6(a)	Vector Graphics
3.9.5.1.6(b)	Vector Graphics
3.9.6.1.6	Vector Graphics
3.9.7.1.6	Vector Graphics
3.11.1.1.1	Vector Graphics
3.11.2.3(a)	Scanned
3.11.2.3(b)	Scanned
3.11.3.2(a)	Scanned
3.11.3.2(b)	Vector Graphics
3.11.3.2(c)	Scanned
3.11.3.2(d)	Scanned
3.11.3.2(e)	Vector Graphics
3.11.3.2(f)	Vector Graphics
3.11.3.2(g)	Vector Graphics
4.2.1.0	Vector Graphics
4.2.1.1.4	Scanned
4.2.1.1.6	Vector Graphics
4.2.1.2.1	Scanned
4.2.1.2.2	Scanned
4.2.1.2.3	Scanned
4.2.1.2.4	Scanned
4.2.1.2.6	Vector Graphics
4.2.1.4.8(a)	Scanned
4.2.1.4.8(b)	Scanned
4.2.3.0	Vector Graphics
4.2.3.2.6(a)	Vector Graphics
4.2.3.2.6(b)	Scanned
4.2.3.2.8(a)	Scanned
4.2.3.2.8(b)	Scanned
4.2.3.2.8(C)	Scanned
4.3.2.1.4	Vector Graphics
4.3.2.1.6	Vector Graphics
4.3.3.0	Vector Graphics
4.3.3.1.1(a)	Vector Graphics
4.3.3.1.1(b)	Vector Graphics
4.3.3.1.1(C)	Vector Graphics
4.3.3.1.4	Vector Graphics
4.3.3.1.6(a)	Vector Graphics
4.3.3.1.6(b)	Vector Graphics
4.3.4.0	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
4.3.4.1.1(a)	Scanned
4.3.4.1.1(b)	Scanned
4.3.4.1.1(C)	Scanned
4.3.4.1.6	Vector Graphics
4.3.5.1.1	Scanned
4.3.5.1.4	Scanned
4.3.5.1.6	Vector Graphics
4.3.6.0	Scanned
4.3.6.1.1	Scanned
4.3.6.1.4	Scanned
4.3.6.1.6(a)	Scanned
4.3.6.1.6(b)	Vector Graphics
4.4.2.3(a)	Scanned
4.4.2.3(b)	Scanned
4.4.3.2	Scanned
5.2.1.0	Scanned
5.2.1.1.1(a)	Scanned
5.2.1.1.1(b)	Scanned
5.2.1.1.2(a)	Scanned
5.2.1.1.2(b)	Scanned
5.2.1.1.3(a)	Scanned
5.2.1.1.3(b)	Scanned
5.2.1.1.6(a)	Scanned
5.2.1.1.6(b)	Scanned
5.3.1.0	Vector Graphics
5.3.1.1.1	Scanned
5.3.1.1.2	Scanned
5.3.1.1.3	Scanned
5.3.1.1.4	Scanned
5.3.1.1.5	Scanned
5.3.1.1.9(a)	Scanned
5.3.1.1.9(b)	Scanned
5.3.1.1.9(c)	Scanned
5.3.2.0	Scanned
5.3.2.1.1	Scanned
5.3.2.1.4	Scanned
5.3.2.1.6(a)	Vector Graphics
5.3.2.1.6(b)	Vector Graphics
5.3.2.2.1	Scanned
5.3.2.2.6(a)	Vector Graphics
5.3.2.2.6(b)	Vector Graphics
5.3.2.2.8(a)	Scanned
5.3.2.2.8(b)	Scanned
5.3.2.2.8(c)	Scanned
5.3.2.2.8(d)	Scanned
5.3.2.2.8(e)	Scanned
5.3.2.2.8(f)	Scanned
5.3.3.0	Scanned
5.3.3.1.1	Scanned

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
5.3.3.1.2	Scanned
5.3.3.1.4	Scanned
5.3.3.1.6(a)	Vector Graphics
5.3.3.1.6(b)	Vector Graphics
5.3.3.1.6(c)	Scanned
5.4.1.0	Vector Graphics
5.4.1.1.1	Vector Graphics
5.4.1.1.2	Scanned
5.4.1.1.3	Scanned
5.4.1.1.4	Scanned
5.4.1.1.5	Scanned
5.4.1.1.6(a)	Vector Graphics
5.4.1.1.6(b)	Vector Graphics
5.4.1.1.6(c)	Vector Graphics
5.4.1.1.6(d)	Scanned
5.4.1.1.8(a)	Scanned
5.4.1.1.8(b)	Scanned
5.4.1.1.8(c)	Scanned
5.4.1.1.8(d)	Scanned
5.4.1.1.8(e)	Scanned
5.4.1.1.8(f)	Scanned
5.4.1.1.8(g)	Scanned
5.4.1.1.9	Scanned
5.4.1.2.1	Scanned
5.4.1.2.2	Scanned
5.4.1.2.3	Scanned
5.4.1.2.4	Scanned
5.4.1.2.6(a)	Vector Graphics
5.4.1.2.6(b)	Vector Graphics
5.4.1.2.6(c)	Vector Graphics
5.4.1.2.6(d)	Vector Graphics
5.4.1.2.6(e)	Vector Graphics
5.4.1.2.6(f)	Vector Graphics
5.4.1.2.6(g)	Vector Graphics
5.4.1.2.6(h)	Scanned
5.4.1.2.7	Scanned
5.4.1.2.8(a)	Scanned
5.4.1.2.8(b)	Scanned
5.4.1.2.8(c)	Scanned
5.4.1.2.8(d)	Scanned
5.4.1.2.8(e)	Scanned
5.4.1.2.8(f)	Scanned
5.4.1.2.8(g)	Scanned
5.4.1.2.8(h)	Scanned
5.4.1.2.8(i)	Scanned
5.4.2.0	Scanned
5.4.2.1.1(a)	Scanned
5.4.2.1.1(b)	Scanned
5.4.2.1.2(a)	Scanned

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
5.4.2.1.2(b)	Scanned
5.4.2.1.3(a)	Scanned
5.4.2.1.3(b)	Scanned
5.4.2.1.6(a)	Vector Graphics
5.4.2.1.6(b)	Vector Graphics
5.4.2.1.6(c)	Scanned
5.4.2.1.8(a)	Scanned
5.4.2.1.8(b)	Scanned
5.4.2.2.1	Scanned
5.4.2.2.2	Scanned
5.5.1.0	Scanned
5.5.1.1.1	Scanned
5.5.1.1.2	
5.5.1.1.3(a)	Scanned
5.5.1.1.3(b)	Scanned
5.5.1.1.4	Scanned
5.5.1.1.6	Vector Graphics
5.5.1.1.8(a)	Scanned
5.5.1.1.8(b)	Scanned
5.5.1.1.8(c)	Scanned
5.5.1.1.8(d)	Scanned
5.5.1.2.1	Scanned
5.5.1.2.2	Scanned
5.5.1.2.3	Scanned
5.5.1.2.4	Scanned
5.5.1.2.6	Vector Graphics
5.5.1.2.8(a)	Scanned
5.5.1.2.8(b)	Scanned
5.5.1.2.8(c)	Scanned
5.5.2.0	Scanned
5.5.2.1.6(a)	Vector Graphics
5.5.2.1.6(b)	Vector Graphics
5.5.3.1.6	Vector Graphics
5.5.3.2.6	Vector Graphics
5.6.1.1.1	Scanned
6.2.1.0	Scanned
6.2.1.1.1	Scanned
6.2.1.1.3	Scanned
6.2.1.1.4(a)	Scanned
6.2.1.1.4(b)	Scanned
6.2.1.1.4(c)	Scanned
6.2.1.1.8(a)	Scanned
6.2.1.1.8(b)	Scanned
6.2.1.1.8(c)	Scanned
6.2.1.1.8(d)	Scanned
6.2.1.1.8(e)	Scanned
6.2.2.0	Scanned
6.2.2.1.1(a)	Scanned
6.2.2.1.1(b)	Scanned

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
6.2.2.1.4(a)	Scanned
6.2.2.1.4(b)	Scanned
6.3.1.0	Scanned
6.3.1.1.1	Scanned
6.3.1.1.4	Scanned
6.3.1.1.6(a)	Vector Graphics
6.3.1.1.6(b)	Vector Graphics
6.3.2.0	Scanned
6.3.2.1.1	Scanned
6.3.2.1.2	Scanned
6.3.2.1.3	Scanned
6.3.2.1.4	Scanned
6.3.3.0	Scanned
6.3.3.1.1(a)	Scanned
6.3.3.1.1(b)	Scanned
6.3.3.1.4(a)	Scanned
6.3.3.1.4(b)	Scanned
6.3.3.1.6(a)	Vector Graphics
6.3.3.1.6(b)	Vector Graphics
6.3.3.1.6(c)	Vector Graphics
6.3.3.1.6(d)	Vector Graphics
6.3.3.1.8(a)	Scanned
6.3.3.1.8(b)	Scanned
6.3.3.1.8(c)	Scanned
6.3.3.1.8(d)	Scanned
6.3.4.0	Vector Graphics
6.3.4.1.1	Vector Graphics
6.3.4.1.4	Vector Graphics
6.3.4.1.5	Vector Graphics
6.3.4.1.6(a)	Vector Graphics
6.3.4.1.6(b)	Vector Graphics
6.3.4.1.6(c)	Scanned
6.3.5.0	Vector Graphics
6.3.5.1.1	Scanned
6.3.5.1.4(a)	Scanned
6.3.5.1.4(b)	Scanned
6.3.5.1.4(c)	Scanned
6.3.5.1.6(a)	Vector Graphics
6.3.5.1.6(b)	Vector Graphics
6.3.5.1.6(c)	Vector Graphics
6.3.5.1.6(d)	Scanned
6.3.5.1.7(a)	Scanned
6.3.5.1.7(b)	Scanned
6.3.5.1.7(c)	Scanned
6.3.5.1.7(d)	Vector Graphics
6.3.5.1.7(e)	Vector Graphics
6.3.5.1.8(a)	Vector Graphics
6.3.5.1.8(b)	Vector Graphics
6.3.5.1.8(c)	Vector Graphics

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
6.3.5.1.8(d)	Vector Graphics
6.3.5.1.8(e)	Vector Graphics
6.3.5.1.8(f)	Vector Graphics
6.3.5.1.8(g)	Vector Graphics
6.3.5.1.9(a)	Vector Graphics
6.3.5.1.9(b)	Scanned
6.3.5.1.9(c)	Scanned
6.3.6.0	Scanned
6.3.6.1.1	Scanned
6.3.6.1.2	Scanned
6.3.6.1.3	Scanned
6.3.6.2.1(a)	Scanned
6.3.6.2.1(b)	Scanned
6.3.6.2.4(a)	Scanned
6.3.6.2.4(b)	Scanned
6.3.7.0	Scanned
6.3.7.1.1	Vector Graphics
6.3.7.1.2	Vector Graphics
6.3.7.1.3(a)	Scanned
6.3.7.1.3(b)	Scanned
6.3.7.1.4	Scanned
6.3.7.1.5	Scanned
6.3.7.1.7	Scanned
6.3.8.0	Scanned
6.3.8.1.1	Scanned
6.3.8.1.4	Scanned
6.3.8.1.5(a)	Scanned
6.3.8.1.5(b)	Scanned
6.3.8.1.6(a)	Scanned
6.3.8.1.6(b)	Scanned
6.4.1.0	Scanned
6.4.1.1.1	Vector Graphics
6.4.1.1.2	Vector Graphics
6.4.1.1.3	Vector Graphics
6.4.1.1.4(a)	Vector Graphics
6.4.1.1.4(b)	Scanned
6.4.1.1.5	Scanned
6.4.1.1.7	Scanned
6.4.2.0	Scanned
6.4.2.1.1(a)	Scanned
6.4.2.1.1(b)	Scanned
6.4.2.1.2	Scanned
6.4.2.1.4(a)	Scanned
6.4.2.1.4(b)	Scanned
6.4.2.1.4(c)	Scanned
6.4.2.1.5	Scanned
6.4.2.1.6(a)	Vector Graphics
6.4.2.1.6(b)	Vector Graphics
6.4.2.1.8(a)	Scanned

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
6.4.2.1.8(b)	Scanned
6.4.2.1.8(c)	Scanned
6.4.2.1.8(d)	Scanned
7.2.1.0	Vector Graphics
7.2.1.1.1	Vector Graphics
7.2.1.1.4	Vector Graphics
7.3.2.0	Vector Graphics
7.3.2.1.6(a)	Vector Graphics
7.3.2.1.6(b)	Vector Graphics
7.3.2.2.6	Vector Graphics
7.4.1.0	Scanned
7.4.1.1.1	Scanned
7.4.1.1.4(a)	Scanned
7.4.1.1.4(b)	Scanned
7.4.1.1.5	Scanned
7.4.1.1.6	Vector Graphics
7.4.2.0	Scanned
7.4.2.1.4	Scanned
7.4.2.1.6	Vector Graphics
7.5.1.1.6(a)	Vector Graphics
7.5.1.1.6(b)	Vector Graphics
7.5.1.1.6(c)	Vector Graphics
7.5.1.1.6(d)	Vector Graphics
7.5.1.1.6(e)	Vector Graphics
7.5.1.1.6(f)	Vector Graphics
7.5.1.1.6(g)	Vector Graphics
7.5.1.1.6(h)	Vector Graphics
7.5.1.1.6(i)	Vector Graphics
7.5.1.1.6(j)	Vector Graphics
7.5.1.1.6(k)	Vector Graphics
7.5.1.1.6(l)	Vector Graphics
7.5.2.1.6(a)	Vector Graphics
7.5.2.1.6(b)	Vector Graphics
7.5.2.1.6(c)	Vector Graphics
7.5.2.1.6(d)	Vector Graphics
7.5.2.1.6(e)	Vector Graphics
7.5.2.1.6(f)	Vector Graphics
7.5.2.1.6(g)	Vector Graphics
7.5.2.1.6(h)	Vector Graphics
7.5.2.1.6(i)	Vector Graphics
7.5.2.1.6(j)	Vector Graphics
8.2.1	Scanned
8.2.2.3.1.1(a)	Scanned
8.2.2.3.1.1(b)	Scanned
8.2.2.3.1.1(c)	Scanned
8.2.2.3.2.1	Scanned
8.2.2.3.2.2(a)	Scanned
8.2.2.3.2.2(b)	Scanned
8.2.2.3.2.2(c)	Scanned

**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
8.2.2.3.2.2(d)	Scanned
8.2.2.3.2.2(e)	Scanned
9.2.3	Scanned
9.2.4	Scanned
9.2.6	Scanned
9.2.11	Scanned
9.2.12	Scanned
9.2.15(a)	Scanned
9.2.15(b)	Scanned
9.3.1.1.2	Scanned
9.3.1.1.3(a)	Scanned
9.3.1.1.3(b)	Scanned
9.3.1.2	Scanned
9.3.1.3	Scanned
9.3.1.4(a)	Scanned
9.3.1.4(b)	Scanned
9.3.1.5	Scanned
9.3.1.6.1	Scanned
9.3.1.6.2	Vector Graphics
9.3.2.3(a)	Scanned
9.3.2.3(b)	Scanned
9.3.2.3(c)	Vector Graphics
9.3.2.4	Scanned
9.3.2.5(a)	Scanned
9.3.2.5(b)	Vector Graphics
9.3.2.5(c)	Vector Graphics
9.3.2.5(d)	Vector Graphics
9.3.2.7(a)	Scanned
9.3.2.7(b)	Scanned
9.3.2.7(c)	Scanned
9.3.4.1(a)	Scanned
9.3.4.1(b)	Scanned
9.3.4.1(c)	Scanned
9.3.4.1(d)	Scanned
9.3.4.3	Scanned
9.3.4.4	Scanned
9.3.4.5	Scanned
9.3.4.7	Scanned
9.3.4.10(a)	Scanned
9.3.4.10(b)	Scanned
9.3.4.10(c)	Scanned
9.3.4.12(a)	Scanned
9.3.4.12(b)	Scanned
9.3.4.13	Scanned
9.3.4.16(a)	Scanned
9.3.4.17(a)	Scanned
9.3.4.17(b)	Scanned
9.3.4.17(c)	Scanned
9.3.4.17(d)	Scanned



**MIL-HDBK-5H**  
**1 December 1998**

<b>Figure No.</b>	<b>Current Form</b>
9.3.4.17(e)	Scanned
9.3.4.17(f)	Scanned
9.3.4.17(g)	Scanned
9.3.4.17(h)	Scanned
9.3.5.1(a)	Scanned
9.3.5.1(b)	Scanned
9.3.5.2	Scanned
9.3.5.6	Scanned
9.3.6.2	Scanned
9.3.6.7	Scanned
9.3.6.8(a)	Scanned
9.3.6.8(b)	Scanned
9.3.6.8(c)	Scanned
9.3.6.8(d)	Scanned
9.4.1.3	Scanned
9.4.1.3.4(a)	Scanned
9.4.1.3.4(b)	Scanned
9.4.1.3.4(c)	Scanned
9.4.1.3.4(d)	Scanned
9.4.1.3.4(e)	Scanned
9.4.1.5.2(a)	Scanned
9.4.1.5.2(b)	Scanned
9.4.1.5.2(c)	Scanned
9.4.1.5.2(d)	Scanned
9.4.1.5.2(e)	Scanned
9.4.1.5.2(f)	Scanned
9.4.1.5.2(g)	Scanned
9.4.1.5.2(h)	Scanned
9.4.1.5.3	Scanned
9.4.1.6	Scanned
9.4.1.7.2	Scanned
9.4.1.7.2, cont.	Scanned
9.4.2.2	Scanned
9.4.2.3.2	Scanned
9.4.2.3.5(a)	Scanned
9.4.2.3.5(b)	Scanned
9.4.2.5.2	Scanned
9.4.2.5.3	Scanned
9.5.1.3	Scanned
9.5.1.5.1(a)	Scanned
9.5.1.5.1(b)	Scanned
9.5.1.5.1(c)	Scanned
9.5.1.5.3	Scanned
9.6.3	Scanned
A.1	Scanned

**MIL-HDBK-5H**  
**1 December 1998**

This page intentionally blank.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

## INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7, and send to preparing activity.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

### I RECOMMEND A CHANGE:

1. DOCUMENT NUMBER  
MIL-HDBK-5H

2. DOCUMENT DATE (YYYYMMDD)  
1998-12-01

3. DOCUMENT TITLE METALLIC MATERIALS AND ELEMENTS FOR AEROSPACE VEHICLES STRUCTURES

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

### 6. SUBMITTER

a. NAME (Last, First, Middle Initial)

b. ORGANIZATION

c. ADDRESS (Include Zip Code)

d. TELEPHONE (Include Area Code)  
(1) Commercial  
(2) AUTOVON  
(if applicable)

7. DATE SUBMITTED  
(YYYYMMDD)

### 8. PREPARING ACTIVITY

a. NAME ASC/ENSI

b. TELEPHONE (Include Area Code)  
(1) Commercial (2) AUTOVON

c. ADDRESS (Include Zip Code)  
2530 LOOP ROAD W B560  
WRIGHT-PATTERSON AFB, OH 45433-7101

**IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:**  
Defense Standardization Program Office (DLSC-LM)  
8725 John J. Kingman road, Suite 2533 Ft. Belvoir, VA 22060-2533  
Telephone (703) 767-6888 AUTOVON 427-6888