

MIL-HDBK-692B
14 October 1983

SUPERSEDING
MIL-HDBK-692A(MR)
9 September 1977

MILITARY STANDARDIZATION HANDBOOK

A GUIDE TO THE SELECTION OF
RUBBER O-RINGS



FSC 5330

MIL-HDBK-692B

DEPARTMENT OF DEFENSE

WASHINGTON, D. C.

MIL-HDBK-692B(MR)

A Guide to the Selection of Rubber O-Rings

1. This handbook was developed by the Army Materials and Mechanics Research Center, in accordance with established procedures.

2. This publication was approved on 29 September 1983 for printing and inclusion in the military standardization handbook series.

3. This handbook provides information to aid in the selection of the proper military specification or nationally recognized industry and technical society publication on rubber O-rings, based on the environment(s) in which the O-ring is to be used. The handbook is not intended to be referenced in purchase specifications or other contractual documents nor shall it supersede any specification requirements.

4. Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Director, US Army Materials and Mechanics Research Center, ATTN: DRXMR-SMS, Watertown, MA 02172, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

MIL-HDBK-692B

FOREWORD

Designers and engineers, faced with the task of specifying a suitable type of rubber O-ring for use in a specific application, are often hindered by a lack of information as to which types of rubber will function properly under a given set of environmental conditions. It is the purpose of this handbook to provide such information.

MIL-HDBK-692B

TABLE OF CONTENTS

		<u>Page</u>
	FOREWORD.....	ii
	REFERENCED DOCUMENTS.....	iv
SECTION 1.	SCOPE.....	1
1.1	Scope.....	1
2.	USE OF HANDBOOK.....	2
2.1	Selection table.....	2
2.1.1	Inactive specifications.....	2
2.2	Table objective.....	2
2.3	Example.....	2
3.	COMPATIBILITY OF ELASTOMERS IN SERVICE FLUIDS.....	3
3.1	Service fluids.....	3
4.	ADDITIONAL INFORMATION.....	4
4.1	Source of information.....	4
5.	METRIC EQUIVALENTS.....	5
	APPENDIX.....	6
	O-RING SELECTION TABLE.....	9

MIL-HDBK-692B

REFERENCED DOCUMENTS

The following documents of the issue in effect on the date of this handbook form a part of this handbook.

SPECIFICATIONS

FEDERAL

- TT-S-735 - Standard Test Fluids; Hydrocarbon
- ZZ-R-710 - Rubber Gasket Material, 35 Durometer Hardness
- ZZ-R-765 - Rubber, Silicone

MILITARY

- MIL-P-116 - Preservation, Methods of
- MIL-R-900 - Rubber Gasket Material, 45 Durometer Hardness
- MIL-R-2765 - Rubber Sheet, Strip, Extruded, and Molded Shapes, Synthetic, Oil Resistant
- MIL-R-3065 - Rubber, Fabricated Parts
- MIL-R-3533 - Rubber, Synthetic; Sheet, Strip and Molded
- MIL-P-4861 - Packing, Preformed, Rubber, Packing - Packaging of
- MIL-P-5315 - Packing, Preformed, Hydrocarbon Fuel Resistant
- MIL-P-5425 - Plastic, Sheet, Acrylic, Heat Resistant
- MIL-P-5510 - Packing, Preformed, Straight Thread Tube Fitting Boss, Type I Hydraulic (-65° - 160°F)
- MIL-P-5516 - Packings, Preformed, Petroleum Hydraulic Fluid Resistant, 160°F
- MIL-G-5572 - Gasoline, Aviation: Grades 80/87, 100/130, 115/145
- MIL-H-5606 - Hydraulic Fluid, Petroleum Base; Aircraft, Missile, and Ordnance
- MIL-T-5624 - Turbine Fuel, Aviation, Grades JP-4 and JP-5
- MIL-R-6855 - Rubber, Synthetic, Sheets, Strips, Molded or Extruded Shapes
- MIL-R-7362 - Rubber, Synthetic, Solid, Sheets, Strips and Fabricated Parts, Synthetic Oil Resistant
- MIL-E-9500 - Ethylene Glycol, Technical
- MIL-P-17553 - Packing, Preformed, O-Ring, Synthetic Rubber
- MIL-H-19457 - Hydraulic Fluid, Fire Resistant, Non-Neurotoxic
- MIL-G-21569 - Gasket, Cylinder, Liner Seal, Synthetic Rubber
- MIL-G-21610 - Gasket, Heat Exchanger, Various Cross Section Rings, Synthetic Rubber
- MIL-G-22050 - Gasket and Packing Material, Rubber, for Use with Polar Fluids, Steam, and Air at Moderately High Temperatures

MIL-HDBK-692B

- MIL-M-23573 - Monoethanolamine Chelating Agent Solution
- MIL-G-23652 - Gasket and Packing Material Petroleum and Phosphate Ester Fluid Resistant
- MIL-G-23983 - Gasket and Packing Material, Oil Resistant Rubber, Access Hull Applications
- MIL-P-25732 - Packing, Preformed, Petroleum Hydraulic Fluid Resistant, Limited Service at 275°F (135°C)
- MIL-R-25897 - Rubber, Fluorocarbon Elastomer, High-Temperature, Fluid Resistant
- MIL-R-25988 - Rubber, Fluorosilicone Elastomer, Oil-and-Fuel-Resistant, Sheets, Strips, Molded Parts, and Extruded Shapes
- MIL-P-26536 - Propellant, Hydrazine
- MIL-R-83248 - Rubber, Fluorocarbon Elastomer, High Temperature, Fluid and Compression Set Resistant
- MIL-H-83282 - Hydraulic Fluid, Fire Resistant, Synthetic Hydrocarbon Base, Aircraft, NATO Code Number H-537
- MIL-R-83285 - Rubber, Ethylene-Propylene, General Purpose
- MIL-R-83412 - Rubber, Ethylene-Propylene, Hydrazine Resistant
- MIL-P-83461 - Packings, Preformed, Petroleum Hydraulic Fluid Resistant, Improved Performance at 275°F (135°C)
- MIL-P-83461/1 - Packing, Preformed, Petroleum Hydraulic Fluid Resistant, Improved Performance at 275°F (135°C) Sizes and Tolerances
- MIL-R-83485 - Rubber, Fluorocarbon Elastomer, Improved Performance at Low Temperatures
- MIL-R-83485/1 - Rubber, Fluorocarbon Elastomer, Improved Performance at Low Temperature, Sizes and Tolerances
- MIL-P-87175 - Packing, Preformed, Petroleum Hydraulic Fluid Resistant, Phosphonitrilic Fluoroelastomer
- MIL-P-87175/1 - Packing, Preformed, Petroleum Hydraulic Fluid Resistant, Grade 70, Sizes and Tolerances
- MIL-P-87175/2 - Packing, Preformed, Petroleum Hydraulic Fluid Resistant, Grade 80, Sizes and Tolerances

STANDARDS

MILITARY

- MIL-STD-129 - Marking for Shipment and Storage
- MIL-STD-190 - Identification Marking of Rubber Products
- MIL-STD-417 - Classification System and Tests for Solid Elastomeric Materials
- MIL-STD-1523- Age Control of Age Sensitive Elastomeric Material
- MS 3393 - Packing, Preformed, Straight Thread Tube Fitting Boss, Hydraulic, Minus 65 Deg. F to Plus 275 Deg. F
- MS 9020 - Packing, Preformed - AMS 7271, 'O' Ring
- MS 9021 - Packing, Preformed - AMS 7271, 'O' Ring
- MS 9068 - Packing, Preformed - AMS 3304, 'O' Ring
- MS 9241 - Packing, Preformed - Rubber, AMS 7272, 'O' Ring
- MS 9355 - Packing, Preformed - AMS 7272, 'O' Ring
- MS 9385 - Packing, Preformed - AMS 7267, Seal
- MS 9386 - Packing, Preformed - AMS 7267, O-Ring
- MS 9387 - Packing, Preformed - Seal

MIL-HDEK-692B

MS 9966 - Packing, Preformed - AMS 7273, Seal
 MS 9967 - Packing, Preformed - AMS 7273, O-Ring
 MS 9970 - Packing, Preformed - AMS 7279 O-Ring
 MS 24690 - Packing, Preformed - High Pressure Air Valve
 MS 28775 - Packing, Preformed, Hydraulic, +275°F, ('O' Ring)
 MS 28778 - Packing, Preformed, Straight Thread Tube Fitting Boss
 MS 28900 - Packing, Preformed, for Electrical Use
 MS 29512 - Packing, Preformed, Hydrocarbon Fuel Resistant, Tube Fitting, 'O' Ring
 MS 29513 - Packing, Preformed, Hydrocarbon Fuel Resistant, O-Ring
 MS 29561 - Packing, Preformed, 'O' Ring, Synthetic Lubricant Resistant
 MS 33666 - Packing Preformed Aeronautical Elastomeric, Range of Sizes
 MS 90064 - Packing, Preformed, Round (For Use With Waveguide Flanges and Dummy Loads)

ARMY-NAVY AERONAUTICAL

AN 6227 - Packing - 'O' Ring Hydraulic
 AN 6230 - Gasket - 'O' Ring Hydraulic
 AN 123851 thru
 AN 123950 - Packing, Preformed - AMS 7274, 'O' Ring
 AN 123951 thru
 AN 124050 - Seal - 'O' Ring, AMS 7270

NON-GOVERNMENT PUBLICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS

AIR 786 - Elastomer Compatibility Considerations Relative to O-Ring and Sealant Selection
 AMS 2810 - Identification and Packaging Elastomeric Products
 AMS 2817 - Packaging and Identification, Preformed Packings
 AMS 3209 - Chloroprene Rubber - Weather Resistant, 65-75
 AMS 3210 - Chloroprene Rubber - Electrical Resistant, 65-75
 AMS 3226 - Nitrile Rubber - Hot Oil and Coolant Resistant - Low Swell, 45-55
 AMS 3237 - Butyl Rubber - Phosphate Ester Resistant, 35-45
 AMS 3238 - Butyl Rubber - Phosphate Ester Resistant, 65-75
 AMS 3239 - Butyl Rubber - Phosphate Ester Resistant, 85-95
 AMS 3243 - Chloroprene Rubber - Flame Resistant, 55-65
 AMS 3244 - Chloroprene Rubber - Flame Resistant, 65-75
 AMS 3248 - Synthetic Rubber-Phosphate Ester Resistant, Ethylene Propylene Type, 55-65
 AMS 3249 - Synthetic Rubber-Hydrazine-Base-Fluid Resistant, Ethylene Propylene Type, 75-85
 AMS 3304 - Silicone Rubber - General Purpose, 65-75
 AMS 3305 - Silicone Rubber - General Purpose, 75-85
 AMS 3348 - Silicone Rubber - 1150 psi, High Resiliency, 25-35
 AMS 3349 - Silicone Rubber - 1100 psi, High Resilience, 65-75
 AMS 3356 - Silicone Rubber - Lubricating Oil & Comp. Set Resistant, Elect. Grade, 55-65

MIL-HDBK-692B

- AMS 7260 - Rings, Packing-Nitrile Rubber, Fuel & Low Temp. Resistant, 70-80
- AMS 7261 - Rings, Sealing, Phosphonitrilic Fluoroelastomer, High-Temperature-Fluid Resistant, FZ Type
- AMS 7261/1 - Rings, Sealing, Phosphonitrilic Fluoroelastomer, High-Temperature-Fluid Resistant, 65-75, FZ Type
- AMS 7261/2 - Rings, Sealing, Phosphonitrilic Fluoroelastomer, High-Temperature-Fluid Resistant, 75-85, FZ Type
- AMS 7261/3 - Rings, Sealing, Phosphonitrilic Fluoroelastomer, High-Temperature-Fluid Resistant, 85-95, FZ Type
- AMS 7262 - Rings, Sealing, Ethylene Propylene Rubber, Phosphate Ester, Hydraulic Fluid Resistant, 85-95
- AMS 7266 - Rings, Sealing-Fluorosilicone Rubber, General Purpose, High Temperature, Fuel and Oil Resistant, 65-75
- AMS 7267 - Rings, Sealing-Silicone Rubber, Ht. Resistant, Low Compression Set, 70-80
- AMS 7268 - Rings, Sealing-Silicone Rubber, Low Compression Set, Non-Oil Resistant, 65-75
- AMS 7269 - Rings, Sealing, Silicone Rubber - Low Out-Gassing Space and Vacuum Service, 45 - 55
- AMS 7270 - Rings, Sealing-Nitrile Rubber, Fuel Resistant, 65-75
- AMS 7271 - Rings, Sealing-Nitrile Rubber, Fuel & Low Temp. Resistant, 60-70
- AMS 7272 - Rings, Sealing-Nitrile Rubber, Synthetic Lubricant Resistant, 65-75
- AMS 7273 - Rings, Sealing-Fluorosilicone Rubber, High Temperature Fuel and Oil Resistant, 70-80
- AMS 7274 - Rings, Sealing-Synthetic Rubber, Oil Resistant, 65-75
- AMS 7276 - Rings, Sealing, Fluorocarbon Rubber, High Temperature-Fluid Resistant, Very-Low Compression Set, FKM Type, 70-80
- AMS 7279 - Rings, Sealing - Fluorocarbon Rubber, High Temp. Fluid Resistant, 85-95
- AMS 7280 - Rings, Sealing - Fluorocarbon Rubber, High Temp. Fluid Resistant, Low Compression Set, FKM Type, 70-80
- AS 568A - Aerospace Size Standard for O-Rings
- J 120A - Recommended Practice for Rubber O-Rings for Automotive Seal and Packing Applications

(Application for copies should be addressed to the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

MIL-HDEK-692B

NATIONAL AEROSPACE STANDARD

NAS 617 - Packing, Preformed, Straight Thread Tube Fitting Boss, Synthetic
Lubricant Resistant

(Application of copies should be addressed to the National Standards
Association, Inc., 1321 Fourteenth Street, N. W., Washington, DC 20005.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM 13-413001-20 - Influence of Organic Liquids on Rubber Materials

(Application for copies should be addressed to the American Society for
Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

MIL-HDBK-692B

SECTION 1. SCOPE

1.1 Scope. This handbook lists the currently available types of O-rings for which military or nationally recognized technical society specifications exist, and indicates the environments to which each type of O-ring is resistant. Plastic or metal O-rings, O-rings fabricated from rubber in combination with other materials, and ring shaped packings and gaskets with other than round cross sections are not included. Information relative to the effect of a particular fluid on various elastomers is not included in this handbook (see 3).

MIL-HDBK-692B

SECTION 2. USE OF HANDBOOK

2.1 Selection table. It is most important that users of this handbook understand the make-up of the selection table. The table is not intended to be a complete list of O-ring uses. The table is a compilation of the requirements cited by the referenced O-ring specifications. For example, for specification MIL-P-5315, the chart lists "-65 to +158" under "Air" and "+158" under "ASTM Reference Fuel B." These entries mean that Specification MIL-P-5315 contains tests and requirements for rubber O-rings at -65°F in air, at +158°F in air and at +158°F in Reference Fuel B. These table entries do not necessarily imply that MIL-P-5315 O-rings are unsuited for use at temperatures higher than 158°F in either air or fuel.

2.1.1 Inactive specifications. Specifications MIL-P-5516, MIL-R-25897, and MIL-STD-417 are inactive for new designs. They have been left in the table selection for reference purposes only. For new design consult Cancellation Notices of the applicable specification for replacement document.

2.2 Table objective. The fact that the selection table does not in all cases provide information concerning the maximum resistance of O-rings to various combinations of temperature and environment should not detract from its usefulness. The table can well serve to fulfill its prime objective, namely, to lead the designer or engineer from a particular group of desired properties to one or more O-ring specifications which cover these properties.

2.3 Example. The following example illustrates the method of selecting a specification under which O-rings, suitable for use in a particular application, may be procured.

- a. It is desired to obtain O-rings which can withstand exposure in air over the range -40 to +257°F and which are resistant to petroleum base oils over the same temperature range.
- b. The O-ring selection table lists five types of O-rings which meet the air service temperature requirement. (SAEJ120R Class 1, AMS 7270, AMS 7274, AMS 3226, and MIL-R-7362, Type 1).
- c. MIL-R-7362, Type 1 would not be selected because it contains no numerical values in the table under "Petroleum Base Oils", indicating no such test was performed. The superscript "a" in the table indicates the temperature, in degrees F, at which specification tests are performed.
- d. The selection of one of the four applicable specifications should be made on the basis of the other requirements contained in the specifications, as shown in the selection table. For example, if high tensile strength is desired, AMS 7270 or AMS 7274 should be chosen. If performance tests are required, SAEJ120R, Class 1 should be selected.

MIL-HDBK-692B

SECTION 3. COMPATIBILITY OF ELASTOMERS IN SERVICE FLUIDS

3.1 Service fluids. Military usage of fluids is so wide and varied that it is beyond the scope of this handbook to include usage data. However, two excellent sources of information on the compatibility of elastomers in various fluids can be found in Aerospace Information Report (AIR 786) and American Society for Testing and Materials Handbook (ASTM 13-413001-20).

MIL-HDBK-692B

SECTION 4. ADDITIONAL INFORMATION

4.1 Source of information. For those cases where more information is desired than is furnished in the selection table, the user is encouraged to contact Committee G-4 on Elastic Seals of the Society of Automotive Engineers or the O-ring Division of the Rubber Manufacturers Association. Additional sources of information are provided in the Appendix to this handbook.

MIL-HDBK-692B

SECTION 5. METRIC EQUIVALENTS.

$$\text{Degree Celsius (C}^\circ\text{)} = \frac{\text{degree F}-32}{1.8}$$

$$1 \text{ pound per square inch (psi)} = 6.894 \text{ Kilo pascal (KPa)}$$

Custodian:

Army - MR

Air Force - 99

Preparing activity:

Army - MR

Review Activities:

Army - AR, AV, EA, GL

Air Force - 82

DLA - IS

Project No. 5330-A090

User Activities:

Army - MD, ME

(KBWP# ID-0282A/DISK 0136A. FOR AMMRC USE ONLY)

MIL-HDBK-692B

APPENDIX

Additional Sources of Information
on O-Rings

Availability

Department of the Army Supply Manual
SM 9-C5330-SL, Volumes 1-A through 1-I
(Descriptions are provided for the more
than 10,000 rubber O-rings stocked by
the Department of Defense).

Cost

Department of the Army Supply Manual
SM 9-C5330-SL, Vol. 2.

Design and Material Selection

- MIL-H-5440, "Hydraulic Systems, Aircraft Types I and II, Design and Installation, Requirements For."
- MIL-F-5509, "Fittings, Flared Tube, Fluid Connection."
- MIL-P-5514, "Gland Design; Packings, Hydraulic, General Requirements For."
- MIL-P-5518, "Pneumatic Systems, Aircraft; Design, Installation, and Data Requirements For."
- MIL-HDBK-149, "Rubber and Rubber-Like Materials."
- MIL-HDBK-212, "Gasket Materials (Nonmetallic)."
- NAVSHIPS 93793, "O-Ring Seals For Submarine Antenna Systems Applications."
- Machine Design, published by the Penton Publishing Company, "The Seals Book".
- SAE AIR 786, "Elastomer Compatibility Considerations Relative to "O" Ring and Sealant Selection."
- SAE AIR 851A, "O-Ring Tension Testing Calculations."
- SAE AIR 1707, "Patterns of O-Ring Failure."
- SAE ARP 979, "Backup Rings and Special Sealing Devices, Performance Qualification Testing for."
- SAE ARP 1231, "Gland Design, Elastomeric O-Ring Seals, General Consideration."
- SAE ARP 1232, "Gland Design, Elastomeric O-Ring Seals, Static Radial."

MIL-HDBK-692B

ASD Technical Report 61-234, "Handbook of Design Data of an Elastomeric Material Used in Aerospace systems."

"Seals", Lubrication, Vol. XLIX, No. 8, published by Texaco, Inc.

"The Seals Book", Machine Design, published by the Penton Publishing Company.

WADC Technical Report 59-786, "Design Data For O-Rings and Similar Elastic Seals."

Inspection

MIL-STD-413, "Visual Inspection Guide For Elastomeric O-Rings."

SAE AS 708, "O-Ring Packings and Gaskets, Top Quality Visual (TVQ) - Surface Inspection Guide and Acceptance Standards" (Inactive for new Design).

SAE AS 871A, "Manufacturing and Inspection Standards For Preformed Packings (O-Rings)."

RMA, "O-Ring Inspection Guide, Surface Imperfection Control" -1974 Ed. Rubber Manufacturers Assn., 1901 Pennsylvania Ave. N. W., Washington, DC 20006¹/_.

Pneumatic Applications

SAE ARP 820, "O-Ring Packings, 3000 psi Hydraulic Service, Physical and Performance Tests for Type II (-65 to +275° F)."

Size

SAE AS 568A, "Aerospace Size Standard for O-Rings."

Storage Life

MIL-HDBK-695, "Rubber Products, Shelf Storage Life."

Air Force Technical Manual T.O. 00-20-K-7, 15 March 1974, "Inspection and Age Control."

Air Force Technical Manual AFML-TR-67-235, "Literature Survey on the Effects of Long Term Shelf Aging of Elastomeric Materials."

MIL-HDBK-692B

The American Society of Mechanical Engineers, Paper Number 61-AV26,
"Missile System Elastomers - Predicting Field Life Expectancies."

Army Ballistic Missile Agency Standard 29, "Rubber Synthetic and Related
Items, Age Control of."

Department of the Army Supply Bulletin SB5-60, "Deteriorating Items."

National Aeronautics and Space Administration, MSFC-STD-105, "Synthetic
Rubber, Age Control of."

1/Reference may be made to handbooks supplied by members of the Rubber
Manufacturers Association, O-Ring Division.

MIL-DBR-692B

0-CRC Selection Table

SPECIFICATION REPORTS - DEBRAL AND CYCLOPENTHANE				OTHER SPECIFICATION REPORTS			
REPORT NUMBER	REPORT TITLE	REPORT NUMBER	REPORT TITLE	REPORT NUMBER	REPORT TITLE	REPORT NUMBER	REPORT TITLE
12	DEBRAL	13	DEBRAL	14	DEBRAL	15	DEBRAL
16	DEBRAL	17	DEBRAL	18	DEBRAL	19	DEBRAL
20	DEBRAL	21	DEBRAL	22	DEBRAL	23	DEBRAL
24	DEBRAL	25	DEBRAL	26	DEBRAL	27	DEBRAL
28	DEBRAL	29	DEBRAL	30	DEBRAL	31	DEBRAL
32	DEBRAL	33	DEBRAL	34	DEBRAL	35	DEBRAL
36	DEBRAL	37	DEBRAL	38	DEBRAL	39	DEBRAL
40	DEBRAL	41	DEBRAL	42	DEBRAL	43	DEBRAL
44	DEBRAL	45	DEBRAL	46	DEBRAL	47	DEBRAL
48	DEBRAL	49	DEBRAL	50	DEBRAL	51	DEBRAL
52	DEBRAL	53	DEBRAL	54	DEBRAL	55	DEBRAL
56	DEBRAL	57	DEBRAL	58	DEBRAL	59	DEBRAL
60	DEBRAL	61	DEBRAL	62	DEBRAL	63	DEBRAL
64	DEBRAL	65	DEBRAL	66	DEBRAL	67	DEBRAL
68	DEBRAL	69	DEBRAL	70	DEBRAL	71	DEBRAL
72	DEBRAL	73	DEBRAL	74	DEBRAL	75	DEBRAL
76	DEBRAL	77	DEBRAL	78	DEBRAL	79	DEBRAL
80	DEBRAL	81	DEBRAL	82	DEBRAL	83	DEBRAL
84	DEBRAL	85	DEBRAL	86	DEBRAL	87	DEBRAL
88	DEBRAL	89	DEBRAL	90	DEBRAL	91	DEBRAL
92	DEBRAL	93	DEBRAL	94	DEBRAL	95	DEBRAL
96	DEBRAL	97	DEBRAL	98	DEBRAL	99	DEBRAL
100	DEBRAL	101	DEBRAL	102	DEBRAL	103	DEBRAL
104	DEBRAL	105	DEBRAL	106	DEBRAL	107	DEBRAL
108	DEBRAL	109	DEBRAL	110	DEBRAL	111	DEBRAL
112	DEBRAL	113	DEBRAL	114	DEBRAL	115	DEBRAL
116	DEBRAL	117	DEBRAL	118	DEBRAL	119	DEBRAL
120	DEBRAL	121	DEBRAL	122	DEBRAL	123	DEBRAL
124	DEBRAL	125	DEBRAL	126	DEBRAL	127	DEBRAL
128	DEBRAL	129	DEBRAL	130	DEBRAL	131	DEBRAL
132	DEBRAL	133	DEBRAL	134	DEBRAL	135	DEBRAL
136	DEBRAL	137	DEBRAL	138	DEBRAL	139	DEBRAL
140	DEBRAL	141	DEBRAL	142	DEBRAL	143	DEBRAL
144	DEBRAL	145	DEBRAL	146	DEBRAL	147	DEBRAL
148	DEBRAL	149	DEBRAL	150	DEBRAL	151	DEBRAL
152	DEBRAL	153	DEBRAL	154	DEBRAL	155	DEBRAL
156	DEBRAL	157	DEBRAL	158	DEBRAL	159	DEBRAL
160	DEBRAL	161	DEBRAL	162	DEBRAL	163	DEBRAL
164	DEBRAL	165	DEBRAL	166	DEBRAL	167	DEBRAL
168	DEBRAL	169	DEBRAL	170	DEBRAL	171	DEBRAL
172	DEBRAL	173	DEBRAL	174	DEBRAL	175	DEBRAL
176	DEBRAL	177	DEBRAL	178	DEBRAL	179	DEBRAL
180	DEBRAL	181	DEBRAL	182	DEBRAL	183	DEBRAL
184	DEBRAL	185	DEBRAL	186	DEBRAL	187	DEBRAL
188	DEBRAL	189	DEBRAL	190	DEBRAL	191	DEBRAL
192	DEBRAL	193	DEBRAL	194	DEBRAL	195	DEBRAL
196	DEBRAL	197	DEBRAL	198	DEBRAL	199	DEBRAL
200	DEBRAL	201	DEBRAL	202	DEBRAL	203	DEBRAL

* The material listed in this table is the basis for the selection of the material to be used in the development of the design.
 * It is to be noted that the material listed in this table is not intended to be used as the basis for the selection of the material to be used in the development of the design.
 * The material listed in this table is not intended to be used as the basis for the selection of the material to be used in the development of the design.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL*(See Instructions - Reverse Side)*

1. DOCUMENT NUMBER MIL-HDBK-692B	2. DOCUMENT TITLE A GUIDE TO THE SELECTION OF RUBBER O-RINGS	
3a. NAME OF SUBMITTING ORGANIZATION		4. TYPE OF ORGANIZATION (Mark one) <input type="checkbox"/> VENDOR <input type="checkbox"/> USER <input type="checkbox"/> MANUFACTURER <input type="checkbox"/> OTHER (Specify): _____
b. ADDRESS (Street, City, State, ZIP Code)		
5. PROBLEM AREAS		
a. Paragraph Number and Wording:		
b. Recommended Wording:		
c. Reason/Rationale for Recommendation:		
6. REMARKS		
7a. NAME OF SUBMITTER (Last, First, MI) - Optional		b. WORK TELEPHONE NUMBER (Include Area Code) - Optional
c. MAILING ADDRESS (Street, City, State, ZIP Code) - Optional		8. DATE OF SUBMISSION (YYMMDD)

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge (*DO NOT STAPLE*), and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY



NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE \$300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Director
US Army Materials & Mechanics Research Center
ATTN: DRXMR-SMS
Watertown, MA 02172

