

METRIC

MIL-PRF-32538

7 October 2015

PERFORMANCE SPECIFICATION

LUBRICATING OIL, HELICOPTER TRANSMISSION SYSTEM,
SYNTHETIC BASE, NATO CODE NUMBER: O-165

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for one grade of a synthetic base helicopter transmission system lubricating oil, which has a nominal viscosity of 9 mm²/s at 100 °C and which is typically made with neopentyl polyol ester base stocks. This oil is identified by NATO Code Number O-165.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements cited in sections 3 and 4 of this specification, whether or not they are listed.

Comments, suggestions, or questions on this document should be addressed to: Commander, Naval Air Warfare Center, Aircraft Division Lakehurst, Code 4.1.2, Mail Stop 120-3, Route 547, Joint Base MDL, NJ 08733-5100 or emailed to michael.sikora@navy.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at <https://assist.dla.mil>

AMSC N/A

FSC 9150



MIL-PRF-32538

2.2 Government documents.

2.2.1 Specifications and standards. The following specifications and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

FEDERAL STANDARD

FED-STD-791 - Testing Method of Lubricants, Liquid Fuels, and Related Products

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-7808 - Lubricating Oil, Aircraft Turbine Engine, Synthetic Base

MIL-PRF-23699 - Lubricating Oil, Aircraft Turbine Engine, Synthetic Base, NATO Code Numbers O-152, O-154, O-156, and O-167

MIL-DTL-85694 - Spectrometric Oil Standards

DOD-PRF-85734 - Lubricating Oil, Helicopter Transmission System, Synthetic Base

(Copies of these documents are available online at <http://quicksearch.dla.mil> or <https://assist.dla.mil>.)

2.2.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE TECHNICAL MANUAL

DEPARTMENT OF THE NAVY

NAVAIR 17-15-50.2 - Joint Oil Analysis Program Manual Volume II, Spectrometric and Physical Test Laboratory Operating Requirements and Procedures.

(Copies of this document are available from james.mcdonnell@navy.mil or the Naval Air Systems Command, Navy Oil Analysis Program, 22229 Elmer Road, Building 2360, Unit 4, Patuxent River, MD 20670-1534.)

MIL-PRF-32538

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

ASTM INTERNATIONAL

ASTM D92	-	Standard Test Method for Flash and Fire Points by Cleveland Open Cup Tester
ASTM D97	-	Standard Test Method for Pour Point of Petroleum Products
ASTM D445	-	Standard Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and Calculation of Dynamic Viscosity)
ASTM D892	-	Standard Test Method for Foaming Characteristics of Lubricating Oils
ASTM D972	-	Standard Test Method for Evaporation Loss of Lubricating Greases and Oils
ASTM D2532	-	Standard Test Method for Viscosity and Viscosity Change After Standing at Low Temperature of Aircraft Turbine Lubricants
ASTM D2603	-	Standard Test Method for Sonic Shear Stability of Polymer-Containing Oils
ASTM D3427	-	Standard Test Method for Air Release Properties of Petroleum Oils
ASTM D4057	-	Standard Practice for Manual Sampling of Petroleum and Petroleum Products
ASTM D4177	-	Standard Practice for Automatic Sampling of Petroleum and Petroleum Products
ASTM D4636	-	Standard Test Method for Corrosiveness and Oxidation Stability of Hydraulic Oils, Aircraft Turbine Engine Lubricants, and Other Highly Refined Oils
ASTM D5185	-	Standard Test Method for Multielement Determination of Used and Unused Lubricating Oils and Base Oils by Inductively Coupled Plasma Atomic Emission Spectrometry (ICP-AES)
ASTM D5949	-	Standard Test Method for Pour Point of Petroleum Products (Automatic Pressure Pulsing Method)
ASTM D5950	-	Standard Test Method for Pour Point of Petroleum Products (Automatic Tilt Method)
ASTM D5985	-	Standard Test Method for Pour Point of Petroleum Products (Rotational Method)
ASTM D6595	-	Standard Test Method for Determination of Wear Metals and Contaminants in Used Lubricating Oils or Used Hydraulic Fluids by Rotating Disc Electrode Atomic Emission Spectrometry

(Copies of these documents are available from www.astm.org.)

MIL-PRF-32538

AMERICAN SOCIETY FOR QUALITY (ASQ)

ANSI/ASQ Z1.4 - Sampling Procedures and Tables for Inspection by Attributes

(Copies of this document are available from www.asq.org.)

NATIONAL TOXICOLOGY PROGRAM

Annual Report on Carcinogens

(Copies of this document are available from <http://ntp.niehs.nih.gov>.)

SOCIETY OF AEROSPACE ENGINEERS (SAE) INTERNATIONAL

AEROSPACE MATERIAL SPECIFICATIONS (AMS)

SAE AMS3217/1 - Test Slabs, Acrylonitrile butadiene (NBr-H), Medium-High
Acrylonitrile, 65-75
SAE AMS3217/4 - Test Slabs, Fluoroelastomer (FKM), 65-75

AEROSPACE RECOMMENDED PRACTICE (ARP)

SAE ARP5088 - Test Method for the Determination of Total Acidity in
Polyol Ester and Diester Gas Turbine Lubricants by
Automatic Potentiometric Titration

(Copies of these documents are available from <http://www.sae.org>.)

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

MIL-PRF-32538

3. REQUIREMENTS

3.1 Qualification. The lubricating oil furnished under this specification shall be a product that is authorized by the qualifying activity for listing on the applicable qualified products list before contract award (see 4.2, 6.3, 6.4, and 6.5).

3.2 Materials. The composition of the lubricating oil is not limited; however, materials containing barium, organic compounds of titanium, and known or suspected human carcinogens (as defined by the National Toxicology Program's Annual Report on Carcinogens) are prohibited. Recycled basestocks are permitted; however, each batch shall be fully tested in accordance with the qualification requirements of this specification. If a tricresyl phosphate (TCP) additive is used, the TCP additive shall not contain more than 0.2 percent by weight of ortho cresol containing isomers of tricresyl phosphate. The manufacturer may be required to submit certification of conformance to this section (see 6.2).

3.2.1 Acid assay. The acid components, in mole-percent, of the finished oil submitted as the qualification test sample, and noted on batch conformance reports, shall be determined in accordance with FED-STD-791, method 3500 or other equivalent gas chromatography methods as determined by the qualifying activity. The manufacturer may then select a range of 10 mole-percent for each acid component to bracket the values measured on the qualification sample by the qualifying laboratory. The major acid components (10 mole-percent or greater) of production lots of oil shall fall within the stated range for each acid. The minor acid components shall not exceed 10 total mole-percent in bulk lots.

a. Alternate methods may be used if approved by the qualifying activity; however, only FED-STD-791, method 3500, shall be used for referee tests.

3.3 Chemical and physical requirements. The lubricating oil shall conform to the requirements specified in table I.

MIL-PRF-32538

TABLE I. Physical, chemical, and performance requirements.

Characteristic	Requirement	Test Method	Test Reference Paragraph
Acid assay	Report (see 3.2.1)	FED-STD-791, Method 3500	
Low Temperature Viscosity, mm ² /s, at -32 °C (-25 °F), maximum Percent change after 72 hours at -32 °C (-25 °F), maximum	13,000 ±5	ASTM D2532	4.4.1
Viscosity, mm ² /s, at 100 °C (212 °F) at 40 °C (104 °F), minimum	8.75 – 9.25 48	ASTM D445	
Flash point, minimum	232 °C (450 °F)	ASTM D92	
Pour point, maximum	-40 °C (-40 °F)	ASTM D97 or ASTM D5950 ASTM D5985 ASTM D5949	
Total acid number, mg KOH/g, maximum	1.5	SAE ARP5088	
Evaporation loss, percent by weight, 6.5 hours at 204 °C (400 °F), maximum	5.0	ASTM D972	4.4.2
Foaming, foam volume, mL, maximum 5 minutes aeration at 24 °C (75 °F) 1 minute settling at 24 °C (75 °F) 5 minutes aeration at 93.5 °C (200 °F) 1 minute settling at 93.5 °C (200 °F) 5 minutes aeration at 24 °C (75 °F) (after test at 93.5 °C, above) 1 minute settling at 24 °C (75 °F)	25 none 25 none 25 none	ASTM D892	
Rubber compatibility Rubber swell, percent increase SAE AMS3217/1, 72 hours at 70 °C (158 °F) SAE AMS3217/4, 72 hours at 204 °C (400 °F) Standard silicone rubber, 96 hours at 121 °C (250 °F) Tensile strength loss, percent, max Standard silicone rubber, 96 hours at 121 °C (250 °F)	5 - 25 5 - 25 0 - 25 80	FED-STD-791 Method 3604 Method 3433	4.4.3

MIL-PRF-32538

TABLE I. Physical, chemical, and performance requirements - Continued.

Characteristic	Requirement	Test Method	Test Reference Paragraph
Compatibility Turbidity Sediment, mg/L, maximum	Compatible None 10.0	FED-STD-791 Method 3403	4.4.4
Air release value at 50 °C (122 °F), maximum	3.3 minutes	ASTM D3427	
Low temperature Storage Stability, 6 weeks at -18 °C (0 °F)	No crystallization, separation or gelling		4.4.5
Stability testing of first production run	Meet conformance inspection tests		4.4.6
Sediment Visual undissolved water Sediment through 1.2 micron filter, maximum Total ash content, maximum	none 10 mg/L 1 mg/L	FED-STD- 791, Method 3010	4.4.7
Shear stability, viscosity loss at 40 °C (104 °F), maximum	4 percent	ASTM D2603	4.4.8
Trace metal content by RDE-AES, mg/kg (ppm by weight), maximum Aluminum (Al) Iron (Fe) Chromium (Cr) Silver (Ag) Copper (Cu) Tin (Sn) Magnesium (Mg) Nickel (Ni) Titanium (Ti) Silicon (Si) Zinc (Zn) Lead (Pb) Molybdenum (Mo) Boron (B)	 2 2 2 1 1 11 2 2 2 10 2 2 3 2	ASTM D6595	4.4.9

MIL-PRF-32538

TABLE I. Physical, chemical, and performance requirements - Continued.

Characteristic	Requirement	Test Method	Test Reference Paragraph
Trace metal content by ICP-AES, mg/kg (ppm by weight), maximum		ASTM D5185	4.4.9
Aluminum (Al)	2		
Iron (Fe)	2		
Chromium (Cr)	2		
Silver (Ag)	1		
Copper (Cu)	1		
Tin (Sn)	4		
Magnesium (Mg)	2		
Nickel (Ni)	2		
Titanium (Ti)	2		
Silicon (Si)	10		
Zinc (Zn)	2		
Lead (Pb)	2		
Molybdenum (Mo)	3		
Boron (B)	2		
Corrosion and oxidative stability		ASTM D4636, Alternate Procedure 2	4.4.10
a) 72 hours at 150 °C (302 °F)			
Viscosity at 40 °C (104 °F), percent change	-5 to +15		
Total acid number change, maximum	2.0		
Metal weight chg, mg/cm ² , maximum			
Steel	±0.2		
Silver (Ag)	±0.2		
Aluminum (Al)	±0.2		
Magnesium (Mg)	±0.2		
Copper (Cu)	±0.4		
Sludge content (filtered through 10 µm), mg/100 mL of oil, maximum	50		

MIL-PRF-32538

TABLE I. Physical, chemical, and performance requirements - Continued.

Characteristic	Requirement	Test Method	Test Reference Paragraph
Corrosion and oxidative stability b) 72 hours at 175 °C (347 °F) Viscosity at 40 °C (104 °F), percent change Total acid number change, maximum Metal weight chg, mg/cm ² , maximum Steel Silver (Ag) Aluminum (Al) Magnesium (Mg) Copper (Cu) Sludge content, (filtered through 10 µm), mg/100 mL oil, maximum	-5 to +25 3.0 ±0.2 ±0.2 ±0.2 ±0.2 ±0.4 50	ASTM D4636, Alternate Procedure 2	4.4.10
Corrosion and oxidative stability c) 72 hours at 204 °C (400 °F) Viscosity at 40 °C (104 °F), percent change, maximum Total acid number change, maximum Metal weight chg, mg/cm ² , maximum Steel Silver (Ag) Aluminum (Al) Magnesium (Mg) Copper (Cu) Sludge content (filtered through 10 µm), mg/100 mL oil, maximum	+120 15 ±0.2 ±0.2 ±0.2 ±0.2 ±0.4 50	ASTM D4636, Alternate Procedure 2	4.4.10

MIL-PRF-32538

3.4 Bench performance requirements. Bench performance requirements shall be as specified in table II.

TABLE II. Bench performance requirements.

Characteristic	Requirement	Test Method	Test Reference Paragraph
Gear load carrying ability, Relative Rating as % Hercolube A – average of 6 determinations minimum	190%	FED-STD-791, Method 6508	4.4.11
Bearing corrosion, percentage of test samples with no corrosion on raceway, minimum	50% Pass	Appendix A	4.4.12

3.5 Toxicity. The lubricating oil shall have no adverse effect on the health of personnel when used for its intended purpose (see 6.8).

4. VERIFICATION

4.1 Classification of inspections. The inspection and testing of lubricating oil shall be classified as follows:

- a. Qualification inspection (see 4.2).
- b. Conformance inspection (see 4.3).

4.2 Qualification inspection. Qualification inspection shall consist of testing to all of the requirements specified in this specification. When required by the qualifying activity, additional flight test service evaluations may be required on candidate formulations (see 4.2.1).

4.2.1 Service evaluation. When candidate lubricants that were the result of unique or unusual formulation or manufacturing technologies are submitted for qualification testing, the qualifying activity (see 4.2) may require additional flight test evaluations. The additional evaluations shall be conducted by the qualifying activity, or its designated representative, and shall consist of the following:

- a. Model type test. A 150-hour, test cell operated, evaluation shall be conducted on a minimum of two different models of helicopter main transmissions used by the US Military.

MIL-PRF-32538

- b. Flight evaluation. A 500-hour flight evaluation shall be conducted in a Government owned aircraft having the same main transmission model as used in the Model type test above.

4.2.1.1 Evaluation criteria. The rating criteria for both the model type test and the flight evaluation will be reported as satisfactory or unsatisfactory. The satisfactory rating is contingent upon the successful completion of the test duration without a lubricant-related discrepancy and the satisfactory condition of the lubricant-wetted parts upon post-test transmission disassembly and inspection. The post-test condition of the candidate lubricant shall be free of deleterious features.

4.2.2 Requalification. Requalification shall be required when any change is made in source of manufacture, purity, or composition of the lubricating oil base stocks or additives (see 6.3.3). A minor change in the oil formulation may be made without requalification testing, but only after notification to, and approval by, the qualifying activity. Two specific requalification categories are reblend and rebrand, outlined in 4.2.2.1 and 4.2.2.2.

4.2.2.1 Reblend lubricating oil. A reblend lubricating oil is an original qualified product, as specified in 4.2, in which one or more ingredients have been blended by a manufacturer other than the manufacturer of the original formulation. A sample of the reblended lubricating oil shall be subjected to the qualification tests (see 4.2). Reblend approvals are initiated by the process specified in 6.3.

4.2.2.2 Rebrand lubricating oil qualification. A rebrand lubricating oil is a lubricating oil which has successfully passed the qualification tests (see 4.2) and is manufactured by the original formulator at the original manufacturing site but is packaged/distributed using a second party identifying trade name. Rebrand approvals are initiated by the process specified in 6.3.

4.2.3 Qualification inspection sample. The qualification test sample shall consist of 208 liters (55 gallons) of finished lubricating oil and 19 liters (5 gallons) of the base oil without additives. A minimum of 100 grams of each additive ingredient used in the manufacture of the qualification test sample shall be submitted prior to qualification (see 6.3.2).

4.3 Conformance inspection. Conformance inspection of production lots shall consist of all of the tests specified in table IV. Failure of production lots to pass any of the conformance tests shall be cause for rejection of the lot.

4.3.1 Manufacturing tolerances. Finished helicopter transmission oils shall be of the same composition and manufactured at the same plants and by the same methods as those used in the qualified formulation.

4.3.1.1 Additives. Additives shall be of the same composition and manufactured at the same plants and by the same methods as those used in the qualified formulation. Additive treat rates for each manufactured batch shall not vary from those specified in table III.

MIL-PRF-32538

TABLE III. Additive batch concentration tolerances.

Nominal Composition of the Approved Material, % wt	Range as Percentage of the Nominal Value
≥ 2	± 5
$>0.1 - <2$	± 10
≤ 0.1	± 20

4.3.1.2 Basestocks. Basestocks shall be of the same composition and manufactured at the same plants and by the same methods as those used in the qualified formulation. Incidental cross contamination by neopentyl polyol esters other than those used in the original qualification, but suitable by nature and quality for use in aviation helicopter transmission oil applications, shall not exceed 1.0 percent by weight.

4.3.2 Government lot acceptance. Government lot acceptance testing shall be in accordance with the contract.

4.3.2.1 First production lot samples. Stability testing on the first production run shall be performed as outlined in 4.4.6. A sample of five cases of 1 quart containers (120 containers) of material from the first production lot supplied to the procuring agency after qualification, and one case of every production lot supplied to the procuring activity thereafter, shall be forwarded to the Naval Air Systems Command, Attn: AIR 4.4.2.2, Propulsion Lubricants Team, 22229 Elmer Road, Building 2360, Unit 4, Patuxent River, MD 20670-1534.

MIL-PRF-32538

TABLE IV. Conformance tests.

Characteristic	Requirement	Test Reference Paragraphs
Acid assay	Table I	
Viscosity, mm ² /s, at 40 °C (104 °F) at 100 °C (212 °F)	Table I	
Flash point, °C	Table I	
Pour point, °C	Table I	
Total acid number, maximum	Table I	
Evaporation loss, percent by weight	Table I	4.4.2
Foaming, foam volume, mL, maximum	Table I	
Sediment	Table I	
Trace metal content, ppm, maximum	Table I	4.4.9
Corrosion and oxidative stability 72 hours at 175 °C (347 °F)	Table I	4.4.10
Gear load carrying capacity	Table II	4.4.13.1
Bearing corrosion	Table II	4.4.13.2

4.3.3 Sampling and inspection of oil. Each bulk lot (see 6.9) of material shall be sampled at random in accordance with ASTM D4057 or ASTM D4177 for the conformance inspection tests (see table IV). Inspections shall meet or exceed requirements specified in this specification.

4.3.3.1 Conformance test inspection report. The conformance inspection report (see 6.2) on each lot of oil shall be provided via electronic means or mailed to the following address: Naval Air Systems Command, Attn: AIR 4.4.2.2, Propulsion Lubricants Team, 22229 Elmer Road, Building 2360, Unit 4, Patuxent River, MD 20670-1534.

4.3.4 Examination of filled containers. A random sample of filled containers from each packaged lot (see 6.9), taken in accordance with ANSI/ASQ-Z1.4, shall be examined with regard to fill, closure, sealing and leakage.

4.4 Test methods. All tests shall be performed in accordance with tables I, II, and III.

4.4.1 Low temperature viscosity. For the purposes of determining the percent viscosity change, the initial viscosity shall be determined 35 ±1 minutes after the viscometer is placed in the bath maintained at -32° ±1.05 °C and again at 72 hours ±5 minutes after completion of initial viscosity.

4.4.2 Evaporation loss. Bath temperature shall be maintained at 204° ±1 °C (400° ±2 °F), for the 6.5 hour test period. Air temperature shall be maintained at 204° ±1 °C (400° ±2 °F), using a pre-heater, if necessary.

MIL-PRF-32538

4.4.3 Rubber compatibility. Standard elastomer stocks shall conform to SAE AMS3217/1 and SAE AMS3217/4.

4.4.3.1 Rubber swell. SAE AMS3217/1 and SAE AMS3217/4 shall be tested in accordance with FED-STD-791, method 3604. Standard Silicone Rubber shall be tested in accordance with FED-STD-791, method 3433.

4.4.4 Compatibility. The compatibility test shall be performed in accordance with FED-STD-791, method 3403 with the following exception: petroleum ether, with a boiling range of 30 to 60 °C, n-heptane, or hexane, shall be used in place of 1,1,1-trichloroethane (O-T-620). Upon completion of the 168 hour oven period, the test flasks shall be stored in the dark at room temperature $24^{\circ} \pm 5^{\circ} \text{C}$ ($75^{\circ} \pm 10^{\circ} \text{F}$) for 21 days before visual inspection for turbidity. Sediment shall be determined in accordance with FED-STD-791, method 3010. If the amount of sediment collected after the exposure period is greater than the limit specified in table I additional testing may be performed on the mixture to determine that its performance meets the requirements of this specification. The additional testing may include all of the tests specified in this specification. Referee lubricating oils shall consist of selected oils qualified under this specification, MIL-PRF-23699, MIL-PRF-7808, and DOD-PRF-85734.

4.4.5 Low temperature storage. Three one quart samples of oil shall be stored in a cold chamber maintained at $-18^{\circ} \pm 2.5^{\circ} \text{C}$ ($0^{\circ} \pm 5^{\circ} \text{F}$) for 6 weeks. At the end of the storage period, the oil shall be visually inspected for evidence of crystallization, additive separation, and gelling.

4.4.6 Stability testing of first production run. Five cases of one quart containers (120 containers) from the first production batch of the tentatively qualified oil procured for U.S. government use (original qualification, rebblend, or rebrand) shall be stored at a temperature of not lower than -32°C (-25°F) and not greater than 60°C (140°F) for 12 months (see 4.3.1). At the end of the 12 month storage period, the samples shall be tested in accordance with the conformance tests specified in table IV and 4.3.

4.4.6.1 Tentative qualification approval. Tentative qualification approval is given to products meeting the qualification inspection (see 4.2). Final qualification approval shall be awarded upon successful completion of the stability testing of first production run. Failure to pass this test shall be cause for withdrawal of approval.

4.4.7 Sediment. Sediment measurement may be made using a silver membrane filter. If the total sediment does not exceed 1 mg/L, the ash content does not need to be determined.

4.4.8 Shear stability. Use an irradiation period of 30 minutes on a 30 mL oil sample at a power setting which causes 11.5 ± 0.5 percent viscosity loss to a 30 mL sample of ASTM Reference Fluid, when irradiated for five minutes. ASTM Reference Fluid A is a petroleum oil containing a polymer capable of being broken down by turbulence at high rates of shear; typical viscosities are $10.7 \text{ mm}^2/\text{s}$ at 100°C and $57 \text{ mm}^2/\text{s}$ at 40°C . ASTM Reference Fluid A may be obtained from vendors listed in the ASTM D2603 method.

MIL-PRF-32538

4.4.9 Trace metal content. The trace metal content of the oil for qualification testing shall be determined both with a Rotating Disc Electrode - Atomic Emission Spectrometer (RDE-AES) and an Inductively Coupled Plasma - Atomic Emission Spectrometer (ICP-AES).

4.4.9.1 Spectrometer standardization. The spectrometer shall be standardized and correlated in accordance with the JOAP Program Manual, NAVAIR 17-15-50.2 using MIL-DTL-85694 standards. Immediately after standardizing the spectrometer, five determinations of the oil for trace metal content shall be performed. The average of the five determinations shall be reported. Samples requiring trace metal content determinations may be sent to: Naval Air Station, Hazmart Building 2385, Sample (AIR 4.4.6) – NOAP, 22680 Hammond Road, Patuxent River, MD 20670.

4.4.9.2 ICP adjustments. In accordance with ASTM D5185, modifications that allow for the adjustments in the dilution of the sample are allowed to accurately measure 2 ppm (mg/kg) of metals in the ICP-AES spectrometer.

4.4.9.3 Trace metal conformance testing option. Trace metal content for conformance testing (table III) can be tested using either RDE-AES spectrometer or ICP-AES spectrometer for the same elements outlined in table I.

4.4.10 Corrosion and oxidation stability. The corrosion and oxidation stability test shall be performed in accordance with ASTM D4636, Alternate Procedure 2, with the following modifications:

- a. Duplicate tests shall be run at three separate test temperatures, each conducted for a 72-hour duration, at the bath or block temperatures of: $150^{\circ} \pm 2.5^{\circ} \text{C}$ ($302^{\circ} \pm 5^{\circ} \text{F}$), $175^{\circ} \pm 2.5^{\circ} \text{C}$ ($347^{\circ} \pm 5^{\circ} \text{F}$), and $204^{\circ} \pm 2.5^{\circ} \text{C}$ ($400^{\circ} \pm 5^{\circ} \text{F}$). The individual results shall be reported.
- b. A suitable liquid medium or fluidized sand bath heating apparatus may be used in lieu of an aluminum block heater.
- c. After the sample tube has been in a liquid heating medium (or aluminum block) for 15 minutes, connect the dry air supply, adjust the air flow rate, and begin the test time.
- d. An electrolytic grade silver test square shall be substituted for the cadmium plated steel square; stainless steel or nickel-chrome wire may be used to tie the metal coupons together at all test conditions.
- e. Post-test oil viscosity sample is compared with viscosity of new oil samples tested at 40°C (104°F). Post-test oil total acid number is compared to the total acid number of the new oil sample. The total acid number shall be determined in accordance with SAE ARP5088.
- f. The glassware from FED-STD-791, method 5308 can be used.

The post-test sludge content shall be determined as follows:

MIL-PRF-32538

- g. Decant oil from the test tube through a preweighed 10.0 micron polytetrafluoroethylene filter (Militec LCWP 047-00 or equivalent as approved by the qualifying activity) and measure filtrate volume.
- h. Set filtrate aside for viscosity and acid number tests.
- i. Remove all sludge from test equipment with rubber policeman, wash equipment and filtered sludge with petroleum ether, oven dry sludge sample, and weigh and compute sludge weight per 100 ml of oil.
- j. Do not add the petroleum ether washings to the oil filtrate used for viscosity and acid number. Petroleum ether, with a boiling range of 30° to 60 °C, n-heptane, or hexane shall be used in place of 1,1,1-trichloroethane (O-T-620).

4.4.11 Gear load carrying ability. The average of six determinations shall be not less than 190 percent of the reference oil (Hercolube A, see 4.4.11.1), when tested in accordance with FED-STD-791, method 6508 and table II, with the exception that all determinations be performed at an elevated test oil temperature of 100° ±1 °C (212° ±2 °F). All six determinations shall be made on the same machine. The reference oil average rating used to obtain the relative ratings shall also be reported. Only the Ryder gear machines having a reference oil average rating of 1,700-2,200 lb/in. after eight determinations are acceptable.

4.4.11.1 Source for standard reference oil for Ryder Gear Test (see table II). Standard reference oil may be obtained from the Naval Air Systems Command, Attn: AIR 4.4.2.2, Propulsion Lubricants Team, 22229 Elmer Road, Building 2360, Unit 4, Patuxent River, MD 20670-1534.

4.4.12 Bearing corrosion. The candidate oil shall successfully pass two series of bearing corrosion tests:

- a. The first series of tests shall be conducted on the candidate oil as received (new oil) with a minimum of 18 of 36 bearing raceways being free from corrosion;
- b. The second series shall be conducted on the post-test filtrate from the 150 °C corrosion and oxidation stability test (stressed oil) (see table I) with a minimum of 18 of 36 bearing raceways being free from corrosion.
- c. Any batch of bearing corrosion tests shall also include one pass and one fail reference oil test bearing for quality control purposes. Reference oils shall consist of selected oils qualified under this specification, MIL-PRF-23699, and DOD-PRF-85734.

4.4.13 Conformance inspection testing methods. The following information is in support of the conformance testing required in table IV.

4.4.13.1 Ryder gear load carrying capacity conformance testing. The Ryder Gear test (see table II) shall be performed on the first ten full-scale production lots of each newly qualified lubricating oil supplied to the procuring activity. Additional requirements for performing the Ryder Gear test on subsequent production batches may be specified in the procurement contracts. Additional load carrying test methods may be deemed suitable for qualification of management

MIL-PRF-32538

of change issues at the discretion of the qualifying activity. The products shall meet the conformance test requirements as stated in 4.4.13.1.1.

4.4.13.1.1 Load carrying conformance test criteria. Lubricating oil products shall exhibit performance greater than or equal to 190 percent of the Hercolube A reference fluid value as measured by six determinations.

4.4.13.2 Bearing corrosion conformance inspection procedures. The bearing corrosion test shall be performed on all production batches of the lubricating oil supplied, except as noted in 4.4.13.2.1. Each production batch of the oil shall successfully pass one series of bearing corrosion tests (see table II) on the new oil. This series shall consist of nine candidate specimens and one each of the pass and fail reference oils (see 4.4.12).

4.4.13.2.1 Corrosion additive. Confirmation of the presence of the corrosion additive may be conducted using a quantitative laboratory analytical method of analysis approved by the qualifying activity. Confirmation of the specified additive package by such approved methods may be substituted for a bearing corrosion test to satisfy the conformance test requirement.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activity within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. These lubricating oils are intended for use in helicopter transmission systems. These oils are designed for operation within the approximate bulk oil temperature range of -32° to 200 °C (-25° to 392 °F). These lubricating oils are also intended for applications where corrosion inhibition is desired. These lubricating oils are not intended for use in gas turbine engine systems. These lubricating oils are not intended for use in gearboxes containing silicone and fluorosilicone seals.

6.2 Acquisition requirements. Acquisition documents should specify the following:

- a. Title, number, and date of this specification.
- b. Quantity required

MIL-PRF-32538

- c. If certification of conformance to material prohibitions is required (see 3.2).
- d. Submittal of conformance test results (see 4.3.3.1).
- e. Packaging requirements (see 5.1).

6.3 Qualification process. The general outline of the qualification process is described in the SD-6. Clarification information concerning submitting a test sample to the Naval Air System Command for qualification to MIL-PRF-32538 follows.

6.3.1 Requesting qualification. At the initiation of the qualification process, prospective suppliers must forward a written request for such action to the Naval Air Systems Command. The activity responsible for qualification is the Naval Air Systems Command, Attn: AIR 4.4.2.2, Propulsion Lubricants Team, 22229 Elmer Road, Building 2360, Unit 4, Patuxent River, MD 20670-1534. Information pertaining to qualification of products may be obtained from that activity. This letter must contain general information on the proposed candidate material. The Naval Air Systems Command will respond in writing with a formal "letter of authorization" providing detailed instructions for the submission of product samples, cost of testing, and test data.

6.3.2 Qualification sample. Upon receiving authorization by the Naval Air Systems Command, qualification samples may be forwarded to the qualifying activity, as detailed in the authorization letter. These samples will be tested in accordance with the letter of authorization. Each sample must be plainly identified by a securely attached, durable tag or label marked with the following information:

**QUALIFICATION INSPECTION SAMPLE
LUBRICATING OIL, HELICOPTER TRANSMISSION SYSTEM,
SYNTHETIC BASE, NATO CODE NUMBER: O-165
MIL-PRF-32538**

Type of sample: (basestock, additive, or finished oil)

Name of manufacturer: _____

Product code number: _____

Batch number: _____

Date of manufacture: _____

Submitted by (name) on (date) for qualification inspection in accordance with MIL-PRF-32538 under authorization of (reference authorizing letter, see 4.2).

6.3.3 Qualification inspection test report. The manufacturer must submit a certified test report to the qualification activity (see 4.2) before any qualification test sample is supplied. Each reformulation request must also include a certified test report. These reports should be submitted in electronic format and use the latest version of the SAE AS5780 Qualified Products Formulation Pro-forma and Qualification Report (see <https://www.eauditnet.com/>).

MIL-PRF-32538

6.3.3.1 Qualification test report requirements. The test report must contain laboratory data performed by the submitter or independent lab showing the results of all tests required by this specification and product classification, with the exception of the tests for compatibility, low temperature storage, stability testing of first production run, gear load carrying ability, and shear stability.

6.3.4 Formulation Data. The manufacturer must submit the complete formulation data (in hardcopy format) giving the chemical name of each ingredient, the percentage of each ingredient, and the manufacturer and tradename of each ingredient. The manufacturer must use the latest version of the SAE AS5780 Qualified Products Formulation Pro-forma and Qualification Report (see <https://www.eauditnet.com/>). The manufacturer must also submit the MSDS of the candidate product and for each of the additive components used in the formulation.

6.4 Qualification. With respect to products requiring qualification, awards will be made only for the products which are, at the time of award of contract, qualified for inclusion in the Qualified Products List, QPL-32538, whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from the Naval Air Systems Command, Attn: AIR 4.4.2.2, Propulsion Lubricants Team, 22229 Elmer Road, Building 2360, Unit 4, Patuxent River, MD 20670-1534.

6.5 Qualified Products Database. Current oils qualified to this specification can be found at <https://assist.dla.mil>. Manufacturers with oils qualified to this specification are required to update their CAGE code listing annually at <https://www.sam.gov>. Even if an oil formulation does not have any changes (as described in 4.2), manufacturers are required to recertify their products every two years.

6.6 Subject term (key word) listing.

Corrosion inhibition
Lubricant

6.7 International standardization agreement implementation. This specification implements NATO STANAG1135. When amendment, revision, or cancellation of this specification is proposed, the preparing activity must coordinate the action with the U.S. National Point of Contact for the international standardization agreement, as identified in the ASSIST database at <https://assist.dla.mil>.

6.8 Toxicity. Questions pertinent to this effect should be referred by the contracting activity to the appropriate departmental medical service who will act as its advisor.

MIL-PRF-32538

6.8.1 Safety Data Sheets (SDSs). Contracting officers will identify those activities requiring copies of completed Safety Data Sheets prepared in accordance with FED-STD-313. The pertinent Government mailing addresses for submission of data are listed in FED-STD-313.

6.9 Definitions.

- Bulk lot - A bulk lot is defined as an indefinite quantity of homogeneous mixture of material offered for acceptance in a single isolated container or manufactured by a single plant run (not exceeding 24 hours) through the same processing equipment, with no change in ingredient material.
- Packaged lot - A packaged lot is defined as an indefinite number of 208 liter (55 gallon) drums or smaller unit packages of identical size and type offered for acceptance and filled with a homogeneous mixture of material manufactured by a single plant run (not exceeding 24 hours) through the same processing equipment, with no change in ingredient material.

MIL-PRF-32538
APPENDIX A

METHOD FOR DETERMINING CORROSION PREVENTATIVE PROPERTIES OF SYNTHETIC GAS TURBINE LUBRICANTS

A.1 SCOPE

A.1.1 This test method uses ASTM D1743 as a basis to determine the corrosion preventative properties of synthetic gas turbine lubricants using tapered roller bearings stored under wet conditions. This Appendix is a mandatory part of the specification. The information contained herein is intended for compliance.

A.2 APPLICABLE DOCUMENTS

ASTM INTERNATIONAL

ASTM D1141	Standard Practice for the Preparation of Substitute Ocean Water
ASTM D1193	Standard Specification for Reagent Water
ASTM D1743	Standard Test Method for Determining Corrosion Preventative Properties
ASTM D235	Mineral Spirits (Petroleum Spirits) (Hydrocarbon Dry Cleaning Solvent)

(Copies of these documents are available from www.astm.org.)

A.3 TERMINOLOGY

A.3.1 Description of terms specific to this specification. Corrosion - the chemical or electrochemical reaction between a material, usually a metal, and its environment that produces a deterioration of the material and its properties.

A.4 SUMMARY OF TEST METHOD

A.4.1 Summary. Clean, new bearings are immersed in an aviation gas turbine lubricant and rotated, so as to evenly distribute the lubricant over the bearing surfaces. The bearings are subsequently dipped in distilled water, then stored at $52^{\circ} \pm 1^{\circ} \text{C}$ and 100 percent relative humidity. After a specified time period, the bearings are cleaned and the races of the bearing cups are examined for evidence of corrosion.

A.5 SIGNIFICANCE AND USE

A.5.1 Significance and use. This test method differentiates the relative corrosion preventative capabilities of aviation gas turbine lubricants under the conditions of the test.

A.6 APPARATUS

- a. Timken bearings: Each bearing consists of 2 separate parts.
- b. Bearing Cone: consisting of cone and roller assembly (Timken Part No. LM 11949).
- c. Bearing Cup (Timken Part No. LM 11910).

MIL-PRF-32538
APPENDIX A

- d. Container, 237 cm³ clear glass jar (85.7 mm high, 69.8 mm diameter) fitted with a lid containing a PTFE¹ liner. Note the lids shall be replaced after 10 tests or earlier if it is apparent that the jar has not remained sealed throughout the test (refer to A.10a and A.10b).
- e. Bearing Support, a glass adapter with a taper between the range of 14/35 to 19/38 is suitable.
- f. Glass rod fitted with a rubber policeman.
- g. Watch glass or alternative glassware that can withstand heating to 71 °C in an oven (the size required will depend on the number of bearings being prepared).
- h. Oven, air-circulating, capable of maintaining the temperatures 52° ±1°C and 71° ±1°C. (Note the oven should be dark inside and in an area essentially free of vibration.)

A.7 REAGENTS

- a. Distilled Water (ASTM D1193 Type II reagent grade).
- b. Isopropyl alcohol ² (Reagent grade)
- c. Solvent rinse solution:

Isopropyl alcohol	90%
Distilled Water	9%
Ammonium Hydroxide ³	1% (Reagent Grade)
- d. Stoddard Solvent ⁴ (as described in specification ASTM D235).
- e. Synthetic seawater (as described in specification ASTM D1141, combined stock solution 1 and 2).
- f. 50:50 mixture by volume of Isopropyl alcohol and Stoddard solvent

A.8 PREPARATION OF BEARINGS

A.8.1 Bearing examination. Examine the test bearings carefully and only select those that are entirely free of corrosion. During the bearing preparation handle the bearing with tongs. Care shall be taken to avoid touching the bearings with fingers.

A.8.2 Bearing cleaning procedure. The procedure below describes the use of heated solvents to clean the bearings. The solvents shall only be heated under a suitable fume extraction system.

¹ Polytetrafluoroethylene

² Warning: Flammable

³ Warning: Poison. Causes burns. Vapor extremely irritating. Can be fatal if swallowed. Harmful if inhaled.

⁴ Warning: Combustible, Vapor Harmful.

MIL-PRF-32538
APPENDIX A

- a. Separate and wash the selected bearing thoroughly in hot (52° to 66 °C) Stoddard solvent to remove rust preventative. To ensure complete removal of the rust preventative, subject the bearing to a second wash in Stoddard solvent heated to between 52° and 66 °C.
- b. Remove the bearing from the Stoddard solvent and immerse in solvent rinse solution at ambient temperature. This is to remove the Stoddard solvent and any fingerprints that are present.
- c. Transfer the bearing from the ambient solvent rinse solution to fresh solvent rinse solution heated to between 66 °C and 100 °C.
- d. Assemble the cup and cone on a bearing support (A.6e) and slowly rotate the bearing while immersed using the glass fitted with a rubber policeman.
- e. Remove the bearing from the solvent rinse solution, separate the two components and place on a filter paper to drain.
- f. Transfer the bearing to a watch glass (or alternative glassware) and place this in an oven set at 71° ±1 °C for 15 minutes to dry the bearing.
- g. Remove the bearing from the oven and place it in a dessicator to cool for a minimum of 30 minutes.
- h. When cooled re-examine the bearing to ensure the surfaces are still free of corrosion and the bearing can be turned freely. (Care should be taken not to spin the bearings once they have been prepared as this may damage the race.)

A.9 PROCEDURE

- a. For each test, select bearings that are entirely free of corrosion. The bearings shall only be handled while wearing clean, oil resistant gloves.
- b. Separate the bearing cup and cone and immerse both components in the test oil. Leave to stand for 10 minutes at ambient temperature.
- c. Assemble the bearing cup and cone and place it on the glass support in such a manner that the weight of the cup will maintain contact between the races and rolling elements.
- d. Hold the glass support and re-immerses the bearing in the test oil at ambient temperature, and slowly rotate the cup for 30 seconds using the glass rod fitted with a rubber policeman. Remove the glass support and bearing from the test oil and allow to drain for one minute.
- e. After draining, completely immerse the glass support and bearing for 10 seconds in freshly boiled distilled water that has been allowed to cool to room temperature. Use a new supply of water for each bearing.
- f. Add 5 mL of synthetic seawater to a glass jar (see A.6d). Transfer the bearing and glass support from the distilled water to the glass jar, allowing any water on the bearing to remain. Tighten the screw cap firmly and store the jar in a dark oven, located in an area essentially free of vibration, at 52° ±1 °C for 48 hours.

MIL-PRF-32538
APPENDIX A

A.10 RATING PROCEDURE

- a. Upon completion of the storage period, remove the jars from the oven. Visually determine if any condensation is present in the sealed jars. If condensation is not present, then the PTFE liner of the lid should be considered suspect and the lid should be replaced.
- b. Remove the bearing from the test jar. An audible hiss is often heard when the lid seal is broken, which adds further confidence in the sealing ability of the lid.
- c. Remove the bearing from the jar and separate the two components. Place the bearing cup in a 50:50 mixture by volume of isopropyl alcohol and Stoddard solvent. The solvent mixture can be heated to facilitate the removal of the oil, while observing the proper precautions for a flammable mixture. Agitate the cup vigorously to remove the oil.
- d. Transfer the bearing cup from the solvent and allow to dry on clean filter paper.
- e. Wipe the cup raceway with lint free paper, so as to remove any staining and repeat the rinsing using fresh solvent mixture if necessary to ensure all traces of the oil and stains are removed.
- f. Examine the cup raceway for evidence of corrosion without the use of magnification using the IP 220 rating criteria as shown in table A-I. Record the rating for each bearing.

TABLE A-I. Rating criteria.

Rating	Degree of Corrosion
0	No corrosion
1	No more than three small spots sufficient to be visible to the naked eye and less than 1 mm in diameter.
2	Small areas of corrosion covering up to 1% of the surface.
3	Areas of corrosion covering between 1% and 5% of the surface.
4	Areas of corrosion covering between 5% and 10% of the surface.
5	Areas of corrosion covering more than 10% of the surface

A.11 REPORT

A.11.1 Test result report. Report the test result as the total count of bearings tested in the test oil, the number of bearings that were recorded for each rating category, and the recorded rating of the pass and fail reference oil.

MIL-PRF-32538

CONCLUDING MATERIAL

Custodians:

Army - AT
Navy - AS
Air Force - 20
DLA - GS

Preparing activity:

Navy - AS
(Project 9150-2014-001)

Review activities:

Army - AV
Navy - SH
Air Force - 68

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at <https://assist.dla.mil>.