

INCH-POUND

MIL-PRF-32569

20 December 2016

PERFORMANCE SPECIFICATION

MATTRESS, FOAM, FLAME RESISTANT, SHIPBOARD

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers flame resistant foam shipboard mattresses (see 6.3.2) for use aboard U.S. Navy vessels.

1.2 Classification. The mattresses covered by this specification are of the following sizes, as specified (see 6.2).

1.2.1 Sizes. The sizes of mattress are as follows (see 3.5):

- a. 1 – Crew (Short)
- b. 2 – Crew (Regular)
- c. 3 – Crew (Long)
- d. 4 – Chief Petty Officer (CPO) (Regular)/Officer (Narrow)
- e. 5 – CPO (Long)
- f. 6 – Crew Sub (Small)
- g. 7 – Crew Sub (Regular)
- h. 8 – Officer (Wide)
- i. 9 – Officer/CPO Sub

Comments, suggestions, or questions on this document should be addressed to: Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard DC 20376-5160 or emailed to CommandStandards@navy.mil, with the subject line "Document Comment". Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at <https://assist.dla.mil>.

AMSC N/A

FSC 7210

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

MIL-PRF-32569

1.3 Part or identifying number (PIN). PINs to be used for a mattress acquired to this specification are created as follows:

M **32569** - **X**
 Prefix for Military Specification - Size (see
 Specification Number code below)

Size Code	
Size	Code
1	1
2	2
3	3
4	4
5	5
6	6
7	7
8	8
9	9

Examples:

M32569-1

M32569-8

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 or 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 or 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

COMMERCIAL ITEM DESCRIPTIONS

A-A-50195 - Thread, Aramid

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-129 - Military Marking for Shipment and Storage

(Copies of these documents are available online at <http://quicksearch.dla.mil>.)

MIL-PRF-32569

2.2.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

NAVAL SEA SYSTEMS COMMAND (NAVSEA) PUBLICATIONS

S9510-AB-ATM-010 - Nuclear Powered Submarine Atmosphere Control Manual

(Copies of the chapter titled “Material Control Program” are available by email request to CommandStandards@navy.mil.)

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

ASTM INTERNATIONAL

ASTM D1424	- Standard Test Method for Tearing Strength of Fabrics by Falling-Pendulum (Elmendorf-Type) Apparatus
ASTM D3574	- Standard Test Methods for Flexible Cellular Materials – Slab, Bonded, and Molded Urethane Foams
ASTM D5034	- Standard Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)
ASTM D6193	- Standard Practice for Stitches and Seams
ASTM D6413/D6413M	- Standard Test Method for Flame Resistance of Textiles (Vertical Test)
ASTM D6988	- Standard Guide for Determination of Thickness of Plastic Film Test Specimens
ASTM E162	- Standard Test Method for Surface Flammability of Materials Using a Radiant Heat Energy Source
ASTM E662	- Standard Test Method for Specific Optical Density of Smoke Generated by Solid Materials
ASTM E800	- Standard Guide for Measurement of Gases Present or Generated During Fires
ASTM E1590	- Standard Test Method for Fire Testing of Mattresses
ASTM F1566	- Standard Test Methods for Evaluation of Innersprings, Boxsprings, Mattresses or Mattress Sets

(Copies of these documents are available online at www.astm.org.)

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION (ISO)

ISO/IEC 17025 - General Requirements for the Competence of Testing and Calibration Laboratories

(Copies of this document are available online at www.iso.org.)

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

MIL-PRF-32569

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection in accordance with 4.1.

3.2 Materials. All materials used in the construction of the mattress shall be flame resistant and conform to the requirements of [table I](#).

3.2.1 Recycled, recovered, environmentally preferable, or biobased materials. Recycled, recovered, environmentally preferable, or biobased materials should be used to the maximum extent possible, provided that the material meets or exceeds the operational and maintenance requirements, and promotes economically advantageous life cycle costs.

TABLE I. Material requirements.

Material	Characteristic	Requirement
Ticking fabric ^{1/}	Tear strength	Warp: 3.5 lbs min.; Filling: 3.5 lbs min.
	Breaking strength	Warp: 94 lbs min.; Filling: 58 lbs min.
	Flammability:	
	Char length	5.0 inches max.
	After flame	2.0 seconds max.
	Molten or flaming drops	None
Foam core ^{2/}	Flammability:	
	Flame spread index	10 (max.) and no molten or flaming drops ^{3/}
	Smoke density, D _{MAX}	200 and no molten or flaming drops ^{3/}
	Fire gas toxicity	^{3/} , ^{4/}
NOTES: ^{1/} The flammability tests shall be performed in the initial condition and after conducting 15 laundering cycles (see table IV). ^{2/} For foam cores consisting of multiple types of foam, each foam type shall be tested individually. ^{3/} When materials are not identical on both sides, each side shall be tested as a different specimen. ^{4/} See 3.8.2.		

3.3 Mattress requirements. The foam mattress shall consist of a foam core and a fabric mattress ticking cover.

3.3.1 Foam core. The foam core shall be constructed of synthetic flexible foam or sponge material, and may be either solid foam or modified foam, such as pin cored foam, or foam with a convoluted surface (see 6.3.4) on one side, to accomplish the specified mattress firmness. If convoluted foam is used, the convoluted surface shall face away from the outside mattress surface, located on either the inside face of the top or bottom layer, and be laminated from two or more layers. The convoluted surface shall have $\frac{3}{4} \pm \frac{1}{8}$ inch flat peaks. No convoluted surface shall permit rounded peaks. Otherwise, foam mattress cores may be molded in one piece, or may be assembled by laminating to achieve thickness, and by butting to achieve width or length. However, not more than one butt joint per mattress shall be permitted, either along the width, or along the length. All non-convoluted surfaces shall have a flat surface.

3.3.1.1 Cement bond. Cement used to adhere the various sections of foam shall form a bond stronger than the adjoining foam, when separated by hand. Also, cemented seams shall be soft and similar to the rest of the foam.

MIL-PRF-32569

3.3.1.2 Foam core density. The density of the foam core for solid foam mattresses shall be 5.8 ± 0.4 lb/ft³. The density of the foam core for pin-cored or convoluted foam mattresses shall be as required to meet the other performance requirements of this specification. The foam density shall be determined in accordance with 4.5.1.b.

3.3.1.3 Foam core indentation force deflection (IFD). The IFD of the foam core shall be 33 ± 4 pounds at 4 inches at 25 percent deflection when tested in accordance with 4.5.1.c.

3.3.1.4 Foam core compression set. The compression set of the foam core shall be 12 percent maximum at a deflection of 50 percent when tested in accordance with 4.5.1.d.

3.3.1.5 Foam core tensile strength. The tensile strength of the foam core shall be 12 lb/in² minimum when tested in accordance with 4.5.1.e.

3.3.1.6 Foam core tear strength. The tear strength of the foam core shall be 2.5 lb/in minimum when tested in accordance with 4.5.1.f.

3.3.1.7 Foam core resiliency. The resiliency of the foam core shall be 25 percent minimum when tested in accordance with 4.5.1.g.

3.3.1.8 Foam core dry heat aging. The change in IFD after dry heat aging shall be 20 percent maximum when tested in accordance with 4.5.1.h.

3.3.1.9 Foam core flammability. The foam core flammability shall be in accordance with the requirements in [table I](#) when tested in accordance with [table IV](#).

3.3.2 Mattress ticking cover. The foam mattress ticking (see 6.3.) cover shall be fabricated from one piece of ticking fabric and shall be fabricated such as to contain the foam insert without any looseness or bunching of the cover. The ticking fabric shall be permanently flame resistant and have an alternating blue warp stripe pattern on bleached or natural white background. The flammability and physical requirements shall be as required by [table I](#). As shown on [figure 1](#), the cover shall be a four-corner box construction with two internal and centered side seams and four internal corner seams. The cover shall have one end closure seam located on the bottom of the end of the mattress and extending the full width of the mattress. The end closure shall consist of folding both fabric edges inward, prior to sewing.




FIGURE 1. Foam mattress ticking configuration.

3.3.2.1 Thread. The thread used for constructing the mattress cover shall be polyaramid in accordance with A-A-50195 in size, finish, and ply to meet all requirements of this specification.

MIL-PRF-32569

3.3.2.2 Seam and stitching. The stitch types shall conform to ASTM D6193. All seams shall be securely stitched. Seams shall not slip or pull out. All stitching shall be 8 to 10 stitches per inch. The panel and border edges shall have $\frac{3}{8}$ to $\frac{1}{2}$ inch seam allowances. Proper seam allowance and stitching shall be maintained to prevent raw edges, run-offs, twists, pleats, puckers, or open seams. Thread tension shall be maintained so there is no tight or loose stitching. All stitching shall be uniformly gauged throughout the panel and border edges. Thread breaks and ends of stitching not caught in another line of stitching shall be backstitched with a 301 stitch type at least $\frac{1}{2}$ inch. All seams shall be formed with 301 or 401 stitch types.

3.4 Labeling.

3.4.1 Identification and construction label. Each mattress shall have a combination identification, size, and instruction label. The label shall be tagged and the color of the inscription shall be black. The label shall be permanently attached to the ticking. The label shall be centered on the short end of the mattress and be attached within the end closure seam. The label shall conform to the legal requirements of the state in which the mattress is manufactured. As a minimum, each mattress shall have a label showing the following information:

- a. Manufacturer's identification
- b. Contract or order number and date of manufacture
- c. Item name, specification number, and size number
- d. National Stock Number (NSN)
- e. Lot number

The lettering shall be permanent and legible. The instruction portion shall state the following: "Flame resistant treated ticking. Clean with mild, neutral pH detergent. Do not use harsh chemicals." This information shall be printed in bold capital letters a minimum height of no less than 0.125 inch.

3.4.2 Bar code label. Each mattress unit shall be individually bar-coded with a pressure sensitive label. The bar code element shall be a 13-digit NSN. There shall be a 12-digit Universal Product Code (UPC) assigned for all NSNs by the Government. The initials "UPC" shall appear beneath the code. The bar codes for NSN and UPC shall be a medium to high density, clearly legible and readable by scanner, and shall be located so that they are completely visible on the item when packaged as specified. Attachment of the label shall cause no damage to the mattress. The label shall be positioned on the outside of the plastic covering on the same end of the mattress that has the identification/instruction label in accordance with MIL-STD-129.

3.5 Physical requirements. Finished mattress dimensions and weights shall be as specified in [table II](#).

MIL-PRF-32569

TABLE II. Finished mattress dimensions and weights.

Size No.	Description	Length (inches)	Width (inches)	Depth (inches)	Maximum Weight (pounds)
1	Crew (Short)	72.5	26	4	28.7
2	Crew (Regular)	76	26	4	30.1
3	Crew (Long)	80	26	4	31.7
4	CPO (Regular) / Officer (Narrow)	76	28	5	40.1
5	CPO (Long)	80	28	5	42.3
6	Crew Sub (Small)	73	24	4	26.7
7	Crew Sub (Regular)	76	24	4	27.8
8	Officer (Wide)	76	34	5	48.7
9	Officer/CPO Sub	76	26	5	37.3
Tolerances		±0.5	+0.5; -0.25	+0.25; -0.25	

3.6 Performance requirements. The finished mattress shall meet the performance characteristics identified in [table III](#) for fire resistance, firmness, and durability when subjected to verification methods identified in section 4.

TABLE III. End item performance.

Characteristic	Requirement
Fire resistance ^{1/}	a. Maximum net peak heat release ≤150 kW b. Average specific extinction area ≤162.75 yd ² /lb (300 m ² /kg) (see 4.5.3.1.2) c. No flaming droplets or flaming material ^{2/}
Durability	a. Permanent deformation ≤20% of depth (pass/fail after 75,000 cycles) b. Retain structural integrity. After 75,000 cycles the visual and tactual examination shall indicate that the ticking is intact, with no evident seam failures or worn through areas; the cushioning shall not have any tactual indication of structural degradation of the foam
NOTES:	
^{1/} When mattress foam core material is not identical on both sides, each side shall be tested as a different specimen.	
^{2/} This means no flaming droplets or flaming material, which fall from the test mattress during the fire test, shall continue flaming after reaching the test platform or floor.	

3.7 Protective temporary plastic covering. To keep the mattress clean and protect it from damage by liquids or other foreign matter, each mattress shall be completely sealed into a clear, medium density polyethylene plastic bag no less than 3 mils in thickness (see 4.5.4). Air holes are permissible at one end of the bag to aid in removing excess air prior to sealing.

3.8 Toxicity.

3.8.1 Health hazard assessment (HHA) toxicity. When evaluated in accordance with 4.6.1 (the HHA), the finished mattress shall have no adverse effect on the health of personnel when used for its intended purpose (see 4.6.1 and 6.4).

MIL-PRF-32569

3.8.2 Fire gas toxicity. The foam material shall be evaluated for types of gases and the toxicity levels released in accordance with 4.6.2.

3.9 Off-gassing. The finished mattress (sizes 6, 7, or 9 only) shall be evaluated for off-gassing in accordance with the requirements of 4.7. Based on the circumstances of use and the chemical nature of the mattress, the Navy will determine whether off-gas testing is required or if an administrative assessment is acceptable. In order to be considered acceptable for use in submarines, the mattress shall be assigned to either the "Permitted" or "Limited" category (see 4.7 and 6.5).

3.10 Workmanship. The finished mattress shall be clean and free from defects (cuts, holes, tears, stains, splicing, or repairs) and other conditions affecting form, fit, function, and appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

- a. First article inspection (see 4.2).
- b. Conformance inspection (see 4.3).

4.2 First article inspection. When specified (see 6.2), first article inspection of end item shall be accomplished in accordance with the inspection methods and criteria identified in [table IV](#) for mattresses. When specified (see 6.2), end item off-gas acceptance for size 6, 7, and 9 mattresses is required as part of first article inspection. Only one mattress from size 6, 7, or 9 (preferably size 6) shall be submitted from a single plant for Navy off-gas evaluation in accordance with 3.9. No future end item off-gas acceptance is required provided mattress composition, components, and materials remain identical to the Navy mattress accepted for off-gas. When specified (see 6.2), HHA toxicity and fire gas toxicity shall be evaluated (see 3.8.1, 3.8.2, 4.6.1, and 4.6.2). No future HHA toxicity evaluation is required provided mattress composition, components, and materials remain identical to the Navy mattress accepted for toxicity.

MIL-PRF-32569

TABLE IV. Component and end item examination and tests.

Test Item	Characteristic	Requirement	Examination/Test Method
Component and Material Inspection			
Ticking fabric	Tear strength	table I	ASTM D1424
	Breaking strength	table I	ASTM D5034
Foam core	Density	3.3.1.2	4.5.1.b
	Indentation force deflection (IFD)	3.3.1.3	4.5.1.c
	Compression set	3.3.1.4	4.5.1.d
	Tensile strength	3.3.1.5	4.5.1.e
	Tear strength	3.3.1.6	4.5.1.f
	Resilience	3.3.1.7	4.5.1.g
	Dry heat aging	3.3.1.8	4.5.1.h
Component Flammability Performance Characteristics			
Ticking fabric ^{1/}	Char length	table I	ASTM D6413/D6413M
	After flame	table I	ASTM D6413/D6413M
	Molten or flaming drops	table I	ASTM D6413/D6413M
Foam core	Molten or flaming drops	table I	ASTM E162/E662
	Flame spread index	table I	ASTM E162
	Smoke density, D _{MAX}	table I	ASTM E662 ^{2/}
	Fire gas toxicity	3.8.2	4.6.2
End Item Performance Characteristics			
Mattress	Dimensions	table II	4.5.2.1
	Weight	table II	4.5.2.2
	Durability	table III	4.5.3.2
	Workmanship	3.10	4.5.5
	Fire resistance	table III	4.5.3.1
NOTES:			
^{1/} Fire test requirements for ticking fabric shall apply to initial flammability and flammability after 15 launderings.			
^{2/} Testing shall be conducted in both flaming and non-flaming modes.			

4.2.1 First article units. The mattresses selected as sample units from the first article lot shall be thoroughly checked for all mattress requirements in [table IV](#) and herein (see 6.2). The sample shall be representative of the construction, workmanship, components, and materials to be used during production. The sampling rate shall be as specified in 4.4.

MIL-PRF-32569

4.3 Conformance inspection. Conformance inspection shall include the inspections of 4.3.1 through 4.3.2.

4.3.1 In-process examination. Visual examinations shall be made during the manufacture of the mattress to ensure construction details are in accordance with the requirements specified in section 3. Examinations shall be made prior to the final closing of the mattress where such details cannot be examined after final mattress closure. Dimensional and labeling examinations shall be made after final closure of the mattress. Materials and components that can be classified as a defect in accordance with [tables IV](#) and [V](#) shall be removed from production.

4.3.2 Inspection of end item. The end item inspection shall be in accordance with [table IV](#). A failure of any sample shall constitute a failure of the entire lot.

4.3.3 Lot. A lot shall consist of all mattresses that are produced under similar conditions and are ready for inspection or shipment at one time. Unless otherwise specified (see 6.2), the lot size shall be expressed in the number of finished mattresses.

4.4 Sampling.

4.4.1 Sampling for inspection of first article and end item. Samples, consisting of finished mattresses and components, shall be randomly selected from each lot. Except for durability testing (see 4.4.2), the sampling rate shall be 3 units on lots of 1 to 250, 5 units on lots of 251 to 1,200, 7 units on lots of 1,201 to 10,000, and 10 units on lots from 10,001 to 35,000. The inspections shall be as specified in 4.2.1 for first article and 4.3.1 and 4.3.2 for end item.

4.4.2 Sampling for durability testing. A single mattress shall be selected from each lot. For each depth of mattress, one sample unit shall be tested. The test sample shall be marked with an "X" on the label. For those plants producing mattresses of only a single depth, an additional mattress shall be provided to be used as part of the test apparatus to accommodate the translation of the rollator beyond the width of the test sample unit. However, the additional mattress shall neither be tested nor evaluated as a sample test unit.

4.4.3 Test sample preparation. Unless otherwise specified (see 6.2), samples for individual tests shall be prepared in accordance with the specified test method.

4.5 Inspection methods.

4.5.1 Foam performance testing. Foam performance testing shall be performed in accordance with ASTM D3574 as follows:

- a. Thickness. Foam thickness shall be determined by placing the foam on a flat surface and taking thickness measurements in accordance with Measurement of Test Specimens at a point approximately 3 inches in from the sides and end of the foam at each of the four corners.
- b. Density. Foam density shall be determined in accordance with the Density test.
- c. IFD. Foam IFD shall be determined in accordance with the Indentation Force Deflection Test—Specified Deflection test for a specified deflection of 25 percent. The sample size shall be 15 inches by 15 inches by 4 inches thick.
- d. Compression set. Foam compression set shall be determined in accordance with the Constant Deflection Compression Set test.
- e. Tensile strength. The tensile strength of the foam shall be tested in accordance with the Tensile test.
- f. Tear strength. The tear strength of the foam shall be tested in accordance with the Tear Resistance test.
- g. Resilience. The resilience of the foam shall be determined in accordance with the Resilience (Ball Rebound) test.
- h. Dry heat aging. The dry heat aging properties of the foam shall be determined in accordance with the Dry Heat Aging test and evaluated with the before and after test results of the IFD test.
- i. Cement bond. The cement bond shall be evaluated with the flat of the hand such that no difference between the foam and the cement seam can be detected when the hand is moved over the seam.

MIL-PRF-32569

4.5.2 Verification of physical requirements. The physical requirements of the finished mattress for each size shall be inspected in accordance with this specification.

4.5.2.1 Dimensions. The finished mattress samples shall be placed on a flat and level surface for verification of the specified length, width, and depth. Depth measurements shall be taken at a point approximately 3 inches in from the sides and ends of the mattress at each corner. Depth shall be taken as the average of measurements taken at each of the four corners of the mattress. The mattress samples shall be measured for length by measuring at three locations along the width and averaging the three dimensions. Similarly, the width shall be measured as the average of three measurements taken along the length of the mattress. Length and width measurements shall be made between tape stitch lines. See [figure 2](#) for locations of length, width, and depth measurements (see 3.5).

4.5.2.2 Weight. The weight of the mattress shall be measured in accordance with standard commercial practice using a load cell with a resolution of 0.25 pound (0.1 kilogram) or less.

4.5.3 Verification of performance requirements. The finished mattress samples shall be tested for fire resistance, firmness, and durability in accordance with the performance requirements of this specification.

4.5.3.1 Fire performance. The mattress samples shall be tested in accordance with ASTM E1590, including all optional results, with the exceptions noted in 4.5.3.1.1. Any failure shall be cause for rejection of the lot. The sampling rate for the fire testing shall be as specified in 4.4.1.

4.5.3.1.1 Test exceptions.

a. The full-sized test sample shall be mounted label side up on an open frame bunk or support system that will allow direct flame impingement to the bottom surface and sides of the mattress by the ignition source. The welded bed frame shall conform to [figure 3](#).

b. ASTM E1590, Test Configuration C shall be used. As specified (see 6.2), the report required by ASTM E1590 shall include all optional results identified in the Reports section.

c. The “T” burner described in the Ignition Source section of ASTM E1590 shall be replaced with a burner as shown on [figure 4](#), having a nominal 12 by 12 inch top surface. The burner shall have a minimum 4-inch layer of silica sand, 0.08 inch (2 millimeters) to 0.12 inch (3 millimeters) in size, to provide the horizontal surface through which the gas is supplied. The sand layer shall be flush with the top of the burner.

d. The burner shall be positioned such that the top edge of the burner is 15 inches \pm 0.5 inch below the bottom edge of the test specimen and centered with respect to the long side of the test specimen with half of the width of the burner under the mattress as shown on [figure 5](#).

e. The test specimen shall be exposed to a fire producing a total heat output of 50 kilowatts (kW) \pm 3 kW for the first 5 minutes of the test, followed by an increase to 100 kW \pm 5 kW for an additional 10 minutes. The total fire exposure time shall be 15 minutes.

f. Measurements for carbon monoxide (CO) and carbon dioxide (CO₂) shall also be made.

g. The burner shall be turned off. Combustion shall be allowed to continue until one or more of the following conditions are reached:

- (1) All flaming combustion has ceased.
- (2) 30 minutes have elapsed from the time the burner was ignited.

4.5.3.1.2 Average specific extinction area. Average specific extinction area (yd²/lb [m²/kg]) is defined as the total smoke released (y² [m²]) divided by the total mass loss (lb [kg]).

4.5.3.1.3 Fire testing provisions. All fire tests specified in this document shall be conducted by an independent testing laboratory that is accredited to ISO/IEC 17025 and is approved by the NAVSEA Technical Authority. Accreditation shall be obtained from a recognized accreditation body such as American Association for Laboratory Accreditation (A2LA) or International Code Council’s International Accreditation Services (IAS). The scope of accreditation shall include specific flammability and fire tests. All other fire test provisions shall be as specified (see 6.2 and 6.6).

MIL-PRF-32569

4.5.3.2 Durability testing. The mattress shall be tested in accordance with the Durability Test for Mattress or Mattress Set, or Both section described by ASTM F1566, with the exceptions noted in 4.5.3.2.1.

4.5.3.2.1 Test exceptions. Test exceptions shall be as follows:

- a. As the firmness rating has already been determined, it is not necessary to repeat.
- b. The test duration is not 100,000 cycles, but is performed in blocks of 25,000 cycles as follows:

(1) Stop at 25,000 cycles. Inspect for any signs of wear, tear, damage, or degradation on any part of the mattress in accordance with the following:

- (a) Visually inspect the condition of the ticking.
- (b) Tactually inspect the condition of the cushioning.
- (c) Take pictures of any problems that can be seen visually.

(2) Stop at 50,000 cycles.

(a) Allow mattress to recover for 72 ± 1 hours. Measure the height and by comparing to the initial height, determine the percent permanent deformation for pass/fail.

(b) Inspect for any signs of wear, tear, damage, or degradation on any part of the mattress in accordance with the following:

- 1 Visually inspect the condition of the ticking.
- 2 Tactually inspect the condition of the cushioning.
- 3 Take pictures of any problems that can be seen visually.

(3) Stop at 75,000 cycles.

(a) Allow mattress to recover for 24 ± 1 hours. Measure the height and by comparing to the initial height, determine the percent permanent deformation for pass/fail.

(b) Inspect for any signs of wear, tear, damage, or degradation on any part of the mattress in accordance with the following:

- 1 Visually inspect the condition of the ticking.
- 2 Tactually inspect the condition of the cushioning.
- 3 Take pictures of any problems that can be seen visually.

4.5.4 Protective temporary plastic covering. The thickness of the temporary plastic covering shall be determined in accordance with ASTM D6988.

4.5.5 Workmanship inspections. Visual inspections shall be conducted to check for any manufacturing defects in the finished mattress. The finished mattress shall be clean and free from defects in accordance with 3.10 and [table V](#) and other conditions affecting form, fit, function, and appearance. Failure of a major defect shall constitute a failure of the entire lot. If there is a failure of a minor defect, then sample mattresses that failed this inspection shall be removed from the production run and a second set of samples selected. Failure of this second set of samples shall result in failure of the lot.

MIL-PRF-32569

TABLE V. Manufacturing defects.

Defect Category	Characteristic	Defects
Critical		
1	Protective Temporary Plastic Covering	Cover omitted.
Major		
101	Dimensions	Foam core length, width, or depth extends beyond the finished mattress or recedes from the finished mattress greater than allowed in 3.5 and table II .
102		Mattress not in accordance with 3.5 and table II .
103	Weight	Mattress exceeding maximum weight specified in 3.5 and table II .
104	Material	Incorrect or unapproved material used.
105		Mattress has objectionable odor.
106	Ticking	Broken or missing yarns: a. Three or more contiguous, regardless of length. b. Two contiguous, 2 inches or more in length.
107		Any hole, cut, tear, or smash (see 6.3.3).
108		Any mend or patch.
109		Thin or open place.
110		Floats or skips – multiple ½ inch in combined warp and filling directions.
111		Light place or fine filling bar, clearly noticeable.
112		Any open seam.
113		Raw edges over 1 inch in length.
114	Construction	Design and construction of the finished mattress not as specified in section 3.
115		Mattress ends have loose, sagging appearance; foam core not evenly distributed such that the mattress exterior appears warped or twisted; clearly noticeable lumps; and corner(s) not firm.
116		Stitch type and stitches per inch not as specified; needle chew or needle cutting; end of stitching when not caught in another seam; broken stitch not repaired as specified; open seam, skipped or run-off stitches, raw edges.
117		Seam allowances not as specified; loose or tight tension; badly pleated, caught or twisted in any unrelated row of stitching as specified in 3.3.2.2.
118		Thread breaks and ends of stitching not caught in another line of stitching, backstitched less than ½ inch.
119		Thread type not as specified.
120		Hard spot or large lump which can be felt through tick.

MIL-PRF-32569

4.6 Toxicity.

4.6.1 HHA toxicity. An HHA will be conducted to ensure conformance to 3.8.1, as specified (see 6.2). The Navy and Marine Corps Public Health Center (NMCPHC) will evaluate the mattress using data provided by the manufacturer/distributor to the NMCPHC (see 3.8.1 and 6.4).

4.6.2 Fire gas toxicity. During the conduct of the smoke density test specified in 3.8.2, the foam material shall be evaluated for fire gas toxicity in accordance with ASTM E800. The average value of the maximum value of the gas concentration measured at each condition (flaming and non-flaming) shall be recorded for the following gases: carbon monoxide (CO); hydrogen chloride (HCl); hydrogen fluoride (HF); nitrogen oxides (NO_x); hydrogen bromide (HBr); hydrogen cyanide (HCN); and sulfur dioxide (SO₂), as specified (see 6.2). When making toxicity measurements, the sampling of gases shall be made during the testing of the second and the third specimen at each test condition, from the geometrical center of the chamber at the time when the maximum specific optical density of smoke is reached. The number of samples shall be four; two each in the flaming and non-flaming condition. The concentration of each toxic gas shall be determined as parts per million (ppm) in the chamber volume.

4.7 Off-gassing. The mattress shall be evaluated for off-gassing in accordance with S9510-AB-ATM-010 chapter titled "Material Control Program" (see 3.9 and 6.5). If the Navy determines that off-gas testing is required, testing shall be conducted at a NAVSEA approved test facility (see 3.9). The Navy will review the off-gas test results and assign a usage category. Additionally, the Navy will assign a usage category if an administrative review is conducted in lieu of off-gas testing (see 3.9).

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The mattresses covered by this specification are intended for use aboard U.S. Navy vessels. Due to extensive testing and approvals needed, end users should always procure through the NSN system.

6.2 Acquisition requirements. Acquisition documents should specify the following:

- a. Title, number, and date of this specification.
- b. Size required (see 1.2).
- c. The specific issue of individual documents referenced (see 2.2.1, 2.2.2, and 2.3).
- d. When first article inspection/testing is required (see 3.1 and 4.2).
- e. Requirements for an HHA (see 3.8.1, 4.2, and 4.6.1).
- f. Requirements for fire gas toxicity (see 3.8.2, 4.2, 4.6.2, and 6.9).
- g. When off-gas testing is required (see 3.9, 4.2, 4.7, and 6.5).
- h. Test sample preparation (see 4.4.3).
- i. Requirement for a test report, including all optional results, in accordance with ASTM E1590 (see 4.5.3.1.1.b).
- j. Additional fire testing provisions (see 4.5.3.1.3 and 6.6).
- k. Packaging requirements (see 5.1).
- l. When review of MSDS, spread sheet (component quantity [weight] and location in mattress), and samples of each component are required (see 6.4).

MIL-PRF-32569

m. Where certificates of compliance are acceptable (see 6.7).

6.3 Definitions. The following definitions, adopted from the Code of Federal Regulations - Title 16, Volume 2, Part 1632, with modifications, apply for the purpose of this specification.

6.3.1 Core. Core is the main support system that may be present in a mattress, such as springs, foam, or resilient filling.

6.3.2 Mattress. Mattress is a ticking filled with a resilient material such as synthetic flexible foam or innerspring unit used alone or in combination with other products intended or promoted for sleeping upon.

6.3.3 Smash. Smash is a relatively large hole in fabric characterized by broken warp ends and floating picks.

6.3.4 Surface. Surface is one side of a mattress that can be tested.

6.3.5 Ticking. Ticking is the outermost layer of fabric that encloses the foam core.

6.4 HHA toxicity evaluation. The NMCPHC requires sufficient information to permit an HHA of the product. Upon completion of the HHA, a copy will be provided by the NMCPHC to the Government for evaluation. The HHA process is described on the NMCPHC's website, <http://www.med.navy.mil/sites/nmcpHC/industrial-hygiene/Pages/health-hazard-assessment.aspx>.

6.5 Material certification. Materials to be installed in submarines are to be controlled to prevent off-gassing, which contaminates the submarine's atmosphere and can result in health hazards to personnel or deleterious effects on machinery. These controls are administered through the Submarine Material Control Program, which is described in the Nuclear Powered Submarine Atmosphere Control Manual, S9510-AB-ATM-010 chapter titled "Material Control Program." Under the Submarine Material Control Program, all materials considered for use on submarines require certification and assignment of a usage category. Under the certification process, candidate materials are selected by Navy activities or contractors, and a request for certification is submitted to Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard, DC 20376-5160 or emailed to CommandStandards@navy.mil. The certification request is accompanied by detailed information, including descriptions of the material, method of application, usage, and storage. A chemical analysis is conducted, which can be accomplished through off-gas testing. If off-gas testing is required, it must be conducted in a Government approved laboratory. Information pertaining to this test requirement may be obtained from Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard, DC 20376-5160 or emailed to CommandStandards@navy.mil. Based on the chemical analysis results, a usage category is assigned to the material defining whether, and to what extent, the material may be used on submarines.

6.6 Additional fire testing provisions. NAVSEA reserves the right to witness the tests, and perform any of the tests set forth herein where such testing is deemed necessary to assure compliance to prescribed requirements. NAVSEA will provide a letter that indicates the approved laboratories which are accredited to ISO/IEC 17025 and which details how to obtain and maintain accreditation (see 6.2).

6.7 Certificate of compliance. Where certificates of compliance are submitted (see 6.2), the Government reserves the right to test such items to determine the validity of the certification. The supplier is permitted to provide a certificate of compliance for each component. The supplier must attach to the certificate of compliance the passing test reports that identify the test results required for each component ([table I](#)), and provide them to the end item producer. Each certificate of compliance must be made available to the Government representative.

6.8 Equivalent material requests. Requests to use equivalent materials should be sent to the contracting officer for approval by the Navy. Any changes to materials used for fabricating mattresses occurring after initial first article inspection should be evaluated to the requirements of [table I](#) and requires approval by NAVSEA.

6.9 Fire gas toxicity evaluation. NAVSEA recommends inclusion of the fire gas toxicity evaluation (see 3.8.2 and 4.6.2). Measurement of the concentration of each toxic gas should be as prescribed in 4.6.2 and provided in the first article test report (see 6.2). The Navy will use the data provided for evaluation purposes.

MIL-PRF-32569


6.10 Subject term (key word) listing.

Core

Fire performance

Ticking

MIL-PRF-32569



NOTE:

1. The tolerance for locations of the length and width measurements is ± 1 inch.

FIGURE 2. Test specimen dimensional measurement locations.

MIL-PRF-32569







FIGURE 3. Test sample bed frame.


MIL-PRF-32569

**TOP VIEW****SIDE VIEW**FIGURE 4. Gas burner.

MIL-PRF-32569



ELEVATION VIEW OF TEST SPECIMEN & BURNER



PLAN VIEW OF TEST SPECIMEN & BURNER

FIGURE 5. Test specimen and burner layout.

MIL-PRF-32569

Custodians:

Army – GL
Navy – SH
Air Force – 11

Preparing activity:

Navy – SH
(Project 7210-2015-001)

Review activities:

Army – AV, MI
Navy – CG, NU
Air Force – 03
DLA – CT

Civil agency:

GSA – FAS

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at <https://assist.dla.mil>.