

NOT MEASUREMENT SENSITIVE
------------------------------

MIL-PRF-85582D

09 May 2002

SUPERSEDING

MIL-PRF-85582C

30 September 1997

## PERFORMANCE SPECIFICATION

## PRIMER COATINGS: EPOXY, WATERBORNE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 Scope. This specification covers the requirements for corrosion inhibiting, chemical and solvent resistant, waterborne, epoxy primer coatings that have a maximum volatile organic compound (VOC) content of 340 grams per liter (g/L) (2.8 pounds per gallon [lb/gal]).

1.2 Classification. The primer coatings will be of the following types and classes, as specified (see 6.2):

1.2.1 Types. The types of primer coatings are as follows:

- Type I - Standard pigments
- Type II - Low infrared reflective pigments

1.2.2 Classes. The classes of primer coatings are as follows:

- Class C1 - Barium chromate based corrosion inhibitors
- Class C2 - Strontium chromate based corrosion inhibitors
- Class N - Non-chromate based corrosion inhibitors

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, Naval Air Warfare Center Aircraft Division, Code 414100 B120-3, Highway 547, Lakehurst, NJ 08733-5100, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.
---

AMSC N/A

FSC 8010

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

## MIL-PRF-85582D

## 2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications and standards. The following specifications and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2).

## SPECIFICATIONS

## DEPARTMENT OF DEFENSE

MIL-A-8625	-	Anodic Coatings for Aluminum and Aluminum Alloys
MIL-PRF-23699	-	Lubricating Oil, Aircraft Turbine Engine, Synthetic Base, NATO Code Number 0-156
MIL-DTL-81706	-	Chemical Conversion Materials For Coating Aluminum and Aluminum Alloys
MIL-PRF-83282	-	Hydraulic Fluid, Fire Resistant, Synthetic Hydrocarbon Base, Metric, NATO Code Number H-537
MIL-PRF-85285	-	Coating: Polyurethane, High-Solids

## STANDARDS

## FEDERAL

FED-STD-141	-	Paint, Varnish, Lacquer and Related Materials: Methods of Inspection, Sampling and Testing
FED-STD-595	-	Colors Used in Government Procurement

(Unless otherwise indicated, copies of the above specifications and standards are available from the Standardization Documents Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are

## MIL-PRF-85582D

DoD adopted are those listed in the issue of the DoDISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DoDISS are the issues of the documents cited in the solicitation (see 6.2).

## AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

- ASTM-B117 - Salt Spray (Fog) Apparatus, Operating. (DoD adopted)
- ASTM-D1193 - Reagent Water. (DoD adopted)
- ASTM-D1200 - Cup, Viscosity by Ford Viscosity. (DoD adopted)
- ASTM-D1210 - Fineness Of Dispersion Of Pigment-Vehicle Systems By Hegman-Type Gage. (DoD adopted)
- ASTM-D1296 - Solvents and Diluents, Volatile, Odor of. (DoD adopted)
- ASTM-D1475 - Liquid Coatings, Inks, and Related Products, Density of. (DoD adopted)
- ASTM-D1640 - Organic Coating, Drying, Curing, or Film Formation of at Room Temperature. (DoD adopted)
- ASTM-D1849 - Paint, Package Stability of. (DoD adopted)
- ASTM-D2243 - Water Borne Coatings, Freeze-Thaw Resistance of. (DoD adopted)
- ASTM-D2369 - Coatings, Volatile Content of. (DoD adopted)
- ASTM-D2794 - Deformation, Rapid, Resistance of Organic Coatings to the Effects of (Impact). (DoD adopted)
- ASTM-D2803 - Metal, Organic Coatings on, Filiform Corrosion Resistance of. (DoD adopted)
- ASTM-D3335 - Lead, Cadmium, and Cobalt in Paint by Atomic Absorption Spectroscopy, Test for Low Concentrations of. (DoD adopted)
- ASTM-D3718 - Paint, Chromium in, by Atomic Absorption Spectroscopy, Low Concentrations of. (DoD adopted)
- ASTM-D3742 - 1,1,1-Trichloroethane Content
- ASTM-D3792 - Water Content of Water-Reducible Paints by Direct Injection Into a Gas Chromatograph. (DoD adopted)
- ASTM-D3924 - Paint, Varnish, Lacquer, and Related Materials, Conditioning and Testing, Standard Environment for. (DoD adopted)

(Application for copies should be addressed to the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.)

## AMERICAN SOCIETY FOR QUALITY CONTROL (ASQC)

- ASQC-Z1.4 - Procedures, Sampling and Tables for Inspection by Attributes. (DoD adopted)

(Application for copies should be addressed to the American Society for Quality Control, P.O. Box 3005, 611 East Wisconsin Avenue, Milwaukee, WI 53201-4606.)

## MIL-PRF-85582D

### SOCIETY OF AUTOMOTIVE ENGINEERS (SAE)

- SAE-AMS-QQ-A-250/4 - Aluminum Alloy 2024, Plate and Sheet. (DoD adopted)
- SAE-AMS-QQ-A-250/5 - Aluminum Alloy Alclad 2024, Plate and Sheet. (DoD adopted)

(Application for copies should be addressed to the Society of Automotive Engineers, 400 Commonwealth Drive, Warrendale, PA 15096-0001.)

2.4 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

### 3. REQUIREMENTS

3.1 Qualification. The primer coating furnished under this specification shall be a product that is authorized by the qualifying activity for listing on the applicable qualified products list before contract award (see 4.2 and 6.3).

3.2 Material. Materials used in the manufacture of products supplied under this specification shall produce products conforming to the requirements of this specification.

3.3 Composition. The primer coating shall consist of two components, as follows:

Component A - a base component of epoxy resin solution

Component B - a curing agent

The components shall be packaged separately and furnished as a kit (see 6.6.1). When the components are mixed in the proportions specified by the manufacturer and reduced with water conforming to ASTM-D1193, type IV, if required, a product meeting the requirements of this specification shall result. Chlorinated solvents, except for para-chlorotrifluoromethylbenzene or equal, shall be prohibited from the formulation of this primer coating. Incidental cadmium and cadmium compounds shall be not greater than one part per million (ppm). The non-volatile portion shall contain not more than 0.06 percent by weight of lead metal or lead compounds.

3.3.1 Pigment. The pigment of the primer coating shall be contained in component A or B.

3.3.1.1 Class C1. Coatings containing barium chromate as the corrosion inhibitor and other pigments, as required, shall be identified as class C1.

## MIL-PRF-85582D

3.3.1.2 Class C2. Coatings containing strontium chromate as the corrosion inhibitor and other pigments, as required, shall be identified as class C2.

3.3.1.3 Class N. Coatings containing non-chromium corrosion inhibitors, along with extenders and other pigments, shall be identified as class N. Incidental chromium content of class N shall be not greater than 5 ppm.

3.3.2. Solvent content. The volatile organic compound (VOC) content of the admixed primer coating shall be not greater than 340 g/L (2.8 lb/gal) of coating, excluding water (see 4.5.1).

3.4 Physical properties – components before mixing.

3.4.1 Fineness of grind. The fineness of grind of the pigmented component shall be 5 or greater on the Hegman scale when tested in accordance with table I.

3.4.2 Condition in container. Components A and B shall be free of grit, seeds, lumps, abnormal thickening, or livering, and shall not show pigment flotation nor excessive settling. They shall mix to a smooth, homogeneous, and pourable condition (see 4.5.2). In addition, the containers shall exhibit no deformation.

3.4.3 Storage stability. The primer coating components, as packaged by the manufacturer, shall meet all requirements of this specification, when stored at a daily ambient air temperature of 1.7 to 46 °C (35 to 115 °F) for not less than one year and tested in accordance with table I.

3.4.4 Accelerated storage stability. The primer coating components, as packaged by the manufacturer, shall meet all the requirements of this specification, when tested in accordance with table I. The container shall not become deformed and the lid shall not become unsealed during the storage period.

3.4.5 Freeze-thaw stability. The primer coating components, as supplied by the manufacturer, shall meet all the requirements specified herein after being subjected to five cycles of freezing and thawing and when tested in accordance with table I.

3.5 Physical properties - admixed components.

3.5.1 Color.

3.5.1.1 Type I. The color of the admixed type I primer coating shall be the natural color of the corrosion inhibiting pigments used or darker.

3.5.1.2 Type II. The color of the admixed type II primer coating shall be dark green or gray.

## MIL-PRF-85582D

3.5.2 Odor. The odor of the primer coating, as packaged components or as a film after application, shall be characteristic of the thinners used, when tested in accordance with table I.

3.5.3 Viscosity and pot life. The viscosity of the admixed primer coating, when thinned in accordance with the manufacturer's instructions and stirred constantly at  $140 \pm 30$  revolutions per minute (rpm) in an open or closed container, shall not increase by more than 8 seconds through a number 4 Ford cup after 4 hours at  $23 \pm 2$  °C ( $73 \pm 5$  °F). At the end of the 4-hour period, the applied primer coating shall meet all of the requirements of 3.7.1 through 3.7.4, when tested in accordance with table I.

3.6 Physical properties - film.

3.6.1 Surface appearance. The admixed primer coating, applied to a vertical surface, shall not sag, run, nor streak. The dried film shall be free of grit, seeds, craters, blisters or any other surface irregularities when applied in accordance with 4.4.1. No orange peel (wavy appearance) shall be visible when viewed from at least six feet away.

3.6.2 Drying time. The applied primer coating shall be tack-free within 60 minutes and shall dry hard within 6 hours, when tested in accordance with table I.

3.6.3 Lifting. There shall be no evidence of lifting nor any other film irregularity upon application of a gloss polyurethane coating conforming to MIL-PRF-85285 to a primer coating that has air dried for 2, 4, and 18 hours, respectively (see 4.5.3).

3.6.4 Adhesion. The primer coating shall not peel from the substrate when tested in accordance with 4.5.4.

3.6.5 Flexibility. The primer coating shall exhibit an impact elongation of not less than 10 percent, when tested in accordance with 4.5.5.

3.6.6 Infrared reflectance (type II primer coating only). The total reflectance (specular and diffuse) of the type II primer coating, relative to barium sulfate, shall be not greater than ten percent throughout the range of 700 to 2,600 nanometers (nm) (see 4.5.6).

3.7 Resistance properties.

3.7.1 Water resistance. The primer coating, with topcoat, shall withstand immersion in distilled water maintained at  $49 \pm 3$  °C ( $120 \pm 5$  °F) for four days without exhibiting any evidence of wrinkling, blistering, or any other coating deficiency (see 4.5.7).

## MIL-PRF-85582D

3.7.2 Corrosion resistance.

3.7.2.1 Salt spray. The primer coating, with and without a topcoat, shall not exhibit blistering, lifting of either coating, or substrate pitting after exposure to a 5 percent salt spray for 2,000 hours. Class C1 and class C2 primer coatings shall not exhibit corrosion in the scribe (see 4.5.8.1).

3.7.2.2 Filiform. The topcoated primer coating shall not exhibit filiform corrosion extending beyond 6.35 millimeters (mm) (0.25 inch) from the scribe, and the majority of the filaments shall be less than 3.175 mm (0.125 inch) in length (see 4.5.8.2).

3.7.3 Solvent resistance (cure). The primer coating shall withstand 50 passes (25 back and forth rubs) with a cloth rag soaked in methyl ethyl ketone (MEK). Rubbing through to bare substrate constitutes failure of the primer coating to properly cure (see 4.5.9).

3.7.4 Fluid resistance. The primer coating shall withstand immersion for 24 hours in each of synthetic lubricating oil conforming to MIL-PRF-23699 and synthetic hydraulic fluid conforming to MIL-PRF-83282. Four hours after removal from the respective fluid, the coating shall not exhibit any softening, blistering, loss of adhesion, nor any other coating deficiency. Discoloration of the coating is acceptable and shall not be cause for rejection (see 4.5.10).

3.8 Working properties.

3.8.1 Mixing and dilution. The components of the primer coating shall homogeneously blend when mixed with a mechanical mixer in the volume mixing ratio specified by the manufacturer. When the admixed primer coating is diluted to application viscosity with water (according to the manufacturer's instructions), there shall be no evidence of incompatibility and the material shall be capable of application by spray methods (see 3.8.2). Transient incompatibility exhibited during the first half of water addition is allowed. The primer coating shall not separate into visually distinct layers within one hour after water dilution (see 4.5.11).

3.8.2 Application. The admixed primer coating shall be applied by conventional, airless, high volume, low pressure (HVLP), or electrostatic spray equipment installed for water systems. Application shall yield a smooth, uniform film with no runs or sags at a dry-film thickness of 15 to 23 microns ( $\mu\text{m}$ ) (0.6 to 0.9 mil) (see 4.4.1).

3.9 Identification of material. Individual containers greater than one pint and cases of containers less than one pint shall be identified with the following information:

MIL-PRF-85582D, Primer Coatings: Epoxy, Waterborne  
Component identification (as applicable):  
Component A - base component  
Component B - curing agent

## MIL-PRF-85582D

MIL-PRF-85582D, type I or II, class C1, C2, or N (as applicable)

Manufacturer's name and product number

Date of manufacture (month/year)

Batch number/net contents

VOC content in grams/liter

Mixing and thinning instructions

3.9.1 Component A containers. Component A containers shall have the following warning:

“WARNING! COMBUSTIBLE”

3.9.2 Component B containers. Component B containers shall have the following warning:

“WARNING! FLAMMABLE”

3.10 Precaution sheet. A printed precaution sheet with the following information shall be included with each kit (see 6.6.1) as follows:

## PRECAUTIONS

- a. The surface to be coated must be clean (free of oil, dust, etc.).
- b. Spray equipment must be properly grounded. Clean equipment immediately after use.
- c. Mix only the amount of primer coating to be used within 4 hours.
- d. Primer coating from one vendor, or individual component, must never be mixed with that of another vendor.
- e. Apply over pretreated metal. On fiberglass-reinforced plastic, a prior coating of wash primer in accordance with MIL-C-8514 will facilitate stripping without damage to the fiberglass.

## 4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

- a. Qualification inspection (see 4.2).
- b. Conformance inspection (see 4.3).

4.2 Qualification inspection. Qualification inspection shall consist of all the inspections listed in this specification. The qualification inspection performed by the qualification laboratory (see 6.3) shall consist of a review for approval of the submitted manufacturer's test report and subjecting the qualification test sample to examination and testing to determine conformance to all of the requirements specified in section 3. The qualification test sample shall consist of not less

## MIL-PRF-85582D

than one quart (admixed) of the primer coating material. The samples shall be legibly identified (see 6.3.2).

#### 4.3 Conformance inspection.

4.3.1 Primer coating inspection. The conformance inspection shall consist of all the tests specified in table I, with the exception of storage stability (see 3.4.3), accelerated storage stability (see 3.4.4), freeze-thaw stability (see 3.4.5), and corrosion resistance (see 3.7.2.1 and 3.7.2.2). Samples for tests shall consist of one complete unopened kit selected at random from each batch. Containers shall only be opened when being tested.

4.3.2 Visual inspection of filled containers. Samples shall be selected at random from each lot (see 6.9) in accordance with ASQC-Z1.4, inspection level S-2. The lot size for this inspection shall be the number of kits fully prepared for delivery. The selected samples shall be examined for container fill, proper location, and completion of item identification (see 3.9), warning statements (see 3.9.1 and 3.9.2), and the precaution sheet (see 3.10).

4.4 Test panels. Test panels shall be prepared under laboratory test conditions (see 4.5). With the exception of the flexibility test (see 4.5.5) and the filiform corrosion test (see 4.5.8.2), all test panels shall be aluminum alloy 2024 (T3 temper) conforming to SAE-AMS-QQ-A-250/4, measuring 0.51 by 76.2 by 152.4 mm (0.020 by 3 by 6 inches). Test panels shall be conversion coated with coating conforming to MIL-DTL-81706, class 1A.

#### 4.4.1 Application of primer coating. The primer coating shall be prepared for application by:

- a. Thoroughly mixing each component separately.
- b. Mixing the components in the manufacturer's specified volume mixing ratio.
- c. Thinning with water in accordance with the manufacturer's instructions (water reducible only).
- d. Allowing admixed coating to stand for 30 minutes prior to use.
- e. Spraying the test panels with primer coating to a dry-film thickness of 15 to 23  $\mu\text{m}$  (0.6 to 0.9 mil).

If a topcoat is not used, the primer coating shall be allowed to air dry for not less than 14 days, or air dry for not less than one hour followed by 24 hours at  $65.5 \pm 3$  °C ( $150 \pm 5$  °F) prior to testing. If a topcoat is required, the primer coating shall be air-dried for 2 hours and then coated with a polyurethane coating conforming to MIL-PRF-85285 in accordance with 4.4.2.

4.4.2 Application of topcoat. When a topcoat is required by the test method, mix polyurethane coating conforming to MIL-PRF-85285, untinted gloss white conforming to FED-STD-595, color number 17925, and allow it to stand for 30 minutes prior to application. Apply the coating to a total dry-film thickness of 43 to 58  $\mu\text{m}$  (1.7 to 2.3 mils). If applied in two coats, allow the first coat to air dry for 60 minutes prior to application of the second coat. After

## MIL-PRF-85582D

application of the topcoat to the required thickness and prior to testing, allow the coating to air dry for not less than 14 days or allow the coating to air dry for one hour followed by 24 hours at  $65.5 \pm 3$  °C ( $150 \pm 5$  °F).

4.5 Test methods. The tests of this specification shall be conducted in accordance with table I and 4.5.1 through 4.5.10. Unless otherwise specified in the test method or paragraph, laboratory test conditions shall be in accordance with ASTM-D3924.

TABLE I. Test methods.

Test	Requirement Paragraph	Test Paragraph	FED-STD-141 Test Method	ASTM Method
Lead and cadmium content	3.3	---	---	ASTM-D3335
Chlorinated solvent content	3.3	---	---	ASTM-D3742
Chromium content	3.3.1.3	---	---	ASTM-D3718
Solvent content	3.3.2	4.5.1	---	---
Fineness of grind	3.4.1	---	---	ASTM-D1210
Condition in container	3.4.2	4.5.2	---	---
Storage stability <u>1/</u>	3.4.3	---	3022	---
Accelerated storage stability <u>2/</u>	3.4.4	---	---	ASTM-D1849
Freeze-thaw stability	3.4.5	---	---	<u>3/</u> ASTM-D2243
Odor	3.5.2	---	---	ASTM-D1296
Viscosity and pot life	3.5.3	---	---	ASTM-D1200
Surface appearance	3.6.1	4.4.1	---	---
Drying time	3.6.2	---	---	ASTM-D1640
Lifting	3.6.3	4.5.3	---	---
Adhesion	3.6.4	4.5.4	---	---
Flexibility	3.6.5	4.5.5	---	---
Infrared reflectance (type II only)	3.6.6	4.5.6	---	---
Water resistance	3.7.1	4.5.7	---	---
Salt-spray corrosion resistance	3.7.2.1	4.5.8.1	---	---
Filiform corrosion resistance	3.7.2.2	4.5.8.2	---	---
Solvent resistance (cure)	3.7.3	4.5.9	---	---
Fluid resistance	3.7.4	4.5.10	---	---
Mixing and dilution	3.8.1	4.5.11	---	---
Application	3.8.2	4.4.1	---	---

1/ The daily ambient air temperature at the storage location shall be within the range of 1.7 to 46 °C (35 to 115 °F).

2/ The primer coating shall be mixed with a mechanical shaker for 10 minutes instead of 300 stirs in 2 minutes.

3/ One freeze-thaw cycle shall be 16 hours at  $-9 \pm 3$  °C ( $15 \pm 5$  °F) followed by 8 hours at a room temperature of 18 to 29.5 °C (65 to 85 °F).

## MIL-PRF-85582D

4.5.1 Solvent content. The unthinned, admixed primer coating, in accordance with the manufacturer's instructions, shall be used for this test. The VOC content of the primer coating shall be calculated as follows:

$$\text{VOC (g/L)} = A \div B$$

Where:

$$A = [(100 - X_M - W_{H_2O}) \div 100]$$

$$B = [(1 \div P_M) - (W_{H_2O} \div 100,000)]$$

$X_M$  = Solids content of the admixed primer coating (weight percent) determined in accordance with ASTM-D2369, procedure B.

$P_M$  = Density of admixed primer coating (g/L), determined in accordance with ASTM-D1475.

$W_{H_2O}$  = Water content of the admixed primer coating (percent by weight), determined in accordance with ASTM-D3792.

4.5.2 Condition in container. Each component in its unopened container shall stand without agitation for not less than 14 days at room temperature (see 4.5). After this period, the container(s) shall be examined for bulging or other deformation due to internal pressure. Each component container shall be opened and examined, then mixed by hand, vigorously stirring with a paddle for not more than 5 minutes and shall conform to 3.4.2.

4.5.3 Lifting. The primer coating shall be applied to test panels in accordance with 4.4 and 4.4.1, with the exception of drying time, noted as follows: Topcoat shall be applied in accordance with 4.4.2 to primer coating that has air dried for 2, 4, and 18 hours, respectively. After the topcoat has fully cured, the test panels shall be examined for conformance to 3.6.3.

4.5.4 Adhesion. Primer coating shall be applied to the test panels in accordance with 4.4 and 4.4.1. The test panels shall then be immersed in distilled water for not less than 24 hours at a room temperature of 18 to 29.5 °C (65 to 85 °F). After removal, the test panels shall be dried with absorbent paper tissue and, within three minutes of removal from the water, be tested in accordance with FED-STD-141, Method 6301, for conformance to 3.6.4.

4.5.5 Flexibility. Test panels, constructed of aluminum alloy 2024 (O temper) conforming to SAE-AMS-QQ-A-250/4 and measuring 0.51 by 76.2 by 152.4 mm (0.020 by 3 by 6 inches), shall be anodized in accordance with MIL-A-8625, type I. Primer coating shall then be applied to the test panels in accordance with 4.4.1. The flexibility of the coating shall then be tested at the room temperature and relative humidity conditions as specified in ASTM-D3924, using a Gardco GE Universal Impact Tester, Model #172 (see 6.7), with a specialized impactor that weighs 3.6 lb, and has formed on each end four convex spherical segments, each of different radii and extension. Place the coated panel, film side downward, on the rubber pad at the bottom of the impactor guide. Drop the impactor on the panel through the impactor guide, ensuring that the impression of the entire rim of the impactor is made in the panel. Reverse the impactor ends and drop it through the guide on the panel adjacent to the first area of impact. Using 10 power magnification,

## MIL-PRF-85582D

examine for conformance to 3.6.5; record the percent elongation corresponding to the largest spherical impression at which no cracking occurs.

4.5.6 Infrared reflectance (type II primer coating only). The type II primer coating shall be applied to test panels prepared in accordance with 4.4 and 4.4.1. The total reflectance (specular and diffuse) of the primer coating relative to barium sulfate shall be measured using a near infrared spectrophotometer over a range of 700 to 2,600 nm. Examine for conformance to 3.6.6.

4.5.7 Water resistance. Test panels shall be prepared with primer coating (see 4.4 and 4.4.1). One half of the primer coated panels shall be topcoated (see 4.4 through 4.4.2). All panels shall be immersed in distilled water maintained at  $49 \pm 3$  °C ( $120 \pm 5$  °F) for four days. Two hours after removal from the water, the coatings shall be examined for conformance to 3.7.1.

#### 4.5.8 Corrosion resistance.

4.5.8.1 Salt spray. Test panels shall be prepared with primer coating (see 4.4 and 4.4.1). One half of the primer coated panels shall be topcoated (see 4.4.2). Two intersecting lines shall be scribed diagonally across the surface of the primer coating, exposing the bare substrate. The test panels shall then be placed in a 5 percent salt spray cabinet for 2,000 hours, in accordance with ASTM-B117. After removal from the salt spray cabinet, the test panels shall be examined for conformance to 3.7.2.1.

4.5.8.2 Filiform. Test panels, constructed from Alclad aluminum alloy 2024 (T3 temper) conforming to SAE-AMS-QQ-A-250/5, with dimensions of 0.51 by 76.2 by 152.4 mm (0.020 by 3 by 6 inches), shall be conversion coated in material coating conforming to MIL-DTL-81706, class 1A. Primer coating and topcoat shall then be applied to the test panels in accordance with 4.4.1 and 4.4.2. Two intersecting lines shall be scribed across the surface of each test panel and shall penetrate through the cladding and into the base metal. The test panels shall be placed vertically in a desiccator containing 12 Normal (N) HCl for one hour at  $24 \pm 3$  °C ( $75 \pm 5$  °F). Within five minutes of removal from the desiccator, the test panels shall be placed in a desiccator maintained at  $40 \pm 2$  °C ( $104 \pm 3$  °F) and relative humidity of  $80 \pm 5$  percent for 1,000 hours. The test panels shall then be examined for conformance to 3.7.2.2. Filiform corrosion appears as thread-like filaments initiating from the exposed substrate and spreading underneath the coating film. A description of filiform growth is described in ASTM-D2803.

4.5.9 Solvent resistance (cure). The primer coating shall be applied to test panels in accordance with 4.4 and 4.4.1. The primer coating shall then be examined for cure, as follows:

- a. Soak a cotton terry cloth rag in MEK solvent (see 6.8).
- b. Rub the coating with the soaked rag for 50 passes (25 back and forth rubs) with firm finger pressure.
- c. Examine coating for conformance to 3.7.3.

## MIL-PRF-85582D

4.5.10 Fluid resistance. The primer coating shall be applied to test panels in accordance with 4.4 and 4.4.1. The test panels shall then be separately immersed to half their length for 24 hours in glass covered beakers containing the following:

- a. Lubricating oil conforming to MIL-PRF-23699 maintained at  $121 \pm 3$  °C ( $250 \pm 5$  °F)
- b. Hydraulic fluid conforming to MIL-PRF-83282 maintained at  $66 \pm 3$  °C ( $150 \pm 5$  °F)

After removal from the test fluids, cool the test panels to a room temperature of 18 to 29.5 °C (65 to 85 °F) and examine for conformance to 3.7.4.

4.5.11 Mixing and dilution. Stir component A until completely uniform. Mix component A with component B in the volume mixing ratio specified by the manufacturer and examine for conformance to 3.8.1. Thin as specified by the manufacturer. Stir and allow the admixed primer coating to sit for 30 minutes. Examine for conformance to 3.8.2.

## 5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When actual packaging of materiel is to be performed by DoD personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activity within the Military Department or Defense Agency, or within the Military Department's System Command. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

## 6. NOTES

(This section contains information of a general or explanatory nature which may be helpful, but is not mandatory.)

6.1 Intended use. The primer coatings covered by this specification are corrosion-inhibiting and chemical resistant, intended for spray application to most aircraft substrates. These coatings are compatible with polyurethane and epoxy topcoats (see 6.1.1) and may be used as alternatives to MIL-PRF-23377 for many applications. However, primer coatings containing water, such as these coatings, should not be used on iron or bare carbon steel, nor for the wet installation of fasteners or faying surfaces. Type II primer coatings are intended for use where low infrared reflectance is required. Class N may not be substituted for Class C1 or C2, unless authorization for its use is given by the engineering authority for the system or item to which the primer coating is to be applied. These primer coatings are formulated for the unique performance requirements of military aircraft. These requirements include adhesion to a wide variety of metals and composites, flexibility to withstand tactical maneuvers at low temperatures, corrosion resistance in

## MIL-PRF-85582D

a marine environment, resistance to leaking aircraft fluids, and low-infrared reflectance for stealth in combat.

6.1.1 Compatibility. The primer coatings covered by this specification are compatible with coatings conforming to the following specifications:

MIL-PRF-22750 Coating, Epoxy, High-Solids

MIL-C-46168 Coating, Aliphatic Polyurethane, Chemical Agent Resistant

MIL-C-53039 Coating, Aliphatic Polyurethane, Single Component, Chemical Agent Resistant

MIL-PRF-85285 Coating: Polyurethane, High-Solids

TT-P-2756 Coating: Self-Priming Topcoat, Low Volatile Organic Compounds

Compatibility with other coatings should be tested prior to use.

6.2 Acquisition requirements. Acquisition documents must specify the following:

- a. Title, number, and date of the specification.
- b. Type and class required (see 1.2).
- c. Issue of DoDISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.2 and 2.3).
- d. Packaging requirements (see 5.1).
- e. Quantity and kit size identification (see 6.6.1).

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Products List QPL-85582 whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or purchase orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from the Commander, Naval Air Warfare Center Aircraft Division, Code 4.3.4.1, Building 2188, Patuxent River, MD 20670-1908.

6.3.1 Inspection report and other information. When authorizing the forwarding of qualification samples, the qualifying activity will request the manufacturer to submit the qualification inspection sample, the Material Safety Data Sheet (MSDS) (see 6.9), and a test report showing that the material conforms to the requirements of this specification.

## MIL-PRF-85582D

6.3.2 Qualification inspection sample identification. Qualification inspection samples are to be forwarded to the laboratory designated in the letter of authorization (see 6.3) and identified as follows:

Qualification test samples.

Specification MIL-PRF-85582D, type I or II, and class C1, C2, or N (as applicable).

Primer Coatings: Epoxy, Waterborne.

Manufacturer's name and product number

Submitted by (name and date) for qualification testing in accordance with authorization (reference authorizing letter).

6.4 Retention of qualification. To retain qualification approval of products listed on the Qualified Products List (QPL), the manufacturer will be required to verify by certification to the qualifying activity that its product(s) complies with the requirements of this specification. Unless otherwise specified by the qualifying activity, the time of periodic verification by certification will be in two-year intervals from the date of original qualification. The certification action will be initiated by the qualifying activity. Any change in the formulation of a qualified product will necessitate its requalification. The material supplied under contract must be identical, within manufacturing tolerances to the product receiving qualification.

6.5 Conformance rejection and retest. Failure in any conformance inspection will result in the rejection of the batch from which it was obtained and constitutes sufficient justification for removal from the Qualified Products List. Rejected material cannot be resubmitted for acceptance without written approval from the qualification activity (see 6.3). The application for resubmission will contain all details concerning previous rejections and measures taken to correct these deficiencies.

6.6 Part or Identifying Number (PIN). The PIN to be used for primer coatings acquired to this specification is created as follows:

<u>M85582</u>	-	<u>X</u>	-	<u>XX</u>	-	<u>XXXX</u>
Specification identifier		Type designator		Class designator		Kit size designator
		1 = Type I		(C1, C2, or N0)		(see 6.6.1)
		2 = Type II				

6.6.1 Kit size. The primer coatings covered by this specification should be purchased by volume, the unit being a kit containing two components. The kit component sizes need not be of the same size. When this part numbering system is used, the kit size is to be identified as follows:

## MIL-PRF-85582D

Kit size <u>1/</u>	Kit size designator
Less than one pint	<u>2/</u>
4-pint (0.47-liter)	004P
4-quart (0.95-liter)	004Q
4-gallon (3.79-liter)	004G

- 1/ The kit size and its designator may be modified for ease of procurement and is not otherwise limited.
- 2/ Designators for less than pint size kits (small touch up kits) are expressed in cubic centimeters (cc) and designated by "C." Example: A type I, class C1, 50 cc kit is designated M85582-1-C1-050C.

6.7 Impact tester source. An instrument for conducting the test in accordance with ASTM-D2794 (see 4.5.5) is the Gardco GE Universal Impact Tester, Model #172, available from the Paul N. Gardner Company, 316 NE First Street, P.O. Box 10688, Pompano Beach, FL 33061-6688. There may be other instruments equivalent to this unit.

6.8 Safely handling MEK solvent. To minimize exposure to MEK solvent, it is recommended that personnel conducting the solvent resistance (cure) test (see 4.5.9) wear either butyl rubber or Teflon<sup>®</sup> gloves and a half-face respirator equipped with organic vapor cartridges.

6.9 Material Safety Data Sheet (MSDS). An MSDS must be prepared and submitted in accordance with FED-STD-313. The MSDS must also meet the requirements of 29 CFR 1910.1200. The 29 CFR 1910.1200 requires that the MSDS for each hazardous chemical used in an operation must be readily available to personnel using the material. Questions pertinent to the effect(s) of these coatings on the health of personnel using them may be referred by the procuring activity to the appropriate medical service, who will act as its adviser. Contracting officers will identify the activities requiring copies of the MSDS.

6.10 Lot and batch formation. A lot will consist of all of the primer coatings manufactured at one time from one batch, forming part of one contract or purchase order and submitted for acceptance. A batch consists of all primer coatings manufactured during one continuous operation.

6.11 Subject term (key word) listing.

Barium chromate  
Corrosion inhibitive  
Hydrochloric acid  
Low infrared reflectance  
Methyl ethyl ketone (MEK)  
Strontium chromate  
Water reducible

MIL-PRF-85582D

6.12 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:

Army - MR

Navy - AS

Air Force - 99

Preparing activity:

Navy - AS

(Project 8010-0174)

Review activities:

Army - AV, MD1

Navy - CG, OS, SH

Air Force - 11, 84

GSA - FSS (9FTE-10)

Other - DS

## STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

**INSTRUCTIONS**

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7, and send to preparing activity.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

**I RECOMMEND A CHANGE:**

**1. DOCUMENT NUMBER**  
MIL-PRF-85582D

**2. DOCUMENT DATE (YYYYMMDD)**  
20020509

**3. DOCUMENT TITLE**

PRIMER COATINGS: EPOXY, WATERBORNE

**4. NATURE OF CHANGE** (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)**5. REASON FOR RECOMMENDATION****6. SUBMITTER**

a. NAME (Last, First, Middle Initial)

b. ORGANIZATION

c. ADDRESS (Include ZIP Code)

d. TELEPHONE (Include Area Code)

(1) Commercial

(2) DSN  
(If applicable)

**7. DATE SUBMITTED**  
(YYYYMMDD)

**8. PREPARING ACTIVITY**

a. NAME  
COMMANDER  
NAVAL AIR WARFARE CENTER  
AIRCRAFT DIVISION

b. TELEPHONE (Include Area Code)

(1) Commercial (732) 323-2947

(2) DSN 624-2947

c. ADDRESS (Include ZIP Code)  
CODE 414100B120-3  
HIGHWAY 547  
LAKEHURST, NJ 08733-5100

**IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:**  
Defense Standardization Program Office (DLSC-LM)  
8725 John J. Kingman Road, Suite 2533  
Fort Belvoir, Virginia 22060-6221  
Telephone (703) 767-6888 DSN 427-6888