

MIL-B-5687D
Amendment 1
6 Apr 88

MILITARY SPECIFICATION

BEARINGS, SLEEVE, WASHERS, THRUST, SINTERED, METAL POWDER, OIL-IMPREGNATED, GENERAL SPECIFICATION FOR

This amendment forms a part of Military Specification MIL-B-5687D, dated 21 February 1984, and is approved for use by all Departments and Agencies of the Department of Defense..

PAGE 4

Table 1, Under Element change carbon to read "Carbon, Max"

PAGE 6

Add:

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

Change: Existing 4.1.1 Records to read 4.1.2 Records

PAGE 9

4.6.2.4, Delete and substitute:

4.6.2.4 Oil excretion. The bearings shall be heated in an oven or other suitable means. The temperature shall not exceed 300°F (149°C) and be held for a period of not more than 5 minutes. During the period, an oil film or beads shall exude uniformly from the bearing surface (See 3.6).

FSC 3120

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Custodians:

Army - AT
Navy - OS
Air Force - 99

Preparing activity:

Air Force - 84

(Project 3120-0594)

Review activities:

Army - AR, MI
Navy - AS, OS
Air Force - 11
DLA - IS, CS
NSA - NS

Agent:

DLS - IS