

MIL-C-82255A(SA)

16 March 1978

SUPERSEDING

MIL-C-82255(NAVY)

30 December 1964

## MILITARY SPECIFICATION

## CLOTH, COATED, SYNTHETIC RUBBER (NITRILE AND POLYCHLOROPRENE)

This specification is approved for use by the Naval Supply Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

\* 1.1 Scope This specification covers the requirements for four types of synthetic rubber coated cloth.

1.2 Classification The cloth, coated equally on both sides, shall be of the following types:

- Type I - Cloth, nylon, flat knit, chloroprene coated
- Type II - Cloth, cotton, duck, chloroprene coated
- Type III - Cloth, cotton, duck, nitrile coated
- Type IV - Cloth, cotton, airplane, chloroprene coated

## 2. APPLICABLE DOCUMENTS

\* 2.1 Issues of documents The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein.

## SPECIFICATIONS

## FEDERAL

- CCC-C-419 - Cloth, Duck, Cotton, Unbleached, Plied-yarns,  
Army and Numbered
- PPP-P-1136 - Packaging and Packing of Coated (Plastic; Rubber)  
and Laminated Fabrics)

---

Beneficial comments recommendations, additions, deletions and any pertinent data which may be of use in improving this document should be addressed to: Officer in Charge, Navy Clothing & Textile Research Facility, 21 Strathmore Road, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

---

FSC 8305

MIL-C-82255A(SA)

MILITARY

MIL-C-5646 - Cloth, Airplane

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods  
FED-STD-595 - Colors

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection  
by Attributes  
MIL-STD-1487 - Glossary of Cloth Coating Imperfections

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

\* 2.2 Other publications The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to American Trucking Associations, ATTN: Tariff Order Section, 1616 P Street, NW, Washington, DC 20036.)

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606.)

3. REQUIREMENTS

\* 3.1 Standard sample When a standard sample is available, the finished coated cloth shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

\* 3.2 First article When specified, the contractor shall furnish a sample unit(s) for first article approval (see 6.2).

3.3 Materials

MILC82255A(SA)

### 3.3.1 Base fabrics:

3.3.1.1 Cloth, nylon, knitted The base fabric for type I material shall be a plain flat knit nylon and shall weigh 5.5 to 7.5 oz/sq. yd. (0.19 to 0.26 Kg/sq. m).

\* 3.3.1.2 Cloth, cotton duck The base fabric for types II and III materials shall be cloth, cotton duck conforming to type I, No. 10, hard texture of CCC-C-419, except that the requirements for air permeability shall not apply.

3.3.1.3 Cloth, cotton, airplane The base fabric for type IV material shall be cloth, cotton, airplane conforming to MIL-C-5646, except that requirements covering length of roll, length of cut, and compatibility with dope shall not apply.

### 3.3.2 Coating compounds

\* 3.3.2.1 Chloroprene The coating used for types I, II and IV coated fabrics shall be chloroprene rubber formulated to conform to the requirements of this specification. No rubber other than chloroprene shall be used with the exception that a maximum of 5.0 percent SBR (Styrene Butadiene Rubber) or natural rubber may be used for masterbatch purposes. The coating shall be pigmented to match Black No. 37038 of FEDSTD595, applied equally to both sides of base fabric, and shall be fully vulcanized.

\* 3.3.2.2 Nitrile The coating used for type III coated fabric shall be nitrile rubber formulated to conform to the requirements of this specification. No rubber other than nitrile shall be used with the exception that a maximum of 5.0 percent SBR (Styrene Butadiene Rubber) or natural rubber may be used for masterbatch purposes. The coating shall be pigmented to match Black No. 37038 of FEDSTD595, applied equally to both sides of base fabric, and shall be fully vulcanized.

### 3.3.3 Finish

\* 3.3.3.1 Dust When specified, dusting powder shall be whiting, talc, or other finely divided mineral material that does not support mildew growth, except that when blocking of coated surfaces during processing is not a serious problem, the use of zinc stearate is permitted. In order to acquire the cleanest finish possible, only the minimum amount of dusting powder necessary to prevent blocking should be applied.

\* 3.3.3.2 Topcoat When specified, a thin lacquer or rubber base topcoat shall be used as a finish coat. The topcoat must be flexible, tack-free, nonstiffening, mildew resistant, weather resistant, and completely compatible with the chloroprene or nitrile coating compounds.

MIL-C-82255A(SA)

\* 3.4 Physical requirements The coated fabrics, after vulcanization, shall conform to the requirements listed in table I when tested as specified in 4.4.

Table I - Physical requirements

| Characteristic                         | Type I  |        | Type II |        | Type III |        | Type IV |        |
|--|---------|--------|---------|--------|----------|--------|---------|--------|
|  | Min     | Max.   | Min.    | Max.   | Min.     | Max    | Min.    | Max.   |
| Thickness, inch                        | -       | 0.021  | 0.047   | 0.053  | 0.038    | 0.062  | 0.023   | 0.027  |
| (mm)                                   | -       | (0.53) | (1.19)  | (1.35) | (0.97)   | (1.57) | (0.58)  | (0.69) |
| Weight, oz/sq yd                       | -       | 19.0   | 49.0    | 59.0   | -        | 43.0   | 24.0    | 29.0   |
| (Kg/sq.m)                              | -       | (0.65) | (1.67)  | (2.00) | -        | (1.46) | (0.82)  | (0.99) |
| Breaking strength, lbs<br>(N)          |         |        |         |        |          |        |         |        |
| Warp                                   | 100     | -      | 245     | -      | 245      | -      | 90      | -      |
|  | (445)   |        | (1090)  |        | (1090)   |        | (400)   |        |
| Filling                                | 100     | -      | 160     | -      | 160      | -      | 90      | -      |
|  | (445)   |        | (712)   |        | (712)    |        | (400)   |        |
| Tearing strength, grams                |         |        |         |        |          |        |         |        |
| Warp                                   | 4500    | 1/     | 4000    | -      | 4200     | -      | 900     | -      |
| Filling                                | 4500-   |        | 2500    | -      | 3000     | -      | 800     | -      |
| Hydrostatic resistance,<br>psi (Pa) 2/ |         |        |         |        |          |        |         |        |
| Initial                                | 70      | -      | 250     | -      | 250      | -      | 150     | -      |
| After 100 hrs<br>Weatherometer 3/      | 65      | -      | 250     | -      | 200      | -      | 150     | -      |
| Adhesion of coating                    |         |        |         |        |          |        |         |        |
| Lbs/2 inch width<br>(N/5cm)            | 10      | -      | 10      | -      | 10       | -      | 10      | -      |
|  | (25.4)- |        | (25.4)- |        | (25.4)-  |        | (25.4)  | -      |
| Blocking (scale rating)                |         | No. 3  |         | No.3   |          | No.3   |         | No. 3  |

1/ Tear test for type I material shall be conducted in accordance with Test Method 5136 of FED-STD-191 and the result reported in grams.

2/ For metric conversion multiply pounds per square inch by 6894.0 to obtain pascals.

3/ After subjection to weathering, but prior to hydrostatic, the test specimens shall be examined visually for deterioration. There shall be no signs of cracking, blistering, excessive stiffening or delamination of coating from base fabric.

MIL-C-82255A(SA)

\* 3.4.1 Color matching When dusting powder has been used as a finish the dust shall be removed from the vulcanized sample with a wet cloth and the sample allowed to dry before color matching.

\* 3.5 Width All selvages of the coated fabric shall be trimmed. The finished trimmed width shall be as specified (see 6.2).

3.6 Length and put-up The coated fabric shall be put-up on rolls as specified in PPP-P-1136. The length of the rolls shall be as specified in Table II. Each roll shall contain not more than three (3) pieces and no piece shall be less than ten (10) yards. Splices (seams) in the coated fabric are not permitted in shipping rolls.

Table II - Length of rolls (maximum linear yards)

|          |   |                  |
|----------|---|------------------|
| Type I   | - | 90 yards, linear |
| Type II  | - | 30               |
| Type III | - | 40               |
| Type IV  | - | 50               |

3.7 Workmanship The finished coated fabric shall be clean, evenly coated, and shall conform to the quality of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels.

#### 4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection Unless otherwise specified in the contract the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 First article approval When required, the first article, submitted in accordance with 3.2, shall be inspected for finish, color and overall appearance and shall be tested for physical properties in accordance with test methods specified in 4.4.

4.3 Inspection Sampling for inspection shall be in accordance with MIL-STD-105, except where otherwise indicated herein.

## MIL-C-82255A(SA)

4.3.1 Component and material inspection In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all requirements of referenced specifications and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document. In addition, a certificate of compliance shall be submitted and will be acceptable for the base fabric requirements of 3.3.1, the coating compounds of 3.3.2, and the finish requirements of 3.3.3.

4.3.2 Examination of the end item Defects found during the examination shall be classified as specified in 4.3.2.1 thru 4.3.2.4. Definitions of coated fabric defects applicable to this specification are described in MIL-STD-1487.

4.3.2.1 Yard-by-yard examination The required yardage of each roll shall be examined on one side only; however, the side to be examined shall be alternated in every other roll. The defects listed below shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the coated cloth, in which case only the more serious defects shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The unit of product for this examination shall be one linear yard. The inspection level shall be level II of MIL-STD-105. The acceptable quality level shall be 1.0 for major defects and 4.0 for total defects per 100 units. The number of rolls selected for this examination shall be in accordance with Table III. An approximate equal number of yards shall be examined from each roll in the sample.

| Defects   | Classification |       |
|---|----------------|-------|
|   | Major          | Minor |
| 1. Any cut, hole, tear or uncoated area   | X              |       |
| 2. Any scratch or scuff mark resulting in a weak place or coating removal <u>1/</u>                           | X              |       |
| 3. Any blister or lump:   |                |       |
| a. hollow   | X              |       |
| b. solid  |                | X     |
| 4. Any permanent crease or wrinkle:   |                |       |
| a. Adhesion of surfaces   | X              |       |
| b. No adhesion of surfaces  |                | X     |
| 5. Any separation of coating from base cloth  | X              |       |
| 6. Permanent stain, streak or other blemish - one inch (2.5cm) or more in combined directions                 |                | X     |
| 7. Impression in coating resulting from seamed splicing   |                | X     |
| 8. Any thinly coated area evidenced by light area or window - one inch (2.5cm) or more in combined directions |                | X     |

MIL-C 92255A(SA)

| Defects  | Classification |       |
|--|----------------|-------|
|  | Major          | Minor |
| 9. Any scorched area   | X              |       |
| 10. Embedded foreign matter, affecting appearance or serviceability: |                |       |
| a. Seriously   | X              |       |
| b. Not seriously   |                | X     |
| <hr/>  |                |       |
| 1/ Clearly visible at normal inspection distance of 3 feet.          |                |       |

4.3 2.2 Overall examination Each defect listed shall be counted not more than once in each roll examined. The sample unit for this examination shall be one roll. The sample size (number of rolls selected as sample) for this examination and the acceptance numbers shall be as listed in table III.

#### Defects

Objectionable odor (odors of chemicals commonly used in coating compounds shall not be regarded as objectionable)  
Width below minimum specified  
Uneven coating  
Excessive dusting powder  
Not fully cured  
Overall uncleanness  
Color not as specified, off shade, not uniform, mottled, blotchy  
Tackiness (coating adheres to opposite surface upon unrolling)  
Puckering, waviness, dimensional distortion (material does not lie uniformly flat along its entire width when no tension is applied)  
Selvages not trimmed  
Trimmed edges curled, folded over, not straight, scalloped

Table II - Sample sizes and acceptance numbers for yard-by-yard and overall examinations

| Lot size in yards  | Sample size in rolls | Acceptance No. |
|--------------------|----------------------|----------------|
| Up to 1,200 1/     | 3                    | 0              |
| 1,201 thru 3,200   | 5                    | 0              |
| 3,201 thru 10,000  | 8                    | 0              |
| 10,001 thru 35,000 | 13                   | 0              |
| 35,001 and up      | 20                   | 0              |

1/ If a lot contains fewer than 3 rolls, each roll in lot shall be examined.

## MIL-C-82255A(SA)

4.3.2.3 Examination for length of individual rolls The individual roll shall be examined for length and the number of pieces in the roll. Any length found to be more than 2 yards below the length marked on the ticket or any roll found to contain more than three pieces, or any one piece less than 10 yards in length, shall be considered a defect with respect to length. The unit of product for this examination shall be one roll. The sample size for this examination and the acceptance number shall be as listed in Table III.

4.3.2.4 Examination for total yardage in sample The lot shall be unacceptable if the total of the actual lengths of pieces in the sample is less than the total of the lengths marked on piece tickets.

4.3.3 Examination of delivery requirements Examination shall be made in accordance with the provisions of PPP-P-1136 to determine that the packaging, packing, and marking requirements of Section 5 are complied with.

4.4 Testing of the end item The methods of testing specified in FED-STD-191, wherever applicable, and as listed in Table IV shall be followed. The physical values specified apply to the average of the determinations made on a unit of product for test purposes as specified in the applicable test method. The sample unit for test purposes shall be 2 yards full width of coated cloth. The lot size shall be expressed in units of 1 yard. The lot shall be unacceptable if one or more units fail to meet any requirement specified.

| <u>Lot size (yards)</u> | <u>Sample size</u> |
|-------------------------|--------------------|
| 800 or less             | 2                  |
| 801 thru 22,000         | 3                  |
| 22,001 and up           | 5                  |

Table IV - Instructions for testing

| Characteristic                              | Requirement paragraph | Test method |
|---|-----------------------|-------------|
| Weight                                      | Table I               | 5041        |
| Thickness                                   | Table I               | 5030        |
| Breaking strength<br>(Types I, II, III, IV) |                       |             |
| Warp  | Table I               | 5100        |
| Filling                                     | Table I               | 5100        |



MIL-C-82255A(SA)

Table IV - Instruction for testing (cont'd)

| Characteristic                             | Requirement paragraph | Test method    |
|--|-----------------------|----------------|
| Tearing strength<br>(Types II, III and IV) |                       |                |
| Warp                                       | Table I               | 5132           |
| Filling                                    | Table I               | 5132           |
| Hydrostatic                                |                       |                |
| Initial                                    | Table I               | 5512           |
| After 100 hrs.<br>weatherometer            | Table I               | 5804 and 5512  |
| Adhesion of coating                        | Table I               | 5970 <u>1/</u> |
| Blocking                                   | Table I               | 5872           |

1/ If the coating can be separated from the base cloth of the test specimen, without the aid of a solvent or adhesive, the coating may be peeled off dry.

## 5. PACKAGING

5.1 Preservation-packaging Packaging shall be level A or C as specified (see 6.2).

5.1.1 Levels A and C The coated cloth, put up as specified (see 3.6), shall be packaged in accordance with the applicable requirements of PPP-P-1136.

5.2 Packing Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Levels A, B and C The coated cloth shall be packed in accordance with the applicable requirements of PPP-P-1136.

5.3 Marking In addition to any special marking required in the contract or order, shipments shall be marked in accordance with the applicable requirements of PPP-P-1136.

## 6. NOTES

6.1 Intended use The coated fabrics are intended for use in manufacturing various types of interior and exterior protective coverings (tarpaulins, awnings, shelters, welding curtains, etc.).

MIL-C-82255A(SA)

6.2 Ordering data Procurement documents should specify the following:

- a. Title, number and date of this specification
- b. Type required (see 1.2)
- c. Availability of standard sample (3.1)
- d. First article requirements (3.2)
- e. Type of finish required (see 3.3.3)
- f. Width of cloth required (see 3.5)
- g. Length required if other than specified (see 3.6)
- h. Selection of applicable levels of packaging and packing (see 5.1 and 5.2)

6.3 Samples To determine availability of standard sample address the procuring office issuing the invitation for bids (see 3.1).

6.4 Changes from previous issue The margins of this specification are marked with an asterisk to indicate where changes (additions, modification, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodian:  
Navy - SA

Preparing activity:  
Navy - SA

User activity:  
Navy - SH

Project No. 8305-N575

**FOLD**

---

OFFICER IN CHARGE  
NAVY CLOTHING & TEXTILE RESEARCH FACILITY  
21 STRATHMORE ROAD  
NATICK, MA 01760

POSTAGE AND FEES PAID  
DEPARTMENT OF THE NAVY  
DoD-316



**OFFICIAL BUSINESS**  
PENALTY FOR PRIVATE USE \$300

OFFICER IN CHARGE  
NAVY CLOTHING AND TEXTILE RESEARCH FACILITY  
21 STRATHMORE ROAD  
NATICK, MA 01760

---

**FOLD**

| STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL   |  |
|---|--|
| <p><b>INSTRUCTIONS</b> This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.</p> <p><b>NOTE</b> This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.</p> |  |
| DOCUMENT IDENTIFIER (Number) AND TITLE  |  |
| MIL-C-82255A(SA) CLOTH, COATED, SYNTHETIC RUBBER (NITRILE AND POLYCHLOROPRENE)  |  |
| NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER   |  |
| <input type="checkbox"/> VENDOR <input type="checkbox"/> USER <input type="checkbox"/> MANUFACTURER   |  |
| 1 <input type="checkbox"/> HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? <input type="checkbox"/> IS ANY PART OF IT TOO RIGID RESTRICTIVE LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW   |  |
| A GIVE PARAGRAPH NUMBER AND WORDING   |  |
| B RECOMMENDED WORDING CHANGE  |  |
| C REASON FOR RECOMMENDED CHANGE(S)  |  |
| 2 REMARKS   |  |
| SUBMITTED BY (Printed or typed name and address - Optional)   |  |
| TELEPHONE NO  |  |
| DATE  |  |

DD FORM 1426  
1 OCT 76

Replaces edition of 1 Jan 72 which may be used

S/N 0102-LF-001-4260