

MILITARY SPECIFICATION

CLOTH, KNIT, JERSEY, ARAMID

This amendment forms a part of MIL-C-85636(AS), dated 27 July 1984, and is approved for use within Naval Air Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

3.7, add to the end of the paragraph: "(see 6.2.1)"

PAGE 5

4.6, line 9, delete, "one or more units fail" and substitute "one or more sample units fail".

6.2.1, add:

"f. Length and put up requirements if different from standard (see 3.7)".

PAGE 7

Table I, delete and substitute:

TABLE I. Physical properties

<u>Characteristics</u>	<u>Requirements</u>
Weight, ounces per square yard	1.6 ± 0.4
Wales per inch (minimum)	28
Courses per inch (minimum)	31
Type of knit	Jersey
pH	5.0 - 8.0 <u>1/</u>

1/ Determined on the water extract of the cloth

AMSC N/A

FSC 8305

DISTRIBUTION STATEMENT A, Approved for public release; distribution is unlimited.

MIL-C-85636(AS)

PAGE 10

Table V, delete and substitute:

TABLE V Test methods

<u>Characteristic</u>	<u>FED-STD-191 Test Method</u>
Denier per filament	1/
Twist	1/
Cut length of filament	1/
Material identification	1/
Weight	5041
Wales per inch	5070
Courses per inch	5070
pH	2811

1/ Unless otherwise specified, a certificate of compliance may be submitted for the stated requirements.

Preparing Activity
Navy - AS
(Project No. 8305-N113)