

INCH-POUND

*

MIL-DTL-6070C
24 February 1997
 SUPERSEDING
 MIL-P-6070B
 24 FEB. 1986

DETAIL SPECIFICATION

PLYWOOD AND VENEER, AIRCRAFT FLAT PANEL

*

Inactive for new design after 24 February 1997
 For new design use Commercial Item Description A-A-55057, Type C,
 Panels, Wood/Wood Based; Construction and Decorative or HPVA HP-1
 Voluntary Standard for Hardwood and Decorative Plywood

This specification is approved for use by all Departments
 and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers aircraft flat panel plywood and veneer.

1.2 Classification. Aircraft plywood will be furnished in one grade only in the species and of the panel construction as selected from Tables I, II or III.

2. APPLICABLE DOCUMENTS

2.1 Government Documents.

*

2.1.1 Specifications, standards, and handbooks. The following specification, standards and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specification and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2)

SPECIFICATIONS

FEDERAL

MMM-A-181 - Adhesive, Room Temperature and Intermediate-Temperature Setting Resin (Phenol, Resorcinol, and Melamine Base)

A-A-55057 - Panels, Wood/Wood Based; Construction and Decorative

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Industrial Supply Center, ATTN: DISC-ECA 700 Robbins Ave., Philadelphia, PA 19111-5096, by letter or the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document.

AMSC N/A

FSC 5530

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

MIL-DTL-6070C

STANDARDS

DEPARTMENT OF DEFENSE

MIL-STD-129 - Marking for Shipment and Storage

(Unless otherwise indicated, copies of the above specifications, standards, and handbooks are available from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5096).

2.1.2 Other Government documents, drawings and publications. The following other Government documents, drawings and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

National Bureau of Standards Publications

Product Standard PS-1 - Construction and Industrial Plywood

(Application for copies should be addressed to the superintendent of Documents, Government Printing Office, Washington, DC 20402).

- * 2.2 Non-Government publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted will be those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issue of the documents cited in the solicitation (see 6.2).

American National Standards Institute/American Society for Quality Control

ANSI/ASQC Z1.4 - Sampling Procedures and Tables for Inspection by Attributes

(Application for copies should be addressed to the American Society For Quality Control, 611 East Wisconsin Ave., Milwaukee, Wisconsin 53202)

American Society for Testing Materials

ASTM D2395 - Specific Gravity of Wood-Based Materials

ASTM D906 - Test Methods for Strength Properties of Adhesives in Plywood Type Construction in Shear by Tension Loading

ASTM D1151 - Test Method for Testing for Effect of Moisture and Temperature on Adhesive Bonds

ASTM D3953 - Standard Specification for Strapping, Flat Steel, and Seals

(Application for copies should be addressed to the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959)

Hardwood Plywood and Veneer Association

HPVA HP-1 - Voluntary Standard for Hardwood and Decorative Plywood

(Application for copies should be addressed to Hardwood Plywood and Veneer Association, 1825 Michael Faraday Drive, P. O. Box 2789, Reston, VA 22090-0789).

MIL-DTL-6070C

American Trucking Associations, Inc.

National Motor Freight Classification Rules

(Application for copies should be addressed to the American Trucking Association, Inc. 1616 "P" Street, N.W., Washington DC 20036.)

Uniform Classification Committee.

Uniform Freight Classification Rules

(Application for copies should be addressed to the Uniform Classification Committee, 202 Union Station, 516 W. Jackson Blvd., Chicago IL 60606.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

- * 3.1 Species of Wood. The species of wood given by Table I and as specified (see 6.2) in the contract shall be used in aircraft flat panel plywood construction.

3.1.1 Recycled, recovered, or environmentally preferable materials. Recycled, recovered, or environmentally preferable materials should be used to the maximum extent possible provided that the material meets or exceeds the operational and maintenance requirements, and promotes economically advantageous life cycle costs.

- * 3.2 Adhesives. The adhesives used in the manufacture of the plywood shall be of the thermosetting, phenol formaldehyde, melamine formaldehyde, or resorcinol formaldehyde types conforming to MMM-A-181. Application of these adhesives shall be accomplished in hot plate presses to produce joints of uniform quality. Thermosetting Type I emulsion polymer isocyanate adhesives are also acceptable; application of these adhesives can be accomplished in either hot or cold presses (in accordance with the manufacturer's recommendations) to produce joints of uniform quality.

3.3 Veneer. The veneer may be rotary cut, sliced, or sawed except as otherwise specified in Table I.

- * 3.3.1 Thickness of veneer. Thickness of veneer shall be within the tolerances shown in Table II. These thickness' and tolerance apply when the veneer has a moisture content of 8 to 12 percent, inclusive.

3.3.2 Specific gravity. Average specific gravity of all samples from any one crate, stack, flitch, or bolt shall not be less than the minimum specified in Table I, and the average specific gravity of any one sheet of veneer shall not be less than the minimum specified in Table I.

3.4 Defects.

3.4.1 Veneer Defects. Veneer containing the following defects is not acceptable:

- a. Brash Wood
- b. Pronounced Compression Wood (Present in coniferous species only)
- c. Shakes
- d. Compression Failure
- e. Patching in any form
- f. Dote or any other form of decay (mineral streaks, stains, and colorations shall not be considered as defects unless associated with decay).

MIL-DTL-6070C

TABLE I

Group I (High Density)		Group II (Medium Density)		Group III (Low Density)	
Species	Minimum Specific Gravity (1)	Species	Minimum Specific Gravity (1)	Species	Minimum Specific Gravity (1)
American Beech	0.60	Birch (Alaska and Paper)	0.53	Basswood.	0.36
Birch (Sweet and Yellow)	0.58	Khaya (African Mahogany)	0.42	Yellowpoplar.	0.38
Pecan	0.62	Magnolia (Southern)	0.48	Port Orford White Cedar	0.40
Maple (Hard) .	0.60	Mahogany (Tropical American)	0.46	Spruce (Red and Sitka) (Quarter Sliced)	0.36
		Maple, Soft	0.46	Sugar Pine	0.34
		Sweetgum	0.48	Noble Fir (Quarter Sliced)	0.36
		Water-Tupelo	0.47	Western Hemlock (Quarter Sliced)	0.40
		Black Walnut	0.52	Redwood (Quarter Sliced)	0.38
		Douglas Fir #1 (Quarter-Sliced)	0.45	Douglas Fir #2 (Quarter Sliced)	0.38
		American Elm (Quarter Sliced)	0.50	Ponderosa Pine (Quarter Sliced)	0.38
		Sycamore	0.49		

Note: (1) Specific gravity based on weight and volume when oven dry.

3.4.2 Permissible open defects. The face ply shall be free of open defects to provide a smooth finish surface. The inner plies and back may have the same permissible defects as the face, and in addition, open defects as herein after specified. Permissible defects may appear singly as one type only or as a combination of more than one type. When more than one type of defect is present, their total limitation, computed according to the equivalent defects given below, shall not exceed the limit specified for any one type. When defects other than those specified, or concentration of defects, are encountered, they are permitted provided their damaging effect is not more critical than those specified herein. The following shall be regarded with respect to their effect as the equivalent of one 3/8 inch sound knot:

- One 3/8 inch knot hole.
- One 3/4 inch sound tight burl.
- One insect hole 2 inches in length that cuts across the grain 3/8 inch.
- One pitch pocket, with the product of length and width equal to 1/4 square inch.
- One split 8 inches in length and 1/32 inch in width.

3.4.3 Defects in face plies. Permissible defects in face plies shall not exceed the limitations specified herein.

3.4.3.1 Sound tight knots. No single Knot shall exceed 3/8 inch in average diameter. The total number of sound tight knots in face plies shall not be more than six in any 12 inch square, and the sum of the knot diameters in any 12 inch square shall not exceed 3/4 inch.

3.4.3.2 Sound tight burls. No single burl shall exceed 3/4 inch in average diameter. The total number of sound tight burls in face plies shall be not more than six in any 12 inch square, and the sum of the diameters in any 12 inch square shall not exceed 1-1/2 inches.

MIL-DTL-6070C

3.4.3.3 Mild compression wood. Streaks of mild forms of compression wood in face plies shall not aggregate more than 10 percent of the width of the panel and shall in no case be wider than 1/2 inch.

3.4.4 Defect in inner plies and back. The following defects, in addition to those permitted in the face, are acceptable in the inner plies and back.

3.4.4.1 Knot holes. No single knot hole shall exceed 3/8 inch in average diameter. The total number of knot holes shall be not more than six in any 12 inch square and the sum of the diameters in any 12 inch square shall not exceed 3/4 inch.

3.4.4.2 Insect holes. No single hole shall exceed 2 inches in length along the grain, 1/8 inch diameter, nor cut across the grain more than 3/8 inch. The total number of insect holes shall be no more than six in any 12 inch square and the sum of the lengths across the grain shall not exceed 3/4 inch.

3.4.4.3 Pitch pockets and bark pockets. The Product of the length and width of any pitch or bark pocket shall be not more than one fourth square inch. The total number of pitch or bark pockets in any 12 inch square shall be not more than six, and the sum of the pockets shall not exceed one half inch. Pockets shall be not be closer than 24 inches on the same or adjacent grain lines.

3.4.4.4 Splits. Splits shall be no more than 1/32 inch in width and shall not occur more frequently than twice in any 12 inches measured perpendicular to the grain of the ply in question. The length of a split in any ply shall not exceed ten percent of the distance between the edges of a panel as measured along a line parallel to the grain of that ply and passing through the split.

3.5 Straightness of grain. In at least 90% of the area of each sheet of veneer, the slope of the grain from the edge of the sheet shall not be greater than 1 in 10. When both spiral and diagonal grain are present, the combined slope shall be determined by taking the square root of the sum of the squares of the slopes of the two types of cross grains. When the slope of the grain cannot be determined using the methods specified herein, the veneer shall withstand mandrel bending tests, described in paragraph 4.6, at ratios of radius of curvature to thickness as specified in Table IV with breakage of not more than 20 percent of the specimens.

3.6 Thickness tolerance.

3.6.1 Veneer thickness. The allowable tolerances for veneer are given in Table II. The thickness of any sheet shall be considered as the average of ten or more measurements taken on the sheet.

3.6.2 Plywood Thickness. The allowable thickness and tolerances for plywood are given in Table III. The thickness of any sheet shall be considered as the average of ten or more measurements taken on the sheet.

3.7 Thickness. Unless otherwise specified (see 6.2), the thickness of individual plies, the number of plies, and the thickness of the plywood shall be as stated in Table III. All veneer of any one layer shall be of the same thickness.

3.8 Construction. All plies except the core of the center ply shall occur in pairs, be of the same species, thickness and direction of grain, and on opposite sides of the core, to give symmetrical construction. Except as otherwise specified, in Table III footnote 2, all inner plies shall be of one species. In all panels of nine plies or more the two outside plies on each side shall be of the same species and of the thickness specified in Table III. Unless otherwise specified (see 6.2), the grain of all plies shall be at right angles to the grain of adjacent plies and to the edges of the plywood.

MIL-DTL-6070C

TABLE II. Veneer Thickness and Tolerances (8 to 12 Percent Moisture Content).

Veneer Thickness Inch	Tolerances Inch
0.011	$\pm .001$
0.020	$\pm .002$
0.030	$\pm .002$
0.034	$\pm .003$
0.040	$\pm .003$
0.047	$\pm .003$
0.060	$\pm .003$
0.068	$\pm .004$
0.080	$\pm .004$
0.095	$\pm .004$

TABLE III. Permissible Panel Construction.

Number of Plies	Plywood Thickness and Tolerances in Inches	Thickness of Plies in Inches (8-12 Percent Moisture Content)								
		Group I or II Faces with Group II Inner Plies			All Group I or All Group II			All Group III		
		F&B	XB	C	F&B	XB	C	F&B	XB	C
					<u>1/</u>					
3	.035 $\pm .004$	--	--	--	.011	--	.011	--	--	--
3	.070 $\pm .007$.020		.030	.020		.030	.020		.034
3	.100 $\pm .008$.030		.040	.030		.040	.030		.047
3	.125 $\pm .010$.034		.060	.034		.060	.034		.068
3	.155 $\pm .011$.040		.080	.040		.080	.040		.080
3	.185 $\pm .012$.047		.095	.047		.095	.047		.095
5	.160 $\pm .012$.030	.034	.030	.030	.034	.030	.030	.034	.030
5	.190 $\pm .015$.034	.047	.034	.034	.047	.030	.034	.047	.034
5	.225 $\pm .015$.040	.060	.030	.040	.060	.030	.040	.060	.034
5	.250 $\pm .015$.047	.060	.047	.047	.060	.047	.047	.060	.047
5	.315 $\pm .015$.060	.080	.047	.060	.080	.040	.060	.080	.047
5	.375 $\pm .018$.060	.095	.080	.060	.095	.080	.060	.095	.080
7	.410 $\pm .020$	All Plies								.060
7	.460 $\pm .022$	All Plies								.068
7	.540 $\pm .023$	All Plies								.080
9	.590 $\pm .025$	All Plies								.068 <u>2/</u>
9	.695 $\pm .028$	All Plies								.080 <u>2/</u>
11	.085 $\pm .035$	All Plies								.080 <u>2/</u>
11	1.010 $\pm .035$	All Plies								.095 <u>2/</u>

NOTES: 1/ All plies of 0.035 inch plywood must be of Group I species.2/ Faces, backs, and outer cross-bands of plywood having nine or more plies must be of the same species.

CODE: F&B = Face and Back; XB = Cross Bands; C = Core

MIL-DTL-6070C

3.9 Panel size. Unless otherwise specified (see 6.2), the nominal width and length shall be 48 by 96 inch panels.

3.10 Panel trimming. Trimming for length and width shall be full and true. A tolerance of plus 1/4 inch will be allowed in length and width of panels. Panels exceeding 35 inches in width or 59 inches in length may be reduced 6 inches in either or both length or width to eliminate defects which may occur on the edge of the panels. The number of panels thus altered shall not exceed 5 percent of the total number of panels of any lot or shipment.

3.11 Surfaces. Plywood shall be smooth, flat, and free from blisters, wrinkles, laps and other defects not specifically permitted. The surfaces of the finished plywood shall be free from glue, oil, wax, paraffin, tape, or any other substances that will prevent the adhesion of glue or paint finishes. Spot sanding that results in no appreciable change in thickness may be permitted with other limitation. Otherwise if panels are sanded, sanding shall be accomplished on both sides. Sanding shall not reduce the thickness of the face plies by more than 5 percent of their normal thickness.

3.12 Joints.

3.12.1 Edge joints. Plywood shall have all plies either of one-piece veneer or of two or more pieces, properly glued on the edges. Joints shall run parallel with the grain of the pieces. Edges of the pieces of veneer shall be jointed straight and square and shall be glued with a water resistant glue. No metal staples or tape shall be used. In plies other than the face, open joints will be permitted provided that the opening in any one joint does not exceed 1/32 inch.

3.12.2 Scarfig. Large plywood panels may be made from two or more smaller panels by scarfing. The slope of scarfs shall not be greater than 1 in 12. The scarfs shall be glued in a hot-press with thermo-setting, synthetic-resin adhesives.

3.13 Moisture content. Moisture content of all veneers, which are to form any one panel, shall not vary more than 3 percent from the minimum to the maximum at the time of gluing. The finished plywood shall be conditioned to a moisture content of not less than 8 percent nor more than 12 percent.

3.14 Shearing strength. Specimens shall be subjected to shear tests described in section 4. The test specimens shall not show delamination or separation at the bond lines before testing or during the boiling period. When the test specimens have an average shear strength of less than 250 psi, they shall show not less than 30 percent minimum and 60 percent average wood failure. When the test specimens have an average shear strength ranging from 250 to 400 psi, they will show not less than 15 percent minimum and 30 percent average wood failure. Specimens having shear strength greater than 400 psi, no wood failure shall be required.

3.15 Exterior type heat durability. When tested as specified in 4.6.5 the plywood shall show no glue-line delamination due to combustion.

3.16 Identification. Each sheet of plywood shall have marked on the face with suitable light-fast, durable non-bleeding marking fluid, in letters not less than 1/4 inch high with the following data:

Nomenclature
 Manufacturers Name
 Number of Plies
 Panel Thickness
 Species of Face
 Species of Inner Plies
 Contract Number
 Federal Stock Number
 US

MIL-DTL-6070C

3.17 Workmanship. All details of workmanship shall be in accordance with high grade aircraft plywood manufacturing practice for flatness, smoothness, uniformity of thickness, and tightness of cut prevailing among manufacturers normally producing aircraft flat panel plywood and veneer specified herein.

4. VERIFICATION

4.1 Quality conformance inspection. Quality conformance inspection shall be applied as specified to plywood and veneer prior to being offered for acceptance under the contract. Failure of the plywood and veneer to pass the examination or one or more tests shall be cause for rejection. Unless otherwise specified (see 6.2), quality conformance inspection shall consist of the following:

- a. Examination (4.4)
- b. Tests (4.5)
- c. Inspection of preparation for delivery (4.6)

4.2 Inspection lot. A lot shall consist of all aircraft flat panel plywood of the same material size, thickness, and number of plies offered for delivery to the Government at one time.

4.3 Sampling.

4.3.1 Sampling for examination. All veneer and finished aircraft plywood in any lot or shipment shall be examined.

4.3.2 Sampling for straightness of grain. Each sheet of veneer shall be inspected visually. If mandrel bending tests are made (see 3.5), the number of sheets to be tested shall be not less than one sheet from each flitch or five sheets from each crate or stack of veneer shall be selected. From each sheet of veneer selected for tests, bending specimens shall be cut from the entire width within 24 inches of each end, and at intervals not to exceed 6 feet along the length of the sheet in such a way that the specimens shall include representative proportions of any areas in which slope of grain is greater than 1 in 10. When both spiral and diagonal grain are present, the slope of the grain shall be determined in accordance with 3.5.

4.3.2.2 Sampling for specific gravity tests. Samples shall be selected from each crate, stack, bolt, or flitch from which veneer is used. If taken after the veneer is cut, each crate or stack shall be represented by not less than 20 specimens. The samples shall be taken from at least 4 sheets, and the specimens shall be from areas uniformly distributed over selected sheet of veneer. If samples are taken before the veneer is cut, each bolt or flitch shall be represented by not less than 10 specimens. The samples shall be taken from each end of each bolt or flitch.

* 4.3.2.3 Sampling for shear tests on glue joint. A random sample shall be selected in accordance with ANSI/ASQC Z1.4 at inspection level S-1.

* 4.3.2.4 Sampling for determining moisture content. A random sample shall be selected from each inspection lot in accordance with ANSI/ASQC Z1.4 at inspection level S-1.

4.3.3 Sampling for inspection of preparation for delivery. Packaging, packing marking for shipment and storage shall be inspected to determine conformance with the requirements of Section 5. The sample unit shall be one shipping container and the lot size shall be the number of containers offered for delivery at one time. The inspection level shall be S-2 in accordance with ANSI/ASQC Z1.4

4.4 Examination of product. All veneer and finished aircraft plywood shall be examined to determine conformance with the requirements of this specification for workmanship, construction, thickness, straightness of grain, defects, joints, size and finish. Any deviation from these requirements shall be cause for rejection.

MIL-DTL-6070C

4.5 Tests.

4.5.1 Testing straightness of grain. The slope of the grain requirement in 3.5 shall be determined by combining the grain direction of two adjacent faces of a square or rectangular piece. When one or more faces is straight grained, the true slope of the grain is shown on the other face. When there is a slope on both faces, the true or combined slope is greater than the slope on either face. Slope of grain is shown on edge-grained faces by summer-wood bands; by the direction in which a free flowing ink or dye spreads; by the course taken by a narrow strip lifted by a knife point and torn out, or by the Teco or edge slope-grain Detector. Slope of grain from the edge of the sheet may be readily determined in rotary cut veneer by tearing the sheet and measuring the slope of the tear.

4.5.2 Mandrel bending tests. The size of the specimen for mandrel bending tests, when required, (see 3.5), shall be one inch across the grain of the veneer and between nine and eleven inches in length. The ratio of the radius of the mandrel to the thickness of the veneer shall be as specified in Table IV. The specimens shall be cut with the minimum slope of the grain from the edges and shall be oven dry at the time of the test, the tight side of the veneer shall be outward and the open side against the mandrel. The specimens shall be bent at the specified radius to a parallel-sided "U" shape without support on the tension side. Breakage shall consist of fractures extending 1/8 inch or more across the width of the specimen. Tears along the fiber direction that begin at the edge and extend into the specimen along grain sloping from the edge shall not be considered breakage. Whether a specimen breaks shall be determined before removal from the mandrel. Breakage of more than 20 percent of all the specimens tested shall be considered cause for rejection of the flitch, crate, or stack.

Table IV. Ratio of radius (R) of mandrel to thickness (T) of different species for use in mandrel bending tests.

Group of Species			
Thickness of Veneer	Basswood, Soft Maple, Yellowpoplar, Water Tupelo, Sycamore, Mahogany, Khaya	Magnolia, American Elm, Sweetgum, Birch, Alaska and Paper Recan, Black Walnut, Sugar Maple, Yellow Birch, Beech	Douglas-fir, Noble Fir, Western Hemlock, Spruce, White Red and Sitka, Port Orford, White Cedar, Pine Ponderosa, Pine, Sugar
Inches	Ratio R/T		
0.011 and 0.020	46	34	47
0.030	46	34	57
0.034 to 0.047	50	40	57
0.060	55	50	67

4.5.3 Specific gravity tests. Specific gravity of veneer shall be determined in accordance with ASTM D2395. The thickness shall be measured to the nearest 0.001 inch. Specimens may be oven dry at time of test or the weighings may be made at the prevailing moisture contents providing that the proper corrections are made to convert to oven-dry weight and volume for comparison with the values in Table I. If the average specific gravity of the specimens selected is below the minimum specified in Table I, additional specimens, at least 20 from at least 4 additional sheets of veneer or at least 10 from each end of each bolt or flitch, shall be cut and the specific gravity determined. If the average specific gravity of all specimens (original specimens plus additional specimens) is below the minimum specified in Table I, the veneer from that crate, stack, bolt, or flitch shall be rejected. If the average of all determination is above the minimum but the average specific gravities of individual sheets are below the minimum specified in Table I, those individual sheets whose average specific gravity is below the minimum shall be rejected.

MIL-DTL-6070C

4.5.4 Moisture content test. Plywood and veneer shall be tested for compliance with ASTM D2395.

* 4.5.5 Shear tests on glue joints. Dry shear and wet shear tests on glue joints shall be performed in accordance with ASTM D906 and ASTM D1151 to determine compliance with paragraph 3.14. Plywood consisting of more than three plies shall be stripped of all except the three selected for test. Plywood containing seven plies, and over, test shall be made on both the center three plies and either or both of the outer three plies. If shear tests fail to meet either the dry or wet shear requirements, the lot represented shall be rejected or at the option of the manufacturer and with consent of the Government each panel of the lot may be individually tested and rejected or accepted.

* 4.5.6 Heat durability test. One fire test specimen shall be taken at random from any test sample representative of one lot. Testing shall be in accordance with PS 1. If the one specimen fails the test, this shall be cause for rejection of the entire lot.

4.6 Inspection of preparation for delivery. Packaging, packing and marking for shipment shall be examined to determine conformance with Section 5. Defects shall be as indicated in Table V.

Visual Defects, Preparation for Delivery

Examination	Defect
Marking	Omitted; Incorrect; Illegible; Improper size, location or method of application.
Materials	Waster sheets not specified. Component missing or damaged, edge protectors not as specified.
Workmanship	Loose strapping; Incomplete closure blocking and cushioning inadequate or missing; Bulged or distorted container; Plywood not blocked to prevent movement.

5. PACKAGING

* 5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract order (see 6.2). When actual packaging of materiel is to be performed by DoD personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activity within the Military Department or Defense Agency, or within the Military Department's System Command. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

5.2 Marking for shipments. Unless otherwise specified (see 6.2), marking shall conform to MIL-STD-129.

6. NOTES

6.1 Intended use. Plywood covered by this specification is intended for use in the fabrication of structural or highly stressed parts of aircraft, such as; wing and fuselage covering, wing rib webs, etc..

MIL-DTL-6070C

6.2 Ordering data. Procurement documents should specify the following:

- a. Title number and date of this specification.
- b. Species of wood used for faces and inner plies (see 3.1).
- c. Thickness of individual plies, number of plies, and thickness of plywood (see 3.7).
- d. Direction of grain, if different (see 3.8).
- e. Width and length of panels, if different (see 3.9).
- f. Responsibility for inspection, if different (see 4.1).
- g. Quality conformance inspection, if different (see 4.3).
- h. Level of packaging and packing required (see 5.1 and 5.2).
- i. Marking, if different (see 5.3).

6.3 Multiple sizes. Multiple sizes may be furnished under this specification. The number of multiples in size to be furnished should be acceptable to the purchaser and a sufficient excess of material to allow for cutting the panel to the required size or sizes will be provided by the plywood manufacturer.

6.4 Standard sizes. Procurement of aircraft plywood will be expedited and simplified, with less waste of materials and labor on the part of the manufacturer, if the grade, type and construction details, provided for in this specification are followed. Ordering of plywood of large sizes that is later cut to smaller sizes, diagonal grained plywood, veneer of unusual thickness, and more restrictive provisions that herein specified limit the amount of material available and increase the time required for manufacture. Such special requirements should be avoided as much as possible.

6.5 Compression wood. Pronounced compression wood ordinarily has wide annual rings, less than six per inch, and summerwood that lacks definite contrast in appearance with adjacent spring wood. Summerwood of mild compression wood usually occupies less than one-third of the width of the annual rings, and is contrasting and well defined from adjacent springwood.

6.6. Subject term (key word) listing.

Adhesives
 Compression wood
 Flat panel plywood
 Knot hole
 Scarfing
 Veneer

MIL-DTL-6070C

6.7 Changes from previous issue. The margins of this specification are marked with asterisks to indicate where changes from the previous issue were made. This was done as a convenience only and the government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Air Force - 99
Navy - AS

Preparing Activity
DLA - IS

(Project 5530-0060)

Industry Associations
APA - The Engineered Wood Association

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:

1. DOCUMENT NUMBER
MIL-DTL-6070C

2. DOCUMENT DATE (YYMMDD)
970224

3. DOCUMENT TITLE PLYWOOD AND VENEER, AIRCRAFT FLAT PANEL

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)

b. ORGANIZATION

c. ADDRESS (Include Zip Code)

d. TELEPHONE (Include Area Code)
(1) Commercial
(2) AUTOVON
(if applicable)

7. DATE SUBMITTED
(YYMMDD)

8. PREPARING ACTIVITY

a. NAME

b. TELEPHONE Include Area Code)
(1) Commercial
(215) 697-6827

(2) AUTOVON
442-6827

c. ADDRESS (Include Zip Code)

DEFENSE INDUSTRIAL SUPPLY CENTER
ATTN: DISC-ECA, 700 ROBBINS AVENUE,
PHILADELPHIA, PA 19111-5096

IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:
DEFENSE QUALITY AND STANDARDIZATION OFFICE
5203 Leesburg Pike, Suite 1403, Falls Church, VA 22401-3466
Telephone (703) 756-2340 AUTOVON 289-2340