

MIL-E-15090C  
AMENDMENT 2  
25 July 1984  
SUPERSEDING  
AMENDMENT 1  
30 June 1983

MILITARY SPECIFICATION

ENAMEL, EQUIPMENT, LIGHT-GRAY (FORMULA NO. 111)

This amendment forms a part of Military Specification MIL-E-15090C, dated 30 March 1982, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 1

At bottom of page, "Beneficial comments statement", line 3: Delete "SEA 3112" and substitute "SEA 5523".

PAGE 8

- \* Table II, type I, class 2, opposite "Set to touch time, Min": Delete "3" and substitute "----" and opposite "Set to touch time, Max": Delete "----" and substitute "1".

PAGE 12

4.3.2.7: Delete and substitute:

"4.3.2.7 Brittleness and adhesion, types II and III. Test for brittleness and adhesion shall be conducted in accordance with method 6304 of FED-STD-141. The enamel shall be applied to a flat base metal panel to obtain a uniform dry film thickness of  $0.0012 \pm 0.0002$  inch. The film shall be obtained as follows:

Type II - Air dried for 1 hour and baked at 221°F for 24 hours.

Type III - Baked for 30 minutes at 250°F.

Observe whether the film cuts loose in the form of a ribbon without flaking, or otherwise loosening from the panel (see 3.6.3)."

MIL-E-15090C  
AMENDMENT 2

LAST PAGE

DD Form 1426, Standardization Document Improvement Proposal address:  
Delete and substitute:

"COMMANDER  
NAVAL SEA SYSTEMS COMMAND (SEA 5523)  
DEPARTMENT OF THE NAVY  
WASHINGTON, DC 20362"

NOTE: The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodians:  
Army - ME  
Navy - SH  
Air Force - 99

Preparing activity:  
Navy - SH  
(Project 8010-1092)