Downloaded from http://www.everyspec.com

MILITARY SPECIFICATION

Glass, Laminated, Aircraft Glazing

This amendment forms a part of Military Specification MIL-G-25871B, dated 27 November 1978, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.1.2, delete and substitute:

"3.1.2 Interlayer. The material used for interlayer shall be stable without edge sealing and shall have suitable binding characteristics. The material shall be polyvinyl butyral or a suitable high-temperature resistant material, as specified (see 6.2). Unless otherwise specified, polyvinyl butyral, when used, shall be plasticized with either 21.0 ±2 parts by weight of triethylene glycol di-2-ethyl butyrate or 19.0 ±2 parts by weight of di-n-hexyl adipate per 100 parts resin. The laminater's serialized identification number code shall provide traceability as to the type of interlayer used in each laminate (see 6.2). Use of either a different plasticizer or amount of plasticer shall be approved by the procuring activity and specified in applicable drawings, specifications, or in the contract or order."

Custodians:
Air Force - 20
Navy - SH

Review Activity:
DLA-GS

Preparing Activity:
Air Force - 20

(Project 9340-0067)

FSC 9340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.