

MIL-I-23053/3A

~~20 May 1976~~

SUPERSEDING

MIL-I-23053/3

22 March 1968

MILITARY SPECIFICATION SHEET

INSULATION SLEEVING, ELECTRICAL HEAT SHRINKABLE,
POLYVINYL CHLORIDE, SEMI-RIGID, CROSSLINKED AND NON-CROSSLINKED

This specification is approved for use by all Departments
and Agencies of the Department of Defense.

The complete requirements for procuring the sleeving described
herein shall consist of this document and the issue in effect
of MIL-I-23053.

REQUIREMENTS:

Continuous operating temperature range: -20°C (-4°F) to $+105^{\circ}\text{C}$ (221°F).

Classification: The heat shrinkable sleeving shall be furnished in the
following classes, as specified:

Class 1 - Crosslinked


Class 2 - Non-crosslinked

Color: The sleeving shall be furnished in the color specified by the pro-
curing activity and in clear. Colors shall conform to Class I of MIL-STD-104.

Longitudinal change: -10% ⁺¹

A

Military part number: The Military Part Number shall consist of the basic
number of this specification sheet and dash numbers as shown below:



Example: Class 1, red, 0.063 inch as supplied ID sleeving shall be
identified as M23053/3-102-2.

A

denotes changes

FSC 5970

MIL-I-23053/3A

TABLE I. Construction details (inches) 1/

Military Part Number	As supplied	After unrestricted shrinkage	
	I.D. min.	I.D. max.	Wall thickness <u>2/</u>
<u>Class 1</u>			
M23053/3-101-*	.046	.023	.034 + .003
M23053/3-102-*	.063	.031	.034 + .003
M23053/3-103-*	.093	.046	.034 + .003
M23053/3-104-*	.125	.062	.034 + .003
M23053/3-105-*	.187	.093	.034 + .003
M23053/3-106-*	.250	.125	.034 + .003
M23053/3-107-*	.375	.187	.034 + .003
M23053/3-108-*	.500	.250	.034 + .003
<u>Class 2</u>			
M23053/3-201-*	.063	.031	.020 + .003
M23053/3-202-*	.093	.046	.025 + .003
M23053/3-203-*	.125	.062	.025 + .003
M23053/3-204-*	.187	.093	.025 + .003
M23053/3-205-*	.250	.125	.025 + .003
M23053/3-206-*	.312	.156	.025 + .003
M23053/3-207-*	.375	.187	.025 + .003
M23053/3-208-*	.500	.250	.025 + .003
M23053/3-209-*	.750	.375	.025 + .003
M23053/3-210-*	1.000	.500	.030 + .005
M23053/3-211-*	1.500	.750	.035 + .005
M23053/3-212-*	2.000	1.000	.040 + .005

1/ Diameter limits for object to be enclosed shall be as recommended in technical data.

2/ Wall thickness dimensions are less when shrinkage is restricted.

* - The asterisk in the part number shall be replaced by color code designations.

Unrestricted shrinkage: Test method 4.6.5; Class 1, $200 \pm 2^{\circ}\text{C}$ ($392 \pm 4^{\circ}\text{F}$) for 5 minutes; Class 2, $135 \pm 2^{\circ}\text{C}$ ($275 \pm 4^{\circ}\text{F}$) for 5 minutes.

MIL-I-23053/3A

TABLE II. Physical properties 1/

Property	Requirement	Test Procedure and Conditions
<u>As Supplied</u>		
ID, min	Table I	4.6.3
Cold impact	No cracking	4.6.7.2 ASTM D 746, $-10 \pm 2^{\circ}\text{C}$ ($+14 \pm 4^{\circ}\text{F}$)
Heat shock <u>2/</u>	No cracks, flowing or dripping	4.6.8 Class 1: $200 \pm 2^{\circ}\text{C}$ ($392 \pm 4^{\circ}\text{F}$) Class 2: $180 \pm 2^{\circ}\text{C}$ ($356 \pm 4^{\circ}\text{F}$)
Secant modulus, PSI, min	70,000	4.6.13.1 ASTM D 882, 2% strain
Restricted shrinkage	No cracks	4.6.6.1.3 Class 1: $175 \pm 2^{\circ}\text{C}$ ($347 \pm 4^{\circ}\text{F}$) Class 2: $135 \pm 2^{\circ}\text{C}$ ($275 \pm 4^{\circ}\text{F}$)
Voltage withstand	Pass	4.6.6.2
Color stability	Pass	4.6.16 $130 \pm 2^{\circ}\text{C}$ ($266 \pm 4^{\circ}\text{F}$), 48 hours
<u>After Unrestricted Shrinkage</u>		
ID, max	Table I	4.6.3
Wall thickness	Table I	4.6.3
Tensile strength, PSI, min	3,000	4.6.14 ASTM D 638, Speed C
Ultimate elongation, %, min	150	4.6.14 ASTM D 638, Speed C
Dielectric strength, volts per mil, min	480	4.6.2 ASTM D 876
Volume resistivity, ohms - cm, min	10^{11}	4.6.2 ASTM D 876
Water absorption, %, max	1.0	4.6.2 ASTM D 570, Procedure A

MIL-I-23053/3A

TABLE II. Physical properties 1/ (continued)

Property	Requirement	Test Procedure and Conditions
<u>After Unrestricted Shrinkage</u>		
Heat Resistance, Properties After		4.6.9 130 \pm 2°C (266 \pm 4°F), 400 hours
Ultimate elongation, %, min	Class 1 - 75 Class 2 - 100	
Min % retention of as rec'd elongation	65	
Specific gravity, max	1.4	4.6.2 ASTM D 792
Fluid Resistance, Properties After		4.6.11
Tensile strength, PSI, min	2600	
Dielectric strength, volts per mil, min	300	
Flammability	Self-extinguishing 15 seconds and 3 inches	4.6.15.2 (see 6.1.1)
Corrosion	No corrosion	4.6.10.1 136 \pm 2°C (276 \pm 4°F), T68 hours
Fungus resistance	Non-nutrient	4.6.2 ASTM G21

1/ Unless otherwise specified, the stated requirements and test conditions are for all classes.

2/ Mandrel size for this test shall be as follows:

Tubing ID	Mandrel ID
.046 to .187	5/16
.188 to .500	3/8
.501 to 1.000	5/8
1.001 to 2.000	7/8

MIL-I-23053/3A

Shelf life conditions: Storage at 40°C (104°F) for 1 year. Conformance to 3.6.

Intended use: Heat shrinkable PVC sleeving is intended for light duty harnessing or wire bundling.

Custodians

Army - EL

Navy - AS

Air Force - 85

Preparing Activity:

Navy - AS

(Project No. 5970-0478-3)

Review Activities

Army - MI

Navy - EC

Air Force - 80

DSA - GS

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge (*DO NOT STAPLE*), and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY




NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE \$300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Commanding Officer
Naval Air Engineering Center
Engineering Specifications and Standards Department
(ESSD), Code 93
Lakehurst, NJ 08733



STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions - Reverse Side)

1. DOCUMENT NUMBER		2. DOCUMENT TITLE	
3a. NAME OF SUBMITTING ORGANIZATION		3. TYPE OF ORGANIZATION (Mark one)	
b. ADDRESS (Street, City, State, ZIP Code)		<input type="checkbox"/> VENDOR	
		<input type="checkbox"/> USER	
		<input type="checkbox"/> MANUFACTURER	
		<input type="checkbox"/> OTHER (Specify): _____	
5. PROBLEM AREAS			
a. Paragraph Number and Wording:			
b. Recommended Wording:			
c. Reason/Rationale for Recommendation:			
6. REMARKS			
7a. NAME OF SUBMITTER (Last, First, MI) - Optional		b. WORK TELEPHONE NUMBER (Include Area Code) - Optional	
c. MAILING ADDRESS (Street, City, State, ZIP Code) - Optional		8. DATE OF SUBMISSION (YYMMDD)	

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

 DD FORM 1426
 32 MAR 1955

PREVIOUS EDITION IS OBSOLETE.