

INCH-POUND

MIL-I-43553B

AMENDMENT 1

23 June 1994

MILITARY SPECIFICATION

INK, MARKING, EPOXY BASE

This amendment forms a part of MIL-I-43553B, dated 16 December 1992, and is approved for use by all Departments and Agencies of the Department of Defense.

Page 5

3.10.2: Delete and substitute:

"3.10.2. Chemical resistance. Cured ink impressions shall not deteriorate when immersed for 30 minutes in water, denatured ethyl alcohol, methyl alcohol, and cleaning solvent selected in 4.6.1 (see 4.6.3.2)."

Page 7

4.6.1, line 5: After TT-C-490 add: "except per MIL-T-81533 in Method II of Table III"

Page 10

4.6.3.2, second sentence: Delete and substitute:
"These specimens shall be immersed in water, denatured alcohol, methyl alcohol, and cleaning solvent selected in 4.6.1, for a period of 30 minutes in each solution at a temperature of 30 ± 1 degree celsius."

AMSC N/A

1 of 2

FSC 7510

DISTRIBUTION STATEMENT A. Approved for public release;
distribution is unlimited.

MIL-I-43553B
AMENDMENT 1

Page 15

6.8: Delete "1.1.1 trichlorethane"

Custodians:

Army - MI

Navy - AS

Air Force - 99

Preparing activity:

Army - MI

(Project 7510-0379)

Review activities:

Army - AL, AR, EA, MD, ME, GL

Navy - OS

Air Force - 84