

MIL-L-60326 (MU)
 AMENDMENT 1
 30 April 1965

MILITARY SPECIFICATION
 LUBRICANT, FLUOROCARBON
 TELOMER DISPERSION
 (FOR USE WITH AMMUNITION)

This amendment forms a part of Military Specification MIL-L-60326 (MU) dated 19 February 1965.

Paragraph 1.1 - Delete in its entirety and substitute the following:

"1.1 Scope.-This specification covers three types of Fluorocarbon lubricant for use with ammunition (see 6.3)".

Paragraph 1.2 - Add new paragraph:

"1.2 Classification.-The Fluorocarbon lubricant shall consist of the following types:

Type I	Solvent dispersed: 20.0 percent Solids
Type II	Solvent dispersed: 5.0 percent Solids
Type III	Solvent dispersed: 2.5 percent Solids

Paragraph 3.1 - Material: Delete in its entirety and substitute the following:

"3.1 Material.-The lubricant shall consist of the percent fluorocarbon dispersed in 1, 1, 2 Trichloro 1, 2, 2 trifluoroethane."

Paragraph 3.2 and 3.3 - Density and viscosity: Delete in its entirety and substitute the following:

"3.2 Physical properties.-The physical properties of the fluorocarbon shall be as specified in Table I when determined as specified in 4.3.

Table I

Type	I	II	III	Method
Solid in solvent, percent	20 \pm 1	5.0 \pm 0.3	2.5 \pm 0.2	4.3.1
Density, gm/ml \pm 0.08	1.65	1.59	1.58	4.3.4
Viscosity, cps	1600(\neq 100)	12(\neq 1)	6(\neq 1)	4.3.5

FSC 1390

MIL-L-60326 (MU)
AMENDMENT 1

Paragraph 6.3 - Type specified.-The type of fluorocarbon lubricant required shall be specified in the contract. If the type is not specified type I automatically applies.

Custodian:
Army-MU

Preparing activity:
Army-MU

Project No. 1390-A481