

MIL-S-17917A(AS)

AMENDMENT 1

31 August 1971

MILITARY SPECIFICATION

SANDWICH CONSTRUCTION; ALUMINUM ALLOY
FACINGS, BALSA WOOD CORE

This amendment forms a part of Military Specification MIL-S-17917A(AS), 9 July 1969 and has been approved by the Naval Air Systems Command, Department of the Navy.

Page 4

Paragraph 3.5.2 - Delete and substitute:

"3.5.2 Peel strength. The average peeling torque of facing to core shall be no less than 23 pounds load per 3 inch specimen width when tested as specified in 4.5.4. "

Preparing activity:

Navy - AS

Project No. 5680-N010

FSC 5680