

MIL-S-81733C
Amendment 1
29 February 1988

MILITARY SPECIFICATION

SEALING AND COATING COMPOUND, CORROSION INHIBITIVE

This Amendment forms a part of Military Specification MIL-S-81733C, dated 13 March 1980, and is approved for use by all Departments and Agencies of the Department of Defense.

Page 1

1.2.1, under Type II: Insert "-1/6," between "be" and "-1/2".

Page 6

Table II, Application time: Under columns for Type II and Type II Hours: Add "-1/6" and "1/6" respectively.

Table III, Tack free time: Under columns for Type II and Type II Hours add: "-1/6" and "4" respectively.

Page 8

3.3.3, add to the end of the last sentence: ", except that storage hardness for Type II-1/6 materials shall be measured after 7 hour cure."

Page 12

4.7, add to the start of the second sentence: "Except for Type II-1/6,".

Page 13

Table VII, Cure cycle: Under columns for Type and cure: Add "Type II-1/6 hour application time" and "5 hours at standard conditions".

AMSC N/A

FSC 8030

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

MIL-S-81733C
Amendment 1

Page 15

4.8.3.1, line 3: Delete "Within 15 minutes after the beginning of mixing," and substitute: Within 5 minutes after the start of mixing for -1/6 and within 15 minutes for all other dash numbers,".

Page 20

4.8.11, line 4: Delete " $93^{\circ}\pm 2^{\circ}\text{C}$ ($200^{\circ}\pm 5^{\circ}\text{F}$)" and substitute: " $121^{\circ}\pm 2^{\circ}\text{C}$ ($250^{\circ}\pm 5^{\circ}\text{F}$)".

Custodians:

Army - MR
Navy - AS
Air Force - 20

Review activities:

Army - AV, MI
Air Force - 20, 99

User activities:

Army - ME
Navy - MC

Preparing Activity:

Navy - AS
(Project No. 8030-0597)