

MIL-S-81824/3


15 June 1984

## MILITARY SPECIFICATION SHEET

SPLICE, COAXIAL CABLE, ELECTRIC, PERMANENT, CRIMP STYLE  
COPPER, INSULATED, ENVIRONMENT RESISTANT, CLASS 1

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the splice, described herein shall consist of this specification sheet and the latest issue of MIL-S-81824.



## NOTES:

1. Dimensions are in inches.
2. "B" Diameter shall not include color stripe.
3. Metric equivalents (to the nearest .01 mm) are given for general information only and are based upon 1 inch = 25.4 mm.

FIGURE 1. Splice assembly.


## MIL-S-81824/3

TABLE I CONSTRUCTION DETAILS

Military Part Number	Center Conductor Diameter Range	Color Code	A	B	C	D	Shield Splice E			Sealing Sleeve F		Filler Sleeve G			H max.	J max.	MIL-C-17 Applicable Cables
							(a) min	(d) min	(c) max.	(a) min	(b) max	(a) min	(e) max	(f) nom			
M81824/3-1	.020 .010	Yellow	.032 .022	.080 .075	.510 .490	.245 .225	118	.060	.070	118	.025	NONE			.200	270	/94 RG-179 /113 RG-316 /172
M81824/3-2	.020 .010	Yellow	.032 .022	.080 .075	.510 .490	.245 .225	157	.075	.080	157	.051	157	.070	105	.250	315	/95 RG-180
M81824/3-3	.040 .020	Red	.053 .045	.080 .075	.510 .490	.245 .225	236	.118	.137	236	.075	236	.070	118	300	.350	/110 RG-302 /111 RG-303 /170

INCHES	mm	INCHES	mm	INCHES	mm
.010	0.25	.075	1.91	.225	5.72
.020	0.51	.080	2.03	.230	5.84
.022	0.56	.105	2.67	.236	5.99
.025	0.64	.110	2.79	.245	6.22
.026	0.66	.118	3.00	.250	6.35
.032	0.81	.135	3.43	.270	6.86
.040	1.02	.137	3.48	.300	7.62
.045	1.14	.155	3.94	.315	8.00
.050	1.27	.157	3.99	.350	8.89
.053	1.35	.200	5.08	.490	12.45
.060	1.52	.210	5.33	.510	12.95
.070	1.78				

MIL-S-81824/3

SELECTION GUIDE

- (a) As supplied. Cable jacket diameter must be less than this value.
- (b) Recovered I.D., through meltable inserts of sealing sleeve. Cable dielectric diameter must be greater than this value.
- (c) Recovered I.D., through shrinkable shield of shield splice sleeve. Cable shield diameter must be greater than this value. Shield may be folded back over cable jacket to increase its diameter.
- (d) Recovered I.D., through meltable inserts of shield splice sleeve. Cable jacket diameter must be greater than this value.
- (e) Recovered I.D.
- (f) Recovered O.D. measured when installed on metal crimp splice.

TABLE 11. CRIMP TOOLS

Splice Part No.	Basic Crimp Tool No.	Die No.
M81824/3-1 /3-2 /3-3	M22520/5-01 or M22520/10-01	M22520/5-103 USE RED DIE or AWG 26-20 M22520/10-104

MATERIAL: METAL CRIMP SPLICE: Copper per ASTM B75-81a, Tin-plated.

SEALING SLEEVE:

Sleeve Material: Transparent blue poly(vinylidene fluoride) or equivalent. See 3.3.3.

Sealing Material: Fluorocarbon-based thermoplastic, or equivalent.

FILLER SLEEVE: Heat-shrinkable polyolefin based thermoplastic.

SHIELD SPLICE SLEEVE:

Sleeve Material: Transparent blue poly(vinylidene fluoride) or equivalent. See 3.3.3.

Sealing Material: Fluorocarbon-based thermoplastic, or equivalent.

Shield Splice: Copper-wire braid, coated with solder and flux. Type Sn63 RA (QQ-S-571) preferred.

## MIL-S-81824/3

Qualification:

Test Specimens: Splice shall be installed in the center of a four foot length of the cables listed in Table I. The cable shall be the smallest diameter applicable for the splice tested. The Inner Conductor splice shall be installed using the crimp tool listed in Table II. The sealing sleeve, filler sleeve, and shield splice sleeve shall be installed using a standard forced air heat gun.

Requirements: All requirements shall be as specified except the following:

- (1) The Tensile Strength of the test specimen shall be not less than 75% of the unspliced cable. The unspliced cable shall be tested the same as the spliced cable.
- (2) Group IV: Not applicable.
- (3) Voltage Drop: Not applicable. Substitute Attenuation and Structural Return Loss. These tests shall be run per the applicable paragraphs of MIL-C-17. These tests shall be run initially on four foot lengths of cable and then the same pieces of cable shall be cut in half, spliced, and retested prior to conditioning.

<u>Test</u>	<u>Requirement</u>
Attenuation (Insertion Loss)	Not more than 1db increase over unspliced cable. Measured at 3 GHz.
Structural Return Loss	2db maximum decrease over unspliced cable across band 0 to 3 GHz.

## REQUIREMENTS:

1. No etching or solvent treating of the associated cable insulation shall be permitted.
2. Operating frequency range: 50 MHz to 3 GHz.
3. Complete assembly instructions shall be furnished by the vendor with each splice assembly (Figure 1) acquired under this specification. The instruction sheet shall be approved by the qualification activity.

MIL-S-81824/3

Custodians:

Army - ER  
Navy - AS  
USAF - 85

Preparing Activity:

Navy - AS  
(Project No. 5940-0963)

Review Activity:

Army - AV  
Navy -  
USAF - 11, 99  
DSA - GS

User Activity:

Army - MI  
Navy - EC, MC, SH, OS

**INSTRUCTIONS** In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge (*DO NOT STAPLE*), and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

**NOTE** This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY  
Commanding Officer  
Naval Air Engineering Center  
Engineering Specifications and Standards Department  
(ESSD), Code 93  
Lakehurst, NJ 08733



NO POSTAGE  
NECESSARY  
IF MAILED  
IN THE  
UNITED STATES

**OFFICIAL BUSINESS**  
PENALTY FOR PRIVATE USE \$300

**BUSINESS REPLY MAIL**  
FIRST CLASS PERMIT NO. 12503 WASHINGTON, D.C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Commanding Officer  
Naval Air Engineering Center  
Engineering Specifications and Standards Dept.  
(ESSD), Code 93  
Lakehurst, NJ 08733



## STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions - Reverse Side)

1 DOCUMENT NUMBER MIL-S-81824/3		2 DOCUMENT TITLE SPLICE, COAXIAL CABLE, ELECTRIC, PERMANENT, CRIMP STYLE COPPER, INSULATED, ENVIRONMENT RESISTANT, CLASS 1	
3a. NAME OF SUBMITTING ORGANIZATION		4 TYPE OF ORGANIZATION (Mark one)	
b ADDRESS (Street, City, State, ZIP Code)		<input type="checkbox"/> VENDOR	
		<input type="checkbox"/> USER	
5 PROBLEM AREAS		<input type="checkbox"/> MANUFACTURER	
		<input type="checkbox"/> OTHER (Specify) _____	
		a Paragraph Number and Wording	
b Recommended Wording			
c Reason/Rationale for Recommendation			
6 REMARKS			
7a. NAME OF SUBMITTER (Last, First, MI) - Optional		b WORK TELEPHONE NUMBER (Include Area Code) - Optional	
c MAILING ADDRESS (Street, City, State, ZIP Code) - Optional		8 DATE OF SUBMISSION (YYMMDD)	

(TO DETACH THIS FORM, CUT ALONG THIS LINE)