

MIL-T-1368C
Amendment 4 (SH)
12 December 2000
SUPERSEDING
INT. AMENDMENT 3(SH)
24 December 1980
USED IN LIEU OF
AMENDMENT 2
21 February 1966

MILITARY SPECIFICATION

TUBE AND PIPE, NICKEL-COPPER ALLOY,
SEAMLESS AND WELDED

This amendment is issued for use by the NAVAL SYSTEMS COMMAND, with Military Specification MIL-T-1368C, dated 2 June 1965.

PAGE 6

Paragraph 3.5 Add after last sentence:

"Pipe and tubes shall be specified in two dimensions only; for example, an outside diameter and average wall, or as inside diameter and average wall."

PAGE 7

4.1 Delete and substitute:

"4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except, as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certification of quality compliance. A certificate of quality compliance shall be prepared for each lot of material offered for acceptance (see 6.2.1). The certificate shall include actual data of specified chemical and mechanical tests. Qualitative results of nondestructive tests and other inspections or tests shall be recorded on the certificate. The certificate shall also state that each lot has been sampled, tested, and inspected in accordance with the specification and meets all specification requirements. The certificate shall be signed by a responsible representative of the contractor."

MIL-T-1368C
Amendment 4 (SH)

PAGE 8

Paragraph 4.3.2.1, line three: Insert a period after the word "analysis", and delete, "approved by the contracting officer (see 6.2)."

Paragraph 6.2 (i): Delete the line in its entirety.

*Add the following:

6.2.1 Data requirements. When this specification is used in a procurement which incorporates a DD Form 1423 and invokes the provisions of 7-104.9(n) of the Defense Acquisition Regulations, the data requirements identified below will be developed as specified by the Data Item Description (DD Form 1664) and delivered in accordance with the approved Contract Data Requirements List (DD Form 1423) incorporated into the contract. When the provisions of DAR 7-104.9(n) are invoked, the procurement document will specify that the data specified below is to be delivered by the contractor (use of the DID in this case is not required). Deliverable data required by this specification is cited in the following paragraph:

<u>PARAGRAPH</u>	<u>DATA REQUIREMENT</u>	<u>APPLICABLE DID</u>
4.1.1	Certification of Quality Compliance	UDI-A-23264 Certification Data/ Report

(Copies of data item descriptions required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

6.2.1.1 The data requirements of 6.2.1 and any task in section 3, 4, or 5 of this specification required to be performed to meet a data requirement may be waived by the contracting/ acquisition activity upon certification by the offeror that identical data were submitted by the offeror and accepted by the Government under a previous contract for identical item acquired to this specification. This does not apply to specific data which may be required for each contract regardless of whether an identical item has been supplied previously (for example, test reports)."

MIL-T-1368C
Amendment 4 (SH)

Table VI, Delete and substitute:

"Table VI. Commercially available pipe sizes

Nominal Pipe Size		Schedule No. 5		Schedule No. 10		Schedule No. 40		Schedule No. 80	
inch	O.D. inch	Nominal Wall thickness inch	Wt./Ft. inch	Nominal Wall thickness inch	Wt./Ft. inch	Nominal Wall thickness inch	Wt./Ft. inch	Nominal Wall thickness inch	Wt./Ft. inch
1/8	0.4050	-----	-----	0.049	0.2098	0.068	0.2756	0.095	0.3542
1/4	0.5400	-----	-----	0.065	0.3713	0.088	0.4783	0.095	0.6025
3/8	0.6750	-----	-----	0.065	0.4768	0.091	0.6391	0.095	0.8319
1/2	0.8400	0.065	0.6058	0.083	0.7556	0.109	0.9582	0.095	1.2251
3/4	1.0500	0.065	0.7700	0.083	0.9652	0.113	1.2733	0.095	1.6594
1	1.3150	0.065	0.9771	0.109	1.5809	0.133	1.8906	0.095	2.4454
1-1/4	1.6600	0.065	1.2468	0.109	2.0331	0.140	2.5591	0.095	3.3742
1-1/2	1.9000	0.065	1.4344	0.109	2.3477	0.145	3.0603	0.095	4.0888
2	2.3750	0.065	1.8057	0.109	2.9703	0.154	4.1133	0.095	5.6549
2-1/2	2.8750	0.083	2.7869	0.120	3.9758	0.203	6.5231	0.095	8.6265
3	3.5000	0.083	3.4107	0.120	4.8777	0.216	8.5306	0.095	11.5450
3-1/2	4.0000	0.083	3.9098	0.120	5.5993	0.226	10.2573	0.095	14.0810
4	4.5000	0.083	4.4089	0.120	6.3209	0.237	12.1502	0.095	16.8716
5	5.5630	0.109	7.1493	0.134	8.7487	0.258	16.4599	0.095	23.3966
6	6.6250	0.109	8.5414	0.134	10.4601	0.280	21.3654	0.095	32.1741
8	8.6250	-----	-----	-----	-----	0.322	32.1523	0.095	48.8556

Schedule 160

Nominal Pipe Size		I.D.		Wall		Weight per ft.	
inch	O.D. inch	inch	inch	inch	inch	per ft.	ft.
1/2	0.840	0.466	0.187	0.187	1.4685	1.4685	2.7484
3/4	1.050	0.614	0.218	0.218	2.1812	2.1812	4.1202
1	1.315	0.815	0.25	0.25	3.2019	3.2019	5.8710
1-1/4	1.660	1.16	0.25	0.25	4.2392	4.2392	7.2156
1-1/2	1.900	1.338	0.281	0.281	5.4711	5.4711	10.1668
2	2.375	1.689	0.343	0.343	8.3818	8.3818	15.4209
2-1/2	2.875	2.125	0.375	0.375	11.2744	11.2744	20.9252
3	3.500	2.624	0.438	0.438	16.1287	16.1287	
4	4.500	3.438	0.531	0.531	25.3453	25.3453	
5	5.563	4.313	0.625	0.625	37.1152	37.1152	"

Double extra heavy

MIL-T-1368C
Amendment 4 (SH)

LAST PAGE

* DD 1426, SPECIFICATION ANALYSIS SHEET: Delete address and substitute:

"COMMANDER
NAVAL SEA SYSTEMS COMMAND (SEA 05Q)
2531 Jefferson Davis Highway
Arlington, VA 22242-5160"

NOTE: The margins of this amendment are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of the marginal notations and relationship to the last previous amendment.

Preparing activity
Navy - SH
(Project 4710-0219)

NOTICE OF
REINSTATEMENT

NOT MEASUREMENT
SENSITIVE

MIL-T-1368C
NOTICE 2
20 September 1999
SUPERSEDING
NOTICE 1
6 May 1999

MILITARY SPECIFICATION

TUBE AND PIPE, NICKEL-COPPER ALLOY, SEAMLESS AND WELDED

MIL-T-1368C Interim Amendment 3, dated 24 December 1980, is hereby reinstated through 31 December 2000 and may be used for acquisition. If MIL-T-1368C has not been revised or amended by 31 December 2000, Interim Amendment 3 will be canceled.

Preparing activity:

Navy - SH
(Project 4710-0213)

AMSC N/A

FSC 4710

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

MIL-T-1368C
INT. AMENDMENT 3(SH)
24 December 1980

USED IN LIEU OF
AMENDMENT 2
21 February 1966

MILITARY SPECIFICATION

TUBE AND PIPE, NICKEL-COPPER ALLOY,
SEAMLESS AND WELDED

This interim amendment is issued for use by the Naval Sea Systems Command, with Military Specification MIL-T-1368C, dated 2 June 1965.

PAGE 6

Paragraph 3.5 Add after the last sentence:

"Pipe and tubes shall be specified in two dimensions only; for example, an outside diameter and average wall, or as inside diameter and average wall."

PAGE 7

* 4.1 Delete and substitute:

"4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except, as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certification of quality compliance. A certificate of quality compliance shall be prepared for each lot of material offered for acceptance (see 6.2.1). The certificate shall include actual data of specified chemical and mechanical tests. Qualitative results of nondestructive tests and other inspections or tests shall be recorded on the certificate. The certificate shall also state that each lot has been sampled, tested, and inspected in accordance with the specification and meets all specification requirements. The certificate shall be signed by a responsible representative of the contractor."

PAGE 8

Paragraph 4.3.2.1, line three: Insert a period after the word "analysis", and delete, "approved by the contracting officer (see 6.2)."

MIL-T-1368C
INT. AMENDMENT 3(SH)

PAGE 11

Paragraph 6.2 (i): Delete the line in its entirety.

* Add the following:

"6.2.1 Data requirements. When this specification is used in a procurement which incorporates a DD Form 1423 and invokes the provisions of 7-104.9(n) of the Defense Acquisition Regulations, the data requirements identified below will be developed as specified by the Data Item Description (DD Form 1664) and delivered in accordance with the approved Contract Data Requirements List (DD Form 1423) incorporated into the contract. When the provisions of DAR 7-104.9(n) are not invoked, the procurement document will specify that the data specified below is to be delivered by the contractor (use of the DID in this case is not required). Deliverable data required by this specification is cited in the following paragraph:

<u>PARAGRAPH</u>	<u>DATA REQUIREMENT</u>	<u>APPLICABLE DID</u>
4.1.1	Certificate of Quality Compliance	UDI-A-23264 Certification Data/ Report

(Copies of data item descriptions required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

6.2.1.1 The data requirements of 6.2.1 and any task in section 3, 4, or 5 of this specification required to be performed to meet a data requirement may be waived by the contracting/acquisition activity upon certification by the offeror that identical data were submitted by the offeror and accepted by the Government under a previous contract for identical item acquired to this specification. This does not apply to specific data which may be required for each contract regardless of whether an identical item has been supplied previously (for example, test reports)."

MIL-T-1368C
INT. AMENDMENT 3(SH)

PAGE 13

Table VI, Delete and substitute:

"Table VI. Commercially available pipe sizes

Nominal Pipe Size inch	O. D. inch	Schedule No. 5		Schedule No. 10		Schedule No. 40		Schedule NO. 80	
		Nominal thickness inch	Wt./Ft. inch	Nominal thickness inch	Wt./Ft. inch	Nominal thickness inch	Wt./Ft. inch	Nominal thickness inch	Wt./Ft. inch
1/8	0.405	-----	-----	0.049	.2098	0.068	.2756	0.095	.3542
1/4	0.540	-----	-----	0.065	.3713	0.088	.4783	0.119	.6025
3/8	0.675	-----	-----	0.065	.4768	0.091	.6391	0.126	.8319
1/2	0.840	0.065	.6058	0.083	.7556	0.109	.9582	0.147	1.2251
3/4	1.050	0.065	.7700	0.083	.9652	0.113	1.2733	0.154	1.6594
1	1.315	0.065	.9771	0.109	1.5809	0.133	1.8906	0.179	2.4454
1-1/4	1.660	0.065	1.2468	0.109	2.0331	0.140	2.5591	0.191	3.3742
1-1/2	1.900	0.065	1.4344	0.109	2.3477	0.145	3.0603	0.200	4.0888
2	2.375	0.065	1.8057	0.109	2.9703	0.154	4.1133	0.218	5.6549
2-1/2	2.875	0.083	2.7869	0.120	3.9758	0.203	6.5231	0.276	8.6265
3	3.500	0.083	3.4107	0.120	4.8777	0.216	8.5306	0.300	11.5450
3-1/2	4.000	0.083	3.9098	0.120	5.5993	0.226	10.2573	0.318	14.0810
4	4.500	0.083	4.4089	0.120	6.3209	0.237	12.1502	0.337	16.8716
5	5.563	0.109	7.1493	0.134	8.7487	0.258	16.4599	0.375	23.3966
6	6.625	0.109	8.5414	0.134	10.4601	0.280	21.3654	0.432	32.1741
8	8.625	-----	-----	-----	-----	0.322	32.1523	0.500	48.8556

Schedule 160

Nominal Pipe Size inch	O.D. inch	I. D. inch	Wall inch	Weight per ft.
1/2	.840	.466	.187	1.4685
3/4	1.050	.614	.218	2.1812
1	1.315	.815	.250	3.2019
1-1/4	1.660	1.160	.250	4.2392
1-1/2	1.900	1.338	.281	5.4711
2	2.375	1.689	.343	8.3818
2-1/2	2.875	2.125	.375	11.2744
3	3.500	2.624	.438	16.1287
4	4.500	3.438	.531	25.3453
5	5.563	4.313	.625	37.1152

Double extra heavy

Nominal Pipe Size inch	O. D. inch	I. D. inch	Wall inch	Weight per ft.
3/4	1.050	.434	.308	2.7484
1	1.315	.599	.358	4.1202
1-1/4	1.660	.896	.382	5.8710
1-1/2	1.900	1.100	.400	7.2156
2	2.375	1.503	.436	10.1668
2-1/2	2.875	1.771	.552	15.4209
3	3.500	2.300	.600	20.9252

MIL-T-1368C
INT. AMENDMENT 3(SH)

LAST PAGE

* DD 1426, SPECIFICATION ANALYSIS SHEET: Delete address and substitute:

"COMMANDER
NAVAL SEA SYSTEMS COMMAND (SEA 3112)
DEPARTMENT OF THE NAVY
WASHINGTON, DC 20362"

NOTE: The margins of this amendment are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of the marginal notations and relationship to the last previous amendment.

Preparing activity:
Navy - SH
(Project 4710-N558)

MIL-T-1368C
AMENDMENT 2
21 February 1966
SUPERSEDING
AMENDMENT 1
26 October 1965

MILITARY SPECIFICATION

TUBE AND PIPE, NICKEL-COPPER ALLOY, SEAMLESS AND WELDED

This amendment forms a part of Military Specification MIL-T-1368C, dated 2 June 1965, and is mandatory for use by all Departments and Agencies of the Department of Defense.

Page 6, paragraph 3.5. Add after the last sentence:

"Pipe and tubes shall be specified in two dimensions only; for example, as outside diameter and average wall, or as inside diameter and average wall."

Page 8, paragraph 4.3.2.1, line three. Insert a period after the word "analysis", and delete, "approved by the contracting officer (see 6.2)."

Page 11, paragraph 6.2 (i). Delete the line in its entirety.

Page 13, delete table VI and substitute the following table:

FSC 4710

MIL-T-1368C
Amendment -2

Table VI. Commercially available pipe sizes

Nominal Pipe Size inch	O. D. inch	Schedule No. 5		Schedule No. 10		Schedule No. 40		Schedule No. 80	
		Nominal Wall thickness inch	Wt./Ft. lb.	Nominal Wall thickness inch	Wt./Ft. lb.	Nominal Wall thickness inch	Wt./Ft. lb.	Nominal Wall thickness inch	Wt./Ft. lb.
1/8	0.405	-----	-----	0.049	2098	0.068	2756	0.095	3542
1/4	0.540	-----	-----	0.065	3713	0.088	4783	0.119	6025
3/8	0.675	-----	-----	0.065	4768	0.091	6391	0.126	8319
1/2	0.840	0.065	6058	0.083	7556	0.109	9582	0.147	12251
3/4	1.050	0.065	7700	0.083	9632	0.113	12733	0.154	16594
1	1.315	0.065	9771	0.109	15809	0.133	18906	0.179	24454
1-1/4	1.660	0.065	12468	0.109	20331	0.140	25591	0.191	33742
1-1/2	1.900	0.109	14344	0.145	23471	0.200	30603	0.200	40888
2	2.375	0.065	18057	0.109	29703	0.154	41133	0.218	56549
2-1/2	2.875	0.083	27869	0.120	39758	0.203	65231	0.276	86269
3	3.500	0.083	34107	0.120	48777	0.216	85306	0.300	115450
3-1/2	4.000	0.083	39088	0.120	55993	0.226	102573	0.318	140810
4	4.500	0.083	44089	0.120	63209	0.237	121502	0.337	168716
5	5.563	0.109	71493	0.134	87487	0.258	164599	0.375	233966
6	6.625	0.109	85414	0.134	104601	0.280	213654	0.432	321741
8	8.625	-----	-----	-----	-----	0.322	321523	0.500	488356

Schedule 160

Nominal Pipe Size inch	O. D. inch	I. D. inch	Wall inch	Weight per ft.
1/2	0.840	0.746	0.187	1.4685
3/4	1.050	0.914	0.218	2.1812
1	1.315	1.155	0.250	3.2019
1-1/4	1.660	1.460	0.250	4.2392
1-1/2	1.900	1.688	0.281	5.4711
2	2.375	2.089	0.343	8.3818
2-1/2	2.875	2.425	0.375	11.2744
3	3.500	3.024	0.438	16.1287
4	4.500	3.938	0.531	25.3453
5	5.563	4.813	0.625	37.1152

Double extra heavy

Nominal Pipe Size inch	O. D. inch	I. D. inch	Wall inch	Weight per ft.
3/4	1.050	0.834	0.308	2.7434
1	1.315	0.999	0.358	4.1202
1-1/4	1.660	1.296	0.382	5.8710
1-1/2	1.900	1.400	0.400	7.2156
2	2.375	1.903	0.436	10.1648
2-1/2	2.875	2.371	0.552	15.4209
3	3.500	2.900	0.600	20.9252

MIL-T-1368C
AMENDMENT 2

Custodians:

Army - MR
Navy - YD
Air Force - 69

Preparing activity:

Navy - YD

Review activities:

Army - MR, MO, MI
Navy - YD, WP, SH
Air Force - 69

User activities:

Army - WC, MU
Navy - None
Air Force - None

MTL-T-1368C
2 June 1965
SUPERSEDING
MTL-T-1368B
18 March 1958

MILITARY SPECIFICATION

TUBE AND PIPE, NICKEL-COPPER ALLOY, SEAMLESS AND WELDED

This specification is mandatory for use
by all Departments and Agencies of the
Department of Defense.

1. SCOPE

1.1 Scope. This specification covers tube and pipe for use where the strength and corrosion resistance of nickel-copper alloy (Monel) are required.

1.2 Classification. Tube and pipe covered by this specification shall be of the following classes, as specified (see 6.2):

Class A - Seamless, Cold Drawn, Annealed.

Class B - Seamless, Cold Drawn, Stress Relieved.

Class C - Welded, Annealed.

Class D - Welded, Stress Relieved.

1.3 Pipe. Sizes of cold-drawn, seamless, nickel-copper-alloy pipe commercially available shown in 6.5 are for information only. When other schedules or wall thicknesses are required the manufacturer should be consulted.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein.

SPECIFICATION

Military

MTL-C-3993 - Copper and Copper-Base Alloy Mill Products Packaging
of

FSC 47.0

MIL-T-1368C

STANDARDS

Federal

Federal Test Method Standard No. 151 - Metals; Test Methods
FED-STD-182 - Continuous Identification Marking of Nickel and
Nickel Base Alloys

Military

MIL-STD-105 - Sampling Procedures and Tables for Inspection by
Attributes
MIL-STD-129 - Marking for Shipment and Storage

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM)

E190-64 - Guided Bend Test, for Ductility of Welds

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa. 19103.)

Official Classification Committee

Uniform Freight Classification Rules

(Application for copies should be addressed to the Official Classification Committee, 1 Park Avenue at 33rd Street, New York, N.Y. 10016.)

3. REQUIREMENTS

3.1 Material. The material used in the fabrication of the tube and pipe shall be such as to produce items that are in full conformance with chemical and physical requirements of this specification.

MIL-T-1368C

3.2 Chemical requirements. All tube and pipe shall conform to the chemical requirements of table I.

Table I. Composition

Element	Percent
Nickel ¹	63.0 - 70.0
Iron	2.50 max.
Aluminum	.50 max.
Manganese	1.25 max.
Carbon	.20 max.
Silicon	.50 max.
Sulphur	.015 max.
Lead ²	.006 max.
Phosphorus ²	.02 max.
Tin ²	.006 max.
Zinc ²	.02 max.
Copper	Remainder

¹Cobalt counting as Nickel.

²These elements need not be determined or reported by the vendor. However, if determined by the purchaser or contractor, the values will not exceed those shown.

3.3 Mechanical properties. All tube and pipe shall conform to the mechanical properties shown in the following table II:

Table II. Mechanical Properties

Condition	Tensile Strength Per Square Inch (Min.)	Yield Strength at 0.2 Percent Offset or at Extension Indicated (Min.)		Elongation in 2 in. (Minimum)
		Per Square Inch	Extension Under Load in 2 Inches	
	Pounds	Pounds	Inch	Percent
Classes A and C Annealed 5 inch and smaller outside diameter	70,000	28,000	0.0062	35
Over 5 inch outside diameter	70,000	25,000	0.0059	35
Classes B and D Stress relieved All sizes	85,000	55,000	0.0082	15

MIL-T-1368C

3.4 Physical properties.

3.4.1 Tensile strength. Tube or pipe, when tested in accordance with 4.3.3 and 4.5.1, shall meet the applicable mechanical properties in table II.

3.4.2 Flattening (Class A only). Tube or pipe of class A, having an outside diameter at least 3 inches, shall show no injurious defects on any surface after flattening and opening of the flattened section as specified in 4.5.2.

3.4.3 Bending (Class C only). Class C tube or pipe shall show no cracks or openings when bent as specified in 4.5.3.

3.4.4 Flaring (Class A and Class C only). Class A and class C tube or pipe, having an outside diameter of 3 inches or less, shall show no evidence of fracture when tested as specified in 4.5.4.

3.4.5 Hydrostatic test pressure. Each tube or pipe shall withstand an internal hydrostatic test of 1,000 pounds per square inch (p.s.i.) without weepage, leakage, or drop in gage pressure, provided that the fibre stress calculated by the following formula does not exceed the allowable fibre stress S indicated below:

$$P = \frac{2ST}{D}$$

where P = Hydrostatic test pressure, p.s.i.

S = Allowable fibre stress for material in the condition furnished, as follows:

<u>Class</u>	<u>Allowable fibre stress-S</u>
A & C - Annealed: 5 inch outside diameter and smaller	17,500
over 5 inch outside diameter	16,700
B & D - Stress Relieved	21,250

T = Minimum wall thickness in inches; equal to the specified "average" wall minus the permissible "minus" wall tolerance, shown in table III, or the specified minimum wall thickness.

D = Outside diameter of tube or pipe in inches.

MIL-T-1368C

Table III. Permissible variations - outside and inside diameter and wall thickness (average wall).

Specified Outside Diameter or Calculated Nominal Outside Diameter, inch. (When Ordered to Inside Diameter and Average Wall)	Permissible Variations			
	Outside Dia. ^a or Inside Dia. ^{a,b}		Wall Thickness, ^{c,e,f}	
	inch		percent	
	Plus	Minus	Plus	Minus
.400 and under	0.004	0	10	10
Over 0.400 to 5/8, excl.	0.005	0 ^d	12.5	12.5
5/8 to 1-1/2, incl.	0.005	0.005	10	10
Over 1-1/2 to 4-1/2, incl.	0.010	0.010	10	10
Over 4-1/2 to 6, incl.	0.015	0.015	12.5	12.5
Over 6 to 7-1/2, incl.	0.020	0.020	12.5	12.5
Over 7-1/2 to 8-5/8, incl.	0.025	0.025	12.5	12.5

^aThe permissible variations in the above table apply to individual measurements, including out-of-roundness (ovality), except for the following conditions:

Thin-Wall Tube and Pipe. For thin-wall tube and pipe having a nominal wall thickness of 3 percent or less of the nominal outside diameter, in all conditions (temper), the mean outside diameter or mean inside diameter shall conform to the permissible variations of the above table and individual measurements (including ovality) shall conform to the plus and minus values of the table, with the values increased by 0.5 percent of the nominal outside diameter.

Annealed Tube and Pipe over 4-1/2 inch in Nominal Outside Diameter. For annealed tube and pipe over 4-1/2 inches in nominal outside diameter with a nominal wall thickness greater than 3 percent of the nominal outside diameter, the mean outside diameter or mean inside diameter shall conform to the permissible variations of the above table and individual measurements shall not exceed twice the permissible variations of the above table.

^bFor tube and pipe, in all tempers, with an inside diameter of less than 1/2 inch which cannot be successfully drawn over a mandrel, the inside diameter shall be governed by the outside diameter and the wall thickness variations.

^cFor tube and pipe in all tempers with an inside diameter less than 50 percent of the outside diameter, which cannot be successfully drawn over a mandrel, the inside diameter may vary over or under by an amount equal to 10 percent of the nominal wall thickness and the wall thickness may vary plus or minus 12.5 percent.

^dWhen inside diameter is specified, tubes with an inside diameter of 1/2 inch or over and with an outside diameter of under 5/8 inch shall have a permissible variation in inside diameter of plus and minus 0.005 inch.

^eEccentricity. The variation in wall thickness in any one cross section of any one tube or pipe shall not exceed plus or minus 10 percent of the actual (measured) average wall of that section (defined as the average of the thickest and the thinnest wall in that section).

^fWhen minimum wall tube or pipe is required, the wall tolerance will be the total of the plus and minus wall tolerance from the table all applied to the plus side, e.g., in the case of an O.D. .400 and under the wall tolerance would be plus 20 percent minus 0.

MIL-T-1368C

3.5 Permissible variations (Tolerances). Permissible variations in outside diameter and wall thickness shall be as shown in table III.

3.5.1 Tubing for silver brazing. When tubing for silver brazing is specified, tubing O.D. variations shall be negative (plus 0) with the permissible minus variations (tolerance) equal to the total O.D. range as shown in table III.

3.5.2 Length tolerance. When tube or pipe is ordered cut-to-length, the length shall not be less than that specified, but a variation of plus 1/8 inch will be permitted for lengths up to 30 feet, inclusive. For lengths over 30 feet, a variation of plus 1/4 inch will be permitted.

3.5.3 Random lengths. When ordered to random lengths, tube and pipe may be furnished in lengths from 5 to 24 feet, providing not more than 25 percent by weight is furnished in lengths from 5 to 10 feet. In the case of tubes with wall thicknesses of 7/16 of an inch or more, a greater percentage of short lengths, 5 to 10 feet, will be permitted. A greater percentage of short lengths (5 to 10 feet) will also be permitted for pipe.

3.5.4 Ends. Tube shall be furnished with sawed or machine cut and deburred ends, unless ends beveled for welding or threaded ends are specified in the order.

3.6 Marking. Material shall be marked in accordance with 3.6.1.

3.6.1 Commercial marking. Unless otherwise specified (see 6.2), the name or trademark of the manufacturer and the type shall be legibly marked on each tube of five-eighths of an inch outside diameter or larger. The marking fluid used shall be capable of being removed with hot alkaline cleaning solution without rubbing. The marking shall have no deleterious effects on the material or its performance, and the characters shall be sufficiently stable to withstand ordinary handling and storage. On sizes smaller than five-eighths of an inch outside diameter, the above information shall be marked on the shipping container. When continuous identification marking is specified, marking shall conform with the requirements of Fed. Std. No. 182 and shall be designated "seamless" or "welded" as applicable, after "class".

3.7 Workmanship.

3.7.1 Tube or pipe up to and including 5 inch O.D. shall be seamless drawn. Tubes larger than 5 inch O.D. shall be seamless drawn or formed from sheets and welded.

MIL-T-1368C

3.7.2 The surface of all tube or pipe shall be smooth, clean and free from cracks, laminations, laps, screws, scale and other injurious defects to the maximum extent possible as revealed by visual examination. The tube shall be free of burrs with ends cut square and shall be of proper dimensions. Surface imperfections such as handling marks, straightening marks, light mandrel, and die or roll marks will not be considered injurious defects, provided the imperfections do not reduce the wall thickness below the minimum specified in 3.5.

3.7.3 Tubing may be ground to remove minor defects provided such grinding does not reduce the wall thickness below the minimum permissible. Welded tubing shall not contain more than one longitudinal and one circumferential weld in each length. Unless otherwise specified (see 6.2), an individual tube having a surface irregularity in which the depth is greater than 10 percent of the wall thickness or 0.001 inch, whichever is greater as determined by visual examination, shall be rejected.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Lot definition.

4.2.1 Chemical analysis. A lot shall consist of all material made from the same heat or melt.

4.2.2 Visual and dimensional examination, defect inspection, and mechanical properties tests. A lot shall consist of all material from the same heat, of the same size, from the same heat treatment batch, or from a continuous process under the same conditions of temperature, time at heat, and atmosphere.

4.3 Sampling.

4.3.1 Examination. Unless otherwise specified (see 6.2), sampling for examination shall be conducted in accordance with MIL-STD-105 at inspection level III. The acceptable quality level shall be 0.10 rejects per hundred units for major defects and 1.0 rejects per hundred units for minor defects.

MIL-T-1368C

4.3.2 Sampling for chemical analysis. Unless otherwise specified (see 6.2), the manufacturer may submit a ladle analysis as proof that the pipe and tubing submitted, meets the requirement of table I.

4.3.2.1 Alloy identity. Each random mill length prior to shipping shall be tested for alloy identity by a method, such as metal-sorter, check spectrograph, wet chemical analysis, approved by the contracting officer (see 6.2).

4.3.3 Sampling for test. Sampling for tests shall be made in accordance with table IV. Failure of any test specimen, where sampling is involved, to meet the test requirements shall reject the lot represented.

Table IV. Test schedule

Test	No. of test samples ¹	Test Method ²	Reference paragraph
Chemical analysis	1	111.1 or 112.1	- - - -
Tension test & elongation Classes A and B	1	211	4.5.1.1
Classes C and D (circumferential weld)	2	211	4.5.1.2 and 4.5.1.3
Flattening test (Class A)	1	---	4.5.2
Bending test (Class C)	1	---	4.5.3
Flare test (Classes A & C only)	1	---	4.5.4
Hydrostatic test	See note 3	---	- - - -

¹ When the material in the lot cannot be identified by the melt, one sample for each test shall be selected from each 500 pounds of material in the lot.

² Test methods are found in Federal Test Method Std. No. 151.

³ Each length of pipe or tube shall be subjected to the hydrostatic test described in 3,4,5.

MIL-T-1368C

4.4 **Examination.** Examination shall be conducted as specified in table V. Any tube or pipe in the sample containing one or more defects shall be rejected, and if the number of defective tube or pipe in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected.

Table V. Classification of defects in accordance with MIL-STD-105

Major:

- | | |
|-----|--|
| 101 | Dimensions not as specified. |
| 102 | Ends not as specified. |
| 103 | Ends not free from burrs. |
| 104 | Material not processed as required; surface defects, such as pipes, laps, checks, pits, surface tears, twists, scales, etc. exceed the allowable limits. |
| 105 | Tube ovality not within tolerances. |
| 106 | Welded tubing reinforcements beyond permissible variation. |
| 107 | Welded tubing has more than one longitudinal or circumferential weld in each length. |

Minor:

- | | |
|-----|---------------------------|
| 201 | Marking not as specified. |
|-----|---------------------------|
-

4.5 **Tests.** Samples selected in accordance with 4.3.3 shall be tested as indicated in table IV and in the applicable referenced paragraph.

4.5.1 Tension test and elongation.

4.5.1.1 Classes A and B seamless tube or pipe. One longitudinal tension test specimen shall be cut from each tube selected in accordance with 4.3.3. Where practicable, tube or pipe shall be tested in full section with the ends plugged to prevent collapsing in the grips of the testing machine. The form and dimensions of the test specimen and plugs shall be as shown in figure 1 of Method 211 of Fed. Test Method Std. No. 151. For tube whose diameter does not permit testing in full size, test specimens shall be cut longitudinally from the sample tube and prepared as a figure 5 specimen of Method 211 of Fed. Test Method Std. No. 151.

4.5.1.2 Classes C and D welded tube. A tension test specimen shall be cut circumferentially from one end, straightened when hot,

MIL-T-1368C

and machined to shape and to a width of 1-1/2 inches. The longitudinal weld shall be at the midlength of the test specimen. The weld reinforcement shall be removed flush with the tube before testing. The gage length for measuring elongation of the tension test specimen shall be 16 times the thickness of the specimen. Since the test specimen are bent hot, properties may be those of the annealed material.

4.5.1.3 Classes C and D circumferential weld. For welded tube containing a circumferential weld, two tension specimen, taken at opposite sides of the tube, shall be removed longitudinally with the circumferential weld at the midlength of the specimen. The specimen shall be flattened cold and machined to a width of 1-1/2 inches. The weld reinforcement shall be removed flush with the tube on both sides.

4.5.2 Flattening test on Class A seamless tube. Specimen selected in accordance with 4.3.3 shall be flattened cold between parallel plates under a gradually applied load until the distance between the plates is five times or less than the wall thickness. The specimen shall show no injurious defects.

4.5.3 Bend test on Class C, welded tube. Test samples selected in accordance with 4.3.3 shall be prepared for the root bend test. A strip 1-1/2 inches wide by 10 inches long with the weld at midlength shall be cut circumferentially from the sample and flattened hot. The weld reinforcement shall be removed from both sides of the weld. The test specimen shall be bent in a guided-bending jig as specified in ASTM E190 while the root of the weld inside the tube is in tension.

4.5.4 Flare test on Classes A and C. The flare test shall be conducted on classes A and C annealed tube only. One flare test shall be made on the sample selected in accordance with 4.3.3. The test sample shall be flared with an expanding tool having an included angle of 60 degrees until the specified outside diameter has been increased by 30 percent.

4.6 Inspection of preparation for delivery. The packing and marking of the tube and pipe shall be inspected in conformance with the requirements of section 5 of this specification.

5. PREPARATION FOR DELIVERY

5.1 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

MIL-T-1368C

5.1.1 Levels A and B. The tube and pipe shall be packed in accordance with the applicable level A or B requirements of MIL-C-3993.

5.1.2 Level C. The tube and pipe shall be packed in a manner which will insure arrival at destination in satisfactory condition and be acceptable to the carrier at lowest rates. Containers and packing shall comply with Uniform Freight Classification Rules, or with rules and regulations of other carriers, as applicable to the mode of transportation.

5.2 Marking. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with the requirements of MIL-STD-129.

6. NOTES

6.1 Intended use. Tube or pipe covered by this specification is intended for use in applications where the strength and corrosion resistance of nickel-copper alloy (monel) are required.

6.2 Ordering data. Procurement documents should specify the following:

- (a) Title, number and date of this specification.
- (b) Class required (see 1.2).
- (c) Size, outside diameter, wall thickness and length required (see 1.3, 3.5.3, 6.5 and table VI).
- (d) If tubing is intended for silver brazing (see 3.5.1).
- (e) Ends, finish required (see 3.5.4).
- (f) If material marking is to be continuous (see 3.6).
- (g) Surface irregularities (see 3.7.3).
- (h) Sampling, if different (see 4.3.1 and 4.3.2).
- (i) Type of test required for performance of alloy identity (see 4.3.2.1).
- (j) Level of packing required (see 5.1).
- (k) If special requirements are necessary (see 6.5)

MIL-T-1368C

6.3 Tubing which is to be bent in fabricating should be ordered at a thickness sufficient to assure the required wall thickness at the thinnest point of the tube.

6.4 Definitions of heat treatment.

6.4.1 Class A. Class A tube and pipe are produced by cold working followed by annealing. The tube or pipe is supplied with a dull matte finish.

6.4.2 Class B. Class B tube and pipe are thermally treated to relieve a major portion of the internal stresses and have a thin dark oxide surface.

6.4.3 Class C. Class C tube and pipe are formed from sheets or strip and welded. The material is annealed and has a dull matte finish.

6.4.4 Class D. Class D tube and pipe may be formed from sheet or strip and welded. The material is thermally treated to relieve a major portion of the internal stresses, and has a thin oxide surface.

6.5 The standard dimensions for commercially available pipe shown in table VI are for information only (see 1.3).

6.6 Nuclear end-use. When material is intended for nuclear applications, agreement shall be reached between the contractor and the Government, prior to placement of the order, as to applicable nonstandard or nondestructive test requirements, as well as to details of testing techniques and standards for acceptance and rejection.

6.7 Classification change. The following tube and pipe were formerly classified in MIL-T-1368B as indicated below:

MIL-T-1368C

Class A
Class B
Class C
Class D

MIL-T-1368B

Type I, condition 1
Type I, condition 2
Type II, condition 1
Type II, condition 2

Custodians:

Army - MR
Navy - YD
Air Force - 69

Review activities:

Army - MR, MO, MI
Navy - YD, WF, SH
Air Force - 69

User activities:

Army - WC, MU
Navy - None
Air Force - None

Preparing activity:

Navy - YD

(Project No. 4710-0102)

Table VI. Commercial, available pipe sizes

Nominal Pipe Size inch	O. D. inch	Schedule No. 5		Schedule No. 10		Schedule No. 40		Schedule No. 80	
		Nominal Wall thickness inch	Wt./Ft.	Nominal Wall thickness inch	Wt./Ft.	Nominal Wall thickness inch	Wt./Ft.	Nominal Wall thickness inch	Wt./Ft.
1/8	0.405	-----	-----	0.049	.2098	0.068	0.3542	0.095	.3542
1/4	0.540	-----	-----	0.065	.3713	0.088	0.6025	0.119	.6025
3/8	0.675	-----	-----	0.065	.4768	0.091	0.8319	0.126	.8319
1/2	0.840	0.065	.6058	0.083	.7556	0.109	1.2251	0.147	1.2251
3/4	1.050	0.065	.7700	0.083	.9652	0.113	1.6594	0.154	1.6594
1	1.315	0.065	.9771	0.109	1.5809	0.133	2.4454	0.179	2.4454
1-1/4	1.660	0.065	1.2468	0.109	2.0331	0.140	3.3742	0.191	3.3742
1-1/2	1.900	0.109	1.4344	0.145	2.3471	0.200	4.0888	0.200	4.0888
2	2.375	0.065	1.8057	0.109	2.9703	0.154	5.6549	0.218	5.6549
2-1/2	2.875	0.083	2.7869	0.120	3.9758	0.203	8.6265	0.276	8.6269
3	3.500	0.083	3.4107	0.120	4.8777	0.216	11.5450	0.300	11.5450
3-1/2	4.000	0.083	3.9098	0.120	5.5993	0.226	14.0810	0.318	14.0810
4	4.500	0.083	4.4089	0.120	6.3209	0.237	16.8716	0.337	16.8716
5	5.563	0.109	7.1493	0.134	8.7487	0.258	23.3966	0.375	23.3966
6	6.625	0.109	8.5414	0.134	10.4601	0.280	32.1741	0.432	32.1741
8	8.625	-----	-----	-----	-----	0.322	48.8556	0.500	48.8556

Schedule 160

Nominal Pipe Size inch	O. D. inch	I. D. inch	Wall thickness inch	Weight per ft.
1/2	.840	.466	.187	1.4685
3/4	1.050	.614	.218	2.1812
1	1.315	.815	.250	3.2019
1-1/4	1.660	1.160	.250	4.2392
1-1/2	1.900	1.338	.281	5.4711
2	2.375	1.689	.343	8.3818
2-1/2	2.875	2.125	.375	11.2744
3	3.500	2.624	.438	16.1287
4	4.500	3.438	.531	25.3453
5	5.563	4.313	.625	37.1152

Double extra heavy

Nominal Pipe Size inch	O. D. inch	I. D. inch	Wall thickness inch	Weight per ft.
3/4	1.050	.434	.308	2.7484
1	1.315	.599	.358	4.1202
1-1/4	1.660	.896	.382	5.8710
1-1/2	1.900	1.100	.400	7.2156
2	2.375	1.503	.436	10.1668
2-1/2	2.875	1.771	.552	15.4209
3	3.500	2.300	.600	20.9252

MIL-T-1368C