

MIL-V-12276D(MR)  
AMENDMENT-1  
1 August 1973

MILITARY SPECIFICATION  
VARNISH, PHENOLIC, BAKING

This amendment forms a part of Military Specification  
MIL-V-12276D(MR) dated 4 January 1971.

PAGE 12

Paragraph 4.4.7, corrosion resistance, line 7: Delete fourth sentence and substitute "Expose the panels for 250 hours to 20 percent salt spray in accordance with method 6061 of Fed. Test Method Std. No. 141."

Custodian:  
Army - MR

Preparing activity:  
Army - MR

Review activities:  
Army - MR, MU, MD

Project No. 8010-A087

FSC 8010