

INCH POUND

MIL-W-18142C
AMENDMENT 1
5 March 1991

MILITARY SPECIFICATION

WOOD PRESERVATIVE SOLUTIONS,
OIL-SOLUBLE, SHIP AND BOAT USE

This amendment forms a part of MIL-W-18142C, dated 29 June 1990, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 4

Table I.: Delete and substitute the following:

Property	Type A	Type C
Fungicide type	Copper naphthenate	zinc naphthenate
In accordance with	AWPA P 8	B.S. 3770
Minimum concentration	68 grams/gal, as copper, at 77°F	102 grams/gal as zinc, at 77°F
Maximum concentrate	85 grams/gal, as copper, at 77°F	128 grams/gal as zinc, at 77°F
Wax content	None	None
Min. flash point	100°F	100°F
Insolubles		
Blooming	Solvent shall be free from blooming and deposits of crystals when visually inspected by the unaided eye	
Paint compatibility	Solvent shall not interfere with application, drying or adhesive of paints, nor shall it bleed through such coatings	

Page 1 of 2

AMSC N/A

DISTRIBUTION STATEMENT A.
distribution is unlimited.

Approved for public release;

FSC 8030

MIL-E-18142C
AMENDMENT 1

Custodians:

Navy - SH
Air Force - 99

Preparing activity:

Navy - SH
(Project 8030-0644)

Review activities:

Air Force - 20, 84
Army - MR