

MIL-STD-655C
19 September 1985
SUPERSEDING
MIL-STD-655B
10 March 1976

MILITARY STANDARD
PROVISIONS FOR EVALUATING QUALITY
OF
CLOTH, WOOL, WORSTED AND WOOL BLENDS



FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

MIL-STD-655C

DEPARTMENT OF DEFENSE

WASHINGTON, DC 20301

Provisions for Evaluating Quality of Cloth, Wool, Worsted and Wool Blends.

1. This Military Standard is approved for use by all Departments and Agencies of the Department of Defense.

2. Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to U.S. Army Natick Research and Development Center, Natick, MA 01760-5014, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

MIL-STD-655C

FOREWARD

This standard provides a standardized procedure for evaluating quality of woolen, worsted, and wool blended cloths procured for the Department of Defense.

As of the date of approval of this document, the following Military documents will reference this standard:

<u>DOCUMENT</u>	<u>TITLE</u>
MIL-C-823	- Cloth, Serge, Wool; Wool and Nylon, Polyester and Wool
MIL-C-3727	- Cloth, Barathea, Wool
MIL-C-3738	- Cloth, Elastique, Wool
MIL-C-10176	- Cloth, Gabardine: Wool, Polyester and Wool
MIL-C-11065	- Cloth, Flannel, Wool and Nylon, 16-Ounce, Shrink Resistant(GL)
MIL-C-16290	- Cloth, Melton, Wool (Moth-Proofed) (SA)
MIL-C-16291	- Cloth, Flannel, Wool (SA)
MIL-C-17566	- Cloth, Billiard
MIL-C-21115	- Cloth, Tropical: Wool, Polyester/Wool
MIL-C-24903	- Cloth, Elastique, Polyester/Wool (CG)
MIL-C-29405	- Cloth, Broadcloth: Wool and Wool/Nylon (MC)
MIL-C-82252	- Cloth, Broadcloth, Wool and Wool-Synthetic (Moth-Proofed) (NU)

MIL-STD-655C

CONTENTS

<u>Paragraph</u>		<u>Page</u>
1.	SCOPE	1
1.1	Purpose	1
1.2	Scope	1
2.	REFERENCED DOCUMENTS	1
2.1	Government documents	1
2.2	Order of precedence	1
3.	DEFINITIONS	2
3.1	Fabric defects	2
3.2	Quality assurance terms	3
4.	GENERAL REQUIREMENTS	3
5.	DETAILED REQUIREMENTS	4
5.1	End item examination	4
5.1.1	Yard-by-yard examination	4
5.1.2	Shade variation examination	5
5.1.3	Length examination	6
5.1.3.1	Individual roll	6
5.1.3.2	Total yardage in the sample	6
5.1.4	Roll examination	6
5.1.5	Shade match and appearance examination	6
5.1.6	Defect marking (stringing of defects) examination	6
5.2	Inspection procedures	7
6.	NOTES	7
6.1	Applicable documents	7
6.2	Sears fabric defects scales	7
6.3	Changes from previous issue	7

TABLES

<u>NUMBER</u>		<u>PAGE</u>
I	Maximum acceptable point values	5

MIL-STD-655C

1. SCOPE

1.1 Purpose. The purpose of this standard is to provide standardized examination provisions for evaluating quality of woolen, worsted, and wool blended cloths that are the basic materials for quality uniform items.

1.2 Scope. This standard will be made applicable to contracts by reference in the appropriate cloth documents.

2. REFERENCED DOCUMENTS

2.1 Government documents. Unless otherwise specified, the following documents of the issue in effect on date of invitations for bids or request for proposal, form a part of this document to the extent specified herein.

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection
by Attributes

MIL-STD-109 - Quality Assurance Terms and Definitions

(Copies of documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

OTHER GOVERNMENT DOCUMENTS

Laws and Regulations

Rules and Regulations Under the Wool Products Labeling Act

(Application for copies should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.)

2.2 Order of precedence. In the event of a conflict between the text of this standard and the references cited herein, the text of this standard shall take precedence.

MIL-STD-655C

3. DEFINITIONS

3.1 Fabric defects. The fabric defect definitions applicable to the standard are described as follows:

3.1.1 Barre. Bands, streaks, or bars in the fabric characterized by texture, tension, color, luster, or shrinkage differences.

3.1.2 Bowed or skewed filling. Cloth in which the filling yarn does not run at right angles to the warp.

3.1.3 Broken or missing yarn. A yarn partially or entirely missing.

3.1.4 Coarse or heavy yarn. A yarn larger in diameter than normally being used in the cloth.

3.1.5 Defective selvage. Selvage that is curled, folded, rolled, slack, tight, scalloped, wavy, stringy, beaded, loopy, cut, torn, missing, or raveled, or not adequately anchored to the edge of the cloth, preventing the unraveling of the edge.

3.1.6 Excess material. Extra yarn or waste which has been woven into the cloth or spun into the yarn, or extra length of yarn that has not completely been woven into the cloth.

3.1.7 Fine yarn. A yarn smaller in diameter than normally being used in the cloth.

3.1.8 Finishing imperfections. Cloth which has not been uniformly sheared, does not have the same degree and character of finish throughout, has tenting marks, or is streaked, blotched, spotted, or otherwise marked.

3.1.9 Decanting mark. A crease mark or impression extending fillingwise across the cloth.

3.1.10 Heavy or light place. A fillingwise band or bar either across the full width of the cloth or a portion of it containing more or less than the normal number of picks, or containing picks of larger or smaller diameter than normally being used in the cloth.

3.1.11 Hole. A place in the cloth where two or more contiguous yarns have been ruptured.

3.1.12 Knot. Self descriptive. To be scored when it exceeds the limits specified in the basic cloth document.

3.1.13 Misweave. Any deviation from the specified weave pattern.

MIL-STD-655C

3.1.14 Mixed yarn. Yarn which differs from that normally being used in the cloth, such as wrong twist, wrong number of plies, wrong color, or mixed yarn lots.

3.1.15 Neppiness. A speckled condition of the cloth characterized by a number of definite fiber tangles (neps).

3.1.16 Open place. An open streak or crack which results in a clearly noticeable separation between the yarns.

3.1.17 Reed mark. A mark or line running warpwise in the cloth.

3.1.18 Slub. A thick place in the yarn. To be scored when it exceeds the limits specified in the basic cloth document.

3.1.19 Spot, stain or streak. An area in the cloth or on the surface of the cloth showing discoloration, foreign matter, or soil, excluding decating marks.

3.1.20 Uneven yarn. A yarn tighter or slacker than the normal yarn in the body of the cloth.

3.1.21 Wavy cloth. Cloth that is of such a nature (baggy, ridgy, wavy, or contains crease) that it will not lie flat on a cutting table.

3.1.22 Weak spot. A place in the cloth where the surface has been damaged or has been abnormally weakened.

3.1.23 Uneven weaving. Irregular cloth characterized by conditions such as short elliptical or triangular distortions of one or more adjoining yarns, tight or slack places in the same yarn, crimped, rippled, wavy, pebbled, or cockled place in the cloth.

3.2 Quality assurance terms. Definitions of quality assurance terms shall be in accordance with MIL-STD-105 and MIL-STD-109.

4. GENERAL REQUIREMENTS

4.1 This standard contains provisions for visual examination of woolen, worsted and wool blended cloths. Fabric quality in the following quality levels shall be as specified in the applicable cloth document.

Quality Level 8
Quality Level 10
Quality Level 12
Quality Level 15

MIL-STD-655C

5. DETAILED REQUIREMENTS

5.1 End item examination.

5.1.1 Yard-by-yard examination. The total yardage of each roll in the sample shall be examined on the face side. All appropriate defects that are clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit points as specified in this paragraph. The sample size shall be in accordance with the following:

<u>Lot size (yards)</u>	<u>Sample size (rolls) 1/</u>
500 or less	8
501 up to 3,200	13
3,201 to 35,000	20
35,001 to 500,000	32
500,001 and over	50

Point value computation shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{Total yards inspected}} = \text{Points per 100 square yards}$$

The following defect, when present, shall be scored four points for each yard in which it occurs.

Width less than specified.

Except for above defect, all defects as defined in section 3.1 of this standard shall be scored and assigned demerit points as follows:

For defects 3 inches or less in any dimension	- one point
For defects exceeding 3 inches, but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches, but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

1/ No more than one roll shall be taken from any shipping container unless the number of shipping containers in the lot is less than the required number of rolls in which case all shipping containers shall be present in the sample.

MIL-STD-655C

The same yardage shall be given a through - lighting inspection on the face side of the cloth for holes and thin areas not previously scored. Slight open places resulting from removal of burrs, shives, sisal or broken picks not previously scored shall not be scored in through - lighting inspection.

Selvage defects shall be scored when the thickness of the selvage exceeds the thickness of the body of the cloth by an excessive amount $\frac{1}{2}$ or the edge of the cloth is not adequately anchored. No linear yard (increments of 1 yard on the measuring device of the inspection machine) shall be scored more than four points, however, all defects shall be recorded. The lot shall be unacceptable if:

- a. The point value per 100 square yards for the total yardage in the entire sample exceeds the applicable maximum acceptable point value (see table I).
- b. The point value per 100 square yards for the total yardage in any individual roll in the sample exceeds the applicable maximum acceptable point value (see table I).

TABLE I. Maximum acceptable point values

<u>Maximum acceptable point values</u>			
Quality Level		Entire sample	Individual rolls
Normal	8	8 points per 100 sq. yd.	12 points per 100 sq. yd.
	10	10 points per 100 sq. yd.	15 points per 100 sq. yd.
	12	12 points per 100 sq. yd.	18 points per 100 sq. yd.
	15	15 points per 100 sq. yd.	23 points per 100 sq. ud.

5.1.2 Shade variation examination. During the yard-by yard examination, each roll in the sample shall be examined for shade variation. Any roll in the sample containing uneven shade or shade variation side to side, side to center, or end to end, shall be cause for rejection of the entire lot represented by the sample.

$\frac{1}{2}$ In the case of dispute, the thickness of the selvage shall not exceed the thickness of the body of the cloth by more than 40 percent, when tested in accordance with Method 5030 of FED-STD-191.

MIL-STD-655C

5.1.3 Length examination. During the yard-by-yard examination, each roll in the sample shall be examined for length.

5.1.3.1 Individual roll. Any length found to be less than the minimum length specified in the basic cloth document or more than 2 yards less than the length marked on the ticket shall be scored as a defect. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length.

5.1.3.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual length of the rolls in the sample is less than the total of the lengths marked on the roll tickets.

5.1.4 Roll examination. During the yard-by-yard examination each roll in the sample shall be examined for defects listed below. The lot shall be unacceptable if two or more of the following defects are present in the sample:

Back stamping missing, incorrect or illegible from either or both ends or bleed through occurring.
 Back stamping on wrong side.
 Letters less than 1/2 inch in height.
 Not labeled or ticketed in accordance with the Rules and Regulations under the Wool Products Labeling Act.
 Edge of roll build-up, or softness of roll in body of cloth.

5.1.5 Shade match and appearance examination. The shade match and appearance examination shall be as specified in the applicable cloth document.

5.1.6 Defect marking (stringing of defects) examination. During the yard-by-yard examination, each roll in the sample shall be examined for defect marking. Any roll having more than 2-three or four point fabric defects (red string) not strung, or more than 5 fabric defects (red or white strings) not strung shall be classified as a defective roll in regard to the defect marking requirement.

The lot shall be unacceptable if the sample contains more than the number of defective rolls or unstrung defects indicated below:

Sample size (rolls)	Maximum number of defective rolls	Maximum number of unstrung defects
8	0	12
13	1	19
20	2	30

MIL-STD-655C

5.2 Inspection procedures. Inspection procedures, except for sampling plans, shall be as specified in MIL-STD-105, except where otherwise indicated in this document.

6. NOTES

6.1 Applicable documents. The applicable cloth document shall specify:

- a. The fabric quality level (see 4.1).
- b. Shade match and finish requirements (see 5.1.5).
- c. Limits for slub and knot. (Limits to be specified can be found on the Sears Fabric Defect Scales).
- d. Requirements for stringing of defects.

6.2 Sears fabric defect scales. Sears Fabric Defect Scales are available from Sears, Roebuck and Company, Department 817 (ATTN: BSC 23-29), Sears Tower, Chicago, IL 60684.

6.3 Changes from previous issue. Asterisks or vertical lines are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - NU
Air Force - 11

Preparing activity:

Army - GL
Project No. 8305-0011

Review activities:

Navy - MC
Air Force - 82, 99
DLA - CT

User activity:

Navy - AS

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge (*DO NOT STAPLE*), and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

US ARMY NATICK RESEARCH
and DEVELOPMENT CENTER
ATTN: STRNC-ES
Natick, MA 01760-5014

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE \$300



NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY MAIL

FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research
and Development Center
ATTN: STRNC-ES
Natick, MA 01760-5014



