

MIL-STD- 715 (NORC)16 June 1959

Supersedes NAVORD OS 8718

dated March 26, 1958

MILITARY STANDARDFORMULA FOR YELLOW DYE MIXTURE

Ingredient	Auramine Hydrochloride	Guanidine Nitrate	Anthracene
Specification	MIL-A-3664	MIL-G-21352	JAN-A-202 Class B
Percent by Weight	45.0 ± 1.0	45.0 ± 1.0	10.0 ± 0.5

The ingredients shall be blended until a uniform mixture is obtained.

The moisture content of the dye mixture shall not exceed 2.0 percent when tested as specified in Section 4.4 of MIL-B-162.

CAUTION: For safety reasons, the usual precautions for handling and blending of pyrotechnic mixtures must be observed in handling the dry mixture. See section 6.7 of MIL-P-21355 for general safety precautions.

The Replacement Sample Powder Tank Mk 1 Mods, BuOrd Dwg. 423038 has been found satisfactory for handling and storage of the mixture.

Copies of specifications, standards, drawings and publications required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.

FSC 1375

NOTICE: When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may be in any way related thereto. Referenced documents shall be the basis in effect on date of invitation for bids.