

MIL-STD-1623A(SHIPS)
20 MAY 1974
SUPERSEDING
MIL-STD-1623(SHIPS)
10 SEPTEMBER 1973
(SEE 5.4)

MILITARY STANDARD

**FIRE PERFORMANCE REQUIREMENTS AND
APPROVED SPECIFICATIONS FOR INTERIOR
FINISH MATERIALS AND FURNISHINGS**

(NAVAL SHIPBOARD USE)



FSC MISC

MIL-STD-1623A(SHIPS)
20 May 1974

DEPARTMENT OF THE NAVY
NAVAL SHIP SYSTEMS COMMAND
WASHINGTON, D.C. 20362

Fire Performance Requirements and Approved Specifications for
Interior Finish Materials and Furnishings (Naval Shipboard Use)
MIL-STD-1623A(SHIPS)

- #
1. This Military Standard is approved for use by the Naval Ship Systems Command and is available for use by all Departments and Agencies of the Department of Defense.
 2. Recommended corrections, additions, or deletions should be addressed to Commander, Naval Ship Engineering Center, Department of the Navy, Center Building, Prince George's Center, Hyattsville, Maryland 20782.

MIL-STD-1623A(SHIPS)
20 May 1974

FOREWORD

The purpose of this standard is to establish fire performance criteria and provide a list of approved specifications for interior finish materials and furnishings to be used on new and existing Naval ships and submarines.

Although the development of limits for toxic products of combustion is of major concern, the information generally available is not refined to the degree to allow inclusion of finite limits in this standard at this time.

Where no fire test limits appear, technical data was not available as of the date of this standard.

MIL-STD-1623A (SHIPS)
20 May 1974

CONTENTS

	Page
1. SCOPE AND APPLICATION.	1
1.1 Scope	1
1.2 Application	1
2. REFERENCED DOCUMENTS	1
3. REQUIREMENTS	2
3.1 Materials	2
4. FIRE TEST PROVISIONS	7
4.1 Responsibility for testing.	7
4.2 Methods of testing.	7
4.2.1 Surface flammability.	7
4.2.2 Vertical flame resistance	7
4.2.3 Smoke generation.	7
4.2.4 Test for incombustibility	7
5. NOTES.	7 and 8

TABLE

I	Material requirements	3 through 7
---	---------------------------------	-------------

MIL-STD-1623A (SHIPS)
20 May 1974

1. SCOPE AND APPLICATION

1.1 Scope. This standard provides fire performance requirements and approved specifications for eight categories of interior finish materials and furnishings for use on new and existing surface ships and submarines.

1.2 Application. This standard applies to materials for bulkhead sheathing, overhead sheathing, furniture, draperies and curtains, adhesives, deck coverings, thermal insulation, and acoustic materials applications. The fire performance requirements of this standard supersede those contained in the applicable specifications.

2. REFERENCED DOCUMENTS

2.1 The issues of the following documents in effect on the date of invitation for bids form a part of this standard to the extent specified herein.

GOVERNMENTAL

SPECIFICATIONS

FEDERAL

L-F-450 - Flooring, Vinyl Plastic.
L-F-475 - Floor Covering Vinyl, Surface (Tile and Roll), With Racking.
HH-I-551 - Insulation Block, Pipe Covering and Boards, Thermal (Cellular Glass).
QQ-A-250/19 - Aluminum Alloy 5086, Plate and Sheet for Sea Water Application.
SS-C-160 - Cements, Insulation, Thermal.
SS-S-118 - Sound Controlling Blocks and Boards (Acoustical Tiles and Panels, Prefabricated).
SS-T-312 - Tile, Floor, Asphalt, Rubber, Vinyl, Vinyl-Asbestos.
ZZ-M-42 - Mats, Floor, Dental-Chair, Rubber.
CCC-A-680 - Artificial Leather (Cloth Coated), Vinyl Resin, Expanded Layer, (Upholstery).
CCC-C-436 - Cloth, Ticking Twill, Cotton.
CCC-C-700 - Cloth, Coated, Vinyl Coated (Artificial Leather).
CCC-C-1703 - Cloth, Drapery, Glass Fiber.
CCC-W-408 - Wall Covering, Vinyl-Coated.
LLL-F-1238 - Floor Covering, Linoleum.
MMM-A-130 - Adhesive, Contact.

MILITARY

MIL-I-742 - Insulation Board, Thermal, Fibrous Glass.
MIL-M-910 - Mats, Floor, Standing.
MIL-I-2781 - Insulation, Pipe, Thermal.
MIL-I-2818 - Insulation Blanket, Thermal, Fibrous Mineral.
MIL-I-2819 - Insulation Block, Thermal.
MIL-D-3134 - Deck Covering Materials.
MIL-D-3135 - Deck Covering Underlay Materials.
MIL-A-3316 - Adhesives, Fire-Resistant, Thermal Insulation.
MIL-P-15280 - Plastic Material, Unicellular (Sheets and Tubes).
MIL-I-15475 - Insulation Felt, Thermal, Fibrous Glass Semirigid.
MIL-M-15562 - Matting, Floor, Rubber.
MIL-I-16411 - Insulation Felt, Thermal, Glass Fiber.
MIL-D-16680 - Deck Covering Magnesia Aggregate Mixture.
MIL-T-17171 - Table Top, Plastic; Thermosetting Resin.
MIL-D-17951 - Deck Covering, Lightweight, Nonslip, Silicon Carbide Particle Coated Fabric and Sealing Compound.
MIL-T-18830 - Tile, Plastic, Fire Retardant.
MIL-M-19018 - Mats, Floor, Rubber or Plastic, Light Gray; for Shipboard Shower Stalls.
MIL-C-19565 - Coating Compounds, Thermal Insulation Pipe Covering -- Fire- and Water-Resistant, Vapor-Barrier and Weather-Resistant.
MIL-C-19993 - Coating Compound, Fibrous Glass Thermal Insulation Board, Water Vapor Barrier.
MIL-C-20079 - Cloth, Glass; Tape, Textile, Glass; and Thread, Glass.
MIL-R-20092 - Rubber Sheets and Molded Shapes, Cellular, Synthetic Open Cell (Foamed Latex).
MIL-A-21016 - Adhesive, Resilient Deck Covering.

MIL-STD-1623A (SHIPS)
20 May 1974

MILITARY (Cont'd)

- MIL-D-21631 - Deck Covering, Latex Concrete (For Ammunition Ships).
- MIL-I-22023 - Insulation Felt, Thermal and Sound Absorbing Felt, Fibrous Glass, Flexible.
- MIL-I-22344 - Insulation, Pipe, Thermal, Fibrous Glass.
- MIL-C-22395 - Compound, End Sealing, Thermal Insulation Pipe Covering -- Fire-, Water-, and Weather-Resistant.
- MIL-P-22581 - Plastic Sheet, Vibration Damping.
- MIL-D-23003 - Deck Covering Compound, Nonslip, Lightweight.
- MIL-A-23054 - Acoustical Absorptive Board, Fibrous Glass, Perforated Fibrous Glass Cloth Faced.
- MIL-I-23128 - Insulation Blanket, Thermal, Refractory Fiber, Flexible.
- MIL-P-23653 - Plastic Tiles, Vibration Damping.
- MIL-P-24062 - Sprayable Vibration Damping Material for Light Steel Plate.
- MIL-I-24172 - Insulation, Plastic, Cellular Polyurethane, Rigid, Preformed and Foam-in-Place.
- MIL-A-24179 - Adhesive, Flexible Unicellular-Plastic Thermal Insulation.
- MIL-P-24191 - Plastic Sheet, Cast, Acrylic, Shipboard Application (Illumination and Signal Lighting).
- MIL-A-24456 - Adhesive for Plastic Vibration-Damping Tiles.
- MIL-D-24483 - Deck Covering, Spray-On, Nonslip.
- MIL-C-24500 - Cloth, Drapery, Bunk Curtain, Slipcovers, and Label, Polyaramid and Polyaramid/Novoloid Fiber Blends, Shipboard Use.

STANDARDS

FEDERAL

- FED-STD-191 - Textile Test Methods.
- FED-STD-501 - Floor Coverings, Resilient, Nontextile: Sampling and Testing.

PUBLICATION

UNITED STATES COAST GUARD

U.S.C.G. 164.009 - Test for Incombustibility.

(Application for copies should be addressed to the U.S. Coast Guard Headquarters, 400 Seventh Street, S.W., Washington, D.C. 20591.)

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

NONGOVERNMENTAL

AMERICAN IRON AND STEEL INSTITUTE (AISI) Steel Products Manual

(Application for copies should be addressed to the American Iron and Steel Institute, 150 East Forty Second Street, New York, New York 10017.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

- E84-70 - Surface Burning Characteristics of Building Materials, Test for.
- E162-67 - Surface Flammability of Materials Using a Radiant Heat Energy Source, Test for.
- STP 422 - Special Technical Publication. Method for Measuring Smoke from Burning Materials.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using federal agencies.)

MIL-STD-1623A (SHIPS)
20 May 1974

3. REQUIREMENTS

3.1 **Materials.** Interior finish materials and furnishings shall meet the requirements set forth in table I. Thicknesses for bulkhead sheathing, overhead sheathing, and furniture indicates maximum limits in both application and fire tests.

Table I - Material requirements.

Category	Material	Specification	Fire test	Maximum Test limits
# Bulkhead sheathing-1/	High pressure laminate for vertical surfaces	MIL-T-17171, type IV	ASTM E84-70	Flame spread _____ 25 Smoke developed _____ 15 Thickness _____ 0.045 inch
	Fabric-backed vinyl	CCC-W-408, type II	ASTM E84-70	Flame spread _____ 25 Smoke developed _____ 15 Thickness _____ 0.025 inch
	Unsupported vinyl film-aluminum lamination	QQ-A-250/19, (for aluminum only)	ASTM E84-70	Flame spread _____ 25 Smoke developed _____ 15 Thickness film _____ 0.010 inch Thickness aluminum _____ 0.063 inch
	CRES panel	AISI type 304, finish 4	Not applicable	Not applicable
# Overhead sheathing-2/	Fibrous glass opaque suspended ceiling panel	SS-S-118, type IX	ASTM E84-70	Flame spread _____ 25 Smoke developed _____ 35 Thickness _____ 0.750 inch
	Ceramic opaque suspended ceiling panel	SS-S-118, type IX	ASTM E84-70	Flame spread _____ 25 Smoke developed _____ 25 Thickness _____ 0.750 inch
	Acrylic light-diffusing panels/windows (lighting fixture only)	MIL-P-24191,	ASTM E84-70	Flame spread _____ 250 Smoke developed _____ 450 Thickness _____ 0.250 inch
	Vinyl clad perforated aluminum panel	QQ-A-250/19, (for aluminum only)	ASTM E84-70	Flame spread _____ 25 Smoke developed _____ 15 Thickness film _____ 0.010 inch Thickness aluminum _____ 0.063 inch
	CRES panel	AISI type 304, finish 4	Not applicable	Not applicable
	Steel or aluminum exposed grid suspension framework	Commercial	Not applicable	Not applicable
# Furniture	Vinyl upholstery	CCC-A-680, class 2, treatment (a) 1	FED-STD-191, method 5903	Char length _____ 3 inch After flame _____ 2 sec
	Vinyl upholstery	CCC-C-700, class 4, treatment a (1)	FED-STD-191, method 5903	Char length _____ 3 inch After flame _____ 2 sec
	Aromatic polyamide upholstery	Commercial	FED-STD-191, method 5903	Char length _____ 5 inch After flame _____ 1 sec
	Treated cotton ticking	CCC-C-436, type II, class 2	FED-STD-191, method 5903	Char length _____ 5 inch After flame _____ 2 sec

See footnotes at end of table.

MIL-STD-1623A (SHIPS)
20 May 1974

Table I - Material requirements (cont'd).

Category	Material	Specification	Fire test	Maximum Test limits
# Furniture (cont'd)	Neoprene cushioning and mattresses	MIL-R-20092, type II, class 4	ASTM E162-67	Flame spread index _____ 10
	High pressure laminate for table tops	MIL-T-17171, Type I	ASTM E84-70 (bonded)	Flame spread _____ 75 Smoke developed _____ 50 Thickness _____ 0.062 inch
# Draperies and curtains ^{3/}	Fibrous glass	CCC-C-1703	FED-STD-191, method 5903 STP 422	Char length _____ 1.5 inch After flame _____ 1 sec After glow _____ 2 sec DM corrected _____ 20
#	Polyaramid	MIL-C-24500 Type I	FED-STD-191, method 5903 STP 422	Char length _____ 5 inch After flame _____ 1 sec After glow _____ 5 sec DM corrected _____ 20
#	Polyaramid/ Noroloid NOVOLOID <i>yes</i>	MIL-C-24500 Type II	FED-STD-191, method 5903 STP 422	Char length _____ 5 inch After flame _____ 1 sec After glow _____ 5 sec DM corrected _____ 20
# Adhesives ^{4/}	Contact adhesive (sheathing on surface ships)	MMM-A-130		
	Contact adhesive (sheathing on submarines)	MIL-A-24179, Type I		
	Deck tile adhesive	MIL-A-21016		
	Carpet cement	Commercial		
	Bead sealer	MIL-D-17951		
	Thermal insulation	MIL-A-3316, class I		
	Thermal insulation cement	SS-C-160		
	Damping tile cement	MIL-A-24456		
# Deck coverings	Vinyl asbestos tile	MIL-T-18830	FED-STD-501, method 6411	Char length _____ 10 inch Combustion + ignition _____ 4.0 min
	Vinyl tile	SS-T-312, type III	FED-STD-501, method 6411	Char length _____ Combustion + ignition _____
	Vinyl sheet	L-F-450	FED-STD-501, method 6411	Char length _____ Combustion + ignition _____
	Rubber roll	SS-T-312, type II	ASTM E162-67	Flame spread index _____ 25

See footnotes at end of table

MIL-STD-1623A (SHIPS)
20 May 1974

Table I - Material requirements (cont'd).

Category	Material	Specification	Fire test	Maximum Test limits
Deck coverings (cont'd)	Vinyl tile or sheet with backing	L-F-475	FED-STD-501, method 6411	Char length _____ Combustion + ignition _____
	Conductive linoleum	LLL-F-1238, type II, grade H	FED-STD-501, method 6411	Char length _____ Combustion + ignition _____
	Treads - non skid	MIL-D-17951	FED-STD-501, method 6411	Char length _____ 8 inch Combustion + ignition _____ 4.0 min
	Epoxy non-skid	MIL-D-23003	FED-STD-501, method 6411	Char length _____ 6 inch Combustion + ignition _____ 4.25 min
	Latex underlay	MIL-D-3135	FED-STD-501, method 6411	Char length _____ 8 inch Combustion + ignition _____ 4.5 min
	Terrazzo	MIL-D-3134, type I, class 1 type I, class 2	FED-STD-501, method 6411	Char length _____ 7 inch Combustion + ignition _____ 4.0 min
	Latex mastic	MIL-D-3134, type II, class 1	FED-STD-501, method 6411	Char length _____ 7 inch Combustion + ignition _____
	Latex concrete	MIL-D-21631	FED-STD-501, method 6411	Char length _____ 3 inch Combustion + ignition _____ 4.0 min
	Magnesium aggregate	MIL-D-16680	FED-STD-501, method 6411	Char length _____ 3 inch Combustion + ignition _____ 4.0 min
	Standing rubber mat	MIL-M-910	FED-STD-501, method 6411	Char length _____ Combustion + ignition _____
	Electrical grade rubber mat	MIL-M-15562	FED-STD-501, method 6411	Char length _____ 10 inch Combustion + ignition _____
	Shower mat	MIL-M-19018	FED-STD-501, method 6411	Char length _____ Combustion + ignition _____
	Beta fibrous glass carpet	Commercial	ASTM E162-67 without pad	Flame spread index _____ 25
	Aromatic polyamide carpet	Commercial	ASTM E162-67 without pad	Flame spread index _____ 25
	Spray-on non skid	MIL-D-24483	FED-STD-501, method 6411	Char length _____ 6 inch Combustion + ignition _____ 4.25 min
	Barber shop mat	ZZ-M-42	FED-STD-501, method 6411	Char length _____ Combustion + ignition _____

See footnotes at end of table.

MIL-STD-1623A (SHIPS)
20 May 1974

Table I - Material requirements (cont'd).

Category	Material	Specification	Fire test	Maximum Test limits
# Thermal ^{5/} insulation	Insulating board	MIL-I-742	U.S.C.G. 164.009	Pass
	Pipe insulation	MIL-I-2781	U.S.C.G. 164.009	Pass
	Block insulation	MIL-I-2819	U.S.C.G. 164.009	Pass
	Insulating blanket	MIL-I-23128	U.S.C.G. 164.009	Pass
	Insulating felt	MIL-I-16411	U.S.C.G. 164.009	Pass
	Insulating block	HH-I-551	U.S.C.G. 164.009	Pass
	Insulating blanket	MIL-I-2818	U.S.C.G. 164.009	Pass
	Insulating felt	MIL-I-15475	U.S.C.G. 164.009	Pass
	Coating compound	MIL-C-19565	ASTM E84-70 (bonded)	Flame spread _____ Smoke developed _____ 25
	Coating compound	MIL-C-19993	ASTM E84-70 (bonded)	Flame spread _____ Smoke developed _____ 25
	Glass cloth	MIL-C-20079	FED-STD-191, method 5903	Char length _____ After flame _____ After glow _____
	Pipe insulation	MIL-I-22344	ASTM E84-70 (bonded)	Flame spread _____ Smoke developed _____ 25
	Urethane foam	MIL-I-24172	ASTM E84-70 (bonded)	Flame spread _____ Smoke developed _____ 25
	End sealer	MIL-C-22395	ASTM E84-70 (bonded)	Flame spread _____ Smoke developed _____ 25
	PVC - Nitrile	MIL-P-15280	ASTM E84-70 STP 422	Flame spread _____ Optical smoke density _____ 250 Thickness _____ 0.5 inch
# Acoustic materials	Acoustic board	MIL-I-22023	ASTM E84-70 (bonded)	Flame spread _____ Smoke developed _____
	Acoustic insulation	MIL-A-23054	U.S.C.G. 164.009	Pass
	PVC graphite	MIL-P-23653 class 1, 2	ASTM E162-67	Flame spread index _____
	Epoxy-sand (sheet)	MIL-P-22581	ASTM E162-67	Flame spread index _____

See footnotes at end of table.

MIL-STD-1623A (SHIPS)
20 May 1974

Table I - Material requirements (cont'd).

Category	Material	Specification	Fire test	Maximum Test limits
Acoustic materials	Epoxy-sand (sprayable)	MIL-S-24062	ASTM E162-67	Flame spread index _____
	Felt-chromate	Commercial	ASTM E162-67	Flame spread index _____
	Vibration damping plastic tiles	MIL-P-23653, class 3	ASTM E162-67	Flame spread index _____

- 1/ Maximum test limits are based upon material bonded to a non-combustible substrate.
 2/ Maximum test limits are based upon material attached to, or supported by, a non-combustible substrate.
 # 3/ An 8-ounce weight shall be used for materials tested in accordance with FED-STD-191, method 5903.
 # 4/ Fire test limits are not required.
 5/ Materials tested in accordance with U.S.C.G. 164.009 shall pass all requirements for incombustibility.

4. FIRE TEST PROVISIONS

4.1 Responsibility for testing. Unless otherwise required in the applicable material specification, the manufacturer is responsible for conducting fire tests as specified herein. Except as otherwise specified, the manufacturer may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the tests set forth herein where such testing is deemed necessary to assure compliance to prescribed requirements.

4.2 Methods of testing. Fire tests shall be conducted on materials as specified in table I and the notes therein. All fire test procedures shall be in accordance with prescribed standards and test methods, and, unless otherwise specified herein, no less than three specimens shall be tested on material of the same lot with results averaged (arithmetic means). The following tests apply:

4.2.1 Surface flammability.

4.2.1.1 ASTM E84-70 (Tunnel test).

4.2.1.2 ASTM E162-67 (Radiant panel).

4.2.1.3 FED-STD-501, Method 6411.

4.2.2 Vertical flame resistance.

4.2.2.1 FED-STD-191, Method 5903 - A minimum of five specimens from each of the warp and filling directions on material of the same lot shall be tested and their results averaged (arithmetic means).

4.2.3 Smoke generation.

4.2.3.1 ASTM E84-70 (Tunnel test).

4.2.3.2 STP 422 (NBS Smoke Chamber).

4.2.4 Test for incombustibility.

4.2.4.1 U.S.C.G. 164.009 (Heated Tube Test).

5. NOTES

5.1 This standard will be updated periodically as additional data becomes available.

MIL-STD-1623A(SHIPS)
20 May 1974

5.2 This standard will be implemented by the requirements of the applicable material specifications.

5.3 The materials specified in this standard reflect the present state-of-the-art.

5.4 THE MARGINS OF THIS STANDARD ARE MARKED "*" TO INDICATE WHERE CHANGES (ADDITIONS, MODIFICATIONS, CORRECTIONS, DELETIONS) FROM THE PREVIOUS ISSUE HAVE BEEN MADE. THIS WAS DONE AS A CONVENIENCE ONLY AND THE GOVERNMENT ASSUMES NO LIABILITY WHATSOEVER FOR ANY INACCURACIES IN THESE NOTATIONS. BIDDERS AND CONTRACTORS ARE CAUTIONED TO EVALUATE THE REQUIREMENTS OF THIS DOCUMENT BASED ON THE ENTIRE CONTENT IRRESPECTIVE OF THE MARGINAL NOTATIONS AND RELATIONSHIP TO THE LAST PREVIOUS ISSUE.

Preparing activity:
Navy - SH
(Project MISC-N960)

☆ U.S. GOVERNMENT PRINTING OFFICE: 1972—714-863/3404 2-1

FOLD

COMMANDER
NAVAL SHIP ENGINEERING CENTER
CENTER BUILDING - SEC 6124B
PRINCE GEORGE'S CENTER
HYATTSVILLE, MARYLAND 20782

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE \$300

POSTAGE AND FEES PAID
DEPARTMENT OF NAVY

DOD 316



COMMANDER
NAVAL SHIP ENGINEERING CENTER
CENTER BUILDING - SEC 6124B
PRINCE GEORGE'S CENTER
HYATTSVILLE, MARYLAND 20782

FOLD