

METRIC

MIL-STD-1893(AT)

~~14 August 1991~~

SUPERSEDING

(see 6.1)

MILITARY STANDARD

CLEANING ELECTROCHEMICALLY MACHINED NICKEL
BASE ALLOY SURFACES, PROCESS FOR (METRIC)



AMSC N/A

DISTRIBUTION STATEMENT A.
unlimited.

Approved for public release: distribution is

AREA MFFF

MIL-STD-1893(AT)

FOREWORD

1. This Military Standard is approved for use by U.S. Army Tank-Automotive Command, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

2. Beneficial comments (recommendations; additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Tank-Automotive Command, ATTN: AMSTA-GDS, Warren, MI 48397-5000, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

3. The intent of this standard is to define the process used for removing contaminants from electrochemically machined surfaces of nickel base alloy parts.

MIL-STD-1893(AT)

CONTENTS

		Page
Paragraph 1.	SCOPE	1
1.1	Scope	1
2.	REFERENCED DOCUMENTS (Not applicable)	2
3.	DEFINITIONS (Not applicable)	3
4.	GENERAL REQUIREMENTS	4
4.1	Equipment	4
4.1.1	Dipping racks	4
4.2	Materials	4
4.2.1	Degreaser solution	4
4.2.2	Decontamination solution	4
5.	DETAILED REQUIREMENTS	5
5.1	Procedure	5
6.	NOTES	6
6.1	Intended use	6
6.2	Supersession	6
6.3	Subject term (key word) listing	6

MIL-STD-1893(AT)

1. SCOPE

1.1 Scope. This standard defines the process used for removing contaminants from electrochemically machined surfaces of nickel base alloy parts.

MIL-STD-1893(AT)

2. REFERENCED DOCUMENTS

(This section is not applicable to this standard.)

MIL-STD-1893(AT)

3. DEFINITIONS

(This section is not applicable to this standard.)

MIL-STD-1893(AT)

4. GENERAL REQUIREMENTS

4.1 Equipment.

4.1.1 Dipping racks. Plastic coated or stainless steel racks shall be used when immersing parts in decontamination solution.

CAUTION: Iron or low alloy steel racks and handling equipment shall not be used for immersion in solution.

4.2 Materials.

4.2.1 Degreaser solution. Stabilized 1-1-1 trichloroethane.

4.2.2 Decontamination solution. The solution shall be formulated using equal parts by volume of water and nitric acid (HNO_3 , 40° Baume) plus 5 milliliters (0.17 ounce) of hydrochloric acid (HCl , concentrated) for each 3.78 liters (one gallon) of solution.

MLL-STD-1893(AT)

5. DETAILED REQUIREMENTS

5.1 Procedure. The parts shall be cleaned as follows (see 4.1.1 for caution note):

- a. Vapor degrease (see 4.2.1) parts paying special attention to cored passages and narrow openings.
- b. Pressure flush passages and parts with clean cold running water of maximum 100 degrees Celsius ($^{\circ}\text{C}$) [100 degrees Fahrenheit ($^{\circ}\text{F}$)].
- c. Immerse parts in decontamination solution (see 4.2.2) at room temperature for 50 ± 5 minutes.
- d. Pressure flush passages and parts with clean cold running water [maximum 38°C (100°F)].
- e. Rinse in hot water [$54 - 60^{\circ}\text{C}$ ($120 - 140^{\circ}\text{F}$)].
- f. Dry passages and parts with pressure blasts of filtered clean air.
- g. If necessary, repeat steps a thru f to insure complete removal of surface contaminants.

MIL-STD-1893(AT)

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. This standard is intended to define the process for removing contaminants from electrochemically machined surfaces of nickel base alloy parts.

6.2 Supersession. This military standard supersedes AVCO Lycoming Division, internal specification P7207A, dated 27 March 1975.

6.3 Subject term (key word) listing.

Contaminant
Decontamination solution
Degreaser
Dripping racks
Electrochemical
Hydrochloric acid
Nickel base alloy
Nitric acid
Trichloroethane

Custodian:
Army - AT

Preparing activity:
Army - AT

(Project MFFP-A491)

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. **AREA:** MFP

DOCUMENT IDENTIFIER (Number) AND TITLE MIL-STD-1893(AT); Cleaning Electrochemically Machined Base Alloy Surfaces, Process for. (Metric)
NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ **VENDOR** ☐ **USER** ☐ **MANUFACTURER**

1. ☐ **HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?** ☐ **IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.**

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY (Printed or typed name and address — Optional)

TELEPHONE NO.

DATE

DD FORM 1426
1 OCT 76

EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

FOLD

U.S. ARMY TANK - AUTOMOTIVE COMMAND
ATTN: AMSTA-GDS
WARREN, MICHIGAN 48397-5000

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE \$300

POSTAGE AND FEES PAID



U.S. ARMY TANK - AUTOMOTIVE COMMAND
ATTN: AMSTA-GDS
WARREN, MICHIGAN 48397-5000

FOLD