

INCH-POUND

MIL-STD-2175A
25 August 1993
SUPERSEDING
MIL-STD-2175
12 OCTOBER 1984

MILITARY STANDARD

CASTINGS, CLASSIFICATION AND INSPECTION OF



AMSC - N/A

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

AREA NDTI

MIL-STD-2175A

FOREWORD

1. This military standard is approved for use by all Departments and Agencies of the Department of Defense.

2. Beneficial comments (recommendations, additions, and deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commanding Officer, Naval Air Warfare Center Aircraft Division Lakehurst, Systems Requirements Department, Code SR3, Lakehurst, NJ 08733-5100, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

MIL-STD-2175A

CONTENTS

<u>PARAGRAPH</u>		<u>PAGE</u>
1.	SCOPE	1
1.1	Purpose	1
1.2	Applicability	1
1.2.1	Casting methods	1
1.2.2	Casting alloys	1
1.3	Classification	1
1.3.1	Classes	1
1.3.2	Grades	1
2.	APPLICABLE DOCUMENTS	3
2.1	Government documents	3
2.1.1	Specifications and standards	3
2.2	Non-Government publications	3
2.3	Order of precedence	4
3.	DEFINITIONS	5
3.1	Alloy	5
3.2	Casting	5
3.3	Chaplet	5
3.4	Cold shut	5
3.5	Contracting agency	5
3.6	Defect	5
3.7	Diffraction	5
3.8	Discontinuity	5
3.9	Foreign material	5
3.10	Gas holes	5
3.11	Gas porosity	5
3.12	Hot tear	5
3.13	Inclusions	6
3.14	Insert	6
3.15	Misruns	6
3.16	Penetrameter or image quality indicator (IQI)	6
3.17	Radiographic quality level	6
3.18	Segregation	6
3.19	Shrinkage	6
3.20	Shrinkage cavity	6
3.21	Surface irregularities	6
3.22	Visual inspection	6
4.	GENERAL REQUIREMENTS	7
4.1	Personnel qualification	7
4.2	Inspection sequence	7
4.3	Discontinuity removal	7
4.4	Classification of castings	7
4.4.1	Determination of classes and grades	7
4.4.2	Class 1 casting requirements	7
4.5	Inspection lot	7

MIL-STD-2175A

CONTENTS

<u>PARAGRAPH</u>	<u>PAGE</u>
5. DETAIL REQUIREMENTS	8
5.1 Outline of inspections	8
5.1.1 Visual inspection	8
5.1.2 Magnetic particle and liquid penetrant inspection	8
5.1.3 Radiographic inspection	8
5.2 Sampling	8
5.2.1 Visual inspection	8
5.2.2 Magnetic particle and liquid penetrant inspection	8
5.2.3 Radiographic inspection	8
5.3 Inspection methods and acceptance criteria	8
5.3.1 Visual inspection	8
5.3.1.1 Surface roughness	9
5.3.1.2 Gate, riser, and parting line projections	9
5.3.1.3 Surface pits and raised metal	9
5.3.2 Magnetic particle and liquid penetrant inspection	9
5.3.2.1 Inspection method for ferromagnetic materials	9
5.3.2.2 Inspection method for nonferromagnetic materials	9
5.3.2.3 Magnetic particle and liquid penetrant acceptance criteria	10
5.3.3 Radiographic inspection	10
5.3.3.1 Radiographic inspection method	10
5.3.3.2 Radiographic reference standards	10
5.3.3.3 Radiographic acceptance criteria	10
5.4 Reinspection	10
5.4.1 Reinspection of rejected lots	10
5.4.2 Individual casting rejection	11
6. NOTES	12
6.1 Intended use	12
6.2 Issue of DoDISS	12
6.3 Data requirements	12
6.4 Sampling	12
6.5 Cross reference	13
6.6 Radiographic quality grades for machined areas	13
6.7 Producibility considerations	13
6.8 Observational standards	13
6.9 Ultrasonic inspection of thick castings	13
6.10 Subject term (key word) listing	14
6.11 Changes from previous issue	14

TABLE

1. Sampling, radiographic inspection of class 2 castings, and magnetic particle and liquid penetrant inspection of class 4 castings	15
2. Sampling, radiographic inspection of class 3 castings	15
3. Maximum allowable gate, riser, and parting line projections	15
4. Maximum permissible discontinuity size and distribution (in inches) for magnetic particle (MT) and liquid penetrant (PT) inspection	16
5. Notes for tables 6 through 14	18

MIL-STD-2175A

CONTENTS

<u>TABLE</u>		<u>PAGE</u>
6.	Maximum permissible radiographic severity levels for discontinuities in aluminum castings per ASTM E 155.	19
7.	Maximum permissible radiographic severity levels for discontinuities in magnesium castings per ASTM E 155	20
8.	Maximum permissible radiographic severity levels for discontinuities in investment steel castings 1 in. wall or less per ASTM E 192 . . .	21
9.	Maximum permissible radiographic severity levels for discontinuities in heavy walled steel castings 2-4.5 in. per ASTM E 186	22
10.	Maximum permissible radiographic severity levels for discontinuities in steel castings up to 2 in. in thickness per ASTM E 446.	23
11.	Maximum permissible radiographic severity levels for discontinuities in heavy walled 4.5 - 12 in. steel castings per ASTM E 280	24
12.	Maximum permissible radiographic severity levels for discontinuities in high-strength copper-base and nickel-copper alloy castings up to 2 in. in thickness per ASTM E 272	25
13.	Maximum permissible radiographic severity levels for discontinuities in high-strength copper-base and nickel-copper alloy castings 2 - 6 in. in thickness per ASTM E 272	26
14.	Maximum permissible radiographic severity levels for discontinuities in tin bronze castings up to 2 in. in thickness per ASTM E 310 . . .	27
 <u>APPENDIX</u>		
A	TEST REPORT TECHNICAL CONTENT REQUIREMENTS	28

MIL-STD-2175A

1. SCOPE

1.1 Purpose. The purpose of this military standard is to prescribe the non-destructive testing acceptance criteria for the inspection of metal castings that are classified (see 1.3) in accordance with this standard.

1.2 Applicability.

1.2.1 Casting methods. This standard is intended to apply to all casting methods except high pressure die castings (such as the ones covered by ASTM B 85, "Aluminum Alloy Die Castings").

1.2.2 Casting Alloys. This standard applies to casting alloys that fall under one of the alloy families covered in tables 6 through 14 of this standard. Alloys that do not belong to any of the alloy families covered in tables 6 through 14 may be inspected to this standard in accordance with 5.3.3.2.

1.3 Classification. Castings that are inspected in accordance with this standard are classified by classes and applicable grades. The class governs the frequency of inspection (see 6.4), while the grade controls the quality of the casting.

1.3.1 Classes. For design information only, castings are classified as follows:

- a. Class 1. A casting, the single failure of which would endanger the lives of operating personnel, or cause the loss of a missile, aircraft, or other vehicle.
- b. Class 2. A casting, the single failure of which would result in a significant operational penalty. In the case of missiles, aircraft, and other vehicles, this includes loss of major components, unintentional release or inability to release armament stores, or failure of weapon installation components.
- c. Class 3. Castings not included in Class 1 or Class 2 and having a margin of safety of 200 percent or less.
- d. Class 4. Castings not included in Class 1 or Class 2 and having a margin of safety greater than 200 percent.

1.3.2 Grades. Castings, or sections of a casting, shall be of grades A, B, C or D as shown in Tables 6 through 14 for radiographic requirements, and table 4 for magnetic particle and liquid penetrant requirements. For design information only, definitions for the grades are shown below:

- a. Grade A - The highest quality grade of casting, or area of a casting, with minimum allowable discontinuities and very difficult to produce except in local areas.

MIL-STD-2175A

- b. Grade B - The second highest quality grade of casting, or area of a casting, which allows slightly more discontinuities than grade A, and difficult to produce, except in local areas.
- c. Grade C - A high quality grade of casting, or area of a casting, that can be consistently produced.
- d. Grade D - The lowest quality grade of a casting, or area of a casting, that is easily produced and is used primarily for low stress or noncritical areas adjacent to the higher graded areas.

MIL-STD-2175A

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Standards and Specifications (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

MILITARY

MIL-I-25135 - Inspection Materials, Penetrants

STANDARDS

MILITARY

MIL-STD-410 - Nondestructive Testing Personnel Qualification and Certification

MIL-STD-453 - Inspection, Radiographic

MIL-STD-6866 - Inspection, Liquid Penetrant

(Unless otherwise indicated, copies of military specifications and standards are available from the DODSSP, Subscription Services Desk, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM E 155 - Reference Radiographs for Inspection of Aluminum and Magnesium Castings

ASTM E 186 - Reference Radiographs for Heavy-walled (2 to 4.5 in. (51 to 114 mm)) Steel Castings

ASTM E 192 - Reference Radiographs of Investment Steel Castings for Aerospace Applications

ASTM E 272 - Reference Radiographs for High-Strength Copper-Base and Nickel-Copper Alloy Castings

MIL-STD-2175A

- ASTM E 280 - Reference Radiographs for Heavy-walled (4.5 to 12 in. (114 to 305 mm)) Steel Castings
- ASTM E 310 - Reference Radiographs for Tin Bronze Castings
- ASTM E 446 - Reference Radiographs for Steel Castings Up To 2 in. (51 mm) in Thickness
- ASTM E 1255 - Radioscopic Real-Time Examination
- ASTM E 1444 - Magnetic Particle Examination

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

MIL-STD-2175A

3. DEFINITIONS

3.1 Alloy. A metallic substance composed of two or more elements which possesses properties different from those of its constituents.

3.2 Casting. An object at or near finished shape obtained by filling a mold with molten metal and allowing it to solidify.

3.3 Chaplet. Metal core support which is used in the mold cavity and which fuses into the casting.

3.4 Cold shut. An imperfect junction between two flows of metal in a mold caused by the surface of the streams of metal chilling too rapidly, or in effect, being chilled to the extent that fusion does not occur. This discontinuity may have the appearance of a crack or seam with smooth or rounded edges.

3.5 Contracting agency. A prime contractor, subcontractor, or government agency procuring castings.

3.6 Defect. A discontinuity or condition in a casting which exceeds allowable limits. Defects are, by definition, unacceptable.

3.7 Diffraction. A pattern of light or dark areas in a casting radiograph, due to grain structure, which is not detrimental to the casting.

3.8 Discontinuity. An interruption in the normal physical structure or configuration of a part such as cracks, inclusions, and porosity, which may or may not affect the usefulness of a part.

3.9 Foreign materials. Appear as isolated, irregular, or elongated variations of radiographic film density, corresponding to variations in thickness of material, or to cavities. They may be due to the presence of sand, slag, oxide, dross, or metal of different density. External foreign material would, of course, be detected by visual inspection. In radiographic inspection, the distinguishing factor between inclusions and foreign material is that the foreign material indications occur over a larger area while the inclusion indications are singular indications of one inclusion.

3.10 Gas holes. Round or elongated, smooth-edged voids occurring individually, in clusters, or distributed throughout the casting. They are generally caused by trapped air or gases rejected from the metal during solidification.

3.11 Gas porosity. Minute voids usually distributed throughout the entire casting. They are generally caused by trapped air or gases rejected from the metal during solidification.

3.12 Hot tear. Hot tears appear as ragged dark lines of variable width and with no definite line of continuity. Hot tears may exist in groups starting at a surface. They usually result from uneven cooling associated with abrupt changes in wall thickness, and they are formed upon solidification of the molten metal.

MIL-STD-2175A

3.13 Inclusions. Inclusions are particles of foreign material such as sand or slag that are embedded in the cast metal.

3.14 Insert. A piece of steel used to locally increase the rate of heat removal during solidification. It is also called an internal chill.

3.15 Misruns. A misrun is caused by a failure of the molten metal to completely fill the mold. It appears on the radiograph as prominent darkened areas of variable dimensions with a definite and smooth outline.

3.16 Penetrameter or Image Quality Indicator (IQI). A strip of metal that is radiographically similar to the metal being tested, representing a percentage of object thickness and provided with a combination of steps, holes or wires. When placed in the path of X-rays or gamma rays, its image provides a check on the radiographic technique employed.

3.17 Radiographic quality level. The ability of the radiographic procedure to demonstrate a certain IQI sensitivity based on the perception of the IQI holes or wires.

3.18 Segregation. A concentration of alloying elements in specific regions of the casting, usually the result of the primary crystallization of one phase with the subsequent concentration of other elements in the remaining liquid.

3.19 Shrinkage. The term shrinkage, as used in this standard, refers to a network of small voids due to grain boundary solidification phenomena. It is different than the larger and singular voids caused by solidification shrinkage on a large scale, as defined in 3.20 (shrinkage cavity). Shrinkage is usually categorized as either dendritic, filamentary, feathery, or sponge. It is usually below the surface but may extend to the surface. In radiographic inspection, depending on the category, shrinkage may appear as dark irregular patches, as dark feathery streaks, or as a lacy or honeycombed darkened area with a diffuse outline. In penetrant inspection, dendritic shrinkage (sometimes called "microshrinkage"), and sponge shrinkage, are often indistinguishable from each other and appear as a sponge-like cluster of tiny pin holes or spotty irregular areas with feathery outlines. In magnetic particle inspection shrinkage may appear as a jagged area or irregular patch of magnetic particles.

3.20 Shrinkage cavity. Shrinkage cavities occur when insufficient feeding of a section results in a continuous cavity within the section. Shrinkage cavities appear on the radiograph as dark areas that are indistinctly outlined and have irregular dimensions.

3.21 Surface irregularities. In radiographic inspection, they are any images corresponding to an irregularity visible on the surface. In visual inspection they are any interruptions, either positive (raised) or negative (depressed) from the normal cast surface.

3.22 Visual inspection. Inspection of casting surfaces to determine conformance to the requirements for surface roughness, surface irregularities, dimensions, or any visible surface discontinuities.

MIL-STD-2175A

4. GENERAL REQUIREMENTS

4.1 Personnel qualification. Personnel performing penetrant, magnetic particle or radiographic inspections as required by this standard shall be qualified and certified in accordance with MIL-STD-410 for the applicable method being used.

4.2 Inspection sequence. It is the responsibility of the contractor to perform appropriate inspections as necessary and in the proper sequence during processing to assure freedom from harmful discontinuities in the final product. The intent of inspections during processing is to detect flaws which would be detrimental to the final product at the earliest stage in processing so as to minimize the cost of rejected or scrapped castings. The inspection sequence for liquid penetrant, magnetic particle, and radiographic inspections shall be as specified in ASTM-E-1444, MIL-STD-453, and MIL-STD-6866 or as otherwise specified by the design activity on the engineering drawing, applicable specification, or other contractual or engineering documentation.

4.3 Discontinuity removal. If it is determined that rejectable discontinuities shall subsequently be removed by machining on machining stock surfaces, or by blending on as-cast surfaces, then those discontinuities need not be cause for rejection provided reinspection is performed after the material removal to verify that the discontinuity was removed, and the dimensional tolerance requirements of the casting are satisfied.

4.4 Classification of castings.

4.4.1 Determination of classes and grades. The design activity shall establish the class and grade(s) for each casting design (see 1.3). Sections of a casting may be of varying grades depending on the applied stresses to that portion of a casting. Particular attention should be given to areas that contain, or will eventually contain, stress risers after machining (such as sharp internal corners, holes, or notches). If the grade of casting is not indicated on the drawing or other contractual document, grade C shall apply, except for class 4 castings, where grade D shall apply.

4.4.2 Class 1 casting requirements. All areas of class 1 castings shall be of a quality equivalent to, or better than, grade C, except that all highly stressed areas of a class 1 casting shall be of a quality equivalent to, or better than, grade B.

4.5 Inspection Lot. An inspection lot, for the purposes of visual, liquid penetrant, magnetic particle, and radiographic inspection shall be as defined in the casting (material) specification, engineering drawing, or purchase order. If not specified in any of the above documents, an inspection lot shall be defined as all castings of the same part number, of one alloy, produced using the same processing parameters of the casting procedure, and submitted for inspection as a single group.

MIL-STD-2175A

5. DETAIL REQUIREMENTS

5.1 Outline of inspections.

5.1.1 Visual inspection. Visual inspection shall be performed in accordance with, and evaluated to the acceptance criteria of 5.3.1. Sampling shall be in accordance with 5.2.1 (see 6.4).

5.1.2 Magnetic particle and liquid penetrant inspection. Magnetic particle and liquid penetrant inspection shall be performed in accordance with, and evaluated to the acceptance criteria of 5.3.2. Sampling shall be in accordance with 5.2.2 (see 6.4).

5.1.3 Radiographic inspection. Radiographic inspection shall be performed in accordance with, and evaluated to the acceptance criteria of 5.3.3. Sampling shall be in accordance with 5.2.3 (see 6.4).

5.2 Sampling.

5.2.1 Visual inspection. Each casting shall be examined visually.

5.2.2 Magnetic particle and penetrant inspection. Each casting shall be subjected to either magnetic particle or penetrant inspection, as may be appropriate (see 5.3.2), except that class 4 castings shall be sample inspected in accordance with table 1, unless 100 percent inspection is required by the engineering drawing, casting specification or purchase order.

5.2.3 Radiographic inspection. Sampling inspection and inspection coverage shall be as indicated below:

- a. Class 1 castings - Each casting shall be completely examined.
- b. Class 2 castings - Castings shall be selected in accordance with table 1 and completely examined.
- c. Class 3 castings - Castings shall be selected in accordance with table 2 and completely examined.
- d. Class 4 castings - Radiographic examination is not required unless otherwise specified in the casting drawing, specification, contract, or purchase order. If radiographic examination is specified and no sampling is specified, table II shall apply.

5.3 Inspection methods and acceptance criteria.

5.3.1 Visual inspection. Each casting shall be 100% visually inspected. Visual inspection should be performed in areas with an ambient lighting range of no less than 75 foot-candles. Castings shall be free of foreign materials, and shall not contain any cracks, hot tears, cold shuts, and negative core seams (also called parting line below flush). In addition, visual inspections shall be performed to determine conformance to the criteria specified on the engineering drawing, specification, or agreed upon observational standards (see 6.8).

MIL-STD-2175A

5.3.1.1 Surface roughness. Dimensions and surface roughness shall conform to the engineering drawing requirements. Surface roughness requirements specified on the engineering drawing (for example 63 Ra) do not preclude the presence of acceptable liquid penetrant or magnetic particle indications. Visual and tactile comparison with commercially available observational standards may be used to determine conformance to surface roughness requirements.

5.3.1.2 Gate, riser, and parting line projections. If allowance limits for gate, riser, or parting line projections are not specified on the engineering drawing or casting (material) specification, then the maximum limit for gates, risers and parting lines shall be in accordance with table 3.

5.3.1.3 Surface pits and raised metal. Allowable surface pits and raised metal (also called positive metal), other than gates, risers and parting lines, that are not specifically controlled by the engineering drawing or agreed upon observational standards shall be allowed as specified below:

- a. For sand castings, surface pits are acceptable if they have smooth rounded contours and do not cause the casting to fall outside the dimensional requirements of the engineering drawing. Raised metal that has a jagged or irregular surface, or which causes the casting to fall outside of the dimensional requirements of the engineering drawing, shall be removed or blended to conform to the dimensional and surface roughness requirements of the engineering drawing.
- b. For investment and permanent mold castings, random raised metal shall be limited to a height of 0.015-0.030 inch by 0.125 by 0.125 inch and no more than one per square inch. Random surface pits shall be limited to 0.030-0.060 inch in diameter and 0.030 inch in depth and no more than one per square inch. Smaller surface pits or raised metal may be present at random provided they do not interfere with the function of the part.

5.3.2 Magnetic particle and liquid penetrant inspection.

5.3.2.1 Inspection method for ferromagnetic materials. Class 1, 2 and 3 castings and sample castings of class 4 ferromagnetic materials shall be magnetic particle inspected. Magnetic particle inspection shall be in accordance with ASTM E 1444. If necessary, and when approved by the contracting agency, liquid penetrant inspections may be performed in lieu of magnetic particle inspection on ferromagnetic materials if their size or complex shape prohibits adequate inspection with magnetic particle inspection. The surface quality of the castings shall conform to 5.3.2.3. All precipitation hardening stainless steels shall be penetrant inspected in accordance with 5.3.2.2. (due to the possibility of delta ferrite stringers), unless otherwise prohibited by the contracting agency.

5.3.2.2 Inspection method for nonferromagnetic materials. Class 1, 2 and 3 castings and sample castings of class 4 nonferromagnetic material shall be penetrant inspected in accordance with MIL-STD-6866. The design activity shall specify, on the engineering drawing or other applicable documents, the

MIL-STD-2175A

sensitivity level of the penetrant materials to be used in accordance with the classification of MIL-I-25135. If no sensitivity level is specified, the inspection facility shall determine the appropriate sensitivity level for the inspection procedure in accordance with MIL-STD-6866, or the company process specification. The surface quality of the castings shall conform to 5.3.2.3. Penetrant materials which exhibit excessive fluorescent background which could mask or obscure relevant discontinuities on the as-cast surface shall not be used.

5.3.2.3 Magnetic particle and liquid penetrant acceptance criteria. If the design activity does not specify their own magnetic particle or liquid penetrant acceptance criteria on the engineering drawing, then the surface quality of each grade designation shall conform to table 4.

5.3.3 Radiographic inspection.

5.3.3.1 Radiographic inspection method. Radiographic inspection shall be in accordance with MIL-STD-453. The use of nonfilm radiographic techniques (radioscopy) is permitted, provided the method used is sufficiently sensitive to resolve the required radiographic quality level. Radioscopic inspection shall be in accordance with ASTM E 1255. However, prior approval shall be obtained from the contracting agency on the detailed inspection, evaluation and quality control procedures.

5.3.3.2 Radiographic reference standards. Radiographic standards shall be as required in ASTM E 155, ASTM E 186, ASTM E 192, ASTM E 272, ASTM E 280, ASTM E 310 and ASTM E 446. For alloy types where reference radiographs are specifically covered, the reference radiograph shall be of the same alloy family as the casting. For alloys not specifically included in the alloy family covered by the ASTM reference radiographic standards, the design activity shall either select an ASTM standard representative of the quality required, or develop their own radiographic standards containing details comparable to an ASTM standard.

5.3.3.3 Radiographic acceptance criteria. The design activity shall specify on the drawing or other document the radiographic grade(s) for classes 1, 2 and 3 castings designs. The design activity may specify radiographic grade(s) for class 4 casting designs. Either the castings, or areas of the castings, shall be in accordance with the requirements for the applicable grades of tables 6 through 14 of this standard.

5.4 Reinspection.

5.4.1 Reinspection of rejected lots. When an inspection lot is rejected on the basis of a sampling plan, regardless of the inspection method, it may be resubmitted for 100 percent inspection and defective castings removed from the lot per 5.4.2. For lots of class 2 and class 3 castings which were rejected in a radiographic inspection sampling plan, each part shall be completely examined upon reinspection, whereas for class 4 castings, only the areas where the rejectable discontinuities were found need to be inspected.

MIL-STD-2175A

5.4.2 Individual casting rejection. Individual casting rejection shall apply in those instances where all castings in the lot are inspected and any individual casting is found defective in visual, penetrant, magnetic particle, or radiographic inspection. Only the defective casting needs to be rejected, and individual castings meeting the requirements of this standard may be accepted.

MIL-STD-2175A

6. NOTES

(This section contains guidance information of a general or explanatory nature that may be helpful, but is not mandatory)

6.1 Intended use. This standard prescribes acceptance criteria for surface inspections and radiographic inspections applied to metal castings. This standard is not intended to apply to high pressure die castings. Acceptance criteria for die castings may be based on standards and guidelines developed by the American Society for Testing and Materials (ASTM), and the North American Die Casting Association (formerly the American Die Casting Institute (ADCI)). Examples are ASTM B 505 and ADCI "Q", "E", and "M" series standards.

6.2 Issue of DoDISS. When this standard is used in acquisition, the issue of the DoDISS to be applicable to this solicitation must be cited in the solicitation.

6.3 Data requirements. The following Data Item Descriptions (DID's) must be listed, as applicable, on the Contract Data Requirements List (DD Form 1423) when this standard is applied in a contract, in order to obtain the data, except where DOD FAR Supplement 27.475-1 exempts the requirement for a DD Form 1423.

<u>Reference Paragraph(s)</u>	<u>DID Number</u>	<u>DID Title</u>	<u>Suggested Tailoring</u>
Appendix A	DI-MISC-80653	Test Reports	Use contractor format

6.4 Sampling. The following is included as a quick check to aid in identifying the sampling requirements specified herein for the different inspection methods as they apply to each class:

- a. Class 1. For castings classified as class 1, all castings in the lot are inspected by the methods specified in this standard.
- b. Class 2. For castings classified as class 2, all castings in the lot are inspected by the methods specified in this standard, except for radiographic inspection, in which case the castings are sampled per table 1.
- c. Class 3. For castings classified as class 3, all castings in the lot are inspected by the methods specified in this standard, except for radiographic inspection, in which case the castings are sampled per table 2.
- d. Class 4. For castings classified as class 4, all castings in the lot are inspected by visual inspection, while castings are sampled in accordance with table 1 for penetrant or magnetic particle inspection. Radiographic examination is not required unless specified on the engineering drawing, specification, contract, or purchase order.

MIL-STD-2175A

6.5 Cross reference. The class of castings defined in paragraph 1.3 corresponds to those defined in MIL-C-6021H as shown below:

<u>MIL-C-6021H designation</u>	<u>MIL-C-6021G designation</u>
Class 1	Class 1, Class 1A
Class 2	Class 1, Class 1B
Class 3	Class 2, Class 2A
Class 4	Class 2, Class 2B

6.6 Radiographic quality grades for machined areas. Castings that have been found acceptable per the ASTM radiographic standards often times have internal discontinuities (such as shrinkage, porosity, and inclusions) exposed after machining. One way to help alleviate this problem is to quantify (in terms of size) the ASTM reference radiographic discontinuities so that their size on the surface may be approximated. Once this has been done, the engineer or designer should be able to determine if the discontinuities allowed in the radiographic grade will be permissible on the surface. If they are not permissible, then the area that is machined should be zoned to a more stringent radiographic grade.

6.7 Producibility considerations. The class assigned to the casting should represent a realistic value for the functional requirements, do not assign a class 1 casting for a class 2 function. Casting design coupled with foundry practice can make overly severe soundness requirements impractical for a manufacturer to satisfy. Caution should be exercised in specifying the grade of maximum permissible radiographic discontinuity level and surface quality requirements to be met in a casting.

6.8 Observational standards. Observational standards for visual inspection may include sample castings with known discontinuities. Assistance with the visual inspection criteria for steel castings may be obtained by reference to ASTM A 802 and MSS SP-55. MSS SP-55 contains reference photographs that illustrate various types and degrees of surface discontinuities, while ASTM A 802 contains plates that model actual discontinuities and surface roughness. The full titles of ASTM A 802 and MSS SP-55 are shown below:

- a. ASTM A 802 "Steel Castings, Surface Acceptance Standards, Visual Examination" (Copies may be obtained from the ASTM address given in section 2)
- b. MSS SP-55 "Quality Standard for Steel Castings for Valves, Flanges, and Fittings and other Piping Components (Visual Method)" (Copies may be obtained from the Manufacturers Standardization Society of the Valve and Fittings Industry, 127 Park Street, N.E., Vienna, VA 22180)

6.9 Ultrasonic inspection of thick castings. Class 1 and Class 2 castings having a section thickness of 4.50 inches and greater should also be inspected by ultrasonic methods due to the loss of radiographic sensitivity in the thicker sections. It should be noted that ultrasonic examination and radiography are not directly comparable. Therefore, the design activity would

MIL-STD-2175A

need to specify, on the engineering drawing, the appropriate document for ultrasonic inspection along with the appropriate quality level of acceptance criteria contained within that document. One document that could be specified is:

- a. ASTM A 609 "Castings, Carbon, Low-Alloy, and Martensitic Stainless Steel, Ultrasonic Examination Thereof"

6.10 Subject term (key word) listing.

Liquid penetrant testing
Nondestructive testing
Magnetic particle testing
Radiographic testing

6.11 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - MR
Navy - AS
Air Force - 11

Preparing activity:

Navy - AS

(Project No. NDTI-0131)

Review activities:

Army - AR, EA, MI
Navy - SH, OS
Air Force - 70, 71, 80, 82, 84, 99
DLA - IS

User activities:

Army - ME

MIL-STD-2175A

TABLE 1. Sampling, radiographic inspection of class 2 castings, and magnetic particle and liquid penetrant inspection of class 4 castings.

Lot size <u>1/</u>	Sample size <u>2/</u>	Lot size	Sample size
2-5	All	27-36	10
6-8	5	37-51	11
9-11	6	52-82	12
12-15	7	83-162	13
16-20	8	163-971	14
21-26	9	972 and over	15

1/ See 4.5 for lot definition.2/ Acceptance number is 0.TABLE 2. Sampling, radiographic inspection of Class 3 Castings.

Lot size <u>1/</u>	Sample size <u>2/</u>	Lot size	Sample size
2-4	All	18-27	7
5-6	4	28-48	8
7-11	5	49 and over	9
12-17	6		

1/ See 4.5 for lot definition.2/ Acceptance number is 0.Table 3. Maximum allowable gate, riser, and parting line projections.

Casting weight lb.	Nonmachined surface (in.)	Machined surface (in.)
up to 10	.031	.062
over 10 thru 25	.047	.062
over 25 thru 50	.062	.094
over 50	.125	.188

MIL-STD-2175A

TABLE 4. Maximum allowable discontinuity size and distribution (in inches) for magnetic particle (MT) and liquid penetrant (PT) inspection. 1/, 2/, 3/, 4/ (T = Thickness of casting section.)

Discontinuity type		Grade A	Grade B	Grade C	Grade D
Random individual discontinuities (Gas holes, inclusions, discrete shrinkage cavities) 5/, 6/ surface (nonlinear) subsurface (MT only)		1/4 T or the sizes shown below, whichever is less 0.03 dia 0.05 dia	1/3 T or the sizes shown below, whichever is less 0.05 dia 0.09 dia	1/3 T or the sizes shown below, whichever is less 0.09 dia 0.12 dia	1/2 T or the sizes shown below, whichever is less 0.12 dia 0.15 dia
Cracks, hot tears, cold shuts, or through wall indications		-----	----- None Allowed -----	-----	-----
Microshrinkage or shrinkage sponge 2/		0	0.12 dia	0.38 dia	0.75 dia
Microshrinkage or shrinkage sponge 1/, 4/ (linear)		0	0	0.12	0.25
Number of allowable discontinuities within a 2 X 2 inch area	Random individual 8/ discontinuities	2	3	4	4
	Microshrinkage shrinkage- sponge	0	1	1	1

See next page for notes.

MIL-STD-2175A

Notes for table 4.

- 1/ Linear discontinuities (length to width ratio of 3 to 1 or greater) are not allowed except under the following circumstances:
 - (a) Linear dendritic shrinkage, or linear shrinkage sponge indications shall be evaluated in accordance with this table and shall not be allowed to break over an edge, extend through a wall, or be located in internal corners of fillet radii.
 - (b) In magnetic particle inspection, discontinuities 0.030 inches or less in length need not be evaluated for linearity. In penetrant examination, discontinuities 0.015 inches or less in length need not be evaluated for linearity.
- 2/ Discontinuities that are visible under white light without the use of penetrant or magnetic particles may be evaluated to the criteria of this table.
- 3/ Size limits shown are for actual discontinuity size and not bleed out. Indications may be inspected by measuring their size after wiping with a solvent dampened cloth, cotton swab, or brush. Immediately evaluate the discontinuity for size as soon as the solvent has evaporated.
- 4/ For rounded indications exhibiting excessive penetrant bleedout, or doubtful indications of microshrinkage or shrinkage sponge, disposition may be based on the radiographic acceptance criteria after x-raying the part. Linear microshrinkage, or linear shrinkage sponge shall only be acceptable after verification by radiography.
- 5/ For random individual discontinuities, the minimum resolvable size shall be 0.030 inches for magnetic particle inspection and 0.015 inches for penetrant inspection. Discontinuities smaller than these sizes shall be considered non-interpretable.
- 6/ For grade A, any two random individual discontinuities shall be separated by a distance of at least three times the maximum dimension of the larger discontinuity. For grades B, C, and D random individual discontinuities shall be separated by a distance equal to twice the maximum dimension of the larger discontinuity. However, if the total length of the discontinuities that violate this spacing requirement does not exceed the maximum length permitted for a single discontinuity, then these discontinuities shall be considered as one and shall not be cause for rejection.
- 7/ Microshrinkage is also called dendritic shrinkage.
- 8/ The limits for random individual discontinuities do not apply if the discontinuities are smaller than one-half their maximum allowable size and they meet the minimum spacing requirement of note 6/.

MIL-STD-2175A

TABLE 5. Notes for tables 6 through 14.

- (1) An area of like size to the reference radiograph shall be the unit area by which the production radiograph is evaluated. If the production radiograph shows a discontinuity that is equal to or better than the severity level of the reference radiograph, the casting shall be acceptable. If the production radiograph shows a discontinuity of greater severity than the reference radiograph, the casting shall be rejected.
- (2) When two or more types of discontinuities are present (in an area equal to the reference radiographic plate area) to an extent equal to the maximum permissible severity level for each type, the casting shall be rejected.
- (3) Numbers in the tables are ASTM radiographic plate numbers for a particular type and severity of discontinuity. A low number indicates fewer, smaller discontinuities while a higher number indicates more numerous, larger discontinuities.
- (4) The smallest resolvable indication size, below which indications are considered non-interpretable, shall be 0.015 inches.
- (5) Gas holes, sand spots, and inclusions allowed by these tables (even those smaller than the maximum allowable size) shall be cause for rejection when closer than twice their maximum dimension to an edge. Exceptions to this note based on the class and grade of the casting are shown below: 1/
- Class 1 No exceptions from note 5.
- Class 2 No exceptions from note 5 for Grade A and Grade B areas, or other areas that are specified critical or highly stressed. Otherwise, the note 5 discontinuities are acceptable if they are separated from the edge by a distance, equal to, or greater than, the discontinuity's maximum dimension.
- Class 3 Gas holes, sand spots, and inclusions, of the maximum size allowed by these tables, shall be cause for rejection if they are closer than one diameter of their maximum dimension to an edge. This does not apply to gas holes, sand spots, and inclusions smaller than the maximum allowable size.
- Class 4 Edge of part discontinuities are acceptable if they are not crack-like, linear, or round with protruding linear indications.
- 1/ The term "edge" refers to the outer boundary of the radiographic image of the casting. This interpretation need only be made in the standard exposures (views) defined by the approved radiographic technique. Additional radiographic exposures, to determine the distance from the surface of each gas hole, sand spot, or inclusion in other orientations, are not required.

MIL-STD-2175A

TABLE 6. Maximum permissible radiographic severity levels for discontinuities in aluminum castings per ASTM E 155. 3/, 4/, 5/

Discontinuity	Grade A		Grade B		Grade C		Grade D	
	Inch 1/4	3/4	Inch 1/4	3/4	Inch 1/4	3/4	Inch 1/4	3/4
Gas holes	None		1	1	2	2	5	5
Gas porosity (round)	None		1	1	3	3	7	7
Gas porosity (elongated)	None		1	2	3	4	5	5
Shrinkage cavity	None		1	NA 2/	2	NA 2/	3	NA 2/
Shrinkage (sponge)	None		1	1	2	2	4	3
Foreign material (less dense material)	None		1	1	2	2	4	4
Foreign material (more dense material)	None		1	1	2	1	4	3
Cracks 1/	None		None		None		None	
Cold shuts 1/	None		None		None		None	
Surface irregularity 1/	Not to exceed drawing tolerance							
Core shift 1/								

1/ No reference radiographic plates available.

2/ Not available, use the 1/4 inch reference radiographic plate thickness with a severity level 2 units greater than the one shown for the 1/4 inch column.

3/ ASTM E 155 Volume I reference radiographic plates.

4/ For feature thicknesses greater than two inches, the 3/4 inch reference radiographic plates may be used.

5/ See table 5 for additional notes that apply to this table.

MIL-STD-2175A

TABLE 7. Maximum permissible radiographic severity levels for discontinuities in magnesium castings per ASTM E 155. 3/, 4/, 5/

Discontinuity	Grade A	Grade B	Grade C	Grade D
	Inch	Inch	Inch	Inch
	1/4 3/4	1/4 3/4	1/4 3/4	1/4 3/4
Gas holes	None	1 1	3 2	4 4
Microshrinkage (feathery)	None	1 1	4 4	7 7
Microshrinkage (sponge)	None	1 1	3 4	7 8
Foreign material (less dense material)	None	2 2	3 3	4 4
Foreign material (more dense material)	None	1 1	2 2	3 3
Cracks 1/	None	None	None	None
Cold shuts 1/	None	None	None	None
Surface irregularity 1/	Not to exceed drawing tolerance			
Core shift 1/	Not to exceed drawing tolerance			
APPLICABLE TO ALL THICKNESSES				
Reacted sand inclusions	1	3	4	6
Gravity segregation	1	2	3	4
Eutectic segregation				
(a) Microshrinkage type	None	4	5	6
(b) Pipe shrink type	None	None	None	1/3 of size on plate
(c) Hot tear type	None	same as size on plate	same as size on plate	twice the size on plate
Oxide Inclusions	None	1/3 of size on plate	1/2 of size on plate	same as size on plate
Eutectic depletion - Flow line	None	same as size on plate	twice the size on plate	Any length 2/

1/ No reference radiographic plates available.

2/ No other types of discontinuities are allowed to be contained with it in an area of like size to the reference radiographic plate.

3/ ASTM E 155 Volume I and II reference radiograph numbers.

4/ For feature sizes greater than 2 inches, the 3/4 inch reference radiographic plates may be used.

5/ See table 5 for additional notes that apply to this table.

MIL-STD-2175A

TABLE 8. Maximum permissible radiographic severity levels for discontinuities in investment steel castings
1 in. (25.4 mm) wall or less per ASTM E 192. 5/ 6/

Discontinuity	Grade A Inch			Grade B Inch			Grade C Inch			Grade D Inch		
	1/8	3/8	3/4	1/8	3/8	3/4	1/8	3/8	3/4	1/8	3/8	3/4
Gas holes	1	1	1	3	3	3	5	5	5	7 1/	7 2/	7
Foreign material (more dense)	Use "foreign material (less dense) limits"											
Shrinkage cavity	None	None	None	None	None	1	None	None	3	1	2	5
Shrinkage sponge	1	1	1	2 3/	1	1	4	4	5	6	6	7
Shrinkage, dendritic	1	1	1	2	2	2	4	4	4	6	6	6
Shrinkage, filamentary	None	None	None	None	None	1	None	None	2	None	None	3
Foreign material (less dense)	1	1	1	3	3	3	5	6	6	6	7	7
Cold shut	None allowed											
Hot tear	None allowed											
Cold crack	None allowed											
Misrun	None allowed											
Core shift	Not to exceed drawing tolerance											
Mold buckle, positive	Not to exceed drawing tolerance											
Mold buckle, negative	Not to exceed drawing tolerance											
Mold ridge	Not to exceed drawing tolerance											
Excess metal in cracked core	Not to exceed drawing tolerance											
Surface irregularities	Not to exceed drawing tolerance											

1/ Excluding the single largest gas hole.

2/ Excluding the crack-like discontinuities emitting from the gas holes.

3/ Excluding bottom half of the standard reference film.

4/ NA - Not available.

5/ See table 5 for additional notes that apply to this table.

6/ "None" as used in this table means that the discontinuity is not allowed.

MIL-STD-2175A

TABLE 9. Maximum permissible radiographic severity levels for discontinuities in heavy walled steel castings
2 - 4.5 in. (51 - 114 mm) per ASTM E 186. 1/

Code or Category	Discontinuities	Grade A	Grade B	Grade C	Grade D
A	Gas porosity	None	1	2	3
B	Sand/slag inclusions	None	1	2	4
C	Shrinkage type 1	None	2	3	5
C	Shrinkage type 2	None	2	3	4
C	Shrinkage type 3	None	2	3	4
D	Crack	None	None	None	None
E	Hot Tear	None	None	None	None
F	Insert	None	None	None	None

1/ See table 5 for additional notes that apply to this table.

MIL-STD-2175A

TABLE 10. Maximum permissible radiographic severity levels for discontinuities in steel castings up to 2 in. (51 mm) in thickness per ASTM E 446. 2/

Code or Category	Discontinuities	Grade A	Grade B	Grade C	Grade D
A	Gas porosity	None	1	2	3
B	Sand and slag inclusions	None	1	2	3
CA	Shrinkage	None	1	2	3
CB	Shrinkage	None	1	2	3
CC	Shrinkage	None	1	2	3
CD	Shrinkage	None	1	2	3
D	Crack	None	None	None	None
E	Hot tear	None	None	None	None
F	Insert	None	None	1/	1/
G	Mottling	Not to exceed contract or drawing requirements			

1/ Not to exceed contract or drawing requirements.

2/ See table 5 for additional notes that apply to this table.

MIL-STD-2175A

TABLE 11. Maximum permissible radiographic severity levels for discontinuities in heavy walled 4.5 - 12 in. (114 - 305mm) steel castings per ASTM E 280. 1/

Code or Category	Discontinuities	Grade A	Grade B	Grade C	Grade D
A	Gas porosity	1	2	3	4
B	Sand and slag inclusions	1	2	3	4
C	Shrinkage type 1	1	2	3	4
C	Shrinkage type 2	1	2	3	4
C	Shrinkage type 3	1	2	3	4
D	Crack	None	None	None	None
E	Hot tear	None	None	None	None
F	Insert	None	None	None	None

1/ See table 5 for additional notes that apply to this table.

MIL-STD-2175A

TABLE 12. Maximum permissible radiographic severity levels for discontinuities in high-strength copper-base and nickel-copper alloy castings up to 2 in. (51 mm) in thickness per ASTM E 272. ^{3/}

Code or Category	Discontinuities ^{2/}	Grade A	Grade B	Grade C	Grade D
A	Gas porosity	None	1	2	3
Ba	Sand inclusions	None	1	2	3
Bb	Dross inclusions	None	1	2	3
Ca	shrinkage, linear	NA ^{1/}	NA ^{1/}	NA ^{1/}	NA ^{1/}
Cd	Shrinkage, feathery	None	1	2	3
Cd	Shrinkage, spongy	NA ^{1/}	NA ^{1/}	NA ^{1/}	NA ^{1/}

^{1/} Not available.^{2/} Cracks, Hot tears and Inserts are not allowed.^{3/} See table 5 for additional notes that apply to this table.

MIL-STD-2175A

TABLE 13. Maximum permissible radiographic severity levels for discontinuities in high-strength copper-base and nickel-copper alloy castings 2 - 6 in. (51 - 153 mm) in thickness per ASTM E 272. 3/

Code or Category	Discontinuities 2/	Grade A	Grade B	Grade C	Grade D
A	Gas porosity	None	1	2	3
Ba	Sand inclusions	None	1	2	3
Bb	Dross inclusions	None	1	2	3
Ca	Shrinkage, linear	None	1	2	3
Cd	Shrinkage, feathery	NA 1/	NA 1/	NA 1/	NA 1/
Cd	Shrinkage, spongy	None	1	2	3

1/ Not available.

2/ Cracks, Hot tears and Inserts are not allowed.

3/ See table 5 for additional notes that apply to this table.

MIL-STD-2175A

TABLE 14. Maximum permissible radiographic severity levels for discontinuities in tin bronze castings up to 2 in. (51 mm) in thickness per ASTM E 310. 2/

Code or Category	Discontinuities 1/	Grade A	Grade B	Grade C	Grade D
A	Gas porosity	None	1	2	3
B	Sand inclusions	None	1	2	3
Ca	Shrinkage, linear	None	1	2	3
Cd	Shrinkage, feathery or spongy	None	1	2	3
Da	Hot tear	None	None	None	None
Eb	Inserts, chaplets	None	None	None	None

1/ Cracks are not allowed.

2/ See table 5 for additional notes that apply to this table.

MIL-STD-2175A

APPENDIX A

TEST REPORT TECHNICAL CONTENT REQUIREMENTS

10. SCOPE

10.1 Scope. This appendix covers the technical content requirements that shall be included on data records when required by the contract or order. This appendix is mandatory only when data item description DI-MISC-80653 is cited on the DD Form 1423.

20. APPLICABLE DOCUMENTS

This section is not applicable to this appendix.

30. REPORTS

30.1 Data records. When required by the contract or purchase order the data record shall consist of the following:

- a) The certificate of conformance for each lot.
- b) The radiograph(s) of the casting.

30.2 Certificate of conformance. The certificate of conformance for each lot inspected shall consist of the following information:

- a) The casting part number and heat or lot number.
- a) For rejected castings, the reasons for rejection.
- b) The date of inspection.
- c) The inspectors identification and certification level.
- d) A statement that the lot of castings have been accepted in conformance with the requirements of MIL-STD-2175.
- e) The number of castings inspected in each lot, and the number rejected.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:

1. DOCUMENT NUMBER
MIL-STD-2175A

2. DOCUMENT DATE (YYMMDD)
930825

3. DOCUMENT TITLE

CASTINGS, CLASSIFICATION AND INSPECTION OF

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)

b. ORGANIZATION

c. ADDRESS (Include Zip Code)

d. TELEPHONE (Include Area Code)

7. DATE SUBMITTED (YYMMDD)

(1) Commercial
(2) AUTOVON
(If applicable)

8. PREPARING ACTIVITY

a. NAME COMMANDING OFFICER, NAVAL AIR
WARFARE CENTER AIRCRAFT DIVISION LAKEHURST
SYSTEMS REQUIREMENTS DEPARTMENT

b. TELEPHONE (Include Area Code)

(2) AUTOVON

(908) 323-7488

624-7488

c. ADDRESS (Include Zip Code)

CODE SR3
LAKEHURST, NJ 08733-5100

IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:
Defense Quality and Standardization Office
5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466
Telephone (703) 756-2340 AUTOVON 289-2340