



TABLE I. DASH NUMBERS.

DASH NO	A	HEAT TREATMENT	FORMING ^{1/} PROCESS	ADDITIONAL ^{2/} REQUIREMENTS
001	.051	ANNEALED	C	
003	.070	ANNEALED	C	
005	.083	ANNEALED	C	
007	.250	COLD WORKED HIGH TENSILE	C	g

^{1/} SEE REQUIREMENT 3^{2/} SEE REQUIREMENT 4

REQUIREMENTS:

1. MATERIAL. STEEL, CORROSION RESISTANT, TYPE 302 (UNS S30200) AS SPECIFIED IN PROCUREMENT DOCUMENT.
2. LENGTH. STANDARD LENGTH OF WIRE IS 10 FEET MINIMUM, 12 FEET MAXIMUM.
3. FORMING PROCESS. COLD FINISHED - CODE "C"
4. ADDITIONAL REQUIREMENTS.

PASSIVATED OVERALL - CODE "ps"
 CENTERLESS GROUND OVERALL - CODE "g"
 POLISHED OVERALL - CODE "p"

5. PART NUMBER. THE PART NUMBER CONSISTS OF THE BASIC MS NUMBER, PLUS A FORMING PROCESS CODE, PLUS A DASH NUMBER FROM TABLE I.

EXAMPLE: MS14396C001

(SEE TABLE I)

COLD FINISHED (SEE REQUIREMENT 3)

BASIC MS NUMBER

6. MARKING. IRON AND STEEL PRODUCTS SHALL BE MARKED IN ACCORDANCE WITH FED-STD-183 WITH THE EXCEPTION THAT A PART NUMBER FROM THIS MILITARY STANDARD SHALL BE INCLUDED AS PART OF THE IDENTIFICATION MARKING.

NOTES:

1. ALL DIMENSIONS ARE IN INCHES.
2. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATIONS FOR BIDS, OR REQUEST FOR PROPOSAL, EXCEPT THE REFERENCED ADOPTED INDUSTRY DOCUMENTS SHALL GIVE THE DATE OF THE ISSUE ADOPTED.
3. FOR DESIGN FEATURE PURPOSES THIS STANDARD TAKES PRECEDENCE OVER PROCUREMENT DOCUMENTS REFERENCED HEREIN.

P.A. Other Cust	AS MR 99	INTERNATIONAL INTEREST	TITLE WIRE, NONELECTRICAL, ROUND, CORROSION RESISTANT, TYPE 302	MILITARY STANDARD MS14396
PROCUREMENT SPECIFICATION QQ-S-763		SUPERSEDES:		PAGE OF

DD FORM 1 MAY 73 672-1 (COORDINATED)

PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE

9505-0144

APPROVED 28 FEB 1985 REVISED

USER ACTIVITIES:

REVIEWER ACTIVITIES:
AIR FORCE-84
DLA-1S

This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document when applicable.