

User activities:  
Army - AT  
Navy - SH

Review activity:  
DIA - CS

This military standard is approved for use by all Departments and Agencies of the Department of Defense for all new engineering and design applications and for repetitive use shall be made from this document, when applicable.

|   |  |
|---|--|
| FED. SUP CLASS<br>4930  |  |
|   |  |
| <p>NOTES:</p> <ol style="list-style-type: none"><li>1. Dimensions are in inches.</li><li>2. Unless otherwise specified, tolerance is <math>\pm .031</math> inch.</li><li>3. Material: Steel.</li><li>4. Heat treatment: Case harden to a depth of not less than .005 inch.</li><li>5. Finish for steel that is not corrosion resistant shall be in accordance with QQ-P-416, Class 2, Type II, or QQ-Z-325, Type II, Class 2.</li><li>6. Reference documents shall be of the issue in effect on date of invitations for bid or request for proposal.</li><li>7. For design feature purposes, this standard takes precedence over procurement documents referenced herein.</li></ol> |  |
| APPROVED 27 JULY 1954 REVISED 29 AUGUST 1966 21 APRIL 1977  |  |
| ENTIRE STANDARD REVISED   |  |
| P.A. ARMY - ME<br>Other Cust<br>NAVY - YD<br>AIR FORCE - 99   | TITLE<br>Coupling, grease gun;<br>shafer type nozzle |
| MILITARY STANDARD<br>MS 24203   |  |
| PAGE 1 OF 1   |  |
| PROCUREMENT SPECIFICATIONS SUPERSEDES:<br>MIL-L-4387  |  |
| 4930-0274   |  |
| DD FORM 672-1 1 SEP 57 PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE  |  |