

OTHER ACTIVITIES
NAVY - MC, YD





TABLE 1. DASH NUMBERS AND DIMENSIONS

DASH NO	A NOMINAL SIZE INCHES	B NOMINAL SIZE INCHES	C NOMINAL SIZE FEET	TEMPER	FORMING PROCESS ^{1/}
-001	.1900	24	5	SOFT ANNEALED	C
-003	.2500	24	4	LIGHT TEMPER	C
-005	.2500	30	5	HARD	C
-007	.2500	36	6	SOFT ANNEALED	C
-009	.2500	48	8	HALF HARD	C
-011	.2576	48	8	SOFT ANNEALED	C

^{1/} SIZE REQUIREMENT ?

REQUIREMENTS:

- MATERIAL. COPPER BASE ALLOY 110 (CIG C11000) AS SPECIFIED IN PROCUREMENT DOCUMENT.
- FORMING PROCESS. COLD ROLLED - COOK °C
- PART NUMBER. THE PART NUMBER CONSISTS OF THE BASIC PG NUMBER, PLUS A DASH NUMBER FROM TABLE 1.



- MARKING. COPPER AND COPPER BASE ALLOYS SHALL BE MARKED IN ACCORDANCE WITH FED-STD-105 WITH THE EXCEPTION THAT THE PART NUMBER FROM THIS MILITARY STANDARD SHALL BE INCLUDED AS PART OF THE IDENTIFICATION MARKING.

NOTES:

- IN THE EVENT OF A CONFLICT BETWEEN THE TEXT OF THIS STANDARD AND THE REFERENCES CITED HEREIN, THE TEXT OF THIS STANDARD SHALL TAKE PRECEDENCE.
- REFERENCED GOVERNMENT (OR NONGOVERNMENT) DOCUMENTS OF THE ISSUE LISTED IN THAT ISSUE OF THE DEPARTMENT OF DEFENSE TYPES OF SPECIFICATIONS AND STANDARDS (DDTSS) SPECIFIED IN THE SOLICITATION FORM A PART OF THIS STANDARD TO THE EXTENT SPECIFIED HEREIN.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited. This military standard is approved for use by all Departments and Agencies of the Department of Defense. Substitution for all items requiring and design specifications and for reference to use shall be made from this document when applicable.

OTHER ACTIVITIES
ARMY - AR, MI
NAVY - SH
AIR FORCE - 04
DLA - IS

APPROVED 29 OCT 87

U.S. NAVY - 05 ARMY - MR AIR FORCE - 99	INTERNATIONAL INTEREST	TITLE PLATE, METAL, COPPER BASE, ALLOY 110	MILITARY STANDARD	
			MS3229	
PROCUREMENT SPECIFICATION QQ-C-576		SUPERSEDES	PAGE 1 OF 1	