


This military standard is mandatory for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document.

REVIEWER: IS, ME, PM
(SERIALS, AT, AV, MC, GS, ID)



FED. SUP CLASS
5306

TABLE 1

NOMINAL SIZE		.250	.3125	.375	.4375	
THREADS PER INCH (-2A)		20UNC	18UNC	16UNC	14UNC	
D	BODY DIAMETER	MAX MIN	.260 .2127	.324 .2712	.389 .3287	
F	WIDTH ACROSS FLATS	MAX MIN	.475 .362	.500 .434	.5625 .494	
G	WIDTH ACROSS CORNERS	MAX MIN	.540 .498	.707 .665	.795 .747	
H	HEAD HEIGHT	MAX MIN	.188 .156	.220 .186	.264 .232	
R	RADIUS	MAX	.031	.031	.031	
TENSILE STRENGTH LBS-MIN		1,900	3,150	4,650	6,400	
L LENGTH	TOLERANCE (A)		DASH NO.	DASH NO.	DASH NO.	DASH NO.
	SIZE .375 & UNDER	SIZE .4375				
.75	+.02	+.02	1	32	64	
1.00	-.03	-.03	2	33	64	94
1.25			3	34	65	95
1.50	+.02	+.04	4	35	66	96
2.00	-.04	-.06	5	36	67	97
2.50			6	37	68	98
3.00			7	38	69	99
3.50	+.04	+.06	8	39	70	100
4.00	-.06	-.08	9	40	71	101
4.50			10	41	72	102
5.00	+.06	+.08	11	42	73	103
5.50	-.10	-.10	12	43	74	104
6.00			13	44	75	105
6.50			14	45	76	106
7.00			15	46	77	107
7.50			16	47	78	108
8.00			17	48	79	109
8.50			18	49	80	110
9.00			19	50	81	111
9.50			20	51	82	112
10.00			21	52	83	113
11.00			22	53	84	114
12.00	+.10	+.12	23	54	85	115
13.00	-.16	-.18	24	55	86	116
14.00			25	56	87	117
15.00			26	57	88	118
16.00			27	58	89	119
17.00			28	59	90	120
18.00			29	60	91	121
19.00			30	61	92	122
20.00			31	62	93	123

NOTES:

- MATERIAL:** Carbon steel, SAE Grade 1 in accordance with procurement specification, having an ultimate tensile strength of 60,000 psi-min.
- PROTECTIVE COATING:** Phosphate coated in accordance with type 2, class 2 of MIL-P-16232.
- THREADS:** Threads shall be in accordance with Screw-Thread Standards for Federal Services, Handbook H25.
- THREAD LENGTH:** Minimum thread length shall be twice the basic diameter plus 0.25 inch for lengths up to and including 6.00 inches and twice the basic diameter plus 0.50 inch for lengths over 6.00 inches. Bolts too short for the formula thread length shall be threaded as close to the head as practical.
- DIMENSIONS:** All dimensions are in inches unless otherwise specified.
- PART NUMBER:** The MS part number consists of the MS number, plus the dash number.
Example: MS35356-1
- Referenced documents shall be of the issue in effect on date of invitations for bid.
- For design feature purposes, this standard takes precedence over procurement documents referenced herein.

(A) For changes see sheets 1 and 2.

P.A. WC Other Cast SM 82	TITLE BOLT, MACHINE, SQUARE HEAD, STEEL, PHOSPHATE COATED, UNC-2A	MILITARY STANDARD MS35356
PROCUREMENT SPECIFICATION FF-B-575 (A)	SUPERSEDES:	SHEET 1 OF 2

DD FORM 672-1 (Continued)

PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE.

APPROVED 24 JAN 1955 REVISED (A) 6 OCT 1971

TABLE I - Continued										FED. SUP CLASS 5306	
NOMINAL SIZE (A)				.500	.625	.750	.875	1.000	1.125	1.250	
THREADS PER INCH (-2A)				13UNC	11UNC	10UNC	9UNC	8UNC	7UNC	7UNC	
D BODY DIAMETER				MAX MIN	.515 .4435	.642 .5589	.768 .6773	.895 .7946	1.022 .9100	1.149 1.0226	1.277 1.1476
F WIDTH ACROSS FLATS				MAX MIN	.750 .725	.9375 .906	1.125 1.088	1.3125 1.269	1.500 1.450	1.6875 1.631	1.875 1.812
G WIDTH ACROSS CORNERS				MAX MIN	1.061 .995	1.326 1.244	1.591 1.494	1.856 1.742	2.121 1.991	2.386 2.239	2.652 2.469
H HEAD HEIGHT				MAX MIN	.348 .308	.444 .400	.524 .476	.620 .568	.684 .628	.780 .720	.876 .812
R RADIUS				MAX	.031	.062	.062	.062	.093	.093	.093
TENSILE STRENGTH LBS-MIN (A)					8,500	13,600	20,000	27,700	36,400	45,800	58,100
L LENGTH	TOLERANCE (A)				DASH NO.	DASH NO.	DASH NO.	DASH NO.	DASH NO.	DASH NO.	DASH NO.
	SIZE .500	SIZE .625 to .750	SIZE .875 to 1.000	SIZE 1.125 to 1.250							
1.00	+.02 -.03				124						
1.25					125						
1.50	+.04	+.06	+.06	±.12	126	159	192	230	269		
2.00	+.06	+.08	+.10		127	160	193	231	269		
2.50					128	161	194	232	270		
3.00	+.06	+.08	+.10	±.16	129	162	195	233	271	306	341
3.50	+.06	+.10	+.14		130	163	196	234	272	307	342
4.00	+.06				131	164	197	235	273	308	343
4.50					132	165	198	236	274	309	344
5.00	+.06	±.10	+.12	±.18	133	166	199	237	275	310	345
5.50	-.10		-.16		134	167	200	238	276	311	346
6.00					135	168	201	239	277	312	347
6.50					136	169	202	240	278	313	348
7.00					137	170	203	241	279	314	349
7.50					138	171	204	242	280	315	350
8.00					139	172	205	243	281	316	351
8.50					140	173	206	244	282	317	352
9.00					141	174	207	245	283	318	353
9.50					142	175	208	246	284	319	354
10.00					143	176	209	247	285	320	355
11.00					144	177	210	248	286	321	356
12.00					145	178	211	249	287	322	357
13.00					146	179	212	250	288	323	358
14.00					147	180	213	251	289	324	359
15.00					148	181	214	252	290	325	360
16.00					149	182	215	253	291	326	361
17.00	+.12	+.14	+.16	±.22	150	183	216	254	292	327	362
18.00	-.18	-.18	-.20		151	184	217	255	293	328	363
19.00					152	185	218	256	294	329	364
20.00					153	186	219	257	295	330	365
21.00					154	187	220	258	296	331	366
22.00					155	188	221	259	297	332	367
23.00					156	189	222	260	298	333	368
24.00					157	190	223	261	299	334	369
25.00					158	191	224	262	300	335	370
26.00							225	263	301	336	371
27.00							226	264	302	337	372
28.00							227	265	303	338	373
29.00							228	266	304	339	374
30.00							229	267	305	340	375

REVIEWER: IS, ME, MI
USER: AS, AT, AL, NC, OS, VD

APPROVED 24 JAN 1955
REVISED (A) FOR CHANGES SEE SHEETS 1 AND 2.

P.A. WC
Other Cust SH
R2

TITLE
BOLT, MACHINE, SQUARE HEAD, STEEL,
PHOSPHATE COATED, UNC-2A

MILITARY STANDARD
MS35356

PROCUREMENT SPECIFICATION
FF-H-575 (A)

SUPERSEDES

SHEET 2 OF

This military standard is mandatory for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document.

P.A. 6C Other Cust SH 62	TITLE BOLT, MACHINE, SQUARE HEAD, STEEL, PHOSPHATE COATED, UNC-2A	MILITARY STANDARD MS 35356
PROCUREMENT SPECIFICATION FF-H-575 (A)	SUPERSEDES:	SHEET 2 OF

DD FORM 672-1 (Continued)

PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE

☆ U. S. GOVERNMENT PRINTING OFFICE: 1971-714-159/3027

APPROVED 24 JAN 1955 REVISED (A) FOR CHANGES SEE SHEETS 1 AND 2.