


FED. SUP CLASS  
9510

TABLE I. DASH NUMBERS AND DIMENSIONS

DASH NUMBER	A	HEAT TREATMENT	FORMING PROCESS <sup>1/</sup>
-001	.3750	AS FABRICATED	C
-003	.5000	AS FABRICATED	C
-005	.7500	AS FABRICATED	C
-007	.8125	AS FABRICATED	C
-009	.8750	AS FABRICATED	C
-011	.9375	AS FABRICATED	C
-013	1.0000	AS FABRICATED	C
-015	1.1875	AS FABRICATED	C
-017	1.3125	AS FABRICATED	C
-019	1.3750	AS FABRICATED	C
-021	1.4375	AS FABRICATED	C
-023	2.1250	AS FABRICATED	C
-025	2.7500	AS FABRICATED	C
-027	4.5000	AS FABRICATED	C
-029	5.0000	AS FABRICATED	C
-031	6.5000	AS FABRICATED	C
-033	8.0000	AS FABRICATED	C

<sup>1/</sup> SEE REQUIREMENT 3

## REQUIREMENTS:

1. **MATERIAL:** STEEL, CARBON GRADE 1020 (UNS G10200) AS SPECIFIED IN PROCUREMENT DOCUMENT.
2. **LENGTH:** STANDARD LENGTH OF BAR IS 10 FEET MINIMUM, 12 FEET MAXIMUM.
3. **FORMING PROCESS:** COLD DRAWN - CODE "C"
4. **PART NUMBER:** THE PART NUMBER CONSISTS OF THE BASIC MS NUMBER, PLUS A DASH NUMBER FROM TABLE I.

EXAMPLE: MS500107-001

(SEE TABLE I)

BASIC MS NUMBER

5. **MARKING:** IRON AND STEEL PRODUCTS SHALL BE MARKED IN ACCORDANCE WITH FED-STD-183 WITH THE EXCEPTION THAT A PART NUMBER FROM THIS MILITARY STANDARD SHALL BE INCLUDED AS PART OF THE IDENTIFICATION MARKING.

## NOTES:

1. ALL DIMENSIONS ARE IN INCHES.
2. IN THE EVENT OF A CONFLICT BETWEEN THE TEXT OF THIS STANDARD AND THE REFERENCES CITED HEREIN, THE TEXT OF THIS STANDARD SHALL TAKE PRECEDENCE.
3. REFERENCED GOVERNMENT (OR NONGOVERNMENT) DOCUMENTS OF THE ISSUE LISTED IN THAT ISSUE OF THE DEPARTMENT OF DEFENSE INDEX OF SPECIFICATIONS AND STANDARDS (DODISS) SPECIFIED IN THE SOLICITATION FORM A PART OF THIS STANDARD TO THE EXTENT SPECIFIED HEREIN.

U. S. ARMY - MR NAVY - AS	INTERNATIONAL INTEREST	TITLE BAR, METAL, ROUND, STEEL, CARBON, 1020	MILITARY STANDARD	
			MS500107	
PROCUREMENT SPECIFICATION ASTM A108		SUPERSEDED:		SHEET   OF

 USER ACTIVITIES  
 ARMY - ME, MI

 REVIEWER ACTIVITIES  
 ARMY - AR, AT  
 AIR FORCE - 99  
 DLA - IS

 DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.  
 This military standard is approved for use by all Departments and Agencies of the Department of Defense.  
 Exemptions for all new engineering and design applications and for repetitive use shall be made from this document when applicable.

APPROVED 5 MAR 87 REVISED