


FED. SUP CLASS
9505

TABLE I. DASH NUMBERS AND DIMENSIONS

DASH NUMBER	A	HEAT TREATMENT	FORMING ^{1/} PROCESS	ADDITIONAL ^{2/} REQUIREMENTS
-001	.1250	ANNEALED	C	NONE
-003	.1875	ANNEALED	C	po
-005	.2500	ANNEALED	C	NONE
-007	.3125	ANNEALED	C	NONE

^{1/} SEE REQUIREMENT 3^{2/} SEE REQUIREMENT 4

REQUIREMENTS:

- MATERIAL:** STEEL, CORROSION RESISTANT, TYPE 303 (UNS S30300) AS SPECIFIED IN PROCUREMENT DOCUMENT.
- LENGTH:** STANDARD LENGTH OF WIRE IS 10 FEET MINIMUM, 12 FEET MAXIMUM.
- FORMING PROCESS:** COLD FINISHED - CODE "C"
- ADDITIONAL REQUIREMENTS:**
PICKLED OVERALL - CODE "po"
- PART NUMBER:** THE PART NUMBER CONSISTS OF THE BASIC MS NUMBER, PLUS A DASH NUMBER FROM TABLE I.
EXAMPLE: MS500119-001

(SEE TABLE I)
 BASIC MS NUMBER
- MARKING:** IRON AND STEEL PRODUCTS SHALL BE MARKED IN ACCORDANCE WITH FED-STD-183 WITH THE EXCEPTION THAT A PART NUMBER FROM THIS MILITARY STANDARD SHALL BE INCLUDED AS PART OF THE IDENTIFICATION MARKING.

NOTES:

- ALL DIMENSIONS ARE IN INCHES.
- IN THE EVENT OF A CONFLICT BETWEEN THE TEXT OF THIS STANDARD AND THE REFERENCES CITED HEREIN, THE TEXT OF THIS STANDARD SHALL TAKE PRECEDENCE.
- REFERENCED GOVERNMENT (OR NONGOVERNMENT) DOCUMENTS OF THE ISSUE LISTED IN THAT ISSUE OF THE DEPARTMENT OF DEFENSE INDEX OF SPECIFICATIONS AND STANDARDS (DODISS) SPECIFIED IN THE SOLICITATION FORM A PART OF THIS STANDARD TO THE EXTENT SPECIFIED HEREIN.

P. A. ARMY - MR Other Cust	INTERNATIONAL INTEREST	TITLE WIRE, NONELECTRICAL, SQUARE, CORROSION RESISTANT STEEL, TYPE 303	MILITARY STANDARD	
			MS500119	
AIR FORCE-20			PAGE	OF
PROCUREMENT SPECIFICATION ASTM A581	SUPERSEDES:			

DD FORM 672-1 (COORDINATED)

PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE

9505-0187

USER ACTIVITIES:
NAVY-OSREVIEWER ACTIVITIES:
ARMY-AR, MI
AIR FORCE-99
DLA-IS

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document, when applicable.

AMSC N/A

APPROVED 21 APR 87 REVISED