



TTCC. When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility, nor any obligation whatsoever, and the fact that the Government may have furnished or in any way supplied the said drawings, specifications, or other data is not to be regarded as implying in any manner that the Government in any way endorses or approves the particular product or process shown or described in such drawings, specifications, or other data, or that any patent rights or other rights in any such drawings, specifications, or other data may in any way be related thereto.

FED. SUP CLASS
5310



BEFORE FORMING



AFTER FORMING

PART NO. MS90217-1 | FIDN

NOTES:

1. All dimensions in inches
2. Unless otherwise specified, tolerances are $\pm 1/64$ on fractions, $\pm .005$ on decimals, and $\pm 1/2^\circ$ on angles.
3. Material shall be beryllium copper conforming to condition H, of Specification QQ-C-533.
4. The washer shall be heat-treated to condition HT in salt bath after forming.
5. Referenced specification shall be of the issue in effect on date of invitation for bids.

(A) ENTIRE STANDARD REVISED

CUSTODIANS:
Army-Signal Corps
Navy-Bureau of Ships
Air Force
PROCUREMENT SPECIFICATION

MILITARY STANDARD

MS90217

APPROVED 7 Dec 1953 - DIVISION (A) 25 Nov 1953