MS9795

FED. SUP CLASS
5306



PART NUMBER	L	K	APPROX WEIGHT LB/100
MS9795-13	.938	.128- .188	2.04
MS9795-14	1.000	.190- .250	2.13
MS9795-15	1.062	.252- .312	2.21
MS9795-16	1.125	.315- .375	2.30
MS9795-17	1.188	.378- .438	2.38
MS9795-18	1.250	.440- .500	2.47
MS9795-19	1.312	.502- .562	2.54
MS9795-20	1.375	.565- .625	2.63
MS9795-21	1.438	.628- .688	2.72
MS9795-22	1.500	.690- .750	2.80
MS9795-23	1.562	.752- .812	2.89
MS9795-24	1.625	.815- .875	2.98
MS9795-25	1.688	.878- .938	3.06
MS9795-26	1.750	.940-1.000	3.15
MS9795-27	1.812	1.002-1.062	3.23
MS9795-28	1.875	1.065-1.125	3.31
MS9795-29	1.938	1.128-1.188	3.39
MS9795-30	2.000	1.190-1.250	3.48
MS9795-31	2.125	1.315-1.375	3.65
MS9795-32	2.250	1.440-1.500	3.82
MS9795-33	2.375	1.565-1.625	3.99
MS9795-34	2.500	1.690-1.750	4.16
MS9795-35	2.625	1.815-1.875	4.33
MS9795-36	2.750	1.940-2.000	4.50
MS9795-37	2.875	2.065-2.125	4.67
MS9795-38	3.000	2.190-2.250	4.84
MS9795-39	3.125	2.315-2.375	5.01
MS9795-40	3.250	2.440-2.500	5.18
MS9795-41	3.375	2.565-2.625	5.34
MS9795-42	3.500	2.690-2.750	5.52
MS9795-43	3.625	2.815-2.875	5.69
MS9795-44	3.750	2.940-3.000	5.86
MS9795-45	3.875	3.065-3.125	6.02
MS9795-46	4.000	3.190-3.250	6.19
MS9795-47	4.125	3.315-3.375	6.37
MS9795-48	4.250	3.440-3.500	6.54
MS9795-49	4.375	3.565-3.625	6.70
MS9795-50	4.500	3.690-3.750	6.87
MS9795-51	4.625	3.815-3.875	7.04
MS9795-52	4.750	3.940-4.000	7.22
MS9795-53	4.875	4.065-4.125	7.39
MS9795-54	5.000	4.190-4.250	7.55
MS9795-55	5.125	4.315-4.375	7.72
MS9795-56	5.250	4.440-4.500	7.89
MS9795-57	5.375	4.565-4.625	8.07
MS9795-58	5.500	4.690-4.750	8.23
MS9795-59	5.625	4.815-4.875	8.40
MS9795-60	5.750	4.940-5.000	8.54
MS9795-61	5.875	5.065-5.125	8.71
MS9795-62	6.000	5.190-5.250	8.87

1. SHANK SHALL BE STRAIGHT WITHIN .003 TOTAL PER INCH OF BOLT LENGTH.
2. THE CONCENTRICITY OF THREAD PD IN RELATION TO THE SHANK SHALL BE WITHIN .006 FIR.
3. THE CONCENTRICITY OF THE SHANK IN RELATION TO THE WASHER FACE DIAMETER AND HEXAGON SHALL BE WITHIN .013 FIR.
4. INCOMPLETE THREADS NOT TO ENTER FILLET.
5. MATERIAL: CORROSION RESISTANT STEEL AMS 5643. (B) REINSTATED 15 AUG 84
6. HARDNESS: ROCKWELL C32-38.
7. MANUFACTURING SPECIFICATION: AMS 7474.
8. FLUORESCENT PENETRANT INSPECTION PER AMS 2645.
9. SURFACE TEXTURE: USAS B46.1-1962. UNLESS OTHERWISE SPECIFIED, SURFACES TO BE 125 MICROINCHES EXCEPT UPSET HEAD.
10. BREAK SHARP EDGES .003-.015 UNLESS OTHERWISE SPECIFIED.
11. DIMENSIONS IN INCHES. UNLESS OTHERWISE SPECIFIED, TOLERANCES: LINEAR DIMENSIONS ±.010, ANGULAR DIMENSIONS ±5°.
12. DO NOT USE UNASSIGNED PART NUMBERS.

AS & AMS ARE SOCIETY OF AUTOMOTIVE ENGINEERS, INC. PUBLICATIONS.
THIS STANDARD WAS DEVELOPED COOPERATIVELY WITH THE MILITARY SERVICES BY THE SAE AEROSPACE PART STANDARDS DIV.

APPROVED 11 MAR 70 REVISED (A) 21 DEC 83 (B) 15 AUG 84

Review activities:
AIR FORCE-82
DLA-IS

This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document when applicable.

P.A. - AS (B) Other Cust. AV 99	INTERNATIONAL INTEREST (B)	TITLE: BOLT, MACHINE - HEXAGON HEAD, DRILLED, 1 HOLE, FULL SHANK, AMS 5643, .250-28 UNJF-3A	MILITARY STANDARD MS9795
PROCUREMENT SPECIFICATION NONE		SUPERSEDES:	PAGE 1 OF 1

DD FORM 672-1 (Coordinated) PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE

5306-0852