



1. MATERIAL: STEEL, AMS 6320, AMS 6322 OR AMS 6327
2. HARDNESS: ROCKWELL C26-32.
3. FINISH: CADMIUM PLATE AMS 2400. DIMENSIONS ARE AFTER PLATING EXCEPT WHERE SHOWN.
4. SURFACE TEXTURE: ANSI B46.1-1962. UNLESS OTHERWISE SPECIFIED, SURFACES TO BE 125 MICRONS.
5. DIMENSIONING AND TOLERANCING: ANSI Y14.5-1966.
6. MANUFACTURING SPECIFICATION: AMS 7456 EXCEPT THREAD FORM.
7. MAGNETIC PARTICLE INSPECTION PER AMS 2640 AFTER PLATING.
8. BREAK MARKS: EDGES .003-.015 UNLESS OTHERWISE SPECIFIED.
9. DIMENSIONING IN THE DRAWING: UNLESS OTHERWISE SPECIFIED, TOLERANCES: LINEAR DIMENSIONS $\pm .010$.
10. MARK PART NUMBER AND MANUFACTURER'S IDENTIFICATION ON CONTAINER.
11. DO NOT USE UNASSIGNED PART NUMBERS.

AS & AMS ARE SOCIETY OF AUTOMOTIVE ENGINEERS, INC. PUBLICATIONS.
THIS STANDARD WAS DEVELOPED COOPERATIVELY WITH THE MILITARY SERVICES BY THE SAE AEROSPACE PART STANDARDS DIV.

P.A. Air Force -II Other Cost Navy -AS	TITLE STUD-STEPPED, DRILLED, 2 DIA ENGAGEMENT, STEEL .625-11 UNJS x .5625-18 UNJF	MILITARY STANDARD MS9840
PROCUREMENT SPECIFICATION AMS 7456	SUPERSEDES:	SHEET 1 OF 1

This standard has been approved by the Dept. of the Air Force and the Department of the Navy and is mandatory for use by that activity. All other military activities are required to employ this standard where suitable.

Review activities:
Air Force - 82

Air Force - 82

APPROVED	27 Aug 71	REVISED
----------	-----------	---------